

(12) **United States Patent**  
**Basker et al.**

(10) **Patent No.:** **US 10,249,536 B2**  
(45) **Date of Patent:** **Apr. 2, 2019**

(54) **SEMICONDUCTOR FINS FOR FINFET DEVICES AND SIDEWALL IMAGE TRANSFER (SIT) PROCESSES FOR MANUFACTURING THE SAME**

(58) **Field of Classification Search**  
CPC combination set(s) only.  
See application file for complete search history.

(71) Applicant: **International Business Machines Corporation**, Armonk, NY (US)

(56) **References Cited**  
U.S. PATENT DOCUMENTS

(72) Inventors: **Veeraraghavan S. Basker**, Schenectady, NY (US); **Kangguo Cheng**, Schenectady, NY (US); **Theodorus E. Standaert**, Clifton Park, NY (US)

7,074,662 B2 7/2006 Lee et al.  
7,993,999 B2 8/2011 Basker et al.  
(Continued)

(73) Assignee: **International Business Machines Corporation**, Armonk, NY (US)

OTHER PUBLICATIONS  
Notice of Allowance dated Mar. 28, 2018 received in U.S. Appl. No. 15/464,028.  
(Continued)

(\* ) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

*Primary Examiner* — Reema Patel  
*Assistant Examiner* — Steven Christopher  
(74) *Attorney, Agent, or Firm* — Scully, Scott, Murphy & Presser, P.C.; Steven J. Meyers

(21) Appl. No.: **15/464,007**

(22) Filed: **Mar. 20, 2017**

(57) **ABSTRACT**

(65) **Prior Publication Data**  
US 2017/0194358 A1 Jul. 6, 2017

A method of forming a semiconductor structure includes providing a semiconductor substrate, forming at least one precursor semiconductor fin from the semiconductor substrate, etching through at least a portion of the at least one precursor semiconductor fin to form at least one patterned precursor semiconductor fin having a gap therein. The at least one patterned precursor semiconductor fin includes a first vertical surface and a second vertical surface with the gap therebetween. In addition, the method further includes forming a semiconductor material in the gap of the at least one patterned precursor semiconductor fin, in which the first vertical surface and the second vertical surface laterally surround the semiconductor material, and transforming the at least one patterned precursor semiconductor fin into at least one semiconductor fin including the semiconductor material therein.


**Related U.S. Application Data**

(62) Division of application No. 14/739,008, filed on Jun. 15, 2015, now Pat. No. 9,601,378.

(51) **Int. Cl.**  
**H01L 29/66** (2006.01)  
**H01L 21/8234** (2006.01)  
(Continued)

(52) **U.S. Cl.**  
CPC ..... **H01L 21/823431** (2013.01); **H01L 21/02236** (2013.01); **H01L 21/02532** (2013.01);  
(Continued)

**20 Claims, 16 Drawing Sheets**



- (51) **Int. Cl.**  
*H01L 21/84* (2006.01)  
*H01L 21/306* (2006.01)  
*H01L 21/308* (2006.01)  
*H01L 21/02* (2006.01)  
*H01L 21/324* (2006.01)  
*H01L 29/78* (2006.01)  
*H01L 29/161* (2006.01)  
*H01L 29/10* (2006.01)  
*H01L 27/12* (2006.01)  
*H01L 29/36* (2006.01)  
*H01L 27/088* (2006.01)
- (52) **U.S. Cl.**  
 CPC .. *H01L 21/02636* (2013.01); *H01L 21/02645*  
 (2013.01); *H01L 21/308* (2013.01); *H01L*  
*21/3081* (2013.01); *H01L 21/3086* (2013.01);  
*H01L 21/30604* (2013.01); *H01L 21/324*  
 (2013.01); *H01L 21/823412* (2013.01); *H01L*  
*21/845* (2013.01); *H01L 27/0886* (2013.01);  
*H01L 27/1211* (2013.01); *H01L 29/1037*  
 (2013.01); *H01L 29/161* (2013.01); *H01L*  
*29/36* (2013.01); *H01L 29/6656* (2013.01);  
*H01L 29/66795* (2013.01); *H01L 29/785*  
 (2013.01); *H01L 29/7851* (2013.01); *H01L*  
*21/02255* (2013.01)

- (56) **References Cited**  
 U.S. PATENT DOCUMENTS
- |                   |         |                   |       |               |         |
|-------------------|---------|-------------------|-------|---------------|---------|
| 8,497,177 B1 *    | 7/2013  | Chang             | ..... | H01L 29/66795 | 438/283 |
| 8,703,556 B2      | 4/2014  | Kelly et al.      |       |               |         |
| 8,975,129 B1      | 3/2015  | Shieh et al.      |       |               |         |
| 2013/0234204 A1   | 9/2013  | Kang et al.       |       |               |         |
| 2013/0244392 A1 * | 9/2013  | Oh                | ..... | H01L 29/66477 | 438/299 |
| 2014/0197456 A1 * | 7/2014  | Wang              | ..... | H01L 29/785   | 257/192 |
| 2014/0339643 A1 * | 11/2014 | Cheng             | ..... | H01L 21/76224 | 257/369 |
| 2015/0295089 A1 * | 10/2015 | Huang             | ..... | H01L 29/7853  | 257/401 |
| 2015/0325692 A1   | 11/2015 | Zang              |       |               |         |
| 2015/0364603 A1   | 12/2015 | Cheng et al.      |       |               |         |
| 2016/0093697 A1   | 3/2016  | Bergendahl et al. |       |               |         |
| 2016/0336187 A1   | 11/2016 | Liou et al.       |       |               |         |
| 2016/0351411 A1   | 12/2016 | Xie et al.        |       |               |         |

OTHER PUBLICATIONS

List of IBM Patents or Patent Applications Treated as Related dated Mar. 20, 2017 2 pages.  
 Office Action dated Oct. 22, 2018 received in U.S. Appl. No. 15/463,972.

\* cited by examiner




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10




FIG. 11




FIG. 12




FIG. 13




FIG. 14




FIG. 15






FIG. 17




FIG. 18




FIG. 19




FIG. 20




FIG. 21




FIG. 22




FIG. 23




FIG. 24




FIG. 25




FIG. 26

**SEMICONDUCTOR FINS FOR FINFET  
DEVICES AND SIDEWALL IMAGE  
TRANSFER (SIT) PROCESSES FOR  
MANUFACTURING THE SAME**

BACKGROUND

The present application relates to semiconductor fins for FinFET devices, and particularly to semiconductor fins for FinFET devices and sidewall image transfer (SIT) processes for manufacturing the same.

FinFET devices are widely used in the semiconductor industry. However, there may be difficulties associated with the manufacture of the semiconductor fins for the FinFET devices.

For instance, high atomic percentage germanium (Ge) channels are currently being proposed as channel materials for future nodes. However, with conventional methods, it is almost impossible to form stable high atomic % germanium films without significant physical/damage occurring to these high atomic % germanium films caused by wet etching processes and/or dry etching processes (e.g., RIE) when taking these films downstream.

In addition, another difficulty with manufacturing semiconductor fins for FinFET devices is that a tight fin pitch may be needed for continued scaling of FinFET to 7 nm nodes and beyond. However, 7 nm nodes calls for 28 nm fin pitch which is well beyond conventional lithography patterning and even conventional sidewall transfer image (SIT) techniques. Currently, double SIT (SIT2) is being used in an attempt to form semiconductor fins with a tight pitch for a 7 nm node. SIT2 basically repeats the conventional SIT process. However, since conventional SIT2 processes form mandrels on different levels of a wafer from one another there may be certain drawbacks associated with these conventional processes. For instance, one the drawbacks to using conventional SIT2 processes is that it increases manufacturing costs. In addition, another drawback to conventional SIT2 processes is the difficulty in cutting (removing) the unwanted semiconductor fins after SIT2 due to the tight fin pitch (semiconductor fins are closely spaced and therefore it is difficult to completely cut the unwanted fin without compromising the adjacent device semiconductor fins).

SUMMARY

In accordance with an exemplary embodiment of the present application, a method of forming a semiconductor structure is provided. The method includes providing a semiconductor substrate, forming at least one precursor semiconductor fin from the semiconductor substrate, etching through at least a portion of the at least one precursor semiconductor fin to form at least one patterned precursor semiconductor fin having a gap therein. The at least one patterned precursor semiconductor fin includes a first vertical surface and a second vertical surface with the gap therebetween. In addition, the method further includes forming a semiconductor material in the gap of the at least one patterned precursor semiconductor fin, in which the first vertical surface and the second vertical surface laterally surround the semiconductor material, and transforming the at least one patterned precursor semiconductor fin into at least one semiconductor fin including the semiconductor material therein.

In accordance with an exemplary embodiment of the present application, a semiconductor structure is provided. The semiconductor structure includes a semiconductor sub-

strate, and at least one fin disposed on the semiconductor substrate. The at least one semiconductor fin includes an inner core comprising silicon germanium (SiGe) material having a germanium content of from 10 atomic % to 90 atomic % therein, and an outer shell laterally surrounding the inner core of the at least one semiconductor fin. The outer shell includes one of Si or SiGe having a germanium content of no greater than 10 atomic %.

In accordance with an exemplary embodiment of the present application, a method for forming a semiconductor structure is provided. The method includes providing a semiconductor substrate, forming at least one mandrel on the semiconductor substrate and forming a first sidewall image transfer (SIT) spacer on sidewalls of the at least one mandrel. The method further includes forming a mandrel SIT spacer on sidewalls of the first SIT spacer and forming a second SIT spacer on sidewalls of the mandrel SIT spacer. Further, the method includes removing the at least one mandrel and the mandrel SIT spacers from the sidewalls of the first SIT, thereby defining a pattern comprising the first SIT spacers and the second SIT spacers on the semiconductor substrate. In addition, the method further includes etching the semiconductor substrate using the first SIT spacers and the second SIT spacers as an etching mask to transfer the pattern of the first SIT spacers and the second SIT spacers into the semiconductor substrate to form a plurality of semiconductor fins from the semiconductor substrate.

BRIEF DESCRIPTION OF SEVERAL VIEWS OF  
THE DRAWINGS

FIG. 1 is a vertical cross-sectional view of a semiconductor structure including a plurality of semiconductor fins according to a first embodiment of the present application.

FIG. 2 is a vertical cross-sectional view of an exemplary semiconductor structure including a silicon-on-insulator (SOI) substrate, a hard mask layer disposed on the SOI substrate, a plurality of mandrels disposed on hard mask layer, and a first sidewall image transfer (SIT) spacer, a sacrificial SIT spacer and a second SIT spacer sequentially formed on sidewalls of the mandrels according to the first embodiment.

FIG. 3 is a vertical cross-sectional view of the exemplary semiconductor structure of FIG. 2 after removing the mandrels to form triple SIT spacer composite structures on the hard mask layer.

FIG. 4 is a vertical cross-sectional view of the exemplary semiconductor structure of FIG. 3 after etching the hard mask layer and a top semiconductor layer of the SOI substrate to form a plurality of precursor semiconductor fin structures each including a sequential stack of a precursor semiconductor fin, a hard mask layer pattern and one of the triple SIT spacer composite structures.

FIG. 5 is a vertical cross-sectional view of the exemplary semiconductor structure of FIG. 4 after a protective oxide layer has been formed on sidewalls of each of the precursor semiconductor fin structures.

FIG. 6 is a vertical cross-sectional view of the exemplary semiconductor structure of FIG. 5 after removing the sacrificial SIT spacer from the triple SIT spacer composite structures of each of the precursor semiconductor fin structures.

FIG. 7 is a vertical cross-sectional view of the exemplary semiconductor structure of FIG. 6 after the patterned hard mask and the precursor semiconductor fins have been pat-

3

terned to form patterned hard mask portions and patterned precursor semiconductor fins in the precursor semiconductor fin structures.

FIG. 8 is a vertical cross-sectional view of the exemplary semiconductor structure of FIG. 7 after epitaxially forming a semiconductor material and a cap in an inner core of the semiconductor fins.

FIG. 9 is a vertical cross-sectional view of the exemplary semiconductor structure of FIG. 8 after the protective oxide layers, and the first SIT spacers and the second SIT spacers have been removed such that only the hard mask portions remain on the semiconductor fins.

FIG. 10 is a vertical cross-sectional view of a plurality of semiconductor fins defined by a plurality of trenches formed in a bulk semiconductor substrate, and wherein the semiconductor fins are formed integrally with the bulk semiconductor substrate according to a second embodiment of the application.

FIG. 11 is a vertical cross-sectional view of an exemplary semiconductor structure including a bulk semiconductor substrate, a dielectric layer disposed on the bulk semiconductor substrate, a plurality of mandrels disposed on the dielectric layer, and a first sidewall image transfer (SIT) spacer, a sacrificial SIT spacer and a second SIT spacer sequentially formed on sidewalls of the mandrels according to the second embodiment.

FIG. 12 is a vertical cross-sectional view of the exemplary semiconductor structure of FIG. 11 after removing the mandrels to form triple SIT spacer composite structures on the dielectric layer.

FIG. 13 is a vertical cross-sectional view of the exemplary structure of FIG. 12 after etching the dielectric layer and the bulk semiconductor substrate to form precursor semiconductor fin structures each including a sequential stack of one of the precursor semiconductor fins formed integrally with the bulk substrate and defined by a plurality of trenches formed in the bulk semiconductor substrate, one of the dielectric layer patterns and one of the triple SIT spacer composite structures.

FIG. 14 is a vertical cross-sectional view of the exemplary structure of FIG. 13 after filling the trenches with an isolation material.

FIG. 15 is a vertical cross-sectional view of the exemplary semiconductor structure of FIG. 14 after removing the sacrificial SIT spacer from the triple SIT spacer composite structures of each of the precursor semiconductor fin structures.

FIG. 16 is a vertical cross-sectional view of the exemplary structure of FIG. 15 after the patterned dielectric layer and the precursor semiconductor fins have been patterned to form patterned dielectric layer portions and patterned precursor semiconductor fins in the precursor semiconductor fin structures.

FIG. 17 is a vertical cross-sectional view of the exemplary semiconductor structure of FIG. 16 after epitaxially forming a semiconductor material and a cap inside the semiconductor fins.

FIG. 18 is a vertical cross-sectional view of the exemplary semiconductor structure of FIG. 17 after performing a condensation and anneal process on the fin.

FIG. 19 is a vertical cross-sectional view of a semiconductor structure including a plurality of semiconductor fins defined by a plurality of trenches in a bulk semiconductor substrate and formed integrally with the bulk semiconductor substrate according to a third embodiment of the present application.

4

FIG. 20 is a vertical cross-sectional view of an exemplary semiconductor structure including a bulk semiconductor substrate, a pad layer disposed on the bulk semiconductor substrate, a plurality of mandrels disposed on the pad layer, and a first sidewall image transfer (SIT) spacer formed on sidewalls of the mandrels according to the second embodiment.

FIG. 21 is a vertical cross-sectional view of the exemplary semiconductor structure of FIG. 20 after forming a mandrel SIT spacer on sidewalls of the first SIT spacers.

FIG. 22 is a vertical cross-sectional view of an exemplary semiconductor structure of FIG. 21 after forming a second SIT spacer on sidewalls of the first mandrel spacers.

FIG. 23 is a vertical cross-sectional view of an exemplary semiconductor structure of FIG. 22 after removing the mandrels and the mandrel SIT spacers, thereby leaving a pattern of the first SIT spacers and the second SIT spacers on the pad layer.

FIG. 24 is a vertical cross-sectional view of an exemplary semiconductor structure of FIG. 23 after etching the pad layer and the bulk semiconductor substrate to form a plurality of first precursor semiconductor fin structures that each include a sequential stack of one of the precursor semiconductor fins formed integrally with the bulk semiconductor substrate and defined by a plurality of trenches formed in the bulk semiconductor substrate, one of the pad layer patterns and one of the first SIT spacers, and a plurality of second precursor semiconductor fin structures that each include a sequential stack of another one of the precursor semiconductor fins formed integrally with the bulk semiconductor substrate and defined by a plurality of trenches formed in the bulk semiconductor substrate, another one of the pad layer patterns and one of the second SIT spacers.

FIG. 25 is a vertical cross-sectional view of an exemplary semiconductor structure including a bulk semiconductor substrate, a pad layer disposed on the bulk semiconductor substrate, a plurality of mandrels disposed on the pad layer, and a first sidewall image transfer (SIT) spacer, a mandrel SIT spacer and a second SIT spacer sequentially formed on sidewalls of the mandrels according to a fourth embodiment of the application.

FIG. 26 is a vertical cross-sectional view of an exemplary semiconductor structure of FIG. 25 after removing the mandrel and the mandrel SIT spacers, thereby leaving a pattern of the first SIT spacers and the second SIT spacers on the pad layer.

#### DETAILED DESCRIPTION

Referring first to FIG. 1, there is shown a semiconductor structure **100** in accordance with a first embodiment of the present application.

The semiconductor structure **100** may be an intermediate stage in the manufacture of a FinFET device. The semiconductor structure **100** includes a plurality of semiconductor fins **10** spaced apart from each other on an insulator layer **20** (e.g., BOX) of an SOI substrate **1** (See SOI substrate **1** in FIG. 2). The semiconductor fins **10** in this embodiment are formed by patterning a top semiconductor layer **30** of the SOI substrate **1** as explained in further detail hereinafter in connection with the fabrication method illustrated and described in FIGS. 2-9. Alternatively, and in other embodiments, the plurality of semiconductor fins **10** may be formed from a bulk semiconductor substrate instead of from the SOI substrate **1**.

In addition, and in other embodiments, the SOI substrate **1** may further include a handle substrate (not shown). The

handle substrate may comprise, for example, a semiconductor material. The semiconductor material of the handle substrate can include, but is not limited to, silicon (Si), germanium (Ge), silicon germanium (SiGe), silicon germanium carbide (SiGeC), silicon carbide (SiC), an III-V compound semiconductor, an II-VI compound semiconductor or any combinations thereof. Multilayers of semiconductor materials can also be used as the semiconductor material of the handle substrate. In one embodiment, the handle substrate is comprised of silicon. In some embodiments, the handle substrate is a non-semiconductor material including, for example, a dielectric material and/or a conductive material.

The semiconductor fins **10** each include an inner core **12** located inside the semiconductor fins **10** and an outer shell **14a**, **14b** (formed by etching the top semiconductor layer **30** of the SOI substrate **1**) which surrounds the inner core **12** of the semiconductor fins **10**. The semiconductor fins **10** may have a width in the range of, for example, 4 nm-16 nm. The inner core **12** may include a semiconductor material which is formed by, for example, a selective epitaxial growth (SEG) process performed within a patterned precursor semiconductor fin **18** as described in further detail in connection with FIGS. 2-9. The inner core **12** may include a semiconductor material including but not limited to, for example, silicon germanium (SiGe), germanium (Ge), an III-V compound semiconductor or any combinations thereof. Also, the inner core **12** of the semiconductor fins **10** may have a width in the range of, for example, 2 nm-12 nm.

The outer shell **14a**, **14b** of the semiconductor fins **10** which surrounds the inner core **12** of the semiconductor fins **10** may include a semiconductor material which is capable of protecting the semiconductor material in the inner core **12** of the semiconductor fins **10** from any attack thereon during downstream processes (e.g. wet etching or reactive ion etching (RIE)). For example, in some embodiments, the outer shell **14a**, **14b** may include Si or SiGe with a low percentage of germanium (i.e., 10 atomic % or less of germanium). The width of the outer shell **14a**, **14b** of the semiconductor fins **10** may be the range of, for example, 2 nm-6 nm.

In the present embodiment, the inner core **12** of the semiconductor fins **10** include silicon germanium (SiGe) with Ge present in an amount from 10 atomic % to 90 atomic %. In some embodiment, the inner core **12** of the semiconductor fins **10** include SiGe with Ge in a high percentage amount (i.e., 50 atomic %-90 atomic % of germanium). In other embodiments, the inner core **12** of the semiconductor fins **10** include SiGe with Ge present in an amount from 20 atomic % to 90 atomic %. In some embodiments, the outer shell **14a**, **14b** of the semiconductor fins **10** include silicon (Si) or silicon germanium with a low percentage of germanium (i.e., 10 atomic % or less of Ge). In the present embodiment, the outer shell **14a**, **14b** includes silicon.

In addition, the semiconductor fins **10** further include a cap **16** located on the upper surface of the semiconductor material that provides the inner core **12**. In the present embodiment, the cap **16** includes silicon, and has an upper surface which is co-planar with an upper surface of the outer shell **14a**, **14b** of the semiconductor fins **10**. In other embodiments, the cap **16** can alternatively include SiGe with a low percentage of Ge (i.e., 10 atomic % or less of Ge). Moreover, the width of the cap **16** may be in the range of, for example, 2 nm-8 nm. In other embodiments, the cap **16** may be omitted.

Reference is now made to FIGS. 2-7, which illustrate a method for fabricating the semiconductor structure **100**

shown in FIG. 1 according to the first embodiment of the present application. Specifically, and referring to FIG. 2, an SOI substrate **1** is first provided but exemplary embodiments are not limited thereto. Alternatively, in other embodiments, a bulk semiconductor substrate may be provided instead of the SOI substrate **1** to form the semiconductor fins **10**.

In the present embodiment, the SOI substrate **1** includes, for example, the insulator layer **20** (e.g., BOX) and the top semiconductor layer **30** contacting the top surface of the insulator layer **20**. In other embodiments, the SOI substrate **1** may optionally further include a handle substrate (not shown) disposed below the insulator layer **20**.

The SOI substrate **1** may be fabricated using techniques well known to those skilled in the art. For example, the SOI substrate **1** may be formed by conventional processes including, but not limited to, Separation by Implanted Oxygen (SIMOX) process, which employs high dose ion implantation of oxygen and high temperature annealing to form insulator layer **20** (e.g., BOX layer) in a bulk wafer, or wafer bonding. The SOI substrate **1** may also be formed using other processes. The method of fabricating the SOI substrate **1** is not critical to the present application.

The top semiconductor layer **30** may include any semiconductor material. In one embodiment, the semiconductor material that provides the top semiconductor layer **30** can be, for example, silicon. In another embodiment, the semiconductor material that provides the top semiconductor layer **30** can be, for example, silicon germanium (SiGe) with a low concentration of germanium (e.g. 10 atomic % or less of germanium).

The insulator layer **20** of the SOI substrate **1** may include a dielectric material such as, for example, silicon dioxide, silicon nitride, boron nitride or any other suitable insulating materials or combinations thereof. In an embodiment, the insulator layer **20** may be, for example, a buried oxide layer (BOX). The insulator layer **20** may, or may not, include multiple dielectric layers, e.g., a stack including at least a silicon dioxide layer and a silicon nitride layer.

Next, a dielectric layer (e.g., hard mask layer) **40** is deposited onto the top semiconductor layer **30** of the SOI substrate **1** using a deposition process such as, for example, chemical vapor deposition (CVD), atomic layer deposition (ALD), physical vapor deposition (PVD), evaporation, or spin-coating. The hard mask layer **40** may include, for example, a dielectric material such as, for example, an oxide or a nitride. In the present embodiment, the hard mask layer **40** includes silicon nitride. Alternatively, and in other embodiments, the hard mask layer **40** includes silicon dioxide. Moreover, in some embodiments, the formation of the hard mask layer **40** may be omitted.

Next, a mandrel layer (not shown) is formed on the hard mask layer **40** using a deposition process such as, for example, atomic layer deposition (ALD) or chemical vapor deposition (CVD). The mandrel layer may include, for example, polycrystalline silicon (polysilicon), amorphous silicon, amorphous carbon, or other suitable material. The mandrel layer is then subsequently patterned and etched using, for example, conventional lithography and etching processes to form a plurality of mandrels **50** on the hard mask layer **40**, as shown in FIG. 2. The mandrels **50** can each have a width in the range of, for example, 15 nm-40 nm.

A conformal deposition process is then performed to form a first spacer material (not shown) on the top surface of the mandrels **50**, the sides of the mandrels **50**, and on exposed surfaces of the hardmask layer **40**. In one embodiment, the first spacer material comprises an oxide, but other materials

are applicable as well. For example, and in another embodiment, the first spacer material may include a nitride. In an embodiment where the hard mask layer 40 includes a nitride, then the first spacer material should be an oxide. Alternatively, and in embodiments in which the hard mask layer 40 includes an oxide, then the first spacer material should include a nitride. Further, the first spacer material is etched using a sidewall image transfer (SIT) spacer formation etch process. The SIT spacer formation etch process includes, for example, a direction reactive ion etch (RIE) which removes the first spacer material from the top surfaces of the mandrels 50 and from the upper surfaces of the hard mask layer 40. As a result of the above RIE process, the first spacer material remains intact only on the sides of the mandrels 50. This first spacer material on the sides of the mandrels 50 is referred to hereinafter as first SIT spacer 52.

In addition, another conformal deposition process is then performed to form a sacrificial spacer material (not shown) on the exposed top surfaces the mandrels 50 and on the first SIT spacers 52 located on the sides of the mandrels 50, and also on exposed surfaces of the hardmask layer 40. In one embodiment, the sacrificial spacer material comprises a nitride such as, for example, titanium nitride (TiN), but other materials are applicable as well. For example, and in another embodiment, the sacrificial spacer material may include amorphous silicon or amorphous carbon. Further, the sacrificial spacer material is etched using the SIT spacer formation etch process mentioned above. The SIT spacer formation etch process removes the sacrificial spacer material from the top surfaces of the mandrels and from the upper surfaces of the hard mask layer 40. As a result of the above RIE process, the sacrificial spacer material remains intact only on the sides of the first SIT spacers 52. This sacrificial spacer material on the sides of the first SIT spacers 52 is referred to hereinafter as the sacrificial SIT spacer 54.

Moreover, another conformal deposition process is then performed to form a second spacer material (not shown) on the exposed top surface of the mandrels 50, on the sacrificial SIT spacer 54 located on the sides of the first SIT spacer 52, and also on exposed surfaces of the hardmask layer 40. In one embodiment, the second spacer material includes, for example, an oxide, but other materials are applicable as well. For example, and in another embodiment, the second spacer material may include a nitride. In embodiments in which the hard mask layer 40 includes a nitride, then the second spacer material should then be an oxide. Alternatively, and in embodiments in which the hard mask layer 40 includes an oxide, then the second spacer material should include a nitride.

Further, the second spacer material is etched using an SIT spacer formation etch process as mentioned above. The SIT spacer etch process removes the second spacer material from the top surfaces of the mandrels 50 and from the upper surfaces of the hard mask layer 40. As a result of the RIE process, the second spacer material remains intact only on the sides of the sacrificial SIT spacer 54. This second spacer material on the sides of the sacrificial SIT spacer 54 is referred to hereinafter as a second SIT spacer 56.

In the present embodiment, the first SIT spacer 52, the sacrificial SIT spacer 54 and the second SIT spacer 56 are sequentially disposed on the sides of each of the mandrels 50. In addition, and in the present embodiment, the upper surfaces of the first SIT spacer 52, the sacrificial SIT spacer 54 and the second SIT spacer 56 are all coplanar with each other, and the lower surfaces of the first SIT spacer 52, the sacrificial SIT spacer 54 and the second SIT spacer 56 are all coplanar with each other.

Next, as shown in FIG. 3, the mandrels 50 are then removed selective to the first SIT spacer 52, the second SIT spacer 56 and the sacrificial SIT spacer 54 using, for example, an anisotropic dry etch and/or wet etching process leaving a plurality of triple SIT spacer composite structures 60 located on the top surface of the hard mask layer 40. The triple SIT spacer composite structures 60 each include one of the first SIT spacers 52, one of the second SIT spacers 56 and one of the sacrificial SIT spacers 54 that is located in between the first SIT spacer 52 and the second SIT spacer 56. The wet etching process may include, example, a tetramethylammonium (TMA) etch, a tetraethylammonium (TEA) etch, an ammonium hydroxide etch or an etch using hydrogen bromide (HBr) chemistry.

Further, as shown in FIG. 3, a pattern of the plurality of triple SIT spacer composite structures 60 is revealed as a result of the above removal of the mandrels 50. Following removal of the mandrels 50, the triple SIT spacer composite structures 60 are then used to transfer the pattern to the hardmask layer 40 and the top semiconductor layer 30 of the SOI substrate 1. In the present exemplary embodiment, the pattern of the triple SIT spacer composite structures 60 is first transferred to the hardmask layer 40, thereby forming the patterned hardmasks 41. (See, e.g., FIG. 4). This step may be carried out using an anisotropic etching process such as, for example, a RIE process. The patterned hardmasks 41 can then be used to pattern the top semiconductor layer 30 of the SOI substrate 1. Again, for example, a RIE process may be used to pattern the top semiconductor layer 30 of the SOI substrate 1. The particular etch chemistry used can be varied for etching selectivity between the hardmask layer 40 and the top semiconductor layer 30. Alternatively, as provided above, the use of a hardmask layer 40 in this process flow is optional. Thus, in the instance where a hardmask layer 40 is not employed, the pattern of the triple SIT spacer composite structures 60 is at this step transferred directly into the top semiconductor layer 30. (e.g., using RIE).

In the present embodiment, and as shown in FIG. 4, the result of the above patterning of the hard mask layer 40 and the top semiconductor layer 30 using the triple SIT spacer composite structures 60 as an etch mask results in the formation of a plurality of precursor semiconductor fin structures 70 located on the top surface of insulator layer 20 of the SOI substrate 1. The plurality of precursor semiconductor fin structures 70 each include a sequential stack of a precursor semiconductor fin 14 (formed from patterning the top semiconductor layer 30), one of the patterned hard masks 41 and one of the plurality of triple SIT spacer composite structures 60.

Referring to FIG. 5, an oxide layer (not shown) is deposited over the top and side surfaces of each of the precursor semiconductor fin structures 70, and on exposed surfaces of the top surface of the insulator layer 20 in between the precursor semiconductor fin structures 70 using a conformal deposition process such as, for example, ALD or PCVD. An etch process such as, for example, RIE is performed to remove the oxide layer from the top surface of each of the precursor semiconductor fin structures 70, and from portions of the top surface of the insulator layer 20 in between the precursor semiconductor fin structures 70 such that the oxide layer remains on only the sidewalls of each the precursor semiconductor fin structures 70. This oxide on the sides of each of the precursor semiconductor fin structures 70 is referred to hereinafter as a protective oxide spacer 72.

The protective oxide spacer 72 laterally surrounds and contacts the triple SIT spacer composite structures 60, the patterned hard mask 41 and the precursor semiconductor fin

14 of each the precursor semiconductor fin structures 70. In addition, the protective oxide spacer 72 contacts exposed portions of the top surface of the insulator layer 20. Also, an upper surface of the protective oxide spacer 72 is coplanar with an upper surface (e.g., upper surface of triple spacer composite structure 60) of the precursor semiconductor fin structures 70, and a bottom surface of the protective oxide spacer 72 is co-planar with a bottom surface (e.g., bottom surface of the precursor semiconductor fin 14) of the precursor semiconductor fin structures 70. The protective oxide spacer 72 may be used to protect the outer surface of the precursor semiconductor fin 14 during an epitaxial growth process discussed hereinafter. In addition, the protective oxide spacer may be formed have a thickness of, for example, 10-20 nm.

Next, referring to FIG. 6, an etching process is performed to remove the sacrificial SIT spacer 54 (i.e., the middle spacer of the triple SIT spacer composite structure 60) from the triple SIT spacer composite structures 60, thereby leaving a first gap 74 between the first SIT spacer 52 and the second SIT spacer 56 in each of the precursor semiconductor fin structures 70, which exposes a top surface of the patterned hard masks 41. The etching process for removing the sacrificial SIT spacer 54 may be, for example, a wet etching process or a dry etching process. In the present embodiment, a wet etching process is performed using, for example, for ammonium peroxide chemistry or sulfuric peroxide.

Referring to FIG. 7, an RIE process using the first SIT spacer 52 and the second SIT spacer 56 of each of the precursor semiconductor fin structures 70 as an etch mask is performed to etch all the way through a corresponding one of the patterned hard masks 41 and a corresponding one of the precursor semiconductor fins 14 of each of the precursor semiconductor fin structures 70, thereby forming a second gap 76 between patterned hard mask portions 41a, 41b (formed by etching the patterned hard mask 41) and a third gap 78 in the patterned precursor semiconductor fins 18 (formed by etching the precursor semiconductor fins 14) in each of the precursor semiconductor fin structures 70. The patterned precursor semiconductor fins 18 include a first vertical sidewall 14a and second vertical sidewall 14b with the third gap 78 located between the first vertical sidewall 14a and the second vertical sidewall 14b of the patterned precursor semiconductor fins 18. The third gap 78 of the patterned precursor semiconductor fins 18 exposes a top surface of the insulator layer 20.

Next, referring to FIG. 8, a semiconductor material may be formed in the third gap 78 of the precursor semiconductor fins 18 by, for example, a selective epitaxial growth (SEG) process using the first and second vertical sidewalls 14a, 14b of the patterned precursor semiconductor fins 18 of each of the precursor semiconductor fin structures 70 as a seed to grow a semiconductor material such as, for example, SiGe, Ge or III-V semiconductors, or a combination thereof in the third gap 78 of the patterned precursor semiconductor fins 18. In the present embodiment, an SiGe layer including germanium in an amount from 10 atomic % to 90 atomic % is epitaxially grown from the first and second vertical sidewalls 14a, 14b of the patterned precursor semiconductor fins 18 using an SEG process in the third gap 78 of the patterned precursor semiconductor fins 18 in each of the precursor semiconductor fin structures 70. In some embodiments, the semiconductor material epitaxially grown in third gap 78 is SiGe with a high percentage of germanium present (i.e., 50 atomic %-90 atomic % of germanium).

Next, a cap 16 including, for example, silicon or silicon germanium with a low germanium content (e.g. 10 atomic %

or less of germanium) is epitaxially formed on the semiconductor material (e.g., SiGe with 10 atomic % to 90 atomic % of germanium) in the third gap 78 of the patterned precursor semiconductor fins 18 to thereby transform the patterned precursor semiconductor fins 18 in each of the precursor semiconductor fin structures 70 into a plurality of semiconductor fins 10. Alternatively, and in other embodiments, the cap 16 is formed on the semiconductor material using other methods known in the art besides SEG. In the present embodiment, the cap 16 includes silicon. In other embodiments, the cap 16 is omitted.

After formation of the semiconductor material in the third gap 78 of the patterned precursor semiconductor fin 18, the patterned precursor semiconductor fin 18 having the semiconductor material formed therein may then hereinafter be referred to as a fin 10, if no cap 16 is being formed. Otherwise, in embodiments in which the cap 16 is being formed, the patterned precursor semiconductor fin 18 can then be referred to as a fin 10, once the cap 16 is formed on the semiconductor material in the third gap 78 of the patterned precursor semiconductor fin 18.

The semiconductor material (e.g., SiGe with 10 atomic % to 90 atomic % of germanium) inside the third gap 78 of the patterned precursor semiconductor fins 18 is hereinafter referred to as the inner core 12 of the semiconductor fins 10, and the first and second vertical sidewalls 14a, 14b of the patterned precursor semiconductor fins 18 is now hereinafter referred to as the outer shell of the semiconductor fins 10. Thus, the semiconductor fins 10 formed in the present embodiment include an inner core 12 including a semiconductor material (e.g., SiGe with 10 atomic % to 90 atomic % of germanium) therein, an outer shell 14a, 14b that laterally contacts and surrounds the inner core 12 of the semiconductor fins 10, and a cap (e.g. Si) that is located on an upper surface of the semiconductor material that provides the inner core 12. In some embodiment, the cap 16 is present on the inner core 12 and a top surface of the cap 16 is coplanar with a top surface of the first and second vertical sidewalls of the outer shell 14a, 14b of the semiconductor fins 10 in each of the precursor semiconductor fin structures 70. In other embodiments as mentioned above, the cap 16 may be omitted.

Next, referring to FIG. 9, the protective oxide spacers 72, and the first SIT spacers 52, and the second SIT spacers 56 of each of the precursor semiconductor fin structures 70 are all removed, thereby leaving the hard mask portions 41a, 41b on the semiconductor fins 10. The protective oxide spacers 72, and the first SIT spacer 52, and the second SIT spacer 56 may be removed by, for example, a wet etching process using for example, hydrofluoric acid (HF) or by a dry etch process such as, for example, RIE.

Further, the patterned hard mask portions 41a, 41b are all removed from the precursor semiconductor fin structures 70 using for example, a wet etch (e.g., hot phosphoric acid) or a dry etch (e.g., RIE) to thereby leave the plurality of semiconductor fins 10 on the insulator layer 20 of the SOI substrate 1 and form the semiconductor structure 100 as shown in FIG. 1.

Moreover, a gate structure (not shown) may be formed over the semiconductor fins 10, and then a source region (not shown) and a drain region (not shown) may be, for example, epitaxially grown on exposed portions of the semiconductor fins 10. Further, the source region and drain region may be provided with a desired dopant to define a plurality of FinFETs by any suitable method known in the art (e.g., ion implantation).

FIG. 10 illustrates a semiconductor structure 200 according to a second embodiment of the present application. Elements in the present embodiment that are the same as an element of the first embodiment will be labeled in the specification and the drawings with the same reference numeral as that element of the first embodiment.

The semiconductor structure 200 is an intermediate structure in the manufacture of a FinFET device and includes a plurality of trenches 202 formed in a bulk semiconductor substrate 203 that define a plurality of semiconductor fins 210 that are integral with the bulk semiconductor substrate 203. The bulk semiconductor substrate 203 may be formed from a semiconductor material such as, for example, silicon (Si), germanium (Ge), silicon germanium (SiGe), silicon germanium carbide (SiGeC), silicon carbide (SiC), an III-V compound semiconductor, an II-VI compound semiconductor or any combinations thereof. In the present embodiment, the bulk semiconductor substrate 203 is formed of, for example, silicon. Alternatively, and in some embodiments, the bulk semiconductor substrate 203 is formed of, for example, SiGe with germanium present in a low amount (e.g., 10 atomic % or less of germanium). It is noted that exemplary embodiments of the present invention are not limited to using a bulk semiconductor substrate 203 but rather in other embodiments an SOI substrate may instead also be used to form the semiconductor fins 210.

Referring back to the present embodiment illustrated in FIG. 10, the semiconductor fins 210 each include a lower portion 212, and an upper portion 214 located on an upper surface of the lower portion 212. For example, in the present embodiment, the lower portion 212 is formed from part of the bulk semiconductor substrate 203 and includes essentially the same material as the bulk semiconductor substrate. In some embodiments, the lower portion 212 of the semiconductor fins 210 includes, for example, silicon, or SiGe with germanium present in a low amount (e.g., 10 atomic % or less of germanium). Moreover, in the present embodiment, the upper portion 214 of the semiconductor fins 210 includes a semiconductor material such as, for example, SiGe, Ge, a III-V semiconductor, or a combination thereof formed by, for example, an epitaxial growth process within a patterned precursor semiconductor fin 203a' as described in further detail in connection with FIGS. 11-19. In some embodiments, the upper portion 214 of the semiconductor fins 210 includes, for example, SiGe with 10 atomic % to 90 atomic % of Ge. In other embodiments, the upper portion 214 of the semiconductor fins 210 includes, for example, SiGe with 20 atomic % to 90 atomic % of Ge. Each of the semiconductor fins 210 may have a width of, for example, 4 nm-16 nm.

In addition, the semiconductor structure 200 further includes an isolation material 220 located in the trenches 202 formed in the bulk semiconductor substrate 203 and between each of the semiconductor fins 210 among the plurality of semiconductor fins 210. For example, in an embodiment, the isolation material 220 includes, for example, an oxide such as silicon dioxide. The isolation material 220 partially fills the trenches 202. In other words, in the present embodiment, an upper surface of the isolation material 220 in the trenches 202 is lower than an upper surface of the trenches 202. In addition, in the present embodiment, an upper surface of the isolation material 220 is higher than an upper surface of the lower portion 212 of the semiconductor fins 210, and the upper surface of the isolation material 220 is lower than an upper surface of the upper portion 214 of the semiconductor fins 210.

Reference is now made to FIGS. 11-19, which illustrate a method for fabricating the semiconductor structure 200 shown in FIG. 10 according to the second embodiment of the present application. Specifically, and referring to FIG. 11, a bulk semiconductor substrate 203 is provided. In the present embodiment, the bulk semiconductor substrate 203 includes, for example, silicon or silicon germanium with germanium in an amount of 10 atomic % or less, but as noted above exemplary embodiments are not limited thereto. Alternatively, and in other embodiments, an SOI substrate may be provided instead in the bulk semiconductor substrate 203.

Next, a dielectric layer 230 is deposited onto the top surface of the bulk semiconductor substrate 203 using a deposition process such as, for example, chemical vapor deposition (CVD), atomic layer deposition (ALD), physical vapor deposition (PVD), evaporation, or spin-coating. The dielectric layer 230 may include, for example, a dielectric material such as, for example, an oxide or a nitride. In the present embodiment, the dielectric layer 230 includes an oxide (e.g., silicon dioxide). Alternatively, and in other embodiments, the dielectric layer 230 includes silicon nitride. Moreover, in some embodiments, the formation of the dielectric layer 230 may be omitted.

Next, a plurality of mandrels 50 may be formed on the dielectric layer 230, and then a first SIT spacer 52', a sacrificial SIT spacer 54 and a second SIT spacer 56' may be sequentially formed on the sidewalls of the mandrels 50 in essentially the same manner as described above with regard to the first embodiment illustrated in FIG. 2, except that in the present embodiment, the first and second SIT spacers 52', 56' are formed of a nitride instead of an oxide. Otherwise all of the materials, sizes and processes for forming the mandrels 50, the first SIT spacer 52', the sacrificial SIT spacer 54, and the second SIT spacer 56' in the present embodiment may be the same as set forth above in connection with the mandrels 50, the first SIT spacer 52, the sacrificial SIT spacer 54, and the second SIT spacer 56 in the first embodiment. However, in accordance with the present embodiment, the dielectric layer 230 may include a nitride and the first SIT spacer 52' and the second SIT spacer 56' may instead each include an oxide.

Next, referring to FIG. 12, the mandrels 50 may then be removed selective to the first SIT spacer 52', the second SIT spacer 56' and the sacrificial SIT spacer 54 using an anisotropic dry etch and/or wet etching process in essentially the same manner as discussed above in FIG. 3 of the first embodiment, thereby leaving a plurality of triple SIT spacer composite structures 60' located on the top surface of the dielectric layer 230. The triple SIT spacer composite structures 60' each include the first SIT spacer 52', the second SIT spacer 56' and the sacrificial SIT spacer 54 in between the first SIT spacer 52' and the second SIT spacer 56'. Further, as shown in FIG. 12, a pattern of the plurality of triple spacer composite structures 60' is revealed as a result of the removal of the mandrels 50.

Following removal of the mandrels 50, the triple SIT spacer composite structures 60' are then used to transfer the pattern to the dielectric layer 230 and the bulk semiconductor substrate 203, as shown in FIG. 13. In the present exemplary embodiment, the pattern of the triple SIT spacer composite structures 60' is first transferred to the dielectric layer 230, forming the patterned dielectric layers 231. This step may be carried out using, for example, a RIE process.

The patterned dielectric layer 231 can then be used to pattern the bulk semiconductor substrate 203. Again, for example, a RIE process may be used to etch trenches 202

into the bulk semiconductor substrate **203**, thereby defining a plurality of precursor semiconductor fin structures **70'**. The precursor semiconductor fin structures **70'** each include a sequential stack of a precursor semiconductor fin **203a** (formed from patterning the bulk semiconductor substrate **203**) that is integral with the bulk semiconductor substrate **203**, one of the patterned dielectric layers **231** and one of the plurality of triple SIT spacer composite structures **60'**. The particular etch chemistry used can be varied for etching selectivity between the dielectric layer **230** and the bulk semiconductor substrate **203**. Alternatively, as provided above, the use of a dielectric layer **230** in this process flow is optional. Thus, in the instance where a dielectric layer **230** is not employed, the pattern of the triple spacer composite structures **60'** is at this step transferred directly into the bulk semiconductor substrate **203** (e.g., using RIE).

Now referring to FIG. 14, the trenches **202** between the precursor semiconductor fin structures **60'** may then be filled with an isolation material **220** such as, for example, an oxide including silicon dioxide. A planarization process can follow the trench fill, thereby providing, for example, a shallow trench isolation (STI). In the present embodiment, the top surface of the isolation material **220** in each of the trenches **202** is coplanar with the top surface of each of the trenches **220**. An STI liner may also be provided as needed in the trenches prior to depositing the trench dielectric material therein. Alternatively, and in other embodiments, a protective oxide spacer such as the protective oxide layer **72** set forth in the FIG. 5 of the first embodiment may instead be formed on the sidewalls of the precursor semiconductor fins structures **70'** in similar fashion as set forth in the FIG. 5 of the first embodiment rather than filling the trenches **202** with isolation material **220**.

Next, referring to FIG. 15, an etching process is performed to remove the sacrificial SIT spacer **54** (i.e., the middle spacer of the triple SIT spacer composite structure **60'**) from each of the precursor semiconductor fin structures **70'**, thereby leaving a first gap **74'** between the first SIT spacer **52'** and the second SIT spacer **56'** in each of the precursor semiconductor fin structures **70'**, which thereby exposes a top surface of the patterned dielectric layers **231** in each of the precursor semiconductor fin structures **70'**. The same process for removing the sacrificial SIT spacer **54** as set forth in FIG. 6 of the first embodiment may also be used in the present embodiment to remove the sacrificial SIT spacer **54**.

Referring to FIG. 16, an RIE process using the first SIT spacer **52'** and the second SIT spacer **56'** of each of the precursor semiconductor fin structures **70'** as an etch mask is performed to etch all the way through a corresponding one of the patterned dielectric layers **231** and a corresponding one of the precursor semiconductor fins **203a** of each of the precursor semiconductor fin structures **70'**, thereby forming a second gap **76'** between patterned dielectric layer portions **231a**, **231b** (formed by etching the patterned dielectric layer **231**) and a third gap **78'** in the patterned precursor semiconductor fins **203a'** (formed by etching the precursor semiconductor fins **203a**) in each of the precursor semiconductor fin structures **70'**. The patterned precursor semiconductor fins **203a'** each include a base portion **206**, a first vertical sidewall **208** and second vertical sidewall **209** extending upward from the base portion **206** in a direction away from the bulk semiconductor substrate **203** with the third gap **78'** located between the first vertical sidewall **208** and the second vertical sidewall **209**. The third gap **78'** of the

patterned precursor semiconductor fins **203a'** exposes a top surface of the base portion **206** of the patterned precursor semiconductor fins **203a'**.

Next, referring to FIG. 17, a semiconductor material **215** is formed in the third gap **78'** of the patterned precursor semiconductor fins **203a'** by, for example, a selective epitaxial growth (SEG) process using the first vertical sidewall **208**, the second vertical sidewalls **209** and the upper surface of the base portion **206** of the patterned precursor semiconductor fins **203'** of each of the precursor semiconductor fin structures **70'** as a seed to grow the semiconductor material **215** (e.g., SiGe, Ge or III-V semiconductors, or a combination thereof) in the third gap **78'** of the patterned precursor semiconductor fins **203a'**. In the present embodiment, an SiGe layer including germanium in an amount from 10 atomic % to 90 atomic % is deposited and epitaxially grown in the third gap **78'** of the patterned precursor semiconductor fins **203a'** in each of the precursor semiconductor fin structures **70'** from the first and second vertical sidewalls **208**, **209** and the upper surface of the base portion **206** of the patterned precursor semiconductor fins **203a'**. In some embodiments, the layer of semiconductor material **215** deposited and epitaxially grown in third gap **78'** is SiGe with a high percentage of germanium present (i.e., 50 atomic %-90 atomic % of germanium).

Next, a cap **216** including, for example, silicon or silicon germanium with a low germanium content (e.g. 10 atomic % or less of germanium) is epitaxially formed on the semiconductor material **215** (e.g., SiGe layer with 10 atomic %-90 atomic % of germanium) in the third gap **78'** of the patterned precursor semiconductor fins **203a'**. Alternatively, and in other embodiments, the cap **216** is formed on the SiGe layer **215** using other methods known in the art besides SEG. In the present embodiment, the cap **216** includes, for example, silicon. Also, in some embodiment, the cap **216** located on the semiconductor material layer **215** fills the second gap **76'** and an upper surface of the cap **216** is higher than upper surfaces of the patterned dielectric layer portions **231a**, **231b**.

After the growth of semiconductor material **215** (e.g., SiGe with 10 atomic %-90 atomic % of germanium) inside the third gap **78'** and the optional deposition of the cap **216**, a condensation/annealing process may then be carried out. For example, in the present embodiment, condensation may be achieved by thermal oxidation of the semiconductor material **215** (e.g., SiGe with 10 atomic %-90 atomic % of germanium) in the third gap **78'** of the patterned precursor semiconductor fins **203a'** and the cap **216**.

As a result of the condensation and annealing process, the patterned precursor semiconductor fins **203a'** are now transformed into a plurality of semiconductor fins **210** which each include a lower portion **212** and an upper portion **214** located on the lower portion **212**. In particular, the first and second vertical sidewalls **208**, **209** of the patterned precursor semiconductor fins **203a'** and the cap **216** are all transformed into the semiconductor material **215** (e.g., SiGe with 10 atomic %-90 atomic % germanium) inside the third gap **78** of the patterned precursor semiconductor fins **203a'** by the above condensation and anneal process to define an upper portion **214** of the semiconductor fins **210**. Alternatively, and in other embodiment, the cap **216** may not be transformed into the semiconductor material **215** but rather the cap **216** remains essentially unchanged.

On the other hand, the lower portion **212** of the semiconductor fins **210**, which is formed from the base portion **206** of the patterned precursor semiconductor fins **203a'**, remains largely unchanged (e.g., only a minimal amount of the

semiconductor material **215** diffuses into the lower portion **212** of the semiconductor fin **210**) by the condensation/anneal process. Thus, the lower portion **212** of the semiconductor fin **210** still includes essentially the same material (e.g., Si) as the base portion **206** of the patterned precursor semiconductor fins **203a'** that was present prior to the condensation and anneal process. The lower portion **212** of the semiconductor fin **210** can be regarded as the inactive region of the semiconductor fin **210** for a FinFET device, and the upper portion **214** can be regarded as an active region of the semiconductor fin **210** for a FinFET device.

The condensation/anneal process causes the germanium to be uniformly distributed across the upper portion **214** of the semiconductor fin **210**. In addition, the condensation and annealing process causes the oxidation of the patterned dielectric layer portions **231a**, **231b** to thereby transform the patterned dielectric layer portions **231a**, **231b** into an oxidized dielectric layer **282** and also causes the formation of an additional oxide layer **284** on an upper surface of the oxidized dielectric layer **282** in the first gap **74'** of the precursor semiconductor fin structure **70'**.

The condensation/annealing process may be performed at a temperature in a range of, for example, 500-950° C. in an oxidizing atmosphere (e.g., nitrogen (N<sub>2</sub>)/oxygen (O<sub>2</sub>)) for a time period in a range of, for example, 5 minutes to 2 hours. It is noted that the lower the temperature used for the condensation/anneal process, the longer the process time for the condensation/anneal can be. Moreover, it is also noted that the higher the temperature used for the condensation/anneal process, the shorter the process time for the condensation/anneal can be. For example, in some embodiments, a temperature of 500° C. is used for the condensation/anneal process with a process time of 2 hours. In other embodiments, a temperature of 950° C. is used for the condensation/anneal process with a process time of five minutes.

Lastly, the oxidized dielectric layer **282**, the additional oxide layer **284** are removed from the precursor semiconductor fin structures **70'** using for example, a wet etch (e.g., hot phosphoric acid) or a dry etch (e.g., RIE), and the isolation material **220** in the trenches **202** between the precursor semiconductor fin structures **70'** is partially recessed by, for example, a suitable dry etching or wet etching process known in the art to thereby form the semiconductor structure **200** of FIG. **10** including the plurality of trenches **220** formed in the bulk semiconductor substrate **203** and which defines the plurality of semiconductor fins **210** that are integral with the bulk semiconductor substrate **203**.

Moreover, a gate structure (not shown) may be formed over the semiconductor fins **210**, and then a source region (not shown) and a drain region (not shown) may be, for example, epitaxially grown on exposed portions of the semiconductor fins **210**. Further, the source region and drain region may be provided with a desired dopant to define a plurality of FinFETs by any suitable method known in the art (e.g. ion implantation).

With the above-mentioned methods of exemplary embodiments of the present application, channels formed of, for example, SiGe having a high atomic percentage of germanium (i.e., 50 atomic %-90 atomic % of germanium) may be formed without the above-mentioned difficulties encountered in the conventional art in connection with forming high atomic % Ge channels for nodes. As discussed above, with conventional methods, it may be extremely difficult to form stable high atomic % germanium films without these germanium films incurring significant physical/damage caused by wet etching processes and/or dry

etching processes (e.g., RIE) when taking these high atomic % germanium films downstream.

In contrast, in exemplary embodiments of the present application, a precursor semiconductor fin (used to form the final semiconductor fins) and having an inner core filled with semiconductor material (e.g., SiGe with a high atomic % of Ge) and an outer shell (e.g., Si) surrounding the inner core may prevent due to its outer shell (e.g. Si) an attack on the semiconductor material (e.g., SiGe) that will ultimately be part of a channel region of a node. Also, since only a thin semiconductor layer (e.g. SiGe layer) is formed inside the precursor semiconductor fin inner core, the thin semiconductor layer will have a low probability of defect formation.

Now referring to FIG. **19**, a semiconductor structure **300** according to a third embodiment of the present application is shown. The semiconductor structure **300** may be an intermediate structure in the manufacture of a FinFET device and includes a plurality of trenches **302** formed in a bulk semiconductor substrate **303** that define a plurality of semiconductor fins **310** that are integral with the bulk semiconductor substrate **303**. The bulk semiconductor substrate **303** may be formed from a semiconductor material such as, for example, silicon (Si), germanium (Ge), silicon germanium (SiGe), silicon germanium carbide (SiGeC), silicon carbide (SiC), an III-V compound semiconductor, an II-VI compound semiconductor or any combinations thereof. Alternatively, and in other exemplary embodiments, an SOI substrate may be used instead of the bulk semiconductor substrate **303**.

Reference is now made to FIGS. **20-24**, which illustrate a method for fabricating the semiconductor structure **300** shown in FIG. **20** according to the third embodiment of the present application. Specifically, and referring to FIG. **20**, a bulk semiconductor substrate **303** is provided. The bulk semiconductor substrate **303** includes, for example, silicon (Si), germanium (Ge), silicon germanium (SiGe), silicon germanium carbide (SiGeC), silicon carbide (SiC), an III-V compound semiconductor, an II-VI compound semiconductor or any combinations thereof. Alternatively, and in exemplary embodiments, an SOI substrate may be used instead of the bulk semiconductor substrate **303**.

Next, a pad layer **340** is deposited onto the top surface of the bulk semiconductor substrate **303** using a deposition process such as, for example, chemical vapor deposition (CVD), atomic layer deposition (ALD), physical vapor deposition (PVD), evaporation, or spin-coating. The pad layer **340** may include, for example, a dielectric material such as, for example, a nitride or an oxide. In the present embodiment, the pad layer **340** includes a nitride (e.g., silicon nitride). Alternatively, and in other embodiments, the pad layer **340** includes an oxide (e.g. silicon oxide). Moreover, in some embodiments, the formation of the pad layer **340** may be omitted.

Next, a mandrel layer (not shown) is formed on the pad layer **340** using a deposition process such as, for example, atomic layer deposition (ALD) or chemical vapor deposition (CVD). The mandrel layer may include, for example, amorphous silicon, or amorphous carbon, or other suitable material. The mandrel layer is then subsequently patterned and etched using, for example, conventional lithography and etching processes to form a plurality of mandrels **350** on the pad layer **340**, as shown in FIG. **20**. The mandrels **350** can each have a width in the range of, for example, 15 nm-40 nm. In the present embodiment, there are two mandrels **350** formed but exemplary embodiments are not limited thereto but rather in other embodiments, less than two mandrels **350** or more than two mandrels **350** may be formed.

A conformal deposition process is then performed to form a first spacer material (not shown) on the top surface of the mandrels **350**, the sides of the mandrels **350**, and on exposed surfaces of the pad layer **340**. In one embodiment, the first spacer material comprises an oxide, but other materials are applicable as well. For example, alternatively in another embodiment, the first spacer material may be, for example, a nitride. It is noted that in embodiments where the pad layer **340** includes a nitride that the first spacer material should be an oxide. Alternatively, in embodiments in which the pad layer **340** includes an oxide, then the first spacer material should include a nitride.

Further, the first spacer material is etched using a sidewall image transfer (SIT) spacer formation etch process. The SIT spacer etch process is, for example, an RIE process which removes the first spacer material from the top surfaces of the mandrels **350** and from the upper surfaces of the pad layer **340** in between the mandrels **350**. As a result of the above RIE process, the first spacer material remains intact only on the sides of the mandrels **350**. This first spacer material on the sides of the mandrels **350** is referred to hereinafter as first SIT spacer **352**. The first SIT spacer **352** has a width of, for example, 6 nm-16 nm.

In addition, another conformal deposition process is then performed to form a mandrel spacer material (not shown) on the exposed top surfaces the mandrels **350** and on the first SIT spacers **352** located on the sides of the mandrels **350**, and on exposed surfaces of the pad layer **350**. In the present embodiment, the mandrel spacer material should comprise the same material as the mandrels **350** (e.g., polysilicon, amorphous silicon, or amorphous carbon).

Further, now referring to FIG. **21**, the mandrel spacer material is etched using the SIT spacer formation etch process. The SIT spacer etch process removes the mandrel spacer material from the top surfaces of the mandrels **350** and from the upper surfaces of the pad layer **340**. As a result of the RIE process, the mandrel spacer material remains intact only on the first SIT spacers **352** located on the sides of the mandrels **350**. This mandrel spacer material on the first SIT spacer **352** is referred to hereinafter as the mandrel SIT spacer **354**. The mandrel SIT spacer **354** has a width of, for example, from 15 nm-40 nm.

Moreover, as shown in FIG. **22**, a second SIT spacer **356** is then formed on the sidewalls of the mandrel SIT spacer **354**. The second SIT spacer **356** may be formed by the same processes and using the same materials as set forth above for forming the first SIT spacer **352**. In some embodiments, the second SIT spacer **356** may be formed of, for example, an oxide. In other embodiments, the second SIT spacer **356** may be formed of, for example, a nitride. The second SIT spacer **356** may have a width of, for example, 6 nm-16 nm.

It is noted that in the present embodiment, the mandrels **350** and the mandrel SIT spacer **354** should be formed of the same materials as each other. In some embodiments, the mandrels **350** and the mandrel SIT spacer **354** are each formed of amorphous silicon. In other embodiments, the mandrels **350** and the mandrel SIT spacer **354** are each formed of amorphous carbon. In still other embodiments, the mandrels **350** and the mandrel SIT spacer **354** are each formed of polysilicon. In addition, in the present embodiment, the mandrels **350** and the mandrel SIT spacer **354** should be approximately the same size as each other. Moreover, in the present embodiment, the first SIT spacer **352** and the second SIT spacer **356** should be formed of the same material as each other.

Next, referring to FIG. **23**, the mandrels **350** and the mandrel SIT spacers **354** may then be removed using an

anisotropic dry etch such as, for example, RIE, thereby leaving the first SIT spacers **352** and the second SIT spacers **356** on the pad layer **340**. Accordingly, in the present embodiment for each mandrel **350**, there are two (2) first SIT spacers **352** and two (2) second SIT spacers **356** formed for a total of eight (8) SIT spacers (i.e., four (4) first SIT spacers **352** and four (4) second SIT spacers **354**) formed in one SIT process but exemplary embodiments are limited thereto. Rather, in other embodiments more or less than two mandrels may be formed.

A pattern of the first SIT spacers **352** and the second SIT spacers **356** is revealed as a result of the above removal of the mandrels **350**, and the mandrel SIT spacers **354**, as shown in FIG. **23**. The pattern of the first SIT spacer **352** and the second SIT spacer **356** is then used to transfer the pattern to the pad layer **340** and the bulk semiconductor substrate **303**.

In the present exemplary embodiment shown in FIG. **24**, the pad layer **340**, once patterned, is referred to hereinafter as a patterned pad layer **341**. In this example, the pattern of the first SIT spacers **352** and the second SIT spacers **356** is first transferred to the pad layer **340**, forming the patterned pad layers **341**. This step may be carried out using, for example, a RIE process.

The patterned pad layer **341** can then be used to pattern the bulk semiconductor substrate **303**. Again, for example, a RIE process may be used to etch trenches **302** into the bulk semiconductor substrate **303**, thereby defining a plurality of first precursor semiconductor fin structures **360** and a plurality of second precursor semiconductor fin structures **362**. The first precursor semiconductor fin structures **362** each include a sequential stack of a semiconductor fin **310** that is integral with the bulk semiconductor substrate **303** (formed from patterning the bulk semiconductor substrate **303**), a corresponding one of the patterned pad layers **341** and a corresponding one of the first SIT spacers **352**. The second precursor semiconductor fin structures **362** each include a sequential stack of a semiconductor fin **310** that is integral with the bulk semiconductor substrate **303** (formed from patterning the bulk semiconductor substrate **303**), a corresponding one of the patterned pad layers **341** and a corresponding one of the second SIT spacers **356**.

The particular etch chemistry used can be varied for etching selectivity between the pad layer **340** and the bulk semiconductor substrate **303**. Alternatively, as provided above, the use of a pad layer **340** in this process flow is optional. Thus, in the instance where a dielectric layer is not employed, the pattern of the first SIT spacer **352** and the second SIT spacer **356** is at this step transferred directly into the bulk semiconductor substrate **303** (e.g., using RIE).

Next, the first SIT spacers **352** and the second SIT spacers **354** can then be removed from the first precursor semiconductor fin structures **360** and the second precursor semiconductor fin structures **362** using an RIE process, and the patterned pad layers **341** of the first precursor semiconductor fin structures **360** and the second precursor semiconductor fin structures **362** can then be removed using an RIE process to thereby form the semiconductor structure **300** of FIG. **19**.

As a result of forming four (4) SIT spacers (e.g., two (2) first SIT spacer **352** and two (2) second SIT spacers **356**) per mandrel for a total of eight (8) SIT spacers (i.e. four (4) first SIT spacers **352** and four (4) second SIT spacers **356**) using mandrel/SIT spacer process of the present embodiment, the fin density can be quadruple that of the original mandrel density. In particular, with methods of exemplary embodiments, the mandrel/SIT spacer process can be performed "X" times (with no limitation for the value of X) as one

process on the same level as each other to end up with a fin density that is 2× of the original mandrel density to thereby provide semiconductor fins having a tight pitch by performing the mandrel/SIT spacer process in one step.

For example, using a single SIT process (e.g., one mandrel) in accordance with exemplary embodiments of the application, the semiconductor fins **310** may be formed with pitches in the range of, for example, 36 nm-60 nm. In addition, using a double SIT process (e.g., two mandrels) in accordance with exemplary embodiments of the application, the semiconductor fins **310** may be formed with pitches in the range of, for example, 16 nm-60 nm.

Moreover, a gate structure (not shown) may be formed over the semiconductor fins **310**, and then a source region (not shown) and a drain region (not shown) may be, for example, epitaxially grown on exposed portions of the semiconductor fins. Further, the source region and drain region may be provided with a desired dopant to define a plurality of FinFETs by, for example, any other suitable method known in the art (e.g. ion implantation).

Now referring to FIGS. **25-26**, a fourth embodiment of the present application, which is a slight modification of the third embodiment of the present application is described below. Elements in the present embodiment which are in common with elements in the third embodiment will be labeled in the specification and drawings in connection with the present embodiments with the same reference numeral as that element in the third embodiment.

In particular, referring to FIG. **25**, in the present embodiment, a pad layer **340** is first formed on a bulk semiconductor substrate **303**, and then a plurality of mandrels **350** are formed on the pad layer **340** in the same manner as set forth above in connection with the third embodiment depicted in FIG. **20**. Further, a first SIT spacer **452** is then formed on sidewalls of the mandrels **350**, and a mandrel SIT spacer **354** is formed on sidewalls of the first SIT spacer **452**. In addition, a second SIT spacer **456** is then formed on the sidewalls of the mandrel SIT spacers **354**.

It is noted that the first SIT spacer **452**, the mandrel SIT spacer **354** and the second SIT spacers **456** may be formed in essentially the same manner and using the same materials and processes as used for forming the first SIT spacer **352**, the mandrel SIT spacer **354** and the second SIT spacer **356** in the third embodiment, except that in the present embodiment, the first SIT spacer **452** and the second SIT spacer **456** are formed of different materials from each other. For instance, in some embodiments, the first SIT spacer **452** is formed of oxide and the second SIT spacer **456** is formed of nitride. Alternatively, and in other embodiments, the first SIT spacer **452** is formed of nitride and the second SIT spacer **456** is formed of an oxide. Other than the above-mentioned difference, the third embodiment and the present embodiment are essentially the same as each other.

Next, referring to FIG. **26**, the mandrels **350** and the mandrel SIT spacer **354** may then be removed using an anisotropic dry etch such as RIE, leaving the first SIT spacers **452** and the second SIT spacers **456**. As discussed, the first SIT spacers **452** are formed of different materials than second SIT spacers **456**, thereby leaving two sets of different spacers on the pad layer **340**.

Further, a pattern of the first SIT spacer **452** and the second SIT spacer **456** may then be transferred to the pad layer **340** and the bulk semiconductor substrate **303** in essentially the same manner as discussed in connection with FIG. **24** of the third embodiment.

Lastly, the first SIT spacers **452** and the second SIT spacers **456**, and patterned pad layer (not shown) can then be

removed from each of a plurality of first precursor semiconductor fin structures (not shown) and a plurality of second precursor semiconductor fin structures (not shown) using, for example, an RIE process in similar fashion as discussed in connection with FIG. **24** of the third embodiment to thereby form a semiconductor structure which is similar to the semiconductor structure **300** of FIG. **19**.

Moreover, a gate structure (not shown) may be formed over the semiconductor fins, and then a source region (not shown) and a drain region (not shown) may be epitaxially grown on exposed portions of the semiconductor fins. Further, the source region and drain region may be provided with a desired dopant to define a plurality of FinFETs by any suitable method known in the art (e.g. ion implantation).

With the above-mentioned methods of exemplary embodiments of the present application, semiconductor fins for FinFET devices may be formed with tight pitches. Moreover, unlike in the conventional art, with exemplary embodiments of the present application multiple mandrels may be formed on a same level of a wafer as each other in one step for performing a mandrel/SIT spacer process. On the contrary, the conventional art forms the mandrels on different levels of a wafer from one another which thereby increases the manufacturing costs associated therewith. Another drawback to conventional SIT2 processes is that they may encounter difficulties in cutting (removing) the unwanted semiconductor fins after SIT2 due to the tight fin pitch (semiconductor fins are closely spaced and therefore it is difficult to completely cut the unwanted fin without compromising the adjacent device semiconductor fins).

While the present application has been described in terms of specific embodiments, it is evident in view of the foregoing description that numerous alternatives, modifications and variations will be apparent to those skilled in the art. Each of the various embodiments of the present application can be implemented alone, or in combination with any other embodiments of the present application unless expressly disclosed otherwise or otherwise impossible as would be known to one of ordinary skill in the art. Accordingly, the present application is intended to encompass all such alternatives, modifications and variations which fall within the scope and spirit of the present application and the following claims.

What is claimed is:

1. A semiconductor structure comprising:

a semiconductor substrate; and

at least one semiconductor fin disposed on the semiconductor substrate, wherein the at least one semiconductor fin includes an inner core comprising a silicon germanium (SiGe) material having a germanium content of from 10 atomic % to 90 atomic %, and an outer shell laterally surrounding the inner core of the at least one semiconductor fin, wherein the outer shell is composed of Si.

2. The semiconductor structure of claim 1, wherein the outer shell has a height that is greater than a height of the inner core.

3. The semiconductor structure of claim 2, further comprising a cap located on, and in direct physical contact with, a topmost surface of the inner core, the cap further comprising sidewalls physically contacting an upper portion of an inner sidewall of the outer core.

4. The semiconductor structure of claim 3, wherein the cap has a topmost surface that is coplanar with a topmost surface of the outer core.

21

5. The semiconductor structure of claim 1, wherein the germanium content of the silicon germanium material is from 20 atomic % to 90 atomic %.

6. The semiconductor structure of claim 2, wherein bottommost surfaces of the inner core and outer shell are coplanar with each other and are in direct physical contact with a topmost surface of the semiconductor substrate.

7. The semiconductor structure of claim 2, wherein an insulator layer is positioned between the semiconductor substrate and the at least one semiconductor fin, and wherein bottommost surfaces of the inner core and outer shell are coplanar with each other and are in direct physical contact with a topmost surface of the insulator material.

8. The semiconductor structure of claim 3, wherein the sidewalls of the cap are vertically aligned with sidewalls of the inner core.

9. The semiconductor structure of claim 1, further comprising a gate structure located on physically exposed surfaces of the at least one semiconductor fin.

10. The semiconductor structure of claim 1, wherein the inner core has an epitaxial relationship with the outer shell.

11. A semiconductor structure comprising:  
 a semiconductor substrate; and  
 at least one semiconductor fin disposed on the semiconductor substrate, wherein the at least one semiconductor fin includes an inner core comprising a silicon germanium (SiGe) material having a germanium content of from 10 atomic % to 90 atomic %, and an outer shell laterally surrounding the inner core of the at least one semiconductor fin, wherein the outer shell is composed of SiGe having a germanium content of no greater than 10 atomic %.

22

12. The semiconductor structure of claim 11, wherein the outer shell has a height that is greater than a height of the inner core.

13. The semiconductor structure of claim 12, further comprising a cap located on, and in direct physical contact with, a topmost surface of the inner core, the cap further comprising sidewalls physically contacting an upper portion of an inner sidewall of the outer core.

14. The semiconductor structure of claim 13, wherein the cap has a topmost surface that is coplanar with a topmost surface of the outer core.

15. The semiconductor structure of claim 11, wherein the germanium content of the silicon germanium material is from 20 atomic % to 90 atomic %.

16. The semiconductor structure of claim 12, wherein bottommost surfaces of the inner core and outer shell are coplanar with each other and are in direct physical contact with a topmost surface of the semiconductor substrate.

17. The semiconductor structure of claim 12, wherein an insulator layer is positioned between the semiconductor substrate and the at least one semiconductor fin, and wherein bottommost surfaces of the inner core and outer shell are coplanar with each other and are in direct physical contact with a topmost surface of the insulator material.

18. The semiconductor structure of claim 13, wherein the sidewalls of the cap are vertically aligned with sidewalls of the inner core.

19. The semiconductor structure of claim 11, further comprising a gate structure located on physically exposed surfaces of the at least one semiconductor fin.

20. The semiconductor structure of claim 11, wherein the inner core has an epitaxial relationship with the outer shell.

\* \* \* \* \*