

(19)



(11)

EP 2 563 867 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention of the grant of the patent:
30.09.2015 Bulletin 2015/40

(51) Int Cl.:
C09D 7100 (2006.01) C09D 7112 (2006.01)

(21) Application number: **11717556.2**

(86) International application number:
PCT/EP2011/056492

(22) Date of filing: **22.04.2011**

(87) International publication number:
WO 2011/134908 (03.11.2011 Gazette 2011/44)

(54) IMPROVED LOW TITANIUM DIOXIDE COATINGS

VERBESSERTE BESCHICHTUNGEN MIT GERINGEM TITANDIOXIDANTEIL
REVÊTEMENTS AMÉLIORÉS À FAIBLE TENEUR EN DIOXYDE DE TITANE

(84) Designated Contracting States:
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

- **WOODS, Anthony, David**
Slough Berkshire SL1 6NG (GB)
- **EMMETT, Simon, Nicholas**
Egham Surrey TW20 0NS (GB)
- **PEREZ-AMOROS, Javier**
Reading Berkshire RG1 3LJ (GB)

(30) Priority: **27.04.2010 US 328401 P**
27.04.2010 EP 10161204

(74) Representative: **Akzo Nobel IP Department**
Velperweg 76
6824 BM Arnhem (NL)

(43) Date of publication of application:
06.03.2013 Bulletin 2013/10

(73) Proprietor: **Akzo Nobel Coatings International B.V.**
6824 BM Arnhem (NL)

(56) References cited:
EP-A2- 0 113 435 US-A- 4 277 385
US-A- 5 201 948

(72) Inventors:
• **WHEELER, Stephen, Arthur**
Slough Berkshire SL1 2HP (GB)

EP 2 563 867 B1

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

[0001] This invention relates to reduced energy content pigmented coating compositions, especially pigmented paints of low to medium sheen, also known as matt or soft sheen paints. In particular it relates to paints of pigment volume content from 78 to 88% and having sheen of less than 30% when measured at 85°.

[0002] Light coloured pigmented paints usually contain high levels of titanium dioxide, TiO₂. This is because such pastel shades are predominantly white with a small amount of non-white colour added. Titanium dioxide is the best source of whiteness due to its high refractive index relative to typical binders used in paints. Unfortunately, TiO₂ requires large amounts of energy to extract it from the ground and then purify. In fact, in known high pigment volume content (PVC) paints of pastel/light colour, for example matt whites and matt light shades as hereinbelow described, the high TiO₂ content (typically 10 to 20vol%) used in order to achieve the desired colour and opacity is the main contributor to the total energy content of the paint.

[0003] By energy content, we mean the energy required to extract, refine and manufacture the ingredients comprising the paint; and the energy required to manufacture the paint itself.

[0004] Since most energy is generated by burning fossil fuel, high energy content usually results in high carbon dioxide emissions - hence the use of the alternative measure 'embedded CO₂' to indicate the energy content.

[0005] The adverse effect of such emissions on the global environment, especially climate change, is generally accepted by most serious commentators. Thus there is a need to reduce the energy consumed in producing such paints.

[0006] One approach to this is to reduce the TiO₂ content of the paint. However, this simply reduces the opacity of the dried coating and, whilst each coat of dried paint may well have reduced energy content, additional coats will be required in order to achieve opacity. Consequently, any benefit is lost or at least, significantly diminished. Other approaches replace some or all of the TiO₂ with extender pigments such as chalk. Whilst such extenders require less energy than TiO₂ to extract and refine, the lower refractive index of such extenders is very close to the binders used in paint. As such, they do not scatter light as well as TiO₂ and in order to compensate for the reduced amount of TiO₂ more extender must be added to the paint to achieve the correct colour and opacity. However, this raises the PVC further, eventually to the extent that air is trapped in the dried paint film. Whilst this increases the opacity, it also usually results in poorer wet scrub resistance.

[0007] One possible way out of this dilemma is to use calcined clay as this has good opacity and is less detrimental to the scrub resistance. However, manufacture of calcined clay requires clay to be heated to 1000°C thereby consuming large amounts of energy. Clearly, this does not result in significant energy savings and is thus not a preferred option.

[0008] United States Patent US 4,277,385 discloses paint compositions having PVC between 75 and 85% and further teaches that to avoid cracking in high PVC paint films, the formulation should be free of non-opacifying inorganic pigments (another name for extenders) essentially replacing them with non-film forming solid polymer particles. However, no attempt is made to minimise the TiO₂ content in these formulations and, thus the problem of high energy content and high CO₂ emissions are not addressed.

[0009] European Patent application EP 0113435 describes an aqueous paint having reduced TiO₂ content at PVC from 20 to 80%. It teaches to use mixtures comprising pigmented vesiculated polymer beads and larger opaque polymer particles having microvoids- but no pigments, to replace TiO₂ whilst maintaining burnish/scrub resistance. However, as pointed out in that application, pigmented vesiculated polymer beads themselves contain TiO₂ and thus add considerably to the TiO₂ content. This does little, if anything, to reduce the total energy content of the paint. Pigmented vesiculated polymer beads are polymer particles containing both and TiO₂ microvoids.

[0010] Thus, there is a need for improved paint compositions having reduced TiO₂ content and thus low energy content whilst also having good opacity and good wet scrub resistance.

[0011] Accordingly, there is provided an aqueous pigmented coating composition having a PVC of from 78 to 88% comprising, based on the total volume solids of the dry coating unless otherwise stated,

a) opacifying pigment particles comprising

- i) from 3 to 10% titanium dioxide
- ii) from 0 to 20% of hollow polymeric particles

b) non-opacifying extender particles comprising

- i) calcium magnesium carbonate and/or
- ii) calcium carbonate and/or
- iii) nepheline syenite and/or
- iv) kaolin

wherein i)+ii)+iii)+iv) = 40 to 80% and iv) is 0 to 20%

c) polymer binder particles of calculated Fox Tg of from 25 to 70°C having an acid value of from 15 to 65mg KOH/g of polymer and wherein the polymer particles are derived from acrylic monomers and optionally further comprising styrene and/or its derivatives

d) dispersant having a weight average molecular weight of at least 3500 Daltons.

e) fugitive coalescing solvent

wherein the composition is free of non-fugitive coalescing solvent.

[0012] Preferably the pigment volume content is from 79 to 85, more preferably from 80 to 85, even more preferably from 80 to 84 and most preferably from 81 to 83%. Any difference between the actual PVC and the sum of a) and b) is made up with other non-opacifying extender pigments as defined hereinbelow.

[0013] Preferably, the opacifying pigment particles are white.

[0014] More preferably, the opacifying pigment particles consist of TiO₂ and hollow polymer particles. Even more preferably, the opacifying pigment particles consist of TiO₂ only. TiO₂ produced by the well known chloride process is preferred in this invention as it requires less energy to manufacture and thus introduces less embedded CO₂ to the coating.

[0015] The titanium dioxide is preferably in the rutile form as anatase is a less efficient scatterer and thus more is required to achieve the same degree of opacity.

[0016] Preferably the TiO₂ comprises 3 to 9, more preferably from 3 to 8, even more preferably from 5 to 8, yet more preferably from 6 to 8, still more preferably from 5 to 7 and most preferably from 6 to 7vol% of the composition.

[0017] Hollow polymeric, preferably spherical, particles, may also be used to provide white opacity. Suitable such particles contain a void of from 30 to 50% by vol of the particle. Such particles are available as aqueous dispersions under the tradename Ropaque™. However, the composition preferably contains less than 10% by volume of such polymeric hollow sphere white pigments because they contribute significantly to the energy content of the paint. Additionally, they tend to provide unwanted gloss to the dried paint film following drying. More preferably, the composition is free of such hollow polymeric particles.

[0018] Similarly, calcined clay, a white pigment may be used as a partial replacement for TiO₂. However, since the production of calcined clay is itself energy intensive, care must be taken to limit the amount of calcined clay used in the formulation. To take maximum advantage of the energy savings to be made it is preferred that the coating composition is free of calcined clay. Nevertheless, preferably, up to 30vol% of calcined clay may be used, more preferably from 5 to 20vol% and most preferably from 10 to 15vol%. Pigmented vesiculated polymer beads are also preferably avoided.

[0019] Of course, coloured opacifying pigments of different hue may also be added to the compositions of the present invention, in addition to the other opacifying pigment particles, to produce pastel/light colours as discussed in greater detail hereinbelow.

[0020] By non-opacifying extender particles is meant inorganic particles that have a refractive index the same as or similar to that of the polymer binder. Since the opacifying strength of a particulate material is a consequence of the difference in refractive index of the material and the medium in which it is dispersed and its particle size, such extenders are regarded essentially as non-opacifiers, see page 35 to 37, Paint and Surface Coatings - theory and practice edited by R.Lambourne and published by John Wiley and Sons. That is not to say that they do not contribute to opacity at all but rather that any contribution is small in comparison to TiO₂.

[0021] Extenders are usually not pure white and can provide some grey or yellow hue to the coating.

[0022] Suitable examples of non-opacifying extender particles include calcium magnesium carbonate, calcium carbonate, nepheline syenite, kaolin, talc, silica, diatomaceous silica, mica and calcium sulphate. Preferably, the non-opacifying extender particles are selected from the group consisting of calcium magnesium carbonate, calcium carbonate, nephelene syenite and kaolin. Preferably, the non-opacifying extender particles are selected from the list consisting of calcium magnesium carbonate, calcium carbonate, nephelene syenite and kaolin. Even more preferably they are selected from the group consisting of calcium magnesium carbonate, calcium carbonate and kaolin.

[0023] The mineral known as dolomite is a convenient and cost effective source of calcium magnesium carbonate, CaMg(CO₃)₂. Dolomite is a preferred source of calcium magnesium carbonate for use in the present invention. It is available in powder form of differing mean particle sizes.

[0024] Suitable forms of calcium carbonate include calcite including precipitated calcite. Socal P3 is an example of suitable precipitated calcium carbonate, in the form of calcite. A suitable ground calcium carbonate is Omyacoat 850 OG.

[0025] Nepheline syenite can be used to partly or wholly replace the calcium carbonate

[0026] Kaolin, Al₂Si₂O₅(OH)₄, is a type of clay. Adding kaolin above 20vol% to the composition (calculated on the dry coating) results in poor wet scrub resistance. Furthermore, at such high levels of kaolin, the coating viscosity is too high to allow easy application using conventional application techniques-such as rollers or brushes-and allow the paint to

flow to produce an acceptably smooth finish. Advantageously, the amount of kaolin should be from 0.5 to 20, more preferably from 5 to 15 and most preferably from 6 to 12vol%.

[0027] Preferably, the non-opacifying extender particles comprise from 60 to 75, more preferably from 65 to 75 and most preferably from 66 to 73vol% of the dry coating.

[0028] Advantageously, from 20 to 50% of the total volume solids of the dry coating should comprise extender particles having mean particle size d_{50} of ≤ 2 microns. This ensures that the TiO_2 particles are sufficiently spaced apart so that scattering is efficient and therefore opacity optimised.

[0029] The particle sizes of the extenders are quoted as d_{50} diameters. This means that 50% of the particles by volume are below this diameter.

[0030] The binder comprises an aqueous dispersion of polymer binder particles, often referred to as latex. More preferably, such dispersions are made using emulsion polymerisation methods.

[0031] For simplicity, the word 'polymer' in this specification is used to cover homopolymers and copolymers comprising two or more monomer variants.

[0032] The polymer comprising the binder particles is preferably a styrene-acrylic polymer or a pure acrylic.

[0033] By pure acrylic is meant that the polymer is derived only from monomers selected from the esters of acrylic acid and methacrylic acid and the acids themselves.

[0034] By styrene-acrylic is meant that some styrene and/or its copolymerisable derivatives are copolymerised in the polymer. Suitable such styrene derivatives include α -methyl styrene and vinyl toluene.

[0035] More preferred are styrene-acrylic polymer particles as these require the least amount of energy to produce them compared to the pure acrylics and most preferably, the polymer binder in the present invention is derived from styrene, butyl acrylate and a copolymerisable acid. Most preferably, the copolymerisable acid is acrylic acid and/or methacrylic acid.

[0036] Preferably the binder level of the coating is from 5 to 20%, more preferably 5 to 15 and most preferably from 8 to 15% calculated on volume solids.

[0037] Suitable acrylic monomers include alkyl esters of acrylic or methacrylic acid such as methyl methacrylate, ethyl methacrylate, butyl methacrylate, ethyl acrylate, butyl acrylate, hexyl acrylate, n-octyl acrylate, lauryl methacrylate, 2-ethylhexyl methacrylate, nonyl acrylate, decyl acrylate, benzyl methacrylate, isobutyl methacrylate, isobornyl methacrylate the hydroxyalkyl esters of the same acids such as 2-hydroxyethyl acrylate, 2-hydroxyethyl methacrylate, and 2-hydroxypropyl methacrylate.

[0038] The acid value of the polymer is preferably from 15 to 60, more preferably from 15 to 55, even more preferably from 15 to 45 and most preferably from 16 to 30mg KOH/g non-vol polymer. Below an acid value of 15mg KOH/g polymer produces dried paint of poorer wet scrub resistance, whilst above 65 mg KOH/g polymer tends to degrade the wet scrub resistance of the dried paint.

[0039] The acid value is varied by copolymerising acid functional monomers into the polymer comprising the particles. Suitable such monomers include acrylic acid, methacrylic acid and maleic acid or its anhydride. Preferably, the acid used is acrylic acid.

[0040] Polymers of mean particle size no more than 0.3 μm are preferred as they are better at binding together the particulate components of the composition.

[0041] Preferably the number average mean particle size of the polymer particles is from 0.05 to 0.30 μm , more preferably from 0.07 to 0.15 μm and most preferably from 0.08 to 0.14 μm . The number refers to the diameter of the particles. The smaller particle size is preferred as it results in improved scrub resistance, which is particularly important at the high PVC of the present invention.

[0042] The glass transition temperature, T_g , of the polymer binder can be adjusted by the choice of monomers and the relative amounts of each comprising the polymer. Preferably, T_g is from 26 to 70°C, more preferably from 26 to 55°C, even more preferably from 26 to 45°C and most preferably from 27 to 35°C.

[0043] For the avoidance of doubt, any reference to T_g in this specification is to calculated Fox T_g unless otherwise stated.

[0044] When higher T_g polymers are used, more coalescing and/or plasticizing solvents are required to enable a coherent coating film to form at normal room temperature of approximately 20 to 25°C. Lower T_g polymers are preferred as these can film form effectively with reduced levels of solvents thereby keeping both the volatile organic content of the paint and the energy content of the paint to a minimum.

[0045] Pigment dispersants generally comprise a hydrophilic portion and a hydrophobic portion and, depending on the nature of the dispersing medium and the pigment surface, one portion will have a greater affinity for the pigment surface and the other portion for the dispersing medium. In this way a stable dispersion of pigment dispersed in the medium can be produced.

[0046] In the present invention, the dispersant is required to disperse and stabilise the non-polymeric opacifying pigments (including any colour pigments) and non-opacifying extender particles. The weight average molecular weight of the dispersant must be at least 3500 Daltons, preferably 4000, more preferably 5000 and most preferably 6000

Daltons. The upper limit of the weight average molecular weight is preferably 50000 Daltons, more preferably 40000, even more preferably 30000, still more preferably 20000 and most preferably 15000 Daltons. The most preferred average molecular weight of the dispersant is from 3500 to 20000 Daltons.

[0047] Suitable dispersants for use in the present invention include Orotan™ 681, Orotan™ 731, Orotan 2002, Dispex HDN (a hydrophobic sodium salt of an acrylic copolymer), Dispex N40 (a sodium salt of an acrylic polymer). Each of these has molecular weight greater than 3500 Daltons.

[0048] Pastel colours are usually produced by adding small amounts of various colour pigments, in the form of a concentrated dispersion (also known as colorants or tinters), to a white paint.

[0049] In order to achieve the desired scrub resistance it is important that the coalescing solvent is fugitive, meaning that it must leave the paint film. Depending on the solvent and the polymer composition of the binder, this may happen very quickly or may take some days. For guidance, we have found that a coating such as example 1 of the invention (2wt% Texanol on liquid paint) contains only 0.06wt% of Texanol in the film after 24 hrs of drying under drying ambient conditions and only 0.01wt% after a further six days.

[0050] Preferably, the fugitive coalescing solvent is able to reduce the calculated Fox Tg of the polymer to from -10 to -80°C, more preferably to from -10 to -60°C, even more preferably to from -10 to -40°C and most preferably to from -10 to -20°C. The reduction is preferably achieved using up to 4wt%, even more preferably up to 3wt%, yet more preferably up to 2wt%, still more preferably up to 1% and most preferably up to 0.5wt% calculated on the liquid formulation.

[0051] The extent to which a coalescing solvent reduces the calculated Fox Tg of a particular polymer may be calculated according to equation 1:

$$1/T_g = V_p/T_{g_p} + \alpha V_s/T_{g_s} \quad \text{equation 1}$$

where T_g_p and T_g_s is the glass transition temperature of the polymer and the solvent respectively

T_g is the glass transition temperature of the plasticised system

V_p and V_s are the volume fractions of the polymer and the solvent respectively

α is a factor accounting for small changes in plasticising efficiency and is assumed to be 1 for the purposes of this invention.

[0052] Suitable fugitive coalescing solvents include Lusolvan™ FBH (di-isobutyl ester of a mixture of dicarboxylic acids), Lusolvan™ PP (di-isobutyl ester of a mixture of dicarboxylic acids), Loxanol™ EFC 300 (linearic ester), Butyl Carbitol™, Butyl Cellosolve, Dowanol™ EPh (ethylene glycol phenyl ether), Dowanol™ PPh (propylene glycol phenyl ether), Dowanol TPnB (tripropylene glycol n-butyl ether),™Dowanol DPnB, DBE_9™ (a mixture of refined dimethyl glutarate and dimethyl succinate), Eastman DB™ solvent, Eastman EB™ (ethylene glycol monbutyl ether), Texanol™ (2,2,4-trimethyl-1,3-pentanediol monoisobutyrate), Dapro™ FX 511, Velate™ 262, Arcosolve™ DPnB, Arcosolve™ TPnB and benzyl alcohol

[0053] A list of solvents and their glass transition temperatures can be found in the article 'An Applied Approach to Film Formation' by JW Taylor and TD Klots, presented at the 29th Annual Waterborne, High Solids and Powder Coatings Symposium.

[0054] Some representative glass transition temperatures of solvents are listed below:

Pamolyn™ 300	-80°C
Texanol™	-84°C
Arcosolv™ PtB	-88°C
Carbitol™ Acetate	-95°C
Butyl carbitol™ acetate	-100°C

[0055] Thickeners are used in coating compositions to control the viscosity and rheology profile of the compositions. Suitable rheology modifiers for use in the present invention include carboxymethyl cellulose types such as Blanose™ 731; hydroxyethyl cellulose such as Natroso™ I 250 and Tylose™ H grades; hydrophobically modified hydroxyethyl cellulose such as Natrolsol™ Plus and Tylose™ HX grades; ethyl and ethylmethyl hydroxyethyl cellulose such as Beromocoll™ EHM grades; non-ionic synthetic associative thickener (NSAT's) such as Acrysol™ RM825, Acrysol™ SCT 275, Acrysol™ RM2020, Aquaflo™ NHS300, Coapur™ 830W, Rheolate™ 450, Bermodol™ PUR grades; hydrophobically modified alkali swellable emulsion (HASE) thickeners such as Acrysol™ TT935, Acrysol™ DR73, Ciba Rheovis™ and Alkali swellable synthetic thickeners such as Acrysol™ ASE 60.

[0056] The NSAT, HASE, ASST and HEUR type thickeners are preferred over the cellulosic types.

[0057] The benefits of the invention are advantageously achieved in coloured coating compositions normally requiring high levels of TiO₂. Such colours are the greys and lightly coloured coatings, often referred to as pastel or light colours,

and of course, the whites.

[0058] These, and all colours, can be defined using the well known Y, C*, h* system. In the system, any colour can be represented by

- 5 i. its hue, depicted by h*
- ii. its chroma, C*,
- iii. its light reflectance value, Y

[0059] These terms are defined scientifically by the Commission Internationale de l'Eclairage (CIE) [see 'International Lighting Vocabulary', 4th Edition, published IEC/CIE 017.4-1987. ISBN 978 3 900734 07 7].

[0060] For the avoidance of any doubt, any reference to coating colour in this specification is to the colour of the coating when dry, unless otherwise stated.

[0061] Hue is a measure of how close the colour is to red, yellow, green and blue. It is depicted by hue angle ranging from 0 to 360° where the angle defines the position of the hue in colour space, where red, yellow, green and blue are at angles of 0, 90, 180 and 270° respectively. Angles between these 'cardinal points' indicate intermediate colours eg a hue angle of 45° is a reddish yellow (orange) colour.

[0062] Chroma is a measure of colour intensity, ie the extent to which it is either a pastel/ light colour or a strong colour or something in between. Chroma can take values from 0 to 100 with the higher numbers indicating stronger colours. Colours having a chroma value of 0 are 'neutral' greys lying on an axis from black to white.

[0063] The light reflectance value is a measure of the perceived lightness of the colour, ranging from 0 to 100, with 0 representing black and 100 white.

[0064] Figure 1 shows a simplified representation of the Y, C*, h* system. It shows a slice of colour space at about the mid point of the light reflectance value, Y, range. The Y axis runs from 0 to 100. Red, yellow, green and blue are shown in their appropriate positions on the hue, circle. The C* axis runs from zero at the origin to 100 at the perimeter. At each value of Y, further slices of hue are associated representing lighter and darker colours. At both the dark and the light end of the Y scale, the colours are less intense, and thus chroma is inevitably low. For this reason, colour space is often depicted as a sphere, although in truth it is more an irregular cylinder in shape.

[0065] Using the CIE notation, the grey or light coloured compositions which benefit most from the present invention, can be identified as those colours, including whites, satisfying the following criteria;

30

$$C^* < C_{critical} \quad \text{equation 1}$$

35

$$Y > mC^* + 35 \quad \text{equation 2}$$

where m and C_{critical} take the values in Table 1 below.

40

Table 1

Hue angle h*	m	C _{critical}
0	0.098	39.063
10	0.063	42.739
20	0.231	40.130
30	0.399	37.522
40	0.498	37.444
50	0.579	38.000
60	0.655	39.500
70	0.732	41.000
80	0.793	45.286
90	0.854	49.571
100	0.803	47.136
110	0.740	43.955

55

EP 2 563 867 B1

(continued)

5

10

15

20

25

30

35

40

Hue angle h*	m	C _{critical}
120	0.663	41.727
130	0.580	39.909
140	0.498	38.565
150	0.416	37.696
160	0.346	37.381
170	0.318	39.586
180	0.283	40.850
190	0.190	39.350
200	0.101	38.000
210	0.060	38.000
220	0.021	38.333
230	-0.007	40.000
240	-0.041	40.314
250	-0.083	38.600
260	-0.125	36.886
270	-0.167	35.171
280	-0.152	34.640
290	-0.131	34.240
300	-0.079	34.000
310	0.016	34.000
320	0.112	34.000
330	0.207	34.000
340	0.235	34.471
350	0.161	35.647
360	0.098	39.063

[0066] Above the C_{critical} value the colour intensity is too high to be perceived as a pastel colour.

[0067] The values of m and C_{critical} at intermediate hue angles can be calculated by linear interpolation.

[0068] The table enables the calculation of C* and Y for any given hue and thus the whites, grey or pastel/light shades are explicitly identified.

[0069] Coatings having chroma, C* less than about 5 and a Y value more than 95 are perceived by the human eye as white.

[0070] The values of C*, Y and h* of any colour may be calculated from the spectral reflectance curve of the colour, measured using a spectrophotometer in accordance with the manufacturers instructions. A suitable spectrophotometer is the Datacolor Spectraflash SF 600.

[0071] Preferably, the dried coating compositions of the invention satisfy equations 1 and 2. More preferably, the dried coating compositions have a chroma less than 5 and a Y value greater than 85.

[0072] Preferably, the gloss value of the dried coating is less than 30%, when measured at 85°, more preferably less than 20%, even more preferably less than 10%, yet more preferably less than 5% and most preferably from 2 to 8%.

[0073] The coating composition may also contain other ingredients that are standard for coatings such as waxes, rheological modifiers, surfactants, anti-foams, tackifiers, plasticisers, crosslinking agents, flow aids, biocides and clays.

[0074] In a further aspect of the invention there is provided a method of coating an article or structure having a surface with a composition as defined in any one of the preceding claims including the steps of applying at least one liquid layer

EP 2 563 867 B1

of the coating by brush, roller, pad or spray; allowing or causing the layer to dry and/or harden.

[0075] In a still further aspect of the invention there is provided an article or structure having a surface coated with a composition as defined according to the present invention.

[0076] The invention will now be illustrated by the following examples.

[0077] The following ingredients were used in preparing the examples.

[0078] Tioxide™ TR92 is a Rutile form of TiO₂ (density of 4.05g/cm³) available from Huntsman Tioxide Europe Ltd, Hartlepool, Cleveland, United Kingdom.

Microdol™ H200 and H600 are both dolomites (density of 2.85g/cm³) and are available from Omya. Omya House, Derby, United Kingdom

Socal™ P3 is precipitated calcium carbonate (density of 2.70g/cm³) and is available from Solvay, Rheinberg, Germany. China Clay Supreme-kaolin (density 2.60g/cm³) is available from Imerys.

Ropaque™ Ultra E is a 30% non-vol dispersion of hollow polymeric spherical particles (density of 0.591 g/cm³) and is available from Rohm and Haas, Philadelphia, USA.

Steabright™ is a talc (density of 2.78g/cm³) available from Rio Tinto PLC, London, United Kingdom

Texanol™ is an ester alcohol coalescent available from Eastman Chemical Company, Tennessee, USA.

TegMer™ 804 is a tetra ethylene glycol ester available from Hallstar, 120 South Riverside Plaza, Suite 1620, Chicago, Illinois 60606, USA.

Orotan™ 731-A is a pigment dispersing agent (25wt% non-vol; density of non-vol is 1 g/cm³) available from Rohm & Haas Philadelphia, USA.

Disponil™ A1580 is a surfactant (80wt% non-vol; density of non-vol is 1.00 g/cm³) and is available from Cognis Deutschland GmbH & Co. KG. PO Box 130164, Germany.

Dispex N40 is a dispersant available from Ciba.

Dispelair™ CF 823 is a defoamer (60wt% non-vol; density of non-vol is 1.00g/cm³) and is available from Blackburn Chemicals Ltd, Whitebirk Industrial Estate, Blackburn, United Kingdom.

Blanose™ 7M 31C SCS 9554 (density 1.59g/cm³) is available from Hercules GmbH, Dusseldorf, Germany.

Natrosol Plus 331 is a cellulosic thickener available from Hercules Aqualon. Acticide CHR 0107 a biocide is available from Thor at Wincham Avenue, Wincham, Northwich, Cheshire, England.

Aquaflow™ NHS 300 (23wt% non-vol; density of non-vol is 1.00g/cm³) is available from Hercules GmbH, Dusseldorf, Germany.

China Clay Supreme (density is 2.60g/cm³) is available from Imerys.

Latex 1 is a styrene/butyl acrylate/methacrylic acid copolymer of Tg 10°C and Acid value 23.5mg KOH/g polymer and 50wt% solids content.

Latex 2 is a styrene/butyl acrylate/acrylic acid copolymer of Tg 50°C and Acid Value 37.4mg KOH/g polymer and 50wt% solids content.

Latex 3 is a styrene/butyl acrylate/acrylic acid copolymer of Tg 30°C and Acid Value 23.5mg KOH/g polymer and 50wt% solids content.

Test Procedures

[0079] The following test methods were used in evaluating the examples:

Molecular Weight of Dispersant

[0080] Aqueous GPC was used set up was used to measure molecular weight.

The equipment and conditions used were;

Columns: 2 x 30cm TSK GMPWXL GPC columns from Tosoh

Eluent: 0.3M Sodium Nitrate, 0.01M Sodium Phosphate with pH adjusted to 7.5 using 0.1 M NaOH

Flow rate: 1.0 ml/min

Detector; Waters 410 differential refractive index detector.

Software; Waters Millennium 32 v3.05.01

The instrument was calibrated with Dextran standards covering the range 342 - 401000 g/mol.

Samples were prepared by diluting 0.1 g in 10 mls of eluent and filtering through a 0.45 micron PVDF membrane.

Injection Volume was 100µl

Opacity (Contrast Ratio)

[0081] Opacity was measured in accordance with BS 3900-D4.

At least 90% is considered acceptable.

EP 2 563 867 B1

The measured opacity is not linear in its relationship to how the eye perceives opacity. Thus, small differences in measured opacity are seen by the eye as much larger differences.

Gloss

5

[0082] Gloss was measured in accordance with BS EN ISO 2813, BS 3900-D5.

Wet Scrub Resistance

10 **[0083]** Scrub resistance of the dried film was measured in accordance with BS EN ISO 11998 using 200 cycles with the modification that the loss was recorded as mg/cm². A loss of less than 6mg/cm² removal is acceptable.

High Shear Viscosity

15 **[0084]** The high shear viscosity is measured at 25°C using an ICI Cone and Plate viscometer (available from Research Equipment London Ltd, London, TW2 5NX) operating at 10,000s⁻¹.

Rotothinner viscosity (Paint)

20 **[0085]** The medium shear viscosity is measured at 25°C using a Rotothinner viscometer (available from Sheen Instruments Ltd, Kingston-upon-Thames, Surrey, UK) fitted with a standard disc rotor rotating at about 562rpm which is equivalent to a shear rate of ca 250 s⁻¹.

Particle Size of Extenders

25 **[0086]** The particle size of the extenders was measured using a Mastersizer in accordance with ISO 13323 part 1 and 2.

Examples

30 **[0087]** The invention will now be illustrated by the following examples. Numbered examples are of the invention and comparative examples are referenced with letters. In all cases the wt% formulation refers to the liquid paint and the vol% to the dried coating.

[0088] The following method was used to make the paints in each case.

Millbase stage

35 **[0089]** Using a 5 litre metal dispersion vessel, load the Water (1), Texanol, Orotan or Dispex, Disponil, Acticide and half the amount of Dispelair. Place vessel under High Speed Dispenser fitted with a saw tooth blade. Stir at slow speed so that no splashing is observed. Add Microdol H200 and H600, Socal P3, China Clay Supreme, Steabright and Tioxide TR92, run for 2 minutes at slow speed then add Blanose or Natrosol thickener. Over 5minutes slowly increase the speed as the paint thickens. Unit should be running at approximately 2500 r.p.m. (depending on volume), but without splashing. Stir for a further 30minutes. Stop unit half way through to ensure no pigment has stuck to sides/base of vessel by hand stirring. Turn unit back on to high speed, after 30 minutes reduce to slow speed. Check the state of dispersion of the millbase for bits by brushing out on a card. If acceptable amount of bits, add Water (2) and run for a further 2minutes and then switch off the stirrer.

40 The total amount of water showed in the example formulation was in the ratio of: water (1) : water (2) : water (3) =45.5 : 30.3 : 24.2

Paint stage

50 **[0090]** Load Latex 1 into a suitably sized vessel and place under a stirrer fitted with a paddle blade. Load Ropaque, the rest of the Dispelair, the Millbase prepared above, Water (3) and Aquaflow. Adjust the stirrer speed as the volume in the vessel increases, being careful to avoid splashing.

55 **[0091]** Stir for a further 15 minutes at low speed (approx 500 r.p.m).

Examples 1 and A

[0092] Examples 1 and A are essentially identical other than the Tg of the polymer binder particles differ.

EP 2 563 867 B1

Example 1 of the invention formulated using a latex comprising Tg 50°C polymer particles passes the wet scrubs test whereas Comparative example A using polymer binder particles of Tg 10°C, fails the wet scrubs test.

Example	1		Comparative Example A	
	wt% (wet coating)	vol% (dry coating)	wt (% of wet coating)	vol% (dry coating)
Aquaflow NHS 300	0.50	0.34	0.50	0.34
Acticide CHR 0107	0.24	0.07	0.24	0.07
Disponil A1580	0.50	1.62	0.50	1.62
Dispelair CF823	0.25	0.66	0.25	0.66
Dispex N40	0.20	0.23	0.50	1.33
Blanose 7M 31C	0.50	1.33	0.20	0.23
Texanol	2.00	0	2.00	0
Water	35.31	0	35.31	0
Tioxide TR92	6.50	6.84	6.50	6.84
Socal P3	12.50	19.64	12.50	19.64
Steabright	8.50	12.97	8.50	12.97
China Clay Supreme	5.50	8.97	5.50	8.97
Microdol H600	8.50	13.11	8.50	13.11
Microdol H200	8.50	12.88	8.50	12.88
Ropaque (Tm) Ultra E	4.00	8.58	4.00	8.58
Latex 1 (Tg 10°C)	0	0	6.50	12.76
Latex 2 (Tg 50°C)	6.50	12.76	0	0
Total	100.00	100.00	100.00	100.00
Wet sScrubs weight loss (mg/cm ²)		5		9
Density (kg/L)		1.49		1.49
PVC (%)		82.99		82.99
vol% solids		35.12		35.12
Sum non-opacifying particles (% of dry vol)		67.56		67.56

[0093] The Tg of the polymer binder (Latex 2 of Tg 50°C) in the presence of the coalescing solvent is calculated using equation 1 as previously discussed

$$1/Tg = V_p/Tg_p + \alpha V_s/Tg_s \quad \text{equation 1}$$

[0094] The Tg of Texanol is -84°C
 The volume fractions are calculated based on the polymer and the solvent alone.
 So for example 1 the total weight% of polymer is 3.25 (being 50% of 6.5) and the solvent is 2.00. The specific gravity of the polymer and the solvent is 1.08 and 0.95 respectively and the volume fraction is therefore 0.151 and 0.849 respectively.
 So the Tg of the polymer in the presence of the Texanol is -23.0°C.

EP 2 563 867 B1

Examples 2 and B

[0095] These are essentially identical other than the PVC.
Comparative example B, at a PVC of 90.31% fails the wet scrubs test.

5

10

15

20

25

30

35

40

Example	2		Comparative Example B	
	wt% (wet coating)	vol% (dry coating)	wt (% of wet coating)	vol% (dry coating)
Aquaflow NHS 300	1.50	1.01	1.50	1.11
Acticide CHR 0107	0.24	0.07	0.24	0.08
Disponil A1580	0.50	1.60	0.50	1.76
Dispelair CF823	0.23	0.60	0.23	0.66
Orotan731 A	1.00	0.65	1.00	0.72
Blanose 7M 31C	0.50	1.32	0.50	1.45
Texanol	2.00	0	2.00	0
Water	33.53	0	38.19	0
Tioxide TR92	6.50	6.77	6.50	7.44
Socal P3	12.50	19.43	12.5	21.37
Steabright	8.50	12.83	8.50	14.11
China Clay Supreme	5.50	8.88	5.50	9.76
Microdol H600	8.50	12.97	8.50	14.26
Microdol H200	8.50	12.74	8.50	14.01
Ropaque (Tm) Ultra E	4.00	8.49	4.00	9.34
Latex 2 (Tg 50°C)	6.50	12.63	1.84	3.93
Total	100.00	100.00	100.00	100.00
Wet scrubs weight loss (mg/cm ²)		2.4		15.0
Density (kg/L)		1.49		1.49
PVC (%)		82.12		90.30
vol% solids		35.55		32.27
Sum non-opacifying particles (% of dry vol)		66.86		73.51

45

Examples 3 and C

[0096] Example 3 and Comparative example C are identical except that the Tg of the latex in the former is 30°C whereas for the latter it is 10°C. Both coatings are at higher PVC than 1 and A.

50

55

Example	3		Comparative Example C	
	wt% (wet coating)	vol% (dry coating)	wt (% of wet coating)	vol% (dry coating)
Aquaflow NHS 300	1.50	0.92	1.50	1.06
Acticide CHR 0107	0.24	0.07	0.24	0.08
Disponil A1580	0.50	1.46	0.50	1.68

EP 2 563 867 B1

(continued)

Example	3		Comparative Example C	
	wt% (wet coating)	vol% (dry coating)	wt (% of wet coating)	vol% (dry coating)
Dispelaire CF823	0.25	0.59	0.23	0.63
Orotan731 A	0	0.00	1.00	0.69
Dispex N40	0.25	0.26	0	0
Blanose 7M 31C	0	0	0.50	1.39
Natrosol Plus	0.25	1.28	0	0
Texanol	2.00	0	2.00	0
Water (Mains)	27.29	0	36.06	0
Tioxide TR92	7.50	7.14	6.50	7.12
Socal P3	14.95	21.25	12.5	20.44
Steabright	10.00	13.81	8.5	13.50
China Clay Supreme	6.56	9.68	5.5	9.34
Microdol H600	0	0	8.5	13.64
Microdol H200	20.01	27.42	8.5	13.40
Ropaque (Tm) Ultra E	4.00	7.77	4.00	8.93
Tg 10 Latex (Latex 1)	0	0	3.97	8.11
Tg 30 Latex (Latex 3)	4.70	8.35	0	0
Total	100.00	100.00	100.00	100.00
Wet scrubs weight loss (mg/cm ²)		5.2		16.5
Density (kg/L)		1.63		1.49
PVC(%)		87.07		86.37
vol% solids		42.36		33.77
Sum non-opacifying particles (% of dry vol)		72.16		70.31
vol% solids		42.36		33.77

Examples 4a and 4b

[0097] Effect of dispersant choice. Using a hydrophobically modified dispersant (Orotan 731A) or a hydrophilic dispersant (Dispex N40) makes no difference to the wet scrubs.

Example	4a		4b	
	wt% (wet coating)	vol% (dry coating)	wt (% of wet coating)	vol% (dry coating)
Aquaflow NHS 300	1.50	1.02	1.50	1.01
Acticide CHR 0107	0.24	0.07	0.24	0.07
Disponil A1580	0.50	1.61	0.50	1.61
Dispelaire CF823	0.25	0.65	0.25	0.65

EP 2 563 867 B1

(continued)

Example	4a		4b	
	wt% (wet coating)	vol% (dry coating)	wt (% of wet coating)	vol% (dry coating)
Orotan 731 A	1.00	0.66	0	0
Dispex N40	0	0	0.25	0.29
Natrosol Plus 331	0.50	2.82	0.50	2.81
Texanol	2.00	0	2.00	0
Water (Mains)	34.18	0	34.50	0
Tioxide TR92	7.50	7.87	7.50	7.84
Socal P3	12.55	19.65	12.61	19.68
Steabright	8.40	12.78	8.44	12.79
China Clay Supreme	5.50	8.95	5.53	8.96
Microdol H200	16.79	25.37	16.88	25.41
Ropaque (Tm) Ultra E	4.00	8.56	4.00	8.53
Tg 10 Latex (Latex 1???)	0	0	0	0
Tg 30 Latex (Latex 3???)	5.10	9.99	5.30	10.34
Total	100.00	100.00	100.00	100.00
Wet scrubs weight loss (mg/cm ²)		3.1		3.4
Density (kg/L)		1.50		1.50
PVC (%)		83.18		83.22
vol% solids		35.40		35.57
Sum non-opacifying particles (% of dry vol)		66.75		66.85

Example 5 and D

[0098] Natrosol Plus is a hydrophobically modified thickener and Blanose 7M731 is a carboxy methylecellulose. Either may be used in the invention.

Example	5		Comparative Example D	
	wt% (wet coating)	vol% (dry coating)	wt (% of wet coating)	vol% (dry coating)
Aquaflow NHS 300	0.50	0.34	0.50	0.33
Acticide CHR 0107	0.24	0.07	0.24	0.07
Disponil A1580	0.50	1.62	0.50	1.59
Dispelair CF823	0.25	0.66	0.25	0.65
Orotan731 A	0	0	0	0
Dispex N40	0.20	0.23	0.20	0.23
Blanose 7M 31C	0.50	1.33	0	0
Natrosol Plus 331	0	0	0.50	2.79

EP 2 563 867 B1

(continued)

Example	5		Comparative Example D	
	wt% (wet coating)	vol% (dry coating)	wt (% of wet coating)	vol% (dry coating)
Texanol	2.00	0	2.00	0
Water (Mains)	35.31	0	35.31	0
Tioxide TR92	6.50	6.84	6.50	6.74
Socal P3	12.50	19.64	12.50	19.35
Steabright	8.50	12.97	8.50	12.78
China Clay Supreme	5.50	8.97	5.50	8.84
Microdol H600	8.50	13.11	8.50	12.92
Microdol H200	8.50	12.88	8.50	12.69
Ropaque (Tm) Ultra E	4.00	8.58	4.00	8.46
Tg 50 Latex (Latex 2)	6.50	12.76	6.50	12.58
Total	100.00	100.00	100.00	100.00
Wet scrubs weight loss (mg/cm ²)		5.0		3.2
Density (kg/L)		1.49		1.48
PVC (%)		82.99		81.77
vol% solids		35.12		35.46
Sum non-opacifying particles (% of dry vol)		67.56		66.57

Examples 6 and E

[0099] The effect of non-fugitive coalescing solvent (Archer RC) can be seen in that Comparative example E fails the wet scrub test.

Example	6		Comparative Example E	
	wt% (wet coating)	vol% (dry coating)	wt (% of wet coating)	vol% (dry coating)
Aquaflow NHS 300	1.50	1.01	1.50	0.93
Acticide CHR 0107	0.24	0.07	0.24	0.07
Disponil A1580	0.50	1.60	0.50	1.47
Dispelair CF823	0.23	0.60	0.23	0.55
Orotan731 A	1.00	0.65	1.00	0.60
Blanose 7M 31C	0.50	1.32	0.50	1.22
Texanol	2.00	0	0	0
Archer RC	0	0	2.00	7.89
Water	33.53	0	33.53	0
Tioxide TR92	6.50	6.77	6.50	6.24
Socal P3	12.50	19.43	12.50	17.90

EP 2 563 867 B1

(continued)

Example	6		Comparative Example E	
	wt% (wet coating)	vol% (dry coating)	wt (% of wet coating)	vol% (dry coating)
Steabright	8.50	12.83	8.50	11.82
China Clay Supreme	5.50	8.88	5.50	8.18
Microdol H600	8.50	12.97	8.50	11.95
Microdol H200	8.50	12.74	8.50	11.74
Ropaque (Tm) Ultra E	4.00	8.49	4.00	7.82
Tg 50 latex (Latex 2)	6.50	12.63	6.50	11.63
Total	100.00	100.00	100.00	100.00
Wet scrubs weight loss (mg/cm ²)		2.4		15.0
Density (kg/L)		1.49		1.49
PVC (%)		82.12		75.64
vol% solids		35.55		38.63
Sum non-opacifying particles (% of dry vol)		66.86		61.58

Claims

1. An aqueous coating composition having a PVC of from 78 to 88% comprising, based on the total volume solids of the dry coating unless otherwise stated,
 - a) opacifying pigment particles comprising
 - i) from 3 to 10% titanium dioxide
 - ii) from 0 to 20% of hollow polymeric particles
 - b) non-opacifying extender particles comprising
 - i) calcium magnesium carbonate and/or
 - ii) calcium carbonate and/or
 - iii) nepheline syenite and/or
 - iv) kaolin
 wherein i)+ii)+iii)+iv) = 40 to 80% and iv) is 0 to 20%
 - c) polymer binder particles of calculated Fox Tg of from 25 to 70°C having an acid value of from 15 to 65mg KOH/g of polymer and wherein the polymer particles are derived from acrylic monomers and optionally further comprising styrene and/or its derivatives
 - d) dispersant having a weight average molecular weight of at least 3500 Daltons
 - e) fugitive coalescing solvent
 wherein the composition is free of non-fugitive coalescing solvent.
2. A coating composition according to claim 1 wherein any difference between the actual PVC and the sum of a) and b) is made up with other non-opacifying extender particles.
3. A coating composition according to claim 1 or claim 2 wherein the opacifying pigments are white.

EP 2 563 867 B1

4. A coating composition according to claim 3 wherein the white opacifying pigments are selected from titanium dioxide and hollow polymeric particles.
5. A coating composition according to any one of the previous claims wherein the polymeric hollow spheres comprise less than 10% by vol.
6. A coating composition according to any one of the previous claims wherein the extender particles are selected from the group consisting of calcium magnesium carbonate, calcium carbonate, nephelene syenite and kaolin.
7. A coating composition according to claim 6 wherein from 20 to 50% of the total volume solids of the dry coating comprises extender particles of $d_{50} \leq 2$ microns.
8. A coating composition according to anyone of the previous claims wherein the polymer binder is derived from styrene, butyl acrylate and methacrylic acid.
9. A coating composition according to any one of the previous claims wherein the binder comprises from 5 to 20% of the dried coating.
10. A coating composition according to any one of the preceding claims wherein the acid value of the polymer binder is from 15 to 60mg KOH/g of polymer.
11. A coating composition according to any one of the preceding claims wherein the acid component comprises acrylic acid and/or methacrylic acid and/or maleic acid and/or its anhydride.
12. A coating composition according to any one of the preceding claims containing up to 4wt% of fugitive coalescing solvent based on the liquid formulation.
13. A coating composition according to any one of the preceding claims wherein the coalescing solvent reduces the calculated Fox Tg of the polymer binder to from -10 to -80°C.
14. A coating composition according to any one of the preceding claims and further containing colour pigments.
15. A coating composition according to any one of the previous claims and having a colour when dry satisfying the criteria of

$$C^* < C_{critical}$$

and

$$Y > mC^* + 35$$

when calculated using m and $C_{critical}$ according to the table below

Hue angle h^*	m	$C_{critical}$
0	0.098	39.063
10	0.063	42.739
20	0.231	40.130
30	0.399	37.522
40	0.498	37.444
50	0.579	38.000
60	0.655	39.500

EP 2 563 867 B1

(continued)

	Hue angle h*	m	C _{critical}
5	70	0.732	41.000
	80	0.793	45.286
	90	0.854	49.571
	100	0.803	47.136
10	110	0.740	43.955
	120	0.663	41.727
	130	0.580	39.909
15	140	0.498	38.565
	150	0.416	37.696
	160	0.346	37.381
	170	0.318	39.586
20	180	0.283	40.850
	190	0.190	39.350
	200	0.101	38.000
	210	0.060	38.000
25	220	0.021	38.333
	230	-0.007	40.000
	240	-0.041	40.314
30	250	-0.083	38.600
	260	-0.125	36.886
	270	-0.167	35.171
35	280	-0.152	34.640
	290	-0.131	34.240
	300	-0.079	34.000
	310	0.016	34.000
40	320	0.112	34.000
	330	0.207	34.000
	340	0.235	34.471
45	350	0.161	35.647
	360	0.098	39.063

16. A coating composition according to claim 15 having a C* value of less than 5 and a Y value greater than 85.

50 17. A coating composition according to any one of the preceding claims and having a sheen of less than 15% when measured at 85°.

18. A method of coating an article or structure having a surface with a composition as defined in any one of the preceding claims including the steps of applying at least one liquid layer of the coating by brush, roller, pad or spray; allowing or causing the layer to dry and/or harden.

55

19. An article or structure having a surface coated with a composition as defined in any one of claims 1 to 12.

Patentansprüche

- 5 1. Wässrige Beschichtungszusammensetzung mit einer Pigmentvolumenkonzentration (PVK) von 78 bis 88%, umfassend, bezogen auf das Gesamtvolumen der Feststoffe der trockenen Beschichtung, wenn nichts anderes angegeben ist,
- 10 a) deckende Pigmentteilchen umfassend
- i) von 3 bis 10% Titandioxid
- ii) von 0 bis 20% hohle polymere Teilchen
- b) nichtdeckende Verschnittmittelteilchen umfassend
- 15 i) Kalzium-Magnesium-Karbonat und/oder
- ii) Kalziumkarbonat und/oder
- iii) Nephelinsyenit und/oder
- iv) Kaolin
- wobei i)+ii)+iii)+iv) = 40 bis 80% und iv) 0 bis 20% ist
- 20 c) Polymerbindemittelteilchen mit einer berechneten Fox Tg von 25 bis 70°C mit einem Säurewert von 15 bis 65 mg KOH/g Polymer, wobei die Polymerteilchen von Acrylmonomeren abgeleitet sind und gegebenenfalls weiterhin Styrol und/oder seine Derivate umfassen
- d) ein Dispergiemittel mit einem Gewichtsmittel des Molekulargewichts von wenigstens 3500 Dalton
- e) ein flüchtiges, koaleszierendes Lösungsmittel
- 25 wobei die Zusammensetzung frei ist von einem nicht flüchtigen koaleszierenden Lösungsmittel.
2. Beschichtungszusammensetzung nach Anspruch 1, wobei ein Unterschied zwischen der tatsächlichen PVK und der Summe aus a) und b) mit anderen nichtdeckenden Verschnittmittelteilchen erzeugt wird.
- 30 3. Beschichtungszusammensetzung nach Anspruch 1 oder 2, wobei die deckenden Pigmente weiß sind.
4. Beschichtungszusammensetzung nach Anspruch 3, wobei die weißen deckenden Pigmente aus Titandioxid und hohlen polymeren Teilchen ausgewählt sind.
- 35 5. Beschichtungszusammensetzung nach einem der vorhergehenden Ansprüche, wobei die polymeren Hohlkugeln weniger als 10 Volumenprozent ausmachen.
- 40 6. Beschichtungszusammensetzung nach einem der vorhergehenden Ansprüche, wobei die Verschnittmittelteilchen aus der Gruppe ausgewählt sind bestehend aus Kalzium-Magnesium-Karbonat, Kalziumkarbonat, Nephelinsyenit und Kaolin.
7. Beschichtungszusammensetzung nach Anspruch 6, wobei von 20 bis 50% des Gesamtfeststoffvolumens der trockenen Beschichtung Verschnittmittelteilchen mit einem d50 von ≤ 2 Mikron umfassen.
- 45 8. Beschichtungszusammensetzung nach einem der vorhergehenden Ansprüche, wobei das Polymerbindemittel von Styrol, Butylacrylat und Methacrylsäure abgeleitet ist.
9. Beschichtungszusammensetzung nach einem der vorhergehenden Ansprüche, wobei das Bindemittel von 5 bis 20% der getrockneten Beschichtung umfasst.
- 50 10. Beschichtungszusammensetzung nach einem der vorhergehenden Ansprüche, wobei der Säurewert des Polymerbindemittels von 15 bis 60 mg KOH/g Polymer beträgt.
11. Beschichtungszusammensetzung nach einem der vorhergehenden Ansprüche, wobei der Säurekomponente Acrylsäure und/oder Methacrylsäure und/oder Maleinsäure und/oder deren Anhydrid umfasst.
- 55 12. Beschichtungszusammensetzung nach einem der vorhergehenden Ansprüche, die bis zu 4 Gew.-% des flüchtigen, koaleszierenden Lösungsmittels, bezogen auf der flüssigen Formulierung, enthält.

EP 2 563 867 B1

13. Beschichtungszusammensetzung nach einem der vorhergehenden Ansprüche, wobei das koaleszierende Lösungsmittel die berechnete Fox Tg des Polymerbindemittels auf -10 bis -80°C reduziert.
14. Beschichtungszusammensetzung nach einem der vorhergehenden Ansprüche, die weiterhin Farbpigmente enthält.
15. Beschichtungszusammensetzung nach einem der vorhergehenden Ansprüche, die im trockenen Zustand eine Farbe hat, die die folgenden Kriterien erfüllt

$$C^* < C_{\text{kritisch}}$$

und

$$Y > mC^* + 35$$

wenn unter Verwendung von m und C_{kritisch} nach der untenstehenden Tabelle berechnet

Farbtonwinkel h*	m	C_{kritisch}
0	0.098	39.063
10	0.063	42.739
20	0.231	40.130
30	0.399	37.522
40	0.498	37.444
50	0.579	38.000
60	0.655	39.500
70	0.732	41.000
80	0.793	45.286
90	0.854	49.571
100	0.803	47.136
110	0.740	43.955
120	0.663	41.727
130	0.580	39.909
140	0.498	38.565
150	0.416	37.696
160	0.346	37.381
170	0.318	39.586
180	0.283	40.850
190	0.190	39.350
200	0.101	38.000
210	0.060	38.000
220	0.021	38.333
230	-0.007	40.000
240	-0.041	40.314

EP 2 563 867 B1

(fortgesetzt)

Farbtonwinkel h*	m	C _{kritisch}
250	-0.083	38.600
260	-0.125	36.886
270	-0.167	35.171
280	-0.152	34.640
290	-0.131	34.240
300	-0.079	34.000
310	0.016	34.000
320	0.112	34.000
330	0.207	34.000
340	0.235	34.471
350	0.161	35.647
360	0.098	39.063

16. Beschichtungszusammensetzung nach Anspruch 15 mit einem C*-Wert von weniger als 5 und einem Y-Wert von mehr als 85.

17. Beschichtungszusammensetzung nach einem der vorhergehenden Ansprüche mit einem Glanz von weniger als 15%, wenn bei 85° gemessen.

18. Verfahren zur Beschichtung eines Artikels oder einer Struktur, der oder die eine Oberfläche aufweist, mit einer Zusammensetzung nach einem der vorhergehenden Ansprüche, umfassend die Schritte des Auftragens von mindestens einer flüssigen Schicht der Beschichtung durch Pinsel, Rolle, Kissen oder Sprühnebel; und des Trocknenlassens oder Trocknens und/oder Härtenlassens oder Härten der Schicht.

19. Artikel oder Struktur, der oder die eine Oberfläche aufweist, die mit einer Zusammensetzung gemäß einem der Ansprüche 1 bis 12 beschichtet ist.

Revendications

1. Composition de revêtement aqueuse ayant un PVC allant de 78 à 88% comprenant, sur la base du volume total des matières solides du revêtement sec, sauf indication contraire,

a) des particules de pigment opacifiant comprenant

i) de 3 à 10% de dioxyde de titane

ii) de 0 à 20% de particules polymères creuses

b) des particules de matière de charge non-opacifiante comprenant

i) du carbonate de calcium-magnésium et/ou

ii) du carbonate de calcium et/ou

iii) de la syénite néphélinique et/ou

iv) du kaolin

où i) + ii) + iii) + iv) = 40 à 80% et iv) est de 0 à 20%

c) des particules de liant polymère de T_g de Fox calculée allant de 25 à 70°C ayant un indice d'acide allant de 15 à 65 mg de KOH/g de polymère, les particules de polymère dérivant de monomères acryliques et comprenant en outre éventuellement du styrène et/ou ses dérivés

EP 2 563 867 B1

d) un dispersant ayant un poids moléculaire moyen en poids d'au moins 3500 Daltons

e) un solvant coalescent fugitif

où la composition est exempte de solvant coalescent non-fugitif.

- 5 **2.** Composition de revêtement selon la revendication 1, dans laquelle toute différence entre le PVC réel et la somme de a) et b) est compensée par d'autres particules de matière de charge non opacifiante.
- 3.** Composition de revêtement selon la revendication 1 ou 2, dans laquelle les pigments opacifiants sont blancs.
- 10 **4.** Composition de revêtement selon la revendication 3, dans laquelle les pigments opacifiants blancs sont choisis parmi le dioxyde de titane et les particules polymères creuses.
- 5.** Composition de revêtement selon l'une quelconque des revendications précédentes, dans laquelle les sphères polymères creuses représente moins de 10% en vol.
- 15 **6.** Composition de revêtement selon l'une quelconque des revendications précédentes, dans laquelle les particules de matière de charge sont choisies dans le groupe constitué de carbonate de calcium-magnésium, de carbonate de calcium, de syénite néphélinique et de kaolin.
- 20 **7.** Composition de revêtement selon la revendication 6, dans laquelle de 20 à 50% du volume total des matières solides du revêtement sec comprend des particules de matière de charge ayant une valeur $d_{50} \leq 2$ microns.
- 8.** Composition de revêtement selon l'une quelconque des revendications précédentes, dans laquelle le liant polymère est dérivé du styrène, d'acrylate de butyle et d'acide méthacrylique.
- 25 **9.** Composition de revêtement selon l'une quelconque des revendications précédentes, dans laquelle le liant représente de 5 à 20% du revêtement séché.
- 10.** Composition de revêtement selon l'une quelconque des revendications précédentes, dans laquelle l'indice d'acide du liant polymère est de 15 à 60 mg de KOH/g de polymère.
- 30 **11.** Composition de revêtement selon l'une quelconque des revendications précédentes, dans laquelle le composant acide comprend de l'acide acrylique et/ou de l'acide méthacrylique et/ou de l'acide maléique et/ou son anhydride.
- 35 **12.** Composition de revêtement selon l'une quelconque des revendications précédentes, contenant jusqu'à 4% en poids de solvant coalescent fugitif sur la base de la formulation liquide.
- 13.** Composition de revêtement selon l'une quelconque des revendications précédentes, dans laquelle le solvant coalescent réduit la Tg de Fox calculée du liant polymère de -10 à -80°C.
- 40 **14.** Composition de revêtement selon l'une quelconque des revendications précédentes et contenant en outre des pigments colorés.
- 45 **15.** Composition de revêtement selon l'une quelconque des revendications précédentes et ayant une couleur satisfaisant, à l'état sec, les critères suivants

$$C^* < C_{\text{critique}}$$

50 et

$$Y > mC^* + 35$$

55 lorsqu'elle est calculée en utilisant m et C_{critique} selon le tableau ci-dessous

EP 2 563 867 B1

	Angle de teinte h*	m	C _{critique}
5	0	0,098	39,063
	10	0,063	42,739
	20	0,231	40,130
	30	0,399	37,522
10	40	0,498	37,444
	50	0,579	38,000
	60	0,655	39,500
15	70	0,732	41,000
	80	0,793	45,286
	90	0,854	49,571
	100	0,803	47,136
20	110	0,740	43,955
	120	0,663	41,727
	130	0,580	39,909
25	140	0,498	38,565
	150	0,416	37,696
	160	0,346	37,381
	170	0,318	39,586
30	180	0,283	40,850
	190	0,190	39,350
	200	0,101	38,000
35	210	0,060	38,000
	220	0,021	38,333
	230	-0,007	40,000
40	240	-0,041	40,314
	250	-0,083	38,600
	260	-0,125	36,886
	270	-0,167	35,171
45	280	-0,152	34,640
	290	-0,131	34,240
	300	-0,079	34,000
50	310	0,016	34,000
	320	0,112	34,000
	330	0,207	34,000
	340	0,235	34,471
55	350	0,161	35,647
	360	0,098	39,063

EP 2 563 867 B1

16. Composition de revêtement selon la revendication 15 ayant une valeur Cl* inférieure à 5 et une valeur Y supérieure à 85.

5 17. Composition de revêtement selon l'une quelconque des revendications précédentes et ayant un lustre inférieure à 15% quand il est mesuré à 85°.

10 18. Procédé de revêtement d'un article ou d'une structure ayant une surface avec une composition telle que définie dans l'une quelconque des revendications précédentes comportant les étapes consistant à appliquer au moins une couche liquide du revêtement par brosse, rouleau, tampon ou pulvérisation; à laisser ou forcer la couche à sécher et/ou durcir.

15 19. Article ou structure ayant une surface revêtue d'une composition telle que définie dans l'une quelconque des revendications 1 à 12.

20

25

30

35

40

45

50

55




Fig. 1

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 4277385 A [0008]
- EP 0113435 A [0009]

Non-patent literature cited in the description

- Paint and Surface Coatings - theory and practice. John Wiley and Sons, 35-37 [0020]
- International Lighting Vocabulary. 1987 [0059]