

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
2 August 2007 (02.08.2007)

PCT

(10) International Publication Number
WO 2007/085553 A1

(51) International Patent Classification:

D21H 21/28 (2006.01) **D21H 17/20** (2006.01)
D21H 19/10 (2006.01)

(21) International Application Number:

PCT/EP2007/050427

(22) International Filing Date: 17 January 2007 (17.01.2007)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:

06100864.5 26 January 2006 (26.01.2006) EP

(71) Applicant (for all designated States except US): **CIBA SPECIALTY CHEMICALS HOLDING INC.** [CH/CH]; Klybeckstrasse 141, CH-4057 Basel (CH).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **LENNARTZ, Michael** [DE/DE]; Binzener Strasse 5a, 79539 Lörrach (DE). **HUNGER, Charles** [CH/CH]; Fuchsmattstrasse 34, CH-4107 Ettingen (CH). **KARPPI, Asko Olavi** [FI/FI]; Solmukatu 18, FI-20540 Turku (FI).

(74) Common Representative: **CIBA SPECIALTY CHEMICALS HOLDING INC.**; Patent Department, Klybeckstrasse 141, CH-4057 Basel (CH).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: A COMPOSITION FOR SURFACE COLOURATION OF PAPER

(57) Abstract: The invention relates to a composition for surface colouration of paper web comprising a) from 0.1 to 30% by weight, based on the total weight of the composition, of a colouring pigment, b) from 0.1 to 20% by weight, based on the total weight of the composition of a starch/latex copolymer, characterized in that, in addition to starch, the monomeric components that are copolymerized comprise i) styrene or a substituted styrene, ii) an acrylate and/or methacrylate and, optionally, iii) one or more further ethylenically unsaturated monomers, c) from 0 to 20% by weight, based on the total weight of the composition, of starch or a starch derivative, d) from 0 to 10% by weight, based on the total weight of the composition of one or more auxiliaries and e) water to complete to 100% by weight, based on the total weight of the composition.



WO 2007/085553 A1

A Composition for Surface Colouration of Paper

The present invention relates to a composition for surface colouration of paper web comprising a colouring pigment, a synthetic starch/latex copolymer and, optionally, further additives and the use thereof for surface colouration of said paper web.

5

Despite the fact that the economical advantages of surface colouration of paper have long been recognized, in practice, surface colouration is not widespread when compared with stock dyeing. The main reason for this situation (see, for example, "On-machine surface coloration", A.S.Tindal, Surface Application of Paper Chemicals, **1997**, 175-191) is that

10

surface coloured paper generally exhibits poor bleed fastness when contacted with liquids such as water, alcohol or beverages.

One attempt to overcome this problem has been disclosed in WO 03/004766, whereby a dye composition containing a binder and thickener, which is a polyvinylpyrrolidone derivative, is applied to the paper surface. Preferably, the paper surface is treated with a fixing agent prior to the dyeing process in order to improve bleed fastness, but no concrete values are given to indicate the effectiveness of this approach.

15

A further approach to overcome the bleeding problems associated with surface colouration of paper has been disclosed in WO 04/090228. This document discloses a composition for controlling the bleed fastness of organic colouring pigments in paper coatings comprising a colouring pigment and, essentially, a binder. Suitable binders are selected from an extremely wide variety of entities, but most preferred and efficient are binders based on copolymers of starch with styrene/butadiene latex. However, relatively high quantities of binder are required to achieve the desired bleed fastness and it has also been observed that the resulting dyeings lack sufficiently high quality for certain applications, due to, for example, excessive mottling and lack of homogeneity.

20

25

Consequently, there is a need for a system for surface colouration of paper in which the disadvantages of previous compositions are overcome.

30

It has now been found that compositions comprising colouring pigments and particular starch based copolymer binders result in dyeings which, in addition to exhibiting excellent bleed

fastness at relatively low application concentrations, are of exceptionally high quality, in particular, with respect to mottling, colour strength and homogeneity.

Therefore, a composition comprising

- 5 a) from 0.1 to 30%, preferably from 1 to 25%, by weight, based on the total weight of the composition, of a colouring pigment,
- b) from 0.1 to 20%, preferably from 0.5 to 10% and most preferably from 1 to 5%, by weight, based on the total weight of the composition of a starch/latex copolymer, characterized in that, in addition to starch the monomeric components that are copolymerized comprise
- 10 i) styrene or a substituted styrene,
- ii) an acrylate and/or methacrylate and, optionally ,
- iii) one or more further ethylenically unsaturated monomers,
- c) from 0 to 20%, preferably from 0 to 10%, by weight, based on the total weight of the composition, of starch or a starch derivative,
- 15 d) from 0 to 10% by weight, based on the total weight of the composition of one or more auxiliaries and
- e) water to complete to 100% by weight, based on the total weight of the composition has been found.

- 20 With regard to the colouring pigment, component a) of the composition, this may be selected from any colouring pigment as described in the Colour Index International, fourth online edition (Society of Dyers and Colourists and American Association of Textile Chemists and Colorists 2002) under the designations C.I. Pigment Yellows 1 to 221, C.I. Pigment Oranges 1 to 81, C.I. Pigment Reds 1 to 283, C.I. Pigment Violets 1 to 53, C.I. Pigment Blues 1 to 81,
- 25 C.I. Pigment Greens 1 to 56, C.I. Pigment Browns 1 to 47 and C.I. Pigment Blacks 1 to 35.

- Preferably, the colouring pigment is selected from C.I. Pigment Yellow 1, 3, 12, 13, 14, 17, 34, 42, 51, 53, 62, 74, 83, 93, 95, 109, 110, 111, 128, 129, 139, 147, 168, 174, 184, 188, 191:1 and 199, C.I. Pigment Orange 5, 13, 16, 23, 34, 49, 61, 63, 64, 71, 73, and 81, C.I.
- 30 Pigment Red 2, 4, 5, 12, 23, 38, 48:1, 48:2, 48:3, 48:4, 49:1, 52:2, 53:1, 57, 57:1, 81, 101, 104, 110, 112, 144, 146, 166, 177, 181, 184, 185, 202, 206, 214, 220, 221, 254, 255, 264, 270, 272, 282 and 283, C.I. Pigment Violet 3, 19, 23, and 37, C.I. Pigment Blue 1, 15, 15:1, 15:2, 15:3, 15:4, 29, 60 and 66, C.I. Pigment Green 60 and 66, C.I. Pigment Brown 23 and 24 and from C.I. Pigment Black 7, 10 and 34.

The ratios of starch to unsaturated monomers for the preparation of the starch/latex copolymer, component b) of the composition, generally lie within the range of
i) from 5 to 50%, preferably from 5 and 40%, by weight of starch and
ii) from 50 to 95%, preferably from 60 to 95%, by weight of the monomeric components,
5 whereby the copolymers may advantageously be utilized in the form of aqueous dispersions. These polymer dispersions generally contain between 20 and 50%, preferably between 25 and 35%, dry weight of solids.

10 Aqueous dispersions of similar copolymers have been described in WO 00/46264, which document also discloses a process for their preparation.

Polymerisable starch or starch derivatives suitable for incorporating into component b) and also as the optional component c) of the composition of the invention may include practically all thinned starches of plant origin including starches from corn, wheat, potatoes, tapioca,
15 rice, sago and sorghum. Waxy and high amylose starches may also be suitable. The starches can be thinned by acid hydrolysis, oxidative hydrolysis or enzymatic degradation. Further derivatized starches also suitable include those such as starch ethers, starch esters, cross-linked starches, oxidized starches and chlorinated starches, for example, carboxymethyl cellulose and hydroxyethyl methyl cellulose. Typical examples are the
20 commercially available amylopectin, dextrin and, as a typical example of oxidized starch, Perfectamyl® 4692.

However, component b) of the composition of the invention is preferably obtained by copolymerization of a degraded, oxidized anionic starch.

25 In addition to the starch component of the copolymer, component b) of the composition of the invention, the individual monomers and their relative amounts are critical for providing the advantageous properties provided by the invention.

Thus, in a further preferred aspect, the starch/latex copolymer, component b) of the
30 composition of the invention, is obtained, preferably by emulsion polymerization of a mixture of monomers consisting of
i) from 20 to 40% by weight of styrene or a substituted styrene,
ii) from 20 to 50% of an acrylate or a methacrylate and

iii) from 5 to 20% by weight of one or more further ethylenically unsaturated monomers in the presence of from 15 to 40%, preferably from 15 to 35%, by weight of starch,

Substituted styrenes may include, for example, α -methyl styrene, or styrenes substituted in the phenyl ring by alkyl groups, such as methyl, halogens, such as chlorine or alkoxy groups such as methoxy. However, styrene itself is the most preferred component.

Acrylates or methacrylates are preferably lower alkyl esters such as methyl, ethyl, n- or isopropyl and n-, iso-, sec- or tert-butyl esters or their mixtures, n-butyl acrylate being the most preferred component.

With regard to the third ethylenically unsaturated monomer, this may be selected from a wide variety of compounds containing one single unsaturated double bond, i.e. excluding dienes of previously disclosed starch/latex copolymers such as 1,3-butadiene or isoprene. Examples of suitable ethylenically unsaturated monomers are hydroxylated alkyl methacrylates, alkyl vinyl ketones, substituted acrylamides, methacrylic acid, N-methylol acrylamide, 2-hydroxyethyl acrylate, crotonic acid, itaconic acid, fumaric acid, maleic acid, maleic anhydride, vinyl halides, vinylidene halides, vinyl esters, vinyl ethers, vinyl carbazole, N-vinyl pyrrolidone, vinyl pyridine, ethylene, propylene, isobutylene, vinyl triethoxy silane and triphenyl vinyl silane. Preferred monomers include dimethylamino ethyl acrylate, dimethylamino propyl acrylamide, vinyl acetate, acrylic acid, acrylamide, maleic anhydride, monovinyl silicon compounds including vinyl trimethyl silane, ethyl vinyl ether, butyl vinyl ether, 2-ethylhexyl acrylate vinylidene chloride, butyl vinyl ether and, especially acrylonitrile.

In a most preferred aspect, the starch/latex copolymer, component b) of the composition of the invention is a product obtained by emulsion polymerization of

- i) from 20 to 40% by weight of styrene,
- ii) from 20 to 50% by weight of a C₁-C₄alkylacrylate, especially n-butyl acrylate and
- iii) from 5 to 20% by weight of vinyl acetate or, especially, acrylonitrile, in the presence of from 15 to 35% by weight of an oxidatively degraded anionic starch, in the form of an aqueous dispersion having a dry content of between 25 and 35% by weight.

Furthermore, the composition of the invention may contain further auxiliaries selected from fixing agents, dispersants, additional binder and binder resins, insolubilizing and/or

crosslinking agents, anionic, cationic and neutral polymers, wet-strength agents, antifoams and biocides.

Suitable auxiliaries may, for example, include polyethyleneimines and derivatives thereof, inorganic salts such as sodium chloride, magnesium chloride and potassium chloride, alum, 5 polydiallyl dimethyl ammonium chloride, polyamide amine resins, polyvinyl alcohol, polyvinyl pyrrolidone and homo and copolymers thereof, polyesters and polyethers, glyoxal derivatives, monoethanolamine, acrylic acid/alkyl acrylate copolymers and styrene/acrylate copolymers.

- 10 The composition of the invention is suitable for use in surface colouration of paper web after sheet formation.

Preferably, the composition is applied to the paper web after it has been dried to 80 to 95% in the size press or by means of an on-line coater. Alternatively, the composition can be 15 applied once the paper has been fully dried in an off-machine coating process, such as by spraying, curtain coating or by conventional coating processes.

Such application processes are described in "Pigment Coating and Surface Sizing of Papers" by E. Lehtinen, published by Tappi International, 2000.

- 20 Consequently, in a still further aspect, the invention relates to a method for the surface colouration of paper by applying to the paper surface a composition comprising
- a) from 0.1 to 30% by weight, based on the total weight of the composition, of a colouring pigment, whereby the colouring pigment is in solid form or in the form of a dispersion, in which form many colouring pigments are commercially available,
 - 25 b) from 0.1 to 20% by weight, based on the total weight of the composition of a starch/latex copolymer, characterized in that, in addition to starch, the monomeric components that are copolymerized comprise
 - i) styrene or a substituted styrene,
 - ii) an acrylate and/or methacrylate and, optionally,
 - 30 iii) one or more further ethylenically unsaturated monomers,
 - c) from 0 to 20% by weight, based on the total weight of the composition, of starch or a starch derivative,
 - d) from 0 to 10% by weight, based on the total weight of the composition of one or more auxiliaries and

e) water to complete to 100% by weight, based on the total weight of the composition and also to paper, which has been treated with a composition of the invention or according to the method above.

- 5 Where, in the above method, the pigment is used in the form of a dispersion, addition of the starch/latex copolymer generally suffices to achieve the desired effect, i.e. bleed fastness of the resulting dyed paper web, without addition of further starch binder, component c) of the composition, which is clearly advantageous.
- 10 The inventive compositions comprising colouring pigments and particular starch based copolymer binders result in dyeings exhibiting excellent bleed fastness at relatively low application concentrations and which are of exceptionally high quality, in particular, with respect to colour strength and homogeneity, including lack of mottling, as opposed to previously known combinations.

15

The following examples further illustrate the invention, without intending to be restrictive in nature; parts and percentages are by weight unless otherwise indicated.

Examples

I. Size Press Application

Base Paper:

- 5 The base paper used for the application was fabricated on a laboratory paper machine at UMIST, Manchester, UK from a 70/30 mixture of hard and soft woods pulp beaten to 35° SR, containing 10% retained clay (plus 1% calcium carbonate) filler, 0.4% Hercat® 27JP4 pseudo neutral size, 1% alum and 0.02% Percol® 230 retention agent. The resulting paper has a base weight of 103g/m² and a Cobb value of 95g/m².

10

Application:

- Defined amounts of pigment and copolymer (see Table 1) are added to 44g of a 10% aqueous solution of size press starch (Perfectamyl® 4692) and the mixture made up to 100g with water, where after the mixture is applied to the base paper in a Mathis size press running at 5m/min., with a pressure of 200kPas and at a temperature of 50°C.

15

After drying, the resulting colour strengths of the dyeings are then measured, whereby the values given in Tables 1 and 2 are corrected, taking the reference dyeing without copolymer addition as standard (100%), to take into account the amount of colorant actually residing on the paper surface. The absolute measured values of colour strength are given in

20

parentheses.

Additionally, the bleed fastness of the dyeings towards water and 50% alcohol/water are measured by firstly moistening the dyeing with deionised water and alcohol/water

25

respectively and placing the moist dyeings between two sheets of white filter papers which are moistened with deionised water and alcohol/water respectively. The resulting sandwich is placed between two glass plates weighted with a 1kg weight. After 1 hour at room temperature, the individual sheets are dried and the bleed fastness assessed by means of the grey scale, whereby a value between 1 (very strong bleeding) and 5 (zero bleeding) is obtained.

30

The results of the measurements are summarized in the following Table 1:

Table 1

Example No.	%/C.I.Pigment	% Copolymer	% Pick-up	% Colour Strength	Bleed Water PF ¹ /GF ²	Bleed Alcohol PF/GF
1	7/Violet 23	None	48.8	100	2/2	5/5
2	7/Violet 23	2.2/Polymer A ³	51.6	76.5 (81)	4/4-5+	5/5
3	7/Violet 23	4.3/Polymer A	51.6	76.6 (80)	4-5/4-5	5/5
4	7/Violet 23	6.4/Polymer A	51.9	75.7 (84)	5/5	5/5
5	7/Violet 23	5/Pensize ⁴ 730	44.2	91.7 (83)	4/4	5/5
6	7/Violet 23	10/Pensize 730	45.7	96.1 (90)	4-5/4-5	5/5
7	7/Violet 23	15/Pensize 730	41.6	102.0 (87)	4-5/4-5	5/5
8	7/Violet 23	2/Raiprint 501 ⁵	46.6	60.1 (58)	3-4/3-4	5/5
9	7/Violet 23	4/Raiprint 501	46.9	57.2 (55)	4-5/4-5+	5/5
10	7/Violet 23	6/Raiprint 501	46.3	61.2 (58)	4-5/4-5	5/5
11	7/Violet 23	2.2Raiprint 300 ⁶	51.6	90.2 (93)	3/3-4	5/5
12	7/Violet 23	4.4/Raiprint 300	47.5	85.2 (83)	4+/4-5	5/5
13	7/Violet 23	6.6Raiprint 300	44.7	76.5 (70)	4-5/4-5+	5/5
14	8/Blue 15:1	None	42.9	100	2-3/2	5/5
15	8/Blue 15:1	2.2/Polymer A	37.7	104.7 (92)	4/4	5/5
16	8/Blue 15:1	4.3/Polymer A	36.7	112.2 (96)	4-5+/4-5+	5/5
17	8/Blue 15:1	6.4/Polymer A	36.5	112.9 (96)	5/5	5/5
18	8/Blue 15:1	5/Pensize 730	37.3	73.8 (64)	4-5/4-5	5/5
19	8/Blue 15:1	10/Pensize 730	33.5	93.5 (73)	4-5/4-5	5/5
20	8/Blue 15:1	15/Pensize 730	33.3	105.6 (82)	4-5/4-5	5/5
21	8/Blue 15:1	2/Raiprint 501	41.2	86.5 (83)	3-4+/4	5/5
22	8/Blue 15:1	4/Raiprint 501	37.6	96.0 (84)	4-5/4-5+	5/5
23	8/Blue 15:1	6/Raiprint 501	39.0	96.8 (88)	4-5+/4-5+	5/5
24	8/Blue 15:1	2.2/Raiprint 300	40.9	97.7 (93)	4/4	5/5
25	8/Blue 15:1	4.4/Raiprint 300	38.4	86.1 (77)	5/5	5/5
26	8/Blue 15:1	6.6/Raiprint 300	34.9	88.5 (72)	5/5	5/5
27	7/Red 2	None	38.5	100	3/3	5/5

28	7/Red 2	2.2/Polymer A	44.2	92.3 (106)	4-5+/4-5+	5/5
29	7/Red 2	4.3/Polymer A	42.4	95.2 (105)	5/5	5/5
30	7/Red 2	6.4/Polymer A	44.9	92.5 (108)	5/5	5/5
31	7/Red 2	5/Pensize 730	34.1	77.8 (69)	4-5/4-5	5/5
32	7/Red 2	10/Pensize 730	35.8	87.1 (81)	5/5	5/5
33	7/Red 2	15/Pensize 730	30.5	118.4 (94)	5/5	5/5
34	7/Red 2	2/Raiprint 501	38.0	83.1 (82)	4-5/4-5	5/5
35	7/Red 2	4/Raiprint 501	35.5	93.1 (86)	5/4-5+	5/5
36	7/Red 2	6/Raiprint 501	39.3	87.2 (89)	5/4-5+	5/5
37	7/Red 2	2.2/Raiprint 300	40.5	87.4 (92)	4-5+/4-5+	5/5
38	7/Red 2	4.4/Raiprint 300	36.2	72.3 (68)	5/5	5/5
39	7/Red 2	6.6/Raiprint 300	35.0	77.0 (70)	5/5	5/5
40	8/Yellow 1	None	38.7	100	3+/2-3	5/5
41	8/Yellow 1	2.2/Polymer A	39.4	89.4 (91)	5/5	5/5
42	8/Yellow 1	4.3/Polymer A	36.7	102.1 (97)	5/5	5/5
43	8/Yellow 1	6.4/Polymer A	37.7	101.5 (99)	5/5	5/5
44	8/Yellow 1	5/Pensize 730	41.0	62.3 (66)	4-5+/4-5+	5/5
45	8/Yellow 1	10/Pensize 730	32.5	85.6 (72)	5/5	5/5
46	8/Yellow 1	15/Pensize 730	32.1	103.6 (86)	5/5	5/5
47	8/Yellow 1	2/Raiprint 501	38.6	71.3 (71)	4-5+/4-5	5/5
48	8/Yellow 1	4/Raiprint 501	37.7	73.8 (72)	5/5	5/5
49	8/Yellow 1	6/Raiprint 501	40.0	78.4 (81)	5/5	5/5
50	8/Yellow 1	2.2/Raiprint 300	38.0	60.2 (59)	5/5	5/5
51	8/Yellow 1	4.4/Raiprint 300	37.1	54.2 (52)	5/5	5/5
52	8/Yellow 1	6.6/Raiprint 300	32.7	41.4 (35)	5/5	5/5
53	5/Black 7	None	38.4	100	4/4	5/5
54	5/Black 7	2.2/Polymer A	37.4	96.5 (94)	4-5/4-5	5/5
55	5/Black 7	4.3/Polymer A	33.9	100.7 (89)	5/5	5/5
56	5/Black 7	6.4/Polymer A	33.7	92.2 (81)	5/5	5/5
57	5/Black 7	5/Pensize 730	40.6	31.2 (33)	3-4/4	5/5
58	5/Black 7	10/Pensize 730	34.5	47.8 (43)	4-5/5	5/5

59	5/Black 7	15/Pensize 730	34.1	56.3 (50)	4-5+/5	5/5
60	5/Black 7	2/Raiprint 501	37.7	55.0 (54)	4-5/4-5	5/5
61	5/Black 7	4/Raiprint 501	34.9	64.9 (59)	4-5/4-5	5/5
62	5/Black 7	6/Raiprint 501	37.0	65.5 (63)	4-5+/5	5/5
63	5/Black 7	2.2/Raiprint 300	41.8	27.6 (30)	4-5/4-5+	5/5
64	5/Black 7	4.4/Raiprint 300	39.8	33.8 (35)	5/5	5/5
65	5/Black 7	6.6/Raiprint 300	40.6	23.7 (25)	5/5	5/5

¹ PF = Bleed fastness between filter papers; ² GF = Bleed fastness between glass fibre sheet

³ Polymer A is an experimental product obtained by emulsion copolymerization of 25% starch(Raisamyl® 01121, oxidatively degraded anionic starch), 38.6% styrene, 28.6% n-butyl acrylate and 7.8% acrylonitrile;

5 ⁴ Pensize® 730 is a commercially available aqueous formulation of a starch/styrene/butadiene latex copolymer;

⁵ Raiprint® 501 is a commercially available product obtained by copolymerization of 25% Raisamyl® 150 EH (a cationic starch), 38.62% styrene, 28.61% n-butylacrylate and 7.76% acrylonitrile;

10 ⁶ Raiprint® 300 is a commercially available product obtained by copolymerization of 20% Raisafix® 01015 SW (an amphoteric starch), 24.8% styrene, 40% n-butyl acrylate and 15.2% acrylonitrile.

From the above Table 1, the advantages of the experimental Polymer A over the commercial
15 product Pensize 730 are clearly visible. Thus, for example, taking into account the pick-up from the size press bath, it may be calculated that in order to obtain acceptable bleed fastness of 4-5 minimum at comparable depth of colour, with C.I. Pigment Violet 23, 2.22% of Polymer A is required, whilst 4.57% Pensize 730 must be applied. Similar comparisons for C.I. Pigment Blue 15.1 and C.I. Pigment Red 2 result in values of 0.83% as opposed to 5.0%
20 and 0.98% as opposed to 3.58%, respectively.

In addition, the superior efficiency of the experimental polymer A, in general, demonstrates the advantages of this copolymer in comparison to the commercially available Raiprint® products.

25

Also of note are the results obtained with C.I. Pigment Black 7, whereby solely Polymer A can be seen to produce dyeings of adequate colour strength.

In a further series of experiments, dyeings of the dark shades, violet, blue and red, were examined in greater detail. The results are summarized in the following Table 2:

Table 2

Example No.	%/ C.I. Pigment	% Copolymer	% Pick-up	% Colour Strength	Bleed Water PF ¹ /GF ²	Bleed Alcohol PF/GF
66	7/Violet 23	None	58.3	100	2-3/3-4	5/5
67	7/Violet 23	1/Polymer A ³	52.1	95.1 (85)	4-5/5	5/5
68	7/Violet 23	1.8/Polymer A	53.4	92.3 (85)	4-5+/5	5/5
69	7/Violet 23	5/Polymer A	53.4	95.0 (87)	5/5	5/5
70	7/Violet 23	8/Polymer A	50.9	97.3 (85)	5/5	5/5
71	7/Violet 23	2/Pensize ⁴ 730	46.3	88.0 (70)	4/4+	5/5
72	7/Violet 23	3.75/Pensize 730	50.9	83.6 (73)	4-5/5	5/5
73	7/Violet 23	10/Pensize 730	42.6	109.4 (80)	5/5	5/5
74	7/Violet 23	18.75/Pensize 730	40.4	115.2 (80)	5/5	5/5
75	8/Blue 15:1	None	49.4	100	3/3-4	5/5
76	8/Blue 15:1	1/Polymer A	41.7	111.4 (94)	4-5/4+	5/5
77	8/Blue 15:1	1.8/Polymer A	40.7	115.2 (95)	4-5+/4-5	5/5
78	8/Blue 15:1	5/Polymer A	42.5	112.7 (97)	4-5+/4-5+	5/5
79	8/Blue 15:1	8/Polymer A	41.1	119.0 (99)	4-5+/4-5+	5/5
80	8/Blue 15:1	2/Pensize 730	41.0	67.5 (56)	4-5/4+	5/5
81	8/Blue 15:1	3.75/Pensize 730	43.4	67.2 (59)	4-5+/4-5	5/5
82	8/Blue 15:1	10/Pensize 730	38.4	95.1 (74)	5/4-5+	5/5
83	8/Blue 15:1	18.75/Pensize 730	34.1	128.7 (89)	5/5	5/5
84	7/Red 2	None	41.0	100	3-4/4	5/5
85	7/Red 2	1/Polymer A	41.2	103.4 (104)	5/5	5/5
86	7/Red 2	1.8/Polymer A	40.4	102.5 (101)	5/5	5/5
87	7/Red 2	5/Polymer A	41.6	103.5 (105)	5/5	5/5
88	7/Red 2	8/Polymer A	41.1	112.6 (113)	5/5	5/5

89	7/Red 2	2/Pensize 730	41.7	64.8 (66)	4-5+/5	5/5
90	7/Red 2	3.75/Pensize 730	41.2	68.6 (69)	5/5	5/5
91	7/Red 2	10/Pensize 730	37.1	99.3 (90)	5/5	5/5
92	7/Red 2	18.75/Pensize 730	36.4	102.0 (115)	5/5	5/5

¹ to ⁴, see footnotes at end of Table 1

As in the previous experiments, the quantities of Polymer A required for producing dyeings of acceptable bleed fastness and depth of colour are considerably lower than the quantities of Pensize 730. Thus for example, in the case of C.I. Pigment Violet 23, 0.96% of Polymer A is required, whilst 4.26% of Pensize 730 is necessary. Analogous values with C.I. Pigment Blue 15:1 are 0.73% as opposed to above 3.84% and for C.I. Pigment Red 2, 0.41% as opposed to 3.71% Pensize 730.

Once again, the poor performance of the Pensize® 730 series in terms of color strength and dyeing efficiency is apparent when small or medium amounts of this copolymer are employed.

In one further series of experiments, not only the quantities of copolymer, but also the quantities of pigment were varied. The colour strengths in the Table represent the absolute measured values after drying. The results are summarized in the following Table 3:

Table 3

Example No.	%/ C.I. Pigment	% Copolymer	% Pick-up	% Colour Strength	Bleed Water PF ¹ /GF ²	Bleed Alcohol PF/GF
93	7/Violet 23	None	54.8	100	2-3/3	5/5
94	3.5/Violet 23	2.6/Polymer A ³	53.9	59	5/5	5/5
95	7/Violet 23	5.2/Polymer A	48.8	85	5/5	5/5
96	14/Violet 23	10.4/Polymer A	42.2	108	5/5	5/5
97	21/Violet 23	15.6/Polymer A	39.8	137	5/5	5/5
98	3.5/Violet 23	5.3/Pensize ⁴ 730	45.1	42	4-5+/5	5/5
99	7/Violet 23	10.5/Pensize 730	44.6	82	4-5+/5	5/5
100	14/Violet 23	21/Pensize 730	36.7	129	4-5+/5	5/5
101	21/Violet 23	31.5/Pensize 730	32.1	142	4-5+/5	5/5

102	8/Blue 15:1	None	46.3	100	3/4-5	5/5
103	4/Blue 15:1	2.5/Polymer A	47.3	62	4-5+/5	5/5
104	8/Blue 15:1	5/Polymer A	44.4	99	4-5+/5	5/5
105	16/Blue 15:1	10/Polymer A	37.9	140	4-5+/5	5/5
106	24/Blue 15:1	15/Polymer A	35.9	175	4-5+/5	5/5
107	4/Blue 15:1	5/Pensize 730	44.2	41	4-5+/5	5/5
108	8/Blue 15:1	10/Pensize 730	39.3	72	4-5+/3-4+	5/5
109	16/Blue 15:1	20/Pensize 730	32.3	124	4-5+/4	5/5
110	24/Blue 15:1	30/Pensize 730	29.9	176	4-5+/5	5/5
111	7/Red 2	None	42.9	100	3-4/4+	5/5
112	3.5/Red 2	2.1/Polymer A	45.2	62	5/5	5/5
113	7/Red 2	4.2/Polymer A	41.3	99	5/5	5/5
114	14/Red 2	8.4/Polymer A	36.9	141	5/5	5/5
115	21/Red 2	12.6/Polymer A	33.1	173	5/5	5/5
116	3.5/Red 2	5/Pensize 730	41.3	49	5/5	5/5
117	7/Red 2	10/Pensize 730	38.1	89	5/5	5/5
118	14/Red 2	20/Pensize 730	31.4	148	5/5	5/5
119	21/Red 2	30/Pensize 730	26.8	200	5/5	5/5

¹ to ⁴, see footnotes at end of Table 1

Again the advantages of Polymer A are especially apparent at low concentrations when compared to Pensize 730.

Claims

1. A composition comprising

a) from 0.1 to 30% by weight, based on the total weight of the composition, of a colouring
5 pigment,

b) from 0.1 to 20% by weight, based on the total weight of the composition of a starch/latex
copolymer, characterized in that, in addition to starch, the monomeric components that are
copolymerized comprise

i) styrene or a substituted styrene,

10 ii) an acrylate and/or methacrylate and, optionally,

iii) one or more further ethylenically unsaturated monomers,

c) from 0 to 20% by weight, based on the total weight of the composition, of starch or a
starch derivative,

d) from 0 to 10% by weight, based on the total weight of the composition of one or more
15 auxiliaries and

e) water to complete to 100% by weight, based on the total weight of the composition.

2. A composition according to claim 1, in which the colouring pigment is selected from

pigments disclosed in the Colour Index International under the designations C.I. Pigment

20 Yellows 1 to 221, C.I. Pigment Oranges 1 to 81, C.I. Pigment Reds 1 to 283, C.I. Pigment

Violets 1 to 53, C.I. Pigment Blues 1 to 81, C.I. Pigment Greens 1 to 56, C.I. Pigment Browns

1 to 47 and C.I. Pigment Blacks 1 to 35.

3. A composition according to claim 1 or claim 2, wherein the starch/latex copolymer consists

25 of

i) from 5 to 50% by weight of starch and

ii) from 50 to 95% by weight of the monomeric components.

4. A composition according to any one of claims 1 to 3, wherein the starch component of the

30 copolymer, component b) of the composition, is a degraded, oxidized anionic starch.

5. A composition according to any one of claims 1 to 4, in which the starch/latex copolymer is
obtained by copolymerization of

i) from 20 to 40% by weight of styrene or a substituted styrene,

- ii) from 20 to 50% of an acrylate or a methacrylate and
- iii) from 5 to 20% by weight of one or more further ethylenically unsaturated monomers, in the presence of from 15 to 40% by weight of starch.

5 6. A composition according to any one of claims 1 to 5, in which the starch/latex copolymer is in the form of an aqueous dispersion having a dry content of from 20 to 50% by weight.

7. A composition according to any one of claims 1 to 6, wherein the auxiliary is selected from fixing agents, dispersants, binder resins, insolubilizing and/or cross linking agents, anionic,
10 cationic and neutral polymers, wet-strength agents, antifoams and biocides.

8. Use of the composition according to any one of claims 1 to 7 for the surface colouration of paper.

15 9. A method for the surface colouration of paper by applying to the paper surface a composition comprising
a) from 0.1 to 30% by weight, based on the total weight of the composition, of a colouring pigment, whereby the colouring pigment is in solid form or in the form of a dispersion,
b) from 0.1 to 20% by weight, based on the total weight of the composition of a starch/latex
20 copolymer, characterized in that, in addition to starch, the monomeric components that are copolymerized comprise

- i) styrene or a substituted styrene,
- ii) an acrylate and/or methacrylate and, optionally,
- iii) one or more further ethylenically unsaturated monomers,

25 c) from 0 to 20% by weight, based on the total weight of the composition, of starch or a starch derivative,
d) from 0 to 10% by weight, based on the total weight of the composition of one or more auxiliaries and
e) water to complete to 100% by weight, based on the total weight of the composition.

30

10. Paper, which has been treated with a composition according to any one of claims 1 to 7 or by the method according to claim 9.

INTERNATIONAL SEARCH REPORT

International application No

PCT/EP2007/050427

A. CLASSIFICATION OF SUBJECT MATTER

INV. D21H21/28 D21H19/10 D21H17/20

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

D21H

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 2004/090228 A (CIBA SPECIALTY CHEMICALS HOLDING INC; DAVENPORT, RAY; HUNGER, CHARLES;) 21 October 2004 (2004-10-21) cited in the application tables 1-4	1, 9, 10
A	WO 00/46264 A (RAISIO CHEMICALS LTD; LINDSTROEM, MARI; NURMI, KARI; TAMMI, ANNA-LIISA) 10 August 2000 (2000-08-10) cited in the application the whole document	1, 9, 10
A	US 5 131 981 A (HAHN ET AL) 21 July 1992 (1992-07-21) examples	1
-/--		

☒ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

* Special categories of cited documents :

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the International filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

G document member of the same patent family

Date of the actual completion of the international search

28 February 2007

Date of mailing of the international search report

18/04/2007

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Naeslund, Per

INTERNATIONAL SEARCH REPORT

International application No

PCT/EP2007/050427

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 2004/035925 A (BASF CORPORATION; BASF AKTIENGESELLSCHAFT; PELLETIER, JOHN; PAKAN, DWI) 29 April 2004 (2004-04-29) abstract -----	1
A	PATENT ABSTRACTS OF JAPAN vol. 016, no. 298 (C-0958), 2 July 1992 (1992-07-02) & JP 04 082993 A (SANYOU SHIKISO KK), 16 March 1992 (1992-03-16) abstract -----	1
A	WO 03/004766 A (BASF CORPORATION; DECKERS, JAMES, A; JOSE, STEPHEN, S; JENNINGS, MICHA) 16 January 2003 (2003-01-16) cited in the application the whole document -----	1-10
A	US 4 855 343 A (DEGEN ET AL) 8 August 1989 (1989-08-08) abstract -----	1,9,10
A	US 5 498 648 A (DE CLERCQ ET AL) 12 March 1996 (1996-03-12) abstract -----	1,9,10
A	US 6 426 381 B1 (KOENIG JOACHIM ET AL) 30 July 2002 (2002-07-30) claims -----	1-10
A	US 4 835 212 A (DEGEN ET AL) 30 May 1989 (1989-05-30) examples -----	1-10

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2007/050427

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 2004090228	A	21-10-2004	AU 2004227117 A1 BR PI0409371 A CA 2522181 A1 CN 1774541 A EP 1613809 A1 JP 2006522878 T KR 20050113279 A MX PA05011040 A	21-10-2004 25-04-2006 21-10-2004 17-05-2006 11-01-2006 05-10-2006 01-12-2005 12-12-2005
WO 0046264	A	10-08-2000	AU 2550700 A CA 2356752 A1 CN 1339042 A DE 60016186 D1 DE 60016186 T2 EP 1165642 A1 JP 2002536473 T RU 2242483 C2	25-08-2000 10-08-2000 06-03-2002 30-12-2004 24-11-2005 02-01-2002 29-10-2002 20-12-2004
US 5131981	A	21-07-1992	AU 2295788 A CA 1302022 C DE 3732981 A1 DK 544388 A EP 0309908 A2 FI 884421 A JP 1104898 A	06-04-1989 02-06-1992 13-04-1989 31-03-1989 05-04-1989 31-03-1989 21-04-1989
WO 2004035925	A	29-04-2004	AU 2003276092 A1	04-05-2004
JP 04082993	A	16-03-1992	NONE	
WO 03004766	A	16-01-2003	US 2004123404 A1 US 2003005527 A1	01-07-2004 09-01-2003
US 4855343	A	08-08-1989	AU 594492 B2 AU 7685587 A BR 8704166 A CA 1294721 C DE 3627594 A1 DK 422187 A EP 0257412 A1 ES 2018508 T5 FI 873236 A JP 2518858 B2 JP 63050596 A NZ 221423 A	08-03-1990 18-02-1988 12-04-1988 21-01-1992 18-02-1988 15-02-1988 02-03-1988 16-04-1991 15-02-1988 31-07-1996 03-03-1988 24-02-1989
US 5498648	A	12-03-1996	AU 4951693 A DE 4229142 A1 WO 9405855 A1 EP 0658228 A1 ES 2089839 T3 FI 933829 A NO 933099 A	29-03-1994 03-03-1994 17-03-1994 21-06-1995 01-10-1996 02-03-1994 02-03-1994
US 6426381	B1	30-07-2002	AT 272077 T AU 739568 B2 AU 3140499 A BR 9908024 A	15-08-2004 18-10-2001 06-09-1999 07-11-2000

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2007/050427

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 6426381	B1	CA 2321058 A1	26-08-1999
		DE 19806745 A1	19-08-1999
		WO 9942490 A1	26-08-1999
		EP 1056783 A1	06-12-2000
		ES 2226364 T3	16-03-2005
		JP 2002504563 T	12-02-2002
		PT 1056783 T	30-11-2004
US 4835212	A	30-05-1989	
		AU 591375 B2	30-11-1989
		AU 1110588 A	04-08-1988
		CA 1303765 C	16-06-1992
		DE 3702712 A1	11-08-1988
		DK 44588 A	31-07-1988
		EP 0276770 A2	03-08-1988
		ES 2023442 T5	16-01-1992
		FI 880037 A	31-07-1988
		JP 2518884 B2	31-07-1996
		JP 63203895 A	23-08-1988
		NO 880391 A	01-08-1988
		NZ 223346 A	28-06-1989