



US 20060088669A1

(19) **United States**(12) **Patent Application Publication**
Li et al.(10) **Pub. No.: US 2006/0088669 A1**(43) **Pub. Date: Apr. 27, 2006**(54) **METHOD FOR MANUFACTURING
BRIGHTNESS ENHANCEMENT FILM OF
LIQUID CRYSTAL DISPLAY AND
STRUCTURE THEREOF**(30) **Foreign Application Priority Data**

Jan. 22, 2003 (TW)..... 92101406

(75) Inventors: **Tung Lung Li**, Tucheng City (TW); **Pei
Lun Wu**, Pingjhen City (TW); **Long
Hai Wu**, Bade City (TW)**Publication Classification**(51) **Int. Cl.****C09K 19/00** (2006.01)(52) **U.S. Cl.** **428/13**


Correspondence Address:

**THE WEBB LAW FIRM, P.C.
700 KOPPERS BUILDING
436 SEVENTH AVENUE
PITTSBURGH, PA 15219 (US)**

(57)

ABSTRACT(73) Assignee: **Optimax Technology Corporation**,
Pingjhen City (TW)(21) Appl. No.: **11/297,678**(22) Filed: **Dec. 8, 2005****Related U.S. Application Data**(62) Division of application No. 10/761,085, filed on Jan.
20, 2004.

A brightness enhancement film for use on a display includes a first substrate, a first light transmitting layer mounted on said first substrate, a second light transmitting layer mounted on said first light transmitting layer, a third light transmitting layer mounted between said first light transmitting layer and second light transmitting layer, and a second substrate mounted on said second light transmitting layer, wherein said first and said second light transmitting layer have a first and a second chiral character, respectively, and said third light transmitting layer has a wide-band chiral character.






Fig. 1 (PRIOR ART)




Fig. 2A




Fig. 2B




Fig. 2C




Fig. 2D




Fig. 2E




Fig. 2F




Fig. 2G




Fig. 2H




Fig. 3A




Fig. 3B




Fig. 4




Fig. 5

METHOD FOR MANUFACTURING BRIGHTNESS ENHANCEMENT FILM OF LIQUID CRYSTAL DISPLAY AND STRUCTURE THEREOF

CROSS REFERENCE TO RELATED APPLICATION

[0001] This application is a divisional of U.S. patent application Ser. No. 10/761,085, filed Jan. 20, 2004, entitled "Method For Manufacturing Brightness Enhancement Film Of Liquid Crystal Display And Structure Thereof."

BACKGROUND OF THE INVENTION

[0002] 1. Field of the Invention

[0003] The present invention relates to a manufacturing method for a brightness enhancement film, and more particularly to a manufacturing method for a brightness enhancement film of a liquid crystal display (LCD) and the structure thereof.

[0004] 2. Description of Related Art

[0005] A backlight module, also known as a backlight unit, is generally an optical assembly providing a backlight source for products and applied to digital camera, PDA (Personal Digital Assistant), GPS (Global Positioning System), medical apparatus, notebook, LCD Monitor, and etc. Owing to the TFT LCD panel itself does not have a light-emitting function, it must have a light source mounted in the LCD panel. A backlight module is an important optical assembly of a light source. Therefore, a backlight module is a key component for the TFT LCD, a popular product in the present days.

[0006] The inner structure of a backlight module basically includes a light source, a reflective sheet, a light guide plate, a diffuser, a prism sheet and a frame base. Technically, a backlight module is firstly made by the method of injection molding that the propylene (acrylic sheet) is pressed to form a sheet with a smooth surface (i.e. a light guide plate). Subsequently, the diffusion spots are printed at the bottom of the light guide plate with high reflective, light-unabsorbable materials by screen printing method. And the light from the cold cathode fluorescent lamp (CCFL) which is situated at the lateral side of the thick end of the light guide plate transmits to the thin end of the light guide plate through reflection. When the light meets the diffusion spots, the reflex scatters by different angles and then transmits from the front side of the light guide plate on account of breaking the total reflection rule. The various sizes of diffusion spots and different spacings between thereof enable the light guide plate to be luminant uniformly. The reflective sheet then reflects the light leaking out from the bottom of the light guide plate back to the light guide plate for increasing the efficiency of light usage.

[0007] However, the choke point of developing TFT LCD technology is the brightness. Generally, only 5%~8% of the light source from the LCD lamp remains after transmitted through substrates to the user's eyes. According to the standard of CRT monitors, the brightness for TFT LCD is not enough. Although plenty of researches are conducted on the solution to improving brightness, such as increasing luminance of backlight source or LCD, i.e. increasing the aperture ratio of TFT LCD or luminance of all components, most of these solutions can not solve the problem without

heat dissipating problem and over-consumption of electricity. For the purpose of improving brightness, 3M Company provides a solution by using the brightness enhancement films (BEF) and dual brightness enhancement films (DBEF). A brightness enhancement film is to centralize the scattered light through refracting the lateral light by V-type thin stripes. Using 3M brightness enhancement films may efficiently centralize the light scattered everywhere to the main axis of sight of the display for improving brightness without modifying the structures and over-consumption of electricity. It is a better solution nowadays but the costs are more expensive.

[0008] Another solution widely used by industry is to utilize cholesteric liquid crystal (CLC) brightness enhancement film, which is based on the optical rotation property of the cholesteric macromolecules. Please refer to FIG. 1, which is the diagram illustrating the merchandise of CLC brightness enhancement film of Nitto Denko Company. The CLC brightness enhancement film includes the substrate 11, the alignment film 12, and the plurality of CLC layers 13. Each CLC layer 13 has different ranges of transparent wavelength respectively. Through the reflective sheet 151, the light guide plate 152, the ¼ wavelength plate 16, and the polarizer 17 shown in FIG. 1, the light is efficiently transmitted from the light source 14 to the main axis of sight of a display. Since the CLC layers 13 have different optical properties when the cholesteric molecules are cured under different operating conditions, the plurality of CLC layers 13 are made by multiple coating and curing processes. Those processes are very intricate, for example, the CLC layers including red (R), green (G), and blue (B) cholesteric liquid crystal layers, which are three different polarized wavelengths shown in FIG. 1, have to be coated with a cholesteric molecules layer in sequence and subsequently cured under different operating conditions. A further method for manufacturing a plurality of CLC layers is to add dyes into them and manipulate the curing conditions. And the relative processes are more complicated. It is therefore desirous to develop a fast and simple method for manufacturing a plurality of CLC films, i.e. brightness enhancement films.

SUMMARY OF THE INVENTION

[0009] It is an object of the present invention to provide a method for manufacturing a plurality of CLC films fast and simply, i.e. brightness enhancement films.

[0010] In accordance with one aspect of the present invention, the method for manufacturing the brightness enhancement film of the LCD includes steps of: (a) providing a first substrate; (b) forming a first macromolecule liquid crystal on the first substrate; (c) curing a part of the first macromolecule liquid crystal on the first substrate for forming a first light transmitting layer; (d) providing a second substrate; (e) forming a second macromolecule liquid crystal on the second substrate; (f) curing a part of the second macromolecule liquid crystal on the second substrate for forming a second light transmitting layer; (g) combining a non-curing part of the first macromolecule liquid crystal and the second macromolecule liquid crystal for forming a third macromolecule liquid crystal between the first light transmitting layer and the second light transmitting layer; and (h) curing the third macromolecule liquid crystal for forming a third light transmitting layer.

[0011] Preferably, the first substrate and the second substrate are polyethylene terephthalate substrates (PET).

[0012] Preferably, the first substrate and the second substrate each further includes an alignment film.

[0013] Preferably, the first macromolecule liquid crystal and the second macromolecule liquid crystal are cholesteric liquid crystal (CLC).

[0014] Preferably, the cholesterol molecules of the first light transmitting layer and the second light transmitting layer include a single pitch.

[0015] Preferably, the first light transmitting layer and the second light transmitting layer have the same chiral character.

[0016] Preferably, the method step (b) is finished through coating.

[0017] Preferably, the method step (c) is finished through UV light which transmits the first substrate to cure a part of the first macromolecule liquid crystal.

[0018] Preferably, the first substrate can absorb a part of the UV light.

[0019] Preferably, the method step (c) further includes a step of: (c1) providing a gas for the first macromolecule liquid crystal to control the curing thickness of the first macromolecule liquid crystal, wherein the quantity of the gas of the curing part of the first macromolecule liquid crystal is different from the quantity of the gas of a non-curing part of the first macromolecule liquid crystal.

[0020] Preferably, the method step (e) is finished through coating.

[0021] Preferably, the method step (f) is finished through UV light which transmits the second substrate to cure a part of the second macromolecule liquid crystal.

[0022] Preferably, the second substrate can absorb a part of the UV light.

[0023] Preferably, the method step (f) further includes a step of: (f1) providing a gas for the second macromolecule liquid crystal to control the curing thickness of the second macromolecule liquid crystal, wherein the quantity of the gas of the curing part of the second macromolecule liquid crystal is different from the quantity of the gas of a non-curing part of the second macromolecule liquid crystal.

[0024] Preferably, the method step (g) further includes a step of: (g1) diffusing the first macromolecule liquid crystal and the second macromolecule liquid crystal after combining to make the third macromolecule liquid crystal spread equally between the first light transmitting layer and second light transmitting layer.

[0025] Preferably, the method step (h) further includes a step of: (h1) removing the second substrate.

[0026] In accordance with another aspect of the present invention, the method for making brightness enhancement film includes steps of: (a) providing a first substrate and a second substrate; (b) forming a first and a second macromolecule liquid crystal on the first and the second substrate, respectively; (c) curing a part of the first macromolecule liquid crystal on the first substrate and a part of the second macromolecule liquid crystal on the second substrate for forming a first light transmitting layer between the first substrate and the first macromolecule liquid crystal and

forming a second transmitting layer between the second substrate and the second macromolecule liquid crystal, respectively; (d) combining a non-curing part of the first macromolecule liquid crystal and the second macromolecule liquid crystal for forming a third macromolecule liquid crystal between the first light transmitting layer and the second light transmitting layer; and (e) curing the third macromolecule liquid crystal for forming a third light transmitting layer.

[0027] Preferably, the method step (c) further includes a step of: (c1) providing a gas for the macromolecule liquid crystal to control the curing thickness of the first and the second macromolecule liquid crystal, wherein the quantity of the gas of the curing part of the first and the second macromolecule liquid crystal is different from the quantity of the gas of a non-curing part of the first and the second macromolecule liquid crystal.

[0028] Preferably, the method step (c) cures a part of the first and the second macromolecule liquid crystal under different temperature control, respectively.

[0029] Preferably, the method step (d) further includes a step of: (d1) diffusing the first macromolecule liquid crystal and the second macromolecule liquid crystal after combining to make the third macromolecule liquid crystal spread equally between the first light transmitting layer and second light transmitting layer.

[0030] Preferably, step (e) further includes a step of: (e1) removing the second substrate.

[0031] Preferably, the second substrate is a $\frac{1}{4}$ -wavelength plate.

[0032] It is another object of the present invention to provide a brightness enhancement film put in use on a display, the brightness enhancement film includes a first substrate; a first light transmitting layer mounted on the first substrate; a second light transmitting layer mounted on the first light transmitting layer; a third light transmitting layer mounted between the first light transmitting layer and second light transmitting layer; and a second substrate mounted on the second light transmitting layer, wherein the first and the second light transmitting layer have a first and a second chiral character, respectively, and the third light transmitting layer has a wide-band chiral character.

[0033] Certainly, the display is a LCD.

[0034] Certainly, the first substrate is a polyethylene terephthalate substrate (PET).

[0035] Certainly, the brightness enhancement film further includes a first alignment film mounted between the first substrate and the first light transmitting layer.

[0036] Certainly, the first substrate is a $\frac{1}{4}$ -wavelength plate.

[0037] Certainly, the first, the second and the third light transmitting layer are all made of cholesteric liquid crystal (CLC).

[0038] It is more an object of the present invention to provide a structure of a display, the structure includes a luminary for providing a backlight; a light guide plate mounted on a side of the luminary for guiding the scattering direction of the backlight; a brightness enhancement diffu-

sion sheet mounted on the light guide plate for increasing luminance; and a liquid crystal layer mounted on the brightness enhancement diffusion sheet; wherein the brightness enhancement diffusion sheet further includes a first substrate; a first light transmitting layer mounted on the first substrate; a second light transmitting layer mounted on the first light transmitting layer; a third light transmitting layer mounted between the first light transmitting layer and second light transmitting layer; a $\frac{1}{4}$ -wavelength plate mounted on the second light transmitting layer; and a polarizer mounted on the $\frac{1}{4}$ -wavelength plate wherein the first and the second light transmitting layer have a first and a second chiral character, respectively, and the third light transmitting layer has a wide-band chiral character.

[0039] Preferably, the structure further includes a reflect sheet mounted below the light guide plate for increasing the efficiency of light.

[0040] The foregoing and other features and advantages of the present invention will be more clearly understood through the following descriptions with reference to the drawings, wherein:

BRIEF DESCRIPTION OF THE DRAWINGS

[0041] **FIG. 1** is a schematic view showing a preferred backlight module structure having a brightness enhancement film according to the prior art;

[0042] **FIGS. 2A-2H** are flowchart showing a method for manufacturing a brightness enhancement film in accordance with a preferred embodiment of the present invention;

[0043] **FIGS. 3A-3B** are a schematic views showing structures of brightness enhancement films in accordance with a preferred embodiment of the present invention;

[0044] **FIG. 4** is a schematic view showing a backlight module having a brightness enhancement film in accordance with a preferred embodiment of the present invention; and

[0045] **FIG. 5** is a schematic view showing a brightness enhancement diffusion sheet used in LCD module according to a preferred embodiment of the present invention.

DETAILED DESCRIPTION OF THE INVENTION

[0046] It is an object of the present invention to provide a method for manufacturing a plurality of CLC films fast and simply, i.e. brightness enhancement films.

[0047] Please refer to **FIG. 2**, which is the flowchart showing the method for manufacturing the brightness enhancement film in accordance with the present invention. The manufacturing method includes steps of: (1) providing the first substrate **21**, as shown in **FIG. 2A**; (2) forming the first macromolecule liquid crystal **22** on the first substrate **21** by coating, as shown in **FIG. 2B**; (3) curing the part of the first macromolecule liquid crystal **22** on the first substrate **21** by UV light which is transmitted through the first substrate **21** so as to form the first light transmitting layer **221**, as shown in **FIG. 2C**; (4) providing the second substrate **23**, as shown in **FIG. 2D**; (5) forming the second macromolecule liquid crystal **24** on the second substrate **23** by coating, as shown in **FIG. 2E**; (6) curing the part of the second macromolecule liquid crystal **24** on the second substrate **23** by UV light which is transmitted through the second sub-

strate **23** so as to form the second light transmitting layer **241**, as shown in **FIG. 2F**; (7) combining the non-curing part of the first macromolecule liquid crystal **22** and the second macromolecule liquid crystal **24** for forming the third macromolecule liquid crystal **25** between the first light transmitting layer **221** and the second light transmitting layer **241**, as shown in **FIG. 2G**; and (8) curing the third macromolecule liquid crystal **25** by UV light which is transmitted through the first substrate **21** or the second substrate **23** so as to form the third light transmitting layer **251**. In this embodiment, the first substrate **21** and the second substrate **23** further include alignment films **212**, **232** in addition to the substrate bodies **211**, **231**, respectively.

[0048] In accordance with one aspect of the present invention, the first macromolecule liquid crystal **22**, the second macromolecule liquid crystal **24** and the third macromolecule liquid crystal **25** are cholesteric liquid crystal layers. However, after the processes of the above steps, the cholesterol molecules of the first light transmitting layer **221** and the second light transmitting layer **241** include the single pitch. In other words, the first light transmitting layer **221** and the second light transmitting layer **241** have the same optical character, i.e. specific chiral character. During the process of curing by UV light for forming the first light transmitting layer **221** and the second light transmitting layer **241**, the UV light is transmitted through the first substrate **21** to cure a part of the first macromolecule liquid crystal **22** and is transmitted through the second substrate **23** to cure a part of the second macromolecule liquid crystal **24**. In accordance with the aspect of the present invention, the first substrate **21** and the second substrate **23** can absorb partial UV light in order to be adjusted to the operation conditions when curing the macromolecule liquid crystal **22**, **24** for forming the light transmitting layer **221**, **241**. Furthermore, the macromolecule liquid crystal **22**, **24** according to the present application are accomplished through coating but the formation of the macromolecule liquid crystal **22**, **24** is not limited in this way.

[0049] In accordance with another aspect of the present invention, the method for making the brightness enhancement film includes steps of: (a) providing the first substrate **21** and the second substrate **23**; (b) forming the first and the second macromolecule liquid crystal **22**, **24** on the first and the second substrate **21**, **23** by coating, respectively; (c) curing a part of the first macromolecule liquid crystal **22** on the first substrate **21** and a part of the second macromolecule liquid crystal **24** on the second substrate **23** for forming the first light transmitting layer **221** between the first substrate **21** and the first macromolecule liquid crystal **22** and forming the second transmitting **241** layer between the second substrate **23** and the second macromolecule liquid crystal **24**, respectively; (d) combining the non-curing part of the first macromolecule liquid crystal **22** and the second macromolecule liquid crystal **24** for forming the third macromolecule liquid crystal **25** between the first light transmitting layer **221** and the second light transmitting layer **241**; and (e) curing the third macromolecule liquid crystal **25** for forming the third light transmitting layer **251**. In accordance with the previous embodiment, the first macromolecule liquid crystal **22**, the second macromolecule liquid crystal **24** and the third macromolecule liquid crystal **25** are cholesteric liquid crystal layers. However, after the processes of the above steps, the cholesterol molecules of the first light transmitting layer **221** and the second light transmitting layer **241** include the

single pitch. In other words, the first light transmitting layer 221 and the second light transmitting layer 241 have the same optical character, i.e. specific chiral character.

[0050] Please refer to FIG. 3A, which discloses a brightness enhancement film manufactured by a fast and simple method mentioned above. The structure includes the first substrate 31, the second substrate 32, the first light transmitting layer 33, the second light transmitting layer 34, and the third light transmitting layer 35. The first light transmitting layer 33 is mounted on the first substrate 31. The second light transmitting layer 34 is mounted on the first light transmitting layer 33. The third light transmitting layer 35 is mounted between the first light transmitting layer 33 and second light transmitting layer 34. The second substrate 32 is mounted on the second light transmitting layer 34. The first and the second light transmitting layer 33, 34 have the first and the second chiral character, respectively, and the third light transmitting layer 35 has the wide-band chiral character. The brightness enhancement film according to this embodiment could be put in use on the backlight module of the LCD for increasing luminance of the backlight module, wherein the first substrate 31 and the second substrate 32 are polyethylene terephthalate (PET) substrates. Moreover, the brightness enhancement film further includes the first alignment film 311 and the second alignment film 321. The first alignment film 311 is mounted between the first substrate 31 and the first light transmitting layer 33. The second alignment film 321 is mounted between the second substrate 32 and the second light transmitting layer 34. Certainly, the first, the second and the third light transmitting layer 33, 34, 35 are all made of cholesteric liquid crystal (CLC) wherein the cholesterol molecules of the first light transmitting layer 33 and the second light transmitting layer 34 include the single pitch and the chiral character, respectively. As shown in FIG. 3A, the first, the second and the third light transmitting layer 33, 34, 35 include blue (B), green (G) and red (R) cholesteric liquid crystal layers, which are three different polarized wavelengths, respectively. However, different and desired polarized wavelengths could be obtained by changing operation conditions of the manufacturing method mentioned above. Besides, the second substrate 32 could be the $\frac{1}{4}$ -wavelength plate according to the previous method. As shown in FIG. 3B, it is also possible to combine the $\frac{1}{4}$ -wavelength plate 36 and the polarizer 37 instead after removing the second substrate 32 in the manufacturing process.

[0051] Please refer to FIG. 4, which is a preferred embodiment of a backlight module having a brightness enhancement film in accordance with the present invention. The backlight module includes the luminary 41, the light guide plate 42, and the brightness enhancement sheet 43. The luminary 41 is used for providing the backlight. The light guide plate 42 is mounted on the side of the luminary 41 for guiding the scattering direction of the backlight. The brightness enhancement sheet 43 is mounted on the light guide plate 42 for increasing luminance. The brightness enhancement sheet 43 is made according to the method mentioned above. The brightness enhancement sheet 43 includes the first substrate 431, the multilayer brightness enhancement sheet, and the $\frac{1}{4}$ -wavelength plate 45. The multilayer brightness enhancement sheet are mounted between the first substrate 431 and the $\frac{1}{4}$ -wavelength plate 45. The multilayer brightness enhancement sheet further includes the first light transmitting layer 433, the third light

transmitting layer 435 and the second light transmitting layer 434 in sequence. The first light transmitting layer 433 and the second light transmitting layer 434 have the first and the second chiral character, respectively, while the third light transmitting layer 35 has the wide-band chiral character. Moreover, the first substrate 431 is the polyethylene terephthalate (PET) substrate and the brightness enhancement sheet further includes the first alignment film 432 mounted between the first substrate 431 and the first light transmitting layer 433. Certainly, the first, the second and the third light transmitting layer 433, 434, 435 are all made of cholesteric liquid crystal (CLC). Therefore, the cholesterol molecules of the first light transmitting layer 433 and the second light transmitting layer 434 include the single pitch after processed by the method mentioned above. As shown in FIG. 4, the backlight module according to the present application further includes the polarizer 46 and the reflective sheet 44. The reflective sheet 44 is mounted below the light guide plate 42 for improving the efficiency of light usage.

[0052] Please refer to FIG. 5, which is a schematic view showing a brightness enhancement diffusion sheet according to the present invention put in use on a LCD. As shown in FIG. 5, the LCD includes the luminary 51, the light guide plate 52, the brightness enhancement diffusion sheet 54, and the liquid crystal layer 55. The luminary 51 is used for providing the backlight. The light guide plate 52 is mounted on the side of the luminary 51 for guiding the scattering direction of the backlight. The brightness enhancement diffusion sheet 54 is mounted on the light guide plate 52 for increasing luminance. The liquid crystal layer 55 is mounted on the brightness enhancement diffusion sheet 54. The brightness enhancement diffusion sheet 54 is made according to the method mentioned above. The brightness enhancement diffusion sheet 54 includes the first substrate 544, the multilayer brightness enhancement sheet 541, the $\frac{1}{4}$ -wavelength plate 542, and the polarizer 543. The multilayer brightness enhancement sheet 541 includes the first light transmitting layer, the second light transmitting layer and the third light transmitting layer in accordance with the structure mentioned above. The first light transmitting layer and the second light transmitting layer have the first and the second chiral character respectively, while the third light transmitting layer 35 has the wide-band chiral character. Therefore, the preferred LCD is obtained by means of combining the component in accordance with the present invention. While specific embodiments have been shown and described, many modifications and variations could be made by one skilled in the art.

[0053] While the invention has been described in terms of what are presently considered to be the most practical and preferred embodiments, it is to be understood that the invention need not be limited to the disclosed embodiment. On the contrary, it is intended to cover various modifications and similar arrangements included within the spirit and scope of the appended claims which are to be accorded with the broadest interpretation so as to encompass all such modifications and similar structures. Therefore, the above description and illustration should not be taken as limiting the scope of the present invention which is defined by the appended claims.

What is claim is:

1. A brightness enhancement film put in use on a display, said brightness enhancement film comprising:

- a first substrate;
- a first light transmitting layer mounted on said first substrate;
- a second light transmitting layer mounted on said first light transmitting layer;
- a third light transmitting layer mounted between said first light transmitting layer and second light transmitting layer; and
- a second substrate mounted on said second light transmitting layer, wherein said first and said second light transmitting layer have a first and a second chiral character, respectively, and said third light transmitting layer has a wide-band chiral character.

2. The brightness enhancement film according to claim 1, wherein said display is a LCD.

3. The brightness enhancement film according to claim 1, wherein said first substrate is a polyethylene terephthalate substrate (PET).

4. The brightness enhancement film according to claim 1, further comprises a first alignment film mounted between said first substrate and said first light transmitting layer.

5. The brightness enhancement film according to claim 1, wherein said first substrate is a $\frac{1}{4}$ -wavelength plate.

6. The brightness enhancement film according to claim 1, wherein said first, said second and said third light transmitting layers are all made of cholesteric liquid crystal (CLC).

7. A structure of a display, said structure comprising:

- a luminary for providing a backlight;
- a light guide plate mounted on a side of said luminary for guiding the scattering direction of said backlight;

a brightness enhancement diffusion sheet mounted on said light guide plate for increasing luminance; and

a liquid crystal layer mounted on said brightness enhancement diffusion sheet;

wherein said brightness enhancement diffusion sheet further comprises:

- a first substrate;
- a first light transmitting layer mounted on said first substrate;
- a second light transmitting layer mounted on said first light transmitting layer;
- a third light transmitting layer mounted between said first light transmitting layer and second light transmitting layer;
- a $\frac{1}{4}$ -wavelength plate mounted on said second light transmitting layer; and
- a polarizer mounted on said $\frac{1}{4}$ -wavelength plate wherein said first and said second light transmitting layer have a first and a second chiral character, respectively, and said third light transmitting layer has a wide-band chiral character.

8. The structure according to claim 7, further comprising a reflect sheet mounted below said light guide plate for increasing the efficiency of light.

* * * * *