



US 20170125650A1

(19) **United States**

(12) **Patent Application Publication**

**Pickett et al.**

(10) **Pub. No.: US 2017/0125650 A1**

(43) **Pub. Date: May 4, 2017**

(54) **DISPLAY DEVICES COMPRISING  
GREEN-EMITTING QUANTUM DOTS AND  
RED KSF PHOSPHOR**

*F21V 8/00* (2006.01)

*H01L 33/48* (2006.01)

*H01L 33/56* (2006.01)

(71) Applicant: **Nanoco Technologies Ltd.**, Manchester (GB)

(52) **U.S. Cl.**

CPC ..... *H01L 33/507* (2013.01); *H01L 33/486* (2013.01); *H01L 33/56* (2013.01); *G02B*

(72) Inventors: **Nigel L. Pickett**, Manchester (GB);  
**Nathalie C. Gresty**, Chester (GB);  
**James Harris**, Manchester (GB)

*6/0073* (2013.01); *G02F 1/133621* (2013.01);  
*G02B 6/005* (2013.01); *G02F 2001/133614* (2013.01)

(21) Appl. No.: **15/337,557**

(22) Filed: **Oct. 28, 2016**

(57)

**ABSTRACT**

**Related U.S. Application Data**

(60) Provisional application No. 62/249,595, filed on Nov. 2, 2015.


**Publication Classification**


(51) **Int. Cl.**

*H01L 33/50* (2006.01)


*G02F 1/1335* (2006.01)

LED devices emitting white light comprise a blue-emitting LED, green-emitting quantum dots (QDs) and red-emitting  $\text{K}_2\text{SiF}_6\text{:Mn}^{4+}$  (KSF) phosphor. A backlight unit (BLU) for a liquid crystal display (LCD) comprises one or more blue-emitting LEDs and a polymer film containing green-emitting QDs and KSF phosphor. The QDs and/or KSF phosphor may be encapsulated in beads that provide protection from oxygen and/or moisture.







**FIG. 1**




**FIG. 2**



**FIG. 3**



**FIG. 4**



**FIG. 5**




FIG. 6




FIG. 7





FIG. 8





**FIG. 9**







FIG. 10




**FIG. 11**




**FIG. 12**




**FIG. 13**



**FIG. 14**




**FIG. 15**




**FIG. 16**





**FIG. 17**



**FIG. 18**

# DISPLAY DEVICES COMPRISING GREEN-EMITTING QUANTUM DOTS AND RED KSF PHOSPHOR

## CROSS-REFERENCE TO RELATED APPLICATIONS:

[0001] This application claims the benefit of U.S. Provisional Application No. 62/249,595 filed on Nov. 2, 2015, the contents of which are hereby incorporated by reference in their entirety.

## STATEMENT REGARDING FEDERALLY SPONSORED RESEARCH OR DEVELOPMENT

[0002] Not Applicable

## BACKGROUND OF THE INVENTION

[0003] 1. Field of the Invention.

[0004] The present invention relates to materials and processes for the production of display devices. More specifically, the invention relates to backlight units for display devices comprising quantum dots and  $K_2SiF_6 \cdot Mn^{4+}$  (KSF) phosphor.

[0005] 2. Description of the Related Art including information disclosed under 37 CFR 1.97 and 1.98.

[0006] Quantum dots (QDs) have been used in the backlight unit (BLU) of liquid crystal displays (LCDs) to improve the color gamut compared to conventional LCD backlight units comprising a blue LED and a conventional rare earth phosphor. The color gamut is compared to standards in the Commission Internationale de l'Eclairage (CIE) 1931 color space. Such standards include the National Television System Committee 1953 (NTSC 1953) and the Digital Cinema Initiatives-P3 (DCI-P3) color triangles. In 2012, the International Telecommunications Union recommended a new standard for ultra-high definition television (UHDTV), known as Rec. 2020. The color triangle for Rec. 2020 is significantly larger than the NTSC 1953 and DCI-P3 color triangles, covering 76% of the color space seen by the human eye.

[0007] QDs have been used to produce BLUs with good overlap with the NTSC 1953 and DCI-P3 color space. However, achieving good overlap with Rec. 2020 is a challenge, in part owing to the full-width at half-maximum (FWHM) of the spectral emission peaks of the QDs.

[0008] A recent presentation suggested that, to achieve greater than 90% overlap with the Rec. 2020 color space, green QDs emitting at 526 nm with a FWHM of 30 nm and red-emitting QDs emitting at 640 nm with a FWHM of 30 nm would be required. [J. Hartolve, J. Chen, S. Kan, E. Lee and S. Gensler, *Bringing Better Pixels to UHD with Quantum Dots*. Presented at Quantum Dots Forum, 18 Mar., 2015, San Francisco] FWHM values in this region may be achieved using cadmium-based QDs, such as CdSe. However, in the EU, the Restriction of the Use of Certain Hazardous Substances (RoHS) Directive limits the amount of cadmium (and other heavy-metals) that may be used in electrical and electronic equipment. Similar legislation is being adopted throughout the world. Thus, there is a need to develop display devices comprising heavy-metal-free QDs, i.e. QDs without the incorporation of toxic elements such as Pb, Hg or Cd, such as Group III-V-based QDs, which are compliant with RoHS and other health and safety legislation. Such heavy-metal-free QDs may include Group III-V-

based materials (such as InP), as well as alloys of e.g. Group III-V materials alloyed with other elements, e.g. InPZnS (as described in U.S. Publication No. 2014/0264172.). In Group III-V-based materials, the quantum confinement effects are stronger than those in Group III-V materials (including CdSe). This leads to a larger change in emission wavelength from a given change in particle size, and consequently a broader FWHM is displayed by Group III-V materials than Group II-V materials. FWHM values are typically broader for red-emitting heavy-metal-free QDs than green-emitting heavy-metal-free QDs.

[0009] One potential means for providing a broad color gamut is to combine green-emitting QDs with a narrow-band-emitting red phosphor, such as  $K_2SiF_6 \cdot Mn^{4+}$  (KSF). KSF has four emission maxima at 613 nm, 631 nm, 636 nm and 648 nm, each with a FWHM < 5 nm. [P. Pust, P. J. Schmidt and W. Schnick, *Nat. Mater.*, 2015, 14, 454] Zhang et al. recently reported a white LED comprising a blue GaN LED, green-emitting  $CH_3NH_3PbX_3$  ( $X=Br, I, Cl$ ) QDs and a red-emitting KSF phosphor. [F. Zhang, H. Zhong, C. Chen, X. G. Wu, X. Hu, H. Huang, J. Han, B. Zhou and Y. Dong, *ACS Nano*, 2015, 9, 4533] The device covered ~130% of the NTSC color space, with 96% overlap. To form the LED device, KSF powder was blended with silicone gel and left to cure for 30 minutes.  $CH_3NH_3PbBr_3$  QDs were dissolved in chloroform with polymethylmethacrylate. The layer of silicone gel with KSF was painted onto the surface of a blue GaN LED chip, followed by casting a layer of QDs in PMMA. Though the study demonstrates that a large color gamut may be achieved by combining green QDs with a red KSF phosphor, the  $CH_3NH_3PbX_3$  QDs are not currently commercially available and contain lead, another heavy-metal subject to RoHS regulations. Further, the on-chip configuration may create thermal stability issues due to the close proximity of the QDs to the LED chip, resulting in short device lifetimes.

[0010] Manganese-activated fluoride complex phosphors are phosphors having  $Mn^{4+}$  as an activator and a fluoride complex salt of an alkali metal, an amine, or an alkaline earth metal as a base crystal. The coordination center in the fluoride complex that forms the base crystal is a trivalent metal (B, Al, Ga, In, Y, Sc or a lanthanoid), a tetravalent metal (Si, Ge, Sn, Ti, Zr, Re, Hf), or a pentavalent metal (V, P, Nb or Ta) with 5 to 7 fluorine atoms coordinated around the coordination center.

[0011] A preferred  $Mn^{4+}$ -activated fluoride complex phosphor is  $A_2MF_6 \cdot Mn$  having a hexafluoro complex salt of an alkali metal as a base crystal (where A is selected from the group consisting of Li, Na, K, Rb, Cs and  $NH_4$ , and M is selected from the group consisting of Ge, Si, Sn, Ti and Zr). Particularly preferred is a  $Mn^{4+}$ -activated fluoride complex phosphor where A is K (potassium) or Na (sodium), and M is Si (silicon) or Ti (titanium)—for example,  $K_2SiF_6 \cdot Mn^{4+}$  (KSF).

[0012] There is a need in the art to provide a means to integrate heavy-metal-free QDs and KSF phosphor into display devices, whereby the optical stability of the QDs is maintained.

## BRIEF SUMMARY OF THE INVENTION

[0013] Herein, a method is disclosed for combining a blue-emitting LED, green-emitting QDs, and red-emitting KSF phosphor to produce white light with a wide color gamut, in such a way that the optical properties of the QDs

are not deteriorated by exposure to heat. LED devices comprising a blue-emitting LED chip, green-emitting QDs and red-emitting KSF phosphor are also disclosed.

**[0014]** In some embodiments, the QDs and/or the KSF phosphor are incorporated into polymer beads. In some embodiments, the QDs and the KSF phosphor are incorporated into the same bead. In alternative embodiments, the QDs and the KSF phosphor are incorporated into separate beads. In other embodiments, the QDs and the KSF phosphor are incorporated into a “core/shell bead” having a central core comprising a first material surrounded by a shell comprising a second material. The KSF phosphor may be incorporated into the core of the bead and QDs into the shell of the bead. Alternatively, the QDs may be incorporated into the core of the bead and KSF phosphor into the shell of the bead.

**[0015]** In some embodiments, the QDs and/or the KSF phosphor are deposited into the cup portion of an LED package.

**[0016]** In some embodiments, the QDs and/or the KSF phosphor are incorporated into a film that is positioned remotely from the LED chip.

#### BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWING(S)

**[0017]** FIG. 1 is a cross-sectional view of a polymer bead comprising green quantum dots and KSF phosphor particles.

**[0018]** FIG. 2 is a cross-sectional view of two polymer beads; one bead containing KSF phosphor and the other bead containing green quantum dots.

**[0019]** FIG. 3 is a cross-sectional view of a core/shell polymer bead comprising a core comprising KSF phosphor particles and a shell comprising green quantum dots.

**[0020]** FIG. 4 is a cross-sectional view of a core/shell polymer bead comprising a core comprising green quantum dots and a shell comprising KSF phosphor particles.

**[0021]** FIG. 5 is a cross-sectional view of an LED comprising an LED chip and an LED cup filled with KSF phosphor and green quantum dot polymer beads.

**[0022]** FIG. 6 is a cross-sectional view of an LED comprising an LED chip and an LED cup filled with KSF phosphor, and a remote film comprising green quantum dots.

**[0025]** FIG. 9 is a cross-sectional view of an LED comprising an LED chip and an LED cup filled with polymer beads comprising KSF phosphor, and a remote film comprising green quantum dots.

**[0026]** FIG. 10 is a cross-sectional view of an LED and a remote film comprising polymer beads comprising KSF phosphor and polymer beads comprising green quantum dots.

**[0027]** FIG. 11 is a cross-sectional view of an LED and a remote film comprising polymer beads comprising KSF phosphor and green quantum dots.

**[0028]** FIG. 12 is a cross-sectional view of an LED and a remote film comprising KSF phosphor particles and green quantum dots.

**[0029]** FIG. 13 is a simulated spectrum of a film containing green-emitting quantum dots and KSF phosphor.

**[0030]** FIG. 14 is a simulated spectrum of a film containing green-emitting quantum dots and red-emitting quantum dots.

**[0031]** FIG. 15 is a normalized emission spectrum of polymer beads containing KSF phosphor.

**[0032]** FIG. 16 is a normalized emission spectrum of polymer beads containing green-emitting quantum dots.

**[0033]** FIG. 17 is a normalized emission spectrum of beads containing both green-emitting quantum dots and KSF phosphor.

**[0034]** FIG. 18 is an exploded view of a liquid crystal display (LCD) equipped with a quantum dot backlight unit.

#### DETAILED DESCRIPTION OF THE INVENTION

**[0035]** A blue-emitting LED may be combined with green-emitting QDs, and red-emitting KSF phosphor to produce white light with a wide color gamut in such a way that the optical properties of the QDs are not adversely affected by exposure to heat.

**[0036]** In a simulation, a combination of green-emitting quantum dots with KSF phosphor was shown to provide similar color performance relative to both the DCI and Rec. 2020 standards as compared to a combination of green-emitting and red-emitting quantum dots. However, the combination of green-emitting quantum dots and KSF phosphor was photometrically brighter. The simulation data is shown in Table 1.

TABLE 1

Green PL,	Green FWHM,	Red PL,	Red FWHM,		DCI Coverage		Rec2020 Coverage	
nm	nm	nm	nm	Lum	CIE 1931	CIE1976	CIE 1931	CIE1976
536	42		KSF	11.30	90.9%	96.2%	70.5%	78.8%
536	38		KSF	11.33	91.2%	96.2%	71.4%	79.7%
536	42	640	60	9.08	90.9%	96.0%	68.7%	77.5%
536	38	640	60	9.07	91.2%	96.1%	69.6%	78.3%
536	38	635	55	9.64	91.3%	96.1%	69.2%	77.5%
536	38	645	55	8.44	91.2%	96.1%	71.6%	81.1%

**[0023]** FIG. 7 is a cross-sectional view of an LED comprising an LED chip and an LED cup filled with KSF phosphor polymer beads and green quantum dot polymer beads.

**[0024]** FIG. 8 is a cross-sectional view of an LED comprising an LED chip and an LED cup filled with polymer beads comprising KSF phosphor and green quantum dots.

**[0037]** A simulated spectrum of a film containing green-emitting quantum dots and KSF phosphor [excited with blue light?] is shown in FIG. 13 and a simulated spectrum of a film containing green-emitting quantum dots and red-emitting quantum dots is shown in FIG. 14. Also shown in FIGS. 13 and 14 are the transmission spectra of the red, green, and blue color filters used in a typical LCD television set.

**[0038]** In certain embodiments, the QDs and/or the KSF phosphor are incorporated into polymer beads. The incorporation of QDs into polymer beads is described in U.S. Pat. No. 7,544,725 “Labelled Beads;” U.S. Pat. No. 8,859,442 “Encapsulated Nanoparticles;” U.S. Pat. No. 8,847,197 “Semiconductor Nanoparticle-Based Materials;” and U.S. Pat. No. 8,957,401 “Semiconductor Nanoparticle-Based Materials;” and in published patent applications: U.S. Pub. No. 2014/0264192 “Preparation of Quantum Dot Beads Having a Silyl Surface Shell” and U.S. Pub. No. 2014/0264196 “Multi-Layer-Coated Quantum Dot Beads,” the disclosures of which are hereby incorporated by reference in their entireties. Similar techniques may be used to incorporate phosphor particles into polymer beads. The incorporation of phosphor particles, such as KSF phosphor particles, is described in U.S. Pat. No. 7,323,696 “Phosphor Particle Coded Beads.”

**[0039]** In some embodiments, green-emitting QDs and red-emitting KSF phosphor may be incorporated into the same bead, as illustrated in FIG. 1. Incorporating the QDs and the KSF phosphor into the same bead may be advantageous for ease of processing.

**[0040]** In alternative embodiments, green-emitting QDs and red-emitting KSF phosphor may be incorporated into separate beads, as illustrated in FIG. 2. Incorporating the QDs and the KSF phosphor into separate beads can offer an effective means of color mixing, since suitable ratios of green- and red-emitting beads may be combined to produce a desired white point in the CIE 1931 color space.

**[0041]** In yet other embodiments, green-emitting QDs and red-emitting KSF phosphor may be incorporated into a core/shell bead—i.e., a bead having a central core comprising a first material surrounded by a shell comprising a second material. KSF phosphor may be incorporated into the core of the bead and green-emitting QDs into the shell of the bead, as shown in FIG. 3, or green-emitting QDs may be incorporated into the core of the bead and KSF phosphor into the shell of the bead, as shown in FIG. 4.

**[0042]** In some embodiments, the QDs and/or the KSF phosphor are deposited into the cup portion of an LED package. Techniques to deposit QDs and phosphor particles into LED cups are known in the art and can include combining the particles with an optically-transparent resin, depositing the resin in an LED cup, and allowing the resin to cure. For example, the incorporation of QDs into an acrylate resin and subsequent deposition into LED cups is described in U.S. Pub. No. 2013/0105839 “Acrylate Resin for QD-LED” the disclosure of which is hereby incorporated by reference in its entirety. Examples of suitable resins include, but are not restricted to, acrylates, silicones and epoxies.

**[0043]** In some embodiments, the QDs and/or the KSF phosphor are incorporated into a film that is positioned remotely from the LED chip. This is particularly advantageous for separating the QDs from the LED chip, which prevents thermal degradation of the QDs due to heat emitted by the LED. Techniques to incorporate QDs into a resin matrix are known in the prior art, for example, as disclosed in U.S. Patent Pub. No. 2015/0047765 “Quantum Dot Films Utilizing Multi-Phase Resins;” U.S. Patent Pub. No. 2015/0275078 “Quantum Dot Compositions;” and U.S. Patent Pub. No. 2015/0255690 “Methods for Fabricating High

Quality Quantum Dot Polymer Films.” Similar techniques may be used to incorporate KSF phosphor particles into resin matrices.

**[0044]** In some embodiments, the QDs and/or the KSF phosphor are first incorporated into polymer beads, which are subsequently incorporated into a polymer film. The formation of a polymer film incorporating QD beads is described in U.S. Patent Pub. No. 2013/0075692 “Semiconductor Nanoparticle-Based Light-Emitting Materials which is hereby incorporated by reference in its entirety.

**[0045]** In alternative embodiments, the QDs and/or the KSF phosphor are incorporated directly into a polymer or resin matrix and processed into a film.

**[0046]** In one particular embodiment, illustrated in FIG. 5, a white-emitting LED comprises a blue LED chip and an LED cup filled with KSF phosphor and green-emitting quantum dot polymer beads. By incorporating the QDs into beads, the QDs are protected from thermal degradation resulting from heat generated by the LED chip.

**[0047]** In another embodiment, as shown in FIG. 6, a white-emitting LED comprises a blue-emitting LED chip, an LED cup filled with red-emitting KSF phosphor, and a remote polymer film comprising green-emitting QDs. The remote location of the QD film, such that it is not in direct contact with the LED chip, protects the QDs from thermal degradation by the LED.

**[0048]** In a further embodiment, as shown in FIG. 7, a white-emitting LED comprises a blue-emitting LED chip and an LED cup filled with red-emitting KSF phosphor polymer beads and green-emitting QD polymer beads.

**[0049]** In a further embodiment, illustrated in FIG. 8, a white-emitting LED comprises a blue-emitting LED chip and an LED cup filled with polymer beads comprising red-emitting KSF phosphor and green-emitting QDs. The KSF phosphor and QDs may be randomly distributed throughout the beads, as illustrated in FIG. 1, or may be formed into core/shell beads, as shown in FIGS. 3 and 4.

**[0050]** In another embodiment, as shown in FIG. 9, a white-emitting LED comprises a blue-emitting LED chip, an LED cup filled with polymer beads comprising red-emitting KSF phosphor, and a “remote film” comprising green-emitting quantum dots—i.e., a film physically separated from the LED package.

**[0051]** In a further embodiment, as shown in FIG. 10, a white-emitting LED comprises a blue-emitting LED chip, and a remote polymer film comprising red-emitting KSF phosphor contained in polymer beads and polymer beads comprising green-emitting QDs.

**[0052]** In a further embodiment, illustrated in FIG. 11, a white-emitting LED comprises a blue-emitting LED chip, and a remote polymer film comprising polymer beads comprising red-emitting KSF phosphor and green-emitting QDs. The KSF phosphor and QDs may be randomly distributed throughout the beads, as shown in FIG. 1, or may be formed into core/shell beads, as shown in FIGS. 3 and 4.

**[0053]** In a further embodiment, as shown in FIG. 12, a white-emitting LED comprises a blue-emitting LED chip, and a remote polymer film comprising red-emitting KSF phosphor particles and green-emitting QDs.

**[0054]** In alternative embodiments, another narrowband phosphor may be substituted for the KSF phosphor.

**[0055]** The invention has particular application in the backlight units used in liquid crystal displays. A liquid crystal display is an electronically modulated optical device

made up of any number of segments controlling a layer of liquid crystals arrayed in front of a light source (backlight) or reflector to produce images in color or monochrome. A backlight is a form of illumination used in liquid crystal displays (LCDs). Because LCDs do not themselves produce light (unlike, for example, CRT displays and LED displays), they need an illumination source (ambient light or a special light source) to produce a visible image. Backlights may illuminate the LCD from the side or back of the display panel.

**[0056]** An exemplary QD-based backlight unit is shown in FIG. 18. The illustrated BLU includes a brightness enhancement film (BEF) and a liquid crystal matrix (LCM). The QD-containing layer is shown displaced laterally from its actual position in order to permit visualization of the LEDs. In an embodiment of the invention, the “QD” layer is a polymer film comprising green-emitting quantum dots and KSF phosphor. The quantum dots and/or the KSF phosphor may be contained within beads that provide protection from heat, oxygen and/or moisture.

#### EXAMPLES

**[0057]** Method for Making QD/Polymer- and KSF-Containing Beads

**[0058]** Preparation of Polyvinyl Alcohol (PVOH) Solution:

**[0059]** Aqueous PVOH solution was prepared by dissolving PVOH in distilled water and stirring overnight. For further dissolution of the undissolved PVOH part the whole solution was heated at 70° C. for 3-4 hr. For bead synthesis, the PVOH solution was filtered to remove any undissolved polyvinyl acetate and/or dust particles.

**[0060]** Standard Resin Preparation

**[0061]** General Procedure

**[0062]** First, the required amount of QD dot solution was transferred to a glass vial containing a stirring bar under an inert atmosphere. Toluene was removed from the QD dot solution using reduced pressure with continuous stirring. Once all traces of visible solvent were removed, the residue was heated to 40° C. for 45 minutes under vacuum to ensure that all traces of residual solvent were removed. The stock solution was prepared by adding degassed lauryl methacrylate (LMA) and the cross-linker trimethylolpropane trimethacrylate (TMPTM) to the degassed photoinitiator(s) and stirring in the dark to ensure complete dissolution of the photoinitiator(s). Then, the required amount of the stock solution was added to the dry QD residue under an inert atmosphere and in dark conditions. The entire resin solution was stirred overnight to ensure complete dispersion of the QDs.

**[0063]** Bead Synthesis

**[0064]** General Procedure

**[0065]** First, the required amount of TWEEN® 80 non-ionic, sorbitan ester surfactant [CRODA AMERICAS LLC, WILMINGTON DEL. 19801] was added to the reaction vessel followed by the required amount of PVOH solution and stirred for at least 30 minutes for complete dissolution of the surfactant into the PVOH solution. The whole solution mixture was degassed for a few hours by applying a vacuum/nitrogen cycle. After completion of the degassing procedure, the reaction vessel was placed inside a rig equipped with a four UV-LED head. Then, the required amount of QD resin solution was injected into the PVOH/surfactant solution under constant stirring. After a certain stirring time, the bead

polymerization was started by activating the UV light source for several minutes (depending on the reaction conditions). After the polymerization, the beads were washed twice with cold distilled water then once with a water/acetonitrile (50/50 volume ratio) mixture then twice with only acetonitrile. Usually, the beads were washed in a centrifuge machine. After washing, the beads were dried under vacuum for several hours or overnight.

**[0066]** A Typical Bead Synthesis was Carried out as Follows:

**[0067]** KSF Beads

**[0068]** First, 0.4 g of TWEEN 80 surfactant was added to 10 mL of a 4% PVOH solution and stirred for 30 minutes for complete dissolution of the surfactant into the PVOH solution and degassed for a few hours by applying a vacuum/nitrogen cycle. For KSF resin preparation, first the required amount of KSF was degassed and then the required amount of degassed LMA/TMPTM (1:0.154 volume ratio with 1% IRGACURE® 819 photo-initiator [BASF SE COMPANY CARL-BOSCH-STR. 38 LUDWIGSHAFEN, GERMANY 67056]) resin was added from the LMA/TMPTM stock solution. The KSF resin solution was stirred overnight under an inert atmosphere and in dark conditions. The next day, 0.5 mL of the KSF resin solution was injected into 10 mL of degassed PVOH/surfactant solution under constant stirring at 800 rpm with a cross magnetic stirrer bar and under a nitrogen atmosphere. After 10 minutes of stirring, bead polymerization was started by activating the UV light source for 10 minutes. The resulting beads were washed by the method described above and dried under vacuum for several hours.

**[0069]** Green QD Beads

**[0070]** First, 0.4 gram of TWEEN 80 surfactant was added to 10 mL of a 4% PVOH solution and stirred for 30 minutes for complete dissolution of the surfactant into the PVOH solution and degassed for a few hours by applying a vacuum/nitrogen cycle. For green QD resin preparation, first a QD solution was dried under vacuum. Then, 3 grams of degassed LMA/TMPTM (1/0.154 volume ratio with 1% IRGACURE 819) resin was added from the LMA/TMPTM stock solution and stirred overnight under an inert atmosphere and in dark conditions. The whole QD resin solution was stirred overnight to ensure complete dispersion of the QDs. 0.5 mL of the QD resin solution was injected the next day into 10 mL of the degassed PVOH/surfactant solution under constant stirring at 800 rpm with a cross magnetic stirrer bar and under an N<sub>2</sub> atmosphere. After 10 minutes of stirring, bead polymerization was started by activating the UV light source for 10 minutes. The resulting beads were washed by the method described above and dried under vacuum for several hours.

**[0071]** QD/KSF White Beads

**[0072]** First, 0.4 g TWEEN 80 surfactant was added to 10 mL of a 4% PVOH solution and stirred for 30 minutes to obtain complete dissolution of the surfactant into the PVOH solution and degassed for a few hours by applying a vacuum/nitrogen cycle. For QD/KSF white bead synthesis, first KSF and green QD resin were prepared separately following the same procedure described above. Then, a quantity of KSF and green QD resin were mixed together for 2 hours to produce “white” KSF/QD beads—i.e., beads that provide white light when excited by and mixed with blue light.

**[0073]** These and other advantages of the present invention will be apparent to those skilled in the art from the foregoing specification. Accordingly, it is to be recognized

by those skilled in the art that changes or modifications may be made to the above-described embodiments without departing from the broad inventive concepts of the invention. It is to be understood that this invention is not limited to the particular embodiments described herein and that various changes and modifications may be made without departing from the scope of the present invention as literally and equivalently covered by the following claims.

What is claimed is:

1. A light-emitting device comprising:
  - a source of electromagnetic radiation in the blue portion of the spectrum;
  - one or more particles of  $\text{K}_2\text{SiF}_6\text{Mn}^{4+}$  (KSF) phosphor optically coupled to the source of electromagnetic radiation; and
  - a plurality of quantum dots optically coupled to the source of electromagnetic radiation.
2. The light-emitting device recited in claim 1 wherein the source of electromagnetic radiation is a blue light emitting diode (LED).
3. The light-emitting device recited in claim 2 wherein the one or more particles of KSF phosphor are contained within at least one polymer bead.
4. The light-emitting device recited in claim 2 wherein the quantum dots are contained within at least one polymer bead.
5. The light-emitting device recited in claim 2 wherein the quantum dots are contained within at least one first type polymer bead and the one or more particles of KSF phosphor are contained within at least one second type polymer bead.
6. The light-emitting device recited in claim 2 wherein the quantum dots are contained within a plurality of polymer beads, each polymer bead comprising one or more particles of KSF phosphor and a plurality of quantum dots.
7. The light-emitting device recited in claim 6 wherein the beads comprise a polymer selected from the group consisting of acrylates, silicones, and epoxies.
8. The light-emitting device recited in claim 2 wherein the quantum dots are green-emitting quantum dots.
9. The light-emitting device recited in claim 2 wherein the quantum dots are heavy-metal-free quantum dots.
10. The light-emitting device recited in claim 4 wherein the LED is housed in a cup-type package and the KSF phosphor is in a polymer matrix and the KSF phosphor in the polymer matrix and the at least one polymer bead with quantum dots are contained within the cup.
11. The light-emitting device recited in claim 2 wherein the LED is housed in a cup-type package, the KSF phosphor is contained within the cup, and the plurality of quantum dots are in a film remote from the LED package.
12. The light-emitting device recited in claim 5 wherein the LED is housed in a cup-type package, and the one first type polymer bead and one second type polymer bead are contained in a matrix in the cup of the LED package.
13. The light-emitting device recited in claim 6 wherein the LED is housed in a cup-type package, and the polymer beads comprising one or more particles of KSF phosphor and a plurality of quantum dots are contained in the cup of the LED package.
14. The light-emitting device recited in claim 3 wherein the LED is housed in a cup-type package, and the polymer beads comprising one or more particles of KSF phosphor are contained in the cup of the LED package and the plurality of quantum dots are in a film remote from the LED package.
15. The light-emitting device recited in claim 5 wherein the quantum dots are contained within the at least one first type polymer bead and the one or more particles of KSF phosphor contained within at least one second type polymer bead are in a film remote from the LED.
16. The light-emitting device recited in claim 6 wherein the plurality of polymer beads comprising one or more particles of KSF phosphor and a plurality of quantum dots are in a film remote from the LED.
17. The light-emitting device recited in claim 2 wherein the one or more particles of KSF phosphor and the plurality of quantum dots are both contained in a film remote from the LED.
18. A bead comprising an optically-transparent resin and a plurality of KSF phosphor particles embedded in the resin.
19. The bead recited in claim 18 further comprising:
  - a plurality of quantum dots embedded in the resin.
20. A bead comprising a central core portion surrounded by a shell portion comprising an optically-transparent resin and a plurality of KSF phosphor particles embedded in the shell portion resin.
21. The bead recited in claim 20 further comprising a plurality of quantum dots in the core portion.
22. A bead comprising a central core portion comprising an optically-transparent resin surrounded by a shell portion and a plurality of KSF phosphor particles embedded in the core portion resin.
23. The bead recited in claim 22 further comprising a plurality of quantum dots in the shell portion.
24. A method for generating white light comprising:
  - providing a source of electromagnetic radiation in the blue portion of the spectrum;
  - providing one or more particles of  $\text{K}_2\text{SiF}_6\text{Mn}^{4+}$  (KSF) phosphor optically coupled to the source of electromagnetic radiation; and
  - providing a plurality of green-emitting quantum dots optically coupled to the source of electromagnetic radiation.
25. The method recited in claim 24 wherein the source of electromagnetic radiation is a blue light-emitting diode (LED).
26. A backlight unit for a liquid crystal display comprising:
  - a source of electromagnetic radiation in the blue portion of the spectrum;
  - a polymer film optically coupled to the source of electromagnetic radiation and containing one or more particles of  $\text{K}_2\text{SiF}_6\text{Mn}^{4+}$  (KSF) phosphor and a plurality of quantum dots.
27. The backlight unit recited in claim 26 wherein the source of electromagnetic radiation is a blue light emitting diode (LED).
28. The backlight unit recited in claim 26 wherein the one or more particles of KSF phosphor are contained within at least one polymer bead.
29. The backlight unit recited in claim 26 wherein the quantum dots are contained within at least one polymer bead.
30. The backlight unit recited in claim 26 wherein the quantum dots are contained within at least one first type polymer bead and the one or more particles of KSF phosphor are contained within at least one second type polymer bead.
31. The backlight unit recited in claim 26 wherein the quantum dots are contained within a plurality of polymer

beads, each polymer bead comprising one or more particles of KSF phosphor and a plurality of quantum dots.

**32.** The backlight unit recited in claim **31** wherein the beads comprise a polymer selected from the group consisting of acrylates, silicones, and epoxies.

**33.** The backlight unit recited in claim **26** wherein the quantum dots are green-emitting quantum dots.

**34.** The backlight unit recited in claim **26** wherein the quantum dots are heavy-metal-free quantum dots.

\* \* \* \* \*