



(22) Date de dépôt/Filing Date: 2003/11/12
(41) Mise à la disp. pub./Open to Public Insp.: 2004/05/18
(45) Date de délivrance/Issue Date: 2006/10/03
(30) Priorité/Priority: 2002/11/18 (DE102 53 712.7)

(51) Cl.Int./Int.Cl. *C21C 5/44* (2006.01),
C08K 3/08 (2006.01), *C08K 3/04* (2006.01),
C08K 3/22 (2006.01), *C09K 3/00* (2006.01),
F27D 1/16 (2006.01)

(72) Inventeurs/Inventors:
JANSEN, HELGE, DE;
DALDRUP, HEINRICH GROSSE, DE

(73) Propriétaire/Owner:
REFRATECHNIK HOLDING GMBH, DE

(74) Agent: BORDEN LADNER GERVAIS LLP

(54) Titre : LOT DE MATERIEL DE REPARATION REFRACTAIRE
(54) Title: REFRACTORY REPAIR MATERIAL BATCH

(57) **Abrégé/Abstract:**

The invention relates to a refractory repair batch material, which includes a refractory, in particular basic resistor component in granule form and a binder system, the binder system containing at least one hard bitumen component in granule form, at least one ignitable metal powder and at least one combustible mineral oil.



Abstract

The invention relates to a refractory repair batch material, which includes a refractory, in particular basic resistor component in granule form and a binder system, the binder system containing at least one hard bitumen component in granule form, at least one ignitable metal powder and at least one combustible mineral oil.

5

Refractory repair material batch

- 10 The invention relates to a refractory repair material batch for repairing worn areas in refractory linings, in particular in metallurgical furnaces or vessels, e.g. in converters.
- 15 Repair materials of this type are also known as hot-repair materials, since they are introduced into the hot furnace or into the hot vessel. They are used to repair what are known as pre-worn locations, i.e. locations in the refractory lining which are
- 20 experiencing spalling or flaking which does not yet require complete removal and replacement of the refractory lining. In such applications, depending on the nature and structure of the batch, materials are, for example, pneumatically sprayed or cast or poured or
- 25 introduced by centrifuging. Spraying allows accurate and controlled application to the locations which are to be repaired, and consequently this is the preferred method.
- 30 It is known to spray basic hot-repair materials, in particular including basic linings, which are made up with water and generally do not contain any carbon. Moreover, basic hot-repair materials which may contain carbon and are anhydrous are also known. However, these
- 35 repair materials cannot be sprayed.

The water in the hot-repair materials leads to very substantial thermal shocks at the repair locations and

- 2 -

therefore to the formation of cracks which adversely affect the success of the repair. Moreover, it is only possible to achieve relatively low bonding forces between repair material and repair location, and consequently the wear resistance at the repair location is reduced. Moreover, the water attacks the basic material of the refractory lining, which may be destroyed by hydration.

10 Although carbon-containing hot-repair materials do not have the abovementioned drawbacks of the water-containing hot-repair materials, they cannot be sprayed.

15 An embodiment of the invention may provide an anhydrous hot-repair material which is non-toxic and is not a problem in terms of health and safety at work and which can be made in free-flowing or trickling form and can therefore be sprayed, cast, poured and centrifuged, ensures very good adhesion and wear resistance and does not cause any harmful thermal shocks.

According to an aspect of the present invention, there is provided a refractory repair batch material, for repairing lining material, said repair material including a refractory in granule form and a binder system, wherein the binder system contains at least one hard bitumen component in granule form, at least one ignitable metal powder and at least one combustible mineral oil. Advantageous refinements of the invention are given in the subclaims.

- 2a -

According to the invention, the hot-repair material includes at least one resistor component, in the form of a refractory material which is known per se, such as MgO, dolomite, Al_2O_3 , MgAl_2O_4 , SiO_2 , ZrO_2 , chromium
5 oxide. This refractory material is selected as a function of the lining material which is to be repaired and is preferably used in a grain size which is matched to the grain size of the lining material of the furnace or vessel.

10

The generally free-flowing resistor component in granule form is embedded in a multifunctional binder system comprising at least one hard bitumen component

in granule form, at least one metal powder which is ignitable at the temperature of use and at least one mineral oil which is combustible at the temperature of use.

5

The binder system binds together the grains of the resistor component in the manner of a binder, so that it is possible to produce a processable hot-repair material of controllable consistency. The consistency
10 can be set in such a manner that the material can either be sprayed or cast or poured or can flow freely or can be centrifuged; accordingly, to this extent the material is technologically universally applicable.

15 The binder system is self-igniting and ignites at the latest when it comes into contact with the hot repair location; moreover, the binder system reacts exothermically. During application, the binder system first of all becomes sticky and adheres or embeds
20 itself very successfully at the repair location by penetrating into the pores or recesses, so that even steep to vertical or overhanging wall regions which have become worn can be repaired.

25 Moreover, as a result of coking of the bitumen, the binder system forms a carbon matrix which binds the resistor component by means of the carbon binding mechanism which is known per se, with the matrix carbon
- as is likewise known per se - reducing the wettability
30 of the repair material in situ with respect to the metallurgical material in the furnace or vessel after it has been applied in the desired way.

The metal powder of the binder system should ignite at
35 approximately 500°C and cause the mineral oil, which serves as an energy carrier and is in particular a heavy oil, for example flux oil or used oil, to burn, so that the hard bitumen melts, producing the required mobility of the repair material in the hot state, and

- 4 -

cokes and thereby ensures the above-described properties which are desired in accordance with the invention.

5 The finely particulate metal powder, which is preferably used in a fineness of 90% by weight < 45 μm , is oxidized and the metal oxides induce sintering reactions between the resistor grains of the repair material and also between the resistor grains of the
10 repair material and the lining material, so that very good adhesion is produced by ceramic bonding too.

The mineral oil, which is preferably a flux oil, serves both as an energy carrier and to bind dust, so that the
15 material does not form dust when it is being made up and can be handled very easily during repair work. It is also used to set the desired consistency of the material as a function of the particular application technique.

20

For example, slightly more flux oil is used for a material which is to be sprayed than for a free-flowing material.

25 To improve the carbon binding of the material, it is preferable to add at least one further carbon carrier, such as graphite, e.g. flake graphite, or carbon black.

The repair material according to the invention is
30 therefore distinguished by carbon binding and ceramic binding and thereby ensures a particularly high wear resistance. It can easily be matched to the lining material by selecting the resistor component and can be used universally on account of the choice of
35 consistency. Thermal shocks are not produced. The repair materials according to the invention can be sprayed using standard spraying machines.

It is preferable to use the following batches for the

- 5 -

hot-repair material according to the invention:

5 45 - 90% by weight,
in particular 67 - 80% by weight of resistor
component,
e.g. MgO sinter,

10 1.5 - 25% by weight,
in particular 4 - 10% by weight of metal powder,
e.g. Si powder,

15 3.5 - 20% by weight,
in particular 10 - 15% by weight of hard bitumen
granules,

5 - 10% by weight,
in particular 6 - 8% by weight of mineral oil,
e.g. flux oil.

20 According to the invention, first of all the dry
components of the hot-repair material batch, such as
resistor component, hard bitumen, metal powder and, if
used, the further carbon carrier components, which may
be added in an amount of up to 6% by weight, are mixed
25 in a positive mixer and then the mineral oil is added.
The material is then packaged in sacks and can then be
delivered ready for processing.

30 By way of example, a material comprising the following
constituents was mixed in a positive mixer using the
process according to the invention:

35 70% by weight of MgO sinter,
4% by weight of flake graphite,
6% by weight of Si powder,
13% by weight of hard bitumen granules,
7% by weight of flux oil.

This repair material was sprayed on site in a

- 6 -

steelworks onto a pre-worn location which was to be repaired in the converter mouth of a converter using an existing rotor-spraying machine. The repair location was still intact even after 30 batch changes. By contrast, the known repair materials previously used in this steelworks were only able to withstand up to a maximum of 15 batches.

CLAIMS:

1. A refractory repair batch material, for repairing lining material, said repair material including a refractory in granule form and a binder system, wherein the binder system contains at least one hard bitumen component in granule form, at least one ignitable metal powder and at least one combustible mineral oil.
2. The repair material as claimed in claim 1, wherein the refractory is a basic resistor component.
3. The repair material as claimed in claim 2, wherein the resistor component is MgO and/or dolomite and/or Al_2O_3 and/or MgAl_2O_4 and/or SiO_2 and/or ZrO_2 and/or chromium oxide.
4. The repair material as claimed in claim 2 or 3, wherein the resistor component is present in a grain size which corresponds to the grain size of the lining material which is to be repaired.
5. The repair material as claimed in any one of claims 1 to 4, which has a consistency which can be sprayed or cast or poured or is free-flowing or can be centrifuged.
6. The repair material as claimed in any one of claims 1 to 5, which reacts in a self-igniting manner at the temperatures of use.
7. The repair material as claimed in any one of claims 1 to 6, which reacts exothermically at temperatures of use.

-8-

8. The repair material as claimed in any one of claims 1 to 7, which forms a carbon binding at temperatures of use.
9. The repair material as claimed in any one of claims 1 to 8, which forms a ceramic binding at temperatures of use.
10. The repair material as claimed in any one of claims 1 to 9, wherein the metal powder ignites at approximately 500°C.
11. The repair material as claimed in any one of claims 1 to 10, wherein the mineral oil burns at temperatures of use.
12. The repair material as claimed in any one of claims 1 to 11, wherein the mineral oil is heavy oil.
13. The repair material as claimed in any one of claims 1 to 12, wherein the hard bitumen melts and cokes, form a carbon binding, at temperatures of use.
14. The repair material as claimed in any one of claims 1 to 13, wherein the metal powder oxidizes and brings about sintering reactions between the refractory grains and also between the refractory grains and the lining material.
15. The repair material as claimed in any one of claims 1 to 14, wherein the metal powder has a fineness of 90% by weight < 45 μm .
16. The repair material as claimed in any one of claims 1 to 15, which contains at least one further carbon carrier.
17. The repair material as claimed in claim 16, wherein the at least one further carbon carrier is graphite.

-9-

18. The repair material as claimed in any one of claims 1 to 17, which has the following compositions:

45 - 90%

by weight of refractory,

1.5 - 25%

by weight of metal powder,

3.5 - 20%

by weight of hard bitumen granules,

5 - 10%

by weight of mineral oil.

19. The repair material as claimed in claim 18, wherein 67-80% by weight of refractory is present.

20. The repair material as claimed in claim 18 or 19, wherein 4-10% of by weight of metal powder is present.

21. The repair material as claimed in any one of claims 18 to 20, wherein 10-15% by weight of hard bitumen granules is present.

22. The repair material as claimed in any one of claims 18 to 21, wherein 6-8% by weight of mineral oil is present.

23. A process for producing a refractory repair batch material as claimed in any one of claims 1 to 22, wherein the dry components, comprising refractory, hard bitumen, metal powder and, if used, the further carbon carrier, are mixed in a positive mixer and then the mineral oil is added.

24. The process as claimed in claim 23, wherein the material is packaged in sacks.

-10-

25. The repair material as claimed in claim 12, wherein the heavy oil is flux oil.
26. The repair material as claimed in claim 12, wherein the heavy oil is used oil.
27. The repair material as claimed in claim 17, wherein the graphite is flake graphite in amounts of up to 6% by weight.
28. The repair material as claimed in claim 17, wherein the graphite is carbon black in amounts of up to 6% by weight.
29. The repair material as claimed in any one of claims 18 to 22, wherein the refractory is MgO sinter.
30. The repair material as claimed in any one of claims 18 to 22 and 29, wherein the metal powder is Si powder.
31. The repair material as claimed in any one of claims 18 to 22, 29 and 30, wherein the mineral oil is flux oil.