(19) World Intellectual Property Organization

International Bureau



(43) International Publication Date 6 July 2006 (06.07.2006)

PCT

(10) International Publication Number WO 2006/071860 A1

(51) International Patent Classification:

C08G 69/44 (2006.01) A61L 31/10 (2006.01) A61L 31/16 (2006.01) A61K 47/48 (2006.01)

(21) International Application Number:

PCT/US2005/047065

(22) International Filing Date:

22 December 2005 (22.12.2005)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

11/023,837

27 December 2004 (27.12.2004) US

(71) Applicant (for all designated States except US): AD-VANCED CARDIOVASCULAR SYSTEMS, INC. [US/US]; 3200 Lakeside Drive, Santa Clara, CA 95054 (US).

- (72) Inventor; and
- (75) Inventor/Applicant (for US only): HOSSAINY, Syed Faiyaz Ahmed [US/US]; 34325 Tupelo Street, Fremont, California 94555 (US).
- (74) Agent: KERRIGAN, Cameron K.; Squire, Sanders and Dempsey L.L.P., 1 Maritime Plaza, Suite 300, San Francisco, California 94111-3492, (US).

- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: POLY(ESTER AMIDE) BLOCK COPOLYMERS

(57) Abstract: Provided herein is a copolymer that includes a soft block (A) that contains poly(ester amide) (PEA) and a hard block (B). The copolymer can be any of AB, ABA or BAB type block copolymers. By varying the relative amount of the PEA block and the hard block, one can obtain a copolymer with a Tg for mechanical integrity in drug-delivery stent applications. The copolymer can be used alone or optionally in combination with a biobeneficial material and/or a biocompatible polymer to form an implantable device or a coating on an implantable device. When the copolymer is used in combination with a biobeneficial material, the copolymer and the biobeneficial material can be co-deposited or applied in sequence during the coating process. A coating formed of the copolymer may also include a bioactive agent. The implantable device can be implanted in a patient to treat, prevent, or ameliorate a disorder such as atherosclerosis, thrombosis, restenosis, hemorrhage, vascular dissection or perforation, vascular aneurysm, vulnerable plaque, chronic total occlusion, claudication, anastomotic proliferation for vein and artificial grafts, bile duct obstruction, ureter obstruction, and/or tumor obstruction.



POLY(ESTER AMIDE) BLOCK COPOLYMERS

Syed Faiyaz Ahmed Hossainy

5 BACKGROUND OF THE INVENTION

Field of the Invention

This invention generally relates to poly(ester amide) block copolymers useful for forming a bioabsorbable device such as a stent or for coating an implantable device such as a drug-delivery stent.

10 Description of the Background

15

20

Percutaneous transluminal coronary angioplasty (PTCA) is a procedure for treating heart disease. A catheter assembly having a balloon portion is introduced percutaneously into the cardiovascular system of a patient via the brachial or femoral artery. The catheter assembly is advanced through the coronary vasculature until the balloon portion is positioned across the occlusive lesion. Once in position across the lesion, the balloon is inflated to a predetermined size to radially compress against the atherosclerotic plaque of the lesion to remodel the lumen wall. The balloon is then deflated to a smaller profile to allow the catheter to be withdrawn from the patient's vasculature.

A problem associated with the above procedure includes formation of intimal flaps or torn arterial linings which can collapse and occlude the conduit after the balloon is deflated. Moreover, thrombosis and restenosis of the artery may develop over several months after the procedure, which may require another angioplasty

procedure or a surgical by-pass operation. To reduce the partial or total occlusion of the artery by the collapse of arterial lining and to reduce the chance of the development of thrombosis and restenosis, a stent is implanted in the lumen to maintain vascular patency.

5

10

15

20

Stents are used not only as a mechanical intervention but also as a vehicle for providing pharmacological therapy. As a mechanical intervention, stents act as scaffoldings, functioning to physically hold open and, if desired, to expand the wall of the passageway. Typically, stents are capable of being compressed, so that they can be inserted through small vessels via catheters, and then expanded to a larger diameter once they are at the desired location. Examples in patent literature disclosing stents which have been applied in PTCA procedures include stents illustrated in U.S. Patent No. 4,733,665 issued to Palmaz, U.S. Patent No. 4,800,882 issued to Gianturco, and U.S. Patent No. 4,886,062 issued to Wiktor.

Pharmacological therapy can be achieved by medicating the stents. Medicated stents provide for the local administration of a therapeutic substance at the diseased site. In order to provide an efficacious concentration to the treated site, systemic administration of such medication often produces adverse or toxic side effects for the patient. Local delivery is a preferred method of treatment in that smaller total levels of medication are administered in comparison to systemic dosages, but are concentrated at a specific site. Local delivery thus produces fewer side effects and achieves more favorable results. One proposed method for medicating stents involves the use of a polymeric carrier coated onto the surface of a stent.

Accordingly, there is a need to have stent coatings with improved biological compatibility and improved mechanical properties.

The embodiments of the present invention provide for polymers and combination of polymers for coating stents and other implantable medical devices, where the polymers forming the coatings are biologically compatible and absorbable.

SUMMARY OF THE INVENTION

5

10

In an aspect of the present invention, provided herein is a copolymer that includes a soft block (A) which can be a poly(ester amide) (PEA) block (A) and another block (B). The copolymer can be any of AB, ABA, and BAB type block copolymer. By varying the relative amount of the soft block (e.g. PEA block) and the hard block, one can obtain a copolymer with a T_g for mechanical integrity in drugdelivery stent applications.

The copolymer can be used alone or optionally in combination with a

15 biobeneficial material and/or a biocompatible polymer to form a coating on an

implantable device or to form the implantable device itself. When the copolymer is

used in combination with a biobeneficial material, the copolymer and the biobeneficial

material can be co-deposited or applied in sequence during the coating process.

The implantable device or the coating may also include a bioactive agent.

20 Exemplary bioactive agents include, but are not limited to, paclitaxel, docetaxel, estradiol, nitric oxide donors, super oxide dismutases, super oxide dismutases mimics, 4-amino-2,2,6,6-tetramethylpiperidine-1-oxyl (4-amino-TEMPO), tacrolimus,

dexamethasone, rapamycin, rapamycin derivatives, 40-*O*-(2-hydroxy)ethyl-rapamycin (everolimus), 40-*O*-(3-hydroxy)propyl-rapamycin, 40-*O*-[2-(2-hydroxy)ethoxy]ethyl-rapamycin, and 40-*O*-tetrazole-rapamycin, ABT-578, clobetasol, prodrugs thereof, codrugs thereof, and combinations thereof. The implantable device can be implanted in a patient to treat or prevent a disorder such as atherosclerosis, thrombosis, restenosis, hemorrhage, vascular dissection or perforation, vascular aneurysm, vulnerable plaque, chronic total occlusion, claudication, anastomotic proliferation for vein and artificial grafts, bile duct obstruction, ureter obstruction, tumor obstruction, or combinations thereof.

10 DETAILED DESCRIPTION

5

15

20

Poly(ester amide) block copolymer

In one aspect of the present invention, provided herein is a copolymer that includes a soft block which can be a poly(ester amide) (PEA) block (A) and a hard block (B) derived from a biocompatible polymer. The copolymer can be any of AB, ABA, and BAB type block copolymer. By varying the relative amount of the soft block (e.g., a PEA block) and the hard block, one can obtain a copolymer with a glass transition temperature (Tg) for mechanical integrity in drug-delivery stent applications.

The terms "hard" and "soft" are relative terms and, as used herein, refer to mechanical strength and toughness of the block copolymer defined herein. The term "hard block" refers to the block that has a higher mechanical strength and toughness whereas the term "soft block" refers to the block that has a lower mechanical strength and toughness. Generally, the hard block in a block copolymer has a glass Tg higher

than the T_g of the soft block. However, the hard block in a block copolymer described herein may sometimes have a T_g approximately the same as or lower than the T_g of a soft block.

The copolymer can be used alone or optionally in combination with a biobeneficial material and/or a biocompatible polymer to form a coating on an implantable device or to form the implantable device itself. When the copolymer is used in combination with a biobeneficial material, the copolymer and the biobeneficial material can be co-deposited or applied in sequence during the coating process.

5

10

15

20

The implantable device or the coating may also include a bioactive agent. Exemplary bioactive agents include, but are not limited to, paclitaxel, docetaxel, estradiol, nitric oxide donors, super oxide dismutases, super oxide dismutases mimics, 4-amino-2,2,6,6-tetramethylpiperidine-1-oxyl (4-amino-TEMPO), tacrolimus, dexamethasone, rapamycin, rapamycin derivatives, 40-*O*-(2-hydroxy)ethyl-rapamycin (everolimus), 40-*O*-(3-hydroxy)propyl-rapamycin, 40-*O*-[2-(2-hydroxy)ethoxy]ethyl-rapamycin, and 40-*O*-tetrazole-rapamycin, ABT-578, clobetasol, prodrugs thereof, codrugs thereof, and combinations thereof. The implantable device can be implanted in a patient to treat or prevent a disorder such as atherosclerosis, thrombosis, restenosis, hemorrhage, vascular dissection or perforation, vascular aneurysm, vulnerable plaque, chronic total occlusion, claudication, anastomotic proliferation for vein and artificial grafts, bile duct obstruction, ureter obstruction, tumor obstruction, or combinations thereof.

A. Poly(ester amide) Block (A)

10

15

20

Poly(ester amide), as used herein, encompasses any polymer having both ester and amide groups in its backbone. In one embodiment, the PEA is formed of a diacid and another moiety having both amino and hydroxyl functionalities. One of such PEA is described in, e.g., U.S. Patent No. 6,503,538, B1. The diacid is preferably a C2-C12 diacid, aliphatic or with unsaturation. The amino acid can be, for example, glycine, valine, alanine, proline, glutamine, methionine, leucine, isoleucine, or phenylalanine. An optional second amino acid may be included. The second amino acid can be, for example, lysine, tyrosine, tryptophan, arginine, histidine, glutamic acid, aspartic acid, threonine, serine, or cysteine. The second amino acid may contain a side group to enable the attachment of pharmacologically active compounds or property modifiers. PEA polymers with various thermal properties can be readily prepared by varying these components during synthesis.

PEA can be made by condensation polymerization utilizing, among others, diamino subunits and dicarboxylic acids (Scheme I). In Scheme I, the dicarboxylic acids are converted to an active di-p-nitrophenyl derivative. As shown in Scheme I, when the dicarboxylic acid and the diamino subunits are used stoichiometrically, the PEA formed would have one terminal carboxylic acid group and one amino group. When the dicarboxylic acid and the diamino subunits are not used at a ratio of 1:1, the PEA thus formed can have end groups in favor of the carboxylic acid group, if the dicarboxylic acid subunit is used more than the diamino subunit, or in favor of the amino group, if the diamino subunit is used more than the dicarboxylic acid subunit.

Accordingly, the PEA molecule would have reactive carboxylic acid or amino end groups.

Scheme I

$$+ \frac{1}{12} \frac{1}{12}$$

The soft block can also be derived from PEA having another moiety attached thereto, e.g., poly(ethylene glycol) (PEG), 4-amino-2,2,6,6-tetramethylpiperidine-1-oxyl (4-amino-TEMPO), or a combination thereof. In some embodiments, the soft block can be PEA, PEA-PEG, PEA-4-amino-TEMPO, PEG, or a combination thereof.

B. Hard Block (B)

The hard blocks of the PEA block copolymer can be formed of a material having a higher Tg than PEA. In some embodiments, the material is one or more biocompatible polymer. Exemplary biocompatible polymers include, but are not limited to, poly(D,L-lactic acid) (PDLLA, polyglycolic acid (PGA), poly(D,L-lactic acid-co-glycolic acid) (PDLLG), glycerol-sebacic acid, polytyrosine carbonate,

polytyrosine, tyrosine oligomer, or tyrosine di-peptide, poly(3-hydroxybutyrate) (PHB), poly(3-hydroxybutyrate-co-3-hydroxyvalerate) (PHBV), poly(3-hydroxyvalerate) (PHV), polyphosphazene, or combinations thereof. The polymer forming the hard block may also include functional groups such as OH, NH₂, COOH, SH, positive or negative charge, SO₃H, SO₄H, halo groups or PEG.

In some embodiments, the hard block is a tyrosine di-peptide. An exemplary tyrosine di-peptide block has a structure of

5

In some embodiments, the tyrosine di-peptide block can be formed of racemic tyrosine.

This di-peptide structure is relatively rigid and can increase the T_g and the tensile modulus of the copolymer. In addition, the carboxyl group and the primary amine group on the block can conjugate other reactive moieties such as -COOH, -NH₂, aldehyde, keto, hydroxyl, thiol, acyl, and other moieties so as to allow the attachment of functional molecules such as a drug molecule for forming a prodrug, heparin for imparting anti-thrombonic properties to the copolymer, iodo or bromo containing molecules for imparting radioopacity to the copolymer, and other marker compounds

for diagnostic uses. The chemistry of forming a prodrug via an ester group, a Schiff base group or other groups that can release the drug molecule under *in vivo* conditions is described in U.S. application Serial No. 10/871,658. The chemistry of attaching heparin to a polymer is described in U.S. application Serial No. 10/857,141. The teachings of both U.S. application Serial Nos. 10/871,658 and 10/871,658 are incorporated herein by reference.

In some embodiments, the iodo or bromo compound can have a general formula X-Ar-R where X is I or Br and R is a reactive moiety. For example, the iodo or bromo compound can have a structure of

10

15

5

where X can be (1) an organic group R_1 , provided that R_1 has one or more halo groups such as iodo or bromo groups, (2) halo groups such as iodo or bromo groups, or (3) combinations thereof,

where R and R_1 taken independently can be any chemical grouping having one or more reactive groups capable of conjugating to the carboxyl group or amino group of the tyrosine di-peptide block, which can be, for example, carboxyl groups, aldehyde groups, ester, amino groups, alcohol, thiol, PEG, a leaving group such as tosylate or mesylate, and

where n is a positive integer such as 1, 2, or 3.

The tyrosine di-peptide block can be any structural derivative of the tyrosine di-peptide. For example, the tyrosine di-peptide can be desamine tyrosyl-tyrosine di-peptide, desamino tyrosyl-tyrosine hexyl ester (DTH), desamino tyrosyl-tyrosine palmityl ester (DTP), *n*-benzyloxycarbonyl-tyrosyl-tyrosine hexyl ester (z-TTH), or combinations thereof. Other tyrosine di-peptides are provided in Biomedical Polymers: Designed-to-degrade Systems, Shalaby W. Shalaby (Editor), 1994. Note, in z-TTH, the benzoyl protecxted group can be reacted to conjugate biobeneficial moieties.

5

10

15

20

In some embodiments, the tyrosine di-peptide can be randomly incorporated into a PEA polymer. The NH₂ and/or COOH groups on the tyrosine di-peptide can be used to conjugate the bromo or iodo compound, a biobeneficial moiety, and/or a bioactive agent described herein.

Biocompatible Polymer

The PEA block copolymer described herein can be used alone or in combination with a biocompatible polymer, optionally with biobeneficial material and/or a bioactive agent to form a bioabsorbable device such as stent or a coating on an implantable device such as a stent. The biocompatible polymer can be any biocompatible polymer known in the art, which can be biodegradable or nondegradable. Representative examples of polymers that can be used to coat an implantable device in accordance with the present invention include, but are not limited to, poly(ester amide), ethylene vinyl alcohol copolymer (commonly known by the generic name EVOH or by the trade name EVAL), poly(3-hydroxyvalerate),

poly(L-lactic acid), polycaprolactone, poly(lactide-co-glycolide), poly(3hydroxybutyrate), poly(3-hydroxybutyrate-co-3-hydroxyvalerate), polydioxanone, polyorthoester, polyanhydride, poly(glycolic acid), poly(D,L-lactic acid), poly(D,Llactide-co-glycolide) (PDLLAGA), poly(glycolic acid-co-trimethylene carbonate), polyphosphoester, polyphosphoester urethane, poly(amino acids), polycyanoacrylates, poly(trimethylene carbonate), poly(iminocarbonate), polyurethanes, polyphosphazenes, silicones, polyesters, polyolefins, polyisobutylene and ethylenealphaolefin copolymers, acrylic polymers and copolymers, vinyl halide polymers and copolymers, such as polyvinyl chloride, polyvinyl ethers, such as polyvinyl methyl ether; polyvinylidene halides, such as vinylidene fluoride based home or copolymer under the trade name SolefTM or KynarTM, for example, polyvinylidene fluoride (PVDF) or poly(vinylidene-co-hexafluoropropylene) (PVDF-co-HFP) and polyvinylidene chloride, polyacrylonitrile, polyvinyl ketones, polyvinyl aromatics, such as polystyrene, polyvinyl esters, such as polyvinyl acetate, copolymers of vinyl monomers with each other and olefins, such as ethylene-methyl methacrylate copolymers, acrylonitrile-styrene copolymers, ABS resins, and ethylene-vinyl acetate copolymers, polyamides, such as Nylon 66 and polycaprolactam, alkyd resins, polycarbonates, polyoxymethylenes, polyimides, polyethers, poly(glyceryl sebacate), poly(propylene fumarate), epoxy resins, polyurethanes, rayon, rayon-triacetate, cellulose acetate, cellulose butyrate, cellulose acetate butyrate, cellulose nitrate, cellulose propionate, cellulose ethers, carboxymethyl cellulose, or

5

10

15

20

combinations thereof.

agent, if included in the coating and/or if binding the bioactive agent to a substrate, which can be the surface of an implantable device or a coating thereon. Controlled release and delivery of bioactive agent using a polymeric carrier has been extensively researched in the past several decades (see, for example, Mathiowitz, Ed., Encyclopedia of Controlled Drug Delivery, C.H.I.P.S., 1999). For example, PLA based drug delivery systems have provided controlled release of many therapeutic drugs with various degrees of success (see, for example, U.S. Patent No. 5,861,387 to Labrie, et al.). The release rate of the bioactive agent can be controlled by, for example, selection of a particular type of biocompatible polymer, which can provide a desired release profile of the bioactive agent. The release profile of the bioactive agent can be further controlled by selecting the molecular weight of the biocompatible polymer and/or the ratio of the biocompatible polymer to the bioactive agent. One of ordinary skill in the art can readily select a carrier system using a biocompatible polymer to provide a controlled release of the bioactive agent.

5

10

15

20

A preferred biocompatible polymer is a polyester, such as one of PLA, PLGA, PGA, PHA, poly(3-hydroxybutyrate) (PHB), poly(3-hydroxybutyrate-co-3-hydroxyvalerate), poly((3-hydroxyvalerate), poly(3-hydroxyhexanoate), poly(4-hydroxybutyrate), poly(4-hydroxyvalerate), poly(4-hydroxyhexanoate), and a combination thereof, and polycaprolactone (PCL).

Bioactive Agents

5

10

15

20

The PEA copolymers disclosed herein can form a coating or a bioabsorbable device such as a bioabsorbable stent with one or more bioactive agents. These bioactive agents can be any therapeutic, prophylactic, or diagnostic agents. These agents can have anti-proliferative or anti-inflammmatory properties or can have other properties such as antineoplastic, antiplatelet, anti-coagulant, anti-fibrin, antithrombonic, antimitotic, antibiotic, antiallergic, antioxidant as well as cystostatic agents. Examples of suitable therapeutic and prophylactic agents include synthetic inorganic and organic compounds, proteins and peptides, polysaccharides and other sugars, lipids, and DNA and RNA nucleic acid sequences having therapeutic, prophylactic or diagnostic activities. Nucleic acid sequences include genes, antisense molecules which bind to complementary DNA to inhibit transcription, and ribozymes. Some other examples of other bioactive agents include antibodies, receptor ligands, enzymes, adhesion peptides, blood clotting factors, inhibitors or clot dissolving agents such as streptokinase and tissue plasminogen activator, antigens for immunization, hormones and growth factors, oligonucleotides such as antisense oligonucleotides and ribozymes and retroviral vectors for use in gene therapy. Examples of antiproliferative agents include rapamycin and its functional or structural derivatives, 40-O-(2-hydroxy)ethyl-rapamycin (everolimus), and its functional or structural derivatives, paclitaxel and its functional and structural derivatives. Examples of rapamycin derivatives include methyl rapamycin (ABT-578), 40-O-(3hydroxy)propyl-rapamycin, 40-O-[2-(2-hydroxy)ethoxy]ethyl-rapamycin, and 40-O-

tetrazole-rapamycin. Examples of paclitaxel derivatives include docetaxel. Examples of antineoplastics and/or antimitotics include methotrexate, azathioprine, vincristine, vinblastine, fluorouracil, doxorubicin hydrochloride (e.g. Adriamycin® from Pharmacia & Upjohn, Peapack N.J.), and mitomycin (e.g. Mutamycin® from Bristol-Myers Squibb Co., Stamford, Conn.). Examples of such antiplatelets, anticoagulants, 5 antifibrin, and antithrombins include sodium heparin, low molecular weight heparins, heparinoids, hirudin, argatroban, forskolin, vapiprost, prostacyclin and prostacyclin analogues, dextran, D-phe-pro-arg-chloromethylketone (synthetic antithrombin), dipyridamole, glycoprotein IIb/IIIa platelet membrane receptor antagonist antibody, recombinant hirudin, thrombin inhibitors such as Angiomax ä (Biogen, Inc., 10 Cambridge, Mass.), calcium channel blockers (such as nifedipine), colchicine, fibroblast growth factor (FGF) antagonists, fish oil (omega 3-fatty acid), histamine antagonists, lovastatin (an inhibitor of HMG-CoA reductase, a cholesterol lowering drug, brand name Mevacor® from Merck & Co., Inc., Whitehouse Station, NJ), monoclonal antibodies (such as those specific for Platelet-Derived Growth Factor 15 (PDGF) receptors), nitroprusside, phosphodiesterase inhibitors, prostaglandin inhibitors, suramin, serotonin blockers, steroids, thioprotease inhibitors, triazolopyrimidine (a PDGF antagonist), nitric oxide or nitric oxide donors, super oxide dismutases, super oxide dismutase mimetic, 4-amino-2,2,6,6tetramethylpiperidine-1-oxyl (4-amino-TEMPO), estradiol, anticancer agents, dietary 20 supplements such as various vitamins, and a combination thereof. Examples of anti-

inflammatory agents including steroidal and non-steroidal anti-inflammatory agents

include tacrolimus, dexamethasone, clobetasol, combinations thereof. Examples of such cytostatic substance include angiopeptin, angiotensin converting enzyme inhibitors such as captopril (e.g. Capoten® and Capozide® from Bristol-Myers Squibb Co., Stamford, Conn.), cilazapril or lisinopril (e.g. Prinivil® and Prinzide® from Merck & Co., Inc., Whitehouse Station, NJ). An example of an antiallergic agent is permirolast potassium. Other therapeutic substances or agents which may be appropriate include alpha-interferon, bioactive RGD, and genetically engineered epithelial cells. The foregoing substances can also be used in the form of prodrugs or co-drugs thereof. The foregoing substances are listed by way of example and are not meant to be limiting. Other active agents which are currently available or that may be developed in the future are equally applicable.

The dosage or concentration of the bioactive agent should be less than the level at which the bioactive agent produces toxic effects and greater than the level at which non-therapeutic results are obtained. The dosage or concentration of the bioactive agent can depend upon factors such as the particular circumstances of the patient, the nature of the trauma; the nature of the therapy desired, the time over which the ingredient administered resides at the vascular site, and if other active agents are employed, the nature and type of the substance or combination of substances. Therapeutic effective dosages can be determined empirically, for example by infusing vessels from suitable animal model systems and using immunohistochemical, fluorescent or electron microscopy methods to detect the agent

15

20

and its effects, or by conducting suitable in vitro studies. Standard pharmacological test procedures to determine dosages are understood by one of ordinary skill in the art.

Examples of Implantable Device

5

10

15

20

As used herein, an implantable device may be any suitable medical substrate that can be implanted in a human or veterinary patient. Examples of such implantable devices include self-expandable stents, balloon-expandable stents, stent-grafts, grafts (e.g., aortic grafts), artificial heart valves, cerebrospinal fluid shunts, pacemaker electrodes, and endocardial leads (e.g., FINELINE and ENDOTAK, available from Guidant Corporation, Santa Clara, CA). The underlying structure of the device can be of virtually any design. The device can be made of a metallic material or an alloy such as, but not limited to, cobalt chromium alloy (ELGILOY), stainless steel (316L), high nitrogen stainless steel, e.g., BIODUR 108, cobalt chrome alloy L-605, "MP35N," "MP20N," ELASTINITE (Nitinol), tantalum, nickel-titanium alloy, platinum-iridium alloy, gold, magnesium, or combinations thereof. "MP35N" and "MP20N" are trade names for alloys of cobalt, nickel, chromium and molybdenum available from Standard Press Steel Co., Jenkintown, PA. "MP35N" consists of 35% cobalt, 35% nickel, 20% chromium, and 10% molybdenum. "MP20N" consists of 50% cobalt, 20% nickel, 20% chromium, and 10% molybdenum. Devices made from bioabsorbable or biostable polymers could also be used with the embodiments of the present invention.

Method of Use

In accordance with embodiments of the invention, a coating of the various described embodiments can be formed on an implantable device or prosthesis, e.g., a stent. For coatings including one or more active agents, the agent will retain on the medical device such as a stent during delivery and expansion of the device, and released at a desired rate and for a predetermined duration of time at the site of implantation.

5

10

15

20

Preferably, the medical device is a stent. A stent described herein is useful for a variety of medical procedures, including, by way of example, treatment of obstructions caused by tumors in bile ducts, esophagus, trachea/bronchi and other biological passageways. A stent described herein is particularly useful for treating occluded regions of blood vessels caused by abnormal or inappropriate migration and proliferation of smooth muscle cells, thrombosis, and restenosis. Stents may be placed in a wide array of blood vessels, both arteries and veins. Representative examples of sites include the iliac, renal, and coronary arteries.

For implantation of a stent, an angiogram is first performed to determine the appropriate positioning for stent therapy. An angiogram is typically accomplished by injecting a radiopaque contrasting agent through a catheter inserted into an artery or vein as an x-ray is taken. A guidewire is then advanced through the lesion or proposed site of treatment. Over the guidewire is passed a delivery catheter which allows a stent in its collapsed configuration to be inserted into the passageway. The delivery catheter is inserted either percutaneously or by surgery into the femoral artery,

brachial artery, femoral vein, or brachial vein, and advanced into the appropriate blood vessel by steering the catheter through the vascular system under fluoroscopic guidance. A stent having the above-described coating may then be expanded at the desired area of treatment. A post-insertion angiogram may also be utilized to confirm appropriate positioning.

5

10

While particular embodiments of the present invention have been shown and described, it will be obvious to those skilled in the art that changes and modifications can be made without departing from this invention in its broader aspects. Therefore, the appended claims are to encompass within their scope all such changes and modifications as fall within the true spirit and scope of this invention.

CLAIMS

What is claimed is:

- 1. A copolymer comprising a soft block (A) that comprises poly(ester amide) (PEA) and a hard block (B), wherein the hard block comprises a block derived from a polymer selected from the group consisting of poly(D,L-lactic acid) (PDLLA, polyglycolic acid (PGA), poly(D,L-lactic acid-co-glycolic acid) (PDLLG), glycerol-sebacic acid, polytyrosine carbonate, polytyrosine, tyrosine oligomer, or tyrosine dipeptide, poly(3-hydroxybutyrate) (PHB), poly(3-hydroxybutyrate-co-3-hydroxyvalerate) (PHBV), poly(3-hydroxyvalerate) (PHV), polyphosphazene, and combinations thereof.
 - 2. The block copolymer of claim 1, wherein the soft block is selected from the group consisting of PEA, PEA-PEG, or a combination thereof.
 - 3. The block copolymer of claim 2, wherein the hard block comprises functional groups.
- 15 4. The block copolymer of claim 1 wherein the hard block comprises tyrosine di-peptide.
 - 5. A copolymer comprising a poly(ester amide) block and a tyrosine dipeptide block.
- 6. The copolymer of claim 4, wherein the tyrosine di-peptide can be
 wherein the tyrosine di-peptide block is

racemic tyrosine di-peptide, desamine tyrosyl tyrosine di-peptide, desamine tyrosyl-tyrosine di-peptide, desamino tyrosyl-tyrosine hexyl ester (DTH), desamino tyrosyl-tyrosine palmityl ester (DTP), *n*-benzyloxycarbonyl-tyrosyl-tyrosine hexyl ester (z-TTH), or combinations thereof.

- 7. The polymer of claim 1, which is an AB, ABA or BAB type block copolymer.
- 8. A polymeric composition comprising a moiety derived from the polymer of claim 4 and a moiety derived from a compound having the structure of

10

5

wherein X can be (1) an organic moiety R_1 , provided that R_1 has one or more halo groups such as iodo or bromo groups, (2) halo groups such as iodo or bromo groups, or (3) combinations thereof,

wherein R and R₁ taken independently can be any chemical grouping having

one or more reactive groups capable of conjugating to the carboxyl group or amino

group of the tyrosine di-peptide block, the reactive groups being selected from the

group consisting of carboxyl groups, aldehyde groups, amino groups, alcohol, ester,

thiol, PEG, leaving groups, mesylate and tosylate, and

wherein n is a positive integer between 1 and 3.

9. A coating on an implantable device comprising the copolymer of claim1 and optionally a bioactive agent.

- 10. A coating on an implantable device comprising the copolymer of claim
 5 and optionally a bioactive agent.
 - 11. The coating of claim 9 further comprising a biobeneficial material.
 - 12. The coating of claim 10 further comprising a biobeneficial material.
- 13. The coating of claim 9 wherein the bioactive agent is selected from the group consisting of paclitaxel, docetaxel, estradiol, nitric oxide donors, super oxide dismutases, super oxide dismutases mimics, 4-amino-2,2,6,6-tetramethylpiperidine-1-oxyl (4-amino-TEMPO), tacrolimus, dexamethasone, rapamycin, rapamycin derivatives, 40-*O*-(2-hydroxy)ethyl-rapamycin (everolimus), 40-*O*-(3-hydroxy)propyl-rapamycin, 40-*O*-[2-(2-hydroxy)ethoxy]ethyl-rapamycin, and 40-*O*-tetrazole-rapamycin, ABT-578, clobetasol, progenitor cell capturing antibody, prohealing drugs, prodrugs thereof, co-drugs thereof, and a combination thereof.
 - 14. An absorbable stent formed of a material comprising the copolymer of claim 1.
 - 15. An absorbable stent formed of a material comprising the copolymer of claim 5.
- 20 16. The stent of claim 14, further comprising a biobeneficial material.
 - 17. The stent of claim 15, further comprising a biobeneficial material.
 - 18. The stent of claim 14, further comprises a bioactive agent.

19. The stent of claim 15, further comprises a bioactive agent.

- 20. A method of treating, preventing, or ameliorating a disorder in a patient comprising implanting in the patient an implantable device comprising the coating of claim 9, wherein the disorder is selected from the group consisting of atherosclerosis, thrombosis, restenosis, hemorrhage, vascular dissection or perforation, vascular aneurysm, vulnerable plaque, chronic total occlusion, claudication, anastomotic proliferation for vein and artificial grafts, bile duct obstruction, ureter obstruction, tumor obstruction, and combinations thereof.
- 21. A method of treating, preventing, or ameliorating a disorder in a patient comprising implanting in the patient an implantable device comprising the coating of claim 10, wherein the disorder is selected from the group consisting of atherosclerosis, thrombosis, restenosis, hemorrhage, vascular dissection or perforation, vascular aneurysm, vulnerable plaque, chronic total occlusion, claudication, anastomotic proliferation for vein and artificial grafts, bile duct obstruction, ureter obstruction, tumor obstruction, and combinations thereof.
 - 22. A method of treating, preventing, or ameliorating a disorder in a patient comprising implanting in the patient the implantable device of claim 14, wherein the disorder is selected from the group consisting of atherosclerosis, thrombosis, restenosis, hemorrhage, vascular dissection or perforation, vascular aneurysm, vulnerable plaque, chronic total occlusion, claudication, anastomotic proliferation for vein and artificial grafts, bile duct obstruction, ureter obstruction, tumor obstruction, and combinations thereof.

20

23. A method of treating, preventing, or ameliorating a disorder in a patient comprising implanting in the patient the implantable device of claim 15, wherein the disorder is selected from the group consisting of atherosclerosis, thrombosis, restenosis, hemorrhage, vascular dissection or perforation, vascular aneurysm,

vulnerable plaque, chronic total occlusion, claudication, anastomotic proliferation for vein and artificial grafts, bile duct obstruction, ureter obstruction, tumor obstruction, and combinations thereof.

INTERNATIONAL SEARCH REPORT

Int onal application No PCT/US2005/047065

A. CLASSIFICATION OF SUBJECT MATTER C08G69/44 A61L31/16 A61L31/10 A61K47/48 According to International Patent Classification (IPC) or to both national classification and IPC **B. FIELDS SEARCHED** Minimum documentation searched (classification system followed by classification symbols) C08G A61L Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched Electronic data base consulted during the international search (name of data base and, where practical, search terms used) EPO-Internal, WPI Data, BIOSIS, COMPENDEX, INSPEC C. DOCUMENTS CONSIDERED TO BE RELEVANT Category* Citation of document, with indication, where appropriate, of the relevant passages Relevant to claim No. US 6 365 172 B1 (BARROWS THOMAS HARRY) X 1 - 3, 72 April 2002 (2002-04-02) examples 3,27 9-23 X US 6 511 748 B1 (BARROWS THOMAS H) 1-3.728 January 2003 (2003-01-28) example 5 Y US 6 503 538 B1 (CHU CHIH-CHANG ET AL) 9 - 237 January 2003 (2003-01-07) examples 25,26; tables 1,2 Further documents are listed in the continuation of Box C. See patent family annex. Special categories of cited documents: "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the *A* document defining the general state of the art which is not considered to be of particular relevance invention *E* earlier document but published on or after the international "X" document of particular relevance; the claimed invention filing date cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such docu-"O" document referring to an oral disclosure, use, exhibition or ments, such combination being obvious to a person skilled in the art. other means document published prior to the international filing date but later than the priority date claimed "&" document member of the same patent family Date of the actual completion of the international search Date of mailing of the international search report 24 March 2006 12/04/2006 Name and mailing address of the ISA/ Authorized officer European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Vaccaro, E Fax: (+31-70) 340-3016

national application No. PCT/US2005/047065

INTERNATIONAL SEARCH REPORT

Box II Observations where certain claims were found unsearchable (Continuation of item 2 of first sheet)
This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:
1. X Claims Nos.: — because they relate to subject matter not required to be searched by this Authority, namely:
Although claims 20-23 are directed to a method of treatment of the human/animal body, the search has been carried out and based on the alleged effects of the compound/composition.
Claims Nos.: because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
3. Claims Nos.: because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).
Box III Observations where unity of invention is lacking (Continuation of item 3 of first sheet)
This International Searching Authority found multiple inventions in this international application, as follows:
1. As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:
Remark on Protest The additional search fees were accompanied by the applicant's protest. No protest accompanied the payment of additional search fees.

INTERNATIONAL SEARCH REPORT

Intended national nation natio

Patent document cited in search report		Publication date		Patent family member(s)		Publication date
US 6365172	B1	02-04-2002	US	6120788	A ⁻	19-09-2000
US 6511748	B1	28-01-2003	US	2003134099	A1	17-07-2003
US 6503538	B1	07-01-2003	AU CA EP JP WO	8701501 2419429 1313794 2004507600 0218477	A1 A2 T	13-03-2002 07-03-2002 28-05-2003 11-03-2004 07-03-2002