

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization

International Bureau

(43) International Publication Date
06 June 2019 (06.06.2019)



(10) International Publication Number
WO 2019/106109 A1

(51) International Patent Classification:

C07D 403/14 (2006.01) H01L 51/50 (2006.01)

(21) International Application Number:

PCT/EP2018/083054

(22) International Filing Date:

29 November 2018 (29.11.2018)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

17204642.7 30 November 2017 (30.11.2017) EP

(71) Applicant: CYNORA GMBH [DE/DE]; Wemer-von-Siemens-Str. 2 - 6, 76646 Bruchsal (DE).

(72) Inventor: SEIFERMANN, Stefan; Hardkopfweg 3, 77815 Bühl (DE).

(74) Agent: HOPPE, Georg J.; Darani, Beuckestr. 20, 14163 Berlin (DE).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JO, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.


(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH,

GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).


Published:

— with international search report (Art. 21(3))

(54) Title: ORGANIC MOLECULES FOR USE IN OPTOELECTRONIC DEVICES



Formula I



Formula II

(57) Abstract: The invention relates to an organic molecule, in particular for the application in optoelectronic devices. According to the invention, the organic molecule has -one first chemical moiety with a structure of formula I, and -one second chemical moiety with a structure of formula II, wherein § represents the binding site of a single bond linking the first chemical moiety to the second chemical moiety, and # represents the binding site of a single bond linking the second chemical moiety to the first chemical moiety.



ORGANIC MOLECULES FOR USE IN OPTOELECTRONIC DEVICES

The invention relates to organic molecules and their use in organic light-emitting diodes (OLEDs) and in other optoelectronic devices.

Description


The object of the present invention is to provide molecules which are suitable for use in optoelectronic devices.

This object is achieved by the invention, which provides a new class of organic molecules.

According to the invention, the organic molecules are purely organic molecules, i.e. they do not contain any metal ions in contrast to metal complexes known for use in optoelectronic devices.

According to the present invention, the organic molecules exhibit emission maxima in the blue, sky-blue or green spectral range. The organic molecules exhibit in particular emission maxima between 420 nm and 520 nm, preferably between 440 nm and 495 nm, more preferably between 450 nm and 470 nm. The photoluminescence quantum yields of the organic molecules according to the invention are, in particular, 20 % or more. The molecules according to the invention exhibit in particular thermally activated delayed fluorescence (TADF). The use of the molecules according to the invention in an optoelectronic device, for example an organic light-emitting diode (OLED), leads to higher efficiencies of the device. Corresponding OLEDs have a higher stability than OLEDs with known emitter materials and comparable color.


The organic light-emitting molecules according to the invention comprise or consist of one first chemical moiety comprising or consisting of a structure of Formula I,



Formula I

and

- one second chemical moiety comprising or consisting of a structure of Formula II,



Formula II

wherein the first chemical moiety is linked to the second chemical moiety via a single bond.

§ represents the binding site of a single bond linking the first chemical moiety to the second chemical moiety.

represents the binding site of a single bond linking the second chemical moiety to the first chemical moiety.

Z is at each occurrence independently from another selected from the group consisting of: a direct bond, CR^3R^4 , $C=CR^3R^4$, $C=O$, $C=NR^3$, NR^3 , O , SiR^3R^4 , S , $S(O)$ and $S(O)_2$.

R^{11} is at each occurrence independently from another selected from the group consisting of: hydrogen, deuterium,

C_1 - C_5 -alkyl,

wherein one or more hydrogen atoms are optionally substituted by deuterium;

C_2 - C_8 -alkenyl,

wherein one or more hydrogen atoms are optionally substituted by deuterium;

C_2 - C_8 -alkynyl,

wherein one or more hydrogen atoms are optionally substituted by deuterium;

C_6 - C_{18} -aryl,

which is optionally substituted with one or more substituents R^6 ; and

C_3 - C_{17} -heteroaryl,

which is optionally substituted with one or more substituents R^6 .

R^{12} is at each occurrence independently from another selected from the group consisting of: hydrogen, deuterium,

C_1 - C_5 -alkyl,

wherein one or more hydrogen atoms are optionally substituted by deuterium;

C₂-C₈-alkenyl,

wherein one or more hydrogen atoms are optionally substituted by deuterium;

C₂-C₈-alkynyl,

wherein one or more hydrogen atoms are optionally substituted by deuterium;

C₆-C₁₈-aryl,

which is optionally substituted with one or more substituents R⁶; and

C₃-C₁₇-heteroaryl,

which is optionally substituted with one or more substituents R⁶.

R^{II}, R^{III} and R^{IV} is independently from another selected from the group consisting of:

hydrogen, deuterium,

C₁-C₅-alkyl,

wherein one or more hydrogen atoms are optionally substituted by deuterium;

C₂-C₈-alkenyl,

wherein one or more hydrogen atoms are optionally substituted by deuterium;

C₂-C₈-alkynyl,

wherein one or more hydrogen atoms are optionally substituted by deuterium; and

C₆-C₁₈-aryl,

which is optionally substituted with one or more substituents R⁶.

R^a is at each occurrence independently from another selected from the group consisting of: hydrogen, deuterium, N(R⁵)₂, OR⁵, Si(R⁵)₃, B(OR⁵)₂, OSO₂R⁵, CF₃, CN, F, Br, I,

C₁-C₄₀-alkyl,

which is optionally substituted with one or more substituents R⁵ and

wherein one or more non-adjacent CH₂-groups are optionally substituted by R⁵C=CR⁵, C≡C, Si(R⁵)₂, Ge(R⁵)₂, Sn(R⁵)₂, C=O, C=S, C=Se, C=NR⁵, P(=O)(R⁵), SO, SO₂, NR⁵, O, S or CONR⁵;

C₁-C₄₀-alkoxy,

which is optionally substituted with one or more substituents R⁵ and

wherein one or more non-adjacent CH₂-groups are optionally substituted by R⁵C=CR⁵, C≡C, Si(R⁵)₂, Ge(R⁵)₂, Sn(R⁵)₂, C=O, C=S, C=Se, C=NR⁵, P(=O)(R⁵), SO, SO₂, NR⁵, O, S or CONR⁵;

C₁-C₄₀-thioalkoxy,

which is optionally substituted with one or more substituents R⁵ and

wherein one or more non-adjacent CH₂-groups are optionally substituted by R⁵C=CR⁵, C≡C, Si(R⁵)₂, Ge(R⁵)₂, Sn(R⁵)₂, C=O, C=S, C=Se, C=NR⁵, P(=O)(R⁵), SO, SO₂, NR⁵, O, S or CONR⁵;

C₂-C₄₀-alkenyl,

which is optionally substituted with one or more substituents R⁵ and wherein one or more non-adjacent CH₂-groups are optionally substituted by R⁵C=CR⁵, C≡C, Si(R⁵)₂, Ge(R⁵)₂, Sn(R⁵)₂, C=O, C=S, C=Se, C=NR⁵, P(=O)(R⁵), SO, SO₂, NR⁵, O, S or CONR⁵;

C₂-C₄₀-alkynyl,

which is optionally substituted with one or more substituents R⁵ and wherein one or more non-adjacent CH₂-groups are optionally substituted by R⁵C=CR⁵, C≡C, Si(R⁵)₂, Ge(R⁵)₂, Sn(R⁵)₂, C=O, C=S, C=Se, C=NR⁵, P(=O)(R⁵), SO, SO₂, NR⁵, O, S or CONR⁵;

C₆-C₆₀-aryl,

which is optionally substituted with one or more substituents R⁵; and

C₃-C₅₇-heteroaryl,

which is optionally substituted with one or more substituents R⁵.

R⁵ is at each occurrence independently from another selected from the group consisting of: hydrogen, deuterium, N(R⁶)₂, OR⁶, Si(R⁶)₃, B(OR⁶)₂, OSO₂R⁶, CF₃, CN, F, Br, I,

C₁-C₄₀-alkyl,

which is optionally substituted with one or more substituents R⁶ and wherein one or more non-adjacent CH₂-groups are optionally substituted by R⁶C=CR⁶, C≡C, Si(R⁶)₂, Ge(R⁶)₂, Sn(R⁶)₂, C=O, C=S, C=Se, C=NR⁶, P(=O)(R⁶), SO, SO₂, NR⁶, O, S or CONR⁶;

C₁-C₄₀-alkoxy,

which is optionally substituted with one or more substituents R⁶ and wherein one or more non-adjacent CH₂-groups are optionally substituted by R⁶C=CR⁶, C≡C, Si(R⁶)₂, Ge(R⁶)₂, Sn(R⁶)₂, C=O, C=S, C=Se, C=NR⁶, P(=O)(R⁶), SO, SO₂, NR⁶, O, S or CONR⁶;

C₁-C₄₀-thioalkoxy,

which is optionally substituted with one or more substituents R⁶ and wherein one or more non-adjacent CH₂-groups are optionally substituted by R⁶C=CR⁶, C≡C, Si(R⁶)₂, Ge(R⁶)₂, Sn(R⁶)₂, C=O, C=S, C=Se, C=NR⁶, P(=O)(R⁶), SO, SO₂, NR⁶, O, S or CONR⁶;

C₂-C₄₀-alkenyl,

which is optionally substituted with one or more substituents R⁶ and wherein one or more non-adjacent CH₂-groups are optionally substituted by R⁶C=CR⁶, C≡C, Si(R⁶)₂, Ge(R⁶)₂, Sn(R⁶)₂, C=O, C=S, C=Se, C=NR⁶, P(=O)(R⁶), SO, SO₂, NR⁶, O, S or CONR⁶;

C₂-C₄₀-alkynyl,

which is optionally substituted with one or more substituents R^6 and wherein one or more non-adjacent CH_2 -groups are optionally substituted by $R^6C=CR^6$, $C\equiv C$, $Si(R^6)_2$, $Ge(R^6)_2$, $Sn(R^6)_2$, $C=O$, $C=S$, $C=Se$, $C=NR^6$, $P(=O)(R^6)$, SO , SO_2 , NR^6 , O , S or $CONR^6$;

C_6 - C_{60} -aryl,

which is optionally substituted with one or more substituents R^6 ; and

C_3 - C_{57} -heteroaryl,

which is optionally substituted with one or more substituents R^6 .

R^6 is at each occurrence independently from another selected from the group consisting of hydrogen, deuterium, OPh , CF_3 , CN , F ,

C_1 - C_5 -alkyl,

wherein optionally one or more hydrogen atoms are independently from each other substituted by deuterium, CN , CF_3 , or F ;

C_1 - C_5 -alkoxy,

wherein optionally one or more hydrogen atoms are independently from each other substituted by deuterium, CN , CF_3 , or F ;

C_1 - C_5 -thioalkoxy,

wherein optionally one or more hydrogen atoms are independently from each other substituted by deuterium, CN , CF_3 , or F ;

C_2 - C_5 -alkenyl,

wherein optionally one or more hydrogen atoms are independently from each other substituted by deuterium, CN , CF_3 , or F ;

C_2 - C_5 -alkynyl,

wherein optionally one or more hydrogen atoms are independently from each other substituted by deuterium, CN , CF_3 , or F ;

C_6 - C_{18} -aryl,

which is optionally substituted with one or more C_1 - C_5 -alkyl substituents;

C_3 - C_{17} -heteroaryl,

which is optionally substituted with one or more C_1 - C_5 -alkyl substituents;

$N(C_6$ - C_{18} -aryl)₂;

$N(C_3$ - C_{17} -heteroaryl)₂; and

$N(C_3$ - C_{17} -heteroaryl)(C_6 - C_{18} -aryl).

The substituents R^a , R^3 , R^4 or R^5 , independently from each other, optionally form a mono- or polycyclic, aliphatic, aromatic and/or benzo-fused ring system with one or more substituents R^a , R^3 , R^4 or R^5 .

In one embodiment, R^{II}, R^{III}, and R^{IV} is independently from each other at each occurrence selected from the group consisting of H, methyl and phenyl.

In one embodiment, R¹¹ and R¹² is independently from each other at each occurrence selected from the group consisting of H, methyl,

phenyl, which is optionally substituted with one or more substituents R⁶;

1,3,5-triazinyl, which is optionally substituted with one or more substituents R⁶;

pyridinyl, which is optionally substituted with one or more substituents R⁶; and

pyrimidyl, which is optionally substituted with one or more substituents R⁶.

In one embodiment, R¹¹ and R¹² is Ph, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃, and Ph.

In one embodiment, R¹¹ and R¹² is Ph at each occurrence.


In one embodiment, R^{II} is hydrogen.

In one embodiment, R^{III} is hydrogen.

In one embodiment, R^{IV} is hydrogen.

In one embodiment R^{II}, R^{III}, and R^{IV} is H.

In a further embodiment of the invention, the second chemical moiety comprises or consists of a structure of Formula IIa:



Formula IIa

wherein # and R^a are defined as above.

In a further embodiment of the invention, R^a is at each occurrence independently from another selected from the group consisting of:

hydrogen,

Me,

ⁱPr,

^tBu,

CN,

CF₃,

Ph, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃, and Ph,

pyridinyl, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃, and Ph,

pyrimidinyl, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃, and Ph,

carbazolyl, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃, and Ph,

triazinyl, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃, and Ph,

and N(Ph)₂.

In a further embodiment of the invention, R^a is at each occurrence independently from another selected from the group consisting of:

hydrogen,

Me,

ⁱPr,

^tBu,

CN,

CF₃,


Ph, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃, and Ph,

pyridinyl, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃, and Ph,

pyrimidinyl, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃, and Ph, and

triazinyl, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃, and Ph.

In a further embodiment of the invention, the second chemical moiety comprises or consists of a structure of Formula IIb, a structure of Formula IIb-2, a structure of Formula IIb-3 or a structure of Formula IIb-4:



wherein

R^b is at each occurrence independently from another selected from the group consisting of deuterium, $N(R^5)_2$, OR^5 , $Si(R^5)_3$, $B(OR^5)_2$, OSO_2R^5 , CF_3 , CN , F , Br , I ,

C_1 - C_{40} -alkyl,

which is optionally substituted with one or more substituents R^5 and

wherein one or more non-adjacent CH_2 -groups are optionally substituted by $R^5C=CR^5$, $C\equiv C$, $Si(R^5)_2$, $Ge(R^5)_2$, $Sn(R^5)_2$, $C=O$, $C=S$, $C=Se$, $C=NR^5$, $P(=O)(R^5)$, SO , SO_2 , NR^5 , O , S or $CONR^5$;

C_1 - C_{40} -alkoxy,

which is optionally substituted with one or more substituents R^5 and

wherein one or more non-adjacent CH_2 -groups are optionally substituted by $R^5C=CR^5$, $C\equiv C$, $Si(R^5)_2$, $Ge(R^5)_2$, $Sn(R^5)_2$, $C=O$, $C=S$, $C=Se$, $C=NR^5$, $P(=O)(R^5)$, SO , SO_2 , NR^5 , O , S or $CONR^5$;

C_1 - C_{40} -thioalkoxy,

which is optionally substituted with one or more substituents R^5 and

wherein one or more non-adjacent CH_2 -groups are optionally substituted by $R^5C=CR^5$, $C\equiv C$, $Si(R^5)_2$, $Ge(R^5)_2$, $Sn(R^5)_2$, $C=O$, $C=S$, $C=Se$, $C=NR^5$, $P(=O)(R^5)$, SO , SO_2 , NR^5 , O , S or $CONR^5$;

C_2 - C_{40} -alkenyl,

which is optionally substituted with one or more substituents R^5 and

wherein one or more non-adjacent CH_2 -groups are optionally substituted by $R^5C=CR^5$, $C\equiv C$, $Si(R^5)_2$, $Ge(R^5)_2$, $Sn(R^5)_2$, $C=O$, $C=S$, $C=Se$, $C=NR^5$, $P(=O)(R^5)$, SO , SO_2 , NR^5 , O , S or $CONR^5$;

C_2 - C_{40} -alkynyl,

which is optionally substituted with one or more substituents R^5 and

wherein one or more non-adjacent CH_2 -groups are optionally substituted by $R^5C=CR^5$, $C\equiv C$, $Si(R^5)_2$, $Ge(R^5)_2$, $Sn(R^5)_2$, $C=O$, $C=S$, $C=Se$, $C=NR^5$, $P(=O)(R^5)$, SO , SO_2 , NR^5 , O , S or $CONR^5$;

C₆-C₆₀-aryl,


which is optionally substituted with one or more substituents R⁵; and

C₃-C₅₇-heteroaryl,


which is optionally substituted with one or more substituents R⁵.

Apart from that, the aforementioned definitions apply.


In an additional embodiment of the invention, the second chemical moiety comprises or consists of a structure of Formula IIc, a structure of Formula IIc-2, a structure of Formula IIc-3 or a structure of Formula IIc-4:




Formula IIc



Formula IIc-2



Formula IIc-3



Formula IIc-4

wherein the aforementioned definitions apply.

In a further embodiment of the invention, R^b is at each occurrence independently from another selected from the group consisting of:

Me, ⁱPr, ^tBu, CN, CF₃,

Ph, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃, and Ph,

pyridinyl, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃, and Ph,

carbazolyl, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃, and Ph,

triazinyl, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃, and Ph,

and N(Ph)₂.

In a further embodiment of the invention, R^b is at each occurrence independently from another selected from the group consisting of:

Me,

ⁱPr,

^tBu,

CN,

CF₃,

Ph, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃, and Ph,
 pyridinyl, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃, and Ph,
 pyrimidinyl, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃, and Ph, and
 triazinyl, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃, and Ph.


In a further embodiment of the invention, R^b is at each occurrence independently from another selected from the group consisting of:


pyridinyl, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃, and Ph,
 pyrimidinyl, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃, and Ph, and
 triazinyl, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃, and Ph.

In a further embodiment of the invention, R^b is at each occurrence independently from another selected from the group consisting of:

triazinyl, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃, and Ph.

Below, examples for the second chemical moiety of the organic molecule are shown:






wherein the aforementioned definitions apply for #, Z, R^a, R³, R⁴ and R⁵.

In one embodiment, R^a and R⁵ is at each occurrence independently from another selected from the group consisting of hydrogen (H), methyl (Me), i-propyl (CH(CH₃)₂) (iPr), t-butyl (tBu), phenyl (Ph), CN, CF₃, and diphenylamine (NPh₂).


In one embodiment of the invention, the organic molecules comprise or consist of a structure of Formula III:



Formula III

wherein the aforementioned definitions apply.

In a further embodiment of the invention, the organic molecules comprise or consist of a structure of Formula IIIa:



Formula IIIa

wherein

R^c is at each occurrence independently from another selected from the group consisting of:

Me,


iPr,

tBu,

Ph, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, iPr, tBu, CN, CF₃, and Ph,

pyridinyl, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃, and Ph,
 pyrimidinyl, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃, and Ph,
 carbazolyl, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃, and Ph,
 triazinyl, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃, and Ph,
 and
 N(Ph)₂,
 and wherein R¹¹, R¹², R^{II}, R^{III} and R^{IV} are defined as above.


In a further embodiment of the invention, the organic molecule comprises or consists of a structure of Formula IIIb:



Formula IIIb

wherein the aforementioned definitions apply.

In a further embodiment of the invention, the organic molecules comprise or consist of a structure of Formula IIIc:




Formula IIIc

wherein the aforementioned definitions apply.

In a further embodiment of the invention, the organic molecules comprise or consist of a structure of Formula IIId:


15



Formula III d

wherein the aforementioned definitions apply.


In a further embodiment of the invention, the organic molecules comprise or consist of a structure of Formula III e:



Formula III e

wherein the aforementioned definitions apply.

In a further embodiment of the invention, the organic molecules comprise or consist of a structure of Formula III f:




Formula III f

wherein the aforementioned definitions apply.

In a further embodiment of the invention, the organic molecules comprise or consist of a structure of Formula III g:


16



Formula IIIg

wherein the aforementioned definitions apply.

In a further embodiment of the invention, the organic molecules comprise or consist of a structure of Formula IIIh:



Formula IIIh

wherein the aforementioned definitions apply.

As used above and herein, the terms "aryl" and "aromatic" may be understood in the broadest sense as any mono-, bi- or polycyclic aromatic moieties. Accordingly, an aryl group contains 6 to 60 aromatic ring atoms, and a heteroaryl group contains 5 to 60 aromatic ring atoms, of which at least one is a heteroatom. Notwithstanding, throughout the application the number of aromatic ring atoms may be given as subscripted number in the definition of certain substituents. In particular, the heteroaromatic ring includes one to three heteroatoms. Again, the terms "heteroaryl" and "heteroaromatic" may be understood in the broadest sense as any mono-, bi- or polycyclic hetero-aromatic moieties that include at least one heteroatom. The heteroatoms may at each occurrence be the same or different and be individually selected from the group consisting of N, O and S. Accordingly, the term "arylene" refers to a divalent substituent that bears two binding sites to other molecular structures and thereby serving as a linker structure. In case, a group in the exemplary embodiments is defined differently from the definitions given here, for example, the number of aromatic ring atoms or number of heteroatoms differs from the given definition, the definition in the exemplary embodiments is to be applied. According to the invention, a condensed (annulated) aromatic or heteroaromatic

polycycle is built of two or more single aromatic or heteroaromatic cycles, which formed the polycycle via a condensation reaction.

In particular, as used throughout the present application the term aryl group or heteroaryl group comprises groups which can be bound via any position of the aromatic or heteroaromatic group, derived from benzene, naphthalene, anthracene, phenanthrene, pyrene, dihydropyrene, chrysene, perylene, fluoranthene, benzanthracene, benzphenanthrene, tetracene, pentacene, benzpyrene, furan, benzofuran, isobenzofuran, dibenzofuran, thiophene, benzothiophene, isobenzothiophene, dibenzothiophene; pyrrole, indole, isoindole, carbazole, pyridine, quinoline, isoquinoline, acridine, phenanthridine, benzo-5,6-quinoline, benzo-6,7-quinoline, benzo-7,8-quinoline, phenothiazine, phenoxazine, pyrazole, indazole, imidazole, benzimidazole, naphthoimidazole, phenanthroimidazole, pyridoimidazole, pyrazinoimidazole, quinoxalinoimidazole, oxazole, benzoxazole, naphthooxazole, anthroxazol, phenanthroxazol, isoxazole, 1,2-thiazole, 1,3-thiazole, benzothiazole, pyridazine, benzopyridazine, pyrimidine, benzopyrimidine, 1,3,5-triazine, quinoxaline, pyrazine, phenazine, naphthyridine, carboline, benzocarboline, phenanthroline, 1,2,3-triazole, 1,2,4-triazole, benzotriazole, 1,2,3-oxadiazole, 1,2,4-oxadiazole, 1,2,5-oxadiazole, 1,2,3,4-tetrazine, purine, pteridine, indolizine and benzothiadiazole or combinations of the abovementioned groups.

As used throughout the present application the term cyclic group may be understood in the broadest sense as any mono-, bi- or polycyclic moieties.

As used above and herein, the term alkyl group may be understood in the broadest sense as any linear, branched, or cyclic alkyl substituent. In particular, the term alkyl comprises the substituents methyl (Me), ethyl (Et), n-propyl (ⁿPr), i-propyl (ⁱPr), cyclopropyl, n-butyl (ⁿBu), i-butyl (ⁱBu), s-butyl (^sBu), t-butyl (^tBu), cyclobutyl, 2-methylbutyl, n-pentyl, s-pentyl, t-pentyl, 2-pentyl, neo-pentyl, cyclopentyl, n-hexyl, s-hexyl, t-hexyl, 2-hexyl, 3-hexyl, neo-hexyl, cyclohexyl, 1-methylcyclopentyl, 2-methylpentyl, n-heptyl, 2-heptyl, 3-heptyl, 4-heptyl, cycloheptyl, 1-methylcyclohexyl, n-octyl, 2-ethylhexyl, cyclooctyl, 1-bicyclo[2,2,2]octyl, 2-bicyclo[2,2,2]-octyl, 2-(2,6-dimethyl)octyl, 3-(3,7-dimethyl)octyl, adamantyl, 2,2,2-trifluorethyl, 1,1-dimethyl-n-hex-1-yl, 1,1-dimethyl-n-hept-1-yl, 1,1-dimethyl-n-oct-1-yl, 1,1-dimethyl-n-dec-1-yl, 1,1-dimethyl-n-dodec-1-yl, 1,1-dimethyl-n-tetradec-1-yl, 1,1-dimethyl-n-hexadec-1-yl, 1,1-dimethyl-n-octadec-1-yl, 1,1-diethyl-n-hex-1-yl, 1,1-diethyl-n-hept-1-yl, 1,1-diethyl-n-oct-1-yl, 1,1-diethyl-n-dec-1-yl, 1,1-diethyl-n-dodec-1-yl, 1,1-diethyl-n-tetradec-1-yl, 1,1-diethyl-n-hexadec-1-yl, 1,1-diethyl-n-octadec-1-yl, 1-(n-propyl)-cyclohex-1-yl, 1-(n-butyl)-cyclohex-1-yl, 1-(n-hexyl)-cyclohex-1-yl, 1-(n-octyl)-cyclohex-1-yl and 1-(n-decyl)-cyclohex-1-yl.

As used above and herein, the term alkenyl comprises linear, branched, and cyclic alkenyl substituents. The term alkenyl group exemplarily comprises the substituents ethenyl, propenyl, butenyl, pentenyl, cyclopentenyl, hexenyl, cyclohexenyl, heptenyl, cycloheptenyl, octenyl, cyclooctenyl or cyclooctadienyl.

As used above and herein, the term alkynyl comprises linear, branched, and cyclic alkynyl substituents. The term alkynyl group exemplarily comprises ethynyl, propynyl, butynyl, pentynyl, hexynyl, heptynyl or octynyl.

As used above and herein, the term alkoxy comprises linear, branched, and cyclic alkoxy substituents. The term alkoxy group exemplarily comprises methoxy, ethoxy, n-propoxy, i-propoxy, n-butoxy, i-butoxy, s-butoxy, t-butoxy and 2-methylbutoxy.

As used above and herein, the term thioalkoxy comprises linear, branched, and cyclic thioalkoxy substituents, in which the O of the exemplarily alkoxy groups is replaced by S.

As used above and herein, the terms "halogen" and "halo" may be understood in the broadest sense as being preferably fluorine, chlorine, bromine or iodine.

Whenever hydrogen (H) is mentioned herein, it could also be replaced by deuterium at each occurrence.

It is understood that when a molecular fragment is described as being a substituent or otherwise attached to another moiety, its name may be written as if it is a fragment (e.g. naphthyl, dibenzofuryl) or as if it is the whole molecule (e.g. naphthalene, dibenzofuran). As used herein, these different ways of designating a substituent or attached fragment are considered to be equivalent.

In one embodiment, the organic molecules according to the invention have an excited state lifetime of not more than 150 μs , of not more than 100 μs , in particular of not more than 50 μs , more preferably of not more than 10 μs or not more than 7 μs in a film of poly(methyl methacrylate) (PMMA) with 10% by weight of organic molecule at room temperature.

In one embodiment of the invention, the organic molecules according to the invention represent thermally-activated delayed fluorescence (TADF) emitters, which exhibit a ΔE_{ST} value, which corresponds to the energy difference between the first excited singlet state (S1) and the first excited triplet state (T1), of less than 5000 cm^{-1} , preferably less than 3000 cm^{-1} , more

preferably less than 1500 cm^{-1} , even more preferably less than 1000 cm^{-1} or even less than 500 cm^{-1} .

In a further embodiment of the invention, the organic molecules according to the invention have an emission peak in the visible or nearest ultraviolet range, i.e., in the range of a wavelength of from 380 to 800 nm, with a full width at half maximum of less than 0.50 eV, preferably less than 0.48 eV, more preferably less than 0.45 eV, even more preferably less than 0.43 eV or even less than 0.40 eV in a film of poly(methyl methacrylate) (PMMA) with 10% by weight of organic molecule at room temperature.

In a further embodiment of the invention, the organic molecules according to the invention have an emission peak in the visible or nearest ultraviolet range, i.e., in the range of a wavelength of from 380 to 800 nm, with a full width at half maximum of less than 0.40 eV in a film of poly(methyl methacrylate) (PMMA) with 10% by weight of organic molecule at room temperature.

In a further embodiment of the invention, the organic molecules according to the invention have a "blue material index" (BMI), calculated by dividing the photoluminescence quantum yield (PLQY) in % by the CIEy color coordinate of the emitted light, of more than 150, in particular more than 200, preferably more than 250, more preferably of more than 300 or even more than 500.


Orbital and excited state energies can be determined either by means of experimental methods or by calculations employing quantum-chemical methods, in particular density functional theory calculations. The energy of the highest occupied molecular orbital E^{HOMO} is determined by methods known to the person skilled in the art from cyclic voltammetry measurements with an accuracy of 0.1 eV. The energy of the lowest unoccupied molecular orbital E^{LUMO} is calculated as $E^{\text{HOMO}} + E^{\text{gap}}$, wherein E^{gap} is determined as follows: For host compounds, the onset of the emission spectrum of a film with 10% by weight of host in poly(methyl methacrylate) (PMMA) is used as E^{gap} , unless stated otherwise. For emitter molecules, E^{gap} is determined as the energy at which the excitation and emission spectra of a film with 10% by weight of emitter in PMMA cross.

The energy of the first excited triplet state T1 is determined from the onset of the emission spectrum at low temperature, typically at 77 K. For host compounds, where the first excited singlet state and the lowest triplet state are energetically separated by $> 0.4\text{ eV}$, the phosphorescence is usually visible in a steady-state spectrum in 2-Me-THF. The triplet energy

can thus be determined as the onset of the phosphorescence spectrum. For TADF emitter molecules, the energy of the first excited triplet state T1 is determined from the onset of the delayed emission spectrum at 77 K, if not otherwise stated measured in a film of PMMA with 10% by weight of emitter. Both for host and emitter compounds, the energy of the first excited singlet state S1 is determined from the onset of the emission spectrum, if not otherwise stated measured in a film of PMMA with 10% by weight of host or emitter compound.

The onset of an emission spectrum is determined by computing the intersection of the tangent to the emission spectrum with the x-axis. The tangent to the emission spectrum is set at the high-energy side of the emission band and at the point at half maximum of the maximum intensity of the emission spectrum.

A further aspect of the invention relates to a process for preparing the organic molecules (with an optional subsequent reaction) of the invention, wherein a palladium catalyzed cross-coupling reaction is used:




According to the invention, a 1-fluorobenzene, which is substituted with a coupling group CG^1 and which is substituted with a coupling group CG^2 (cf. **E2**) is used as a reactant, which is reacted with two 1,3,5-triazines (**E3** and **E4**), one substituted with a coupling group CG^3 (reactant **E3**) and one with a coupling group CG^4 (reactant **E4**). The coupling groups CG^1 and CG^4 are chosen as a reaction pair to introduce the heterocycle of **E4** at the position of CG^1 . Accordingly, coupling groups CG^2 and CG^3 are chosen reaction pair for introducing the heterocycle of **E3** at the position of CG^2 . Preferably, a so-called Suzuki coupling reaction is used. Here, CG^1 is a boronic acid group or a boronic acid ester group, in particular a boronic

acid pinacol ester group, and CG^4 is chosen from Cl, Br or I. Analogously, CG^2 is a boronic acid group or a boronic acid ester group, in particular a boronic acid pinacol ester group, and CG^3 is chosen from Cl, Br or I. The person skilled in the art is aware that in order to introduce different heterocycles via the coupling reactions of **E3** with **E2** and **E4** with **E2**, either first **E2** is reacted with **E3** and the resulting intermediate is subsequently reacted with **E4** to yield **E1**, or first **E2** is reacted with **E4** and the resulting intermediate is subsequently reacted with **E3** to yield **E1**.

For the reaction of a nitrogen heterocycle in a nucleophilic aromatic substitution with an aryl halide, preferably an aryl fluoride, typical conditions include the use of a base, such as tribasic potassium phosphate or sodium hydride, for example, in an aprotic polar solvent, such as dimethyl sulfoxide (DMSO) or N,N-dimethylformamide (DMF), for example.

An alternative synthesis route comprises the introduction of a nitrogen heterocycle via copper- or palladium-catalyzed coupling to an aryl halide or aryl pseudohalide, preferably an aryl bromide, an aryl iodide, aryl triflate or an aryl tosylate.

Alternatively, the organic molecule according to the invention can be synthesized via the following synthesis route:



wherein the aforementioned definitions and descriptions apply.

A further aspect of the invention relates to the use of an organic molecule according to the invention as a luminescent emitter or as an absorber, and/or as host material and/or as electron

transport material, and/or as hole injection material, and/or as hole blocking material in an optoelectronic device.

The optoelectronic device may be understood in the broadest sense as any device based on organic materials that is suitable for emitting light in the visible or nearest ultraviolet (UV) range, i.e., in the range of a wavelength of from 380 to 800 nm. More preferably, the optoelectronic device may be able to emit light in the visible range, i.e., light with a wavelength from 400 to 800 nm.

In the context of such use, the optoelectronic device is more particularly selected from the group consisting of:

- organic light-emitting diodes (OLEDs),
- light-emitting electrochemical cells,
- OLED sensors, especially in gas and vapour sensors not hermetically shielded,
- organic diodes,
- organic solar cells,
- organic transistors,
- organic field-effect transistors,
- organic lasers and
- down-conversion elements.

In a preferred embodiment in the context of such use, the optoelectronic device is a device selected from the group consisting of an organic light emitting diode (OLED), a light emitting electrochemical cell (LEC), and a light-emitting transistor.

In the case of the use, the fraction of the organic molecule according to the invention in the emission layer in an optoelectronic device, more particularly in OLEDs, is 1 % to 99 % by weight, more particularly 5 % to 80 % by weight. In an alternative embodiment, the proportion of the organic molecule in the emission layer is 100 % by weight.

In one embodiment, the light-emitting layer comprises not only the organic molecules according to the invention but also a host material whose triplet (T1) and singlet (S1) energy levels are energetically higher than the triplet (T1) and singlet (S1) energy levels of the organic molecule.

A further aspect of the invention relates to a composition comprising or consisting of:

- (a) at least one organic molecule according to the invention, in particular in the form of an emitter and/or a host, and
- (b) one or more emitter and/or host materials, which differ from the organic molecule according to the invention and
- (c) optional one or more dyes and/or one or more solvents.

In one embodiment, the light-emitting layer comprises (or essentially consists of) a composition comprising or consisting of:

- (a) at least one organic molecule according to the invention, in particular in the form of an emitter and/or a host, and
- (b) one or more emitter and/or host materials, which differ from the organic molecule according to the invention, and
- (c) optionally, one or more dyes and/or one or more solvents.

In one particular embodiment, the light-emitting layer EML comprises (or essentially consists of) a composition comprising or consisting of:

- (i) 1-50 % by weight, preferably 5-40 % by weight, in particular 10-30 % by weight, of one or more organic molecules according to the invention;
- (ii) 5-99 % by weight, preferably 30-94.9 % by weight, in particular 40-89% by weight, of at least one host compound H; and
- (iii) optionally, 0-94 % by weight, preferably 0.1-65 % by weight, in particular 1-50 % by weight, of at least one further host compound D with a structure differing from the structure of the molecules according to the invention; and
- (iv) optionally, 0-94 % by weight, preferably 0-65 % by weight, in particular 0-50 % by weight, of a solvent; and
- (v) optionally, 0-30 % by weight, in particular 0-20 % by weight, preferably 0-5 % by weight, of at least one further emitter molecule F with a structure differing from the structure of the molecules according to the invention.

Preferably, energy can be transferred from the host compound H to the one or more organic molecules according to the invention, in particular transferred from the first excited triplet state T1(H) of the host compound H to the first excited triplet state T1(E) of the one or more organic molecules according to the invention and/ or from the first excited singlet state S1(H) of the host compound H to the first excited singlet state S1(E) of the one or more organic molecules according to the invention.

In a further embodiment, the light-emitting layer EML comprises (or essentially consists of) a composition comprising or consisting of:

- (i) 1-50 % by weight, preferably 5-40 % by weight, in particular 10-30 % by weight, of one organic molecule according to the invention;
- (ii) 5-99 % by weight, preferably 30-94.9 % by weight, in particular 40-89% by weight, of one host compound H; and
- (iii) optionally 0-94 % by weight, preferably 0.1-65 % by weight, in particular 1-50 % by weight, of at least one further host compound D with a structure differing from the structure of the molecules according to the invention; and
- (iv) optionally 0-94 % by weight, preferably 0-65 % by weight, in particular 0-50 % by weight, of a solvent; and
- (v) optionally 0-30 % by weight, in particular 0-20 % by weight, preferably 0-5 % by weight, of at least one further emitter molecule F with a structure differing from the structure of the molecules according to the invention.

In one embodiment of the invention, the host compound H has a highest occupied molecular orbital HOMO(H) having an energy $E^{\text{HOMO}}(\text{H})$ in the range of from -5 to -6.5 eV and the at least one further host compound D has a highest occupied molecular orbital HOMO(D) having an energy $E^{\text{HOMO}}(\text{D})$, wherein $E^{\text{HOMO}}(\text{H}) > E^{\text{HOMO}}(\text{D})$.

In a further embodiment, the host compound H has a lowest unoccupied molecular orbital LUMO(H) having an energy $E^{\text{LUMO}}(\text{H})$ and the at least one further host compound D has a lowest unoccupied molecular orbital LUMO(D) having an energy $E^{\text{LUMO}}(\text{D})$, wherein $E^{\text{LUMO}}(\text{H}) > E^{\text{LUMO}}(\text{D})$.

In another embodiment, the host compound H has a highest occupied molecular orbital HOMO(H) having an energy $E^{\text{HOMO}}(\text{H})$ and a lowest unoccupied molecular orbital LUMO(H) having an energy $E^{\text{LUMO}}(\text{H})$, and

the at least one further host compound D has a highest occupied molecular orbital HOMO(D) having an energy $E^{\text{HOMO}}(\text{D})$ and a lowest unoccupied molecular orbital LUMO(D) having an energy $E^{\text{LUMO}}(\text{D})$,

the organic molecule according to the invention has a highest occupied molecular orbital HOMO(E) having an energy $E^{\text{HOMO}}(\text{E})$ and a lowest unoccupied molecular orbital LUMO(E) having an energy $E^{\text{LUMO}}(\text{E})$,

wherein

$E^{\text{HOMO}}(\text{H}) > E^{\text{HOMO}}(\text{D})$ and the difference between the energy level of the highest occupied molecular orbital HOMO(E) of organic molecule according to the invention ($E^{\text{HOMO}}(\text{E})$) and the

energy level of the highest occupied molecular orbital HOMO(H) of the host compound H ($E^{\text{HOMO}}(\text{H})$) is between -0.5 eV and 0.5 eV, more preferably between -0.3 eV and 0.3 eV, even more preferably between -0.2 eV and 0.2 eV or even between -0.1 eV and 0.1 eV; and $E^{\text{LUMO}}(\text{H}) > E^{\text{LUMO}}(\text{D})$ and the difference between the energy level of the lowest unoccupied molecular orbital LUMO(E) of organic molecule according to the invention ($E^{\text{LUMO}}(\text{E})$) and the lowest unoccupied molecular orbital LUMO(D) of the at least one further host compound D ($E^{\text{LUMO}}(\text{D})$) is between -0.5 eV and 0.5 eV, more preferably between -0.3 eV and 0.3 eV, even more preferably between -0.2 eV and 0.2 eV or even between -0.1 eV and 0.1 eV.

In a further aspect, the invention relates to an optoelectronic device comprising an organic molecule or a composition as described herein, more particularly in the form of a device selected from the group consisting of organic light-emitting diode (OLED), light-emitting electrochemical cell, OLED sensor (more particularly gas and vapour sensors not hermetically externally shielded), organic diode, organic solar cell, organic transistor, organic field-effect transistor, organic laser and down-conversion element.

In particular embodiments, the optoelectronic device is a device selected from the group consisting of an organic light emitting diode (OLED), a light emitting electrochemical cell (LEC), and a light-emitting transistor.

In one embodiment of the optoelectronic device of the invention, the organic molecule according to the invention is used as emission material in a light-emitting layer EML.

In one embodiment of the optoelectronic device of the invention, the light-emitting layer EML consists of the composition according to the invention described herein.

When the optoelectronic device is an OLED, it may, for example, exhibit the following layer structure:

1. substrate
2. anode layer A
3. hole injection layer, HIL
4. hole transport layer, HTL
5. electron blocking layer, EBL
6. emitting layer, EML
7. hole blocking layer, HBL
8. electron transport layer, ETL
9. electron injection layer, EIL

10. cathode layer,

wherein the OLED comprises each layer only optionally, different layers may be merged and the OLED may comprise more than one layer of each layer type defined above.

Furthermore, the optoelectronic device may optionally comprise one or more protective layers protecting the device from damaging exposure to harmful species in the environment including, exemplarily moisture, vapor and/or gases.

In one embodiment of the invention, the optoelectronic device is an OLED, which exhibits the following inverted layer structure:

1. substrate
2. cathode layer
3. electron injection layer, EIL
4. electron transport layer, ETL
5. hole blocking layer, HBL
6. emitting layer, B
7. electron blocking layer, EBL
8. hole transport layer, HTL
9. hole injection layer, HIL
10. anode layer A

wherein the OLED with an inverted layer structure comprises each layer only optionally, different layers may be merged and the OLED may comprise more than one layer of each layer types defined above.

In one embodiment of the invention, the optoelectronic device is an OLED, which may exhibit stacked architecture. In this architecture, contrary to the typical arrangement, where the OLEDs are placed side by side, the individual units are stacked on top of each other. Blended light may be generated with OLEDs exhibiting a stacked architecture, in particular white light may be generated by stacking blue, green and red OLEDs. Furthermore, the OLED exhibiting a stacked architecture may optionally comprise a charge generation layer (CGL), which is typically located between two OLED subunits and typically consists of a n-doped and p-doped layer with the n-doped layer of one CGL being typically located closer to the anode layer.

In one embodiment of the invention, the optoelectronic device is an OLED, which comprises two or more emission layers between anode and cathode. In particular, this so-called tandem

OLED comprises three emission layers, wherein one emission layer emits red light, one emission layer emits green light and one emission layer emits blue light, and optionally may comprise further layers such as charge generation layers, blocking or transporting layers between the individual emission layers. In a further embodiment, the emission layers are adjacently stacked. In a further embodiment, the tandem OLED comprises a charge generation layer between each two emission layers. In addition, adjacent emission layers or emission layers separated by a charge generation layer may be merged.

The substrate may be formed by any material or composition of materials. Most frequently, glass slides are used as substrates. Alternatively, thin metal layers (e.g., copper, gold, silver or aluminum films) or plastic films or slides may be used. This may allow a higher degree of flexibility. The anode layer A is mostly composed of materials allowing to obtain an (essentially) transparent film. As at least one of both electrodes should be (essentially) transparent in order to allow light emission from the OLED, either the anode layer A or the cathode layer C is transparent. Preferably, the anode layer A comprises a large content or even consists of transparent conductive oxides (TCOs). Such anode layer A may exemplarily comprise indium tin oxide, aluminum zinc oxide, fluorine doped tin oxide, indium zinc oxide, PbO, SnO, zirconium oxide, molybdenum oxide, vanadium oxide, wolfram oxide, graphite, doped Si, doped Ge, doped GaAs, doped polyaniline, doped polypyrrol and/or doped polythiophene.

Preferably, the anode layer A (essentially) consists of indium tin oxide (ITO) (e.g., $(\text{InO}_3)_{0.9}(\text{SnO}_2)_{0.1}$). The roughness of the anode layer A caused by the transparent conductive oxides (TCOs) may be compensated by using a hole injection layer (HIL). Further, the HIL may facilitate the injection of quasi charge carriers (i.e., holes) in that the transport of the quasi charge carriers from the TCO to the hole transport layer (HTL) is facilitated. The hole injection layer (HIL) may comprise poly-3,4-ethylendioxy thiophene (PEDOT), polystyrene sulfonate (PSS), MoO_2 , V_2O_5 , CuPC or CuI, in particular a mixture of PEDOT and PSS. The hole injection layer (HIL) may also prevent the diffusion of metals from the anode layer A into the hole transport layer (HTL). The HIL may exemplarily comprise PEDOT:PSS (poly-3,4-ethylendioxy thiophene: polystyrene sulfonate), PEDOT (poly-3,4-ethylendioxy thiophene), mMTDATA (4,4',4''-tris[phenyl(m-tolyl)amino]triphenylamine), Spiro-TAD (2,2',7,7'-tetrakis(n,n-diphenylamino)-9,9'-spirobifluorene), DNTPD (N1,N1'-(biphenyl-4,4'-diyl)bis(N1-phenyl-N4,N4-di-m-tolylbenzene-1,4-diamine), NPB (N,N'-bis-(1-naphthalenyl)-N,N'-bis-phenyl-(1,1'-biphenyl)-4,4'-diamine), NPNPB (N,N'-diphenyl-N,N'-di-[4-(N,N-diphenyl-amino)phenyl]benzidine), MeO-TPD (N,N,N',N'-tetrakis(4-methoxyphenyl)benzidine), HAT-CN (1,4,5,8,9,11-hexaazatriphenylen-hexacarbonitrile) and/or Spiro-NPD (N,N'-diphenyl-N,N'-bis-(1-naphthyl)-9,9'-spirobifluorene-2,7-diamine).

Adjacent to the anode layer A or hole injection layer (HIL) typically a hole transport layer (HTL) is located. Herein, any hole transport compound may be used. Exemplarily, electron-rich heteroaromatic compounds such as triaryl amines and/or carbazoles may be used as hole transport compound. The HTL may decrease the energy barrier between the anode layer A and the light-emitting layer EML. The hole transport layer (HTL) may also be an electron blocking layer (EBL). Preferably, hole transport compounds bear comparably high energy levels of their triplet states T1. Exemplarily the hole transport layer (HTL) may comprise a star-shaped heterocycle such as tris(4-carbazoyl-9-ylphenyl)amine (TCTA), poly-TPD (poly(4-butylphenyl-diphenyl-amine)), [alpha]-NPD (poly(4-butylphenyl-diphenyl-amine)), TAPC (4,4'-cyclohexylidene-bis[N,N-bis(4-methylphenyl)benzenamine]), 2-TNATA (4,4',4''-tris[2-naphthyl(phenyl)amino]triphenylamine), Spiro-TAD, DNTPD, NPB, NPNPB, MeO-TPD, HAT-CN and/or TrisPcz (9,9'-diphenyl-6-(9-phenyl-9H-carbazol-3-yl)-9H,9'H-3,3'-bicarbazole). In addition, the HTL may comprise a p-doped layer, which may be composed of an inorganic or organic dopant in an organic hole-transporting matrix. Transition metal oxides such as vanadium oxide, molybdenum oxide or tungsten oxide may exemplarily be used as inorganic dopant. Tetrafluorotetracyanoquinodimethane (F4-TCNQ), copper-pentafluorobenzoate (Cu(I)pFBz) or transition metal complexes may exemplarily be used as organic dopant.

The EBL may exemplarily comprise mCP (1,3-bis(carbazol-9-yl)benzene), TCTA, 2-TNATA, mCBP (3,3-di(9H-carbazol-9-yl)biphenyl), tris-Pcz, CzSi (9-(4-tert-Butylphenyl)-3,6-bis(triphenylsilyl)-9H-carbazole), and/or DCB (N,N'-dicarbazolyl-1,4-dimethylbenzene).

Adjacent to the hole transport layer (HTL), typically, the light-emitting layer EML is located. The light-emitting layer EML comprises at least one light emitting molecule. Particular, the EML comprises at least one light emitting molecule according to the invention. In one embodiment, the light-emitting layer comprises only the organic molecules according to the invention. Typically, the EML additionally comprises one or more host material. Exemplarily, the host material is selected from CBP (4,4'-Bis-(N-carbazolyl)-biphenyl), mCP, mCBP Sif87 (dibenzo[b,d]thiophen-2-yltriphenylsilane), CzSi, Sif88 (dibenzo[b,d]thiophen-2-yl)diphenylsilane), DPEPO (bis[2-(diphenylphosphino)phenyl] ether oxide), 9-[3-(dibenzofuran-2-yl)phenyl]-9H-carbazole, 9-[3-(dibenzofuran-2-yl)phenyl]-9H-carbazole, 9-[3-(dibenzothiophen-2-yl)phenyl]-9H-carbazole, 9-[3,5-bis(2-dibenzofuranyl)phenyl]-9H-carbazole, 9-[3,5-bis(2-dibenzothiophenyl)phenyl]-9H-carbazole, T2T (2,4,6-tris(biphenyl-3-yl)-1,3,5-triazine), T3T (2,4,6-tris(triphenyl-3-yl)-1,3,5-triazine) and/or TST (2,4,6-tris(9,9'-spirobifluorene-2-yl)-1,3,5-triazine). The host material typically should be selected to exhibit

first triplet (T1) and first singlet (S1) energy levels, which are energetically higher than the first triplet (T1) and first singlet (S1) energy levels of the organic molecule.

In one embodiment of the invention, the EML comprises a so-called mixed-host system with at least one hole-dominant host and one electron-dominant host. In a particular embodiment, the EML comprises exactly one light emitting molecule according to the invention and a mixed-host system comprising T2T as electron-dominant host and a host selected from CBP, mCP, mCBP, 9-[3-(dibenzofuran-2-yl)phenyl]-9H-carbazole, 9-[3-(dibenzofuran-2-yl)phenyl]-9H-carbazole, 9-[3-(dibenzothiophen-2-yl)phenyl]-9H-carbazole, 9-[3,5-bis(2-dibenzofuranyl)phenyl]-9H-carbazole and 9-[3,5-bis(2-dibenzothiophenyl)phenyl]-9H-carbazole as hole-dominant host. In a further embodiment the EML comprises 50-80 % by weight, preferably 60-75 % by weight of a host selected from CBP, mCP, mCBP, 9-[3-(dibenzofuran-2-yl)phenyl]-9H-carbazole, 9-[3-(dibenzofuran-2-yl)phenyl]-9H-carbazole, 9-[3-(dibenzothiophen-2-yl)phenyl]-9H-carbazole, 9-[3,5-bis(2-dibenzofuranyl)phenyl]-9H-carbazole and 9-[3,5-bis(2-dibenzothiophenyl)phenyl]-9H-carbazole; 10-45 % by weight, preferably 15-30 % by weight of T2T and 5-40 % by weight, preferably 10-30 % by weight of light emitting molecule according to the invention.

Adjacent to the light-emitting layer EML an electron transport layer (ETL) may be located. Herein, any electron transporter may be used. Exemplarily, compounds poor of electrons such as, e.g., benzimidazoles, pyridines, triazoles, oxadiazoles (e.g., 1,3,4-oxadiazole), phosphinioxides and sulfone, may be used. An electron transporter may also be a star-shaped heterocycle such as 1,3,5-tri(1-phenyl-1H-benzo[d]imidazol-2-yl)phenyl (TPBi). The ETL may comprise NBphen (2,9-bis(naphthalen-2-yl)-4,7-diphenyl-1,10-phenanthroline), Alq3 (Aluminum-tris(8-hydroxyquinoline)), TSPO1 (diphenyl-4-triphenylsilylphenyl-phosphinoxide), BPyTP2 (2,7-di(2,2'-bipyridin-5-yl)triphenyle), Sif87 (dibenzo[b,d]thiophen-2-yltriphenylsilane), Sif88 (dibenzo[b,d]thiophen-2-yl)diphenylsilane, BmPyPhB (1,3-bis[3,5-di(pyridin-3-yl)phenyl]benzene) and/or BTB (4,4'-bis-[2-(4,6-diphenyl-1,3,5-triazinyl)]-1,1'-biphenyl). Optionally, the ETL may be doped with materials such as Liq. The electron transport layer (ETL) may also block holes or a holeblocking layer (HBL) is introduced.

The HBL may, for example, comprise BCP (2,9-dimethyl-4,7-diphenyl-1,10-phenanthroline = Bathocuproine), BALq (bis(8-hydroxy-2-methylquinoline)-(4-phenylphenoxy)aluminum), NBphen (2,9-bis(naphthalen-2-yl)-4,7-diphenyl-1,10-phenanthroline), Alq3 (Aluminum-tris(8-hydroxyquinoline)), TSPO1 (diphenyl-4-triphenylsilylphenyl-phosphinoxide), T2T (2,4,6-tris(biphenyl-3-yl)-1,3,5-triazine), T3T (2,4,6-tris(triphenyl-3-yl)-1,3,5-triazine), TST (2,4,6-

tris(9,9'-spirobifluorene-2-yl)-1,3,5-triazine), and/or TCB/TCP (1,3,5-tris(N-carbazolyl)benzol/1,3,5-tris(carbazol)-9-yl) benzene).

A cathode layer C may be located adjacent to the electron transport layer (ETL). For example, the cathode layer C may comprise or may consist of a metal (e.g., Al, Au, Ag, Pt, Cu, Zn, Ni, Fe, Pb, LiF, Ca, Ba, Mg, In, W, or Pd) or a metal alloy. For practical reasons, the cathode layer may also consist of (essentially) non-transparent metals such as Mg, Ca or Al. Alternatively or additionally, the cathode layer C may also comprise graphite and or carbon nanotubes (CNTs). Alternatively, the cathode layer C may also consist of nanoscale silver wires.

An OLED may further, optionally, comprise a protection layer between the electron transport layer (ETL) and the cathode layer C (which may be designated as electron injection layer (EIL)). This layer may comprise lithium fluoride, cesium fluoride, silver, Liq (8-hydroxyquinolinolitolithium), Li_2O , BaF_2 , MgO and/or NaF .

Optionally, also the electron transport layer (ETL) and/or a hole blocking layer (HBL) may comprise one or more host compounds.

In order to modify the emission spectrum and/or the absorption spectrum of the light-emitting layer EML further, the light-emitting layer EML may further comprise one or more further emitter molecule F. Such an emitter molecule F may be any emitter molecule known in the art. Preferably such an emitter molecule F is a molecule with a structure differing from the structure of the molecules according to the invention. The emitter molecule F may optionally be a TADF emitter. Alternatively, the emitter molecule F may optionally be a fluorescent and/or phosphorescent emitter molecule which is able to shift the emission spectrum and/or the absorption spectrum of the light-emitting layer EML. Exemplarily, the triplet and/or singlet excitons may be transferred from the emitter molecule according to the invention to the emitter molecule F before relaxing to the ground state S_0 by emitting light typically red-shifted in comparison to the light emitted by emitter molecule E. Optionally, the emitter molecule F may also provoke two-photon effects (i.e., the absorption of two photons of half the energy of the absorption maximum).

Optionally, an optoelectronic device (e.g., an OLED) may exemplarily be an essentially white optoelectronic device. Exemplarily such white optoelectronic device may comprise at least one (deep) blue emitter molecule and one or more emitter molecules emitting green and/or red light. Then, there may also optionally be energy transmittance between two or more molecules as described above.

As used herein, if not defined more specifically in the particular context, the designation of the colors of emitted and/or absorbed light is as follows:

violet: wavelength range of >380-420 nm;
deep blue: wavelength range of >420-480 nm;
sky blue: wavelength range of >480-500 nm;
green: wavelength range of >500-560 nm;
yellow: wavelength range of >560-580 nm;
orange: wavelength range of >580-620 nm;
red: wavelength range of >620-800 nm.

With respect to emitter molecules, such colors refer to the emission maximum. Therefore, exemplarily, a deep blue emitter has an emission maximum in the range of from >420 to 480 nm, a sky-blue emitter has an emission maximum in the range of from >480 to 500 nm, a green emitter has an emission maximum in a range of from >500 to 560 nm, a red emitter has an emission maximum in a range of from >620 to 800 nm.

A deep blue emitter may preferably have an emission maximum of below 480 nm, more preferably below 470 nm, even more preferably below 465 nm or even below 460 nm. It will typically be above 420 nm, preferably above 430 nm, more preferably above 440 nm or even above 450 nm.

Accordingly, a further aspect of the present invention relates to an OLED, which exhibits an external quantum efficiency at 1000 cd/m² of more than 8%, more preferably of more than 10%, more preferably of more than 13%, even more preferably of more than 15% or even more than 20% and/or exhibits an emission maximum between 420 nm and 500 nm, preferably between 430 nm and 490 nm, more preferably between 440 nm and 480 nm, even more preferably between 450 nm and 470 nm and/or exhibits a LT80 value at 500 cd/m² of more than 100 h, preferably more than 200 h, more preferably more than 400 h, even more preferably more than 750 h or even more than 1000 h. Accordingly, a further aspect of the present invention relates to an OLED, whose emission exhibits a CIE_y color coordinate of less than 0.45, preferably less than 0.30, more preferably less than 0.20 or even more preferably less than 0.15 or even less than 0.10.

A further aspect of the present invention relates to an OLED, which emits light at a distinct color point. According to the present invention, the OLED emits light with a narrow emission

band (small full width at half maximum (FWHM)). In one aspect, the OLED according to the invention emits light with a FWHM of the main emission peak of less than 0.50 eV, preferably less than 0.48 eV, more preferably less than 0.45 eV, even more preferably less than 0.43 eV or even less than 0.40 eV.

A further aspect of the present invention relates to an OLED, which emits light with CIE_x and CIE_y color coordinates close to the CIE_x (= 0.131) and CIE_y (= 0.046) color coordinates of the primary color blue (CIE_x = 0.131 and CIE_y = 0.046) as defined by ITU-R Recommendation BT.2020 (Rec. 2020) and thus is suited for the use in Ultra High Definition (UHD) displays, e.g. UHD-TVs. Accordingly, a further aspect of the present invention relates to an OLED, whose emission exhibits a CIE_x color coordinate of between 0.02 and 0.30, preferably between 0.03 and 0.25, more preferably between 0.05 and 0.20 or even more preferably between 0.08 and 0.18 or even between 0.10 and 0.15 and/ or a CIE_y color coordinate of between 0.00 and 0.45, preferably between 0.01 and 0.30, more preferably between 0.02 and 0.20 or even more preferably between 0.03 and 0.15 or even between 0.04 and 0.10.

In a further aspect, the invention relates to a method for producing an optoelectronic component. In this case an organic molecule of the invention is used.

The optoelectronic device, in particular the OLED according to the present invention can be produced by any means of vapor deposition and/or liquid processing. Accordingly, at least one layer is

- prepared by means of a sublimation process,
- prepared by means of an organic vapor phase deposition process,
- prepared by means of a carrier gas sublimation process,
- solution processed or printed.



The methods used to produce the optoelectronic device, in particular the OLED according to the present invention are known in the art. The different layers are individually and successively deposited on a suitable substrate by means of subsequent deposition processes. The individual layers may be deposited using the same or differing deposition methods.

Vapor deposition processes exemplarily comprise thermal (co)evaporation, chemical vapor deposition and physical vapor deposition. For active matrix OLED display, an AMOLED backplane is used as substrate. The individual layer may be processed from solutions or dispersions employing adequate solvents. Solution deposition process exemplarily comprise spin coating, dip coating and jet printing. Liquid processing may optionally be carried out in an

inert atmosphere (e.g., in a nitrogen atmosphere) and the solvent may optionally be completely or partially removed by means known in the state of the art.


Examples

General synthesis scheme I

General procedure for synthesis **AAV1**:

2-fluorophenyl-1,3-diboronic acid pinacol ester (1.00 equivalents), 2-chloro-4,6-diphenyl-1,3,5-triazine (2.50 equivalents), tetrakis(triphenylphosphine)palladium(0) (0.05 equivalent), and tribasic potassium phosphate (3.00 equivalents) are stirred under nitrogen atmosphere in a tetrahydrofuran (THF)/water mixture (ratio of 2:1) at 80 °C for 5 h. After cooling down to room temperature (rt), the crude product is precipitated by adding dichloromethane to the reaction mixture. The precipitate is filtered off, washed with dichloromethane and subsequently dried in vacuo. The desired compound was obtained as a solid with 66% yield. It was used for further conversions without purification.

General procedure for synthesis **AAV2**:



Z1 (1 equivalent each), the corresponding donor molecule D-H (1.00 equivalent) and tribasic potassium phosphate (2.00 equivalents) are suspended under nitrogen atmosphere in DMSO and stirred at 120 °C (16 h). After chilling to rt the reaction mixture is poured into water in order to precipitate the organics. The precipitate is filtered off (fiber glass filter), washed with water and subsequently dissolved in dichloromethane. If no precipitation is observed, dichloromethane is added, the phases separated and the organic layer washed with water. The resulting solution or the organic layer, respectively, is dried over MgSO₄, filtrated and concentrated. The crude product is purified by recrystallization or by flash chromatography. The product is obtained as a solid.

In particular, the donor molecule D-H is a 3,6-substituted carbazole (e.g., 3,6-dimethylcarbazole, 3,6-diphenylcarbazole, 3,6-di-tert-butylcarbazole), a 2,7-substituted carbazole (e.g., 2,7-dimethylcarbazole, 2,7-diphenylcarbazole, 2,7-di-tert-butylcarbazole), a 1,8-substituted carbazole (e.g., 1,8-dimethylcarbazole, 1,8-diphenylcarbazole, 1,8-di-tert-butylcarbazole), a 1-substituted carbazole (e.g., 1-methylcarbazole, 1-phenylcarbazole, 1-tert-butylcarbazole), a 2-substituted carbazole (e.g., 2-methylcarbazole, 2-phenylcarbazole, 2-tert-butylcarbazole), or a 3-substituted carbazole (e.g., 3-methylcarbazole, 3-phenylcarbazole, 3-tert-butylcarbazole).

For example, a halogen-substituted carbazole, particularly 3-bromocarbazole, can be used as D-H.

In a subsequent reaction, a boronic acid ester functional group or boronic acid functional group may, for example, be introduced at the position of the one or more halogen substituents, which was introduced via D-H, to yield the corresponding carbazol-3-ylboronic acid ester or carbazol-3-ylboronic acid, e.g., via the reaction with bis(pinacolato)diboron (CAS No. 73183-34-3). Subsequently, one or more substituents R^a may be introduced in place of the boronic acid ester group or the boronic acid group via a coupling reaction with the corresponding halogenated reactant R^a-Hal, preferably R^a-Cl and R^a-Br.

Alternatively, one or more substituents R^a may be introduced at the position of the one or more halogen substituents, which was introduced via D-H, via the reaction with a boronic acid of the substituent R^a [R^a-B(OH)₂] or a corresponding boronic acid ester.

HPLC-MS:

HPLC-MS spectroscopy is performed on a HPLC by Agilent (1100 series) with MS-detector (Thermo LTQ XL). A reverse phase column 4,6mm x 150mm, particle size 5,0 μm from Waters (without pre-column) is used in the HPLC. The HPLC-MS measurements are performed at room temperature (rt) with the solvents acetonitrile, water and THF in the following concentrations:

solvent A:	H ₂ O (90%)	MeCN (10%)
solvent B:	H ₂ O (10%)	MeCN (90%)
solvent C:	THF (100%)	

From a solution with a concentration of 0.5mg/ml an injection volume of 15 μL is taken for the measurements. The following gradient is used:

Flow rate [ml/min]	time [min]	A[%]	B[%]	D[%]
3	0	40	50	10
3	10	10	15	75
3	16	10	15	75
3	16.01	40	50	10
3	20	40	50	10

Ionisation of the probe is performed by APCI (atmospheric pressure chemical ionization).

Cyclic voltammetry

Cyclic voltammograms are measured from solutions having concentration of 10⁻³ mol/l of the organic molecules in dichloromethane or a suitable solvent and a suitable supporting electrolyte (e.g. 0.1 mol/l of tetrabutylammonium hexafluorophosphate). The measurements are conducted at room temperature under nitrogen atmosphere with a three-electrode assembly (Working and counter electrodes: Pt wire, reference electrode: Pt wire) and calibrated using FeCp₂/FeCp₂⁺ as internal standard. The HOMO data was corrected using ferrocene as internal standard against a saturated calomel electrode (SCE).

Density functional theory calculation

Molecular structures are optimized employing the BP86 functional and the resolution of identity approach (RI). Excitation energies are calculated using the (BP86) optimized structures employing Time-Dependent DFT (TD-DFT) methods. Orbital and excited state energies are

calculated with the B3LYP functional. Def2-SVP basis sets (and a m4-grid for numerical integration) are used. The Turbomole program package is used for all calculations.

Photophysical measurements

Sample pretreatment: Spin-coating

Apparatus: Spin150, SPS euro.

The sample concentration is 10 mg/ml, dissolved in a suitable solvent.

Program: 1) 3 s at 400 U/min; 20 s at 1000 U/min at 1000 Upm/s. 3) 10 s at 4000 U/min at 1000 Upm/s. After coating, the films are dried at 70 °C for 1 min.

Photoluminescence spectroscopy and TCSPC (*Time-correlated single-photon counting*)

Steady-state emission spectroscopy is measured by a Horiba Scientific, Model FluoroMax-4 equipped with a 150 W Xenon-Arc lamp, excitation- and emission monochromators and a Hamamatsu R928 photomultiplier and a time-correlated single-photon counting option. Emission and excitation spectra are corrected using standard correction fits.

Excited state lifetimes are determined employing the same system using the TCSPC method with FM-2013 equipment and a Horiba Yvon TCSPC hub.

Excitation sources:

NanoLED 370 (wavelength: 371 nm, pulse duration: 1,1 ns)

NanoLED 290 (wavelength: 294 nm, pulse duration: <1 ns)

SpectraLED 310 (wavelength: 314 nm)

SpectraLED 355 (wavelength: 355 nm).

Data analysis (exponential fit) is done using the software suite DataStation and DAS6 analysis software. The fit is specified using the chi-squared-test.

Photoluminescence quantum yield measurements

For photoluminescence quantum yield (PLQY) measurements an *Absolute PL Quantum Yield Measurement C9920-03G* system (Hamamatsu Photonics) is used. Quantum yields and CIE coordinates are determined using the software U6039-05 version 3.6.0.

Emission maxima are given in nm, quantum yields Φ in % and CIE coordinates as x,y values. PLQY is determined using the following protocol:

- 1) Quality assurance: Anthracene in ethanol (known concentration) is used as reference.
- 2) Excitation wavelength: the absorption maximum of the organic molecule is determined and the molecule is excited using this wavelength.
- 3) Measurement

Quantum yields are measured for sample of solutions or films under nitrogen atmosphere. The yield is calculated using the equation:

$$\Phi_{PL} = \frac{n_{\text{photon, emitted}}}{n_{\text{photon, absorbed}}} = \frac{\int \frac{\lambda}{hc} [Int_{\text{emitted}}^{\text{sample}}(\lambda) - Int_{\text{absorbed}}^{\text{sample}}(\lambda)] d\lambda}{\int \frac{\lambda}{hc} [Int_{\text{emitted}}^{\text{reference}}(\lambda) - Int_{\text{absorbed}}^{\text{reference}}(\lambda)] d\lambda}$$

wherein n_{photon} denotes the photon count and $Int.$ the intensity.

Production and characterization of optoelectronic devices

OLED devices comprising organic molecules according to the invention can be produced via vacuum-deposition methods. If a layer contains more than one compound, the weight-percentage of one or more compounds is given in %. The total weight-percentage values amount to 100 %, thus if a value is not given, the fraction of this compound equals to the difference between the given values and 100%.

The not fully optimized OLEDs are characterized using standard methods and measuring electroluminescence spectra, the external quantum efficiency (in %) in dependency on the intensity, calculated using the light detected by the photodiode, and the current. The OLED device lifetime is extracted from the change of the luminance during operation at constant current density. The LT50 value corresponds to the time, where the measured luminance decreased to 50 % of the initial luminance, analogously LT80 corresponds to the time point, at which the measured luminance decreased to 80 % of the initial luminance, LT 95 to the time point, at which the measured luminance decreased to 95 % of the initial luminance etc.


Accelerated lifetime measurements are performed (e.g. applying increased current densities). Exemplarily LT80 values at 500 cd/m² are determined using the following equation:

$$LT80\left(500 \frac{cd^2}{m^2}\right) = LT80(L_0) \left(\frac{L_0}{500 \frac{cd^2}{m^2}}\right)^{1.6}$$


wherein L_0 denotes the initial luminance at the applied current density.

The values correspond to the average of several pixels (typically two to eight), the standard deviation between these pixels is given.

Example 1




Example 1 was synthesized according to **AAV1** (66% yield), **AAV2** (86% yield), wherein 3-bromocarbazole was used as donor molecule D-H, and the following reactions:



MS (HPLC-MS), m/z (26.27 min): 936.70

Figure 1 depicts the emission spectrum of example 1 (10% by weight in PMMA). The emission maximum is at 459 nm. The photoluminescence quantum yield (PLQY) is 52%, the full width at half maximum is 0.43 eV, and the emission lifetime is 13 μs . The CIE_x value is 0.16 and CIE_y value is 0.17.

The emission maximum of example 1 (for 1% by weight in PMMA) is at 444 nm.

Example 2

Example **2** was synthesized according to **AAV1** (66% yield) and **AAV2** (69% yield).

MS (HPLC-MS), m/z (11.57 min): 705.33


Figure 2 depicts the emission spectrum of example **2** (10% by weight in PMMA). The emission maximum is at 472 nm. The photoluminescence quantum yield (PLQY) is 80%, the full width at half maximum is 0.42 eV, and the emission lifetime is 6 μ s. The CIE_x value is 0.17 and CIE_y value is 0.42. The energy of the highest occupied molecular orbital E^{HOMO} of example **2** is -6.01 eV.

The emission maximum of example **2** for 1% by weight in PMMA is at 461 nm.

Example D1


Example **1** was tested in the OLED **D1**, which was fabricated with the following layer structure:










Layer No.	Thickness	D1
10	100 nm	Al
9	2 nm	Liq
8	20 nm	NBPhen
7	10 nm	MAT1
6	50 nm	Example 1 (20%): mCBP (80%)
5	10 nm	mCBP
4	10 nm	TCTA
3	40 nm	NPB
2	5 nm	HAT-CN
1	50 nm	ITO
substrate		glass





Device **D1** yielded an external quantum efficiency (EQE) at 1000 cd/m² of (14.5 \pm 0.1)%. The emission maximum is at 475 nm with a FWHM of 69 nm at 6 V. The corresponding CIE_x value is 0.16 and CIE_y is 0.29.


Additional Examples Of Organic Molecules According To The Invention











Figures


Figure 1 Emission spectrum of example 1 (10% by weight) in PMMA.

Figure 2 Emission spectrum of example 2 (10% by weight) in PMMA.

Claims

1. Organic molecule, comprising


- one first chemical moiety comprising a structure of Formula I,



Formula I

and

- one second chemical moiety comprising a structure of Formula II,



Formula II

wherein the first chemical moiety is linked to the second chemical moiety via a single bond;

wherein

§ represents the binding site of a single bond linking the first chemical moiety to the second chemical moiety;

represents the binding site of a single bond linking the second chemical moiety to the first chemical moiety;

Z is at each occurrence independently from another selected from the group consisting of a direct bond, CR³R⁴, C=CR³R⁴, C=O, C=NR³, NR³, O, SiR³R⁴, S, S(O) and S(O)₂;

R¹¹ is at each occurrence independently from another selected from the group consisting of hydrogen, deuterium, C₁-C₅-alkyl,

wherein one or more hydrogen atoms are optionally substituted by deuterium;
C₂-C₈-alkenyl,

wherein one or more hydrogen atoms are optionally substituted by deuterium;
C₂-C₈-alkynyl,

wherein one or more hydrogen atoms are optionally substituted by deuterium;
C₆-C₁₈-aryl,

which is optionally substituted with one or more substituents R⁶; and
C₃-C₁₇-heteroaryl,

which is optionally substituted with one or more substituents R⁶;

R¹² is at each occurrence independently from another selected from the group consisting of
hydrogen, deuterium,

C₁-C₅-alkyl,

wherein one or more hydrogen atoms are optionally substituted by deuterium;

C₂-C₈-alkenyl,

wherein one or more hydrogen atoms are optionally substituted by deuterium;

C₂-C₈-alkynyl,

wherein one or more hydrogen atoms are optionally substituted by deuterium;

C₆-C₁₈-aryl,

which is optionally substituted with one or more substituents R⁶; and

C₃-C₁₇-heteroaryl,

which is optionally substituted with one or more substituents R⁶;

R^{II}, R^{III} and R^{IV} is independently from another selected from the group consisting of
hydrogen, deuterium,

C₁-C₅-alkyl,

wherein one or more hydrogen atoms are optionally substituted by deuterium;

C₂-C₈-alkenyl,

wherein one or more hydrogen atoms are optionally substituted by deuterium;

C₂-C₈-alkynyl,

wherein one or more hydrogen atoms are optionally substituted by deuterium; and

C₆-C₁₈-aryl,

which is optionally substituted with one or more substituents R⁶;

R^a, R³ and R⁴ is at each occurrence independently from another selected from the group
consisting of: hydrogen, deuterium, N(R⁵)₂, OR⁵, Si(R⁵)₃, B(OR⁵)₂, OSO₂R⁵, CF₃, CN, F, Br, I,
C₁-C₄₀-alkyl,

which is optionally substituted with one or more substituents R^5 and wherein one or more non-adjacent CH_2 -groups are optionally substituted by $R^5C=CR^5$, $C\equiv C$, $Si(R^5)_2$, $Ge(R^5)_2$, $Sn(R^5)_2$, $C=O$, $C=S$, $C=Se$, $C=NR^5$, $P(=O)(R^5)$, SO , SO_2 , NR^5 , O , S or $CONR^5$;

C_1 - C_{40} -alkoxy,

which is optionally substituted with one or more substituents R^5 and wherein one or more non-adjacent CH_2 -groups are optionally substituted by $R^5C=CR^5$, $C\equiv C$, $Si(R^5)_2$, $Ge(R^5)_2$, $Sn(R^5)_2$, $C=O$, $C=S$, $C=Se$, $C=NR^5$, $P(=O)(R^5)$, SO , SO_2 , NR^5 , O , S or $CONR^5$;

C_1 - C_{40} -thioalkoxy,

which is optionally substituted with one or more substituents R^5 and wherein one or more non-adjacent CH_2 -groups are optionally substituted by $R^5C=CR^5$, $C\equiv C$, $Si(R^5)_2$, $Ge(R^5)_2$, $Sn(R^5)_2$, $C=O$, $C=S$, $C=Se$, $C=NR^5$, $P(=O)(R^5)$, SO , SO_2 , NR^5 , O , S or $CONR^5$;

C_2 - C_{40} -alkenyl,

which is optionally substituted with one or more substituents R^5 and wherein one or more non-adjacent CH_2 -groups are optionally substituted by $R^5C=CR^5$, $C\equiv C$, $Si(R^5)_2$, $Ge(R^5)_2$, $Sn(R^5)_2$, $C=O$, $C=S$, $C=Se$, $C=NR^5$, $P(=O)(R^5)$, SO , SO_2 , NR^5 , O , S or $CONR^5$;

C_2 - C_{40} -alkynyl,

which is optionally substituted with one or more substituents R^5 and wherein one or more non-adjacent CH_2 -groups are optionally substituted by $R^5C=CR^5$, $C\equiv C$, $Si(R^5)_2$, $Ge(R^5)_2$, $Sn(R^5)_2$, $C=O$, $C=S$, $C=Se$, $C=NR^5$, $P(=O)(R^5)$, SO , SO_2 , NR^5 , O , S or $CONR^5$;

C_6 - C_{60} -aryl,

which is optionally substituted with one or more substituents R^5 ; and

C_3 - C_{57} -heteroaryl,

which is optionally substituted with one or more substituents R^5 ;

R^5 is at each occurrence independently from another selected from the group consisting of: hydrogen, deuterium, $N(R^6)_2$, OR^6 , $Si(R^6)_3$, $B(OR^6)_2$, OSO_2R^6 , CF_3 , CN , F , Br , I ,

C_1 - C_{40} -alkyl,

which is optionally substituted with one or more substituents R^6 and wherein one or more non-adjacent CH_2 -groups are optionally substituted by $R^6C=CR^6$, $C\equiv C$, $Si(R^6)_2$, $Ge(R^6)_2$, $Sn(R^6)_2$, $C=O$, $C=S$, $C=Se$, $C=NR^6$, $P(=O)(R^6)$, SO , SO_2 , NR^6 , O , S or $CONR^6$;

C_1 - C_{40} -alkoxy,

which is optionally substituted with one or more substituents R^6 and

wherein one or more non-adjacent CH₂-groups are optionally substituted by R⁶C=CR⁶, C≡C, Si(R⁶)₂, Ge(R⁶)₂, Sn(R⁶)₂, C=O, C=S, C=Se, C=NR⁶, P(=O)(R⁶), SO, SO₂, NR⁶, O, S or CONR⁶;

C₁-C₄₀-thioalkoxy,

which is optionally substituted with one or more substituents R⁶ and

wherein one or more non-adjacent CH₂-groups are optionally substituted by R⁶C=CR⁶, C≡C, Si(R⁶)₂, Ge(R⁶)₂, Sn(R⁶)₂, C=O, C=S, C=Se, C=NR⁶, P(=O)(R⁶), SO, SO₂, NR⁶, O, S or CONR⁶;

C₂-C₄₀-alkenyl,

which is optionally substituted with one or more substituents R⁶ and

wherein one or more non-adjacent CH₂-groups are optionally substituted by R⁶C=CR⁶, C≡C, Si(R⁶)₂, Ge(R⁶)₂, Sn(R⁶)₂, C=O, C=S, C=Se, C=NR⁶, P(=O)(R⁶), SO, SO₂, NR⁶, O, S or CONR⁶;

C₂-C₄₀-alkynyl,

which is optionally substituted with one or more substituents R⁶ and

wherein one or more non-adjacent CH₂-groups are optionally substituted by R⁶C=CR⁶, C≡C, Si(R⁶)₂, Ge(R⁶)₂, Sn(R⁶)₂, C=O, C=S, C=Se, C=NR⁶, P(=O)(R⁶), SO, SO₂, NR⁶, O, S or CONR⁶;

C₆-C₆₀-aryl,

which is optionally substituted with one or more substituents R⁶; and

C₃-C₅₇-heteroaryl,

which is optionally substituted with one or more substituents R⁶;

R⁶ is at each occurrence independently from another selected from the group consisting of: hydrogen, deuterium, OPh, CF₃, CN, F,

C₁-C₅-alkyl,

wherein one or more hydrogen atoms are optionally, independently from each other substituted by deuterium, CN, CF₃, or F;

C₁-C₅-alkoxy,

wherein one or more hydrogen atoms are optionally, independently from each other substituted by deuterium, CN, CF₃, or F;

C₁-C₅-thioalkoxy,

wherein one or more hydrogen atoms are optionally, independently from each other substituted by deuterium, CN, CF₃, or F;

C₂-C₅-alkenyl,

wherein one or more hydrogen atoms are optionally, independently from each other substituted by deuterium, CN, CF₃, or F;

C₂-C₅-alkynyl,

wherein one or more hydrogen atoms are optionally, independently from each other substituted by deuterium, CN, CF₃, or F;

C₆-C₁₈-aryl,

which is optionally substituted with one or more C₁-C₅-alkyl substituents ;

C₃-C₁₇-heteroaryl,

which is optionally substituted with one or more C₁-C₅-alkyl substituents ;

N(C₆-C₁₈-aryl)₂;

N(C₃-C₁₇-heteroaryl)₂, and

N(C₃-C₁₇-heteroaryl)(C₆-C₁₈-aryl);

wherein the substituents R^a, R³, R⁴ or R⁵ independently from each other optionally form a mono- or polycyclic, aliphatic, aromatic and/or benzo-fused ring system with one or more substituents R^a, R³, R⁴ or R⁵.

2. The organic molecule according to claim 1, wherein R¹¹ and R¹² is independently from each other at each occurrence selected from the group consisting of

H, methyl,

phenyl, which is optionally substituted with one or more substituents R⁶;


1,3,5-triazinyl, which is optionally substituted with one or more substituents R⁶;

pyridinyl, which is optionally substituted with one or more substituents R⁶;

pyrimidyl, which is optionally substituted with one or more substituents R⁶.

3. The organic molecule according to claim 1 or 2, wherein R^{II}, R^{III}, and R^{IV} is independently from each other at each occurrence selected from the group consisting of H, methyl and phenyl.


4. The organic molecule according to one or more of claims 1 to 3, wherein the second chemical moiety comprises a structure of Formula IIa:



Formula IIa

wherein # and R^a are defined as in claim 1.

5. The organic molecule according to one or more of claims 1 to 4, wherein the second chemical moiety comprises a structure of Formula IIb:



Formula IIb

wherein

R^b is at each occurrence independently from another selected from the group consisting of hydrogen, deuterium, $N(R^5)_2$, OR^5 , $Si(R^5)_3$, $B(OR^5)_2$, OSO_2R^5 , CF_3 , CN, F, Br, I,

C_1 - C_{40} -alkyl,

which is optionally substituted with one or more substituents R^5 and

wherein one or more non-adjacent CH_2 -groups are optionally substituted by $R^5C=CR^5$, $C\equiv C$, $Si(R^5)_2$, $Ge(R^5)_2$, $Sn(R^5)_2$, $C=O$, $C=S$, $C=Se$, $C=NR^5$, $P(=O)(R^5)$, SO, SO_2 , NR^5 , O, S or $CONR^5$;

C_1 - C_{40} -alkoxy,

which is optionally substituted with one or more substituents R^5 and

wherein one or more non-adjacent CH_2 -groups are optionally substituted by $R^5C=CR^5$, $C\equiv C$, $Si(R^5)_2$, $Ge(R^5)_2$, $Sn(R^5)_2$, $C=O$, $C=S$, $C=Se$, $C=NR^5$, $P(=O)(R^5)$, SO, SO_2 , NR^5 , O, S or $CONR^5$;

C_1 - C_{40} -thioalkoxy,

which is optionally substituted with one or more substituents R^5 and

wherein one or more non-adjacent CH_2 -groups are optionally substituted by $R^5C=CR^5$, $C\equiv C$, $Si(R^5)_2$, $Ge(R^5)_2$, $Sn(R^5)_2$, $C=O$, $C=S$, $C=Se$, $C=NR^5$, $P(=O)(R^5)$, SO, SO_2 , NR^5 , O, S or $CONR^5$;

C_2 - C_{40} -alkenyl,

which is optionally substituted with one or more substituents R^5 and

wherein one or more non-adjacent CH_2 -groups are optionally substituted by $R^5C=CR^5$, $C\equiv C$, $Si(R^5)_2$, $Ge(R^5)_2$, $Sn(R^5)_2$, $C=O$, $C=S$, $C=Se$, $C=NR^5$, $P(=O)(R^5)$, SO, SO_2 , NR^5 , O, S or $CONR^5$;

C_2 - C_{40} -alkynyl,

which is optionally substituted with one or more substituents R^5 and

wherein one or more non-adjacent CH_2 -groups are optionally substituted by $R^5C=CR^5$, $C\equiv C$, $Si(R^5)_2$, $Ge(R^5)_2$, $Sn(R^5)_2$, $C=O$, $C=S$, $C=Se$, $C=NR^5$, $P(=O)(R^5)$, SO, SO_2 , NR^5 , O, S or $CONR^5$;

C₆-C₆₀-aryl,


which is optionally substituted with one or more substituents R⁵; and

C₃-C₅₇-heteroaryl,

which is optionally substituted with one or more substituents R⁵;

and wherein apart from that the definitions in claim 1 apply.

6. The organic molecule according to one or more of claims 1 to 4, wherein the second chemical moiety comprises a structure of Formula IIc:



Formula IIc

wherein

R^b is at each occurrence independently from another selected from the group consisting of: hydrogen, deuterium, N(R⁵)₂, OR⁵, Si(R⁵)₃, B(OR⁵)₂, OSO₂R⁵, CF₃, CN, F, Br, I,

C₁-C₄₀-alkyl,

which is optionally substituted with one or more substituents R⁵ and

wherein one or more non-adjacent CH₂-groups are optionally substituted by R⁵C=CR⁵, C≡C, Si(R⁵)₂, Ge(R⁵)₂, Sn(R⁵)₂, C=O, C=S, C=Se, C=NR⁵, P(=O)(R⁵), SO, SO₂, NR⁵, O, S or CONR⁵;

C₁-C₄₀-alkoxy,

which is optionally substituted with one or more substituents R⁵ and

wherein one or more non-adjacent CH₂-groups are optionally substituted by R⁵C=CR⁵, C≡C, Si(R⁵)₂, Ge(R⁵)₂, Sn(R⁵)₂, C=O, C=S, C=Se, C=NR⁵, P(=O)(R⁵), SO, SO₂, NR⁵, O, S or CONR⁵;

C₁-C₄₀-thioalkoxy,

which is optionally substituted with one or more substituents R⁵ and

wherein one or more non-adjacent CH₂-groups are optionally substituted by R⁵C=CR⁵, C≡C, Si(R⁵)₂, Ge(R⁵)₂, Sn(R⁵)₂, C=O, C=S, C=Se, C=NR⁵, P(=O)(R⁵), SO, SO₂, NR⁵, O, S or CONR⁵;

C₂-C₄₀-alkenyl,

which is optionally substituted with one or more substituents R⁵ and

wherein one or more non-adjacent CH₂-groups are optionally substituted by R⁵C=CR⁵, C≡C, Si(R⁵)₂, Ge(R⁵)₂, Sn(R⁵)₂, C=O, C=S, C=Se, C=NR⁵, P(=O)(R⁵), SO, SO₂, NR⁵, O, S or CONR⁵;

C₂-C₄₀-alkynyl,

which is optionally substituted with one or more substituents R⁵ and

wherein one or more non-adjacent CH₂-groups are optionally substituted by R⁵C=CR⁵, C≡C, Si(R⁵)₂, Ge(R⁵)₂, Sn(R⁵)₂, C=O, C=S, C=Se, C=NR⁵, P(=O)(R⁵), SO, SO₂, NR⁵, O, S or CONR⁵;

C₆-C₆₀-aryl,

which is optionally substituted with one or more substituents R⁵; and

C₃-C₅₇-heteroaryl,

which is optionally substituted with one or more substituents R⁵;

and wherein apart from that the definitions in claim 1 apply.

7. The organic molecule according to claim 5 or 6, wherein R^b is at each occurrence independently from another selected from the group consisting of:

- Me, ⁱPr, ^tBu, CN, CF₃,
 - Ph, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃ and Ph;
 - pyridinyl, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃ and Ph;
 - pyrimidinyl, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃ and Ph;
 - carbazolyl, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃ and Ph;
 - triazinyl, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃, and Ph;
- and
- N(Ph)₂.

8. The organic molecule according to claim 5 or 6, wherein R^b is at each occurrence independently from another selected from the group consisting of:

- pyridinyl, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃ and Ph;
- pyrimidinyl, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃ and Ph;
- carbazolyl, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃ and Ph;
- triazinyl, which is optionally substituted with one or more substituents independently from each other selected from the group consisting of Me, ⁱPr, ^tBu, CN, CF₃, and Ph;

and

- N(Ph)₂.

9. Use of molecule according to one or more of claims 1 to 8 as luminescent emitter and/or a host material and/or an electron transport material and/or a hole injection material and/or a hole blocking material in an optoelectronic device.

10. The use according to claim 9, wherein the optoelectronic device is selected from the group consisting of:

- organic light-emitting diodes (OLEDs),
- light-emitting electrochemical cells,
- OLED-sensors,
- organic diodes,
- organic solar cells,
- organic transistors,
- organic field-effect transistors,
- organic lasers and
- down-conversion elements.

11. Composition, comprising:

- (a) at least one organic molecule according to one or more of claims 1 to 8, in particular in the form of an emitter and/or a host, and
- (b) one or more emitter and/or host materials, which differ from the organic molecule of one or more of claims 1 to 8 and
- (c) optionally, one or more dyes and/or one or more solvents.

12. Optoelectronic device, comprising an organic molecule according to one or more of claims 1 to 8 or a composition according to claim 11, in particular in form of a device selected from the group consisting of organic light-emitting diode (OLED), light-emitting electrochemical cell, OLED-sensor, organic diode, organic solar cell, organic transistor, organic field-effect transistor, organic laser and down-conversion element.

13. The optoelectronic device according to claim 12, comprising

- a substrate,
- an anode, and
- a cathode, wherein the anode or the cathode are disposed on the substrate and

- at least one light-emitting layer, which is arranged between the anode and the cathode and which comprises the organic molecule according to any of claims 1 to 8 or a composition according to claim 11.

14. Method for producing an optoelectronic device, wherein an organic molecule according to any one of claims 1 to 8 or a composition according to claim 11 is used, in particular comprising the processing of the organic molecule using a vacuum evaporation method or from a solution.

15. The method according to claim 14, comprising the processing of the organic molecule using a vacuum evaporation method or from a solution.

Figures

Figure 1





Figure 2



INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2018/083054

A. CLASSIFICATION OF SUBJECT MATTER
INV. C07D403/14 H01L51/50
ADD.
According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED
Minimum documentation searched (classification system followed by classification symbols)
C07D H01L
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
EPO-Internal, WPI Data, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 2014/146752 A1 (MERCK PATENT GMBH [DE]) 25 September 2014 (2014-09-25) page 30; compound 13 page 33; compounds 43, 45 page 34; compounds 46, 47 page 35; compound 58 page 90; compound S79 -----	1-15

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier application or patent but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- "&" document member of the same patent family

Date of the actual completion of the international search 1 March 2019	Date of mailing of the international search report 11/03/2019
--	---

Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer Panday, Narendra
--	---

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2018/083054

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 2014146752	A1	25-09-2014	
		CN 105051014 A	11-11-2015
		CN 107739352 A	27-02-2018
		EP 2976329 A1	27-01-2016
		EP 3375785 A1	19-09-2018
		JP 2016516085 A	02-06-2016
		JP 2018184404 A	22-11-2018
		KR 20150132872 A	26-11-2015
		US 2016072076 A1	10-03-2016
		WO 2014146752 A1	25-09-2014
