



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>C09D 125/06, 125/02, 125/16, 125/14, 133/02, 133/08, 133/10</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 98/10026</b> <b>(43) International Publication Date:</b> 12 March 1998 (12.03.98)
<b>(21) International Application Number:</b> PCT/AU97/00584 <b>(22) International Filing Date:</b> 8 September 1997 (08.09.97) <b>(30) Priority Data:</b> PO 2163 6 September 1996 (06.09.96) AU <b>(71) Applicant (for all designated States except US):</b> ICI AUSTRALIA OPERATIONS PROPRIETARY LIMITED [AU/AU]; 1 Nicholson Street, Melbourne, VIC 3000 (AU). <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only):</b> CAREY, Michelle [AU/AU]; 2/14 Newry Street, Prahran, VIC 3181 (AU). ELSBURY, Karen [AU/GB]; 11 Park Drive, Acton, London W3 8ND (GB). HOULIHAN, Patrick [AU/AU]; 1/23 Denham Street, Hawthorn, VIC 3122 (AU). LEARY, Bruce [AU/AU]; Cnr Boundary and Mornington Flinders Road, Red Hill, VIC 3937 (AU). MADIGAN, Lisa [AU/AU]; 10 Vail Street, Prahran, VIC 3181 (AU). WEERASINGHE, Thamala [LK/AU]; 9 Settlers Court, Rowville, VIC 3178 (AU). MARISE, Chantel [AU/AU]; G02/101 Grattan Street, Carlton, VIC 3053 (AU). GEORGE, Susan [AU/AU]; 4/1 Howard Court, Clayton, VIC 3168 (AU).	<b>(74) Agent:</b> CARTER SMITH & BEADLE; P.O. Box 557, Camberwell, VIC 3124 (AU). <b>(81) Designated States:</b> AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). <b>Published</b> <i>With international search report.</i> <i>With amended claims and statement.</i>	
<b>(54) Title:</b> STAIN RESISTANT WATER-BORNE COATING COMPOSITION		
<b>(57) Abstract</b> <p>Aqueous coating compositions are described where the binder includes an anionically stabilised addition polymerised polymeric dispersion. The monomers used to prepare the dispersion are acrylic acid and methacrylic acid as a carboxylic monomer and styrene, alpha methyl styrene or vinyl toluene as a hydrophobic high Tg aromatic monomer and an alkyl acrylate ester as a low Tg monomer. The relative weight proportions of the monomers are required to satisfy a formula. Blends of high and low Tg dispersions are also described. Paints formulated with the binders exhibit an excellent balance of stain resistance, tint strength and viscosity stability.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

<b>AL</b>	Albania	<b>ES</b>	Spain	<b>LS</b>	Lesotho	<b>SI</b>	Slovenia
<b>AM</b>	Armenia	<b>FI</b>	Finland	<b>LT</b>	Lithuania	<b>SK</b>	Slovakia
<b>AT</b>	Austria	<b>FR</b>	France	<b>LU</b>	Luxembourg	<b>SN</b>	Senegal
<b>AU</b>	Australia	<b>GA</b>	Gabon	<b>LV</b>	Latvia	<b>SZ</b>	Swaziland
<b>AZ</b>	Azerbaijan	<b>GB</b>	United Kingdom	<b>MC</b>	Monaco	<b>TD</b>	Chad
<b>BA</b>	Bosnia and Herzegovina	<b>GE</b>	Georgia	<b>MD</b>	Republic of Moldova	<b>TG</b>	Togo
<b>BB</b>	Barbados	<b>GH</b>	Ghana	<b>MG</b>	Madagascar	<b>TJ</b>	Tajikistan
<b>BE</b>	Belgium	<b>GN</b>	Guinea	<b>MK</b>	The former Yugoslav Republic of Macedonia	<b>TM</b>	Turkmenistan
<b>BF</b>	Burkina Faso	<b>GR</b>	Greece	<b>ML</b>	Mali	<b>TR</b>	Turkey
<b>BG</b>	Bulgaria	<b>HU</b>	Hungary	<b>MN</b>	Mongolia	<b>TT</b>	Trinidad and Tobago
<b>BJ</b>	Benin	<b>IE</b>	Ireland	<b>MR</b>	Mauritania	<b>UA</b>	Ukraine
<b>BR</b>	Brazil	<b>IL</b>	Israel	<b>MW</b>	Malawi	<b>UG</b>	Uganda
<b>BY</b>	Belarus	<b>IS</b>	Iceland	<b>MX</b>	Mexico	<b>US</b>	United States of America
<b>CA</b>	Canada	<b>IT</b>	Italy	<b>NE</b>	Niger	<b>UZ</b>	Uzbekistan
<b>CF</b>	Central African Republic	<b>JP</b>	Japan	<b>NL</b>	Netherlands	<b>VN</b>	Viet Nam
<b>CG</b>	Congo	<b>KE</b>	Kenya	<b>NO</b>	Norway	<b>YU</b>	Yugoslavia
<b>CH</b>	Switzerland	<b>KG</b>	Kyrgyzstan	<b>NZ</b>	New Zealand	<b>ZW</b>	Zimbabwe
<b>CI</b>	Côte d'Ivoire	<b>KP</b>	Democratic People's Republic of Korea	<b>PL</b>	Poland		
<b>CM</b>	Cameroon	<b>KR</b>	Republic of Korea	<b>PT</b>	Portugal		
<b>CN</b>	China	<b>KZ</b>	Kazakstan	<b>RO</b>	Romania		
<b>CU</b>	Cuba	<b>LC</b>	Saint Lucia	<b>RU</b>	Russian Federation		
<b>CZ</b>	Czech Republic	<b>LI</b>	Liechtenstein	<b>SD</b>	Sudan		
<b>DE</b>	Germany	<b>LK</b>	Sri Lanka	<b>SE</b>	Sweden		
<b>DK</b>	Denmark	<b>LR</b>	Liberia	<b>SG</b>	Singapore		
<b>EE</b>	Estonia						

## STAIN RESISTANT WATER-BORNE COATING COMPOSITION

### TECHNICAL FIELD OF THE INVENTION

This invention relates to water-borne coating compositions and in particular to coating compositions that exhibit good stain resistance properties.

### 5 BACKGROUND OF THE INVENTION

Paints are widely used in households for application to both interior and exterior surfaces. For interior surfaces, particularly in kitchens and living areas the resistance of a paint film to domestic stains is an important property. This is especially the case for trim and wall paints that are frequently exposed to  
10 domestic stains.

Domestic staining materials include food, oil or grease and beverages such as coffee and red wine. For semi and low gloss interior paints, properties such as mar resistance and wet and dry scrub properties are also important. Good performance for these properties enables the stained surface to be  
15 cleaned by scrubbing without causing the treated area to "gloss up" and exhibit a gloss that is different from the surrounding area. However, it is clearly preferable that the paint be not very susceptible to staining materials as well as being able to be effectively cleaned.

Painted surfaces are also susceptible to staining from the substrate, especially in the case of timber substrates containing tannins. The tannin material can "print through" the paint film, discolouring the paint after it has  
20 dried. This problem is particularly evident with water-borne latex paints. Various factors can effect this substrate staining and special water-borne latex paints have been developed to overcome this problem. However, in this  
25 invention we are not concerned with this type of staining but staining on the outermost surface of the paint. Paints that perform well for substrate staining do not necessarily exhibit good resistance to domestic stains and vice-versa.

Conventional organic solvent based paints that have alkyd resins as binders and which form tightly crosslinked paint films generally exhibit excellent  
30 stain resistance properties. It is believed this is due to the low solubility of the staining material in the paint film. However, these paints are losing favour because of the combined adverse effects of volatilised organic solvents on the environment and inconvenience for the applicator from long recoat times and

clean up requiring the use of organic solvents. Water-borne versions of alkyds suffer from yellowing problems, particularly in kitchen areas and have not yet met the needs of the market. Conventional water based or latex paints in which the paint film is formed by the coalescence of vinyl or acrylic thermoplastic polymer particles are widely used but hitherto have not exhibited excellent stain resistance together with the required balance of other paint properties, including hardness, film coalescence, pH viscosity stability, and tint strength.

It is essential for adequate mechanical film properties of conventional water based paints that there is good polymer particle coalescence over the range of temperatures encountered in ordinary use. Coalescence is directly related to the hardness or glass transition temperature ( $T_g$ ) of the polymer particles. Low  $T_g$  polymers allow coalescence at lower temperatures than for higher  $T_g$  polymers. The hardness of a paint film influences properties such as scuff and abrasion resistance. Maximising film hardness is important especially for paints in kitchens and living areas. Hardness is usually increased by increasing the  $T_g$  of the polymer particles. However, enhancing the hardness by increasing the  $T_g$  of the polymer in the particle leads to poorer coalescence. In practice the compromise between these properties is overcome by using a volatile temporary organic plasticiser that allows the use of higher  $T_g$  polymer particles than otherwise would be able to be used. However, such formulations suffer from the disadvantage of poor early film hardness. This occurs as the volatile plasticiser may take some days before completely volatilising and being removed from the paint film. The use of volatile plasticisers is also not favoured in some applications as it leads to the release into the atmosphere of organic solvents. For trim paints it is desirable that they have film hardness greater than conventional water-borne latex paints intended for broad wall application.

Viscosity stability is an important property for commercial paint formulations. Paint products are commercially manufactured within permissible tolerances to predetermined specifications. It is important that satisfactory paint characteristics are maintained across the allowable range in the specification. With regard to aqueous latex paints, pH is a manufacturing variable that may

be in a range of, for example, 8.5 to 9.5. Viscosity is a paint property that may vary with pH change and for such paints it is important that viscosity at both low and high shear rates is within acceptable limits throughout the pH specification range. Viscosity at low shear rates tends to influence flow and levelling properties. Viscosity at high shear rates affects ease of brushing. A further aspect of viscosity stability is the effect of storage on this property. It is obviously desirable that viscosity does not significantly change with time given the possible long shelf life of commercial products.

The tint strength of a paint is an important property as it indicates whether a paint can be tinted to a particular colour using a standard tinting formula. It is a requirement that paints across a range of product types have similar tint strength so that common tinting formulae may be used across that range. The tint strength is a measure of the amount of coloured tinter that must be added to a white base paint to give a particular colour. If the base paint requires a smaller amount of the tinter it is described as being of low tint strength. Paint with low tint strength may be reformulated with higher levels of titanium dioxide pigment but this can add significantly to formulation costs. Conversely if the tint strength of a base paint is high it would be possible for it to be reformulated with lower levels of titanium dioxide pigment to give the required tint strength at a lower formulation cost. For such a reformulation to be acceptable opacity would be required to be maintained. Accordingly, it is desirable that the tint strength is close to or equal to other products across the range without having to reformulate the product with high levels of titanium dioxide pigment. In addition, tint strength must be stable over time because of the possible long shelf life of paints.

The binders used for conventional water based paints include a wide range of materials. A recent review article entitled "Polymers for Water-Based Coatings - A Systematic Overview" by J.C. Padget in Journal of Coatings Technology, Vol 66. No. 839, December 1994 at pp 89 - 101 summarises the various types of materials used. These range from disperse polymers in water such as those used in latex paints to fully water soluble solution polymers. A further class of binders are referred to as water reducible resins which are a hybrid between the water insoluble polymer binders and fully water soluble

binders. Such hybrid resin systems usually require significant levels of organic cosolvents to be present and these systems are intended for industrial rather than domestic household applications. An example of such a resin system is disclosed in US patent No. 4,230,609 (Burroway et al).

5           The use of copolymerisable acrylic acid in addition copolymers is summarised in Table 2 of the Padgett article and this shows the general effect of increasing the acrylic acid level from 0 to 100%. The viscosity characteristics on neutralisation are set out as the level of acid is increased. At acrylic acid levels of 1% or more the viscosity is described as increasing on  
10 neutralisation. At levels of acrylic acid of from 1 - 2% this viscosity increase is described as being substantially overcome by using a hydrophobic co-monomer such as styrene. This would be as a replacement for a less hydrophobic hard co-monomer such as methyl methacrylate. We have found that while maintaining viscosity stability such latexes tend, when formulated as paints, to  
15 perform unsatisfactorily for tint strength and stain resistance. We have observed similar performance in paints formulated from latexes described in Australian Patent No. 500,903 in the name of Hoechst. Example 1 of that patent describes the preparation of a butyl acrylate/styrene/methacrylic acid/acrylic acid/acetoacetic acid allyl ester in the weight proportions of  
20 300/300/12/6/12. This calculates as 1.90% methacrylic acid and 0.95% acrylic acid on total monomers.

In Rohm and Haas European Patent No. EP 0 466 409 the preparation of a number of latexes is described for use in blending hard and soft latexes to provide paints with good block resistance. The composition of the samples  
25 containing carboxylic acid co-monomers are set out in TABLE 1 where the monomer amounts are by weight:

TABLE 1

Sample No	EHA	BA	MMA	Styrene	AN	MAA
1	-	1105	39.1	496.4	-	42.5
2	-	459	19.5	1179	-	34
3	-	969	680	-	-	34
4	-	459	1190	-	-	34
5	510	-	393	695.3	425	34
6	855.1	-	39.3	350.2	425	34
7	-	969	39.3	640.9	-	34
8	-	816	39.3	793.9	-	34

EHA = Ethyl hexyl acrylate

BA = Butyl acrylate

MMA = Methyl methacrylate

AN = Acrylonitrile

MAA = Methacrylic acid

In samples 2 - 8 the methacrylic acid level is approximately 2.0% and for sample 1 it is 2.5%.

PCT Patent Application No. PCT/AU94/00600 discloses water-borne soil resistance coatings. These coatings make use of a binder that is a blend of low and high Tg polymeric dispersions in particular ratios. While soil resistant coatings of this invention have good properties with regard to soil resistance they do not exhibit very good stain resistance properties when tested as interior trim paints.

Aqueous paints which comprise latex polymer particles having different hardnesses have been proposed to improve specific properties of paint films including film hardness, block resistance, coalescence and soil resistance.

In Rohm and Haas European Patent No. EP 0 466 409, referred to previously, blends of hard and soft emulsion polymers are used. The hard emulsion polymer has a Tg greater than 20°C and the soft emulsion polymer has a Tg less than 20°C. The compositions described in

this prior art specification are claimed to be particularly useful in providing good block resistance when formulated as interior semi-gloss paints whilst retaining good film formation properties at low temperature. No statement is made about stain resistance. At page 5 of this prior art specification the inventors explain that if a soft emulsion polymer is blended with increasing amounts of a hard emulsion polymer, the minimum film forming temperature (MFFT) of the blend will remain about equal to the MFFT of the soft polymer until the hard polymer is about 50 weight percent of the polymer blend. As it is important for their compositions to have good low temperature film coalescence the preferred binder compositions have 60% by weight soft and 40% by weight hard polymer. In their examples the soft to hard latex polymer ratio varies from 4:1 to 1.5 : 1 and all the soft polymers have a MFFT greater than 0°C.

Japanese patent J 5 9215-365-A in the name of Nippon Acryl Kagaku discloses compositions obtained by mixing 35-45 wt % acrylic resin emulsion of Tg 25 to 50°C and 55-65 wt % acrylic resin emulsion of Tg -10 to +15°C . These compositions thus have a soft to hard ratio of 1.9:1 to 1.2:1. These compositions also have an organic plasticiser which may be volatile. Whilst these paints have particular application as ventilator coatings to prevent the smearing of the surface, stain resistant properties are not examined, though they would be expected to be poor based on the monomer composition.

Hoy discusses the effect of a number of composition and processing variables in an article entitled "Effect of Reaction Pathway on Emulsion Polymer Structure" in Journal of Coatings Technology Vol 51, No. 651 April 1979 at pages 28 - 41. In a number of model systems he examines the effect of high Tg monomer on viscosity in very dilute systems. His model systems use various monomers and when he uses styrene his study is confined to polymeric dispersions where the overall Tg of the dispersions was from 27 to 100°C. His study suggests that the use of styrene as a co-monomer would lead to polymeric dispersions where the carboxylic groups were buried.

Australian patent No. 666 797 discloses latex paints having good stain resistance properties. These paints are required to have a non-cellulosic thickener and use a binder that has at least 40 mole percent of styrene and  $\alpha$ -methyl styrene. An example of a preferred polymer is a copolymer of 49



mole % styrene, 11 mole %  $\alpha$ -methyl styrene, 22 mole % 2-ethyl hexyl acrylate and 18 mole % methyl methacrylate. This preferred composition together with other preferred latex compositions do not have present any carboxylic acid moieties. While we have found paints described in this patent have generally good stain properties they are less than optimum for stain resistance to certain common household staining materials.

### SUMMARY OF THE INVENTION

This invention provides in one form an aqueous coating composition comprising an anionically stabilised addition polymerised polymeric dispersion polymerised from a carboxylic acid containing ethylenically unsaturated monomer selected from acrylic acid and methacrylic acid, a hydrophobic aromatic ethylenically unsaturated high Tg monomer selected from styrene, alpha-methyl styrene, vinyl toluene and a C<sub>2</sub>-C<sub>12</sub> acrylate ester monomer characterised in that the relative proportions of ethylenically unsaturated monomers are selected such that Equation I is satisfied.

$$a = \frac{5 + b}{(c + d/2.4)^2} \quad \text{I}$$

where a = 2.0 - 13.0

b = weight percent hydrophobic aromatic high Tg monomer

c = weight percent acrylic acid

d = weight percent methacrylic acid

Preferably the weight percent of hydrophobic aromatic monomer is 8 to 70 and more preferably 10 to 50. Preferably the polymeric dispersion has a number average particle size less than 200 nanometers, more preferably 150 nanometers and most preferably less than 120 nanometers.

Preferably a = 2.5 - 10.0.

A further form of this invention provides an aqueous coating composition comprising a blend of a low Tg and a high Tg aqueous polymeric dispersion characterised in that: the polymer dispersion with low Tg has a Tg less than 0°C, the polymer dispersion with high Tg has a Tg of at least 25°C, the volume ratio of low Tg polymer dispersion to high Tg polymer dispersion is from 0.4:1 to 3:1, the high Tg polymer dispersion is defined above. In this further form preferably the low Tg polymer dispersion is non-ionically stabilised.

In a still further form of this invention an aqueous polymeric dispersion is provided in which the addition of polymerisable monomers are selected to satisfy Equation I.

### DETAILED DESCRIPTION OF THE INVENTION

5 We have found that the anionically stabilised polymeric dispersions of the present invention may confer useful properties when formulated as water-borne paints. The Tg of the polymeric dispersion may vary widely but is preferably in the range -15 to 60°C and more preferably -5 to 25°C. When the Tg of polymer in the polymeric dispersion is in the range of 0 - 30°C they may  
10 be used as the sole polymeric binder and paints exhibiting good stain resistance, viscosity, stability and tint strength can be prepared. These good properties are generally maintained when an additional binder is used. However, the beneficial properties other than viscosity stability tend to worsen as other binders are used in combination with the dispersions of the present  
15 invention. When the Tg is 25°C and above paints may be formulated by combining this polymeric dispersion with an aqueous polymeric dispersion of low Tg. This low Tg polymeric dispersion may be non-ionically or anionically stabilised. The low Tg polymeric dispersion may have a composition as defined in Equation I.

20 The anionically stabilised latex of this invention are copolymers of addition polymerisable ethylenically unsaturated comonomers.

We have found that good paint properties are obtained provided the specified ethylenically unsaturated monomers are used in proportions such that the relationship defined in Equation I is maintained. When monomers are  
25 selected such that  $a$  in Equation I is less than 2, paints tend to exhibit unsatisfactory viscosity stability. When  $a$  is greater than 13, good viscosity stability is usually maintained but poorer tint strength and stain resistance are observed.

30 Styrene, alpha-methyl styrene and vinyl toluene are suitable hydrophobic aromatic monomers.

Mixtures of acrylic and methacrylic acid may be used as well as each acid alone. Acrylic acid is our preferred acid. The level of methacrylic acid in a polymeric dispersion is preferably less than 6% of total monomers and more

preferably less than 4% of total monomers.

Styrene is our preferred hydrophobic aromatic high Tg monomer. In our preferred formulation styrene may be the sole hydrophobic aromatic high Tg monomer. Alternatively, mixtures of styrene and alpha methyl styrene or vinyl  
5 toluene may be used.

Preferred alkyl acrylates are ethyl acrylate, butyl acrylate and 2-ethyl hexyl acrylate.

We use the term high or low Tg monomer as meaning the Tg of a homopolymer of such a monomer. High Tg is greater than 40°C and low Tg is  
10 less than 20°C.

Apart from styrene, alpha-methyl styrene, vinyl toluene, acrylic acid, methacrylic acid and alkyl acrylates other optional comonomers may be used. Examples of useful comonomers include alkyl acrylates and methacrylates where the alkyl group has 1 to 20 (and more preferably 1 to 8) carbon atoms,  
15 vinyl acetate, acrylonitrile and simple or substituted olefines such as butadiene ethylene and vinyl chloride. Monomers such as methyl methacrylate and higher alkyl methacrylate esters are usually preferred. Monomers containing other functional groups such as hydroxyl or amino groups may also be used. Minor amounts of other functional monomers such as ureido, or acetoacetate  
20 containing monomers directed towards specific objectives such as adhesion promotion or crosslinking may also be incorporated. Such functional monomers are usually incorporated at less than 15% w/w of total monomers.

In preferred compositions 5 - 10% of acetoacetoxy ethyl methacrylate (AAEM) monomers may be incorporated into these dispersions to improve the  
25 burnish resistance and hardness of resultant paint films. We have found that by using a crosslinkable latex such as by including 5 - 10% of AAEM it is possible to achieve a good balance of paint properties. The selection of the optimal comonomers and their relative proportions is based on well established principles in the art and generally balance properties such as film toughness,  
30 adhesion, hardness and cost.

The molecular weight of the copolymers in the polymeric dispersions of the present invention is generally similar to known latexes and typically would be at least 100,000 and more commonly at least 200,000. A light gelling

structure in the particles is permitted in a similar fashion to the gel structure of known commercial latexes. In some cases it is desirable to enhance the gel structure by including minor amounts usually less than 1% of polyfunctional acrylate or methacrylate monomers provided film formation is not unacceptably  
5 compromised. An example of a suitable acrylate is glyceryl propoxy triacrylate.

The aqueous dispersions either anionically or non-ionically stabilised, of the present invention may be prepared by known means, for example, emulsion polymerisation. It is a preferment of this invention that when a blend of higher and low Tg aqueous dispersions is used, the low Tg polymer dispersion is non-  
10 ionically or sterically stabilised. The term sterically stabilised is an art recognised term in colloid science and means that, in aqueous systems, colloidal stability is conferred by the presence of a sheath of water soluble polymeric or oligomeric chains anchored to the particle surface. By sterically stabilised dispersions we mean that whilst other types of stability, such as  
15 anionic or cationic, may be present, colloidal stability is able to be conferred by steric stabilisation alone. For the purposes of this invention a convenient test to ascertain whether the dispersion is sterically stabilised or not is to increase the ionic concentration of the aqueous phase to such an extent that ionic stabilisation is nullified and then to assess the stability of the dispersion.

20 The non sterically stabilised dispersions are anionically stabilised. We mean that while other forms of stabilisation may be present to some extent, these other forms of stabilisation are insufficient to stabilise the dispersions in the absence of the anionic stabilisation. In practice, the stability of a dispersion may be determined by increasing the ionic strength of the aqueous medium to  
25 nullify the anionic stabilisation and assessing the stability of the dispersion. If it is anionically stabilised, the dispersion would flocculate under these conditions. In practice a simple test to determine whether a dispersion is anionically stabilised is to reduce the pH of the aqueous medium until it is about 5. If the dispersion flocculates we regard it as anionically stabilised.

30 Examples of the preparation of non-ionically stabilised polymer dispersions suitable for the working of the present invention are described in Australian Patent No. 618,176. Also within the scope of the present invention are polymer dispersions which have a core/shell structure whereby either the

hard particles or soft particles or both are structured so that the outer shell of the particle differs in polymer composition from that of the centre of the particle.

The preparation of anionically stabilised dispersion is well known and is documented in standard texts. Examples of the preparation of anionically stabilised dispersions suitable for the high Tg dispersion are described in  
5 Australian Patent Application number 16642/72.

Preferably the aqueous medium used for polymerisation is buffered with, for example, sodium bicarbonate which causes partial ionisation of the carboxylic acid contributing to in-process stability.

10 The aqueous dispersions are usually thermoplastic and remain thermoplastic after film formation. However, within the scope of the present invention are crosslinkable polymer dispersions where cross-linking takes place after film formation. Examples are well known in the art and particularly useful examples are described in our copending application entitled "Crosslinkable  
15 Aqueous Coating Compositions" (PCT AU94/00599).

An important characteristic of the aqueous dispersions of the present invention is their glass transition temperatures (Tg). The term glass transition temperature is well known in the art and generally defines the onset of long range molecular motion wherein the polymer preserves the outward  
20 appearance of a solid but becomes rubbery and then tacky with increasing temperature and undergoes plastic flow and elastic deformation. The theoretical Tg is often calculated in accordance with the Fox equation  $1/T_g = \sum W_i/T_i$ . However, Tg can be measured in accordance with the differential thermal analysis method set out in the Journal of Paint Technology, Volume 41,  
25 pages 167 - 168 (1969) or by testing for softening points, using minimum film forming temperature gradient bars or thermomechanical analysis (TMA). In practice we find in most cases that the Tg as determined by the various available methods is close to the theoretical Fox Tg. However, in some cases significant variations can occur and typically anionic latexes behave as if their  
30 Tg is 10 - 15°C above the Fox Tg and with non-ionic latexes they behave as if their Tg is less than their Fox Tg. In those instances we prefer to use Tg as measured on actual dispersions, after film formation using a measurement such as TMA.

In the embodiment of the present invention where a blend of high and low Tg dispersions are used, the low Tg dispersion should have a Tg of 0°C maximum. However a better balance of paint film properties is usually achieved when the Tg is in the range -40 to -5°C and more preferably -20 to  
5 -10°C.

Not only are stain resistant paints obtained in the present invention but in certain applications paints can be formulated using a blend of high and low Tg dispersions and these paints do not require the addition of volatile organic plasticisers. Accordingly, paints can be prepared that comply with the zero  
10 VOC requirement for low pollution paints.

In this embodiment that uses blends of high and low Tg dispersions, the high Tg dispersion of the present invention has a Tg of at least 25°C, more preferably in the range 30 - 70°C, and most preferably 30 - 40°C. There should be a difference of at least 35°C and more preferably 45°C between the  
15 Tg's of the high and low Tg polymeric dispersions.

In this embodiment the relative proportions of the low and high Tg dispersions is important to its working and for this embodiment we require that the volume ratio of low Tg polymeric dispersion to high Tg polymeric dispersion to be from 0.4:1 to 3:1. This is of course calculated on a non-volatile basis. In  
20 practice there is usually little difference between the weight and volume ratios. If the particles are based on the same monomers it is convenient to use the weight ratios as the densities of the particles are essentially the same. Weight ratios are used in the Examples. Preferably the volume ratio of low Tg polymeric dispersion to high Tg polymeric dispersion is from 0.6:1 to 1.5:1.

25 At ratios above the 3:1 upper limit the stain resistance of paint films becomes less than optimal and inadequate film hardness is achieved. At ratios below 0.4:1 film properties such as ability to coalesce satisfactorily at low temperatures is adversely affected and the defect termed "mud cracking" arises. Paints exhibiting an excellent balance of properties can also be  
30 achieved by using a binder of blends of low and high Tg polymeric dispersions where both dispersions are anionically stabilised. Suitable ratios are the same as in the case where the low Tg dispersions were non-ionically stabilised.

The compositions of the present invention are particularly suitable for

gloss and semi-gloss paints but also have application in low sheen and flat paints. For best results we have found it to be advantageous to use small particle size polymer dispersions, especially for the high Tg polymer dispersion in the dispersion blend embodiment and especially for gloss and semi-gloss  
5 paints. The particle size should preferably be less than 200 nm in diameter, more preferably less than 150 nm and most preferably less than 120 nm. Preferred paints have a gloss of at least 10 (60°head) and more preferably at least 40 (60°head).

Whilst the major portion of the binder in this invention in the blend  
10 embodiment is the combination of a low Tg and high Tg polymer dispersion as described above, other binders may be included. If a third polymeric dispersion is included it may be regarded as a high or low Tg dispersion if its Tg meets the criteria set out above. For example, within the scope of the present invention are binders of polymer dispersions of -15°C (40%), -10°C (10%) and  
15 +50°C (50%). In this case both the -15°C and -10°C dispersions are regarded together as the low Tg, and in this case the low Tg to high Tg ratio is 1:1. Furthermore, minor amounts of dispersions that are neither low or high Tg as defined in this invention may be used as well as minor amounts of solution polymers and other additives as used in art recognised quantities.  
20 Unpigmented or clear coatings are also embraced within the scope of the present invention. Stain resistant properties are of most advantage in interior coatings, the compositions of the present invention also have application as exterior paints.

Paint formulating ingredients such as pigments, pigment dispersants,  
25 mineral extenders, plastic extenders, wet edge solvents, rheology modifiers and fungicides may be incorporated in art recognised quantities. These materials may influence overall paint properties including stain resistance, tint strength and viscosity stability. Formulation methodology is well known and the influence of these various materials on paint properties is able to be  
30 ascertained by routine experimentation.

The invention will be further described by reference to the following examples of preferred embodiments.

Example 1

This example illustrates the preparation and evaluation of a low sheen interior paint according to the invention.

1.1 Preparation of aqueous dispersion of Fox Tg + 22°C.

5	<u>Material</u>	<u>Wt%</u>
	A. Water	21.984
	Nonyl phenol ethoxylate sulphate surfactant*	0.350
	B. Water	0.097
	Sodium carbonate	0.018
10	Ammonium persulphate	0.014
	C. Water	3.836
	Sodium carbonate	0.197
	Ammonium persulphate	0.034
	D. Methyl methacrylate	18.371
15	Butyl acrylate	16.615
	Styrene	7.188
	N-(2-Methacryloyloxy ethyl) ethylene urea (25% in methyl methacrylate)	1.331
	Acrylic acid	0.865
20	Nonyl phenol ethoxylate sulphate surfactant*	0.700
	Water	27.761
	E. Defoamer	0.010
	Biocide	0.080
	Ammonium hydroxide (25% in water)	<u>0.549</u>
25		<u>100.0</u>

\* 60% in water

Stage A was added to a vessel equipped with stirrer, condenser and feed facilities and heated to 80°C with stirring under a nitrogen blanket. Feed stage D was premixed and emulsified under high shear. Stage B was added to



stage A and stirred for 10 minutes prior to concurrently starting feed stages C and D. Both C and D were added over 240 minutes while maintaining the reaction temperature at 80°C. At the end of the feeds, the reaction was held at 80°C for a further 1 hour and then cooled to room temperature. Stage E was added and stirred for 10 minutes.

The solids of this dispersion was 45% by weight. It had a pH of 8.0 and the particle size (Dn) was 80 nm. This dispersion had an "a" value of 5.2. This dispersion was designated Dispersion 1.

### 1.2 Preparation of a low sheen paint using Dispersion 1

	<u>Material</u>	<u>Wt%</u>
10	A	
	Water	13.5
	Propylene glycol	1.0
	Amino methyl propanol	0.1
	Poly acrylic acid sodium salt dispersant	0.3
15	Octyl phenol nonionic surfactant	0.5
	Defoamer	0.3
	Titanium Dioxide (Rutile pigment)	25.5
	Amorphous silica	2.5
	Calcium carbonate extender	6.5
20	B	
	Dispersion 1	22.0
	Water	19.9
	C	
	Propylene glycol	5.0
	Texanol*	2.0
	Associative thickener	0.3
25	Cellulosic thickener	0.5
	Biocide	<u>0.1</u>
		<u>100.0</u>

\* 2,2,4-trimethyl 1,3-pentane diol mono isobutyrate

The materials from stage A were added sequentially with stirring and then were dispersed for 10 - 15 minutes with high speed mixing to achieve good pigment dispersion. The millbase was gradually let down with stage B

and the mixture was stirred for 10 minutes and then the pH was adjusted to 9.0 using ammonium hydroxide (25% solution in water). Stage C materials were added sequentially with 10 minutes stirring between each, the thickener being gradually added in a pencil thin stream. The stirrer speed was increased as the viscosity increased to ensure efficient mixing. The composition was stirred at a moderate speed for a further 10 minutes.

The resulting paint had volume solids 36%, PVC 38%, and pH 9.0. This was designated Paint 1.

### 1.3 Evaluation of Paint

Paint 1 (one coat) was drawn down. The paint film was then left to dry for one week at 25°C. The reagents used to test paint stain resistance include blue food colouring, red ink, red wine, tea and coffee solutions and a special hydrophobic testing compound, "K and N". These staining agents were applied to paint films and left to stain for one hour. Excess stain reagent was then removed and the paint film thoroughly cleaned using a household cleaner and paper tissue. The panel was visually assessed for stain resistance and rated relative to an appropriate control using a scale of 1 - 5 where 5 = excellent stain resistance and 1 = poor stain resistance. Generally a rating of at least 3 is required for paints with good stain resistance properties.

To assess tint strength, a standard tinter at a specified concentration was added to paint. The tinted paint was then shaken for five minutes using a Red Devil High Speed Paint Mixer to ensure adequate tinter incorporation. The tinted paint was applied to a Leneta 5DX card to give a wet film build of 40µm and force dried for 20 minutes at 80°C. A second coat of paint, also at a wet film build of 40µm, was applied over the first paint coat and force dried for 20 minutes at 80°C. Using a Milton Roy Colour Graph Spectrophotometer, the tint strength of the paint was measured against a computer stored colour reference. Paints were rated for tint strength on a scale of 1 - 5 where 1 is poor being more than 20% low in tint strength, and 5 is excellent, being less than 5% low in tint strength.

A rating of 4 or 5 is desirable for commercial paints.

Paint viscosities were measured with a Brookfield low shear viscometer and Cone and Plate high shear viscometer after 1, 2, 3 and 4 weeks storage at

50°C. They were also measured at low (8.5) and high (9.5) pH. They were rated for viscosity stability on a scale of 1 - 5 where 1 is poor and 5 is excellent. Generally paints were assessed as poor when the low shear viscosity increased by more than 100% and excellent when the low shear  
5 viscosity increased by less than 20%. To be rated as at least 3, the high shear viscosity had to be within acceptable ranges for brush application after storage. Acceptable paints had a rating of at least 3.

Paint 1 was rated as 4 for stain resistance, 5 for tint strength and 5 for viscosity stability.

10 Examples 2 - 3

These Examples illustrate the preparation of aqueous dispersions according to the invention. The method of Example 1 was repeated with the relative proportions of methyl methacrylate and butyl acrylate being adjusted to give Fox Tgs of 10 and 27.

15 These dispersions were designated Dispersions 2 and 3 respectively. Each of these dispersions had an "a" value of 5.2 and particle size 87nm and 90nm respectively. Paints were formulated as in Example 1 replacing Dispersion 1 with Dispersion 2 and Dispersion 3 in turn to produce Paint 2 and Paint 3. The evaluation results for Paint 2 and Paint 3 were 4 and 4 for stain  
20 resistance, 5 and 5 for tint strength and 5 and 4 for viscosity stability respectively.

Examples 4 - 7

These Examples illustrate the preparation of aqueous polymeric dispersions according to the invention having varying Tgs. These dispersions  
25 were generally too high in Tg to enable paints with suitable levels of volatile plasticiser to be formulated when the dispersion was used as the sole binder. However, they are particularly useful when combined with a lower Tg dispersion according to an alternative embodiment of the present invention. A Fox Tg of +35°C dispersion was prepared using the method of Example 1 with the  
30 following materials:

	<u>Material</u>	<u>Wt%</u>
A.	Water	30.833
	Nonyl phenol ethoxylate sulphate surfactant*	0.350

	B.	Water	0.093
		Sodium carbonate	0.017
		Ammonium persulphate	0.013
	C.	Water	3.665
5		Sodium carbonate	0.033
		Ammonium persulphate	0.188
	D.	Methyl methacrylate	20.616
		Butyl acrylate	11.962
		Styrene	6.872
10		Acetoacetoxy ethyl methacrylate	2.121
		Acrylic acid	0.827
		Nonyl phenol ethoxylate sulphate surfactant*	0.669
		Water	20.953
	E.	Defoamer	0.010
15		Biocide	0.080
		Ammonium hydroxide (25% in water)	<u>0.698</u>
		* 60% in water	<u>100.00%</u>

The solids of this dispersion was 43% by weight and the particle size (Dn) was 90 nm. It had a MFFT of 44°C (crack point). This dispersion was designated Dispersion 4. Dispersions 5, 6 and 7 were prepared in similar fashion except that the relative proportions of methyl methacrylate and butyl acrylate were adjusted to give Fox Tgs of 30, 40 and 45 respectively. Particle sizes of Dispersions 4, 5, 6 and 7 were 82, 90, 85 and 95 nm respectively.

#### Example 8 - 14

These examples are within the scope of the present invention illustrate generally good paint properties as the "a" value in Equation I is varied within the defined range. The "a" value was varied by changing the styrene level of Example 1 and/or the (meth)acrylic acid level.

Dispersions were prepared as in Example 1 with the following styrene and carboxylic acid monomer levels as set out in TABLE 2. The methyl

methacrylate and butyl acrylate levels were adjusted to give the appropriate Tg. The "a" value, Tg and paint evaluation results when formulated as a low sheen paint as in Example 1 are also set out in TABLE 2.

TABLE 2

Example No	Tg	% Styrene	% AA	% MA	Particle Size (nm)	a	Stain	TS	VS
8	22	57	3	0	105	6.9	4	3	4
9	22	8	2	0	90	3.3	4	3	3
10	22	29	2	0	93	8.5	4	3	5
11	0	44	2	0	85	12.3	4	5	5
12	0	44	3	0	90	5.4	4	4	5
13	0	43	4	0	-	3	4	5	5
14	22	16	1	2	80	6.2	4	4	4

AA = Acrylic Acid

MA = Methacrylic Acid

TS = Tint Strength

VS = Viscosity Stability

#### Example 15 - 16

These Examples illustrate the use of alkyl acrylate ester monomers other than butyl acrylate.

Example 1 was repeated except that the butyl acrylate monomer was replaced with ethyl acrylate (Example 15) and 2 ethyl hexyl acrylate (Example 16). The levels of each of these two monomers and the level of methyl methacrylate were adjusted to give the same Fox Tg as in Example 1. These two dispersions were designated Dispersion 15 and Dispersion 16 respectively and had particle sizes 85 and 90nm respectively. When evaluated in a paint as in Example 1, the test results were as follows:

Stain resistance 4 and 4, tint strength 5 and 4, viscosity stability 5 and 5

respectively.

Example 17

This Example illustrates the use of a blend of dispersions according to the invention and the evaluation of a gloss paint formulated with this blend of dispersions.

**17.1 Preparation of aqueous dispersion of Fox Tg - 15°C.**

	<u>Material</u>	<u>Wt%</u>			
	A.	Fatty alcohol ethoxylate surfactant*	1.191		
		Water	12.671		
10		t-butyl perbenzoate	0.368		
		30% hydrochloric acid	trace		
	B.	Ferrous sulphate	0.008		
		Water	0.885		
				<u>Feed 1</u>	<u>Feed 2</u>
15	C.	Methyl methacrylate	1.608	2.910	9.161
		Butyl acrylate	3.066	5.549	17.465
		Glyceryl propoxy triacrylate	0.053	0.095	0.299
		Acetoacetoxy ethyl methacrylate	0.525	0.950	2.992
		Fatty alcohol ethoxylate surfactant*	0.715	0.461	0.960
20		Water	4.847	7.397	23.471
				<u>Feed 1</u>	<u>Feed 2</u>
	D.	Sodium Erythorbate	0.028	0.038	0.132
		Water	0.264	0.414	1.308
	E.	Defoamer	0.050		
25		Cosolvent	0.050		
		Biocide	0.080		
			100.000		

\* As described in Example 3 of International Patent Application No. PCT/AU90/00565.

Stage A was added to a vessel equipped with stirrer, condenser and feed facilities and heated to 70°C with stirring under a nitrogen blanket. Stage D Feeds 1, 2 and 3 were separately made up as stock solutions. Stage C Feeds 1, 2 and 3 were each premixed and separately emulsified under high shear and stage D Feeds 1, 2 and 3 were added to Stage C Feeds 1, 2 and 3 respectively. Stage B was added to Stage A and stirred for 10 minutes prior to starting stage C and D feeds. Feed 1 was fed over 50 minutes, Feed 2 over 45 minutes and Feed 3 over 120 minutes maintaining the reaction temperature at 70°C. At the end of the feeds, the reaction mixture was allowed to cool to room temperature and stage E was added and stirred for 10 minutes.

The solids of this dispersion was 48% by weight and the particle size (Dn) was 90 nm. It had a MFFT <10°C (crack point). This dispersion was designated Dispersion 17.

#### 17.2 Preparation of gloss paint having a ratio of low Tg to high Tg

##### 15 polymeric dispersion of 0.67 to 1.0.

	<u>Material</u>	<u>Wt%</u>
A.	Water	7.3
	Propylene glycol	1.0
	Amino methyl propanol	0.1
20	Nonionic ethoxylate surfactant	0.4
	Polyacrylic acid sodium salt dispersant	0.3
	Defoamer	0.2
	Titanium Dioxide (Rutile pigment)	19.0
B.	Dispersion blend (60% Dispersion 4 and	
25	40% Dispersion 17 on a non-volatile basis)	59.2
	Water	3.1
C.	Propylene glycol	5.3
	Texanol	2.6
	Associative thickener	1.0
30	Cellulosic thickener	0.4
	Biocide	<u>0.1</u>
		<u>100.0</u>

### 17.3 Paint Evaluation

This paint was evaluated using the methods of Example 1 and was rated as 4 for stain resistance, 4 for tint strength and 5 for viscosity stability.

#### Example 18

5 This Example illustrates the preparation of a gloss paint in accordance with the invention.

The method of Example 17 was repeated except that the paint formulation was as follows:

	A	Water	5.0
10		Propylene glycol	1.0
		Amino methyl propanol	0.1
		Polyacrylic acid sodium salt dispersant	0.3
		Propylene/ethylene oxide nonionic surfactant	0.5
		Defoamer	0.3
15		Titanium Dioxide (Rutile pigment)	21.0
	B	Dispersion blend (60% Dispersion 4 and 40% Dispersion 17 on a non-volatile basis)	59.0
		Water	6.0
	C	Propylene glycol	4.0
20		Texanol	1.4
		Associative thickener	1.0
		Cellulosic thickener	0.3
		Biocide	<u>0.1</u>
			<u>100.0</u>

25 This paint was designated Paint 16 and had the same PVC and volume solids as Paint 17. Its evaluation rating was the same as for Paint 17.

#### Example 19

30 This Example illustrates the preparation of a gloss paint in accordance with the invention. The method of Example 17 was repeated except that the paint formulation was as follows:



	A	Water	8.0
		Propylene glycol	1.0
		Amino methyl propanol	0.1
		Polycarboxylic acid dispersant	0.2
5		Nonionic surfactant	0.5
		Defoamer	0.3
		Titanium Dioxide	21.0
	B	Dispersion blend (60% Dispersion 4 and 40% Dispersion 17 on a non-volatile basis)	59.0
10		Water	1.2
	C	Propylene glycol	5.0
		Texanol	2.6
		Associative thickener	0.7
		Cellulosic thickener	0.3
15		Biocide	<u>0.1</u>
			<u>100.0</u>

This paint was designated Paint 19 and had a PVC of 17 and volume solids of 38%. Again, its evaluation according to the method in Example 1 was the same as Paint 17.

#### 20 Example 20

This Example illustrates the preparation of a low sheen paint using a blend of low and high Tg polymeric dispersions. The method of Example 17 was repeated except that the paint formulation was as follows:

	A	Water	13.5
25		Propylene glycol	1.0
		Amino methyl propanol	0.1
		Sodium polyacrylate dispersant	0.3
		Nonyl phenol ethoxylate nonionic surfactant	0.5
		Defoamer	0.3
30		Titanium Dioxide (Rutile pigment)	18.0
		Amorphous silica	3.6
		Hydrous clay	7.0

	B	Dispersion blend (60% Dispersion 4 and 40% Dispersion 17 and a non-volatile basis)	36.0
		Ropaque (Rohm and Haas)	5.4
		Water	5.9
5	C	Propylene glycol	5.0
		Texanol	2.5
		Associative thickener	0.5
		Cellulosic thickener	0.3
		Biocide	<u>0.1</u>
10			<u>100.0</u>

The resulting paint was designated Paint 20 and had a PVC of 38 and volume solids of 39. It was rated 3 - 4 for stain resistance and 4 for tint strength and 5 for viscosity stability.

#### Example 21

15 This Example illustrates the preparation of a low sheen paint using a different blend of low and high Tg polymeric dispersions.

The method of Example 1 was repeated except that the paint formulation had a blend 40% Dispersion 4 and 60% Dispersion 17 (22 parts in total). The paint was rated as 3 for stain resistance, 4 for tint strength and 5 for viscosity  
20 stability.

#### Example 22

This Example illustrates the preparation of a low sheen paint using a blend of low and high Tg polymeric dispersions.

25 The method of Example 17 was repeated except that the paint formulation was as follows:

	A	Water	10.0
		Propylene glycol	1.0
		Amino methyl propanol	0.1
		Polycarboxylic acid dispersant	0.3
30		Nonyl phenol surfactant	0.5
		Defoamer	0.3
		Titanium Dioxide (Rutile pigment)	16.8

	Amorphous silica	3.0
	Clay	7.2
B	Dispersion blend (60% Dispersion 4 and 40% Dispersion 17 on a non-volatile basis)	37.0
5	Water	15.9
C	Propylene glycol	5.0
	Texanol	2.0
	Associative thickener	0.3
	Cellulosic thickener	0.5
10	Biocide	<u>0.1</u>
		<u>100.0</u>

This paint was designated Paint 22 and had a PVC of 40 and a volume solids of 35.

#### Examples 23 - 33

15        These examples illustrate the preparation and testing of paints formulated with variations in the ratios of low and high Tg dispersions as well as variations in the Tg of the high Tg dispersion. These blends were formulated as low sheen paints as in Example 20. The variations and results of the evaluation are set out in TABLE 3.

TABLE 3

Example No	Anionic Dispersion (Tg)	Ratio of low Tg to High Tg Dispersion	SR	TS	VS
23	Dispersion 5 (30)	40 : 60	4	4	4
24	Dispersion 6 (40)	40 : 60	4	5	4
25	Dispersion 7 (45)	40 : 60	4	5	5
26	Dispersion 5 (30)	50 : 50	3-4	4	5
27	Dispersion 4 (35)	50 : 50	3-4	4	5
28	Dispersion 6 (40)	50 : 50	3-4	4	5
29	Dispersion 7 (45)	50 : 50	3-4	4	5
30	Dispersion 5 (30)	60 : 40	3	4	5
31	Dispersion 4 (35)	60 : 40	3	3-4	5
32	Dispersion 6 (40)	60 : 40	3	4	5
33	Dispersion 7 (45)	60 : 40	3	4	5

SR = Stain Resistance

TS = Tint Strength

VS = Viscosity Stability

#### Examples 34 - 35

These examples illustrate the the preparation of aqueous dispersions using high Tg hydrophobic aromatic monomers other than styrene.

Example 1 was repeated at the same Tg with a weight for weight replacement of the styrene monomer with vinyl toluene (Example 34) and alpha methyl styrene (Example 35). For Example 34 the methyl methacrylate percentage was 18.538 and the butyl acrylate percentage was 16.426. For Example 35 the methyl methacrylate percentage was 16.834 and the butyl

acrylate percentage was 18.130. The dispersions were designated Dispersion 34 and Dispersion 35 respectively.

These were evaluated in a paint as set out in Example 1 and gave the following test results. Stain resistance 4 and 4; Tint strength 4 and 4; viscosity stability 5 and 5.

#### Examples 36 - 41

These Examples are comparative examples outside the scope of the present invention. These Examples show less than satisfactory performance when the value of "a" in the formula is outside the defined range.

10 Dispersions 36, 37 and 38 were prepared in accordance with Example 1 with appropriate adjustments to acrylic acid level and/or styrene level to give a Tg of 22°C for each example.

Examples 39 and 40 were dispersions that corresponded to Samples 1 and 8 of Rohm and Haas European Patent No. EP O 466 409. Example 41 corresponds to Example 1 of Hoecsht's Australian Patent No. 500,903. Each of these dispersions was evaluated in paints for stain resistance, tint strength and viscosity stability as in Example 1 to produce the results set out in TABLE 4. None of these paints was considered to be satisfactory.

**TABLE 4**

Example No.	a	% Styrene	% AA	% MA	SR	TS	VS
36	0	0	2	0	5	5	1
37	11.4	16	0	3	3	3	1
38	1.9	42	5	0	5	3	1
39	27.3	29.5	0	2.5	2	3	2
40	68.4	47.2	0	2.0	2	2	3
41	17.5	47.6	0.95	1.9	2	3	2

AA = Acrylic Acid

MA = Methacrylic Acid

SR = Stain resistance

TS = Tint Strength

5 VS = Viscosity Stability

The claims of the invention are as follows:

1. An aqueous coating composition comprising an anionically stabilised addition polymerised polymeric dispersion polymerised from a carboxylic acid containing ethylenically unsaturated monomer selected from acrylic acid and methacrylic acid, a hydrophobic aromatic ethylenically unsaturated high Tg monomer selected from styrene, alpha methyl styrene and vinyl toluene and an C<sub>2</sub> - C<sub>12</sub> acrylate ester monomer characterised in that the relative proportions of ethylenically unsaturated monomers are selected such that the following Equation I is satisfied:

$$a = \frac{5 + b}{(c + d/2.4)^2} \quad \text{I}$$

where a = 2 - 13

b = weight percent hydrophobic aromatic high Tg monomer

c = weight percent acrylic acid

d = weight percent methacrylic acid

2. An aqueous coating composition as defined in Claim 1 wherein the hydrophobic aromatic ethylenically unsaturated monomer is in the range 8 - 70%.
3. An aqueous coating composition as defined in Claim 1 or Claim 2 wherein the hydrophobic aromatic ethylenically unsaturated monomer is styrene.
4. An aqueous coating composition as defined in any one of Claims 1 to 3 wherein a in Equation I is in the range 2.5 to 10.
5. An aqueous coating composition as defined in any one of claims 1 to 4 wherein the Tg of the polymeric dispersion is in the range -15 to 60°C.
6. An aqueous coating composition as defined in Claim 5 wherein the Tg of the polymeric dispersion is -5 to 25°C.
7. An aqueous coating composition as defined in any one of Claims 1 to 6 wherein the particle size of the polymeric dispersion is 200 nanometers (number average) maximum.
8. An aqueous coating composition as defined in Claim 7 wherein the particle size of the polymeric dispersion is 150 nanometers maximum.
9. An aqueous coating composition as defined in Claim 8 wherein the particle size of the polymeric dispersion is 120 nanometers maximum.

10. An aqueous coating composition comprising a blend of low Tg and high Tg aqueous polymeric dispersions wherein the polymer dispersion with low Tg has a Tg less than 0°C and the polymer dispersion with high Tg has a Tg of at least 25°C and is as defined in any one of claims 1 - 9 and wherein the volume ratio of low Tg to high Tg polymer dispersion is from 0.4:1 to 3:1.
- 5 11. An aqueous coating composition as defined in Claim 6 wherein the low Tg polymer dispersion is non-ionically stabilised.
12. An aqueous coating composition as defined in Claim 4 wherein the low Tg polymer dispersion is as defined in any one of Claims 1 - 9.
- 10 13. An aqueous polymeric dispersion as defined in any one of Claims 1 to 9.



## AMENDED CLAIMS

[received by the International Bureau on 19 December 1997 (19.12.97);  
original claims 1 and 3-13 amended; new claims 1-17 added;  
remaining claim unchanged (3 pages)]

The claims of the invention are as follows:

1. An aqueous coating composition comprising an anionically stabilised addition polymerised polymeric dispersion polymerised from a carboxylic acid containing ethylenically unsaturated monomer selected from acrylic acid and methacrylic acid, a hydrophobic aromatic ethylenically unsaturated high Tg monomer selected from styrene and alpha methyl styrene and an C<sub>2</sub> - C<sub>12</sub> acrylate ester monomer characterised in that the relative proportions of ethylenically unsaturated monomers are selected such that the following Equation I is satisfied:

$$a = \frac{5 + b}{(c + d/2.4)^2} \quad \text{I}$$

where a = 2 - 13

b = weight percent hydrophobic aromatic high Tg monomer

c = weight percent acrylic acid

d = weight percent methacrylic acid

and characterised in that the polymeric dispersion has Tg 30°C maximum.

2. An aqueous coating composition as defined in Claim 1 wherein the hydrophobic aromatic ethylenically unsaturated monomer is in the range 8 - 70%.
3. An aqueous coating composition as defined in Claims 1 or 2 wherein the hydrophobic aromatic ethylenically unsaturated monomer is in the range 15-50%.
4. An aqueous coating composition as defined in any one of Claims 1 to 3 wherein the hydrophobic aromatic ethylenically unsaturated monomer is styrene.
5. An aqueous coating composition comprising an anionically stabilised addition polymerised polymeric dispersion polymerised from a carboxylic acid containing ethylenically unsaturated monomer selected from acrylic acid and methacrylic acid, a hydrophobic aromatic ethylenically unsaturated high Tg monomer selected from styrene, alpha methyl styrene and vinyl toluene and an C<sub>2</sub> - C<sub>12</sub> acrylate ester monomer characterised in that the relative proportions of ethylenically unsaturated monomers are selected such that the following Equation I is satisfied:

$$a = \frac{5 + b}{(c + d/2.4)^2}$$

$$(c + d/2.4)^2$$

I

where

$$a = 2 - 13$$

b = weight percent hydrophobic aromatic high Tg monomer

c = weight percent acrylic acid

5 d = weight percent methacrylic acid

and further characterised in that the polymeric dispersion has Tg 30°C maximum and the maximum weight percent of acrylate ester monomer is 60%.

6. An aqueous coating composition as defined in any one of Claims 1 to 5 wherein a in Equation I is in the range 2.5 to 9.5.
- 10 7. An aqueous coating composition as defined in any one of Claims 1 to 6 wherein the weight majority of the carboxylic acid containing ethylenically unsaturated monomer is acrylic acid.
8. An aqueous coating composition as defined in any one of Claims 1 to 7 wherein the Tg of the polymeric dispersion is - 15°C minimum.
- 15 9. An aqueous coating composition as defined in Claim 8 wherein the Tg of the polymeric dispersion is -5 to 30°C.
10. An aqueous coating composition as defined in any one of Claims 1 to 9 wherein the particle size of the polymeric dispersion is 200 nanometers (number average) maximum.
- 20 11. An aqueous coating composition as defined in Claim 10 wherein the particle size of the polymeric dispersion is 150 nanometers maximum.
12. An aqueous coating composition as defined in Claim 10 wherein the particle size of the polymeric dispersion is 120 nanometers maximum.
13. An aqueous coating composition comprising a blend of low Tg and high  
25 Tg aqueous polymeric dispersions wherein the polymer dispersion with low Tg has a Tg less than 0°C and the polymer dispersion with high Tg has a Tg of at least 25°C and is as defined in any one of Claims 1 to 12 with the proviso that the Tg maximum limitation of Claim 1 is removed and vinyl toluene is included in Claim 1 as a further hydrophobic aromatic ethylenically unsaturated high Tg  
30 monomer and wherein the volume ratio of low Tg to high Tg polymer dispersion is from 0.4:1 to 3:1.
14. An aqueous coating composition as defined in Claim 13 wherein the low Tg polymer dispersion is non-ionically stabilised.
15. An aqueous coating composition as defined in Claim 13 wherein the low

Tg polymer dispersion is as defined in any one of Claims 1 to 12 with the proviso that vinyl toluene is included in Claim 1 as a further hydrophobic aromatic ethylenically unsaturated high Tg monomer.

5 16. An aqueous polymeric dispersion as defined in any one of Claims 1 to 12.

17. An aqueous polymeric dispersion as defined in any one of Claims 1 to 12 except that the polymeric dispersion has a Tg greater than 30°C but not more than 60°C and further characterised in that the weight majority of carboxylic acid containing ethylenically unsaturated monomer is acrylic acid.

**STATEMENT UNDER ARTICLE 19**

**Claims 1 and 3 to 13 are replaced by amended claims 1 and 3 to 17. Claim 2 is unchanged.**

## INTERNATIONAL SEARCH REPORT

International Application No.

PCT/AU 97/00584

**A. CLASSIFICATION OF SUBJECT MATTER**Int Cl<sup>6</sup>: C09D 125/06, 125/02, 125/16, 125/14, 133/02, 133/08, 133/10

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)

IPC C09D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)  
WPAT: C09D and (acrylic(w) acid or methacrylic(w) acid) and (toluene or styrene) and acrylate# and (stain: or mark:)**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	AU 16642/76 A (HOECHST AKTIENGESELL SCHAFT) 9 February 1978 Example 5, claim 1	1-4, 7-9, 12-13
X	EP 0562730 A (ROHM AND HASS COMPANY) 29 September 1993 Table 1.2.3, claims 1, 7	1-9, 12-13

 Further documents are listed in the continuation of Box C See patent family annex

\* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&amp;" document member of the same patent family

Date of the actual completion of the international search

7 October 1997

Date of mailing of the international search report

10 OCT 1997

Name and mailing address of the ISA/AU  
AUSTRALIAN INDUSTRIAL PROPERTY ORGANISATION  
PO BOX 200  
WODEN ACT 2606  
AUSTRALIA Facsimile No.: (02) 6285 3929

Authorized officer

ALBERT S. J. YONG

Telephone No.: (02) 6283 2160



C (Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4987177 A (DEN HARTOG et al) 22 January 1991 Example 1	1-3, 7-9, 13
X	US 4794139 A (BRADEN et al) 27 December 1988 Claim 3	1-4, 7-9, 13
A	AU 54937/94 A (MINNESOTA MINING AND MANUFACTURING) 15 September 1994 Whole document	1-13
A	EP 0525977 A (MORTON INTERNATIONAL) 3 February 1993 Example 7	1-13
A	EP 0466409 A (ROHM AND HAAS) 15 January 1992 See whole document	1-13
A	Derwent Abstract Accession No. 92-320334/39, class A82 G02, JP 04225065 A (JAPAN RUBBER) 14 August 1992 abstract	1-13
A	Derwent abstract Accession No. 03088Y/02, class A14 G02, JP 51137-743 A (ASAHI CHEMICAL) 27 November 1976 abstract	1-13

**INTERNATIONAL SEARCH REPORT**  
Information on patent family members

International Application No.  
**PCT/AU 97/00584**

This Annex lists the known "A" publication level patent family members relating to the patent documents cited in the above-mentioned international search report. The Australian Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

Patent Document Cited in Search Report		Patent Family Member					
AU	16642/76	BE	845025	BR	7604855	CA	1068429
		CH	624417	DE	2535372	DK	3559/76
		ES	450388	FI	762247	FR	2320319
		GB	1541891	IT	1065102	JP	52022085
		LU	75549	MX	148991	NL	7608630
		NO	762737	PT	65450	SE	7608853
EP	562730	AU	35183/93	BR	9301277	CA	2091661
		CN	1076946	DE	69305554	ES	2093923
		FI	931380	HK	76/97	IL	1049810
		JP	7278485	MX	9301519	NO	930979
US	4987177	AU	65869/90	CA	2029185	EP	483420
US	4794139						
AU	54937/94	CA	2114706	EP	614955	ZA	9400791
EP	525977	AU	18620/92	CA	2072222	FI	922991
		JP	7048535	NO	922508	US	5340870
EP	466409	AU	80149/91	CA	2045366	EP	466409
		FI	913259	JP	5112758	NO	912603
		NZ	238836	PT	98209		
END OF ANNEX							