

WO 2010/036363 A2



Published:

- *without international search report and to be republished
upon receipt of that report (Rule 48.2(g))*

This application claims priority to United States provisional patent application 61/194,461 filed September 26, 2008.

TITLE OF THE INVENTION

5 NBT Based Lead-Free Piezoelectric Materials for High Power Applications

FIELD OF THE INVENTION

The disclosed invention relates to hard lead free piezoelectric materials.

BACKGROUND OF THE INVENTION

10

Hard PZT ferroelectric materials such as PZT4 and PZT8 have been the mainstay in last half century for high power applications. However, the lead content in PZT type ceramics is an environmental concern in electronic devices. For example, the European Union is proposing
15 directives on waste from electrical and electronic equipment as well restrictions on hazardous substances and end-of life vehicles. The USA and Japan are expected to issue similar environmental regulations. It therefore is desirable to develop lead-free piezoelectric ceramics to replace lead-based materials.

20

Lead-free ceramic compounds may be categorized into three primary types, all of which have the ABO_3 perovskite formulation: (1) $BaTiO_3$ ("BT"), (2) $K_{0.5}Na_{0.5}NbO_3$ ("KNN") and (3) $Na_{0.5}Bi_{0.5}TiO_3$ ("NBT"). These compounds, however, either display low T_c (≤ 120 °C), show low piezoelectric activity, multiple polymorphic phase transitions as well as
25 depolarization temperature which limit their utility. Various properties of these compounds are shown in Table I. In Table I, KCN is $K_4CuNb_8O_{23}$ and MPB is Morphotropic Phase Boundary.

Table I: Dielectric and Piezoelectric Properties of Lead-free Piezoelectrics

Material	ϵ_r/ϵ_0	loss	d_{33} (pC/N)	k_o	k_{33}	T_c (°C)	$T_{o,r}/$ T_d (°C)	Q
BaTiO ₃	1700	0.01	190	0.36	0.5	115	0	100
BaTiO ₃ -CaTiO ₃ -Co	1420	0.005	150	0.31	0.46	105	-45	800
(K _{0.5} Na _{0.5})NbO ₃ (HP)	500	0.02	127	0.46	0.6	420	200	240
(K _{0.5} Na _{0.5})NbO ₃	290	0.04	80	0.35	0.51	420	195	100
KNN-Li (7%)	950	0.084	240	0.45	0.64	460	~20	/
KNN-Li3%; Ta20% (LF3)	920-1256	0.024-0.02	190-230	0.46-0.505	0.62	310-323	50-70	/
KNN-LF4*	1570	/	410	0.61	/	253	25	/
KNN-SrTiO ₃ (5%)	950	/	200	0.37	/	277	27	70
KNN-LiTaO ₃ (5%)	570	0.04	200	0.36	/	430	55	50
KNN-LiNbO ₃ (6%)	500	0.04	235	0.42	0.61	460	70	50
KNN-LiSbO ₃ (5%)	1288	0.019	283	0.50	/	392	45	40
KNN-KCN	290	0.006	90	0.36	0.55	410	190	1500
NBT-KBT-LBT	1550	0.034	216	0.401	/	350	160	/
NBT-KBT-BT	820	0.03	145	0.162	0.519	302	224	110
NBT-KBT-BT (MPB)	730	0.02	173	0.33	0.59	290	162	150
PZT5A	1700	0.02	370	0.60	0.71	365	/	75
PZT5H	3400	0.02	600	0.65	0.75	193	/	75

Lead-free ceramic compounds such as solid solutions of NBT with K_{0.5}Bi_{0.5}TiO₃ ("KBT"), NBT-KBT-BT, NBT-KBT- with Li_{0.5}Bi_{0.5}TiO₃ ("LBT") show a morphotropic phase boundary analogous to PZT and relaxor-PT systems. NBT-KBT, NBT-KBT-BT, and NBT-KBT-LBT, however, exhibit a nonpolar antiferroelectric phase transition temperature that occurs below their T_c that limits their temperature range of use. Lead-free ceramic compounds such as KNN-LiNbO₃ ("KNN-LN"), KNN-LiTaO₃ ("KNN-LT"), KNN-LiSbO₃ ("KNN-LS"), and KNN-Sr(Ba)TiO₃ have piezoelectric properties comparable to hard PZT ceramic compounds. However, these KNN type lead-free compounds exhibit low mechanical quality factor Q and a shift in the orthorhombic-tetragonal polymorphic phase transition temperature from about 200 °C to about room temperature. This polymorphic phase transition significantly limits their utility due to property variations.

A need therefore exists for high performance lead free piezoelectric ceramic materials that avoid the toxic lead of prior art Pb(Zr_xTi_{1-x})O₃ ("PZT") piezoelectric ceramics and the disadvantages of prior art, lead free

piezoelectric ceramics.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 shows a compositional diagram of NBT-based compositions;

5 Fig. 2 (a) shows piezoelectric coefficient (d_{33}) and mechanical quality factor (Q_m) as a function of Mn level in BNBK 79 piezoelectric compounds;

Fig. 2(b) shows dielectric permittivity (K) and dielectric loss ($\tan \delta$) as a function of Mn dopant level in BNBK 79 piezoelectric compounds;

10 Fig. 2 (c) shows electromechanical coupling factors (k_{ij}) as a function of Mn dopant level in BNBK79 piezoelectric compounds;

Fig. 3 shows polarization hysteresis for BNBK 79-0.8wt%MnO₂ piezoelectric compound of example 1G compared to PZT4 and PZT8;

15 Fig. 4 shows strain hysteresis of lead free BNBK 79 of example 1A and 0.8wt%MnO₂ doped BNBK 79 of example 1G piezoelectric compounds compared to PZT4 and PZT8;

Fig. 5(a) shows dielectric permittivity and dielectric loss as a function of temperature for undoped BNBK 79 piezoelectric compounds at 1 kHz, 10 kHz and 100 kHz;

20 Fig. 5(b) shows dielectric permittivity and dielectric loss for 0.5wt% MnO₂ doped BNBK 79 piezoelectric compounds at 1 kHz, 10 kHz and 100 kHz;

Fig. 5(c) shows dielectric permittivity and dielectric loss for 0.8wt% MnO₂ doped BNBK 79 piezoelectric compounds at 1 kHz, 10 kHz and
25 100 kHz;

Fig. 5(d) shows dielectric permittivity and dielectric loss for 1.0 wt% MnO₂ doped BNBK 79 piezoelectric compounds at 1 kHz, 10 kHz and 100 kHz;

30 Fig. 6 shows electromechanical coupling factors in extensional mode and thickness mode for 0.8 wt% MnO₂ doped BNBK 79 of Example

1G piezoelectric compounds;

Fig. 7 shows variation of planar electromechanical coupling factor as a function of temperature for BNBK 79-0.8wt% MnO₂ piezoelectric compounds compared to PZT4 and PZT8.

5 Figs. 8(a)-8(c) show temperature dependence of dielectric behavior for Co₂O₃ doped vacancy defect engineered BNKLBT ceramics.

Fig. 9 shows temperature dependence of electromechanical coupling factor, including thickness coupling k_t and planar coupling k_p , for Co₂O₃ doped vacancy defect engineered BNKLBT ceramics, exhibiting
10 a very stable temperature behavior till their depolarization temperature T_d .

Fig. 10 shows the temperature dependence of mechanical quality factor Q , for Co₂O₃ doped vacancy defect engineered BNKLBT ceramics, where the Q values are larger than 700 at room temperature, gradually
15 decreased with increasing temperature, keep yet high Q value around 200 when the temperature approaching the depolarization temperature T_d .

SUMMARY OF THE INVENTION

20 The NBT-based piezoelectric materials disclosed herein typically possess high internal bias field of more than about 5kV/cm and high mechanical quality factor of more than about 700, comparable to PZT4 and PZT8. The NBT-based materials of the general formula $x\text{Na}_m\text{Bi}_n\text{TiO}_3 - y\text{K}_m\text{Bi}_n\text{TiO}_3 - z\text{Li}_m\text{Bi}_n\text{TiO}_3 - p\text{BaTiO}_3$ where ($0 < x \leq 1$), preferably ($0.3 \leq x \leq 0.95$),
25 more preferably ($0.3 \leq x \leq 0.8$), ($0 \leq y \leq 1$), preferably ($0 \leq y \leq 0.7$), more preferably ($0 \leq y \leq 0.2$), ($0 \leq z \leq 1$), preferably ($0 \leq z \leq 0.5$), more preferably ($0 \leq z \leq 0.2$); ($0.3 \leq m \leq 0.7$), preferably ($0.4 \leq m \leq 0.6$), more preferably ($0.45 \leq m \leq 0.55$); ($0.3 \leq n \leq 0.7$), preferably ($0.4 \leq n \leq 0.6$), more preferably ($0.45 \leq n \leq 0.55$); ($0 < p < 1$), preferably ($0 < p \leq 0.2$), more preferably ($0 < p \leq 0.1$);
30 ($x+y+z+p=1$), ($0.9 \leq m+n \leq 1.1$) and ($0.9 \leq m/n \leq 1.1$), may be modified with

various acceptor dopants (single dopant, multiple dopant) to have a wide temperature usage range of from about -50°C to about 200°C. The low densities of NBT-based piezoelectric compounds, on the order of about 5.8g/cc vs. about 7.6 g/cc for PZT piezoelectric compounds, enable the
 5 NBT- based piezoelectric compounds to achieve high acoustic velocities.

The NBT-based piezoelectric compounds possess improved "hardening" effect compared to conventional hard PZT piezoelectric compounds and may be used to replace lead containing piezoelectric materials such as PZT4 and PZT 8.

10 The NBT-based piezoelectric compounds are environmentally friendly materials that may be used in high power electronic devices such as high power ultrasonic transducers (probes), ultrasonic motors, piezoelectric transformers and high intensity focused ultrasound transducers.

15 DETAILED DESCRIPTION OF THE INVENTION

In a first aspect, undoped compounds within the region bounded by $y \leq 50\%$, $z \leq 20\%$ shown in Fig. 1 may be produced. These compounds are within the general formula (I) $x\text{Na}_m\text{Bi}_n\text{TiO}_3 - y\text{K}_m\text{Bi}_n\text{TiO}_3 - z\text{Li}_m\text{Bi}_n\text{TiO}_3 -$
 20 $p\text{BaTiO}_3$ where ($0 < x \leq 1$), preferably ($0.3 \leq x \leq 0.95$), more preferably ($0.3 \leq x \leq 0.8$); ($0 \leq y \leq 1$), preferably ($0 \leq y \leq 0.7$), more preferably ($0 < y \leq 0.2$) and ($0 \leq z \leq 1$), preferably ($0 \leq z \leq 0.5$), more preferably ($0 < z \leq 0.2$); ($0.3 \leq m \leq 0.7$), preferably ($0.4 \leq m \leq 0.6$), more preferably ($0.45 \leq m \leq 0.55$); ($0.3 \leq n \leq 0.7$), preferably ($0.4 \leq n \leq 0.6$), more preferably ($0.45 \leq n \leq 0.55$); ($0 < p < 1$),
 25 preferably ($0 < p \leq 0.2$), more preferably ($0 < p \leq 0.1$), ($x+y+z+p=1$) and ($0.9 \leq m/n \leq 1.1$).

Starting materials which may be used include but are not limited to K_2CO_3 (99.9% pure from Alfa Aesar), Na_2CO_3 (99.9% pure from Alfa Aesar), Li_2CO_3 (99.9% pure from Alfa Aesar), BaCO_3 (99.9% pure from
 30 Alfa Aesar), Bi_2O_3 (99.99% pure from MCP) and TiO_2 (99.99% pure from

Ishihara). Dopant sources which may be employed include but are not limited to Al_2O_3 , CoO , Co_2O_3 , Re_2O_3 (where Re is rare earth element), NiCO_3 , MnO_2 , MnCO_3 , Fe_2O_3 , fluoride and mixtures thereof. The dopants have a purity of 99.99% or more and are commercially available from sources such as Alfa Aesar.

Manufacture of piezoelectric compounds within general formula (I) entails use of starting materials such as those above that are dried at about 120°C in air for about 10 hrs to about 20 hrs to remove moisture.

The dried starting materials are blended into a mixture for use in manufacture of undoped BNBK type compound such as $x\text{Na}_{0.5}\text{Bi}_{0.5}\text{TiO}_3 - y\text{K}_{0.5}\text{Bi}_{0.5}\text{TiO}_3 - z\text{BaTiO}_3$. The mixture then is calcined in an oxidizing atmosphere such as air at about 700°C to about 950°C , preferably about 800°C to about 900°C , more preferably about 850°C to about 880°C for about 0.5 hr to about 5 hrs, preferably about 1 hr to about 3 hrs, more preferably about 2 hrs to yield a calcined mixture. The calcined mixture then is vibration milled in a lower alkanol such as anhydrous ethanol to produce a milled material that has a particle size of about 0.5 micron to about 3 microns preferably about 1 micron to about 2 microns, more preferably about 1 micron.

The milled material is optionally mixed with up to about 2 wt. % of an optional organic binder based on the weight of milled material to produce a milled material composition. Useful binders include but are not limited to polyvinyl alcohol, polyvinyl butyral, and aqueous acrylic polymer emulsions such as Rhoplex from Rohm & Haas, polyethyleneimine and mixtures thereof. The milled material, optionally with binder composition is compressed at about 3000 PSI to about 10000 PSI, preferably about 5000 PSI to about 8000 PSI, more preferably about 5000 PSI to about 6000 PSI to yield a preform.

The preform is heated to about 500°C to about 600°C , preferably about 350°C to about 550°C , more preferably about 500°C to about 550°C to remove binder that may be present and to yield a green

preform. The green preform then is sintered at about 1000°C to about 1250°C, preferably about 1050°C to about 1150°C, more preferably about 1100°C for about 0.5 hr to about 5 hrs, preferably about 1 hr to about 2 hrs, more preferably about 2 hrs to yield a sintered product.

5 The density of the sintered product typically is about 5.0g/cm³ to about 5.7g/cm³, preferably about 5.7g/cm³ which represents $\geq 95\%$ of the theoretical density. The sintered products typically have a perovskite type crystal structure.

The sintered products are polished to a thickness of about 0.5 mm.
 10 The resulting polished products are electroded with fire-on-silver paste such a DuPont 6160 to produce an electroded sample. The electroded samples are poled at about 20°C to about 120°C, preferably about 20°C to about 50°C, more preferably about 25°C (room temperature) with an electric field of about 30 kV/cm to about 60kV/cm, preferably about
 15 40kV/cm to about 50kV/cm, more preferably about 40kV/cm for about 3 min to about 30 min, preferably about 5 min to about 10 min, more preferably about 10 min.

In a second aspect, doped piezoelectric compounds of general formula (IA), ((xNa_mBi_nTiO₃-yK_mBi_nTiO₃-zLi_mBi_nTiO₃-pBaTiO₃)-rM) (IA),
 20 where (0<x≤1), preferably (0.3≤x≤0.95), more preferably (0.3≤x≤0.8); (0≤y≤1), preferably (0≤y≤0.7), more preferably (0≤y≤0.2), (0≤z≤1), preferably (0≤z≤0.5), more preferably (0≤z≤0.2); (0<p<1), preferably (0<p≤0.2), more preferably (0<p≤0.1); (x+y+z+p=1); 0.3≤m≤0.7, preferably 0.4≤m≤0.6, more preferably 0.45≤m≤0.55; 0.3≤n≤0.7, preferably 0.4≤n≤0.6,
 25 more preferably 0.45≤n≤0.55; and 0.9≤m/n≤1.1, preferably 0.95≤m/n≤1.05, more preferably 0.98≤m/n≤1.02 and (0 wt%<r≤5wt%), preferably 0.2 wt%≤r≤2 wt%, more preferably 0.5 wt%≤r≤1wt%, where r is based on the weight of a compound within the scope of
 xNa_mBi_nTiO₃- yK_mBi_nTiO₃- zLi_mBi_nTiO₃-pBaTiO₃ where x, y, z, m, n and p
 30 are defined as above, and M is a dopant such as Al₂O₃, CoO, Co₂O₃,

Re₂O₃ where Re is rare earth element, NiCO₃, MnO₂, MnCO₃, Fe₂O₃, fluoride and mixtures thereof may be produced.

In this second aspect, the starting materials are dried and then blended into a mixture for use in manufacture of undoped compound within the scope of general formula (I). The mixture then is calcined in an oxidizing atmosphere such as air at about 700°C to about 950°C, preferably about 800°C to about 900°C, more preferably about 850°C to about 880°C for about 0.5 hr to about 5 hrs, preferably about 1 hr to about 3 hrs, more preferably about 2 hrs to yield a calcined mixture. The calcined mixture then is blended with a dopant to provide a doped mixture suitable for manufacture of a compound with the general formula (IIA) that is vibration milled in a lower alkanol such as anhydrous ethanol to produce a milled material that has a particle size of about 0.5 micron to about 3 microns, preferably about 1 micron to about 2 microns, more preferably about 1 micron.

The milled material optionally may be mixed with an optional organic binder in an amount of up to about 2 wt.%, based on the weight of milled material to produce a milled material composition. Useful binders include but are not limited to polyvinyl alcohol, polyvinyl butyral, aqueous acrylic polymer emulsions such as Rhoplex from Rohm & Haas, polyethyleneimine and mixtures thereof.

The milled material composition is compressed at about 3000 PSI to about 10000 PSI, preferably about 5000 PSI to about 8000 PSI, more preferably about 5000 PSI to about 6000 PSI to yield a preform. The preform then is heated to about 500°C to about 600 °C, preferably about 350°C to about 550°C, more preferably about 550°C to remove binder that may be present and to yield a green preform. The green preform is sintered at about 1000°C to about 1250°C, preferably about 1050°C to about 1150°C, more preferably about 1100°C for about 0.5 hr to about 5 hrs, preferably about 1 hr to about 2 hrs, more preferably about 2 hrs to yield a sintered product.

The sintered products are polished and electroded with fire-on-silver paste such as DuPont 6160 to produce electroded samples. The electroded samples are poled at about 20°C to about 120°C, preferably about 20°C to about 50°C, more preferably about 25°C (room

5 temperature) with an electric field of about 30 kV/cm to about 60kV/cm, preferably about 40kV/cm to about 50kV/cm, more preferably about 40kV/cm for about 3 min to about 30 min, preferably about 5 min to about 10 min, more preferably 10 min.

In a third aspect, compounds of the general formula (II)

10 $x\text{Na}_m\text{Bi}_n\text{TiO}_3-y\text{K}_m\text{Bi}_n\text{TiO}_3-z\text{Li}_m\text{Ba}_n\text{TiO}_3$ (II) such as $x\text{Na}_{0.5}\text{Bi}_{0.5}\text{TiO}_3-y\text{K}_{0.5}\text{Bi}_{0.5}\text{TiO}_3-z\text{Li}_{0.5}\text{Ba}_{0.5}\text{TiO}_3$ where ($0 < x \leq 1$), preferably ($0.3 \leq x \leq 0.95$), more preferably ($0.30 \leq x \leq 0.8$); ($0 < y \leq 1$), preferably ($0 < y \leq 0.7$), more preferably ($0 < y \leq 0.5$), ($0 < z \leq 1$), preferably ($0 < z \leq 0.5$), more preferably ($0 < z \leq 0.2$) ($x+y+z=1$); $0.3 \leq m \leq 0.7$, preferably $0.4 \leq m \leq 0.6$,
15 more preferably $0.45 \leq m \leq 0.55$; $0.3 \leq n \leq 0.7$, preferably $0.4 \leq n \leq 0.6$, more preferably $0.45 \leq n \leq 0.55$; $0.9 < m+n < 1.1$ and $0.9 \leq m/n \leq 1.1$, preferably $0.95 \leq m/n \leq 1.05$, more preferably $0.98 \leq m/n \leq 1.02$ may be produced.

In this third aspect, dried starting materials such as K_2CO_3 , Na_2CO_3 , TiO_2 , Bi_2O_3 , BaCO_3 and Li_2CO_3 are blended into a mixture for
20 use in manufacture of undoped piezoelectric compound within general formula (II). The mixture then is calcined in air at about 700°C to about 950°C, preferably about 800°C to about 900°C, more preferably about 850°C to about 880°C for about 0.5 hr to about 5 hrs, preferably about 1 hr to about 3 hrs, more preferably about 2 hrs to yield a calcined
25 mixture.

The calcined mixture then is vibration milled in a lower alcohol such as anhydrous ethanol to produce a milled material that has a particle size of about 0.5 micron to about 3 microns, preferably about 1 micron to about 2 microns, more preferably about 1 micron. The milled
30 material then is optionally mixed with up to about 2 wt. % of an organic

binder based on the weight of milled material to produce a milled material composition. Useful binders include but are not limited to polyvinyl alcohol, polyvinyl butyral, aqueous acrylic polymer emulsions such as Rhoplex from Rohm & Haas, polyethyleneimine and mixtures thereof.

The milled material composition, optionally with binder, is compressed at about 3000 PSI to about 8000 PSI preferably about 5000 PSI to about 8000 PSI, more preferably about 5000 PSI to about 6000 PSI to yield a preform. The preform then is heated to about 500°C to about 550°C, preferably about 550°C to remove binder that may be present and to yield a green preform. The green preform then is sintered at about 1000°C to about 1250°C, preferably about 1050°C to about 1150°C, more preferably about 1100°C for about 0.5 hrs to about 5 hrs, preferably about 1 hrs to about 2 hrs, more preferably about 2 hrs to yield a sintered product.

The sintered products are polished and electroded with fire-on-silver paste such as DuPont 6160 to produce electroded samples. The electroded samples are poled at about 20°C to about 120°C, preferably about 20°C to about 50°C, more preferably about 25°C with an electric field of about 20 kV/cm to about 60 kV/cm, preferably about 40 kV/cm to about 50 kV/cm, more preferably about 40 kV/cm for about 3 min to about 30 minutes, preferably about 5 min to about 10 min, more preferably about 10 min.

In a fourth aspect, doped compounds within the general formula (IIA) $((x\text{Na}_m\text{Bi}_n\text{TiO}_3 - y\text{K}_m\text{Bi}_n\text{TiO}_3 - z\text{Li}_m\text{Ba}_n\text{TiO}_3) - v\text{N})$ (IIA) where $(0 < x \leq 1)$, preferably $(0.3 \leq x \leq 0.9)$, more preferably $(0.30 \leq x \leq 0.8)$; $(0 < y \leq 1)$, preferably $(0 < y \leq 0.7)$, more preferably $(0 < y \leq 0.2)$, $(0 < z \leq 1)$, preferably $(0 < z \leq 0.5)$, more preferably $(0 < z \leq 0.2)$; $(x + y + z = 1)$, $0.3 \leq m \leq 0.7$, preferably $0.4 \leq m \leq 0.6$, more preferably $0.45 \leq m \leq 0.55$, $0.3 \leq n \leq 0.7$, preferably $0.4 \leq n \leq 0.6$, more preferably $0.45 \leq n \leq 0.55$; $0.9 \leq m/n \leq 1.1$, preferably $0.95 \leq m/n \leq 1.05$,

more preferably $0.98 \leq m/n \leq 1.02$; $0.9 < m+n < 1.1$ and N is a dopant such as Al_2O_3 , CoO , Co_2O_3 , Re_2O_3 where Re is rare earth element, NiCO_3 , MnO_2 , MnCO_3 , Fe_2O_3 , fluoride and mixtures thereof may be produced and ($0 < v \leq 5\text{wt}\%$) preferably $0.2 \text{ wt}\% \leq v \leq 2 \text{ wt}\%$, more preferably $0.5 \text{ wt}\% \leq v \leq 1\text{wt}\%$, where v is based on the weight of a compound within the scope of the formula $x\text{Na}_m\text{Bi}_n\text{TiO}_3 - y\text{K}_m\text{Bi}_n\text{TiO}_3 - z\text{Li}_m\text{Ba}_n\text{TiO}_3$ where x, y, z, m and n are defined as above.

In this fourth aspect, starting materials are dried and then blended into a mixture for use in manufacture of undoped compounds within the scope of general formula (II). The mixture then is calcined in air at about 700°C to about 950°C , preferably about 800°C to about 900°C , more preferably about 850°C to about 880°C for about 0.5 hrs to about 3 hrs, preferably about 1 hr to about 2 hrs, more preferably about 2 hrs to yield a calcined mixture. The calcined mixture then is blended with a dopant to provide a doped mixture that is vibration milled in a lower alkanol such as anhydrous ethanol to produce a milled material that has a particle size of about 0.5 micron to about 3 microns, preferably about 1 micron to about 2 microns, more preferably about 1 micron.

The milled material optionally may be mixed with up to about 2 wt.% of an organic binder, based on the weight of milled material to produce a milled material composition. Useful binders include but are not limited to polyvinyl alcohol, polyvinyl butyral, aqueous acrylic polymer emulsions such as Rhoplex from Rohm & Haas, polyethyleneimine and mixtures thereof.

The milled material composition is compressed at about 3000 PSI to about 10000 PSI, preferably about 5000 PSI to about 8000 PSI, more preferably about 5000 PSI to about 6000 PSI to yield a preform. The preform then is heated to about 500°C to about 700°C , preferably about 550°C to remove any binder present to yield a green preform. The green preform then is sintered at about 1000°C to about 1250°C , preferably

about 1050°C to about 1150°C, more preferably about 1100°C for about 0.5 hr to about 5 hrs, preferably about 1 hr to about 2 hrs, more preferably about 2 hrs to yield a sintered product.

The sintered products are polished and electroded with fire-on-silver paste such as DuPont 6160 to produce an electroded sample. The electroded samples are poled at about 20°C to about 120°C, preferably 20°C to about 50°C, more preferably about 25°C with an electric field of about 30 kV/cm to about 60 kV/cm, preferably about 40 kV/cm to about 50 kV/cm, more preferably about 40 kV/cm for about 3 min to about 30 min, preferably about 5 min to about 10 min, more preferably 10 min.

In a fifth aspect, compounds of the general formula (III) $(x\text{Na}_m\text{Bi}_n\text{TiO}_3-y\text{Li}_m\text{Bi}_n\text{TiO}_3-z\text{BaTiO}_3)$ (III) where $(0 < x \leq 1)$, preferably $(0.3 \leq x \leq 0.95)$, more preferably $(0.3 \leq x \leq 0.8)$; $(0 < y \leq 1)$, preferably $(0 < y \leq 0.7)$, more preferably $(0 < y \leq 0.2)$ and $(0 < z \leq 1)$, preferably $(0 < z \leq 0.5)$, more preferably $(0 < z \leq 0.2)$; $(x+y+z=1)$ $0.3 \leq m \leq 0.7$, preferably $0.4 \leq m \leq 0.6$, more preferably $0.45 \leq m \leq 0.55$; $0.3 \leq n \leq 0.7$, preferably $0.4 \leq n \leq 0.6$, more preferably $0.45 \leq n \leq 0.55$; $0.9 < m+n < 1.1$, and $0.9 \leq m/n \leq 1.1$, preferably $0.95 \leq m/n \leq 1.05$, more preferably $0.98 \leq m/n \leq 1.02$, may be produced.

Dried starting materials such as Na_2CO_3 , TiO_2 , Bi_2O_3 , BaCO_3 and Li_2CO_3 are blended into a mixture for use in manufacture of undoped piezoelectric compounds within general formula (III) such as $x\text{Na}_{0.5}\text{Bi}_{0.5}\text{TiO}_3-y\text{Li}_{0.5}\text{Bi}_{0.5}\text{TiO}_3-z\text{BaTiO}_3$. The mixture then is calcined in air at about 700°C to about 950°C, preferably about 800°C to about 900°C, more preferably about 850°C to about 880°C for about 0.5 hr to about 2 hrs, preferably about 2 hrs yield a calcined mixture. The calcined mixture then is vibration milled in a lower alkanol such as anhydrous ethanol to produce a milled material that has a particle size of about 0.5 micron to about 3 microns, preferably about 1 micron to about 2

microns, more preferably about 2 microns. The milled material then is optionally mixed with up to about 2 wt. % of an organic binder based on the weight of milled material to produce a milled material composition. Useful binders include but are not limited to polyvinyl alcohol, polyvinyl butyral, aqueous acrylic polymer emulsions such as Rhoplex from Rohm & Haas, polyethyleneimine and mixtures thereof.

The milled material, optionally with binder, is compressed at about 3000 PSI to about 10000 PSI, preferably about 5000 PSI to about 8000 PSI, more preferably about 5000 PSI to about 6000 PSI to yield a preform. The preform then is heated to about 500°C to about 650°C, preferably about 550°C to remove binder that may be present and to yield a green preform. The green preform then is sintered at about 1000°C to about 1250°C, preferably about 1050°C to about 1150°C, more preferably about 1100°C for about 0.5 hr to about 5 hrs, preferably about 1 hr to about 2hrs, more preferably about 2 hrs to yield a sintered product.

The sintered products are polished and electroded with fire-on-silver paste such as DuPont 6160 to produce an electroded sample. The electroded samples are poled at about 20°C to about 120°C, preferably about 20°C to about 50°C, more preferably about 25°C with an electric field of about 30 kV/cm to about 60 kV/cm, preferably about 40 kV/cm to about 50 kV/cm, more preferably about 40 kV/cm for about 3 min to about 30 min, preferably about 5 min to about 10 min, more preferably about 10 min.

In a sixth aspect, doped compounds of the general formula IIIA $((x\text{Na}_m\text{Bi}_n\text{TiO}_3-y\text{Li}_m\text{Bi}_n\text{TiO}_3-z\text{BaTiO}_3)-w\text{N})$ (IIIA) where $(0 < x \leq 1)$, preferably $(0.3 \leq x \leq 0.95)$, more preferably $(0.3 \leq x \leq 0.8)$; $(0 < y \leq 1)$, preferably $(0 < y \leq 0.7)$, more preferably $(0 < y \leq 0.2)$ and $(0 < z \leq 1)$, preferably $(0 < z \leq 0.5)$, more preferably $(0 < z \leq 0.2)$, $(x+y+z=1)$; $0.3 \leq m \leq 0.7$, preferably $0.4 \leq m \leq 0.6$, more preferably $0.45 \leq m \leq 0.55$; $0.3 \leq n \leq 0.7$, preferably $0.4 \leq n \leq 0.6$, more preferably

0.45 ≤ n ≤ 0.55; 0.9 < m+n < 1.1, and 0.9 ≤ m/n ≤ 1.1, preferably 0.95 ≤ m/n ≤ 1.05, more preferably 0.98 ≤ m/n ≤ 1.02 (0 < w ≤ 5wt%) preferably 0.2 wt% ≤ w ≤ 2 wt%, more preferably 0.5 wt% ≤ w ≤ 1 wt%, where w is based on the weight of a compound within the scope of the formula $x\text{Na}_m\text{Bi}_n\text{TiO}_3\text{-}$
5 $y\text{Li}_m\text{Bi}_n\text{TiO}_3\text{-}z\text{BaTiO}_3$ where x, y, z, m and n are defined as above and where N is a dopant such as Al₂O₃, CoO, Co₂O₃, Re₂O₃ where Re is rare earth element, NiCO₃, MnO₂, MnCO₃, Fe₂O₃, fluoride and mixtures thereof.

In this sixth aspect, starting materials are dried and then blended
10 into a mixture for use in manufacture of undoped piezoelectric compounds within general formal (III). The mixture then is calcined in air at about 700°C to about 950°C, preferably about 800°C to about 900°C, more preferably about 850°C to about 880°C for about 0.5 hr to about 5 hrs, preferably about 1 hr to about 3 hrs, more preferably about 2 hrs to
15 yield a calcined mixture.

The calcined mixture then is blended with a dopant to provide a doped mixture that is vibration milled in a lower alkanol such as anhydrous ethanol to produce a milled material that has a particle size of about 0.5 micron to about 3 microns, preferably about 1 micron to about
20 2 microns, more preferably about 2 microns.

The milled material optionally may be mixed with an organic binder in an amount of up to about 2 wt.%, based on the weight of milled material to produce a milled material composition. Useful binders include but are not limited to polyvinyl alcohol, polyvinyl butyral,
25 aqueous acrylic polymer emulsions such as Rhoplex from Rohm & Haas, polyethyleneimine and mixtures thereof. The milled material composition is compressed at about 3000 PSI to about 10000 PSI, preferably about 5000 PSI to about 8000 PSI, more preferably about 5000 PSI to about 6000 PSI to yield a preform.

30

The preform is heated to about 500°C to about 650°C, preferably about 550°C to remove binder that may be present to yield a green preform. The green preform then is sintered at about 1000°C to about 1250°C, preferably about 1050°C to about 1150°C, more preferably about 1100°C about 0.5 hr to about 5hrs, preferably about 1 hr to about 2 hrs, more preferably about 2 hrs to yield a sintered product.

The sintered products are polished and electroded with fire-on-silver paste such as DuPont 6160 to produce an electroded sample. The electroded samples are poled at room temperature with an electric field of about 30 kV/cm to about 60 kV/cm, preferably about 40 kV/cm to about 50 kV/cm, more preferably about 40 kV/cm for about 3 min to about 30 min, preferably about 5 min to about 10 min, more preferably about 10 min.

The invention is further described below by reference to the following, non-limiting examples.

Example 1A: Manufacture of an undoped piezoelectric compound of the formula $x\text{Na}_{0.5}\text{Bi}_{0.5}\text{TiO}_3 - y\text{K}_{0.5}\text{Bi}_{0.5}\text{TiO}_3 - p\text{BaTiO}_3$ where x is 0.79, y is 0.14, and p is 0.07, hereinafter referred to as BNBK79

0.64gms K_2CO_3 , 2.77gms Na_2CO_3 , 10.57 gms TiO_2 , 14.19 gms Bi_2O_3 and 1.83 gms BaCO_3 are blended to yield a mixture. The mixture is calcined in air at 880°C for 2 hrs to yield a calcined composition. The calcined composition then is vibration milled in anhydrous ethanol to produce a milled material that has a particle size of 1 micron. The milled material then is mixed with 2 wt. % Rhoplex binder from Rohm and Haas where the amount of binder is based on the weight of milled material. The resulting milled material-binder composition is compressed at 5000 PSI to yield a preform in the form of a disk that measures 12 mm diameter by 1 mm thick.

The preform is heated in air to 550 °C to burn out the binder and to yield a green preform. The green preform then is sintered in air at

1100°C for 2 hrs to yield $x\text{Na}_{0.5}\text{Bi}_{0.5}\text{TiO}_3\text{-}y\text{K}_{0.5}\text{Bi}_{0.5}\text{TiO}_3\text{-}z\text{BaTiO}_3$ ($\text{B}_1\text{NB}_2\text{K}$) where x is 0.79, y is 0.14, and z is 0.07 sintered product. The sintered product is polished to 0.5 mm thickness and electroded with fire-on-silver paste (DuPont 6160) on the parallel faces for planar and thickness modes property characterizations. The electroded disks are poled at 30 °C with an applied field of 60kV/cm for 5 min.

Example 1B: Manufacture of piezoelectric compound that has the formula $(x\text{Na}_{0.5}\text{Bi}_{0.5}\text{TiO}_3\text{-}y\text{K}_{0.5}\text{Bi}_{0.5}\text{TiO}_3\text{-}p\text{BaTiO}_3)\text{-}0.5\text{Mn}$ where x is 0.79, y is 0.14, and p is 0.07, hereinafter referred to as BNBK 79-0.5wt%MnO₂

0.64gms K₂CO₃, 2.77gms Na₂CO₃, 10.57gms TiO₂ and 14.19 gms Bi₂O₃ and 1.83 gms BaCO₃ are blended to yield a mixture. The mixture then is calcined in air at 880 °C for 2 hours to yield a calcined composition. The calcined composition then is mixed with 0.14gms MnO₂(0.5wt%MnO₂ based on the weight of the calcined composition) to yield a doped mixture. The doped mixture is vibration milled in anhydrous ethanol to produce a milled material that has a particle size of 1 micron. The milled material is mixed with 2wt. % Rhoplex binder from Rohm and Haas where the amount of binder is based on the weight of milled material. The resulting milled material-binder composition is compressed at 5000 PSI to yield a preform in the form of a disk that measures 12 mm diameter by 1 mm thick. The preform is heated in air to 550 °C to burn out the binder and to yield a green preform. The green preform then is sintered in air at 1100°C for 2 hrs to yield a sintered piezoelectric compound of the formula $(x\text{Na}_{0.5}\text{Bi}_{0.5}\text{TiO}_3\text{-}y\text{K}_{0.5}\text{Bi}_{0.5}\text{TiO}_3\text{-}z\text{BaTiO}_3)\text{-}0.5\text{Mn}$ where x is 0.79, y is 0.14, and z is 0.07. The sintered product is polished to 0.5 mm thickness and electroded with fire-on-silver paste (DuPont 6160) on the parallel faces for planar mode property characterizations. The electroded disks are poled at 30 °C with an applied field of 60kV/cm for 30 min.

Example 1C: Manufacture of piezoelectric of the formula $(x\text{Na}_{0.5}\text{Bi}_{0.5}\text{TiO}_3 - y\text{K}_{0.5}\text{Bi}_{0.5}\text{TiO}_3 - p\text{BaTiO}_3) - 0.7\text{Mn}$ where x is 0.79, y is 0.14, and p is 0.07 hereinafter referred to as BNBK 79-0.7wt%MnO₂.

5 The procedure of example 1B is followed except that 0.2 gms. MnO₂ is employed.

Example 1D: Manufacture of piezoelectric of the formula $(x\text{Na}_{0.5}\text{Bi}_{0.5}\text{TiO}_3 - y\text{K}_{0.5}\text{Bi}_{0.5}\text{TiO}_3 - p\text{BaTiO}_3) - 0.8\text{Mn}$ where x is 0.79, y is 0.14, and p is 0.07, hereinafter referred to as BNBK 79-0.8wt%MnO₂.

10

The procedure of example 1B is followed except that 0.23 gm of MnO₂ is employed.

15 Example 1E: Manufacture of piezoelectric of the formula $(x\text{Na}_{0.5}\text{Bi}_{0.5}\text{TiO}_3 - y\text{K}_{0.5}\text{Bi}_{0.5}\text{TiO}_3 - p\text{BaTiO}_3) - 1.0 \text{ wt.} \% \text{ Mn}$ where x is 0.79, y is 0.14, and p is 0.07 doped with 1.0 wt% MnO₂, hereinafter referred to as BNBK 79-1.0wt%MnO₂.

20 The procedure of example 1B is followed except that 0.28 gms. MnO₂ is employed.

Example 1F: Manufacture of piezoelectric of the formula $(x\text{Na}_{0.5}\text{Bi}_{0.5}\text{TiO}_3 - y\text{K}_{0.5}\text{Bi}_{0.5}\text{TiO}_3 - p\text{BaTiO}_3) - 1.0\text{wt}\%\text{Co}_2\text{O}_3$ where x is 0.79, y is 0.14, and p is 0.07 doped with 1.0 wt% Co₂O₃, hereinafter referred to as BNBK 79-1.0wt%Co₂O₃.

25

The procedure of example 1B is followed except that 0.28gms. Co₂O₃ is used as a dopant instead of MnO₂.

30

Example 1G: Manufacture of piezoelectric of the formula $(x\text{Na}_{0.5}\text{Bi}_{0.495}\text{TiO}_3 - y\text{K}_{0.5}\text{Bi}_{0.495}\text{TiO}_3 - p\text{BaTiO}_3) - 0.8\text{Mn}$ where x is 0.79, y is 0.14, p is 0.07, hereinafter referred to as vacancy defect engineered BNBK 79-0.8wt%MnO₂.

35

The procedure of example 1B is followed except that 14.05 gms Bi₂O₃ and 0.23 gms MnO₂ are employed.

Example 2: Manufacture of piezoelectric of the formula $x\text{Na}_{0.5}\text{Bi}_{0.5}\text{TiO}_3 - y\text{K}_{0.5}\text{Bi}_{0.5}\text{TiO}_3 - z\text{Li}_{0.5}\text{Bi}_{0.5}\text{TiO}_3$ where $x=0.69$, $y=0.26$ and $z=0.05$ hereinafter referred to as ("BNBKT").

5 The procedure of example 1A is followed except that 1.35gms K_2CO_3 , 2.74gms Na_2CO_3 , 0.14 gms Li_2CO_3 , 14.40gms TiO_2 and 17.30 gms Bi_2O_3 are employed.

10 Example 2A: Manufacture of doped $(x\text{Na}_{0.5}\text{Bi}_{0.5}\text{TiO}_3 - y\text{K}_{0.5}\text{Bi}_{0.5}\text{TiO}_3 - z\text{Li}_{0.5}\text{Bi}_{0.5}\text{TiO}_3) - v\text{MnO}_2$ where $x=0.69$, $y=0.26$, $z=0.05$ and $v=0.8\text{wt}\%$, hereinafter referred to as ("BNBKTR")

 The procedure of example 1B is followed except that 1.35gms K_2CO_3 , 2.74gms Na_2CO_3 , 0.14 gms Li_2CO_3 , 14.40gms TiO_2 and 17.30
15 gms Bi_2O_3 and 0.27 gm MnO_2 are employed.

Example 3: Manufacture of $x\text{Na}_{0.5}\text{Bi}_{0.5}\text{TiO}_3 - z\text{BaTiO}_3$ ($x+z=1$) where $x=0.8$ and $z=0.2$.

20 The procedure of example 1A is followed except that 3.26gms Na_2CO_3 , 12.31gms TiO_2 , 14.34gms Bi_2O_3 and 6.06gms BaCO_3 are used as starting materials.

25 Example 4: Manufacture of $x\text{Na}_{0.5}\text{Bi}_{0.5}\text{TiO}_3 - y\text{K}_{0.5}\text{Bi}_{0.5}\text{TiO}_3$ ($x+y=1$) where $x=0.7$ and ($y=0.3$).

 The procedure of example 1A is followed except that 1.59gms K_2CO_3 , 2.85gms Na_2CO_3 , 12.31gms TiO_2 , 17.92gms Bi_2O_3 are employed as starting materials.

30

Example 5: Manufacture of $x\text{Na}_{0.5}\text{Bi}_{0.5}\text{TiO}_3$ - $y\text{K}_{0.5}\text{Bi}_{0.5}\text{TiO}_3$ - $z\text{Li}_{0.5}\text{Bi}_{0.5}\text{TiO}_3$ - $p\text{BaTiO}_3$ ($x+y+z+p=1$) ("BNKLBT"), where $x=0.83$, $y=0.084$, $z=0.03$ and $p=0.056$

5 The procedure of example 1A is followed except that 0.445gms K_2CO_3 , 3.38gms Na_2CO_3 , 0.085gms Li_2CO_3 , 1.70gms BaCO_3 , 12.31gms TiO_2 and 16.92gms Bi_2O_3 are employed as starting materials.

10 Example 5A: Manufacture of $(x\text{Na}_{0.5}\text{Bi}_{0.5}\text{TiO}_3$ - $y\text{K}_{0.5}\text{Bi}_{0.5}\text{TiO}_3$ - $z\text{Li}_{0.5}\text{Bi}_{0.5}\text{TiO}_3$ - $p\text{BaTiO}_3)$ - $r\text{Co}_2\text{O}_3$ where $x=0.83$, $y=0.084$, $z=0.03$, $p=0.056$ and $r=1.5\text{wt}\%$.

 The procedure of example 1B is followed except that 0.445gms K_2CO_3 , 3.38gms Na_2CO_3 , 0.085gms Li_2CO_3 , 1.70gms BaCO_3 , 12.31gms TiO_2 , 16.92gms Bi_2O_3 and 0.49gms Co_2O_3 are employed as starting materials.

20 Example 6: Manufacture of vacancy defect engineered $(x\text{Na}_{0.5}\text{Bi}_{0.495}\text{TiO}_3$ - $y\text{K}_{0.5}\text{Bi}_{0.495}\text{TiO}_3$ - $z\text{Li}_{0.5}\text{Bi}_{0.495}\text{TiO}_3$ - $p\text{BaTiO}_3)$ - $r\text{Co}_2\text{O}_3$, where $x=0.83$, $y=0.084$, $z=0.03$, $p=0.056$ and $r=1.5\text{wt}\%$.

 The procedure of example 1B is followed except that 0.445 gms K_2CO_3 , 3.38gms Na_2CO_3 , 0.085 gms Li_2CO_3 , 1.70gms BaCO_3 , 12.31 gms TiO_2 , 16.75 gms Bi_2O_3 and 0.49gms Co_2O_3 are employed as starting materials.

 Example 7: $x\text{Na}_{0.5}\text{Bi}_{0.5}\text{TiO}_3$ - $y\text{K}_{0.5}\text{Bi}_{0.5}\text{TiO}_3$ - $z\text{Li}_{0.5}\text{Bi}_{0.5}\text{TiO}_3$ - $p\text{BaTiO}_3$ ($x+y+z+p=1$) ("BNKLBT"), where $x=0.85$, $y=0.072$, $z=0.03$ and $p=0.048$.

30 The procedure of example 1A is followed except that 0.38gms K_2CO_3 , 3.47gms Na_2CO_3 , 0.085 gms Li_2CO_3 , 1.45gms BaCO_3 , 12.31 gms TiO_2 , and 17.06gms Bi_2O_3 are employed as starting materials.

Example 8: $x\text{Na}_{0.5}\text{Bi}_{0.5}\text{TiO}_3$ - $y\text{K}_{0.5}\text{Bi}_{0.5}\text{TiO}_3$ - $z\text{Li}_{0.5}\text{Bi}_{0.5}\text{TiO}_3$ - $p\text{BaTiO}_3$
($x+y+z+p=1$) ("BNKLBT"), where $x=0.80$, $y=0.102$, $z=0.03$ and $p=0.068$.

The procedure of example 1A is followed except that 0.54gms
5 K_2CO_3 , 3.26gms Na_2CO_3 , 0.085 gms Li_2CO_3 , 2.06gms BaCO_3 , 12.31 gms
 TiO_2 , and 16.70gms Bi_2O_3 are employed as starting materials.

Example 9: ($x\text{Na}_{0.5}\text{Bi}_{0.5}\text{TiO}_3$ - $y\text{K}_{0.5}\text{Bi}_{0.5}\text{TiO}_3$ - $z\text{Li}_{0.5}\text{Bi}_{0.5}\text{TiO}_3$ - $p\text{BaTiO}_3$)-
10 $r\text{Co}_2\text{O}_3$, $r=1.5\%$, ($x+y+z+p=1$) where $x=0.85$, $y=0.072$, $z=0.03$ and
 $p=0.048$.

The procedure of example 1B is followed except that 0.38gms
 K_2CO_3 , 3.47gms Na_2CO_3 , 0.085 gms Li_2CO_3 , 1.45gms BaCO_3 , 12.31 gms
15 TiO_2 , 17.06 gms Bi_2O_3 and 0.49gms Co_2O_3 are employed as starting
materials.

Example 10: ($x\text{Na}_{0.5}\text{Bi}_{0.5}\text{TiO}_3$ - $y\text{K}_{0.5}\text{Bi}_{0.5}\text{TiO}_3$ - $z\text{Li}_{0.5}\text{Bi}_{0.5}\text{TiO}_3$ - $p\text{BaTiO}_3$)-
20 $r\text{Co}_2\text{O}_3$, $r=1.5\%$, ($x+y+z+p=1$) where $x=0.80$, $y=0.102$, $z=0.03$ and
 $p=0.068$.

The procedure of example 1B is followed except that 0.54gms
 K_2CO_3 , 3.26gms Na_2CO_3 , 0.085gms Li_2CO_3 , 2.06gms BaCO_3 , 12.31 gms TiO_2 ,
16.70 gms Bi_2O_3 and 0.49gms Co_2O_3 are employed as starting materials.

25 Various properties of BNBK type ceramics as compared to
commercial PZT ceramics is shown in Tables II, III and IV. The
polarization hysteresis for BNBK 79-0.8wt%MnO₂ piezoelectric
compound of example 1G compared to PZT4 and PZT8 is shown in Fig. 3;

Table II. Characteristic piezoelectric properties of BNBK lead free ceramics compared to commercial hard PZT.

Material	$T_C (^{\circ}C)$	$T_d (^{\circ}C)$	$\epsilon_{33}^T / \epsilon_0$	loss	P_r (C/m ²)	E_C (kV/cm)	E_i (kV/cm)	d_{33} (pC/N)	k_{33}	Q	r (g/cc)	v_3^D (m/s)
Ex. 1G BNBK-Mn	285	232	510	0.6%	0.22	37.0	6	96	0.46	1100	5.8	5070
Ex. 1A BNBK79	280	224	650	4.0%	0.29	25.0	0	135	0.54	110	5.7	-----
PZT4	328	-----	1300	0.4%	0.36	14.2	3	289	0.70	500	7.6	4570
PZT8	300	-----	1000	0.4%	0.27	19.0	7	225	0.64	1000	7.6	4600

Table III: Elastic compliance s_{ij} (10⁻¹² m²/N), elastic stiffness c_{ij} (10¹⁰ N/m²)

5 constants, Piezoelectric Coefficients, d_{ij} (pC/N), e_{ij} (C/m²), g_{ij} (10⁻³Vm/N), h_{ij} (10⁸V/m), d_h (pC/N), Electromechanical Coupling Factors k_{ij} , Dielectric Constants, ϵ_{ij} (ϵ_0), and Dielectric Impermeability Constants, β (10⁻⁴/ ϵ_0), for hard BNBK lead free ceramics and compared to hard PZT.

EX.	Material	s_{11}^E	s_{12}^E	s_{13}^E	s_{33}^E	s_{44}^E	s_{66}^E	s_{11}^D	s_{12}^D	s_{13}^D	s_{33}^D	s_{44}^D	s_{66}^D
1G	BNBK-Mn	9.2	-2.1	-2.5	10.1	22.0	22.6	9.2	-2.1	-2.2	8.0	16.5	22.6
	PZT4	12.3	-4.1	-5.2	15.5	39.0	32.7	10.9	-5.4	-2.1	7.9	19.3	32.7
	PZT8	11.5	-3.4	-4.8	13.5	31.9	29.8	10.4	-4.4	-2.3	8.0	22.6	29.8

EX.	Material	c_{11}^E	c_{12}^E	c_{13}^E	c_{33}^E	c_{44}^E	c_{66}^E	c_{11}^D	c_{12}^D	c_{13}^D	c_{33}^D	c_{44}^D	c_{66}^D
1G	BNBK-Mn	12.9	4.1	4.2	12.0	4.5	4.4	12.9	4.1	4.1	14.9	6.1	4.4
	PZT4	13.9	7.6	7.1	11.5	2.6	3.1	14.5	8.0	5.7	15.9	5.2	3.1
	PZT8	13.7	7.2	7.5	12.3	3.1	3.4	14.0	7.5	6.4	16.1	4.4	3.4

EX.	Material	d_{33}	d_{31}	d_{15}	e_{33}	e_{31}	e_{15}	g_{33}	g_{31}	g_{15}	h_{33}	h_{31}	h_{15}
1G	BNBK-Mn	96	-15	153	10.1	-0.3	6.9	21.2	-3.3	33.3	28.4	-0.9	20.0
	PZT4	289	-126	496	15.1	-5.2	12.7	25.1	-10.7	38.0	26.9	-9.3	19.7
	PZT8	225	-97	330	13.2	-4.0	10.4	25.4	-10.9	29.0	25.7	-7.8	13.1

EX.	Material	k_{33}	k_{31}	k_{15}	k_t	k_p	ϵ_{33}^T	ϵ_{11}^T	ϵ_{33}^S	ϵ_{11}^S	β_{33}^T	β_{11}^T	β_{33}^S	β_{11}^S
1G	BNBK-Mn	0.46	0.07	0.50	0.44	0.12	510	460	345	404	19.6	21.7	25.0	29.0
	PZT4	0.70	0.33	0.71	0.51	0.58	1300	1475	635	730	7.7	6.8	15.8	13.7
	PZT8	0.64	0.30	0.55	0.48	0.51	1000	1290	580	900	10.0	7.8	17.2	11.1

10 Table III, as presented above, shows material constants for vacancy defect engineered BNBK 79-0.8wt% MnO₂ piezoelectric compound of Example 1G compared to PZT4 and PZT8 hard ceramics, measured according to IEEE Standards on Piezoelectricity.

Table IV: Characteristic piezoelectric properties of pure and Co-doped (1.5wt% Co_2O_3) xNBT-yKBT-zLBT-pBT (abbreviated as xN-yK-zL-pBT) lead free ceramics.

EX.	xN-yK-zL-pBT	T_c ($^{\circ}\text{C}$)	T_d ($^{\circ}\text{C}$)	$\epsilon_{33}^T / \epsilon_0$	loss	P_r (C/m^2)	E_c (kV/cm)	E_i (kV/cm)	d_{33} (pC/N)	k_p	k_t	Q
Ex.5	83-8.4-3-5.6	280	188	890	3%	25	30	-----	170	0.17	0.49	100
Ex.7	85-7.2-3-4.8	290	120	970	3%	30	30	-----	190	0.25	0.50	100
Ex.8	80-10.2-3-6.8	265	210	830	3%	22	30	-----	150	0.17	0.49	90
	Co_2O_3-doped											
Ex.5A	83-8.4-3-5.6	280	200	650	0.7%	23	36	6	120	0.15	0.48	700
Ex.9	85-7.2-3-4.8	285	175	600	0.6%	30	35	3	140	0.22	0.51	700
Ex.10	80-10.2-3-6.8	285	220	510	0.6%	21	32	5	110	0.10	0.49	800

5

Table IV as presented above, shows characteristic properties of xNBT-yKBT-zLBT-pBT lead free ceramics without and with dopant Co_2O_3 .

Fig. 2 and Table V show various properties of MnO_2 doped NBT piezoelectric materials of examples 1A-1E.

10

Table V

Ex.	MnO_2 (wt%)	Mechanical quality factor	Piezoelectric d coefficient	dielectric constant	dielectric loss	thickness mode coupling	planar mode coupling
1A	0	120	118	610	0.025	0.48	0.18
1B	0.5	850	105	520	0.006	0.48	0.12
1C	0.7	1050	100	490	0.004	0.48	0.11
1D	0.8	1100	104	500	0.004	0.49	0.11
1E	1	769	102	480	0.005	0.46	0.11

Fig. 3 shows polarization hysteresis for BNBK 79-0.8wt%MnO₂ piezoelectric compound of example 1G compared to PZT4 and PZT8;

15

Fig. 4 shows strain hysteresis of lead free BNBK 79 of example 1A and 0.8wt%MnO₂ doped BNBK 79 of example 1G piezoelectric compounds compared to PZT4 and PZT8;

Figs. 5 (a) shows temperature dependence of dielectric behavior for undoped BNBK 79 of example 1A. Figs. 5(b)-(d) show temperature dependence of dielectric behavior for Mn doped BNBK79 piezoelectric

20

compounds of examples 1B, 1D and 1E respectively. As shown in Figs. 5(a)-5(d), depolarization temperature (T_d) decreases slightly from 250°C to 230°C with increasing Mn dopant level.

Fig. 6 shows temperature dependence of electromechanical coupling factors (k_{ij}) for vacancy defect engineered 0.8 wt.% MnO_2 doped BNBK79 piezoelectric compound of example 1G. Lateral coupling factor k_{31} is 7% at room temperature and thickness coupling factor k_t is 44% at room temperature. As shown in Fig. 6, k_{31} increases to 10% at 235°C and k_t increases to 50% at 235°C.

Fig. 7 shows planar electromechanical coupling factor variation as a function of temperature for vacancy defect engineered BNBK79-0.8wt% MnO_2 piezoelectric compound of Example 1G compared to PZT 4 and PZT8. As shown in Fig. 7, planar electromechanical coupling factor increases slightly with temperature up to 235°C, whereas the coupling factor of PZT4 and PZT8 ceramics decrease continuously, dropping by 25%-50% at the same temperature.

Figs. 8 (a)-8(c) show temperature dependence of dielectric behavior for Co_2O_3 doped vacancy defect engineered BNKLBT ceramics of examples 10, 5A and 9, respectively.

Fig. 9 shows temperature dependence of electromechanical coupling factor, including thickness coupling k_t and planar coupling k_p , for Co_2O_3 doped vacancy defect engineered BNKLBT ceramics of examples 10, 5A and 9, exhibiting a very stable temperature behavior till their depolarization temperature T_d .


Fig. 10 shows the temperature dependence of mechanical quality factor Q , for Co_2O_3 doped vacancy defect engineered BNKLBT ceramics of examples 10, 5A and 9, where the Q values are larger than 700 at room temperature, gradually decreased with increasing temperature, keep yet high Q value around 200 when the temperature approaching the depolarization temperature T_d .

The disclosed piezoelectric compounds may be employed in electronic devices such as ultrasonic transducers that typically operate at 20kHz and above as well as in high intensity focused ultrasound (HIFU) transducers. The disclosed piezoelectric compounds also may be
5 employed as stators in ultrasonic motors and as components in piezoelectric transformers.

Ultrasonic motors, and their construction, are well known as shown in US Pat. 7576472, the teachings of which are incorporated by reference herein by their entirety. Piezoelectric transformers and their
10 construction also are known, as shown by US Pat. 7,593,241, the teachings of which are incorporated by reference herein by their entirety.

CLAIMS:

1. A piezoelectric compound having the formula $x\text{Na}_m\text{Bi}_n\text{TiO}_3$ -
 $y\text{K}_m\text{Bi}_n\text{TiO}_3$ - $z\text{Li}_m\text{Bi}_n\text{TiO}_3$ - $p\text{BaTiO}_3$ where $(0 < x \leq 1)$, $(0 \leq y \leq 1)$, $(0 \leq z \leq 1)$, $(0 < p \leq 1)$, $(x+y+z+p=1)$, $(0.3 \leq m \leq 0.7)$, $(0.3 \leq n \leq 0.7)$, $(0.9 \leq m/n \leq 1.1)$.
5
2. A piezoelectric compound having the formula $((x\text{Na}_m\text{Bi}_n\text{TiO}_3$ -
 $y\text{K}_m\text{Bi}_n\text{TiO}_3$ - $z\text{Li}_m\text{Bi}_n\text{TiO}_3$ - $p\text{BaTiO}_3)$ - $r\text{M}$) where $(0 < x \leq 1)$, $(0 \leq y \leq 1)$,
10 $(0 \leq z \leq 1)$, $(0 < p \leq 1)$, $(x+y+z+p=1)$, $(0.3 \leq m \leq 0.7)$, $(0.3 \leq n \leq 0.7)$, $(0.9 \leq m/n \leq 1.1)$ and $(0 \text{ wt}\% < r \leq 5 \text{ wt}\%)$ where r is based on the weight of a compound within the scope of $x\text{Na}_m\text{Bi}_n\text{TiO}_3$ - $y\text{K}_m\text{Bi}_n\text{TiO}_3$ - $z\text{Li}_m\text{Bi}_n\text{TiO}_3$ - $p\text{BaTiO}_3$ and M is a dopant selected from the group consisting of Al_2O_3 , CoO , Co_2O_3 , Re_2O_3 where Re is rare earth
15 element, NiCO_3 , MnO_2 , MnCO_3 , Fe_2O_3 , fluoride and mixtures thereof.
3. A piezoelectric compound having the formula $x\text{Na}_m\text{Bi}_n\text{TiO}_3$ -
 $y\text{K}_m\text{Bi}_n\text{TiO}_3$ - $z\text{Li}_m\text{Ba}_n\text{TiO}_3$ where $(0 < x \leq 1)$, $(0 < y \leq 1)$, $(0 \leq z \leq 1)$,
20 $(x+y+z=1)$, $(0.3 \leq m \leq 0.7)$, $(0.3 \leq n \leq 0.7)$, $(0.9 < m+n < 1.1)$ and $(0.9 \leq m/n \leq 1.1)$.
4. A piezoelectric compound having the formula $((x\text{Na}_m\text{Bi}_n\text{TiO}_3$ -
 $y\text{K}_m\text{Bi}_n\text{TiO}_3$ - $z\text{Li}_m\text{Ba}_n\text{TiO}_3)$ - $v\text{N}$) where $(0 < x \leq 1)$, $(0 < y \leq 1)$, $(0 \leq z \leq 1)$,
25 $(x+y+z=1)$, $(0.3 \leq m \leq 0.7)$, $(0.3 \leq n \leq 0.7)$, $(0.9 \leq m/n \leq 1.1)$, $(0.9 < m+n < 1.1)$ and N is a dopant selected from the group consisting of Al_2O_3 , CoO , Co_2O_3 , Re_2O_3 where Re is rare earth element, NiCO_3 , MnO_2 , MnCO_3 , Fe_2O_3 , fluoride and mixtures thereof and
where $(0 < v \leq 5 \text{ wt}\%)$ where v is based on the weight of a
30 compound within the scope of the formula $x\text{Na}_m\text{Bi}_n\text{TiO}_3$ -



5. A piezoelectric compound having the formula $(xNa_mBi_nTiO_3-yLi_mBi_nTiO_3-zBaTiO_3)(III)$ where $(0 < x \leq 1)$, $(0 < y \leq 1)$, $(0 < z \leq 1)$, $(x+y+z=1)$, $(0.3 \leq m \leq 0.7)$, $(0.3 \leq n \leq 0.7)$, $(0.9 < m+n < 1.1)$ and $(0.9 \leq m/n \leq 1.1)$.

5
6. A piezoelectric compound having the formula $((xNa_mBi_nTiO_3-yLi_mBi_nTiO_3-zBaTiO_3)-wN)$ where $(0 < x \leq 1)$, $(0 < y \leq 1)$, $(0 < z \leq 1)$, $(x+y+z=1)$, $(0.3 \leq m \leq 0.7)$, $(0.3 \leq n \leq 0.7)$, $(0.9 < m+n < 1.1)$, $(0.9 \leq m/n \leq 1.1)$ and $(0 < w \leq 5wt\%)$ where w is based on the weight of a compound within the scope of the formula $xNa_mBi_nTiO_3-yLi_mBi_nTiO_3-zBaTiO_3$ and where N is a dopant selected from the group consisting of Al_2O_3 , CoO , Co_2O_3 , Re_2O_3 where Re is rare earth element, $NiCO_3$, MnO_2 , $MnCO_3$, Fe_2O_3 , fluoride and mixtures thereof.

10

15
7. The compound of claim 2 wherein M is MnO_2 , x is 0.79, y is 0.14, $z=0$, p is 0.07 and r is 0.5%.

20
8. The compound of claim 7 wherein $m=0.5$ and $n=0.495$.
9. The compound of claim 2 wherein M is Co_2O_3 , x is 0.80, y is 0.102, z is 0.03, p is 0.068 and r is 1.5%.

25
10. The compound of claim 9 wherein $m=0.5$ and $n=0.495$.
11. A piezoelectric compound having the formula $xNa_{0.5}Bi_{0.5}TiO_3-yLi_{0.5}Bi_{0.5}TiO_3-zBaTiO_3$ where $(0.3 \leq x \leq 0.95)$, $(0 < y \leq 0.7)$, $(0 < z \leq$

30

0.2) and $(x+y+z=1)$.

12. A method of manufacture of a piezoelectric compound of the formula $x\text{Na}_{0.5}\text{Bi}_{0.5}\text{TiO}_3-y\text{K}_{0.5}\text{Bi}_{0.5}\text{TiO}_3-z\text{BaTiO}_3$ where $(0 < x \leq 1), (0 < y \leq 1), (0 < z \leq 1)$ and $(x+y+z=1)$ comprising, forming a mixture of K_2CO_3 , Na_2CO_3 , Li_2CO_3 , BaCO_3 , Bi_2O_3 or TiO_2 starting materials in amounts suitable for yielding a compound within $x\text{Na}_{0.5}\text{Bi}_{0.5}\text{TiO}_3-y\text{K}_{0.5}\text{Bi}_{0.5}\text{TiO}_3-z\text{BaTiO}_3$, calcining the mixture at about 800C to about 950C for about 0.5 hrs to about 2 hrs to yield a calcined mixture, milling the calcined mixture to a particle size of about 0.5 microns to about 2 microns to produce a calcined mixture, compressing the calcined mixture at about 3000PSI to about 10000PSI to yield a preform, heating the preform to about 500°C to about 600 °C to yield a green preform sintering the green preform at about 1060°C to about 1220°C for about 0.5 hrs to about 2 hrs to yield a piezoelectric compound of the formula $x\text{Na}_{0.5}\text{Bi}_{0.5}\text{TiO}_3-y\text{K}_{0.5}\text{Bi}_{0.5}\text{TiO}_3-z\text{BaTiO}_3$ where $(0 < x \leq 1), (0 < y \leq 1), (0 < z \leq 1)$ and $(x+y+z=1)$.
13. A method of manufacture of a piezoelectric compound of the formula $(x\text{Na}_{0.5}\text{Bi}_{0.5}\text{TiO}_3-y\text{K}_{0.5}\text{Bi}_{0.5}\text{TiO}_3-z\text{BaTiO}_3)-r\text{M}$ where $(0 < x \leq 1), (0 < y \leq 1), (0 < z \leq 1), (x+y+z=1), (0 < r \leq 5 \text{ wt}\%)$ and M is a dopant comprising, forming a mixture of K_2CO_3 , Na_2CO_3 , Li_2CO_3 , BaCO_3 , Bi_2O_3 or TiO_2 starting materials in amounts suitable for yielding a compound within the formula $x\text{Na}_{0.5}\text{Bi}_{0.5}\text{TiO}_3-y\text{K}_{0.5}\text{Bi}_{0.5}\text{TiO}_3-z\text{BaTiO}_3$ where $(0 < x \leq 1), (0 < y \leq 1), (0 < z \leq 1), (x+y+z=1)$, calcining the mixture at about 800C to about 950C for about 0.5 hrs to about 2 hrs to yield a calcined mixture, blending a dopant M selected from the group consisting of Al_2O_3 , CoO , Co_2O_3 , Re_2O_3 where Re is rare earth element,

NiCO₃, MnO₂, MnCO₃, Fe₂O₃, fluoride and mixtures thereof with the calcined mixture to produce a doped mixture,

milling the doped mixture to a particle size of about 0.5 microns to about 2 microns to produce a calcined mixture,

compressing the calcined mixture at about 3000PSI to about 10000PSI to yield a preform, heating the preform to about

500°C to about 600 °C to yield a green preform, sintering the green preform at about 1060°C to about 1220°C for about 0.5

hrs to about 2 hrs to yield a piezoelectric compound of the

formula (xNa_{0.5}Bi_{0.5}TiO₃-yK_{0.5}Bi_{0.5}TiO₃-zBaTiO₃)-rM where (0<x ≤1),(0<y≤1),(0<z ≤1), (x+y+z=1), (0<r ≤ 5 wt%).

14. An ultrasonic transducer comprising the piezoelectric of claim 2.

15. The transducer of claim 14 wherein the transducer is a high intensity focused ultrasound (HIFU) transducer.

16. An ultrasonic motor comprising a piezoelectric compound of claim 2.

17. A piezoelectric transformer comprising a piezoelectric compound of claim 2.

1/12





FIG. 1

2/12



(a) Piezoelectric coefficient (d_{33}), mechanical quality factor Q_m , and (b) dielectric constant (K), dielectric loss ($\tan\delta$) and (c) electromechanical coupling factors (k_{ij}) as a function of the amount Mn.

FIG. 2

3/12




FIG. 3

4/12




FIG. 4

5/12




FIG. 5a

6/12




FIG. 5b




FIG. 5c

7/12




FIG. 5d

8/12




FIG. 6

9/12




FIG. 7

10/12




FIG. 8a




FIG. 8b

11/12




FIG. 8c




FIG. 9

12/12




FIG. 10