



HU000035653T2

(19) **HU**(11) Lajstromszám: **E 035 653**(13) **T2****MAGYARORSZÁG****Szellemi Tulajdon Nemzeti Hivatala**

EURÓPAI SZABADALOM SZÖVEGÉNEK FORDÍTÁSA

(21) Magyar ügyszám: **E 14 747646**(22) A bejelentés napja: **2014. 08. 05.**(51) Int. Cl.: **C09D 11/101** (2006.01)**C09D 11/30** (2006.01)**C07D263/22** (2006.01)

(96) Az európai bejelentés bejelentési száma:

EP 20140747646

(97) Az európai bejelentés közzétételi adatai:

EP 3033399 A1 **2015. 02. 19.**

(86) A nemzetközi (PCT) bejelentési szám:

PCT/EP 14/066767

(97) Az európai szabadalom megadásának meghirdetési adatai:

EP 3033399 B1 **2017. 10. 11.**

(87) A nemzetközi közzétételi szám:

WO 15022228

(30) Elsőbbségi adatok:

13180035**2013. 08. 12.****EP**

(73) Jogosult(ak):

BASF SE, 67056 Ludwigshafen am Rhein (DE)

(72) Feltaláló(k):

GUENTHER, Erhard, 67454 Haßloch (DE)**ABDALLAH, Radwan, 67063 Ludwigshafen (DE)****DANDOLA, Giovanni, 69120 Heidelberg (DE)****KUNSMANN-KEITEL, Dagmar Pascale, 67117****Limburgerhof (DE)****LOISEL, Edouard, 69181 Leimen (DE)**

(74) Képviselő:

SBGK Szabadalmi Ügyvivői Iroda, Budapest

(54)

N-vinil-oxazolidinont tartalmazó tinta tintasugaras nyomtatáshoz

Az európai szabadalom ellen, megadásának az Európai Szabadalmi Közlönyben való meghirdetésétől számított kilenc hónapon belül, felszólalást lehet benyújtani az Európai Szabadalmi Hivatalnál. (Európai Szabadalmi Egyezmény 99. cikk(1))

A fordítást a szabadalmas az 1995. évi XXXIII. törvény 84/H. §-a szerint nyújtotta be. A fordítás tartalmi helyességét a Szellemi Tulajdon Nemzeti Hivatala nem vizsgálta.

(19)



(11)

EP 3 033 399 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
11.10.2017 Bulletin 2017/41

(51) Int Cl.:
C09D 11/101 (2014.01) **C09D 11/30** (2014.01)
C07D 263/22 (2006.01)

(21) Application number: **14747646.9**

(86) International application number:
PCT/EP2014/066767

(22) Date of filing: **05.08.2014**

(87) International publication number:
WO 2015/022228 (19.02.2015 Gazette 2015/07)

(54) **INK-JET PRINTING INK COMPRISING N-VINYLOXAZOLIDINONE**

TINTENSTRAHLDRUCKTINTE MIT N-VINYLOXAZOLIDINON

ENCRE D'IMPRESSION PAR JET D'ENCRE CONTENANT DE LA N-VINYLOXAZOLIDINONE

(84) Designated Contracting States:
**AL AT BE BG CH CY CZ DE DK EE ES FI FR GB
GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO
PL PT RO RS SE SI SK SM TR**

(30) Priority: **12.08.2013 EP 13180035**

(43) Date of publication of application:
22.06.2016 Bulletin 2016/25

(73) Proprietor: **BASF SE**
67056 Ludwigshafen am Rhein (DE)

(72) Inventors:
• **GUENTHER, Erhard**
67454 Haßloch (DE)

- **ABDALLAH, Radwan**
67063 Ludwigshafen (DE)
- **DANDOLA, Giovanni**
69120 Heidelberg (DE)
- **KUNSMANN-KEITEL, Dagmar Pascale**
67117 Limburgerhof (DE)
- **LOISEL, Edouard**
69181 Leimen (DE)

(74) Representative: **BASF IP Association**
BASF SE
G-FLP-C006
67056 Ludwigshafen (DE)


(56) References cited:
WO-A1-2010/103281 JP-A- S57 109 813
US-A- 4 774 309

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 3 033 399 B1

Description

[0001] The invention relates to the use of a radiation curable composition as printing ink for ink-jet printing, wherein the radiation curable composition comprises N-vinyloxazolidinone of formula I



in which R_1 to R_4 independently from each other are a hydrogen atom or an organic radical having not more than 10 carbon atoms.

[0002] Often radiation curable compositions are used as printing inks. With radiation curable compositions no solvents which have to be removed during or after the printing process are required. Even without solvent, the printing ink should be fluid at room temperature. For this purpose, printing inks frequently comprise so-called reactive diluents; these are low molecular weight compounds which become part of the resulting coating after curing. The choice of reactive diluents also affects the performance characteristics of the imprinted substrates obtained.

[0003] EP-A-555 069 discloses that the performance characteristics of radiation curable compositions can be improved by adding solid monomers, in particular N-vinylcaprolactam. However, the handling of such solid monomers is disadvantageous. According to WO 2010/057839 N-vinylcaprolactam may be replaced by a mixture of N-vinylcaprolactam with an N-vinylamide.

[0004] US 4 639 472 discloses radiation curable compositions comprising N-vinyloxazolidinone. Printing inks are mentioned as one possible application of such radiation curable compositions.


[0005] A printing process of particular importance is ink-jet printing. In an ink-jet printing process droplets of the printing ink are electrically charged to a specific degree. The droplets bearing such specific electrical charge are subjected to an electrostatic field which deflects the droplets on their way to the substrate to be printed. Droplets bearing a higher charge are more deflected by the electrostatic field, thus obtaining the desired print. It is known to use radiation curable compositions as printing ink for ink-jet printing.

[0006] In the case of ink-jet printing inks, in particular of UV-curable ink-jet printing inks, it is important that the adhesion of the printing ink to the substrate to be printed is very good. Particularly critical is the adhesion to nonpolar, plastic substrates like polypropylene. Furthermore in ink-jet printing processes a low viscosity of the printing ink is important, which allows the quick and easy formation of droplets. UV-curable inks for ink-jet printing usually are free of solvents, hence the radiation curable compounds themselves should have a sufficient low viscosity. In addition, a high reactivity in radiation curing is required, so that the printing and curing process runs quick and easily.

[0007] Object of the present invention were printing inks, in particular radiation curable printing inks, for ink-jet printing. The printing inks should have a high reactivity in radiation curing, a low viscosity and should allow an ink-jet printing process with good characteristics regarding the performance of the process and the printed substrate obtained. In particular the printing ink should have a good adhesion to nonpolar substrates, for example to polypropylene.

[0008] Accordingly, an ink-jet printing process wherein the above radiation curable composition is used as printing ink has been found.

[0009] The radiation curable composition which is used as printing ink in ink-jet printing comprises an N-vinyloxazolidinone of formula I



in which R_1 to R_4 independently from each other are a hydrogen atom or an organic radical having not more than 10 carbon atoms.

[0010] Preferably at least two of R_1 to R_4 in formula I are a hydrogen atom.

[0011] In a particular preferred embodiment at least two of R_1 to R_4 in formula I are a hydrogen atom and any remaining R_1 to R_4 are an organic radical having not more than 10 carbon atoms.

[0012] Preferably the organic radical has not more than 4 carbon atoms.

[0013] In a particular preferred embodiment the organic radical is an alkyl or alkoxy radical.

[0014] In a preferred embodiment the organic radical is a C1 to C4 alkyl radical or a C1 to C4 alkoxy radical.

[0015] In a most preferred embodiment the organic radical is a methyl radical.

[0016] As examples of N-vinyloxazolidinone of formula I compounds may be mentioned, wherein all of R_1 to R_4 are a hydrogen atom (for short NVO) or

R_1 is a C1 to C4 alkyl radical, in particular a methyl radical, and all of R_2 to R_4 are a hydrogen atom (N-vinyl-5-methyl oxazolidinone, for short NVMO) or

R_1 and R_2 are a hydrogen atom and R_3 and R_4 are a C1 to C4 alkyl radical, in particular a methyl radical.

[0017] Particularly preferred are NVO and NVMO, most preferred is NVMO.

[0018] It is understood that any reference to the N-vinyloxazolidinone in this patent specification includes also a mixture of different N-vinyloxazolidinones of formula I.

[0019] The synthesis of N-vinyloxazolidinone compounds of formula I is known. N-vinyloxazolidinone may be produced according to the process described in US 4 831 153 by pyrolyzing N-(1-hydroxyalkyl)-2-oxazolidinone. Preferably it is synthesized according to the well-known Reppe process by reacting acetylene with oxazolidinone.

[0020] After synthesis the N-vinyloxazolidinone may be stabilized in order to prevent premature polymerization.

[0021] Suitable stabilizers are all customary stabilizers which prevent premature polymerization in the case of N-vinyloxazolidinone of the formula I. Mixtures of stabilizers are also particularly suitable. Nitroxyl compounds, such as 1-oxyl-2,2,6,6-tetramethylpiperidine, 4-hydroxy-1-oxyl-2,2,6,6-tetramethylpiperidine, phenol derivatives having at least one substituent in the alpha-position to the phenol group, such as 2,6-di-tert-butyl-4-methylphenol, tocopherols, quinones and hydroquinones, such as hydroquinone monomethyl ether, N-oxyl compounds, aromatic amines and phenylenediamines, imines, sulfonamides, oximes, hydroxylamines, urea derivatives, phosphorus-containing compounds, sulfur-containing compounds, complexing agents based on tetraazaannulene (TAA) and/or metal salts, and, if appropriate, mixtures thereof, may be mentioned as stabilizers. Phosphorus-containing compounds are, for example, triphenylphosphine, triphenylphosphite, hypophosphorous acid, trinonyl phosphite, triethyl phosphite or diphenylisopropylphosphine.)

[0022] The radiation curable composition preferably comprises at least 0.5 % by weight, particularly preferably at least 2.5 % by weight, more preferably at least 5 % by weight and in a particularly preferred embodiment at least 10 % by weight of the N-vinyloxazolidinone.

[0023] The radiation curable composition preferably comprises up to 80 % by weight, particularly preferably up to 60 % by weight, more preferably up to 50 % by weight and in a particularly preferred embodiment up to 40 % by weight, respectively up to 30 % by weight of the N-vinyloxazolidinone.

[0024] Hence the radiation curable composition which is used as ink-jet printing ink may comprise for example from 0.5 to 50 % by weight, particularly from 2.5 to 40 % by weight and particularly preferred from 5 to 30 % by weight of the N-vinyloxazolidinone.

[0025] All above percentages by weight are based on the total radiation curable composition which is used as ink-jet printing ink.

[0026] The radiation curable composition may comprise further constituents, for example further radiation curable compounds or additives, such as stabilizers, photoinitiators etc.

[0027] Further radiation curable compounds may be compounds with polymerizable, ethylenically unsaturated groups as, for example, vinyl groups, as vinyl ether, vinyl ester or N-vinyl groups, allyl groups or (meth)acryloyl groups.

[0028] The expression "(meth)acryloyl group" stands for a acryloyl group or a methacryloyl group, preferably an acryloyl group.

[0029] Compounds with at least one (meth)acryloyl group are hereinafter referred to as (meth)acryloyl compounds for short.

[0030] Such further radiation curable compounds may be monomers or oligomers.

5 Monomers

[0031] Monomers herein are defined to be compounds having one polymerizable, ethylenically unsaturated group. Monomers preferably have a molecular weight of less than 300, in particular less than 200, g/mol. They serve in particular as reactive diluents. Possible monomers are, for example selected from C1-C20-alkyl (meth)acrylates, vinyl esters of

carboxylic acids comprising up to 20 carbon atoms, vinylaromatics having up to 20 carbon atoms, ethylenically unsaturated nitriles, vinyl ethers of alcohols comprising 1 to 10 carbon atoms.

[0032] Vinyl esters of carboxylic acids having 1 to 20 carbon atoms are, for example, vinyl laureate, vinyl stearate, vinyl propionate, vinyl versatate and vinyl acetate.

[0033] Suitable vinylaromatic compounds are vinyltoluene, α - and p-methylstyrene, α -butylstyrene, 4-n-butylstyrene, 4-n-decylstyrene and preferably styrene.

[0034] Examples of nitriles are acrylonitrile and methacrylonitrile.

[0035] Vinyl methyl ether or vinyl isobutyl ether may be mentioned as vinyl ethers. Vinyl ethers of alcohols comprising 1 to 4 carbon atoms are preferred.

[0036] Suitable (meth)acrylates are in particular C1- to C10-alkyl acrylates and methacrylates, especially C1- to C8-alkyl acrylates and methacrylates.

[0037] Methyl acrylate, ethyl acrylate, n-butyl acrylate, n-hexyl acrylate, octyl acrylate and 2-ethylhexyl acrylate and mixtures of these monomers are very particularly preferred.

[0038] In addition polar monomers being substituted by an isocyanate, amino, amido, epoxy, hydroxyl or acid groups are also suitable.

[0039] For example, monomers having carboxyl, sulfo or phosphonic acid groups (e.g. vinylphosphonic acid) may be mentioned. Carboxyl groups are preferred. For example, acrylic acid, methacrylic acid, itaconic acid, maleic acid or fumaric acid or acryloyloxypropionic acid may be mentioned.

[0040] Further monomers are, for example, also monomers comprising hydroxyl groups, in particular C1-C10-hydroxy-alkyl (meth)acrylates, (meth)acrylamide and monomers comprising ureido groups, such as ureido (meth)acrylates.

[0041] Mono(meth)acrylates of dihydric or polyhydric alcohols, e.g. monoacrylates or monomethacrylates of ethylene glycol or propylene glycol, may also be mentioned as further monomers.

[0042] Reaction products of (meth)acrylic acid and monoepoxides, e.g. phenyl glycidyl ether or glycidyl versatate, are also suitable.

[0043] Phenoxyethylglycol mono(meth)acrylate, glycidyl acrylate, glycidyl methacrylate, amino (meth)acrylates, such as 2-aminoethyl (meth)acrylate, or N-vinylpyrrolidone or N-vinyl-N-methylacetamide may also be mentioned as further monomers.

In a preferred embodiment monomers are compounds with a (meth)acryloyl group.

Oligomers

[0044] Oligomers herein are defined to be compounds having two to ten polymerizable, ethylenically unsaturated groups. Compounds having on average from 1.5 to 6, in particular from 2 to 5 polymerizable groups are preferred.

[0045] The weight average molecular weight Mw of the oligomers is preferably at least 300, more preferably at least 500g/mol; preferably Mw is less than 5000, particularly preferably less than 3000, g/mol (determined by gel permeation chromatography using polystyrene as a standard and tetrahydrofuran as an eluent).

[0046] The oligomers are in particular (meth)acryloyl compounds.

[0047] The oligomers are in particular (meth)acrylates of polyfunctional alcohols or of alkoxyated polyfunctional alcohols.

Examples of such alcohols are bifunctional alcohols, such as ethylene glycol, diethylene glycol, triethylene glycol, propylene glycol, dipropylene glycol, tripropylene glycol, butanediol, pentanediol, hexanediol, neopentyl glycol, alkoxyated phenolic compounds, such as ethoxyated or propoxyated bisphenols, cyclohexanedimethanol, trifunctional and higher-functional alcohols, such as glycerol, trimethylolpropane, butanetriol, trimethylolmethane, pentaerythritol, ditrimethylolpropane, dipentaerythritol, sorbitol, mannitol and the corresponding alkoxyated, in particular ethoxyated and propoxyated, alcohols.

[0048] The alkoxyated alcohols are obtainable in a known manner by reacting the above alcohols with alkylene oxides, in particular ethylene oxide or propylene oxide. The degree of alkoxylation to the hydroxyl group is preferably from 0 to 10, i.e. 1 mol of hydroxyl group can preferably be alkoxyated with up to 10 mol of alkylene oxides.

[0049] (Meth)acrylates of polyesterols may also be mentioned as oligomers.

[0050] Suitable polyesterols are, for example, those which can be prepared by esterification of polycarboxylic acids, preferably dicarboxylic acids, with polyols, preferably diols. The starting materials for such polyesters containing hydroxyl groups are known to the person skilled in the art. Preferably used dicarboxylic acids are succinic acid, glutaric acid, adipic acid, sebacic acid, o-phthalic acid, the isomers and hydrogenation products thereof and esterifiable derivatives, such as anhydrides or dialkyl esters of said acids. Maleic acid, fumaric acid, tetrahydrophthalic acid or the anhydrides thereof are also suitable. Suitable polyols are the above mentioned alcohols, preferably ethylene glycol, 1,2- and 1,3-propylene glycol, butane-1,4-diol, hexane-1,6-diol, neopentyl glycol, cyclohexanedimethanol and polyglycols of the ethylene glycol and propylene glycol type.

[0051] (Meth)acrylates of polyesterols can be prepared in a plurality of stages or in one stage, as described, for example, in EP 279 303, from acrylic acid, polycarboxylic acid and polyol.

[0052] Epoxide (meth)acrylates or urethane (meth)acrylates may also be suitable oligomers.

[0053] Epoxide (meth)acrylates are, for example, those which are obtainable by reacting epoxidized olefins or poly- or mono- or diglycidyl ethers, such as bisphenol A diglycidyl ether, with (meth)acrylic acid.

[0054] The reaction is known to the person skilled in the art and is described, for example, in R. Holmann, U.V. and E.B. Curing Formulation for Printing Inks and Paints, London 1984.

[0055] Urethane (meth)acrylates are in particular reaction products of hydroxyalkyl (meth)acrylates with poly- or diisocyanates (cf. also R. Holmann, U.V. and E.B. Curing Formulation for Printing Inks and Paints, London 1984).

[0056] The above compounds may comprise further functional groups, for example hydroxyl groups which are not esterified with (meth)acrylic acid.

[0057] Further oligomers are, for example, low molecular weight unsaturated polyesters which in particular have double bonds as a result of a content of maleic acid or fumaric acid and are copolymerizable.

[0058] Preferred oligomers are fluid at 20°C, 1 bar.

[0059] In a preferred embodiment, oligomers are (meth)acryloyl compounds, in particular (meth)acrylates of polyfunctional alcohols, in particular (meth)acryloyl compounds which, apart from hydroxyl groups or ether groups have no further functional groups.

[0060] Most preferred oligomers are (meth)acryloyl compounds which are fluid at 20°C, 1 bar, and have from 2 to 4 (meth)acryloyl groups.

Polymers

[0061] In addition to the above monomers and/or oligomers the radiation curable composition may comprise polymers which already have a high molecular weight. Such polymers may have a molecular weight Mw of more than 3000, in particular more than 5000

(determined by gel permeation chromatography using polystyrene as a standard and tetrahydrofuran as an eluent).

[0062] Suitable polymers may have reactive groups, for example polymerizable, ethylenically unsaturated groups or other functional groups which react with corresponding groups of any monomer or oligomer, so that bonding to the above monomers or oligomers takes place during the curing. Also suitable, however, are polymers without such groups, which subsequently form an independent continuous phase or an interpenetrating network in the coating obtained.

[0063] Suitable polymers are, for example, polyesters, polyadducts, in particular polyurethanes, or polymers obtainable by free radical polymerization. Polymers obtainable by free radical polymerization are particularly suitable, preferably those which comprise at least 40% by weight, particularly preferably at least 60% by weight, very particularly preferably at least 80% by weight, of so-called main monomers, selected from C1-C20-alkyl (meth)acrylates, vinyl esters of carboxylic acids comprising up to 20 carbon atoms, vinyl ethers of monoalcohols comprising up to 20 C atoms vinylaromatics having up to 20 carbon atoms and/or ethylenically unsaturated nitriles.

[0064] In a preferred embodiment the radiation curable composition which is used as ink-jet printing ink comprises (meth)acryloyl compounds.

[0065] In particularly preferred embodiment the radiation curable composition which is used as ink-jet printing ink comprises monomers with (meth)acryloyl groups (for short (meth)acryloyl monomers and/or oligomers with (meth)acryloyl compounds (for short (meth)acryloyl oligomers).

[0066] In a specifically preferred embodiment the radiation curable composition which is used as ink-jet printing ink comprises (meth)acryloyl oligomers, preferably (meth)acryloyl oligomers with two to five (meth)acryloyl groups.

[0067] In a preferred embodiment at least 70 % by weight of all radiation curable compounds of the radiation curable composition are (meth)acryloyl compounds and the N-vinylloxazolidinone.

[0068] Besides the radiation curable compounds, the radiation curable composition may comprise additives, for example pigments, including effect pigments, dyes, fillers, stabilizers, e.g. UV absorbers, antioxidants or biocides, leveling agents, antifoams, wetting agents, antistatic agents, etc.

[0069] The radiation curable composition may comprise water or organic solvents. Preferably it comprises little or no water or organic solvent (unreactive compound fluid at 20°C, 1 bar).

[0070] In a preferred embodiment, the radiation curable composition comprises less than 20% by weight of water or organic solvents, particularly preferably less than 10 parts by weight and in particular less than 5 parts by weight of water or organic solvents, based on 100 parts by weight of printing ink. Very particularly preferably, the radiation curable composition comprises substantially no or less than 1 by weight of % water or organic solvents.

[0071] Preferably, the radiation curable composition comprises at least one photoinitiator.

[0072] The photoinitiator may be, for example, so-called α -cleavers, i.e. photoinitiators in which a chemical bond is cleaved so that 2 free radicals form, which initiate the further crosslinking or polymerization reactions.

[0073] For example, acylphosphine oxides (Lucirin® brands from BASF), hydroxyalkylphenones (e.g. Irgacure® 184), benzoin derivatives, benzil derivatives, dialkylxyacetophenones may be mentioned.

[0074] In particular, they may also be so-called H-abstractors which remove a hydrogen atom from the polymer chain; for example, these are photoinitiators having a carbonyl group. This carbonyl group shifts into a C-H bond with formation of a C-C-O-H group.

[0075] In particular, acetophenone, benzophenone and derivatives thereof may be mentioned here.

[0076] Benzoin derivatives or benzoin ethers may also be mentioned.

[0077] Photoinitiators can be used alone or as a mixture, mixtures of photoinitiators having different modes of action may also be particularly suitable.

[0078] Photoinitiators can also be bound to an above polymer or oligomer, if present.

[0079] In the case of thermal curing or a combination of radiation curing and thermal curing, one or more thermally activatable initiators, such as peroxides, azo compounds, etc., may be added.

[0080] The radiation curable composition generally comprises at least one dye or one pigment.

[0081] The radiation curable composition can be prepared in any desired manner by adding the individual constituents in any sequence and mixing.

[0082] The radiation curable composition is used as printing ink in ink-jet printing.

[0083] The radiation curable composition is printed on substrates and preferably subsequently cured by radiation.

[0084] Different substrates may be printed, for example paper, metal films or polymer films, like polyethylene terephthalate, polyamide, polystyrene, polyvinylchloride, polycarbonate, polyolefines like polyethylene or polypropylene or aluminium. In particular polyolefine substrates like polyethylene substrates or polypropylene substrates may be printed, even if they are not corona pretreated..

[0085] A preferred embodiment of this invention is an ink-jet printing process, wherein a polypropylene substrate or a polyethylene substrate are printed. A most preferred substrate is polyethylene.

[0086] The radiation curable composition has good performance characteristics in ink-jet printing; it has a high reactivity in radiation curing, a low viscosity and results in a print with very good adhesion, especially good adhesion to polymer films, in particular to polypropylene. In particular it is an advantage of the radiation curable composition that less reactive diluent is required. Compared to other reactive diluents less N-vinyl oxazolidinone is required to obtain a radiation curable composition of a sufficient low viscosity and very good suitability as printing ink for ink jet.

Examples

Example 1

[0087] As N-vinyl oxazolidinone a compound of formula I with R_1 to R_4 being a hydrogen atom was used (for short NVO) and a compound with R_1 being a methyl radical and all of R_2 to R_4 being hydrogen (N-vinyl-5-methyl oxazolidinone, for short NVMO) was used.

[0088] NVO was used as reactive diluent in ink-jet printing inks.

[0089] For comparison identical ink-jet printing inks have been prepared using N-vinyl caprolactam (NVC) and 4-acryloyl morpholine (ACMO) which are well known reactive diluents.

[0090] For this purpose, a printing ink was prepared by mixing oligomers containing acrylate groups (Laromer® products of BASF), dispersants and pigment (pigment paste) and then adding the above monomers and as further monomer isobornyl acrylate.

[0091] The printing inks were applied to the substrate by means of a bar applicator and exposed to an energy of 120 W/m on a UV exposure unit equipped with a high pressure UV mercury lamp. The coated substrate was lying on belt which is passed under the UV lamp. With low speeds of the belt the exposure to radiation is long. The speed of the belt was increased in steps of 5 m/min and checked whether the coating was cured by mechanical testing (scratching). The highest belt speed possible is a measure of reactivity.

Adhesion

[0092] For the investigation of the adhesion of the obtained coatings, a "Crystal" Scotch adhesive tape was used. The

adhesive tape was stuck to the exposed coating and peeled off again and it was determined whether the coating had become detached therewith. The belt speed for the preparation of the layers was 15 m/min, respectively 3 times 15 m/min (3 x 15). The layer thickness was 6, respectively 12 μm .

5 Rating 0 (no delamination) - 5 (complete delamination)


[0093] The composition of the printing inks and results of the adhesion test are to be found in Table 1.

Table 1: Inkjet printing ink

10	Example	Example 1	Example 2	Comparison Example 1	Comparison Example 2
	Monomer	NVO	NVMO	ACMO	NVC
15	Parts by weight of the above monomer	30	30	30	30
	Isobornyl acrylate [parts by weight]	32	32	32	32
	Laromer® PO 77 F	8	8	8	8
	Laromer® DPGDA	10.4	10.4	10.4	10.4
20	Mill Base UV Cyan (pigment) [parts by weight]	10	10	10	10
	Lucirin® TPO XL [parts by weight] (photoinitiator)	3.5	3.5	3.5	3.5
	Darocur® 1173 [parts by weight] (photoinitiator)	4	4	4	4
25	Further additives (parts by weight)	2.1	2.1	2.1	2.1
	Total [parts by weight]	100	100	100	100
	Viscosity I.C.I at 23°C, 1/20 s [mPas]	Lower 10	Lower 10	13	15
30	Belt speed [m/min] at which sample can still be cured (layer 6 μm) (measure of the reactivity)	40	40	35	30
	Adhesion (layer 6 μm , belt speed 15 m/min)				
	Polyethylene terephthalate film (PET X13 Melinax)	0	1	5	0
35	Polyethylene film	0	1	2	1
	Polypropylene film	1	1	3	1
	Adhesion (layer 12 μm , belt speed 3 x 15 m/min)				
	Polyethylene terephthalate film	5	0	5	5
40	Polyethylene film	0	0	5	5
	Polypropylene film	5	5	5	5
	Example	Example 1	Example 2	Comparison Example 1	Comparison Example 2
45	Adhesion (layer 24 μm , belt speed 3 x 15 m/min for comparison examples, 2 x 15 m/min for examples)				
	Polyethylene terephthalate film	5	5	5	5
	Polyethylene film	0	0	5	5
50	Polypropylene film	0	0	5	5

Claims

- 55 1. Use of a radiation curable composition as printing ink for ink-jet printing, wherein the radiation curable composition comprises N-vinylloxazolidinone of formula I




in which R_1 to R_4 independently from each other are a hydrogen atom or an organic radical having not more than 10 carbon atoms.

2. Use of a radiation curable composition according to claim 1, wherein at least two of R_1 to R_4 in formula I are a hydrogen atom and any remaining R_1 to R_4 are an organic radical having not more than 10 carbon atoms.
3. Use of a radiation curable composition according to claim 1 or 2, wherein the N-vinylloxazolidinone of formula I is a compound with all of R_1 to R_4 being a hydrogen atom or a compound with R_1 being a C1 to C4 alkyl group and all of R_2 to R_4 being a hydrogen atom or a compound with R_1 and R_2 being a hydrogen atom and R_3 and R_4 being a C1 to C4 alkyl group
4. Use of a radiation curable composition according to any of claims 1 to 3, wherein the radiation curable composition comprises the N-vinylloxazolidinone in an amount of from 0.5 to 80% by weight.
5. Use of a radiation curable composition according to any of claims 1 to 4, wherein the radiation curable composition additionally comprises compounds having at least one (meth)acryloyl group (hereinafter referred to as (meth)acryloyl compounds for short).
6. Use of a radiation curable composition according to any of claims 1 to 5, wherein the radiation curable composition comprises (meth)acryloyl compounds having two to five (meth)acryloyl groups.
7. Use of a radiation curable composition according to any of claims 1 to 6, wherein at least 70 % by weight of all radiation curable compounds of the radiation curable composition are (meth)acryloyl compounds and the N-vinylloxazolidinone.
8. Use of a radiation curable composition according to any of claims 1 to 7, wherein the radiation curable composition comprises less than 10 % by weight of water or organic solvents.
9. Use of a radiation curable composition according to any of claims 1 to 8, wherein the radiation curable composition comprises at least one photoinitiator.
10. Ink-jet printing process wherein the radiation curable composition of any of claims 1 to 9 is used as printing ink.
11. Ink-jet printing process according to claim 10, wherein the radiation curable composition is printed on substrates and subsequently cured by radiation.
12. Ink-jet printing process according to claim 10 or 11, wherein a polypropylene substrate is printed.

Patentansprüche

1. Verwendung einer strahlungshärtbaren Zusammensetzung als Drucktinte zum Tintenstrahldrucken, wobei die strahlungshärtbare Zusammensetzung N-Vinylloxazolidinon der Formel I umfasst,



wobei R_1 bis R_4 unabhängig voneinander ein Wasserstoffatom oder ein organischer Rest mit nicht mehr als 10 Kohlenstoffatomen sind.

2. Verwendung einer strahlungshärtbaren Zusammensetzung gemäß Anspruch 1, wobei wenigstens zwei von R_1 bis R_4 in Formel I ein Wasserstoffatom sind und alle verbleibenden R_1 bis R_4 sind ein organischer Rest mit nicht mehr als 10 Kohlenstoffatomen sind.

3. Verwendung einer strahlungshärtbaren Zusammensetzung gemäß Anspruch 1 oder 2, wobei das N-Vinyloxazolidinon der Formel I ist:

eine Verbindung, bei der alle R_1 bis R_4 ein Wasserstoffatom sind, oder
eine Verbindung, bei der R_1 eine C1- bis C4-Alkylgruppe ist und alle von R_2 bis R_4 ein Wasserstoffatom sind, oder
eine Verbindung, bei der R_1 und R_2 ein Wasserstoffatom sind und R_3 und R_4 eine C1- bis C4-Alkylgruppe sind.

4. Verwendung einer strahlungshärtbaren Zusammensetzung gemäß einem der Ansprüche 1 bis 3, wobei die strahlungshärtbare Zusammensetzung das N-Vinyloxazolidinon in einer Menge von 0,5 bis 80 Gew.-% umfasst.

5. Verwendung einer strahlungshärtbaren Zusammensetzung gemäß einem der Ansprüche 1 bis 4, wobei die strahlungshärtbare Zusammensetzung zusätzlich Verbindungen umfasst, die wenigstens eine (Meth)acryloylgruppe aufweisen (nachstehend abgekürzt als (Meth)acryloylverbindungen bezeichnet).

6. Verwendung einer strahlungshärtbaren Zusammensetzung gemäß einem der Ansprüche 1 bis 5, wobei die strahlungshärtbare Zusammensetzung (Meth)acryloylverbindungen mit zwei bis fünf (Meth)acryloylgruppen umfasst.

7. Verwendung einer strahlungshärtbaren Zusammensetzung gemäß einem der Ansprüche 1 bis 6, wobei wenigstens 70 Gew.-% aller strahlungshärtbaren Verbindungen der strahlungshärtbaren Zusammensetzung (Meth)acryloylverbindungen und das N-Vinyloxazolidinon sind.

8. Verwendung einer strahlungshärtbaren Zusammensetzung gemäß einem der Ansprüche 1 bis 7, wobei die strahlungshärtbare Zusammensetzung weniger als 10 Gew.-% an Wasser oder organischen Lösungsmitteln umfasst.

9. Verwendung einer strahlungshärtbaren Zusammensetzung gemäß einem der Ansprüche 1 bis 8, wobei die strahlungshärtbare Zusammensetzung wenigstens einen Photoinitiator umfasst.


10. Tintenstrahldruckverfahren, wobei die strahlungshärtbare Zusammensetzung gemäß einem der Ansprüche 1 bis 9 als Drucktinte verwendet wird.

11. Tintenstrahldruckverfahren gemäß Anspruch 10, wobei die strahlungshärtbare Zusammensetzung auf Substrate gedruckt und anschließend durch Strahlung gehärtet wird.

12. Tintenstrahldruckverfahren gemäß Anspruch 10 oder 11, wobei ein Polypropylensubstrat bedruckt wird.

Revendications

1. Utilisation d'une composition durcissable par irradiation comme encre d'impression pour l'impression au jet d'encre, dans laquelle la composition durcissable par irradiation comprend une N-vinyloxazolidinone ayant la formule I



dans laquelle les groupes R_1 à R_4 , indépendamment les uns des autres, sont un atome d'hydrogène ou un radical organique ne comportant pas plus de 10 atomes de carbone.

2. Utilisation d'une composition durcissable par irradiation selon la revendication 1, dans laquelle au moins deux des groupes R_1 à R_4 dans la formule I sont un atome d'hydrogène et tous les groupes R_1 à R_4 restants sont un radical organique ne comportant pas plus de 10 atomes de carbone.

3. Utilisation d'une composition durcissable par irradiation selon la revendication 1 ou 2, dans laquelle la N-vinyloxazolidinone selon la formule I est :

un composé dans lequel tous les groupes R_1 à R_4 sont un atome d'hydrogène, ou
un composé dans lequel R_1 est un groupe alkyle C1 à C4 et tous les groupes R_2 à R_4 sont un atome d'hydrogène, ou
un composé dans lequel les groupes R_1 et R_2 sont un atome d'hydrogène et les groupes R_3 et R_4 sont un groupe alkyle C1 à C4.

4. Utilisation d'une composition durcissable par irradiation selon l'une quelconque des revendications 1 à 3, dans laquelle la composition durcissable par irradiation comprend la N-vinyloxazolidinone dans une quantité de 0,5 à 80 % en poids.

5. Utilisation d'une composition durcissable par irradiation selon l'une quelconque des revendications 1 à 4, dans laquelle la composition durcissable par irradiation comprend en plus des composés comportant au moins un groupe (méth)acryloyle (désignés ci-après sous le nom de composés (méth)acryloyle pour abrégé).

6. Utilisation d'une composition durcissable par irradiation selon l'une quelconque des revendications 1 à 5, dans laquelle la composition durcissable par irradiation comprend des composés (méth)acryloyle comportant deux à cinq groupes (méth)acryloyle.

7. Utilisation d'une composition durcissable par irradiation selon l'une quelconque des revendications 1 à 6, dans laquelle au moins 70 % en poids de tous les composés durcissables par irradiation de la composition durcissable par irradiation sont des composés (méth)acryloyle et la N-vinyloxazolidinone.

8. Utilisation d'une composition durcissable par irradiation selon l'une quelconque des revendications 1 à 7, dans laquelle la composition durcissable par irradiation comprend moins de 10 % en poids d'eau ou de solvants organiques.

9. Utilisation d'une composition durcissable par irradiation selon l'une quelconque des revendications 1 à 8, dans laquelle la composition durcissable par irradiation comprend au moins un photoinitiateur.

10. Procédé d'impression au jet d'encre, dans lequel la composition durcissable par irradiation selon l'une quelconque des revendications 1 à 9 est utilisée comme encre d'impression.

11. Procédé d'impression au jet d'encre selon la revendication 10, dans lequel la composition durcissable par irradiation est imprimée sur des substrats, et ensuite durcie par irradiation.

12. Procédé d'impression au jet d'encre selon la revendication 10 ou 11, dans lequel un substrat en polypropylène est imprimé.

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- EP 555069 A [0003]
- WO 2010057839 A [0003]
- US 4639472 A [0004]
- US 4831153 A [0019]
- EP 279303 A [0051]


Non-patent literature cited in the description

- **R. HOLMANN.** *U.V. and E.B. Curing Formulation for Printing Inks and Paints*, 1984 [0054] [0055]

Szabadalmi igénypontok

1. Sugárzással kikeményíthető készítmény alkalmazása nyomtató tintaként tinta-sugaras nyomtatáshoz,

ahol a sugárzással kikeményíthető készítmény I képletű N-vinil-oxazolidinont tartalmaz,



amely képletben $R_1 - R_4$ jelentése egymástól függetlenül hidrogénatom vagy 10 szénatomnál nem több szénatomot tartalmazó szerves csoport.

2. Az 1. igénypont szerinti sugárzással kikeményíthető készítmény alkalmazása, ahol az I képletben $R_1 - R_4$ közül legalább kettőnek jelentése hidrogénatom és a többi $R_1 - R_4$ bármelyikének jelentése 10 szénatomnál nem több szénatomot tartalmazó szerves csoport.

3. Az 1. vagy 2. igénypont szerinti sugárzással kikeményíthető készítmény alkalmazása, ahol az I képletű N-vinil-oxazolidinon egy olyan vegyület, ahol $R_1 - R_4$ mindegyikének jelentése hidrogénatom vagy egy olyan vegyület, ahol R_1 jelentése C1 - C4 alkilcsoport és $R_2 - R_4$ mindegyikének jelentése hidrogénatom vagy egy olyan vegyület, ahol R_1 és R_2 jelentése hidrogénatom és R_3 és R_4 jelentése C1 - C4 alkilcsoport.

4. Az 1-3. igénypontok bármelyike szerinti sugárzással kikeményíthető készítmény alkalmazása, ahol a sugárzással kikeményíthető készítmény az N-vinil-oxazolidinont 0,5 - 80 tömeg% mennyiségben tartalmazza.

5. Az 1-4. igénypontok bármelyike szerinti sugárzással kikeményíthető készítmény alkalmazása, ahol a sugárzással kikeményíthető készítmény továbbá legalább egy (met)akrilóil-csoporttal rendelkező vegyületet (amelyre a továbbiakban rövidítetten (met)akrilóil-vegyületként hivatkozunk) tartalmaz.

6. Az 1-5. igénypontok bármelyike szerinti sugárzással kikeményíthető készítmény alkalmazása, ahol a sugárzással kikeményíthető készítmény kettőtől ötig terjedő számú (met)akrilóil-csoporttal rendelkező (met)akrilóil-vegyületet tartalmaz.

7. Az 1-6. igénypontok bármelyike szerinti sugárzással kikeményíthető készítmény alkalmazása, ahol a sugárzással kikeményíthető készítmény összes sugárzással kikeményíthető vegyületének legalább 70 tömeg%-a (met)akrilóil-vegyület és N-vinil-oxazolidinon.



8. Az 1-7. igénypontok bármelyike szerinti sugárzással kikeményíthető készítmény alkalmazása, ahol a sugárzással kikeményíthető készítmény kevesebb, mint 10 tömeg%-ban tartalmaz vizet vagy szerves oldószereket.

9. Az 1-8. igénypontok bármelyike szerinti sugárzással kikeményíthető készítmény alkalmazása, ahol a sugárzással kikeményíthető készítmény legalább egy fotoiniciátort tartalmaz.

10. Tintasugaras nyomtatási eljárás, ahol az 1-9. igénypontok bármelyike szerinti sugárzással kikeményíthető készítményt alkalmazzuk nyomtatási tintaként.

11. A 10. igénypont szerinti tintasugaras nyomtatási eljárás, ahol sugárzással kikeményíthető készítményt nyomtatjuk a szubsztrátra és ezt követően sugárzással kikeményítjük.

12. A 10. vagy 11. igénypont szerinti tintasugaras nyomtatási eljárás, ahol egy polipropilén szubsztrátra nyomtatunk.