



HU000032607T2

(19) **HU**(11) Lajstromszám: **E 032 607**(13) **T2****MAGYARORSZÁG**
Szellemi Tulajdon Nemzeti Hivatala**EURÓPAI SZABADALOM**
SZÖVEGÉNEK FORDÍTÁSA

(21) Magyar ügyszám: **E 12 712682** (51) Int. Cl.: **C08J 9/14** (2006.01)
(22) A bejelentés napja: **2012. 04. 11.** **B32B 27/40** (2006.01)
(96) Az európai bejelentés bejelentési száma: **EP 20120712682** **C08G 18/09** (2006.01)
EP 20120712682 **C08G 18/32** (2006.01)
(97) Az európai bejelentés közzétételi adatai: **C08G 18/40** (2006.01)
EP 2697296 A1 **2012. 10. 18.** **C08G 18/42** (2006.01)
(97) Az európai szabadalom megadásának meghirdetési adatai: **C08G 18/48** (2006.01)
EP 2697296 B1 **2017. 02. 22.** **C08G 18/50** (2006.01)
C08G 18/66 (2006.01)
C08G 18/76 (2006.01)

(86) A nemzetközi (PCT) bejelentési szám: **PCT/EP 12/056485**
(87) A nemzetközi közzétételi szám: **WO 12140025**

(30) Elsőbbségi adatok: 11162679 2011. 04. 15. EP	(73) Jogosult(ak): BASF SE, 67056 Ludwigshafen am Rhein (DE)
(72) Feltaláló(k): TOMOVIC, Zeljko, 49448 Lemförde (DE) JACOBMEIER, Olaf, 32312 Lübbecke (DE) KAMPF, Gunnar, 32351 Stemwede-haldem (DE)	(74) Képviselő: SBGK Szabadalmi Ügyvivői Iroda, Budapest

(54) **Eljárás kemény poliuretánhabok előállítására**

Az európai szabadalom ellen, megadásának az Európai Szabadalmi Közlönyben való meghirdetésétől számított kilenc hónapon belül, felszólalást lehet benyújtani az Európai Szabadalmi Hivatalnál. (Európai Szabadalmi Egyezmény 99. cikk(1))

A fordítást a szabadalmas az 1995. évi XXXIII. törvény 84/H. §-a szerint nyújtotta be. A fordítás tartalmi helyességét a Szellemi Tulajdon Nemzeti Hivatala nem vizsgálta.

Process for producing rigid polyurethane foams

5 Description

The invention relates to a process for producing rigid polyurethane foams and to rigid polyurethane foams produced by the process of the invention and also to a polyol component.

10

Rigid polyurethane foams have been known for a long time and have been described widely. Rigid polyurethane foams are used predominantly for thermal insulation, for example in refrigeration appliances, transport means or buildings and for producing structural elements, in particular sandwich elements.

15

An important field of use of rigid polyurethane foams is composite elements. The production of composite elements composed of, in particular, metallic covering layers and a core of foams based on isocyanates, usually polyurethane (PUR) or polyisocyanurate (PIR) foams, frequently also referred to as sandwich elements, on continuously operating double belt plants is at present practiced on a large scale. Apart from sandwich elements for coolstore insulation, elements having colored covering layers are becoming ever more important for construction of façades of a variety of buildings. Apart from coated steel sheets, stainless steel sheets, copper sheets or aluminum sheets are used as covering layers.

25

It is important that the rigid polyurethane foams fill the hollow spaces uniformly and without voids, so that very good bonding to the covering layers gives a stable construction which ensures good thermal insulation. To prevent foam defects, the foamable PU reaction mixture has to be introduced within a short time into the hollow space to be insulated. Low-pressure or preferably high-pressure machines are usually used for filling such articles with foam.

30

A summary overview of the production of rigid polyurethane foams and their use as covering layer or core layer in composite elements and also their use as insulating layer in refrigeration or heating engineering may be found, for example, in "Polyurethane", Kunststoff-Handbuch, volume 7, 3rd edition 1993, edited by Dr. Günter Oertel, Carl-Hanser-Verlag, Munich/Vienna.

35



SZTNH-100033931

Suitable rigid polyurethane foams can be produced in a known manner by reacting organic polyisocyanates with one or more compounds having at least two reactive hydrogen atoms in the presence of blowing agents, catalysts and optionally auxiliaries and/or additives.

As compounds having at least two hydrogen atoms which are reactive toward isocyanate groups, preference is given to using polyether alcohols and/or polyester alcohols for producing the polyurethanes. The choice of polyols is made, in particular, on the basis of costs and the desired use properties (e.g. EP-A 1 632 511, US-B 6,495,722, WO 2006/108833).

However, the surface properties of the known rigid polyurethane foams are still capable of improvement, especially in the production of composite elements since these properties have a substantial influence on the adhesion of the covering layers to the foam. In the production of foams by the spray foam process, too, a good surface is of great importance.

WO 2010/111021 A1 relates to a process for producing a rigid PU foam, wherein the polyol component used is a mixture of a sorbitol-based polypropylene oxide having an OH number of 480 mg KOH/g, a glycerol-based polypropylene oxide having an OH number of 156 mg KOH/g, and an ethylenediamine-based polypropylene oxide having an OH number of 640 mg KOH/g.

JP 6 100652 A relates to a polyol composition for a rigid PU foam comprising a polyether polyol B prepared by means of a TDA- and TEOA-started alkylene oxide, a polyether polyol D prepared by means of a Mannich base-started alkylene oxide and a polyether polyol E prepared by means of an EDA-started alkylene oxide.

EP 1510543 A2 describes a polyol component for the production of rigid PU foams comprising a polyetherol 1 based on sorbitol (OH number 490); polyetherol 2 based on EDA (OH number 750) und a polyetherol 3 based on ethylene glycol (OH number 200).

- WO 02/50161 A2 describes polyol mixtures for the production of rigid PU foams, comprising a polyetherol A started with EDA, a polyetherol B started with sucrose/propylene glycol/water, and an aromatic polyester polyol.
- 5 DE 100 09 649 A1 describes open-cell rigid PU foams produced from polyol mixtures which, as well as a polyetherol 1 based on EDA (OH number 470); a polyetherol 2 based on sucrose/glycerol (OH number 485) and a polyetherol 5 based on glycerol (OH number 400), comprise further polyetherols and a castor oil glycerol ester.
- 10 WO 2010/046361 A1 describes a process for producing closed-cell rigid PU foams, wherein polyol mixtures comprising polyetherols based on sorbitol, polyetherols based on glycerol, polyetherols based on cycloaliphatic diamines, aromatic polyester polyols and polyetherols based on TDA are used.
- 15 DE 198 17 507 A1 describes a process for producing rigid PU foams, in which a polyol mixture A is used, comprising, inter alia, as well as a polyether polyol based on sucrose and a polyether polyol based on EDA, an aromatic polyester polyol.
- 20 US 6,114,440 describes a formulation for a rigid PU foam. The polyol component used is a mixture of 25 parts by weight each of N,N,N',N'-tetrakis(2-hydroxypropyl)ethylenediamine, a sucrose-based polyether polyol and a glycerol-based polyether polyol (G-600).
- 25 EP 1 512 707 A2 describes open-cell rigid PU foams that are produced from polyol mixtures comprising, inter alia, polyetherols 1 based on EDA (OH number 470), polyetherols 2 based on sucrose/glycerol (OH number 485) and polyetherols 5 based on glycerol (OH number 400), and also further polyetherols and a castor oil glycerol ester.
- 30 DE 10 2004 044915 A1 describes rigid PU foams and polyol mixtures comprising, as well as a polyetherol 1, 2 or 3 started with sucrose or sorbitol (OH number 490 or 500) and a polyetherol 4 started with EDA (OH number 750), an aromatic polyester polyol

5 (OH number 385).

JP 200 281826 A describes rigid PU foams and polyol components that are suitable for production thereof, comprising polyetherols A and B based on EDA (OH number 750
5 or 470), and an aromatic polyester polyol F-I.

WO2005/044915 discloses rigid PU foams and polyol mixtures comprising, as well as polyether polyols based on sucrose (OH number 360), trifunctional polyether polyols (OH number 170) and EDA-started polyols (OH number 640), a TDA-based polyol B
10 and an aromatic polyester polyol.

EP 2 461 022 A1, which has an earlier priority date but is not a prior publication, relates to core foams made from reinforced PU foam, which are produced using polyol mixtures comprising polyether polyols based on EDA, further polyether polyols ($f =$
15 2.0, MW 400) and an aromatic polyester.

EP 2 368 585 A1, which has an earlier priority date but is not a prior publication, describes a process for producing rigid PU foams and polyol mixtures comprising polyetherols based on EDA (OH number 640), polyetherols based on sorbitol (OH
20 number 480) and polyetherols based on glycerol (OH number 156), and also aromatic polyester polyols and polyetherols based on TDA.

The documents EP 0 728 783 A1, EP 0 826 708 A1 and WO 2010/106067 A1 describe processes for producing rigid PU foams, in which the polyol component comprises
25 castor oil. Castor oil can be advantageous for the surface properties of the foam. On the other hand, castor oil can in the presence of water lead, due to phase separation, to instability of the polyol component, which can lead to problems in processing. Water is frequently used as inexpensive and environmentally friendly blowing agent in the polyol component. A disadvantage of the process described in EP 0 826 708 A1 is the
30 high viscosity of the polyol component and also the very poor adhesion of the rigid PU foams formed. The rigid PU foams produced by the process described in EP 0 728 783 A1 are also capable of improvement in respect of their surface properties and adhesion. The rigid PU foams produced as described in WO 2010/106067 A1 display good

adhesion and a good surface, but are still capable of improvement in respect of the storage stability of the polyol component in the case of relatively large amounts of water (> 1.5 parts by weight).

- 5 It is therefore an object of the invention to develop a process for producing rigid polyurethane foams which leads to foams having good adhesion, good curing and surface quality and whose polyol component has good storage stability and thus good processing properties.
- 10 The object has surprisingly been able to be achieved by a process for producing rigid polyurethane foams by reacting
- a) organic polyisocyanates with
 - b) compounds having at least two hydrogen atoms which are reactive toward
 - 15 isocyanate groups in the presence of
 - c) blowing agents,
 - d) catalysts and optionally
 - e) auxiliaries and additives,
- 20 wherein a mixture consisting of
- b1) from 20 to 60 parts by weight of one or more high-functionality polyether alcohols having functionalities of from 3.5 to 5.5 and a hydroxyl number of from
 - 25 400 to 550 mg KOH/g and having hydroxyl-containing high-functionality compounds as starter substances,
 - b2) from 5 to 15 parts by weight of one or more polyether alcohols based on aliphatic amines and having functionalities of 4 and a hydroxyl number of from 470 to 800 mg KOH/g,
 - b3) from 10 to 30 parts by weight of one or more polyether alcohols having
 - 30 functionalities of from 2 to 3 and a hydroxyl number of from 220 to 430 mg KOH/g, and
 - b4) optionally from 1 to 5 parts by weight of water
- is used as component b).
- 35 The total parts by weight of b1) to b4) in the polyol component b) by definition do not exceed 100 parts by weight. The polyol component b) can also comprise catalysts,

stabilizers and customary auxiliaries and additives.

The hydroxyl number is determined in accordance with DIN 53240.

5 The invention further provides the polyol component b) consisting of a mixture of

- b1) from 20 to 60 parts by weight of one or more high-functionality polyether
alcohols having functionalities of from 3.5 to 5.5 and a hydroxyl number of from
400 to 550 mg KOH/g and having hydroxyl-containing high-functionality
10 compounds as starter substances,
- b2) from 5 to 15 parts by weight of one or more polyether alcohols based on
aliphatic amines and having functionalities of 4 and a hydroxyl number of from
470 to 800 mg KOH/g,
- b3) from 10 to 30 parts by weight of one or more polyether alcohols having
15 functionalities of from 1.5 to 3 and a hydroxyl number of from 150 to 450 mg
KOH/g, and
- b4) optionally from 1 to 5 parts by weight of water.

As regards the individual components used in the process of the invention and for the
20 polyol component b) of the invention, the following may be said:

a) Possible organic polyisocyanates are the aliphatic, cycloaliphatic, araliphatic and preferably aromatic polyfunctional isocyanates known per se.

25 Specific examples are: alkylene diisocyanates having from 4 to 12 carbon atoms in the
alkylene radical, e.g. dodecane 1,12-diisocyanate, 2-ethyltetramethylene
1,4-diisocyanate, 2-methylpentamethylene 1,5-diisocyanate, tetramethylene
1,4-diisocyanate and preferably hexamethylene 1,6-diisocyanate; cycloaliphatic
diisocyanates, e.g. cyclohexane 1,3- and 1,4-diisocyanate and also any mixtures of
30 these isomers, 1-isocyanato-3,3,5-trimethyl-5-isocyanatomethylcyclohexane
(isophorone diisocyanate), hexahydrotolylene 2,4- and 2,6-diisocyanate and also the
corresponding isomer mixtures, dicyclohexylmethane 4,4'-, 2,2'- and 2,4'-diisocyanate
and also the corresponding isomer mixtures, and preferably aromatic diisocyanates and
polyisocyanates, e.g. tolylene 2,4- and 2,6-diisocyanate and the corresponding isomer
35 mixtures, diphenylmethane 4,4'-, 2,4'- and 2,2'-diisocyanate and the corresponding
isomer mixtures, mixtures of diphenylmethane 4,4'- and 2,4'- diisocyanates,
polyphenylpolymethylene polyisocyanates, mixtures of diphenylmethane 4,4'-, 2,4'-

and 2,2'-diisocyanates and polyphenylpolymethylene polyisocyanates (crude MDI) and mixtures of crude MDI and tolylene diisocyanates. The organic diisocyanates and polyisocyanates can be used individually or in the form of their mixtures.

- 5 Use is frequently also made of modified polyfunctional isocyanates, i.e. products which are obtained by chemical reaction of organic diisocyanates and/or polyisocyanates. Mention may be made by way of example of diisocyanates and/or polyisocyanates comprising ester, urea, biuret, allophanate, carbodiimide, isocyanurate, uretdione and/or urethane groups.

10

Specific examples are: organic, preferably aromatic polyisocyanates comprising urethane groups and having NCO contents of from 33.6 to 15% by weight, preferably from 31 to 21% by weight, based on the total weight, for example reaction products of low molecular weight diols, triols, dialkylene glycols, trialkylene glycols or polyoxyalkylene glycols, and having molecular weights up to 6000, in particular molecular weights up to 1500, modified diphenylmethane 4,4'-diisocyanate, modified diphenylmethane 4,4'- and 2,4'-diisocyanate mixtures or modified crude MDI or tolylene 2,4- or 2,6-diisocyanate, with examples of dialkylene glycols or polyoxyalkylene glycols, which can be used individually or as mixtures, being: diethylene glycol, dipropylene glycol, polyoxyethylene, polyoxypropylene and polyoxypropylene-polyoxyethylene glycols, triols and/or tetrols. Also suitable are prepolymers comprising NCO groups and having NCO contents of from 25 to 3.5% by weight, preferably from 21 to 14% by weight, based on the total weight, and prepared from the polyester polyols and/or preferably polyether polyols described below and diphenylmethane 4,4'-diisocyanate, mixtures of diphenylmethane 2,4'- and 4,4'-diisocyanate, tolylene 2,4- and/or 2,6- diisocyanates or crude MDI.

Liquid polyisocyanates comprising carbodiimide groups and/or isocyanurate rings and having NCO contents of from 33.6 to 15% by weight, preferably from 31 to 21% by weight, based on the total weight, e.g. compounds based on diphenylmethane 4,4'-, 2,4'- and/or 2,2'-diisocyanate and/or tolylene 2,4- and/or 2,6-diisocyanate, have also been found to be useful.

The modified polyisocyanates can optionally be mixed with one another or with unmodified organic polyisocyanates such as diphenylmethane 2,4'-, 4,4'-diisocyanate, crude MDI, tolylene 2,4- and/or 2,6- diisocyanate.

The following polyisocyanates have been found to be particularly useful and are preferably employed: mixtures of tolylene diisocyanates and crude MDI or mixtures of modified organic polyisocyanates comprising urethane groups and having an NCO content of from 33.6 to 15% by weight, in particular ones based on tolylene diisocyanates, diphenylmethane 4,4'-diisocyanate, diphenylmethane diisocyanate isomer mixtures or crude MDI and in particular crude MDI having a diphenylmethane diisocyanate isomer content of from 25 to 80% by weight, preferably from 30 to 55% by weight.

- 5
- 10 b) The polyether polyols b1), b2) and b3) used are prepared by known methods, for example from one or more alkylene oxides having from 2 to 4 carbon atoms in the alkylene radical by anionic polymerization using alkali metal hydroxides such as sodium or potassium hydroxide or alkali metal alkoxides such as sodium methoxide, sodium or potassium ethoxide or potassium isopropoxide as catalysts with addition of
- 15 at least one starter molecule comprising from 2 to 8, preferably from 2 to 6, reactive hydrogen atoms in bound form or by cationic polymerization using Lewis acids such as antimony pentachloride, boron fluoride etherate, etc. or bleaching earth as catalysts. It is also possible to use multimetal cyanide compounds, known as DMC catalysts. Tertiary amines such as triethylamine, tributylamine, trimethylamine,
- 20 dimethylethanolamine and/or dimethylcyclohexylamine can also be used as catalyst.

Suitable alkylene oxides for preparing the polyether polyols b1), b2) and b3) are, for example, ethylene oxide, 1,2-propylene oxide, 1,3-propylene oxide, 1,2- or 2,3-butylene oxide, tetrahydrofuran, styrene oxide, preferably ethylene oxide and

25 1,2-propylene oxide. The alkylene oxides can be used individually, alternately in succession or as mixtures.

Possible starter molecules for the polyether alcohols b1), b2) and b3) used according to the invention are the following compounds:

- 30
- b1) Use is made of hydroxyl-comprising high-functionality compounds, in particular sugars, starches or lignin, as starter substances. Glucose, sucrose and sorbitol are of particular practical importance here. Since these compounds are present in solid form under the usual reaction conditions of alkoxylation, it is generally customary to
- 35 alkoxylate these compounds together with coinitiators. Suitable coinitiators are, in particular, water and polyfunctional lower alcohols, e.g. glycerol, trimethylolpropane, pentaerythritol, ethylene glycol, diethylene glycol, propylene glycol and homologues

thereof.

5 b2) Starter molecules used are, in particular, ammonia, polyfunctional aliphatic amines, in particular those having from 2 to 6 carbon atoms and primary and secondary amino groups, and also amino alcohols having from 2 to 6 carbon atoms in the main chain. Preference is given to using ethylenediamine, monoalkylethylenediamines, 1,3-propylenediamine and also various butylenediamines and hexamethylenediamines; and ethanolamine, diethanolamine and triethanolamine as amino alcohols.

10 b3) Water and/or low molecular weight bifunctional or trifunctional alcohols are used as starter substances. In particular, linear or branched alcohols having from 2 to 12 carbon atoms, especially those having from 2 to 6 carbon atoms, in the main chain are used. Compounds preferably used as starter substances are water and, for example, glycerol, trimethylolpropane, ethylene glycol, propylene glycol, diethylene glycol,
15 dipropylene glycol, 1,4-butanediol, pentaerythritol, 1,6-hexanediol and homologues thereof.

It is possible to use one or more polyether alcohols as b3). Preference is given to using one or more polyether alcohols.

20 The polyether alcohols b1) preferably have functionalities of from 3.7 to 5.2 and a hydroxyl number of from 400 to 520 mg KOH/g and particularly preferably functionalities of from 3.9 to 5 and a hydroxyl number of from 400 to 500 mg KOH/g and very particularly preferably functionalities of from 4 to 4.5 and a hydroxyl number
25 of from 450 to 500 mg KOH/g.

The proportion of the component b1) is preferably from 30 to 60 parts by weight, particularly preferably from 40 to 60 parts by weight.

30 The polyether alcohols b2) have a functionality of 4 and a hydroxyl number of from 470 to 800 mg KOH/g and preferably a functionality of 4 and a hydroxyl number of 730-800 mg KOH/g.

The proportion of the component b2) is from 5 to 15 parts by weight.

35 The polyether alcohols b3) have functionalities of from 2 to 3 and a hydroxyl number of 220-430 mg KOH/g.

Preference is given to polyether alcohols b3) having a functionality of 3 and a hydroxyl number of 380-420 mg KOH/g.

5 The proportion of the component b3) is preferably from 10 to 25 parts by weight, particularly preferably from 10 to 20 parts by weight.

Further information regarding the polyether alcohols b1), b2) and b3) used and also their preparation may be found, for example, in *Kunststoffhandbuch*, volume 7 "Polyurethane", edited by Günter Oertel, Carl-Hanser-Verlag Munich, 3rd edition, 1993.

10

The component b) can comprise from 1 to 5 parts by weight, in particular from 1.5 to 5 parts by weight and very particularly preferably from 2 to 5 parts by weight, of water b4).

15

In one embodiment, the proportion of water b4) is from 2 to 5% by weight. This embodiment can be combined with other embodiments of the process of the invention.

c) As blowing agent for the process of the invention, it is possible to use the blowing agents customary for producing rigid polyurethane foams.

20

As blowing agents c), it is possible to use water and additionally generally known chemically and/or physically acting compounds. For the purposes of the present invention, chemical blowing agents are compounds which react with isocyanate to form gaseous products, for example water or formic acid. Physical blowing agents are 25 compounds which are dissolved or emulsified in the starting materials for polyurethane production and vaporize under the conditions of polyurethane formation. These are, for example, hydrocarbons, halogenated hydrocarbons and other compounds, for example perfluorinated alkanes such as perfluorohexane, chlorofluorocarbons, and ethers, esters, ketones, acetals and also inorganic and organic compounds which liberate 30 nitrogen on heating, or mixtures thereof, for example (cyclo)aliphatic hydrocarbons having from 4 to 8 carbon atoms or fluorinated hydrocarbons such as 1,1,1,3,3-pentafluoropropane (HFC 245 fa), trifluoromethane, difluoromethane, 1,1,1,3,3-pentafluorobutane (HFC 365 mfc), 1,1,1,2-tetrafluoroethane, difluoroethane and heptafluoropropane.

35

Low-boiling aliphatic hydrocarbons, preferably n-pentane and/or isopentane, in particular n-pentane, are advantageously used as blowing agent.

n-Pentane has a boiling point of 36°C, isopentane a boiling point of 28°C. The boiling points are therefore in a range which is favorable for the blowing process.

- 5 Since the aliphatic hydrocarbons which are suitable as blowing agents are flammable and explosive, the foaming plants have to be equipped with the appropriate safety devices as are also necessary when using n-pentane as blowing agent.

10 It is advantageous to use the aliphatic hydrocarbons together with water as blowing agent. The amount of aliphatic hydrocarbons used is from 2 to 25% by weight, preferably from 5 to 15% by weight, based on the component b). The proportion of water depends on the desired foam density of the rigid polyurethane foam and is generally from 2 to 2.5%.

- 15 d) Catalysts (d) used for producing the rigid polyurethane foams are, in particular, compounds which strongly accelerate the reaction of the compounds comprising reactive hydrogen atoms, in particular hydroxyl groups, of the component (b) with the organic, optionally modified polyisocyanates (a).

20 Suitable catalysts (d) are strongly basic amines, for example amidines such as 2,3-dimethyl-3,4,5,6-tetrahydropyrimidine, tertiary amines such as triethylamine, tributylamine, dimethylcyclohexylamine, dimethylbenzylamine, N-methylmorpholine, N-ethylmorpholine, N-cyclohexylmorpholine, N,N,N',N'-tetramethylethylenediamine, N,N,N',N'-tetramethylbutanediamine, N,N,N',N'-tetramethyl-1,6-hexanediamine,
25 pentamethyldiethylenetriamine, tetramethyldiamino(ethyl ether), bis(2-dimethyl-aminoethyl) ether, bis(dimethylaminopropyl)urea, dimethylpiperazine, 1,2-dimethyl-imidazole, 1-azabicyclo[3.3.0]octane and preferably 1,4-diazabicyclo[2.2.2]octane, and alkanolamine compounds such as triethanolamine, triisopropanolamine, N-methyldiethanolamine and N-ethyldiethanolamine, N,N-
30 dimethylaminoethoxyethanol, N,N,N'-trimethylaminoethylethanolamine and dimethylethanolamine.

Further possible catalysts are: tris(dialkylaminoalkyl)-s-hexahydrotriazines, in particular tris(N,N-dimethylaminopropyl)-s-hexahydrotriazine, tetraalkylammonium
35 hydroxides such as tetramethylammonium hydroxide, alkali metal hydroxides such as sodium hydroxide and alkali metal alkoxides such as sodium methoxide and potassium isopropoxide and also alkali metal salts of long-chain fatty acids having from 10 to 20

carbon atoms and optionally lateral OH groups.

If isocyanurate groups are to be incorporated into the rigid foam, specific catalysts are required. As isocyanurate catalysts, use is usually made of metal carboxylates, in particular potassium acetate and solutions thereof. The catalysts can, depending on
5 requirements, be used either alone or in any mixtures with one another.

Preference is given to using from 0.001 to 7% by weight, in particular from 0.05 to 5%
10 by weight, of catalyst or catalyst combination, based on the weight of the component (b).

e) Auxiliaries and/or additives (e) can optionally be incorporated into the reaction mixture for producing the rigid polyurethane foams. Mention may be made by way of example of surface-active substances, foam stabilizers, cell regulators, fillers, dyes,
15 pigments, flame retardants, hydrolysis inhibitors, fungistatic and bacteriostatic substances.

Possible surface-active substances are, for example, compounds which serve to aid the homogenization of the starting materials and may also be suitable for regulating the
20 cell structure of the plastics. Mention may be made by way of example of emulsifiers such as the sodium salts of castor oil sulfates or of fatty acids and also salts of fatty acids with amines, e.g. diethylamine oleate, diethanolamine stearate, diethanolamine ricinoleate, salts of sulfonic acids, e.g. alkali metal or ammonium salts of dodecylbenzenesulfonic acid or dinaphthylmethanedisulfonic acid and ricinoleic acid;
25 foam stabilizers such as siloxane-oxyalkylene copolymers and other organo-polysiloxanes, ethoxylated alkylphenols, ethoxylated fatty alcohols, paraffin oils, castor oil esters and ricinoleic esters, Turkey red oil and peanut oil and cell regulators such as paraffins, fatty alcohols and dimethylpolysiloxanes. The above-described oligomeric acrylates having polyoxyalkylene and fluoroalkane radicals as side groups
30 are also suitable for improving the emulsifying action, the cell structure and/or for stabilizing the foam. The surface-active substances are usually employed in amounts of from 0.01 to 5 parts by weight, based on 100 parts by weight of the component (b).

For the purposes of the present invention, fillers, in particular reinforcing fillers, are
35 the customary organic and inorganic fillers, reinforcing materials, weighting agents, agents for improving the abrasion behavior in paints, coating compositions, etc., known per se. Specific examples are: inorganic fillers such as siliceous minerals, for

example sheet silicates such as antigorite, serpentine, horn blendes, amphiboles, chrysotile, talc; metal oxides such as kaolin, aluminum oxides, titanium oxides and iron oxides, metal salts such as chalk, barite and inorganic pigments such as cadmium sulfide, zinc sulfide and also glass, etc. Preference is given to using kaolin (china clay),
5 aluminum silicate and coprecipitates of barium sulfate and aluminum silicate and also natural and synthetic fibrous minerals such as wollastonite, metal fibers and in particular glass fibers of various lengths which may be coated with a size. Possible organic fillers are, for example: carbon, melamine, rosin, cyclopentadienyl resins and graft polymers and also cellulose fibers, polyamide, polyacrylonitrile, polyurethane,
10 polyester fibers based on aromatic and/or aliphatic dicarboxylic esters and in particular carbon fibers.

The inorganic and organic fillers can be used individually or as mixtures and are advantageously incorporated into the reaction mixture in amounts of from 0.5 to 50%
15 by weight, preferably from 1 to 40% by weight, based on the weight of the components (a) and (b), but the content of mats, nonwovens and woven fabrics of natural and synthetic fibers can reach values of up to 80% by weight.

As flame retardants, it is possible to employ organic phosphoric esters and/or
20 phosphonic esters. Preference is given to using compounds which are not reactive toward isocyanate groups. Chlorine-comprising phosphoric esters are also among the preferred compounds. Suitable flame retardants are, for example, tris(2-chloropropyl) phosphate, triethyl phosphate, diphenyl cresyl phosphate, diethyl ethanephosphinate, tricresyl phosphate, tris(2-chloroethyl) phosphate, tris(1,3-dichloropropyl) phosphate,
25 tris(2,3-dibromopropyl) phosphate, tetrakis(2-chloroethyl) ethylene diphosphate, dimethyl methanephosphonate, diethyl diethanolaminomethylphosphonate and also commercial halogen-comprising flame retardant polyols.

In addition, it is also possible to use bromine-comprising flame retardants. As
30 bromine-comprising flame retardants, preference is given to using compounds which are reactive toward the isocyanate group. Such compounds are, for example, esters of tetrabromophthalic acid with aliphatic diols and alkoxylation products of dibromobutenediol. Compounds derived from the group of brominated neopentyl compounds comprising OH groups can also be employed.

35 Apart from the abovementioned halogen-substituted phosphates, it is also possible to use inorganic or organic flame retardants such as red phosphorus, aluminum oxide

hydrate, antimony trioxide, arsenic oxide, ammonium polyphosphate and calcium sulfate, expandable graphite or cyanuric acid derivatives such as melamine, or mixtures of at least two flame retardants such as ammonium polyphosphates and melamine and optionally maize starch or ammonium polyphosphate, melamine and expandable graphite and/or aromatic or nonaromatic polyesters for making the polyisocyanate polyaddition products flame resistant. In general, it has been found to be advantageous to use from 5 to 50 parts by weight, preferably from 5 to 25 parts by weight, of the flame retardants mentioned per 100 parts by weight of the component (b).

10

Further details regarding the abovementioned other customary auxiliaries and additives may be found in the specialist literature, for example the monograph by J.H. Saunders and K.C. Frisch "High Polymers", volume XVI, Polyurethanes, parts 1 and 2, Interscience Publishers 1962 and 1964, or Kunststoff-Handbuch, Polyurethane, volume VII, Hanser-Verlag, Munich, Vienna, 3rd edition, 1993.

15

To produce the rigid polyurethane foams, the polyisocyanates a) and the polyol component b) are reacted in such amounts that the isocyanate index is in the range from 100 to 150, preferably from 105 to 140, and particularly preferably from 110 to 130. The isocyanate index is the molar ratio of isocyanate groups to groups which are reactive toward isocyanate groups, multiplied by 100.

20

The rigid foams of the invention are preferably produced on continuously operating double belt plants. Here, the polyol component and the isocyanate component are metered by means of a high-pressure machine and mixed in a mixing head. Catalysts and/or blowing agents can be added to the polyol mixture beforehand by means of separate pumps. The reaction mixture is applied continuously to the lower covering layer. The lower covering layer with the reaction mixture and the upper covering layer run into the double belt. Here, the reaction mixture foams and cures. After leaving the double belt, the continuous strip is cut into the desired dimensions. In this way, it is possible to produce sandwich elements having metallic covering layers or insulation elements having flexible covering layers.

25

30

The starting components are mixed at a temperature of from 15 to 90°C, preferably from 20 to 60°C, in particular from 20 to 45°C. The reaction mixture can be cast into closed support tools by means of high- or low-pressure metering machines. Discontinuous sandwich elements, for example, are manufactured by this technology.

35

The invention further provides rigid polyurethane foams, produced by the process of the invention.

- 5 The rigid polyurethane foams produced by the process of the invention have a density of from 0.02 to 0.75 g/cm³, preferably from 0.025 to 0.24 g/cm³ and in particular from 0.03 to 0.1 g/cm³. They are particularly suitable as insulation material in the building and refrigeration sector, e.g. as intermediate layer for sandwich elements or for filling housings of refrigerators and freezer chests with foam.

10

The rigid PUR foams produced by the process of the invention have good surfaces with few defects and display good adhesion and good curing. The polyol component (b) simultaneously has good storage stability at 20°C or 5°C over several months.

- 15 The invention is illustrated by the examples below:

Comparative example 1

A polyol component was produced by mixing

- 20 56.0 parts by weight of a polyether alcohol having a hydroxyl number of 490 mg KOH/g and based on propylene oxide and a mixture of sucrose and glycerol as starter,

8.0 parts by weight of a polyether alcohol having a hydroxyl number of 770 mg KOH/g and based on propylene oxide and ethylenediamine as starter,

20 parts by weight of castor oil,

- 25 12 parts by weight of tris-2-chloroisopropyl phosphate,

2 parts by weight of Tegostab[®] B8462 from Goldschmidt,

0.5 part by weight of potassium acetate in ethylene glycol, 50% strength solution, and

2.1 parts by weight of water.

- 30 The polyol component is not stable at 20°C and also at 5°C and separates into two phases after 24 hours.

Comparative example 2

A polyol component was produced by mixing

- 35 75.4 parts by weight of a polyether alcohol having a hydroxyl number of 490 mg KOH/g and based on propylene oxide and a mixture of sucrose and glycerol as starter,

8.0 parts by weight of a polyether alcohol having a hydroxyl number of 770 mg

KOH/g and based on propylene oxide and ethylenediamine as starter,
12 parts by weight of tris-2-chloroisopropyl phosphate,
2 parts by weight of Tegostab[®] B8462 from Goldschmidt,
0.5 part by weight of potassium acetate in ethylene glycol, 50% strength solution, and
5 2.1 parts by weight of water.

The polyol component is stable at 20°C and also at 5°C. This was reacted with a
polymeric MDI having an NCO content of 30.9% by weight (Lupranat[®] M50 from
BASF SE) in the presence of n-pentane (6 parts by weight), dimethylcyclohexylamine
10 and water at an isocyanate index of 120. The amounts of dimethylcyclohexylamine and
water were selected so that the gel time was 45 seconds and the resulting foam had a
density of 36 g/l.

Example 1

15

A polyol component was produced by mixing
55.4 parts by weight of a polyether alcohol having a hydroxyl number of 490 mg
KOH/g and based on propylene oxide and a mixture of sucrose and glycerol as starter,
8.0 parts by weight of a polyether alcohol having a hydroxyl number of 770 mg
20 KOH/g and based on propylene oxide and ethylenediamine as starter,
20 parts by weight of a polyether alcohol having a hydroxyl number of 400 mg KOH/g
and based on propylene oxide and glycerol as starter,
12 parts by weight of tris-2-chloroisopropyl phosphate,
2 parts by weight of Tegostab[®] B8462 from Goldschmidt,
25 0.5 part by weight of potassium acetate in ethylene glycol, 50% strength solution, and
2.1 parts by weight of water.

The polyol component is stable for several months at 20°C, and also at 5°C. This was
reacted with a polymeric MDI having an NCO content of 30.9% by weight (Lupranat[®]
30 M50 from BASF SE) in the presence of n-pentane (6 parts by weight),
dimethylcyclohexylamine and water at an isocyanate index of 120. The amounts of
dimethylcyclohexylamine and water were selected so that the gel time was 45 seconds
and the resulting foam had a density of 36 g/l.

35 Comparative example 3

A polyol component was produced by mixing
55.4 parts by weight of a polyether alcohol having a hydroxyl number of 490 mg

- KOH/g and based on propylene oxide and a mixture of sucrose and glycerol as starter,
8.0 parts by weight of a polyether alcohol having a hydroxyl number of 770 mg
KOH/g and based on propylene oxide and ethylenediamine as starter,
10 parts by weight of a polyether alcohol having a hydroxyl number of 400 mg KOH/g
5 and based on propylene oxide and glycerol as starter,
10 parts by weight of a polyester alcohol having a hydroxyl number of 210 mg KOH/g
and produced by reacting phthalic anhydride, oleic acid, diethylene glycol and
monoethylene glycol,
12 parts by weight of tris-2-chloroisopropyl phosphate,
10 2 parts by weight of Tegostab[®] B8462 from Goldschmidt,
0.5 part by weight of potassium acetate in ethylene glycol, 50% strength solution, and
2.1 parts by weight of water.

The polyol component is stable for months at 20°C, and also at 5°C. This was reacted
15 with a polymeric MDI having an NCO content of 30.9% by weight (Lupranat[®] M50
from BASF SE) in the presence of n-pentane (6 parts by weight),
dimethylcyclohexylamine and water at an isocyanate index of 120. The amounts of
dimethylcyclohexylamine and water were selected so that the gel time was 45 seconds
and the resulting foam had a density of 36 g/l.

20 Curing of the PU foams produced was determined by means of the indenter test. For
this purpose, a steel indenter having a hemispherical end having a radius of 10 mm was
pressed to a depth of 10 mm into the foam formed by means of a tensile/compressive
testing machine at 3, 4, 5 and 6 minutes after mixing of the components in a
25 polystyrene cup. The maximum force required in N is a measure of the curing of the
foam. The sum of curing after 3, 4, 5 and 6 minutes is reported.

For the adhesion experiments, sandwich elements (200×200×80 mm) having metallic
covering layers were foamed in the laboratory in a closed heated mold. The
30 temperature of the mold was 40°C and the total density of the foam was 36 g/l. After
curing of the system, test specimens having dimensions of 100×100×80 mm were
sawn and the adhesion of the foam to the covering layer (tensile strength in Table 1)
was determined in accordance with DIN EN ISO 527-1 / DIN 53292.

35 The frequency of surface defects was determined quantitatively by an optical method.
For this purpose, a foam specimen was cut down to a plane one millimeter from the
lower covering layer, i.e. the covering layer to which the polyurethane reaction

solution had been applied in the double belt process.

In the quantitative assessment of the surface, the surface of the foam was illuminated from the right and then from the left and in each case photographed. The images were superimposed and analyzed by means of image analysis software. The defects on the surface appear as black areas. The percentage of the black areas based on the total surface area is a measure of the frequency of surface defects in the foam.

Furthermore, an additional qualitative assessment of the nature of the surface of the foams was carried out by removing the covering layer from a 1m × 2m foam specimen and visually assessing the surface.

The results are shown in Table 1.

Table 1

	Comparative example 1	Comparative example 2	Example 1	Comparative example 3
Stability of the polyol component at 20°C	unstable	stable	stable	stable
Stability of the polyol component at 5°C	unstable	stable	stable	stable
Total curing after 3, 4, 5 and 6 min [N]		344	352	340
Tensile strength [N/mm ²]		0.22	0.32	0.29
Surface (qualitative)		poor	very good	very good
Surface (quantitative) [%]		9.1	0.7	1.2

The results in Table 1 show that the stability of the polyol component is good at 20°C and 5°C and the surface properties, the curing and the adhesion of the foams produced by the process of the invention are very good.

The storage stability of the polyol components used in the process of the invention is

very good; polyol components corresponding to example 1, which each comprise 5 parts by weight of water, are even stable for months at 20°C and also at 5°C.

The PU foams obtained according to comparative example 2 have a significantly lower
5 tensile strength and a poorer surface.

Eljárás kemény poliuretánhabok előállítására

SZABADALMI IGÉNYPONTOK

1. Eljárás kemény poliuretánhabok előállítására

- a) szerves polizocianátoknak
- b) legalább két, izocianát-csoportokkal reaktív hidrogénatommal rendelkező vegyületekkel való reakciójával,
- c) gázképző anyagok,
- d) katalizátorok valamint adott esetben
- e) segédanyagok és adalékanyagok jelenlétében,

azzal jellemezve, hogy b) komponensként egy olyan keveréket alkalmazunk, amely áll

b1) 20-60 tömegrész egy vagy több olyan nagyfunktionalitású poliéter-alkoholokból, amelyeknek funkcionalitása 3,5-5,5 és hidroxí-száma 400-550 mg KOH/g, és startervegyületekként hidroxil-tartalmú nagyfunktionalitású vegyületekkel rendelkeznek,

b2) 5-15 tömegrész egy vagy több olyan poliéter-alkoholokból, amelyek 4-es funkcionalitású és 470-800 mg KOH/g hidroxí-számú alifás aminokon alapulnak,

b3) 10-30 tömeg% egy vagy több olyan poliéter-alkoholokból, amelyek 2-3 funkcionalitással és 220-430 mg KOH/g hidroxí-számmal rendelkeznek, és

b4) adott esetben 1-5 tömegrész vízből,

ahol a b) poliól-komponensek b1)-b4) tömegrészei nem haladják meg a 100 tömegrészt.

2. Az 1. igénypont szerinti eljárás, **azzal jellemezve, hogy** a b2) poliéter-alkoholok funkcionalitása 4 és hidroxí-száma 730-800 mg KOH/g.

3. Az 1. vagy 2. igénypont szerinti eljárás, **azzal jellemezve, hogy** a b3) poliéter-alkoholok funkcionalitása 3 és hidroxí-száma 380-420 mg KOH/g.

4. Az 1-3. igénypontok egyike szerinti eljárás, **azzal jellemezve, hogy** a reakciót egy 100 és 150 közötti izocianát-indexen valósítjuk meg.

5. Az 1-4. igénypontok egyike szerinti eljárás, **azzal jellemezve, hogy** a gázképző anyagként n-pentánt és/vagy izopentánt alkalmazunk.

6. Poliuretán keményhabok, amelyeket az 1. igénypont szerinti eljárással állítottunk elő.

7. Egy b) poliól-komponens, amely áll



SZTNH-100033930

- b1) 20-60 tömegrész egy vagy több olyan nagyfunktionalitású poliéter-alkoholokból, amelyeknek funkcionalitása 3,5-5,5 és hidroxí-száma 400-550 mg KOH/g, és starter-vegyületekként hidroxil-tartalmú nagyfunktionalitású vegyületekkel rendelkeznek,
- b2) 5-15 tömegrész egy vagy több olyan poliéter-alkoholokból, amelyek 4-es funkcionalitású és 470-800 mg KOH/g hidroxí-számú alifás aminokon alapulnak,
- b3) 10-30 tömeg% egy vagy több olyan poliéter-alkoholokból, amelyek 2-3 funkcionalitással és 220-430 mg KOH/g hidroxí-számmal rendelkeznek, és
- b4) adott esetben 1-5 tömegrész vízből,
- ahol a b) poliól b1)-b4) tömegrészei nem haladják meg a 100 tömegrészt.

A meghatalmazott:



Dr. Bódisz Árpád

Nyilvános Ügyvivő

SBGK Szabadalmi Ügyvivői Iroda

H-1062 Budapest, Aranyos ut. 113.

Tel: 461-1000 Fax: 461-1000

E-mail: bdisz@sbgk.hu