

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property

Organization

International Bureau

(43) International Publication Date

21 November 2019 (21.11.2019)



(10) International Publication Number

WO 2019/220004 A1

(51) International Patent Classification:

C01D 15/02 (2006.01)

C22B 26/12 (2006.01)

C01D 15/08 (2006.01)

TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

(21) International Application Number:

PCT/FI2019/050275

(22) International Filing Date:

05 April 2019 (05.04.2019)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

PCT/FI2018/050377

18 May 2018 (18.05.2018)

FI

Declarations under Rule 4.17:

— as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))

— of inventorship (Rule 4.17(iv))

Published:

— with international search report (Art. 21(3))

(71) Applicant: **OUTOTEC (FINLAND) OY** [FI/FI]; Rauhanpuisto 9, 02230 Espoo (FI).

(72) Inventors: **TIIHONEN, Marika**; Nuolitie 16 A, 02240 Espoo (FI). **HAAVANLAMMI, Liisa**; Lyhdekuja 1 D, 02200 Espoo (FI). **KOLEHMAINEN, Eero**; Rentukantie 11 as 5, 28660 Pori (FI). **KINNUNEN, Sami**; Teljänkuja 2 as 18, 28130 Pori (FI). **SAVIKANGAS, Juho**; Roihutie 3 as 2, 28220 Pori (FI).

(74) Agent: **SEPPO LAINE OY**; Porkkalankatu 24, 00180 Helsinki (FI).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JO, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM,

(54) Title: METHOD FOR RECOVERING LITHIUM HYDROXIDE

(57) Abstract: The present invention relates to a method and arrangement for recovering lithium hydroxide from a mineral containing lithium, by pulping the raw material containing lithium in the presence of water and an alkali metal carbonate, leaching the obtained slurry twice, first at an elevated temperature, and secondly in an aqueous solution containing an alkali earth metal hydroxide, separating the thus obtained slurry into solids and a solution containing lithium hydroxide, the latter being purified, whereby lithium hydroxide monohydrate can be recovered from the purified solution by crystallising, and finally separating the solution obtained during the crystallization from the process and recycling it to one or more of the previous process steps.



WO 2019/220004 A1

METHOD FOR RECOVERING LITHIUM HYDROXIDE

FIELD OF THE INVENTION

The present invention relates to a method and an arrangement for
5 recovering lithium hydroxide.

BACKGROUND OF THE INVENTION

CN102115101 discloses a method for producing lithium carbonate from spodumene mineral by performing a sulfuric acid treatment in order to obtain lithium sulfate, followed by a step of preparing the lithium carbonate
10 mother liquor, from which the carbonate product can be separated, and finally the lithium hydroxide is obtained from the mother liquor by adding lime to causticize said mother liquor. Also barium hydroxide is said to be useful as a causticizing hydroxide.

CN 100455512 C discloses a process for preparing lithium hydroxide monohydrate by adding sodium hydroxide to a lithium sulfate solution in order to obtain liquid lithium hydroxide, followed by cooling, filtering and separating the lithium hydroxide from the sodium sulfate, whereafter a series of re-crystallization steps are performed to provide the pure lithium hydroxide mono-
15 hydrate.

In CN 1214981 C a similar process is described, wherein the step of adding sodium hydroxide into the lithium sulfate solution is carried out, followed by cooling and separating to obtain the liquid lithium hydroxide. The lithium hydroxide solution is then concentrated and crystallized, whereby a coarse lithium hydroxide monohydrate product can be separated. In this publication
20 the pure lithium hydroxide monohydrate is obtained by reacting the coarse product with barium hydroxide, followed by concentrating and crystallizing.

However, these processes all proceed via the lithium sulfate.

BRIEF DESCRIPTION OF THE INVENTION

An object of the present invention is thus to provide a method and
30 an arrangement for recovering lithium hydroxide with high yield and high purity, typically of battery grade, without the need for multiple purification steps.

Particularly, it is an object of the invention to provide a method and an arrangement for recovering lithium hydroxide with high yield and high purity, typically of battery grade, using simple purification steps and recirculations.

Battery grade lithium hydroxide herein means lithium hydroxide monohydrate crystals having a purity of 56.5%, or higher of lithium hydroxide.

In addition, the process concept is sulphate and acid free, without the formation of undesired crystallized byproducts. The objects of the invention are achieved by a method and an arrangement which is characterized by what is stated in the independent claims. The preferred embodiments of the invention are disclosed in the dependent claims.

The present invention relates to a method for recovering lithium hydroxide from a raw material containing lithium. The method comprises the following steps of

- pulping the raw material containing lithium in the presence of water and an alkali metal carbonate for producing a first slurry containing lithium,
- leaching the first slurry containing lithium in a first leaching step at an elevated temperature for producing a second slurry containing lithium carbonate,
- leaching the second slurry or a fraction thereof in a second leaching step in an aqueous solution containing an alkali earth metal hydroxide for producing a third slurry containing lithium hydroxide,
- separating the third slurry into solids and a solution containing lithium hydroxide by solid-liquid separation and providing a purified solution containing lithium hydroxide, and
- recovering lithium hydroxide monohydrate by crystallising from the purified solution containing lithium hydroxide.

Preferably, the method further comprises the steps of

- purifying the solution separated from the solids of the third slurry in a separate purification step, and
- separating the solution obtained during the crystallization from the process, and recycling it to one or more of the previous process steps, or back to the crystallization

According to an embodiment of the present invention the raw material containing lithium can be any raw material from which it is desired to recover lithium. Typically the raw material containing lithium is selected from a mineral containing lithium, preferably from spodumene, petalite or lepidolite or mixtures thereof, most suitably from spodumene.

According to an embodiment of the present invention the raw material containing lithium is selected from a mineral containing lithium which has undergone heat treatment, whereby a particularly preferred material is beta-spodumene.

5 According to an embodiment of the present invention the first leaching solution is separated from the solids after the first leaching step, whereby only the solids are carried to the second leaching step.

 According to an embodiment of the present invention the first leaching solution is separated from the solids after the first leaching step and is recycled either to the pulping step or to the first leaching step, or a fraction to each.

 According to an embodiment of the present invention the solids are separated from the solution in the separation step by any suitable solid-liquid separation method, typically by thickening and/or filtering.

15 According to an embodiment of the present invention the purifying step carried out on the solution obtained from the second solid/liquid separation step, is preferably performed by ion exchange, typically by using cation exchange resin.

 According to an embodiment of the present invention the crystallizing of the lithium hydroxide monohydrate is performed by heating and cooling, or alternatively by merely concentrating the solution by heating.

 According to an embodiment of the present invention the bleed solution obtained while crystallizing the lithium hydroxide monohydrate is recovered and recycled to one or more of the previous process steps, for example the pulping step, the second leaching step, a separation step, and/or back to the crystallization step.

 Optionally, the bleed solution obtained from the crystallization step is pretreated prior to recycling it to previous process steps, e.g. by carbonation, using a carbonate or CO₂.

30 When performing a first, optional, solid-liquid separation between the leaching steps, it is possible to recover the solution used in the first leaching step, containing any excess of the leaching chemical, i.e. the alkali metal carbonate, and recycle it. This recycling, in turn, reduces the need for a separate pH adjustment in the later stages of the process, and likewise reduces the chemical consumption in the process.

According to a preferred embodiment of the present invention, when a first solid-liquid separation is carried out between the two leaching steps, the obtained solids are partly recovered and carried to a separate process for recovering pure lithium carbonate.

5 When applying this preferred embodiment, the method can also include the steps of recycling the crystallized lithium carbonate to the second hydroxide leaching step.

The present invention relates also to an arrangement for recovering lithium hydroxide from a raw material containing lithium according to the above
10 method, which arrangement comprises

- a pulping unit 1 for pulping the raw material containing lithium in the presence of water and an alkali metal carbonate,
- a first leaching unit 2 for leaching a first slurry containing lithium at an elevated temperature,
- 15 – a second leaching unit 3 for leaching a second slurry containing lithium carbonate, or a fraction thereof, in the presence of water and an alkali earth metal hydroxide,
- a solid-liquid-separation unit 31 for separating a third slurry containing lithium hydroxide into solids and a solution containing lithium,
- 20 and
- a crystallising unit 4 for recovering lithium hydroxide monohydrate from a solution containing lithium.

Preferably, the arrangement further comprises:

- 25 - a purification unit 32 connected to the solid-liquid-separation unit 31, for purifying the solution obtained from said separation unit 31, and a line 403,414 for carrying a solution from the crystallizing unit 4 to a point further upstream of the crystallizing unit (4), or back to the crystallization unit 4.

30

According to an embodiment of the invention the arrangement comprises also the necessary lines for carrying the solutions to be recycled to their intended units.

BRIEF DESCRIPTION OF THE DRAWINGS

In the following the invention will be described in greater detail by means of preferred embodiments with reference to Figures 1, 2, 3, 4 and 5, which all show general flow diagrams and arrangements of units of certain
5 embodiments of the invention.

DETAILED DESCRIPTION OF THE INVENTION

An embodiment of the method of the invention, as presented schematically in Figure 1, is a method for recovering lithium hydroxide from a raw material containing lithium, the method of this particular embodiment including
10 pulping 1 the raw material in the presence of sodium carbonate, leaching the obtained slurry in a first leaching step 2, followed by leaching in a second leaching step 3, in the presence of calcium hydroxide, whereafter the obtained slurry is separated 31 into solids and a liquid, whereby the liquid can be carried to a crystallization step 4, for producing high purity lithium hydroxide.

Another embodiment of the invention, as presented schematically in
15 Figure 2, is a method for recovering lithium hydroxide from a raw material containing lithium, this embodiment further specifying that a first solid-liquid separation 21 can be carried out already after the first leaching step 2, whereby at least a fraction of the liquid fraction can be recycled to either the pulping step
20 1, via line 211, or to the first leaching step 2, via line 212.

Further embodiments of the invention are illustrated in Figures 3 to 5, whereby Figure 3 shows a number of optional details of the method and arrangement of the invention, based on a specific embodiment, and Figures 4 and 5 show a couple of specific options relating to the purification step 32. All
25 these options are described in more detail below.

The dotted lines in the drawings indicate that the units within these dotted lines can be combined in certain embodiments of the invention.


In the present invention, the raw material containing lithium is typically selected from spodumene, petalite, lepidolite or mixtures thereof. The raw material is preferably a lithium-containing mineral in calcined form, more preferably obtained by heat treating the raw material, most suitably by using a temperature of approximately 1050°C.
30

A particularly preferred mineral is spodumene, providing beta-spodumene in a calcination step.
35

The method of the invention comprises pulping 1 the raw material containing lithium in the presence of water and an alkali metal carbonate for extracting the lithium from the raw material and producing a first slurry containing lithium. The pulping 1 can be performed in any suitable vessel or reactor by
5 contacting a feed containing lithium mineral with an alkali metal carbonate and water for producing a first slurry containing lithium.

The alkali metal carbonate is preferably selected from sodium and potassium carbonate, most suitably being at least partly composed of sodium carbonate. Typically, the alkali metal carbonate is present in excess. After
10 pulping, the first lithium-containing slurry is leached 2 for a first time for producing a second slurry containing lithium carbonate.

The presence of alkali metal carbonate and process conditions result in the formation of lithium carbonate and analcime solids, which can be presented in the case of spodumene and sodium carbonate with the following
15 formula (1).



The first leaching 2 of the first slurry containing lithium is typically
20 performed in a suitable autoclave or series of autoclaves at an elevated temperature.

In an embodiment of the invention, the first leaching step is carried out at a temperature of 160 to 250°C, preferably at a temperature of 200 to 220°C. Likewise, the first leaching step is preferably carried out at a pressure
25 of 10 to 30bar, preferably 15 to 25bar. Suitable conditions for the first leaching step are typically achieved using high-pressure steam.

In another embodiment, at least a fraction of the water and alkali metal carbonate carried to the pulping step is a recycled aqueous solution containing said alkali metal carbonate.

30 An optional solid-liquid separation step 21 can be carried out, wherein the solution can be separated from the solids after the first leaching step 2, and the solids carried to the second leaching step 3.

In an embodiment, the solution separated from the solids in the optional separation step 21 is recycled to one or more of the preceding steps.

Preferably, the solution is recycled either to the pulping step or to the first leaching step, or a fraction to each. More preferably, the solution is recycled to the pulping step.

5 In the second leaching step 3, the lithium-containing phase (here typically the solids, or the entire second slurry) is leached 3 for a second time using a hydroxide reagent, i.e. an alkaline earth metal hydroxide, followed by a separation of solids from the solution by solid-liquid separation 31 and by the preparation of lithium hydroxide -containing solution of relatively high purity.


10 The alkali earth metal hydroxide used in the second leaching step 3 is preferably selected from calcium and barium hydroxide, more preferably being calcium hydroxide, optionally prepared by reaction of calcium oxide (CaO) in the aqueous solution..

15 In an embodiment of the invention, the alkali earth metal hydroxide used in the second leaching step 3 is mixed with water or an aqueous solution prior to addition to the second leaching step 3.

Preferably, at least a fraction of the solution separated from the solids in separation step 31, containing among others lithium and sodium, is added to said second leaching step in the form of a recycled solution, preferably mixed with fresh alkali earth metal hydroxide prior to addition to the second leaching step, more preferably mixed with fresh alkali earth metal hydroxide in a separate slurring step 30.

25 The second leaching step 3 is typically carried out at a temperature of 10-100°C, preferably 20-60°C, and most suitably 20-40°C. Typically, the second leaching step 3 is carried out at atmospheric pressure.

30 The presence of alkaline earth metal hydroxide and process conditions result in the formation of lithium hydroxide, which can be presented in the case of analcime, lithium carbonate and calcium hydroxide with the following formula (2).



35 After the two leaching steps 2,3 have been performed, the obtained third lithium hydroxide -containing slurry is separated 31 into a solid phase and a solution. The separation 31 can be done with any suitable solid-liquid separation method. For example, the third slurry can be routed to a thickener, from where the overflow can be routed directly to purification and the underflow can

be filtered further in order to recover all lithium hydroxide present in the solution and separate it from solid impurities, or a simple filtering technique can be used. Typically, all solid-liquid separations described herein require a supply of washing water for washing of the solids, although no such supply is separately
5 mentioned. The obtained solids from this separation of the third slurry into solids and a solution are typically composed of unwanted residues, which can be discarded, e.g. as tailings.

As stated above, the third slurry separated from the second leaching step 3 is purified 32 before carrying it to the crystallization step. This purification
10 step is preferably based on purification of dissolved ions and components, and more preferably includes an ion exchange or a membrane separation, or both, most suitably by using a cation exchange resin, particularly a selective cation exchange resin.

The ion exchange can be performed for example by using a method
15 disclosed in Finnish patent 121 785.

Typically the purifying by ion exchange is performed by using cation exchange resin, wherein the cation exchange group is for example iminodiacetic acid (IDA) or aminophosphonic acid (APA).

Selective cation exchange resins typically have a chelating functional group attached to the resin matrix. These chelating functional groups
20 usually have a much higher selectivity towards multi-valent metal cations, such as heavy and alkaline earth metal cations, compared to the monovalent alkali metal cations (Li, Na, K). Suitable resin functionalities are, for example the above mentioned iminodiacetate and the aminophosphonate. These chelating
25 resins can be used to purify the typical cationic impurities, such as calcium ions (Ca^{2+}) from lithium hydroxide solutions.

In an embodiment, the step of purifying the solution obtained from the third slurry is carried out at least partly using a resin that has been regenerated in a separate regeneration step.

30 Preferably, the regeneration step is carried out using a recycled solution from a subsequent process step, more preferably being the separated solution obtained during the crystallization, optionally in purified form.

In a preferred embodiment, this regeneration is carried out using at least acidic solution for metal elution, preferably being hydrochloric acid (HCl),
35 and an alkaline solution for neutralization, preferably being sodium hydroxide (NaOH) or an alkaline lithium hydroxide solution, more preferably a recycled

solution containing lithium hydroxide. Further, water can be fed to the regeneration step. The regenerated resin can be fed back to the ion exchange.

These purification and regeneration steps can, however, also be combined, and carried out in the same purification unit.

5 The membrane separation can be carried out using a semi-permeable membrane, which separates ionic or other dissolved compounds from aqueous solutions. More precisely, the membrane separation can be used to fractionate the dissolved ions and compounds by their size (depending on the pore size of the membrane material), and/or their charge (depending on
10 the surface charge of the membrane material). A positive surface charge repels cations (with a stronger repelling action for multi-valent cations) and attracts anions, and vice versa. These phenomena will enable the purification of, for example, multi-valent metal cations, complexed species (such as aluminium hydroxide complexes), polymeric species (such as dissolved silica) and
15 larger anions (e.g. sulfate and carbonate ions) from lithium hydroxide solutions. With the membrane separation, no regeneration is required.

Since lithium hydroxide is a strong alkali having a high concentration of hydroxide ions, metals that are strongly complexed by hydroxide ions (such as aluminium ions, Al^{3+}) cannot be purified by the above mentioned selective cation exchange resins. Therefore, these ions are purified using the
20 herein described recirculations.

The selective cation exchange is preferably used in the polishing removal of multivalent metal cations that form sparingly soluble hydroxide compounds (typically calcium hydroxide). These metals (or metal cations)
25 should be removed, or at least their concentrations should be reduced to very low levels in the solution to be carried to the crystallization, in order to prevent them from contaminating the crystallized lithium hydroxide monohydrate product. The removal of these metals is not as efficient with membranes, and is thus preferably done by ion exchange, particularly with a selective cation exchange resin.
30

In case a membrane separation is carried out, either alone or combined with an ion exchange, a recycle stream is provided from the membrane separation, which is suitable for carrying to the second leaching step 3.

In membrane separation, the retained ions and compounds will end
35 up in a concentrated fraction, typically called the "retentate", which can be recycled to the second leaching step as described above. The other obtained

fraction is the permeated liquid fraction, i.e. the “permeate”, which is fed to the crystallization, optionally via the ion exchange purification, if these purifications are combined.

5 The fraction to which each ion and compound ends up in the membrane separation depends on their characteristics: for example their charge and size. This targeting of the retention can be done based on selection of the desired membrane type, based on surface charge and/or pore size.

For the charge, the targeted retained species would typically be multi-valent metal cations, for example: calcium ions (Ca^{2+}), magnesium ions
10 (Mg^{2+}) vs. permeated (or zero to negatively retained) monovalent alkali metal cations, such as lithium ions (Li^{+}) or sodium ions (Na^{+}).

For the size, the retained species would typically be larger compounds, for example: polymeric species (such as dissolved silica), complexed ions (such as aluminium hydroxide complexes), and the largest types of anions
15 (such as carbonate, CO_3^{2-} , and sulfate, SO_4^{2-}), whereas the smallest types of anions (such as hydroxide, OH^{-}), are permeated (or: has zero or negative retention).

Based on the above, it is particularly preferred to combine a membrane separation with an ion exchange, most suitably by first carrying out a
20 membrane separation, and then an ion exchange for polishing removal of multivalent metal cations.

Finally, crystals of lithium hydroxide monohydrate are recovered by crystallising 4 from the purified lithium-containing solution. The crystallizing is typically performed by heating the purified solution containing lithium to a temperature of approximately the boiling point of the solution, to evaporate the liquid, or by recrystallizing the monohydrate from a suitable solvent.
25

In an embodiment of the invention, two or more crystallization units are used, preferably being sequentially arranged.

The method of the invention enables production of pure lithium hydroxide monohydrate with excellent yield and purity in a continuous and simple
30 process, typically providing battery grade lithium hydroxide monohydrate crystals, having a purity of 56.5% or higher of lithium hydroxide.

In another embodiment, the purified solution containing lithium hydroxide is mixed with one or more solutions recycled from subsequent steps of the method before being carried to the crystallization step 4, or these solutions
35 can be fed separately to the crystallization 4.

Preferably, the crystallization step 4 is followed by a solid-liquid separation step 41.

The bleed solution obtained while crystallizing 4 the lithium hydroxide monohydrate can be recovered and recycled to one or more of the previous process steps, for example the pulping step 1, second leaching step 3, a separation step 31, and/or back to the crystallization step 4.

Thus, it is preferred to recycle at least a fraction of the solution separated from the crystallization step to a preceding step with lower alkalinity, or back to the crystallization step 4.

10 The advantage achieved by recycling said fraction to a preceding step with lower alkalinity is that some impurities in the crystallization liquids (e.g. aluminium and silicon) have a solubility that increases with increasing alkalinity (e.g. caused by increasing lithium hydroxide concentration), whereby these alkali-soluble impurities can be removed by recycling them in solution to
15 a step of lower alkalinity. One preferred alternative is to recycle at least a fraction of said crystallization liquid, or bleed solution, to the second leaching step 3, or to a preceding step (typically the pulping or first leaching), from which they can be carried to the second leaching step 3. In said lower alkalinity environment, these impurities form sparingly soluble compounds (e.g. aluminium
20 hydroxide), and can be discarded with the solids in separation step 31. Also soluble carbonate ions are carried to the second leaching step 3, or to a preceding step (typically the pulping 1 or first leaching 2, from which they can be carried to the second leaching step) using this recycle option. Carbonate ions
25 form sparingly soluble compounds in the second leaching step 3 and can be discarded with the solids in the separation step 31.

In an embodiment of the invention, at least a fraction of the solution separated from the crystallization step is recycled to the second leaching step, and optionally a further fraction to the pulping step. The advantage of these
30 recycling options is that the soluble impurities remaining in the liquids after crystallization (main impurities being sodium, potassium, aluminium and carbonate ions, as well as soluble silicon and silicates) can be circulated upstream, where they can be removed. Particularly in the leaching steps, these impurities form sparingly soluble compounds, which can be discarded as solids
35 after the second leaching step. Without this recycling option, these impurities are typically concentrated in the crystallization step, and contaminated in the product.

In another embodiment, at least a fraction of the solution separated from the crystallization step is recycled back to the crystallization step. In a typical crystallization process, the crystallization slurry is maintained in a continuous circulation, from which product crystals are continuously separated, and the advantage of recycling at least a fraction of the remaining mother liquid is that it increases the yield of the process.

As mentioned above, it is preferred to recycle at least a fraction of the solution separated from the crystallization step to the second leaching step or back to the crystallization. It is, however, particularly preferred to recycle the solution at least to the second leaching, or advantageously to both the second leaching and the crystallization.

In a further embodiment, at least a fraction of the solution separated from the crystallization step is carried to a lithium precipitation step, which preferably is carried out as a carbonation, wherein the solution is reacted with either carbon dioxide or an alkali metal carbonate in order to form a lithium carbonate slurry.

This optional lithium precipitation step has the advantage of reacting lithium hydroxide contained in the crystallization bleed solution into the corresponding carbonate. This lithium hydroxide should preferably not be returned to the pulping or first leaching steps of the process.

After the optional lithium precipitation step, the lithium carbonate slurry is preferably subjected to a solid-liquid separation step, from which at least a fraction of the solids is carried to a conversion step. In this preferred conversion step, the solids are mixed with an alkali earth metal slurry, the conversion step preferably performed at a temperature close to the boiling point of water, more preferably at a temperature of 90 to 100 °C, whereby the lithium carbonate of the solids is solubilized as lithium hydroxide, also forming calcium carbonate.

After the optional lithium precipitation step, the lithium carbonate slurry is preferably subjected to a solid-liquid separation step, from which at least a fraction of the solids is carried to a conversion step, and then recycled to the solid-liquid separation step following the second leaching step.

Preferably, at least a fraction of the solution separated from the solids after the optional lithium precipitation step is recycled to the pulping step, or to the first leaching step, or a fraction to each, more preferably at least a fraction to the pulping step.

The advantage achieved by recycling said fraction to pulping or first leaching is that some impurities (e.g. sodium and potassium) have a high solubility in the crystallization liquids, but these impurities form sparingly soluble compounds (e.g. analcime) in the pulping and/or first leaching step and they
5 can be discarded in the separation step 31.

In an embodiment of the invention, the solids obtained in the crystallization step, containing crystals of lithium hydroxide monohydrate, are purified using a washing solution before recovery as the product.

The purified crystals of lithium hydroxide monohydrate are preferably
10 separated from the washing solution, are dried, and thereafter recovered.

The spent washing solution is, in turn, preferably separated from the purified crystals of lithium hydroxide monohydrate, and is recycled to the crystal washing step or to a step of regenerating a resin intended for being carried to the purification step, or to the crystallization step, or a fraction of the spent
15 washing solution is recycled to two or all three of these steps.

It is particularly preferred to recycle at least a fraction of this spent washing solution (or crystallization mother liquid) to the regeneration step, since the solution is relatively pure and contains uncrystallized lithium hydroxide, which should be reused, particularly in a step upstream from the crystallization, or in the crystallization. Thus, the regeneration 33 is an option for the
20 recycling.

The present invention relates also to an arrangement for recovering lithium hydroxide from a raw material containing lithium according to the method of the present invention. The referral numbers referring to Figure 1 in connection with the description of the method correspond to the referral numbers used in connection with the description of the arrangement, thus the method steps of the method correspond to the units of the arrangement. The arrangement comprises

- 30 – a pulping unit 1 for pulping the raw material containing lithium in the presence of water and an alkali metal carbonate,
- a first leaching unit 2 for leaching a first slurry containing lithium at an elevated temperature,
- a second leaching unit 3 for leaching a second slurry containing lithium carbonate, or a fraction thereof, in the presence of water and an
35 alkali earth metal hydroxide,

- a solid-liquid-separation unit 31 for separating a third slurry containing lithium hydroxide into solids and a solution containing lithium hydroxide,
- a purification unit 32 connected to the solid-liquid-separation unit 31, for purifying the solution obtained from said separation unit 31, and
- a crystallising unit 4 for recovering lithium hydroxide monohydrate from a solution containing lithium,
 - which further comprises a line 403,414 for carrying a solution from the crystallizing unit 4 to a point further upstream of the crystallizing unit 4, or back to the crystallization unit 4.

In an embodiment of the invention, the arrangement further comprises a calcination unit 10 for heat treating the raw material intended to be carried to the pulping unit 1.

The pulping unit 1 preferably contains also a feed inlet 101 for supplying the raw material containing lithium to the unit 1.

Further, an inlet 111 can be added, in connection with the pulping unit 1, for carrying a recycled aqueous solution containing alkali metal carbonate to the pulping unit 1.

The first leaching unit 2 is preferably an autoclave.

In an embodiment, the first leaching unit 2 is connected to the pulping unit 1 via a slurry line 102.

In an embodiment, a solid-liquid separation unit 21 is arranged between the first leaching unit 2 and the second leaching unit 3.

Preferably, a recycle line 211,212 leads from the first leaching unit 2, or from the liquid section of a solid-liquid separation unit 21 connected to said first leaching unit 2, to a unit upstream from said first leaching unit 2.

More preferably, a recycle line 211,212 leads from the first leaching unit 2, or from the liquid section of a solid-liquid separation unit 21 placed in connection with said first leaching unit 2, either as line 211 to the pulping unit 1 or as line 212 to the first leaching unit 2, or a separate line 211 and 212 to each.

Even more preferably, a recycle line 211 leading from the first leaching unit 2, or from the liquid section of a solid-liquid separation unit 21 connected to said first leaching unit 2, to the pulping unit 1.

In an embodiment of the invention, the second leaching unit 3 is a tank reactor, preferably a stirred tank reactor.

Preferably, the second leaching unit 3 includes an inlet 303 for alkali earth metal hydroxide or an aqueous slurry thereof.

In another embodiment, the second leaching unit 3 is connected to a slurring unit 30 for mixing an alkali earth metal hydroxide into an aqueous
5 slurry.

In a further embodiment, the second leaching unit 3 is connected to the first leaching unit 2, or to a downstream solid-liquid separation unit 21, via a slurry line 203.

The purification unit 32 used in the purification of the solution separated from the third slurry preferably includes a membrane separation unit or
10 an ion exchange unit, or both, preferably an ion exchange unit, and more preferably a cation exchange unit, particularly being a selective cation exchange unit.

In a preferred embodiment (see Fig. 3), where the purification unit
15 32 is an ion exchange unit, it is connected to a regeneration unit 33 for regenerating a purification resin. This regenerated resin can then be fed via a recycle line 332 back to the ion exchange unit 32. However, these purification and regeneration steps can also be carried out in a single unit 32 (see dotted line around units 32 and 33 of Fig. 3).

No such regeneration is required when the purification unit 32 is a
20 membrane separation unit (see Fig. 4). However, in the case a membrane separation unit is used, the unit provides two streams, one being a purified solution, which can be carried directly to the crystallization unit 4, while the other is a recycle stream, which is suitable for carrying to the second leaching unit 3,
25 for example via a recycle line 323.

In a further embodiment of the invention (see Fig. 5), the arrangement of the invention can include both an ion exchange unit 32a and a membrane separation unit 32b, and thus also a regeneration unit 33. Due to the presence of the membrane separation unit 32b, a recycle stream can be provided, carrying a recycle stream via line 323 to the second leaching unit 3.
30

In said embodiment it is particularly preferred to position the ion exchange unit 32a downstream from the membrane separation unit 32b.

In an embodiment of the invention, the arrangement includes two or more crystallization units 4, preferably being sequentially arranged.

Preferably, the crystallization unit 4, or a downstream purification unit 32, or an optional regeneration unit 33, is connected to the second leaching unit 3, or the downstream solid-liquid separation unit 31 via liquid line 304.

In an embodiment, the arrangement comprises a solid-liquid separation unit 41 connected to the crystallization unit 4 for separating the crystals obtained in the crystallization unit 4 from the spent solution.

Preferably, a recycle line 403, 414 is arranged between the crystallizing unit 4, and/or the liquid section of the solid-liquid separation unit 41 connected to the crystallization unit 4, and an upstream unit.

More preferably, a recycle line 403 is arranged between the crystallizing unit 4, and/or the liquid section of the solid-liquid separation unit 41 connected to the crystallization unit 4, and the second leaching unit 3, and optionally a further line arranged between the crystallization unit 4, and/or the liquid section of the solid-liquid separation unit 41 connected to the crystallization unit 4, and the pulping unit 1.

In an embodiment of the invention, the arrangement comprises a lithium precipitation unit 42 connected to the crystallization unit 4 or the solid-liquid separation unit 41 through a line 421.

Preferably, the lithium precipitation unit 42 includes a feed inlet 422 for feeding carbon dioxide or an alkali metal carbonate to the unit 42.

More preferably, the arrangement includes a solid-liquid separation unit 43 connected to and downstream from the lithium precipitation unit 42.

Even more preferably, the lithium precipitation unit 42, and/or a solids section of a solid-liquid separation unit 43 connected to said lithium precipitation unit 42, is connected via a recycle line 434 to a conversion unit 44.

In an embodiment of the invention, the conversion unit 44 contains an inlet 344 for alkali earth metal hydroxide or an aqueous slurry thereof.

Preferably, the conversion unit 44 is connected to a slurring unit 30 for mixing an alkali earth metal hydroxide into an aqueous slurry, and from which slurry can be fed to the conversion unit 44.

More preferably, the conversion unit 44 is connected via line 443 to the second leaching unit 3, and/or to the solid-liquid separation unit 31 connected to the second leaching unit 3.

In an embodiment, the liquid section of a solid-liquid separation unit 41, 43, preferably a unit 43 following the optional precipitation unit 42, is connected via line 431 to the pulping unit 1, whereby at least a fraction of the solu-

tion obtained in the separation unit 41,43 can be recycled to said pulping unit 1.

Alternatively, the liquid section of said solid-liquid separation unit 41,43, preferably a unit 43 following the optional precipitation unit 42, is connected via a further recycle line 432 to the first leaching unit 2, whereby at least a fraction of the solution obtained in the separation unit 41,43 can be recycled to said first leaching unit 2.

The solids obtained in separation unit 41,43, preferably a unit 43 following the optional precipitation unit 42, can optionally be recycled to a conversion unit 44 for solubilization, particularly via a recycle line 434.

In an embodiment, the liquid section of the solid-liquid separation unit 41 is connected to the crystallization unit 4 via recycle line 414, for recycling the spent solution separated from the crystallization step back to the crystallization unit 4.

In another embodiment of the invention, the arrangement includes a purification unit 45 connected to the crystallization unit 4, and/or to a solid-liquid separation unit 41 connected to the crystallization unit 4, wherein the solids obtained in the crystallization step can be purified.

Preferably, the purification unit 45 includes a feed inlet 451 for feeding a washing solution into the purification unit 45.

In an embodiment, the arrangement includes a solid-liquid separation unit 46 connected to and downstream from the purification unit 45, for separating the purified crystals of lithium hydroxide monohydrate from the spent washing solution.

Preferably, the purification unit 45, or a solid-liquid separation unit 46, connected to and downstream from the purification unit 45 is connected via a recycle line 452 to the upstream purification unit 32, or to an optional regeneration unit 33.

More preferably, a solid-liquid separation unit 46 connected to and downstream from the purification unit 45 is connected via a recycle line 464 to the crystallization unit 4.

Even more preferably, a solid-liquid separation unit 46 connected to and downstream from the purification unit 45 is connected via a recycle line 465 to the purification unit 45.

In another option, the arrangement of the invention comprises a combined purification unit 41,45,46 for purifying the crystals obtained in the

crystallization unit 4 from the spent solution, and separating the purified crystals from the spent washing solution.

In this alternative option, the recycle line 414 connects the combined unit 41,45,46 to the crystallization unit. Likewise, the feed inlet 451 is connected to the combined purification unit 41,45,46. Further, the recycle line 452 connects the combined purification unit 41,45,46 is connected to the upstream purification unit 32, or to a separate regeneration unit 33, and the recycle 464 line connects the combined purification unit 41,45,46 to the crystallization unit (4). Finally, the recycle line 465 connects a solids section of the combined purification unit 41,45,46 to the liquid section of the same combined unit 41,45,46.

In an embodiment of the invention, the arrangement includes a drying unit 47, connected to the crystallization unit 4, or connected to a solids section of a solid-liquid separation unit 41,46 downstream from the crystallization unit 4, wherein the obtained crystals of lithium hydroxide monohydrate can be dried.

Preferably, the drying unit 47 includes a product outlet 471 through which the final, battery grade, product can be recovered.

20

REFERENCE NUMBERS

The reference numbers according to an embodiment of the present invention, as used in Figures 1 to 5, are shown below (some of these units and lines being optional):

	10	calcination unit
	1	pulping unit
	101	feed inlet for supplying raw material to the pulping unit 1
30	102	slurry line for carrying a first slurry from the pulping unit 1 to the first leaching unit 2
	111	feed inlet for supplying recycled solution to the pulping unit 1
35	2	first leaching unit

	203	slurry line for carrying a second slurry from the first leaching unit 2 to the second leaching unit 3
	21	solid-liquid separation unit
5	211	recycle line from separation unit 21 to pulping unit 1
	212	recycle line from separation unit 21 to first leaching unit 2
	3	second leaching unit
	30	slurrying unit for mixing an alkali earth metal hydroxide into an aqueous slurry
10	303	inlet for supplying alkali earth metal hydroxide or an aqueous solution thereof to the second leaching unit 3
	304	liquid line for carrying a third slurry from the second leaching unit 3, or from the separation unit 31, to the purification unit 32 or to the optional regeneration unit 33
15		
	31	solid-liquid separation unit
	313	recycle line for carrying a solution obtained from the separation unit 31 to the second leaching unit 3, or to the optional slurrying unit 30
20		
	32	purification unit downstream from the S/L separation unit 31, and upstream from the crystallization unit 4
	323	recycle line for carrying a recycle stream from the purification unit 32 to the second leaching unit 3
25		
	33	regeneration unit
	332	recycle line for carrying a regenerated stream from the regeneration unit 33 to the purification unit 32
	4	crystallizing unit
	401	recycle line from crystallizing unit 4 to pulping unit 1 (not shown in the drawings)
30		
	403	recycle line from crystallizing unit 4, or the separation unit 41, to the second leaching unit 3
	41	solid-liquid separation unit
	414	recycle line from a downstream point of the crystallization unit 4, or from the separation unit 41, back to the crystallizing unit 4
35		

	42	lithium precipitation unit
	421	slurry line for carrying a reacted slurry from the crystallization unit 4, or the separation unit 41, to the lithium precipitation unit 42
5	422	feed inlet for supplying carbon dioxide or an alkali metal carbonate to the precipitation unit 42
	43	solid-liquid separation unit
	431	recycle line for carrying a solution from the precipitation unit 42, or the separation unit 43, to the pulping unit 1
10	432	recycle line for carrying a solution from the precipitation unit 42, or the separation unit 43, to the first leaching unit 2
	434	recycle line for carrying a solid fraction from the lithium precipitation unit 42, or the separation unit 43, to the conversion unit 44
15	44	conversion unit
	344	inlet for supplying the conversion unit with alkali earth metal hydroxide or an aqueous slurry thereof
20	443	recycle line for carrying slurry from the conversion unit 44 to the second leaching unit 3 or the separation unit 31
	45	purification or washing unit
	451	feed inlet for supplying washing solution to the purification or washing unit 45
25	452	recycle line for carrying spent washing solution to the upstream purification unit 32, or to an optional regeneration unit 33
	46	solid-liquid separation unit
30	464	recycle line for carrying spent solution from purification unit 45 or the separation unit 46 to the crystallization unit 4
	465	recycle line for carrying spent solution from purification unit 45 or the separation unit 46 to the purification or washing unit 45
35	47	drying unit

471 product outlet for crystallized and optionally purified
and dried lithium hydroxide monohydrate

5 It will be obvious to a person skilled in the art that, as the technology advances, the inventive concept can be implemented in various ways. The invention and its embodiments are not limited to the examples described above but may vary within the scope of the claims.

10 EXAMPLES

EXAMPLE 1

The soda leaching was carried out on a slurry containing lithium, and obtained by pulping a beta-spodumene mineral sample. The leaching was performed in an autoclave with the presence of high-pressure steam and at a
15 temperature of 220°C with a retention time of 1.5 h, with an initial solids content of 29.5 wt-%, a sodium to lithium excess in the feed of 10%, giving a pH of about 11.5.

The solids were separated from the obtained leached solution through filtration, and the obtained solid fraction was carried to a second leaching vessel, where leaching tests were carried out as shown in the following
20 Table 1:

Table 1

Test	Time h	Temperature °C	pH	Li mg/L	Na mg/L	Al mg/L	Ca mg/L	Mn mg/L	Mg mg/L	P mg/L	K mg/L	Fe mg/L	Si mg/L	B mg/L	Be mg/L	S mg/L	Ti mg/L	Bi mg/L
CL1	1	38	10.9	6610	630	51	11	<1	<1	<50	30	<2	161	<2	<1	<20	<1	<5
CL1	2	35	10.9	6820	687	77	11	<1	<1	<50	31	<2	169	<2	<1	<20	<1	<5
CL2	1	22	11.4	6840	528	<5	34	<1	<1	<50	22	<2	16	<2	<1	<20	<1	<5
CL2	2	22	11.4	6870	528	8	25	<1	<1	<50	23	<2	26	<2	<1	<20	<1	<5

These tests showed that the used ~10% Ca(OH)₂ excess to lithium content was sufficient to provide the desired

end-result, i.e. a lithium hydroxide solution with a low content of impurities. Also the temperature of 20-40°C was sufficient. The lower temperature of 22°C produced a more pure solution in general, particularly in relation to the content of aluminium and silicon. Further, the aluminium and the silicon are efficiently reduced with the help of the recycling steps of the present invention.

The calcium concentration in the solution was higher at this lower temperature compared to the concentration achieved at the higher temperatures.

EXAMPLE 2

The LiOH production process was carried out as a bench scale pilot according to the flow sheet shown in Fig. 3 (without the recycling line 432). The purification step 32 was performed with selective cation exchange. The raw material was a calcined beta-spodumene concentrate, with 6.5 % Li₂O concentration. In the second leaching step 3, the solid residue obtained after S/L separation 31 contained mainly analcime and calcium carbonate, and had an average Li concentration of 0.2 %, which corresponded to a Li extraction of 91 %. High purity LiOH·H₂O crystals were produced with a single crystallization

stage. With the flow sheet shown in Fig. 3 (without the recycling line 432), the average impurity profile of the product crystals is shown in Table 2. From Table 2 it can be seen that low Al and Ca contents can be achieved due to selective cation exchange purification and applied circulation of solutions.

Table 2: Impurity analysis of product LiOH·H₂O crystals

Al	Cr	Mn	Ni	Cu	Cd	Pb	Be	B	Na	Mg	P	K	Ca	Ti	Fe	Zn	Bi	SO ₄	C	Cl ⁻
ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	%
<20	<1	<1	<1	<1	<1	<1	<10	<5	<200	<1	<10	<50	<5	<10	<1	<5	<20	<10	<0.2	<0.005

CLAIMS

1. A method for recovering lithium hydroxide from a mineral containing lithium, selected from spodumene, petalite or lepidolite or mixtures thereof, wherein the method comprises
- 5
- pulping the raw material containing lithium in the presence of water and an alkali metal carbonate for producing a first slurry containing lithium,
 - leaching the first slurry containing lithium in a first leaching step at an elevated temperature for producing a second slurry containing lithium carbonate,

10

 - leaching the second slurry or a fraction thereof in a second leaching step in an aqueous solution containing an alkali earth metal hydroxide for producing a third slurry containing lithium hydroxide,
 - separating the third slurry into solids and a solution containing lithium hydroxide by solid-liquid separation and purifying the obtained solution, thus providing a purified solution containing lithium hydroxide, and

15

 - recovering lithium hydroxide monohydrate by crystallising from the purified solution containing lithium hydroxide, and
 - separating the solution obtained during the crystallization from the process, and recycling it to one or more of the previous process steps, or back to the crystallization.

20
2. The method according to claim 1, wherein the raw material used in the pulping step is a lithium-containing mineral in calcined form, preferably obtained by heat treating the raw material, more preferably by using a temperature of approximately 1050°C.
- 25
3. The method according to claim 1 or 2, wherein the mineral raw material used in the pulping step is spodumene, preferably beta-spodumene.
- 30
4. The method according to any preceding claim, wherein at least a fraction of the water and alkali metal carbonate carried to the pulping step is a recycled aqueous solution containing said alkali metal carbonate.
- 35
5. The method according to any preceding claim, wherein the alkali metal carbonate used in the pulping step is selected from sodium and potassium carbonate, preferably being at least partly composed of sodium carbonate.

6. The method according to any preceding claim, wherein the first leaching step is carried out at a temperature of 160 to 250°C, preferably at a temperature of 200 to 220°C.
- 5 7. The method according to any preceding claim, wherein the first leaching step is carried out at a pressure of 10 to 30bar, preferably 15 to 25bar.
8. The method according to any preceding claim, wherein suitable conditions are achieved for the first leaching step using high-pressure steam.
- 10 9. The method according to any preceding claim, wherein the solution is separated from the solids after the first leaching step in a separate solid-liquid separation step, and the solids are carried to the second leaching step.
- 15 10. The method according to any preceding claim, wherein the solution is separated from the solids after the first leaching step, and the solution is recycled to one or more of the preceding steps.
11. The method according to any one of the preceding claims, wherein the solution
20 is separated from the solids after the first leaching step, and the solution is recycled either to the pulping step or to the first leaching step, or a fraction to each.
12. The method according to claim 11, wherein the solution is recycled to the pulping step.
- 25 13. The method according to any one of the preceding claims, wherein the alkali earth metal hydroxide used in the second leaching step is selected from calcium and barium hydroxide, preferably being calcium hydroxide.
- 30 14. The method according to any one of the preceding claims, wherein the alkali earth metal hydroxide used in the second leaching step is mixed with water or an aqueous solution prior to addition to the second leaching step.
- 35 15. The method according to any one of the preceding claims, wherein at least a fraction of the solution separated from the solids in the solid-liquid separation of the third slurry is added to said second leaching step in the form of a recycled solution, preferably mixed with fresh alkali earth metal hydroxide prior to addition to

the second leaching step, more preferably mixed with fresh alkali earth metal hydroxide in a separate slurring step.

16. The method according to any one of the preceding claims, wherein the second
5 leaching step is carried out at a temperature of 10-100°C, preferably 20-60°C, and most suitably 20-40°C.

17. The method according to any one of the preceding claims, wherein the second
10 leaching step is carried out at atmospheric pressure.

18. The method according to any one of the preceding claims, wherein the step of
purifying the solution obtained from the third slurry includes a purification based on
the purification of dissolved ions and components, preferably an ion exchange or a
membrane separation, or both.

19. The method according to any one of the preceding claims, wherein the step of
purifying the solution obtained from the third slurry is carried out by an ion ex-
change, preferably carried out by using a cation exchange resin, particularly a se-
lective cation exchange resin.

20. The method according to claim 19, wherein the ion exchange is carried out at
least partly using a purification resin that has been regenerated in a separate re-
generation step, which regenerated resin typically is recycled back to the ion ex-
change.

21. The method according to claim 20, wherein the regeneration step is carried
out using a recycled solution from a subsequent process step, preferably being the
separated solution obtained from the crystallization, or from a subsequent washing
step.

22. The method according to any one of claim 1 to 18, wherein the step of purify-
ing the solution obtained from the third slurry is carried out by membrane separa-
tion, whereby the membrane separation yields a purified stream, which is carried
to the crystallization step, and a recycle stream, which preferably is carried to the
35 second leaching step.

23. The method according to any one of claims 1 to 18, wherein the step of purify-
ing the solution obtained from the third slurry is carried out by first performing a

membrane separation, and by carrying the thus purified solution to an ion exchange step, for further purification.

24. The method according to any one of the preceding claims, wherein the crystallising of the lithium hydroxide monohydrate is performed by heating the purified solution containing lithium to a temperature of approximately the boiling point of the solution.

25. The method according to any one of the preceding claims, wherein the crystallising of the lithium hydroxide monohydrate is performed in two or more crystallization units, preferably being sequentially arranged.

26. The method according to any one of the preceding claims, wherein the purified solution containing lithium hydroxide is mixed with one or more solutions recycled from subsequent steps of the method before being carried to the crystallization step, or they are all fed separately to the crystallization step.

27. The method according to any one of claims 1 to 26, wherein at least a fraction of the solution separated from the crystallization step is recycled to a preceding step with lower alkalinity.

28. The method according to any one of claims 1 to 26, wherein at least a fraction of the solution separated from the crystallization step is recycled to the second leaching step, and optionally a further fraction to the pulping step.

29. The method according to any one of claims 1 to 26, wherein at least a fraction of the solution separated from the crystallization step is carried to a lithium precipitation step, which preferably is carried out as a carbonation, wherein the solution is reacted with either carbon dioxide or an alkali metal carbonate in order to form a lithium carbonate slurry.

30. The method according to claim 29, wherein the lithium carbonate slurry is subjected to a solid-liquid separation step, from which at least a fraction of the solids is carried to a conversion step, wherein the solids are mixed with an alkali earth metal slurry, the conversion step preferably performed at a temperature close to the boiling point of the solution used in the conversion step, typically being an aqueous solution, more preferably at a temperature of 90 to 100 °C, whereby the lithium carbonate of the solids is solubilized at least partly as lithium hydroxide.

31. The method according to claim 29 or 30, wherein the carbonate slurry is subjected to a solid-liquid separation step, from which at least a fraction of the solids is carried to a conversion step, and then recycled to the solid-liquid separation
5 step following the second leaching step.

32. The method according to claim 29, wherein the lithium carbonate slurry is subjected to a solid-liquid separation step, from which at least a fraction of the formed solution is recycled to the pulping step, or to the first leaching step, or a fraction to
10 each, preferably at least a fraction to the pulping step.

33. The method according to any one of claims 1 to 26, wherein at least a fraction of the solution separated from the crystallization step is recycled back to the crystallization step.
15

34. The method according to any one of the preceding claims, wherein the solids obtained in the crystallization step, containing crystals of lithium hydroxide monohydrate, are purified using a washing solution before recovery as the product.

20 35. The method according to claim 34, wherein the purified crystals of lithium hydroxide monohydrate are separated from the washing solution, are dried, and thereafter recovered.

36. The method according to claim 34, wherein the spent washing solution is separated from the purified crystals of lithium hydroxide monohydrate, and is recycled
25 to the crystal washing step or to the step of purifying the solution separated from the third slurry or to a regeneration step preceding said purification step, or to the crystallization step, or a fraction of the spent washing solution is recycled to two or more of these steps.

30

37. An arrangement for recovering lithium carbonate from a raw material containing lithium according to the method of any one of claims 1 to 36, which arrangement comprises

- 35 – a pulping unit (1) for pulping the raw material containing lithium in the presence of water and an alkali metal carbonate,
- a first leaching unit (2) for leaching a first slurry containing lithium at an elevated temperature,

- a second leaching unit (3) for leaching a second slurry containing lithium carbonate, or a fraction thereof, in the presence of water and an alkali earth metal hydroxide,
- a solid-liquid-separation unit (31) for separating a third slurry containing lithium hydroxide into solids and a solution containing lithium hydroxide,
- a purification unit (32) connected to the solid-liquid-separation unit (31), for purifying the solution obtained from said separation unit (31), and
- a crystallising unit (4) for recovering lithium hydroxide monohydrate from a solution containing lithium,
 - which further comprises a line (403,414) for carrying a solution from the crystallizing unit (4) to a point further upstream of the crystallization unit (4), or back to the crystallization unit (4).

38. The arrangement according to claim 37, which further comprises a calcination unit (10) for heat treating the raw material intended to be carried to the pulping unit (1).

39. The arrangement according to claim 37 or 38, wherein the pulping unit (1) contains a feed inlet (101) for supplying the raw material containing lithium to the unit (1).

40. The arrangement according to any of claims 37 to 39, which includes an inlet (111) in connection with the pulping unit (1) for carrying a recycled aqueous solution containing alkali metal carbonate to the pulping unit (1).

41. The arrangement according to any of claims 37 to 40, wherein the first leaching unit (2) is an autoclave.

42. The arrangement according to any of claims 37 to 41, wherein the first leaching unit (2) is connected to the pulping unit (1) via a slurry line (102).

43. The arrangement according to any of claims 37 to 42, wherein a solid-liquid separation unit (21) is arranged between the first leaching unit (2) and the second leaching unit (3).

44. The arrangement according to any of claims 37 to 43, which includes a recycle line (211,212) leading from the first leaching unit (2), or from the liquid section of a

solid-liquid separation unit (21) connected to said first leaching unit (2), to a unit upstream from said first leaching unit (2).

45. The arrangement according to any of claims 37 to 43, which includes a recycle line (211,212) leading from the first leaching unit (2), or from the liquid section of a solid-liquid separation unit (21) placed in connection with said first leaching unit (2), either as line (211) to the pulping unit (1) or as line (212) to the first leaching unit (2), or a separate line (211) and (212) to each.

46. The arrangement according to any of claims 37 to 43, which includes a recycle line (211) leading from the first leaching unit (2), or from the liquid section of a solid-liquid separation unit (21) connected to said first leaching unit (2), to the pulping unit (1).

47. The arrangement according to any of claims 37 to 46, wherein the second leaching unit (3) is a tank reactor, preferably a stirred tank reactor.

48. The arrangement according to any of claims 37 to 47, wherein the second leaching unit (3) includes an inlet (303) for alkali earth metal hydroxide or an aqueous slurry thereof.

49. The arrangement according to any of claims 37 to 47, wherein the second leaching unit (3) is connected to a slurring unit (30) for mixing an alkali earth metal hydroxide into an aqueous slurry.

50. The arrangement according to any of claims 37 to 49, wherein the second leaching unit (3) is connected to the first leaching unit (2), or to a downstream solid-liquid separation unit (21), via a slurry line (203).

51. The arrangement according to any of claims 37 to 50, which purification unit (32) includes an ion exchange unit or a membrane separation unit, preferably a cation exchange unit, particularly containing a selective cation exchange resin.

52. The arrangement according to any of claims 37 to 51, wherein the purification unit (32) is an ion exchange unit, and is connected to a regeneration unit (33) for regenerating a purification resin, and wherein a line (332) is typically connected between the purification unit (32) and the regeneration unit (33), for recycling regenerated resin back to the ion exchange unit.

53. The arrangement according to any of claims 37 to 51, wherein the purification unit (32) is a membrane separation unit, which is connected both to the crystallization unit (4), by feeding the crystallization unit (4) with purified solution, and to the second leaching unit (3), via recycle line (323), for returning a recycle stream to the leaching step.

54. The arrangement according to any of claims 37 to 51, wherein the purification unit (32) is a combination of a membrane separation unit and an ion exchange unit, wherein the membrane separation unit has an outlet that is connected to an inlet of the ion exchange unit.

55. The arrangement according to any of claims 37 to 54, which includes two or more crystallization units (4), preferably being sequentially arranged.

56. The arrangement according to any of claims 37 to 55, wherein the crystallization unit (4), or a downstream purification unit (32) or a downstream regeneration unit (33), is connected to the second leaching unit (3), or the downstream solid-liquid separation unit (31) via liquid line (304).

57. The arrangement according to any one of claims 37 to 56, which comprises solid-liquid separation unit (41) connected to the crystallization unit (4) for separating the crystals obtained in the crystallization unit (4) from the spent solution.

58. The arrangement according to any one of claims 37 to 57, which comprises a recycle line (403,414) arranged between the crystallizing unit (4), and/or the liquid section of the solid-liquid separation unit (41) connected to the crystallization unit (4), and an upstream unit.

59. The arrangement according to any one of claims 37 to 58, which comprises a recycle line (403) arranged between the crystallizing unit (4), and/or the liquid section of the solid-liquid separation unit (41) connected to the crystallization unit (4), and the second leaching unit (3), and optionally a further line arranged between the crystallization unit (4), and/or the liquid section of the solid-liquid separation unit (41) connected to the crystallization unit (4), and the pulping unit (1).

60. The arrangement according to any one of claims 37 to 59, which comprises a lithium precipitation unit (42) connected to the crystallization unit (4) or the solid-liquid separation unit (41) through a line (421).

5 61. The arrangement according to claim 60, wherein the lithium precipitation unit (42) includes a feed inlet (422) for feeding carbon dioxide or an alkali metal carbonate to the unit (42).

10 62. The arrangement according to any one of claims 60 to 61, which includes a solid-liquid separation unit (43) connected to and downstream from the lithium precipitation unit (42).

15 63. The arrangement according to any one of claims 60 to 62, wherein the lithium precipitation unit (42), and/or a solid section of a solid-liquid separation unit (43) connected to said lithium precipitation unit (42), is connected via a recycle line (434) to a conversion unit (44), whereby at least a fraction of the solids obtained in the separation unit (43) can be recycled to the conversion unit (44) for solubilization.

20 64. The arrangement according to claim 63, wherein the conversion unit (44) contains an inlet (344) for alkali earth metal hydroxide or an aqueous slurry thereof.

25 65. The arrangement according to claim 63 or 64, wherein the conversion unit (44) is connected to a slurring unit (30) for mixing an alkali earth metal hydroxide into an aqueous slurry, and from which slurry can be fed to the conversion unit (44).

30 66. The arrangement according to claim 63, wherein the conversion unit (44) is connected via line (443) to the second leaching unit (3), and/or to the solid-liquid separation unit (31) connected to the second leaching unit (3).

67. The arrangement according to claim 62, wherein the liquid section of the solid-liquid separation unit (43) is connected via line (431) to the pulping unit (1), whereby at least a fraction of the solution obtained in the separation unit (43) can be recycled to said pulping unit (1).

68. The arrangement according to claim 62, wherein the liquid section of the solid-liquid separation unit (43) is connected via a further recycle line (432) to the first

leaching unit (2), whereby at least a fraction of the solution obtained in the separation unit (43) can be recycled to said first leaching unit (2).

69. The arrangement according to any of claims 56 to 58, wherein the liquid section of the solid-liquid separation unit (41) is connected to the crystallization unit (4) via recycle line (414), for recycling the spent solution separated from the crystallization step back to the crystallization unit (4).

70. The arrangement according to any of claims 37 to 69, which includes a purification unit (45) connected to the crystallization unit (4), and/or to a solid-liquid separation unit (41) connected to the crystallization unit (4), wherein the solids obtained in the crystallization step can be purified.

71. The arrangement according to claim 70, wherein the purification unit (45) includes a feed inlet (451) for feeding a washing solution into the purification unit (45).

72. The arrangement according to claim 70 or 71, which includes a solid-liquid separation unit (46) connected to and downstream from the purification unit (45), for separating the purified crystals of lithium hydroxide monohydrate from the spent washing solution.

73. The arrangement according to any of claims 70 to 72, wherein the purification unit (45), or a solid-liquid separation unit (46) connected to and downstream from the purification unit (45) is connected via a recycle line (452) to the upstream purification unit (32) or to an optional regeneration unit (33) connected to said purification unit (32).

74. The arrangement according to any of claims 70 to 72, wherein a solid-liquid separation unit (46) connected to and downstream from the purification unit (45) is connected via a recycle line (464) to the crystallization unit (4).

75. The arrangement according to any of claims 70 to 72, wherein a solid-liquid separation unit (46) connected to and downstream from the purification unit (45) is connected via a recycle line (465) to the purification unit (45).

76. The arrangement according to any of claims 37 to 55, which comprises a combined purification unit (41,45,46) for purifying the crystals obtained in the crystalli-

zation unit (4) from the spent solution, and separating the purified crystals from the spent washing solution.

5 77. The arrangement according to claim 76, wherein the combined purification unit (41,45,46) is connected to the crystallization unit (4) via recycle line (414), for recycling the spent solution separated from the crystallization step back to the crystallization unit (4).

10 78. The arrangement according to claim 76, wherein the combined purification unit (41,45,46) includes a feed inlet (451) for feeding a washing solution into the unit (41,45,46).

15 79. The arrangement according to claim 76, wherein the combined purification unit (41,45,46) is connected via a recycle line (452) to the upstream purification unit (32), or to a separate regeneration unit (33).

80. The arrangement according to claim 76, wherein the combined purification unit (41,45,46) is connected via a recycle line (464) to the crystallization unit (4).

20 81. The arrangement according to claim 76, wherein a solids section of the combined purification unit (41,45,46) is connected via a recycle line (465) to the liquid section of the same combined unit (41,45,46).

25 82. The arrangement according to any of claims 37 to 81, which includes a drying unit (47), connected to the crystallization unit (4), or connected to a solids section of a solid-liquid separation unit (41,46) downstream from the crystallization unit (4), or to a solids section of a combined purification and separation unit (41,45,46) downstream from the crystallization unit (4), in which drying unit (47) the obtained crystals of lithium hydroxide monohydrate can be dried.

30

83. The arrangement according to claim 82, wherein the drying unit (47) includes a product outlet (471) through which the final product can be recovered.




Fig. 1




Fig. 2

Fig. 3





Fig. 4



INTERNATIONAL SEARCH REPORT

International application No
PCT/FI2019/050275

A. CLASSIFICATION OF SUBJECT MATTER
INV. C01D15/02 C01D15/08 C22B26/12
ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
C01D C22B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 3 343 910 A (MAURICE ARCHAMBAULT ET AL) 26 September 1967 (1967-09-26) column 2, lines 18-50 example A column 6, lines 4-18 claims	1-83
X	CA 2 822 196 A1 (SICHUAN TIANQI LITHIUM IND INC [CN]) 28 June 2012 (2012-06-28) page 1 "2. Beta-spodumene sodium carbonate pressure extraction method" ----- -/-	1-83



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

5 July 2019

Date of mailing of the international search report

12/07/2019

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Besana, Sonia

INTERNATIONAL SEARCH REPORT

International application No
PCT/FI2019/050275

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	YA CHEN ET AL: "Preparation of lithium carbonate from spodumene by a sodium carbonate autoclave process", HYDROMETALLURGY, ELSEVIER SCIENTIFIC PUBLISHING CY. AMSTERDAM, NL, vol. 109, no. 1, 14 May 2011 (2011-05-14), pages 43-46, XP028267179, ISSN: 0304-386X, DOI: 10.1016/J.HYDROMET.2011.05.006 [retrieved on 2011-05-20] the whole document -----	1-83

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/FI2019/050275

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 3343910	A	26-09-1967	BE 627542 A	05-07-2019
			GB 1052747 A	05-07-2019
			US 3343910 A	26-09-1967

CA 2822196	A1	28-06-2012	CA 2822196 A1	28-06-2012
			CN 102020294 A	20-04-2011
			WO 2012083677 A1	28-06-2012
