



(51) International Patent Classification:

C08F 283/01 (2006.01) **H01F 27/32** (2006.01)
C08L 67/06 (2006.01) **H01F 41/12** (2006.01)
C09D 167/06 (2006.01) **H02K 3/30** (2006.01)
H01B 3/42 (2006.01)

(21) International Application Number:

PCT/US2010/062316

(22) International Filing Date:

29 December 2010 (29.12.2010)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

61/291,128 30 December 2009 (30.12.2009) US

(71) Applicant (for all designated States except US): **E. I. DU PONT DE NEMOURS AND COMPANY** [US/US]; 1007 Market Street, Wilmington, Delaware 19898 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **HERM, Michael** [DE/DE]; Schubertstrasse 33, 42553 Velbert (DE). **BOEHM, Frank-Rainer** [DE/DE]; Kleiner Kamp 8, 51519 Odenthal (DE). **RICHTER, Anja** [DE/DE]; Wuppertal (DE). **GRUENE DE JONG, Ulrike** [DE/DE]; Krummacher Strasse 163, 42115 Wuppertal (DE). **TRAPPMANN, Barbara** [DE/DE]; Dusseldorf (DE). **RITTINGHAUS, Volker** [DE/DE]; Stahlsberg 47, 42279 Wuppertal (DE).

(74) Agent: **MYERS, Brian, J.**; E. I. du Pont de Nemours and Company, Legal Patent Records Center, 4417 Lancaster Pike, Wilmington, Delaware 19805 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: COMPOSITION FOR FIXING WOUND ITEMS

(57) Abstract: The invention provides a composition for fixing wound items comprising A) 5 to 90 wt% of at least one α , β -unsaturated polyester resin based on at least one unsaturated mono-, di- or tricarboxylic acids and/or mono-, di- or tricarboxylic acid group containing molecules, at least one polyol, at least one acrylic or methacrylic group containing component, B) 2 to 80 wt% of at least one monomeric and/or oligomeric ethylenically unsaturated component having a vapour pressure in a range of 0 to 1 mbar at 20C, preferred 0 to 0.5 mbar at 20C, C) 0.1 to 40 wt% of at least one monomeric and/or oligomeric unsaturated component different from B) having a vapour pressure in a range of 0 to 10 mbar at 20C, preferred 0 to 5 mbar at 20C, D) 0 to 15 wt% of at least one customary additive, and E) 0 to 30 wt% of at least one monomer and/or polymer containing epoxy or glycidyl ether or ester moieties, the wt% being based on the total weight of the composition. The composition of the present invention provides low curing emissions, low viscosities and excellent impregnation properties. After curing, these impregnation materials show high mechanical toughness levels even at elevated temperatures.



Title of the Invention

Composition for Fixing Wound Items

5

Field of the Invention

The present invention refers to a composition for fixing wound items, in particular electrical windings in electrical equipment providing
10 excellent impregnation properties into the wound items as well as extraordinarily good mechanical toughness, especially at high temperatures.

Background of the Invention

The use of unsaturated polymers in compositions suitable for
15 impregnating (e.g. by techniques of immersion, dipping, trickling or casting) wound items such as electrical coils and windings, especially windings of magnet wires in electrical devices as well as for casting of electrical devices such as stators, rotors and transformers, for mechanical toughening and fixing, is well known in the art. Various resins can be used
20 for those applications, which typically provide electrical insulation, stabilization of the electrical winding against vibrations, improved aging behaviour and protection against chemical and mechanical impact. As downsizing and efficiency increase of electrical devices is a more and more important topic, the operating temperatures of especially electrical
25 motors become higher. Impregnating materials which are used in motors with high operating temperatures have to be chemically stable at the operating temperatures and also mechanically tough to withstand mechanical forces and/or impact at these elevated temperatures.

Impregnation materials based on unsaturated polyesters dissolved
30 in styrene typically show good mechanical toughness, also at elevated temperatures. They have low viscosities, so impregnation quality is typically not an issue. However, such systems show a strong loss of styrene upon curing of the impregnation material, resulting in a significant

amount of volatile organic compounds (VOC). Therefore, there is a strong demand for mechanically tough impregnation materials with low to zero emissions.

5 Mechanical properties can e.g. be improved using fillers, however, impregnation materials containing such fillers are typically not very homogeneous. This could cause problems regarding storage conditions of the composition and can additionally lead to failure of the penetration into the cavities of electrical windings as well as to failure of the impregnation during operation of the electrical device.

10 Also, mechanical properties can be improved using binder resins with higher molecular weights and / or rigid polymer building blocks. Especially useful are building blocks which contain rigid ring structures, e.g. di- or polycyclopentadiene as described in DE-A 3107450, EP-A 101585, EP-A 871677, EP-A 963413 or EP-A 968501. However, the
15 viscosities of such impregnation materials (especially in low or zero VOC diluents) are typically high, so that the application process becomes more difficult than with standard impregnation materials, e.g. heat has to be applied. This increases the danger of premature curing of the impregnating material. Furthermore, a good impregnation quality with
20 excellent penetration of the impregnation material into the device's magnet wire windings is much more difficult to achieve if the impregnation material has a high viscosity.

Summary of the Invention

The invention provides a composition for fixing wound items
25 comprising

A) 5 to 90 wt% of at least one α , β -unsaturated polyester resin based on at least one unsaturated mono-, di- or tricarboxylic acids and/or mono-, di- or tricarboxylic acid group containing molecules, at least one polyol, at least one acrylic or methacrylic group containing
30 component,

- B) 2 to 80 wt% of at least one monomeric and/or oligomeric ethylenically unsaturated component having a vapour pressure in a range of 0 to 1 mbar at 20°C, preferred 0 to 0.5 mbar at 20°C,
- C) 0.1 to 40 wt% of at least one monomeric and/or oligomeric unsaturated component different from B) having a vapour pressure in a range of 0 to 10 mbar at 20°C, preferred 0 to 5 mbar at 20°C,
- D) 0 to 15 wt% of at least one customary additive, and
- E) 0 to 30 wt% of at least one monomer and/or polymer containing epoxy or glycidyl ether or ester moieties,
- the wt% being based on the total weight of the composition.

The composition of the present invention provides low curing emissions, low viscosities and excellent impregnation properties into the wound items. After curing, these impregnation materials show high mechanical toughness levels even at elevated temperatures.

Detailed Description

The features and advantages of the present invention will be more readily understood, by those of ordinary skill in the art, from reading the following detailed description. It is to be appreciated those certain features of the invention, which are, for clarity, described above and below in the context of separate embodiments, may also be provided in combination in a single embodiment. Conversely, various features of the invention that are, for brevity, described in the context of a single embodiment, may also be provided separately or in any sub-combination. In addition, references in the singular may also include the plural (for example, "a" and "an" may refer to one, or one or more) unless the context specifically states otherwise.

The slight variations above and below the stated ranges of numerical values can be used to achieve substantially the same results as values within the ranges. Also, the disclosure of these ranges is intended as a

continuous range including every value between the minimum and maximum values.

The term "typical" means "known to a person skilled in the art".

5 All the number average molar mass data stated in the present description are determined or to be determined by gel permeation chromatography (GPC; divinylbenzene-cross-linked polystyrene as the immobile phase, tetrahydrofuran as the liquid phase, polystyrene standards, according to DIN 55672).

10 The term (meth)acryl refers to acryl and/or methacryl in this document.

The composition according to the invention comprises at least one α , β -unsaturated polyester resin as component A) in a range of 5 to 90 wt%, preferably 10 to 75 wt%, particularly preferred are 15 to 70 wt%, the wt% being based on the total weight of the composition.

15 The at least one polyester resin of A) may comprise also at least one α , β -unsaturated polyester imide resin comprising at least one imide having 5-membered cyclic imide moieties.


20 The polyester resin of component A) may have a hydroxyl value of 0 to 120 mg KOH/g, preferably 0 to 80, an acid value of 0 to 70 mg KOH/g, preferably 0 to 50 mg KOH/g, as well as a urethane group concentration of 0 to 0.1 mol per 100g resin A).

The acid value is defined as the number of mg of potassium hydroxide (KOH) required to neutralise the carboxylic groups of 1 g of the resin, according to DIN EN ISO 2114.

25 The term hydroxyl value in this description is defined as the number of mg of potassium hydroxide (KOH) which is equal to the number of mg acetic acid for acetalizing of 1 g of the resin, determined according to DIN 53240.


The polyester component A) can be obtained by reaction of

- (a) at least one α , β - ethylenically unsaturated dicarboxylic acid, its anhydride and/or an ester of the α , β - ethylenically unsaturated dicarboxylic acid, and
- (b) at least one alcohol having one or more, preferably 2, 3 or 4, hydroxyl functionalities per molecule, and,
- (c) in case of a polyester imide, at least one imide group containing substance with the formula




(Formula 1)

or



(Formula 2)

or



(Formula 3)

in which

- R_1 is an aliphatic, cycloaliphatic or aromatic moiety in which the carbonyl groups in R_1 are in a 1,2-position and that contains at least one further reactive carboxyl or hydroxyl group or a C=C double bond or combinations thereof,
- R_2 is an aliphatic, aromatic or cycloaliphatic moiety with 2 to 20 carbon atoms that may also contain oxygen or nitrogen atoms,

R_3 is an aliphatic, cycloaliphatic or aromatic moiety in which at least 2 of 4 carbonyl groups in R_3 are in a 1,2-position, and X is a hydroxyl or carboxy functionality, and

- (d) at least one component which is chemically bound into the resin and which contains at least one (meth)acrylic double bond, and
- (e) possibly one or more mono, di- or tricarboxylic acids which are different from (a), and
- (f) possibly one or more polyether polyols, polyolefinic polyols or polymeric polyols which are different from b), and
- (g) possibly one or more polyisocyanates.

The ratio of the reaction components (a) to (g) is chosen in such a way, known to a person skilled in the art, that 100g of component A) contain 0.05 to 0.50 mol of polymerizable, α , β - ethylenically unsaturated groups from component (a), in case of a polyester imide the amount of imidically bonded nitrogen in A) is at least 0.5 wt%, preferably at least 1.5 wt% on the resin, and the ratio of the reaction components (a) to (g) is chosen in such amounts that the aforementioned hydroxyl value, acid value and urethane group concentration are achieved, as known by a person skilled in the art. The number average molecular mass (M_n) of component A) is in a range of, for example, 400 to 8000 g/mol, preferably in a range of 500 to 5000 g/mol.

Typical α , β - ethylenically unsaturated dicarboxylic acids (a) are, for example, those with 4 or 5 carbon atoms, or their anhydrides or esters. Examples are maleic anhydride, fumaric acid, itaconic acid or anhydride, methylene malonic acid, citraconic anhydride or mesaconic acid. Preferably, maleic anhydride and fumaric acid are used.

Typical alcohols of (b) are, for example, mono-, di- or trifunctional alcohols with 2 to 18 carbon atoms like 8(9)-hydroxytricyclo[5.2.1.0^{2,6}]dec-3-en, 1,4-bis-hydroxymethyl cyclohexane, 2,2-bis-(4-hydroxycyclohexyl)-propane, ethylene glycol, propylene glycol, 1,3-propane diol, neopentyl glycol (NPG), trimethylol propane (TMP), glycerol, tris(hydroxyethyl)isocyanurate (THEIC) and pentaerythritol. The use of

alcohols with a functionality greater than 2 leads to branched structures. Preferred alcohols of (b) are 1,3-propane diol, neopentyl glycol, THEIC and trimethylol propane.

Typical imide group containing moieties (c) are the reaction products of tricarboxylic acids or their anhydrides, like trimellitic anhydride, 3,3',4-benzophenone tricarboxylic acid anhydride, tricarballic acid or unsaturated cycloaliphatic, aromatic or aliphatic dicarboxylic acid anhydrides like tetrahydrophthalic anhydride, hexahydrophthalic anhydride, phthalic anhydride, *endo*-methylene tetrahydrophthalic anhydride or maleic anhydride with aliphatic, cycloaliphatic, heterocyclic or aromatic aminoalcohols or aminocarboxylic acids. Appropriate aminoalcohols are e.g. ethanolamine, propanolamine, butanolamine, their higher homologues, 4-aminocyclohexanol, 4-aminobenzyl alcohol or aromatically amino-substituted phenyl ether alcohols. Suitable aminocarboxylic acids are e.g. aminoacetic acid, aminopropionic acid, aminocaproic acid and 4-aminobenzoic acid.

Further examples for substances (c) are reaction products of tetracarboxylic acids or their anhydrides like pyromellitic anhydride, benzophenone tetracarboxylic acid dianhydride, butane tetracarboxylic acid dianhydride, cyclopentane tetracarboxylic acid dianhydride with aliphatic, cycloaliphatic, heterocyclic or aromatic aminoalcohols or aminocarboxylic acids, and/or reaction products of 2 mols of tricarboxylic acids or their anhydrides like trimellitic anhydride, tricarballic acid or 3,3',4-benzophenone tricarboxylic acid anhydride with 1 mol aromatic diamines like 4,4'-diamino diphenylmethane, 4,4'-diamino diphenylether or aliphatic and/or cycloaliphatic diamines like 4,4'-diamino dicyclohexylmethane, ethylene diamine, propylene diamine or aliphatic etheramines. Instead of the above mentioned diamines, also the respective diisocyanates can be used. Preferred imide group containing substances (c) are the reaction products of tetrahydrophthalic anhydride or trimellitic anhydride with ethanolamine.

Typical examples for the (meth)acryl functional components (d) are functional polyester (meth)acrylates, functional polyether (meth)acrylates, functional silicone (meth)acrylates, functional (meth)acrylated poly(butadiene) or functional urethane (meth)acrylates, in which the functional group can be, for example, a hydroxy, carboxy, epoxy and/or isocyanate group. Further examples are carboxy (meth)acrylates and their derivatives such as acid halides, hydroxy (meth)acrylates, epoxy (meth)acrylates and amino (meth)acrylates, for example, hydroxybutyl (meth)acrylate, glycidyl (meth)acrylate, trimethylolpropane di(meth)acrylate, pentaerythritol tri(meth)acrylate, (meth)acrylic acid chloride. Preferred are glycidyl (meth)acrylate, (meth)acrylic acid chloride and hydroxyethyl (meth)acrylate.

Typical carboxylic acids (e) different from a) can be saturated and/or unsaturated aliphatic, cycloaliphatic and/or aromatic mono-, di-, tri- and/or tetracarboxylic acids, anhydrides and/or esters, especially alkyl esters having 1 to 4 carbon atoms in the alkyl chain. Examples are dicyclopentadiene dimaleinate, tetrahydrophthalic acid anhydride, *endo*-methylene tetrahydrophthalic anhydride, trimellitic anhydride, terephthalic acid, isophthalic acid, tetrachlorophthalic acid, hexachlorophthalic acid, adipic acid, glutaric acid, sebacic acid, oligo- and/or polymeric fatty acids, carboxyfunctional polyolefins.

Typical examples for (f) different from b) are polyethylene glycol, polypropylene glycol, polytetrahydro furane, reaction products of the addition of ethylene oxide or propylene oxide to polyfunctional alcohols with 2 to 4 hydroxy groups like glycerol, trimethylol ethane, trimethylol propane, triethanolamine or pentaerythritol or with polyfunctional phenols with 2 to 4 hydroxyl groups like catechol, hydroquinone, bisphenol A or bisphenol F, further examples are hydroxyfunctional homo- or copolymers obtained by radical polymerization, hydroxyfunctional polycarbonates or hydroxyfunctional polyester with weight average molar masses between 400 and 10000 g/mol or polyolefinic polyols such as hydroxyfunctional

polymers of ethylene, propylene, butylene, octene, isoprene, butadiene, chloroprene or combinations thereof.

The polyisocyanates (g) are preferably polyisocyanates containing 2 or more isocyanate groups, for example, aliphatic, cycloaliphatic or aromatic diisocyanates with 6 to 18 carbon atoms like 1,6-hexamethylene diisocyanate, 2,4'- and 4,4'-dicyclohexylmethane diisocyanate, 3-isocyanatomethyl-3,5,5-trimethyl cyclohexylisocyanate, 2,2,3- and 2,4,4-trimethyl hexamethylene diisocyanate, cyclohexanone 1,3- and 1,4-diisocyanate, 2,4- and 2,6-toluylene diisocyanate, 2,4'- and 4,4'-diphenylmethane diisocyanate, polyisocyanates that are obtained by reaction of a polyisocyanate with a substoichiometric amount of polyols, or trimerization products of above mentioned polyisocyanates, or products with biuret structures made from above mentioned polyisocyanates, or products with uretdione structures made from above mentioned polyisocyanates. Preferred are aromatic isocyanates like 2,4'- and 4,4'-diphenylmethane diisocyanate and their mixtures.

In case all components (a) to (g) are used the component (g) is preferably used in such an amount that the urethane group content of the unsaturated polyester or polyester imide A) is in the range of 0 to 0,1 mol per 100g of A).

The polyester imides or polyesters A) may be prepared by methods well known to a person skilled in the art, for example, by polyesterification by heating the components, e.g. to temperatures of 120 to 240°C in a melt process under inert gas or in an azeotropic process, possibly in the presence of polyesterification catalysts.

The ratios of the amounts of the components (a) to (g) are chosen in such a way, known to a person skilled in the art, that the number average molar mass of the resulting resin A) is in the range of 400 to 8000 g/mol, preferably 500 to 5000 g/mol.

The composition according to the invention comprises 2 to 80 wt%, preferably 4 to 65 wt%, of at least one monomeric and/or oligomeric ethylenically unsaturated component (B) characterized by ethylenically

unsaturated structures having one or more vinylic or allylic double bonds, which are radically polymerizable. Component (B) has a vapour pressure in a range of 0 to 1 mbar at 20°C, preferred 0 to 0.5 mbar at 20°C.

Examples are phthalic acid diallyl ester, triallyl isocyanurate, diallyl

- 5 bisphenol A, pentaerythritol tri or tetra allyl ether. Component (B) may be also (meth)acrylic acid esters like hydroxyethyl (meth)acrylate, hydroxypropyl (meth)acrylate, phenoxyethyl (meth)acrylate, dicyclopentadiene (meth)acrylate, butane diol di(meth)acrylate, hexane diol (meth)acrylate, dipropylene glycol di(meth)acrylate, trimethylol
- 10 propane di- and tri(meth)acrylate, pentaerythritol di- and tri(meth)acrylate, epoxy resin (meth)acrylates, (meth)acrylates of reaction products of a polyaddition of ethylene or propylene oxide with polyols such as trimethylol propane or pentaerythritol, and (meth)acrylates of oligo(ethylene glycol) or oligo(propylene glycol). Preferred examples for (B) are hexane diol
- 15 dimethacrylate, butane diol dimethacrylate and (meth)acrylates of reaction products of a polyaddition of ethylene oxide with trimethylol propane or mixtures thereof.

- Up to 50 wt%, preferred 0 to 10 wt% of the component (B) can consist of monomers with polymerizable groups like maleic or fumaric bis-
- 20 alkyl esters, in which the alkyl groups contain 1 to 4 carbon atoms, or like mono- or bis-maleic imides (see also DE-A-2040094, DE-A-2719903, DE-A-3247058 and EP-A-0255802).

- The composition according to the invention comprises 0.1 to 40 wt%, preferably 1 to 40 wt%, of at least one monomeric and/or oligomeric
- 25 unsaturated component (C) different from component (B) characterized by ethylenically unsaturated structures having one or more vinylic or allylic double bonds, which are radically polymerizable. Examples are styrene, vinyl toluene, p-methyl styrene, tert.-butyl styrene, divinyl benzene, N-vinyl pyrrolidone, hydroxybutyl vinyl ether, butane diol vinyl ether, triethylene
- 30 glycol divinyl ether, phthalic acid diallyl ester, fumaric acid diallyl ester, triallyl phosphate, triallyl isocyanurate, diallyl benzene, diallyl bisphenol A, pentaerythritol tri or tetra allyl ether. Component (C) may be also

(meth)acrylic acid esters like hydroxyethyl (meth)acrylate, hydroxypropyl (meth)acrylate, phenoxyethyl (meth)acrylate, dicyclopentadiene (meth)acrylate, butane diol di(meth)acrylate, hexane diol (meth)acrylate, dipropylene glycol di(meth)acrylate, trimethylol propane di- and tri(meth)acrylate, pentaerythritol di- and tri(meth)acrylate, epoxy resin (meth)acrylates, (meth)acrylates of reaction products of a polyaddition of ethylene or propylene oxide with polyols such as trimethylol propane or pentaerythritol, and (meth)acrylates of oligo(ethylene glycol) or oligo(propylene glycol). Preferred examples for (C) are styrene, vinyl toluene, hexane diol dimethacrylate, butane diol dimethacrylate and (meth)acrylates of reaction products of a polyaddition of ethylene oxide with trimethylol propane or mixtures thereof. Component (C) has a vapour pressure in a range of 0 to 10 mbar at 20°C, preferred 0 to 5 mbar at 20°C.

Up to 50 wt.%, preferred 0 to 10 wt.-% of the component (C) can consist of monomers with polymerizable groups like maleic or fumaric bis-alkyl esters, in which the alkyl groups contain 1 to 4 carbon atoms, or like mono- or bis-maleic imides (see also DE-A-2040094, DE-A-2719903, DE-A-3247058 and EP-A-0255802).

The composition according to the invention comprises 0 to 15 wt%, preferably 0 to 10 wt%, more preferably 0.1 to 10 wt%, of at least one customary additive as component (D) which are additives as known to a person skilled in the art, for example, extenders, plasticising components, accelerators, for example metal salts, substituted amines; initiators, for example photo initiators such as chlorine containing photoinitiators, aromatic ketones, hydroxyalkyl phenones, initiators such as peroxides, hydroperoxides, ketone peroxides, heat-responsive initiators such as C-C-labile 1,2-substituted tetraphenyl ethanes having, for example, the formula YPh_2C-CPh_2Y with Ph: phenyl, Y: -OH, -OCH₃, -OC₆H₅, -CH₃, -CN, -NH₂, -Cl or -OSi(CH₃)₃; stabilisers (inhibitors), for example, hydroquinones, quinones, quinone-type inhibitors, phenol-type inhibitors, organic salts of

metals and/or sterically hindered aliphatic or aromatic amines;
alkylphenols, alkylphenol ethers, defoamers and flow control agents.

For the adjustment of special properties like curing speed, surface
hardness and surface smoothness, further polymerizable oligomers,
5 polymers or copolymers can be added, for example, liquid
poly(butadiene)s like (meth)acrylated poly(butadiene),
epoxy(meth)acrylates, urethane (meth)acrylates, polyester
(meth)acrylates, unsaturated polyesters and polyester imides which are
different from (A).

10 Further additives may be fiber-like reinforcement agents like
carbon, glass, polyamide, polyester, polyacrylonitrile, polyaramide,
polyamideimide or polycarbonate fibers or fillers like chalk, talc, aluminium
hydroxide, quartz flour, slate flour, clay or microdolomite; organic and
inorganic pigments, dyes, thixotropy agents and shrinkage reducing
15 agents.

The amount of such additives in the composition is depending on
the respective application, and is known to a person skilled in the art.

The composition according to the invention comprises 0 to 30 wt%,
preferably 0 to 20 wt%, more preferably 0.1 to 20 wt%, of at least one
20 monomer and/or polymer containing epoxy or glycidyl ether or ester
moieties as component (E), comprising monomers or polymers containing
epoxy or glycidyl ether or ester moieties such as bisphenol A
diglycidylether, bisphenol F diglycidylether and/or the appropriate
oligomers and polymers, glycidol, aliphatic and/or aromatic epoxides such
25 as styrene oxide, glycidyl methacrylate, versatic acid glycidyl ester,
epoxidized poly(butadiene)s, poly(chloroprenes) and poly(isoprenes).

The components (A), (B), (C), (D) and (E) of the composition
according to the invention may be mixed as readily prepared materials in
any sequence. The components (A), (B) and/or D) and/or (E) may also be
30 dissolved in (C) and afterwards mixed together, and the components (A),
(C) and/or (D) and/or (E) may also be dissolved in (B) and afterwards

mixed together. It is also possible to pre-mix components (B) and (C), and then dissolve components (A) and/or (D) and/or (E) in this mixture.

The use of the composition according to the invention may be proceeded by processes known in the art, for example, by dip
5 impregnation, vacuum impregnation or trickle impregnation. In the dip impregnation process, the substrates are dipped into the composition for a certain time or pulled through the composition. The substrate may be heated to temperatures below the curing temperature of the composition before dipping. In the vacuum impregnation process, the substrates are
10 placed into a closed container, vacuum is applied, then the composition of the invention can be flushed into the container. In the trickle impregnation process, the composition according to this invention can be trickled with e.g. a nozzle onto a rotating substrate.

It can be useful to heat the substrate to temperatures below the
15 curing temperature of the composition in order to improve, compared to non-heated substrates, the penetration of the impregnating resin into the substrate, especially into wire coils. The heating may be provided by methods known in the art, for example, by electrical current or in an oven, for example, during or before impregnation process.

20 After the impregnation process the composition according to this invention can be cured. This can be proceeded, for example, by radical polymerization, and for this radical polymerization it is useful to add radical initiators as part of component D) to the composition of the invention. The curing may be carried out by heating the impregnated substrate and/or by
25 irradiation the impregnated substrate with high-energy radiation.

The heat for curing can be produced, for example, by passing an electrical current through the windings; it is also possible to use an oven or an infrared (IR) or a near infrared radiation (NIR) source. The heating temperature (object temperature) may be in the range of 80 to 180°C.
30 Typical curing times are, for example, 1 minute to 180 minutes, in case of NIR radiation the curing time may be shorter, for example, below 1 minute. The composition according to this invention can also be cured at

temperatures below 80°C, for example at ambient temperatures, under the use of additives such as aromatic amines or salts of cobalt, copper, cerium or vanadium.

5 The coating according to this invention can also be cured by the application of high-energy radiation, e.g. ultraviolet (UV) light or electron beam. For UV curing, adequate initiators can be used, for example, photoinitiators that absorb in a wavelength range of 190 to 450 nm.

Also the combination of photoinitiators with thermally labile initiators is possible, e.g. for a combination of heat curing and UV curing.

10 The high-energy radiation may be used for the acceleration of the curing process, but also for the through-curing of the applied composition, depending on the impregnation layer thickness. UV- and electron beam radiation can also be used to cure only the surface of the impregnation composition of the invention applied on the substrate, in order to reduce
15 emission of volatile monomers of the composition in a thermal curing step afterwards.

The compositions according to this invention can be used in several fields of applications. They are especially useful for fixing of wound items, for example, coiled substrates, especially of coiled wires like magnet wires
20 in electrical devices like rotors, stators or transformers, or of coiled metal foils in the electrical sector, or coiled substrates on the basis of glass fibers, plastic fibers or plastic foils, and may also be used for the impregnation of fabrics.

The invention will be described with reference to the following
25 examples:

Examples

Example 1

Composition of Prior Art a)

30 Composition of prior art a) is the commercial DuPont impregnating resin Voltatex® 4012, which is a resin based on an unsaturated polyester

different from the polyester according to this invention, dissolved in styrene (viscosity at 25°C: 240mPas).

Example 2

5 Composition of Prior Art b)

Composition of prior art b) is the commercial DuPont impregnating resin Voltatex® 4302, which is a resin based on an unsaturated polyester different from the polyester according to this invention, dissolved in the acrylate of the reaction product of a polyaddition of ethylene oxide with
10 trimethylol propane (viscosity at 25°C: 7300mPas).

Example 3

Composition according to the Invention

Component (A) is an unsaturated polyester based on 57 parts by
15 weight of maleic anhydride, 28 parts by weight of tetrahydrophthalic anhydride, 14 parts by weight of trimethylol propane, 32 parts by weight of neopentyl glycol and 11 parts by weight of ethanolamine, which is further reacted with 13 parts by weight of a methacrylic acid derivative.

Component (A) has the following properties: acid value 17mgKOH/g,
20 double bond equivalent weight 210g/mol.

55 parts by weight of component (A) are heated to 100°C and dissolved in a mixture of 20 parts by weight of the acrylate of the reaction product of a polyaddition of ethylene oxide with trimethylol propane (component (B)) and 13 parts by weight of vinyl toluene (component (C)). After cooling to
25 <40°C, 1.4 parts by weight of a C-C radical initiator (benzpinakol ether, component (D)) are added and mixed well (viscosity at 25°C: 3500mPas).

Tests

Curing loss

30 5g of the liquid impregnation material as described in examples 1-3

are poured into an aluminium dish (50mm diameter, 12mm height). The impregnation material is heated in a convection oven at 130°C for 3 hours. After curing, the loss of mass by evaporation during the thermal cure is measured (Curing loss). This value is determined as follows:

- 5 Curing loss = $1 - (\text{net sample weight before cure} / \text{net sample weight after cure})$

This procedure was carried out with 10 samples for each impregnation material, and the averages were determined.

Example 1 (prior art a): Curing loss = 11.9 wt.-%

- 10 Example 2 (prior art b)): Curing loss = 1.0 wt.-%

Example 3 (acc. to invention): Curing loss = 2.0 wt.-%

Bending force

- 15 The bending forces of the impregnation materials were measured according to IEC61033. The results are shown in Table 1.

Table 1:

material	bending force at 25°C	bending force at 130°C	bending force at 155°C	bending force at 180°C
Example 1 (prior art a))	222 N	138 N	94 N	63 N
Example 2 (prior art b))	135 N	34 N	29 N	28 N
Example 3 (invention)	451 N	286 N	251 N	105 N

- 20 As the data show, the impregnation material according to this invention exhibits extraordinary mechanical properties especially at elevated temperatures while delivering low emissions upon curing and maintaining good impregnation properties due to medium viscosities.

Claims

What is claimed is

1. A composition for fixing wound items comprising
 - 5 A) 5 to 90 wt% of at least one α , β -unsaturated polyester resin based on at least one unsaturated mono-, di- or tricarboxylic acids and/or mono-, di- or tricarboxylic acid group containing molecules, at least one polyol, at least one acrylic or methacrylic group containing component,
 - 10 B) 2 to 80 wt% of at least one monomeric and/or oligomeric ethylenically unsaturated component having a vapour pressure in a range of 0 to 1 mbar at 20°C, preferred 0 to 0.5 mbar at 20°C,
 - C) 0.1 to 40 wt% of at least one monomeric and/or oligomeric unsaturated component different from B) having a vapour pressure
 - 15 in a range of 0 to 10 mbar at 20°C, preferred 0 to 5 mbar at 20°C,
 - D) 0 to 15 wt% of at least one customary additive, and
 - E) 0 to 30 wt% of at least one monomer and/or polymer containing epoxy or glycidyl ether or ester moieties,
 - the wt% being based on the total weight of the composition.
 - 20
2. The composition of claim 1 comprising 10 to 75 wt% of component A).
3. The composition of claims 1 and 2 comprising 4 to 65 wt% of component B).
- 25
4. The composition of claims 1 to 3 comprising 1 to 40 wt% of component C).
5. The composition of claims 1 to 4 wherein the α , β -unsaturated polyester resin of A) comprises at least one α , β -unsaturated polyester
- 30 imide resin.

6. The composition of claims 1 to 5 wherein the α , β -unsaturated polyester resin of A) has a hydroxyl value of 0 to 80 mg KOH/g, an acid value of 0 to 50 mg KOH/g and a urethane group concentration of 0 to 0.1 mol per 100g resin A).


7. The composition of claims 1 to 6 wherein the α , β -unsaturated polyester resin of A) has a number average molecular mass (M_n) in a range of 500 to 5000 g/mol.

8. The composition of claims 1 to 7 wherein the α , β -unsaturated polyester resin of A) is obtained by reaction of

(a) at least one α , β - ethylenically unsaturated dicarboxylic acid, its anhydride and/or an ester of the α , β - ethylenically unsaturated dicarboxylic acid, and


(b) at least one alcohol having one or more, preferably 2, 3 or 4, hydroxyl functionalities per molecule, and,

(c) in case of a polyester imide, at least one imide group containing substance with the formula




(Formula 1)

or



(Formula 2)

or



(Formula 3)

in which

5 R_1 is an aliphatic, cycloaliphatic or aromatic moiety in which the carbonyl groups in R_1 are in a 1,2-position and that contains at least one further reactive carboxyl or hydroxyl group or a C=C double bond or combinations thereof,

R_2 is an aliphatic, aromatic or cycloaliphatic moiety with 2 to 20 carbon atoms that may also contain oxygen or nitrogen atoms,

10 R_3 is an aliphatic, cycloaliphatic or aromatic moiety in which at least 2 of 4 carbonyl groups in R_3 are in a 1,2-position, and

X is a hydroxyl or carboxy functionality, and

- (d) at least one component which is chemically bound into the resin and which contains at least one (meth)acrylic double bond, and
- 15 (e) possibly one or more mono, di- or tricarboxylic acids which are different from (a), and
- (f) possibly one or more polyether polyols, polyolefinic polyols or polymeric polyols which are different from b), and
- (g) possibly one or more polyisocyanates.

20

9. The composition of claim 7 wherein the α , β -unsaturated polyester resin of A) is obtained by reaction of components (a) to (g) in a ratio that 100g of component A) contain 0.05 to 0.50 mol of polymerizable, α , β - ethylenically unsaturated groups from component (a).

25

10. A wound item fixed with the composition according to claims 1 to 9.

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2010/062316

A. CLASSIFICATION OF SUBJECT MATTER

INV. C08F283/01 C08L67/06 C09D167/06 H01B3/42 H01F27/32
H01F41/12 H02K3/30

ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

C08L C09D C08F C08G H02K H01F H01B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 00/46297 A1 (NESTE CHEMICALS OY [FI]; AIROLA KARRI [FI]; FAERM OUTI [FI]; MAHBUB PA) 10 August 2000 (2000-08-10) page 5, line 31 - page 6, line 18; examples Polyester B, Example 2, Example 8 -----	1-9
X	US 3 485 733 A (ALELIO GAETANO F D) 23 December 1969 (1969-12-23) column 12, line 66 - column 12, line 69; examples Alkyd Resin G, VI, VIII, XVII -----	1-10
X	FR 2 401 946 A1 (UCB SA [BE]) 30 March 1979 (1979-03-30) claims 1,3, 16-18; examples C3, 10a); table II ----- -/-	1-9

☒ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

22 March 2011

Date of mailing of the international search report

04/04/2011

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Enescu, Cristina

INTERNATIONAL SEARCH REPORT

International application No

PCT/US2010/062316

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 03/101918 A2 (VALSPAR SOURCING INC [US]; ROBERTSON BRIAN A [CA]) 11 December 2003 (2003-12-11) examples Example 1 Run 1, Example 2 Gelcoat 2a; tables 1a, 2a -----	1-9
A	WO 92/01015 A1 (HERBERTS & CO GMBH [DE]) 23 January 1992 (1992-01-23) examples 1, 7; table 4 -----	1-10
A	CA 2 119 206 A1 (CIBA GEIGY AG [CH]) 19 September 1994 (1994-09-19) page 12, line 26 - page 12, line 28; example 11 -----	1-9
A	EP 0 350 730 A2 (BAYER AG [DE]) 17 January 1990 (1990-01-17) page 4, line 3 - page 4, line 7; examples 1-3 -----	1-9
A	US 5 096 938 A (BECK ERICH [DE] ET AL) 17 March 1992 (1992-03-17) examples 1,2,4; table 1 -----	1-9

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2010/062316

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 0046297	A1	10-08-2000	AU 2444000 A 25-08-2000
		EP 1151040 A1 07-11-2001	
		FI 990189 A 03-08-2000	
		US 6617417 B1 09-09-2003	

US 3485733	A	23-12-1969	NONE

FR 2401946	A1	30-03-1979	BE 870175 A1 05-03-1979
		DE 2838691 A1 15-03-1979	
		NL 7809014 A 07-03-1979	
		US 4206025 A 03-06-1980	

WO 03101918	A2	11-12-2003	AU 2003231863 A1 19-12-2003
		AU 2009233645 A1 26-11-2009	
		CA 2484191 A1 11-12-2003	
		MX PA04011714 A 14-02-2005	
		US 2005215708 A1 29-09-2005	
		US 2010113682 A1 06-05-2010	

WO 9201015	A1	23-01-1992	DE 4022235 A1 16-01-1992
		EP 0495028 A1 22-07-1992	
		JP 5501734 T 02-04-1993	
		PT 98280 A 31-08-1993	

CA 2119206	A1	19-09-1994	AT 210155 T 15-12-2001
		AU 682334 B2 02-10-1997	
		AU 5775394 A 22-09-1994	
		BR 9401197 A 18-10-1994	
		DE 59409985 D1 17-01-2002	
		EP 0615980 A2 21-09-1994	
		ES 2167353 T3 16-05-2002	
		JP 6298818 A 25-10-1994	
		MA 23097 A1 01-10-1994	
		ZA 9401879 A 19-09-1994	

EP 0350730	A2	17-01-1990	DE 3823702 A1 25-01-1990

US 5096938	A	17-03-1992	DE 3704098 A1 25-08-1988
		EP 0279303 A2 24-08-1988	
		ES 2032880 T3 01-03-1993	
		JP 2635347 B2 30-07-1997	
		JP 63196613 A 15-08-1988	
