

**(12) PATENT**  
**(19) AUSTRALIAN PATENT OFFICE**

**(11) Application No. AU 200121626 B2**  
**(10) Patent No. 774286**

(54) Title  
**Adhesion promoters for monomer-free reactive polyurethanes**

(51)<sup>7</sup> International Patent Classification(s)  
**C08G 018/10                      C09J 175/04**  
**C08G 018/12**

(21) Application No: **200121626**

(22) Application Date: **2000.11.25**

(87) WIPO No: **WO01/40342**

(30) Priority Data

(31) Number	(32) Date	(33) Country
<b>19957351</b>	<b>1999.11.29</b>	<b>DE</b>
<b>10055786</b>	<b>2000.11.10</b>	<b>DE</b>

(43) Publication Date : **2001.06.12**

(43) Publication Journal Date : **2001.08.23**

(44) Accepted Journal Date : **2004.06.24**

(71) Applicant(s)  
**Henkel Kommanditgesellschaft auf Aktien**

(72) Inventor(s)  
**Michael Krebs; Christoph Lohr; Andreas Brenger**

(74) Agent/Attorney  
**SPRUSON and FERGUSON, GPO Box 3898, SYDNEY NSW 2001**

(56) Related Art  
**DE 19700014**

# AU 200121626

(12) NACH DEM VERTRAG ÜBER DIE INTERNATIONALE ZUSAMMENARBEIT AUF DEM GEBIET DES PATENTWESENS (PCT) VERÖFFENTLICHTE INTERNATIONALE ANMELDUNG

(19) Weltorganisation für geistiges Eigentum  
Internationales Büro



(43) Internationales Veröffentlichungsdatum  
7. Juni 2001 (07.06.2001)

PCT

(10) Internationale Veröffentlichungsnummer  
WO 01/40342 A1

(51) Internationale Patentklassifikation<sup>7</sup>: C08G 18/10,  
18/12, C09J 175/04

[DE/DE]; Bogenstrasse 1, 40724 Hildren (DE). LOHR, Christoph [DE/DE]; Am Wolfshahn 16, 42117 Wuppertal (DE). BRENGER, Andreas [DE/DE]; Volmerswerther Strasse 391, 40221 Düsseldorf (DE).

(21) Internationales Aktenzeichen: PCT/EP00/11771

(22) Internationales Anmeldedatum:  
25. November 2000 (25.11.2000)

(81) Bestimmungsstaaten (*national*): AU, BG, BR, BY, CA, CN, CZ, HU, ID, IN, JP, KR, MX, NO, NZ, PL, RO, RU, SG, SI, SK, UA, US, UZ, VN, YU, ZA.

(25) Einreichungssprache: Deutsch

(84) Bestimmungsstaaten (*regional*): europäisches Patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR).

(26) Veröffentlichungssprache: Deutsch

(30) Angaben zur Priorität:  
199 57 351.4 29. November 1999 (29.11.1999) DE  
100 55 786.4 10. November 2000 (10.11.2000) DE

Veröffentlicht:  
— Mit internationalem Recherchenbericht.  
— Vor Ablauf der für Änderungen der Ansprüche geltenden Frist; Veröffentlichung wird wiederholt, falls Änderungen eintreffen.

(71) Anmelder (für alle Bestimmungsstaaten mit Ausnahme von US): HENKEL KOMMANDITGESELLSCHAFT AUF AKTIEN [DE/DE]; Henkelstrasse 67, 40589 Düsseldorf (DE).

Zur Erklärung der Zweibuchstaben-Codes, und der anderen Abkürzungen wird auf die Erklärungen ("Guidance Notes on Codes and Abbreviations") am Anfang jeder regulären Ausgabe der PCT-Gazette verwiesen.

(72) Erfinder; und

(75) Erfinder/Anmelder (nur für US): KREBS, Michael

(54) Title: ADHESION PROMOTERS FOR MONOMER-FREE REACTIVE POLYURETHANES

(54) Bezeichnung: HAFTUNGSVERSTÄRKER FÜR MONOMERFREIE REAKTIVE POLYURETHANE

(57) Abstract: Polyurethane compositions are produced in a two-stage method. In a first step, a diol component with a molecular weight of less than 2000 is reacted with a monomeric diisocyanate with a molecular weight of less than 500 and the unreacted monomeric diisocyanate is removed from this reaction product. In a second step, the resulting high-molecular diisocyanate is reacted with a polyol to produce a reactive prepolymer with isocyanate and groups. The addition of polyisocyanates which are capable of migration and which have a substantially lower vapor pressure than diphenylmethanediisocyanate, improves the addition behavior of the invention polyurethane compositions. Reactive polyurethane compositions of this type are suitable for using as binding agents for reactive one or two component adhesives/sealants, which may optionally contain solvents. These compositions are also suitable for producing reactive hot melt adhesives when suitable polyols are selected. A substantial advantage of these compositions compared to known polyurethane compositions is the considerably lower proportion of monomeric diisocyanates with a molecular weight of less than 500.

(57) Zusammenfassung: Polyurethan-Zusammensetzungen werden in einem zweistufigen Verfahren hergestellt, wobei in einem ersten Schritt eine Diolkomponente mit einem Molekulargewicht kleiner als 2000 mit einem monomeren Diisocyanat mit einem Molekulargewicht kleiner als 500 umgesetzt wird und aus diesem Umsetzungsprodukt das nicht umgesetzte monomere Diisocyanat entfernt wird und dann in einem zweiten Schritt das so entstandene hochmolekulare Diisocyanat mit einem Polyol umgesetzt wird, so dass ein reaktives Prepolymer mit Isocyanat-Endgruppen entsteht. Ein Zusatz von migrationsfähigen Polyisocyanaten, die einen wesentlich niedrigeren Dampfdruck als Diphenylmethandiisocyanat aufweisen, verbessert das Haftverhalten der erfindungsgemässen Polyurethan-Zusammensetzungen. Derartige reaktive Polyurethan-Zusammensetzungen eignen sich zur Verwendung als Bindemittel für reaktive ein- oder zweikomponentige Kleb-/Dichtstoffe, die ggf., lösungsmittelhaltig sein können. Weiterhin eignen sich diese Zusammensetzungen bei entsprechender Auswahl der Polyole zur Herstellung von reaktiven Schmelzklebstoffen. Wesentlicher Vorteil dieser Zusammensetzungen gegenüber bekannten Polyurethan-Zusammensetzungen ist der drastisch reduzierte Anteil an monomeren Diisocyanaten mit einem Molekulargewicht unter 500.

WO 01/40342 A1

Adhesion promoters for monomer-free  
reactive polyurethanes

---

This invention relates to compositions based on polyols and high molecular-weight diisocyanates with a low content of monomeric diisocyanates, and to their production and their use as binders for reactive one- or two-pack  
5 adhesives/sealants, reactive hot melt adhesives or solvent-based polyurethane adhesives.

Reactive polyurethane adhesives/sealants, particularly one-pack, moisture-curing systems, generally contain polymers  
10 that are liquid at room temperature with urethane groups, optionally urea groups and reactive isocyanate groups. For many applications, these compositions are solvent-free and very highly viscous and/or paste-like, and they are processed at room temperature or at a slightly elevated  
15 temperature of between about 50°C and about 100°C.

Reactive, one-pack, moisture-curing polyurethane hot melt adhesives are moisture-curing or moisture-crosslinking adhesives that are solid at room temperature and are  
20 applied as an adhesive in the form of their melt, and the polymer components of which contain urethane groups and reactive isocyanate groups. As a result of the cooling of this melt after application and joining of the substrate parts to be bonded, a rapid physical setting of the hot-  
25 melt adhesive first takes place by means of its solidification. This is followed by a chemical reaction of the isocyanate groups still present with moisture from the environment to form a crosslinked, infusible adhesive. Reactive hot-melt adhesives based on isocyanate-terminated  
30 polyurethane prepolymers are described e.g. by H.F. Huber and H. Müller in "Shaping Reactive Hotmelts Using LMW Copolyesters", Adhesives Age, November 1987, pages 32 to 35.

Laminating adhesives can either be constituted similarly to the reactive hot melt adhesives or they are applied as one-pack systems from a solution in organic solvents; a further embodiment consists of two-pack, solvent-based or solvent-free systems in which the polymer constituents of the one component contain urethane groups and reactive isocyanate groups and, in the two-pack systems, the second component contains polymers or oligomers with hydroxyl groups, amino groups, epoxy groups and/or carboxyl groups. In these two-pack systems the isocyanate group-containing component and the second component are mixed immediately before application, usually with the aid of a mixing and dispensing system.

Reactive polyurethane adhesives/sealants are distinguished by a very high overall performance. In the last few years, therefore, more and more new applications have been opened up for these adhesives/sealants. Compositions for such adhesives and/or sealants are already known from very many patent applications and other publications.

In addition to many advantages, these polyurethane compositions also have some disadvantages caused by the system. One of the most serious disadvantages is the residual monomer content of isocyanates, especially the more volatile diisocyanates. Adhesives/sealants, and especially the hot melt adhesives, are processed at an elevated temperature. The hot melt adhesives, for example, are processed at between 100°C and 200°C, laminating adhesives between room temperature and 150°C. Even at room temperature, volatile isocyanates such as TDI or IPDI have a not insignificant vapour pressure. This noticeable vapour pressure is particularly serious especially in the case of spray application, since in this case significant quantities of isocyanate vapours can occur over the object being treated, which are toxic owing to their irritant and sensitising action. Protective measures must therefore be taken to prevent health hazards to persons charged with the

processing. These measures, such as e.g. the requirement to monitor compliance with the maximum allowable concentration, are expensive. In particular, exhaust ventilation measures for the vapours at the point of  
5 formation and delivery are very cost-intensive and also form an obstacle to certain application methods, such as in particular the spray application of reactive polyurethane adhesives/sealants.

10 The development of reactive polyurethane compositions with a drastically reduced proportion of monomeric diisocyanates is therefore highly desirable for these fields of application, as in some cases this would make it possible to use them in many applications in which their use was not  
15 previously possible owing to the workshop hygiene problems mentioned above.

According to the Schulz-Flory statistical model, when diisocyanates with isocyanate groups of approximately equal  
20 reactivity are reacted with hydroxyl group-containing compounds, the remaining content of monomeric diisocyanate in the reaction product depends on the NCO/OH ratio of the reactants in the prepolymer synthesis. With an NCO/OH ratio of 2, as is frequently necessary for the prepolymer  
25 composition, approximately 25% of the monomeric diisocyanate used remains as a monomer in the prepolymer. If, for example, 10 wt.% diphenylmethane diisocyanate (MDI) is used in a prepolymer synthesis with an NCO/OH ratio of 2, an order of magnitude of approximately 2 wt.% monomeric  
30 MDI is found in the prepolymer in accordance with the statistical estimate mentioned above. At 150°C the pure MDI already has a vapour pressure of 0.8 mbar. While it is true that, according to Raoult's law, this vapour pressure is lower in compositions, it is still higher than the non-  
35 toxic range for workshop hygiene. Under the application conditions described above, especially when being applied as a hot melt adhesive over a large area in a thin layer, considerable quantities of the residual monomer therefore

pass into the air space above and must be removed by exhaust ventilation. A significant reduction in the monomer content by a power of ten, by reducing the NCO/OH ratio, cannot generally be achieved in practice since the average  
5 molecular weight would then increase exponentially and the resulting polyurethane compositions would become extremely viscous and would be impossible to process. In practice, therefore, other routes are taken for prepolymer synthesis. For example, synthesis is performed with a sufficiently  
10 high NCO/OH ratio and the monomeric diisocyanate removed in a second step after pre-polymerisation; this can take place by distilling off the unreacted monomeric diisocyanate under vacuum, for example, or by subsequent chemical bonding of the monomeric diisocyanate. Thus, EP-A-316738  
15 describes a process for the production of polyisocyanates containing urethane groups with a urethane group-free starting diisocyanate of no more than 0.4 wt.% by reacting aromatic diisocyanates with polyhydric alcohols and subsequently removing the unreacted, excess starting  
20 diisocyanate, the removal of the excess starting diisocyanate by distillation taking place in the presence of an aliphatic polyisocyanate containing isocyanate groups.

25 EP-A-0393903 describes a process for the production of prepolymers in which, in a first step, monomeric diisocyanate is reacted with a polyol. A catalyst is then added in a sufficient quantity for a considerable proportion of the residual isocyanate functionality to be  
30 converted to allophanate functionality. When the theoretical NCO content is reached, the reaction is stopped by rapid cooling and addition of salicylic acid.

WO-95/06124 describes polyurethane compositions with a low  
35 proportion of monomeric diisocyanates which are produced by reacting polyols with trifunctional isocyanates and optionally adding monofunctional chain terminators. A disadvantage of this process is the low availability of

trifunctional, low molecular-weight isocyanates; the trifunctional homologues of diphenylmethane diisocyanate in particular are not commercially available in pure form.

The work by V.A. Kudishina and E.F. Morgunova, *Sin. Fiz.-Khim. Polim.* (1970), part 7, 125-129, cold-curing polyurethane adhesives based on hydroxyfunctional polyesters or polyethers and isocyanate-containing hardeners are described. The isocyanate-containing hardeners are reaction products of tolylene diisocyanate (TDI) or of diphenylmethane diisocyanate (MDI), ethylene glycol and glycerin. It is stated that these hardener components lead to a substantial reduction in the toxicity of the adhesives, although these still produce a quantity of isocyanate of 1.7% in the air space of the corresponding test chamber. These workplace concentrations of isocyanates are no longer tolerable in industrialised western countries under today's standards of workshop hygiene.

Despite the aforementioned prior art, therefore, there is still a need for improved polyurethane compositions with a low proportion of monomeric diisocyanates that are suitable for use as adhesives/sealants, especially for reactive hot melt adhesives. In particular, the raw materials used for these should be readily and cheaply accessible and readily converted, and the adhesion properties should be at least equal to those of the conventional hot melt adhesives.

In an embodiment of the invention, there is provided a reactive polyurethane adhesive/sealant composition based on reaction products of one or more polyols and one or more high molecular-weight diisocyanates, wherein the one or more high molecular weight diisocyanates are produced by reaction of at least one diol having an average molecular weight (number average  $M_n$ ) of less than 2000 with at least one monomeric diisocyanate having a molecular weight of less than 500, and further wherein the one or more high molecular-weight diisocyanates used contain no more than 10 wt.% monomeric diisocyanate before the reaction with the one or more polyols.

Another achievement of the object according to the invention consists in adding to the aforementioned reaction products of polyols and high molecular-weight diisocyanates, migratory polyisocyanates having a

substantially lower vapour pressure than e.g. monomeric diphenylmethane diisocyanate (MDI).

The present invention also provides a process for the  
5 production of these reaction products of polyols and high  
molecular-weight diisocyanates. In a first step of this  
process, the diol component with an average molecular  
weight (number average  $M_n$ ) of less than 2000, especially  
less than 1500, is reacted with a large stoichiometric  
10 excess of monomeric diisocyanate with a molecular weight of  
less than 500 to give a high molecular-weight diisocyanate.  
After this reaction, the high molecular-weight diisocyanate  
is precipitated out of the reaction mixture, optionally by  
adding a non-solvent, and freed from unreacted diisocyanate  
15 by filtration or centrifugation. In a subsequent second  
step, this high molecular-weight diisocyanate is reacted  
with a polyol so that a reactive prepolymer with isocyanate  
terminal groups is formed having a very small content of  
monomeric diisocyanates with a molecular weight of less  
20 than 500. In a preferred embodiment, at least one migratory  
polyisocyanate with a low vapour pressure is then added to  
this reactive prepolymer with a very small content of  
monomeric volatile diisocyanates.

25 Another process for the production of such compositions  
consists in the fact that, after the first step of reacting  
the diol component with the monomeric diisocyanate, the  
excess monomeric diisocyanate is removed from the reaction  
mixture by distillation or removed from the reaction  
30 mixture by selective extraction and then, in a second step,  
this high molecular-weight diisocyanate is also reacted  
with a polyol to give a reactive prepolymer with isocyanate  
terminal groups. In the case of a prepolymer with  
isocyanate terminal groups purified in this way too, in a  
35 preferred embodiment at least one migratory polyisocyanate  
with substantially lower vapour pressure than MDI is added  
for adhesive applications according to the invention.



Monomeric diisocyanates within the meaning of this invention are those aromatic, aliphatic or cycloaliphatic diisocyanates having a molecular weight of less than 500. Examples of suitable aromatic diisocyanates are all isomers of tolylene diisocyanate (TDI), either as a pure isomer or as a mixture of several isomers, 1,5-naphthalene diisocyanate (NDI), 1,4-naphthalene diisocyanate (NDI), diphenylmethane 4,4'-diisocyanate (MDI), diphenylmethane 2,4'-diisocyanate and mixtures of 4,4'-diphenylmethane diisocyanate with the 2,4' isomer, xylylene diisocyanate (XDI), 4,4'-diphenyldimethylmethane diisocyanate, di- and tetraalkyldiphenylmethane diisocyanate, 4,4'-dibenzyl diisocyanate, 1,3-phenylene diisocyanate, 1,4-phenylene diisocyanate. Examples of suitable cycloaliphatic diisocyanates are the hydrogenation products of the aforementioned aromatic diisocyanates, such as e.g. 4,4'-dicyclohexylmethane diisocyanate ( $H_{12}$ MDI), 1-isocyanatomethyl-3-isocyanato-1,5,5-trimethylcyclohexane (isophorone diisocyanate, IPDI), cyclohexane 1,4-diisocyanate, hydrogenated xylylene diisocyanate ( $H_6$ XDI), 1-methyl-2,4-diisocyanatocyclohexane, m- or p-tetramethylxylene diisocyanate (m-TMXDI, p-TMXDI) and dimerised fatty acid diisocyanate. Examples of aliphatic diisocyanates are tetramethoxybutane 1,4-diisocyanate, butane 1,4-diisocyanate, hexane 1,6-diisocyanate (HDI), 1,6-diisocyanato-2,2,4-trimethylhexane, 1,6-diisocyanato-2,4,4-trimethylhexane, lysine diisocyanate and 1,12-dodecane diisocyanate ( $C_{12}$ DI).

These monomeric diisocyanates are reacted with low molecular-weight diols in a first reaction step to give high molecular-weight diisocyanates. The diols used for this purpose have an average molecular weight (number average  $M_n$ ) of less than 2000, preferably less than 1500. The OH number of the diol, determined in accordance with DIN 53240, is decisive for the number average.

Typically, all linear or slightly branched C<sub>2</sub>-C<sub>18</sub> alkanediols may be used for this purpose. In addition, low molecular-weight polyethers and low molecular-weight alkoxylation products of aromatic dihydroxy compounds (diphenols) can be used.

Specific examples of the diols to be used according to the invention are ethylene glycol, 1,2-propanediol, 1,3-propanediol, 2,2-dimethyl-1,3-propanediol, 2-methylpropanediol, 1,6-hexanediol, 2,4,4-trimethyl-1,6-hexanediol, 2,2,4-trimethyl-1,6-hexanediol, 1,4-cyclohexanedimethanol, diethylene glycol, triethylene glycol, tetraethylene glycol, dipropylene glycol, tripropylene glycol, tetrapropylene glycol, poly(oxytetramethylene) glycol with a molecular weight of up to 650, alkoxylation products of bisphenol A, alkoxylation products of bisphenol F, of isomeric dihydroxyanthracenes, of isomeric dihydroxynaphthalenes, of pyrocatechol, of resorcinol, of hydroquinone with up to 8 alkoxy units per aromatic hydroxy group or mixtures of the above diols.

This reaction of the monomeric diisocyanates with the diols takes place by the method that is known *per se*, optionally with the addition of aprotic solvents. In order to avoid the formation of higher oligomers, a high stoichiometric excess of diisocyanates in relation to the diols used is usefully employed. Catalysts that are known *per se* can optionally be used to accelerate the reaction between the isocyanate group and the alcohol group. The reaction and the stoichiometric ratio of monomeric diisocyanate to diol should be selected such that exclusively a 2:1 adduct of monomeric diisocyanate and diol is formed, as far as possible, and the formation of higher oligomers is largely suppressed

On completion of the reaction, the reaction product is freed from monomeric diisocyanate as far as possible; the resulting high molecular-weight diisocyanate within the meaning of this invention should contain no more than 10,

preferably no more than 5 and especially no more than 2 wt.% monomeric diisocyanate, based on the high molecular-weight diisocyanate. The proportion by weight of the monomeric diisocyanate is determined by gas chromatography.

5 The purification step can take place by methods that are known *per se*. When low alkanediols are used, it has proved useful to take advantage of the low solubility of the high molecular-weight diisocyanate in some solvents, in that, on completion of the diol/ diisocyanate reaction, a non-

10 solvent for the high molecular-weight diisocyanate is added, which is, at the same time, a solvent for the monomeric diisocyanate. As a result, the high molecular-weight diisocyanate is precipitated out of the reaction mixture and freed from unreacted monomeric diisocyanate by

15 filtration or centrifugation. This method should be employed especially when the lower-volatility monomeric diisocyanates, such as e.g. MDI, are to be used.

Non-solvents in this case are, in particular, non-polar, aprotic, organic solvents, such as e.g. ethyl acetate, chlorobenzene, xylenes, toluene or, in particular, special boiling-point spirits.

20

When volatile monomeric diisocyanates, such as e.g. TDI, TMXDI, IPDI, XDI are used, the excess monomeric diisocyanate can also be removed from the reaction mixture by distillation. For this purpose, the distillation preferably takes place under vacuum with the aid of a thin-layer evaporator or a thin-film evaporator. These

25

30 distillation methods are described e.g. in *Kunststoff-Handbuch* volume 7, "Polyurethane", G.W. Becker (editor), Hanser-Verlag, Munich, 3rd edition 1993, page 425.

Another way of removing the monomeric diisocyanate from the reaction mixture is the selective extraction of the monomeric diisocyanate, e.g. using supercritical carbon dioxide or other supercritical aprotic solvents. This extraction method is known e.g. from WO-97/46603.

35

The monomer-free or low-monomer, high molecular-weight diisocyanate produced in this way is reacted with polyols in a second reaction step, by a method that is known *per se*, to give prepolymers. The NCO/OH ratio is 1.2:1 - 5:1.

5 Since the high molecular-weight diisocyanate is already very largely monomer-free, higher NCO/OH ratios of up to 10:1 can be used in the second reaction step.

A large number of higher molecular-weight polyhydroxy

10 compounds can be used as polyols in this process. The polyhydroxy compounds with two or three hydroxyl groups per molecule in the molecular weight range of 400 to 20000, preferably in the range of 1000 to 6000, which are liquid at room temperature, glassy solid/amorphous or crystalline,

15 are preferably suitable as polyols. Examples are di- and/or trifunctional polypropylene glycols; random and/or block copolymers of ethylene oxide and propylene oxide can also be used. Another group of polyethers that can preferably be used are the polytetramethylene glycols

20 (poly(oxytetramethylene) glycol, poly-THF), which are produced e.g. by the acid polymerisation of tetrahydrofuran, the molecular weight range of these polytetramethylene glycols lying between 600 and 6000, preferably in the range of 800 to 5000.

25 The liquid, glassy amorphous or crystalline polyesters that can be produced by condensation of di- or tricarboxylic acids, such as e.g. adipic acid, sebacic acid, glutaric acid, azelaic acid, suberic acid, undecanedioic acid, dodecanedioic acid, 3,3-dimethylglutaric acid, terephthalic

30 acid, isophthalic acid, hexahydrophthalic acid, dimerised fatty acid or mixtures thereof with low molecular-weight diols or triols, such as e.g. ethylene glycol, propylene glycol, diethylene glycol, triethylene glycol, dipropylene glycol, 1,4-butanediol, 1,6-hexanediol, 1,8-octanediol,

35 1,10-decanediol, 1,12-dodecanediol, dimerised fatty alcohol, glycerin, trimethylolpropane or mixtures thereof, are also suitable as polyols.

Another group of polyols to be used according to the invention are polyesters based on  $\epsilon$ -caprolactone, also known as "polycaprolactones".

However, polyester polyols of oleochemical origin can also  
5 be used. These polyester polyols can be produced, for example, by the complete ring opening of epoxidised triglycerides of an at least partially olefinically unsaturated, fatty acid-containing fat mixture with one or more alcohols with 1 to 12 C atoms and subsequent partial  
10 transesterification of the triglyceride derivatives to alkyl ester polyols with 1 to 12 C atoms in the alkyl radical. Other suitable polyols are polycarbonate polyols and dimerised diols (Henkel), as well as castor oil and its derivatives. The hydroxyfunctional polybutadienes, as  
15 obtainable, for example, with the trade name "Poly-bd", can be used as polyols for the compositions according to the invention.

Linear and/or slightly branched acrylic ester copolymer  
20 polyols, which are produced, for example, by the free-radical copolymerisation of acrylates or methacrylates with hydroxyfunctional acrylic acid and/or methacrylic acid compounds, such as hydroxyethyl (meth)acrylate or hydroxypropyl (meth)acrylate, are also suitable as polyols.  
25 Because of this method of production, the hydroxyl groups in these polyols are usually randomly distributed, so that these are either linear or slightly branched polyols with an average OH functionality. Although the difunctional compounds are preferred for the polyols, polyols with  
30 higher functionality can also be used, at least in smaller quantities.

The selection of the polyol or polyols depends on the type of application of this adhesive/sealant composition. For  
35 highly viscous or paste-like liquid adhesives/sealants, at least predominantly liquid polyols are preferably used. In the case of two-pack adhesives/sealants, one component can contain a prepolymer with reactive isocyanate terminal

groups from the polyols and the second component a hydroxyfunctional polyol or hydroxyfunctional polyurethane. However, the high molecular-weight diisocyanate can also be used as hardener for a hydroxyfunctional component, the  
5 hydroxyfunctional component containing either one or more of the above polyols or a hydroxyl group-containing polyurethane prepolymer.

When the polyurethane compositions according to the  
10 invention are used as reactive hot melt adhesives, the polyol components are selected such that the composition is solid at room temperature. This can occur on the one hand by using solid amorphous and/or solid crystalline polyhydroxy compounds, but it can also occur by  
15 incorporating a considerable proportion of short-chain polyhydroxy compounds, since these compositions are also solid at room temperature because of the high concentration of urethane groupings. Selection criteria for the polyols can be found e.g. in the aforementioned paper by H.F. Huber  
20 and H. Müller.

The compositions according to the invention can optionally also contain catalysts which accelerate the formation of the polyurethane prepolymer during its production and/or  
25 which accelerate the moisture curing after application of the adhesive/sealant. The organo-metallic compounds of tin, iron, titanium or bismuth, such as tin(II) salts of carboxylic acids, e.g. tin(II) acetate, tin(II) ethyl hexoate and tin(II) diethyl hexoate, are suitable as  
30 catalysts that can be used according to the invention. Another class of compounds is represented by the dialkyltin(IV) carboxylates. The carboxylic acids have 2, preferably at least 10, especially 14 to 32 C atoms. Dicarboxylic acids can also be used. The following can be  
35 expressly mentioned as acids: adipic acid, maleic acid, fumaric acid, malonic acid, succinic acid, pimelic acid, terephthalic acid, phenylacetic acid, benzoic acid, acetic acid, propionic acid and 2-ethylhexanoic, caprylic, capric,

lauric, myristic, palmitic and stearic acid. Specific compounds are dibutyltin and dioctyltin diacetate, maleate, bis(2-ethyl hexoate), dilaurate, tributyltin acetate, bis( $\beta$ -methoxycarbonylethyl)tin dilaurate and bis( $\beta$ -  
5 acetylethyl)tin dilaurate.

Tin oxides, sulfides and thiolates can also be used. Specific compounds are: bis(tributyltin) oxide, bis(trioctyltin) oxide, dibutyltin and dioctyltin bis(2-  
10 ethylhexyl thiolate), dibutyltin and dioctyltin didodecyl thiolate, bis( $\beta$ -methoxycarbonylethyl)tin didodecyl thiolate, bis( $\beta$ -acetylethyl)tin bis(2-ethylhexyl thiolate), butyltin and octyltin tris(thioglycolic acid 2-ethyl  
15 2-ethyl hexoate), dibutyltin and dioctyltin bis(thioglycolic acid 2-ethyl hexoate), tributyltin and trioctyltin (thioglycolic acid 2-ethyl hexoate) and butyltin and octyltin  
tris(thioethylene glycol 2-ethyl hexoate), dibutyltin and dioctyltin bis(thioethylene glycol 2-ethyl hexoate), tributyltin and trioctyltin (thioethylene glycol 2-ethyl  
20 hexoate) with the general formula  $R_{n+1}Sn(SCH_2CH_2OCOC_8H_{17})_{3-n}$ , wherein R is an alkyl group with 4 to 8 C atoms, bis( $\beta$ -methoxycarbonylethyl)tin bis(thioethylene glycol 2-ethyl hexoate), bis( $\beta$ -methoxycarbonylethyl)tin bis(thioglycolic acid 2-ethyl hexoate) and bis( $\beta$ -acetylethyl)tin  
25 bis(thioethylene glycol 2-ethyl hexoate) and bis( $\beta$ -acetylethyl)tin bis(thioglycolic acid 2-ethyl hexoate).

In addition, aliphatic tertiary amines are also suitable, especially with a cyclic structure. Among the tertiary  
30 amines, those additionally having groups that are reactive towards the isocyanates, especially hydroxyl and/or amino groups, are also suitable. The following can be mentioned specifically: dimethylmonoethanolamine, diethylmonoethanolamine, methylethylmonoethanolamine,  
35 triethanolamine, trimethanolamine, tripropanolamine, tributanolamine, trihexanolamine, tripentanolamine, tricyclohexanolamine, methyldiethanolamine, ethyldiethanolamine, propyldiethanolamine,

butyldiethanolamine, pentyldiethanolamine, hexyldiethanolamine, cyclohexyldiethanolamine, phenyldiethanolamine and the ethoxylation and propoxylation products thereof, diazabicyclooctane (DABCO),  
5 triethylamine, dimethylbenzylamine (Desmorapid DB, BAYER), bisdimethylaminoethyl ether (Calalyst A 1, UCC), tetramethylguanidine, bisdimethylaminomethyl phenol, 2-(2-dimethylaminoethoxy)ethanol, 2-dimethylaminoethyl-3-dimethylaminopropyl ether, bis(2-dimethylaminoethyl) ether,  
10 N,N-dimethylpiperazine, N-(2-hydroxyethoxyethyl)-2-azanorbornane, or unsaturated bicyclic amines, e.g. diazabicycloundecene (DBU) and Texacat DP-914 (Texaco Chemical), N,N,N,N-tetramethyl-1,3-butanediamine, N,N,N,N-tetramethyl-1,3-propanediamine and N,N,N,N-tetramethyl-1,6-  
15 hexanediamine. The catalysts can also be present in oligomerised or polymerised form, e.g. as N-methylated polyethyleneimine.

Especially preferred catalysts, however, are the derivatives of morpholine. Specific examples of suitable  
20 morpholino compounds are bis(2-(2,6-dimethyl-4-morpholino)ethyl)-(2-(4-morpholino)ethyl)amine, bis(2-(2,6-dimethyl-4-morpholino)ethyl)-(2-(2,6-diethyl-4-morpholino)ethyl)amine, tris(2-(4-morpholino)ethyl)amine, tris(2-(4-morpholino)propyl)amine, tris(2,4-morpholino)-  
25 butyl)amine, tris(2-(2,6-dimethyl-4-morpholino)ethyl)amine, tris(2-(2,6-diethyl-4-morpholino)ethyl)amine, tris(2-(2-methyl-4-morpholino)ethyl)amine or tris(2-(2-ethyl-4-morpholino)ethyl)amine, dimethylaminopropylmorpholine, bis-(morpholinopropyl)methylamine,  
30 diethylaminopropylmorpholine, bis(morpholinopropyl)-ethylamine, bis(morpholinopropyl)propylamine, morpholino-propylpyrrolidone or N-morpholinopropyl-N'-methylpiperazine, dimorpholinodiethyl ether (DMDEE) or di-  
2,6-dimethylmorpholinoethyl) ether.  
35 The above morpholine derivatives exhibit particularly high catalytic activity, especially for the water- (moisture-) isocyanate reaction. For this reason, even very small concentrations of catalyst are highly efficient for



crosslinking or curing the adhesives; the concentrations of the catalyst in the adhesive formulation can be between 0.001 and 2 wt.%, preferably between 0.02 and 0.9 wt.%.

5 Furthermore, the composition according to the invention can optionally also contain stabilisers, adhesion-promoting additives such as tackifying resins, fillers, pigments, plasticisers and/or solvents.

"Stabilisers" within the meaning of this invention can be  
10 understood as, on the one hand, stabilisers that bring about a constant viscosity of the polyurethane prepolymer during production, storage or application. Monofunctional carboxylic acid chlorides, monofunctional, highly reactive isocyanates, but also non-corrosive inorganic acids, for  
15 example, are suitable for this purpose; benzoyl chloride, toluenesulfonyl isocyanate, phosphoric acid or phosphorous acid can be mentioned as examples. In addition, anti-oxidants, UV stabilisers or hydrolysis stabilisers are also meant by stabilisers within the meaning of this invention.

20 The selection of these stabilisers depends, on the one hand, on the main components of the composition and, on the other hand, on the application conditions and the anticipated loads on the cured product. If the polyurethane prepolymer is predominantly built up of polyether building  
25 blocks, mainly anti-oxidants are necessary, optionally in combination with UV stabilisers. Examples of these are the commercial sterically hindered phenols and/or thioethers and/or substituted benzotriazoles or the sterically hindered amines of the HALS type ("Hindered Amine Light  
30 Stabiliser").

If substantial components of the polyurethane prepolymer consist of polyester building blocks, hydrolysis stabilisers, e.g. of the carbodiimide type, can be used.

35

If the compositions according to the invention are used as hot melt adhesives, laminating adhesives or adhesives/sealants, these can also contain tackifying resins, such as

e.g. abietic acid, abietate, terpene resins, terpene phenol resins or hydrocarbon resins and fillers (e.g. silicates, talc, calcium carbonates, clays or carbon black), plasticisers (e.g. phthalates) or thixotropic agents (e.g. bentones, pyrogenic silicas, urea derivatives, fibrillated or pulped chopped fibres) or pigment pastes or pigments.

Migratory polyisocyanates having a substantially lower vapour pressure than MDI are especially suitable as  
10 adhesion-promoting additives in the embodiment according to the invention.

Mainly triisocyanates, such as e.g. thiophosphoric acid tris(p-isocyanatophenyl ester), triphenylmethane-4,4',4"-  
15 triisocyanate and especially the various isomeric trifunctional homologues of diphenylmethane diisocyanate (MDI), are suitable as migratory, adhesion-promoting polyisocyanates with a substantially lower vapour pressure than MDI. The latter mainly include isocyanato-bis((4-  
20 isocyanatophenyl)methyl)benzene, 2-isocyanato-4-((3-isocyanatophenyl)methyl)-1-((4-isocyanatophenyl)methyl)-benzene, 4-isocyanato-1,2-bis((4-isocyanatophenyl)methyl)benzene, 1-isocyanato-4-((2-isocyanatophenyl)methyl)-2-((3-isocyanatophenyl)methyl)-  
25 benzene, 4-isocyanato- $\alpha$ -1-(o-isocyanatophenyl)- $\alpha$ -3(p-isocyanatophenyl)-m-xylene, 2-isocyanato-(o-isocyanatophenyl)- $\alpha'$ -(p-isocyanatophenyl)-m-xylene, 2-isocyanato-1,3-bis((2-isocyanatophenyl)methyl)benzene, 2-isocyanato-1,4-bis((4-isocyanatophenyl)methyl)benzene, isocyanatobis-  
30 ((isocyanatophenyl)methyl)benzene, 1-isocyanato-2,4-bis((bis((4-isocyanatophenyl)methyl)benzene and mixtures thereof, optionally with a small proportion of higher-functional homologues. Since the trifunctional homologues of diphenylmethane diisocyanate are produced in the same  
35 way as diphenylmethane diisocyanate by the condensation of formaldehyde with aniline with subsequent phosgenation, proportions of diisocyanate are still present in the technical mixture of the trifunctional homologues of MDI,

but this must be no more than 20 wt.%, based on the triisocyanate mixture, and the proportion of tetra- and higher-functional isocyanates must be no more than 25 wt.%.

5 Adducts of diisocyanates and low molecular-weight triols are also suitable as triisocyanates, especially the adducts of aromatic diisocyanates and triols, such as e.g. trimethylolpropane or glycerin. The above restrictions relating to the diisocyanate content and the higher-  
10 functional components also apply to these adducts. Aliphatic triisocyanates, such as e.g. the biuretisation product of hexamethylene diisocyanate (HDI) or the isocyanuratisation product of HDI, or the same trimerisation products of isophorone diisocyanate (IPDI),  
15 are also suitable for the compositions according to the invention, provided that the proportion of diisocyanates is <1 wt.% and the proportion of tetra- and higher-functional isocyanates is no more than 25 wt.%.

20 Owing to their good availability, the aforementioned trimerisation products of HDI and IPDI are particularly preferred.

The aforementioned migratory polyisocyanates can either be incorporated directly in the prepolymer synthesis or,  
25 however, they can be mixed into the prepolymer mixture still in the reaction vessel immediately after the prepolymer synthesis in a so-called "one-pot" reaction. Another option consists in adding the adhesion-promoting, migratory polyisocyanates separately in a later formulation  
30 step.

For use as a laminating adhesive, an addition of epoxy resins, phenolic resins, novolak resins, resol resins or melamine resins and similar may also be necessary to  
35 achieve certain additional properties, such as heat resistance and chemical resistance. In this case, the prepolymers can also be produced in solution, preferably in polar, aprotic solvents. The preferred solvents have a

boiling range of about 50°C to 140°C. Although halogenated hydrocarbons are also suitable, ethyl acetate, methyl ethyl ketone (MEK) or acetone are especially preferred.

5 The adhesive/sealant compositions according to the invention can be used, like the conventional, known polyurethane adhesives/sealants, as a reactive, one- or two-pack adhesive/sealant, as a reactive hot melt adhesive or as a solvent-based adhesive in one- or two-pack form. A  
10 considerable advantage compared with the known polyurethane adhesives/sealants is the significantly smaller proportion of monomeric diisocyanates with a molecular weight of less than 500, which are toxic from a workshop hygiene point of view.

15

#### Examples

##### **1. Production of high molecular-weight diisocyanates**

The monomeric diisocyanates were added to ethyl acetate and  
20 heated to 50°C. The heating was then turned off and the appropriate diol was metered in within 10 minutes. Owing to the heat of reaction, the reaction mixture heated up to approx. 60°C. After a 15 minute reaction period, the mixture was heated to 80°C. A further 15 minutes later, the  
25 catalyst was added and the reaction was continued for a further 30 minutes. Ethyl acetate, chlorobenzene, petrol, acetone, n-heptane and were used as precipitating agents for the high molecular-weight diisocyanate. The properties of the high molecular-weight diisocyanates are listed in  
30 table 1 which follows:

Table 1

Example	Monomeric diisocyanate	Diol <sup>1)</sup>	Molar ratio	Solvent	Catalyst <sup>2)</sup>	Work up <sup>3)</sup>	Monomer content	NCO content
1	MDI	ethylene glycol	10:2	ethyl acetate	2 dr. DBTL	A1	<0.5%	14.1%
2	MDI	NPG	10:1	ethyl acetate	2 dr. DBTL	A2	<0.8%	13.0%
3	MDI	diethylene glycol	10:1	ethyl acetate	2 dr. DBTL	A1	<0.5%	13.0%
4	MDI	1,3-propanediol	10:1	ethyl acetate	2 dr. DBTL	A1	<0.5%	13.9%
5	MDI	NPG	10:1	xylene	-	A1	<0.5%	13.1%
6	MDI	HPN	10:1	ethyl acetate	2 dr. DBTL	A1	<0.6%	11.0%
7	MDI	diethylene glycol	10:2	ethyl acetate	2 dr. DBTL	A3	<0.5%	12.7%
8	MDI	HPN	10:2	ethyl acetate	-	A4	<0.5%	10.7%
9	TDI	ethylene glycol	10:1	ethyl acetate	2 dr. DBTL	A5	<0.6%	19.7%
10	MDI	1,2-propylene glycol	10:4	ethyl acetate	DBTL	A6	<0.8%	13.2%
11	MDI	1,2-propylene glycol	10:2	ethyl acetate	DBTL	A7	<0.6%	13.9%
12	MDI	1,2-propylene glycol	10:2	ethyl acetate	DBTL	A8	<0.6%	19.2%

Notes to the table:

- 1) NPG: neopentyl glycol, HPN: neopentyl glycol hydroxypivalate
- 2) dr.: drops, DBTL: dibutyltin dilaurate
- 3) Methods of working up:
  - 5 A1: isolation after precipitating the reaction mixture during synthesis
  - A2: as A1, followed by crystallising out in a refrigerator to complete the precipitation
  - A3: as A1, filtrate precipitated with hexane
  - 10 A4: crystallisation in refrigerator, precipitation with hexane
  - A5: as A1, then filtrate treated with hexane
  - A6: precipitated and washed with petrol
  - A7: precipitated and washed with petrol and washed
  - 15 with chlorobenzene

As can be seen from the table, the monomer residues can be reduced to less than 0.5 wt.% by subsequent recrystallising/washing of the high molecular-weight diisocyanate in aprotic solvents.

**2. Reaction of the high molecular-weight diisocyanates with polyols**25 Example 13:

The high molecular-weight diisocyanate of example 11 was reacted by a known method with the hydroxyfunctional polyester Dynacoll 7380 (Creanova, polyester of dodecanedioic acid and 1,6-hexanediol, OH value 30) (characteristic number 2.2). The resulting PU prepolymer had an NCO content of 1.97 wt.% (theoretical value 2.01 wt.%) and a viscosity of 24.8 Pa.s at 130°C. The residual monomer content was <0.1 wt.%. This product displayed good properties as a reactive hot melt adhesive.

35

Example 14:

The high molecular-weight diisocyanate of example 12 was reacted with Dynacoll 7380 (characteristic number 2.2) by the same method as example 13. NCO content 2.1 wt.% (theoretical wt.%. This product also displayed good properties as a reactive hot melt adhesive.

Example 15 (comparison):

For comparison purposes, a standard prepolymer for a PU hot melt adhesive consisting of 4,4'-diphenylmethane diisocyanate was reacted with Dynacoll 7380 (characteristic number 2.2). NCO content 2.31 wt.% (theoretical value 2.35 wt.%), viscosity 4.5 Pa.s at 130°C. The residual monomer content was determined as 2.8 wt.%.

While it is true that the compositions according to the invention have a somewhat higher melt viscosity compared with the comparison product, this does not impair their use as hot melt adhesives. The substantial advantage compared with the prior art is the substantially reduced content of monomeric diisocyanate in the hot melt adhesive according to the invention.

Example 16:

In the same way, a high molecular-weight diisocyanate was made from a polypropylene glycol with Mn = 880 and diphenylmethane diisocyanate, from which the monomeric MDI was then removed to the extent that a residual monomer content of 0.1% resulted. A hot melt adhesive was produced from 100 parts of a polyol mixture for a standard polyurethane hot melt adhesive (QR 6202, Henkel) with an average OH value of 32.5 and 76.5 parts of the aforementioned high molecular-weight diisocyanate.

Example 17:

In the same way, a hot melt adhesive was made from 100 parts of a polyol mixture with an average hydroxyl value of 32.5, 6 parts ethylene vinyl acetate copolymer (vinyl

acetate content 28%) and 66.7 parts of the aforementioned high molecular-weight diisocyanate.

Example 18:

- 5 2 wt.% tris(6-isocyanatohexyl) isocyanurate - HDI trimer, residual monomer content 0.2% - was subsequently mixed into the hot melt adhesive according to example 16.

Example 19:

- 10 In the same way as in example 18, 2 wt.% HDI trimer was mixed into the hot melt adhesive of example 2.

Test of suitability for application

- 15 The hot melt adhesives of examples 16 and 18 were tested in comparison with a standard hot melt adhesive from the prior art (PURMELT QR 6202, Henkel), comparative example 21, for their suitability for the film coating of MDF\* (medium-density fibres). The results are summarised in table 2 which follows.



Table 2

Processing	Example 16	Example 21
Roller temperature: [°C]	150	150
Cobwebbing:	very good	very good
Wetting:	1-2	1-2
Wetting profile:	1-2	1-2
Other:		

Test:	Example 16	Example 21
Initial strength of PVC film:	3.5	3.88
Initial strength of veneer:	2.5	2.75
Initial strength of CPL:	2.75	3.0
PVC film adhesion:	1.75	1.75
Veneer adhesion:	1.75	1.75
CPL adhesion:	1.75	1.75
Thermal stability of PVC film: [°C]	148.2	>150
Thermal stability of veneer: [°C]	150.0	>150
Thermal stability of CPL: [°C]	148.2	>150
Low-temperature stability of PVC film: [°C]	<-30	<-30
Low-temperature stability of veneer: [°C]	<-30	<-30
Low-temperature stability of CPL: [°C]	<-30	<-30

The strengths were evaluated by the German school system of marking, with 1 = very good to 5 = unsatisfactory.

As can be seen from the table, the initial strengths of the adhesive according to example 16 are evaluated as significantly better than those of a commercial hot melt adhesive for the same application. Only the thermal stability is lower than with the conventional hot melt adhesive.

When using the adhesive according to the invention as in example 18, the initial strength is also clearly better compared with comparative example 21; the final strength, i.e. the heat resistance reaches values of  $>150^{\circ}\text{C}$  and thus contains a clear improvement compared with example 16. In other words, the requirements both for a very low content of volatile, low molecular-weight diisocyanates and for good adhesion and thermal stability properties are met in this case.

For a window profile coating (primed PVC profile with PVC film), hot melt adhesives from examples 17 and 19 were comparatively tested with a hot melt adhesive from the prior art for this application. The commercial hot melt adhesive from the prior art was PURMELT QR 5300 (Henkel), comparative test 20. The test results are compiled in table 3.

25

Table 3

Example	Profile temperature [°C]	Peel strength [N/mm] after					
		10 min	1 h	4 h	1 d	2 d	7 d
17	20	0.3	0.4	0.8	2.8	2.9	3.1
19	20	0.7	1.7	1.7	3.2	3.7FR	4.2FR
20	20	<0.1	0.1	0.9	2.7	4.3FR	4.7FR
17	53	0.6	0.9	1.0	3.2	2.9	3.1
19	50	1.5	1.9	1.7	3.2	3.6FR	4.3FR
20	50	1.1	1.3	1.4	3.6FR	3.9FR	3.8FR

35

Evaluation of results:

The hot melt adhesive according to example 17 displays very good processing properties, good wetting on the  
5 substrates, cobwebbing on peeling and a somewhat higher initial peel strength than comparative example 20 from the prior art. In the course of the chemical curing reaction, however, the desired film tear without peeling (FR) is not achieved in example 17. In example 19 according to the  
10 invention, not only are high initial peel strengths achieved, but the desired film tear is also achieved after advanced curing of the hot melt adhesive. Here too, the adhesion-improving additive according to the invention brings about clearly improved adhesive properties,  
15 combined with the absence of volatile, low molecular-weight monomeric diisocyanates.

It is clear from the above results that, while it is true that the hot melt adhesives according to examples 17 and  
20 18 have excellent properties in respect of their low content of monomeric, volatile diisocyanates, their adhesion properties are inferior compared with commercial hot melt adhesives based on conventional, low molecular-weight diisocyanates. The hot melt adhesive compositions  
25 according to examples 18 and 19 display adhesion properties equally as good as the conventional hot melt adhesives of the prior art, and in addition, they have the low content of volatile monomeric diisocyanates.

**The claims defining the invention are as follows:**

1. A reactive polyurethane adhesive/sealant composition based on reaction products of one or more polyols and one or more high molecular-weight diisocyanates, wherein the one or more high molecular weight diisocyanates are produced by reaction of  
5 at least one diol having an average molecular weight (number average  $M_n$ ) of less than 2000 with at least one monomeric diisocyanate having a molecular weight of less than 500, and further wherein the one or more high molecular-weight diisocyanates used contain no more than 10 wt.% monomeric diisocyanate before the reaction with the one or more polyols.

10 2. A composition according to claim 1, wherein the at least one monomeric diisocyanate is selected from the group consisting of all isomers of tolylene diisocyanate (TDI) including as a pure isomer and as a mixture of several isomers, 1,5-naphthalene diisocyanate, 4,4'-diphenylmethane diisocyanate, 2,4'-diphenylmethane diisocyanate, xylene diisocyanate (XDI), 4,4'-dicyclohexylmethane diisocyanate ( $H_{12}$ MDI), 1-  
15 isocyanatomethyl-3-isocyanato-1,5,5-trimethyl diisocyanate (isophorone diisocyanate, IPDI), cyclohexane 1,4-diisocyanate, hydrogenated xylylene diisocyanate ( $H_6$ XDI), 1-methyl-2,4-diisocyanato-cyclohexane, hexane-1,6-diisocyanate (HDI), m- or p-tetramethylxylene diisocyanate (m-TMXDI, p-TMXDI) and mixtures thereof.

20 3. A composition according to claim 1 or 2, wherein the at least one diol is selected from the group consisting of  $C_2$ - $C_{18}$  alkanediols including all isomers thereof, ethylene glycol, 1,2-propanediol, 1,3-propanediol, 2,2-dimethyl-1,3-propane-diol, 2-methylpropanediol, 1,6-hexanediol, 2,4,4-trimethyl-1,6-hexanediol, 2,2,4-trimethyl-1,6-hexanediol, 1,4-cyclo-hexane-dimethanol, diethylene glycol, triethylene glycol, tetraethylene glycol, dipropylene glycol, tripropylene glycol, tetrapropylene glycol, poly(oxytetra-methylene) glycol with a molecular weight of up to 650, alkoxylation  
25 products of bisphenol A, alkoxylation products of bisphenol F, alkoxylation products of isomeric dihydroxy-anthracenes, alkoxylation products of isomeric dihydroxy-naphthalenes, alkoxylation products of pyrocatechol, alkoxylation products of resorcinol, alkoxylation products of hydroquinone with up to 8 alkoxy units per aromatic hydroxy  
30 group and mixtures thereof.

4. A composition according to any one of claims 1 to 3, wherein the one or more polyols is selected from the group consisting of difunctional polyethylene glycols, trifunctional polyethylene glycols, polypropylene glycols, random copolymers of ethylene oxide and propylene oxide, block copolymers of ethylene oxide and propylene oxide,

poly(oxytetramethylene) glycols, linear polyester polyols, branched polyester polyols, polycaprolactones, hydroxyfunctional polybutadienes, hydrogenation products of hydroxyfunctional polybutadienes, hydroxyfunctional poly(meth)acrylates and mixtures thereof.

5 5. A composition according to claim 4, wherein the number average of the molecular weight of the one or more polyols is 400 to 20000.

6. A composition according to claim 4 or 5, wherein the number average of the molecular weight is 1000 to 6000.

7. A composition according to any one of claims 1 to 6, wherein the composition  
10 comprises migratory polyisocyanates to promote the adhesion, the polyisocyanates having a substantially lower vapour pressure than diphenylmethane diisocyanate.

8. A composition according to claim 7, wherein the migratory, adhesion-promoting polyisocyanates are selected from the group consisting of thiophosphoric acid tris(p-isocyanatophenyl ester), triphenylmethane-4,4',4''-triisocyanate, isomeric  
15 trifunctional homologues of diphenylmethane diisocyanate (MDI), isomeric trifunctional homologues of isocyanato-bis((4-isocyanatophenyl)-methyl)-benzene, 2-isocyanato-4-((3-isocyanato-phenyl)-methyl)-1-((4-isocyanato-phenyl)-methyl)-benzene, 4 isocyanato-1,2-bis((4-isocyanato-phenyl)methyl)benzene, 1-isocyanato-4-((2-isocyanatophenyl)methyl)-2-((3-isocyanato-phenyl)methyl)-benzene, 4-isocyanato- $\alpha$ -  
20 1-(o-isocyanato-phenyl)- $\alpha$ -3(p-isocyanato-phenyl)-m-xylene, 2-isocyanato-(o-isocyanato phenyl)- $\alpha'$ -(p-isocyanatophenyl)-m-xylene, 2-isocyanato-1,3-bis((2-isocyanatophenyl)methyl)benzene, 2-isocyanato-1,4-bis((4-isocyanatophenyl)methyl)benzene, isocyanatobis((isocyanato-phenyl)-methyl)benzene, 1-isocyanato-2,4-bis((bis((4-isocyanatophenyl)-methyl)-benzene, adducts of diisocyanates and low molecular-weight triols, adducts of diisocyanates and trimethylolpropane, adducts of diisocyanates and glycerin, adducts of aromatic diisocyanates and triols, adducts of aromatic diisocyanates and trimethylolpropane, adducts of aromatic diisocyanates and glycerin, biuretisation product of hexamethylene diisocyanate (HDI), isocyanuratisation product of HDI, trimerisation products of isophorone diisocyanate  
30 (IPDI) and mixtures thereof.

9. A reactive polyurethane adhesive sealant composition substantially as hereinbefore described with reference to any one of the examples.

10. A process for the production of a composition according to any one of the preceding claims, wherein

a) in a first step, the diol component is reacted with a stoichiometric excess of monomeric diisocyanate to give a high molecular-weight diisocyanate,

b) the high molecular weight diisocyanate is precipitated out of the reaction mixture, optionally by adding a non-solvent for the high molecular-weight diisocyanate,

5 c) the high molecular weight diisocyanate is separated from unreacted monomeric diisocyanate by way of filtration or centrifugation and

d) in a second step the high molecular-weight diisocyanate is reacted with one or more polyols so that a reactive prepolymer with isocyanate terminal groups is formed.

10 11. A process for the production of a composition according to any one of claims 1 to 9, wherein

a) in a first step, the diol component is reacted with a stoichiometric excess of monomeric diisocyanate to give a high molecular-weight diisocyanate,

b) the excess monomeric diisocyanate is removed from the reaction mixture by distillation, and

15 c) in a second step the high molecular-weight diisocyanate is reacted with one or more polyols so that a reactive prepolymer with isocyanate terminal groups is formed.

12. A process for the production of a composition according to any one of claims 1 to 9, wherein

20 a) in a first step, the diol component is reacted with a stoichiometric excess of monomeric diisocyanate to give a high molecular-weight diisocyanate,

b) the excess monomeric diisocyanate is removed from the reaction mixture by selective extraction and

c) in a second step the high molecular-weight diisocyanate is reacted with one or more polyols so that a reactive prepolymer with isocyanate terminal groups is formed.

25 13. A process according to any one of claims 10 to 12, wherein the adhesion-promoting polyisocyanate according to claim 7 or 8 is added directly in the second step during the production of the reactive prepolymer with isocyanate terminal groups.

30 14. A process according to any one of claims 10 to 12, wherein the adhesion-promoting polyisocyanate is mixed into the prepolymer mixture immediately after the prepolymer synthesis.

15 15. A process for the production of a polyurethane adhesive composition, wherein an adhesion-promoting polyisocyanate according to claim 7 or 8 is added, by mixing, to a reactive prepolymer with isocyanate terminal groups produced by a process according to 10 to 12 during the formulation of the adhesive composition.

16. A process according to claims 10 to 15, wherein, in the second step, the NCO/OH ratio is 1.2:1 to 5:1.

17. Use of a composition according to any one of claims 1 to 9 as a binder for a reactive one-pack adhesive/ sealant, two-pack adhesive/ sealant, reactive hot melt adhesive or a solvent-based adhesive.

18. A process for the production of a reactive polyurethane adhesive sealant composition comprising the steps substantially as hereinbefore described with reference to any one of the examples.

19. A composition produced by the process of any one of claims 10 to 16 or 18.

**Dated 5 April, 2004**

**Henkel Kommanditgesellschaft auf Aktien**

**Patent Attorneys for the Applicant/Nominated Person  
SPRUSON & FERGUSON**