

(12) PATENT
(19) AUSTRALIAN PATENT OFFICE

(11) Application No. **AU 200070017 B2**
(10) Patent No. **769434**

(54) Title
Polyethylene moulding compound with an improved ESCR-stiffness relation and an improved swelling rate, a method for the production thereof and the use thereof

(51)⁶ International Patent Classification(s)
C08F 010/02 C08L 023/06
C08F 002/00

(21) Application No: **200070017** (22) Application Date: **2000.09.09**

(87) WIPO No: **WO01/23446**

(30) Priority Data

(31) Number	(32) Date	(33) Country
19945980	1999.09.24	DE

(43) Publication Date : **2001.04.30**
(43) Publication Journal Date : **2001.06.28**
(44) Accepted Journal Date : **2004.01.29**

(71) Applicant(s)
Basell Polyolefine GmbH

(72) Inventor(s)
Joachim Berthold; Ludwig Bohm; Johannes-Friedrich Enderle ; Reinhard Schubbach

(74) Agent/Attorney
Davies Collison Cave,GPO Box 3876,SYDNEY NSW 2001

(56) Related Art
US 5422400
EP 129312
GB 2056996

AU 200070017

(12) NACH DEM VERTRAG ÜBER DIE INTERNATIONALE ZUSAMMENARBEIT AUF DEM GEBIET DES
PATENTWESENS (PCT) VERÖFFENTLICHTE INTERNATIONALE ANMELDUNG

(19) Weltorganisation für geistiges Eigentum
Internationales Büro



(43) Internationales Veröffentlichungsdatum
5. April 2001 (05.04.2001)

PCT

(10) Internationale Veröffentlichungsnummer
WO 01/23446 A1

(51) Internationale Patentklassifikation: C08F 10/02,
2/00, C08L 23/06, C08F 23/16

(21) Internationales Aktenzeichen: PCT/EP00/08817

(22) Internationales Anmeldedatum:
9. September 2000 (09.09.2000)

(25) Einreichungssprache: Deutsch

(26) Veröffentlichungssprache: Deutsch

(30) Angaben zur Priorität:
199 45 980.0 24. September 1999 (24.09.1999) DE

(71) Anmelder (für alle Bestimmungsstaaten mit Ausnahme von
US): BASELL POLYOLEFINE GMBH [DE/DE]; Am
Yachthafen 2, D-77694 Kehl (DE).

(72) Erfinder; und

(75) Erfinder/Anmelder (nur für US): BERTHOLD, Joachim

[DE/DE]; Am Flachland 54, D-65779 Kelkheim (DE).
BÖHM, Ludwig [DE/DE]; Leonhardstrasse 36, D-65795
Hattersheim (DE). ENDERLE, Johannes-Friedrich
[DE/DE]; Spohrstrasse 36, D-60318 Frankfurt (DE).
SCHUBBACH, Reinhard [DE/DE]; Hölzweg 17,
D-83346 Bergen (DE).

(81) Bestimmungsstaaten (national): AU, BR, CA, CN, IN, JP,
KR, RU, US, ZA.

(84) Bestimmungsstaaten (regional): europäisches Patent (AT,
BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC,
NL, PT, SE).

Veröffentlicht:

— Mit internationalem Recherchenbericht.

Zur Erklärung der Zweibuchstaben-Codes, und der anderen
Abkürzungen wird auf die Erklärungen ("Guidance Notes on
Codes and Abbreviations") am Anfang jeder regulären Ausgabe
der PCT-Gazette verwiesen.

WO 01/23446 A1

(54) Title: POLYETHYLENE MOULDING COMPOUND WITH AN IMPROVED ESCR-STIFFNESS RELATION AND AN
IMPROVED SWELLING RATE, A METHOD FOR THE PRODUCTION THEREOF AND THE USE THEREOF

(54) Bezeichnung: POLYETHYLEN FORMMASSE MIT VERBESSERTER ESCR-STEIFIGKEITSRELATION UND
SCHWELLRATE, VERFAHREN ZU IHRER HERSTELLUNG UND IHRE VERWENDUNG

(57) Abstract: The invention relates to a polyethylene moulding compound with multimodal molar weight distribution. Said mould-
ing compound is provided with a total density of $\geq 0.940 \text{ g/cm}^3$ and an $\text{MFI}_{190/5}$ in the range of 0.01 to 10 dg/min. The inventive
moulding compound contains 30 to 60 wt. % of low-molecular ethylene homopolymer A which is provided with a viscosity number
 VZ_A in the range of 40 to 150 cm^3/g . The moulding compound also comprises 30 to 65 wt. % of a high-molecular copolymer B
consisting of ethylene and an additional olefin with 4 to 10 C-atoms and having a viscosity number VZ_B in the range of 150 to 800
 cm^3/g . Said moulding compound further comprises 1 to 30 wt. % of ultrahigh-molecular ethylene homopolymer C which is provided
with a viscosity number VZ_C in the range of 900 to 3,000 cm^3/g . The invention also relates to a method for producing the moulding
compound in a three-step process and to the use thereof for producing hollow bodies.

(57) Zusammenfassung: Die Erfindung betrifft eine Polyethylen-Formmasse mit multimodaler Molmassenverteilung, die eine Ge-
samtdichte von $\geq 0.940 \text{ g/cm}^3$ besitzt und einen $\text{MFI}_{190/5}$ im Bereich von 0,01 bis 10 dg/min. Die erfindungsgemäße Formmasse
enthält eine Menge von 30 bis 60 Gew.-% an niedermolekularem Ethylenhomopolymer A, das eine Viskositätszahl VZ_A im Bereich
von 40 bis 150 cm^3/g besitzt, eine Menge von 30 bis 65 Gew.-% an hochmolekularem Copolymer B aus Ethylen und einem weiteren
Olefin mit 4 bis 10 C-Atomen, das eine Viskositätszahl VZ_B im Bereich von 150 bis 800 cm^3/g besitzt, und eine Menge von 1 bis 30
Gew.-% an ultrahochmolekularem Ethylenhomopolymer C, das eine Viskositätszahl VZ_C im Bereich von 900 bis 3000 cm^3/g besitzt.
Die Erfindung betrifft auch ein Verfahren zum Herstellen der Formmasse in einem Dreistufenprozess und ihre Verwendung für die
Herstellung von Hohlkörpern.

Polyethylene moulding compound with an improved ESCR/stiffness relation and an improved swelling rate, a method for the production thereof and the use thereof

The present invention relates to a polyethylene moulding compound having a multi-modal molecular weight distribution and to a method for the production of this

5 moulding compound in the presence of a catalytic system comprising a Ziegler catalyst and co-catalyst via a multistep reaction sequence consisting of successive liquid-phase polymerizations, and to hollow articles produced from the moulding compound by extrusion blow moulding.

10

Polyethylene is widely used for the production of mouldings and containers since it is a material having a low inherent weight which nevertheless has particularly high mechanical strength, high corrosion resistance to moisture and water in combination with atmospheric oxygen and absolutely reliable long-term resistance and since

15 polyethylene has good chemical resistance and in particular can easily be processed for bottles, canisters and fuel tanks in motor vehicles.

EP-A-603,935 has already described a moulding compound based on polyethylene which has a bimodal molecular weight distribution and which is also suitable, inter

20 alia, for the production of pipes.

A raw material having an even broader molecular weight distribution is described in US Patent 5,338,589 and is prepared using a highly active catalyst disclosed in WO 91/18934 in which magnesium alkoxide is employed in the form of a gelatinous

25 suspension. Surprisingly, it has been found that the use of this material in mouldings, in particular in pipes, facilitates a simultaneous improvement in the properties of stiffness and creep tendency, which are usually contradictory in partially crystalline thermoplastics, on the one hand, and stress cracking resistance and toughness on the other hand.

30

The known bimodal products are distinguished, in particular, by good processing properties at the same time as an outstanding stress cracking/stiffness ratio. This combination of properties is of particular importance in the production of hollow articles from plastics, such as bottles, canisters and fuel tanks in motor vehicles. In

5 addition to this property combination, however, the production of plastic hollow articles requires the highest possible swelling rate of the plastic melt, since the swelling rate is directly responsible for enabling the optimum setting of wall thickness control, the formation of the weld line and the weldability in industrial production in extrusion blow moulding.

10

It is known that plastics having high swelling rates can be produced well using so-called Phillips catalysts, i.e. polymerization catalysts based on chromium compounds. However, the plastics produced in this way have an unfavourable stress cracking/stiffness ratio compared with the known plastics having a bimodal molecular weight distribution.

15

EP-A-0 797 599 discloses a process which even gives a polyethylene having a trimodal molecular weight distribution in successive gas-phase and liquid-phase polymerizations. Although this polyethylene is already very highly suitable for the
20 production of hollow articles in extrusion blow moulding plants, it is, however, still in need of further improvement in its processing behaviour owing to the plastic melt swelling rate, which is still too low.

The present invention seeks to develop a polyethylene moulding

25

compound by means of which an even better ratio of stiffness to stress cracking resistance compared with all known materials can be achieved and which, in addition, has a high swelling rate of its melt, which, in the production of hollow articles by the extrusion blow moulding process, not only enables optimum wall thickness control, but at the same time also facilitates excellent weld line formation and wall
30 thickness distribution.

This is achieved by a moulding compound of the generic type mentioned at the outset, whose characterizing features are to be regarded as being that it comprises from 30 to 60% by weight of a low-molecular-weight ethylene homopolymer A, from 65 to 30% by weight of a high-molecular-weight copolymer

- 5 B comprising ethylene and another olefin having from 4 to 10 carbon atoms, and from 1 to 30% by weight of an ultrahigh-molecular-weight ethylene homopolymer or copolymer C, where all percentages are based on the total weight of the moulding compound.

- 10 The invention furthermore also relates to a method for the production of this moulding compound in cascaded suspension polymerization, and to hollow articles made from this moulding compound with very excellent mechanical strength properties.

- 15 The polyethylene moulding compound according to the invention has a density in the range $\geq 0.940 \text{ g/cm}^3$ at a temperature of 23°C and has a broad trimodal molecular weight distribution. Preferably, the high-molecular-weight copolymer B comprises small proportions of up to 5% by weight of further olefin monomer units having from 4 to 10 carbon atoms. Examples of comonomers of this type are 1-
20 butene, 1-pentene, 1-hexene, 1-octene or 4-methyl-1-pentene. The ultrahigh-molecular-weight ethylene homopolymer or copolymer C may optionally also comprise an amount of from 0 to 10% by weight of one or more of the above-mentioned comonomers.

- 25 The polyethylene moulding compound preferably has excellent convertibility into hollow articles, expressed by a swelling rate in the range from 100 to 300%.

The moulding compound according to the invention furthermore has a melt flow index, in accordance with ISO 1133, expressed as $\text{MFI}_{190/5}$, in the range from 0.01

- 30 to 10 dg/min and a viscosity number VN_{tot} , measured in accordance with ISO/R

3a

1191 in decalin at a temperature of 135°C, in the range from 190 to 700 cm³/g, preferably from 250 to 500 cm³/g.

As now claimed, according to one aspect, the present invention provides

- 5 polyethylene moulding compound having a trimodal molecular weight distribution which has an overall density of ≥ 0.940 g/cm³, at a temperature of 23°C, and an MFI_{190/5} in the range from 0.01 to 10 dg/min, characterized in that it comprises an amount of from 30 to 60% by weight of low-molecular-weight ethylene homopolymer A which has a viscosity number VN_A in the range from 40 to 150
- 10 cm³/g, an amount of from 30 to 65% by weight of high-molecular-weight copolymer B comprising ethylene and a further olefin having from 4 to 10 carbon atoms which has a viscosity number VN_B in the range from 150 to 800 cm³/g, and an amount of from 1 to 30% by weight of ultrahigh-molecular-weight ethylene homopolymer or copolymer C which has a viscosity number VN_C in the range from 900 to 3000
- 15 cm³/g.

The trimodality can be described as a measure of the position of the centres of the

three individual molecular weight distributions with the aid of the viscosity numbers VN in accordance with ISO/R 1191 of the polymers formed in the successive polymerization steps. The following band widths of the polymers formed in the individual reaction steps should be taken into account here:

5

The viscosity number VN_1 measured on the polymer after the first polymerization step is identical with the viscosity number VN_A of the low-molecular-weight polyethylene A and is in accordance with the invention in the range from 40 to 180 cm³/g.

10

VN_B of the relatively high-molecular-weight polyethylene B formed in the second polymerization step can be calculated from the following mathematical formula:

$$VN_B = \frac{VN_2 - w_1 \cdot VN_1}{1 - w_1}$$

- 15 where w_1 represents the proportion by weight of the low-molecular-weight polyethylene formed in the first step, measured in % by weight, based on the total weight of the polyethylene having a bimodal molecular weight distribution formed in the first two steps, and VN_2 represents the viscosity number measured on the polymer after the second polymerization step. The value calculated for VN_B is normally in the
20 range from 150 to 800 cm³/g.

VN_C for the ultrahigh-molecular-weight homopolymer or copolymer C formed in the third polymerization step is calculated from the following mathematical formula:

$$VN_C = \frac{VN_3 - w_2 \cdot VN_2}{1 - w_2}$$

- 25 where w_2 represents the proportion by weight of the polyethylene having a bimodal molecular weight distribution formed in the first two steps, measured in % by weight,

5

10

1
2

2
3

fr. de ...
main
... (linea)

weight, based on the total weight of the mixture.

The moulding compound according to the invention is particularly suitable for the production of hollow articles, such as fuel canisters, chemical-resistant containers, canisters, drums and bottles, by firstly plasticating the polyethylene moulding compound in an extruder at temperatures in the range from 200 to 250°C, and then extruding the compound through a die into a blow mould, and cooling it therein.

For conversion into hollow articles, use can be made of both conventional single-screw extruders having a smooth feed zone and high-performance extruders having a finely grooved barrel and forced conveying feed section. The screws are typically designed as decompression screws with a length of from 25 to 30 D (D = diameter). The decompression screws have a discharge zone in which temperature differences in the melt are compensated and in which the relaxation stresses formed due to shearing are intended to be dissipated.

Example 1 (according to the invention):

The polymerization of ethylene was carried out in a continuous method in three reactors connected in series. A Ziegler catalyst, a sufficient amount of suspension medium, ethylene and hydrogen were fed into the first reactor. The amount of ethylene and hydrogen was set in such a way that one part by volume of hydrogen was present per nine parts by volume of ethylene.

The catalyst was a Ziegler catalyst as described in Example 2 of WO 91/18934, which had the catalyst component a having the operation number 2.2 therein, and which is added together with a co-catalyst comprising an organometallic compound of a metal from group I, II or III of the Periodic Table of the Elements.

The catalyst was metered continuously into the first reactor with the co-catalyst and

usert, 1987
a...
/...die G.../

The polymerization in the first reactor was carried out at a temperature of 76°C and a pressure of 0.78 MPa for a period of 3.3 hours with a hydrogen content in the gas space of from 67 to 68% by volume.

The polymerization in the second reactor was carried out at a temperature of 84°C and a pressure of 0.5 MPa for a period of 54 minutes.

The polymerization in the third reactor was carried out at a temperature of 47°C and
20 a pressure of ≤ 0.23 MPa for a period of 30 minutes.

25 The viscosity numbers and proportions w_A , w_B and w_C of polymer A, B and C applying to the polyethylene moulding compound produced in accordance with Example 1 are given in Table 1 shown below together with the corresponding data for the moulding compounds produced in accordance with the following Examples 2 to 4.

man Sorant

Example 2 (according to the invention)

Example 1 was repeated with the following changes:

- 5 The polymerization in the first reactor was carried out at a temperature of 82°C and a pressure of 0.89 MPa for a period of 2.6 hours with a hydrogen content of 68% by volume in the gas space of the reactor.

- 10 The suspension from the first reactor was then transferred into a second reactor, in which the amount of hydrogen had been reduced to 10 parts by volume in the gas space of the reactor and the amount of C₄ comonomer had been increased to 0.7 parts by volume in the gas space of the reactor. The reduction in the amount of hydrogen was again carried out via interim H₂ decompression.

- 15 The polymerization in the second reactor was carried out at a temperature of 80°C and a pressure of 0.37 MPa for a period of 66 minutes.

- 20 The suspension from the second reactor was transferred into the third reactor, and the amount of hydrogen in the gas space of the third reactor was set to 0.6% by volume and that of C₄ comonomer to 0.8% by volume.

The polymerization in the third reactor was carried out at a temperature of 80°C and a pressure of 0.15 MPa for a period of 36 minutes.

- 25 The viscosity numbers and proportions w_A, w_B and w_C of polymer A, B and C applying to the polyethylene moulding compound produced in accordance with Example 2 are given in Table 1 shown below together with the corresponding data for the moulding compounds produced in accordance with the other examples.

er
und
us
D
/
/

Example 3 (according to the invention)

Example 2 was repeated with the following changes:

The polymerization in the first reactor was carried out at a temperature of 80°C and a
5 pressure of 0.74 MPa for a period of 2.1 hours with a hydrogen content of 65% by
volume in the gas space of the reactor.

The suspension from the first reactor was then transferred into a second reactor, in which the amount of hydrogen had been reduced to 4.1 parts by volume in the gas space of the reactor and the amount of C₄ comonomer had been increased to 1.1 parts by volume in the gas space of the reactor. The reduction in the amount of hydrogen was again carried out via interim H₂ decompression.

The polymerization in the second reactor was carried out at a temperature of 80°C
15 and a pressure of 0.24 MPa for a period of 54 minutes.

The suspension from the second reactor was transferred into the third reactor, and the amount of hydrogen in the gas space of the third reactor was set to 1.1% by volume and that of C₄ comonomer to 0.8% by volume.

The polymerization in the third reactor was carried out at a temperature of 60°C and a pressure of 0.12 MPa for a period of 30 minutes.

25 The viscosity numbers and proportions w_A , w_B and w_C of polymer A, B and C applying to the polyethylene moulding compound produced in accordance with Example 3 are given in Table 1 shown below together with the corresponding data for the moulding compounds produced in accordance with the other examples.

gli
No

an
ipl

an

Example 4 (according to the invention)

Example 3 was repeated with the following changes:

5 The polymerization in the first reactor was carried out at a temperature of 80°C and a pressure of 0.82 MPa for a period of 2.2 hours with a hydrogen content of 74% by volume in the gas space of the reactor.

10 The suspension from the first reactor was then transferred into a second reactor, in which the amount of hydrogen had been reduced to 4.0 parts by volume in the gas space of the reactor and the amount of C₄ comonomer had been increased to 1.3 parts by volume in the gas space of the reactor. The reduction in the amount of hydrogen was again carried out via interim H₂ decompression.

15 The polymerization in the second reactor was carried out at a temperature of 80°C and a pressure of 0.20 MPa for a period of 54 minutes.

20 The suspension from the second reactor was transferred into the third reactor, and the amount of hydrogen in the gas space of the third reactor was set to 1.0% by volume and that of C₄ comonomer to 1.0% by volume.

The polymerization in the third reactor was carried out at a temperature of 60°C and a pressure of 0.08 MPa for a period of 30 minutes.

25 The viscosity numbers and proportions w_A, w_B and w_C of polymer A, B and C applying to the polyethylene moulding compound produced in accordance with Example 2 are given in Table 1 shown below together with the corresponding data for the moulding compounds produced in accordance with the other examples.

ch
car10
-U

fu

Comparative Example (CE):

Example 1 was repeated, but with the difference that the polymerization was terminated after the second reaction step.

5

The polymerization in the first reactor was carried out at a temperature of 84°C and a pressure of 0.90 MPa for a period of 4.2 hours with a hydrogen content of 76% by volume in the gas space of the reactor.

10 The suspension from the first reactor was then transferred into a second reactor, in which the amount of hydrogen had been reduced to 3.0 parts by volume in the gas space of the reactor and the amount of C₄ comonomer had been increased to 1.9 parts by volume in the gas space of the reactor. The reduction in the amount of hydrogen was again carried out via interim H₂ decompression.

15

The polymerization in the second reactor was carried out at a temperature of 83°C and a pressure of 0.21 MPa for a period of 80 minutes.

20 This gave a polyethylene having a bimodal molecular weight distribution, as corresponds to the prior art in accordance with EP-A 603 935.

30
3030
3030
30

Table 1

Example	1	2	3	4	CE
W _A	0.35	0.45	0.55	0.55	0.52
W _B	0.55	0.45	0.35	0.35	0.48
W _C	0.10	0.10	0.10	0.10	0
VN ₁ [cm ³ /g]	80	80	100	60	55
MFR(2)	3.5	2.3	2.3	2.0	0.7
MFR(3)	1.2	0.7	0.55	0.56	---
MFR/5 [g/10']	1.07	0.55	0.30	0.36	0.4
MFR/21.6 [g/10']	17.9	11	9.5	13.8	13.4
FRR 21.6/5	17	20	31.6	36.3	33.6
VN _{tot} [cm ³ /g]	306	325	392	373	329
Density [g/cm ³]	0.954	0.952	0.953	0.954	0.954
FT 0°C [kJ/m ²]	9.6	10.7	12.6	7.8	6
FCM [N/mm ²]	1270	1200	1240	1280	1275
SR rheometer [%]	200	151	153	143	91
SCR [h]	3.7	16	54.2	54.1	39

150
170
180
190
200
210
220
230
240
250
260
270
280
290
300
310
320
330
340
350
360
370
380
390
400
410
420
430
440
450
460
470
480
490
500
510
520
530
540
550
560
570
580
590
600
610
620
630
640
650
660
670
680
690
700
710
720
730
740
750
760
770
780
790
800
810
820
830
840
850
860
870
880
890
900
910
920
930
940
950
960
970
980
990
1000

The abbreviations for the physical properties in Table 1 have the following meanings:

- FCM = flexural creep modulus, measured in accordance with ISO 54852-Z4 in N/mm² as the one-minute value,
- 5 - SCR = stress cracking resistance of the moulding compound according to the invention. It is determined by an internal measurement method. This laboratory method has been described by M. Fleißner in Kunststoffe 77 (1987), pp. 45 ff. This publication shows that there is a correlation between the determination of slow crack growth in the creep test on test bars with all-round notches and the brittle branch in the long-term failure test under internal hydrostatic pressure in accordance with ISO 1167. A shortening of the time to failure is achieved by shortening the crack initiation time by the notches (1.6 mm/razor blade) in ethylene glycol as stress crack-promoting medium at 10 a temperature of 80°C and a tensile stress of 3.5 MPa. The samples are produced by sawing three test specimens measuring 10 x 10 x 90 mm out of a pressed sheet with a thickness of 10 mm. The test specimens are provided with all-round notches in the centre using a razor blade in a notching device produced especially for the purpose (shown in Figure 5 in the publication by 15 Fleißner). The notch depth is 1.6 mm.
- FT = fracture toughness of the moulding compound according to the invention. It is likewise determined by an internal measurement method on test bars measuring 10 x 10 x 80 mm which had been sawn out of a pressed 25 sheet with a thickness of 10 mm. Six of these test bars are notched in the centre using a razor blade in the notching device mentioned above. The notch depth is 1.6 mm. The measurement is carried out substantially in accordance with the Charpy measurement method in accordance with ISO 179 with modified test specimens and modified impact geometry (distance between supports). All test specimens are conditioned to the measurement temperature of 30

1.6 mm
razor blade

- 0°C over a period of from 2 to 3 hours. A test specimen is then placed without delay onto the support of a pendulum impact tester in accordance with ISO 179. The distance between the supports is 60 mm. The drop of the 2 J hammer is triggered, with the drop angle being set to 160°, the pendulum length to 225 mm and the impact velocity to 2.93 m/sec. In order to evaluate the measurement, the quotient of the impact energy consumed and the initial cross-sectional area at the notch a_{FM} in mJ/mm^2 is calculated. Only values for complete fracture and hinge fracture can be used here as the basis for a common mean (see ISO 179).
- 5
- 10
- SR = swelling rate, measured in a high-pressure capillary rheometer at a shear rate of 1440 1/s in a 2/2 round-hole die with a conical entry (angle = 15°) at a temperature of 190°C.
- 15
- The measurement values clearly show that the moulding compound according to the invention in all cases resulted in better strength properties and also had better processing properties during production.

/ 107 Vessel

/ 107 Vessel

15a

Throughout this specification and the claims which follow, unless the context requires otherwise, the word "comprise", or variations such as "comprises" or "comprising", will be understood to imply the inclusion of a stated integer or step or group of integers or steps but not the exclusion of any other integer or step or
5 group of integers or steps.

The reference to any prior art in this specification is not, and should not be taken as, an acknowledgment or any form of suggestion that the prior art forms part of the common general knowledge in Australia.

15a

15a

THE CLAIMS DEFINING THE INVENTION ARE AS FOLLOWS:

1. Polyethylene moulding compound having a trimodal molecular weight distribution which has an overall density of $\geq 0.940 \text{ g/cm}^3$, at a temperature of 23°C, and an $\text{MFI}_{190/5}$ in the range from 0.01 to 10 dg/min, characterized in that it comprises an amount of from 30 to 60% by weight of low-molecular-weight ethylene homopolymer A which has a viscosity number VN_A in the range from 40 to 150 cm^3/g , an amount of from 30 to 65% by weight of high-molecular-weight copolymer B comprising ethylene and a further olefin having from 4 to 10 carbon atoms which has a viscosity number VN_B in the range from 150 to 800 cm^3/g , and an amount of from 1 to 30% by weight of ultrahigh-molecular-weight ethylene homopolymer or copolymer C which has a viscosity number VN_C in the range from 900 to 3000 cm^3/g .
2. Polyethylene moulding compound according to Claim 1, characterized in that it has excellent convertibility into hollow articles, expressed by a swelling rate in the range from 100 to 300%.
3. Polyethylene moulding according to claim 1 or claim 2 wherein polymer B comprises up to 5% by weight of the further olefin.
4. Method for the production of a polyethylene moulding compound according to Claim 1, in which the polymerization of the monomers is carried out in suspension at temperatures in the range from 20 to 120°C, a pressure in the range from 2 to 60 bar and in the presence of a highly active Ziegler catalyst composed of a transition-metal compound and an organoaluminium compound, characterized in that the polymerization is carried out in three steps, with the molecular weight of the polyethylene produced in each step in each case being regulated with the aid of hydrogen.
5. Use of a polyethylene moulding compound according to Claim 1 for the

production of hollow articles, such as fuel tanks, canisters, drums or bottles, where the polyethylene moulding compound is firstly plasticated in an extruder at temperatures in the range from 200 to 250°C and then extruded through a die into a blow mould and cooled therein.

5

6. Polyethylene moulding compound, as hereinbefore described with reference to the examples.

DATED THIS 29th day of October, 2003.

10

BASELL POLYOLEFINE GMBH

By Its Patent Attorneys

DAVIES COLLISON CAVE

5
6
7
8
9

10
11
12
13
14