

**(12) PATENT**  
**(19) AUSTRALIAN PATENT OFFICE**

**(11) Application No. AU 199912910 B2**  
**(10) Patent No. 736400**

(54) Title  
Biodegradable thermoplastic composition

(51)<sup>6</sup> International Patent Classification(s)  
C08L 067/04 C08L 067/02  
A61L 015/62 D01F 006/92

(21) Application No: 199912910 (22) Application Date: 1998 .10 .30

(87) WIPO No: WO99/23163

(30) Priority Data

(31) Number 08/962432	(32) Date 1997 .10 .31	(33) Country US
-----------------------	------------------------	-----------------

(43) Publication Date : 1999 .05 .24  
(43) Publication Journal Date : 1999 .07 .22  
(44) Accepted Journal Date : 2001 .07 .26

(71) Applicant(s)  
Kimberly-Clark Worldwide, Inc.

(72) Inventor(s)  
Fu-Jya Tsai; Brian T. Etzel

(74) Agent/Attorney  
SPRUSON and FERGUSON, GPO Box 3898, SYDNEY NSW 2001

(56) Related Art  
JP 10-110332  
JP 10-102323  
EP 765913

12910/99

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>6</sup> : <b>C08L 67/04, 67/02, A61L 15/62, D01F 6/92 // (C08L 67/04, 67:02) (C08L 67/02, 67:04)</b>		A1	(11) International Publication Number: <b>WO 99/23163</b> (43) International Publication Date: <b>14 May 1999 (14.05.99)</b>
<p>(21) International Application Number: <b>PCT/US98/23068</b></p> <p>(22) International Filing Date: <b>30 October 1998 (30.10.98)</b></p> <p>(30) Priority Data: 08/962,432 31 October 1997 (31.10.97) US</p> <p>(71) Applicant: <b>KIMBERLY-CLARK WORLDWIDE, INC.</b> [US/US]; 401 North Lake Street, Neenah, WI 54956 (US).</p> <p>(72) Inventors: <b>TSAI, Fu-Jya</b>; 2517 Gatewood Drive, Appleton, WI 54915 (US). <b>ETZEL, Brian, T.</b>; 3 Pamela Court, Appleton, WI 54915 (US).</p> <p>(74) Agents: <b>CONNELLY, Thomas, J. et al.</b>; Kimberly-Clark Worldwide, Inc., 401 North Lake Street, Neenah, WI 54956 (US).</p>		<p>(81) Designated States: <b>AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, HR, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).</b></p> <p><b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p> <div style="border: 1px solid black; padding: 5px; text-align: center;"> <b>IP AUSTRALIA</b>  <b>24 MAY 1999</b>  <b>RECEIVED</b> </div>	
<p>(54) Title: <b>BIODEGRADABLE THERMOPLASTIC COMPOSITION</b></p> <p>(57) Abstract</p> <p>Disclosed is a thermoplastic composition comprising an unreacted mixture of a poly(lactic acid) polymer; a polybutylene succinate polymer or a polybutylene succinate adipate polymer, or a mixture of such polymers; and a wetting agent. The thermoplastic composition exhibits substantial biodegradable properties yet is easily processed. The thermoplastic composition is useful in making multicomponent fibers or nonwoven structures that may be used in a disposable absorbent product intended for the absorption of fluids such as body fluids.</p>			

## Biodegradable Thermoplastic Composition

### Background of the Invention

#### Field of the Invention

The present invention relates to a thermoplastic composition. The thermoplastic composition 5 comprises a substantially unreacted mixture of a poly(lactic acid) polymer, a polybutylene succinate polymer or a polybutylene succinate adipate polymer or a mixture of such polymers, and a wetting agent. The thermoplastic composition suitably exhibits substantial biodegradable properties yet is easily processed. The thermoplastic composition is useful in making multicomponent fibers or nonwoven structures that may be used in a disposable absorbent product intended for the 10 absorption of fluids such as body fluids.

#### Description of the Related Art

Disposable absorbent products currently find widespread use in many applications. For example, in the infant and child care areas, diapers and training pants have generally replaced reusable cloth absorbent articles. Other typical disposable absorbent products include feminine care products such as sanitary napkins or tampons, adult incontinence products, and health care products such as surgical drapes or wound dressings. A typical disposable absorbent product generally comprises a composite structure including a topsheet, a backsheet, and an absorbent structure between the topsheet and backsheet. These products usually include some type of fastening system for fitting the product onto the wearer.

15

Disposable absorbent products are typically subjected to one or more liquid insults, such as of water, urine, menses, or blood, during use. As such, the outer cover backsheet materials of the disposable absorbent products are typically made of liquid-insoluble and liquid impermeable materials, such as polypropylene films, that exhibit a sufficient strength and handling capability so that the disposable absorbent product retains its integrity during use by a wearer and does not 20 allow leakage of the liquid insulting the product.

25

Although current disposable baby diapers and other disposable absorbent products have been generally accepted by the public, these products still have need of improvement in specific areas. For example, many disposable absorbent



products can be difficult to dispose of. For example, attempts to flush many disposable absorbent products down a toilet into a sewage system typically lead to blockage of the toilet or pipes connecting the toilet to the sewage system. In particular, the outer cover materials typically used in the disposable absorbent

5 products generally do not disintegrate or disperse when flushed down a toilet so that the disposable absorbent product cannot be disposed of in this way. If the outer cover materials are made very thin in order to reduce the overall bulk of the disposable absorbent product so as to reduce the likelihood of blockage of a toilet or a sewage pipe, then the outer cover material typically will not exhibit sufficient

10 strength to prevent tearing or ripping as the outer cover material is subjected to the stresses of normal use by a wearer.

Furthermore, solid waste disposal is becoming an ever increasing concern throughout the world. As landfills continue to fill up, there has been an increased demand for material source reduction in disposable products, the incorporation of

15 more recyclable and/or degradable components in disposable products, and the design of products that can be disposed of by means other than by incorporation into solid waste disposal facilities such as landfills.

As such, there is a need for new materials that may be used in disposable absorbent products that generally retain their integrity and strength during use, but

20 after such use, the materials may be more efficiently disposed of. For example, the disposable absorbent product may be easily and efficiently disposed of by composting. Alternatively, the disposable absorbent product may be easily and efficiently disposed of to a liquid sewage system wherein the disposable absorbent product is capable of being degraded.

25 Although degradable monocomponent fibers are known, problems have been encountered with their use. In particular, known degradable fibers typically do not have good thermal dimensional stability such that the fibers usually undergo severe heat-shrinkage due to the polymer chain relaxation during downstream heat treatment processes such as thermal bonding or lamination.

30 For example, although fibers prepared from poly(lactic acid) polymer are known, problems have been encountered with their use. In particular, poly(lactic acid) polymers are known to have a relatively slow crystallization rate as compared to, for example, polyolefin polymers, thereby often resulting in poor processability of the aliphatic polyester polymers. In addition, the poly(lactic acid) polymers generally

do not have good thermal dimensional-stability. The poly(lactic acid) polymers usually undergo severe heat-shrinkage due to the relaxation of the polymer chain during downstream heat treatment processes, such as thermal bonding and lamination, unless an extra step such as heat setting is taken. However, such a heat setting step generally limits the use of the fiber in *in-situ* nonwoven forming processes, such as spunbond and meltblown, where heat setting is very difficult to be accomplished.

It is therefore an object of the present invention to provide a thermoplastic composition which exhibits desired processability, liquid wettability, and thermal dimensional-stability properties.

It is also an object of the present invention to provide a thermoplastic composition which may be easily and efficiently formed into a fiber.

It is also an object of the present invention to provide a thermoplastic composition which is suitable for use in preparing nonwoven structures.

It is also an object of the present invention to provide a fiber or nonwoven structure that is readily degradable in the environment.

It is also an object of the present invention to provide a disposable absorbent product that may be used for the absorption of fluids such as bodily fluids, yet which such disposable absorbent product comprises components that are readily degradable in the environment.

### **Summary of the Invention**

According to a first aspect, the present invention consists in a thermoplastic composition blend comprising:

a. a poly(lactic acid) polymer in a weight amount that is greater than 0 but less than 100 weight percent,

b. a polymer selected from the group consisting of a polybutylene succinate polymer, a polybutylene succinate adipate polymer, and a mixture of such polymers, in a weight amount that is greater than 0 but less than 100 weight percent,

c. a wetting agent, which exhibits a hydrophilic-lipophilic balance ratio that is between about 10 to about 40, in a weight amount that is greater than 0 to about 15 weight percent,

wherein all weight percents are based on the total weight amount of the poly(lactic acid) polymer; the polymer selected from the group consisting of a polybutylene succinate polymer, a polybutylene succinate adipate polymer, and a mixture of such polymers; and the wetting agent present in the thermoplastic composition,

wherein the poly(lactic acid) polymer, the polymer selected from the group consisting of a polybutylene succinate polymer, a polybutylene succinate adipate polymer, and a mixture of such polymers, and the wetting agent are substantially unreacted with each other.



According to a second aspect, the present invention consists in a multicomponent fiber prepared from a thermoplastic composition, wherein the thermoplastic composition comprises:

- a. a poly(lactic acid) polymer in a weight amount that is greater than 0 but less than 100 weight percent,
- b. a polymer selected from the group consisting of a polybutylene succinate polymer, a polybutylene succinate adipate polymer, and a mixture of such polymers, in a weight amount that is greater than 0 but less than 100 weight percent,
- c. a wetting agent, which exhibits a hydrophilic-lipophilic balance ratio that is between about 10 to about 40, in a weight amount that is greater than 0 to about 15 weight percent,

10 wherein all weight percents are based on the total weight amount of the poly(lactic acid) polymer; the polymer selected from the group consisting of a polybutylene succinate polymer, a polybutylene succinate adipate polymer, and a mixture of such polymers; and the wetting agent present in the thermoplastic composition;

15 wherein the poly(lactic acid) polymer, the polymer selected from the group consisting of a polybutylene succinate polymer, a polybutylene succinate adipate polymer, and a mixture of such polymers and the wetting agent are substantially unreacted with each other,

wherein the multicomponent fiber exhibits an Advancing Contact Angle value that is less than about 80 degrees and a Receding Contact Angle value that is less than about 60 degrees.

According to a third aspect, the present invention consists in a disposable absorbent product comprising a liquid-permeable topsheet, a backsheet attached to the topsheet, and an absorbent core positioned between the liquid-permeable topsheet and the backsheet, wherein the liquid-permeable topsheet comprises a multicomponent fiber prepared from a thermoplastic composition, wherein the thermoplastic composition comprises:

- a. a poly(lactic acid) polymer in a weight amount that is greater than 0 but less than 100 weight percent,
- b. a polymer selected from the group consisting of a polybutylene succinate polymer, a polybutylene succinate adipate polymer, and a mixture of such polymers, in a weight amount that is greater than 0 but less than 100 weight percent,
- c. a wetting agent, which exhibits a hydrophilic-lipophilic balance ratio that is between about 10 to about 40, in a weight amount that is greater than 0 to about 15 weight percent,

30 wherein all weight percents are based on the total weight amount of the poly(lactic acid) polymer; the polymer selected from the group consisting of a polybutylene succinate polymer, a polybutylene succinate adipate polymer, and a mixture of such polymers; and the wetting agent present in the thermoplastic composition;



wherein the poly(lactic acid) polymer, the polymer selected from the group consisting of a polybutylene succinate polymer, a polybutylene succinate adipate polymer, and a mixture of such polymers, and the wetting agent are substantially unreacted with each other,

wherein the multicomponent fiber exhibits an Advancing Contact Angle value that is less than about 80 degrees and a Receding Contact Angle value that is less than about 60 degrees.

The present invention concerns a thermoplastic composition that is suitably substantially biodegradable and yet which is easily prepared and readily processable into desired final structures, such as fibers or nonwoven structures.

One aspect of the present invention concerns a thermoplastic composition that comprises a mixture of a first component, a second component, and a third component.

One embodiment of such a thermoplastic composition comprises a substantially unreacted mixture of a poly(lactic acid) polymer; a polybutylene succinate polymer or a polybutylene succinate adipate polymer or a mixture of such polymers; and a wetting agent for the poly(lactic acid) polymer, the polybutylene succinate polymer or the polybutylene succinate adipate polymer or a mixture of such polymers.

In another aspect, the present invention concerns a multicomponent fiber that is suitably substantially degradable and yet which is easily prepared and readily processable into desired final structures, such nonwoven structures.

One aspect of the present invention concerns a multicomponent fiber that comprises a substantially unreacted mixture of a poly(lactic acid) polymer; a polybutylene succinate polymer or a polybutylene succinate adipate polymer or a mixture of such polymers; and a wetting agent for the aliphatic polyester polymer and the polybutylene succinate polymer or the polybutylene succinate adipate polymer or a mixture of such polymers.

In another aspect, the present invention concerns a nonwoven structure comprising the multicomponent fiber disclosed herein.

One embodiment of such a nonwoven structure is a frontsheet useful in a disposable absorbent product.

In another aspect, the present invention concerns a process for preparing the multicomponent fiber disclosed herein.

In another aspect, the present invention concerns a disposable absorbent product comprising the multicomponent fiber disclosed herein.

#### **Detailed Description of the Preferred Embodiments**

The present invention is directed to a thermoplastic composition which includes a first component, a second component, and a third component. As used herein, the term "thermoplastic"



4b

is meant to refer to a material that softens when exposed to heat and substantially returns to its original condition when cooled to room temperature.

It has been discovered that, by using an unreacted mixture of a poly(lactic acid) polymer, a polybutylene succinate polymer or a polybutylene succinate adipate polymer or a mixture of such polymers, and a wetting agent, a thermoplastic composition may be prepared wherein such thermoplastic composition is suitably substantially degradable yet which thermoplastic composition is easily processed into fibers and nonwoven structures that exhibit effective fibrous mechanical properties.

The first component in the thermoplastic composition is poly(lactic acid) polymer. Poly(lactic acid) polymer is generally prepared by the polymerization of lactic acid. However, it will be recognized by one skilled in the art that a chemically

22  
23  
24  
25  
26  
27  
28  
29  
30



equivalent material may also be prepared by the polymerization of lactide. As such, as used herein, the term "poly(lactic acid) polymer" is intended to represent the polymer that is prepared by either the polymerization of lactic acid or lactide.

Lactic acid and lactide are known to be asymmetrical molecules, having two optical isomers referred to, respectively, as the levorotatory (hereinafter referred to as "L") enantiomer and the dextrorotatory (hereinafter referred to as "D") enantiomer. As a result, by polymerizing a particular enantiomer or by using a mixture of the two enantiomers, it is possible to prepare different polymers that are chemically similar yet which have different properties. In particular, it has been found that by modifying the stereochemistry of a poly(lactic acid) polymer, it is possible to control, for example, the melting temperature, melt rheology, and crystallinity of the polymer. By being able to control such properties, it is possible to prepare a thermoplastic composition and a multicomponent fiber exhibiting desired melt strength, mechanical properties, softness, and processability properties so as to be able to make attenuated, heat-set, and crimped fibers.

Examples of poly(lactic acid) polymers that are suitable for use in the present invention include a variety of poly(lactic acid) polymers that are available from Chronopol Inc., Golden, Colorado.

It is generally desired that the poly(lactic acid) polymer be present in the thermoplastic composition in an amount effective to result in the thermoplastic composition exhibiting desired properties. The poly(lactic acid) polymer will be present in the thermoplastic composition in a weight amount that is greater than 0 but less than 100 weight percent, beneficially between about 5 weight percent to about 95 weight percent, suitably between about 10 weight percent to about 90 weight percent, and more suitably between about 15 weight percent to about 85 weight percent, wherein all weight percents are based on the total weight amount of the poly(lactic acid) polymer, the polybutylene succinate polymer or polybutylene succinate adipate polymer or a mixture of such polymers, and the wetting agent present in the thermoplastic composition. The compositional ratio of the three components in the thermoplastic composition is generally important to obtain the desired properties of the thermoplastic composition, such as wettability, biodegradability, thermal stability and processability.

The second component in the thermoplastic composition is a polybutylene succinate polymer, a polybutylene succinate adipate polymer, or a mixture of such

polymers. A polybutylene succinate polymer is generally prepared by the condensation polymerization of a glycol and a dicarboxylic acid or an acid anhydride thereof. A polybutylene succinate polymer may either be a linear polymer or a long-chain branched polymer. A long-chain branched polybutylene succinate 5 polymer is generally prepared by using an additional polyfunctional component selected from the group consisting of trifunctional or tetrafunctional polyols, oxycarboxylic acids, and polybasic carboxylic acids. Polybutylene succinate polymers are known in the art and are described, for example, in European Patent Application 0 569 153 A2 to Showa Highpolymer Co., Ltd., Tokyo, Japan. A 10 polybutylene succinate adipate polymer is generally prepared by the polymerization of at least one alkyl glycol and more than one aliphatic multifunctional acid. Polybutylene succinate adipate polymers are also known in the art.

Examples of polybutylene succinate polymers and polybutylene succinate adipate polymers that are suitable for use in the present invention include a variety of 15 polybutylene succinate polymers and polybutylene succinate adipate polymers that are available from Showa Highpolymer Co., Ltd., Tokyo, Japan, under the designation Bionolle 1903 polybutylene succinate polymer, with long chain branches, or Bionolle 1020 polybutylene succinate polymer, which is an essentially linear polymer.

20 It is generally desired that the polybutylene succinate polymer, the polybutylene succinate adipate polymer, or a mixture of such polymers be present in the thermoplastic composition in an amount effective to result in the thermoplastic composition exhibiting desired properties. The polybutylene succinate polymer, the polybutylene succinate adipate polymer, or a mixture of such polymers will be 25 present in the thermoplastic composition in a weight amount that is greater than 0 but less than 100 weight percent, beneficially between about 5 weight percent to about 95 weight percent, suitably between about 10 weight percent to about 90 weight percent, and more suitably between about 15 weight percent to about 85 weight percent, wherein all weight percents are based on the total weight amount of 30 the poly(lactic acid) polymer, the polybutylene succinate polymer, the polybutylene succinate adipate polymer, or a mixture of such polymers; and the wetting agent present in the thermoplastic composition.

It is generally desired that the poly(lactic acid) polymer and the polybutylene succinate polymer and/or the polybutylene succinate adipate polymer exhibit a

weight average molecular weight that is effective for the thermoplastic composition to exhibit desirable melt strength, fiber mechanical strength, and fiber spinning properties. In general, if the weight average molecular weight of a particular polymer is too high, this represents that the polymer chains are heavily entangled which may 5 result in a thermoplastic composition comprising that polymer being difficult to process. Conversely, if the weight average molecular weight of a particular polymer is too low, this represents that the polymer chains are not entangled enough which may result in a thermoplastic composition comprising that polymer exhibiting a relatively weak melt strength, making high speed processing very difficult. Thus, 10 poly(lactic acid) polymers, polybutylene succinate polymers, and/or polybutylene succinate adipate polymers suitable for use in the present invention respectively exhibit weight average molecular weights that are beneficially between about 10,000 to about 2,000,000, more beneficially between about 50,000 to about 400,000, and 15 suitably between about 100,000 to about 300,000. The weight average molecular weight for polymers or polymer blends can be determined using a method as described in the Test Methods section herein.

It is also desired that the poly(lactic acid) polymer and the polybutylene succinate polymer and/or the polybutylene succinate adipate polymer exhibit a polydispersity index value that is effective for the thermoplastic composition to exhibit 20 desirable melt strength, fiber mechanical strength, and fiber spinning properties. As used herein, "polydispersity index" is meant to represent the value obtained by dividing the weight average molecular weight of a polymer by the number average molecular weight of the polymer. In general, if the polydispersity index value of a particular polymer is too high, a thermoplastic composition comprising that polymer 25 may be difficult to process due to inconsistent processing properties caused by polymer segments comprising low molecular weight polymers that have lower melt strength properties during spinning. Thus, it is desired that the poly(lactic acid) polymer, the polybutylene succinate polymer, and/or the polybutylene succinate adipate polymer respectively exhibit a polydispersity index value that is beneficially 30 between about 1 to about 15, more beneficially between about 1 to about 4, and suitably between about 1 to about 3. The number average molecular weight for polymers or polymer blends can be determined using a method as described in the Test Methods section herein.

In the present invention, it is desired that the poly(lactic acid) polymer, the polybutylene succinate polymer, and the polybutylene succinate adipate polymer be biodegradable. As a result, the thermoplastic composition comprising these polymers, either in the form of a fiber or in the form of a nonwoven structure, will be

5 substantially degradable when disposed of to the environment and exposed to air and/or water. As used herein, "biodegradable" is meant to represent that a material degrades from the action of naturally occurring microorganisms such as bacteria, fungi, and algae.

In the present invention, it is also desired that the poly(lactic acid) polymer, the polybutylene succinate polymer, and the polybutylene succinate adipate polymer be compostable. As a result, the thermoplastic composition comprising these polymers, either in the form of a fiber or in the form of a nonwoven structure, will be

10 substantially compostable when disposed of to the environment and exposed to air and/or water. As used herein, "compostable" is meant to represent that a material is

15 capable of undergoing biological decomposition in a compost site such that the material is not visually distinguishable and breaks down into carbon dioxide, water, inorganic compounds, and biomass, at a rate consistent with known compostable materials.

As used herein, the term "hydrophobic" refers to a material having a contact angle of water in air of at least 90 degrees. In contrast, as used herein, the term "hydrophilic" refers to a material having a contact angle of water in air of less than 90 degrees. For the purposes of this application, contact angle measurements are determined as set forth in the Test Methods section herein. The general subject of contact angles and the measurement thereof is well known in the art as, for example,

20 in Robert J. Good and Robert J. Stromberg, Ed., in "Surface and Colloid Science - Experimental Methods", Vol. II, (Plenum Press, 1979).

It is generally desired that the poly(lactic acid) polymer, the polybutylene succinate polymer, the polybutylene succinate adipate polymer, or a mixture of such polymers, be melt processable. It is therefore desired that the polymers used in the

30 present invention exhibit a melt flow rate that is beneficially between about 1 gram per 10 minutes to about 600 grams per 10 minutes, suitably between about 5 grams per 10 minutes to about 200 grams per 10 minutes, and more suitably between about 10 grams per 10 minutes to about 150 grams per 10 minutes. The melt flow

rate of a material may be determined according to ASTM Test Method D1238-E, incorporated in its entirety herein by reference.

As used herein, the term "fiber" or "fibrous" is meant to refer to a material wherein the length to diameter ratio of such material is greater than about 10.

5 Conversely, a "nonfiber" or "nonfibrous" material is meant to refer to a material wherein the length to diameter ratio of such material is about 10 or less.

Either separately or when mixed together, the poly(lactic acid) polymer and the polybutylene succinate polymer and/or the polybutylene succinate adipate polymer are generally hydrophobic. Since it is desired that the thermoplastic composition of 10 the present invention, and fibers prepared from the thermoplastic composition, generally be hydrophilic, it has been found that there is a need for the use of another component in the thermoplastic composition of the present invention in order to achieve the desired properties. Furthermore, it has been found desirable to improve the processability of the poly(lactic acid) polymer, and the polybutylene succinate 15 polymer and/or the polybutylene succinate adipate, since such polymers are not chemically identical and are, therefore, somewhat incompatible with each other which negatively affects the processing of a mixture of such polymers. For example, the poly(lactic acid) polymer, the polybutylene succinate polymer, and/or the polybutylene succinate adipate polymer are sometimes difficult to effectively mix and 20 prepare as an essentially homogeneous mixture on their own. As such, the present invention generally requires the use of a wetting agent that allows for the effective preparation and processing of the poly(lactic acid) polymer, the polybutylene succinate polymer, and/or the polybutylene succinate adipate polymer into a single thermoplastic composition.

25 Thus, the third component in the thermoplastic composition is a wetting agent for the poly(lactic acid) polymer and the polybutylene succinate polymer and/or the polybutylene succinate adipate polymer. Wetting agents suitable for use in the present invention will generally comprise a hydrophilic section which will generally be compatible to poly(lactic acid) polymer and the hydrophilic sections of polybutylene 30 succinate polymer or polybutylene succinate adipate polymer and a hydrophobic section which will generally be compatible to the hydrophobic sections of polybutylene succinate polymer or polybutylene succinate adipate polymer. These hydrophilic and hydrophobic sections of the wetting agent will generally exist in separate blocks so that the overall wetting agent structure may be di-block or

random block. It is generally desired that the wetting agent initially functions as a plasticizer and an agent to enhance cohesion between the different polymers in order to improve the preparation and processing of the thermoplastic composition. It is then generally desired that the wetting agent then serves as a surfactant in a material processed from the thermoplastic composition, such as a fiber or nonwoven structure, by modifying the contact angle of water in air of the processed material. The hydrophobic portion of the wetting agent may be, but is not limited to, a polyolefin such as polyethylene or polypropylene. The hydrophilic portion of the wetting agent may contain ethylene oxide, ethoxylates, glycols, alcohols or any combinations thereof. Examples of suitable wetting agents include UNITHOX®480 and UNITHOX®750 ethoxylated alcohols, or UNICID® Acid Amide Ethoxylates, all available from Petrolite Corporation of Tulsa, Oklahoma.

It is generally desired that the wetting agent exhibit a weight average molecular weight that is effective for the thermoplastic composition to exhibit desirable melt strength, fiber mechanical strength, and fiber spinning properties. In general, if the weight average molecular weight of a wetting agent is too high, the wetting agent will not blend well with the other components in the thermoplastic composition because the wetting agent's viscosity will be so high that it lacks the mobility needed to blend. Conversely, if the weight average molecular weight of the wetting agent is too low, this represents that the wetting agent will generally not blend well with the other components and have such a low viscosity that it causes processing problems. Thus, wetting agents suitable for use in the present invention exhibit weight average molecular weights that are beneficially between about 1,000 to about 100,000, suitably between about 1,000 to about 50,000, and more suitably between about 1,000 to about 10,000. The weight average molecular weight for a material can be determined using a method as described in the Test Methods section herein.

It is generally desired that the wetting agent exhibit an effective hydrophilic-lipophilic balance ratio (HLB ratio). The HLB ratio of a material describes the relative ratio of the hydrophilicity of the material. The HLB ratio is calculated as the weight average molecular weight of the hydrophilic portion divided by the total weight average molecular weight of the material, which value is then multiplied by 20. If the HLB ratio value is too low, the wetting agent will generally not provide the desired improvement in hydrophilicity. Conversely, if the HLB ratio value is too high, the wetting agent will not blend into the thermoplastic composition because of chemical

incompatibility and differences in viscosities with the other components. Thus, wetting agents useful in the present invention exhibit HLB ratio values that are beneficially between about 10 to about 40, suitably between about 10 to about 20, and more suitably between about 12 to about 16.

5 It is generally desired that the wetting agent be present in the thermoplastic composition in an amount effective to result in the thermoplastic composition exhibiting desired properties such as desirable heat shrinkage and desirable contact angle values. In general, a minimal amount of the wetting agent will be needed to achieve an effective blending and processing with the other components in the

10 thermoplastic composition. In general, too much of the compatibilizer may lead to processing problems of the thermoplastic composition or to a final thermoplastic composition that does not exhibit desired properties such as desired advancing and receding contact angle values. The wetting agent will be present in the thermoplastic composition in a weight amount that is greater than 0 to about 15

15 weight percent, beneficially between about 0.5 weight percent to about 15 weight percent, more beneficially between about 1 weight percent to about 13 weight percent, suitably between about 1 weight percent to about 10 weight percent, and more suitably between about 1 weight percent to about 5 weight percent, wherein all weight percents are based on the total weight amount of the poly(lactic acid)

20 polymer; the polybutylene succinate polymer, the polybutylene succinate adipate polymer, or a mixture of such polymers; and the wetting agent present in the thermoplastic composition.

While the principal components of the thermoplastic composition of the present invention have been described in the foregoing, such thermoplastic composition is

25 not limited thereto and can include other components not adversely effecting the desired properties of the thermoplastic composition. Exemplary materials which could be used as additional components would include, without limitation, pigments, antioxidants, stabilizers, surfactants, waxes, flow promoters, solid solvents, plasticizers, nucleating agents, particulates, and other materials added to enhance

30 the processability of the thermoplastic composition. If such additional components are included in a thermoplastic composition, it is generally desired that such additional components be used in an amount that is beneficially less than about 10 weight percent, more beneficially less than about 5 weight percent, and suitably less than about 1 weight percent, wherein all weight percents are based on the total

weight amount of the poly(lactic acid) polymer; the polybutylene succinate polymer, the polybutylene succinate adipate polymer, or a mixture of such polymers; and the wetting agent present in the thermoplastic composition.

The thermoplastic composition of the present invention is generally simply a

5 mixture of the poly(lactic acid) polymer; the polybutylene succinate polymer, the polybutylene succinate adipate polymer, or a mixture of such polymers; the wetting agent, and, optionally, any additional components. In order to achieve the desired properties for the thermoplastic composition of the present invention, it is desirable that the poly(lactic acid) polymer; the polybutylene succinate polymer, the

10 polybutylene succinate adipate polymer, or a mixture of such polymers; and the wetting agent remain substantially unreacted with each other. As such, each of the poly(lactic acid) polymer; the polybutylene succinate polymer, the polybutylene succinate adipate polymer, or a mixture of such polymers; and the wetting agent remain distinct components of the thermoplastic composition.

15 Each of the poly(lactic acid) polymer and the polybutylene succinate polymer, the polybutylene succinate adipate polymer, or a mixture of such polymers will generally form separate regions or domains within a prepared mixture forming the thermoplastic composition. However, depending on the relative amounts that are used of each of the poly(lactic acid) polymer and the polybutylene succinate

20 polymer, the polybutylene succinate adipate polymer, or a mixture of such polymers, an essentially continuous phase may be formed from the polymer that is present in the thermoplastic composition in a relatively greater amount. In contrast, the polymer that is present in the thermoplastic composition in a relatively lesser amount may form an essentially discontinuous phase, forming separate regions or domains

25 within the continuous phase of the more prevalent polymer wherein the more prevalent polymer continuous phase substantially encases the less prevalent polymer within its structure. As used herein, the term "encase", and related terms, are intended to mean that the more prevalent polymer continuous phase substantially encloses or surrounds the less prevalent polymer's separate regions or

30 domains.

In one embodiment of a thermoplastic composition or a multicomponent fiber of the present invention, it is desired that the poly(lactic acid) polymer form an essentially continuous phase and that the polybutylene succinate polymer, the polybutylene succinate adipate polymer, or a mixture of such polymers form an

essentially discontinuous phase, wherein the poly(lactic acid) polymer substantially encases regions or domains of the polybutylene succinate polymer, the polybutylene succinate adipate polymer, or a mixture of such polymers. In such an embodiment, it is desired that the poly(lactic acid) polymer is present in the thermoplastic composition or multicomponent fiber in a weight amount that is between about 5 weight percent to about 90 weight percent and that the polybutylene succinate polymer, the polybutylene succinate adipate polymer, or a mixture of such polymers is present in the thermoplastic composition or multicomponent fiber in a weight amount that is between about 5 weight percent to about 20 weight percent, wherein

5 all weight percents are based on the total weight amount of the poly(lactic acid) polymer, the polybutylene succinate polymer or polybutylene succinate adipate polymer or a mixture of such polymers, and the wetting agent present in the thermoplastic composition or the multicomponent fiber.

10

In one embodiment of the present invention, after dry mixing together the

15 poly(lactic acid) polymer; the polybutylene succinate polymer, the polybutylene succinate adipate polymer, or a mixture of such polymers; and the wetting agent to form a thermoplastic composition dry mixture, such thermoplastic composition dry mixture is beneficially agitated, stirred, or otherwise blended to effectively uniformly mix the poly(lactic acid) polymer; the polybutylene succinate polymer, the

20 polybutylene succinate adipate polymer, or a mixture of such polymers; and the wetting agent such that an essentially homogeneous dry mixture is formed. The dry mixture may then be melt blended in, for example, an extruder, to effectively uniformly mix the poly(lactic acid) polymer; the polybutylene succinate polymer, the polybutylene succinate adipate polymer, or a mixture of such polymers; and the

25 wetting agent such that an essentially homogeneous melted mixture is formed. The essentially homogeneous melted mixture may then be cooled and pelletized.

Alternatively, the essentially homogeneous melted mixture may be sent directly to a spin pack or other equipment for forming fibers or a nonwoven structure.

Alternative methods of mixing together the components of the present

30 invention include first mixing together the poly(lactic acid) polymer and the polybutylene succinate polymer, the polybutylene succinate adipate polymer, or a mixture of such polymers and then adding the wetting agent to such a mixture in, for example, an extruder being used to mix the components together. In addition, it is also possible to initially melt mix all of the components together at the same time.

Other methods of mixing together the components of the present invention are also possible and will be easily recognized by one skilled in the art.

The present invention is also directed to a multicomponent fiber which is prepared from the thermoplastic composition of the present invention. For purposes 5 of illustration only, the present invention will generally be described in terms of a multicomponent fiber comprising only three components. However, it should be understood that the scope of the present invention is meant to include fibers with three or more components.

When the thermoplastic composition of the present invention is formed into a 10 multicomponent fiber, an exposed surface on at least a portion of the multicomponent fiber will typically be formed from the more prevalent polymer present in the multicomponent fiber. Such an exposed surface on at least a portion of the multicomponent fiber which will generally permit thermal bonding of the multicomponent fiber to other fibers which may be the same or different from the 15 multicomponent fiber of the present invention. As a result, the multicomponent fiber can then be used to form thermally bonded fibrous nonwoven structures such as a nonwoven web.

Typical conditions for thermally processing the various components include using a shear rate that is beneficially between about 100 seconds<sup>-1</sup> to about 20 50000 seconds<sup>-1</sup>, more beneficially between about 500 seconds<sup>-1</sup> to about 5000 seconds<sup>-1</sup>, suitably between about 1000 seconds<sup>-1</sup> to about 3000 seconds<sup>-1</sup>, and most suitably at about 1000 seconds<sup>-1</sup>. Typical conditions for thermally processing the components also include using a temperature that is beneficially between about 100°C to about 500°C, more beneficially between about 150°C to 25 about 300°C, and suitably between about 175°C to about 250°C.

Methods for making multicomponent fibers are well known and need not be described here in detail. The melt spinning of polymers includes the production of continuous filament, such as spunbond or meltblown, and non-continuous filament, such as staple and short-cut fibers. To form a spunbond or meltblown fiber, 30 generally, a thermoplastic composition is extruded and fed to a distribution system where the thermoplastic composition is introduced into a spinneret plate. The spun fiber is then cooled, solidified, and drawn by an aerodynamic system, to be formed into a conventional nonwoven. Meanwhile, to produce short-cut or staple fiber rather than being directly formed into a nonwoven structure the spun fiber is cooled,

solidified, and drawn, generally by a mechanical rolls system, to an intermediate filament diameter and collected. Subsequently, the fiber may be "cold drawn" at a temperature below its softening temperature, to the desired finished fiber diameter and crimped or texturized and cut into a desirable fiber length.

5 Multicomponent fibers can be cut into relatively short lengths, such as staple fibers which generally have lengths in the range of about 25 to about 50 millimeters and short-cut fibers which are even shorter and generally have lengths less than about 18 millimeters.

The resultant multicomponent fibers of the present invention are desired to  
10 exhibit an improvement in hydrophilicity, evidenced by a decrease in the contact angle of water in air. The contact angle of water in air of a fiber sample can be measured as either an advancing or a receding contact angle value because of the nature of the testing procedure. The advancing contact angle measures a material's initial response to a liquid, such as water. The receding contact angle gives a  
15 measure of how a material will perform over the duration of a first insult, or exposure to liquid, as well as over following insults. A lower receding contact angle means that the material is becoming more hydrophilic during the liquid exposure and will generally then be able to transport liquids more consistently. Both the advancing and receding contact angle data is desirably used to establish the highly hydrophilic  
20 nature of a multicomponent fiber of the present invention.

In one embodiment of the present invention, it is desired that the multicomponent fiber exhibits an Advancing Contact Angle value that is beneficially less than about 80 degrees, more beneficially less than about 75 degrees, suitably less than about 70 degrees, more suitably less than about 60 degrees, and most  
25 suitably less than about 50 degrees, wherein the Advancing Contact Angle value is determined by the method that is described in the Test Methods section herein.

In another embodiment of the present invention, it is desired that the multicomponent fiber exhibits a Receding Contact Angle value that is beneficially less than about 60 degrees, more beneficially less than about 55 degrees, suitably  
30 less than about 50 degrees, more suitably less than about 45 degrees, and most suitably less than about 40 degrees, wherein the Receding Contact Angle value is determined by the method that is described in the Test Methods section herein.

In another embodiment of the present invention, it is desired that the difference between the Advancing Contact Angle value and the Receding Contact Angle value,

commonly known as the contact angle hysteresis, be as small as possible. As such, it is desired that the multicomponent fiber exhibits a difference between the Advancing Contact Angle value and the Receding Contact Angle value that is beneficially less than about 30 degrees, more beneficially less than about 25

5 degrees, suitably less than about 20 degrees, and more suitably less than about 10 degrees.

Typical poly(lactic acid) polymer materials often undergo heat shrinkage during downstream thermal processing. The heat-shrinkage mainly occurs due to the thermally-induced chain relaxation of the polymer segments in the amorphous phase

10 and incomplete crystalline phase. To overcome this problem, it is generally desirable to maximize the crystallization of the poly(lactic acid) polymer material before the bonding stage so that the thermal energy goes directly to melting rather than to allow for chain relaxation and reordering of the incomplete crystalline structure. The typical solution to this problem is to subject the material to a heat-setting treatment.

15 As such, when prepared materials, such as fibers, are subjected to heat-setting upon reaching a bonding roll, the fibers won't substantially shrink because such fibers are already fully or highly oriented. The present invention alleviates the need for this additional processing step because of the composition of the multicomponent fiber of the present invention. In general, the addition of the polybutylene succinate polymer,

20 the polybutylene succinate adipate polymer, or a mixture of such polymers, and the wetting agent decrease the heat shrinkage of a multicomponent fiber as compared to a fiber that is prepared from only poly(lactic acid) polymer.

In one embodiment of the present invention, it is desired that the multicomponent fiber exhibit an amount of shrinking, at a temperature of about 90°C,

25 that is beneficially less than about 15 percent, more beneficially less than about 10 percent, and suitably less than about 5 percent, wherein the amount of shrinking is based upon the difference between the initial and final lengths of the fiber divided by the initial length of the fiber multiplied by 100. The method by which the amount of shrinking that a fiber exhibits may be determined is included in the Test Methods

30 section herein.

In one embodiment of the present invention, it is desired that the multicomponent fiber exhibit an amount of shrinking, suitably less than about 5 percent at a temperature of about 90°C, that results in a nonwoven structure formed from the multicomponent fiber to exhibit a quilting or waviness effect that increases

the surface area of the nonwoven structure since the shrinking of the multicomponent fibers causes the nonwoven structure to exhibit a three dimensional topography. Such a quilting or waviness effect of the nonwoven structure has been found to improve the softness and z-directional transport of a liquid within the 5 nonwoven structure.

It is generally desired that multicomponent fibers also exhibit desired mechanical strength properties, such as a break stress value as well as a modulus value, such that the multicomponent fibers maintain their integrity during use. In one embodiment of the present invention, it is desired that a multicomponent fiber 10 prepared from the thermoplastic composition of the present invention exhibits an improved break stress value as well as an improved modulus value as compared to a fiber that is prepared solely from poly(lactic acid) polymer. In one embodiment of the present invention, it is desired that a multicomponent fiber prepared from the thermoplastic composition of the present invention exhibits a break stress value that 15 is at least twice the break stress value exhibited by an otherwise identical fiber that is prepared solely from the poly(lactic acid) polymer used to prepare the multicomponent fiber.

In one embodiment of the present invention, it is desired that the multicomponent fiber exhibit a break stress value that is greater than about 10 MPa, 20 beneficially greater than about 15 MPa, suitably greater than about 20 MPa, and up to about 100 MPa.

In another embodiment of the present invention, it is desired that the multicomponent fiber exhibit a modulus value that is less than about 150 MPa, beneficially less than about 125 MPa, and suitably less than about 100 MPa.

25 The multicomponent fibers of the present invention are suited for use in disposable products including disposable absorbent products such as diapers, adult incontinent products, and bed pads; in catamenial devices such as sanitary napkins, and tampons; and other absorbent products such as wipes, bibs, wound dressings, and surgical capes or drapes. Accordingly, in another aspect, the present invention 30 relates to a disposable absorbent product comprising the multicomponent fibers of the present invention.

In one embodiment of the present invention, the multicomponent fibers are formed into a fibrous matrix for incorporation into a disposable absorbent product. A fibrous matrix may take the form of, for example, a fibrous nonwoven web. Fibrous

nonwoven webs may be made completely from the multicomponent fibers of the present invention or they may be blended with other fibers. The length of the fibers used may depend on the particular end use contemplated. Where the fibers are to be degraded in water as, for example, in a toilet, it is advantageous if the lengths are 5 maintained at or below about 15 millimeters.

In one embodiment of the present invention, a disposable absorbent product is provided, which disposable absorbent product comprises a liquid-permeable topsheet, a backsheet attached to the liquid-permeable topsheet, and an absorbent structure positioned between the liquid-permeable topsheet and the backsheet, 10 wherein the liquid-permeable topsheet comprises multicomponent fibers of the present invention.

Absorbent products and structures according to all aspects of the present invention are generally subjected, during use, to multiple insults of a body liquid. Accordingly, the absorbent products and structures are desirably capable of 15 absorbing multiple insults of body liquids in quantities to which the absorbent products and structures will be exposed during use. The insults are generally separated from one another by a period of time.

#### Test Methods

##### 20 Melting Temperature

The melting temperature of a material was determined using differential scanning calorimetry. A differential scanning calorimeter, under the designation Thermal Analyst 2910 Differential Scanning Calorimeter, which was outfitted with a liquid nitrogen cooling accessory and used in combination with Thermal Analyst 2200 25 analysis software (version 8.10) program, both available from T.A. Instruments Inc. of New Castle, Delaware, was used for the determination of melting temperatures.

The material samples tested were either in the form of fibers or resin pellets. It is preferred to not handle the material samples directly, but rather to use tweezers and other tools, so as not to introduce anything that would produce erroneous 30 results. The material samples were cut, in the case of fibers, or placed, in the case of resin pellets, into an aluminum pan and weighed to an accuracy of 0.01mg on an analytical balance. If needed, a lid was crimped over the material sample onto the pan.

The differential scanning calorimeter was calibrated using an indium metal standard and a baseline correction performed, as described in the manual for the differential scanning calorimeter. A material sample was placed into the test chamber of the differential scanning calorimeter for testing and an empty pan is used

5 as a reference. All testing was run with a 55 cubic centimeter/minute nitrogen (industrial grade) purge on the test chamber. The heating and cooling program is a 2 cycle test that begins with equilibration of the chamber to -75°C, followed by a heating cycle of 20°C/minute to 220°C, followed by a cooling cycle at 20°C/minute to -75°C, and then another heating cycle of 20°C/minute to 220°C.

10 The results were evaluated using the analysis software program wherein the glass transition temperature (Tg) of inflection, endothermic and exothermic peaks were identified and quantified. The glass transition temperature was identified as the area on the line where a distinct change in slope occurs and then the melting temperature is determined using an automatic inflection calculation.

15

Apparent Viscosity

A capillary rheometer, under the designation Göttfert Rheograph 2003 capillary rheometer, which was used in combination with WinRHEO (version 2.31) analysis software, both available from Göttfert Company of Rock Hill, South Carolina, was

20 used to evaluate the apparent viscosity rheological properties of material samples. The capillary rheometer setup included a 2000 bar pressure transducer and a 30 mm length/30 mm active length/1 mm diameter/0 mm height/180° run in angle, round hole capillary die.

If the material sample being tested demonstrates or is known to have water

25 sensitivity, the material sample is dried in a vacuum oven above its glass transition temperature, i.e. above 55 or 60°C for poly(lactic acid) materials, under a vacuum of at least 15 inches of mercury with a nitrogen gas purge of at least 30 standard cubic feet per hour for at least 16 hours.

Once the instrument is warmed up and the pressure transducer is calibrated,

30 the material sample is loaded incrementally into the column, packing resin into the column with a ramrod each time to ensure a consistent melt during testing. After material sample loading, a 2 minute melt time precedes each test to allow the material sample to completely melt at the test temperature. The capillary rheometer takes data points automatically and determines the apparent viscosity (in

Pascal·second) at 7 apparent shear rates (in second<sup>-1</sup>): 50, 100, 200, 500, 1000, 2000, and 5000. When examining the resultant curve it is important that the curve be relatively smooth. If there are significant deviations from a general curve from one point to another, possibly due to air in the column, the test run should be

5 repeated to confirm the results.

The resultant rheology curve of apparent shear rate versus apparent viscosity gives an indication of how the material sample will run at that temperature in an extrusion process. The apparent viscosity values at a shear rate of at least 1000 second<sup>-1</sup> are of specific interest because these are the typical conditions found in

10 commercial fiber spinning extruders.

#### Molecular Weight

A gas permeation chromatography (GPC) method is used to determine the molecular weight distribution of samples, such as of poly(lactic acid) whose weight

15 average molecular weight ( $M_w$ ) is between about 800 to about 400,000.

The GPC is set up with two PLgel Mixed K linear 5 micron, 7.5 x 300 millimeter analytical columns in series. The column and detector temperatures are 30°C. The mobile phase is high-performance liquid chromatography (HPLC) grade tetrahydrofuran (THF). The pump rate is 0.8 milliliter per minute with an injection

20 volume of 25 microliters. Total run time is 30 minutes. It is important to note that new analytical columns must be installed about every 4 months, a new guard column about every month, and a new in-line filter about every month.

Standards of polystyrene polymers, obtained from Aldrich Chemical Co., should be mixed into a solvent of dichloromethane(DCM):THF (10:90), both HPLC

25 grade, in order to obtain 1mg/mL concentrations. Multiple polystyrene standards can be combined in one standard solution provided that their peaks do not overlap when chromatographed. A range of standards of about 687 to 400,000 molecular weight should be prepared. Examples of standard mixtures with Aldrich polystyrenes of varying weight average molecular weights include: Standard 1 (401,340; 32,660;

30 2,727), Standard 2 (45,730; 4,075), Standard 3 (95,800; 12,860) and Standard 4 (184,200; 24,150; 687).

Next, prepare the stock check standard. Dissolve 10g of a 200,000 molecular weight poly(lactic acid) standard, Catalog#19245 obtained from Polysciences Inc., to 100ml of HPLC grade DCM to a glass jar with a lined lid using an orbital shaker (at

least 30 minutes). Pour out the mixture onto a clean, dry, glass plate and first allow the solvent to evaporate, then place in a 35°C preheated vacuum oven and dry for about 14 hours under a vacuum of 25mm of mercury. Next, remove the poly(lactic acid) from the oven and cut the film into small strips. Immediately grind the samples 5 using a grinding mill (with a 10 mesh screen) taking care not to add too much sample and causing the grinder to freeze up. Store a few grams of the ground sample in a dry glass jar in a dessicator, while the remainder of the sample can be stored in the freezer in a similar type jar.

It is important to prepare a new check standard prior to the beginning of each 10 new sequence and, because the molecular weight is greatly affected by sample concentration, great care should be taken in its weighing and preparation. To prepare the check standard weigh out  $0.0800g \pm 0.0025g$  of 200,000 weight average molecular weight poly(lactic acid) reference standard into a clean dry scintillation vial. Then, using a volumetric pipet or dedicated repipet, add 2ml of DCM to the vial and 15 screw the cap on tightly. Allow the sample to dissolve completely. Swirl the sample on an orbital shaker, such as a Thermolyne Roto Mix (type 51300) or similar mixer, if necessary. To evaluate whether is it dissolved hold the vial up to the light at a 45° angle. Turn it slowly and watch the liquid as it flows down the glass. If the bottom of the vial does not appear smooth, the sample is not completely dissolved. It may take 20 the sample several hours to dissolve. Once dissolved, add 18ml of THF using a volumetric pipet or dedicated repipet, cap the vial tightly and mix.

Sample preparations begins by weighing  $0.0800g \pm 0.0025g$  of the sample into a clean, dry scintillation vial (great care should also be taken in its weighing and preparation). Add 2ml of DCM to the vial with a volumetric pipet or dedicated repipet 25 and screw the cap on tightly. Allow the sample to dissolve completely using the same technique described in the check standard preparation above. Then add 18ml of THF using a volumetric pipet or dedicated repipet, cap the vial tightly and mix.

Begin the evaluation by making a test injection of a standard preparation to 30 test the system equilibration. Once equilibration is confirmed inject the standard preparations. After those are run, first inject the check standard preparation and then the sample preparations. Inject the check standard preparation after every 7 sample injections and at the end of testing. Be sure not to take any more than two injections from any one vial, and those two injections must be made within 4.5 hours of each other.

There are 4 quality control parameters to assess the results. First, the correlation coefficient of the fourth order regression calculated for each standard should be not less than 0.950 and not more than 1.050. Second, the relative standard deviation of all the weight average molecular weights of the check standard preparations should not be more than 5.0 percent. Third, the average of the weight average molecular weights of the check standard preparation injections should be within 10 percent of the weight average molecular weight on the first check standard preparation injection. Lastly, record the lactide response for the 200 microgram per milliliter ( $\mu\text{g/mL}$ ) standard injection on a SQC data chart. Using the chart's control lines, the response must be within the defined SQC parameters.

5 Calculate the Molecular statistics based on the calibration curve generated from the polystyrene standard preparations and constants for poly(lactic acid) and polystyrene in THF at 30°C. Those are: Polystyrene ( $K= 14.1*10^5$ ,  $\alpha=0.700$ ) and poly(lactic acid) ( $K=54.9*10^5$ ,  $\alpha=0.639$ ).

10

15 Heat Shrinkage of Fibers

The required equipment for the determination of heat shrinkage include: a convection oven (Thelco model 160DM laboratory oven, available from Precision and Scientific Inc., of Chicago, Illinois), 0.5g (+/- 0.06g) sinker weights, 1/2 inch binder 20 clips, masking tape, graph paper with at least 1/4 inch squares, foam posterboard (11 by 14 inches) or equivalent substrate to attach the graph paper and samples to. The convection oven should be capable of a temperature of about 90°C.

Fiber samples are melt spun at their respective spinning conditions. In general, a 30 filament bundle is preferred and mechanically drawn to obtain fibers 25 with a jetstretch ratio of beneficially 50 or higher. Only fibers of the same jetstretch ratio can be compared to one another in regards to their heat shrinkage. The jetstretch ratio of a fiber is the ratio of the speed of the drawdown roll divided by the linear extrusion rate (distance/time) of the melted polymer exiting the spinneret. The spun fiber is usually collected onto a bobbin using a winder. The collected fiber 30 bundle is separated into 30 filaments, if a 30 filament bundle has not already been obtained, and cut into 9 inch lengths.

The graph paper is taped onto the posterboard where one edge of the graph paper is matched with the edge of the posterboard. One end of the fiber bundle is taped, no more than the end 1 inch. The taped end is clipped to the posterboard at

the edge where the graph paper is matched up such that the edge of the clip rests over one of the horizontal lines on the graph paper while holding the fiber bundle in place (the taped end should be barely visible as it is secured under the clip). The other end of the bundle is pulled taught and lined up parallel to the vertical lines on

5 the graph paper. Next, at 7 inches down from the point where the clip is binding the fiber, pinch the 0.5g sinker around the fiber bundle. Repeat the attachment process for each replicate. Usually, 3 replicates can be attached at one time. Marks can be made on the graph paper to indicate the initial positions of the sinkers. The samples are placed into the oven at a temperature of about 90°C such that the samples hang

10 vertically and do not touch the posterboard. At time intervals of 5, 10 and 15 minutes quickly mark the new location of the sinkers on the graph paper and return samples to the oven.

After the testing is complete, remove the posterboard and measure the distances between the origin (where the clip held the fibers) and the marks at 5, 10

15 and 15 minutes with a ruler graduated to 1/16 inch. Three replicates per sample is recommended. Calculate averages, standard deviations and percent shrinkage. The percent shrinkage is calculated as (initial length - measured length) divided by the initial length and multiplied by 100. As reported in the examples herein and as used throughout the claims, the Heat Shrinkage value represents the amount of heat

20 shrinkage that a fiber sample exhibits at a temperature of about 90°C for a time period of about 15 minutes, as determined according to the preceding test method.

#### Contact Angle

The equipment includes a DCA-322 Dynamic Contact Angle Analyzer and

25 WinDCA (version 1.02) software, both available from ATI-CAHN Instruments, Inc., of Madison, Wisconsin. Testing was done on the "A" loop with a balance stirrup attached. Calibrations should be done monthly on the motor and daily on the balance (100mg mass used) as indicated in the manual.

Thermoplastic compositions are spun into fibers and the freefall sample

30 (jetstretch of 0) is used for the determination of contact angle. Care should be taken throughout fiber preparation to minimize fiber exposure to handling to ensure that contamination is kept to a minimum. The fiber sample is attached to the wire hanger with scotch tape such that 2-3 cm of fiber extends beyond the end of the hanger. Then the fiber sample is cut with a razor so that 1.5 cm is extending beyond the end

of the hanger. An optical microscope is used to determine the average diameter (3 to 4 measurements) along the fiber.

The sample on the wire hanger is suspended from the balance stirrup on loop "A". The immersion liquid is distilled water and it is changed for each specimen. The 5 specimen parameters are entered (i.e. fiber diameter) and the test started. The stage advances at 151.75microns/second until it detects the Zero Depth of Immersion when the fiber contacts the surface of the distilled water. From the Zero Depth of Immersion, the fiber advances into the water for 1 cm, dwells for 0 seconds and then immediately recedes 1 cm. The auto-analysis of the contact angle done by the 10 software determines the advancing and receding contact angles of the fiber sample based on standard calculations identified in the manual. Contact angles of 0 or <0 indicate that the sample has become totally wettable. Five replicates for each sample are tested and a statistical analysis for mean, standard deviation, and coefficient of variation percent are calculated. As reported in the examples herein 15 and as used throughout the claims, the Advancing Contact Angle value represents the advancing contact angle of distilled water on a fiber sample determined according to the preceding test method. Similarly, as reported in the examples herein and as used throughout the claims, the Receding Contact Angle value represents the receding contact angle of distilled water on a fiber sample determined 20 according to the preceding test method.

#### Mechanical Properties

A suitable technique for determining the mechanical properties of the fiber can employ a Sintech tensile tester (SINTECH 1/D) and Testworks 3.03 software, both 25 available from MTS System Co., of Cary, North Carolina. Equipment and software having substantially equivalent capabilities may also be employed. Fiber testing is carried out using a 10 pound load cell and fiber grips. It is necessary to have grips which are designated for the testing of fibers. Numerous configurations which fulfill this purpose are available from the aforementioned MTS System Co. All fiber testing 30 is done using a one-inch gauge length and 500 mm/minute grip separation speed. A bundle of 30 fibers is threaded into the grips with care taken to minimize the chance for any contamination. An extrapolated diameter for the fiber bundle is determined from the average diameter of the individual fibers determined via optical microscopy and converted into a theoretical diameter for the fiber bundle as if it were a single

fiber. In each experiment, the fiber bundle is stretched until breakage occurs and the software creates a stress-versus-strain plot and calculates the mechanical properties for the sample. Mechanical properties of interest in the study are break stress and percent strain at the break. Five replicates are run and a statistical analysis

5 performed. In each experiment, the fiber is stretched until breakage occurs and the software creates a stress-versus-strain plot and calculates the desired mechanical properties for the sample. The mechanical properties can include, for example, Young's modulus, stress at break, and percent strain or elongation at break.

10 **EXAMPLES**

Various materials were used as components to form thermoplastic compositions and multicomponent fibers in the following Examples. The designation and various properties of these materials are listed in Table 1.

15 Samples 1 and 2 are poly(lactic acid) (PLA) polymers obtained from Chronopol Inc., Golden, Colorado.

A polybutylene succinate (PBS), available from Showa Highpolymer Co., Ltd., Tokyo, Japan, under the designation Bionolle 1020 polybutylene succinate, was obtained.

20 A polybutylene succinate (PBS) with long chain branching, available from Showa Highpolymer Co., Ltd., Tokyo, Japan, under the designation Bionolle 1903 polybutylene succinate, was obtained.

25 The wetting agent used throughout the examples was obtained from Petrolite Corporation of Tulsa, Oklahoma, under the designation UNITHOX®480 ethoxylated alcohol, which exhibited a number average molecular weight of about 2250, an ethoxylate percent of about 80 weight percent, and an HLB value of about 16.

Table 1

Material Designation	L:D Ratio	Melting Temp. (°C)	Weight Average Molecular Weight	Number Average Molecular Weight	Polydispersity Index	Residual Lactic Acid Monomer
PLA Sample 1	100:0	175	187,000	118,000	1.58	<1%
PLA Sample 2	95:5	140-145	190,000	108,000	1.76	<3%
Bionolle 1020	N/A	95	40,000 to 1,000,000	20,000 to 300,000	~2 to ~3.3	N/A
Bionolle 1903	N/A	120	40,000 to 1,000,000	20,000 to 300,000	~2 to ~3.3	N/A

5

Example 1

Thermoplastic compositions were prepared using varying amounts of a poly(lactic acid) polymer, a polybutylene succinate, and a wetting agent. To prepare a specific thermoplastic composition, the various components were first dry mixed and then melt blended in a counter-rotating twin screw to provide vigorous mixing of the components. The melt mixing involves partial or complete melting of the components combined with the shearing effect of rotating mixing screws. Such conditions are conducive to optimal blending and even dispersion of the components of the thermoplastic composition. Twin screw extruders such as a Haake Rheocord 90, available from Haake GmbH of Karlsruhe, Germany, or a Brabender twin screw mixer (cat no 05-96-000) available from Brabender Instruments of South Hackensack, New Jersey, or other comparable twin screw extruders, are well suited to this task. The melted composition is cooled following extrusion from the melt mixer on either a liquid cooled roll or surface and/or by forced air passed over the extrudate. The cooled composition is then subsequently pelletized for conversion to fibers.

Converting these resins into fiber and nonwoven was conducted on a in-house 0.75 inch diameter extruder with a 24:1 L:D (length:diameter) ratio screw and three heating zones which feed into a transfer pipe from the extruder to the spin pack, which constitutes the 4th heating zone and contains a 0.62 inch diameter Koch® 5 SMX type static mixer unit, available from Koch Engineering Company Inc. of New York, New York, and then into the spinning head (5th heating zone) and through a spin plate which is simply a plate with numerous small holes through which the molten polymer will be extruded through. The spin plate used herein had 15 to 30 holes, where each hole has a 20 mil diameter. The temperature of each heating 10 zone is indicated sequentially under the extrusion temperatures heading in Table 2. The fibers are air quenched using air at a temperature range of 13°C to 22°C, and drawn down by a mechanical draw roll and passed on to either a winder unit for collection, or to a fiber drawing unit for spunbond formation and bonding, or through accessory equipment for heat setting or other treatment before collection.

15 The fibers were then evaluated for contact angle and heat shrinkage. The composition of the various fibers and the results of the evaluations are shown in Table 3.

Those skilled in the art will recognize that the present invention is capable of 20 many modifications and variations without departing from the scope thereof. Accordingly, the detailed description and examples set forth above are meant to be illustrative only and are not intended to limit, in any manner, the scope of the invention as set forth in the appended claims.

TABLE 2

<u>Sample #</u>	<u>Extrusion Temperatures (°C)</u>
*1	150/175/155/160/160
*2	180/185/185/190/190
*3	150/155/160/170/170
*4	150/150/160/170/170
*5	150/150/160/170/170
*6	175/185/190/195/200
*7	170/175/180/185/190
*8	190/205/205/210/210
9	175/185/190/195/200
10	175/185/190/195/200
11	165/175/175/185/185
12	165/175/175/185/185
13	165/175/175/185/185
14	180/190/190/195/200
15	160/165/170/170/175

\*Not an example of the present invention.

TABLE 3

Sample #	PLA Type	PLA Wt %	PBS Type	PBS Wt %	Wetting Agent Wt %	Composition of Fiber		Contact Angle Advancing	Receding	Heat Shrinkage	Jet Stretch
						Wetted	Agent				
*1	PLA Sample 2	100 %	--	--	--	94°	75°	13 %	96		
*2	--	--	Bionolle 1020	100 %	--	93°	60°	0 %	96		
*3	PLA Sample 2	70 %	Bionolle 1020	30 %	--	85°	62°	3 %	96		
*4	PLA Sample 2	85 %	Bionolle 1020	15 %	--	99°	53°	29 %	96		
*5	PLA Sample 2	61 %	Bionolle 1020	26 %	13 %	97°	48°	2 %	96		
*6	PLA Sample 1	90 %	Bionolle 1903	10 %	--	81°	59°	6 %	96		
*7	PLA Sample 1	100 %	--	--	--	84°	66°	27 %	96		
*8	--	--	Bionolle 1903	100 %	--	102°	65°	-1 %	9.8		
9	PLA Sample 1	86 %	Bionolle 1903	9 %	5 %	73°	44°	3 %	96		
10	PLA Sample 1	78 %	Bionolle 1903	9 %	13 %	71°	44°	-2 %	96		
11	PLA Sample 1	87 %	Bionolle 1903	10 %	3 %	77°	49°	3 %	96		
12	PLA Sample 1	87 %	Bionolle 1020	10 %	3 %	75°	48°	4 %	96		
13	PLA Sample 1	89 %	Bionolle 1903	10 %	1 %	79°	55°	5 %	96		
14	PLA Sample 1	9 %	Bionolle 1903	86 %	1 %	48°	39°	0 %	51		
15	PLA Sample 1	10 %	Bionolle 1020	87 %	3 %	50°	41°	--	--		

\* Not an example of the present invention.

**The claims defining the invention are as follows:**

1. A thermoplastic composition blend comprising:
  - a. a poly(lactic acid) polymer in a weight amount that is greater than 0 but less than 100 weight percent,
  - b. a polymer selected from the group consisting of a polybutylene succinate polymer, a polybutylene succinate adipate polymer, and a mixture of such polymers, in a weight amount that is greater than 0 but less than 100 weight percent,
  - c. a wetting agent, which exhibits a hydrophilic-lipophilic balance ratio that is between about 10 to about 40, in a weight amount that is greater than 0 to about 15 weight percent,
- 10 wherein all weight percents are based on the total weight amount of the poly(lactic acid) polymer; the polymer selected from the group consisting of a polybutylene succinate polymer, a polybutylene succinate adipate polymer, and a mixture of such polymers; and the wetting agent present in the thermoplastic composition,
- 15 wherein the poly(lactic acid) polymer, the polymer selected from the group consisting of a polybutylene succinate polymer, a polybutylene succinate adipate polymer, and a mixture of such polymers, and the wetting agent are substantially unreacted with each other.
2. The thermoplastic composition of claim 1 wherein the poly(lactic acid) polymer is present in a weight amount that is between about 5 weight percent to about 95 weight percent, the polymer selected from the group consisting of a polybutylene succinate polymer, a polybutylene succinate adipate polymer, and a mixture of such polymers, is present in a weight amount that is between about 5 weight percent to about 95 weight percent, and the wetting agent is present in a weight amount that is between about 0.5 weight percent to about 15 weight percent.
- 25 3. The thermoplastic composition of claim 2 wherein the poly(lactic acid) polymer is present in a weight amount that is between about 10 weight percent to about 90 weight percent, the polymer selected from the group consisting of a polybutylene succinate polymer, a polybutylene succinate adipate polymer, and a mixture of such polymers, is present in a weight amount that is between about 10 weight percent to about 90 weight percent, and the wetting agent is present in a weight amount that is between about 1 weight percent to about 13 weight percent.
- 30 4. The thermoplastic composition of any one of claims 1 to 3 wherein the wetting agent exhibits a hydrophilic-lipophilic balance ratio that is between about 10 to about 20.



5. The thermoplastic composition of any one of claims 1 to 4 wherein the wetting agent is an ethoxylated alcohol.

6. The thermoplastic composition of any one of claims 1 to 5 wherein the poly(lactic acid) polymer is present in a weight amount that is between about 75 weight percent to about 90 weight percent and the polymer selected from the group consisting of a polybutylene succinate polymer, a polybutylene succinate adipate polymer, and a mixture of such polymers, is present in a weight amount that is between about 5 weight percent to about 20 weight percent, and the wetting agent is an ethoxylated alcohol.

7. A multicomponent fiber prepared from a thermoplastic composition, wherein the thermoplastic composition comprises:

a. a poly(lactic acid) polymer in a weight amount that is greater than 0 but less than 100 weight percent,

b. a polymer selected from the group consisting of a polybutylene succinate polymer, a polybutylene succinate adipate polymer, and a mixture of such polymers, in a weight amount that is greater than 0 but less than 100 weight percent,

c. a wetting agent, which exhibits a hydrophilic-lipophilic balance ratio that is between about 10 to about 40, in a weight amount that is greater than 0 to about 15 weight percent,

wherein all weight percents are based on the total weight amount of the poly(lactic acid) polymer; the polymer selected from the group consisting of a polybutylene succinate polymer, a polybutylene succinate adipate polymer, and a mixture of such polymers; and the wetting agent present in the thermoplastic composition;

wherein the poly(lactic acid) polymer, the polymer selected from the group consisting of a polybutylene succinate polymer, a polybutylene succinate adipate polymer, and a mixture of such polymers and the wetting agent are substantially unreacted with each other,

wherein the multicomponent fiber exhibits an Advancing Contact Angle value that is less than about 80 degrees and a Receding Contact Angle value that is less than about 60 degrees.

8. The multicomponent fiber of claim 7 wherein the poly(lactic acid) polymer is present in a weight amount that is between about 5 weight percent to about 95 weight percent, the polymer selected from the group consisting of a polybutylene succinate polymer, a polybutylene succinate adipate polymer, and a mixture of such polymers, is present in a weight amount that is between about 5 weight percent to about 95 weight percent, and the wetting agent is present in a weight amount that is between about 0.5 weight percent to about 15 weight percent.

9. The multicomponent fiber of claim 7 or 8 wherein the wetting agent exhibits a hydrophilic-lipophilic balance ratio that is between about 10 to about 20.



10. The multicomponent fiber of any one of claims 7 to 9 wherein the wetting agent is an ethoxylated alcohol.

11. The multicomponent fiber of any one of claims 7 to 10 wherein the multicomponent fiber exhibits an Advancing Contact Angle value that is less than about 75 degrees and a Receding Contact Angle value that is less than about 55 degrees.

12. The multicomponent fiber of any one of claims 7 to 11 wherein the difference between the Advancing Contact Angle value and the Receding Contact Angle value is less than about 30 degrees.

13. The multicomponent fiber of any one of claims 7 to 12 wherein the multicomponent fiber exhibits a Heat Shrinkage value that is less than about 15 percent.

14. The multicomponent fiber of any one of claims 7 to 13 wherein the poly(lactic acid) polymer is present in a weight amount that is between about 75 weight percent to about 90 weight percent, the polymer selected from the group consisting of a polybutylene succinate polymer, a polybutylene succinate adipate polymer, and a mixture of such polymers, is present in a weight amount that is between about 5 weight percent to about 20 weight percent, the wetting agent is an ethoxylated alcohol, the difference between the Advancing Contact Angle value and the Receding Contact Angle value is less than about 30 degrees, and the multicomponent fiber exhibits a Heat Shrinkage value that is less than about 15 percent.

15. A disposable absorbent product comprising a liquid-permeable topsheet, a backsheet attached to the topsheet, and an absorbent core positioned between the liquid-permeable topsheet and the backsheet, wherein the liquid-permeable topsheet comprises a multicomponent fiber prepared from a thermoplastic composition, wherein the thermoplastic composition comprises:

a. a poly(lactic acid) polymer in a weight amount that is greater than 0 but less than 100 weight percent,

b. a polymer selected from the group consisting of a polybutylene succinate polymer, a polybutylene succinate adipate polymer, and a mixture of such polymers, in a weight amount that is greater than 0 but less than 100 weight percent,

c. a wetting agent, which exhibits a hydrophilic-lipophilic balance ratio that is between about 10 to about 40, in a weight amount that is greater than 0 to about 15 weight percent,

30 wherein all weight percents are based on the total weight amount of the poly(lactic acid) polymer; the polymer selected from the group consisting of a polybutylene succinate polymer, a



polybutylene succinate adipate polymer, and a mixture of such polymers; and the wetting agent present in the thermoplastic composition;

5 wherein the poly(lactic acid) polymer, the polymer selected from the group consisting of a polybutylene succinate polymer, a polybutylene succinate adipate polymer, and a mixture of such polymers, and the wetting agent are substantially unreacted with each other,

wherein the multicomponent fiber exhibits an Advancing Contact Angle value that is less than about 80 degrees and a Receding Contact Angle value that is less than about 60 degrees.

16. The disposable absorbent product of claim 15 wherein the poly(lactic acid) polymer is present in a weight amount that is between about 5 weight percent to about 95 weight percent, the 10 polymer selected from the group consisting of a polybutylene succinate polymer, a polybutylene succinate adipate polymer, and a mixture of such polymers, is present in a weight amount that is between about 5 weight percent to about 95 weight percent, and the wetting agent is present in a weight amount that is between about 0.5 weight percent to about 15 weight percent.

17. The disposable absorbent product of claim 15 or 16 wherein the wetting agent exhibits 15 a hydrophilic-lipophilic balance ratio that is between about 10 to about 20.

18. The disposable absorbent product of any one of claims 15 to 17 wherein the wetting agent is an ethoxylated alcohol.

19. The disposable absorbent product of any one of claims 15 to 18 wherein the 20 multicomponent fiber exhibits an Advancing Contact Angle value that is less than about 75 degrees and a Receding Contact Angle value that is less than about 55 degrees.

20. The disposable absorbent product any one of claims 15 to 19 wherein the difference between the Advancing Contact Angle value and the Receding Contact Angle value is less than about 30 degrees.

21. The disposable absorbent product of any one of claims 15 to 20 wherein the 25 multicomponent fiber exhibits a Heat Shrinkage value that is less than about 15 percent.

22. The disposable absorbent product of any one of claims 15 to 21 wherein the poly(lactic acid) polymer is present in a weight amount that is between about 75 weight percent to about 90 weight percent, the polymer selected from the group consisting of a polybutylene succinate polymer, a polybutylene succinate adipate polymer, and a mixture of such polymers, is 30 present in a weight amount that is between about 5 weight percent to about 20 weight percent, the wetting agent is an ethoxylated alcohol, the difference between the Advancing Contact Angle value and the Receding Contact Angle value is less than about 30 degrees, and the multicomponent fiber exhibits a Heat Shrinkage value that is less than about 15 percent.

23. A thermoplastic composition blend, substantially as hereinbefore described with 35 reference to any one of the examples but excluding any comparative examples.



24. A process for preparing a thermoplastic composition blend, substantially as hereinbefore described with reference to any one of the examples but excluding any comparative examples.

25. A thermoplastic composition blend prepared by the process of claim 24.

5 26. A thermoplastic composition blend according to any one of claims 1 to 6, 23 or 25 when used for preparing a multicomponent fiber.

27. A multicomponent fiber, substantially as hereinbefore described with reference to any one of the examples but excluding any comparative examples.

10 28. A process for preparing a multicomponent fiber, substantially as hereinbefore described with reference to any one of the examples but excluding any comparative examples.

29. A multicomponent fiber prepared by the process of claim 28.

30. A multicomponent fiber according to any one of claims 7 to 14, 27 or 29 when used in a disposable absorbent product.

15 31. A disposable absorbent product, substantially as hereinbefore described with reference to any one of the examples but excluding any comparative examples.

32. A process for preparing a disposable absorbent product, substantially as hereinbefore described with reference to any one of the examples but excluding any comparative examples.

20 33. A disposable absorbent product prepared by the process of claim 32.

34. A disposable absorbent product according to any one of claims 15 to 22, 31 or 33, when used for absorbing fluid.

**Dated 29 May, 2001**  
**Kimberly-Clark Worldwide, Inc.**

**Patent Attorneys for the Applicant/Nominated Person**  
**SPRUSON & FERGUSON**

