

US011833636B2

(12) **United States Patent**  
**Watanabe et al.**

(10) **Patent No.:** **US 11,833,636 B2**

(45) **Date of Patent:** **Dec. 5, 2023**

(54) **SUBSTRATE POLISHING APPARATUS,  
METHOD OF CREATING THICKNESS MAP,  
AND METHOD OF POLISHING A  
SUBSTRATE**

(71) Applicant: **EBARA CORPORATION**, Tokyo (JP)

(72) Inventors: **Katsuhide Watanabe**, Tokyo (JP);  
**Yoichi Shiokawa**, Tokyo (JP); **Keita  
Yagi**, Tokyo (JP); **Akira Nakamura**,  
Tokyo (JP)

(73) Assignee: **EBARA CORPORATION**, Tokyo (JP)

(\* ) Notice: Subject to any disclaimer, the term of this  
patent is extended or adjusted under 35  
U.S.C. 154(b) by 307 days.

(21) Appl. No.: **17/028,072**

(22) Filed: **Sep. 22, 2020**

(65) **Prior Publication Data**

US 2021/0101250 A1 Apr. 8, 2021

(30) **Foreign Application Priority Data**

Oct. 3, 2019 (JP) ..... 2019/182848

(51) **Int. Cl.**  
**B24B 37/013** (2012.01)  
**B24B 49/12** (2006.01)  
**B24B 49/10** (2006.01)

(52) **U.S. Cl.**  
CPC ..... **B24B 37/013** (2013.01); **B24B 49/12**  
(2013.01); **B24B 49/105** (2013.01)

(58) **Field of Classification Search**  
CPC ... B24B 37/013; B24B 37/005; B24B 37/042;  
B24B 37/04; B24B 37/10; B24B 37/105;  
(Continued)

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,240,552 A \* 8/1993 Yu ..... B24B 37/04  
438/959

7,018,271 B2 3/2006 Wiswesser et al.  
(Continued)

FOREIGN PATENT DOCUMENTS

EP 1618991 B1 \* 1/2008 ..... B24B 37/005  
JP 2013-107167 A 6/2013

(Continued)

OTHER PUBLICATIONS

U.S. Appl. No. 16/441,904; Non-Final Office Action; dated May 5,  
2021; 24 pages.

*Primary Examiner* — Joel D Crandall

*Assistant Examiner* — Michael A Gump


(74) *Attorney, Agent, or Firm* — BakerHostetler

(57) **ABSTRACT**

To measure thickness in a polishing treatment more effi-  
ciently. A substrate polishing apparatus comprises a rotat-  
ably configured polishing table provided with a sensor that  
outputs a signal related to a thickness, a rotatably configured  
polishing head that faces the polishing table, a substrate  
being attachable to a face of the polishing head that faces the  
polishing table, and a controller. The controller acquires a  
signal from the sensor when the sensor passes over a surface  
to be polished of the substrate, specifies an orbit of the  
sensor with respect to the substrate on a basis of a profile of  
the signal, calculates a thickness of the substrate at each  
point on the orbit on a basis of the signal, and creates a  
thickness map on a basis of the calculated thickness at each  
point on a plurality of orbits of the sensor.

**19 Claims, 16 Drawing Sheets**

1000



(58) **Field of Classification Search**

CPC ..... B24B 49/12; B24B 49/105; B24B 49/02;  
B24B 49/10; B24B 49/04; B24B 7/228;  
H01L 21/67092  
USPC ..... 451/6  
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

8,696,924 B2 4/2014 Tada et al.  
2007/0224915 A1\* 9/2007 David ..... B24B 37/013  
451/6  
2013/0065493 A1\* 3/2013 Takahashi ..... B24B 49/105  
451/259  
2013/0273814 A1 10/2013 Kobayashi et al.  
2014/0030956 A1\* 1/2014 Zhang ..... B24B 51/00  
451/5  
2014/0242878 A1\* 8/2014 Cherian ..... B24B 49/12  
451/6  
2015/0017887 A1\* 1/2015 Kobayashi ..... B24B 37/013  
451/73  
2015/0140907 A1\* 5/2015 Watanabe ..... B24B 37/04  
451/73  
2016/0059375 A1\* 3/2016 Ito ..... H01L 22/12  
451/6  
2018/0061032 A1 3/2018 Benvegna

FOREIGN PATENT DOCUMENTS

JP 2013-222856 A 10/2013  
JP 2015020242 A \* 2/2015 ..... B24B 37/013  
WO WO 2015/200098 A1 12/2015  
WO WO 2015/200101 A1 12/2015

\* cited by examiner

Fig. 1A





Fig. 1B

100B






Fig. 1C

Fig. 2




Fig. 3




Fig. 4




Fig. 5




Fig. 6




Fig. 7




Fig. 8




Fig. 9




Fig. 10




Fig. 11




Fig. 12




Fig. 13




Fig. 14




Fig. 15




Fig. 16






Fig. 17





Fig. 18



1

**SUBSTRATE POLISHING APPARATUS,  
METHOD OF CREATING THICKNESS MAP,  
AND METHOD OF POLISHING A  
SUBSTRATE**

TECHNICAL FIELD

The present invention relates to a substrate polishing apparatus, a method of creating a thickness map, and a method of polishing a substrate.

BACKGROUND ART

One apparatus used to manufacture semiconductor devices is a chemical mechanical polishing (CMP) apparatus. A typical CMP apparatus is provided with a polishing table to which a polishing pad is attached, and a polishing head to which a substrate is attached. In a typical CMP apparatus, a substrate is polished by supplying a polishing solution to the polishing pad and rotating at least one of the polishing table and the polishing head while putting the polishing pad and the substrate in contact with each other.

In a polishing step using a CMP apparatus, the film thickness of the polished substrate is measured by a thickness measuring instrument, and if the desired thickness or thickness profile has not been achieved, the substrate is polished again. PTL 1 is known as one example of a technology that detects whether or not a substrate has been polished a desired amount.

CITATION LIST

Patent Literature

PTL 1: Japanese Patent Laid-Open No. 2013-222856

SUMMARY OF INVENTION

Technical Problem

Typically, thickness measurement is performed using a special-purpose measuring device (for example, a measuring device installed together with the CMP apparatus), and because the measurement is time-consuming, thickness measurement is a factor contributing to lowered production efficiency in the CMP step. Consequently, there is a demand to make thickness measurement more efficient to raise the production efficiency of the CMP step.

Solution to Problem

To address the above problem, there is disclosed a substrate polishing apparatus comprising a rotatably configured polishing table provided with a sensor that outputs a signal related to a thickness, a rotatably configured polishing head that faces the polishing table, a substrate being attachable to a face of the polishing head that faces the polishing table, and a controller. The controller acquires a signal from the sensor when the sensor passes over a surface to be polished of the substrate, specifies an orbit of the sensor with respect to the substrate on a basis of a profile of the signal, calculates a thickness of the substrate at each point on the orbit on a basis of the signal, and creates a thickness map on a basis of the calculated thickness at each point on a plurality of orbits of the sensor.

BRIEF DESCRIPTION OF DRAWINGS

FIG. 1A is a schematic configuration diagram of a substrate polishing apparatus according to an embodiment;

2

FIG. 1B is a schematic configuration diagram of a substrate polishing apparatus according to another embodiment;

FIG. 1C is a diagram illustrating a substrate polishing apparatus according to yet another embodiment;

5 FIG. 2 is a front view of the substrate polishing apparatus according to the embodiment;

FIG. 3 is a diagram illustrating orbits on a substrate of an eddy current sensor as seen from the substrate;

10 FIG. 4 is a flowchart illustrating overall operations by the substrate polishing apparatus according to the embodiment;

FIG. 5 is a flowchart illustrating a method of creating a water polishing thickness map during a water polishing treatment according to the embodiment;

15 FIG. 6 is a flowchart illustrating a method of creating a polishing thickness map during a polishing treatment according to the embodiment;

FIG. 7 is a diagram illustrating an example of a sensor output map;

20 FIG. 8 is a diagram illustrating a sensor output map for explaining steps 506 and 508;

FIG. 9 is a diagram illustrating a profile of a polishing signal used for explanation;

FIG. 10 is a diagram illustrating profiles A-A', B-B', and C-C';

25 FIG. 11 is a diagram for explaining a process of averaging a thickness map;

FIG. 12 is a diagram illustrating an example of an averaged thickness map;

30 FIG. 13 is a diagram for explaining a process of interpolating a thickness map;

FIG. 14 is a diagram illustrating an example of a method of computing a polishing rate;

FIG. 15 is a front view of a substrate polishing apparatus according to another embodiment;

35 FIG. 16 is a diagram for explaining the creation of a map expressing a distribution of dishing on a substrate;

FIG. 17 is a diagram illustrating an example of a method of computing the polishing progress on the basis of a polishing signal; and

40 FIG. 18 is a diagram illustrating a different example of a method of computing the polishing progress on the basis of a polishing signal.

DESCRIPTION OF EMBODIMENTS

Hereinafter, embodiments of the present invention will be described in detail and with reference to the drawings.

FIG. 1A is a schematic configuration diagram of a substrate polishing apparatus 100A according to an embodiment. The substrate polishing apparatus 100A in the present embodiment is a CMP apparatus. The CMP apparatus 100A is provided with a polishing chamber 101 and a controller 140. A substrate 121 treated in previous steps is attached to a polishing table (not illustrated) inside the polishing chamber 101 and polished. The previous steps include a step of forming a thin film of a metal or an oxide for example on the substrate 121, and a step of forming a pattern on the substrate 121 by etching the thin film. The polishing table is provided with a thickness measuring instrument 150. During or after the polishing of the substrate 121, the thickness measuring instrument 150 generates a signal related to the thickness of the thin film on the substrate 121, and sends the generated signal to the controller 140. The controller 140 creates a thickness map expressing a thickness distribution on the substrate 121 on the basis of the signal. On the basis of the thickness map, the controller 140 may polish the substrate 121 further or optimize the parameters of subse-

quent polishing cycles (such as the pressure that presses the substrate **121** against the polishing table, the rotational speed of the polishing table and the polishing head that holds the substrate **121**, the amount of slurry supplied to the surface of the substrate **121** to be polished, and the temperature of the surface of the substrate **121** to be polished). When the desired polishing is achieved, the substrate **121** is washed and dried inside a cleaning chamber (not illustrated) provided in the substrate polishing apparatus **100A**, and then passed on to the next steps. The next steps include a step of forming an additional thin film on the substrate **121** and a step of dicing the substrate **121** into a plurality of chips, for example.

FIG. 1B is a schematic configuration diagram of a substrate polishing apparatus **100B** according to another embodiment. The substrate polishing apparatus **100B** is a CMP apparatus, and is provided with two polishing chambers **101A** and **101B**. A substrate **121** is first polished in the polishing chamber **101A**. A signal from a thickness measuring instrument **150** provided in the polishing chamber **101A** is sent to the controller **140**, and a thickness map is created. After the polishing in the polishing chamber **101A**, the substrate **121** is sent to the polishing chamber **101B**. The controller **140** polishes the substrate **121** further in the polishing chamber **101B** on the basis of the thickness map.

FIG. 1C illustrates substrate polishing apparatuses **100C-1** and **100C-2** according to yet another embodiment. The first substrate polishing apparatus **100C-1** is a CMP apparatus. The second substrate polishing apparatus **100C-2** may be a CMP apparatus or a different type of polishing apparatus. The substrate **121** is first polished in a polishing chamber **101** of the CMP apparatus **100C-1**. A signal from a thickness measuring instrument **150** provided in the polishing chamber **101** of the CMP apparatus **100C-1** is sent to the controller **140**, and a thickness map is created. Note that the controller **140** may be provided in either of the substrate polishing apparatuses **100C-1** and **100C-2**. After the polishing in the CMP apparatus **100C-1**, the substrate **121** is sent to the second substrate polishing apparatus **100C-2**. The controller **140** polishes the substrate **121** further in the polishing chamber **101** of the second substrate polishing apparatus **100C-2** on the basis of the thickness map.

FIG. 2 is a front view of the substrate polishing apparatus **100** according to the embodiment. The substrate polishing apparatus **100** illustrated in FIG. 2 corresponds to any of the substrate polishing apparatuses **100A**, **100B**, **100C-1**, and **100C-2** in FIGS. 1A, 1B, and 1C. The substrate polishing apparatus **100** in FIG. 2 is a CMP apparatus. However, the substrate polishing apparatus **100** is not limited to a CMP apparatus. It is sufficient for the substrate polishing apparatus **100** to be an apparatus that polishes a substrate by rotating a polishing table provided with an eddy current sensor.

The CMP apparatus **100** is provided with a polishing table **110**, a polishing head **120**, and a liquid supplying mechanism **130**. The CMP apparatus **100** is additionally provided with a controller **140** for controlling each component. The controller **140** is provided with a storage device **141**, a processor **142**, and an input/output device **143**, for example.

A polishing pad **111** is removably attached to the top surface of the polishing table **110**. Here, the “top surface” of the polishing table **110** is a term referring to the surface of the polishing table **110** that faces the polishing head **120**. Consequently, the “top surface” of the polishing table **110** is not limited to the “surface positioned on top in the vertical direction”. The polishing head **120** is provided facing the polishing table **110**. A substrate **121** is removably attached to

the surface of the polishing head **120** that faces the polishing table **110**. The liquid supplying mechanism **130** is configured to supply a polishing solution such as a slurry to the polishing pad **111**. Note that the liquid supplying mechanism **130** may also be configured to supply liquids other than a polishing solution, such as a cleaning solution or a chemical solution.

The substrate polishing apparatus **100** is capable of using a vertical movement mechanism not illustrated to lower the polishing head **120** and bring the substrate **121** into contact with the polishing pad **111**. However, the vertical movement mechanism may also be capable of moving the polishing table **110** vertically. The polishing table **110** and the polishing head **120** are made to rotate by a device such as a motor not illustrated. The CMP apparatus **100** polishes the substrate **121** by rotating both the polishing table **110** and the polishing head **120** while the substrate **121** and the polishing pad **111** are in contact with each other.

The CMP apparatus **100** is further provided with an airbag **122** partitioned into a plurality of concentric compartments. The airbag **122** is provided on the polishing head **120**. The airbag **122** may also be provided on the polishing table **110** instead of or in addition to the airbag **122** provided on the polishing head **120**. The airbag **122** is a member for adjusting the polishing pressure of the substrate **121** in different areas of the substrate **121**. The airbag **122** is configured to change in volume depending on the pressure of air introduced internally. Note that although the term “air” bag is used, a fluid other than air, such as nitrogen gas or pure water for example, may also be introduced into the airbag **122**.

An eddy current sensor **150** is provided inside the polishing table **110**. Specifically, the eddy current sensor **150** is installed at a position passing through the center of the substrate **121** being polished. The eddy current sensor **150** corresponds to the thickness measuring instrument **150** in FIGS. 1A, 1B, and 1C. The eddy current sensor **150** induces an eddy current in a conductive layer at the surface of the substrate **121**. The eddy current sensor **150** additionally detects the thickness of the conductive layer at the surface of the substrate **121** from changes in the impedance caused by a magnetic field produced by the eddy current.

Here, the magnitude of the signal output by the eddy current sensor **150** also changes according to factors other than the thickness of the conductive layer at the surface of the substrate **121**. Factors that affect the magnitude of the signal output by the eddy current sensor **150** include the density and the width of interconnects formed on the substrate **121** as well as the presence or absence of lower-layer interconnects, for example. Consequently, to detect the thickness of the thin film on the substrate **121** precisely, the factors that affect the magnitude of the signal output by the eddy current sensor **150** must be considered. Note that herein, “lower-layer interconnects” refer to interconnects that are not exposed on the surface of the substrate **121**. Consequently, in FIG. 2, interconnects positioned lower in the vertical direction of FIG. 2 are lower-layer interconnects. However, depending on the attitude of the substrate **121**, the “lower-layer” interconnects are not necessarily positioned lower in the vertical direction. Furthermore, the shape of the interconnects is not particularly limited.

The factors that affect the magnitude of the signal (as described above, factors such as the density and the width of interconnects as well as the presence or absence of lower-layer interconnects, for example) may change depending on the location on the substrate **121**. Consequently, to detect the thickness of the thin film on the substrate **121** precisely using the eddy current sensor **150**, the location on the substrate

**121** that is measured by the eddy current sensor **150** must be specified. In other words, to detect the thickness of the thin film on the substrate **121** precisely using the eddy current sensor **150**, the orbit of the eddy current sensor **150** as seen from the substrate **121** must be specified.

Here, in the case that is free from any type of error such as dimensional error in each component, assembly error, and error in the rotational speed (hereinafter referred to as “ideal conditions”) and also in the case where the rotational speed of the polishing table **110** and the rotational speed of the polishing head **120** are a predetermined combination, the orbit of the eddy current sensor **150** as seen from the substrate is limited to a few paths. As an example, in the case where the rotational speed of the polishing table **110** is 70 rpm ( $70 \text{ min}^{-1}$ ) and the rotational speed of the polishing head **120** is 77 rpm ( $11 \text{ min}^{-1}$ ), the orbits on the substrate **121** of the eddy current sensor **150** as seen from the substrate **121** is the one illustrated in FIG. 3. FIG. 3 is a view seen from the surface of the substrate **121**, and the orbits of the eddy current sensor **150** are illustrated as solid-line arrows. Under these conditions, the orbit of the eddy current sensor **150** rotates 36 times for every rotation of the polishing table **110**. In other words, an interval  $\theta$  between the orbits of the eddy current sensor **150** as seen from the substrate **121** is 36 degrees. Consequently, there are 10 orbits in this case ( $360 \text{ (degrees)} / 36 \text{ (degrees/orbit)} = 10 \text{ (orbits)}$ ). Note that the signs “1” to “10” indicated in FIG. 3 are signs labeling the orbits of the first to tenth orbits of the eddy current sensor **150**.

Note that in reality, the CMP apparatus **100** is not necessarily in ideal conditions. Also, the rotational speed of the polishing table **110** and the rotational speed of the polishing head **120** are not necessarily constant. Depending on the polishing process, the rotational speed of the polishing table **110** and the rotational speed of the polishing head **120** may also be changed while polishing the substrate **121**. Consequently, the orbits of the eddy current sensor **150** may differ from those illustrated in FIG. 3.

Note that a plurality of eddy current sensors **150** may also be distributed throughout the polishing table **110**. The plurality of eddy current sensors **150** follow respectively different orbits on the substrate **121** at the same time. Consequently, by using the signals from the plurality of eddy current sensors **150** at the same time, the time taken to create a thickness map according to the method described later can be shortened.

FIG. 4 is a flowchart illustrating overall operations by the substrate polishing apparatus **100** according to the embodiment.

In step **402**, a polishing treatment is performed. Specifically, the substrate **121** is attached to the polishing head **120**, and a slurry is supplied from the liquid supplying mechanism **130**. With the substrate **121** pressed against the polishing table **110** by the polishing head **120**, the polishing table **110** and the polishing head **120** are both made to rotate, and the substrate **121** is polished. During the polishing, a “polishing thickness map” is created on the basis of the output signal from the eddy current sensor **150**. The polishing treatment in step **402** is continued until a predetermined end condition is satisfied, such as until a preset polishing time for polishing the film targeted by the polishing by a certain amount elapses, for example. When the polishing treatment ends, the flow proceeds to step **404**.

In step **404**, a water polishing treatment is performed. Specifically, water or pure water (hereinafter simply referred to as water) is supplied from the liquid supplying mechanism **130** instead of the slurry. While the water is being supplied from the liquid supplying mechanism **130**, the

polishing table **110** and the polishing head **120** continue to rotate. The slurry is washed away and removed by the water, and the polished surface of the substrate **121** is cleaned. Because the slurry is removed, the substrate **121** is substantially not polished during the water polishing, or the polishing rate is greatly lowered compared to the polishing in step **402**. During the water polishing, a “water polishing thickness map” is created on the basis of the output signal from the eddy current sensor **150**. The water polishing treatment in step **404** is continued for a preset time that is long enough to wash away the slurry sufficiently, for example. When the water polishing treatment ends, the flow proceeds to step **406**.

In step **406**, it is determined whether or not a repolishing treatment of the substrate **121** is necessary, on the basis of the created thickness maps. For example, it is determined whether or not a desired thickness or thickness profile has been achieved throughout the entire surface of the substrate **121** or in at least a portion of the substrate **121**. In the case where the desired thickness or thickness profile has not been achieved, the repolishing treatment is determined to be necessary, and the flow proceeds to step **408**. On the other hand, in the case where the desired thickness or thickness profile has been achieved, the operations by the substrate polishing apparatus **100** end. Note that while step **406** is being performed, the water polishing treatment may be continued by continuing the rotation of the polishing table **110** and the polishing head **120** and also continuing to supply water or pure water from the liquid supplying mechanism **130**. Also, while step **406** is being performed, the polishing head **120** may be raised up briefly and separated from the polishing table **110**.

In step **408**, a repolishing condition is computed. For example, the duration of the polishing in the repolishing treatment is set on the basis of the thickness maps. Also, on the basis of the thickness maps, the controller **140** may increase or decrease the internal pressure of the airbag **122**, raise the polishing pressure in thick areas (that is, areas where the polishing progress is low), and lower the polishing pressure in thin areas (that is, areas where the polishing progress is high). By this control, the polished state of the substrate **121** can be made uniform. The polishing treatment in step **402** is performed again in accordance with the repolishing condition computed in this way.

FIG. 5 is a flowchart illustrating a method of creating a water polishing thickness map during the water polishing treatment (that is, step **404**) according to the embodiment. FIG. 6 is a flowchart illustrating a method of creating a polishing thickness map during the polishing treatment (that is, step **402**) according to the embodiment. First, FIG. 5 will be referenced to describe a method of creating the water polishing thickness map (hereinafter also simply referred to as the thickness map).

In step **502**, a sensor output map is acquired as three-dimensional data. The acquired sensor output map is stored in the storage device **141**. The “sensor output map” is a map expressing the magnitude of the output signal from the eddy current sensor **150** across the entire polished surface of the substrate **121**. Consequently, data points in the sensor output map are positioned two-dimensionally on the substrate **121**. Because the output signal from the eddy current sensor **150** is recorded at each data point, the sensor output map is three-dimensional data (two dimensions are used to express the position while one dimension is used to express the magnitude of the output signal, for a total of three dimensions).

Note that as described earlier, because the magnitude of the signal output by the eddy current sensor **150** is not determined solely by the thickness of the conductive layer at the surface of the substrate **121**, it should be appreciated that the sensor output map is different from a thickness map that expresses the thickness distribution itself on the substrate **121**.

Before the substrate **121** is polished in step **504**, the sensor output map is generated using the output signal from the eddy current sensor **150** for a different substrate **121** (hereinafter referred to as the reference substrate) of the same type as the substrate **121** to be polished in step **504**. Here, a “substrate of the same type” means a “substrate provided with, or at least designed to have, the same interconnect pattern”. The sensor output map is generated from the signal output by the eddy current sensor **150** while the CMP apparatus **100** is activated, or more specifically, in the case where the polishing table **110** and the polishing head **120** are made to rotate.

The interval  $\theta$  between the orbits of the eddy current sensor **150** as seen from the substrate **121** when generating the sensor output map is preferably an interval by which variations in the output signal from the eddy current sensor **150** can be resolved sufficiently. For example, preferably, the rotational speeds of the polishing table **110** and the polishing head **120** when generating the sensor output map are set such that the interval  $\theta$  between the orbits of the eddy current sensor **150** as seen from the substrate **121** is 10 degrees or less. For example, in the case where the interval  $\theta$  between the orbits of the eddy current sensor **150** as seen from the substrate **121** is exactly 2 degrees, the number of orbits is 180 (360 (degrees)/2 (degrees/orbit)=180 (orbits)). By having the eddy current sensor **150** travel along a large number of orbits on the substrate **121**, the signal from the eddy current sensor **150** is output for substantially the entire surface of the substrate **121**. It is possible to generate and acquire the sensor output map from the output signal for substantially the entire surface of the substrate **121**. As another setting, the rotational speed of the polishing table **110** may be set to 60 rpm while the rotational speed of the polishing head **120** may be set to 61 rpm, for example. In this case,  $\theta$  is approximately 6 degrees. Also, it is known that during the polishing of the substrate **121**, the substrate **121** may rotate inside or on the polishing head **120**. In cases where this rotation phenomenon of the substrate **121** may occur, the rotation phenomenon of the substrate **121** may be considered when calculating  $\theta$ . For example, the rotation speed of the substrate **121** may be calculated according to the formula (revolutions of polishing head **120**) $\times$ (inner diameter of polishing head **120**)/(outer diameter of substrate **121**). Also, when generating and acquiring the sensor output map, a plurality of combinations of the rotational speeds of the polishing table **110** and the polishing head **120** may be used.

In this way, the sensor output map preferably has a resolution (number of data points) by which variations in the output signal from the eddy current sensor **150** can be resolved sufficiently. For example, although dependent on factors such as the size of the substrate **121** and the shape of the interconnects on the substrate **121**, the number of data points in the sensor output map is preferably 100 points by 100 points or more, more preferably 1000 points by 1000 points. However, the data points in the sensor output map may also be expressed in  $r\theta$  coordinates or some other coordinates rather than in  $xy$  coordinates.

To generate the sensor output map, it is necessary to make the eddy current sensor **150** travel along a plurality of orbits.

To make the eddy current sensor **150** travel along a plurality of orbits, it is necessary to rotate the polishing table **110** many times. For example, in the case where  $\theta$  is exactly 2 degrees, it is necessary to rotate the polishing table **110** at least 180 times. In the case where an abrasive exists on the polishing pad **111**, the polishing of the substrate **121** progresses while the polishing table **110** is rotating many times. If the polishing of the substrate **121** progresses when acquiring the sensor output map, an accurate sensor output map cannot be acquired. Consequently, the acquisition of the sensor output map is preferably executed under conditions in which the substrate **121** is not substantially polished.

To avoid substantially polishing the substrate **121**, it is necessary to remove the abrasive on the polishing pad **111** and keep the polishing pad **111** in a clean state. To remove the abrasive on the polishing pad **111** and keep the polishing pad **111** in a clean state, water (pure water) may be supplied from the liquid supplying mechanism **130** to the polishing pad **111** while the sensor output map is acquired. In the case where a clean polishing pad **111** is used and the polishing pad **111** itself does not have polishing ability, the substrate **121** is unlikely to be polished substantially. Strictly speaking, however, because the substrate **121** and the polishing pad **111** are in contact, there is a possibility that the substrate **121** will be polished (abraded) even in the case of using a clean polishing pad **111**. However, the polishing amount of the substrate **121** in a clean environment is considered to be small enough to ignore.

In the case where the polishing pad **111** itself has polishing ability, such as when abrasive grains are embedded in the polishing pad **111**, the substrate **121** may be polished even if the polishing pad **111** is kept clean. In this case, the sensor output map is acquired after removing the polishing pad **111** attached to the polishing table **110** and attaching a polishing pad **111** that does not have polishing ability to the polishing table **110**. After the sensor output map is acquired, the polishing pad **111** is replaced again (returned to the original configuration).

An example of a sensor output map **700** acquired according to the method described above is illustrated in FIG. 7. As FIG. 7 demonstrates, a sensor output map **700** has periodic unevenness. This is because a periodic pattern is formed in the substrate **121** used to generate the sensor output map **700**.

The values of the signal output from the eddy current sensor **150** (or the values of the signal that should be output from the eddy current sensor **150**) can be profiled on a line of any shape drawn on the acquired sensor output map (for example, the sensor output map **700**). In other words, the profile of any orbit can be computed from the acquired sensor output map.

In step **504**, the profile of a polishing signal while the substrate **121** is being polished is acquired as two-dimensional data. More specifically, step **504** is divided into a step of polishing the substrate **121** with the substrate **121** pressed against the polishing table **110** while also rotating the polishing head **120** with the substrate **121** attached thereto and the polishing table **110**, and a step of acquiring the profile of the polishing signal as two-dimensional data. Here, the “polishing signal” refers to the signal output by the eddy current sensor **150** while the substrate **121** is being polished due to the rotation of the polishing table **110** and the polishing head **120**. Here, a “profile” refers to two-dimensional data plotting the magnitude of the output signal of the eddy current sensor **150** on a certain orbit (one dimension is used to indicate the position on the orbit and one dimension expresses the magnitude of the output signal, for a total of

two dimensions). After acquiring the sensor output map in step 502, the controller 140 activates the CMP apparatus 100 and acquires the signal (polishing signal) output from the eddy current sensor 150 while the substrate 121 is being polished. The profile of the polishing signal preferably has a number of data points by which variations in the output signal from the eddy current sensor 150 can be resolved sufficiently. Although dependent on factors such as the length of the orbit and the shape of the interconnects on the substrate 121, the number of data points on a single profile is preferably 10 points or more. More preferably, the number of data points on a single profile is 100 points or more.

In step 506, the orbit having a profile that is most similar to the profile of the polishing signal from the eddy current sensor 150 is extracted from the sensor output map. Also, in step 508, the extracted orbit is specified as the orbit of the eddy current sensor 150 as seen from the substrate 121. The controller 140 reads out the sensor output map from the storage device 141 or the like, and extracts, from the sensor output map, the orbit having the profile that is most similar to the profile of the polishing signal from the eddy current sensor 150. Insofar as the polishing of the substrate 121 does not progress excessively, the signal from the eddy current sensor 150 obtained from the same orbit is considered to be similar even if the polishing of the substrate 121 progresses. Consequently, the extracted orbit can be specified as the orbit of the eddy current sensor 150 as seen from the substrate 121.

The signal from the eddy current sensor 150 depends at least partially on the thickness of the conductive layer at the surface of the substrate 121. Consequently, the polishing signal from the eddy current sensor 150 increases or decreases depending on how far the polishing of the substrate 121 has progressed. For this reason, there is a possibility that the magnitude of the signal from the eddy current sensor 150 when the sensor output map was acquired may be different from the magnitude of the polishing signal from the eddy current sensor 150. Accordingly, in step 506, both the magnitude of the signal from the eddy current sensor 150 when the sensor output map was acquired and the magnitude of the signal from the eddy current sensor 150 when the polishing signal was acquired may be normalized. Normalization makes it possible to perform simple addition or subtraction on a profile cut out from the sensor output map and the profile of the polishing signal. For example, by taking the sum of the differences between the profile on a certain orbit in the sensor output map from the eddy current sensor 150 and the profile of the polishing signal from the eddy current sensor 150, the similarity between the two profiles can be determined. For example, the two profiles are determined to be most similar when the sum of the differences is minimized. As another method, the similarity may be determined by comparing at least one of the peak shape, peak position, or peak size of the profile on a certain orbit in the sensor output map to at least one of the peak shape, peak position, or peak size of the profile of the polishing signal from the eddy current sensor 150 for example. Otherwise, any known method for determining the similarity between profiles may also be used.

Step 506 and step 508 will be described further by taking the sensor output map 700 as an example. As an example, the profiles on an orbit A-A', an orbit B-B', and an orbit C-C' are cut out from the sensor output map 700 in FIG. 8. As described later, the angle interval  $\theta$  between orbits (between profiles) may be 0.1 degrees or less, and the number of cut-out profiles may be four or more. Furthermore, as described later, the shape of each orbit may also be curved.

It should be appreciated that the orbits illustrated in FIG. 8 are merely examples for the sake of explanation. Also, in step 504, it is assumed that a profile 900 of the polishing signal as illustrated in FIG. 9 is obtained.

The controller 140 acquires the profile on each orbit of the sensor output map 700. In this example, there are three orbits as illustrated in FIG. 8. Consequently, in this example, three profiles of the sensor output map 700 are acquired as illustrated in FIG. 10 (the profile A-A', the profile B-B', and the profile C-C', where "profile X-X'" means "the profile on the orbit X-X' of the sensor output map 700"). Note that the profiles in FIG. 10 do not strictly reproduce the profiles of the sensor output map 700 in FIG. 8. It should be understood that the differences between FIG. 8 and FIG. 10 occur merely out of convenience in the explanation.

The controller 140 uses any technique for similarity comparison to extract the orbit having the profile that is most similar to the profile 900 of the polishing signal. For example, after normalizing the profile 900 of the polishing signal and the profiles A-A', B-B', and C-C', the controller 140 calculates and/or determines the similarity from the magnitude of the mean squared error. In this example, assume that the profile C-C' is calculated as being the most similar to the profile 900 of the polishing signal. The controller 140 specifies the extracted orbit C-C' as the orbit of the eddy current sensor 150 as seen from the substrate 121.

When comparing the similarities of the profiles, the interval between the profiles cut out from the sensor output map is preferably as small as possible. In the embodiment, profiles are cut out from the sensor output map such that the interval  $\theta$  between the orbits of the eddy current sensor 150 as seen from the substrate 121 is 0.1 degrees or less. Consequently, in the case where the symmetry of the interconnect pattern described later is not considered, 3600 profiles ( $360 \text{ (degrees)} / 0.1 \text{ (degrees)} = 3600 \text{ (dimensionless)}$ ) are compared to the profile of the polishing signal from the eddy current sensor 150.

In the case where the interconnect pattern on the substrate 121 has rotational symmetry, profiles on symmetric orbits have substantially the same values. Consequently, in the case where the interconnect pattern has rotational symmetry, the number of profiles to compare may be reduced according to the symmetry. For example, in the case where the interconnect pattern has rotational symmetry of order 2, the range in which profiles are cut out from the sensor output map may be a range of 180 degrees. Similarly, the range may be 120 degrees for rotational symmetry of order 3, 90 degrees for rotational symmetry of order 4, and  $360/n$  degrees for rotational symmetry of order  $n$ .

Note that the interval between profiles when cutting out profiles from the sensor output map may be different from the interval  $\theta$  between orbits of the eddy current sensor 150 when acquiring the sensor output map. Profiles on any orbit can be cut out from the sensor output map, irrespectively of the orbits of the eddy current sensor 150 when acquiring the sensor output map.

Additionally, an orbit extracted from the sensor output map may be curved. This is because, as illustrated in FIG. 3, the actual orbits of the eddy current sensor 150 may be curved. The shape (such as the curvature) of the extracted orbit may be computed from properties such as the shapes, the positional relationship, and the rotational speeds of the polishing table 110 and the polishing head 120.

When an orbit of the eddy current sensor 150 is specified as described above, next, in step 510, the thickness at each point on the specified orbit is determined. The thickness  $t(x)$ ,

y) at each point on an orbit of the eddy current sensor 150 can be determined according to the following formula on the basis of an initial thickness  $t_i(x, y)$ , a final thickness  $t_f(x, y)$ , and a polishing progress  $\alpha(x, y)$  at the position (x, y) on the substrate 121.

$$t(x, y) = t_i(x, y) + \{t_f(x, y) - t_i(x, y)\} \times \alpha(x, y)$$

The initial thickness  $t_i(x, y)$  indicates the thickness in the initial state before polishing the substrate 121 (note that even in the initial state, an in-plane distribution of thickness may exist due to features such as interconnects formed on the substrate 121). The final thickness  $t_f(x, y)$  indicates the thickness in the state after polishing the substrate 121 until a target thickness and thickness distribution is reached. The initial thickness  $t_i(x, y)$  and the final thickness  $t_f(x, y)$  may be stored respectively in the storage device 141 as an initial thickness map and a final thickness map, for example. Similarly to the sensor output map described earlier, the initial thickness map and the final thickness map may be generated before the substrate 121 is polished in step 504 by performing a thickness measurement on a reference substrate, which is a different substrate 121 of the same type as the substrate 121 to be polished in step 504. To perform the thickness measurement for generating the initial thickness map and the final thickness map, it is preferable to use an optical thickness measuring instrument, for example. By using an optical thickness measuring instrument, it is possible to obtain the initial thickness and the final thickness at each point on the substrate 121 at a relatively high spatial resolution.

The polishing progress  $\alpha(x, y)$  is an indicator that indicates how far the polishing of the substrate 121 (the substrate 121 that is actually polished in step 504) has progressed. For example, the polishing progress  $\alpha(x, y)$  may be defined to take a value of 0 (zero) in the initial state before polishing the substrate 121, to take a value of 1 in the final state when a target thickness has been reached by polishing, and to take an intermediate value between 0 and 1 in a state between the initial state and the final state, the intermediate value increasing as the state approaches the final state. The polishing progress  $\alpha(x, y)$  can be computed on the basis of the polishing signal acquired in step 504.

FIG. 17 is a diagram illustrating an example of a method of computing the polishing progress  $\alpha(x, y)$  on the basis of a polishing signal. In FIG. 17, the horizontal axis represents the position on the substrate 121 (for example, the position on an orbit of the eddy current sensor 150 specified in step 508), and the vertical axis represents the magnitude of the output signal from the eddy current sensor 150. FIG. 17 illustrates a polishing signal 1704 acquired while the substrate 121 is being polished in step 504. FIG. 17 additionally illustrates an output signal 1702 from the eddy current sensor 150 acquired from a substrate 121 corresponding to the initial state (the reference substrate, that is, a different substrate 121 of the same type as the substrate 121 to be polished in step 504), and an output signal 1706 from the eddy current sensor 150 obtained from a substrate 121 corresponding to the final state (a substrate obtained by polishing the reference substrate, that is, a different substrate 121 of the same type as the substrate 121 to be polished in step 504, under the same polishing conditions as step 504 until the target thickness is achieved). Note that the output signal 1702 in the initial state and the output signal 1706 in the final state may be stored in the storage device 141 in advance as sensor output maps.

Referring to FIG. 17, assume for example that at the position (x, y) on the substrate 121, the polishing signal 1704

has a value V, the output signal 1702 in the initial state has a value  $V_i$ , and the output signal 1706 in the final state has a value  $V_f$ . At this time, the polishing progress at the position (x, y) on the substrate 121 can be computed according to the following formula, for example.

$$\alpha(x, y) = (V - V_i) / (V_f - V_i)$$

FIG. 18 is a diagram illustrating a different example of a method of computing the polishing progress  $\alpha(x, y)$  on the basis of a polishing signal. The horizontal and vertical axes in FIG. 18 are similar to FIG. 17. However, the horizontal axis in FIG. 18 is enlarged compared to the horizontal axis in FIG. 17. FIG. 18 illustrates a single signal 1802 that is representative of the polishing signal 1704, the output signal 1702 in the initial state, and the output signal 1706 in the final state in FIG. 17 (in other words, the signal 1802 in FIG. 18 corresponds to any one of the signals 1702, 1704, and 1706).

In FIG. 18, a zone Z of a predetermined range containing the position (x, y) on the substrate 121 is set. For example, the zone Z may be a partial zone of a certain orbit of the eddy current sensor 150 specified in step 508. In the zone Z, the area of the portion enclosed by the curve representing the signal 1802 and the horizontal axis is calculated. For example, assume that S is the area of the portion calculated for the polishing signal 1704,  $S_i$  is the area of the portion calculated for the output signal 1702 in the initial state, and  $S_f$  is the area of the portion calculated for the output signal 1706 in the final state. At this time, the polishing progress at the position (x, y) on the substrate 121 can be computed according to the following formula, for example.

$$\alpha(x, y) = (S_f - S) / (S_f - S_i)$$

In the above method, the polishing progress  $\alpha(x, y)$  is computed on the basis of a proportional calculation of the area of the portion under the curve representing the signal 1802 in the zone Z, but as another method, the polishing progress  $\alpha(x, y)$  may also be computed on the basis of a proportional calculation of the peak value of the signal 1802 in the zone Z.

Next, in step 512, the thickness data at each point on the orbit determined in step 510 above is combined with the thickness data at each point on one or a plurality of other orbits already computed, and thereby the thickness map is created or updated. Additionally, in the next step 514, it is determined whether or not a predetermined polishing end condition is satisfied (such as determining whether or not polishing has been performed for a preset polishing time, or determining whether or not the thickness of a predetermined area or the average value of the thickness of each area on the substrate 121 is in a predetermined range, for example), and if the predetermined polishing end condition has not been satisfied yet, the process is repeated from step 504 again.

To describe the process in step 512 specifically, FIG. 3 will be referenced again for convenience. In FIG. 3, ten orbits 1 to 10 are drawn. For example, assume that by a certain point in time, the process from step 504 to step 512 has already been performed twice, and as a result, thickness data at each point on the two orbits 1 and 2 has been computed and stored in the storage device 141. This thickness data forms a thickness map in the partial area corresponding to the above two orbits out of the entire substrate 121. Furthermore, assume that by executing step 510 for a third time at this point, thickness data at each point on the orbit 3 is obtained. In step 512, the controller 140 adds the thickness data at each point on the orbit 3 to the thickness map of the partial area corresponding to the orbits 1 and 2,

and stores the result in the storage device **141** as a new thickness map. The new thickness map includes thickness data at each point on the three orbits **1**, **2**, and **3**. In this way, by repeating the process from step **504** to step **512** a plurality of times, the thickness map is expanded/updated to cover a broader area of the substrate **121** or the entire substrate **121**.

When the predetermined polishing end condition is satisfied in the determination in step **514**, in the next step **516**, an averaging process and an interpolation process are performed on the thickness map created as described above. FIG. **11** is a diagram for explaining the process of averaging the thickness map. As described earlier, the substrate **121** is diced into individual chips (that is, dies) in a later step. On the substrate **121**, a plurality of demarcated die areas **1102** are arranged. Although dependent on the shape and size of the die areas **1102**, a plurality of points **1104** may exist in the thickness map inside a single die area **1102**. Each point **1104** in the thickness map has the thickness data computed in step **510** above at the position corresponding to that point on the substrate **121**. Note that the thickness data of each point **1104** may also be corrected according to properties such as a known interconnect pattern at that point **1104**. The controller **140** computes a representative value of the thickness of each die area **1102** by averaging the thickness data at the plurality of points **1104** existing inside each die area **1102**, and uses the representative value of the thickness of each die area **1102** computed in this way to create an averaged thickness map. FIG. **12** is a diagram illustrating an example **1200** of an averaged thickness map. As FIG. **12** demonstrates, the averaged thickness map **1200** is expressed as having a constant thickness for each die area **1102**.

FIG. **13** is a diagram for explaining the process of interpolating the thickness map in step **516**. As described above, the thickness at each point on orbits of the eddy current sensor **150** is computed, and a thickness map is constructed from the thickness data at each point. Consequently, thickness data does not exist in the thickness map for areas on the substrate **121** where an orbit of the eddy current sensor **150** does not pass through. The interpolation process in step **516** is a process of interpolating such data by using the data stored in the thickness map.

At this point, it is assumed that a plurality of airbags **122** of the CMP apparatus **100** are provided concentrically with respect to the substrate **121**. In this case, because the polishing pressure of the substrate **121** is constant inside each concentric ring, the polished substrate **121** is expected to reach a similar polished state throughout the circumferential direction of each concentric ring. Accordingly, when performing the interpolation process in step **516**, by increasing the correlation strength of interpolation in the circumferential direction, the accuracy of the interpolation can be improved.

For example, as illustrated in FIG. **13**, assume that four die areas **1102-2**, **1102-3**, **1102-4**, and **1102-5** exist adjacent to a certain die area **1102-1**. The die areas **1102-2** and **1102-3** are adjacent to the die area **1102-1** in the circumferential direction of the substrate **121**, while the die areas **1102-4** and **1102-5** are adjacent to the die area **1102-1** in the radial direction of the substrate **121**. It is assumed that the die area **1102-1** does not have thickness data. On the other hand, it is assumed that the die areas **1102-2**, **1102-3**, **1102-4**, and **1102-5** have thickness data, and the respective thickness values (that is, the representative values described above that are obtained by averaging the thickness at the plurality of points inside each die area) are designated **T2**, **T3**, **T4**, and **T5**.

The controller **140** computes an average thickness **T1** of the die area **1102-1** by interpolating the thickness values **T2**, **T3**, **T4**, and **T5** of the four die areas adjacent to the die area **1102-1**. To increase the correlation strength of the interpolation in the circumferential direction of the substrate **121** as described above, the following interpolation formula can be used, for example. However, it is assumed that  $u > v$  and  $u + v = 1/2$ , and the ratio  $u/v$  expresses that interpolation in the circumferential direction has a correlation  $u/v$  times the correlation in the radial direction of the substrate **121**.

$$T1 = u(T2 + T3) + v(T4 + T5)$$

By executing each step according to the flowchart in FIG. **5** as above, the thickness map in the water polishing treatment is completed.

Next, the flowchart in FIG. **6** will be referenced to describe a method of creating a polishing thickness map during the polishing treatment (that is, step **402** in the flowchart in FIG. **4**). Hereinafter, the polishing thickness map will also be simply referred to as the thickness map. In the flowchart in FIG. **6**, the steps other than steps **622** and **624** are the same as the steps in the flowchart in FIG. **5**.

As described above, during the water polishing treatment, because the polishing rate is extremely low, there is little or no progression in the polishing of the substrate **121**. Consequently, in the case of creating a thickness map during the water polishing treatment, as described with regard to step **512** in FIG. **5**, it is possible to update the thickness map by directly combining the thickness data of a new orbit (for example, the orbit **3**) with the already-computed thickness map (for example, the partial thickness map corresponding to the orbits **1** and **2**). However, in the polishing treatment in step **402** in FIG. **4**, the substrate **121** is being polished at a markedly higher polishing rate than the water polishing, and therefore if the thickness data of a new orbit is simply combined with the already-computed thickness map, thickness data after polishing has progressed to a certain extent will be combined with the thickness map from before the polishing progressed, and a correct thickness map cannot be obtained. To avoid such a situation, the method in the flowchart in FIG. **6** that creates a thickness map during the polishing treatment is performed with the addition of steps **622** and **624**.

In step **622**, the polishing rate of the substrate **121** is computed on the basis of thickness data corresponding to a plurality of orbits. FIG. **14** is a diagram illustrating an example of a method of computing the polishing rate. FIG. **14** illustrates a thickness distribution of orbits **1** to **6** (see FIG. **3**, for example). Assume that the thickness data of the orbit **1** is acquired first, and the thickness data of each of the orbits **2**, **3**, **4**, **5**, and **6** is acquired sequentially thereafter. Because the polishing of the substrate **121** gradually progresses while the thickness data of the orbits **1** to **6** are acquired, the average thickness of each orbit decreases in the order of the orbits **1**, **2**, **3**, **4**, **5**, and **6**. The polishing table **110** rotates once while the thickness data for two neighboring orbits (for example, the orbits **1** and **2**) is acquired.

First, the controller **140** computes an average thickness distribution **1402** of three successive orbits including the most recent orbit **6** (in other words, the orbits **4**, **5**, and **6**), and additionally computes an average thickness distribution **1404** of preceding three successive orbits (in other words, the orbits **1**, **2**, and **3**). Next, the controller **140** computes the difference between the two average thickness distributions **1402** and **1404**, and by dividing the difference by the number of rotations (in this example, three rotations) of the polishing table **110** between the two average thickness distributions,

the controller **140** computes a distribution **1406** of the polishing amount per rotation of the polishing table **110** (in other words, the polishing rate). Note that in the three graphs illustrated in FIG. **14**, the horizontal axis represents the position in the radial direction of the substrate **121**. By computing the polishing rate from average thickness distributions of three orbits, the polishing rate can be computed precisely. Obviously, the polishing rate may also be computed from average thickness distributions of two orbits or of four or more orbits. Also, instead of using average thickness distributions, the polishing rate may also be computed from the difference between the thickness distribution of a certain orbit and the thickness distribution of another orbit.

Next, in step **624**, the polishing rate of the substrate **121** obtained in step **622** above is used to correct the thickness data in each orbit already computed (that is, the thickness map that has been created up to the current point in time). After that, in step **512** described earlier, the corrected thickness data (or thickness map) and the thickness data of the orbit determined in step **510** are combined.

For example, assume that at a certain point in time, a thickness map corresponding to the entire surface of the substrate **121** is obtained. In step **624**, the controller **140** subtracts the polishing amount indicated by the distribution **1406** of the polishing rate obtained in step **622** from the thickness map. Because the distribution **1406** of the polishing rate is a distribution in the radial direction of the substrate **121**, the amount subtracted from the thickness map is the same amount in the circumferential direction of the substrate **121**. In other words, the subtraction from the thickness map is performed concentrically. The thickness map after subtraction is a corrected thickness map reflecting that the polishing of the substrate **121** has progressed from the point in time at which the pre-subtraction thickness map was acquired until the current point in time. Consequently, in the next step **512**, by combining the corrected thickness map with the thickness data of the orbit computed in the current step **510**, the thickness map can be updated correctly.

The thickness map updated while accounting for the polishing rate of the substrate **121** in this way is averaged and interpolated in step **516**, similarly to the case of water polishing described above, and then an averaged thickness map having an average thickness for each die area **1102** (for example, an averaged thickness map **1200** like the one illustrated in FIG. **12**) is obtained.

By executing each step according to the flowchart in FIG. **6** as above, the thickness map in the polishing treatment is completed.

FIG. **15** is a front view of a substrate polishing apparatus **100** according to another embodiment. The substrate polishing apparatus **100** according to the embodiment is further provided with an optical sensor **1500** in addition to the configuration illustrated in FIG. **2**. As illustrated in the diagram, the optical sensor **1500** is provided in the polishing table **110**. The optical sensor **1500** may be provided at any position in the polishing table **110** insofar as the substrate **121** is measurable from that position.

The optical sensor **1500** irradiates the polished surface of the substrate **121** with irradiating light, and measures the optical properties of reflected light reflected by the polished surface of the substrate **121**. The optical sensor **1500** measures the optical spectrum of the substrate **121**, for example. As described earlier, the polished surface of the substrate **121** is demarcated into a plurality of die areas **1102**. Each die area **1102** has a unique film structure and interconnect pattern, and for this reason, the light reflected from each part

of each die area **1102** has a characteristic spectrum. Consequently, by using the optical spectrum from the substrate **121** measured by the optical sensor **1500**, it is possible to create thickness maps during the polishing and water polishing of the substrate **121**, similarly to the methods illustrated by the flowcharts in FIGS. **5** and **6** described above.

In the embodiment of FIG. **15**, the substrate polishing apparatus **100** is provided with both the eddy current sensor **150** and the optical sensor **1500**. Consequently, the substrate polishing apparatus **100** is capable of creating both a thickness map of the substrate **121** based on the signal from the eddy current sensor **150** and a thickness map of the substrate **121** based on the signal from the optical sensor **1500**. As described earlier, the eddy current sensor **150** detects impedance changes caused by inducing an eddy current in the conductive layer at the surface of the substrate **121**. Accordingly, the thickness map created on the basis of the signal from the eddy current sensor **150** expresses a distribution of the thickness of the conductive layer, or in other words the metal layer, on the substrate **121**. On the other hand, the thickness map created on the basis of the signal from the optical sensor **1500** expresses a distribution of the thickness of the oxide film on the substrate **121**.

FIG. **16** illustrates an example **1620** of a thickness map obtained by using the eddy current sensor **150** and an example **1640** of a thickness map obtained by using the optical sensor **1500**. In each of the thickness maps **1620** and **1640**, the thickness is averaged for each die area **1102**. By subtracting the thickness map **1640** according to the optical sensor **1500** from the thickness map **1620** according to the eddy current sensor **150** in each die area **1102** on the basis of the two thickness maps **1620** and **1640**, for example, a dishing map **1660** that expresses a distribution of the amount of dishing on the substrate **121** can be created. On the basis of the dishing map **1660**, it is determined whether or not a desired amount of dishing has been achieved, and in the case where the desired amount of dishing has not been achieved, a repolishing treatment may be performed. Also, on the basis of the dishing map **1660**, the parameters of subsequent polishing cycles (such as the pressure that presses the substrate **121** against the polishing table, the rotational speed of the polishing table and the polishing head that holds the substrate **121**, the amount of slurry supplied to the surface of the substrate **121** to be polished, and the temperature of the surface of the substrate **121** to be polished) may be optimized.

On the basis of the thickness maps or the dishing map created as described above, the controller **140** of the substrate polishing apparatus **100** may also determine the treatment parameters in previous steps, determine the treatment parameters in next steps, or perform data processing for quality management, such as yield management.

The foregoing describes several embodiments of the present invention. However, the foregoing embodiments are for facilitating the understanding of the present invention, and do not limit the present invention. The present invention may be modified and improved without departing from the scope of the invention, and any equivalents obtained through such modification and improvement obviously are included in the present invention. Furthermore, any combination or omission of the components described in the claims and the specification is possible insofar as at least one or some of the issues described above can be addressed, or insofar as at least one or some of the effects are exhibited.

#### REFERENCE SIGNS LIST

- 100A substrate polishing apparatus
- 100B substrate polishing apparatus

- 100C-1 substrate polishing apparatus
- 100C-2 substrate polishing apparatus
- 101 polishing chamber
- 101A polishing chamber
- 101B polishing chamber
- 110 polishing table
- 111 polishing pad
- 120 polishing head
- 121 substrate
- 122 airbag
- 130 liquid supplying mechanism
- 140 controller
- 141 storage device
- 142 processor
- 143 input/output device
- 150 thickness measuring instrument
- 700 sensor output map
- 900 profile of polishing signal
- 1102 die area
- 1104 each point in thickness map
- 1200 averaged thickness map
- 1402 average thickness distribution
- 1404 average thickness distribution
- 1406 distribution of polishing rate
- 1500 optical sensor
- 1620 thickness map
- 1640 thickness map
- 1660 dishing map
- 1702 output signal in initial state
- 1704 polishing signal
- 1706 output signal in final state
- 1802 signal

What is claimed is:

1. A substrate polishing apparatus comprising:
  - a rotatably configured polishing table provided with a sensor that outputs a signal related to a thickness;
  - a rotatably configured polishing head that faces the polishing table, a substrate being attachable to a face of the polishing head that faces the polishing table; and
  - a controller, wherein the controller:
    - generates, by use of output signals from the sensor for a reference substrate, a sensor output map representing a magnitude of the output signals from the sensor across an entire polished surface of the reference substrate,
    - acquires a polishing signal from the sensor when the sensor passes over a surface to be polished of the substrate,
    - extracts, from the sensor output map, an orbit having a profile that is most similar to a profile of the polishing signal to specify the extracted orbit as an orbit of the sensor with respect to the substrate,
    - calculates a thickness of the substrate at each point on the specified orbit of the sensor on a basis of the polishing signal, and
    - creates a thickness map on a basis of the calculated thickness at each point on a plurality of orbits of the sensor.
2. The substrate polishing apparatus according to claim 1, wherein the sensor is one or a plurality of eddy current sensors.
3. The substrate polishing apparatus according to claim 2, wherein the controller additionally:
  - calculates a polishing progress of the substrate based at least on the polishing signal.

4. The substrate polishing apparatus according to claim 3, wherein the controller calculates the polishing progress on a basis of a comparison of the polishing signal from the sensor acquired while polishing the substrate, an output signal from the sensor with respect to the reference substrate in an initial state, and an output signal from the sensor with respect to the reference substrate in a final state.
5. The substrate polishing apparatus according to claim 3, wherein the controller calculates the thickness at each point of the substrate on a basis of the calculated polishing progress.
6. The substrate polishing apparatus according to claim 5, wherein the calculated thickness is further based on an initial thickness and a final thickness of the reference substrate wherein the initial thickness and the final thickness have been obtained through thickness measurements on the reference substrate before polishing the substrate.
7. The substrate polishing apparatus according to claim 1, wherein the sensor is one or a plurality of optical sensors.
8. The substrate polishing apparatus according to claim 1, wherein the sensor is one or a plurality of eddy current sensors and one or a plurality of optical sensors.
9. The substrate polishing apparatus according to claim 8, wherein the controller additionally creates a dishing map that expresses a distribution of a dishing amount of the substrate on a basis of a comparison between a first thickness map created using a signal from the one or plurality of eddy current sensors and a second thickness map created using a signal from the one or plurality of optical sensors.
10. The substrate polishing apparatus according to claim 9, wherein the controller additionally:
  - determines whether or not a desired dishing amount has been achieved on a basis of the dishing map, and
  - in a case where the desired dishing amount has not been achieved, the controller causes the substrate to be repolished using the polishing table and the polishing head, a second polishing table and a second polishing head provided with the substrate polishing apparatus, or a third polishing table and a third polishing head provided with another substrate polishing apparatus.
11. The substrate polishing apparatus according to claim 9, wherein the controller additionally determines a treatment parameter of a previous step, determines a treatment parameter of a next step, or performs data processing for quality management on a basis of the thickness map or the dishing map.
12. The substrate polishing apparatus according to claim 9, wherein the controller additionally optimizes a polishing parameter on a basis of the thickness map or the dishing map.
13. The substrate polishing apparatus according to claim 1, wherein the controller acquires the polishing signal from the sensor during a water polishing treatment performed after polishing the substrate.
14. The substrate polishing apparatus according to claim 1, wherein

19

the controller acquires the polishing signal from the sensor while polishing the substrate.

15. The substrate polishing apparatus according to claim 1, wherein the controller additionally:

calculates a polishing rate distribution of the substrate based on a thickness distribution of a plurality of orbits of the sensor,

calculates a polishing amount of the substrate that is polished during a predetermined time period on a basis of the polishing rate distribution, and

updates the thickness map by subtracting the polishing amount from the thickness map that has been created at a predetermined point in time and combining the subtracted thickness map with thickness data corresponding to a current orbit.

16. The substrate polishing apparatus according to claim 1, wherein

the controller additionally:

determines whether or not a desired thickness or a desired thickness profile has been achieved on a basis of the thickness map, and

in a case where the desired thickness or thickness profile has not been achieved, the controller causes the substrate to be repolished using the polishing table and the polishing head, a second polishing table and a second polishing head provided with the substrate polishing apparatus, or a third polishing table and a third polishing head provided with another substrate polishing apparatus different from the substrate polishing apparatus.

17. The substrate polishing apparatus according to claim 1, further comprising:

an airbag configured to adjust a polishing pressure of the substrate, wherein

the controller additionally controls an internal pressure of the airbag on a basis of the thickness map.

18. A method of creating a thickness map of a substrate, executed by a substrate polishing apparatus provided with:

a rotatably configured polishing table provided with a sensor that outputs a signal related to a thickness, and a rotatably configured polishing head that faces the polishing table, the substrate being attachable to a face of the polishing head that faces the polishing table, the method comprising:

generating, by use of output signals from the sensor for a reference substrate, a sensor output map representing a

20

magnitude of the output signals from the sensor across an entire polished surface of the reference substrate; acquiring a polishing signal from the sensor when the sensor passes over a surface to be polished of the substrate;

extracting, from the sensor output map, an orbit having a profile that is most similar to a profile of the polishing signal to specify the extracted orbit as an orbit of the sensor with respect to the substrate;

calculating a thickness of the substrate at each point on the specified orbit of the sensor on a basis of the polishing signal; and

creating the thickness map on a basis of the calculated thickness at each point on a plurality of orbits of the sensor.

19. A method of polishing a substrate, executed by a substrate polishing apparatus provided with:

a rotatably configured polishing table provided with a sensor that outputs a signal related to a thickness, and a rotatably configured polishing head that faces the polishing table, the substrate being attachable to a face of the polishing head that faces the polishing table, the method comprising:

generating, by use of output signals from the sensor for a reference substrate, a sensor output map representing a magnitude of the output signals from the sensor across an entire polished surface of the reference substrate;

rotating the polishing table;

rotating the polishing head having the substrate attached thereto;

polishing the substrate with the substrate pressed against the polishing table;

acquiring a polishing signal from the sensor when the sensor passes over a surface to be polished of the substrate;

extracting, from the sensor output map, an orbit having a profile that is most similar to a profile of the polishing signal to specify the extracted orbit as an orbit of the sensor with respect to the substrate;

calculating a thickness of the substrate at each point on the specified orbit of the sensor on a basis of the polishing signal; and

creating a thickness map on a basis of the calculated thickness at each point on a plurality of orbits of the sensor.

\* \* \* \* \*