

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
30 May 2003 (30.05.2003)

PCT

(10) International Publication Number  
WO 03/044001 A1

(51) International Patent Classification<sup>7</sup>: C07D 301/06

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW.

(21) International Application Number: PCT/US02/31669

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(22) International Filing Date: 3 October 2002 (03.10.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
09/998,939 15 November 2001 (15.11.2001) US

(71) Applicant: ARCO CHEMICAL TECHNOLOGY, L.P.  
[US/US]; Two Greenville Crossing, 4001 Kennett Pike,  
Suite 238, Greenville, DE 19807 (US).

**Published:**  
— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(72) Inventor: HANCU, Dan; 19 Amity Pointe Court, Clifton Park, NY 12065 (US).

(74) Agents: CARROLL, Kevin, M. et al.; Lyondell Chemical Company, 3801 West Chester Pike, Newtown Square, PA 19073 (US).



WO 03/044001 A1

(54) Title: DIRECT EPOXIDATION PROCESS USING CARBONATE MODIFIERS

(57) Abstract: The invention is a process for epoxidizing an olefin with hydrogen and oxygen in the presence of a modifier and a catalyst comprising a noble metal and titanium zeolite. The modifier is (a) calcium carbonate in the presence of carbon dioxide or (b) ammonium bicarbonate. The process results in increased catalyst activity, selectivity to epoxide, and increased catalyst life.

01-2585A

## DIRECT EPOXIDATION PROCESS USING CARBONATE MODIFIERS

5

## FIELD OF THE INVENTION

This invention relates to an epoxidation process using a carbonate-containing modifier. The process comprises reacting olefin, hydrogen, and oxygen in the presence of a modifier and a catalyst comprising a noble metal and a titanium zeolite. The modifier is (a) calcium carbonate in the presence of carbon dioxide or (b) ammonium bicarbonate. Surprisingly, the process results in higher activity and selectivity to epoxide, as well as increased catalyst life.

## BACKGROUND OF THE INVENTION

Many different methods for the preparation of epoxides have been developed. Generally, epoxides are formed by the reaction of an olefin with an oxidizing agent in the presence of a catalyst. The production of propylene oxide from propylene and an organic hydroperoxide oxidizing agent, such as ethyl benzene hydroperoxide or tert-butyl hydroperoxide, is commercially practiced technology. This process is performed in the presence of a solubilized molybdenum catalyst, see U.S. Pat. No. 3,351,635, or a heterogeneous titania on silica catalyst, see U.S. Pat. No. 4,367,342. Hydrogen peroxide is another oxidizing agent useful for the preparation of epoxides. Olefin epoxidation using hydrogen peroxide and a titanium silicate zeolite is demonstrated in U.S. Pat. No. 4,833,260. One disadvantage of both of these processes is the need to pre-form the oxidizing agent prior to reaction with olefin.

Another commercially practiced technology is the direct epoxidation of ethylene to ethylene oxide by reaction with oxygen over a silver catalyst. Unfortunately, the silver catalyst has not proved very useful in epoxidation of higher olefins. Therefore, much current research has focused on the direct epoxidation of higher olefins with oxygen and hydrogen in the presence of a catalyst. In this process, it is believed that oxygen and hydrogen react in situ to form an oxidizing agent. Thus, development of an efficient process (and

catalyst) promises less expensive technology compared to the commercial technologies that employ pre-formed oxidizing agents.

Many different catalysts have been proposed for use in the direct epoxidation of higher olefins. For example, JP 4-352771 discloses the 5 epoxidation of propylene oxide from the reaction of propylene, oxygen, and hydrogen using a catalyst containing a Group VIII metal such as palladium on a crystalline titanosilicate. U.S. Pat. No. 5,859,265 discloses a catalyst in which a platinum metal, selected from Ru, Rh, Pd, Os, Ir and Pt, is supported on a titanium or vanadium silicalite. Additionally, it is disclosed that the 10 catalyst may also contain additional elements, including Fe, Co, Ni, Re, Ag, or Au.

One disadvantage of the described direct epoxidation catalysts is that they are prone to ring-open the epoxide product under standard reaction 15 conditions to form less desirable ring-opened by-products such as glycols or glycol ethers. U.S. Pat. No. 6,008,388 describes a direct olefin epoxidation process in which the selectivity for the reaction of olefin, oxygen, and hydrogen in the presence of a noble metal-modified titanium zeolite is greatly enhanced by the addition of a nitrogen compound to the reaction mixture. Also, increasing the catalyst activity as well as maximizing the catalyst life are 20 important objectives in order to achieve an economical process. As with any chemical process, it is desirable to develop new direct epoxidation methods and catalysts.

In sum, new processes for the direct epoxidation of olefins are needed. Especially desirable are processes that increase activity, selectivity to the 25 epoxide, as well as improving catalyst life. I have discovered an effective, convenient epoxidation process that reduces unwanted ring-opened products, increases catalyst activity, and improves catalyst life.

#### SUMMARY OF THE INVENTION

The invention is an olefin epoxidation process that comprises reacting 30 olefin, oxygen, and hydrogen in the presence of a modifier and a catalyst comprising a noble metal and titanium zeolite. The modifier is either (a) calcium carbonate in the presence of carbon dioxide or (b) ammonium bicarbonate. This process surprisingly gives significantly reduced ring-

opened by-products, and increased catalyst activity and life compared to processes that do not use the modifier.

#### DETAILED DESCRIPTION OF THE INVENTION

The process of the invention employs a catalyst that comprises a noble metal and titanium zeolite. Suitable titanium zeolites are those crystalline materials having a porous molecular sieve structure with titanium atoms substituted in the framework. The choice of titanium zeolite employed will depend upon a number of factors, including the size and shape of the olefin to be epoxidized. For example, it is preferred to use a relatively small pore titanium zeolite such as a titanium silicalite if the olefin is a lower aliphatic olefin such as ethylene, propylene, or 1-butene. Where the olefin is propylene, the use of a TS-1 titanium silicalite is especially advantageous. For a bulky olefin such as cyclohexene, a larger pore titanium zeolite such as a titanium zeolite having a structure isomorphous with zeolite beta may be preferred.

Titanium zeolites comprise the class of zeolitic substances wherein titanium atoms are substituted for a portion of the silicon atoms in the lattice framework of a molecular sieve. Such substances are well known in the art.

Particularly preferred titanium zeolites include the class of molecular sieves commonly referred to as titanium silicalites, particularly "TS-1" (having an MFI topology analogous to that of the ZSM-5 aluminosilicate zeolites), "TS-2" (having an MEL topology analogous to that of the ZSM-11 aluminosilicate zeolites), and "TS-3" (as described in Belgian Pat. No. 1,001,038). Titanium-containing molecular sieves having framework structures isomorphous to zeolite beta, mordenite, ZSM-48, ZSM-12, and MCM-41 are also suitable for use. The titanium zeolites preferably contain no elements other than titanium, silicon, and oxygen in the lattice framework, although minor amounts of boron, iron, aluminum, sodium, potassium, copper and the like may be present.

Preferred titanium zeolites will generally have a composition corresponding to the following empirical formula  $x\text{TiO}_2 (1-x)\text{SiO}_2$  where  $x$  is between 0.0001 and 0.5000. More preferably, the value of  $x$  is from 0.01 to 0.125. The molar ratio of Si:Ti in the lattice framework of the zeolite is

advantageously from 9.5:1 to 99:1 (most preferably from 9.5:1 to 60:1). The use of relatively titanium-rich zeolites may also be desirable.

The catalyst employed in the process of the invention also contains a noble metal. While any of the noble metals can be utilized (i.e., gold, silver, 5 platinum, palladium, iridium, ruthenium, osmium), either alone or in combination, palladium is particularly desirable. Typically, the amount of noble metal present in the catalyst will be in the range of from 0.01 to 20 weight percent, preferably 0.05 to 10 weight percent.

The manner in which the noble metal is incorporated into the catalyst is 10 not considered to be particularly critical. For example, the noble metal may be supported on the titanium zeolite by impregnation, adsorption, ion-exchange, precipitation. Alternatively, the noble metal may be first supported on another support such as an inorganic oxide, inorganic chloride, carbon, or organic polymer resins, or the like, and then physically mixed with the titanium 15 zeolite. Preferred inorganic oxides include oxides of Group 2, 3, 4, 5, 6, 13, or 14 elements. Particularly preferred inorganic oxide supports include silica, alumina, titania, zirconia, niobium oxides, tantalum oxides, molybdenum oxides, tungsten oxides, amorphous titania-silica, amorphous zirconia-silica, amorphous niobia-silica, and the like. Preferred organic polymer resins 20 include polystyrene, styrene-divinylbenzene copolymers, crosslinked polyethyleneimines, and polybenzimidizole. Suitable supports also include organic polymer resins grafted onto inorganic oxide supports, such as polyethylenimine-silica. Preferred supports also include carbon. Particularly preferred supports include carbon, silica, silica-aluminas, titania, zirconia, and 25 niobia.

There are no particular restrictions regarding the choice of noble metal compound used as the source of the noble metal. For example, suitable compounds include the nitrates, sulfates, halides (e.g., chlorides, bromides), carboxylates (e.g. acetate), and amine complexes of noble metals.

30 Similarly, the oxidation state of the noble metal is not considered critical. In the case of palladium for instance, the palladium may be in an oxidation state anywhere from 0 to +4 or any combination of such oxidation states. To achieve the desired oxidation state or combination of oxidation

states, the noble metal compound may be fully or partially pre-reduced after addition to the catalyst. Satisfactory catalytic performance can, however, be attained without any pre-reduction.

After noble metal incorporation, the catalyst is recovered. Suitable catalyst recovery methods include filtration and washing, rotary evaporation and the like. The catalyst is typically dried at a temperature greater than about 50°C prior to use in epoxidation. The drying temperature is preferably from about 50°C to about 300°C. The catalyst may additionally comprise a binder or the like and may be molded, spray dried, shaped or extruded into any desired form prior to use in epoxidation. The catalyst may be optionally thermally treated in a gas such as nitrogen, helium, vacuum, hydrogen, oxygen, air, or the like. The thermal treatment temperature is typically from about 50 to about 550°C.

The epoxidation process of the invention comprises reacting olefin, oxygen, and hydrogen in the presence of a modifier and the catalyst. The modifier is either (a) calcium carbonate in the presence of carbon dioxide or (b) ammonium bicarbonate. The ammonium bicarbonate or calcium carbonate can be simply added to the reaction medium in which the epoxidation is being performed. The ammonium bicarbonate or calcium carbonate may be added all at once either prior to or following initiation of epoxidation or may be added in an incremental or continuous manner. Ammonium carbonate may also be formed in-situ during the epoxidation reaction.

Sufficient ammonium bicarbonate is necessary to be effective to improve catalyst activity and selectivity to the epoxide as compared to the same reaction carried out under similar conditions in the absence of the ammonium bicarbonate. The amount of ammonium bicarbonate is in the range of from about 10 ppm to about 50,000 ppm (as measured by the weight of ammonium bicarbonate to the weight of the entire reaction mixture), and preferably in the range of from about 100 ppm to about 1500 ppm.

The amount of calcium carbonate used is not believed to be particularly critical, but at a minimum should be effective to improve catalyst activity and selectivity to the epoxide as compared to the same reaction

carried out under similar conditions in the absence of the calcium carbonate. Preferably, the amount of calcium carbonate is in the range of from about 50 ppm to about 10,000 ppm (as measured by the weight of calcium carbonate to the weight of the entire reaction mixture), and most preferably in the range 5 of from about 150 ppm to about 5000 ppm.

When the modifier contains calcium carbonate, it must be used in the presence of carbon dioxide. The carbon dioxide will typically be added to the reaction mixture along with the other reaction gases, comprising oxygen, hydrogen, and light olefins such as propylene which may be introduced in the 10 gas phase. Although the amount of carbon dioxide is not critical, the amount of carbon dioxide in the gas is typically in the range of from about 0.01 volume % to about 90 volume % (as measured by volume CO<sub>2</sub> per total volume of all gases introduced into the reactor), and preferably from about 0.05 volume % to about 5 volume %.

15 The epoxidation process of the invention comprises contacting an olefin, oxygen, and hydrogen in the presence of the modifier and the catalyst. Suitable olefins include any olefin having at least one carbon-carbon double bond, and generally from 2 to 60 carbon atoms. Preferably the olefin is an acyclic alkene of from 2 to 30 carbon atoms; the process of the invention is 20 particularly suitable for epoxidizing C<sub>2</sub>-C<sub>6</sub> olefins. More than one double bond may be present, as in a diene or triene for example. The olefin may be a hydrocarbon (i.e., contain only carbon and hydrogen atoms) or may contain functional groups such as halide, carboxyl, hydroxyl, ether, carbonyl, cyano, or nitro groups, or the like. The process of the invention is especially useful 25 for converting propylene to propylene oxide.

Oxygen and hydrogen are also required for the process of the invention. Although any sources of oxygen and hydrogen are suitable, molecular oxygen and molecular hydrogen are preferred. The molar ratio of hydrogen to oxygen can usually be varied in the range of H<sub>2</sub>:O<sub>2</sub> = 1:100 to 5:1 30 and is especially favorable at 1:5 to 2:1. The molar ratio of oxygen to olefin is usually 1:1 to 1:20, and preferably 1:1.5 to 1:10. Relatively high oxygen to olefin molar ratios (e.g., 1:1 to 1:3) may be advantageous for certain olefins.

In addition to olefin, oxygen and hydrogen, an inert gas carrier may be preferably used in the process. As the carrier gas, any desired inert gas can be used. Suitable inert gas carriers include noble gases such as helium, neon, and argon in addition to nitrogen and carbon dioxide. Saturated 5 hydrocarbons with 1-8, especially 1-6, and preferably with 1-4 carbon atoms, e.g., methane, ethane, propane, and n-butane, are also suitable. Nitrogen and saturated C<sub>1</sub>-C<sub>4</sub> hydrocarbons are the preferred inert carrier gases. Mixtures of the listed inert carrier gases can also be used. The molar ratio of olefin to carrier gas is usually in the range of 100:1 to 1:10 and especially 10 20:1 to 1:10.

Specifically in the epoxidation of propylene according to the invention, propane can be supplied in such a way that, in the presence of an appropriate excess of carrier gas, the explosive limits of mixtures of propylene, propane, hydrogen, and oxygen are safely avoided and thus no 15 explosive mixture can form in the reactor or in the feed and discharge lines.

The amount of catalyst used may be determined on the basis of the molar ratio of the titanium contained in the titanium zeolite to the olefin that is supplied per unit time. Typically, sufficient catalyst is present to provide a titanium/olefin per hour molar feed ratio of from 0.0001 to 0.1.

20 Depending on the olefin to be reacted, the epoxidation according to the invention can be carried out in the liquid phase, the gas phase, or in the supercritical phase. The process of the invention is preferably carried out in the liquid-phase. When a liquid reaction medium is used, the catalyst is preferably in the form of a suspension or fixed-bed. The process may be 25 performed using a continuous flow, semi-batch or batch mode of operation.

If epoxidation is carried out in the liquid phase, it is advantageous to work at a pressure of 1-100 bars and in the presence of one or more solvents. Suitable solvents include, but are not limited to, lower aliphatic 30 alcohols such as methanol, ethanol, isopropanol, and tert-butanol, or mixtures thereof, and water. Fluorinated alcohols can be used. It is also possible to use mixtures of the cited alcohols with water.

The following examples merely illustrate the invention. Those skilled in the art will recognize many variations that are within the spirit of the invention and scope of the claims.

#### EXAMPLE 1: CATALYST PREPARATION

5 TS-1 can be made according to any known literature procedure. See, for example, U.S. Pat. No. 4,410,501, DiRenzo, et. al., Microporous Materials (1997), Vol. 10, 283, or Edler, et. al., J. Chem. Soc., Chem. Comm. (1995), 155.

10 Catalyst 1A: TS-1 (20 g, 1.6 weight % Ti),  $[\text{Pd}(\text{NH}_3)_4](\text{NO}_3)_2$  (2.542 g of a 5 weight percent Pd solution in water, Strem Chemicals), and deionized water (80 g) are placed in a 250-mL single-neck round-bottom flask forming a pale white mixture. The flask is connected to a 15-inch cold water condenser and then blanketed with nitrogen at a 150 cc/min flow rate. The flask is inserted into an oil bath at 80°C and the reaction slurry is stirred. After stirring 15 for 24 hours, the slurry is filtered under pressurized  $\text{N}_2$ , washed with deionized water (150 mL, three times), and then the solid is dried in a vacuum oven at 50°C overnight. The solid catalyst is then calcined in 4% oxygen (remainder nitrogen) at 150°C for 4 hours. Measured Pd loading of the catalyst is 0.47 wt.%.

20 Catalyst 1B: Pd incorporation onto TS-1 is conducted according to the same procedure as for Catalyst 1A, except that 10 g TS-1, 0.8 g of  $[\text{Pd}(\text{NH}_3)_4](\text{NO}_3)_2$  (5 wt. % Pd solution in water), and 40 g deionized water is used. Measured Pd loading of the catalyst is 0.31 wt.%.

#### EXAMPLE 2: PROPYLENE EPOXIDATION STUDIES WITH AND WITHOUT 25 MODIFIERS

To evaluate the performance of the catalysts prepared in Example 1 in the presence of modifiers, the epoxidation of propylene using oxygen and hydrogen is carried out. The following procedure is employed.

30 The catalyst is slurried into 100 grams of methanol/water mixture (75 wt. % MeOH; 25 wt. %  $\text{H}_2\text{O}$ ) and added to the reactor system, consisting of a 300-mL high-pressure reactor and a 1000-mL methanol saturator. The methanol/water mixture does not contain any modifier for runs 2A-2C, but contains a modifier for runs 2D-2I (Table 1 lists the amount of modifier used

for each run). The slurry is then heated to 60°C and stirred at 1500 rpm. A gaseous feed consisting of 10% propylene, 4% oxygen, 1% hydrogen and 85% nitrogen is added to the system with a total flow of 1200 cc/min and a reactor pressure of 300 psi. Both the gas and liquid phase samples are 5 collected and analyzed by G.C.

The epoxidation results, in Table 2, show that the use of ammonium bicarbonate modifier (Run 2D) leads to an unexpected increase in catalyst activity and a decrease in the amount of ring-opened by-products as shown by higher PO/POE ratio compared to unmodified runs 2A-C. "POE" means 10 PO equivalents, which include propylene oxide (PO), propylene glycol (PG), dipropylene glycol (DPG), 1-methoxy-2-propanol (PM-1), 2-methoxy-1-propanol (PM-2), and acetol. Also, the use of other ammonium or carbonate containing compounds fails to produce similar results as seen in runs 2E-I. 15 Interestingly, run 2D shows little if any loss in catalyst activity over the 90-hour epoxidation run compared to runs 2A-C, thus demonstrating increased catalyst life.

#### EXAMPLE 3: PROPYLENE EPOXIDATION STUDIES WITH AND WITHOUT MODIFIERS IN PRESENCE OF CARBON DIOXIDE

To evaluate the performance of the catalysts prepared in Example 1 20 with and without modifiers in the presence of carbon dioxide, the epoxidation of propylene using oxygen and hydrogen is carried out. The following procedure is employed.

The catalyst is slurried into 100 grams of methanol/water mixture (75 wt.% MeOH; 25 wt.% H<sub>2</sub>O) and added to the reactor system, consisting of a 25 300-mL high-pressure reactor and a 1000-mL methanol saturator. The methanol/water mixture does not contain any modifier for run 3A, but contains a modifier for runs 3B-D (run 3B uses 2000 ppm CaCO<sub>3</sub>; run 3C uses 400 ppm KHCO<sub>3</sub>; and run 3D uses 400 ppm tetrapropylammonium hydroxide (TPAOH)). The slurry is then heated to 60°C and stirred at 1500 rpm. A 30 gaseous feed consisting of 10% propylene, 4% oxygen, 1% hydrogen, 84.9% nitrogen, and 0.1% carbon dioxide is added to the system with a total flow of 1200 cc/min and a reactor pressure of 300 psi. Both the gas and liquid phase samples are collected and analyzed by G.C.

The epoxidation results, in Table 3, show that the use of calcium carbonate in the presence of carbon dioxide (Run 3B) leads to an unexpected increase in catalyst activity and higher PO/POE ratio compared to runs using just carbon dioxide (Run 3A) or just calcium carbonate (Run 2I). Also, the 5 use of other modifier compounds fails to produce similar results, as seen in runs 3C-D. Also, run 3B shows little if any loss in catalyst activity over the 45-hour epoxidation run compared to run 3A, thus demonstrating increased catalyst life.

TABLE 1: Amount of Modifier used in Epoxidation Reactions.

Run #	Modifier	Modifier Amount (ppm) <sup>a</sup>
2D	(NH <sub>4</sub> )HCO <sub>3</sub>	500
2E	(NH <sub>4</sub> )H <sub>2</sub> PO <sub>4</sub>	500
2F	(NH <sub>4</sub> )Br	500
2G	NaHCO <sub>3</sub>	500
2H	KHCO <sub>3</sub>	250
2I	CaCO <sub>3</sub>	500

10 <sup>a</sup> Modifier amount is the amount of modifier compound in the methanol/water mixture.

TABLE 2: Propylene Epoxidation for Modified and Non-modified Runs.

Run #	Catalyst	Run time (h)	Modifier	Mean PO Productivity (g PO/g cat/h)	Mean POE <sup>a</sup> Productivity (g POE/g cat/h)	PO/POE (%)
2A *	1A	88.5	-	0.20	0.23	85
2B *	1B	64.5	-	0.21	0.30	72
2C * <sup>b</sup>	1B	70.5	-	0.13	0.14	92
2D	1A	90	(NH <sub>4</sub> )HCO <sub>3</sub>	0.31	0.35	90
2E *	1A	54	(NH <sub>4</sub> )H <sub>2</sub> PO <sub>4</sub>	0.18	0.24	77
2F *	1A	54	(NH <sub>4</sub> )Br	0.19	0.21	89
2G *	1B	64.5	NaHCO <sub>3</sub>	0.018	0.021	89
2H *	1B	40.5	KHCO <sub>3</sub>	0.02	0.023	90
2I * <sup>b</sup>	1B	70.5	CaCO <sub>3</sub>	.044	.047	95

\* Comparative Example

15 <sup>a</sup> POE = PO + ring-opened by-products (PG, DPG, PM-1, PM-2, and acetol).

<sup>b</sup> POE (grams POE) = grams PO<sub>final</sub> + grams PO<sub>converted to ring-opened by-products</sub>.

<sup>b</sup> Run is conducted at 45°C.

TABLE 3: Propylene Epoxidation Results for Carbonates plus CO<sub>2</sub>.

Run #	Catalyst	Run time (h)	Modifier	Mean PO Productivity (g PO/g cat/h)	Mean POE <sup>a</sup> Productivity (g POE/g cat/h)	PO/POE (%)
3A *	1A	52.5	0.1 vol % CO <sub>2</sub>	0.20	0.26	78
3B	1A	45	2000 ppm CaCO <sub>3</sub> + 0.1 vol % CO <sub>2</sub>	0.24	0.27	88
3C *	1A	69	400 ppm KHCO <sub>3</sub> + 0.1 vol % CO <sub>2</sub>	0.033	0.035	94
3D *	1A	55	400 ppm TPAOH + 0.1 vol % CO <sub>2</sub>	0.11	0.12	90

\* Comparative Example

<sup>a</sup> POE = PO + ring-opened by-products (PG, DPG, PM-1, PM-2, and acetol).

g POE (grams POE) = grams PO<sub>final</sub> + grams PO<sub>converted to ring-opened by-products</sub>.

I claim:

1. A process for producing an epoxide comprising reacting an olefin, oxygen, and hydrogen in the presence of a modifier and a catalyst comprising a noble metal and titanium zeolite, wherein the modifier is (a) 5 calcium carbonate in the presence of carbon dioxide or (b) ammonium bicarbonate.
2. The process of claim 1 wherein the titanium zeolite is titanium silicalite.
3. The process of claim 1 wherein the titanium zeolite is TS-1.
- 10 4. The process of claim 1 wherein the catalyst is comprised of from 0.01 to 10 weight percent noble metal.
5. The process of claim 1 wherein the noble metal is palladium.
6. The process of claim 1 wherein the olefin is a C<sub>2</sub>-C<sub>6</sub> olefin.
7. The process of claim 1 wherein the olefin is propylene.
- 15 8. The process of claim 1 wherein the modifier is calcium carbonate in the presence of carbon dioxide.
9. The process of claim 1 wherein the modifier is ammonium bicarbonate.
10. The process of claim 1 further comprising a solvent selected 20 from the group consisting of methanol, ethanol, isopropanol, and tert-butanol, and water.
11. A process comprising reacting propylene, hydrogen and oxygen in a solvent in the presence of ammonium bicarbonate and a catalyst comprising palladium and a titanium silicalite.
- 25 12. The process of claim 11 wherein the titanium silicalite is TS-1.
13. The process of claim 11 wherein the catalyst is comprised of from 0.01 to 10 weight percent palladium.
14. The process of claim 11 wherein the solvent is selected from the group consisting of methanol, ethanol, isopropanol, tert-butanol, and water.
- 30 15. A process comprising reacting propylene, hydrogen and oxygen in a solvent in the presence of a modifier and a catalyst comprising palladium and a titanium silicalite, wherein the modifier is calcium carbonate in the presence of carbon dioxide.

16. The process of claim 15 wherein the titanium silicalite is TS-1.
17. The process of claim 15 wherein the catalyst is comprised of from 0.01 to 10 weight percent palladium.
18. The process of claim 15 wherein the solvent is selected from the 5 group consisting of methanol, ethanol, isopropanol, tert-butanol, and water.

# INTERNATIONAL SEARCH REPORT

International Application No  
PCT/US 02/31669

**A. CLASSIFICATION OF SUBJECT MATTER**  
IPC 7 C07D301/06

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)  
IPC 7 C07D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ, CHEM ABS Data

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 98 00413 A (HARTWELL GEORGE E ; BOWMAN ROBERT G (US); CLARK HOWARD W (US); DOW) 8 January 1998 (1998-01-08) the whole document -----	1-18
A	US 6 008 388 A (JEWSON JENNIFER D ET AL) 28 December 1999 (1999-12-28) cited in the application the whole document -----	1-18

Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

Special categories of cited documents :

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*&\* document member of the same patent family

Date of the actual completion of the international search  20 January 2003	Date of mailing of the international search report  28/01/2003
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016	Authorized officer  Fritz, M

## INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 02/31669

Patent document cited in search report	Publication date	Patent family member(s)		Publication date
WO 9800413	A 08-01-1998	AU 711847 B2		21-10-1999
		AU 3511597 A		21-01-1998
		AU 711962 B2		28-10-1999
		AU 3586997 A		21-01-1998
		AU 712698 B2		11-11-1999
		AU 3646497 A		21-01-1998
		AU 736456 B2		26-07-2001
		AU 5905898 A		19-01-1999
		BR 9710122 A		10-08-1999
		BR 9710124 A		10-08-1999
		BR 9710995 A		14-03-2000
		CN 1226241 A		18-08-1999
		DE 69704869 D1		21-06-2001
		DE 69704869 T2		30-08-2001
		DE 69708880 D1		17-01-2002
		DE 69708880 T2		11-04-2002
		DE 69710472 D1		21-03-2002
		DE 69710472 T2		01-08-2002
		EP 0918762 A1		02-06-1999
		EP 0915861 A1		19-05-1999
		EP 0917532 A1		26-05-1999
		ES 2156391 T3		16-06-2001
		ES 2164358 T3		16-02-2002
		ES 2168653 T3		16-06-2002
		JP 2000514428 T		31-10-2000
		JP 2001505184 T		17-04-2001
		JP 2000514429 T		31-10-2000
		KR 2000022388 A		25-04-2000
		KR 2000022553 A		25-04-2000
		KR 2000022554 A		25-04-2000
		WO 9800413 A1		08-01-1998
		WO 9800414 A1		08-01-1998
		WO 9800415 A1		08-01-1998
		US 5965754 A		12-10-1999
		US 6031116 A		29-02-2000
		US 6309998 B1		30-10-2001
		US 2002052290 A1		02-05-2002
US 6008388	A 28-12-1999	AU 3562899 A		01-11-1999
		BR 9909606 A		19-12-2000
		CA 2327697 A1		21-10-1999
		CN 1297445 T		30-05-2001
		EP 1071675 A1		31-01-2001
		JP 2002511455 T		16-04-2002
		WO 9952885 A1		21-10-1999
		AU 3747399 A		01-11-1999
		BR 9909588 A		19-12-2000
		CA 2327609 A1		21-10-1999
		CN 1297444 T		30-05-2001
		EP 1077963 A1		28-02-2001
		JP 2002511454 T		16-04-2002
		WO 9952884 A1		21-10-1999
		US 6005123 A		21-12-1999