

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
25 August 2011 (25.08.2011)

PCT

(10) International Publication Number  
**WO 2011/101477 A1**

(51) International Patent Classification:  
C25B 11/04 (2006.01)

(21) International Application Number:  
PCT/EP2011/052542

(22) International Filing Date:  
21 February 2011 (21.02.2011)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
MI2010A000268 22 February 2010 (22.02.2010) IT

(71) Applicant (for all designated States except US): **INDUSTRIE DE NORA S.p.A.** [IT/IT]; Via Bistolfi 35, I-20134 Milano (IT).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **BRICHESE, Marianna** [IT/IT]; Via della Sachetta, 3, I-30021 Caorle (IT). **ANTOZZI, Antonio Lorenzo** [IT/IT]; Via Sant'Ambrogio, 20, I-23807 Merate (IT). **CALDERARA, Alice** [IT/IT]; Via della Vittoria, 34, I-26020 Agnadello (IT).

(74) Agent: **PATENTANWÄLTE REITSTÖTTER KINZEBACH**; Sternwartstr. 4, 81679 München (DE).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: ELECTRODE FOR ELECTROCHEMICAL PROCESSES AND METHOD FOR OBTAINING THE SAME

(57) Abstract: An electrode suitable for use as hydrogen-evolving cathode in electrolytic processes is obtained by thermal decomposition of a precursor consisting of an acetic solution of nitrates of ruthenium and optionally of rare earths. The electrode displays a low cathodic hydrogen evolution overpotential, an improved tolerance to current reversal phenomena and a high duration in industrial operating conditions.



WO 2011/101477 A1

# ELECTRODE FOR ELECTROCHEMICAL PROCESSES AND METHOD FOR OBTAINING THE SAME

## FIELD OF THE INVENTION

5

The invention relates to an electrode for electrolytic processes, in particular to a cathode suitable for hydrogen evolution in an industrial electrolytic process and to a method for obtaining the same.

## 10 BACKGROUND OF THE INVENTION

The invention relates to an electrode for electrolytic processes, in particular to a cathode suitable for hydrogen evolution in an industrial electrolytic process. The electrolysis of alkali brines for the simultaneous production of chlorine and alkali and the  
15 electrochemical processes of hypochlorite and chlorate manufacturing are the most typical examples of industrial electrolytic applications where hydrogen is cathodically evolved, but the electrode is not limited to any particular application. In the industry of electrolytic processes, competitiveness depends on several factors and primarily on the reduction of energy consumption, which is directly associated with the operating  
20 voltage. This is the main reason behind the efforts directed to reduce the various components making up the cell voltage, cathodic overvoltage being one of those. Cathodic overvoltages which can be naturally obtained with electrodes of chemically-resistant materials (for instance carbon steel) free of catalytic activation were considered acceptable for a long time. The market nevertheless increasingly requires,  
25 for this specific technology, a caustic product of high concentration, making the use of carbon steel cathodes unviable due to corrosion problems; moreover, the increase in the cost of energy has made the use of catalysts facilitating the cathodic evolution of hydrogen economically more convenient. One possible solution is the use of nickel substrates, chemically more resistant than carbon steel, coupled with platinum-based  
30 catalytic coatings. Cathodes of such kind are normally characterised by acceptably reduced cathode overvoltages, although resulting rather expensive due to their content of platinum and to their limited operative lifetime, probably caused by the poor adhesion of the coating to the substrate. A partial improvement in the adhesion of catalytic

coatings on nickel substrates can be obtained by adding cerium to the formulation of the catalytic layer, optionally as an external porous layer aimed at protecting the underlying platinum-based catalytic layer. However, this type of cathode is prone to suffer considerable damages following the occasional current reversals inevitably taking place  
5 in case of malfunctioning of industrial plants.

A partial improvement in the current reversal tolerance is obtainable by activating the nickel cathodic substrate with a coating consisting of two distinct phases, a first phase containing the noble metal-based catalyst and a second phase comprising palladium,  
10 optionally in admixture with silver, having a protective function. This kind of electrode presents however a sufficient catalytic activity only when the noble metal phase contains high amounts of platinum, preferably with a significant addition of rhodium; replacing platinum with cheaper ruthenium in the catalytic phase entails for example the onset of considerably higher cathodic overvoltages. Furthermore, the preparation of the  
15 coating consisting of two distinct phases requires an extremely delicate process control to achieve sufficiently reproducible results.

It has been thus evidenced the need for providing a new cathode composition for industrial electrolytic processes, in particular for electrolytic processes with cathodic  
20 evolution of hydrogen, characterised, with respect to prior art formulations, by an equivalent or higher catalytic activity, a lower overall cost in terms of raw materials, a higher reproducibility of preparation and a lifetime and tolerance to accidental current reversal equivalent or higher in the usual operative conditions.

## 25 SUMMARY OF THE INVENTION

Various aspects of the invention are set out in the accompanying claims.

In one embodiment, an electrode for electrolytic processes comprises a metal substrate,  
30 for instance made of nickel, copper or carbon steel, coated with a catalytic layer comprising 4-40 g/m<sup>2</sup> of ruthenium optionally in form of oxide, prepared by application and thermal decomposition in multiple coats of a precursor comprising a nitrate of ruthenium in acetic solution free of chlorides. In one embodiment, the catalytic later also

contains 1-10 g/m<sup>2</sup> of rare earths, for instance praseodymium, in form of oxides, and optionally 0.4-4 g/m<sup>2</sup> of palladium.

Under another aspect, a precursor suitable for the manufacturing of an electrode for gas evolution in electrolytic processes, for instance cathodic evolution of hydrogen, comprises a nitrate of ruthenium dissolved in a chloride-free solution containing more than 30%, and more preferably from 35 to 50% by weight, of acetic acid. The inventors surprisingly observed that the activity, the duration and the tolerance to reversals of electrodes used as cathodes for hydrogen evolution catalysed with ruthenium result remarkably superior provided nitrate-based precursors in a substantially chloride-free acetic solution are used in the manufacturing thereof, instead of the common precursor of the prior art consisting of RuCl<sub>3</sub> in hydrochloric solution. Without wishing to limit the invention to any particular theory, this may be due to the formation of a complex species wherein a ruthenium atom is co-ordinated with acetic or carbonyl groups, in the absence of co-ordination bonds with chloride; this complex species imparts morphological, structural or compositional effects reflected in improved performances of the electrode obtained by means of their decomposition especially in terms of duration and current reversal tolerance. In one embodiment, the nitrate of ruthenium employed is Ru (III) nitrosyl nitrate, a commercially available compound expressed by the formula Ru(NO)(NO<sub>3</sub>)<sub>3</sub> or sometimes written as Ru(NO)(NO<sub>3</sub>)<sub>x</sub> to indicate that the average oxidation state of ruthenium may be slightly different than 3. This species, that in one embodiment is present in the precursor at a concentration of 60-200 g/l, has the advantage of being easily available in amounts sufficient to an industrial production of electrodes. In one embodiment, the precursor solution also comprises rare earth nitrates, which have the advantage of providing further stability to the electrode coating obtainable by thermal decomposition of the same precursor. The inventors have found out that the addition of Pr(NO<sub>3</sub>)<sub>2</sub> at a concentration of 15-50 g/l imparts desirable features of functioning stability and tolerance to current reversals to the coating obtained by decomposition of the precursor. In one embodiment, the precursor solution also comprises 5-30 g/l of palladium nitrate; the presence of palladium in the coating obtainable by thermal decomposition of the precursor can have the advantage of imparting an enhanced tolerance to current reversals, especially in the long term.

Under another aspect, a method for producing a ruthenium-based precursor suitable for manufacturing an electrode for gas evolution in electrolytic processes comprises the preparation of a ruthenium solution by dissolution of ruthenium nitrate in glacial acetic acid under stirring, optionally adding a few droplets of nitric acid to facilitate its dissolution, followed by a dilution with 5-20% by weight acetic acid until obtaining the required concentration of ruthenium. In one embodiment, a method for manufacturing a ruthenium and rare earth-based precursor comprises: the preparation of a ruthenium solution by dissolution of a ruthenium nitrate in glacial acetic acid under stirring, optionally adding a few droplets of nitric acid; the preparation of a rare earth solution by dissolution of a rare earth nitrate, for instance  $\text{Pr}(\text{NO}_3)_2$ , in glacial acetic acid under stirring, optionally adding a few droplets of nitric acid; the mixing, optionally under stirring, of the ruthenium solution with the rare earth solution; the dilution with 5-20% by weight acetic acid until obtaining the required concentration of ruthenium and of rare earth. In one embodiment, the dilution with 5-20% acetic acid may also be effected on the ruthenium solution and/or on the rare earth solution before mixing.

Under another aspect, a method for manufacturing an electrode for gas evolution in electrolytic processes, for instance for cathodic evolution of hydrogen, comprises the application in multiple coats on a metal substrate and the subsequent thermal decomposition at 400-600°C of a ruthenium nitrate-based precursor with the optional addition of nitrates of rare earths or palladium in acetic solution as previously described; the precursor may be applied to a mesh or to an expanded or punched mesh of nickel, for instance by means of electrostatic spray techniques, brushing, dipping or other known techniques. After the deposition of each coat of precursor, the substrate may be subjected to a drying step, for instance of 5-15 minutes at 80-100°C, followed by thermal decomposition at 400-600°C for a time not lower than two minutes and usually comprised between 5 and 20 minutes. The above-indicated concentrations indicatively allow the deposition of 10-15 g/m<sup>2</sup> of ruthenium in 4-10 coats.

Some of the most significant results obtained by the inventors are described in the following examples which are not intended to limit the extent of the invention.

## EXAMPLE 1

An amount of  $\text{Ru}(\text{NO})(\text{NO}_3)_3$  corresponding to 100 g of Ru was dissolved in 300 ml of glacial acetic acid with addition of few ml of concentrated nitric acid. The solution was stirred for three hours keeping the temperature at 50°C. The solution was then brought to a volume of 500 ml with 10% by weight acetic acid (ruthenium solution).

Separately, an amount of  $\text{Pr}(\text{NO}_3)_2$  corresponding to 100 g of Pr was dissolved in 300 ml of glacial acetic acid with addition of few ml of concentrated nitric acid. The solution was stirred for three hours keeping the temperature at 50°C. The solution was then brought to a volume of 500 ml with 10% by weight acetic acid (rare earth solution).

480 ml of the ruthenium solution were mixed to 120 ml of the rare earth solution and left under stirring for five minutes. The thus obtained solution was brought to 1 litre with 10% by weight acetic acid (precursor).

A mesh of nickel 200 of 100 mm x 100 mm x 0.89 mm size was subjected to a process of blasting with corundum, etching in 20% HCl at 85°C for 2 minutes and thermal annealing at 500°C for 1 hour. The precursor was then applied by brushing in 6 subsequent coats, carrying out a drying treatment for 10 minutes at 80-90°C and a thermal decomposition for 10 minutes at 500°C after each coat until obtaining a deposition of 11.8 g/m<sup>2</sup> of Ru and 2.95 g/m<sup>2</sup> of Pr.

The sample was subjected to a performance test, showing an ohmic drop-corrected initial cathodic potential of -924 mV/NHE at 3 kA/m<sup>2</sup> under hydrogen evolution in 33% NaOH, at a temperature of 90°C, which indicates an excellent catalytic activity.

The same sample was subsequently subjected to cyclic voltammetry in a range of -1 to +0.5 V/NHE at a 10 mV/s scan rate; after 25 cycles, the cathodic potential was -961 mV/NHE, which indicates an excellent current reversal tolerance.

## EXAMPLE 2

An amount of  $\text{Ru}(\text{NO})(\text{NO}_3)_3$  corresponding to 100 g of Ru was dissolved in 300 ml of glacial acetic acid with addition of few ml of concentrated nitric acid. The solution was stirred for three hours keeping the temperature at 50°C. The solution was then brought to a volume of 1 litre with 10% by weight acetic acid (precursor).

A mesh of nickel 200 of 100 mm x 100 mm x 0.89 mm size was subjected to a process of blasting with corundum, etching in 20% HCl at 85°C for 2 minutes and thermal annealing at 500°C for 1 hour. The previously obtained precursor was then applied by brushing in 7 subsequent coats, carrying out a drying treatment for 10 minutes at 80-90°C and a thermal decomposition for 10 minutes at 500°C after each coat until obtaining a deposition of 12 g/m<sup>2</sup> of Ru.

The sample was subjected to a performance test, showing an ohmic drop-corrected initial cathodic potential of -925 mV/NHE at 3 kA/m<sup>2</sup> under hydrogen evolution in 33% NaOH, at a temperature of 90°C, which indicates an excellent catalytic activity.

The same sample was subsequently subjected to cyclic voltammetry in a range of -1 to +0.5 V/NHE at a 10 mV/s scan rate; after 25 cycles, the cathodic potential was -979 mV/NHE, which indicates an excellent current reversal tolerance.

## COUNTEREXAMPLE 1

A mesh of nickel 200 of 100 mm x 100 mm x 0.89 mm size was subjected to a process of blasting with corundum, etching in 20% HCl at 85°C for 2 minutes and thermal annealing at 500°C for 1 hour. The mesh was then activated by applying  $\text{RuCl}_3$  in nitric solution by brushing at a concentration of 96 g/l, carrying out a drying treatment for 10 minutes at 80-90°C and a thermal decomposition for 10 minutes at 500°C after each coat until obtaining a deposition of 12.2 g/m<sup>2</sup> of Ru.

The sample was subjected to a performance test, showing an ohmic drop-corrected initial cathodic potential of -942 mV/NHE at 3 kA/m<sup>2</sup> under hydrogen evolution in 33% NaOH, at a temperature of 90°C, which indicates a fair catalytic activity.

- 5 The same sample was subsequently subjected to cyclic voltammetry in a range of -1 to +0.5 V/NHE at a 10 mV/s scan rate; after 25 cycles, the cathodic potential was -1100 mV/NHE, which indicates a modest current reversal tolerance.

## COUNTEREXAMPLE 2

10 An amount of RuCl<sub>3</sub> corresponding to 100 g of Ru was dissolved in 300 ml of glacial acetic acid with addition of few ml of concentrated nitric acid. The solution was stirred for three hours keeping the temperature at 50°C. The solution was then brought to a volume of 500 ml with 10% by weight acetic acid (ruthenium solution).

15 Separately, an amount of Pr(NO<sub>3</sub>)<sub>2</sub> corresponding to 100 g of Pr was dissolved in 300 ml of glacial acetic acid with addition of few ml of concentrated nitric acid. The solution was stirred for three hours keeping the temperature at 50°C. The solution was then brought to a volume of 500 ml with 10% by weight acetic acid (rare earth solution).

20 480 ml of the ruthenium solution were mixed to 120 ml of the rare earth solution and left under stirring for five minutes. The thus obtained solution was brought to 1 litre with 10% by weight acetic acid (precursor).

25 A mesh of nickel 200 of 100 mm x 100 mm x 0.89 mm size was subjected to a process of blasting with corundum, etching in 20% HCl at 85°C for 2 minutes and thermal annealing at 500°C for 1 hour. The precursor was then applied by brushing in 7 subsequent coats, carrying out a drying treatment for 10 minutes at 80-90°C and a thermal decomposition for 10 minutes at 500°C after each coat until obtaining a  
30 deposition of 12.6 g/m<sup>2</sup> of Ru and 1.49 g/m<sup>2</sup> of Pr.



The sample was subjected to a performance test, showing an ohmic drop-corrected initial cathodic potential of -932 mV/NHE at 3 kA/m<sup>2</sup> under hydrogen evolution in 33% NaOH, at a temperature of 90°C, which indicates a good catalytic activity.

- 5 The same sample was subsequently subjected to cyclic voltammetry in a range of -1 to +0.5 V/NHE at a 10 mV/s scan rate; after 25 cycles, the cathodic potential was -1080 mV/NHE, which indicates a modest current reversal tolerance.

### 10 COUNTEREXAMPLE 3

An amount of Ru(NO)(NO<sub>3</sub>)<sub>3</sub> corresponding to 100 g of Ru was dissolved in 500 ml of 37% by volume hydrochloric acid with addition of few ml of concentrated nitric acid. The solution was stirred for three hours keeping the temperature at 50°C. The solution was  
15 then brought to a volume of 500 ml with 10% by weight acetic acid (ruthenium solution).

Separately, an amount of Pr(NO<sub>3</sub>)<sub>2</sub> corresponding to 100 g of Pr was dissolved in 500 ml of 37% by volume hydrochloric acid with addition of few ml of concentrated nitric acid. The solution was stirred for three hours keeping the temperature at 50°C (rare  
20 earth solution).

480 ml of the ruthenium solution were mixed to 120 ml of the rare earth solution and left under stirring for five minutes. The thus obtained solution was brought to 1 litre with 1 N hydrochloric acid (precursor).  
25

A mesh of nickel 200 of 100 mm x 100 mm x 0.89 mm size was subjected to a process of blasting with corundum, etching in 20% HCl at 85°C for 2 minutes and thermal annealing at 500°C for 1 hour. The precursor was then applied by brushing in 7 subsequent coats, carrying out a drying treatment for 10 minutes at 80-90°C and a  
30 thermal decomposition for 10 minutes at 500°C after each coat until obtaining a deposition of 13.5 g/m<sup>2</sup> of Ru and 1.60 g/m<sup>2</sup> of Pr.

The sample was subjected to a performance test, showing an ohmic drop-corrected initial cathodic potential of -930 mV/NHE at 3 kA/m<sup>2</sup> under hydrogen evolution in 33% NaOH, at a temperature of 90°C, which indicates a good catalytic activity.

- 5 The same sample was subsequently subjected to cyclic voltammetry in a range of -1 to +0.5 V/NHE at a 10 mV/s scan rate; after 25 cycles, the cathodic potential was -1090 mV/NHE, which indicates a modest current reversal tolerance.

The previous description shall not be intended as limiting the invention, which may be  
10 used according to different embodiments without departing from the scopes thereof, and whose extent is solely defined by the appended claims.

Throughout the description and claims of the present application, the term "comprise"  
and variations thereof such as "comprising" and "comprises" are not intended to  
15 exclude the presence of other elements, components or additional process steps.

## CLAIMS

- 5 1. Precursor suitable for the production of an electrode for gas evolution in electrolytic processes, comprising a ruthenium nitrate dissolved in a chloride-free aqueous solution containing acetic acid at a concentration higher than 30% by weight.
- 10 2. The precursor according to claim 1 wherein the concentration of said acetic acid is 35 to 50% by weight.
3. The precursor according to claim 1 or 2 wherein said ruthenium nitrate is ruthenium nitrosyl nitrate at a concentration of 60 to 200 g/l.
- 15 4. The precursor according to any one of claims 1 to 3 wherein said aqueous solution comprises at least one nitrate of a rare earth.
5. The precursor according to claim 4 wherein said at least one nitrate of a rare earth is  $\text{Pr}(\text{NO}_3)_2$  at a concentration of 15 to 50 g/l.
- 20 6. The precursor according to claim 4 or 5 wherein said aqueous solution comprises palladium nitrate at a concentration of 5 to 30 g/l.
- 25 7. Method for the preparation of the precursor according to any one of claims 1 to 3, comprising the preparation of a ruthenium solution by dissolution of said ruthenium in glacial acetic acid under stirring, with optional addition of nitric acid, followed by a dilution with an aqueous solution of acetic acid at a concentration of 5 to 20% by weight.
- 30 8. Method for the preparation of the precursor according to claim 4 or 5, comprising the following simultaneous or sequential steps:

- preparation of a ruthenium solution by dissolution of said ruthenium nitrate in glacial acetic acid under stirring, with optional addition of nitric acid;

- preparation of a rare earth solution by dissolution of said at least one nitrate of a rare earth in glacial acetic acid under stirring, with optional addition of nitric acid;

- mixing under optional stirring of said ruthenium solution with said rare earth solution;

- subsequent optional dilution with an aqueous solution of acetic acid at a concentration of 5 to 20% by weight.

9. The method according to claim 8 comprising a dilution step of said ruthenium solution and/or said rare earth solution with an aqueous solution of acetic acid at a concentration of 5 to 20% by weight before said mixing step.

10. Method for manufacturing an electrode for gas evolution in electrolytic processes, comprising the application of the precursor according to one of claims 1 to 6 to a metal substrate in multiple coats, with thermal decomposition at 400-600°C for a time of no less than 2 minutes after each coat.

11. The method according to claim 10 wherein said metal substrate is a mesh or a punched or expanded sheet made of nickel.

12. Electrode for cathodic hydrogen evolution in electrolytic processes comprising a metal substrate coated with a catalytic layer containing 4 to 40 g/m<sup>2</sup> of ruthenium in form of metal or oxide obtainable by the method according to any one of claims 9 to 11.

13. The electrode according to claim 12 wherein said catalytic layer further contains 1 to 10 g/m<sup>2</sup> of rare earths in form of oxides and optionally 0.4 to 4 g/m<sup>2</sup> of palladium in form of oxide or metal.

14. The electrode according to claim 13 wherein said rare earths comprise praseodymium oxide.
- 5 15. The electrode according to one of claims 12 to 14 wherein said metal substrate is made of nickel or nickel alloy.

**INTERNATIONAL SEARCH REPORT**

International application No  
PCT/EP2011/052542

**A. CLASSIFICATION OF SUBJECT MATTER**  
INV. C25B11/04  
ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)  
C25B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)  
EPO-Internal, WPI Data, CHEM ABS Data

| Category* | Citation of document, with indication, where appropriate, of the relevant passages   | Relevant to claim No. |
|-----------|--|-----------------------|
| A         | US 5 358 889 A (ISMAIL T. EMESH)<br>25 October 1994 (1994-10-25)<br>column 4, line 9 - line 25; example 1/1<br>column 5; claims 1,3,10<br>column 5, line 31 - line 37<br>----- | 1-9                   |
| X         | WO 2008/043766 A2 (INDUSTRIE DE MNORA<br>S.P.A.) 17 April 2008 (2008-04-17)<br>page 12 - page 14; claims 1,4,7,8<br>-----  | 12-15                 |
| A         | US 2006/231387 A1 (HIROYOSHI HOUDA)<br>19 October 2006 (2006-10-19)<br>the whole document<br>-----   | 1-15                  |
| A         | EP 1 916 320 A2 (CHLORINE ENGINEEERS<br>CORP.) 30 April 2008 (2008-04-30)<br>page 3, line 42 - line 45<br>page 11; claims 1,3,4<br>-----                                       | 1-15                  |

Further documents are listed in the continuation of Box C.

See patent family annex.

\* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search  
  
19 May 2011

Date of mailing of the international search report  
  
26/05/2011

Name and mailing address of the ISA/  
European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040,  
Fax: (+31-70) 340-3016

Authorized officer  
  
Battistig, Marcello

# INTERNATIONAL SEARCH REPORT

Information on patent family members

|   |
|---|
| International application No<br>PCT/EP2011/052542 |
|---|

| Patent document cited in search report | Publication date | Patent family member(s) | Publication date            |
|--|------------------|-------------------------|-----------------------------|
| US 5358889                             | A                | 25-10-1994              | NONE                        |
| -----                                  |                  |                         |                             |
| WO 2008043766                          | A2               | 17-04-2008              | AU 2007306373 A1 17-04-2008 |
|  |                  |                         | CA 2665569 A1 17-04-2008    |
|  |                  |                         | CN 101522952 A 02-09-2009   |
|  |                  |                         | EP 2084308 A2 05-08-2009    |
|  |                  |                         | JP 2010506050 T 25-02-2010  |
|  |                  |                         | KR 20090098792 A 17-09-2009 |
|  |                  |                         | US 2009194411 A1 06-08-2009 |
|  |                  |                         | ZA 200902129 A 28-07-2010   |
| -----                                  |                  |                         |                             |
| US 2006231387                          | A1               | 19-10-2006              | NONE                        |
| -----                                  |                  |                         |                             |
| EP 1916320                             | A2               | 30-04-2008              | CN 101225527 A 23-07-2008   |
|  |                  |                         | JP 4274489 B2 10-06-2009    |
|  |                  |                         | JP 2008133532 A 12-06-2008  |
|  |                  |                         | US 2010155235 A1 24-06-2010 |
|  |                  |                         | US 2008099328 A1 01-05-2008 |
| -----                                  |                  |                         |                             |