



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C09D 151/00	A1	(11) International Publication Number: WO 99/67339 (43) International Publication Date: 29 December 1999 (29.12.99)
<p>(21) International Application Number: PCT/EP99/04340</p> <p>(22) International Filing Date: 22 June 1999 (22.06.99)</p> <p>(30) Priority Data: 98111529.8 23 June 1998 (23.06.98) EP</p> <p>(71) Applicant (for all designated States except US): AKZO NOBEL N.V. [NL/NL]; Velperweg 76, NL-6824 BM Arnhem (NL).</p> <p>(72) Inventors; and (75) Inventors/Applicants (for US only): BUTER, Roelof [NL/NL]; Surinkhof 1, NL-6952 HT Dieren (NL). ROELOFS, Andreas, Henricus, Johannes [NL/NL]; Cadier en Keerpad 16, NL-6845 HV Arnhem (NL).</p> <p>(74) Agent: SCHALKWIJK, Pieter, Cornelis; Akzo Nobel N.V., Intellectual Property Dept. (Dept. AIP), P.O. Box 9300, NL-6800 SB Arnhem (NL).</p>	<p>(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).</p> <p>Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>	
(54) Title: AQUEOUS COATING COMPOSITION COMPRISING AN ADDITION POLYMER AND A RHEOLOGY MODIFIER		
<p>(57) Abstract</p> <p>The invention relates to an aqueous coating composition comprising a mixture of 90 to 99 wt.% of a film forming binder composition comprising an alkali non-swellable core-shell addition polymer dispersion (I), and 1-10 wt.% of a rheology modifying addition polymer dispersion (II). It is required that the total amount of (meth)acrylic acid in 100 parts of the total addition polymer (I) is less than 1.75 wt.%. The aqueous coating composition of the present invention can be advantageously used as a base coat in a base coat/clear coat system. This use shows a decrease in strike-in effect compared to previous known base coat/clear systems.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

AQUEOUS COATING COMPOSITION COMPRISING AN ADDITION
POLYMER AND A RHEOLOGY MODIFIER

5

The invention relates to an aqueous coating composition based on a mixture of a dispersion of an addition polymer and a rheology modifier. Preferably, this aqueous coating composition is mixed with a metallic pigment, such as aluminum, or a pigment, such as a metal oxide-coated mica, so that coatings with a metallic appearance may be obtained. In this way there is obtained a differential light reflection effect referred to as "flop". A problem with coating systems having a metallic appearance is to obtain a high flop as well as a high gloss.

15 To obtain a high flop, the metallic pigment on application of the coating composition should be and remain well oriented. To obtain a high gloss, the metallic pigment-containing coating is provided with an unpigmented, so-called clear coat. This system is generally called a "base coat/clear coat" system. In actual practice, the base coat will be sprayed with the clear coat, without prior curing of the base coat ("wet-on-wet"). Since the clear coat usually contains organic solvents, steps should be taken to prevent disorientation of the metallic pigment in the base coat as a result of the base coat being weakened up by the organic solvents in the clear coat ("strike-in").

25 An aqueous base coat composition is known from EP-A-0 038 127, i.e., a crosslinked core-shell dispersion whereby the shell, when swollen, provides the desired rheological properties. The crosslinking reduces the strike-in. A disadvantage to this system, however, is that the coating composition will have poor film-forming properties, which may manifest itself in poor mechanical properties.

30

Another aqueous base coat composition is known from EP-A-0 287 144, i.e., a swellable non-crosslinked core-shell dispersion having an amount of (meth)acrylic acid in the shell of 10-60 mole%. Exemplified are swellable non-crosslinked core-shell dispersions having more than 2 wt.% (meth)acrylic acid in 100 parts of the addition polymer. Also in this embodiment a decrease in strike-in is observed.

Both systems disclosed in EP-A-0 038 127 and EP-A-0 287 144 contain in the shell a lot of carboxylic groups, neutralized by an amine to provide the desired rheological properties. However, because of this large amount of salt groups, coatings based on these compositions especially when applied and cured at ambient temperature, show a poor water-resistance.

The present invention now provides an aqueous coating composition which may be used as base coat in a base coat/clear coat system, having good mechanical properties, a high flop, a high gloss, practically no strike-in, and a good water-resistance. Due to the fact that higher solid contents can be achieved with the aqueous coating composition of the present invention, a reduction in drying times and number of coats is obtained. In one or more of these properties the aqueous coating composition of the present invention shows improvement over those disclosed in EP-A-0 038 127 and EP-A-0 287 144.

The aqueous coating composition according to the invention comprises a mixture of 90 to 99 wt.% of a filmforming binder composition comprising an alkali non-swellable core-shell addition polymer dispersion (I), and 1-10 wt.% of a rheology modifying addition polymer dispersion (II), the sum of the wt.% indicated for the filmforming binder composition and dispersion (II) always being 100 wt.%,

wherein

the polymer dispersion (I) is prepared in two or more steps by emulsion polymerization, and obtained by copolymerization in a first step of

(1) 60-95 parts by weight (calculated on 100 parts by weight of the total
5 addition polymer (I)) of a monomer mixture A consisting of

(i) 65-100 mole% of a mixture of

(a) 10-98 mole% of a (cyclo)alkyl (meth)acrylate of which the
(cyclo)alkyl group contains 4-12 carbon atoms,

(b) 0-55 mole% styrene,

10 (c) 2-15 mole% hydroxy alkyl (meth)acrylate, and

(d) 0-20 mole% of a di(cyclo)alkyl maleate and/or fumarate of which
the (cyclo)alkyl groups contain 4-12 carbon atoms,

the sum of the mole% indicated for the monomers (a), (b), (c), and (d)
always being 100 mole%, and

15 (ii) 0-35 mole% of a different copolymerizable monoethylenically
unsaturated monomer,

the sum of the mole% indicated for the components (i) and (ii) always being
100 mole%,

and by copolymerization in a subsequent step of

20 (2) 5-40 parts by weight (calculated on 100 parts by weight of the total addition
polymer (I)) of a monomer mixture B consisting of

(e) 1-10 mole% (meth)acrylic acid,

(f) 2-20 mole% hydroxy alkyl (meth)acrylate,

(g) 0-55 mole% styrene, and

25 (h) 15-97 mole% of a different copolymerizable monoethylenically
unsaturated monomer,

the sum of the mole% indicated for the monomers (e), (f), (g), and (h)
always being 100 mole%,

with the carboxylic acid groups derived from the (meth)acrylic acid being at

30 least partially neutralized,

resulting in a non-crosslinked addition polymer I,
whereby the total amount of (meth)acrylic acid in 100 parts of the total addition
polymer (I) is less than 1.75 wt.%, and
wherein

5 the polymer dispersion (II) is prepared by emulsion polymerization, and
obtained by copolymerization of

(iii) 99.5-99.99 parts by weight (calculated on 100 parts by weight of the total
addition polymer (II)) of a monomer mixture C consisting of

- (j) 10-80 wt.% (cyclo)alkyl (meth)acrylate,
10 (k) 20-50 wt.% (meth)acrylic acid,
(m) 0-20 wt.% hydroxyalkyl (meth)acrylate, and
(n) 0-20 wt.% of a different copolymerizable monoethylenically unsaturated
monomer,

the sum of the wt.% indicated for the monomers (j), (k), (m), and (n) always
15 being 100 wt.%, and

(iv) 0.01-0.5 parts by weight (calculated on 100 parts by weight of the total
addition polymer (II)) of a compound having at least two unsaturated
groups,

with the carboxylic acid groups derived from the (meth)acrylic acid being at
20 least partially neutralized.

Preferably, in the first step of the preparation of the polymer dispersion (I), a
monomer mixture A is used, consisting of

- (i) 80-100 mole%, more preferred 100 mole%, of a mixture of
25 (a) 30-95 mole % of a (cyclo)alkyl (meth)acrylate of which the (cyclo)alkyl
group contains 4-12 carbon atoms,
(b) 0-50 mole % styrene,
(c) 5-12 mole % hydroxy alkyl (meth)acrylate, and
(d) 0-8 mole % of a di(cyclo)alkyl maleate and/or fumarate of which the
30 (cyclo)alkyl groups contain 4-12 carbon atoms, and

- (ii) 0-20 mole %, more preferred 0 mole%, of a different copolymerizable monoethylenically unsaturated monomer.

As examples of (cyclo)alkyl (meth)acrylates suitable for use in monomer mixture A and having a (cyclo)alkyl group with 4-12 carbon atoms may be mentioned: butyl acrylate, butyl methacrylate, 2-ethylhexyl acrylate, 2-ethylhexyl methacrylate, octyl acrylate, octyl methacrylate, isobornyl acrylate, isobornyl methacrylate, dodecyl acrylate, dodecyl methacrylate, cyclohexyl acrylate, cyclohexyl methacrylate, and mixtures thereof. Butyl acrylate, butyl methacrylate, and mixtures thereof are preferred.

Examples of hydroxyalkyl (meth)acrylates are 2-hydroxyethyl acrylate, 2-hydroxyethyl methacrylate, 2-hydroxypropyl acrylate, 2-hydroxypropyl methacrylate, 4-hydroxybutyl acrylate, 6-hydroxyhexyl acrylate, p-hydroxycyclohexyl acrylate, p-hydroxycyclohexyl methacrylate, hydroxypolyethylene glycol (meth)acrylates, hydroxypolypropylene glycol (meth)acrylates, and mixtures thereof. 2-Hydroxyethyl methacrylate is preferred.

As examples of di(cyclo)alkyl maleates and/or fumarates with the (cyclo)alkyl groups having 4-12 carbon atoms suitable for use in monomer mixture A may be mentioned dibutyl maleate, dibutyl fumarate, 2-ethylhexyl maleate, 2-ethylhexyl fumarate, octyl maleate, isobornyl maleate, dodecyl maleate, cyclohexyl maleate, and mixtures thereof.

As suitable copolymerizable monoethylenically unsaturated monomers to be used in monomer mixture A may be mentioned: alkyl (meth)acrylates having fewer than 4 carbon atoms in the alkyl group, such as methyl methacrylate, methyl acrylate, ethyl acrylate, ethyl methacrylate, propyl acrylate, propyl methacrylate, and isopropyl acrylate; alkyl maleates and fumarates having

fewer than 4 carbon atoms in the alkyl groups, such as dimethyl maleate, diethyl maleate, diethyl fumarate, and dipropyl maleate; (meth)acrylates having ether groups such as 2-methoxyethyl methacrylate, 2-ethoxyethyl methacrylate, and 3-methoxypropyl acrylate; monovinyl aromatic hydrocarbons, such as vinyl toluene, α -methyl styrene, and vinyl naphthalene; acrylamide and methacrylamide; nitriles such as acrylonitrile and methacrylonitrile; N-alkyl (meth)acrylamide such as N-isopropyl acrylamide, N-isopropyl methacrylamide, N-t-butyl acrylamide, N-t-octyl acrylamide, N,N-dimethyl aminoethyl methacrylate, N,N-diethyl aminoethyl methacrylate; monomers such as vinyl chloride, vinyl acetate, vinyl propionate, and vinyl pyrrolidone, and monomers containing one or more urea or urethane groups, such as for instance the reaction product of 1 mole of isocyanato-ethyl methacrylate and 1 mole of butylamine, 1 mole of benzylamine, 1 mole of butanol, 1 mole of 2-ethylhexanol, and 1 mole of methanol, respectively. Mixtures of these compounds may also be used.

Preferably, in a second step of the preparation of the polymer dispersion (I), a monomer mixture B is used, consisting of

- (e) 5-8 mole% (meth)acrylic acid,
- (f) 5-12 mole% hydroxy alkyl (meth)acrylate,
- (g) 0-30 mole% styrene, and
- (h) 50-90 mole% of a different copolymerizable monoethylenically unsaturated monomer.

Examples of hydroxy alkyl (meth)acrylates have been mentioned above. 2-hydroxyethyl methacrylate is preferred.

Examples of copolymerizable monoethylenically unsaturated monomers which may be used in the monomer mixture B include the examples mentioned above for copolymerizable monoethylenically unsaturated monomers which may be

used in the monomer mixture A. Also included are (cyclo)alkyl (meth)acrylates having a (cyclo)alkyl group with 4-12 carbon atoms. Examples thereof are also mentioned above. Mixtures of these compounds may also be used. Preferably, the copolymerizable monoethylenically unsaturated monomers are selected
5 from methyl methacrylate, butyl acrylate, butyl methacrylate, and mixtures thereof.

Preferably, polymer dispersion (I) is prepared by emulsion polymerization of
10 (1) 70-90, preferably 75-85, parts by weight of monomer mixture A and
(2) 10-30, preferably 15-25, parts by weight of monomer mixture B.
Optionally, different monomer mixtures A and/or B may be used successively.

Since the addition polymer (I) is non-crosslinked, the choice of the monomers in monomer mixtures A and B is such that the functional groups present other
15 than the unsaturated bonds cannot react with each other at the reaction conditions for the preparation of the addition polymer.

It is required that the total amount of (meth)acrylic acid in 100 parts of the total addition polymer (I) is less than 1.75 wt.%, preferably less than 1.5 wt.%, more
20 preferably between 0.5-1.4 wt.%. In this manner, the polymer dispersion (I) is non-swellable. The acid value is 3 to 10 mg KOH/g, preferably 5 to 8 mg KOH/g.

The addition polymer (I) has a Mn of from 50 000 to 2 000 000, preferably from
25 100 000 to 1 000 000.

Preferably, monomer mixture C used in the preparation of the polymer dispersion (II) consists of

- (j) 50-70 wt.% (cyclo)alkyl (meth)acrylate,
- 30 (k) 30-40 wt.% (meth)acrylic acid,

- (m) 0-5 wt.% hydroxyalkyl (meth)acrylate, and
(n) 0-5 wt.% of a different copolymerizable monoethylenically unsaturated monomer.

- 5 Preferably, the polymer dispersion (II) is prepared by emulsion polymerization of
of
(iii) 99.85-99.95 parts by weight of monomer mixture C and
(iv) 0.05-0.15 parts by weight of a compound having at least two unsaturated groups.

10

Preferably, the (cyclo)alkyl (meth)acrylates in monomer mixture C have alkyl groups with 1-4 carbon atoms. Examples include methyl methacrylate, methyl acrylate, ethyl acrylate, ethyl methacrylate, propyl acrylate, propyl methacrylate, isopropyl acrylate, isopropyl methacrylate, n-butyl acrylate, n-butyl methacrylate, isobutyl acrylate, isobutyl methacrylate, sec-butyl acrylate, sec-butyl methacrylate, t-butyl acrylate, t-butyl methacrylate, and mixtures thereof. Preferred are methyl acrylate, ethyl acrylate, and propyl acrylate.

20 Examples of hydroxyalkyl (meth)acrylates and copolymerizable monoethylenically unsaturated monomer to be used in monomer mixture C are given above for monomer mixtures A and B.

25 Examples of the compound having at least two unsaturated groups include divinyl toluene, divinyl benzene, trivinyl benzene, divinyl naphthalene, ethylene glycol di(meth)acrylate, trimethylene glycol di(meth)acrylate, 2-ethyl hexane-1,3-dimethacrylate, divinyl xylene, divinyl ethyl benzene, divinyl ether, divinyl sulfone, allyl ethers of polyhydric compounds, such as glycerol, pentaerythritol, sorbitol, sucrose, and resorcinol, allyl ethers of polyisocyanate compounds, such as triallyl isocyanurate, divinyl ketone, divinyl sulfide, allyl (meth)acrylate,
30 diallyl maleate, diallyl fumarate, diallyl phthalate, diallyl succinate, diallyl

carbonate, diallyl malonate, diallyl oxalate, diallyl adipate, diallyl sebacate, diallyl tartrate, diallyl silicate, triallyl citrate, triallyl phosphate, and N,N'-methylene di(meth)acrylamide. Preferred is a compound having at least two unsaturated groups of which at least one is an allylic group. More preferred are

5 diallyl phthalate, allyl methacrylate, and triallyl isocyanurate.

The addition polymer (II) has an acid value of 175 to 350 mg KOH/g, preferably 200 to 300 mg KOH/g, and a hydroxyl value of 0 to 150 mg KOH/g, preferably 0 to 100 mg KOH/g.

10

By emulsion polymerization is meant here the polymerization of the monomer mixtures of ethylenically unsaturated monomers in water in the presence of a water-soluble or -insoluble initiator and 0.1-5 wt.%, preferably 0.3-2.5 wt.% (calculated on the total monomer mixture(s)) of an emulsifier. The polymer

15 dispersion (I) may be prepared by emulsion polymerization as disclosed in EP-A-0 287 144. The polymer dispersion (II) may be prepared by emulsion polymerization as disclosed in GB 870 994.

The emulsifiers of which use is preferably made in the emulsion polymerization

20 are of an anionic and/or non-ionic nature. Examples of anionic emulsifiers include: potassium laurate, potassium stearate, potassium oleate, sodium decyl sulphate, sodium dodecyl sulphate, sodium dodecylbenzene sulphonic acid, and sodium rosinate. Examples of non-ionic emulsifiers include: linear and

25 branched alkyl and alkylaryl polyethylene glycol and polypropylene glycol ethers and thioethers, alkyl phenoxy poly(ethyleneoxy) ethanols such as the adduct of 1 mole of nonyl phenol and 3-12 moles of ethylene oxide; alkyl (ethyleneoxy) ethanols with 8-18 carbon atoms in the alkyl groups, such as the adduct of 1 mole dodecanol and 3-12 moles of ethylene oxide. Examples of emulsifiers comprising anionic and non-ionic groups are the ammonium or

30 sodium salt of the sulphate of alkyl phenoxy poly(ethyleneoxy) ethanols, such as

the adduct of 1 mole of nonyl phenol and 3-12 moles of ethylene oxide, and the ammonium or sodium salt of the sulphate of alkyl (ethyleneoxy) ethanols with 8-18 carbon atoms in the alkyl groups, such as the adduct of 1 mole C₁₂₋₁₄ alcohol and 3-12 moles of ethylene oxide. Preferred is the ammonium or sodium sulphate salt of the adduct of 1 mole C₁₂₋₁₄ alcohol and 3-12 moles of ethylene oxide.

Also, in emulsion polymerization, the conventional radical initiators may be used in the usual amounts. Examples of suitable radical initiators include water-soluble initiators, such as ammonium persulphate, sodium persulphate, potassium persulphate, and t-butyl hydroperoxide, and water-insoluble initiators, such as bis(2-ethylhexyl) peroxydicarbonate, di-n-butyl peroxydicarbonate, t-butyl perpivalate, cumene hydroperoxide, dibenzoyl peroxide, dilauroyl peroxide, 2,2'-azobisisobutyronitrile, and 2,2'-azobis-2-methylbutyronitrile. As suitable reducing agents which may be used in combination with e.g. a hydroperoxide may be mentioned: ascorbic acid, sodium sulfoxylate formaldehyde, thiosulphates, bisulphates hydrosulphates, water-soluble amines such as diethylene triamine, triethylene tetramine, tetraethylene pentamine, N,N'-dimethyl ethanol amine, and N,N-diethyl ethanol amine, and reducing salts such as cobalt, iron, nickel, and copper sulphate. Optionally, a chain length regulator, for instance n-octyl mercaptan, dodecyl mercaptan, and 3-mercaptopropionic acid, may also be used.

Copolymerization of the monomer mixtures generally is carried out at atmospheric pressure at a temperature of 40 – 100 °C, preferably 60 – 90 °C, in an atmosphere of an inert gas, such as nitrogen. Optionally, however, copolymerization may also be carried out at elevated pressure. The reaction conditions for monomer mixtures A and B should however be chosen in such manner that functional groups present in the monomer mixtures other than the unsaturated bonds cannot react with each other.

According to the invention the carboxylic acid groups derived from the acrylic acid and/or methacrylic acid are at least 40-100% neutralized by the addition of a neutralizing agent. As suitable neutralizing agents for the carboxylic acid may be mentioned ammonia and amines such as N,N-dimethyl ethanol amine, N,N-diethyl ethanol amine, 2-(dimethyl)-amino-2-methyl-1-propanol, triethyl amine, and morpholine. It is preferred that the neutralizing of the carboxylic acid groups should be carried out after the polymerization.

10 The coating composition according to the invention comprises preferably a mixture of 92-95 wt.% of a filmforming binder composition comprising an alkali non-swellable core-shell addition polymer dispersion (I), and 5-7.5 wt.% of a rheology modifying addition polymer dispersion (II).

15 The coating composition of the present invention consists essentially of water, being an aqueous coating composition. However, about 20 wt.% of liquid content of the coating composition may be an organic solvent. As suitable organic solvents may be mentioned such ether group-containing alcohols as hexylglycol, butoxyethanol, 1-methoxy-propanol-2, 1-ethoxy-propanol-2, 1-propoxy-propanol-2, 1-butoxy-propanol-2, and 1-isobutoxy-propanol-2; alcohols, such as methanol, ethanol, propanol, butanol, pentanol, and hexanol; diols, such as ethylene glycol and diethylene glycol.

The coating composition according to the present invention may be cured by physical drying. Alternatively, however, the coating compositions may be cured in the presence of a curing agent which reacts with hydroxyl and/or carboxyl groups.

Examples of suitable curing agents include N-methylol and/or N-methylol ether groups-containing aminoplastes obtained by reacting an aldehyde, for instance

formaldehyde, with an amino or amido groups-containing compound such as melamine, such as Cymel 328, ex Cytec, urea, N,N'-ethylene urea, dicyanodiamide, and benzoguanamine. The resulting compounds are preferably wholly or partially etherified with alcohols having 1-6 carbon atoms, such as methanol, ethanol, n-propanol, isopropanol, n-butanol, isobutanol, amyl alcohol, hexanol, or mixtures thereof. Especially favourable results may be obtained when using a methylol melamine having 4-6 methyl groups per molecule of melamine, at least 3 methylol groups being etherified with butanol or a butanol etherified condensation product of formaldehyde and N,N'-ethylene diurea. Examples of other suitable curing agents include polyisocyanates or water-dispersible blocked polyisocyanate such as a methyl ethyl ketoxime-blocked, isocyanate group-containing adduct of a polyisocyanate to a hydroxycarboxylic acid, e.g. dimethylol propionic acid, and aliphatic or aromatic carbodiimides.

15

In addition to the alkali non-swelling core-shell addition polymer dispersion (I), the filmforming binder composition may also comprise water-dilutable materials such as alkyd resins, polyesters, polyurethanes, and mixtures thereof. Preferably, the water dilutable material is a polyurethane. The filmforming binder composition may comprise 0,1 to 100 wt.% of the alkali non-swelling core-shell addition polymer dispersion (I) and 99,9 to 0 wt.% of at least one water dilutable material, wherein the sum of the wt.% indicated for dispersion (I) and the water dilutable material(s) is always 100 wt.%. More preferably, the filmforming binder composition may comprise 1 to 99 wt.% of the alkali non-swelling core-shell addition polymer dispersion (I) and 99 to 1 wt.% of at least one water dilutable material. Most preferably, the filmforming binder composition may comprise 25 to 75 wt.% of the alkali non-swelling core-shell addition polymer dispersion (I) and 75 to 25 wt.% of at least one water dilutable material.

30

In addition, the coating composition may contain the conventional additives and adjuvants, such as pigments, dispersing agents, dyes, and accelerators for the curing reaction. The applicable pigments may have an acid, a neutral or a basic character. Optionally, the pigments may be pre-treated to modify the properties.

- 5 Examples of suitable pigments include metallic pigments such as aluminum and stainless steel; nacreous pigments, such as mica coated with a metal oxide such as iron oxide and/or titanium dioxide; inorganic pigments, such as titanium dioxide, iron oxide, carbon black, silica, kaolin, talc, barium sulphate, lead silicate, strontium chromate, and chromium oxide; and organic pigments, such as phthalocyanine pigments.
- 10

The solids content of the coating composition ranges from 5-60 wt.%, preferably from 10-40 wt.%. This depends on whether a metallic pigment is used or not. The presence of metallic pigments results in a lower solid content compared to the presence of non-metallic pigments. However, compared to conventional aqueous base coat systems, the solid content of the coating composition of the present invention is in both cases higher.

15

Preferably, the coating composition according to the present invention is used as a base coat in a so-called base coat/clear coat system to provide a high gloss metallic appearance. To this end the coating composition according to the invention comprises so-called "non-leafing" aluminum paste or some other metallic pigment. Use of the coating compositions according to the invention as a base coat may prevent the base coat from being softened by the clear coat after being sprayed with it, so that the metallic effect will not be lost.

20

25

The clear coat used in the base coat/clear coat system may for instance be a clear baking lacquer of a conventional polyacrylate/melamine composition. The clear coat may also be a two-component polyester or

polyacrylate/polyisocyanate composition. The polyisocyanate may be for example the trimer of 1,6-hexamethylene diisocyanate.

The coating composition according to the invention may be applied to a
5 substrate in any desirable manner, such as by roller coating, spraying, brushing, sprinkling, flow coating, dipping, electrostatic spraying, or electrophoresis, preferably by spraying.

Suitable substrates may be made of wood, metal, and synthetic material.
10 Curing may be carried out at ambient temperature or, optionally, at elevated temperature to reduce the curing time. Optionally, the coating composition may be baked at higher temperatures in the range of, for instance, 60 to 160 °C, in a baking oven over a period of 10 to 60 minutes. The clear coat may be applied wet-on-wet on the base coat. Optionally, the base coat may be partially cured
15 prior to the application of the clear coat. Also, the base coat may be fully cured prior to the application of the clear coat.

The compositions are particularly suitable in the preparation of coated metal substrates, such as in the refinish industry, in particular the body shop, to repair
20 automobiles and transportation vehicles and in finishing large transportation vehicles such as trains, trucks, buses, and aeroplanes. The compositions of the present invention may also be used in the first finishing of automobiles.

The invention will be further described in the following examples, which must
25 not be construed as limiting the scope of the present invention.

EXAMPLES

Test methods used in the examples are described below.

- 5 The mean particle size of the dispersions was determined by dynamic light scattering, the dispersion being diluted with water to a solids content of about 0.1 wt.%.

The viscosity was determined with a Brookfield viscometer.

10

The solids content is determined in accordance with ASTM method D 1644-59 with heating at 130 °C over a period of 30 minutes.

- 15 The metallic-flake orientation can be measured by a spectrogoniometer. The intensity of the reflected light at angle β is measured for a given incident angle α . The so-called flop can be obtained by measurement of the intensity of the reflection (L-value) at two different angles.

$$\text{Flop} = \Delta L = L(\beta_1) - L(\beta_2)$$

wherein

- 20 $L(\beta_1)$ = intensity of the reflected light at an angle of $\pm 110^\circ$

$$L(\beta_2) = \text{intensity of the reflected light at an angle of } \pm 25^\circ$$

A silver-shaded low solids metallic base coat /clear coat system exhibits a flop-value of approximately 55 to 75 depending on the metallic grade, when measured in this way.

25

The humidity resistance can be judged visually by the presence of blisters after the test.

The following compounds were used.

30

Trigonox A-W70[®], 70 wt.% t-butyl hydroperoxide in water, ex Akzo Nobel Chemicals

Abex JKB[®], ammonium sulphate of an ethoxylated alkyl alcohol, solids content of 29.3 wt.%, ex Rhône-Poulenc

- 5 Perlankrol EP36[®], sodium sulphate of the adduct of 1 mole dodecanol and 6 moles ethylene oxide, solid content of 29.2 wt.%, ex Ackros

Rhodapex AB/20[®], ammonium sulphate of the adduct of 1 mole C₁₂₋₁₄-alcohol and 9 moles ethylene oxide, solids content of 28.7 wt.%, ex Rhône-Poulenc

Setal EPC 4673, polyesterpolyol, ex. Akzo Nobel Resins

- 10 Cymel 328[®], melamine crosslinker, ex Cytec

Preparation of alkali non-swelling core-shell addition polymer dispersions (I)

15 Example 1

A: Preparation of copolymer A of monomer mixture A in step 1

A 2 l flask fitted with a stirrer, a thermometer, a reflux condenser and dropping funnels A and B was filled with:

435.0 g of demineralized water and

- 20 12.0 g of emulsifier Perlankrol EP36[®].

Dropping funnel A was filled with:

280.0 g of monomer mixture I (see Table I).

Dropping funnel B was filled with a homogeneous mixture of:

140.0 g of demineralized water and

- 25 1.4 g of sodium persulphate.

After deaeration, the contents of both the flask and the dropping funnels were brought under a nitrogen atmosphere, and the contents of the flask were heated to 80 °C. Next, the contents of dropping funnel B were introduced into
30 the flask over a period of 3 minutes.

After the contents of the flask were brought again to 80°C, the contents of dropping funnel A were introduced into the flask at a constant rate over a period of 2.5 hours, after which the contents of the flask were kept at 80°C for another
5 1.5 hours.

B: Preparation of polymer dispersion (I) in Step 2

Dropping funnel A was filled with
70.0 g of monomer mixture II (see Table I)
10 and dropping funnel B was filled with a homogeneous mixture of:
35.0 g of demineralized water and
0.35 g of sodium persulphate.

The contents of dropping funnel B were introduced into the flask, comprising
15 copolymer A, over a period of 3 minutes. The contents of the flask were brought
again to 80°C and the contents of dropping funnel A were introduced into the
flask at a constant rate over a period of 1 hour, after which the contents of the
flask were kept at 80°C for another 2 hours. The reaction was carried out under
a nitrogen atmosphere.

20

On conclusion of the reaction the contents of the flask were cooled to 70°C,
after which there were added dropwise 41,3 g of a 10 wt.% solution of N,N-
dimethyl ethanol amine in water. Subsequently, the contents of the flask were
cooled to ambient temperature and filtered over a 30µm filter cloth. The
25 properties of the dispersion are given in Table II.

Example 2

Example 1 was repeated except for the following:

A: Preparation of copolymer A of monomer mixture A in step 1

5 Dropping funnel A was filled with 280.0 g of monomer mixture III (see Table I)
instead of monomer mixture I.

B: Preparation of polymer dispersion (I) in Step 2

10 Dropping funnel A was filled with 70.0 g of monomer mixture IV (see Table I)
instead of II.

After conclusion of the reaction were added 43.5 g of a 10 wt.% solution of N,N-
dimethyl ethanol amine in water. The properties of the resulting dispersion are
given in Table II.

15

Example 3A: Preparation of copolymer A of monomer mixture A in step 1

A 2 l flask fitted with a stirrer, a thermometer, a reflux condenser, and dropping
funnels A and B was filled with:

20 339.0 g of demineralized water, and
8.0 g of emulsifier Rhodapex AB/20®.

Dropping funnel A was filled with:

25 378.7 g of a monomer pre-emulsion composed of
93.3 g of demineralized water,
5.4 g of Rhodapex AB/20®, and
280.0 g of monomer mixture III (see Table I).

Dropping funnel B was filled with a homogeneous mixture of:

140.0 g of demineralized water and
1.4 g of ammonium persulphate.

30

After deaeration, the contents of both the flask and the dropping funnels were brought under a nitrogen atmosphere, and the contents of the flask were heated to 50°C, after which 5% of the contents of dropping funnel A were introduced into the flask over a period of 2 minutes.

5

Next, the contents of the flask were heated to 80°C and 30% of the contents of dropping funnel B were added to the contents of the flask. The contents of the flask were kept at 80°C for 15 minutes, and subsequently the rest of the contents of the dropping funnels A and B were introduced into the flask at a constant rate over a period of 2.5 hours, after which the contents of the flask were kept at 80°C for another hour.

10

B: Preparation of polymer dispersion (I) in Step 2

Dropping funnel A was filled with:

15 70.0 g of monomer mixture IV (see table I)

and dropping funnel B was filled with a homogeneous mixture of:

35.0 g of demineralized water and

0.35 g of ammonium persulphate.

20 The contents of both dropping funnels were introduced into the flask comprising copolymer A at a constant rate over a period of 1 hour, after which the contents of the flask were kept at 80°C for another hour.

25 On conclusion of the reaction the contents of the flask were cooled to 70°C, after which there were added dropwise 43,5 g of a 10 wt.% solution of N,N-dimethyl ethanol amine in water. Subsequently, the contents of the flask were cooled to ambient temperature and filtered over a 30µm filter cloth. The properties of the dispersion are given in Table II.

Example 4

Example 3 was repeated except for the following:

A: Preparation of copolymer A of monomer mixture A in step 1

- 5 The flask was filled with
338.0 g of demineralized water and
13,4 g of emulsifier Rhodapex AB/20®.

B: Preparation of polymer dispersion (I) in Step 2

- 10 Dropping funnel A was filled with:
70.0 g of monomer mixture V (see Table I)
The properties of the dispersion are given in Table II.

15 Example 5

Example 4 was repeated, except for the following:

A: Preparation of copolymer A of monomer mixture A in step 1

The monomer pre-emulsion was composed of 280.0 g of monomer mixture VI (see Table I) instead of monomer mixture III.

- 20 The properties of the dispersion are given in Table II.

Example 6

Example 4 was repeated, except for the following:

25 B: Preparation of polymer dispersion (I) in Step 2

Dropping funnel A was filled with 70.0 g of monomer mixture VII (see Table I) instead of monomer mixture V.

The properties of the dispersion are given in Table II.

Example 7A: Preparation of copolymer A of monomer mixture A in step 1

A 3 l flask fitted with a stirrer, a thermometer, a reflux condenser, and dropping funnels A and B was filled with:

- 5 621.1 g of demineralized water, and
 5.4 g of a 20 wt.% solution of sodium dodecylbenzene sulphonic acid
solution in demineralized water

Dropping funnel A was filled with:

- 683.8 g of a pre-emulsion composed of
10 507.1 g of monomer mixture VIII (see Table I)
 10.0 g of a 20 wt.% solution of sodium dodecylbenzene sulphonic
acid in demineralized water
 166.7 g of demineralized water

Dropping funnel B was filled with 55.3 g of a homogeneous mixture of

- 15 53.3 g of demineralized water
 2.02 g of sodium persulphate

After deaeration, the contents of both the flask and the dropping funnels were brought under a nitrogen atmosphere, and the contents of the flask were
20 heated to 50°C. After 9.6 g of the contents of dropping funnel A were introduced into the flask in a period of 1 minute, the contents of the flask were heated to 83°C. Subsequently, 25% of the contents of dropping funnel B were introduced into the flask after which the contents of the flask were kept at 83°C for a period of 15 minutes. Subsequently, the rest of the contents of dropping
25 funnel A and B were introduced into the flask at a constant rate over a period of 3 hours, after which the contents of the flask were kept at 83°C for another 30 minutes and subsequently diluted with 143.3 g of demineralized water.

B: Preparation of polymer dispersion (I) in Step 2

Dropping funnel A was filled with

126.7 g of monomer mixture IX (see Table I)

and dropping funnel B was filled with a homogeneous mixture of

5 33.3 g of demineralized water and

0.51 g of sodium persulphate.

The contents of both dropping funnels were introduced into the flask comprising copolymer A at a constant rate over a period of 1 hour, after which the contents
10 of the flask were kept at 80°C for another hour.

On conclusion of the reaction the contents of the flask were cooled to ambient temperature and filtered over a 80µm filter cloth, after which there were added dropwise 13.5 g of a 30 wt.% solution of N,N-dimethyl ethanol amine in
15 demineralized water. The properties of the dispersion are given in Table II.

Example 8

Example 7 was repeated except for the following:

20 A: Preparation of copolymer A of monomer mixture A in step 1

The monomer pre-emulsion was composed of:

507.1 g of monomer mixture X instead of monomer mixture VIII.

For dropping funnel B ammonium persulphate was used instead of sodium persulphate.

25 B: Preparation of polymer dispersion (I) in Step 2

The monomer mixture was composed of:

126.7 g of monomer mixture XI instead of monomer mixture IX.

On conclusion of the reaction the dispersion was neutralized with 11.7 g of a 30 wt.% solution of N,N-dimethyl ethanol amine in demineralized water instead of 13.5 g of this solution. The properties of the dispersion are given in Table II.

5

Example 9

Example 8 was repeated except for the following

A: Preparation of copolymer A of monomer mixture A in step 1

The flask was filled with

10 626.0 g demineralized water and
 3.7 g of emulsifier Perlankrol EP36®.

Dropping funnel A was filled with:

 680.7 g of a pre-emulsion composed of
 507.1 g of monomer mixture X (see Table I),
15 6.85 g of emulsifier Perlankrol EP36®, and
 166.7 g of demineralized water.

B: Preparation of polymer dispersion (I) in Step 2

On conclusion of the reaction the dispersion was neutralized with 12.8 g of a 30
20 wt.% solution of N,N-dimethyl ethanol amine in demineralized water instead of
11.7 g of this solution. The properties of the dispersion are given in Table II.

The preparation of rheology modifying addition polymer dispersions (II)

25

Example 10

A 2 l flask fitted with a stirrer, a thermometer, a reflux condenser, and dropping funnels was filled with:

 460.0 g of demineralized water and
30 2.64 g of Abex JKB®.

Dropping funnel A was filled with:

422.0 g of a monomer pre-emulsion composed of:

150.0 g of demineralized water,

12.0 g of Abex JKB[®], and

5 260.0 g of monomer mixture XII (see Table I).

Dropping funnel B was filled with a homogeneous mixture of

25.0 g of demineralized water and

0.38 g of ammonium persulphate.

Dropping funnel C was filled with a homogeneous mixture of

10 30.0 g of demineralized water and

0.14 g of ammonium persulphate

After deaeration, the contents of both the flask and the dropping funnels were brought under a nitrogen atmosphere and the contents of the flask were heated
15 to 85°C, after which 20 g of the contents of dropping funnel A and the contents of dropping funnel B were introduced into the flask. The contents of the flask were kept at 85 °C for 15 minutes.

Subsequently the rest of the contents of dropping funnel A and the contents of
20 dropping funnel C were introduced into the flask at a constant rate over a period of 90 minutes. Dropping funnel A was rinsed then with 60 g of demineralized water and after this has been introduced into the flask, the contents of the flask were kept at 85°C for another 30 minutes.

25 In the meantime dropping funnel D was filled with a homogeneous mixture of:

30.0 g of demineralized water and

0.60 g Trigonox A-W70[®]

and dropping funnel E was filled with a homogeneous mixture of:

30.0 g of demineralized water and

30 0.25 g of sodium formaldehyde sulfoxylate.

After the contents of the flask were cooled to 63 °C, the contents of dropping funnel D were introduced into the flask and after 10 minutes the contents of dropping funnel E were introduced into the flask at a constant rate over a period of 30 minutes. Subsequently, the contents of the flask were cooled to ambient temperature and filtered over a 30µm filter cloth. The properties of the dispersion are given in Table III.

10 Example 11

Example 10 was repeated except for the following:

Dropping funnel A was filled with 260.0 g of monomer mixture XIII (see Table I) instead of monomer mixture XII.

The properties of the dispersion are given in Table III.

15

Example 12

Example 10 was repeated except for the following:

20 Dropping funnel A was filled with 260.0 g of monomer mixture XIV (see Table I) instead of monomer mixture XII.

The properties of the dispersion are given in Table III.

Example 13

25 Example 10 was repeated except for the following:

The flask was now filled with

279.7 g of demineralized water and

1.0 g of Abex JKB®.

The properties of the dispersion are given in Table III.

30

Base coat compositionsExamples 14-19 and Comparative Examples A and B

Base coat compositions were prepared as follows.

5

A mixture of

22 g of aluminum paste (65% solids in aliphatic/aromatic hydrocarbons, Aquavex Sparkle Silver E5000AR , ex Silberline) and

28 g butoxyethanol

10 was added with stirring to a mixture of

190 g of a polymer dispersion (I) according to Examples 1-6 and

14 g of a polymer dispersion (II) according to Examples 10-12.

15 The base coat compositions were brought to a pH of 7.5-8.0 by the addition of N,N-dimethyl ethanol amine and diluted with water to spraying viscosity (efflux time of 35 sec. in DIN-cup No. 4). The solids contents of all the base coat compositions were in the range of 14-16 wt.% .

20 In an atmosphere having a relative humidity of 65% the base coat compositions of the present invention were sprayed onto primer coated steel test panels in a film thickness of 10-25 μm (in the dry state). Additionally, two test panels were prepared with a conventional low solids solvent borne base coat based on an acrylic/melamine system (comparative example A) and the aqueous core/shell dispersion of Example 5 of EP-A-0 287 144 (comparative example B).

25

After drying to mat at ambient temperature, the panels were tack free. Next, these test panels were partially covered up and the remaining part was repainted by spraying with a conventional clear coat, a two-component polyester/polyisocyanate coating composition, with the polyisocyanate being a

trimer of 1,6-hexamethylene diisocyanate (in a film thickness of 50-60 μm in a dry state).

After curing for one day at ambient temperature, the test panels 14-19 showed
5 a metallic coat of high gloss. After one week at ambient temperature, the solvent- and water-resistance of the test panels 14-19 were excellent, comparable with test panels A and B.

The flop of both the base coat and the base coat provided with clear coat was
10 measured (see Table IV). The flop values of the base coats based on the coating compositions according to the invention are excellent, comparable with test panels A and B. The decrease of flop by the application of the clear coat (strike-in) is practically zero, so that the excellent flop is maintained. However, the flop values of the base coat/ clear coat of test panels A and B are
15 significantly lower showing a considerable strike-in effect.

Examples 20-22 and Comparative Example C

Base coat compositions were prepared as follows.

20

A mixture of

20 g of aluminum paste (65 wt.%, Aquavex Sparkle Silver E5000AR from Silberline),

25.6 g of butoxyethanol,

25 30.2 g of Setal EPC 4673,

23.5 g of Cymel 328[®],

97.8 g of water, and

7.2 g of a 30 wt.% solution of N,N-dimethyl ethanol amine in water

was added with stirring to a mixture of

30 133.3 g of a polymer dispersion (I) according to Examples 7-9

90.7 g of water, and
13.3 g of a polymer dispersion (II) according to Example 13.

The base coat compositions were brought to a pH of 7.5-8.0 by addition of N,N-
5 dimethyl ethanol amine and diluted with water to spraying viscosity (efflux time
of 28 sec in DIN-cup No. 4). Solid content was 20 wt.%.

The base coat compositions were sprayed onto steel test panels in a film
thickness of 12-18 μm (in the dry state). After a flash-off period of 2 minutes at
10 23 °C and 8 minutes at 80 °C, the test panels were repainted with a
conventional clearcoat, in a film thickness of 40-45 μm in the dry state.

The clearcoat was a so-called one component polyacrylate/aminoplaste coating
composition. The aminoplaste is a polymeric melamine type resin. After curing
15 for 24 minutes at 140 °C, a metallic coat of good appearance was obtained.

The test panels were tested for their humidity resistance in comparison with a
reference waterborne base coat (Example 5 of EP-A-0 287 144; Comparative
Example C). The humidity resistance of the test panels 20 to 22 is excellent in
20 comparison to the humidity resistance of test panel C. Table V gives the results
of the test.

Table I
Monomer compositions

	wt. %		mole %
I	30	styrene	36,05
	45	butyl methacrylate	39,61
	20	butyl acrylate	19,53
	5	2-hydroxyethyl methacrylate	4,81
II	40	methyl methacrylate	45,55
	6	methacrylic acid	7,95
	10	2-hydroxyethyl methacrylate	8,76
	16	butyl methacrylate	12,83
	28	butyl acrylate	24,91
III	40	styrene	47,10
	47	butyl methacrylate	40,53
	8	butyl acrylate	7,66
	5	2-hydroxyethyl methacrylate	4,71
IV	40	methyl methacrylate	44,92
	6	methacrylic acid	7,84
	44	butyl acrylate	38,60
	10	2-hydroxyethyl methacrylate	8,64
V	30	methyl methacrylate	34,54
	6	methacrylic acid	8,03
	54	butyl acrylate	48,57
	10	2-hydroxyethyl methacrylate	8,86
VI	40	styrene	46,57
	35	butyl methacrylate	29,85
	20	butyl acrylate	18,92
	5	2-hydroxyethyl methacrylate	4,66
VII	20	methyl methacrylate	23,62
	64	butyl acrylate	59,05
	6	methacrylic acid	8,24
	10	2-hydroxyethyl methacrylate	9,09
VIII	20	butyl acrylate	21,54
	70	butyl methacrylate	67,86
	10	2-hydroxyethyl methacrylate	10,60
IX	39	methyl methacrylate	43,91
	45	butyl acrylate	39,58
	10	2-hydroxyethyl methacrylate	8,66
	6	methacrylic acid	7,85
X	20	butyl acrylate	20,11
	50,5	butyl methacrylate	45,72
	20	styrene	24,76
	9,5	2-hydroxyethyl methacrylate	9,41

Table I (continued)
Monomer compositions

	wt. %		mole %
XI	41	methyl methacrylate	46,68
	35,45	butyl acrylate	31,53
	10,00	butyl methacrylate	8,01
	9,25	2-hydroxyethyl methacrylate	8,10
	4,30	methacrylic acid	5,69
XII	64,00	ethyl acrylate	60,53
	35,85	methacrylic acid	39,41
	0,15	diallyl phthalate	0,058
XIII	64,10	ethyl acrylate	60,58
	35,85	methacrylic acid	39,38
	0,05	allyl methacrylate	0,037
XIV	64,10	ethyl acrylate	60,59
	35,85	methacrylic acid	39,39
	0,05	triallyl isocyanurate	0,019

5

Table II
Properties of addition polymer dispersions

Ex.	Monomer comp.	Solids contents (wt.%)	Viscosity (in Pa.s)	pH	Mean particle size (nm)	OH value	COOH value
1	I/II	35.2	20	8.1	83	25.9	7.8
2	III/IV	35.2	25	8.1	83	25.9	7.8
3	III/IV	35.2	36	8.2	93	25.9	7.8
4	III/IV	34.5	23	8.4	90	25.9	7.8
5	VI/IV	35.3	20	8.3	91	25.9	7.8
6	III/VII	35.3	22	8.5	91	25.9	7.8
7	VIII/IX	38.3	18	8.0	128	43	7.8
8	X/XI	38.5	24	8.1	92	40	5.6
9	X/XI	38.2	23	8.0	89	41	7.8

Table III
Properties of the rheology modifier dispersions

Ex.	Monomer comp.	Solids contents (wt.%)	Viscosity (in Pa.s)	pH	Mean particle size (nm)
10	XII	25	8	3.0	70
11	XIII	25	8	2.8	70
12	XIV	25	8	2.6	71
13	XII	30	10	2.7	121

5

Table IV Flop values

Base coat according to Example	Polymer dispersions according to Examples	Flop of base coat	Flop of base coat/ clear coat	Strike-in
A	----	64	60	4
B	----	66	62	4
14	1/10	64	63	1
15	2/10	66	66	0
16	3/11	66	66	0
17	4/11	65	65	0
18	5/12	64	63	1
19	6/12	65	64	1

10

Table V
Humidity resistance results

Base coat according to Example	Polymer dispersions according to Examples	Presence of blisters after the test
C	----	yes (medium/fine)
20	7/13	no
21	8/13	no
22	9/13	no

15

Claims

1. Aqueous coating composition comprising a mixture of
90 to 99 wt.% of a filmforming binder composition comprising an alkali non-
5 swellable core-shell addition polymer dispersion (I), and
1-10 wt.% of a rheology modifying addition polymer dispersion (II),
the sum of the wt.% indicated for the filmforming binder composition and
dispersion (II) always being 100 wt.%,
wherein
10 the polymer dispersion (I) is prepared in two or more steps by emulsion
polymerization, and obtained by copolymerization in a first step of
(1) 60-95 parts by weight (calculated on 100 parts by weight of the total
addition polymer (I)) of a monomer mixture A consisting of
(i) 65-100 mole% of a mixture of
15 (a) 10-98 mole% of a (cyclo)alkyl (meth)acrylate of which the
(cyclo)alkyl group contains 4-12 carbon atoms,
(b) 0-55 mole% styrene,
(c) 2-15 mole% hydroxy alkyl (meth)acrylate, and
(d) 0-20 mole% of a di(cyclo)alkyl maleate and/or fumarate of which
20 the (cyclo)alkyl groups contain 4-12 carbon atoms,
the sum of the mole% indicated for monomers (a), (b), (c), and (d)
always being 100 mole%, and
(ii) 0-35 mole% of a different copolymerizable monoethylenically
unsaturated monomer,
25 the sum of the mole% indicated for components (i) and (ii) always being
100 mole%,
and by copolymerization in a subsequent step of
(2) 5-40 parts by weight (calculated on 100 parts by weight of the total
addition polymer (I)) of a monomer mixture B consisting of
30 (e) 1-10 mole% (meth)acrylic acid,

- (f) 2-20 mole% hydroxy alkyl (meth)acrylate,
- (g) 0-55 mole% styrene, and
- (h) 15-97 mole% of a different copolymerizable monoethylenically unsaturated monomer,

5 the sum of the mole% indicated for monomers (e), (f), (g), and (h) always being 100 mole%,

with the carboxylic acid groups derived from the (meth)acrylic acid being at least partially neutralized,

resulting in a non-crosslinked addition polymer I,

10 whereby the total amount of (meth)acrylic acid in 100 parts of the total addition polymer (I) is less than 1.75 wt.%, and wherein

the polymer dispersion (II) is prepared by emulsion polymerization, and obtained by copolymerization of

15 (iii) 99.5-99.99 parts by weight (calculated on 100 parts by weight of the total addition polymer (II)) of a monomer mixture C consisting of

- (j) 10-80 wt.% (cyclo)alkyl (meth)acrylate,
- (k) 20-50 wt.% (meth)acrylic acid,
- (m) 0-20 wt.% hydroxyalkyl (meth)acrylate, and

20 (n) 0-20 wt.% of a different copolymerizable monoethylenically unsaturated monomer,

the sum of the wt.% indicated for monomers (j), (k), (m), and (n) always being 100 wt.%, and

25 (iv) 0.01-0.5 parts by weight (calculated on 100 parts by weight of the total addition polymer (II)) of a compound having at least two unsaturated groups,

with the carboxylic acid groups derived from the (meth)acrylic acid being at least partially neutralized.

2. Aqueous coating composition according to claim 1 characterized in that monomer mixture A consists of
- (i) 80-100 mole% of a mixture of
 - (a) 30-95 mole % of a (cyclo)alkyl (meth)acrylate of which the (cyclo)alkyl group contains 4-12 carbon atoms,
 - (b) 0-50 mole % styrene,
 - (c) 5-12 mole % hydroxy alkyl (meth)acrylate, and
 - (d) 0-8 mole % of a di(cyclo)alkyl maleate and/or fumarate of which the (cyclo)alkyl groups contain 4-12 carbon atoms, and
 - (ii) 0-20 mole % of a different copolymerizable monoethylenically unsaturated monomer.
3. Aqueous coating composition according to any one of the preceding claims characterized in that monomer mixture B consists of
- (e) 5-8 mole% (meth)acrylic acid,
 - (f) 5-12 mole% hydroxy alkyl (meth)acrylate,
 - (g) 0-30 mole% styrene, and
 - (h) 50-90 mole% of a different copolymerizable monoethylenically unsaturated monomer.
4. Aqueous coating composition according to any one of the preceding claims characterized in that the total amount of (meth)acrylic acid in 100 parts of the total addition polymer (I) is between 0.5-1.4 wt.%.
5. Aqueous coating composition according to any one of the preceding claims characterized in that monomer mixture C consists of
- (j) 50-70 wt.% (cyclo)alkyl (meth)acrylate,
 - (k) 30-40 wt.% (meth)acrylic acid,
 - (m) 0-5 wt.% hydroxyalkyl (meth)acrylate, and

- (n) 0-5 wt.% of a different copolymerizable monoethylenically unsaturated monomer.
- 5 6. Aqueous coating composition according to any one of the preceding claims characterized in that the polymer dispersion (II) is prepared by emulsion polymerization of
- (iii) 99.85-99.95 parts by weight of monomer mixture C and
- (iv) 0.05-0.15 parts by weight of a compound having at least two unsaturated groups.
- 10 7. Aqueous coating composition according to any one of the preceding claims characterized in that the compound having at least two unsaturated groups has at least one allylic group.
- 15 8. Aqueous coating composition according to claim 7, characterized in that the compound having at least two unsaturated groups is selected from diallyl phthalate, allyl methacrylate, and triallyl isocyanurate.
- 20 9. Aqueous coating composition according to any of the preceding claims, characterized in that the filmforming binder composition comprises in addition to the alkali non-swellable core-shell addition polymer dispersion (I) at least one water-dilutable material.
- 25 10. Aqueous coating composition according to claim 9, characterized in that the filmforming binder composition may comprise 0,1 to 99,9 wt.% of the alkali non-swellable core-shell addition polymer dispersion (I) and 99,9 to 0,1 wt.% of at least one water dilutable material, wherein the sum of the wt.% indicated for dispersion (I) and the water dilutable material(s) is always 100 wt.%.

11. Aqueous coating composition according to claims 9 or 10 characterized in that the water dilutable material is selected from alkyd resins, polyesters, polyurethanes, and mixtures thereof.
- 5 12. Aqueous coating composition according to 11 characterized in that the water dilutable material is polyurethane.
13. Base coat composition comprising an aqueous coating composition according to any one of the preceding claims.
- 10
14. Use of the basecoat composition of claim 13 in the refinishing of cars, the finishing of trucks, buses, trains, and aeroplanes, and the finishing of cars.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 99/04340

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C09D151/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C09D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 292 004 A (NIPPON PAINT CO LTD) 23 November 1988 (1988-11-23) page 2, line 48 -page 4, line 50 ---	1
A	US 3 821 145 A (WALUS A) 28 June 1974 (1974-06-28) claim 1 ---	1
A	WO 94 04581 A (PPG INDUSTRIES INC) 3 March 1994 (1994-03-03) example A -----	1

Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

° Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

8 October 1999

Date of mailing of the international search report

18/10/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Meulemans, R

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 99/04340

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0292004 A	23-11-1988	JP 2634167 B JP 63286473 A KR 9602744 B US 5011882 A	23-07-1997 24-11-1988 26-02-1996 30-04-1991
US 3821145 A	28-06-1974	NONE	
WO 9404581 A	03-03-1994	NONE	