(19) Europäisches Patentamt
European Patent Office
Office européen des brevets

(11) EP 1 186 639 B1

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention of the grant of the patent:
15.12.2004 Bulletin 2004/51

(51) Int Cl.[7]: **C09D 11/00**, B41J 2/21

(21) Application number: **01307642.7**

(22) Date of filing: **07.09.2001**

(54) **Ink jet process with cationic black pigments and underprinting with anionic dyes**

Tintenstrahldruckverfahren mit cationischen schwarzen Pigmenten und einem Unterdruck mit anionischen Farbstoffen

Procede au jet d'encre avec des pigments noirs cationiques et la sousimoression avec des colorants anioniques

(84) Designated Contracting States:
DE FR GB SE

(30) Priority: **11.09.2000 US 660551**

(43) Date of publication of application:
13.03.2002 Bulletin 2002/11

(73) Proprietor: **Hewlett-Packard Company**
Palo Alto, CA 94304 (US)

(72) Inventor: **Kowalski, Mark H., Cabot Corp.,**
Ink Jet Colorants
Billerica, MA 01821 (US)

(74) Representative: **Jackson, Richard Eric et al**
Carpmaels & Ransford,
43 Bloomsbury Square
London WC1A 2RA (GB)

(56) References cited:
EP-A- 0 838 507
EP-A- 0 879 857
EP-A- 0 953 616

- **PATENT ABSTRACTS OF JAPAN vol. 1998, no. 12, 31 October 1998 (1998-10-31) & JP 10 183046 A (SEIKO EPSON CORP), 7 July 1998 (1998-07-07)**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 1 186 639 B1

Printed by Jouve, 75001 PARIS (FR)

Description

TECHNICAL FIELD

[0001] The present invention relates generally to ink-jet inks, and, more particularly, to improving various aspects of the resulting print by an underprinting process.

BACKGROUND ART

[0002] Thermal ink-jet printers offer a low cost, high quality, and comparatively noise-free option to other types of printers commonly used with computers. Such printers employ a resistor element in a chamber provided with an egress for ink to enter from a plenum. The plenum is connected to a reservoir for storing the ink. A plurality of such resistor elements are arranged in a particular pattern, called a primitive, in a printhead. Each resistor element is associated with a nozzle in a nozzle plate, through which ink is expelled toward a print medium. The entire assembly of printhead and reservoir comprise an ink-jet pen.

[0003] In operation, each resistor element is connected through a conductive trace to a microprocessor, where current-carrying signals cause one or more selected elements to heat up. The heating creates a bubble of ink in the chamber, which is expelled through the nozzle toward the print medium. In this way, firing a plurality of such resistor elements in a particular order in a given primitive forms alphanumeric characters, performs area-fills, and provides other print capabilities on the medium.

[0004] Ink-jet inks used in thermal ink-jet printing typically comprise a colorant and a vehicle, with the vehicle often containing water and other relatively low surface tension liquids.

[0005] The tight tolerances of the nozzles (typically less than 30 μm diameter) require that the ink not clog the nozzles. Further, repeated firings of the resistor elements, which must withstand about 100 million firings over the life of the ink cartridge, can result in fouling of the resistor element. Finally, the ink composition must be capable of interacting with the print medium, especially paper, to penetrate the paper without undue spreading, and the ink composition should be smear and water resistant on the paper.

[0006] Inks are known which possess one or more of the foregoing properties. However, few ink compositions are known that posses all of those properties, since an improvement in one property often results in the degradation of another. Thus, inks used commercially represent a compromise in an attempt to achieve an ink evidencing at least an adequate performance in each of the aforementioned properties.

[0007] In commercially-available thermal ink-jet color printers, such as the DeskJet® printer available from Hewlett-Packard Company, a color spectrum is achieved by combining yellow, magenta, and cyan inks in various proportions. Typically, water-soluble dyes are employed. Black ink is either provided separately or by composite printing all three color inks. In the former case, a water-soluble black dye may be used or, more recently, a pigment-based black colorant may be used.

[0008] Water-soluble dyes are commonly used in dye-based inks. However, many dye-based inks, after being printed, exhibit poor water-fastness. There is an increased demand by consumers on the permanence or durability of ink-jet print, including water-fastness, light-fastness, smear-fastness, smudge-fastness, etc. Pigment-based black inks typically evidence the desired water-fastness, but exhibit other undesirable properties, such as slow dry time.

[0009] Color ink underprinting has recently received a lot of attention, given the benefits of color bleed, halo, dry time, media independence, and enhanced optical density (OD). As used herein, color bleed refers to the lateral migration of inks which would otherwise lead to mixing at the color interfaces. The halo-effect occurs when two inks of different chemical potentials including surface tension are printed adjacent each other. At the interface between the two inks, there is an apparent depletion of optical density, resulting in the appearance of a "halo".

[0010] However, there are two main disadvantages associated with color underprinting: (1) poor waterfastness associated with non-waterfast colors used in the color ink, and (2) the writing system using anionic black inks has required the color inks (anionic dyes) to use highly reactive additives to control bleed at black and color boundaries. While the reactive component is required, in order to create the precipitating or gellation mechanism, these materials have severely limited the dye choices for color inks.

[0011] Thus, a printing method is required that provides a printed product having improved properties such as low bleed, high edge acuity, high optical density, fast drying times, good waterfastness, good lightfastness, and good smear-fastness without sacrificing performance in other necessary properties.

DISCLOSURE OF INVENTION

[0012] In accordance with the present invention, a method of printing an ink onto a print medium is provided. In the method, two inks are employed, a first ink that includes at least one water-soluble, color dye having a first charge and

a second ink that includes at least one black pigment having a second and opposite charge. The method comprises:

(a) providing the first ink, which contains at least one water-soluble, color dye having one charge (anionic or cationic) and at least one surfactant;
(b) providing the second ink, which contains at least one black pigment, which has an opposite charge (cationic or anionic);
(c) printing in a first pass across the print medium the first ink; and
(d) printing the second ink over the first ink, totally covering and overlapping the first ink,

whereby the black pigment(s) reacts with the color dye(s) to form an insoluble complex on the print medium due to the use of opposite charges, thereby improving print speed, print quality, bleed, and waterfastness of the ink.

[0013] The printed ink set comprises the second ink totally covering and overlapping the first ink.

BEST MODES FOR CARRYING OUT THE INVENTION

[0014] The present invention uses cationic black pigment inks and underprinting to give advantages in waterfastness for the black ink. Specifically, the present invention defines a method that yields waterfast black prints, even when underprinting with non-waterfast color inks. The present invention defines a method that yields waterfast black prints, even if the particular black colorant is not very waterfast shortly after printing.

[0015] In accordance with the present invention, two different inks are printed onto a print medium: a first ink that includes at least one water-soluble color dye having a first charge and a second ink that includes at least one black pigment having a second and opposite charge. The method comprises:

(a) providing the first ink, which contains at least one water-soluble color dye having one charge (anionic or cationic) and at least one surfactant;
(b) providing the second ink, which contains at least one black pigment, which has an opposite charge (cationic or anionic);
(c) printing in a first pass across the print medium the first ink; and
(d) printing the second ink over the first ink, totally covering and overlapping the first ink,

whereby the black pigment(s) reacts with the color dye(s) to form an insoluble complex on the print medium due to opposite charges, thereby improving print speed, print quality, bleed, and waterfastness of the ink.

[0016] The net result of using the above black pigment ink, the above color ink, and underprinting with the color ink is a simpler ink system that optimizes the chemistry of each colorant and allows the colorants to complex each other, to yield good water-fastness. This allows much greater latitude in dye choice.

[0017] For example and preferably, an anionic color ink may comprise any of the dye-based inks used in ink-jet printing wherein at least one anionic color dye is employed. Many of these inks are well-known and have been disclosed elsewhere; see, e.g., U.S. Patents 5,091,005; 5,098,476; 5,100,470; 5,106,416; 5,108,503; 5,112,399; 5,116,409; 5,118,350; 5,133,803; 5,196,056; and 5,198,023, all assigned to the same assignee as the present application. Typically, these inks comprise a vehicle (one or more water-miscible organic solvents and water) and one or more water-soluble dyes, or colorants. Additives may be present to improve a given property, such as waterfastness, color bleed, and the like.

[0018] Preferably, a cationic black ink in conjunction with the anionic color inks and may comprise any of the pigment-based inks used in ink-jet printing wherein at least one cationic black pigment is employed. Many of pigment-based inks are well-known and have been disclosed elsewhere; see, e.g., U.S. Patents 5,085,698; 5,169,438; and 5,180,425, all assigned to E. I. du Pont de Nemours & Co. Patents are also known that teach combinations of black pigments and color dyes; see, e.g., U.S. Patent 5,745,140, assigned to the same assignee as the present application, and U.S. Patents 5,555,008 and 5,801,738, both assigned to E. I. du Pont de Nemours & Co. Modified carbon black, comprising a surface-treated pigment, is disclosed in U.S. Patent 5,985,015, assigned to Seiko Epson Corp. Generally, surface-treated pigments use quaternary ammonium salts. An example of one such cationic black pigment uses a pyridinium salt treated surface, obtained from Cabot Corp. Alternatively, a cationic dispersant may be used in place of the surface treatment.

[0019] Any printer that can perform underprinting can be used in the practice of the invention. Reconfiguring an existing printer, such as Hewlett-Packard's DeskJet® 720C, can be done to print the color dye-based ink first, followed by printing the black pigment-based ink thereover.

[0020] In operation, the printer prints one volume of color ink in the first pen pass. Then, on the bi-directional retrace, a multiple number of volumes of black ink, for example, six volumes, are printed over the same area. Although six volumes of black ink per one volume of color ink (6:1 black:color) were specifically done, other ratios of ink volume are

also expected to work. In particular, a ratio range of 5:1 to 9:1 black:color may be employed. So long as color ink is printed before black ink, the results disclosed herein are expected to be obtained. For example, the color ink can be printed in the same pass as the black ink. In this instance, the black ink is printed about 50 msec after the color ink.

[0021] Further, other types of black pigment-based inks should also work. For example, cationic dispersant stabilized carbon black is also expected to be effective.

[0022] Additionally, although overprinting black ink with color ink to maintain acceptable hue was not explored, in principle, the overprinting should not affect waterfastness as long as the area is also underprinted with the color ink.

[0023] Finally, it will be appreciated that the combination of cationic black pigments and anionic color dyes is most preferred; for example, anionic color dyes are well-established for ink-jet printing, and their properties are well-characterized. However, while the present invention also contemplates the use of anionic black pigments and cationic color dyes, as well as anionic or cationic black dyes in combination with cationic or anionic color pigments, these latter combinations are less preferred.

[0024] Use of an anionic colorant (dye) and cationic colorant (pigment) permits matching of the two colorants to form the insoluble complex. The insoluble complex is also formed with the other anionic/cationic combinations discussed immediately above.

[0025] The black ink, although it is usually ultimately waterfast, often does not dry fast enough. However, the combination of anionic colorant and surfactant provides a fast drying combination, due to the rapid formation of the insoluble complex and subsequent rapid penetration of the ink vehicle into the print medium. The resulting print is similar to laser-printed black, since the black colorant does not penetrate into the paper. In the case with ink-jet inks that are not underprinted with colorant combinations in accordance with the present invention, the combination of laser-like blackness (O.D.), edge acuity, and fast dry time are not achievable unless reactive additives are used in the color ink.

[0026] Since cyan and magenta are both darker than yellow, it is preferred to perform the underprinting with either or both of these two inks. More preferably, for color balance, black over cyan is printed in one pass direction and black over magenta is printed in the opposite pass direction, employing bi-directional printing.

[0027] The anionic color dye may be any of the well-known and conventional anionic dyes, preferably sulfonate or carboxylate. The carboxylate dyes are more preferred than the sulfonate dyes, since the carboxylate dyes are usually more waterfast, evidence better bleed control in combination with the black pigment ink, evidence better reduced halo effect, and are better insoluble-complex formers. On the other hand, salts, specifically, di-valent salts such as magnesium and calcium cations, should be avoided when using anionic dyes, due to their propensity to cause precipitation of these dyes.

[0028] At least one surfactant is employed with the anionic dye-based ink. The surfactant is present in an amount ranging from about 0.1 to 5 wt%, preferably about 2 wt%, of the ink, and provides a surface tension of about 15 to 40 dynes/cm. Examples include Tergitol and Dowfax surfactants, as well as zwitterionic, Crodofas, and Fluorad surfactants. An example of a zwitterionic surfactant is oleo-betaine. The surfactants are used variously to improve wettability of the ink, bleed control, and penetration of the ink into the print medium, and to improve kogation resistance of the resistors used to jet the ink from the pen. Preferably, the upper range of the surface tension of the color ink is approximately the same as the lower range of the surface tension of the black ink.

[0029] The balance of the dye-based ink comprises the usual water-miscible solvents, additives, and water.

[0030] As mentioned above, the black cationic pigment usually comprises quaternary ammonium groups. Surface-modified pigments are available from colorant vendors, such as Cabot Corp.

[0031] The black pigment ink should have a relatively high surface tension, on the order of 35 to 55 cp, or even higher, but not so high that it prevents jetting from the pen. The ink should contain little or no surfactant, so as to prevent wicking of the ink into the paper. The lack of surfactant results in crisp edges of the printed characters. Preferably, the lower range of the surface tension of the black ink is approximately the same as the upper range of the surface tension of the color ink.

[0032] The balance of the pigment-based ink comprises the usual water-miscible solvents, additives, and water.

[0033] While dispersants may be used with the pigment-based ink, no dispersant is required. Self-dispersing pigments such as those available from Cabot require no dispersant.

[0034] The present invention uses a simple color ink that requires no reactive components and enables one to use a variety of dyes, with charge appropriately opposite to the charge on the pigment. Further, no additional substances are having a charge are required in either the color ink or the black ink in order to control bleed, further simplifying the compositions.

EXAMPLES

Example 1 (Comparison):

[0035] A pair of aqueous-based inks, one an anionic dye-based ink (cyan I) and the other an anionic pigment-based

ink (black), were prepared. The cyan composition is shown in Table I below. The black ink was from Hewlett-Packard's black ink cartridge 51645A, such as found in Hewlett-Packard's DeskJet 720C printer

Table I.

Cyan Dye-Based Ink.		
Component	Cyan I, wt%	Cyan II, wt%
2-pyrrolidone	7.5	7.5
1,5-pentanediol	8.0	8.0
trimethylolpropane	7.5	7.5
$Mg(NO_3)_2 \cdot 6\ H_2O$	6.0	---
Tergitol 15-S-5	2.0	2.0
Dowfax 8390	0.35	0.35
Trizma base	0.2	0.2
Proxel GXL	0.2	0.2
Acid Blue 9 - Na salt, absorption at 1/10,000 (630 nm)	D=0.21	D=0.21
Direct Blue 199 - TMA salt, absorption at 1/10,000 (622 nm)	D=0.12	D=0.12
water	balance	balance

[0036] Two separate sets of print bars were printed on Gilbert Bond paper, one comprising only the black ink and the other comprising the black ink, but underprinted first with the cyan I ink. The black-cyan combination was printed in a volume ratio of 6:1 black:cyan I.

[0037] After 24 hours, a waterfastness test was performed, comprising printing black bars on paper separated by unprinted spaces, placing the printed paper on a clip board supported at 45 degrees, dripping 250 microliters (0.25 ml) water on the printed paper, and measuring transfer of color between printed bars and the unprinted spaces, based on optical density measurements.

[0038] The print bars comprising only the anionic black ink evidenced excellent water-fastness. However, the print bars comprising the anionic black ink underprinted with the anionic cyan I ink evidenced poor waterfastness due to the fact that the color ink, which was non-waterfast, ran down the paper.

Example 2 (Invention):

[0039] A pair of aqueous-based inks, one an anionic dye-based ink (cyan II) and the other a cationic pigment-based ink (black), were prepared. The cyan II ink was similar to cyan I, used in Example 1, except that the ink did not contain the magnesium salt. The black ink had the composition shown in Table II below.

Table II.

Cationic Black Pigment Ink.	
Component	Wt%
2-pyrrolidone	10
1,5-pentanediol	10
Cabot Quat IJX-HP016-1A	5.0
Multranol 4012	0.5
Surfynol 465	0.10
water	balance

[0040] Two separate sets of print bars were printed on Gilbert Bond paper, one comprising only the black ink and the other comprising the black ink, but underprinted first with the cyan II ink. The black-cyan combination was printed in a volume ratio of 6:1 black:cyan II.

[0041] After 24 hours, a waterfastness test was performed, as in Example 1.

[0042] The print bars comprising only the black ink evidenced excellent waterfastness and the print bars comprising the black ink underprinted with cyan II ink evidenced considerably improved waterfastness over the combination of Example 1.

[0043] Thus, the use of the cationic black pigment ink in combination with the anionic color dye ink shows long term waterfastness improvement over underprinted ink where the black ink is cationic instead of anionic.

[0044] A waterfastness test was performed, also as in Example 1, after 5 minutes. No difference in waterfastness was observed after only 5 minutes, compared with 24 hours, for the underprinted combination. However, the non-underprinted black ink, while waterfast after 24 hours, showed considerable lack of waterfastness after only 5 minutes.

[0045] Thus, the use of the cationic black pigment ink in combination with the anionic color dye ink shows waterfastness improvement over no underprinted ink.

INDUSTRIAL APPLICABILITY

[0046] The combination of a first, underprinted anionic dye-based ink and a second, cationic black pigment-based ink printed thereover is expected to find use in ink-jet printing.

[0047] Thus, there has been disclosed a method of printing a first, underprinted anionic dye-based ink and a second, cationic black pigment-based ink printed thereover, which provides improved print speed, print quality, bleed control, and waterfastness.

Claims

1. A method of printing an ink set on a print medium, said method comprising:

   (a) providing a first ink containing at least one water-soluble color dye that has a first charge and at least one surfactant;
   (b) providing a second ink containing at least one black pigment that has a second and opposite charge;
   (c) printing in a first pass across said print medium said first ink; and
   (d) printing said second ink over said first ink, totally covering and overlapping said first ink,

   whereby said at least one black pigment reacts with said at least one color dye to form an insoluble complex on said print medium due to the presence of the opposite charges, thereby improving print speed, print quality, bleed, and waterfastness of said ink.

2. The method of Claim wherein said color ink is printed in said first pass and said black ink is subsequently printed in said first pass, in either direction.

3. The method of Claim 1 wherein said color ink is printed in said first pass and said black ink is subsequently printed in a second pass.

4. The method of Claim I wherein said color dye is selected from the group consisting of cyan, yellow, and magenta.

5. The method of Claim 1 wherein said surfactant is present in said first ink in a concentration ranging from about 0.2 to 5 wt%.

6. The method of Claim 5 wherein said concentration is about 2 wt%.

7. The method of Claim 5 wherein said first ink has a surface tension within a range of about 25 dynes/cm up to that of said second ink.

8. The method of Claim 5 wherein said second ink has a surface tension of at least that of said first ink.

9. The method of Claim 1 wherein said at least one water-soluble color dye in said first ink is anionic and wherein said at least one black pigment in said second ink is cationic.

10. A printed ink obtainable by a process of printing an ink set for an ink-jet printer onto a print medium, said process comprising the steps of:

(a) printing in a first pass across said print medium a first ink containing at least one water-soluble color dye that has a first charge and at least one surfactant; and,
(b) printing a second ink containing at least one black pigment that has a second and opposite charge, said second ink totally covering and overlapping said first ink;

said printed ink evidencing improved print speed, print quality, bleed, and waterfastness.

11. The ink of Claim 10 wherein said color dye is selected from the group consisting of cyan, yellow, and magenta.

12. The ink of Claim 10 wherein said at least one water-soluble color dye in said first ink is anionic and wherein said at least one black pigment in said second ink is cationic.

Patentansprüche

1. Ein Verfahren zum Drucken eines Tintensatzes auf ein Druckmedium, wobei das Verfahren folgende Schritte aufweist:

(a) Bereitstellen einer ersten Tinte, die zumindest einen wasserlöslichen farbigen Farbstoff, der eine erste Ladung aufweist, und zumindest ein oberflächenaktives Mittel enthält;

(b) Bereitstellen einer zweiten Tinte, die zumindest ein schwarzes Pigment enthält, das eine zweite und entgegengesetzte Ladung aufweist;

(c) Drucken der ersten Tinte bei einem ersten Durchgang über das Druckmedium; und

(d) Drucken der zweiten Tinte über die erste Tinte, die erste Tinte völlig überdeckend und überlappend,

wodurch das zumindest eine schwarze Pigment mit dem zumindest einen farbigen Farbstoff reagiert, um aufgrund des Vorhandenseins der entgegengesetzten Ladungen einen unlöslichen Komplex auf dem Druckmedium zu bilden, wodurch Druckgeschwindigkeit, Druckqualität, Verlaufen und Wasserechtheit der Tinte verbessert werden.

2. Das Verfahren gemäß Anspruch 1, bei dem in jeder Richtung die Farbtinte bei dem ersten Durchgang gedruckt wird und die schwarze Tinte nachfolgend bei dem ersten Durchgang gedruckt wird.

3. Das Verfahren gemäß Anspruch 1, bei dem die Farbtinte bei dem ersten Durchgang gedruckt wird und die schwarze Tinte nachfolgend bei einem zweiten Durchgang gedruckt wird.

4. Das Verfahren gemäß Anspruch 1, bei dem der farbige Farbstoff aus der Gruppe ausgewählt ist, die Cyan, Gelb und Magenta umfasst.

5. Das Verfahren gemäß Anspruch 1, bei dem das oberflächenaktive Mittel in der ersten Tinte in einer Konzentration vorhanden ist, die von etwa 0,2 bis 5 Gewichtsprozent schwankt.

6. Das Verfahren gemäß Anspruch 5, bei dem die Konzentration etwa 2 Gewichtsprozent beträgt.

7. Das Verfahren gemäß Anspruch 5, bei dem die erste Tinte eine Oberflächenspannung in einem Bereich von etwa 25 dyn/cm bis zu derjenigen der zweiten Tinte aufweist.

8. Das Verfahren gemäß Anspruch 5, bei dem die zweite Tinte eine Oberflächenspannung von zumindest derjenigen der ersten Tinte aufweist.

9. Das Verfahren gemäß Anspruch 1, bei dem der zumindest eine wasserlösliche farbige Farbstoff in der ersten Tinte anionisch ist, und bei dem das zumindest eine schwarze Pigment in der zweiten Tinte kationisch ist.

10. Eine gedruckte Tinte, die durch einen Prozess eines Druckens eines Tintensatzes für einen Tintenstrahldrucker auf ein Druckmedium erhaltbar ist, wobei der Prozess folgende Schritte aufweist:

(a) Drucken einer ersten Tinte, die zumindest einen wasserlöslichen farbigen Farbstoff, der eine erste Ladung aufweist, und zumindest ein oberflächenaktives Mittel enthält, bei einem ersten Durchgang über das Druckmedium; und

(b) Drucken einer zweiten Tinte, die zumindest ein schwarzes Pigment enthält, das eine zweite und entgegengesetzte Ladung aufweist, wobei die zweite Tinte die erste Tinte völlig überdeckt und überlappt;

wobei die gedruckte Tinte verbesserte Druckgeschwindigkeit, Druckqualität, Verlaufen und Wasserechtheit erfährt.

11. Die Tinte gemäß Anspruch 10, bei der der farbige Farbstoff aus der Gruppe ausgewählt ist, die Cyan, Gelb und Magenta umfasst.

12. Die Tinte gemäß Anspruch 10, bei der der zumindest eine wasserlösliche farbige Farbstoff in der ersten Tinte anionisch ist, und bei der das zumindest eine schwarze Pigment in der zweiten Tinte kationisch ist.

Revendications

1. Procédé d'impression d'un jeu d'encres sur un milieu d'impression, ledit procédé comprenant les étapes consistant à :

(a) fournir une première encre contenant au moins un colorant de couleur hydrosoluble qui possède une première charge et au moins un tensio-actif ;

(b) fournir une deuxième encre contenant au moins un pigment noir qui possède une deuxième charge opposée ;

(c) imprimer ladite première encre dans un premier passage sur ledit milieu d'impression ; et

(d) imprimer ladite deuxième encre sur ladite première encre, ladite deuxième encre recouvrant et chevauchant totalement ladite première encre,

ainsi ledit au moins un pigment noir réagit avec ledit au moins un colorant de couleur pour former un complexe insoluble sur ledit milieu d'impression en raison de la présence des charges opposées, améliorant ainsi la vitesse d'impression, la qualité d'impression, la résistance aux bavures et la solidité à l'eau de ladite encre.

2. Procédé selon la revendication 1, dans lequel ladite encre de couleur est imprimée dans ledit premier passage et ladite encre noire est ensuite imprimée dans ledit premier passage, dans une direction ou l'autre.

3. Procédé selon la revendication 1, dans lequel ladite encre de couleur est imprimée dans ledit premier passage et ladite encre noire est ensuite imprimée dans un deuxième passage.

4. Procédé selon la revendication 1, dans lequel ledit colorant de couleur est choisi dans le groupe constitué du cyan, du jaune et du magenta.

5. Procédé selon la revendication 1, dans lequel ledit tensio-actif est présent dans ladite première encre en une concentration comprise dans la gamme d'environ 0,2% à 5% en poids.

6. Procédé selon la revendication 5, dans lequel ladite concentration est d'environ 2% en poids.

7. Procédé selon la revendication 5, dans lequel ladite première encre possède une tension de surface comprise dans la gamme d'environ 25 dynes/cm à la tension de surface de ladite deuxième encre.

8. Procédé selon la revendication 5, dans lequel ladite deuxième encre possède une tension superficielle au moins égale à celle de ladite première encre.

9. Procédé selon la revendication 1, dans lequel ledit au moins un colorant de couleur hydrosoluble présent dans ladite première encre est anionique et dans lequel ledit au moins un pigment noir présent dans ladite deuxième

encre est cationique.

10. Encre imprimée susceptible d'être obtenue par un procédé d'impression d'un jeu d'encres pour une imprimante à jet d'encre sur un milieu d'impression, ledit procédé comprenant les étapes consistant à :

(a) imprimer, dans un premier passage sur ledit milieu d'impression, une première encre contenant au moins un colorant de couleur hydrosoluble qui possède une première charge et au moins un tensio-actif ; et
(b) imprimer une deuxième encre contenant au moins un pigment noir qui possède une deuxième charge opposée, ladite deuxième encre recouvrant et chevauchant entièrement ladite première encre ;

ladite encre imprimée présentant une vitesse d'impression, une qualité d'impression, une résistance aux bavures et une solidité à l'eau améliorées.

11. Encre selon la revendication 10, dans laquelle le colorant de couleur est choisi dans le groupe constitué du cyan, du jaune et du magenta.

12. Encre selon la revendication 10, dans laquelle ledit au moins un colorant de couleur hydrosoluble présent dans ladite première encre est anionique et dans laquelle ledit au moins un pigment noir présent dans ladite deuxième encre est cationique.

REGISTER ENTRY FOR EP1186639

European Application No EP01307642.7 filing date 07.09.2001

Priority claimed:
11.09.2000 in United States of America - doc: 660551

Designated States DE FR GB SE

Title INK JET PROCESS WITH CATIONIC BLACK PIGMENTS AND UNDERPRINTING WITH ANIONIC DYES

Applicant/Proprietor
HEWLETT-PACKARD COMPANY, Incorporated in USA - Delaware, 3000 Hanover Street, Palo Alto, CA 94304, United States of America
[ADP No. 50014570006]

Inventor
KOWALSKI, MARK H.,
CABOT CORP.,
INK JET COLORANTS, Division,, 157 Concord Road, Billerica,, MA 01821, United States of America
[ADP No. 71281778001]

Classified to
C09D B41J

Address for Service
HEWLETT-PACKARD COMPANY, 3000 Hanover Street, Palo Alto, CA 94304, United States of America
[ADP No. 50014570006]

EPO Representative
RICHARD ERIC JACKSON, Carpmaels & Ransford, 43 Bloomsbury Square, London, WC1A 2RA, United Kingdom
[ADP No. 62363403001]

Publication No EP1186639 dated 13.03.2002
Publication in English

Examination requested 02.08.2002

Patent Granted with effect from 15.12.2004 (Section 25(1)) with title INK JET PROCESS WITH CATIONIC BLACK PIGMENTS AND UNDERPRINTING WITH ANIONIC DYES

10.12.2004 Notification of change of Address For Service name and address of
HEWLETT-PACKARD COMPANY, 3000 Hanover Street, Palo Alto, CA 94304, United States of America
[ADP No. 50014570006]
to
CARPMAELS & RANSFORD, 43 Bloomsbury Square, LONDON, WC1A 2RA, United Kingdom
[ADP No. 00000083001]
dated 08.12.2004. Official evidence filed on EP REG MAIN
Entry Type 7.1 Staff ID. MLUT Auth ID. F51

**** END OF REGISTER ENTRY ****

RENEWAL DETAILS

PUBLICATION NUMBER EP1186639

PROPRIETOR(S)

Hewlett-Packard Company, Incorporated in USA - Delaware, 3000 Hanover Street, Palo Alto, CA 94304, United States of America

DATE FILED 07.09.2001

DATE GRANTED 15.12.2004

DATE NEXT RENEWAL DUE 07.09.2005

DATE NOT IN FORCE

DATE OF LAST RENEWAL

YEAR OF LAST RENEWAL 00

STATUS PATENT IN FORCE

**** END OF REPORT ****