



(86) Date de dépôt PCT/PCT Filing Date: 2015/04/10
(87) Date publication PCT/PCT Publication Date: 2015/10/22
(45) Date de délivrance/Issue Date: 2022/01/11
(85) Entrée phase nationale/National Entry: 2016/08/24
(86) N° demande PCT/PCT Application No.: SE 2015/050428
(87) N° publication PCT/PCT Publication No.: 2015/160302
(30) Priorité/Priority: 2014/04/14 (EP14164524.2)

(51) Cl.Int./Int.Cl. *C22C 38/36* (2006.01),
C21D 7/02 (2006.01), *C22C 38/02* (2006.01),
C22C 38/04 (2006.01), *C22C 38/22* (2006.01),
C22C 38/24 (2006.01)

(72) Inventeurs/Inventors:
HILLSKOG, THOMAS, SE;
BENGTTSSON, KJELL, SE;
DAMM, PETTER, SE;
ENGSTROM SVENSSON, ANNIKA, SE;
ROBERTSSON, RIKARD, SE;
STEINER, KRISTOFFER, SE;

...

(73) Propriétaire/Owner:

(54) Titre : ACIER A OUTIL ECROUI
(54) Title: COLD WORK TOOL STEEL

(57) Abrégé/Abstract:

The invention relates cold work tool steel. The steel comprises the following main components (in wt. %): C 2.2 -2.4 Si 0.1 -0.55 Mn 0.2 -0.8 Cr 4.1 -5.1 Mo 3.1 -4.5 V 7.2 -8.5 balance optional elements, iron and impurities.



(72) **Inventeurs(suite)/Inventors(continued):** FORSBERG, AMANDA, SE; TIDESTEN, MAGNUS, SE;
EMANUELSSON, PAR, SE

(73) **Propriétaires(suite)/Owners(continued):** UDDEHOLMS AB, SE

(74) **Agent:** RIDOUT & MAYBEE LLP

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(10) International Publication Number
WO 2015/160302 A1

(43) International Publication Date
22 October 2015 (22.10.2015)

(51) International Patent Classification:

C22C 33/02 (2006.01) C22C 38/24 (2006.01)
C22C 38/22 (2006.01) C22C 38/36 (2006.01)

(21) International Application Number:

PCT/SE2015/050428

(22) International Filing Date:

10 April 2015 (10.04.2015)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

14164524.2 14 April 2014 (14.04.2014) EP

(71) Applicant: UDDEHOLMS AB [SE/SE]; S-683 85 Hagförs (SE).

(72) Inventors: **HILLSKOG, Thomas**; Mosstorp 237, S-655 93 Karlstad (SE). **BENGTSSON, Kjell**; Myra 161, S-683 93 Råda (SE). **DAMM, Petter**; Kvarnbergsgatan 17, S-652 29 Karlstad (SE). **ENGSTRÖM SVENSSON, Annika**; Fogdhyttan 12, S-682 91 Filipstad (SE). **ROBERTSSON, Rikard**; Villavägen 31, S-683 34 Hagförs (SE). **STEINER, Kristoffer**; Villavägen 31, S-660 60 Molkom (SE). **FORSBERG, Amanda**; Gåsborn Östra Höjden 31, S-682 92 Filipstad (SE). **TIDESTEN, Magnus**; Rågvägen 3, S-683 34 Hagförs (SE). **EMANUELSSON, Pär**; Åleby Gård, S-686 91 Sunne (SE).

(74) Agent: **HYNELL PATENTTJÄNST AB**; Box 138, S-683 23 Hagförs (SE).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: COLD WORK TOOL STEEL

(57) Abstract: The invention relates cold work tool steel. The steel comprises the following main components (in wt. %): C 2.2 -2.4 Si 0.1 -0.55 Mn 0.2 -0.8 Cr 4.1 -5.1 Mo 3.1 -4.5 V 7.2 -8.5 balance optional elements, iron and impurities.



WO 2015/160302 A1

COLD WORK TOOL STEEL

TECHNICAL FIELD

The invention relates to a cold work tool steel.

5

BACKGROUND OF THE INVENTION

Vanadium alloyed powder metallurgy (PM) tool steels have been on market for decades and attained a considerable interest because of the fact that they combine a high wear resistance with an excellent dimensional stability and because they have a good
10 toughness. These steels have a wide range of applications such as for knives, punches and dies for blanking, piercing and cold extrusion. The steels are produced by powder metallurgy. The basic steel composition is firstly atomized and thereafter the powder is filled into a capsule and subjected to hot isostatic pressing (HIP) in order to produce an isotropic steel. The performance of the steels tends to increase with increasing content
15 of vanadium. A high performance steel produced in this way is CPM®10V. It has high carbon and vanadium contents as described in US 4,249,945. Another steel of this kind is disclosed in EP 1 382 704 A1.

Although the known (PM) steel has a higher toughness than conventionally produced
20 tool steels, there is a need for further improvements in order to reduce the risk for tool breakage, such as chipping and fracture and to further improve the machinability. Until now the standard measure to counteract chipping is to reduce the hardness of the tool.

DISCLOSURE OF THE INVENTION

25 The object of the present invention is to provide a powder metallurgy (PM) produced cold work tool steel having an improved property profile leading to an increased life time of the tool.

Another object of the present invention is to optimize the properties, while still
30 maintaining a good wear resistance and at the same time improve the machinability.

A particular object is to provide a martensitic cold work tools steel alloy having an improved property profile for cold working.

The foregoing objects, as well as additional advantages are achieved to a significant measure by providing a cold work tool steel having a composition as set out herein.

5

DETAILED DESCRIPTION

The importance of the separate elements and their interaction with each other as well as the limitations of the chemical ingredients of the claimed alloy are briefly explained in the following. All percentages for the chemical composition of the steel are given in weight % (wt. %) throughout the description.

10

Carbon (2.2 – 2.4 %)

Carbon is to be present in a minimum content of 2.2 %, preferably at least 2.25 %. The upper limit for carbon may be set to 2.4 % or 2.35 %. Preferred ranges are 2.25 – 2.35 % and 2.26 – 2.34 %. In any case, the amount of carbon should be controlled such that the amount of carbides of the type $M_{23}C_6$ and M_7C_3 in the steel is limited to less than 5 vol. %, preferably the steel is free from said carbides.

15

Chromium (4.1 – 5.1 %)

Chromium is to be present in a content of at least 4.1 % in order to provide a good hardenability in larger cross sections during heat treatment. If the chromium content is too high, this may lead to the formation of high-temperature ferrite, which reduces the hot-workability. The chromium content is therefore preferably 4.5 – 5.0 %. The lower limit may be 4.2 %, 4.3 %, 4.4 % or 4.5 %. The upper limit may be 5.1 %, 5.0 %, 4.9 % or 4.8 %.

25

Molybdenum (3.1 – 4.5 %)

Mo is known to have a very favourable effect on the hardenability. Molybdenum is essential for attaining a good secondary hardening response. The minimum content is 3.1 %, and may be set to 3.2 %, 3.3 %, 3.4 % or 3.5 %. Molybdenum is a strong carbide forming element and also a strong ferrite former. The maximum content of

30

molybdenum is therefore 4.5 %. Preferably Mo is limited to 4.2 %, 3.9 % or even 3.7 %.

Tungsten (≤ 2 %)

- 5 In principle, molybdenum may be replaced by twice as much tungsten. However, tungsten is expensive and it also complicates the handling of scrap metal. The maximum amount is therefore limited to 2 %, preferably 1 %, more preferably 0.3 % and most preferably no deliberate additions are made.

10 **Vanadium (7.2 – 8.5 %)**

- Vanadium forms evenly distributed primary precipitated carbides and carbonitrides of the type $M(C,N)$ in the matrix of the steel. In the present steels M is mainly vanadium but significant amounts of Cr and Mo may be present. Vanadium shall therefore be present in an amount of 7.2 – 8.5. The upper limit may be set to 8.4 %, 8.3 %, or 8.25
15 %. The lower limit may be 7.3 %, 7.4 %, 7.5 %, 7.6 %, 7.7 %, 7.75 %, and 7.8 %. The upper and lower limits may be freely combined within the limits set out herein. Preferred ranges include 7.7 – 8.3 %.

Nitrogen (0.02 – 0.15 %)

- 20 Nitrogen may optionally be introduced in the steel in an amount of 0.02 – 0.15 %, preferably 0.02 – 0.08 % or 0.03 – 0.06 %. Nitrogen helps to stabilize the $M(C,N)$ because the thermal stability of vanadium carbonitrides is better than that of vanadium carbides.

25 **Niobium (≤ 2 %)**

- Niobium is similar to vanadium in that it forms carbonitrides of the type $M(C,N)$ and may in principle be used to replace vanadium but that requires the double amount of niobium as compared to vanadium. Hence, the maximum addition of Nb is 2.0%. The combined amount of $(V + Nb/2)$ should be 7.2 – 8.5 %. However, Nb results in a more
30 angular shape of the $M(C,N)$. The preferred maximum amount is therefore 0.5%. Preferably, no niobium is added.

Silicon (0.1 – 0.55 %)

Silicon is used for deoxidation. Si is present in the steel in a dissolved form. Si increases the carbon activity and is beneficial for the machinability. Si is therefore present in an amount of 0.1 – 0.55 %. For a good deoxidation, it is preferred to adjust the Si content to at least 0.2 %. Si is a strong ferrite former and should preferably be limited to ≤ 0.5 %.

Manganese (0.2 – 0.8 %)

Manganese contributes to improving the hardenability of the steel and together with sulphur manganese contributes to improving the machinability by forming manganese sulphides. Manganese shall therefore be present in a minimum content of 0.2 %, preferably at least 0.22 %. At higher sulphur contents manganese prevents red brittleness in the steel. The steel shall contain maximum 0.8 %, preferably maximum 0.6 %. Preferred ranges are 0.22 – 0.52 %, 0.3 – 0.4 and 0.30 - 0.45%.

Nickel ($\leq 3.0\%$)

Nickel is optional and may be present in an amount of up to 3 %. It gives the steel a good hardenability and toughness. Because of the expense, the nickel content of the steel should be limited as far as possible. Accordingly, the Ni content is limited to 1%, preferably 0.3%. Most preferably, no nickel additions are made.

Copper ($\leq 3.0\%$)

Cu is an optional element, which may contribute to increasing the hardness and the corrosion resistance of the steel. If used, the preferred range is 0.02 – 2% and the most preferred range is 0.04 - 1.6%. However, it is not possible to extract copper from the steel once it has been added. This drastically makes the scrap handling more difficult. For this reason, copper is normally not deliberately added.

Cobalt (≤ 5 %)

Co is an optional element. It contributes to increase the hardness of the martensite. The maximum amount is 5 % and, if added, an effective amount is about 4 to 5 %. However,

for practical reasons such as scrap handling there is no deliberate addition of Co. A preferred maximum content is 1 %.

Sulphur ($\leq 0.5\%$)

- 5 S contributes to improving the machinability of the steel. At higher sulphur contents there is a risk for red brittleness. Moreover, a high sulphur content may have a negative effect on the fatigue properties of the steel. The steel shall therefore contain $\leq 0.5\%$, preferably $\leq 0.03\%$.

10 **Phosphorus ($\leq 0.05\%$)**

P is an impurity element, which may cause temper brittleness. It is therefore limited to $\leq 0.05\%$.

Be, Bi, Se, Ca, Mg, O and REM (Rare Earth Metals)

- 15 These elements may be added to the steel in the claimed amounts in order to further improve the machinability, hot workability and/or weldability.

Boron ($\leq 0.6\%$)

- 20 Substantial amounts of boron may optionally be used to assist in the formation of the hard phase MX. Lower amounts of B may be used in order to increase the hardness of the steel. The amount is then limited to 0.01%, preferably $\leq 0.004\%$. Generally, no boron additions are made.

Ti, Zr, Al and Ta

- 25 These elements are carbide formers and may be present in the alloy for altering the composition of the hard phases. However, normally none of these elements are added.

Steel production

- 30 The tool steel can be produced by conventional gas atomizing. Normally the steel is subjected to hardening and tempering before being used.

Austenitizing may be performed at an austenitizing temperature (T_A) in the range of 950 - 1200 °C, typically 1000 - 1100 °C. A typical treatment is hardening at 1020 °C for 30 minutes, gas quenching and tempering at 550 °C for 2x2 hours. This results in a hardness of 59-61 HRC.

5

EXAMPLE

In this example, a steel according to the invention is compared to the known steel CPM®10V. Both steels were produced by powder metallurgy.

10 The basic steel composition was melted and subjected to gas atomization.

The steels thus obtained had the following composition (in wt. %):

		Inventive steel	CPM®10V
15	C	2.3	2.4
	Si	0.37	0.89
	Mn	0.37	0.45
	Cr	4.78	5.25
	Mo	3.6	1.26
20	V	8.0	9.85
	Mo/V	0.45	0.13

balance iron and impurities.

25 The steel were austenitized at 1100 °C for 30 minutes, hardened by gas quenching and tempering twice at 540 °C for 2 hours (2x2h) followed by air cooling. This results in a hardness of 63 HRC for both materials.

30 The composition of the matrix and the amount of primary MX at three different austenitizing temperatures were calculated in a Thermo-Calc simulation with the software version S-build-2532. The results are shown in Table 1.

Table 1.

Inventive steel	C	Si	Mn	Cr	Mo	V	MX (%)
1020 ^o C	0,43	0,43	0,42	4,6	1,54	0,39	15,8
1050 ^o C	0,47	0,42	0,42	4,6	1,65	0,48	15,5
1080 ^o C	0,52	0,42	0,42	4,7	1,76	0,59	15,2

CPM [®] 10V	C	Si	Mn	Cr	Mo	V	MX (%)
1020 ^o C	0,34	1	0,58	5,1	0,51	0,39	17,2
1050 ^o C	0,38	1	0,58	5,1	0,54	0,48	17
1080 ^o C	0,42	1	0,57	5,2	0,58	0,58	16,7

Table 1 reveals that the amount of hard phase in the inventive steel was only about 1.5 % lower than the amount in the comparative steel. In addition, the simulation indicates that the matrix contained significantly higher amounts of carbon and molybdenum than in the comparative steel. Hence, an improved tempering response, as well as a higher hardness, are to be expected from this simulation. This was also confirmed by the calculated values, which indicated a higher hardness for the inventive steel.

Moreover, the inventive steel is less sensitive to hardness decrease at high temperatures such that higher tempering temperatures can be used for removing retained austenite without impairing the hardness.

Surprisingly, it was found that the inventive steel also had a much better toughness. The un-notched impact energy in the transverse direction was 41 J as compared to 11 J for the comparative steel. The reason for this improvement is not fully clarified but it would appear that the low Si-content in combination with a high Mo-content improve the strength of the grain boundaries. Hence, the improved toughness of the inventive steel makes it possible to maintain a high hardness without problems with chipping and therefore improve the durability and lifetime of cold working tools.

Machinability testing

Machinability is a complex topic and may be assessed by a number of different tests for different characteristics. The main characteristics are: tool life, limiting rate of material removal, cutting forces, machined surface and chip breaking. In the present case the
5 machinability of the hot work tool steel was examined by drilling.

The turning machinability test was carried out on a NC Lathe Oerlikon Boehringer VDF 180C. The work-piece dimensions were $\varnothing 115 \times 600$ mm.

10 The V30-value was used to compare the machinability of the steels. The V30-value is specified as the cutting speed, which gives a flank wear of 0.3 mm after 30 minutes of turning. V30 is a standardized test method described in ISO 3685 from 1977. The turning operation was performed at three different cutting speeds until the flank wear of 0.3 mm. The flank wear was measured using light optical microscope. The time to reach
15 the 0.3 mm flank wear was noted. Using values of cutting speeds and the corresponding turning times, the Taylor double logarithmic graph - time versus cutting speed $V \times T^n = \text{constant}$ was plotted, from which it was possible to estimate the cutting speed for the required tool life of 30 minutes. The turning machinability test was carried out without cooling using a Coromant S4 SPGN 120304 hard metal insert, a feed of 0.126
20 mm/revolution and a cutting depth of 1.0 mm.

The inventive steel, which had a V30-value of 51 m/min, was found to perform better than the comparative steel, which only had a V30-value of 39m/min.

25 INDUSTRIAL APPLICABILITY

The cold work tool steel of the present invention is particular useful in applications requiring good wear resistance in combination with a high resistance chipping.

CLAIMS

1. A steel for cold working consisting of in weight % (wt.%):

C 2.2 - 2.4

Si 0.1 - 0.55

Mn 0.2 – 0.8

Cr 4.1 – 5.1

Mo 3.1 – 4.5

V 7.2 – 8.5

optionally one or more of

N 0.02 – 0.15

P ≤ 0.05

S ≤ 0.5

Cu ≤ 3

Co ≤ 5

Ni ≤ 3

W ≤ 2

Nb ≤ 2

Al ≤ 0.1

Ti ≤ 0.1

Zr ≤ 0.1

Ta ≤ 0.1

B ≤ 0.6

Be ≤ 0.2

Bi ≤ 0.2

Se ≤ 0.3

Ca 0.0003 – 0.009

O 0.003 – 0.01

Mg ≤ 0.01

$$\text{REM} \leq 0.2$$

balance Fe apart from impurities.

2. A steel according to claim 1 fulfilling at least one of the following requirements:

C	2.25 - 2.35
Si	0.2 - 0.5
Mn	0.2 – 0.6
Cr	4.5 – 5.0
Mo	3.5 – 3.7
V	7.7 – 8.3
N	0.02 – 0.08
P	≤ 0.03
S	≤ 0.03
Cu	0.02 - 2
Co	≤ 1
Ni	≤ 1
W	≤ 0.3
Nb	≤ 0.5
Al	≤ 0.06
Ti	≤ 0.01
Zr	≤ 0.01
Ta	≤ 0.01
B	≤ 0.01
Be	≤ 0.02
Se	≤ 0.03
Mg	≤ 0.001 .

3. A steel according to claim 1 or 2 fulfilling at least one of the following requirements:

C	2.26 - 2.34
Si	0.22 - 0.52
Mn	0.22 – 0.52
Cr	4.58 – 4.98
Mo	3.51 – 3.69
V	7.75 – 8.25
Cu	≤ 0.5
Ni	≤ 0.3 .

4. A steel according to claim 1, comprising:

C	2.2 - 2.4
Si	0.1 - 0.55
Mn	0.2 – 0.8
Cr	4.1 – 5.1
Mo	3.1 – 4.5
V	7.2 – 8.5
N	0.02 – 0.08

balance Fe apart from impurities.

5. A steel according to any one of claims 1 - 4 fulfilling at least one of the following requirements:

C	2.26 - 2.34
Si	0.22 - 0.52
Mn	0.22 – 0.52
Cr	4.58 – 4.98
Mo	3.51 – 3.69
V	7.75 – 8.25
N	0.03 - 0.06.

6. A steel according to any of one of claims 1 - 5 fulfilling all of the following requirements:

C	2.26 - 2.34
Si	0.22 - 0.52
Mn	0.22 – 0.52
Cr	4.58 – 4.98
Mo	3.51 – 3.69
V	7.75 – 8.25.

7. A steel according to any one of claims 1 - 6, wherein the content of Mo and V are adjusted to fulfil the requirement:

$$\text{Mo/V } 0.4 - 0.5.$$

8. A steel according to any one of claims 1 - 7 having an unnotched impact toughness in the LT direction at 25 °C of 30 - 80 J at a hardness of 60 HRC in the hardened and tempered condition.

9. A steel according to any one of claims 1 - 8 having a compression yield strength of at least 2400 MPa at 60 HRC.

10. A steel according to claim 7, wherein the content of Mo and V are adjusted to fulfil the requirement:

$$\text{Mo/V } 0.42 - 0.48.$$

11. A steel according to claim 8 having an unnotched impact toughness in the LT direction at 25 °C of 35-55 J, at a hardness of 60 HRC in the hardened and tempered condition.