

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
29 September 2011 (29.09.2011)

PCT

(10) International Publication Number
WO 2011/119363 A1

(51) International Patent Classification:
C09J 133/00 (2006.01)

(21) International Application Number:
PCT/US2011/028420

(22) International Filing Date:
15 March 2011 (15.03.2011)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
12/732,406 26 March 2010 (26.03.2010) US

(71) Applicant (for all designated States except US): **3M INNOVATIVE PROPERTIES COMPANY** [US/US]; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).

(72) Inventors: **CLAPPER, Jason, D.**; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US). **LEWANDOWSKI, Kevin, M.**; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US). **MA, Jingjing**; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US). **CHEN, Zhong**; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).

(74) Agents: **KOKKO, Kent, S.**, et al.; 3M Center Office of Intellectual Property Counsel Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii))

Published:

- with international search report (Art. 21(3))

(54) Title: PRESSURE-SENSITIVE ADHESIVES DERIVED FROM 2-ALKYL ALKANOLS

(57) Abstract: Pressure-sensitive adhesives are prepared from (meth)acrylate esters of 2-alkyl alkanols. The adhesives are characterized by exhibiting an overall balance of adhesive and cohesive characteristics and exceptional adhesion to low surface energy substrates.



WO 2011/119363 A1

Pressure-Sensitive Adhesives derived from 2-Alkyl Alkanols

5

Technical Field of the Invention

This invention relates to pressure-sensitive adhesives and tape articles prepared therefrom. The tapes are characterized by exhibiting an overall balance of adhesive and cohesive characteristics and exceptional adhesion to low surface energy substrates.

10

Background of the Invention

Pressure-sensitive tapes are virtually ubiquitous in the home and workplace. In its simplest configuration, a pressure-sensitive tape comprises an adhesive and a backing, and the overall construction is tacky at the use temperature and adheres to a variety of substrates using only moderate pressure to form the bond. In this fashion, pressure-sensitive tapes constitute a complete, self-contained bonding system.

According to the Pressure-Sensitive Tape Council, pressure-sensitive adhesives (PSAs) are known to possess properties including the following: (1) aggressive and permanent tack, (2) adherence with no more than finger pressure, (3) sufficient ability to hold onto an adherend, and (4) sufficient cohesive strength to be removed cleanly from the adherend. Materials that have been found to function well as PSAs include polymers designed and formulated to exhibit the requisite viscoelastic properties resulting in a desired balance of tack, peel adhesion, and shear holding power. PSAs are characterized by being normally tacky at room temperature (e.g., 20°C). PSAs do not embrace compositions merely because they are sticky or adhere to a surface.

These requirements are assessed generally by means of tests which are designed to individually measure tack, adhesion (peel strength), and cohesion (shear holding power), as noted in A.V. Pocius in Adhesion and Adhesives Technology: An Introduction, 2nd Ed., Hanser Gardner Publication, Cincinnati, OH, 2002. These measurements taken together constitute the balance of properties often used to characterize a PSA.

With broadened use of pressure-sensitive tapes over the years, performance requirements have become more demanding. Shear holding capability, for example, which originally was intended for applications supporting modest loads at room

temperature, has now increased substantially for many applications in terms of operating temperature and load. So-called high performance pressure-sensitive tapes are those capable of supporting loads at elevated temperatures for 10,000 minutes. Increased shear holding capability has generally been accomplished by crosslinking the PSA, although
5 considerable care must be exercised so that high levels of tack and adhesion are retained in order to retain the aforementioned balance of properties.

There are a wide variety of pressure sensitive adhesive (PSA) materials available today that include natural crude or synthetic rubbers, block copolymers, and acrylic ester based polymeric compositions. Acrylic ester PSAs in particular have been the focus of a
10 great deal of development over the last half century as the performance demands for PSAs have increased. Acrylic based PSAs may be closely tailored to provide a number of desired attributes such as elasticity, tackiness, transparency, resistance to oxidation and sunlight, etc., as well as have the necessary degree of adhesion and cohesion for demanding tape applications.

Central to all PSAs is a desired balance of adhesion and cohesion that is often achieved by optimizing the physical properties of the acrylic elastomer, such as glass transition temperature and modulus. For example, if the glass transition temperature (T_g) or modulus of the elastomer is too high and above the Dahlquist criterion for tack (storage modulus of 3×10^6 dynes/cm² at room temperature and oscillation frequency of 1 Hz), the
15 material will not be tacky and is not useful by itself as a PSA material. Often in this case, low molecular weight, high T_g resin polymers (tackifiers) or low molecular weight, low T_g polymers (plasticizers) are often used to modulate the T_g and modulus into an optimal PSA range.

Acrylic ester PSAs of today are typically an elastomeric polymer comprised primarily of a low T_g non-polar monomer, as well as a small amount of polar acrylic
25 monomer such as acrylic acid. Two widely used low T_g acrylates in PSAs are 2-ethylhexyl acrylate (EHA) and isooctyl acrylate (IOA), each providing an alkyl chain of eight carbon atoms (C_8). Longer or shorter alkyl chains have a number of disadvantages in terms of PSA performance. For example, shorter alkyl chain (e.g. butylacrylate- C_4) will
30 significantly increase both the T_g and modulus of the elastomer, possibly increasing the room temperature storage modulus above 3×10^6 dynes/cm². Alternatively, longer alkyl

chains (e.g. lauryl acrylate- C_{12}) can lead to crystalline groups within the polymer that will also significantly reduce its degree of tack.

Summary of the Invention

5 The adhesive compositions of this disclosure relate to the novel characteristics of Guerbet alkanol-derived (meth)acrylic monomers to their ability to form (co)polymers with unique and improved properties over comparable, commonly used PSA acrylate (co)polymers. These properties include a very low T_g , a low solubility parameter for acrylic polymers, and a low storage modulus creating a very conformable elastomer. This
10 combination of properties provides PSAs with enhanced adhesion to low surface energy substrates as compared to current acrylic PSA compositions.

 The adhesive (co)polymers of this disclosure comprise (meth)acrylate ester (co)polymers of 2-alkyl alkanols (Guerbet alkanols) wherein the carbon number molar average of said alkanols is 12 to 32 (C_{12} - C_{32}). The adhesive (co)polymers may further
15 comprise (meth)acrylic acid ester monomer of C_1 - C_{12} alkanols (" C_{1-12} alkanols"), wherein the carbon number molar average of the alkanols of all such (meth)acrylic acid ester monomers ((meth)acrylates of Guerbet alkanols and (meth)acrylic acid ester monomers of C_{1-12} alkanols) is 12 to 20 (C_{12} - C_{20}).

 In one aspect the pressure-sensitive adhesive comprises the interpolymerized
20 reaction product of: (a) at least one monomer selected from the group consisting of a (meth)acrylic acid ester monomers of 2-alkyl alkanols; optionally (b) (meth)acrylic acid ester monomers of C_1 - C_{12} alkanols, optionally (c) a acid functional ethylenically unsaturated monomers; optionally d) non-acid functional, ethylenically unsaturated polar monomers; optionally e) vinyl monomers, and optionally (f) non-acid functional,
25 ethylenically a multifunctional (meth)acrylates.

 As used herein the term "(meth)acrylic" or "(meth)acrylate" is inclusive of both acrylic and methacrylic (or acrylate and methacrylate).

 As used herein " C_1 - C_{12} alkanol (meth)acrylate" refers to (meth)acrylate esters of C_1 - C_{12} alkanols.

30 As used herein "Guerbet (meth)acrylate" or "2-alkyl (meth)acrylate" refers to (meth)acrylate esters of 2-alkyl alkanols.

The pressure-sensitive adhesives of the present invention may optionally comprise other monomers, crosslinkers, and other additives. In particular, the pressure sensitive adhesive may further comprise a tackifier.

The pressure-sensitive adhesives of this disclosure provide the desired balance of tack, peel adhesion, and shear holding power, and further conform to the Dahlquist criteria; i.e. the modulus of the adhesive at the application temperature, typically room temperature, is less than 3×10^6 dynes/cm at a frequency of 1 Hz.

Another embodiment of the present invention is a substrate coated with the pressure-sensitive adhesives of the present invention.

Detailed Description

The pressure-sensitive adhesives of the present invention are (meth)acrylate adhesives comprising at least one monomer derived from a 2-alkyl alkanol: i.e. a Guerbet alkanol. The pressure-sensitive adhesives may further comprise at least one (meth)acrylic acid ester of a C_1 - C_{12} alkanol, at least and one or more acid-functional monomers and optionally one or more non-acid functional polar monomers. The pressure-sensitive adhesives of the present invention optionally comprise other monomers which may be added to improve the physical properties of the adhesives, such as crosslinkers, and other additives such as tackifiers or plasticizers.

The molar carbon number average of said 2-alkyl alkanols of the Guerbet (meth)acrylates is 12 to 32 (C_{12} - C_{32}), preferably 12 to 20 (C_{12} - C_{20}). When the optional b) C_{1-12} alkanol (meth)acrylates are present, the carbon number molar average of the alkanols of the a) and b) (meth)acrylic acid ester is 12 to 20 (C_{12} - C_{20}). The carbon number molar average may be calculated by summing the number of moles of each alkanol (Guerbet and C_{1-12} alkanols) multiplied by the carbon number of each alkanol, and dividing the result by the total number of moles of alkanols:


$$\frac{\sum_{\alpha=\omega}[(\text{Moles of alkanol}) \times (\# \text{ carbon atoms for alkanol})]}{\text{# moles of alkanols } \alpha \text{ to } \omega}$$

The (meth)acrylic acid ester monomer of 2-alkyl alkanols are derived from C_{12} - C_{32} Guerbet alkanols, preferably C_{12} - C_{20} Guerbet alkanols. These Guerbet alkanols may be obtained by base-catalyzed self-condensation of linear and/or branched alkanols

containing 4 to 14 and preferably 6 to 12 carbon atoms. Primary or secondary alkanols may be used in the preparation of Guerbet alkanols.

It is known in the art that Guerbet alkanols may be formed from the same or different alkanols i.e. a homo or hetero system. That is, a Guerbet alkanol is the condensation product of two alkanol molecules joined at the *beta* carbon of the alkanol which has retained the hydroxyl functionality; i.e. 2-alkyl alkanols. The resultant product is therefore a branched primary alkanol containing a single hydroxyl group. It is possible to use mixtures of starting materials in the Guerbet reaction and condense them into mixtures of alkanol products. It is also possible to obtain products which are Guerbet alkanols from a short chained alkanol. It is desired for reasons of polarity, T_g and modulus that Guerbet alkanols having a molar carbon number average between 12-32 be used. An overview of Guerbet alkanols was published by A. J. O'Lennick in Soap Cosm. Chem. Spec. (April) 52 (1987). Reference may also be made to U.S. 6,419,797 (Sherf et al.) for method to produce Guerbet alkanols.

The (meth)acrylate ester monomer derived from the Guerbet alkanols is of the formula:




Wherein

$\text{R}^{\text{Guerbet}}$ is derived from a C_{12} - C_{32} 2-alkyl alkanol, i.e. an alkyl groups branched at the 2 position; and

R^3 is H or CH_3 .

Preferably, the (meth)acrylate ester monomer derived from the Guerbet alkanols is of the formula:



wherein

R^1 and R^2 are each independently C_4 to C_{14} saturated, and branched or linear alkyl; and R^3 is H or CH_3 .

The adhesive compositions may comprise Guerbet (meth)acrylate homopolymers, In many preferred embodiments, the adhesive copolymer comprises 51-99 parts by weight of Guerbet (meth)acrylates, relative to 100 parts total monomer.

Preferably, the Guerbet alkanol is derived from linear alkanols, i.e. R^1 and R^2 are linear alkyl groups. It has been found that such (meth)acrylate esters of “linear Guerbet alkanols” provide a lower T_g and storage modulus compared to monomers where R^1 and R^2 are branched. The T_g of the resulting adhesive (co)polymers is $\leq -20^\circ\text{C}$, preferably $\leq -30^\circ\text{C}$, most preferably $\leq -40^\circ\text{C}$

The pressure-sensitive adhesive copolymer may further comprise interpolymerized monomer units of C_1 - C_{12} (meth)acrylate ester monomers. Examples of monomers suitable for use as the C_1 - C_{12} (meth)acrylate ester monomer include the esters of either acrylic acid or methacrylic acid with non-tertiary alkanols such as ethanol, 1-propanol, 2-propanol, 1-butanol, 2-butanol, 1-pentanol, 2-pentanol, 3-pentanol, 2-methyl-1-butanol, 3-methyl-1-butanol, 1-hexanol, 2-hexanol, 2-methyl-1-pentanol, 3-methyl-1-pentanol, 2-ethyl-1-butanol, 3,5,5-trimethyl-1-hexanol, 3-heptanol, 1-octanol, 2-octanol, isooctylalcohol, 2-ethyl-1-hexanol, 1-decanol, 2-propylheptanol, 1-dodecanol, 1-tridecanol, 1-tetradecanol, citronellol, dihydrocitronellol, and the like. In some embodiments, the preferred (meth)acrylate ester monomer is the ester of (meth)acrylic acid with butyl alcohol or isooctyl alcohol, or a combination thereof, although combinations of two or more different (meth)acrylate ester monomer are suitable.

In some embodiments, this disclosure provides an adhesive composition derived from renewable resources. In particular, the present invention provides an adhesive composition derived, in part, from plant materials. In some embodiments, the present invention further provides an adhesive article, wherein the substrate or backing is also derived from renewable resources. The increase in the price of oil, and concomitant petroleum-derived products, has led to volatile prices and supply for many adhesive products. It is desirable to replace all or part of the petroleum-based feedstocks with those derived from renewable sources, such as plants, as such materials become relatively cheaper, and are therefore both economically and socially beneficial. Therefore, the need for such plant-derived materials has become increasingly significant. Many of the (meth)acrylate monomers used herein may be derived from renewable resources. In some embodiments, the preferred (meth)acrylate ester monomer is the ester of (meth)acrylic

acid with an alkanol derived from a renewable source, such as 2-octanol, citronellol, dihydrocitronellol and Guerbet alkanols derived from renewable materials.

In some embodiments it is desirable for the C₁-C₁₂ (meth)acrylate ester monomer to include a high T_g monomer, have a T_g of at least 25°C, and preferably at least 50°C.

5 Examples of suitable monomers useful in the present invention include, but are not limited to, t-butyl acrylate, methyl methacrylate, ethyl methacrylate, isopropyl methacrylate, n-butyl methacrylate, isobutyl methacrylate, s-butyl methacrylate, t-butyl methacrylate, stearyl methacrylate, phenyl methacrylate, cyclohexyl methacrylate, isobornyl acrylate, isobornyl methacrylate, benzyl methacrylate, 3,3,5-trimethylcyclohexyl acrylate, cyclohexyl acrylate, N-octyl acrylamide, and propyl methacrylate or combinations.

If present, the C₁-C₁₂ (meth)acrylate ester monomer is present in an amount of 1 to 49 parts by weight, based on 100 parts total monomers. Most preferably C₁-C₁₂ (meth)acrylate ester monomer is present in an amount of 5 to 45 parts by weight based on 100 parts total monomers. When high T_g monomers are included, the copolymer may include up to 50 parts by weight, preferably up to 10 to 20 parts by weight relative to 100 parts by weight of C₁-C₁₂ (meth)acrylate ester monomer component.

The pressure-sensitive adhesive copolymer may further comprise an acid functional monomer, where the acid functional group may be an acid *per se*, such as a carboxylic acid, or a portion may be salt thereof, such as an alkali metal carboxylate.

20 Useful acid functional monomers include, but are not limited to, those selected from ethylenically unsaturated carboxylic acids, ethylenically unsaturated sulfonic acids, ethylenically unsaturated phosphonic acids, and mixtures thereof. Examples of such compounds include those selected from acrylic acid, methacrylic acid, itaconic acid, fumaric acid, crotonic acid, citraconic acid, maleic acid, oleic acid, β-carboxyethyl (meth)acrylate, 2-sulfoethyl methacrylate, styrene sulfonic acid, 2-acrylamido-2-methylpropanesulfonic acid, vinylphosphonic acid, and mixtures thereof.

25 Due to their availability, acid functional monomers of the acid functional copolymer are generally selected from ethylenically unsaturated carboxylic acids, i.e. (meth)acrylic acids. When even stronger acids are desired, acidic monomers include the ethylenically unsaturated sulfonic acids and ethylenically unsaturated phosphonic acids. The acid functional monomer is generally used in amounts of 0 to 15, preferably 0.5 to 15, most preferably 0.5 to 5, parts by weight, based on 100 parts by weight total monomer.

The pressure-sensitive adhesive copolymer may further comprise polar monomers. The polar monomers useful in preparing the copolymer are both somewhat oil soluble and water soluble, resulting in a distribution of the polar monomer between the aqueous and oil phases in an emulsion polymerization. As used herein the term "polar monomers" are
5 exclusive of acid functional and ketone monomers.

Representative examples of suitable polar monomers include but are not limited to 2-hydroxyethyl (meth)acrylate; N-vinylpyrrolidone; N-vinylcaprolactam; acrylamide; mono- or di-N-alkyl substituted acrylamide; t-butyl acrylamide; dimethylaminoethyl acrylamide; N-octyl acrylamide; poly(alkoxyalkyl) (meth)acrylates including 2-(2-
10 ethoxyethoxy)ethyl (meth)acrylate, 2-ethoxyethyl (meth)acrylate, 2-methoxyethoxyethyl (meth)acrylate, 2-methoxyethyl methacrylate, polyethylene glycol mono(meth)acrylates; alkyl vinyl ethers, including vinyl methyl ether; and mixtures thereof. Preferred polar monomers include those selected from the group consisting of 2-hydroxyethyl (meth)acrylate and N-vinylpyrrolidinone. The polar monomer may be present in amounts
15 of 0 to 10 parts by weight, preferably 0.5 to 10 parts by weight, based on 100 parts by weight total monomer.

The pressure-sensitive adhesive copolymer may further comprise other vinyl monomers. When used, vinyl monomers useful in the (meth)acrylate polymer include vinyl esters (e.g., vinyl acetate and vinyl propionate), styrene, substituted styrene (e.g., α -
20 methyl styrene), vinyl halide, and mixtures thereof. As used herein vinyl monomers are exclusive of acid functional monomers, acrylate ester monomers and polar monomers. Such vinyl monomers are generally used at 0 to 5 parts by weight, preferably 1 to 5 parts by weight, based on 100 parts by weight total monomer.

There are two major crosslinking mechanisms for acrylic adhesives: free-radical
25 copolymerization of multifunctional ethylenically unsaturated groups with the other monomers, and covalent or ionic crosslinking through the functional monomers, such as acrylic acid. Another method is the use of UV crosslinkers, such as copolymerizable benzophenones or post-added photocrosslinkers, such as multifunctional benzophenones and triazines. In the past, a variety of different materials have been used as crosslinking
30 agents, e.g., polyfunctional acrylates, acetophenones, benzophenones, and triazines. Crosslinking may also be achieved using high energy electromagnetic radiation such as gamma or e-beam radiation. In this case, no additional crosslinker may be required.

In order to increase cohesive strength of the coated adhesive composition, a multifunctional (meth)acrylate may be incorporated into the blend of polymerizable monomers. Multifunctional acrylates are particularly useful for emulsion or syrup polymerization. Examples of useful multifunctional (meth)acrylate include, but are not limited to, di(meth)acrylates, tri(meth)acrylates, and tetra(meth)acrylates, such as 1,6-hexanediol di(meth)acrylate, poly(ethylene glycol) di(meth)acrylates, polybutadiene di(meth)acrylate, polyurethane di(meth)acrylates, and propoxylated glycerin tri(meth)acrylate, and mixtures thereof. The amount and identity of multifunctional (meth)acrylate is tailored depending upon application of the adhesive composition. Typically, the multifunctional (meth)acrylate is present in amounts less than 5 parts based on total dry weight of adhesive composition. More specifically, the crosslinker may be present in amounts from 0.01 to 5 parts, preferably 0.05 to 1 parts, based on 100 parts total monomers of the adhesive composition.

In some embodiments, the copolymer may comprise:

- a) up to 100, preferably 51 to 99, more preferably 55 to 95 parts by weight of an (meth)acrylic acid ester monomer of 2-alkyl alkanols, with a molar carbon number average of 12 to 32;
 - b) 0 to 49, preferably 1 to 45, more preferably 5 to 45, parts by weight of an (meth)acrylic acid ester of a C₁-C₁₂ alkanol;
 - c) 0 to 15, preferably 0.1 to 10, most preferably 0.5 to 5, parts by weight of an acid functional ethylenically unsaturated monomer;
 - d) 0 to 10, preferably 0.5 to 10, parts by weight of a non-acid functional, ethylenically unsaturated polar monomer;
 - e) 0 to 5, preferably 1 to 5 parts by weight, of a vinyl monomer; and
 - f) 0 to 5, preferably 0.01 to 5, most preferably 0.05 to 1 parts of a multifunctional (meth)acrylate;
- based on 100 parts by weight total monomer.

The adhesive (co)polymers herein may be prepared by any conventional free radical polymerization method, including solution, radiation, bulk, dispersion, emulsion, and suspension processes. For optical applications, solution, UV and bulk processes are preferred. Other processes may introduce birefringence or foreign materials that may

affect optic properties. The resulting adhesive (co)polymers may be random or block (co)polymers.

The adhesive copolymers may be prepared via suspension polymerizations as disclosed in U.S. 3,691,140 (Silver); 4,166,152 (Baker et al.); 4,636,432 (Shibano et al);
5 4,656,218 (Kinoshita); and 5,045,569 (Delgado).

Water-soluble and oil-soluble initiators useful in preparing the (meth)acrylate adhesive copolymers used in the present invention are initiators that, on exposure to heat, generate free-radicals which initiate (co)polymerization of the monomer mixture. Water-soluble initiators are preferred for preparing the (meth)acrylate polymers by emulsion
10 polymerization. Suitable water-soluble initiators include but are not limited to those selected from the group consisting of potassium persulfate, ammonium persulfate, sodium persulfate, and mixtures thereof; oxidation-reduction initiators such as the reaction product of the above-mentioned persulfates and reducing agents such as those selected from the group consisting of sodium metabisulfite and sodium bisulfite; and 4,4'-azobis(4-
15 cyanopentanoic acid) and its soluble salts (e.g., sodium, potassium). The preferred water-soluble initiator is potassium persulfate. Suitable oil-soluble initiators include but are not limited to those selected from the group consisting of azo compounds such as VAZO™ 64 (2,2'-azobis(isobutyronitrile)) and VAZO™ 52 (2,2'-azobis(2,4-dimethylpentanenitrile)), both available from E.I. du Pont de Nemours Co., peroxides such as benzoyl peroxide and
20 lauroyl peroxide, and mixtures thereof. The preferred oil-soluble thermal initiator is (2,2'-azobis(isobutyronitrile)). When used, initiators may comprise from about 0.05 to about 1 part by weight, preferably about 0.1 to about 0.5 part by weight based on 100 parts by weight of monomer components in the pressure-sensitive adhesive.

Polymerization via emulsion techniques may require the presence of an emulsifier
25 (which may also be called an emulsifying agent or a surfactant). Useful emulsifiers for the present invention include those selected from the group consisting of anionic surfactants, cationic surfactants, nonionic surfactants, and mixtures thereof.

Preferably, the emulsion polymerization is carried out in the presence of anionic surfactant(s). A useful range of surfactant concentration is from about 0.5 to about 8
30 weight percent, preferably from about 1 to about 5 weight percent, based on the total weight of all monomers of the emulsion pressure-sensitive adhesive.

Alternatively, the copolymers can be polymerized by techniques including, but not limited to, the conventional techniques of solvent polymerization, dispersion polymerization, and solventless bulk polymerization. The monomer mixture may comprise a polymerization initiator, especially a thermal initiator or a photoinitiator of a type and in an amount effective to polymerize the comonomers, as previously described.

The copolymerizable mixture may optionally further comprise chain transfer agents to control the molecular weight of the resultant polymer. Examples of useful chain transfer agents include but are not limited to those selected from the group consisting of carbon tetrabromide, alcohols, mercaptans, and mixtures thereof. When present, the preferred chain transfer agents are isooctylthioglycolate and carbon tetrabromide. The polymerizable mixture may further comprise up to about 0.5 parts by weight of a chain transfer agent, typically about 0.01 to about 0.5 parts by weight, if used, preferably about 0.05 parts by weight to about 0.2 parts by weight, based upon 100 parts by weight of the total monomer mixture.

A typical solution polymerization method is carried out by adding the monomers, a suitable solvent, and an optional chain transfer agent to a reaction vessel, adding a free radical initiator, purging with nitrogen, and maintaining the reaction vessel at an elevated temperature, typically in the range of about 40 to 100°C until the reaction is completed, typically in about 1 to 20 hours, depending upon the batch size and temperature.

Examples of the solvent are methanol, tetrahydrofuran, ethanol, isopropanol, acetone, methyl ethyl ketone, methyl acetate, ethyl acetate, toluene, xylene, and an ethylene glycol alkyl ether. Those solvents can be used alone or as mixtures thereof.

In a typical photopolymerization method, a monomer mixture may be irradiated with ultraviolet (UV) rays in the presence of a photopolymerization initiator (i.e., photoinitiators). Preferred photoinitiators are those available under the trade designations IRGACURE™ and DAROCUR™ from Ciba Speciality Chemical Corp., Tarrytown, NY and include 1-hydroxy cyclohexyl phenyl ketone (IRGACURE™ 184), 2,2-dimethoxy-1,2-diphenylethan-1-one (IRGACURE 651), *bis*(2,4,6-trimethylbenzoyl)phenylphosphineoxide (IRGACURE™ 819), 1-[4-(2-hydroxyethoxy)phenyl]-2-hydroxy-2-methyl-1-propan-1-one (IRGACURE™ 2959), 2-benzyl-2-dimethylamino-1-(4-morpholinophenyl)butanone (IRGACURE™ 369), 2-methyl-1-[4-(methylthio)phenyl]-2-morpholinopropan-1-one (IRGACURE™ 907), and 2-

hydroxy-2-methyl-1-phenyl propan-1-one (DAROCUR™ 1173). Particularly preferred photoinitiators are IRGACURE™ 819, 651, 184 and 2959.

Solventless polymerization methods, such as the continuous free radical polymerization method described in U.S. Pat. Nos. 4,619,979 and 4,843,134 (Kotnour et al.); the essentially adiabatic polymerization methods using a batch reactor described in U.S. Pat. No. 5,637,646 (Ellis); and, the methods described for polymerizing packaged pre-adhesive compositions described in U.S. Pat. No. 5,804,610 (Hamer et al.) may also be utilized to prepare the polymers.

The pressure-sensitive adhesives may also contain one or more conventional additives. Preferred additives include tackifiers, plasticizers, dyes, antioxidants, and UV stabilizers. Such additives can be used if they do not affect the superior properties of the emulsion pressure-sensitive adhesives.

Conventional acrylic adhesives do not adhere well to certain substrates, such as certain types of automotive paints and low energy olefinic surfaces. Efforts have been made to improve the adhesion of acrylic adhesives, i.e., develop more aggressive tack, to these types of surfaces; tackifying the base acrylic polymer is commonly practiced. Various types of tackifiers include phenol modified terpenes, hydrocarbon resins such as polyvinyl cyclohexane and poly(t-butyl styrene), and rosin esters such as glycerol esters of rosin and pentaerythritol esters of rosin.

Various types of tackifiers include phenol modified terpenes and rosin esters such as glycerol esters of rosin and pentaerythritol esters of rosin that are available under the trade names Nuroz™, Nutac™ (Newport Industries), Permalyn™, Staybelite™, Foral™ (Eastman). Also available are hydrocarbon resin tackifiers that typically come from C5 and C9 monomers by products of naphtha cracking and are available under the trade names Piccotac™, Eastotac™, Regalrez™, Regalite™ (Eastman), Arkon™ (Arakawa), Norsolene™, Wintack™ (Cray Valley), Nevtack, LX (Neville Chemical Co.), Hikotack™, Hikorez™ (Kolon Chemical), Novares™ (Rutgers N.V.), Quintone™ (Zeon), Escorez™ (Exxonmobile Chemical), Nures™, and H-Rez™ (Newport Industries).

Due to the high solubility parameter of most conventional pressure-sensitive acrylic adhesives and the presence of specific potential interactions between these adhesives and many tackifiers, a limited selection of tackifiers is available to the formulator. As a class, hydrocarbon-based tackifiers, and especially hydrogenated

hydrocarbon resins, are typically unsuitable for use in polar acrylic adhesives formulations due to their nonpolar character.

Rosin acid based tackifiers and selected phenol-modified terpene and alpha-pinene based resins perform well in a variety of conventional acrylic pressure-sensitive adhesives. However, some problems are still associated with the use of this limited range of tackifiers in such acrylic adhesives. Tackified acrylic pressure-sensitive adhesive formulations are often discolored or yellow. The yellow appearance of these tackified acrylic pressure-sensitive adhesives is a direct result of the distinct yellow tinge inherent in many of these tackifiers. Upon aging and exposure to light, this discoloration can become even more pronounced, even with lighter colored grades of resin. Acrylic adhesives without tackifiers typically have excellent aging properties.

Conventional tackified acrylic pressure-sensitive adhesives can also appear cloudy, demonstrating a loss in the characteristic transparency found in many conventional acrylate pressure-sensitive adhesive compositions. The cloudiness is an indication of limited or incomplete compatibility of the tackifier and the acrylic polymers. The reduced compatibility can lead to a degradation of adhesive properties on aging, as evidenced by a loss of tack or reduced peel adhesion. In some cases, the addition of a tackifier to an adhesive composition having acrylic monomers, polymers, oligomers, and any mixture thereof, can be clear and appear to be compatible. However, after removing the solvent, curing the adhesive, or on aging, the adhesive can become cloudy, indicating some incompatibility between the tackifier and acrylic base polymer.

In addition to these losses in clarity and stability of tackified acrylic adhesives, other deleterious effects can be observed when tackifiers are present during bulk acrylic polymerization reactions. Depending on the structure of the tackifier, undesirable effects of adding a tackifier include the inhibition or retardation of the polymerization reaction and/or the alteration of the final polymer structure if the tackifier acts as a chain-transfer or chain-terminating agent. Such effects can adversely influence the performance and stability of acrylates polymerized in the presence of these tackifiers. Chain termination can also result in undesirably high residual volatile materials.

In many embodiments, the present disclosure provides tackified PSA compositions that overcome problems noted in the art. The tackifier is preferably selected from a material that is essentially free of any ethylenically or acetylenically unsaturated bonds.

The tackifier includes, but is not limited to, hydrogenated rosin resins, hydrogenated and esterified rosin resins, hydrogenated terpene resins, aliphatic petroleum resins, aromatic petroleum resins, alicyclic petroleum resins obtained by hydrogenating aromatic petroleum resins, and the like. Preferably, the tackifier used is selected from hydrogenated
5 C₉ petroleum resins such as but not limited to Regalrez™ tackifiers (Eastman) or Arkon™ (Arakawa) tackifiers. Such “hydrophobic tackifiers”, may be used in amounts of 20 to 150 parts, preferably 50 to 100 parts, of said tackifier, relative to 100 parts of said (meth)acrylate ester (co)polymer

The adhesives of the present invention may be coated upon a variety of flexible
10 and inflexible backing materials using conventional coating techniques to produce adhesive-coated materials. Flexible substrates are defined herein as any material which is conventionally utilized as a tape backing or may be of any other flexible material. Examples include, but are not limited to plastic films such as polypropylene, polyethylene, polyvinyl chloride, polyester (polyethylene terephthalate), polycarbonate,
15 polymethyl(meth)acrylate (PMMA), cellulose acetate, cellulose triacetate, and ethyl cellulose. Foam backings may be used. Examples of inflexible substrates include, but are not limited to, metal, metallized polymeric film, indium tin oxide coated glass and polyester, PMMA plate, polycarbonate plate, glass, or ceramic sheet material. The adhesive-coated sheet materials may take the form of any article conventionally known to
20 be utilized with adhesive compositions such as labels, tapes, signs, covers, marking indices, display components, touch panels, and the like. Flexible backing materials having microreplicated surfaces are also contemplated.

The above-described compositions are coated on a substrate using conventional coating techniques modified as appropriate to the particular substrate. For example, these
25 compositions can be applied to a variety of solid substrates by methods such as roller coating, flow coating, dip coating, spin coating, spray coating knife coating, and die coating. These various methods of coating allow the compositions to be placed on the substrate at variable thicknesses thus allowing a wider range of use of the compositions. Coating thicknesses may vary, but coating thicknesses of 2-500 microns (dry thickness),
30 preferably about 25 to 250 microns, are contemplated.

The adhesives of the present disclosure are particularly useful for forming strong bonds to low surface energy (LSE) substrates. As used herein, low surface energy

substrates are those having a surface energy of less than about 45 dynes per centimeter, more typically less than about 40 dynes per centimeter, and most typically less than about 35 dynes per centimeter. Included among such materials are polypropylene, polyethylene (e.g., high density polyethylene or HDPE), polystyrene and poly(methyl methacrylate) (PMMA). Other substrates may also have properties of low surface energy due to a residue, such as an oil residue or a film such as a paint, being on the surface of the substrate. However, even though the present adhesive bonds well to low surface energy surfaces, the invention is not limited to being bonded to low surface energy substrates, as it has been found that the inventive adhesive can also bond well to higher surface energy substrates such as, for example, other plastics, ceramics (e.g., glass), metals.

The substrate is selected depending on the particular application in which it is to be used. For example, the adhesive can be applied to sheeting products, (e.g., decorative graphics and reflective products), label stock, and tape backings. Additionally, the adhesive may be applied directly onto a substrate such as an automotive panel, or a glass window so that another substrate or object can be attached to the panel or window.

The adhesive can also be provided in the form of a pressure-sensitive adhesive transfer tape in which at least one layer of the adhesive is disposed on a release liner for application to a permanent substrate at a later time. The adhesive can also be provided as a single coated or double coated tape in which the adhesive is disposed on a permanent backing. Backings can be made from plastics (e.g., polypropylene, including biaxially oriented polypropylene, vinyl, polyethylene, polyester such as polyethylene terephthalate), nonwovens (e.g., papers, cloths, nonwoven scrims), metal foils, foams (e.g., polyacrylic, polyethylene, polyurethane, neoprene), and the like. Foams are commercially available from various suppliers such as 3M Co., Voltek, Sekisui, and others. The foam may be formed as a coextruded sheet with the adhesive on one or both sides of the foam, or the adhesive may be laminated to it. When the adhesive is laminated to a foam, it may be desirable to treat the surface to improve the adhesion of the adhesive to the foam or to any of the other types of backings. Such treatments are typically selected based on the nature of the materials of the adhesive and of the foam or backing and include primers and surface modifications (e.g., corona treatment, surface abrasion). Additional tape constructions include those described in U.S. 5,602,221 (Bennett et al.), incorporated herein by reference.

For a single-sided tape, the side of the backing surface opposite that where the adhesive is disposed is typically coated with a suitable release material. Release materials are known and include materials such as, for example, silicone, polyethylene, polycarbamate, polyacrylics, and the like. For double coated tapes, another layer of adhesive is disposed on the backing surface opposite that where the adhesive of the invention is disposed. The other layer of adhesive can be different from the adhesive of the invention, e.g., a conventional acrylic PSA, or it can be the same adhesive as the invention, with the same or a different formulation. Double coated tapes are typically carried on a release liner.

Experimental

The following monomers were obtained and used without further purification. Monomers CM 7 and Guerbet Monomers (GM 1-11) were synthesized according to the following Preparatory Examples.

Table 1: Monomers

Monomer designation	Description
CM 1	Isooctyl acrylate (IOA, 3M)
CM 2	2-ethylhexyl acrylate (EHA, Aldrich)
CM 3	Isodecyl acrylate (IDA, Aldrich)
CM 4	2-propylheptyl acrylate (PHA, BASF)
CM 5	lauryl acrylate (LA, Sartomer)
CM 6	lauryl methacrylate (LMA, Sartomer)
CM 7	Acrylate of Exxal 13, a tridecyl alkanol (Exxon)
GM 1	2-butyl-1-octyl acrylate
GM 2	Mixture of: 2-butyl-1-octyl acrylate 2-butyl-1-decyl acrylate 2-hexyl-1-octyl acrylate 2-hexyl-1-decyl acrylate
GM 3	2-hexyl-1-decyl acrylate
GM 4	Mixture of: 2-hexyl-1-decyl acrylate 2-octyl-1-decyl acrylate 2-hexyl-1-dodecyl acrylate 2-octyl-1-dodecyl acrylate
GM 5	2-octyl-1-dodecyl acrylate
GM 6	2-decyl-1-tetradecyl acrylate
GM 7	2-dodecyl-1-hexadecyl acrylate
GM 8	2-tetradecyl-1-octadecyl acrylate
GM 9	Acrylate of Fineoxocol FO180, a C ₁₈ alkanol (Nissan)
GM 10	Acrylate of Fineoxocol FO180N, a C ₁₈ alkanol (Nissan)
GM 11	2-octyl-1-dodecyl methacrylate

Test Methods

Test method 1: Dynamic scanning calorimetric analysis of monomers and homopolymer films

Approximately 10 mg of each of CM 1-7 and GM 1-11 were placed in individual standard aluminum DSC pans (TA Instruments T080715) and placed in the autosampler of a dynamic scanning calorimeter (DSC, TA Instruments). For each sample, pans were individually placed on one of the differential posts in the DSC's enclosed cell along with an empty reference pan on the opposite post. Temperature was raised to 55 °C and held for 10 minutes to thermally anneal the sample which was then cycled between -95 °C and 55 °C twice at 3°C/min. Transitions such as the crystallinity, temperature (T_c), melting

temperature (T_m), and glass transition temperature (T_g) were identified in the scanning profile of heat flow vs. temperature. Typically, crystallization and melting transitions show up as positive and negative heat flow peaks as the sample is cooled and heated, and the latent heat is given off or absorbed, respectively. Conversely a glass transition is generally represented by a shift in the profile slope upon heating as the heat capacity of the sample after the transition is altered. The glass transition temperature was recorded at the inflection point of the curve associated with this shift in heat flow profile.

DSC analysis described above was repeated for homopolymers of each of the monomers. To generate homopolymer samples of the acrylic monomers listed in the preparatory examples above, 5 g of acrylic monomers CM 1-5, and 7, and GM 1-10 from Table 1 were each mixed with 0.05 wt % Irgacure™ 651 (Ciba) for 1 hour in an amber vial with magnetic stirring. Samples were cured in a clamped mold using a 2 mm thick silicone spacer cavity between release liners and glass plates. The mold was placed in a vertical position so that only one edge of the mold was in contact with air and then cured for 10 minutes on each glass face side with UV irradiation (365nm, ~5 mW/cm²). Post cure, the glass plates and silicone spacers were removed to leave the homopolymer film between release liners.

To generate homopolymer samples of the methacrylate monomers, 50 g of monomers CM 6 and GM 11 were each mixed with 50g of toluene and 0.2 g of thermal initiator 2,2'-azobis(2-methyl-butanenitrile) (Vazo™ 67, DuPont), and 0.01g of isooctyl thioglycolate (IOTG, Aldrich) for 10 minutes in an amber bottle with magnetic stirring. Nitrogen was bubbled through this solution for 30 minutes, the bottle was sealed, and placed in a laundrometer for 24 hours at 70 °C. Post polymerization, material was drained from the bottle into aluminum tins and placed in an oven at 70 °C, followed by 24 hours under vacuum to remove all solvent.

Test Method 2: Dynamic mechanical analysis of homopolymer films

Dynamic mechanical analysis (DMA) of each of the homopolymers generated for Test Method 1 was accomplished using an AR2000 parallel plate rheometer (TA Instruments) to characterize the physical properties of each sample as a function of temperature. For each sample, approximately 0.5 g of homopolymer material was centered between 8 mm diameter parallel plates of the rheometer and compressed until the

edges of the sample were uniform with the edges of the top and bottom plates. The furnace doors that surround the parallel plates and shafts of the rheometer were shut and the temperature was raised to 140 °C and held for 5 minutes. The temperature was then ramped from 140 °C to -80 °C at 3 °C/min while the parallel plates were oscillated at a frequency of 1 Hz and a constant % strain of 0.4%. While many physical parameters of the material are recorded during the temperature ramp, storage modulus (G'), loss modulus (G''), and tan delta are of primary importance in the characterization of the homopolymers of this invention.

The glass transition temperature, T_g , of the adhesive composition can be measured by first determining its storage (G') and loss shear moduli (G''). The ratio of G''/G' , a unit less parameter typically denoted “tan delta”, is plotted versus temperature. The maximum point (point where the slope is zero) in the transition region between the glassy region and the rubbery region of the tan delta curve, if well defined, determines the T_g of the adhesive composition at that particular frequency.

For each of the homopolymer films generated, storage modulus was recorded at room temperature (25 °C), T_g was recorded at the peak of the tan delta curve, and the width of the tan delta peak was quantified by taking the peak width at a fixed height of approximately half of the peak intensity (FHPW).

Test Method 3: Aging of adhesive formulated films

Cured adhesive films were aged under two conditions. A sample adhesive film of each formulation was stored at constant temperature (25 °C) and constant relative humidity (50%) for 48 hours after which visual characterization, as well as peel and shear adhesive tests were conducted. A second sample of each formulation was placed in aluminum bins in an oven at 70 °C for one week before visual characterization, peel, and shear testing.

Test Method 4: Visual analysis of adhesive formulated films

Cured adhesive films were characterized for clarity by visually classifying the adhesive film as clear, translucent (trans) or opaque.

Test Method 5: 180° Peel adhesion strength test

Peel adhesion is the force required to remove a coated flexible sheet material from a test panel measured at a specific angle and rate of removal. In the examples of this invention, the peel force is expressed in Newtons per width of coated sheet (Newtons/dm). For each test, a 12.7 mm width of the adhesive coated sheet material approximately 15 cm long was cut and the release layer peeled away from the coated adhesive. The adhesive strip was then applied to the clean face of a stainless steel test panel. A heavy rubber roller was used to apply the strip. The free end of the coated strip was doubled back so that the angel of removal was 180 degrees. The free end was attached to the horizontal arm of the adhesion tester scale. The stainless steel plate was then affixed to the platform of the instrument which is mechanized to move at a controlled rate (30.5 cm/min) away from the scale. The peel test was started soon after the adhesive was applied to the substrate without allowing for an induction time for adhesion to build. The scale reading in ounces was read during the test as an average of both the peak and minimum forces during the peel. Three peel tests were run for each sample and averaged to yield the peel adhesion value.

Peel adhesion was also measured for each sample using the above procedure on test panels of high density polyethylene (HDPE, International Plastics- Edina, MN).

Test Method 6: High temperature shear strength

Shear strength is measured in terms of the time required to pull a defined area of adhesive coated backing material from a stainless steel test panel under the stress of a constant or static load parallel to the test panel.

Shear tests were conducted using adhesive coated PET material with approximately a 0.08 mm thick adhesive coating. Cut adhesive strips were applied to a clean stainless steel panel such that a 12.7 mm by 25.4 mm portion of each strip was in firm contact with the panel and one end portion of each strip was free. The panel with adhesive strip was held in a rack such that the panel forms a 180 degree angle with the extended free end which is then tensioned by applying a 500 gram hanging weight. The rack was enclosed in a 70 °C oven and the time elapsed for each tape example to separate from the test panel is recorded as the shear strength in minutes. Two shear tests were performed for each sample adhesive and the shear strength averaged.

Test Method 7:90° Angle Peel Adhesion Strength Test.

Evaluation of peel adhesion strength at an angle of 90° was performed as described in the ASTM International standard, D3330, Method F, with a 1.3 cm x 20 cm (1/2 in. x 8 in.) test specimen using an IMASS SP-200 slip/peel tester (available from IMASS, Inc., Accord, MA) at a peel rate of 305 mm/minute (12 inches/minute). The samples were adhered to the test panels by rolling down the tapes with a 2.0 kg (4.5 lb.) rubber roller using 4 passes. The peel tests were performed after a 24 hour dwell time in a controlled environment room on the test panel, unless otherwise stated. The average peel adhesion force required to remove the tape from the panel was measured in ounces and is expressed in Newtons/decimeter (N/dm), based on 3 samples.

Preparative Examples (CM7) and Guerbet Monomers (GM 1-10)Method 1

A mixture of the alkanol, acrylic acid (AA, TCI), p-toluene sulfonic acid hydrate (TSA, J.T. Baker), phenothiazine (PT, Aldrich), and toluene were heated to reflux. The liberated water was collected in a Dean and Stark trap. After the reaction was complete (4-6 hours), the reaction was cooled, then washed with 1.0 M NaOH, and water. The solvent was removed under vacuum. The crude oil was then distilled under vacuum to give the product as a colorless oil.

Table 2

	Alkanol	Alkanol, g	AA, g	TSA, g	PT, g	Toluene, mL	Yield, g
CM 7	Exxal 13 (Exxon)	150.00	65.46	1.00	0.50	280	171.35
GM 1	Isofol 12 (Sasol)	300.00	139.05	2.20	1.00	465	334.71
GM 9*	Fineoxocol FO-180 (Nissan)	29.99	8.77	0.35	0.09	100	4.77

* GM9 product was not distilled.

Method 2

A mixture of alkanol, triethylamine (TEA, Alfa Aesar), and methylene chloride (MC) was cooled to 5 °C using an ice bath. Acryloyl chloride (AC, Alfa Aesar) was added dropwise over one hour with mechanical stirring. After 10 hours, the mixture was filtered, then concentrated under vacuum. The remaining oil was diluted with ethyl acetate and washed with 1.0 M HCl, 1.0 M NaOH, and brine. The organic layer was then concentrated under vacuum. The crude oil was mixed with an equal portion of hexane and passed through a column of neutral alumina to remove colored impurities. The alumina was eluted with hexane. The collected filtrate was concentrated under vacuum to give the final product as a colorless oil.

Table 3

	Alkanol	Alkanol, g	TEA, g	MC, g	AC, g	Yield, g
GM 2	Isofol 14T (Sasol)	75.00	38.45	350	34.39	48.98
GM 3	2-hexyl-1-decanol (Aldrich)	100.00	45.97	350	41.10	102.07
GM 4	Isofol 18T (Sasol)	197.17	78.12	700	69.86	195.05
GM 5	Isofol 20 (Sasol)	80.00	29.08	275	25.75	84.31
GM 6	Isofol 24 (Sasol)	100.00	28.53	300	28.10	86.60
GM 7	Isofol 28 (Sasol)	60.50	16.29	250	14.57	60.00
GM 8	Isofol 32 (Sasol)	150.00	35.61	550	31.85	147.61
GM 10	Fineoxocol FO180N (Nissan)	35.00	15.59	150	14.07	29.71

Guerbet Monomer 11 (GM 11)

A flask was charged with Isofol™ 20 (100.00 g, 0.33 mol), methacrylic anhydride (Monomer and Polymer Dajac Lab, Trevose, PA, 59.46 g, 0.38 mol), 4-dimethylamino pyridine (Aldrich, 1.00 g), and ethyl acetate (100 mL). The mixture was stirred at 60 °C for 17 hours, then for an additional 7 hours at 90 °C. The mixture was diluted with ethyl acetate (200 mL), then washed with 1.0 M HCl, and 1.0 M NaOH. The organic layer was

then concentrated under vacuum. The crude oil was mixed with an equal portion of hexane and passed through a column of neutral alumina to remove colored impurities. The alumina was eluted with hexane. The collected fractions were concentrated under vacuum to give the final product as a colorless oil (109.17 g).

5 DSC analysis for monomers CM 1-7 and GM 1-11 were completed following the procedures outlined in Test Method 1. The results are listed below in Table 4. In Table 4 "NO" means not observed.

Table 4. Thermal Transitions of (meth)acrylic monomers measured by DSC

Monomer	Molar Carbon Number Average	T _c (°C)	T _m (°C)
CM 1(IOA)	8	NO	NO
CM 2 (EHA)	8	NO	NO
CM 3 (IDA)	10	NO	NO
CM 4 (PHA)	10	NO	NO
CM 5 (LA)	12	-23.8	0.3
CM 6 (LMA)	12	-24	4
CM 7	13	NO	NO
GM 1	12	NO	NO
GM 2	14	NO	NO
GM 3	16	NO	NO
GM 4	18	-82.1	-61.2
GM 9	18	NO	NO
GM 10	18	NO	NO
GM 5	20	-59.2	-41.2
GM 11	20	-65.2	-48.1
GM 6	24	-30.4	-9.8
GM 7	28	-8.0	7.5
GM 8	32	4.3	21.4

10

As shown in Table 4, monomers with common linear, substituted (meth)acrylic monomers (CM 1-7) start to exhibit crystalline behavior with alkyl chains of C₁₂ or greater. The exception to this is CM 7 which is a highly substituted C₁₃ acrylate. In comparison, the Guerbet alkanol (meth)acrylates (GM 1-11) do not show evidence of
 15 crystallinity until C₁₈ alkyl chains are present in the monomer. Additional substitution of methyl groups on the C₁₈ alkyl chain (GM 9 and 10) serve to depress crystallization of the comparable C₁₈ (GM 4) down below the instruments limit of -100 °C. It is noted that GM 8 with a C₃₂ alkyl chain is in a liquid state at room temperature.

DSC and DMA analysis of homopolymer films of Examples 1-11, Comparative Examples C1-C7

DSC and DMA analysis for CM 1-7 and GM 1-11 were completed following the procedures outlined in Test Methods 1 and 2. The results are listed below in Table 5. In Table 5 “NO” means not observed and “NT” means not tested.

Table 5. Thermal Transitions and mechanical properties of (meth)acrylic homopolymers.

Example	Monomer	Molar Carbon Number Average	DSC Analysis			DMA Analysis		
			Tc (°C)	Tm (°C)	Tg (°C)	Tg (°C)	St. Mod @ 25C (MPa)	FWPH (C)
Comparative 1	CM 1	8	NO	NO	-65.4	-38.1	19,500	26.7
Comparative 2	CM 2	8	NO	NO	-63.4	-46.2	18,800	33.5
Comparative 3	CM 3	10	NO	NO	-62.5	-38.4	8,700	36.7
Comparative 4	CM 4	10	NO	NO	-69.1	-45.7	10,000	39
Comparative 5	CM 5	12	-7.9	3.9	NO	NO	4,475	NO
Comparative 6	CM 6	12	-42.5	-34.5	NO	-10.5	10,980	97
Comparative 7	CM 7	13	NO	NO	-58.6	-31.2	13,300	43.5
1	GM 1	12	NO	NO	-75.8	-47.2	7,200	46.4
2	GM 2	14	NO	NO	-79.1	-52.5	7,780	48.6
3	GM 3	16	NO	NO	-74.8	-47.8	7,200	51.7
4	GM 4	18	NO	NO	-75	-49.2	3,110	55.3
5	GM 9	18	NO	NO	-12.2	NT	NT	NT
6	GM 10	18	NO	NO	-59	-20.9	15,500	67.4
7	GM 5	20	NO	NO	-69.8	-44.9	6,200	52.3
8	GM 11	20	NO	NO	-48.0	-13.2	28,000	53.1
9	GM 6	24	-47	-36.9	NO	NO	4,320	NO
10	GM 7	28	-16.3	-6.4	NO	NT	NT	NT
11	GM 8	32	8.2	13.6	NO	NO	1,930	NO

As shown in Table 5 above, polymers generated from monomers with common linear, substituted (meth)acrylic monomers (CM 1-7) start to exhibit crystalline domains at molar carbon number average of 12 or greater. The exception to this is CM 7 which is a highly methyl substituted C₁₃ acrylate. In comparison, polymers generated using the

synthesized (meth)acrylates of this invention (GM 1-11) do not show evidence of crystallinity below molar carbon number average of 24.

In general, the branched, linear chain structure of the monomers synthesized in this invention (GM 1-8) leads to significantly lower T_g as measured by DSC and DMA compared to homopolymers of common PSA acrylates of linear, methyl substituted chain structure (CM 1,3,5,7). Methyl substitution on the C_{18} branched structure (GM 10) significantly increases its T_g over the comparable non-methyl substituted C_{18} (GM 4).

Examples 12-28, Comparative Examples C8-C19 Peel adhesive properties of adhesive formulated films

An improvement in adhesive performance using Guerbet monomers was demonstrated by carrying out peel tests of tackified and crosslinked adhesive films on multiple substrates following the procedure outlined in Test Method 5.

The failure (F) of each PSA sample is classified as adhesive failure (af), cohesive split (cs), partial cohesive split (pcs), partial transfer (pt), or ghosting (g). Samples of this series that were not tested are identified with NT.

Monomers CM 1-3, 7 and GM 1-4, 10 were each mixed using the following example formula. 28.5 g of GM 1, 0.02 g of IrgacureTM 651 (Ciba), 0.3g of acrylic acid (AA, Alfa Aesar), and 1.2 g of hydroxyethyl acrylate (HEA, Aldrich) were mixed using a magnetic stir bar in a clear glass vial. The glass vial was then purged with nitrogen for 5 minutes to remove dissolved oxygen and then placed in front of a UV light (365nm, ~5 mW/cm²) until a coatable viscosity was achieved. A typical target for this step is an approximate viscosity of 3000 cP at room temperature and acrylic conversion of approximately 10-20%.

Each "thickened" sample was then formulated with low polarity tackifier Regalrez 1094 (Eastman Co.) at 50, 75, 85, or 100 pph (parts per hundred relative to the resin), additional IrgacureTM 651, as well as photocrosslinker, XL-330 (2,4,-bis(trichloromethyl)-6-(4-methoxyphenyl)-triazine, 3M). As an example formulation, 5 g of "thickened" monomer formulation based on GM1 was added to an amber vial along with 2.5g of RegalrezTM 1094 tackifier (50 pph), 0.0045 g (0.09 pph) of Irgacure 651TM and 0.004 g (0.08 pph) of XL-330. The amber vial was then rotated in the dark until the solid ingredients were completely dissolved. The adhesive formulation described above was

coated onto primed PET film at a coating thickness of 0.08mm and covered with a silicone treated release liner. This construction was then cured using approximately 600 mJ/cm² of UV irradiation. This procedure was repeated for each additional adhesive formulation.

5 The results are shown in Table 6. In Table 6 “Trans” means visually translucent, “NT” means not tested and “Carbon Number” means molar carbon number average.

Table 6. 180° Peel Performance for Tackified Adhesive Films on Stainless Steel and HDPE

180° Peel Performance				Immediately after cure				Aging 70 °C for 1 week			
Example	Monomer	Carbon Number	R-1094 Tackifier loading (pph)	Visual	S. Steel (N/dm)	F	HDPE (N/dm)	F	Visual	HDPE (N/dm)	F
C8	CM1	8	50	Opaque	20	af	17	af	Opaque	13	af
C9	CM1	8	75	Opaque	4	af	4	af	Opaque	4	af
C10	CM1	8	85	Opaque	9	2b	2	af	Opaque	3	af
C11	CM2	8	50	Opaque	22	af	23	af	Opaque	14	g
C12	CM2	8	75	Opaque	4	g	4	af	Opaque	4	af
C13	CM2	8	85	Opaque	14	2b	1	af	Opaque	3	g
C14	CM3	10	50	Opaque	55	af	39	af	Opaque	NT	NT
C15	CM3	10	75	Opaque	35	af	38	af	Opaque	NT	NT
C16	CM3	10	85	Opaque	14	af	25	af	Opaque	NT	NT
C17	CM7	13	50	Clear	61	af	48	af	Clear	NT	NT
C18	CM7	13	75	Clear	79	g	23	af	Clear	NT	NT
C19	CM7	13	85	Clear	22	af	3	af	Trans	NT	NT
12	GM1	12	50	Clear	48	af	38	af	Trans	50	af
13	GM1	12	75	Trans	69	af	64	af	Opaque	26	af
14	GM1	12	85	Trans	92	pcs	67	pcs	Opaque	7	af
15	GM2	14	50	Clear	49	pcs	37	af	Clear	44	af
16	GM2	14	75	Clear	85	cs	61	pt	Clear	66	af
17	GM2	14	85	Clear	88	cs	61	pt	Clear	66	af
18	GM2	14	100	Clear	89	cs	46	g	Clear	63	af
19	GM3	16	50	Clear	43	af	33	af	Clear	37	af
20	GM3	16	75	Clear	77	af	49	af	Clear	62	af
21	GM3	16	85	Clear	85	pcs	60	g	Clear	68	af
22	GM3	16	100	Clear	85	pcs	61	g	Clear	69	af
23	GM4	18	50	Clear	42	af	34	af	Clear	37	af
24	GM4	18	75	Clear	94	pcs	79	pcs	Clear	77	af
25	GM4	18	85	Clear	101	cs	76	pcs	Clear	69	af
26	GM4	18	100	Clear	88	cs	71	pcs	Clear	76	af
27	GM10	18	50	Clear	92	pcs	58	af	Clear	NT	NT
28	GM10	18	85	Clear	32	cs	33	cs	Clear	NT	NT

The data of Table 6 indicates poor solubility of the low polarity tackifier (R-1094) with typical C₈ PSA acrylates. Tackifier solubility improves as the molar carbon number is increased above 12. With respect to aging, samples with molar carbon numbers below 14 show opacity of the adhesive upon aging suggesting a phase separation and incompatibility of the polymer with the tackifier. Contrarily, examples 15-28 remain clear upon aging, even with extremely high loadings of tackifier (100 pph).

The data of Table 6 indicates that greater peel performance is achieved with PSAs containing monomers with molar carbon numbers greater than 12, particularly with GM 1-4, and GM 10. Comparative examples CM 1 and CM 2 (IOA and 2EHA respectively) perform poorly in regards to peel adhesive strength most likely due to the poor solubility of this tackifier in these adhesive formulations as demonstrated in Table 6.

In comparison to PSAs generated with comparative example monomers, adhesive films using the Guerbet monomers of this invention show exceptional peel performance on both stainless steel and HDPE, particularly at high loadings of tackifier.

Shear performance of adhesive formulated films of Examples 10-23 and Comparative Examples C8-C19

Adhesives generated in Comparative Examples C8-C19 and Examples 12-14, 19-21, and 23-25 were all tested for shear holding performance following the procedure outlined in Test Method 3. Each sample tested held for over 10,000 minutes at 70 °C at which time the test was discontinued. These results demonstrate that PSA materials generated from the Guerbet monomers of this invention still exhibit a similar high degree of shear holding performance when compared to PSAs based on traditional C₈ acrylate monomers.

Blend (B) Preparatory Examples of Base Monomers

Guerbet acrylates based on GM 4, 6 and 8 were blended with 2-ethylhexyl acrylate (CM 2) following the amounts specified in Table 7 to yield compositions of acrylates with targeted molar carbon number averages of 12-18.

Table 7 Blends of Guerbet Acrylates with 2-Ethylhexyl acrylate (CM 2)

Preparatory Blend Example	CM 2 (g) C ₈	GM 4 (g) C ₁₈	GM 6 (g) C ₂₄	GM 8 (g) C ₃₂	Molar Carbon Number Average
B1	45	55			12
B2	27	73			14
B3	12	88			16
B4	57		43		12
B5	43		57		14
B6	31		69		16
B7	21		79		18
B8	64			36	12
B9	51			49	14
B10	41			59	16

Examples 29-38: Physical Properties of Copolymers

Approximately 2 g of each of the blend examples of B1-B10 was mixed with 0.01 g of photoinitiator I-651 in a small amber vial. Polymerized samples were generated and tested following the same method that was outlined in Test Method 1 above. The results are shown in table 8. In Table 8, “NO” means not observed and “NT” means not tested.

Table 8. Thermal Transitions and mechanical properties of Blend Polymers

Example	Polymer	Molar Carbon Number Average	DSC Analysis			DMA Analysis		
			T _c (°C)	T _m (°C)	T _g (°C)	T _g (°C)	St. Mod @ 25C (MPa)	FWPH (°C)
29	B1	12	NO	NO	-75	-58	6190	40
30	B2	14	NO	NO	-76	-53	4800	44
31	B3	16	NO	NO	-75	-52	4800	50
32	B4	12	NO	NO	-72	-53	5200	36
33	B5	14	NO	NO	-70	-53	5010	36
34	B6	16	NO	NO	-65	-52	3650	37
35	B7	18	NT	NT	NT	NT	NT	NT
36	B8	12	-30	-23	NO	NO	4920	NO
37	B9	14	-21	-12	NO	NO	5840	NO
38	B10	16	-15	-6	NO	NO	NT	NO

Examples 39-68: Adhesive properties of PSAs Based on Blend Monomer Formulations

PSA materials were generated using the blended preparatory examples (B1-B10) as the base monomer system in each formulation. For example 47.5 g of B1 was mixed with 2 g of hydroxyethyl acrylate, 0.5 g of acrylic acid, and 0.03 g of photoinitiator I-651.

- 5 This mixture was “thickened” by partially curing the formulation under UV irradiation similar to Examples 12-28 above. Tackifier (Regalrez™ 1094, R-1094), crosslinker (XL-330), additional photoinitiator (I-651) were added at similar levels to Examples 12-28 and according to Table 9 below and allowed to mix overnight in amber vials. Each adhesive formulation was coated, cured, and tested following the same procedure
- 10 outlined in Examples 12-28, as well as Test Methods 3-6. The results are shown in Table 9. In Table 9 “trans” means translucent.

Table 9. Adhesive Properties of Blend Polymers Before and After Aging

				180° Peel Performance							
Example	Monomer Blend	Molar carbon number average	R-1094 Tackifier loading (pph)	Immediately after cure				Aging 70°C for 1 week			
				Visual	S. Steel (N/dm)	F	HDPE (N/dm)	F	Visual	HDPE (N/dm)	F
39	B1	12	50	Trans	48	af	36	af	Clear	39	af
40	B1	12	75	Trans	66	t	48	t	Trans	32	t
41	B1	12	85	Trans	70	t	44	t	Trans	17	t
42	B2	14	50	Clear	44	af	40	af	Clear	37	af
43	B2	14	75	Trans	77	cs	63	t	Clear	60	af
44	B2	14	85	Trans	81	cs	44	t	Clear	69	af
45	B3	16	50	Clear	45	af	39	af	Clear	36	af
46	B3	16	75	Trans	71	cs	68	cs	Clear	68	pcs
47	B3	16	85	Trans	81	cs	66	cs	Clear	83	pcs
48	B4	12	50	Clear	45	af	24	af	Clear	20	af
49	B4	12	75	Trans	55	pcs	35	af	Clear	31	af
50	B4	12	85	Trans	53	pcs	22	cs	Clear	7	g
51	B5	14	50	Clear	42	g	24	af	Clear	22	af
52	B5	14	75	Trans	64	cs	50	pcs	Clear	36	af
53	B5	14	85	Trans	59	pcs	34	cs	Clear	37	af
54	B6	16	50	Clear	41	pcs	27	af	Clear	24	af
55	B6	16	75	Clear	63	cs	44	pcs	Clear	44	af
56	B6	16	85	Trans	72	cs	55	pcs	Clear	43	af
57	B7	18	50	Clear	38	af	26	af	Clear	24	af
58	B7	18	75	Clear	68	cs	61	cs	Clear	51	cs
59	B7	18	85	Clear	76	cs	68	cs	Clear	71	cs
60	B8	12	50	Clear	41	af	22	af	Clear	18	af
61	B8	12	75	Trans	57	pcs	34	af	Clear	33	af
62	B8	12	85	Trans	60	pcs	37	pcs	Clear	18	g

180° Peel Performance									
Example	Monomer Blend	Molar carbon number average	R-1094 Tackifier loading (pph)	Immediately after cure				Aging 70°C for 1 week	
				Visual	S. Steel (N/dm)	F	HDPE (N/dm)	F	HDPE (N/dm)
63	B9	14	50	Clear	36	af	22	af	16
64	B9	14	75	Trans	66	cs	46	pcs	27
65	B9	14	85	Trans	61	cs	59	pcs	43
66	B10	16	50	Clear	35	pcs	22	af	18
67	B10	16	75	Trans	60	cs	49	pcs	36
68	B10	16	85	Trans	70	cs	66	pcs	48

In general, the initial solubility of the low polarity Regalrez™ 1094 (R1094) tackifier with the blended composition was slightly worse compared to PSA formulations based on non-blended Guerbet acrylates. However, solubility of the tackifier in the blended systems for nearly every molar carbon number average grouping did improve
5 after aging the PSA samples at 70°C for one week. Similar to the non-blended systems (Examples 12-28), blended systems whose molar carbon number average was greater than 12 demonstrated good compability with the Regalrez™ 1094 tackifier after aging.

Regarding adhesive peel performance, blended formulations composed primarily of the C₈ (CM 2) and C₁₈ (GM 4) based acrylates were similar or slightly above
10 formulations based on the single alkyl monomer of the same molar carbon number average. However, as the lower alkyl acrylate component (CM 2) is increased in concentration and blended with higher alkyl acrylates C₂₄ (GM 6) or C₃₂ (GM 8), the adhesive peel performance decreases generally even though the molar carbon number average is kept constant at 12, 14 or 16.

15

Examples 69-74 and C20-C21: Adhesive transfer tape made of GM 1 and GM 4

In examples 69-74 transfer tapes (2 mils or 51 microns coating thickness) with a 2 mil aluminum backing were made in the same way as Examples 12-28, except the monomer composition, formulated with Arkon™ P90 hydrocarbon tackifier (Arakawa
20 Chemical, Chicago, Ill), was coated between two transparent release liners, cured, and transferred to a primed PET liner. The monomer composition is shown in Table 10. 90 Degree Peel was tested using Test Method 7 against high density polyethylene (HDPE), polypropylene (PP) and stainless steel (SS) panels. 70°C static shear were tested using Test Method 6. The adhesive tapes were tested against 3M™ brand 6032 and 9442
25 adhesive tapes. “HEA” is hydroxyethyl acrylate and “AA” is acrylic acid. “#2 bond” refers to a failure mode where the adhesive/backing bond fails. The results were shown in Table 10.

Table 10. Adhesive Transfer Tapes

Adhesive Composition			Tape 90 Degree Peel Performance (N/dm)				70C Shear (min)
Example	Monomer	Arkton P90 (pph)	Dwell (minutes, hours or days)	HDPE	PP	SS	
69	GM1/AA/HEA=95/1/4	60	15min RT	43	60	78	10000+
			24hr RT	46	67	101	
			72hr RT	48	70	99	
			7D 70C	46	77	95	
70	GM1/AA/HEA=95/1/4	70	15min RT	47	67	78	10000+
			24hr RT	59	68	83	
			72hr RT	47	77	94	
			7D 70C	62	85	108	
71	GM1/AA/HEA=97/1/2	70	15min RT	45	67	71	1581
			24hr RT	51	66	76	
			72hr RT	51	70	83	
			7D 70C	55	77	110	
72	GM1/AA=99/1	70	15min RT	58	131	110	#2 bond
			24hr RT	100	108	107	
			72hr RT	94	120	106	
			7D 70C	66	87	131	
73	GM4/AA/HEA=95/1/4	60	15min RT	100	101	108	#2 bond
			24hr RT	105	84	98	
			72hr RT	107	97	107	
			7D 70C	95	55	92	
74	GM4/AA/HEA=95/1/4	70	15min RT	63	65	127	#2 bond
			24hr RT	93	94	98	
			72hr RT	102	91	100	
			7D 70C	87	105	92	
C20	3M 6032		15min RT	18	26	59	66
C21	3M 9442		15min RT	25	26	72	7219

The peel adhesion data in Table 10 show the adhesive tapes have superior adhesion to low surface energy substrates (HDPE & PP) and high energy substrates (SS) as well as good temperature shear in comparison to the commercial acrylic tapes on the market.

Examples 75-76 and Comparative C22: Adhesive foam tape

Adhesives (2 mils or 51 micron coating thickness) were prepared in the same way as Example 69-74 but with the monomer composition shown in Table 11. The adhesive was then laminated to an acrylic foam (42 mils or 1.07 mm) and tested against the indicated substrates. The backing used for peel testing is an aluminum foil (5 mils or 127 microns). “HEA” is hydroxyethyl acrylate, “AA” is acrylic acid, “MA” is methyl acrylate and “IOA” is isooctyl acrylate. Foam tapes made of this invention demonstrate the unique feature of very higher adhesion to both low and high surface substrates compared to a conventional IOA-based adhesive on the same acrylic foam.

Table 11. Adhesive Foam Tapes

Example	Foam Tape		Foam Tape 90° Peel Performance (N/dm)				
	Monomer	Arkon P90 (pph)	Dwell time	PP	HDPE	PC	SS
75	GM1/AA/HEA =95/1/4	60	15 min	283	179	187	263
			72 hour	265	219	251	254
76	GM4/AA/HEA =95/1/4	60	15 min	213	181	189	216
			72 hour	262	243	243	241
C22	IOA/MA/AA =65/35/5	0	15 min	51	44	51	291

Claims

1. A pressure-sensitive adhesive composition comprising (co)polymers of a) (meth)acrylate ester of 2-alkyl alkanols wherein the molar carbon number average of said 2-alkyl alkanols is 12 to 32; and optionally b) (meth)acrylate esters of C₁₋₁₂ alkanols; wherein the molar carbon number average of the alkanols of the a) and b) (meth)acrylic acid esters is 12 to 32.

2. The pressure sensitive adhesive of claim 1 wherein the molar carbon number average of the alkanols of the a) and b) (meth)acrylic acid esters is 12 to 20.

3. The pressure sensitive adhesive of claim 1 further comprising acid monomer units.

4. The pressure sensitive adhesive of claim 1 further comprising non-acid polar monomer units.

5. The pressure sensitive adhesive of claim 1 further comprising b) (meth)acrylate esters of C₁₋₁₂ alkanols.


6. The pressure sensitive adhesive of claim 1 further comprising a tackifier.

7. The pressure sensitive adhesive of claim 6 comprising 20 to 150 parts of said tackifier, relative to 100 parts of said (meth)acrylate ester (co)polymer.

8. The pressure sensitive adhesive of claim 6 wherein said tackifier is selected from hydrogenated rosin resins, hydrogenated and esterified rosin resins, hydrogenated terpene resins, aliphatic petroleum resins, aromatic petroleum resins, and alicyclic petroleum resins.

9. The pressure-sensitive adhesive of claim 1 wherein the 2-alkyl alkanols are derived from linear alkanols.

10. The pressure-sensitive adhesive of claim 1 wherein the 2-alkyl alkanol (meth)acrylate ester is of formula:




wherein

$\text{R}^{\text{Guerbet}}$ is derived from a C_{12} - C_{32} 2-alkyl alkanol, and

R^3 is H or CH_3 .

11. The pressure-sensitive adhesive of claim 10 wherein the 2-alkyl alkanol (meth)acrylate ester is of formula:



wherein

R^1 and R^2 are each independently C_4 to C_{14} saturated, and branched or linear alkyl; and

R^3 is H or CH_3 .

12. The pressure-sensitive adhesive of claim 1 comprising:

- a) 51 to 99 parts by weight of an (meth)acrylic acid ester monomer of 2-alkyl alkanols;
- b) 1 to 49 parts by weight of an (meth)acrylic acid ester of a C_1 - C_{12} alkanol;
- c) 0 to 15 parts by weight of an acid functional ethylenically unsaturated monomer;
- d) 0 to 10 parts by weight of a non-acid functional, ethylenically unsaturated polar monomer;
- e) 0 to 5 parts by weight of a vinyl monomer; and

f) 0 to 5 parts by weight of a multifunctional (meth)acrylate;
based on 100 parts by weight total monomer.

13. The pressure-sensitive adhesive of claim 12 comprising 5 to 45 parts by weight of
5 a (meth)acrylic acid ester of a C₁-C₁₂ alkanol.

14. The pressure-sensitive adhesive of claim 12 comprising 0.1 to 10 parts by weight
of an acid functional ethylenically unsaturated monomer.

10 15. The pressure-sensitive adhesive of claim 12 comprising 0.5 to 10 parts by weight
of a non-acid functional, ethylenically unsaturated polar monomer.

16. The pressure-sensitive adhesive of claim 12 comprising 0.05 to 1 parts of a
multifunctional (meth)acrylate.

15 17. The pressure-sensitive adhesive of claim 1 having a T_g of ≤ -20°C.

18. The pressure-sensitive adhesive of claim 1 further comprising a crosslinking
agent.

20 19. A pressure-sensitive adhesive article comprising a coating of the adhesive of
claim 1 on a backing.

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2011/028420

A. CLASSIFICATION OF SUBJECT MATTER
INV. C09J133/00
ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
C09J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EP0-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 2 072 594 A1 (NITTO DENKO CORP [JP]) 24 June 2009 (2009-06-24) paragraph [0062] -----	1-19

☐

Further documents are listed in the continuation of Box C.

☒

See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

23 May 2011

Date of mailing of the international search report

30/05/2011

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Trauner, H

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2011/028420

Patent document cited in search report	Publication date	Patent family member(s)	Publication date	
EP 2072594	A1	24-06-2009	CN 101522845 A	02-09-2009
			WO 2008047636 A1	24-04-2008
			US 2010021730 A1	28-01-2010
