




(86) Date de dépôt PCT/PCT Filing Date: 2016/07/25
(87) Date publication PCT/PCT Publication Date: 2017/05/26
(85) Entrée phase nationale/National Entry: 2017/07/14
(86) N° demande PCT/PCT Application No.: CN 2016/091590
(87) N° publication PCT/PCT Publication No.: 2017/084379
(30) Priorité/Priority: 2015/11/19 (CN201510801786.1)

(51) Cl.Int./Int.Cl. *C09K 8/68* (2006.01)
(71) Demandeur/Applicant:
SICHUAN GUANGYA POLYMER CHEMICAL CO., LTD.,
CN
(72) Inventeurs/Inventors:
GUO, YONGJUN, CN;
LUO, PINGYA, CN;
WANG, XIANG, CN;
LIU, KUAN, CN
(74) Agent: BCF LLP

(54) Titre : SYSTÈME DE FLUIDE DE FRACTURATION COMPOSITE MULTIFONCTIONNEL
(54) Title: MULTI-FUNCTIONAL HYBRID FRACTURING FLUID SYSTEM



(57) Abrégé/Abstract:

A multifunctional composite fracturing fluid system comprises resistance reducing water and a high-adhesion sand-carrier fluid. The resistance reducing water comprises 0.02% to 0.15% of a resistance reducing agent. In percentage by mass, the high-

(57) Abrégé(suite)/Abstract(continued):

adhesion sand-carrier fluid comprises 0.2% to 0.75% of a thickener. The resistance reducing agent and the thickener are the same association polymer, which is a naturally modified association polymer and/or an organically synthetic association polymer. A multifunctional composite fracturing fluid system is formed using the better drag reduction property of a low-concentration association polymer with relatively good resistance reducing property and a high-concentration association polymer. Compared with the composite fracturing fluid system in the art, said fracturing fluid system is characterized by less types of additives, simple formulation and simple preparation process while having the better drag reduction property, the better shear resistance property and better sands-carrying property. A flowback fluid of said system can be reused after flocculation, sedimentation, filtration and other treatments, thus improving the utilization rate of water for fracturing.

Abstract

The present invention provides a multi-functional hybrid fracturing fluid system, comprising slick water and high viscosity sand carrying fluid, wherein the slick water contains 0.02%~0.15% of friction-reducing agent by mass percentage, the high viscosity sand carrying fluid contains 0.2%~0.75% of thickener by mass percentage; the friction-reducing agent and the thickener are the same associative polymer which is a modified natural associative polymer and/or an organic synthetic associative polymer. The present invention makes use of the good friction reduction performance of low concentration of associative polymer and the good sand carrying performance of the high concentration of associative polymer, to form a multi-functional hybrid fracturing fluid system. Compared with the conventional hybrid fracturing fluid system, the multi-functional hybrid fracturing fluid system of the present invention has advantages of less additive type, simple formula and easy preparation process; at the same time, this system has better performances on friction reduction, shearing resistance and sand carrying. The flowback liquid of the system can be reused after flocculation, sedimentation, filtration and other treatments, improving the utilization rate of the water for fracturing.

MULTI-FUNCTIONAL HYBRID FRACTURING FLUID SYSTEM

CROSS REFERENCE TO RELATED APPLICATION

[0001] This application claims the priority of Chinese patent application No. 201510801786.1, titled “MULTI-FUNCTIONAL HYBRID FRACTURING FLUID SYSTEM”, filed with the Chinese State Intellectual Property Office on November 19, 2015, the entire contents thereof are incorporated herein by reference.

FIELD

[0002] The present invention relates to the field of hydrocarbon reservoir fracturing reformation technology, in particular to a multi-functional hybrid fracturing fluid system suitable for tight hydrocarbon reservoirs and shale hydrocarbon reservoirs.

BACKGROUND

[0003] The world's unconventional oil and gas resources are abundant, of which the proportion of low permeability and ultra-low permeability oil and gas reservoirs is huge. Due to the low permeability and low porosity of low permeability oil and gas reservoirs, it is necessary to stimulate it to form a complex fracture network, so as to increase the yield. The stimulation of the low permeability oil and gas reservoirs in the world is mainly based on hydraulic fracturing technology, and the commonly used fracturing fluid is guar gum fracturing fluid. When using guar gum as a thickener, in order to reach a sufficient viscosity to meet the requirement of sand carrying, usually a cross-linking agent need to be added, through chemical cross-linking a gel fracturing fluid system is formed. But the gel fracturing fluid system is not broken completely, and the

content of water insoluble matter in guar gum thickener is high, thus high amount of residue after breaking will damage the formation. At the same time, because the gel fracturing fluid system is formed by cross-linking technology, this type of gel system is not resistant to shear, so it is not suitable for large-scale fracturing which requires resistant to shear for a long time, or high shear rate tubing, coiled tubing and jet fracturing. Furthermore, high viscosity and high construction friction of gel fracturing fluid system increase the load of fracturing equipments, which is not advantageous to deep well stimulation.

[0004] In recent years, slick water fracturing technology has been used in the Stimulated Reservoir Volume (SRV) in many low permeability oil and gas reservoirs (especially shale gas reservoirs) on the stratum volume reconstruction, which achieved a better yield and increased the injection effect. The so-called slick water fracturing is the fracturing operation in the low permeability oil and gas reservoir reformation, by adding friction-reducing agent (anionic polymer or low concentration of guar gum, etc.), active agent, clay stabilizer or linear gel to water, serving as a working fluid.

[0005] Slick water fracturing can generate a long complex fracture network, but the effective length of the propped fracture will change greatly with the concentration of the proppant and the laying effect. The concentration of the proppant in the slick water fracturing fluid is low, so the fracture conductivity is poor. Later, a new fracturing method-hybrid slick water fracturing technology, which combined gel fracturing technology with slick water fracturing technology, was proposed. The technique involves mainly a large displacement injection of slick water, so that the natural fractures in the formation produce a shear slip, and secondary fractures appear on the side of the fractures, thus a long complex fracture network is formed. A proppant with low sand rate is carried in to support micro fractures. A suspension with high sand proportion using gel carries a proppant with high sand ratio into the formation, supporting the main fractures, thus a better fracture conductivity is formed.

[0006] At present, slick water is mainly prepared by using anionic polymer, low concentration of guar gum or linear gel as friction-reducing agent, and using guar gum and other natural polymers and synthetic polymers as a thickener, so as to form a gel system as a sand carrying fluid with high sand ratio. But the additives
 5 for slick water and gel fracturing fluid are different; in order to meet the needs of various formations, many types of additives are used, resulting in the difficulty in the quality control of raw materials during procurement; at the same time the preparation process for the fluid is also complex (especially in the large-scale Stimulated Reservoir Volume (SRV) process). These consume a lot of manpower
 10 and material resources. In addition, with the continuous improvement of environmental requirements and the lack of water resources, what needs to be considered is to reduce the amount of working fluid required for increasing the yield of fracturing fluid, while achieving “zero discharge” of the working fluid wastewater of fracturing fluid. All the flowback liquid after fracturing needs to be
 15 treated, recycled or re-injected into the formation. Because there are many types of additives added to the fracturing fluid, which makes the composition of the flowback liquid is complicated, the cost of recycle and processing is high.

SUMMARY

20 [0007] In view of the above, the technical problem to be solved by present invention is to provide a multi-functional hybrid fracturing fluid system which is simple to prepare and environmentally friendly.

[0008] The present invention provides use of an associative polymer as friction-reducing agent and thickener, which is a modified natural associative
 25 polymer and/or an organic synthetic associative polymer.

[0009] A multi-functional hybrid fracturing fluid system is also provided in the present invention, comprising slick water and high viscosity sand carrying fluid.

[0010] By mass percentage, said slick water contains 0.02%~0.15% of

friction-reducing agent.

By mass percentage, said high viscosity sand carrying fluid contains 0.2%~0.75% of thickener.

[0011] Said friction-reducing agent and thickener are the same associative polymer which is a modified natural associative polymer and/or an organic
5 synthetic associative polymer.

[0012] Preferably, said modified natural associative polymer is selected from one or more of hydrophobically modified cellulose polymers, hydrophobically modified starch polymers and hydrophobically modified xanthan gum; said
10 organic synthetic associative polymer is hydrophobically modified polyacrylamide and/or derivatives thereof.

[0013] Preferably, by mass percentage, said slick water comprises 0.02%~0.15% of friction-reducing agent, 0.05%~0.3% of enhancer, 0.2%~2% of clay stabilizer, and water solvent as the balance.

[0014] Preferably, by mass percentage, said high viscosity sand carrying fluid comprises 0.2%~0.75% of thickener, 0.1%~0.4% of enhancer, 0.3%~2% of clay
15 stabilizer, 0.03%~0.4% of gel breaker, and water solvent as the balance.

[0015] Said friction-reducing agent and said thickener are the same associative polymer which is modified natural associative polymer or organic synthetic
20 associative polymer; said enhancer in the slick water and said enhancer in the high viscosity sand carrying fluid is selected from one or more of anionic surfactants and nonionic surfactants, respectively.

[0016] Said water solvent in the slick water and said water solvent in the high viscosity sand carrying fluid is clear water or flowback liquid after treatment,
25 respectively.

[0017] Preferably, said anionic surfactant is one or more of alkyl benzene sulfonates, alkyl sulfates and petroleum sulfonates; said nonionic surfactant is one

or more of fatty acid polyoxyethylene ester, nonylphenol polyoxyethylene ether, polyether type surfactant and fatty alcohol polyoxyethylene ether.

[0018] Preferably, said clay stabilizer in the slick water and said clay stabilizer in the high viscosity sand carrying fluid is independently one or more of
5 potassium chloride, ammonium chloride and non-ionic organic clay stabilizers, respectively.

[0019] Preferably, said gel breaker in the high viscosity sand carrying fluid is one or more of potassium persulfate, ammonium persulfate and encapsulated oxidative gel breaker.

10 [0020] Preferably, by mass percentage, said slick water comprises 0.04%~0.15% of friction-reducing agent, 0.1%~0.3% of enhancer, 0.3%~2% of clay stabilizer, and clear water as the balance.

[0021] Preferably, by mass percentage, said slick water comprises 0.08% of friction-reducing agent, 0.2% of enhancer, 1% of clay stabilizer, and clear water
15 as the balance.

[0022] Preferably, by mass percentage, said slick water comprises 0.02%~0.1% of friction-reducing agent, 0.05%~0.25% of enhancer, 0.2%~1.5% of clay stabilizer, and flowback liquid after treatment.

[0023] Preferably, by mass percentage, said high viscosity sand carrying fluid
20 comprises 0.25%~0.75% of thickener, 0.15%~0.4% of enhancer, 0.3%~2% of clay stabilizer, 0.03%~0.4% of oxidative gel breaker, and clear water as the balance.

[0024] Preferably, by mass percentage, said high viscosity sand carrying fluid comprises 0.35% of thickener, 0.2% of enhancer, 1% of clay stabilizer, 0.15% of
25 oxidative gel breaker, and clear water as the balance.

[0025] Preferably, by mass percentage, said high viscosity sand carrying fluid comprises 0.2%~0.65% of thickener, 0.1%~0.3% of enhancer, 0.3%~1.5% of clay

stabilizer, 0.03%~0.4% of oxidative gel breaker, and flowback liquid after treatment as the balance.

[0026] The present invention also provides use of a multi-functional hybrid fracturing fluid system in the Stimulated Reservoir Volume (SRV) of tight
5 hydrocarbon reservoir and shale hydrocarbon reservoir.

[0027] The present invention provides a multi-functional hybrid fracturing fluid system which comprises slick water and high viscosity sand carrying fluid. By mass percentage, said slick water comprises 0.02%~0.15% of friction-reducing agent; by mass percentage, said high viscosity sand carrying fluid comprises
10 0.2%~0.75% of thickener; said friction-reducing agent and thickener are the same associative polymer which is modified natural associative polymers and/or organic synthetic associative polymers. The present invention uses low concentration associative polymer which has a good friction reduction performance and high concentration associative polymer which has a good sand
15 carrying characteristic to form a multi-functional hybrid fracturing fluid system. The system uses low concentration associative polymer as a friction-reducing agent to prepare slick water and uses high concentration associative polymer to prepare high viscosity sand carrying fluid, achieving multiple functions of an associative polymer. Compared with the existing “polyacrylamide or linear gel
20 slick water” + “guar gum fracturing fluid” complex fracturing fluid system, multi-functional hybrid fracturing fluid system has a better performance of sand suspending, thus reducing the amount of sand carrying fluid in slick water and the total amount of fracturing fluid. At the same time, the operation friction of slick water is low, capable of meeting the requirements of large displacement operation;
25 high viscosity sand carrying fluid has a high resistance to shear and a low residue content after gel breaking, so the damage to formation is low. The multi-functional hybrid fracturing fluid system is simple in formula, less additive type, has an easy preparation process, and can save a great amount of manpower and material resources in fracturing operation. Since the composition of this

system is simple, the flowback liquid can be re-formulated to fracturing fluid after flocculation, sedimentation, filtration and other simple treatments, reducing the amount of additives while improving the utilization rate of water for fracturing.

5 BRIEF DESCRIPTION OF THE DRAWINGS

[0028] Fig. 1 is a graph showing the relationship between friction of slick water and displacement.

[0029] Fig. 2 is a graph showing the friction reduction rates of the slick waters of the present invention.

10 [0030] Fig. 3 is a graph showing shearing resistance of the high viscosity sand carrying fluids of the present invention.

[0031] Fig. 4 is a graph showing the static suspended sand in the high viscosity sand carrying fluids of the present invention at different times.

15 [0032] Fig. 5 is a graph showing the static suspended sand in the high viscosity sand carrying fluids of the present invention at different times.

[0033] Fig. 6 is a graph showing friction reduction rates of the high viscosity sand carrying fluids of the present invention.

[0034] Fig. 7 is a graph showing shearing resistance of the high viscosity sand carrying fluids of the present invention.

20

DETAILED DESCRIPTION OF THE INVENTION

[0035] The technical solution in the examples of the present invention will be described in detail below in connection with the accompanying drawings of the examples of the present invention. Apparently, the described examples are merely
25 part of the present invention, and not all examples. All other examples obtained by those of ordinary skill in the art without making creative work are within the

scope of the present invention, based on the examples in the present invention.

[0036] The present invention provides use of an associative polymer as friction-reducing agent and thickener, wherein the associative polymer is a modified natural associative polymer and/or an organic synthetic associative polymer. Preferably, said modified natural associative polymer is one or more of hydrophobically modified cellulose polymers, hydrophobically modified starch polymers and hydrophobically modified xanthan gum; more preferably, one or more of alkyl, esters and nitro-hydrophobic groups modified cellulose polymers, starch polymers and xanthan gum; even more preferably, one or more of alkyl hydrophobically modified hydroxyethyl cellulose. Preferably, said organic synthetic associative polymer is hydrophobically modified polyacrylamide and/or derivatives thereof; more preferably, alkyl, esters and nitro-hydrophobic groups modified polyacrylamide and/or derivatives thereof; even more preferably, associative non-crosslinking fracturing thickener GRF-1H, GRF-1C (effective concentration of the associative polymer is 25%) produced by Sichuan Guangya Polymer Chemical Co. Ltd..

[0037] A multi-functional hybrid fracturing fluid system is also provided in the present invention, comprising slick water and high viscosity sand carrying fluid;

[0038] By mass percentage, said slick water contains 0.02%~0.15% of friction-reducing agent;

[0039] By mass percentage, said high viscosity sand carrying fluid contains 0.2%~0.75% of thickener;

[0040] Said friction-reducing agent and thickener are the same associative polymer which is the same as described above and will not be described further herein.

[0041] According to the present invention, by mass percentage, said slick water comprises 0.02%~0.15% of friction-reducing agent, 0.05%~0.3% of enhancer, 0.2%~2% of clay stabilizer, and water solvent as the balance; by mass percentage,

said high viscosity sand carrying fluid comprises 0.2%~0.75% of thickener, 0.1%~0.4% of enhancer, 0.3%~2% of clay stabilizer, 0.03%~0.4% of gel breaker, and water solvent as the balance. The enhancer in the slick water or the enhancer in the high viscosity sand carrying fluid is each independently one or more of anionic surfactants and nonionic surfactants; the water solvent in the slick water or the water solvent in the high viscosity sand carrying fluid is clear water as the balance or flowback liquid after treatment, respectively.

[0042] According to the present invention, the amount of the associative polymer as a friction-reducing agent in said slick water is preferably 0.04%~0.15%; said associative polymer is the same as described above and will not be described further herein. In the slick water of the multi-functional composition fracturing fluid system of the present invention, the associative polymer is used as a friction-reducing agent to reduce the friction in the whole solution pumping process and reduce the operation pressure during the fracturing operation. The friction reduction effect of the slick water is often associative with the concentration of friction-reducing agent. The friction reduction rate is usually increased first and then decreased with the increase of friction-reducing agent concentration. So the amount of friction-reducing agent needs to be limited to a certain range.

[0043] Enhancer in the slick water can reduce the surface tension of the slick water, make the slick water after fracturing operation return easily and reduce the external fluid damage to the formation. With the increase of the amount of enhancer used, the solution surface tension is often reduced constantly. The content of the enhancer in the slick water of the present invention is preferably 0.1%~0.3%; said enhancer is one or more of anionic surfactants and nonionic surfactants. Said anionic surfactants are known to those of ordinary skill in the art and are not particularly limited. Preferably, in the present invention, the anionic surfactants are alkylbenzene sulfonate, alkyl sulfate, petroleum sulfonate; said sulfate salt is preferably C10~C15 alkyl sulfate salt; said alkylbenzene sulfonate

is preferably C10~C20 alkylbenzene sulfonate salt. Said nonionic surfactants are those known to those of ordinary skill in the art and are not particularly limited. Preferably, in the present invention, the nonionic surfactant is one or more of fatty acid polyoxyethylene ester, nonylphenol ethoxylates, alkylphenol polyoxyethylene ethers, polyether type surfactants, fatty alcohol polyoxyethylene ether; wherein, the number of carbon atoms of fatty acid in said fatty acid polyoxyethylene ester is preferably from 13 to 20; the number of carbon atoms of the alkyl group in said alkylphenol polyoxyethylene ether is preferably from 10 to 20; the number of carbon atoms of the fatty alcohol in said fatty alcohol polyoxyethylene ether is preferably from 10 to 20; the polymerization degree of polyoxyethylene in fatty acid polyoxyethylene ester, alkylphenol polyoxyethylene ethers and fatty alcohol polyoxyethylene ether is preferably from 7 to 20, more preferably from 7 to 15, respectively; and said polyether type surfactant is preferably a polyether-based surfactant in which polyoxyethylene-polyoxypropylene is copolymerized. More preferably, said anionic surfactant in the present invention is sodium dodecylbenzenesulfonate and said nonionic surfactant is associative non-crosslinking fracturing thickener GRF-2B, GRF-3C produced by SiChuan Guangya Polymer Chemical Co. Ltd..

[0044] The clay stabilizer in slick water can inhibit the water swelling of the clay minerals and prevent the clay minerals in the reservoir from experiencing swelling in the fracturing fluid thereby avoiding the damage to reservoir. The adding amount of clay stabilizer is generally related to the clay mineral content in the reservoir. The clay stabilizer matched with the associative polymer thickener in the slick water is preferably one or more of potassium chloride, ammonium chloride and nonionic organic clay stabilizers; more preferably, potassium chloride and/or ammonium chloride.

[0045] Said water solvent can be clear water or flowback liquid after treatment, and there is no particular limit. Said flowback liquid after treatment is the flowback liquid after flocculation, sedimentation, filtration and other simple

treatments, which is well-known to one of ordinary skill in the art and there is no particularly limit.

[0046] In some embodiments of the present invention, by mass percentage, said slick water comprises 0.08% of friction-reducing agent, 0.2% of enhancer, 1% of clay stabilizer, and water solvent as the balance.

[0047] Since the slick water of present invention is simple in composition, so the flowback liquid can be re-formulated to fracturing fluid after flocculation, sedimentation, filtration and other simple treatments, improving the utilization rate of fracturing water. When using flowback liquid to prepare slick water, because there are still a small amount of additives therein, the performance may not meet the application requirements, it is also necessary to add a variety of additives to achieve the property of slick water. By mass percentage, said slick water comprises 0.02%~0.1% of friction-reducing agent, 0.05%~0.25% of enhancer, 0.2%~1.5% of clay stabilizer, and flowback liquid after treatment as the balance. In some embodiments of the present invention, said slick water comprises 0.06% of friction-reducing agent, 0.15% of enhancer, 0.5% of clay stabilizer, and flowback liquid after treatment as the balance.

[0048] According to the present invention, said multi-functional hybrid fracturing fluid system also contains high viscosity sand carrying fluid. By mass percentage, said high viscosity sand carrying fluid comprises 0.2%~0.75% of thickener, 0.1%~0.4% of enhancer, 0.3%~2% of clay stabilizer, 0.03%~0.4% of gel breaker, and water solvent as the balance.

[0049] Said thickener in the high viscosity sand carrying fluid is the same associative polymer as the friction-reducing agent which is described above and will not be described further herein. Said thickener in the high viscosity sand carrying fluid is one or more of anionic surfactants and nonionic surfactants; said water solvent in the high viscosity sand carrying fluid is clear water or flowback liquid after treatment; and said gel breaker is one or more of potassium persulfate,

ammonium persulfate and encapsulated oxidative gel breaker.

[0050] Herein, said thickener, enhancer and clay stabilizer in the high viscosity sand carrying fluid are the same as described above and will not be described further.

5 [0051] The content of said enhancer in the high viscosity sand carrying fluid of the present invention is preferably 0.25%~0.75%, more preferably 0.35%~0.6%, even more preferably 0.35%~0.4%. As a thickener in the high viscosity sand carrying fluid, associative polymer can be used to improve the viscosity of the liquid to meet the requirements of on-site sand carrying. The adding amount of
10 the enhancer increases with the increase of oil and gas reservoir temperature in which it is used. It is used in conjunction with some surfactants to increase the sand carrying performance of sand carrying fluid, while also reducing the amount of the associative polymer, thereby saving costs.

[0052] The enhancer in the high viscosity sand carrying fluid can reduce the
15 surface tension of sand carrying fluid, while also improving its sand carrying performance. The content of said enhancer in the high viscosity sand carrying fluid is preferably 0.15%~0.4%, more preferably 0.2%~0.3%.

[0053] The content of said clay stabilizer in the high viscosity sand carrying fluid is preferably 0.5%~1.5%, more preferably 0.8%~1.2%.

20 [0054] Gel breaker is used to hydrate and decompose the polymer after fracturing, reducing the viscosity of the sand carrying fluid, so that the liquid entering the formation after pressure can be flowback, thus reducing damage to the formation. The amount of gel breaker is generally determined by the formation temperature, decreasing with high formation temperature, and increasing with low formation
25 temperature. The content of said oxidative gel breaker in the present invention is preferably 0.05%~0.3%, more preferably 0.05%~0.25%, even more preferably 0.05%~0.2%, and most preferably 0.08%~0.15%.

[0055] In some embodiments of the present invention, by mass percentage, said

high viscosity sand carrying fluid comprises 0.35% thickener, 0.2% enhancer, 1% clay stabilizer, 0.15% oxidative gel breaker, and water solvent as the balance.

[0056] In some other embodiments of the present invention, by mass percentage, said high viscosity sand carrying fluid comprises 0.4% of thickener, 0.3% of enhancer, 1% of clay stabilizer, 0.08% of oxidative gel breaker, and water solvent as the balance.

[0057] Since the high viscosity sand carrying fluid of present invention is simple in composition, so the flowback liquid can be re-formulated to high viscosity sand carrying fluid after flocculation, sedimentation, filtration and other simple treatments, improving the utilization rate of fracturing water. When using flowback liquid to prepare high viscosity sand carrying fluid, because there are still a small amount of additives therein, the performance may not meet the application requirements, it is also necessary to add a variety of additives to achieve the property of high viscosity sand carrying fluid. By mass percentage, said high viscosity sand carrying fluid comprises 0.2%~0.65% of thickener, 0.1%~0.3% of enhancer, 0.3%~1.5% of clay stabilizer, 0.03%~0.4% of oxidative gel breaker, and flowback liquid after treatment as the balance.

[0058] In some embodiments of the present invention, said high viscosity sand carrying fluid comprises 0.32% of thickener, 0.15% of enhancer, 0.5% of clay stabilizer, 0.2% of oxidative gel breaker, and flowback liquid after treatment as the balance.

[0059] In some other embodiments of the present invention, said high viscosity sand carrying fluid comprises 0.37% of thickener, 0.25% of enhancer, 0.5% clay stabilizer, 0.08% oxidative gel breaker, and flowback liquid after treatment as the balance.

[0060] The multi-functional hybrid fracturing fluid system of the present invention comprises slick water and high viscosity sand carrying fluid. By adding low concentration of associative polymer as a friction-reducing agent in the

water, in combination with the corresponding enhancer and clay stabilizer, the slick water can be prepared; by adding high concentrations of associative polymer as a thickener in the water, in combination with the corresponding enhancer, clay stabilizer and oxidative gel breaker, the sand carrying fluid can be prepared, thus a multi-purpose function of an associative polymer is achieved. The components of slick water and high viscosity sand carrying fluid are basically the same, which can improve the quality control of materials, simplify the preparation process, and save manpower and material resources in the fluid preparation.

[0061] The slick water in this multi-functional hybrid fracturing fluid system has a better performance of sand suspending, and can reduce the amount of sand carrying fluid in the slick water, thus reducing the total fluid amount in fracturing operation. The viscosity of the slick water is slightly higher than that of the conventional slick water, and can generate a higher net pressure, which is favorable to the shear and slip of the natural fractures and the formation and extension of the complex fractures. At the same time, the slick water has a high friction reduction rate and a low operation friction, thus reducing the operation pressure, meeting the requirements of large displacement operation.

[0062] The high viscosity sand carrying fluid in the multi-functional hybrid fracturing fluid system of the present invention belongs to non-cross linking fracturing fluid which has no need for cross-linking. It has advantages of high shearing resistance, low operation friction and low damage rate to formation. These can solve the problem of poor shearing resistance, high operation friction and high residue content caused by the gel fracturing fluid system.

[0063] At the mean time, the slick water and the high viscosity sand carrying fluid in the multi-functional hybrid fracturing fluid system are simple in formula, less additive type, have an easy preparation process. The flowback liquid can be re-formulated to fracturing fluid after flocculation, sedimentation, filtration and other simple treatments, improving the utilization rate of fracturing water.

[0064] The present invention further provides a method for preparing the slick water in the multi-functional hybrid fracturing fluid system, comprising mixing 0.02%~0.15% of friction-reducing agent, 0.05%~0.3% of enhancer, 0.2%~2% of clay stabilizer by mass percentage and water as the balance, stirring, to obtain the slick water.

[0065] Herein, said friction-reducing agent, enhancer, clay stabilizer and water are the same as described above and will not be described further.

[0066] Preferably, friction-reducing agent, enhancer, and clay stabilizer are added to water, wherein the friction-reducing agent is added before the addition of the clay stabilizer. More preferably, friction-reducing agent, enhancer and clay stabilizer are added to water successively. Even most preferably, the slick water is prepared by adding the friction-reducing agent to water, stirring 2~3min, adding enhancer and clay stabilizer, and stirring 1~2min. Adding clay stabilizer before the addition of friction-reducing agent will lower the viscosity of the slick water.

[0067] The present invention further provides a method for preparing a method for preparing the high viscosity sand carrying fluid in the multi-functional hybrid fracturing fluid system, comprising mixing 0.2%~0.75% of thickener, 0.1%~0.4% of enhancer, 0.3%~2% of clay stabilizer, 0.03%~0.4% of oxidative gel breaker by mass percentage and water as the balance, stirring, to obtain the high viscosity sand carrying fluid.

[0068] Herein, said thickener, enhancer, clay stabilizer, oxidative gel breaker and water are the same as described above and will not be described further.

[0069] Preferably, thickener, enhancer, clay stabilizer, and oxidative gel breaker are added to water, wherein the thickener is added before the addition of the clay stabilizer. More preferably, the thickener is added to water first, then the enhancer and the clay stabilizer is added, and the oxidative gel breaker is added finally. Even most preferably, the high viscosity sand carrying fluid is prepared by adding thickener to water and stirring for 5~6min; adding enhancer and clay stabilizer,

further stirring for 2~3min; adding oxidative gel breaker finally and stirring evenly.

[0070] The multi-functional hybrid fracturing fluid system of the present invention is simple in preparation method and relatively of low cost.

5 [0071] The present invention also provides use of the multi-functional hybrid fracturing fluid system in the reformation of tight hydrocarbon reservoir and shale hydrocarbon reservoir.

[0072] For further describe the present invention, the multi-functional hybrid fracturing fluid system provided by the present invention will be described in
10 detail with reference to the following examples.

[0073] All the reagents in the following examples are available commercially.

Example 1

[0074] The associative polymer used as a friction-reducing agent is 0.05% by
15 weight of hydrophobically modified hydroxyethyl cellulose; the enhancer is 0.2% by weight of sodium dodecylbenzenesulfonate (sodium dodecylbenzenesulfonate); and the clay stabilizer is 1% by weight of KCl.

[0075] Water (clear water) for preparing the slick water was weighted by a balance and added into a stirrer. The speed of the stirrer was adjusted until the
20 bottom axle of the stirrer can be seen. Then the associative polymer was added slowly into the stirrer to ensure that the associative polymer was dispersed evenly without agglomeration phenomenon, stirred for 2~3min; then the enhancer and clay stabilizer were added, and further stirred for 1~2min, to obtain the slick water.

25 [0076] The friction of the slick water obtained in example 1 was tested (25°C) to obtain a curve showing the relationship between friction and displacement as shown in Fig. 1, wherein D is the slick water obtained in example 1. It can be seen

from Fig. 1, with the increase of displacement, the friction of the slick water was much lower than that of the clear water, showing that the slick water prepared with the associative polymer has a better friction reduction performance.

[0077] The settling velocity of the proppant in the slick water obtained in example 1 was tested and compared with 0.1% by weight of anionic polyacrylamides slick water. 100 ml of slick water was taken by a 100 ml cylinder. 10 carbo medium density ceramic particles of 40~60 mesh were selected. The settling time of the ceramic particles in the slick water was recorded with a stopwatch, the settling velocity of the ceramic particles was calculated and the result was shown in Table 1. As shown in Table 1, the settling velocity of the ceramic particles in the slick water obtained in example 1 is slower than that in anionic polyacrylamides slick water or clear water, which demonstrated that the slick water obtained in example 1 has a better sand suspending performance than clear water and anionic polyacrylamides slick water.

[0078] The settling time of the proppant with different sand ratios in the slick water obtained in example 1 was tested and compared with 0.1% by weight of anionic polyacrylamides slick water. The settling time is used to evaluate the sand suspending performance of slick water. 200 ml slick water was weighed and added into 250 ml beaker and stirred with a vertical stirrer (600rpm/min); carbo medium density ceramic particles (40~60 mesh) at different sand ratios were measured by cylinder and added into the beaker. After the ceramic particles and slick water were mixed well, stirring was stopped and the time was recorded by a stopwatch to record the time when all particles fell to the bottom of the beaker. The results were shown in Table 2. It can be shown from Table 2 that the settling time of the proppant with 9% sand ratio in the slick water obtained in example 1 is comparable to that of the proppant with 6% sand ratio in 0.1% by weight of anionic polyacrylamides slick water, which demonstrated that the slick water obtained in example 1 has a better sand suspending performance than 0.1% by weight of anionic polyacrylamides slick water.

Example 2

[0079] The associative polymer used as a friction-reducing agent is 0.08% of associative non-crosslinking fracturing thickener GRF-1C by weight percentage, produced by Sichuan Guangya Polymer Chemical Co. Ltd.; the enhancer is 0.2% of GRF-1C by weight percentage; and the clay stabilizer is 1% of KCl by weight percentage.

[0080] Water (clear water) for preparing the slick water was weighted by a balance and added into a stirrer. The speed of the stirrer was adjusted until the bottom axle of the stirrer can be seen. Then the associative polymer was added slowly into the stirrer to ensure that the associative polymer was dispersed evenly without agglomeration phenomenon, stirred for 2~3min; then the enhancer and clay stabilizer were added, and further stirred for 1~2min, to obtain the slick water.

[0081] The friction of the slick water obtained in example 2 was tested (25°C) to obtain the graph as shown in Fig.1, wherein B is the slick water obtained in example 2.

[0082] It can be seen from the figure that, with the increase of displacement, the friction of the slick water prepared with the associative polymer was much lower than that of the clear water, which demonstrated a better friction reduction performance.

[0083] The friction reduction rate at different displacements of the slick water obtained in example 2 was tested (25°C) to obtain the friction reduction rate curve as shown in Fig. 2, wherein B is the slick water obtained in example 2, and D is the 0.1% of anionic polyacrylamides slick water. It can be seen from Fig. 2 that, with the increase of displacement, the friction reduction rate of the slick water prepared with the associative polymer first increased and tended to be gentle, then gradually declined, and the maximum friction reduction rate was 65%. It can also

be seen from Fig. 2 that the friction reduction rate of the slick water prepared with the associative polymer is superior to that of anionic polyacrylamides slick water.

[0084] The surface tension of the slick water obtained in example 2 was tested, and the result was shown in Table 3.

5

Example 3

[0085] The associative polymer used as a friction-reducing agent is 0.1% by weight of associative non-crosslinking fracturing thickener GRF-1H, produced by Sichuan Guangya Polymer Chemical Co. Ltd.; the enhancer is 0.15% by weight of GRF-2B; and the clay stabilizer is 1% by weight of KCl.

[0086] Water (clear water) for preparing the slick water was weighted by a balance and added into a stirrer. The speed of the stirrer was adjusted until the bottom axle of the stirrer can be seen. Then the associative polymer was added slowly into the stirrer to ensure that the associative polymer was dispersed evenly without agglomeration phenomenon, stirred for 2~3min; then the enhancer and clay stabilizer were added, and further stirred for 1~2min, to obtain the slick water.

[0087] The friction of the slick water obtained in example 3 was tested (25°C) to obtain the graph showing the relationship between friction and displacement as shown in Fig.1, wherein C is the slick water obtained in example 3, A is the 0.1% of anionic polyacrylamides slick water by weight percentage and E is clear water. It can be known from Fig. 1 that, with the increase of displacement, the friction of the slick water prepared with the associative polymer increased, but the rate of increase was much smaller than that of the clear water. The friction of the slick water prepared with the associative polymer was lower than that of the slick water prepared with the polyacrylamides, thus a better friction reduction performance was achieved.

[0088] The settling velocity of the proppant in the slick water obtained in

example 3 was tested and compared with 0.1% by weight of anionic polyacrylamides slick water. 100 ml slick water was taken by a 100 ml cylinder. 10 carbo medium density ceramic particles of 40~60 mesh were selected. The settling time of the ceramic particles in the slick water was recorded with a stopwatch, the settling velocity of the ceramic particles was calculated and the result was shown in Table 1. As shown in Table 1, the settling velocity of the ceramic particles in the slick water obtained in example 3 is slower than that in anionic polyacrylamides slick water or clear water, which demonstrated that the slick water obtained in example 3 has a better sand suspending performance than clear water and anionic polyacrylamides slick water.

[0089] The settling time of the proppant with different sand ratios in the slick water obtained in example 3 was tested and compared with 0.1% by weight of anionic polyacrylamides slick water. The settling time is used to evaluate the sand suspending performance of slick water. 200 ml slick water was weighed and added into 250 ml beaker and stirred with a vertical stirrer (600rpm/min); carbo medium density ceramic particles (40~60 mesh) at different sand ratios were measured by cylinder and added into the beaker. After the ceramic particles and slick water were mixed well, stirring was stopped and the time was recorded by a stopwatch to record the time when all particles fell to the bottom of the beaker. The results were shown in Table 2. As shown in Table 2, the settling time of the proppant with 9% sand ratio in the slick water obtained in example 3 is comparable to that of the proppant with 6% sand ratio in 0.1% by weight of anionic polyacrylamides slick water, which demonstrated that the slick water obtained in example 3 has a better sand suspending performance than 0.1% by weight of anionic polyacrylamides slick water.

[0090] At present, the average sand carrying rate in anionic polyacrylamides slick water is 6%. According to the data in Table 4, the average sand ratio in the slick water prepared by associative polymer can be increased to 9%. Therefore, under the condition of the same addition amount of sand, the

amount of sand carrying fluid used can be reduced by 33.3% if the slick water prepared with associative polymer is used to carry sand.

Table 1. test results of settling velocity of the proppant in different slick water.

Slick water	Clear water	Example 3	Example 1	0.1 wt% anionic polyacrylamides slick water
Settling velocity mm/s	100.01	5.64	6.16	17.24

5 Table 2. Settling time of the proppant with different sand ratios in different slick water.

	0.1 wt% anionic polyacrylamides slick water				Example 3			Example 1	
Sand ratio (%)	6	6	7	9	6	7	9	6	7
Settling time (s)	10.09	14.55	13.43	10.19	12.21	11.5	9.89		

Example 4

10 [0091] The associative polymer used as a friction-reducing agent is 0.08% by weight of associative non-crosslinking fracturing thickener GRF-1C (effective concentration of the associative polymer), produced by Sichuan Guangya Polymer Chemical Co. Ltd.; the enhancer is 0.1% by weight of GRF-2C; and the clay stabilizer is 1% by weight of KCl.

[0092] Water (clear water) for preparing the slick water was weighted by a

balance and added into a stirrer. The speed of the stirrer was adjusted until the bottom axle of the stirrer can be seen. Then the associative polymer was added slowly into the stirrer to ensure that the associative polymer was dispersed evenly without agglomeration phenomenon, stirred for 2~3min; then the enhancer and clay stabilizer were added, and further stirred for 1~2min, to obtain the slick water.

[0093] The surface tension of the slick water obtained in example 4 was tested, and the result was shown in Table 3.

Example 5

[0094] The associative polymer used as a friction-reducing agent is 0.08% by weight of associative non-crosslinking fracturing thickener GRF-1C (effective concentration of the associative polymer), produced by Sichuan Guangya Polymer Chemical Co. Ltd.; the enhancer is 0.3% by weight of GRF-2C; and the clay stabilizer is 1% by weight of KCl.

[0095] Water (clear water) for preparing the slick water was weighted by a balance and added into a stirrer. The speed of the stirrer was adjusted until the bottom axle of the stirrer can be seen. Then the associative polymer was added slowly into the stirrer to ensure that the associative polymer was dispersed evenly without agglomeration phenomenon, stirred for 4~5min; then the enhancer and clay stabilizer were added, and further stirred for 1~3min, to obtain the slick water.

[0096] The surface tension of the slick water obtained in example 5 was tested, and the result was shown in Table 3. It can be known from Table 1 that with the increase of the amount of the enhancer added, the surface tension of the slick water reduced.

Table 3. Test results of surface tension of slick water

	Comparative example 1	Example 4	Example 2	Example 5
addition amount of the enhancer GRF-2C (wt%)	0	0.1	0.2	0.3
surface tension (mN/m)	32.6	28.3	27.5	26.7

Example 6

[0097] The associative polymer used as a friction-reducing agent is 0.08% by weight of associative non-crosslinking fracturing thickener GRF-1H, produced by Sichuan Guangya Polymer Chemical Co. Ltd.; the enhancer is 0.1% by weight of GRF-2B; and the clay stabilizer is 1% by weight of KCl.

[0098] Water (clear water) for preparing the slick water was weighted by a balance and added into a stirrer. The speed of the stirrer was adjusted until the bottom axle of the stirrer can be seen. Then the associative polymer was added slowly into the stirrer to ensure that the associative polymer was dispersed evenly without agglomeration phenomenon, stirred for 2~3min; then the enhancer and clay stabilizer were added, and further stirred for 1~2min, to obtain the slick water.

[0099] The surface tension of the slick water obtained in example 6 was tested, and the result was shown in Table 4. It can be known from Table 2 that with the increase of the amount of the enhancer added, the surface tension of the slick water reduced.

Example 7

[00100] The associative polymer used as a friction-reducing agent is 0.08% by weight of associative non-crosslinking fracturing thickener GRF-1H, produced by Sichuan Guangya Polymer Chemical Co. Ltd.; the enhancer is 0.2% by weight of

GRF-2B; and the clay stabilizer is 1% by weight of KCl.

[00101] Water (clear water) for preparing the slick water was weighted by a balance and added into a stirrer. The speed of the stirrer was adjusted until the bottom axle of the stirrer can be seen. Then the associative polymer was added slowly into the stirrer to ensure that the associative polymer was dispersed evenly without agglomeration phenomenon, stirred for 2~3min; then the enhancer and clay stabilizer were added, and further stirred for 1~2min, to obtain the slick water.

[00102]The surface tension of the slick water obtained in example 7 was tested, and the result was shown in Table 4. It can be known from Table 2 that with the increase of the amount of the enhancer added, the surface tension of the slick water reduced.

Example 8

[00103]The associative polymer used as a friction-reducing agent is 0.08% by weight of associative non-crosslinking fracturing thickener GRF-1H, produced by Sichuan Guangya Polymer Chemical Co. Ltd.; the enhancer is 0.3% by weight of GRF-2B; and the clay stabilizer is 1% by weight of KCl.

[00104] Water (clear water) for preparing the slick water was weighted by a balance and added into a stirrer. The speed of the stirrer was adjusted until the bottom axle of the stirrer can be seen. Then the associative polymer was added slowly into the stirrer to ensure that the associative polymer was dispersed evenly without agglomeration phenomenon, stirred for 2~3min; then the enhancer and clay stabilizer were added, and further stirred for 1~2min, to obtain the slick water.

[00105]The surface tension of the slick water obtained in example 8 was tested, and the result was shown in Table 4. It can be known from Table 2 that with the increase of the amount of the enhancer added, the surface tension of the slick

water reduced.

Table 4. Test results of surface tension of the slick water

	Comparative example 1	Example 6	Example 7	Example 8
addition amount of				
the enhancer	0	0.1	0.2	0.3
GRF-2B (wt%)				
surface tension				
(mN/m)	32.6	27.3	26.5	25.7

Example 9

5 [00106]The associative polymer used as a friction-reducing agent is 0.06% by weight of associative non-crosslinking fracturing thickener GRF-1C, produced by Sichuan Guangya Polymer Chemical Co. Ltd.; the enhancer is 0.15% by weight of GRF-2C; and the clay stabilizer is 1% by weight of KCl.

10 [00107] Water for preparing the slick water (flowback liquid after treatment) was weighted by a balance and added into a stirrer. The speed of the stirrer was adjusted until the bottom axle of the stirrer can be seen. Then the associative polymer was added slowly into the stirrer to ensure that the associative polymer was dispersed evenly without agglomeration phenomenon, stirred for 2~3min; then the enhancer and clay stabilizer were added, and further stirred for 1~2min,
15 to obtain the slick water.

[00108]The friction reduction rate at different displacements of the slick water obtained in example 9 was tested (25°C) to obtain the friction reduction rate curve as shown in Fig. 2, wherein F is the slick water obtained in example 9. It can be seen from Fig. 2 that, the friction reduction rate of the slick water obtained in
20 example 9 first increased and then tended to be gentle, and the maximum friction

reduction rate was 64%. It can also be seen from Fig. 2 that the friction reduction rate of the slick water obtained in example 9 is higher than that of anionic polyacrylamides slick water, and is substantively in line with that of the slick water prepared with clear water.

5

Example 10

[00109] The associative polymer used as a friction-reducing agent is 0.06% by weight of associative non-crosslinking fracturing thickener GRF-1C, produced by Sichuan Guangya Polymer Chemical Co. Ltd.; the enhancer is 0.15% by weight
10 of GRF-2C; and the clay stabilizer is 0.5% by weight of KCl.

[00110] Water for preparing the slick water (flowback liquid after treatment) was weighted by a balance and added into a stirrer. The speed of the stirrer was adjusted until the bottom axle of the stirrer can be seen. Then the associative polymer was added slowly into the stirrer to ensure that the associative polymer
15 was dispersed evenly without agglomeration phenomenon, stirred for 2~3min; then the enhancer and clay stabilizer were added, and further stirred for 1~2min, to obtain the slick water.

[00111] The friction reduction rate of the slick water obtained in example 10 was tested. The friction reduction rates tested were basically the same as the friction
20 reduction rate of the slick water obtained in example 2. Table 5 is the composition list of the friction reduction waters having basically the same friction reduction rate.

[00112] It can be seen from Table 5 that when flowback liquid is used to prepare the friction reduction water, the addition amount of the additives decreased in
25 varying degrees.

Table 5. Composition list of the friction reduction water with the same friction reduction rate

	water for preparation	associative polymer GRF-1C	enhancer GRF-2C	KCl	note
Example 2	clear water	0.8 t	2 t	10 t	
Example 11	Flowback liquid after treatment	0.6 t	1.5 t	5 t	note: to prepare 1000m ³ slick water as an example
	reduction rate, %	25%	25%	50%	

Example 11

[00113]The associative polymer thickener is 0.4% by weight of hydrophobically modified hydroxyethyl cellulose; the enhancer is 0.15% by weight of sodium dodecylbenzenesulfonate; and the clay stabilizer is 1% by weight of KCl.

[00114]Water for preparing the high viscosity sand carrying fluid (clear water) was weighted by a balance and added into a stirrer. The speed of the stirrer was adjusted until the bottom axle of the stirrer can be seen. Then the associative polymer was added slowly into the stirrer to ensure that the associative polymer was dispersed evenly without agglomeration phenomenon, stirred for 4~5min; then the enhancer and clay stabilizer were added, further stirred for 2~3min, stirred evenly to obtain the high viscosity sand carrying fluid.

[00115]The shearing resistance of the high viscosity sand carrying fluid obtained in example 11 was tested. Huck RS6000 rheometer was used, and the shearing resistance of the sand carrying fluid was tested under the condition of 90°C, 170 s⁻¹. A shearing resistance curve as showed in FIG. 3 was obtained, wherein a is the high viscosity sand carrying fluid obtained in example 11. It can be known from Fig. 3 that, when the temperature was constant, along with the shearing process, the viscosity of the high viscosity sand carrying fluid basically did not change, showing that the high viscosity sand carrying fluid has a better shearing resistance performance.

[00116]0.1% of oxidative gel breaker ammonium persulfate was added to the high viscosity sand carrying fluid obtained in example 11. The residue amount of the high viscosity sand carrying fluid obtained in example 11 was tested, and the result was shown in Table 6. It can be known from Table 6 that the residue
 5 amount of the high viscosity sand carrying fluid obtained in example 11 was low, showing that the high viscosity sand carrying fluid obtained in example 11 has characteristics of low residue and cleanness.

[00117]Core matrix damage rate of the high viscosity sand carrying fluid obtained in example 11 was tested and result was shown in Table 7. It can be
 10 known from Table 7 that the high viscosity sand carrying fluid obtained in example 11 has low core matrix damage rate, showing that it has a characteristic of low damage.

Example 12

15 [00118]The associative polymer thickener is 0.37% by weight of associative non-crosslinking fracturing thickener GRF-1H, produced by Sichuan Guangya Polymer Chemical Co. Ltd.; the enhancer is 0.12% by weight of GRF-2B; and the clay stabilizer is 1% by weight of KCl.

[00119]Water for preparing the high viscosity sand carrying fluid (clear water)
 20 was weighted by a balance and added into a stirrer. The speed of the stirrer was adjusted until the bottom axle of the stirrer can be seen. Then the associative polymer was added slowly into the stirrer to ensure that the associative polymer was dispersed evenly without agglomeration phenomenon, stirred for 4~5min; then the enhancer and clay stabilizer were added, further stirred for 2~3min,
 25 stirred evenly to obtain the high viscosity sand carrying fluid.

[00120]The shearing resistance of the high viscosity sand carrying fluid obtained in example 12 was tested. Huck RS6000 rheometer was used, and the shearing resistance of the sand carrying fluid was tested under the condition of 90°C, 170

s⁻¹. A shearing resistance curve as showed in Fig. 3 was obtained, wherein C is the high viscosity sand carrying fluid obtained in example 12. It can be known from Fig. 3 that, when the temperature was constant, along with the shearing process, the viscosity of the high viscosity sand carrying fluid basically did not change, showing that the high viscosity sand carrying fluid has a better shearing resistance performance.

[00121]The static suspending performance of the high viscosity sand carrying fluid obtained in example 12 was tested. 30ml of carbo medium density ceramic particles (20~40 mesh) were mixed evenly with 100ml of the high viscosity sand carrying fluid obtained in example 12, and transferred to a cylinder with plug. The cylinder was placed in an oven at 90°C constant temperature and kept warm. The settling times of ceramic particles were observed and result was shown in Fig. 4.C. It can be known from Fig. 4 that the addition of enhancer can increase the sand suspending performance of the high viscosity sand carrying fluid.

Example 13

[00122]The associative polymer thickener is 0.4% by weight of associative non-crosslinking fracturing thickener GRF-1C (effective concentration of the associative polymer), produced by Sichuan Guangya Polymer Chemical Co. Ltd.; the enhancer is 0.35% by weight of GRF-2C; and the clay stabilizer is 1% by weight of KCl.

[00123]Water for preparing the high viscosity sand carrying fluid (clear water) was weighted by a balance and added into a stirrer. The speed of the stirrer was adjusted until the bottom axle of the stirrer can be seen. Then the associative polymer was added slowly into the stirrer to ensure that the associative polymer was dispersed evenly without agglomeration phenomenon, stirred for 4~5min; then the enhancer and clay stabilizer were added, further stirred for 2~3min, stirred evenly to obtain the high viscosity sand carrying fluid.

[00124]The shearing resistance of the high viscosity sand carrying fluid obtained in example 13 was tested. Huck RS6000 rheometer was used, and the shearing resistance of the sand carrying fluid was tested under the condition of 90°C, 170 s⁻¹. A shearing resistance curve as showed in Fig. 3 was obtained, wherein C is the high viscosity sand carrying fluid obtained in example 13. It can be known from Fig. 3 that, when the temperature was constant, along with the shearing process, the viscosity of the high viscosity sand carrying fluid basically did not change, showing that the high viscosity sand carrying fluid has a better shearing resistance performance.

[00125]0.1% of oxidative gel breaker ammonium persulfate was added to the high viscosity sand carrying fluid obtained in example 13. The residue amount of the high viscosity sand carrying fluid obtained in example 13 was tested. The result was shown in Table 6. It can be known from Table 6 that the residue amount of the high viscosity sand carrying fluid obtained in example 13 was low, showing that the high viscosity sand carrying fluid obtained in example 13 has characteristics of low residue and cleanness.

[00126]Core matrix damage rate of the high viscosity sand carrying fluid obtained in example 13 was tested and result was shown in Table 7. It can be known from Table 7 that the high viscosity sand carrying fluid obtained in example 13 has low core matrix damage rate, showing that it has a characteristic of low damage.

Example 14

[00127]The associative polymer thickener is 0.37% by weight of associative non-crosslinking fracturing thickener GRF-1H, produced by Sichuan Guangya Polymer Chemical Co. Ltd.; the enhancer is 0.15% by weight of GRF-2B; the clay stabilizer is 1% by weight of KCl; and the oxidative gel breaker is 0.15% by weight of ammonium persulfate.

[00128] Water for preparing the high viscosity sand carrying fluid (clear water) was weighted by a balance and added into a stirrer. The speed of the stirrer was adjusted until the bottom axle of the stirrer can be seen. Then the associative polymer was added slowly into the stirrer to ensure that the associative polymer was dispersed evenly without agglomeration phenomenon, stirred for 4~5min; then the enhancer and clay stabilizer were added, further stirred for 2~3min, stirred evenly to obtain the sand carrying fluid.

[00129] The static suspending performance of the high viscosity sand carrying fluid obtained in example 14 was tested. 30ml of carbo medium density ceramic particles (20~40 mesh) were mixed evenly with 100ml of the high viscosity sand carrying fluid obtained in example 14, and transferred to a cylinder with plug. The cylinder was placed in an oven at 90°C constant temperature and kept warm. The settling times of ceramic particles were observed and result was shown in Fig. 4.D. It can be known from Fig. 4 that the addition of enhancer can increase the sand suspending performance of the sand carrying fluid. With the increase of the addition amount of the enhancer, the static sand suspending performance of the high viscosity sand carrying fluid first enhanced and then attenuated.

Example 15

[00130] The associative polymer thickener is 0.4% by weight of associative non-crosslinking fracturing thickener GRF-1C (effective concentration of the associative polymer), produced by Sichuan Guangya Polymer Chemical Co. Ltd.; the enhancer is 0.2% by weight of GRF-2C; and the clay stabilizer is 1% by weight of KCl.

[00131] Water for preparing the high viscosity sand carrying fluid (clear water) was weighted by a balance and added into a stirrer. The speed of the stirrer was adjusted until the bottom axle of the stirrer can be seen. Then the associative polymer was added slowly into the stirrer to ensure that the associative polymer

was dispersed evenly without agglomeration phenomenon, stirred for 4~5min; then the enhancer and clay stabilizer were added, further stirred for 2~3min, stirred evenly to obtain the high viscosity sand carrying fluid.

[00132]The static suspending performance of the sand carrying fluid obtained in example 15 was tested. 30ml of carbo medium density ceramic particles (20~40 mesh) were mixed evenly with 100ml of the high viscosity sand carrying fluid obtained in example 15, and transferred to a cylinder with plug. The cylinder was placed in an oven at 90°C constant temperature and kept warm. The settling times of ceramic particles were observed and result was shown in FIG. 5.B. It can be known from Fig. 5 that the addition of enhancer can increase the sand suspending performance of the sand carrying fluid.

Example 16

[00133]The associative polymer thickener is 0.4% by weight of associative non-crosslinking fracturing thickener GRF-1C (effective concentration of the associative polymer), produced by SiChuan Guangya Polymer Chemical Co. Ltd.; the enhancer is 0.3% by weight of GRF-2C; and the clay stabilizer is 1% by weight of KCl.

[00134]Water for preparing the high viscosity sand carrying fluid (clear water) was weighted by a balance and added into a stirrer. The speed of the stirrer was adjusted until the bottom axle of the stirrer can be seen. Then the associative polymer was added slowly into the stirrer to ensure that the associative polymer was dispersed evenly without agglomeration phenomenon, stirred for 4~5min; then the enhancer and clay stabilizer were added, further stirred for 2~3min, stirred evenly to obtain the sand carrying fluid.

[00135]The static suspending performance of the sand carrying fluid obtained in example 16 was tested. 30ml of carbo medium density ceramic particles (20~40 mesh) were mixed evenly with 100ml of the sand carrying fluid obtained in

example 16, and transferred to a cylinder with plug. The cylinder was placed in an oven at 90°C constant temperature and kept warm. The settling times of ceramic particles were observed and result was shown in Fig. 5.C. It can be known from Fig. 5 that the addition of enhancer can increase the sand suspending performance of the sand carrying fluid. With the increase adding amount of enhancer, the static sand suspending performance of the high viscosity sand carrying fluid first enhanced and then attenuated.

Example 17

[00136]The associative polymer thickener is 0.4% by weight of hydrophobically modified hydroxyethyl cellulose; the enhancer is 0.15% of sodium dodecylbenzenesulfonate by weight percentage; the clay stabilizer is 1% by weight of KCl; and the oxidative gel breaker is 0.15% by weight of ammonium persulfate.

[00137]Water for preparing the high viscosity sand carrying fluid (clear water) was weighted by a balance and added into a stirrer. The speed of the stirrer was adjusted until the bottom axle of the stirrer can be seen. Then the associative polymer was added slowly into the stirrer to ensure that the associative polymer was dispersed evenly without agglomeration phenomenon, stirred for 4~5min; then the enhancer and clay stabilizer were added, further stirred for 2~3min, stirred evenly to obtain the sand carrying fluid.

[00138]The friction reduction rate at different displacements of the sand carrying fluid obtained in example 17 was tested. The friction reduction rate curve obtained is shown as Fig. 6, wherein F1 is the sand carrying fluid obtained in example 17. It can be seen from Fig. 6, at high displacement, the friction reduction rate of the sand carrying fluid obtained in example 17 was greater than 50%, showing a low friction characteristic.

Example 18

[00139]The associative polymer thickener is 0.35% by weight of hydrophobically modified hydroxyethyl cellulose by weight; the enhancer is 0.1% by weight of sodium dodecylbenzenesulfonate; the clay stabilizer is 1% by weight of KCl; and
 5 the oxidative gel breaker is 0.15% by weight of ammonium persulfate.

[00140]Water for preparing the high viscosity sand carrying fluid (flowback liquid after treatment) was weighted by a balance and added into a stirrer. The speed of the stirrer was adjusted until the bottom axle of the stirrer can be seen. Then the associative polymer was added slowly into the stirrer to ensure that the
 10 associative polymer was dispersed evenly without agglomeration phenomenon, stirred for 4~5min; then the enhancer and clay stabilizer were added, further stirred for 2~3min, stirred evenly to obtain the sand carrying fluid.

[00141]The friction reduction rate at different displacements of the sand carrying fluid obtained in example 18 was tested. The friction reduction rate curve
 15 obtained is shown as Fig. 6, wherein F2 is the sand carrying fluid obtained in example 18. It can be seen from Fig. 6, at high displacement, the friction reduction rate of the sand carrying fluid obtained in example 18 was greater than 50%, showing a low friction characteristic.

Example 19

[00142]The associative polymer thickener is 0.35% by weight of associative non-crosslinking fracturing thickener GRF-1H, produced by Sichuan Guangya Polymer Chemical Co. Ltd.; the enhancer is 0.1% by weight of GRF-2B; and the clay stabilizer is 0.5% by weight of KCl.

[00143]Water for preparing the high viscosity sand carrying fluid (clear water) was weighted by a balance and added into a stirrer. The speed of the stirrer was adjusted until the bottom axle of the stirrer can be seen. Then the associative polymer was added slowly into the stirrer to ensure that the associative polymer

was dispersed evenly without agglomeration phenomenon, stirred for 4~5min; then the enhancer and clay stabilizer were added, further stirred for 2~3min, stirred evenly to obtain the high viscosity sand carrying fluid.

[00144]The shearing resistance of the high viscosity sand carrying fluid obtained in example 19 was tested. Huck RS6000 rheometer was used, and the shearing resistance of the sand carrying fluid was tested under the condition of 90°C, 170 s⁻¹. A shearing resistance curve as showed in Fig. 7 was obtained. It can be known from Fig. 7 that, when the temperature was constant, along with the shearing process, the viscosity of the sand carrying fluid basically did not change, showing that the high viscosity sand carrying fluid has a better shearing resistance performance.

Example 20

[00145]The associative polymer thickener is 0.37% by weight of associative non-crosslinking fracturing thickener GRF-1C (effective concentration of the associative polymer), produced by Sichuan Guangya Polymer Chemical Co. Ltd.; the enhancer is 0.28% by weight of GRF-2C; the clay stabilizer is 0.5% by weight of KCl; and the oxidative gel breaker is 0.15% by weight of ammonium persulfate.

[00146]Water for preparing the high viscosity sand carrying fluid (clear water) was weighted by a balance and added into a stirrer. The speed of the stirrer was adjusted until the bottom axle of the stirrer can be seen. Then the associative polymer was added slowly into the stirrer to ensure that the associative polymer was dispersed evenly without agglomeration phenomenon, stirred for 4~5min; then the enhancer and clay stabilizer were added, further stirred for 2~3min, stirred evenly to obtain the high viscosity sand carrying fluid.

[00147]The residue amount of the high viscosity sand carrying fluid obtained in example 20 was tested and the result was shown in Table 6. The residue amount

of the high viscosity sand carrying fluid obtained in example 20 was low, showing that the high viscosity sand carrying fluid obtained in example 20 has characteristics of low residue and cleanness.

Table 6. Test results of the residue amount of the sand carrying fluids.

Sand carrying fluid	Residue amount, mg/L	Average residue amount,
		mg/L
Example 11	34.6	
Example 13	38.7	37.6
Example 20	39.5	

5

[00148]Core matrix damage rate of the high viscosity sand carrying fluid obtained in example 20 was tested and the result was shown in Table 7. It can be known from Table 7 that the high viscosity sand carrying fluid obtained in example 20 has low core matrix damage rate, showing that it has a characteristic of low damage.

10

Table 7. test results of matrix damage rate of the sand carrying fluids.

Sand carrying fluid	Core matrix size (d-L) (cm-cm)	Permeability ($10^{-3}\mu\text{m}^2$)		Damage rate (%)
		Permeability before damage	Permeability after damage K_2	
		K_1		
Example 11	H_{1-1} (2.6987-7.591)	1.537	1.416	7.9
Example 13	H_{1-1} (2.6987-7.392)	1.231	1.161	5.6
Example 20	H_{3-3}	0.892	0.808	9.4

(2.6987-7.450)

Comparative example 1

[00149]The associative polymer used as a resistance reducing agent is 0.08% by weight of associative non-crosslinking fracturing thickener GRF-1C (effective concentration of the associative polymer), produced by Sichuan Guangya Polymer Chemical Co. Ltd.; and the clay stabilizer is 1% by weight of KCl.

[00150]Water for preparing the slick water (clear water) was weighted by a balance and added into a stirrer. The speed of the stirrer was adjusted until the bottom axle of the stirrer can be seen. Then the associative polymer was added slowly into the stirrer to ensure that the associative polymer was dispersed evenly without agglomeration phenomenon, stirred for 4~5min; then the enhancer and clay stabilizer were added, and further stirred for 2~3min, to obtain the slick water.

[00151]The surface tension of the slick water obtained in comparative example 1 was tested, and the result was shown in Table 3.

Comparative example 2

[00152]The associative polymer thickener is 0.37% by weight of associative non-crosslinking fracturing thickener GRF-1H, produced by SiChuan Guangya Polymer Chemical Co. Ltd.; and the clay stabilizer is 1% by weight of KCl.

[00153]Water for preparing the high viscosity sand carrying fluid (clear water) was weighted by a balance and added into a stirrer. The speed of the stirrer was adjusted until the bottom axle of the stirrer can be seen. Then the associative polymer was added slowly into the stirrer to ensure that the associative polymer was dispersed evenly without agglomeration phenomenon, stirred for 4~5min; then the enhancer and clay stabilizer were added, and further stirred for 2~3min,

stirred evenly to obtain the high viscosity sand carrying fluid.

[00154]The static suspending performance of the high viscosity sand carrying fluid obtained in comparative example 2 was tested. 30ml of carbo medium density ceramic particles (20~40 mesh) were mixed evenly with 100ml of the sand carrying fluid obtained in comparative example 2, and transferred to a cylinder with plug. The cylinder was placed in an oven at 90°C constant temperature and kept warm. The settling times of ceramic particles were observed and the result was shown in Fig. 4.A. It can be known from Fig. 4 that the addition of enhancer can increase the sand suspending performance of the sand carrying fluid. With the increase adding amount of enhancer, the static sand suspending performance of the high viscosity sand carrying fluid first enhanced and then attenuated.

Comparative example 3

[00155]The associative polymer thickener is 0.37% by weight of associative non-crosslinking fracturing thickener GRF-1H, produced by SiChuan Guangya Polymer Chemical Co. Ltd.; the enhancer is 0.08% by weight of GRF-2B; and the clay stabilizer is 1% by weight of KCl.

[00156]Water for preparing the high viscosity sand carrying fluid (clear water) was weighted by a balance and added into a stirrer. The speed of the stirrer was adjusted until the bottom axle of the stirrer can be seen. Then the associative polymer was added slowly into the stirrer to ensure that the associative polymer was dispersed evenly without agglomeration phenomenon, stirred for 4~5min; then the enhancer and clay stabilizer were added, and further stirred for 2~3min, stirred evenly to obtain the high viscosity sand carrying fluid.

[00157]The static suspending performance of the high viscosity sand carrying fluid obtained in comparative example 3 was tested. 30ml of carbo medium density ceramic particles (20~40 mesh) were mixed evenly with 100ml of the

sand carrying fluid obtained in comparative example 3, and transferred to a cylinder with plug. The cylinder was placed in an oven at 90°C constant temperature and kept warm. The settling times of ceramic particles were observed and the result was shown in Fig. 4.B. It can be known from Fig. 4 that the
 5 addition of enhancer can increase the sand suspending performance of the sand carrying fluid. With the increase adding amount of enhancer, the static sand suspending performance of the sand carrying fluid first enhanced and then attenuated.

10 **Comparative example 4**

[00158]The associative polymer thickener is 0.4% by weight of associative non-crosslinking fracturing thickener GRF-1C (effective concentration of the associative polymer), produced by SiChuan Guangya Polymer Chemical Co. Ltd.; and the clay stabilizer is 1% by weight of KCl.

15 [00159]Water for preparing the high viscosity sand carrying fluid (clear water) was weighted by a balance and added into a stirrer. The speed of the stirrer was adjusted until the bottom axle of the stirrer can be seen. Then the associative polymer was added slowly into the stirrer to ensure that the associative polymer was dispersed evenly without agglomeration phenomenon, stirred for 4~5min;
 20 then the enhancer and clay stabilizer were added, and further stirred for 2~3min, stirred evenly to obtain the high viscosity sand carrying fluid.

[00160]The static suspending performance of the high viscosity sand carrying fluid obtained in comparative example 4 was tested. 30ml of carbo medium density ceramic particles (20~40 mesh) were mixed evenly with 100ml of the
 25 sand carrying fluid obtained in comparative example 4, and transferred to a cylinder with plug. The cylinder was placed in an oven at 90°C constant temperature and kept warm. The settling times of ceramic particles were observed and the result was shown in Fig. 5.A. It can be known from Fig. 5 that the

addition of enhancer can increase the sand suspending performance of the sand carrying fluid.

Comparative example 5

5 [00161]The associative polymer thickener is 0.4% by weight of associative non-crosslinking fracturing thickener GRF-1C, produced by SiChuan Guangya Polymer Chemical Co. Ltd.; the enhancer is 0.4% by weight of GRF-2C; and the clay stabilizer is 1% by weight of KCl.

10 [00162]Water for preparing the high viscosity sand carrying fluid (clear water) was weighted by a balance and added into a stirrer. The speed of the stirrer was adjusted until the bottom axle of the stirrer can be seen. Then the associative polymer was added slowly into the stirrer to ensure that the associative polymer was dispersed evenly without agglomeration phenomenon, stirred for 4~5min; then the enhancer and clay stabilizer were added, and further stirred for 2~3min,
15 stirred evenly to obtain the high viscosity sand carrying fluid.

[00163]The static suspending performance of the high viscosity sand carrying fluid obtained in comparative example 4 was tested. 30ml of carbo medium density ceramic particles (20~40 mesh) were mixed evenly with 100ml of the sand carrying fluid obtained in comparative example 5, and transferred to a
20 cylinder with plug. The cylinder was placed in an oven at 90°C constant temperature and kept warm. The settling times of ceramic particles were observed and the result was shown in Fig. 5.D. It can be known from Fig. 5 that the addition of enhancer can increase the sand suspending performance of the sand carrying fluid. With the increase adding amount of enhancer, the static sand
25 suspending performance of the sand carrying fluid first enhanced and then attenuated.

CLAIMS

1. Use of an associative polymer as friction-reducing agent and thickener, wherein the associative polymer is a modified natural associative polymer and/or organic synthetic associative polymer.

5 2. A multi-functional hybrid fracturing fluid system, characterized in that, it comprises slick water and high viscosity sand carrying fluid,

wherein the slick water contains 0.02%~0.15% of friction-reducing agent by mass percentage;

10 the high viscosity sand carrying fluid contains 0.2%~0.75% of thickener by mass percentage; and

the friction-reducing agent and the thickener are the same associative polymer which is a modified natural associative polymer and/or an organic synthetic associative polymer.

15 3. The multi-functional hybrid fracturing fluid system of claim 2, characterized in that,

the modified natural associative polymer is one or more of hydrophobically modified cellulose polymers, hydrophobically modified starch polymers and hydrophobically modified xanthan gum; and

20 the organic synthetic associative polymer is hydrophobically modified polyacrylamide and/or derivatives thereof.

4. The multi-functional hybrid fracturing fluid system of claim 2, characterized in that,

25 the slick water comprises 0.02%~0.15% of friction-reducing agent, 0.05%~0.3% of enhancer, 0.2%~2% of clay stabilizer by mass percentage and water solvent as the balance;

the high viscosity sand carrying fluid comprises 0.2%~0.75% of thickener, 0.1%~0.4% of enhancer, 0.3%~2% of clay stabilizer, and 0.03%~0.4% of gel breaker by mass percentage, and water solvent as the balance;

the friction-reducing agent and the thickener are the same associative polymer

which is modified natural associative polymer or organic synthetic associative polymer;

the enhancer in the slick water and the enhancer in the high viscosity sand carrying fluid is each independently one or more of anionic surfactants and nonionic surfactants; and

the water solvent in the slick water and the water solvent in the high viscosity sand carrying fluid is each independently clear water or flowback liquid after treatment.

5. The multi-functional hybrid fracturing fluid system of claim 4, characterized in that,

the anionic surfactant is one or more of alkyl benzene sulfonate salts, alkyl sulfate salts and petroleum sulfonate salts; and

the nonionic surfactant is one or more of fatty acid polyoxyethylene ester, nonylphenol polyoxyethylene ether, polyether type surfactant and fatty alcohol polyoxyethylene ether.

6. The multi-functional hybrid fracturing fluid system of claim 4, characterized in that, the clay stabilizer in the slick water and the clay stabilizer in the high viscosity sand carrying fluid is each dependently one or more of potassium chloride, ammonium chloride and non-ionic organic clay stabilizers.

7. The multi-functional hybrid fracturing fluid system of claim 4, characterized in that, the gel breaker in the high viscosity sand carrying fluid is one or more of potassium persulfate, ammonium persulfate and encapsulated oxidative gel breaker.

8. The multi-functional hybrid fracturing fluid system of claim 4, characterized in that, the slick water comprises 0.04%~0.15% of association polymer, 0.1%~0.3% of enhancer, 0.3%~2% of clay stabilizer by mass percentage, and clear water as the balance.

9. The multi-functional hybrid fracturing fluid system of claim 4, characterized in that, by mass percentage, the slick water comprises 0.08% of associative polymer, 0.2% of enhancer, 1% of clay stabilizer by mass percentage, and clear water as the balance.

10. The multi-functional hybrid fracturing fluid system of claim 4, characterized in that, the slick water comprises 0.02%~0.1% of associative polymer, 0.05%~0.25% of enhancer, 0.2%~1.5% of clay stabilizer by mass percentage, and flowback liquid after treatment as the balance.
- 5 11. The multi-functional hybrid fracturing fluid system of claim 4, characterized in that, the high viscosity sand carrying fluid comprises 0.25%~0.75% of associative polymer, 0.15%~0.4% of enhancer, 0.3%~2% of clay stabilizer, 0.03%~0.4% of oxidative gel breaker by mass percentage, and clear water as the balance.
- 10 12. The multi-functional hybrid fracturing fluid system of claim 4, characterized in that, the high viscosity sand carrying fluid comprises 0.35% of associative polymer, 0.2% of enhancer, 1% of clay stabilizer, 0.15% of oxidative gel breaker by mass percentage, and clear water as the balance.
- 15 13. The multi-functional hybrid fracturing fluid system of claim 4, characterized in that, the high viscosity sand carrying fluid comprises 0.2%~0.65% of associative polymer, 0.1%~0.3% of enhancer, 0.3%~1.5% of clay stabilizer, 0.03%~0.4% of oxidative gel breaker by mass percentage, and flowback liquid after treatment as the balance.
- 20 14. Use of the multi-functional hybrid fracturing fluid system of any one of claims 2 to 13 in the volume fracturing reconstruction of tight hydrocarbon reservoir and shale hydrocarbon reservoir.

1 / 4




FIG. 1




FIG. 2

2 / 4




FIG. 3




FIG. 4

3 / 4




FIG. 5




FIG. 6

4 / 4





FIG. 7



AA DRAG REDUCTION RATE
BB DISPLACEMENT

图 2