



HU000033316T2

(19) **HU****MAGYARORSZÁG****Szellemi Tulajdon Nemzeti Hivatala**(11) Lajstromszám: **E 033 316**(13) **T2**

EURÓPAI SZABADALOM SZÖVEGÉNEK FORDÍTÁSA

(21) Magyar ügyszám: **E 13 826953**(22) A bejelentés napja: **2013. 12. 13.**

(96) Az európai bejelentés bejelentési száma:

EP 20130826953

(97) Az európai bejelentés közzétételi adatai:

EP 2935363 A1 **2014. 06. 26.**

(97) Az európai szabadalom megadásának meghirdetési adatai:

EP 2935363 B1 **2017. 03. 29.**(51) Int. Cl.: **C08F136/06** (2006.01)

(86) A nemzetközi (PCT) bejelentési szám:

PCT/IB 13/060905

(87) A nemzetközi közzétételi szám:

WO 14097087

(30) Elsőbbségi adatok:

MI20122203 **2012. 12. 20.** **IT**

(72) Feltaláló(k):

RICCI, Giovanni, I-43126 Parma (IT)**LEONE, Giuseppe, I-20133 Milano (IT)****SOMMAZZI, Anna, I-16038 Santa Margherita-Genova (IT)****MASI, Francesco, I-26866 Sant' Angelo Lodigiano (IT)**

(73) Jogosult(ak):

Versalis S.p.A, 20097 S. Donato Milanese (MI)
(IT)

(74) Képviselő:

PINTZ ÉS TÁRSAI Szabadalmi, Védjegy és
Jogi Iroda Kft., Budapest,

(54) **Eljárás konjugált diének (ko)polimerjeinek előállítására olyan katalitikus rendszer jelenlétében, amely tartalmazza kobalt oxo-nitrogénezett komplexét**

Az európai szabadalom ellen, megadásának az Európai Szabadalmi Közlönyben való meghirdetésétől számított kilenc hónapon belül, felszólalást lehet benyújtani az Európai Szabadalmi Hivatalnál. (Európai Szabadalmi Egyezmény 99. cikk(1))

A fordítást a szabadalmas az 1995. évi XXXIII. törvény 84/H. §-a szerint nyújtotta be. A fordítás tartalmi helyességét a Szellemi Tulajdon Nemzeti Hivatala nem vizsgálta.



(11) **EP 2 935 363 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
29.03.2017 Bulletin 2017/13

(51) Int Cl.:
C08F 136/06 (2006.01)

(21) Application number: **13826953.5**

(86) International application number:
PCT/IB2013/060905

(22) Date of filing: **13.12.2013**

(87) International publication number:
WO 2014/097087 (26.06.2014 Gazette 2014/26)

(54) **PROCESS FOR THE PREPARATION OF (CO)POLYMERS OF CONJUGATED DIENES IN THE PRESENCE OF A CATALYTIC SYSTEM COMPRISING AN OXO-NITROGENATED COMPLEX OF COBALT**

VERFAHREN FÜR DIE HERSTELLUNG VON (CO)POLYMEREN VON KONJUGIERTEN DIENEN IN ANWESENHEIT EINES KATALYTISCHEN SYSTEMS, BEINHALTEND EINEN SAUERSTOFF- UND STICKSTOFFHALTIGEN KOMPLEX VON KOBALT

PROCESSUS DE PRÉPARATION DE (CO)POLYMÈRES DE DIÈNES CONJUGUÉS À L' AIDE D'UN SYSTÈME CATALYTIQUE COMPRENANT UN COMPLEXE DU COBALT AYANT UNE LIAISON OXO-AZOTÉE

(84) Designated Contracting States:
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

(30) Priority: **20.12.2012 IT MI20122203**

(43) Date of publication of application:
28.10.2015 Bulletin 2015/44

(73) Proprietor: **Versalis S.p.A**
20097 S. Donato Milanese (MI) (IT)

(72) Inventors:
• **RICCI, Giovanni**
I-43126 Parma (IT)
• **LEONE, Giuseppe**
I-20133 Milano (IT)
• **SOMMAZZI, Anna**
I-16038 Santa Margherita-Genova (IT)
• **MASI, Francesco**
I-26866 Sant' Angelo Lodigiano (IT)

(74) Representative: **Mauro, Marina Eliana**
Murgitroyd & Company
Piazza Borromeo, 12
20123 Milano (IT)

(56) References cited:
EP-A1- 1 367 069 WO-A1-01/10875

- **JAMES D. NOBBS ET AL: "Thio-Pybox and Thio-Phebox complexes of chromium, iron, cobalt and nickel and their application in ethylene and butadiene polymerisation catalysis", DALTON TRANSACTIONS, vol. 41, no. 19, 2012, page 5949, XP055060219, ISSN: 1477-9226, DOI: 10.1039/c2dt30324h**
- **KIM BU UNG ET AL: "Highly cis-selectivity and low molecular weight distribution polymerization of 1,3-butadiene with cobalt (II) pyridyl bis(imine) complexes in the presence of ethylaluminum sesquichloride: effect of methyl position in the ligand", STUDIES IN SURFACE SCIENCE AND CATALYSIS, ELSEVIER B.V, vol. 159, 2006, pages 873-876, XP009169226, ISSN: 0167-2991**
- **PENGFEI AI ET AL: "Polymerization of 1,3-butadiene catalyzed by cobalt(II) and nickel(II) complexes bearing imino- or amino-pyridyl alcohol ligands in combination with ethylaluminum sesquichloride", JOURNAL OF ORGANOMETALLIC CHEMISTRY, ELSEVIER-SEQUOIA S.A. LAUSANNE, CH, vol. 705, 2012, pages 51-58, XP009168972, ISSN: 0022-328X**

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 2 935 363 B1

Description

[0001] The present invention relates to a process for the preparation of (co)polymers of conjugated dienes.

[0002] More specifically, the present invention relates to a process for the preparation of (co)polymers of conjugated dienes which comprises polymerizing at least one conjugated diene in the presence of a catalytic system comprising an oxo-nitrogenated complex of cobalt.

[0003] It is known that the stereospecific (co)polymerization of conjugated dienes is an extremely important process in the chemical industry for obtaining products which are among the most widely-used rubbers.

[0004] It is also known that among the various polymers which can be obtained from the stereospecific polymerization of 1,3-butadiene (i.e. 1,4-cis, 1,4-trans, 1,2 syndiotactic, 1,2 isotactic, 1,2 atactic, mixed 1,4-cis/1,2 structure having a variable content of 1,2 units), only 1,4-cis polybutadiene and 1,2 **syndiotactic** polybutadiene are produced industrially and commercially **available**. Further details relating to these polymers can be found, for example, in: Takeuchi Y. et al., "new Industrial Polymers", "American Chemical Society Symposium Series" (1974), Vol. 4, pages 15-25; Halasa A. F. et al., "Kirk-Othmer Encyclopedia of Chemical Technology" (1989), 4th Ed., Kroschwitz J. I. Ed., John Wiley and Sons, New York, Vol. 8, pages 1031-1045; Tate D. et al., "Encyclopedia of Polymer Science and Engineering" (1989), 2nd Ed., Mark H. F. Ed., John Wiley and Sons, New York, Vol. 2, pages 537-590; Kerns M. et al., "Butadiene Polymers", in "Encyclopedia of Polymer Science and Technology" (2003), Mark H. F. Ed., Wiley, Vol. 5, pages 317-356.

[0005] 1,4-cis polybutadiene is a synthetic elastomer, generally having a content of 1,4-cis units equal to 96% - 97%, a melting point (T_m) of about -2°C, a crystallization temperature (T_c) of about -25°C and a glass transition temperature (T_g) below -100°C, whose properties are very similar to those of natural rubber and whose main use is in the production of tyres for motor vehicles and/or trucks. In particular, in the production of tyres, polybutadiene with a high content of 1,4-cis units is used.

[0006] 1,4-cis polybutadiene is generally prepared through polymerization processes which use various catalytic systems comprising catalysts based on titanium (Ti), cobalt (Co), nickel (Ni), neodymium (Nd). Catalytic systems comprising catalysts based on cobalt have a high catalytic activity and stereospecificity and can be considered as being the most versatile among those listed above as, by varying their formulation, they are capable of providing all the possible stereoisomers of polybutadiene indicated above, as described, for example, in: Porri L. et al., "Comprehensive Polymer Science" (1989), Eastmond G.C. et al. Eds., Pergamon Press, Oxford, UK, Vol. 4, Part II, pages 53-108; Thiele S. K. H. et al., "Macromolecular Science. Part C: Polymer Reviews" (2003), C43, pages 581-628; Osakada, K. et al., "Advanced Polymer Science" (2004), Vol. 171, pages 137-194; Ricci G. et al., "Advances in Organometallic Chemistry Research" (2007), Yamamoto K. Ed., Nova Science Publisher, Inc., USA, pages 1-36; Ricci G. et al., "Coordination Chemistry Reviews" (2010), Vol. 254, pages 661-676; Ricci G. et al., "Cobalt: Characteristics, Compounds, and Applications" (2011), Lucas J. Vidmar Ed., Nova Science Publisher, Inc., USA, pages 39-81.

[0007] The catalytic system cobalt bis-acetylacetonate/diethylaluminium chloride/water $[\text{Co}(\text{acac})_2/\text{AlEt}_2\text{Cl}/\text{H}_2\text{O}]$, for example, provides a polybutadiene having a content of 1,4-cis units equal to about 97% and it is that normally used for the industrial production of this polymer as described, for example, in Racanelli P. et al., "European Polymer Journal" (1970), Vol. 6, pages 751-761. The catalytic system cobalt tris-acetylacetonate/methylaluminoxane $[\text{Co}(\text{acac})_3/\text{MAO}]$ also provides a polybutadiene having a content of 1,4-cis units equal to about 97%, as described, for example in: Ricci G. et al., "Polymer Communication" (1991), Vol. 32, pages 514-517.

[0008] The catalytic system cobalt tris-acetylacetonate/tri-ethylaluminium/water $[\text{Co}(\text{acac})_3/\text{AlEt}_3/\text{H}_2\text{O}]$, on the other hand, provides a polybutadiene having a mixed 1,4-cis/1,2 equibinary structure as described, for example, in: Furukawa J. et al., "Polymer Journal" (1971), Vol. 2, pages 371-378. Said catalytic system, in the presence of carbon disulfide (CS_2), is used, on the other hand, in processes for the industrial production of highly crystalline 1,2 syndiotactic polybutadiene: further details relating to these processes can be found, for example, in: Ashitaka H. et al., "Journal of Polymer Science: Polymer Chemistry Edition" (1983), Vol. 21, pages 1853-1860; Ashitaka H. et al., "Journal of Polymer Science: Polymer Chemistry Edition" (1983), Vol. 21, pages 1951-1972; Ashitaka H. et al., "Journal of Polymer Science: Polymer Chemistry Edition" (1983), Vol. 21, pages 1973-1988; Ashitaka H. et al., "Journal of Polymer Science: Polymer Chemistry Edition" (1983), Vol. 21, pages 1989-1995.

[0009] An extremely active and stereospecific catalytic system for the preparation of 1,2-syndiotactic polybutadiene can be obtained by the combination of the cobalt allyl complex $(\eta^4\text{-C}_4\text{H}_6)(\eta^5\text{-C}_8\text{H}_{13})\text{Co}$ described, for example, by Natta G. et al., "Chemical Communications" (1967), Issue 24, pages 1263-1265, with carbon disulfide (CS_2), as described, for example, in: Ricci G. et al., "Polymer Communication" (1988), Vol. 29, pages 305-307. Said catalytic system is capable of dimerizing 1,3-butadiene at room temperature, as described, for example, in American patent US 5,879,805, but is only capable of giving 1,2-syndiotactic polymers when operating at low temperatures (-30°C) as described, for example, in: Ricci G. et al., "Polymer Communication" (1988), Vol. 29, pages 305-307.

[0010] 1,2 syndiotactic polybutadienes can also be produced using catalytic systems obtained by a combination of cobalt dichloride (CoCl_2) or cobalt dibromide (CoBr_2) with organic compounds of aluminium (e.g., alkyl compounds of aluminium), water and phosphines (e.g., triphenylphosphine) as described, for example, in the following American pat-

ents: US 5,879,805, US 4,324,939, US 3,966,697, US 4,285,833, US 3,498,963, US 3,522,332, US 4,182,813, US 5,548,045, US 7,009,013. The regioregularity and crystallinity of the polybutadienes obtained with said catalytic systems are much lower (e.g., 80% - 90% of 1,2 units, melting point (T_m) ranging from 75°C to 90°C) with respect to those of the polybutadienes obtained with the catalytic system described in: Ricci G. et al., "Polymer Communication" (1988), Vol. 29, pages 305-307, indicated above.

[0011] Further details relating to the polymerization of 1,3-butadiene with catalytic systems comprising complexes of cobalt with various phosphines are provided, for example, in: Ricci G. et al., "Macromolecules" (2005), Vol. 38, pages 1064-1070; Ricci G. et al., "Journal of Organometallic Chemistry" (2005), Vol. 690, pages 1845-1854; Takeuchi M. et al., "Polymer International" (1992), Vol. 29, pages 209-212; Takeuchi M. et al., "Polymer International" (1995), Vol. 36, pages 41-45; Takeuchi M. et al., "Macromolecular Chemistry and Physics" (1996), Vol. 197, pages 729-743; or in Italian patents IT 1,349,141, IT 1,349,142, IT 1,349,143. The use of various phosphines derives from the fact that it is well known that the steric and electronic properties of phosphines greatly depend on the type of substituents on the phosphorous atom as described, for example, in: Dierkes P. et al., "Journal of Chemical Society, Dalton Transactions" (1999), pages 1519-1530; van Leeuwen P. et al., "Chemical Reviews" (2000), Vol. 100, pages 2741-2769; Freixa Z. et al., "Dalton Transactions" (2003), pages 1890-1901; Tolman C., "Chemical Reviews" (1977), Vol. 77, pages 313-348.

[0012] The documents relating to the use of phosphines indicated above, show how the use of phosphine complexes of cobalt combined with methylaluminoxane (MAO) can allow the microstructure of polybutadiene to be managed, thus allowing polybutadienes with **different** structures to be obtained, depending on the type of phosphine coordinated with the cobalt atom.

[0013] The polymerization of 1,3-butadiene with catalytic systems comprising complexes of cobalt with sterically hindered aliphatic phosphines (e.g., P^tBu_3 , P^iPr_3 , P^tBu_2Me , PCy_3 , $PCyp_3$ wherein P = phosphorous, tBu = *tert*-butyl, iPr = *iso*-propyl, Cy = cyclohexyl and Cyp = cyclopentyl), provides polybutadienes with a prevalently 1,4-*cis* structure, whereas polybutadienes having a mixed 1,4-*cis*/1,2 structure have been obtained using catalytic systems comprising complexes of cobalt with phosphines having a lower steric hindrance (e.g., PCy_2H ; P^tBu_2H ; PEt_3 ; P^nPr_3 wherein P = phosphorous, Cy = cyclohexyl, tBu = *tert*-butyl, Et = ethyl and nPr = *n*-propyl), as described, for example, in: Ricci G. et al., "Advances in Organometallic Chemistry Research" (2007), Yamamoto K. Ed., Nova Science Publisher, Inc., USA, pages 1-36; Ricci G. et al., "Coordination Chemistry Reviews" (2010), Vol. 254, pages 661-676; Ricci G. et al., "Journal of Molecular Catalysis A: Chemical" (2005), Vol. 226, pages 235-241; and in Italian patent application IT 1,349,141.

[0014] Polybutadienes with a high content of 1,4-*cis* units (about 95%) have been obtained with catalytic systems comprising complexes of cobalt with bidentate phosphines [e.g., $CoCl_2[R_2P(CH_2)_nPR_2]/MAO$, wherein Co = cobalt, Cl = chlorine, R = methyl, ethyl, phenyl, $n = 1$ or 2 , P = phosphorous and MAO = methylaluminoxane), regardless of the type of bidentate phosphine coordinated with the cobalt atom, as described, for example, in: Ricci G. et al., "Advances in Organometallic Chemistry Research" (2007), Yamamoto K. Ed., Nova Science Publisher, Inc., USA, pages 1-36; Ricci G. et al., "Coordination Chemistry Reviews" (2010), Vol. 254, pages 661-676; and in Italian patent application IT 1,349,141.

[0015] Catalytic systems comprising complexes of cobalt with **ligands** selected from aromatic phosphines [e.g., $CoCl_2(PRPh_2)_2/MAO$ (wherein Co = cobalt, Cl = chlorine, P = phosphorous, R = methyl, *n*-propyl, ethyl, *iso*-propyl, cyclohexyl, Ph = phenyl, MAO = methylaluminoxane)] have, on the other hand, proved to be extremely active for the 1,2 polymerization of 1,3-butadiene as described, for example, in: Ricci G. et al., "Advances in Organometallic Chemistry Research" (2007), Yamamoto K. Ed., Nova Science Publisher, Inc., USA, pages 1-36; Ricci G. et al., "Coordination Chemistry Reviews" (2010), Vol. 254, pages 661-676; Ricci G. et al., "Macromolecules" (2005), Vol. 38, pages 1064-1070; Ricci G. et al., "Journal of Organometallic Chemistry" (2005), Vol. 690, pages 1845-1854; or in Italian patent application IT 1,349,143. Using these catalytic systems, in fact, polybutadienes with an essentially 1,2 structure have been obtained (within a range of 70% to 88%), having a variable content of 1,2 units in relation to the type of complex and polymerization conditions. It has also been observed that the tacticity of the polybutadienes obtained greatly depends on the type of complex, i.e. the type of phosphine bound to the cobalt atom and that the syndiotacticity index (expressed as a percentage of syndiotactic triads " π "), determined by the ^{13}C -NMR spectra, increases with an increase in the steric requirement of the alkyl group bound to the phosphorous atom.

[0016] The 1,2 polybutadienes obtained with **cobalt systems** with less sterically hindered phosphine **ligands** (e.g., $PMePh_2$; $PEtPh_2$; P^nPrPh_2 wherein P = phosphorous, Me = methyl, Ph = phenyl, nPr = *n*-propyl) have proved to be amorphous, whereas the polybutadienes obtained with catalytic systems using phosphine **ligands** with a higher steric hindrance (e.g., P^iPrPh_2 , $PCyPh_2$ wherein P = phosphorous, iPr = *iso*-propyl, Ph = phenyl, Cy = cyclohexyl), have proved to be crystalline, with a melting point (T_m) of 110°C - 120°C, depending on the polymerization conditions.

[0017] The polymerization of 1,3-butadiene with catalytic systems comprising complexes of cobalt with aromatic phosphines having the formula $CoCl_2(PR_2Ph)_2/MAO$ (wherein Co = cobalt, Cl = chlorine, R = methyl, ethyl, cyclohexyl, Ph = phenyl, MAO = methylaluminoxane), has also been studied, as described, for example, in: Ricci G. et al., "Advances in Organometallic Chemistry Research" (2007), Yamamoto K. Ed., Nova Science Publisher, Inc., USA, pages 1-36; Ricci G. et al., "Coordination Chemistry Reviews" (2010), Vol. 254, pages 661-676; Ricci G. et al., "Journal of Organometallic Chemistry" (2005), Vol. 690, pages 1845-1854; or in Italian patent application IT 1,349,143. Using these catalytic systems,

essentially 1,2-polybutadienes have been obtained, but the syndiotacticity index of the polymers, with the same polymerization conditions, has generally proved to be slightly lower with respect to that of the 1,2-polybutadienes obtained with catalytic systems comprising complexes of cobalt with aromatic phosphines having the formula $\text{CoCl}_2(\text{PRPh})_2/\text{MAO}$ described above.

[0018] More recently, following the success obtained using the above catalytic systems comprising phosphine complexes of cobalt, also various catalytic systems comprising complexes of cobalt with **ligands** containing nitrogen or oxygen as donor atom, have been studied.

[0019] Kim J. S. et al., in "e-Polymer" (European Polymer Federation) (2006), No. 27, for example, describe the polymerization of 1,3-butadiene with catalytic systems comprising complexes of cobalt with bis(imine)pyridine and ethylaluminiumsesquichloride $[\text{Al}_2\text{Et}_3\text{Cl}_3]$ (EASC) **ligands**. These catalytic systems have proved to be particularly active, providing high-molecular-weight polybutadienes having a content of 1,4-cis units equal to 96.4%.

[0020] Catalytic systems comprising complexes of cobalt having the formula $(\text{Salen})\text{Co}(\text{II})$ (wherein Salen = bis(salicylaldehyde)ethylenediimine, Co = cobalt) and methylaluminoxane (MAO), characterized by a high activity and 1,4-cis selectivity, are described, for example by Endo K. et al., in "Journal of Polymer Science: Part A: Polymer Chemistry" (2006), vol. 44, pages 4088-4094.

[0021] Cariou R. et al., in "Dalton Transactions" (2010), Vol. 39, pages 9039-9045, describe the synthesis and characterization of a series of complexes of cobalt (II) $[\text{Co}(\text{II})]$ with bis(benzimidazole) which, when combined with methylaluminoxane (MAO), have proved to be highly selective for the 1,4-cis polymerization of 1,3-butadiene.

[0022] The synthesis and characterization of a series of complexes of cobalt (II) $[\text{Co}(\text{II})]$ with dibenzimidazole **ligands** and their use, combined with ethylaluminiumsesquichloride (EASC), for the polymerization of 1,3-butadiene, are described by Appukuttan et al., in "Polymer" (2009), Vol. 50, pages 1150-1158: the catalytic systems obtained are characterized by a high catalytic activity and also a high 1,4-cis selectivity (up to 97%).

[0023] Complexes of cobalt with 2,6-bis[1-(iminophenyl)ethyl]pyridine **ligands** were synthesized and characterized by Gong D. et al., as described in "Polymer" (2009), Vol. 50, pages 6259-6264. **Said** complexes, combined with methylaluminoxane (MAO), were tested for the polymerization of 1,3-butadiene, providing catalytic systems capable of giving 1,4-cis or 1,4-trans polybutadiene, in relation to the MAO/Co ratio. When operating with a MAO/Co molar ratio equal to 50, in fact, an essentially 1,4 trans polybutadiene was obtained (about 94.4%), whereas, when operating with a MAO/Co molar ratio equal to 100, a prevalently 1,4-cis polybutadiene was obtained (about 79%).

[0024] In "Journal of Molecular Catalysis A: Chemical" (2010), Vol. 325, pages 84-90, Appukuttan V. et al., describe a series of complexes having general formula $[\text{Py}(\text{Bm-R})_2]\text{CoCl}_2$ (wherein Py = pyridyl, Bm = benzimidazolyl, R = hydrogen, methyl, benzimidazole, Co = cobalt, Cl = chlorine), capable of providing, when combined with methylaluminoxane (MAO), high-molecular-weight 1,4-cis polybutadiene.

[0025] In "Journal of Organometallic Chemistry" (2011), Vol. 696, pages 1584-1590, Gong D. et al., describe a series of 2,6-bis(imine)pyridine complexes of cobalt (II) $[\text{Co}(\text{II})]$ which, when combined with methylaluminoxane (MAO) as co-catalyst, show a relatively good activity in the polymerization of 1,3-butadiene, allowing a polybutadiene to be obtained, having a 1,4-cis microstructure within a range of 77.5% to 97%, with control of both the molecular weight and also the molecular weight distribution.


[0026] Finally, Jie S. et al., in "Dalton Transactions" (2011), Vol. 40, pages 10975-10982 and Ai P. et al., in "Journal of Organometallic Chemistry" (2012), Vol. 705, pages 51-58, have recently described the possibility of obtaining polybutadiene with a high content of 1,4-cis units (> 96%) with catalytic systems comprising catalysts based on complexes of cobalt with 3-aryliminomethyl-2-hydroxybenzaldehyde **ligands**, or with **ligands** of the NNO type (imino- or amino-pyridyl alcohols), respectively.

[0027] As already indicated above, as (co)polymers of conjugated dienes, in particular polybutadiene with a high content of 1,4-cis units, are the most widely-used polymers on an industrial scale, in particular for the production of tyres, the study of new processes capable of providing **said** (co)polymers is still of great interest.

[0028] The Applicant has considered the problem of finding a new process for the preparation of (co)polymers of conjugated dienes, such as, for example, polybutadiene, polyisoprene, in particular linear or branched polybutadiene with a high content of 1,4-cis units, i.e. a content of 1,4-cis units $\geq 96\%$.

[0029] The Applicant has now found that the preparation of (co)polymers of conjugated dienes, such as, for example, polybutadiene, polyisoprene, in particular linear or branched polybutadiene with a high content of 1,4-cis units, i.e. a content of 1,4-cis units $\geq 96\%$, can be advantageously **carried out** in the presence of a catalytic system comprising at least one oxo-nitrogenated complex of cobalt having general formula (I) defined hereunder.

[0030] An object of the present invention therefore relates to a process for the preparation of (co)polymers of conjugated dienes which comprises polymerizing at least one conjugated diene in the presence of a catalytic system comprising at least one oxo-nitrogenated complex of cobalt having general formula (I):



wherein:

- R_1 and R_2 , equal to or different from each other, represent a hydrogen atom, or they are selected from linear or branched C_1 - C_{20} , preferably C_1 - C_{15} , alkyl groups, optionally halogenated, cycloalkyl groups optionally substituted; aryl groups optionally substituted;
- Y represents an oxygen atom; or a group -N- R_3 wherein R_3 represents a hydrogen atom, or it is selected from linear or branched C_1 - C_{20} , preferably C_1 - C_{15} , alkyl groups, optionally halogenated, cycloalkyl groups optionally substituted; aryl groups optionally substituted;
- or, when Y represents a group -N- R_3 , R_2 and R_3 can be **optionally** bound to each other to form, together with the other atoms to which they are bound, a cycle containing from 3 to 6 carbon atoms, saturated, unsaturated, or aromatic, optionally substituted with linear or branched C_1 - C_{20} , preferably C_1 - C_{15} , alkyl groups, said cycle optionally containing heteroatoms such as, for example, oxygen, sulfur, nitrogen, silicon, phosphorous, selenium;
- X_1 and X_2 , equal to or different from each other, represent a halogen atom such as, for example, chlorine, bromine, iodine; or they are selected from linear or branched C_1 - C_{20} , preferably C_1 - C_{15} , alkyl groups, -OCOR₄ groups or -OR₄ groups wherein R_4 is selected from linear or branched C_1 - C_{20} , preferably C_1 - C_{15} , alkyl groups.


[0031] For the **aim** of the present description and **of the** following claims, the definitions of the numerical intervals always include the extremes, unless otherwise specified.

[0032] For the **aim** of the present description and **of the** following claims, the term "comprising" also includes the terms "which essentially consist of" or "which consists of".

[0033] According to a preferred embodiment of the present invention, said catalytic system can comprise at least one co-catalyst (b) selected from organic compounds of an element M' different from carbon, said element M' being selected from elements belonging to groups 2, 12, 13 or 14, of the Periodic Table of Elements, preferably from: boron, aluminium, zinc, magnesium, gallium, tin, even more preferably from aluminium, boron.

[0034] The formation of the catalytic system comprising the oxo-nitrogenated complex of cobalt having general formula (I) and the co-catalyst (b), is generally and preferably carried out in an inert liquid medium, more preferably in a hydrocarbon solvent. The choice of oxo-nitrogenated complex of cobalt having general formula (I) and of co-catalyst (b), as well as the particular method used, can vary in relation to the molecular structures and to the desired result, according to what is analogously described in specific literature available to experts in the field for other complexes of transition metals with imine ligands, as described, for example, by L. K. Johnson et al. in "Journal of the American Chemical Society" (1995), Vol. 117, pages 6414-6415, and G. van Koten et al. in "Advances in Organometallic Chemistry" (1982), Vol. 21, pages 151-239.

[0035] According to a further preferred embodiment of the present invention, said co-catalyst (b) can be selected from (b₁) aluminium alkyls having general formula (II):



wherein X' represents a halogen atom such as, for example, chlorine, bromine, iodine, fluorine; R_5 is selected from linear or branched C_1 - C_{20} alkyl groups, cycloalkyl groups, aryl groups, said groups being optionally substituted with one or more silicon or germanium atoms; and n is an integer ranging from 0 to 2.

[0036] According to a further preferred embodiment of the present invention, said co-catalyst (b) can be selected from (b₂) organo-oxygenated compounds of an element M' different from carbon belonging to groups 13 or 14 of the Periodic Table of Elements, preferably organo-oxygenated compounds of aluminium, gallium, tin. Said organo-oxygenated compounds (b₂) can be defined as organic compounds of M', wherein the latter is bound to at least one oxygen atom and to at least one organic group consisting of an alkyl group having from 1 to 6 carbon atoms, preferably methyl.

[0037] According to a further preferred embodiment of the present invention, said co-catalyst (b) can be selected from (b₃) organometallic compounds or mixtures of organometallic compounds of an element M' different from carbon capable

of reacting with the oxo-nitrogenated complex of cobalt having general formula (I), extracting therefrom a substituent X_1 or X_2 σ -bound, to form, on the one hand, at least one neutral compound, and on the other, an ionic compound consisting of a cation containing the metal (Co) coordinated by the **ligand**, and a non-coordinating organic anion containing the metal M', wherein the negative charge is delocalized on a multicentric structure.

[0038] It should be noted that, for the **aim** of the present invention and of the following claims, the term "Periodic Table of Elements" refers to the IUPAC version of the "Periodic Table of Elements" dated June 22, 2007, provided in the following Internet website www.iupac.org/fileadmin/user_upload/news/IUPAC_Periodic_Table-1Jun12.pdf.

[0039] The term " C_1 - C_{20} alkyl groups" refers to linear or branched alkyl groups having from 1 to 20 carbon atoms. Specific examples of C_1 - C_{20} alkyl groups are: methyl, ethyl, n-propyl, iso-propyl, n-butyl, s-butyl, iso-butyl, tert-butyl, pentyl, hexyl, heptyl, octyl, n-nonyl, n-decyl, 2-butyloctyl, 5-methylhexyl, 4-ethylhexyl, 2-ethylheptyl, 2-ethylhexyl.

[0040] The term " C_1 - C_{20} alkyl groups optionally halogenated" refers to alkyl groups having from 1 to 20 carbon atoms, linear or branched, saturated or unsaturated, wherein at least one of the hydrogen atoms is substituted with a halogen atom such as, for example, fluorine, chlorine, bromine, preferably fluorine, chlorine. Specific examples of C_1 - C_{20} alkyl groups optionally halogenated are: fluoromethyl, difluoromethyl, trifluoromethyl, trichloromethyl, 2,2,2-trifluoroethyl, 2,2,2-trichloroethyl, 2,2,3,3-tetrafluoropropyl, 2,2,3,3,3-pentafluoropropyl, perfluoropentyl, perfluorooctyl, perfluorodecyl.

[0041] The term "cycloalkyl groups" refers to cycloalkyl groups having from 3 to 30 carbon atoms. Said cycloalkyl groups can be optionally substituted with one or more groups, equal to or different from each other, selected from: halogen atoms; hydroxyl groups; C_1 - C_{12} alkyl groups; C_1 - C_{12} alkoxy groups; cyano groups; amino groups; nitro groups. Specific examples of cycloalkyl groups are: cyclopropyl, 2,2-difluorocyclopropyl, cyclobutyl, cyclopentyl, cyclohexyl, hexamethylcyclohexyl, pentamethylcyclopentyl, 2-cyclooctylethyl, methylcyclohexyl, methoxycyclohexyl, fluorocyclohexyl, phenylcyclohexyl.

[0042] The term "aryl groups" refers to aromatic carbocyclic groups. Said aromatic carbocyclic groups can be optionally substituted by one or more groups, equal to or different from each other, selected from: halogen atoms such as, for example, fluorine, chlorine, bromine; hydroxyl groups; C_1 - C_{12} alkyl groups; C_1 - C_{12} alkoxy groups; cyano groups; amino groups; nitro groups. Specific examples of aryl groups are: phenyl, methylphenyl, trimethylphenyl, methoxyphenyl, hydroxyphenyl, phenyloxyphenyl, fluorophenyl, pentafluorophenyl, chlorophenyl, bromophenyl, nitrophenyl, dimethylaminophenyl, naphthyl, phenylnaphthyl, phenanthrene, anthracene.

[0043] The term "cyclo" refers to a system containing a ring containing from 3 to 6 carbon atoms, optionally containing, in addition to the nitrogen atom, other heteroatoms selected from nitrogen, oxygen, sulfur, silicon, selenium, phosphorous. Specific examples of cyclo are: pyridine, thiadiazole.

[0044] According to a further preferred embodiment of the present invention, said conjugated diene can be selected, for example, from: 1,3-butadiene, 2-methyl-1,3-butadiene (isoprene), 2,3-dimethyl-1,3-butadiene, 1,3-pentadiene, 1,3-hexadiene, cyclo-1,3-hexadiene, or mixtures thereof. 1,3-Butadiene, isoprene, are preferred.


[0045] According to a further preferred embodiment of the present invention, in said oxo-nitrogenated complex of cobalt having general formula (I) :

- R_1 and R_2 , equal to or different from each other, represent a hydrogen atom, or they are selected from linear or branched C_1 - C_{20} alkyl groups, preferably **are** a methyl group;
- Y is an oxygen atom; or a group -N- R_3 wherein R_3 is selected from phenyl groups substituted with linear or branched C_1 - C_{20} alkyl groups, preferably substituted with one or more methyl, ethyl, *iso*-propyl, tert-butyl groups;
- X_1 and X_2 , the same as each other, are a halogen atom such as, for example, chlorine, bromine, iodine, preferably chlorine.


[0046] The oxo-nitrogenated complex of cobalt having general formula (I) should be considered, according to the present invention, as being in any physical form such as, for example, in the form of an isolated and purified solid, solvated with a suitable solvent, or supported on suitable organic or inorganic solids, preferably having a granular or powder physical form.

[0047] The oxo-nitrogenated complex of cobalt having general formula (I) is prepared starting from ligands known in the art.


[0048] Specific examples of **ligands** which can be used for the **aim** of the present invention are those having the following formulae (L1)-(L6).




(L1);




(L2);




(L3);



(L4);



(L5);



(L6).

[0049] Said **ligands** having formulae (L1)-(L6) can be prepared by means of processes known in the art. Said **ligands** having formulae (L1)-(L6) can be prepared, for example, by means of condensation reactions between primary amines and diketones, as described, for example, in international patent application WO 2001/10875; or by: Parks J. E. and Holm R. H. in "Inorganic Chemistry" (1968), Vol 7(7), pages 1408-1416; Roberts E. and Turner E. E. in "Journal of Chemical Society" (1927), pages 1832-1857; Dudek G. O. and Holm R. H. in "Journal of the American Chemical Society" (1961), Vol. 83, Issue 9, pages 2099-2104. The ligand (L4), i.e. 2,6-di-acetylpyridine, is commercially available (Aldrich).

[0050] The oxo-nitrogenated complex of cobalt having general formula (I) can be prepared by means of processes known in the art. Said oxo-nitrogenated complex of cobalt can be prepared, for example, by the reaction between cobalt compounds having general formula $\text{Co}(\text{X})_2$ wherein X is a halogen atom such as, for example, chlorine, bromine, iodine, preferably chlorine, as such or complexed with ethers [for example, diethylether, tetrahydrofuran (THF), dimethoxyethane], with the **ligands** having formulae (L1)-(L6) indicated above, in a **ligand** (L)/cobalt (Co) molar ratio ranging from 1 to 1.5, preferably operating in the presence of at least one solvent which can be selected, for example, from: chlorinated solvents (for example, methylene chloride), ether solvents [for example, tetrahydrofuran (THF)], alcohol solvents (for example, butanol), hydrocarbon solvents (for example, toluene), or mixtures thereof, at room temperature or higher. The oxo-nitrogenated complex of cobalt thus obtained can be subsequently recovered by means of methods

known in the art such as, for example, precipitation by means of a non-solvent (for example, pentane), followed by separation by means of filtration or decanting and **optional** subsequent dissolution in a suitable solvent followed by crystallization at a low temperature.


[0051] For the **aim** of the present description and of **the** following claims, the phrase "room temperature" refers to a temperature ranging from 20°C to 25°C.

[0052] Specific examples of aluminium alkyls having general formula (II) which are particularly useful for the **aim** of the present invention are: tri-methyl-aluminium, tri-(2,3,3-tri-methyl-butyl)-aluminium, tri-(2,3-di-methyl-hexyl)-aluminium, tri-(2,3-di-methylbutyl)-aluminium, tri-(2,3-di-methyl-pentyl)-aluminium, tri-(2,3-di-methyl-heptyl)-aluminium, tri-(2-methyl-3-ethyl-pentyl)-aluminium, tri-(2-methyl-3-ethyl-hexyl)-aluminium, tri-(2-methyl-3-ethyl-heptyl)-aluminium, tri-(2-methyl-3-propyl-hexyl)-aluminium, tri-ethyl-aluminium, tri-(2-ethyl-3-methyl-butyl)-aluminium, tri-(2-ethyl-3-methyl-pentyl)-aluminium, tri-(2,3-di-ethyl-pentyl-aluminium), tri-*n*-propyl-aluminium, tri-*iso*-propyl-aluminium, tri-(2-propyl-3-methyl-butyl)-aluminium, tri-(2-*iso*-propyl-3-methyl-butyl)-aluminium, tri-*n*-butyl-aluminium, tri-*iso*-butyl-aluminium (TI-BA), tri-*tert*-butyl-aluminium, tri-(2-*iso*-butyl-3-methylpentyl)-aluminium, tri-(2,3,3-tri-methyl-pentyl)-aluminium, tri-(2,3,3-tri-methyl-hexyl)-aluminium, tri-(2-ethyl-3,3-di-methyl-butyl)-aluminium, tri-(2-ethyl-3,3-di-methyl-pentyl)-aluminium, tri-(2-*iso*-propyl-3,3-dimethyl-butyl)-aluminium, tri-(2-tri-methylsilyl-propyl)-aluminium, tri-2-methyl-3-phenyl-butyl)-aluminium, tri-(2-ethyl-3-phenyl-butyl)-aluminium, tri-(2,3-di-methyl-3-phenyl-butyl)-aluminium, tri-(2-phenyl-propyl)-aluminium, tri-[2-(4-fluoro-phenyl)-propyl]-aluminium, tri-[2-(4-chloro-phenyl)-propyl]-aluminium, tri-[2-(3-*iso*-propyl-phenyl)-tri-(2-phenyl-butyl)-aluminium, tri-(3-methyl-2-phenyl-butyl)-aluminium, tri-(2-phenyl-pentyl)-aluminium, tri-[2-(pentafluoro-phenyl)-propyl]-aluminium, tri-(2,2-diphenyl-ethyl)-aluminium, tri-(2-phenyl-methylpropyl)-aluminium, tri-pentyl-aluminium, tri-hexyl-aluminium, tri-cyclohexyl-aluminium, tri-octyl-aluminium, di-ethyl-aluminium hydride, di-*n*-propyl-aluminium hydride, di-*n*-butyl-aluminium hydride, di-*iso*-butyl-aluminium hydride (DIBAH), di-hexyl-aluminium hydride, di-*iso*-hexyl-aluminium hydride, di-octyl-aluminium hydride, di-*iso*-octyl-aluminium hydride, ethyl-aluminium di-hydride, *n*-propyl-aluminium di-hydride, *iso*-butyl-aluminium di-hydride, di-ethyl-aluminium chloride (DEAC), mono-ethyl-aluminium dichloride (EADC), di-methyl-aluminium chloride, di-*iso*-butyl-aluminium chloride, *iso*-butyl-aluminium dichloride, ethyl-aluminium sesquichloride (EASC), and also the corresponding compounds in which one of the hydrocarbon substituents is substituted by a hydrogen atom and those in which one or two of the hydrocarbon substituents are substituted with an *iso*-butyl group. Di-ethyl-aluminium chloride (DEAC), mono-ethyl-aluminium dichloride (EADC), ethyl-aluminium sesquichloride (EASC), are particularly preferred.

[0053] When used for the formation of a catalytic (co)polymerization system according to the present invention, the aluminium alkyls having general formula (II) may preferably be put in contact with an oxo-nitrogenated complex of cobalt having general formula (I), in such proportions that the molar ratio between the cobalt present in the oxo-nitrogenated complex of cobalt having general formula (I) and the aluminium present in the aluminium alkyls having general formula (II) can range from 5 to 5000, preferably from 10 to 1000. The sequence with which the oxo-nitrogenated complex of cobalt having general formula (I) and aluminium alkyl having general formula (II) are put in contact with each other, is not particularly critical.

[0054] Further details relating to the aluminium alkyls having general formula (II) can be found in international patent application WO 2011/061151.

[0055] According to a particularly preferred embodiment, said organo-oxygenated compounds (b_2) can be selected from aluminoxanes having general formula (III):



wherein R_6 , R_7 and R_8 , equal to or different from each other, represent a hydrogen atom, a halogen atom such as chlorine, bromine, iodine, fluorine; or they are selected from linear or branched C_1 - C_{20} alkyl groups, cycloalkyl groups, aryl groups, said groups being optionally substituted with one or more silicon or germanium atoms; and p is an integer ranging from 0 to 1,000.

[0056] As is known, aluminoxanes are compounds containing Al-O-Al bonds, with a variable O/Al ratio, which can be obtained by means of processes known in the art such as, for example, by reaction, under controlled conditions, of an aluminium alkyl, or of an aluminium alkyl halide, with water or with other compounds containing predetermined quantities of available water, such as, for example, in the case of the reaction of aluminium trimethyl with aluminium sulfate hexahydrate, copper sulfate pentahydrate or iron sulfate pentahydrate.

[0057] Said aluminoxanes, and particularly methyl aluminoxane (MAO) are compounds which can be obtained by means of known organometallic chemical processes, such as, for example by the addition of aluminium trimethyl to a suspension in hexane of aluminium sulfate hydrate.

[0058] When used for the formation of a catalytic (co)polymerization system according to the present invention, the aluminoxanes having general formula (III) may preferably be put in contact with an oxo-nitrogenated complex of cobalt having general formula (I), in such proportions that the molar ratio between the aluminium (Al) present in the aluminoxane having general formula (III) and the cobalt present in the oxo-nitrogenated complex of cobalt having general formula (I)




can range from 10 to 10000, preferably from 100 to 5000. The sequence with which the oxo-nitrogenated complex of cobalt having general formula (I) and the aluminosilane having general formula (III) are put in contact with each other, is not particularly critical.

[0059] In addition to the above preferred aluminosilanes having general formula (III), the definition of the compound (b₂) according to the present invention can also include galloxanes, wherein, in general formula (III), gallium is present in substitution of the aluminium, and stannoxanes, wherein, in general formula (III), tin is present in substitution of the aluminium, whose use as co-catalysts in the polymerization of olefins in the presence of metallocene complexes, is known. Further details relating to said galloxanes and stannoxanes can be found, for example, in American patents US 5,128,295 and US 5,258,475.

[0060] Specific examples of aluminosilanes having general formula (III) which are particularly useful for the aim of the present invention are: methylaluminosilane (MAO), ethyl-aluminosilane, *n*-butyl-aluminosilane, tetra-*iso*-butyl-aluminosilane (TIBAO), *tert*-butyl-aluminosilane, tetra-(2,4,4-tri-methyl-pentyl)-aluminosilane (TIOAO), tetra-(2,3-di-methyl-butyl)-aluminosilane (TDMBAO), tetra-(2,3,3-tri-methyl-butyl)-aluminosilane (TTMBAO). Methylaluminosilane (MAO) is particularly preferred.

[0061] Further details relating to the aluminosilanes having general formula (III) can be found in international patent application WO 2011/061151.

[0062] According to a preferred embodiment of the present invention, said compounds or mixtures of compounds (b₃) can be selected from organic compounds of aluminium and especially boron, such as, for example, those represented by the following general formulae:



wherein *w* is an integer ranging from 0 to 3, each group R_C independently represents an alkyl group or an aryl group having from 1 to 10 carbon atoms and each group R_D independently represents an aryl group partially or totally, preferably totally, fluorinated, having from 6 to 20 carbon atoms, P represents a pyrrole radical optionally substituted.

[0063] When used for the formation of a catalytic (co)polymerization system according to the present invention, the compounds or mixtures of compounds (b₃) may be preferably put in contact with an oxo-nitrogenated complex of cobalt having general formula (I), in such proportions that the molar ratio between the metal (M') present in the compounds or mixtures of compounds (b₃) and the cobalt present in the oxo-nitrogenated complex of cobalt having general formula (I) ranges from 0.1 to 15, preferably from 0.5 to 10, more preferably from 1 to 6. The sequence with which the oxo-nitrogenated complex of cobalt having general formula (I) and the compound or mixture of compounds (b₃) are put in contact with each other, is not particularly critical.

[0064] Said compounds or mixtures of compounds (b₃), especially when X₁ and X₂ in the oxo-nitrogenated complex of cobalt having general formula (I) are different from alkyl, must be used in a combination with an aluminosilane having general formula (III) such as, for example, methylaluminosilane (MAO), or, preferably, with an aluminium alkyl having general formula (II), more preferably an aluminium trialkyl having from 1 to 8 carbon atoms in each alkyl residue such as, for example, tri-methyl-aluminium, tri-ethyl-aluminium, tri-*iso*-butylaluminium (TIBA).

[0065] Examples of the methods generally used for the formation of a catalytic (co)polymerization system according to the present invention, when compounds or mixtures of compounds (b₃) are used, are qualitatively schematized in the following list, which however in no way limits the overall scope of the present invention:

(m₁) contact of an oxo-nitrogenated complex of cobalt having general formula (I) wherein at least one of X₁ and X₂ is an alkyl group, with at least one compound or mixture of compounds (b₃) whose cation is capable of reacting with said alkyl group to form a neutral compound, and whose anion is voluminous, non-coordinating and capable of delocalizing the negative charge;

(m₂) reaction of an oxo-nitrogenated complex of cobalt having general formula (I) with at least one aluminium alkyl having general formula (II), preferably an aluminium trialkyl, used in a molar excess of 10/1 to 300/1, followed by reaction with a strong Lewis acid, such as, for example, tris(pentafluorophenyl)boron [compound (b₃)], in an almost stoichiometric quantity or in slight excess with respect to the cobalt (Co);

(m₃) contact and reaction of an oxo-nitrogenated complex of cobalt having general formula (I) with a molar excess of 10/1 to 1000/1, preferably from 100/1 to 500/1, of at least one aluminium trialkyl or an alkyl aluminium halide represented by the formula AlR^mZ_{3-m} wherein R^m is a linear or branched C₁-C₈ alkyl group, or a mixture thereof, Z is a halogen, preferably chlorine or bromine, and *m* is a decimal number ranging from 1 to 3, followed by addition, to the composition thus obtained, of at least one compound or mixture of compounds (b₃) in such quantities that

the ratio between said compound or mixture of compounds (b_3) or the aluminium of said compound or mixture of compounds (b_3) and the cobalt of the oxo-nitrogenated complex of cobalt having general formula (I) ranges from 0.1 to 15, preferably from 1 to 6.

[0066] Examples of compounds or mixtures of compounds (b_3) capable of producing an ionic catalytic system by reaction with an oxo-nitrogenated complex of cobalt having general formula (I) according to the present invention, are described, although with reference to the formation of ionic metallocene complexes, in the following publications, whose contents are incorporated herein as reference:

- W. Beck et al., "Chemical Reviews" (1988), Vol. 88, pages 1405-1421;
- S. H. Stares, "Chemical Reviews" (1993), Vol. 93, pages 927-942;
- European patent applications EP 277 003, EP 495 375, EP 520 732, EP 427 697, EP 421 659, EP 418044;
- published international patent applications WO 92/00333, WO 92/05208.

[0067] Specific examples of compounds or mixtures of compounds (b_3) particularly useful for the **aim** of the present invention are: tributylammonium-tetrakis-pentafluorophenyl-borate tributylammonium-tetrakis-pentafluorophenyl-aluminate, tributylammonium-tetrakis-[(3,5-di-(trifluorophenyl))-borate, tributylammonium-tetrakis-(4-fluorophenyl)]-borate, N,N-dimethylbenzyl-ammonium-tetrakis-pentafluoro-phenyl-borate, N,N-di-methyl-hexylammonium-tetrakis-pentafluorophenyl-borate, N,N-dimethylanilinium-tetrakis-(pentafluorophenyl)-borate, N,N-dimethylanilinium-tetrakis-(pentafluorophenyl)-aluminate, di-(propyl)-ammonium-tetrakis-(pentafluorophenyl)-borate, di-(cyclohexyl)-ammonium-tetrakis-(pentafluorophenyl)-borate, tri-phenyl-carbenium-tetrakis-(pentafluorophenyl)-borate, tri-phenylcarbenium-tetrakis-(penta-fluorophenyl)-aluminate, tris(pentafluorophenyl)boron, tris(pentafluorophenyl)-aluminium, or mixtures thereof. Tetrakis-pentafluorophenyl-borates are preferred.

[0068] For the **aim** of the present description and of the following claims, the term "mole" and "molar ratio" are used with reference to compounds consisting of molecules and also with reference to atoms and ions, omitting, for the latter, the terms gram atom or atomic ratio, even if scientifically more correct.

[0069] Other additives or components can be **optionally** added to the above catalytic system in order to adapt it so as to satisfy specific practical requirements. The catalytic systems thus obtained should therefore be considered as being included in the scope of the present invention. Additives and/or components which can be added in the preparation and/or formulation of the above catalytic system are, for example: inert solvents, such as, for example, aliphatic and/or aromatic hydrocarbons; aliphatic and/or aromatic ethers; weakly coordinating additives (e.g., Lewis bases) selected, for example, from non-polymerizable olefins; sterically hindered or electronically poor ethers; halogenating agents such as, for example, silicon halides, halogenated hydrocarbons, preferably chlorinated; or mixtures thereof.

[0070] As already specified above, said catalytic system can be prepared according to methods known in the art.

[0071] Said catalytic system, for example, can be prepared separately (preformed) and subsequently introduced into the (co)polymerization environment. In this respect, said catalytic system can be prepared by reacting at least one oxo-nitrogenated complex of cobalt having general formula (I) with at least one co-catalyst (b), **optionally** in the presence of other additives or components selected from those listed above, in the presence of a solvent such as, for example, toluene, heptane, at a temperature ranging from 20°C to 60°C, for a time ranging from 10 seconds to 10 hours, preferably from 30 seconds to 5 hours. Further details on the preparation of said catalytic system can be found in the examples provided hereunder.

[0072] Alternatively, said catalytic system can be prepared *in situ*, i.e. directly in the (co)polymerization environment. In this respect, said catalytic system can be prepared by introducing the oxo-nitrogenated complex of cobalt having general formula (I), the co-catalyst (b) and the preselected conjugated diene(s) to be (co)polymerized, separately, operating under the conditions in which the (co)polymerization is **carried out**.

[0073] For the **aim** of the process object of the present invention, said catalytic systems can also be supported on inert solids, preferably consisting of silicon and/or aluminium oxides, such as, for example, silica, alumina or silico-aluminates. The known supporting techniques can be used for supporting said catalytic systems, generally comprising contact, in a suitable inert liquid medium, between the carrier, **optionally** activated by heating to temperatures higher than 200°C, and one or both of components, i.e. the oxo-nitrogenated complex of cobalt having general formula (I) and the co-catalyst (b), of the catalytic system, object of the present invention. For the **aim** of the present invention, it is not necessary for both components to be supported, as the oxo-nitrogenated complex of cobalt having general formula (I) alone, or the co-catalyst (b) **alone**, can be present on the surface of the carrier. In the latter case, the missing component on the surface is subsequently put in contact with the supported component, at the moment in which the catalyst active for the polymerization is to be formed.

[0074] The oxo-nitrogenated complex of cobalt having general formula (I), and the catalytic systems based thereon, which have been supported on a solid by the functionalization of the latter and formation of a covalent bond between the solid and oxo-nitrogenated complex of cobalt having general formula (I), are also included in the scope of the present

invention.

[0075] The quantity of oxo-nitrogenated complex of cobalt having general formula (I) and co-catalyst (b) that can be used in the process, object of the present invention, varies according to the (co)polymerization process to be **carried out**. Said quantity is in any case such as to obtain a molar ratio between the cobalt present in the oxo-nitrogenated complex of cobalt having general formula (I) and the metal present in the co-catalyst (b), e.g., aluminium when the co-catalyst (b) is selected from aluminium alkyls (b_1) or aluminoxanes (b_2), boron when the co-catalyst (b) is selected from compounds or mixtures of compounds (b_3) having general formula (III), included within the values indicated above.

[0076] According to a preferred embodiment of the present invention, said process can be carried out in the presence of an inert organic solvent selected, for example, from: saturated aliphatic hydrocarbons such as, for example, butane, pentane, hexane, heptane, or mixtures thereof; saturated cycloaliphatic hydrocarbons such as, for example, cyclopentane, cyclohexane, or mixtures thereof; mono-olefins such as, for example, 1-butene, 2-butene, or mixtures thereof; aromatic hydrocarbons such as, for example, benzene, toluene, xylene, or mixtures thereof; halogenated hydrocarbons such as, for example, methylene chloride, chloroform, carbon tetrachloride, trichloroethylene, perchloroethylene, 1,2-dichloroethane, chlorobenzene, bromobenzene, chlorotoluene, or mixtures thereof. Said solvent is preferably selected from saturated aliphatic hydrocarbons.

[0077] Alternatively, said process can be carried out using, as solvent, the same conjugated diene(s) to be (co)polymerized, according to the process known as "bulk process".

[0078] According to a preferred embodiment of the present invention, the concentration of the conjugated diene to be (co)polymerized in said inert organic solvent ranges from 5% by weight to 50% by weight, preferably from 10% by weight to 20% by weight, with respect to the total weight of the mixture of conjugated diene and inert organic solvent.

[0079] According to a preferred embodiment of the present invention, said process can be carried out at a temperature ranging from -70°C to $+100^{\circ}\text{C}$, preferably from -20°C to $+80^{\circ}\text{C}$.

[0080] As far as the pressure is concerned, it is preferable to operate at the pressure of the components of the mixture to be (co)polymerized.

[0081] Said process can be **carried out** either in continuous or batchwise.

[0082] As indicated above, said process allows (co)polymers of conjugated dienes to be obtained, such as, for example, polybutadiene, polyisoprene, in particular, linear or branched polybutadiene, with a high content of 1,4-cis units, i.e. a content of 1,4-cis units $\geq 96\%$.

[0083] Some illustrative and non-limiting examples are provided hereunder for a better understanding of the present invention and for its practical embodiment.

EXAMPLES

Reagents and materials

[0084] The reagents and materials used in the following examples of the invention are indicated in the following list, together with their **optional** pretreatments and **their** supplier.

- cobalt dichloride (CoCl_2) (Stream Chemicals): used as such;
- tetrahydrofuran (THF) (Carlo Erba, RPE): kept at reflux temperature on potassium/benzophenone and then distilled under nitrogen;
- methanol (Carlo Erba, RPE) : used as such;
- formic acid (85%) (Carlo Erba, RPE) : used as such;
- 2,6-diacetylpyridine (Aldrich): used as such;
- 2,6-diethylaniline (Aldrich): distilled on sodium (Na) in an inert atmosphere;
- 2,6-di-iso-propylaniline (Aldrich): used as such;
- toluene (Aldrich): pure, $\geq 99,5\%$, distilled on sodium (Na) in an inert atmosphere;
- 1,3-butadiene (Air Liquide): pure, $\geq 99,5\%$, evaporated from the container before each production, dried by passing it through a column packed with molecular sieves and condensed inside the reactor pre-cooled to -20°C ;
- methylaluminumoxane (MAO) (toluene solution at 10% by weight) (Aldrich): used as such;
- dry methylaluminumoxane (MAO_{dry}) : obtained by drying methylaluminumoxane (MAO) (toluene solution at 10% by weight) (Aldrich), under vacuum, at room temperature;
- dichloromethane ($\geq 99\%$) (Aldrich): distilled on diphosphorous pentaoxide (P_2O_5) in an inert atmosphere;
- pentane (Aldrich): pure, $\geq 99,5\%$, distilled on sodium (Na) in an inert atmosphere;
- deuterated tetrachloroethylene ($\text{C}_2\text{D}_2\text{Cl}_4$) (Acros) : used as such;
- deuterated chloroform (CDCl_3) (Acros) : used as such;
- hydrochloric acid in aqueous solution at 37% (Aldrich): used as such.

[0085] The analysis and characterization methods indicated below were used.

Elemental analysis

a) Determination of Co

[0086] For the determination of the weight quantity of cobalt (Co) in the oxo-nitrogenated complexes of cobalt used for the **aim** of the present invention, an aliquot weighed exactly, operating in a dry-box under a nitrogen flow, of about 30-50 mg of sample, was placed in a platinum crucible of about 30 ml, together with a mixture of 1 ml of hydrofluoric acid (HF) at 40%, 0.25 ml of sulfuric acid (H₂SO₄) at 96% and 1 ml of nitric acid (HNO₃) at 70%. The crucible was then heated on a plate, increasing the temperature until the appearance of white sulfuric fumes (about 200°C). The mixture thus obtained was cooled to room temperature (20°C - 25°C), 1 ml of nitric acid (HNO₃) at 70% was added and the mixture was then heated until the re-appearance of fumes. After repeating the sequence a further two times, a limpid, almost colourless solution was obtained. 1 ml of nitric acid (HNO₃) and about 15 ml of water were then added, without heat, and the mixture was then heated to 80°C, for about 30 minutes. The sample thus prepared was diluted with water having a MilliQ purity up to a weight of about 50 g, weighed exactly, to obtain a solution on which analytical instrumental determination was **carried out** using an ICP-OES (optical detection plasma) Thermo Optek IRIS Advantage Duo spectrometer, by comparison with solutions at a known concentration. For this **aim**, a calibration curve was prepared for each analyte, within the range of 0 ppm - 10 ppm, measuring solutions having a known titre obtained by dilution by weight of certified solutions.

[0087] The solution of the sample prepared as described above was diluted again by weight so as to obtain concentrations close to those used as reference, before **carrying out** spectrophotometric analysis. All the samples were prepared in duplicate. The results were considered acceptable if the single data of the tests in duplicate did not differ by more than 2% relative with respect to their average value.

b) Chlorine determination

[0088] For this **aim**, samples of the oxo-nitrogenated complexes of cobalt used for the **aim** of the present invention, about 30 mg - 50 mg, were weighed exactly in 100 ml glasses in a dry-box under a stream of nitrogen. 2 g of sodium carbonate (Na₂CO₃) and 50 ml of MilliQ water were added, outside the dry-box. The mixture was brought to boiling point on a plate under magnetic stirring for about 30 minutes. It was left to cool, diluted sulfuric acid (H₂SO₄) 1/5 was added until the reaction became acid and the mixture was titrated with silver nitrate (AgNO₃) 0.1 N with a potentiometer titrator.

c) Determination of carbon, hydrogen, nitrogen and oxygen

[0089] The determination of the carbon, hydrogen, and nitrogen, in the oxo-nitrogenated complexes of cobalt, used for the **aim** of the present invention, and also in the **ligands** used for the **aim** of the present invention, was **carried out** by means of a Thermo Flash 2000 automatic analyzer, whereas the determination of the oxygen was **carried out** by means of a Thermo EA1100 automatic analyzer.

¹³C-HMR and ¹H-HMR spectra

[0090] The ¹³C-HMR and ¹H-HMR spectra were registered by means of a nuclear magnetic resonance spectrometer mod. Bruker Avance 400, using deuterated tetrachloroethylene (C₂D₂Cl₄) at 103°C, and hexamethyldisiloxane (HDMS) as internal standard, or using deuterated chloroform (CDCl₃), at 25°C, and tetramethylsilane (TMS) as internal standard. Polymeric solutions having concentrations equal to 10% by weight with respect to the total weight of the polymeric solution, were used for the **aim**.

[0091] The microstructure of the polymers [i.e. content of 1,4-cis units (%)] was determined by analysis of the above spectra on the basis of what is indicated in literature by Mochel, V. D., in "Journal of Polymer Science Part A-1: Polymer Chemistry" (1972), Vol. 10, Issue 4, pages 1009-1018.

I.R. Spectra

[0092] The I.R. spectra (FT-IR) were registered by means of Thermo Nicolet Nexus 670 and Bruker IFS 48 spectrophotometers.

[0093] The I.R. spectra (FT-IR) of the **ligands** used in the present invention, were obtained by dispersing the **ligand** to be analyzed in anhydrous potassium bromide (KBr) (disks of KBr), or in a suspension of nujol.

[0094] The I.R. spectra (FT-IR) of the oxo-nitrogenated complexes of cobalt used in the present invention, were

obtained by dispersing the oxo-nitrogenated complex of cobalt to be analyzed in anhydrous potassium bromide (KBr) (disks of KBr), or in a suspension of nujol.

[0095] The I.R. spectra (FT-IR) of the polymers were obtained from polymeric films on tablets of potassium bromide (KBr), said films being obtained by deposition of a solution of the polymer to be analyzed in hot o-dichlorobenzene. The concentration of the polymeric solutions analyzed was equal to 10% by weight with respect to the total weight of the polymeric solution.

Thermal Analysis (DSC)

[0096] The DSC ("differential Scanning Calorimetry") thermal analysis, for determining the melting point (T_m) and the crystallization temperature (T_c) of the polymers obtained, was **carried out** using a Perkin Elmer Pyris differential scanning calorimeter. For this **aim**, 5 mg of polymer were analyzed, with a scanning rate ranging from 1°C/min to 20°C/min; in an inert nitrogen atmosphere.

[0097] The DSC ("Differential Scanning Calorimetry") thermal analysis, for determining the glass transition temperature (T_g) of the polymers obtained was carried out by means of the above calorimeter, using the following thermal program: isotherm for 3 minutes at +70°C; cooling from +70°C to -90°C at a rate of 10°C/min; isotherm for 3 min at -90°C; heating from -90°C to +70°C at a rate of 10°C/min.

Molecular weight determination

[0098] The determination of the molecular weight (MW) of the polymers obtained was **carried out** by means of GPC ("Gel Permeation Chromatography") operating under the following conditions:

- Agilent 1100 pump;
- I.R. Agilent 1100 detector;
- PL Mixed-A columns;
- solvent/eluent: tetrahydrofuran (THF);
- flow-rate 1 ml/min;
- temperature: 25°C;
- molecular mass calculation: Universal Calibration method.

[0099] The weight average molecular weight (M_w) and polydispersion Index" (PDI) corresponding to the M_w/M_n ratio (M_n = number average molecular weight), are specified.

Determination of the branching

[0100] The determination of the branching of the polymers obtained was **carried out** by means of the GPC/MALLS technique obtained by coupling a multi-angle light scattering detector (MALLS) with a traditional SEC/RI elution, operating under the following conditions:

- Agilent 1050 pump;
- I.R. Agilent 1050 detector;
- MALLS Dawn-DSP Wyatt detector - Technology, $\lambda = 632.8$ nm;
- PL GEL Mixed-A (x4) columns;
- solvent/eluent: tetrahydrofuran (THF);
- flow-rate 1 ml/min;
- temperature: 25°C.

[0101] Operating as described above, the absolute measurement can be contemporaneously **carried out** of the molecular weight and gyration radius of the macromolecules that are separated by the chromatographic system: the quantity of light scattered from a macromolecular species in solution can in fact be used directly for obtaining its molecular weight, whereas the angular variation in the scattering is directly correlated to its average dimensions. The fundamental relation which is used is represented by the following equation (1):

$$\frac{K * c}{R_{\theta}} = \frac{1}{M_w P_{\theta}} + 2A_2 c \quad (1)$$

wherein:

- K^* is the optical constant which depends on the wavelength of the light used, **on** the refraction index (dn/dc) of the polymer, **on** the solvent used;
- M_w is the weight average molecular weight;
- c is the concentration of the polymeric solution;
- R_θ is the intensity of the light scattered, measured at the angle θ (excess Rayleigh factor);
- P_θ is the function describing the variation of the light scattered with the angle at which it is measured, equal to 1 for an angle θ equal to 0;
- A_2 is the second virial coefficient.

[0102] For very low concentrations (typical of a GPC system), the equation (1) indicated above is reduced to the following equation (2):

$$\frac{K^*c}{R_\theta} = \frac{1}{M_w P_\theta} \quad (2)$$

wherein K^* , c , R_θ , M_w and P_θ , have the same meanings defined above, and by **carrying out** the measurement on several angles, the extrapolation at angle null of the function K^*c/R_θ in relation to $\sin^2\theta/2$ directly provides the molecular weight of the intercept value and the gyration radius of the slope.

[0103] Furthermore, as this measurement is **carried out** for every slice of the chromatogram, it is possible to obtain a distribution of both the molecular weight and **the** gyration radius.


[0104] The macromolecular dimensions in solution are directly correlated to their branching degree: for the same molecular weight, the smaller the dimensions of the macromolecule with respect to the linear correspondent, the higher the branching degree will be.

[0105] Informations relating to the macrostructure of the polymer is qualitatively deduced from the value of the parameter α , which represents the slope of the curve which correlates the gyration radius with the molecular weight: when, under the same analysis conditions, this value decreases with respect to a macrostructure of the linear type, there is the presence of a polymer having a branched-type macrostructure. The typical value of the parameter α for linear polybutadiene having a high content of 1,4-cis units, in tetrahydrofuran (THF), is equal to 0.58-0.60.

EXAMPLE 1

Synthesis of the **ligand** having formula (L2)

[0106]



[0107] 2.48 mg (14 μ moles) of 2,6-di-iso-propylaniline were introduced into a reaction flask together with 5 ml of methanol, obtaining a limpid solution. 0.25 ml of formic acid and 20 ml of methanol containing 1.96 g (12 μ moles) of 2,6-diacetylpyridine were subsequently added dropwise to said solution, at room temperature. After about 1 hour, the precipitation of a yellow microcrystalline solid product was obtained: said yellow solid was recovered by filtration, washed with cold methanol and dried, under vacuum, at room temperature, obtaining 2.4 g of a light yellow solid product (yield

= 62%) having formula (L2).

[0108] Elemental analysis [found (calculated)]: C: 77.80% (78.22%); H: 8.24% (8.13%); N: 8.51% (8.69%); O: 4.91% (4.96%).

[0109] Molecular weight (MW): 322.45.


[0110] FT-IR (nujol): 1700 cm^{-1} $\nu_{\text{(C=O)}}$; 1648 cm^{-1} $\nu_{\text{(C=N)}}$.

[0111] $^1\text{H-NMR}$ (δ shift from TMS): 1.16 (d, 12H), 2.27 (s, 3H), 2.73 (m, 2H), 2.80 (s, 3H), 7.17 (m, 3H), 7.95 (t, 1H), 8.15 (d, 1H), 8.57 (d, 1H).

EXAMPLE 2

Synthesis of the **ligand** having formula (L6)

[0112]



[0113] 1.96 g (12 mmoles) of 2,6-di-acetylpyridine were introduced into a reaction flask together with 5 ml of methanol and 5 drops of formic acid, obtaining a solution. 5 ml of methanol containing 1.34 g (9 mmoles) of 2,6-diethylaniline were subsequently added dropwise to said solution, at room temperature. After 48 hours, the mixture was cooled to 4°C , obtaining the precipitation of a whitish microcrystalline solid product: said whitish solid product was recovered by filtration, washed with cold methanol and dried, under vacuum, at room temperature, obtaining 1.8 g of a whitish solid product (yield = 67%) having formula (L6).

[0114] Elemental analysis [found (calculated)]: C: 77.58% (77.52%); H: 7.50% (7.53%); N: 9.60% (9.52%); O: 5.30% (5.43%).


[0115] Molecular weight (MW): 294.40.

[0116] FT-IR (nujol): 1648 cm^{-1} $\nu_{\text{(C=N)}}$; 1702 cm^{-1} $\nu_{\text{(C=O)}}$.

EXAMPLE 3

Synthesis of $\text{CoCl}_2(\text{L2})$ [sample GL545]

[0117]



[0118] Anhydrous cobalt dichloride (CoCl_2) (0.401 g; 3.09 mmoles) was introduced into a 100 ml reaction flask together with tetrahydrofuran (THF) (40 ml). The whole was kept under stirring, at room temperature, for a few minutes and the **ligand** having formula (L2) (1.20 g; 3.7 mmoles; molar ratio L2/Co = 1.2) obtained as described in Example 1, was subsequently added. Upon the addition of the **ligand**, a dark blue-coloured suspension was immediately formed, which was kept under stirring, at room temperature, for 1 day. The solvent was then removed under vacuum and the residue obtained was dried under vacuum, at room temperature, and subsequently charged onto the porous septum of a hot extractor for solids and was extracted, in continuous, with pentane at boiling point, for 24 hours, in order to remove the non-reacted **ligand**. Subsequently, the residue remaining on the porous septum was extracted again, in continuous, with dichloromethane at boiling point, for 24 hours, obtaining a green-coloured solution. The dichloromethane was removed under vacuum and the solid residue remaining on the porous septum was recovered and dried under vacuum, at room temperature, obtaining 1.25 g of a dark green solid product corresponding to the complex $\text{CoCl}_2(\text{L2})$, equal to a conversion of 89.4% with respect to the cobalt dichloride charged.


[0119] Elemental analysis [found (calculated)]: C: 55.20% (55.77%); H: 5.50% (5.79%); Cl: 15.30% (15.68%); Co: 12.80% (13.03%); N: 5.90% (6.19%); O: 3.20% (3.54%).

[0120] Molecular weight (MW): 452.28 FT-IR (nujol): 1648 cm^{-1} $\nu_{(\text{C}=\text{O})}$; 1590 cm^{-1} $\nu_{(\text{C}=\text{N})}$; 334 cm^{-1} $\nu_{(\text{Co}-\text{Cl})}$.

EXAMPLE 4

Synthesis of $\text{CoCl}_2(\text{L6})$ [sample GL926]

[0121]



[0122] Anhydrous cobalt dichloride (CoCl_2) (0.832 g; 6.41 mmoles) was introduced into a 100 ml reaction flask together with tetrahydrofuran (THF) (70 ml). The whole was kept under stirring, at room temperature, for a few minutes and the **ligand** having formula (L6) (2.07 g; 7.03 mmoles; molar ratio L6/Co = 1.1) obtained as described in Example 2, was subsequently added. Upon the addition of the **ligand**, a green-coloured suspension was immediately formed, which was kept, under stirring, at room temperature, for 1 day. The solvent was then removed under vacuum and the residue obtained was dried under vacuum, at room temperature, and subsequently charged onto the porous septum of a hot extractor for solids and was extracted, in continuous, with pentane at boiling point, for 24 hours, in order to remove the non-reacted **ligand**. Subsequently, the residue remaining on the porous septum was extracted again, in continuous, with dichloromethane at boiling point, for 24 hours, obtaining a green-coloured solution. The dichloromethane was removed under vacuum and the solid residue remaining on the porous septum was recovered and dried under vacuum, at room temperature, obtaining 2.31 g of a dark green solid product corresponding to the complex $\text{CoCl}_2(\text{L6})$, equal to a conversion of 85% with respect to the cobalt dichloride charged.

[0123] Elemental analysis [found (calculated)]: C: 53.40% (53.79%); H: 4.90% (5.23%); Cl: 16.30% (16.71%); Co: 13.40% (13.89%); N: 6.30% (6.60%); O: 3.50% (3.77%).

[0124] Molecular weight (MW): 424.23


[0125] FT-IR (nujol): 1685 cm^{-1} $\nu_{(\text{C}=\text{O})}$; 1590 cm^{-1} $\nu_{(\text{C}=\text{N})}$; 334 cm^{-1} $\nu_{(\text{Co}-\text{Cl})}$.

[0126] Figure 1 shows the FT-IR spectrum of the complex $\text{CoCl}_2(\text{L6})$ obtained (the nujol bands having been subtracted).

EXAMPLE 5

Synthesis of $\text{CoCl}_2(\text{L4})$ [sample GL922]

[0127]



[0128] Anhydrous cobalt dichloride (CoCl_2) (0.413 g; 3.18 mmoles) was introduced into a 100 ml reaction flask together with tetrahydrofuran (THF) (70 ml). The whole was kept under stirring, at room temperature, for a few minutes and the **ligand** having formula (L4) (i.e. 2,6-di-acetylpyridine) (0.571 g; 3.50 mmoles; molar ratio L4/Co = 1.1), was subsequently added. Upon the addition of the **ligand**, a green-coloured suspension was immediately formed, which was kept, under stirring, at room temperature, for 1 day. The solvent was then removed under vacuum and the residue obtained was dried under vacuum, at room temperature, and subsequently charged onto the porous septum of a hot extractor for solids and was extracted, in continuous, with pentane at boiling point, for 24 hours, in order to remove the non-reacted **ligand**. Subsequently, the residue remaining on the porous septum was extracted again, in continuous, with dichloromethane at boiling point, for 24 hours, obtaining a green-coloured solution. The dichloromethane was removed under vacuum and the solid residue remaining on the porous septum was recovered and dried under vacuum, at room temperature, obtaining 0.82 g of a light green solid product corresponding to the complex $\text{CoCl}_2(\text{L4})$, equal to a conversion of 88% with respect to the cobalt dichloride charged.

[0129] Elemental analysis [found (calculated)]: C: 36.60% (36.89%); H: 2.90% (3.10%); Cl: 24.0% (24.20%); Co: 19.90% (20.11%); N: 4.50% (4.78%); O: 10.70% (10.92%).

[0130] Molecular weight (MW): 293.01

[0131] FT-IR (nujol): 1666 cm^{-1} $\nu_{\text{C=O}}$; 330 cm^{-1} $\nu_{\text{Co-Cl}}$.

[0132] Figure 2 shows the FT-IR spectrum of the complex $\text{CoCl}_2(\text{L4})$ obtained (the nujol bands having been subtracted).

EXAMPLE 6 (GL639)

[0133] 2 ml of 1,3-butadiene equal to about 1.4 g were condensed at a low temperature (-20°C) in a 25 ml test-tube. 7.45 ml of toluene were then added, and the temperature of the solution thus obtained was brought to 20°C . Methylaluminoxane (MAO) in a toluene solution (6.3 ml; 1×10^{-2} moles, equal to about 0.58 g) was then added, and subsequently the complex $\text{CoCl}_2(\text{L2})$ [sample GL545] (2.25 ml of a toluene solution at a concentration equal to 2 mg/ml; 1×10^{-5} moles, equal to about 4.5 mg) obtained as described in Example 3. The whole was kept, under magnetic stirring, at 20°C , for 30 minutes. The polymerization was then quenched by the addition of 2 ml of methanol containing a few drops of hydrochloric acid. The polymer obtained was then coagulated by the addition of 40 ml of a methanol solution containing 4% of Irganox[®] 1076 antioxidant (Ciba), obtaining 1.19 g of polybutadiene having a content of 1,4-cis units equal to 97.6%; further characteristics of the process and of the polybutadiene obtained are indicated in Table 1.

[0134] Figure 3 shows the FT-IR spectrum of the polybutadiene obtained.

EXAMPLE 7 (GL664)

[0135] 2 ml of 1,3-butadiene equal to about 1.4 g were condensed at a low temperature (-20°C) in a 25 ml test-tube. 7.45 ml of toluene were then added, and the temperature of the solution thus obtained was brought to 0°C . Methylaluminoxane (MAO) in a toluene solution (6.3 ml; 1×10^{-2} moles, equal to about 0.58 g) was then added, and subsequently the complex $\text{CoCl}_2(\text{L2})$ [sample GL545] (2.25 ml of a toluene solution at a concentration equal to 2 mg/ml; 1×10^{-5} moles, equal to about 4.5 mg) obtained as described in Example 3. The whole was kept, under magnetic stirring, at 20°C , for 30 minutes. The polymerization was then quenched by the addition of 2 ml of methanol containing a few drops of hydrochloric acid. The polymer obtained was then coagulated by the addition of 40 ml of a methanol solution containing 4% of Irganox[®] 1076 antioxidant (Ciba), obtaining 0.672 g of polybutadiene having a content of 1,4-cis units equal to

98.1%: further characteristics of the process and of the polybutadiene obtained are indicated in Table 1.

[0136] Figure 3 shows the FT-IR spectrum of the polybutadiene obtained.

EXAMPLE 8 (GL682)

[0137] 2 ml of 1,3-butadiene equal to about 1.4 g were condensed at a low temperature (-20°C) in a 25 ml test-tube. 7.45 ml of toluene were then added, and the temperature of the solution thus obtained was brought to 20°C. Dry methylaluminoxane (MAO_{dry}) in a solution of methylene chloride (6.3 ml; 1×10^{-2} moles, equal to about 0.58 g) was then added, and subsequently the complex CoCl₂(L2) [sample GL545] (2.25 ml of a toluene solution at a concentration equal to 2 mg/ml; 1×10^{-5} moles, equal to about 4.5 mg) obtained as described in Example 3. The whole was kept, under magnetic stirring, at 20°C, for 8 minutes. The polymerization was then quenched by the addition of 2 ml of methanol containing a few drops of hydrochloric acid. The polymer obtained was then coagulated by the addition of 40 ml of a methanol solution containing 4% of IrganoX® 1076 antioxidant (Ciba), obtaining 0.66 g of polybutadiene having a content of 1,4-cis units equal to 97.0%: further characteristics of the process and of the polybutadiene obtained are indicated in Table 1.

[0138] Figure 3 shows the FT-IR spectrum of the polybutadiene obtained.

EXAMPLE 9 (B251)

[0139] 15 ml of 1,3-butadiene equal to about 10.5 g were condensed at a low temperature (-20°C) in a 250 ml glass reactor. 100 ml of benzene were then added, and the temperature of the solution thus obtained was brought to 20°C. Methylaluminoxane (MAO) in a toluene solution (9.95 ml; 1.58×10^{-2} moles, equal to about 0.92 g) was then added, and subsequently the complex CoCl₂(L2) [sample GL545] (3.55 ml of a toluene solution at a concentration equal to 2 mg/ml; 1.58×10^{-5} moles, equal to about 7.1 mg) obtained as described in Example 3. The whole was kept, under magnetic stirring, at 20°C, for 240 minutes. The polymerization was then quenched by the addition of 2 ml of methanol containing a few drops of hydrochloric acid. The polymer obtained was then coagulated by the addition of 100 ml of a methanol solution containing 4% of IrganoX® 1076 antioxidant (Ciba), obtaining 5.37 g of polybutadiene having a content of 1,4-cis units equal to 96.7%: further characteristics of the process and of the polybutadiene obtained are indicated in Table 1.

EXAMPLE 10 (B230)

[0140] 15 ml of 1,3-butadiene equal to about 10.5 g were condensed at a low temperature (-20°C) in a 250 ml glass reactor. 100 ml of toluene were then added, and the temperature of the solution thus obtained was brought to 20°C. Methylaluminoxane (MAO) in a toluene solution (9.95 ml; 1.58×10^{-2} moles, equal to about 0.92 g) was then added, and subsequently the complex CoCl₂(L2) [sample GL545] (3.55 ml of a toluene solution at a concentration equal to 2 mg/ml; 1.58×10^{-5} moles, equal to about 7.1 mg) obtained as described in Example 3. The whole was kept, under magnetic stirring, at 20°C for 240 minutes. The polymerization was then quenched by the addition of 2 ml of methanol containing a few drops of hydrochloric acid. The polymer obtained was then coagulated by the addition of 40 ml of a methanol solution containing 4% of IrganoX® 1076 antioxidant (Ciba), obtaining 4.74 g of polybutadiene having a content of 1,4-cis units equal to 96.6%: further characteristics of the process and of the polybutadiene obtained are indicated in Table 1.

[0141] Figure 3 shows the FT-IR spectrum of the polybutadiene obtained.

EXAMPLE 11 (B231)

[0142] 15 ml of 1,3-butadiene equal to about 1.4 g were condensed at a low temperature (-20°C) in a 250 ml glass reactor. 100 ml of heptane were then added, and the temperature of the solution thus obtained was brought to 20°C. Methylaluminoxane (MAO) in a toluene solution (9.95 ml; 1.58×10^{-2} moles, equal to about 0.92 g) was then added, and subsequently the complex CoCl₂(L2) [sample GL545] (3.55 ml of a toluene solution at a concentration equal to 2 mg/ml; 1.58×10^{-5} moles, equal to about 7.1 mg) obtained as described in Example 3. The whole was kept, under magnetic stirring, at 20°C, for 255 minutes. The polymerization was then quenched by the addition of 2 ml of methanol containing a few drops of hydrochloric acid. The polymer obtained was then coagulated by the addition of 100 ml of a methanol solution containing 4% of IrganoX® 1076 antioxidant (Ciba), obtaining 4.10 g of polybutadiene having a content of 1,4-cis units equal to 97.0%: further characteristics of the process and of the polybutadiene obtained are indicated in Table 1.

EXAMPLE 12 (GL967)

[0143] 2 ml of 1,3-butadiene equal to about 1.4 g were condensed at a low temperature (-20°C) in a 25 ml test-tube. 7.65 ml of toluene were then added, and the temperature of the solution thus obtained was brought to 20°C. Methyla-

luminoxane (MAO) in a toluene solution (6.3 ml; 1×10^{-2} moles, equal to about 0.58 g) was then added, and subsequently the complex $\text{CoCl}_2(\text{L6})$ [sample GL926] (2.11 ml of a toluene solution at a concentration equal to 2 mg/ml; 1×10^{-5} moles, equal to about 4.2 mg) obtained as described in Example 4. The whole was kept, under magnetic stirring, at 20°C, for 60 minutes. The polymerization was then quenched by the addition of 2 ml of methanol containing a few drops of hydrochloric acid. The polymer obtained was then coagulated by the addition of 40 ml of a methanol solution containing 4% of Irganox® 1076 antioxidant (Ciba), obtaining 1.04 g of polybutadiene having a content of 1,4-cis units equal to 98.9%: further characteristics of the process and of the polybutadiene obtained are indicated in Table 1.

[0144] Figure 4 shows the ^1H -NMR and ^{13}C -NMR spectra of the polybutadiene obtained.

EXAMPLE 13 (G1054)

[0145] 2 ml of 1,3-butadiene equal to about 1.4 g were condensed at a low temperature (-20°C) in a 25 ml test-tube. 7.65 ml of heptane were then added, and the temperature of the solution thus obtained was brought to 50°C. Methylaluminoxane (MAO) in a toluene solution (6.3 ml; 1×10^{-2} moles, equal to about 0.58 g) was then added, and subsequently the complex $\text{CoCl}_2(\text{L6})$ [sample GL926] (2.11 ml of a toluene solution at a concentration equal to 2 mg/ml; 1×10^{-5} moles, equal to about 4.2 mg) obtained as described in Example 4. The whole was kept, under magnetic stirring, at 20°C, for 60 minutes. The polymerization was then quenched by the addition of 2 ml of methanol containing a few drops of hydrochloric acid. The polymer obtained was then coagulated by the addition of 40 ml of a methanol solution containing 4% of Irganox® 1076 antioxidant (Ciba), obtaining 1.06 g of polybutadiene having a content of 1,4-cis units equal to 98.3%: further characteristics of the process and of the polybutadiene obtained are indicated in Table 1.

[0146] Figure 3 shows the FT-IR spectrum of the polybutadiene obtained.

EXAMPLE 14 (G1055)

[0147] 2 ml of 1,3-butadiene equal to about 1.4 g were condensed at a low temperature (-20°C) in a 25 ml test-tube. 7.65 ml of toluene were then added, and the temperature of the solution thus obtained was brought to 50°C. Methylaluminoxane (MAO) in a toluene solution (6.3 ml; 1×10^{-2} moles, equal to about 0.58 g) was then added, and subsequently the complex $\text{CoCl}_2(\text{L6})$ [sample GL926] (2.11 ml of a toluene solution at a concentration equal to 2 mg/ml; 1×10^{-5} moles, equal to about 4.2 mg) obtained as described in Example 4. The whole was kept, under magnetic stirring, at 20°C, for 60 minutes. The polymerization was then quenched by the addition of 2 ml of methanol containing a few drops of hydrochloric acid. The polymer obtained was then coagulated by the addition of 40 ml of a methanol solution containing 4% of Irganox® 1076 antioxidant (Ciba), obtaining 1.4 g of polybutadiene having a content of 1,4-cis units equal to 98.4%: further characteristics of the process and of the polybutadiene obtained are indicated in Table 1.

[0148] Figure 3 shows the FT-IR spectrum of the polybutadiene obtained.

EXAMPLE 15 (GL970)

[0149] 2 ml of 1,3-butadiene equal to about 1.4 g were condensed at a low temperature (-20°C) in a 25 ml test-tube. 8.2 ml of toluene were then added, and the temperature of the solution thus obtained was brought to 20°C. Methylaluminoxane (MAO) in a toluene solution (6.3 ml; 1×10^{-2} moles, equal to about 0.58 g) was then added, and subsequently the complex $\text{CoCl}_2(\text{L4})$ [sample GL922] (1.5 ml of a toluene solution at a concentration equal to 2 mg/ml; 1×10^{-5} moles, equal to about 3.0 mg) obtained as described in Example 5. The whole was kept, under magnetic stirring, at 20°C, for 90 minutes. The polymerization was then quenched by the addition of 2 ml of methanol containing a few drops of hydrochloric acid. The polymer obtained was then coagulated by the addition of 40 ml of a methanol solution containing 4% of Irganox® 1076 antioxidant (Ciba), obtaining 1.4 g of polybutadiene having a content of 1,4-cis units equal to 97.1%: further characteristics of the process and of the polybutadiene obtained are indicated in Table 1.

[0150] Figure 5 shows the ^1H -NMR and ^{13}C -NMR spectra of the polybutadiene obtained.

[0151] Figure 6 shows the DSC diagrams of the polybutadiene obtained.

EXAMPLE 16 (G1056)

[0152] 2 ml of 1,3-butadiene equal to about 1.4 g were condensed at a low temperature (-20°C) in a 25 ml test-tube. 8.2 ml of heptane were then added, and the temperature of the solution thus obtained was brought to 50°C. Methylaluminoxane (MAO) in a toluene solution (6.3 ml; 1×10^{-2} moles, equal to about 0.58 g) was then added, and subsequently the complex $\text{CoCl}_2(\text{L4})$ [sample GL922] (1.5 ml of a toluene solution at a concentration equal to 2 mg/ml; 1×10^{-5} moles, equal to about 3.0 mg) obtained as described in Example 5. The whole was kept, under magnetic stirring, at 20°C, for 60 minutes. The polymerization was then quenched by the addition of 2 ml of methanol containing a few drops of hydrochloric acid. The polymer obtained was then coagulated by the addition of 40 ml of a methanol solution containing

4% of Irganox® 1076 antioxidant (Ciba), obtaining 1.4 g of polybutadiene having a content of 1,4-cis units equal to 97.8%: further characteristics of the process and **of the** polybutadiene obtained are indicated in Table 1.

[0153] Figure 3 shows the FT-IR spectrum of the polybutadiene obtained.

EXAMPLE 17 (G1057)

[0154] 2 ml of 1, 3-butadiene equal to about 1.4 g were condensed at a low temperature (-20°C) in a 25 ml test-tube. 8.2 ml of toluene were then added, and the temperature of the solution thus obtained was brought to 50°C. Methylaluminoxane (MAO) in a toluene solution (6.3 ml; 1×10^{-2} moles, equal to about 0.58 g) was then added, and subsequently the complex $\text{CoCl}_2(\text{L4})$ [sample GL922] (1.5 ml of a toluene solution at a concentration equal to 2 mg/ml; 1×10^{-5} moles, equal to about 3.0 mg) obtained as described in Example 5. The whole was kept, under magnetic stirring, at 20°C, for 60 minutes. The polymerization was then quenched by the addition of 2 ml of methanol containing a few drops of hydrochloric acid. The polymer obtained was then coagulated by the addition of 40 ml of a methanol solution containing 4% of Irganox® 1076 antioxidant (Ciba), obtaining 1.4 g of polybutadiene having a content of 1,4-cis units equal to 98.1%: further characteristics of the process and **of the** polybutadiene obtained are indicated in Table 1.


[0155] Figure 3 shows the FT-IR spectrum of the polybutadiene obtained.

Table 1: Polymerization of 1,3-butadiene with catalytic systems comprising complexes of cobalt

Examples	Times (min)	Conversion (%)	N ^(a) (h ⁻¹)	T _m ^(b) (°C)	T _c ^(c) (°C)	M _w (g·mol ⁻¹)	M _w /M _n	α ^(e)
6	30	85	4407	-11.9	-43.2	333256	2.2	0.55
7	30	48	2489	-9.2	-38.7	230144	1.5	0.54
8	8	46	9139	-11.8	-37.8	659269	2.8	0.55
9	240	51.1	1573	-12.0	-43.5	271000	2.1	0.54
10	240	45.1	1387	-12.2	-44.3	610000	2.5	0.56
11	255	39	1129	-13.2	-46.1	285000	2.3	0.53
12	60	74.3	1926	-10.5	-40.4	230000	1.5	0.56
13	60	76.0	1970	-15.9	-61.1	180000	1.4	0.53
14	60	100	2592	-16.9	-59.9	210000	1.6	0.54
15	90	100	1728	-12.8	-45.7	134000	2.3	0.46
16	60	100	2592	-16.4	-62.3	131000	1.7	0.48
17	60	100	2592	-17.5	-64.3	132000	1.8	0.49
(a): number of moles of 1,3-butadiene polymerized per hour, per mole of cobalt; (b): melting point; (c): crystallization temperature; (e): linearity index of polybutadiene								

Claims

1. A process for the preparation of (co)polymers of conjugated dienes which comprises polymerizing at least one conjugated diene in the presence of a catalytic system comprising at least one oxo-nitrogenated complex of cobalt having general formula (I):



wherein:


R_1 and R_2 , equal to or different from each other, represent a hydrogen atom, or they are selected from linear or branched C_1 - C_{20} alkyl groups, optionally halogenated, cycloalkyl groups optionally substituted; aryl groups optionally substituted;

Y represents an oxygen atom; or a group $-N-R_3$ wherein R_3 represents a hydrogen atom, or it is selected from linear or branched C_1 - C_{20} alkyl groups, optionally halogenated, cycloalkyl groups optionally substituted; aryl groups optionally substituted;

or, when Y represents a group $-N-R_3$, R_2 and R_3 can be **optionally** bound to each other to form, together with the other atoms to which they are bound, a cycle containing from 3 to 6 carbon atoms, saturated, unsaturated, or aromatic, optionally substituted with linear or branched C_1 - C_{20} alkyl groups, said cycle optionally containing heteroatoms such as oxygen, sulfur, nitrogen, silicon, phosphorous, selenium;

X_1 and X_2 , equal to or different from each other, represent a halogen atom such as chlorine, bromine, iodine; or they are selected from linear or branched C_1 - C_{20} alkyl groups, $-OCOR_4$ groups or $-OR_4$ groups wherein R_4 is selected from linear or branched C_1 - C_{20} alkyl groups.

2. The process for the preparation of (co)polymers of conjugated dienes according to claim 1, wherein said catalytic system comprises at least one co-catalyst (b) selected from organic compounds of an element M' different from carbon, said element M' being selected from elements belonging to groups 2, 12, 13 or 14, of the Periodic Table of Elements, such as: boron, aluminium, zinc, magnesium, gallium, tin.
3. The process for the preparation of (co)polymers of conjugated dienes according to claim 2, wherein said co-catalyst (b) is selected from (b₁) aluminium alkyls having general formula (II):



wherein X' represents a halogen atom such as chlorine, bromine, iodine, fluorine; R_5 is selected from linear or branched C_1 - C_{20} alkyl groups, cycloalkyl groups, aryl groups, said groups being optionally substituted with one or more silicon or germanium atoms; and n is an integer ranging from 0 to 2.

4. The process for the preparation of (co)polymers of conjugated dienes according to claim 2, wherein said co-catalyst (b) is selected from (b₂) organo-oxygenated compounds of an element M' different from carbon belonging to groups 13 or 14 of the Periodic Table of Elements.
5. The process for the preparation of (co)polymers of conjugated dienes according to claim 2, wherein said co-catalyst (b) is selected from (b₃) organometallic compounds or mixtures of organometallic compounds of an element M' different from carbon capable of reacting with the oxo-nitrogenated complex of cobalt having general formula (I), extracting therefrom a substituent X_1 or X_2 σ -bound, to form on the one hand at least one neutral compound, and on the other an ionic compound consisting of a cation containing the metal (Co) coordinated by the **ligand**, and a non-coordinating organic anion containing the metal M' , wherein the negative charge is delocalized on a multicentric structure.
6. A process for the preparation of (co)polymers of conjugated dienes according to any of the previous claims, wherein said conjugated diene is selected from: 1,3-butadiene, 2-methyl-1,3-butadiene (isoprene), 2,3-dimethyl-1,3-butadiene, 1,3-pentadiene, 1,3-hexadiene, cyclo-1,3-hexadiene, or mixtures thereof.
7. The process for the preparation of (co)polymers of conjugated dienes according to any of the previous claims,

wherein in said oxo-nitrogenated complex of cobalt having general formula (I):


R_1 and R_2 , equal to or different from each other, represent a hydrogen atom; or they are selected from linear or branched C_1 - C_{20} alkyl groups, preferably are a methyl group;

Y is an oxygen atom; or a group -N- R_3 wherein R_3 is selected from phenyl groups substituted with linear or branched C_1 - C_{20} alkyl groups, preferably substituted with one or more methyl, ethyl, *iso*-propyl, *tert*-butyl groups;

X_1 and X_2 , the same as each other, are a halogen atom such as chlorine, bromine, iodine, preferably chlorine.

8. The process for the preparation of (co)polymers of conjugated dienes according to claim 3, wherein said aluminium alkyls (b_1) having general formula (II) are diethyl-aluminium chloride (DEAC), mono-ethyl-aluminium dichloride (EADC), ethylaluminumsesquichloride (EASC).




9. The process for the preparation of (co)polymers of conjugated dienes according to claim 4, wherein said organo-oxygenated compounds (b_2) are selected from aluminoxanes having general formula (III):



wherein R_6 , R_7 and R_8 , equal to or different from each other, represent a hydrogen atom, a halogen atom such as chlorine, bromine, iodine, fluorine; or they are selected from linear or branched C_1 - C_{20} alkyl groups, cycloalkyl groups, aryl groups, said groups being optionally substituted with one or more silicon or germanium atoms; and p is an integer ranging from 0 to 1,000.

10. The process for the preparation of (co)polymers of conjugated dienes according to claim 9, wherein said organo-oxygenated compound (b_2) is methylaluminoxane (MAO).

11. The process for the preparation of (co)polymers of conjugated dienes according to claim 5, wherein said compounds or mixtures of compounds (b_3) are selected from organic compounds of aluminium and especially boron, such as those represented by the following general formulae:



wherein w is an integer ranging from 0 to 3, each group R_C independently represents an alkyl group or an aryl group having from 1 to 10 carbon atoms and each group R_D independently represents an aryl group partially or totally, preferably totally, fluorinated, having from 6 to 20 carbon atoms, P represents a pyrrole radical optionally substituted.

12. The process for the preparation of (co)polymers of conjugated dienes according to any of the previous claims, wherein said process is carried out in the presence of an inert organic solvent selected from: saturated aliphatic hydrocarbons such as butane, pentane, hexane, heptane, or mixtures thereof; saturated cycloaliphatic hydrocarbons such as cyclopentane, cyclohexane, or mixtures thereof; mono-olefins such as 1-butene, 2-butene, or mixtures thereof; aromatic hydrocarbons such as benzene, toluene, xylene, or mixtures thereof; halogenated hydrocarbons such as methylene chloride, chloroform, carbon tetrachloride, trichloroethylene, perchloroethylene, 1,2-dichloroethane, chlorobenzene, bromobenzene, chlorotoluene, or mixtures thereof.


13. The process for the preparation of (co)polymers of conjugated dienes according to claim 12, wherein the concentration of the conjugated diene to be (co)polymerized in said inert organic solvent ranges from 5% by weight to 50% by weight with respect to the total weight of the mixture of conjugated diene and inert organic solvent.

14. The process for the preparation of (co)polymers of conjugated dienes according to any of the previous claims, wherein said process is carried out at a temperature ranging from -70°C to +100°C.

Patentansprüche

1. Ein Verfahren für die Herstellung von (Co)polymeren konjugierter Diene, welches das Polymerisieren mindestens

eines konjugierten Diens in Gegenwart eines katalytischen Systems, das mindestens einen sauerstoff- und stickstoffhaltigen Komplex von Kobalt mit der allgemeinen Formel (I) beinhaltet, beinhaltet:



wobei:

R_1 und R_2 , einander gleich oder voneinander verschieden, ein Wasserstoffatom darstellen oder sie ausgewählt sind aus linearen oder verzweigten, optional halogenierten C_1 - C_{20} -Alkylgruppen, optional substituierten Cycloalkylgruppen; optional substituierten Arylgruppen;


Y ein Sauerstoffatom darstellt; oder eine -N- R_3 -Gruppe, wobei R_3 ein Wasserstoffatom darstellt oder es ausgewählt ist aus linearen oder verzweigten, optional halogenierten C_1 - C_{20} -Alkylgruppen, optional substituierten Cycloalkylgruppen; optional substituierten Arylgruppen;

oder, wenn Y eine -N- R_3 -Gruppe darstellt, R_2 und R_3 optional aneinander gebunden sein können, um zusammen mit den anderen Atomen, an die sie gebunden sind, einen Ring zu bilden, der 3 bis 6 Kohlenstoffatome enthält, gesättigt, ungesättigt oder aromatisch, optional substituiert mit linearen oder verzweigten C_1 - C_{20} -Alkylgruppen, wobei der Ring optional Heteroatome wie etwa Sauerstoff, Schwefel, Stickstoff, Silicium, Phosphor, Selen enthält;

X_1 und X_2 , einander gleich oder voneinander verschieden, ein Halogenatom wie etwa Chlor, Brom, Iod darstellen; oder sie ausgewählt sind aus linearen oder verzweigten C_1 - C_{20} -Alkylgruppen, -OCOR₄-Gruppen oder -OR₄-Gruppen, wobei R_4 aus linearen oder verzweigten C_1 - C_{20} -Alkylgruppen ausgewählt ist.

2. Verfahren für die Herstellung von (Co)polymeren konjugierter Diene gemäß Anspruch 1, wobei das katalytische System mindestens einen Cokatalysator (b) beinhaltet, der aus organischen Verbindungen eines Elements M', das sich von Kohlenstoff unterscheidet, ausgewählt ist, wobei das Element M' aus Elementen ausgewählt ist, die zu den Gruppen 2, 12, 13 oder 14 des Periodensystems der Elemente gehören, wie etwa: Bor, Aluminium, Zink, Magnesium, Gallium, Zinn.

3. Verfahren für die Herstellung von (Co)polymeren konjugierter Diene gemäß Anspruch 2, wobei der Cokatalysator (b) ausgewählt ist aus (b₁) Aluminiumalkylen mit der allgemeinen Formel (II):



wobei X' ein Halogenatom wie etwa Chlor, Brom, Iod, Fluor darstellt; R_5 ausgewählt ist aus linearen oder verzweigten C_1 - C_{20} -Alkylgruppen, Cycloalkylgruppen, Arylgruppen, wobei die Gruppen optional mit einem oder mehreren Silicium- oder Germaniumatomen substituiert sind; und n eine ganze Zahl im Bereich von 0 bis 2 ist.

4. Verfahren für die Herstellung von (Co)polymeren konjugierter Diene gemäß Anspruch 2, wobei der Cokatalysator (b) ausgewählt ist aus (b₂) organo-oxygenierten Verbindungen eines Elements M', das sich von Kohlenstoff unterscheidet, das zu den Gruppen 13 oder 14 des Periodensystems der Elemente gehört.

5. Verfahren für die Herstellung von (Co)polymeren konjugierter Diene gemäß Anspruch 2, wobei der Cokatalysator (b) ausgewählt ist aus (b₃) organometallischen Verbindungen oder Mischungen organometallischer Verbindungen eines Elements M', das sich von Kohlenstoff unterscheidet, in der Lage, mit dem sauerstoff- und stickstoffhaltigen Komplex von Kobalt mit der allgemeinen Formel (I) zu reagieren, wobei ein σ -gebundener Substituent X_1 oder X_2 extrahiert wird, um einerseits mindestens eine neutrale Verbindung und andererseits eine ionische Verbindung, bestehend aus einem Kation, welches das durch den Liganden koordinierte Metall (Co) enthält, und einem nicht koordinierenden organischen Anion, welches das Metall M' enthält, wobei die negative Ladung auf einer polyzentrischen Struktur delokalisiert ist, zu bilden.

6. Verfahren für die Herstellung von (Co)polymeren konjugierter Diene gemäß einem der vorhergehenden Ansprüche, wobei das konjugierte Dien aus Folgendem ausgewählt ist: 1,3-Butadien, 2-Methyl-1,3-butadien (Isopren), 2,3-Dimethyl-1,3-butadien, 1,3-Pentadien, 1,3-Hexadien, Cyclo-1,3-hexadien oder Mischungen davon.

7. Verfahren für die Herstellung von (Co)polymeren konjugierter Diene gemäß einem der vorhergehenden Ansprüche, wobei bei dem sauerstoff- und stickstoffhaltigen Komplex von Kobalt mit der allgemeinen Formel (I):


R_1 und R_2 , einander gleich oder voneinander verschieden, ein Wasserstoffatom darstellen; oder sie ausgewählt sind aus linearen oder verzweigten C_1 - C_{20} -Alkylgruppen, vorzugsweise eine Methylgruppe sind;

Y ein Sauerstoffatom ist; oder eine $-N-R_3$ -Gruppe, wobei R_3 ausgewählt ist aus Phenylgruppen, substituiert mit linearen oder verzweigten C_1 - C_{20} -Alkylgruppen, vorzugsweise substituiert mit einer oder mehreren Methyl-, Ethyl-, *iso*-Propyl-, *tert*-Butyl-Gruppen;

X_1 und X_2 , einander gleich, ein Halogenatom wie etwa Chlor, Brom, Iod, vorzugsweise Chlor, sind.

8. Verfahren für die Herstellung von (Co)polymeren konjugierter Diene gemäß Anspruch 3, wobei die Aluminiumalkyle (b_1) mit der allgemeinen Formel (II) Diethylaluminiumchlorid (DEAC), Monoethylaluminiumdichlorid (EADC), Ethylaluminiumsesquichlorid (EASC) sind.




9. Verfahren für die Herstellung von (Co)polymeren konjugierter Diene gemäß Anspruch 4, wobei die organo-oxygenierten Verbindungen (b_2) ausgewählt sind aus Aluminoxanen mit der allgemeinen Formel (III):



wobei R_6 , R_7 und R_8 , einander gleich oder voneinander verschieden, ein Wasserstoffatom, ein Halogenatom wie etwa Chlor, Brom, Iod, Fluor darstellen; oder sie ausgewählt sind aus linearen oder verzweigten C_1 - C_{20} -Alkylgruppen, Cycloalkylgruppen, Arylgruppen, wobei die Gruppen optional mit einem oder mehreren Silicium- oder Germaniumatomen substituiert sind; und p eine ganze Zahl im Bereich von 0 bis 1000 ist.

10. Verfahren für die Herstellung von (Co)polymeren konjugierter Diene gemäß Anspruch 9, wobei die organo-oxygenierte Verbindung (b_2) Methylaluminoxan (MAO) ist.

11. Verfahren für die Herstellung von (Co)polymeren konjugierter Diene gemäß Anspruch 5, wobei die Verbindungen oder Mischungen von Verbindungen (b_3) ausgewählt sind aus organischen Verbindungen von Aluminium und insbesondere Bor, wie etwa den durch die folgenden allgemeinen Formeln dargestellten:



wobei w eine ganze Zahl im Bereich von 0 bis 3 ist, jede Gruppe R_C unabhängig eine Alkylgruppe oder eine Arylgruppe mit 1 bis 10 Kohlenstoffatomen darstellt und jede Gruppe R_D unabhängig eine teilweise oder gänzlich, vorzugsweise gänzlich, fluorierte Arylgruppe mit 6 bis 20 Kohlenstoffatomen darstellt, P einen optional substituierten Pyrrolrest darstellt.

12. Verfahren für die Herstellung von (Co)polymeren konjugierter Diene gemäß einem der vorhergehenden Ansprüche, wobei das Verfahren in Gegenwart eines inerten organischen Lösungsmittels ausgeführt wird, welches aus Folgendem ausgewählt ist:

gesättigten aliphatischen Kohlenwasserstoffen wie etwa Butan, Pentan, Hexan, Heptan oder Mischungen davon; gesättigten cycloaliphatischen Kohlenwasserstoffen wie etwa Cyclopentan, Cyclohexan oder Mischungen davon; Monoolefinen wie etwa 1-Buten, 2-Buten oder Mischungen davon; aromatischen Kohlenwasserstoffen wie etwa Benzen, Toluol, Xylen oder Mischungen davon; halogenierten Kohlenwasserstoffen wie etwa Methylchlorid, Chloroform, Kohlenstofftetrachlorid, Trichlorethylen, Perchlorethylen, 1,2-Dichlorethan, Chlorbenzen, Brombenzen, Chlortoluol oder Mischungen davon.


13. Verfahren für die Herstellung von (Co)polymeren konjugierter Diene gemäß Anspruch 12, wobei die Konzentration

des conjugués diènes pour la (Co)polymérisation dans le solvant organique inerte dans le domaine de 5 p.-% à 50 p.-%, rapporté au poids total de la composition de diène conjugué et de solvant organique inerte, se situe.

14. Procédé pour la fabrication de (Co)polymères conjugués de diènes conformément à l'une des revendications précédentes, dans lequel le procédé est effectué à une température dans le domaine de -70°C à +100 °C.

Revendications

1. Un procédé pour la préparation de (co)polymères de diènes conjugués, lequel comprend la polymérisation d'au moins un diène conjugué en présence d'un système catalytique comprenant au moins un complexe oxo-azoté de cobalt ayant la formule générale (I) :



où :

R₁ et R₂, égaux ou différents l'un de l'autre, représentent un atome d'hydrogène, ou ils sont sélectionnés parmi des groupes alkyle en C₁-C₂₀ linéaires ou ramifiés, facultativement halogénés, des groupes cycloalkyle facultativement substitués ; des groupes aryle facultativement substitués ;


Y représente un atome d'oxygène ; ou un groupe -N-R₃ où R₃ représente un atome d'hydrogène, ou il est sélectionné parmi des groupes alkyle en C₁-C₂₀ linéaires ou ramifiés, facultativement halogénés, des groupes cycloalkyle facultativement substitués ; des groupes aryle facultativement substitués ;

ou, lorsque Y représente un groupe -N-R₃, R₂ et R₃ peuvent être facultativement liés l'un à l'autre afin de former, conjointement avec les autres atomes auxquels ils sont liés, un cycle contenant de 3 à 6 atomes de carbone, saturé, insaturé, ou aromatique, facultativement substitué par des groupes alkyle en C₁-C₂₀ linéaires ou ramifiés, ledit cycle contenant facultativement des hétéroatomes tels que l'oxygène, le soufre, l'azote, le silicium, le phosphore, le sélénium ;

X₁ et X₂, égaux ou différents l'un de l'autre, représentent un atome d'halogène tel que le chlore, le brome, l'iode ; ou ils sont sélectionnés parmi des groupes alkyle en C₁-C₂₀ linéaires ou ramifiés, des groupes -OCOR₄ ou des groupes -OR₄ où R₄ est sélectionné parmi des groupes alkyle en C₁-C₂₀ linéaires ou ramifiés.

2. Le procédé pour la préparation de (co)polymères de diènes conjugués selon la revendication 1, où ledit système catalytique comprend au moins un co-catalyseur (b) sélectionné parmi des composés organiques d'un élément M' différent du carbone, ledit élément M' étant sélectionné parmi des éléments appartenant aux groupes 2, 12, 13 ou 14 du Tableau Périodique des Éléments, tels que : le bore, l'aluminium, le zinc, le magnésium, le gallium, l'étain.

3. Le procédé pour la préparation de (co)polymères de diènes conjugués selon la revendication 2, où ledit co-catalyseur (b) est sélectionné parmi (b₁) des alkyles d'aluminium ayant la formule générale (II) :



où X' représente un atome d'halogène tel que le chlore, le brome, l'iode, le fluor ; R₅ est sélectionné parmi des groupes alkyle en C₁-C₂₀ linéaires ou ramifiés, des groupes cycloalkyle, des groupes aryle, lesdits groupes étant facultativement substitués par un ou plusieurs atomes de silicium ou de germanium ; et n est un entier compris dans la gamme allant de 0 à 2.

4. Le procédé pour la préparation de (co)polymères de diènes conjugués selon la revendication 2, où ledit co-catalyseur (b) est sélectionné parmi (b₂) des composés organo-oxygénés d'un élément M' différent du carbone appartenant aux groupes 13 ou 14 du Tableau Périodique des Éléments.

5. Le procédé pour la préparation de (co)polymères de diènes conjugués selon la revendication 2, où ledit co-catalyseur (b) est sélectionné parmi (b₃) des composés organométalliques ou mélanges de composés organométalliques d'un élément M' différent du carbone capables de réagir avec le complexe oxo-azoté de cobalt ayant la formule générale (I), extrayant de celui-ci un substituent X₁ ou X₂ σ-lié, afin de former d'un côté au moins un composé neutre, et de l'autre un composé ionique consistant en un cation contenant le métal (Co) coordonné par le ligand, et un anion organique non-coordinant contenant le métal M', où la charge négative est délocalisée sur une structure multicentrique.


6. Un procédé pour la préparation de (co)polymères de diènes conjugués selon n'importe lesquelles des revendications précédentes, où ledit diène conjugué est sélectionné parmi : le 1,3-butadiène, le 2-méthyl-1,3-butadiène (isoprène), le 2,3-diméthyl-1,3-butadiène, le 1,3-pentadiène, le 1,3-hexadiène, le cyclo-1,3-hexadiène, ou des mélanges de ceux-ci.

7. Le procédé pour la préparation de (co)polymères de diènes conjugués selon n'importe lesquelles des revendications précédentes, où dans ledit complexe oxo-azoté de cobalt ayant la formule générale (I) :

R₁ et R₂, égaux ou différents l'un de l'autre, représentent un atome d'hydrogène ; ou ils sont sélectionnés parmi des groupes alkyle en C₁-C₂₀ linéaires ou ramifiés, de préférence sont un groupe méthyle ;
Y est un atome d'oxygène ; ou un groupe -N-R₃ où R₃ est sélectionné parmi des groupes phényle facultativement substitués par des groupes alkyle en C₁-C₂₀ linéaires ou ramifiés, préférablement substitués par un ou plusieurs groupes méthyle, éthyle, *iso*-propyle, *tert*-butyle ;
X₁ et X₂, identiques l'un à l'autre, sont un atome d'halogène tel que le chlore, le brome, l'iode, préférablement le chlore.

8. Le procédé pour la préparation de (co)polymères de diènes conjugués selon la revendication 3, où lesdits alkyles d'aluminium (b₁) ayant la formule générale (II) sont le chlorure de di-éthyl-aluminium (DEAC), le dichlorure de mono-éthyl-aluminium (EADC), le sesquichlorure d'éthylaluminium (EASC).




9. Le procédé pour la préparation de (co)polymères de diènes conjugués selon la revendication 4, où lesdits composés organo-oxygénés (b₂) sont sélectionnés parmi des aluminoxanes ayant la formule générale (III) :



où R₆, R₇ et R₈, égaux ou différents l'un de l'autre, représentent un atome d'hydrogène, un atome d'halogène tel que le chlore, le brome, l'iode, le fluor ; ou ils sont sélectionnés parmi des groupes alkyle en C₁-C₂₀ linéaires ou ramifiés, des groupes cycloalkyle, des groupes aryle, lesdits groupes étant facultativement substitués par un ou plusieurs atomes de silicium ou de germanium ; et p est un entier compris dans la gamme allant de 0 à 1 000.

10. Le procédé pour la préparation de (co)polymères de diènes conjugués selon la revendication 9, où ledit composé organo-oxygéné (b₂) est le méthylaluminoxane (MAO).

11. Le procédé pour la préparation de (co)polymères de diènes conjugués selon la revendication 5, où lesdits composés ou mélanges de composés (b₃) sont sélectionnés parmi des composés organiques d'aluminium et surtout de bore, tels que ceux représentés par les formules générales suivantes :



où w est un entier compris dans la gamme allant de 0 à 3, chaque groupe R_C représente indépendamment un groupe alkyle ou un groupe aryle ayant de 1 à 10 atomes de carbone et chaque groupe R_D représente indépendamment un groupe aryle partiellement ou totalement, préférablement totalement, fluoré, ayant de 6 à 20 atomes

de carbone, P représente un radical pyrrolique facultativement substitué.

- 5 12. Le procédé pour la préparation de (co)polymères de diènes conjugués selon n'importe lesquelles des revendications précédentes, ledit procédé étant mis en oeuvre en présence d'un solvant organique inerte sélectionné parmi : des hydrocarbures aliphatiques saturés tels que le butane, le pentane, l'hexane, l'heptane, ou des mélanges de ceux-ci ; des hydrocarbures cycloaliphatiques saturés tels que le cyclopentane, le cyclohexane, ou des mélanges de ceux-ci ; des mono-oléfines telles que le 1-butène, le 2-butène, ou des mélanges de ceux-ci ; des hydrocarbures aromatiques tels que le benzène, le toluène, le xylène, ou des mélanges de ceux-ci ; des hydrocarbures halogénés tel que le chlorure de méthylène, le chloroforme, le tétrachlorure de carbone, le trichloroéthylène, le perchloroéthylène, le 1,2-dichloroéthane, le chlorobenzène, le bromobenzène, le chlorotoluène, ou des mélanges de ceux-ci.
- 10
13. Le procédé pour la préparation de (co)polymères de diènes conjugués selon la revendication 12, où la concentration du diène conjugué devant être (co)polymérisé dans ledit solvant organique inerte est comprise dans la gamme allant de 5 % en poids à 50 % en poids par rapport au poids total du mélange de diène conjugué et de solvant organique inerte.
- 15
14. Le procédé pour la préparation de (co)polymères de diènes conjugués selon n'importe lesquelles des revendications précédentes, ledit procédé étant mis en oeuvre à une température comprise dans la gamme allant de -70 °C à +100 °C.
- 20




Figure 1

FT-IR spectrum of the $\text{CoCl}_2(\text{L6})$ complex [sample GL926] (Example 4)

(the nujol bands have been subtracted)




Figure 2

FT-IR spectrum of the $\text{CoCl}_2(\text{L4})$ complex [sample GL922] (Example 5)

(the nujol bands have been subtracted)




Figure 3

FT-IR spectra of polybutadienes obtained: GL639 (Example 6); GL664 (Example 7); GL682 (Example 8); G1057 (Example 17) G1054 (Example 13); B230 (Example 10); G1055 (Example 14); G1056 (Example 16)




Figure 4

Spectra ^{13}C -NMR (on the left) and ^1H -NMR (on the right) of the polybutadiene of Example 12






Figure 5

Spectra ^{13}C -NMR (on the left) and ^1H -NMR (on the right) of the polybutadiene of Example 15



(A)



(B)

Figure 6

DSC diagrams of the polybutadiene of Example 15: (A) crystallization;

(B) melting

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 5879805 A [0009] [0010]
- US 4324939 A [0010]
- US 3966697 A [0010]
- US 4285833 A [0010]
- US 3498963 A [0010]
- US 3522332 A [0010]
- US 4182813 A [0010]
- US 5548045 A [0010]
- US 7009013 B [0010]
- IT 1349141 [0011] [0013] [0014]
- IT 1349142 [0011]
- IT 1349143 [0011] [0015] [0017]
- WO 200110875 A [0049]
- WO 2011061151 A [0054] [0061]
- US 5128295 A [0059]
- US 5258475 A [0059]
- EP 277003 A [0066]
- EP 495375 A [0066]
- EP 520732 A [0066]
- EP 427697 A [0066]
- EP 421659 A [0066]
- EP 418044 A [0066]
- WO 9200333 A [0066]
- WO 9205208 A [0066]


Non-patent literature cited in the description

- TAKEUCHI Y. et al. new Industrial Polymers. American Chemical Society Symposium Series, 1974, vol. 4, 15-25 [0004]
- HALASA A. F. et al. Kirk-Othmer Encyclopedia of Chemical Technology. John Wiley and Sons, 1989, vol. 8, 1031-1045 [0004]
- TATE D. et al. Encyclopedia of Polymer Science and Engineering. John Wiley and Sons, 1989, vol. 2, 537-590 [0004]
- Encyclopedia of Polymer Science and Technology. KERNS M. et al. Butadiene Polymers. Wiley, 2003, vol. 5, 317-356 [0004]
- PORRI L. et al. Comprehensive Polymer Science. Pergamon Press, 1989, vol. 4, 53-108 [0006]
- THIELE S. K. H. et al. Macromolecular Science. Part C: Polymer Reviews, 2003, vol. C43, 581-628 [0006]
- OSAKADA, K. et al. Advanced Polymer Science, 2004, vol. 171, 137-194 [0006]
- RICCI G. et al. Advances in Organometallic Chemistry Research. Nova Science Publisher, Inc, 2007, 1-36 [0006] [0013] [0014] [0015] [0017]
- RICCI G. et al. Coordination Chemistry Reviews, 2010, vol. 254, 661-676 [0006] [0013] [0014] [0015] [0017]
- RICCI G. et al. Cobalt: Characteristics, Compounds, and Applications. Nova Science Publisher, Inc, 2011, 39-81 [0006]
- RACANELLI P. et al. European Polymer Journal, 1970, vol. 6, 751-761 [0007]
- RICCI G. et al. Polymer Communication, 1991, vol. 32, 514-517 [0007]
- FURUKAWA J. et al. Polymer Journal, 1971, vol. 2, 371-378 [0008]
- ASHITAKA H. et al. Journal of Polymer Science: Polymer Chemistry Edition, 1983, vol. 21, 1853-1860 [0008]
- ASHITAKA H. et al. Journal of Polymer Science: Polymer Chemistry Edition, 1983, vol. 21, 1951-1972 [0008]
- ASHITAKA H. et al. Journal of Polymer Science: Polymer Chemistry Edition, 1983, vol. 21, 1973-1988 [0008]
- ASHITAKA H. et al. Journal of Polymer Science: Polymer Chemistry Edition. 1983, vol. 21, 1989-1995 [0008]
- NATTA G. et al. Chemical Communications, 1967, vol. 24, 1263-1265 [0009]
- RICCI G. et al. Polymer Communication, 1988, vol. 29, 305-307 [0009]
- RICCI G. et al. Polymer Communication, 1988, vol. 29, 305-307 [0009] [0010]
- RICCI G. et al. Macromolecules, 2005, vol. 38, 1064-1070 [0011] [0015]
- RICCI G. et al. Journal of Organometallic Chemistry, 2005, vol. 690, 1845-1854 [0011] [0015] [0017]
- TAKEUCHI M. et al. Polymer International, 1992, vol. 29, 209-212 [0011]
- TAKEUCHI M. et al. Polymer International, 1995, vol. 36, 41-45 [0011]
- TAKEUCHI M. et al. Macromolecular Chemistry and Physics, 1996, vol. 197, 729-743 [0011]
- DIERKES P. et al. Journal of Chemical Society, Dalton Transactions, 1999, 1519-1530 [0011]
- VAN LEEUWEN P. et al. Chemical Reviews, 2000, vol. 100, 2741-2769 [0011]

- **FREIXA Z. et al.** *Dalton Transactions*, 2003, 1890-1901 [0011]
- **TOLMAN C.** *Chemical Reviews*, 1977, vol. 77, 313-348 [0011]
- **RICCI G. et al.** *Journal of Molecular Catalysis A: Chemical*, 2005, vol. 226, 235-241 [0013]
- **KIM J. S. et al.** *e-Polymer* (European Polymer Federation), 2006 [0019]
- **ENDO K. et al.** *Journal of Polymer Science: Part A: Polymer Chemistry*, 2006, vol. 44, 4088-4094 [0020]
- **CARIOU R. et al.** *Dalton Transactions*, 2010, vol. 39, 9039-9045 [0021]
- **APPUKUTTAN et al.** *Polymer*, 2009, vol. 50, 1150-1158 [0022]
- **GONG D. et al.** *Polymer*, 2009, vol. 50, 6259-6264 [0023]
- **APPUKUTTAN V.** *Journal of Molecular Catalysis A: Chemical*, 2010, vol. 325, 84-90 [0024]
- **GONG D.** *Journal of Organometallic Chemistry*, 2011, vol. 696, 1584-1590 [0025]
- **JIE S. et al.** *Dalton Transactions*, 2011, vol. 40, 10975-10982 [0026]
- **AI P. et al.** *Journal of Organometallic Chemistry*, 2012, vol. 705, 51-58 [0026]
- **L. K. JOHNSON et al.** *Journal of the American Chemical Society*, 1995, vol. 117, 6414-6415 [0034]
- **G. VAN KOTEN et al.** *Advances in Organometallic Chemistry*, 1982, vol. 21, 151-239 [0034]
- *Periodic Table of Elements*, 22 June 2007 [0038]
- **PARKS J. E. ; HOLM R. H.** *Inorganic Chemistry*, 1968, vol. 7 (7), 1408-1416 [0049]
- **ROBERTS E. ; TURNER E. E.** *Journal of Chemical Society*, 1927, 1832-1857 [0049]
- **DUDEK G. O. ; HOLM R. H.** *Journal of the American Chemical Society*, 1961, vol. 83, 2099-2104 [0049]
- **W. BECK et al.** *Chemical Reviews*, 1988, vol. 88, 1405-1421 [0066]
- **S. H. STARES.** *Chemical Reviews*, 1993, vol. 93, 927-942 [0066]
- **MOCHEL, V. D.** *Journal of Polymer Science Part A-1: Polymer Chemistry*, 1972, vol. 10, 1009-1018 [0091]

ELJÁRÁS KONJUGÁLT DIÉNEK (KO)POLIMERJEINEK ELŐÁLLÍTÁSÁRA OLYAN KATALITIKUS RENDSZER
JELENLÉTÉBEN, AMELY TARTALMAZZA KOBALT OXO-NITROGÉNEZETT KOMPLEXÉT
SZABADALMI IGÉNYPONTOK

1. Eljárás konjugált diének (ko)polimerjeinek előállítására, amely eljárás tartalmazza legalább egy konjugált dién polimerizálását olyan katalitikus rendszer jelenlétében, amely tartalmazza kobaltnak legalább egy oxo-nitrogénezett (oxo-nitrogenated) komplexét, amely komplex (I) általános képlettel bír:



ahol az általános képletben

R_1 és R_2 , amelyek lehetnek azonosak vagy egymástól különbözők, jelentése hidrogénatom, vagy kiválaszthatók a következők közül: lineáris vagy elágazó láncú C_1 - C_{20} alkil-csoportok, amelyek kívánt esetben (optionally) halogénezettek lehetnek, cikloalkil-csoportok, amelyek kívánt esetben szubsztituáltak lehetnek, aril-csoportok, amelyek kívánt esetben szubsztituáltak lehetnek;


Y jelentése oxigénatom; vagy egy -N- R_3 általános képletű csoport, ahol R_3 jelentése hidrogénatom, vagy kiválasztható a következők közül: lineáris vagy elágazó láncú C_1 - C_{20} alkil-csoportok, amelyek kívánt esetben halogénezettek lehetnek, cikloalkil-csoportok, amelyek kívánt esetben szubsztituáltak lehetnek, aril-csoportok, amelyek kívánt esetben szubsztituáltak lehetnek;

vagy amikor Y jelentése -N- R_3 általános képletű csoport, R_2 és R_3 kívánt esetben kapcsolódhatnak egymáshoz, hogy képezzenek, azokkal a további atomokkal együtt, amelyekhez kötődnek, egy gyűrűt (cycle), amely 3-6 szénatomot tartalmaz és telített, telítetlen vagy aromás, és kívánt esetben szubsztituálva van lineáris vagy elágazó láncú C_1 - C_{20} alkil-csoportokkal, ahol az említett gyűrű kívánt esetben tartalmaz heteroatomokat, amilyenek az oxigén, kén, nitrogén, szilícium, foszfor és szelén;

X_1 és X_2 , amelyek lehetnek azonosak vagy egymástól különbözők, jelentése halogénatom, mint klór-, bróm- vagy jódatom, vagy ezek kiválaszthatók a következők közül: lineáris vagy elágazó láncú C_1 - C_{20} alkil-csoportok, -OCOR₄ általános képletű csoportok vagy -OR₄ általános képletű csoportok, ahol R_4 jelentése a következők közül választható ki: C_1 - C_{20} alkil-csoportok.

2. Az 1. igénypont szerinti eljárás konjugált diének (ko)polimerjeinek előállítására, ahol az említett katalizátor rendszer tartalmaz legalább egy (b) ko-katalizátort, amely egy M' elem, amely széntől eltérő, szerves vegyületeiből választható ki, ahol az említett M' elem olyan elemek közül választható ki, amelyek az Elemek Periódusos Táblázatának 2., 12., 13. vagy 14. csoportjához tartoznak, mint a bór, alumínium, cink, magnézium, gallium és ón.

3. Az 1. igénypont szerinti eljárás konjugált diének (ko)polimerjeinek előállítására, ahol az említett (b) (ko)katalizátor a (b-1) alumínium-alkiliek közül választható ki, amelyek a következő (II) általános képlettel bírnak:



ahol az általános képletben X' jelentése halogénatom, mint klór-, bróm-, jód- vagy fluoratom; R_5 jelentése a következők közül

választható ki: lineáris vagy elágazó láncú C_1 - C_{20} alkil-csoportok, cikloalkil-csoportok és aril-csoportok, ahol az említett csoportok kívánt esetben szubsztituálva lehetnek egy vagy több szilícium- vagy germánium atommal; és n értéke egész szám a 0 és 2 közötti tartományban.

4. A 2. igénypont szerinti eljárás konjugált diének (ko)polimerjeinek előállítására, ahol az említett (b) ko-katalizátor egy M' elem (b_2) szerves-oxigénezett (organo-oxigenated) vegyületei közül választható ki, ahol az M' elem széntől eltérő, és az Elemek Periódusos Táblázatának 13. vagy 14. csoportjához tartozik.

5. A 2. igénypont szerinti eljárás konjugált diének (ko)polimerjeinek előállítására, ahol az említett (b) ko-katalizátor egy M' elem (b_3) szerves-fémes (organometallic) vegyületei vagy szerves-fémes vegyületeinek keverékei közül választható ki, ahol az M' elem széntől eltérő, és képes reagálni kobalt oxo-nitrogénezett komplexével, amely (I) általános képlettel bír, kivonva belőle egy σ -kötésű X_1 vagy X_2 szubsztituens, hogy kialakuljon egyrészt legalább egy semleges vegyület, és másrészt egy ionos vegyület, amely olyan kationból áll, ahol ez tartalmazza a (Co) fémet a ligandum által koordináltan, továbbá egy nem-koordináló szerves anionból, amely tartalmazza az M' fémet, ahol a negatív töltés helyéről elmozdulhat (delocalizate) egy több központú (multicentric) szerkezeten.

6. Az 1-5. igénypontok bármelyike szerinti eljárás konjugált diének (ko)polimerjeinek előállítására, ahol az említett konjugált dién a következők közül választható ki: 1,3-butadién, 2-metil-1,3-butadién (izoprén), 2,3-dimetil-1,3-butadién, 1,3-pentadién, 1,3-hexadién, ciklo-1,3-hexadién, vagy mindezek keverékei.

7. Az 1-6. igénypontok bármelyike szerinti eljárás konjugált diének (ko)polimerjeinek előállítására, ahol a kobalt említett oxo-nitrogénezett, (I) általános képletű komplexében


R_1 és R_2 , amelyek lehetnek azonosak vagy egymástól különbözők, jelentése hidrogénatom, vagy ezek kiválaszthatók lineáris vagy elágazó láncú C_1 - C_{20} alkil-csoportok közül, előnyösen metil-csoport;

Y jelentése oxigénatom; vagy egy $-N-R_3$ általános képletű csoport, ahol R_3 jelentése fenil-csoportok közül választható ki, amelyek szubsztituálva vannak lineáris vagy elágazó láncú C_1 - C_{20} alkil-csoportokkal, előnyösen szubsztituálva vannak egy vagy több metil-, etil-, izopropil- vagy terc-butil-csoportokkal;

X_1 és X_2 amelyek azonosak egymással, jelentése halogénatom, mint klór-, bróm- vagy jódatom, előnyösen klóratom.

8. A 3. igénypont szerinti eljárás konjugált diének (ko)polimerjeinek előállítására, ahol az említett (b_1) alumínium-alkilok, amelyek (II) általános képlettel bírnak, a következők: dietil-alumínium-klorid (DEAC), monoetil-alumínium-diklorid (EADC), etil-alumínium-szeszkviklorid (EASC).


9. A 4. igénypont szerinti eljárás konjugált diének (ko)polimerjeinek előállítására, ahol az említett (b_2) szerves-oxigénezett vegyületek olyan aluminoxánok közül választhatók ki, amelyek a (III) általános képlettel bírnak:




ahol az általános képletben R_5 , R_7 és R_8 , amelyek lehetnek azonosak vagy egymástól különbözők, jelentése hidrogénatom, halogénatom, amilyenek a klór-, bróm-, jód- és fluoratom, vagy jelentése kiválasztató a következők közül: lineáris vagy elágazó láncú C_1 - C_{20} alkil-csoportok, cikloalkil-csoportok és aril-csoportok, ahol az említett csoportok kívánt esetben szubsztituálva lehetnek egy vagy több szilícium- vagy germánium atommal; és p értéke egész szám a 0 és 1000 közötti tartományban.

10. A 9. igénypont szerinti eljárás konjugált diének (ko)polimerjeinek előállítására, ahol az említett (b_2) szerves-oxigénezett vegyület metil-aluminoxán (MAO).

11. Az 5. igénypont szerinti eljárás konjugált diének (ko)polimerjeinek előállítására, ahol az említett (b_3) vegyületek vagy vegyületek keverékei a következők közül választhatók ki: alumínium és elsősorban bór szerves vegyületei, amilyeneket például a következő általános képletek képviselnek:





ahol az általános képletekben w értéke egész szám a 0 és 3 közötti tartományban, minden R_C csoport jelentése egymástól függetlenül alkil-csoport vagy aril-csoport, amelyek 1-10 szénatommal bírnak, és minden R_D csoport jelentése egymástól függetlenül aril-csoport, amely részlegesen vagy teljesen, előnyösen teljesen, fluorozva van és 6-20 szénatommal bír, P jelentése pirrol gyök, amely kivánt esetben szubsztituálva van, és Ph jelentése fenil-csoport.

12. Az 1-11. igénypontok bármelyike szerinti eljárás konjugált diének (ko)polimerjeinek előállítására, ahol az említett eljárást inert szerves oldószer jelenlétében hajtjuk végre, amelyek a következők közül választhatók ki: telített alifás szénhidrogének, mint bután, pentán, hexán, heptán, vagy ezek keverékei; telített cikloalifás szénhidrogének, mint ciklopentán, ciklohexán vagy ezek keverékei; monoolefinek, mint 1-butén, 2-butén, vagy ezek keverékei; aromás szénhidrogének, mint benzol, toluol, xilol, vagy ezek keverékei; halogénezett szénhidrogének, mint metilén-klorid, kloroform, szén-tetraklorid, triklór-etilén, perklór-etilén, 1,2-diklór-etán, klór-benzol, bróm-benzol, klór-toluol, vagy ezek keverékei.

13. A 12. igénypont szerinti eljárás konjugált diének (ko)polimerjeinek előállítására, ahol a (ko)polimerizálandó konjugált dién koncentrációja az említett inert szerves oldószerben az 5 tömeg % és 50 tömeg % közötti tartományban van a konjugált dién és az inert szerves oldószer keverékének össztfömegére vonatkoztatva.

14. Az 1-13. igénypontok bármelyike szerinti eljárás konjugált diének (ko)polimerjeinek előállítására, ahol az említett eljárást a -70°C és $+100^\circ\text{C}$ közötti hőmérséklet-tartományban hajtjuk végre.