

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
9 November 2006 (09.11.2006)

PCT

(10) International Publication Number
WO 2006/117318 A1

(51) International Patent Classification:
C04B 35/119 (2006.01)

(21) International Application Number:
PCT/EP2006/061864

(22) International Filing Date: 27 April 2006 (27.04.2006)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
10 2005 020 781.2 4 May 2005 (04.05.2005) DE

(71) Applicant (for all designated States except US): **DE-GUSSA AG** [DE/DE]; Bennigsenplatz 1, 40474 Düsseldorf (DE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **OSWALD, Monika** [DE/DE]; Burgallee 6c, 63454 Hanau (DE). **DELLER, Klaus** [DE/DE]; Friedhofstrasse 47, 63512 Hainburg (DE).

(74) Common Representative: **DEGUSSA AG**; S-IPM-PAT, Postcode 84/339, Rodenbacher Chaussee 4, 63457 Hanau (DE).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: SLIP CONTAINING ZIRCONIUM DIOXIDE AND ALUMINIUM OXIDE AND SHAPED BODY OBTAINABLE THEREFROM

(57) Abstract: Slip containing at least one aluminium oxide powder and at least one unstabilized zirconium dioxide powder, wherein a) the zirconium dioxide powder i) has a mean particle diameter of less than 300 nm, ii) shows only the monoclinic phase and the tetragonal phase in the X-ray diffraction pattern, with the proportion of tetragonal phase at room temperature being from 20 to 70%, and iii) is present in a proportion of from 2 to 20% by weight, based on the total amount of the slip, b) the aluminium oxide powder i) has a mean particle diameter of more than 300 nm and ii) is present in a proportion of from 80 to 98% by weight, based on the total amount of the slip, and c) the solids content, as the sum of aluminium oxide and zirconium dioxide, is from 50 to 85% by weight, based on the total amount of the slip.



WO 2006/117318 A1

**Slip containing zirconium dioxide and aluminium oxide and
shaped body obtainable therefrom**

The invention relates to a slip containing zirconium
5 dioxide and aluminium oxide and also its production. The
invention further relates to a shaped body obtainable from
the slip and its use.

Tools and construction materials made of aluminium oxide
reinforced with zirconium dioxide have been known for a
10 long time. They have high strengths and fracture
toughnesses. They are produced from powders based on
zirconium oxide/aluminium oxide by mechanical mixing using
a ball mill or the like. The homogeneous distribution of
the powders has been found to be problematical. The shaped
15 bodies obtained display problems in terms of their
strength.

Furthermore, processes in which mixed precipitates are
obtained by neutralization and coprecipitation from a
solution containing zirconium and aluminium components and
20 are then calcined and pulverized have been proposed.
However, it has been found that even for the same
composition of the starting components, powders having
different physicochemical properties are obtained.

The production of materials composed of aluminium oxide
25 reinforced with zirconium dioxide from a slip containing
zirconium dioxide is likewise known.

Zirconium oxide-aluminium oxide materials of the prior art
often do not have the desired toughness and hardness.

The technical object of the invention is therefore to
30 provide a slip which allows the production of shaped bodies
having a high toughness and a high hardness.

A further object of the invention is to provide a process for producing this slip.

A further object of the invention is to provide a shaped body which can be produced using this slip.

5 The invention provides a slip containing at least one aluminium oxide powder and at least one unstabilized zirconium dioxide powder, in which

a) the zirconium dioxide powder

i) has a mean particle diameter of less than 300 nm,

ii) shows only the monoclinic phase and the tetragonal phase in the X-ray diffraction pattern, with the proportion of tetragonal phase at room temperature being from 20 to 70%, and

iii) is present in a proportion of from 2 to 20% by weight, based on the total amount of the slip,

b) the aluminium oxide powder

i) has a mean particle diameter of more than 300 nm and

ii) is present in a proportion of from 80 to 98% by weight, based on the total amount of the slip, and

10 c) the solids content, as the sum of aluminium oxide and zirconium dioxide, is from 50 to 85% by weight, based on the total amount of the slip.

The zirconium dioxide powder of the present invention is unstabilized, i.e. the elements known to those skilled in
15 the art which stabilize zirconium dioxide, for example Y, Ca, Mg or titanium, are not present in the powder or are present only in such small amounts that they produce no stabilizing effect. The powder has a zirconium dioxide

content of at least 97% by weight, in general at least 99% by weight. In addition, it can contain up to 2.5% by weight of hafnium dioxide as accompanying component.

For the purposes of the present invention, the median is
5 the d_{50} of the volume-weighted particle size distribution. According to the present invention, the median size of the zirconium dioxide particles in the slip of the invention is less than 300 nm. The median of the particle size
10 distribution can be based on a trimodal, bimodal or monomodal distribution of the particles, with a monomodal distribution of the zirconium dioxide particles in the slip being particularly preferred. The d_{50} is preferably in the range from 70 to 200 nm.

For the present purposes, particles are individual
15 particles, aggregates and/or agglomerates which are isolated from one another, as can occur in the slip. The zirconium dioxide powder is preferably in the form of aggregated primary particles. Here, the term primary particles refers to particles which cannot be broken up
20 further without breaking chemical bonds.

The zirconium dioxide in the slip of the invention shows only the monoclinic phase and the tetragonal phase in the X-ray diffraction pattern; a cubic phase is not detectable. The proportion of tetragonal phase at room temperature in
25 the slip is from 20 to 70%, and a range from 30 to 50% can be particularly preferred.

The BET surface area of the zirconium dioxide powder present in the slip of the invention is preferably
 $60 \pm 15 \text{ m}^2/\text{g}$.

30 Furthermore, it can be advantageous for the particles of the zirconium dioxide powder to have only a small number of pores or be completely free of pores.

The aluminium oxide powder present in the slip of the invention has a mean particle diameter of more than 300 nm. The upper limit to the mean diameter is preferably less than 20 μm and particularly preferably less than 5 μm .

- 5 The aluminium oxide is advantageously present in unaggregated or only slightly aggregated form. For the present purposes, slightly aggregated means that individual particles have grown together but the predominant proportion is present in the form of individual,
10 unaggregated particles.

The BET surface area of the aluminium oxide powder present in the slip of the invention is preferably from 0.1 to 15 m^2/g .

- Furthermore, it has been found to be advantageous for the
15 aluminium oxide to have an alpha-aluminium oxide content of at least 95%.

- The liquid phase of the slip of the invention can be water, one or more organic solvents or a single-phase mixture of water and organic solvents. The liquid phase advantageously
20 consists completely or predominantly of water.

Here, the term predominantly means that the slip of the invention can additionally contain up to 10% by weight, based on the slip, of pH-regulating additives and/or surface-modifying additives.

- 25 For the purposes of the invention, surface-modified means that at least part of the hydroxy groups present on the surface of the zirconium dioxide powder have reacted with a surface modifier to form a chemical bond. The chemical bond is preferably a covalent, ionic or coordinate bond between
30 the surface modifier and the particle, but can also be a hydrogen bond.

For the present purposes, a coordinate bond means complex formation. Thus, for example, an acid/base reaction of the Brönsted or Lewis type, complex formation or esterification can take place between the functional groups of the
5 modifier and the particle.

The functional group is preferably a carboxylic acid group, an acid chloride group, an ester group, a nitrile or isonitrile group, an OH group, an SH group, an epoxide group, an anhydride group, an acid amide group, a primary,
10 secondary or tertiary amino group, an Si-OH group, a hydrolysable radical of a silane or a C-H acid group as in beta-dicarbonyl compounds. The surface modifier can also comprise more than one such functional group, as in, for example, betaines, amino acids, EDTA.

15 It can be particularly advantageous for 3-aminopropytriethoxysilane (AMEO), ammonium salts of polycarboxylic acids, for example Dolapix CE64 (from Zschimmer & Schwarz) and/or tetraalkylammonium hydroxides such as tetramethylammonium hydroxide or tetraethylammonium
20 hydroxide to be used for surface modification of the zirconium dioxide powder.

The invention further provides a process for producing the slip of the invention, in which

25 a) a dispersion of zirconium dioxide powder which has a zirconium dioxide content of from 30 to 75% by weight and optionally contains up to 10% by weight of pH-regulating additives and/or surface-active additives and in which the particles have a mean diameter of less than 300 nm is added

30 b) continuously or in portions under dispersing conditions to

c) a dispersion of aluminium oxide powder which has an aluminium oxide content of from 70 to 90% by weight, optionally contains up to 10% by weight of

pH-regulating additives and/or surface-active additives and has a mean particle diameter of more than 300 nm,

- 5 d) wherein the amounts of aluminium oxide and zirconium dioxide are selected so that the ratio of zirconium dioxide to aluminium oxide is from 2:98 to 20:80 and
- e) the solids content, as the sum of aluminium oxide and zirconium dioxide, is from 50 to 85% by weight, based on the total amount of the slip.

10 As zirconium dioxide powders, preference is given to using powders which have been produced flame-pyrolytically. For the present purposes, the term flame-pyrolytically means that the powder has been obtained by means of flame hydrolysis or flame oxidation. Flame hydrolysis is, for

15 example, the formation of zirconium dioxide by combustion of zirconium tetrachloride in a hydrogen/oxygen flame. Flame oxidation is, for example, the formation of zirconium dioxide by combustion of an organic zirconium dioxide precursor in a hydrogen/oxygen flame.

20 For example, a zirconium mixed oxide powder having the following features can preferably be used:

- mean primary particle diameter: < 20 nm, preferably 10-16 nm, particularly preferably 12-14 nm;
- Aggregate parameters:
 - 25 ▪ mean area: < 10 000 nm², preferably 5000-8000 nm²,
 - mean equivalent circle diameter: < 100 nm, preferably 50-90 nm,
 - mean aggregate circumference: < 700 nm, preferably 450-600 nm,
 - 30 ▪ mean, maximum aggregate diameter: < 150 nm, particularly preferably 100-150 nm,
 - mean, minimum aggregate diameter: < 100 nm, particularly preferably 60-90 nm.

The production of such a powder is described in the German patent application number 102004061698.1 filed on 22 December 2004. The contents of this patent application are fully incorporated by reference into the present patent application.

The zirconium dioxide dispersion used for producing the slip of the invention should have a good stability towards sedimentation, caking and thickening. Such a dispersion can be obtained by dispersing the powder by means of a high-energy mill. A dispersion produced in this way is pourable for at least 1 month, in general at least 6 months, at room temperature without prior redispersion being necessary. Furthermore, its viscosity in the shear rate range from 1 to 1000 s⁻¹ and at a temperature of 23°C is less than 1000 mPas and particularly preferably less than 100 mPas. The dispersion preferably has a monomodal distribution of the particle sizes.

In the process, a predispersion is divided into at least two substreams, these substreams are placed under a pressure of at least 500 bar, preferably from 500 to 1500 bar, particularly preferably from 2000 to 3000 bar, in a high-energy mill, depressurized through a nozzle and allowed to impinge on one another in a gas- or liquid-filled reaction space and thus milled and the dispersion is then optionally brought to the desired content by means of further dispersion medium.

The process can be carried out with the dispersion which has already been milled once being circulated and being milled a further 2 to 6 times by means of the high-energy mill. In this way, it is possible to obtain a dispersion having a smaller particle size and/or different distribution, for example monomodal or bimodal. Furthermore, the process can preferably be carried out with the pressure in the high-energy mill being from 2000 to 3000 bar. This measure, too, makes it possible to obtain a

dispersion having a smaller particle size and/or different distribution, for example monomodal or bimodal.

The production of such a dispersion is described in the German patent application number 102004061697.3 filed on
5 22 December 2004. The contents of this patent application are fully incorporated by reference into the present patent application.

The invention further provides a shaped body comprising aluminium oxide and zirconium dioxide and having a
10 zirconium dioxide content of from 2 to 20% by weight, wherein the zirconium oxide

- is homogeneously distributed in the shaped body,
- shows tetragonal and monoclinic crystallites in the X-ray diffraction pattern, with the proportion of
15 tetragonal phase being from 20 to 70%, and
- the size of the monoclinic crystallites is from 20 to 40 nm,
- the size of the tetragonal crystallites is from 30 to 50 nm.

20 The shaped body of the invention preferably has no microporosity in the range $< 10 \mu\text{m}$.

The invention further provides a process for producing the shaped body of the invention, in which

- the slip of the invention is firstly cast in a mould and
25 dried to produce a green body and
- the green body is then, after removal from the mould, sintered at temperatures from 1300°C to 1700°C in a gas atmosphere or under reduced pressure.

The invention further provides for the use of the slip of
30 the invention for producing tools, construction materials and bone implants.

Examples

Analysis: The median is determined by means of dynamic light scattering. Instrument used: Horiba LB-500. The viscosity of the dispersion is determined by means of a Brookfield rotational viscometer at 23°C as a function of the shear rate. The BET surface area is determined in accordance with DIN 66131.

Aluminium oxide:

Powder: The aluminium oxide powder used is CT 3000 SG from Almatix GmbH. The material has a monomodal particle size distribution having a d_{50} of 0.8 μm . The BET surface area is 7.5 m^2/g .

Dispersion 1 (D1): 3000 g of aluminium oxide powder are milled in the presence of 690 g of water, 18 g of Optapix AC95, 18 g of Dolapix CE64 and 1.2 g of Contraspum in a stirred ball mill (loading: 5000 g, milling media consisting of aluminium oxide) for 3 hours. The composition of the dispersion is shown in Table 1. The slip is passed through a 125 μm sieve before further use.

Zirconium dioxide

Powder: A solution comprising zirconium octoate corresponding to 24.4% by weight of ZrO_2 and 0.3% by weight of HfO_2 , 39.6% by weight of octanoic acid, 3.5% by weight of 2-(2-butoxyethoxy)ethanol and 32.2% by weight of petroleum spirit and a solution comprising zirconium n-propoxide corresponding to 27.8% by weight of ZrO_2 and 0.5% by weight of HfO_2 , 30.5% by weight of n-propanol and 41.2% by weight of tetra-n-propoxide are mixed in a ratio of 90:10 at a temperature of 50°C. 1500 g/h of the resulting homogeneous solution are atomized in 5 standard m^3/h of air by means of a nozzle having a diameter of 0.8 mm. The resulting aerosol is fed into a flame produced from hydrogen (5.0 standard m^3/h) and primary air (10 standard m^3/h) and burnt into a reaction space.

In addition, 20 standard m³/h of (secondary) air are introduced into the reaction space. The hot gases and the solid product are subsequently cooled in a cooling section. The powder obtained is deposited in filters.

- 5 The zirconium dioxide powder obtained has the following physicochemical properties: ZrO₂ content: 98.72% by weight, HfO₂ content: 1.28% by weight; BET surface area: 63 m²/g; monoclinic/tetragonal ratio (XRD): 64/36; tamped density: 95 g/l; loss on drying: 1.03% by weight; loss on ignition:
10 2.08% by weight; pH: 5.32.

- Dispersion 2 (D2): 42.14 kg of deionized water and 1.75 kg of Dolapix CE64 (from Zschimmer & Schwartz) are placed in a batch vessel and the 43.9 kg of the zirconium dioxide powder prepared above are subsequently added by means of
15 the suction hose of an Ystral Conti-TDS 3 (stator slits: 4 mm ring and 1 mm ring, rotor/stator spacing: about 1 mm) under shear conditions. After sucking-in is complete, the suction port is closed and shearing is continued at 3000 rpm for 10 minutes. This predispersion is passed five
20 times through a Sugino Ultimaizer HJP-25050 high-energy mill at a pressure of 2500 bar using diamond nozzles having a diameter of 0.3 mm. The dispersion obtained in this way has a zirconium dioxide content of 50% by weight, a median of 112 nm and a viscosity at 100 s⁻¹ and 23°C of 27 mPas.
25 It is stable towards sedimentation, caking and thickening for at least 6 months.

Slip S1 (comparison): The aluminium oxide dispersion D1 serves as comparison. The composition is shown in Table 1.

- Slip S2 (according to the invention):** The zirconium dioxide
30 dispersion (D II) is introduced with the aid of a stand stirrer into the aluminium oxide dispersion (D1). The composition is shown in Table 1.

Table 1: Slip composition

	Amount of S1 (% by mass)	Amount of S2 (% by mass)
Aluminium oxide ^{a)}	100	89.6
Water	23	23
Zirconium oxide dispersion D2	-	10.3
Optapix AC 95 ^{b)}	0.6	0.6
Dolapix CE 64 ^{c)}	0.6	0.6
Contraspum	0.04	0.04

a) CT 3000 SG, Alcoa; b), c):Zschimmer & Schwarz;

Production of the test specimens

The test specimens were produced by solid casting, i.e. the slip is poured into a plaster mould and the body is formed, i.e. the plaster withdraws the water from the slip and consolidates it. The entire mould is filled bit by bit in this way; continual introduction of further slip results in formation of the finished test specimen. The test specimens are fired in an electrically heated laboratory muffle furnace. The firing curve was set according to the values in Table 2:

Table 2: Sintering curve

Ramp [Wh]	Target temperature [°C]	Hold time [h]
100	400	
300	1600	2
300	RT	

Test procedures

The sintered specimens were sawn to a size of 6 × 8 × 55 mm and ground before examination. These values were determined using EN 843-1 as a guide, with the standard providing for dimensions of 3 × 4 × 50 mm. The specimens are polished to

a fineness of 20 μm , and the edges are subsequently chamfered.

The strengths of the specimens were determined in a 4-point bend test by means of a TIRA Test 2850 universal testing machine; the lower contact spacing is 40 mm and the upper contact spacing is 20 mm.

The determination of the porosity and overall density was carried out by the buoyancy method.

The Vickers hardness was determined on polished sections using an instrument from Zwick Prüftechnik GmbH. The measurements were carried out using a load of 0.5 kg, so that the hardness is reported as $\text{HV}_{0.5}$. To prepare the polished sections, the specimens are embedded in an epoxy resin and the surface is polished to a fineness of 1 μm .

The scanning electron microscopic studies were carried out using a Jeol 6460F instrument, and the elemental analysis was carried out by means of an EDX instrument from Röntec. For sample preparation, carbon was vapour-deposited on the polished sections.

The epoxy resin around the prepared polished sections was removed and the ceramic specimens were aged at 1500°C for 1 hour. This exposes the grain boundaries around the particles and the individual constituents of the microstructure can be made very readily visible under the scanning electron microscope.

Results

Strength examination: It is found that the zirconium dioxide dispersion increases the strength of an Al_2O_3 ceramic.

Porosity and overall density: The two slips S1 and S2 have porosity values of less than 1.5%, so that the material can be described as "dense". The absolute values of < 1.5%

indicate that the porosity is in the region of the detection limit of the measurement method.

The addition of the dispersion D2 leads to an increase in the overall density. The slip S1 gives an overall density
5 of about 3.9, and the slip S2 gives an overall density of about 4.0 g/cm³.

Determination of the hardness and evaluation of the Vickers indentations: The hardnesses of the specimens examined are very high, and their means vary within a range from 17 to
10 19 GPa. Furthermore, the addition of the nanosize zirconium dioxide particles (slip S2) leads to an increase in the absolute hardness and a slight reduction in the range of variation compared to slip S1. This effect is not known for
microsize zirconium dioxide particles. Here, the addition
15 of microsize zirconium dioxide particles leads to a reduction in the hardness of the total microstructure.

The shaped body obtained from the slip S1 has significantly longer cracks than the shaped body obtained from slip S2.

20 Examination of microstructure: Transmission electron micrographs show that the shaped body obtained from the slip S2 is very densely sintered. Furthermore, no large pores can be seen. The shaped body obtained from the slip S1, on the other hand, displays a significant microporosity
25 in the range < 10 µm. The zirconium dioxide particles are very homogeneously distributed in the microstructure. They are located predominantly in the interstices between the aluminium oxide particles. The zirconium dioxide particles are monoclinic and tetragonal crystallites. Quantitative
30 phase analysis of the zirconium dioxide indicates that the monoclinic/tetragonal ratio in the shaped body obtained from the slip S2 is essentially the same as that in the slip S2 itself.

It is found that the size of the aluminium oxide particles in the shaped body obtained from the slip S2 is significantly smaller than in the shaped body S1 obtained from the slip S1. The nanosize zirconium dioxide powder in the slip S2 according to the invention acts as growth inhibitor for the aluminium oxide particles. This effect correlates very well with the properties found, viz. higher strength combined with higher hardness and smaller cracks in the micrographs of the Vickers hardness. The intercalated zirconium dioxide particles also lead to stressing of the microstructure, as a result of which cracks in the microstructure cannot propagate easily. This in turn improves the strength and the hardness.

Claims:

1. Slip containing at least one aluminium oxide powder and at least one unstabilized zirconium dioxide powder, characterized in that
 - 5 a) the zirconium dioxide powder
 - i) has a mean particle diameter of less than 300 nm,
 - ii) shows only the monoclinic phase and the tetragonal phase in the X-ray diffraction pattern, with the proportion of tetragonal phase at room temperature being from 20 to 70%, and
 - iii) is present in a proportion of from 2 to 20% by weight, based on the total amount of the slip,
 - b) the aluminium oxide powder
 - i) has a mean particle diameter of more than 300 nm and
 - ii) is present in a proportion of from 80 to 98% by weight, based on the total amount of the slip, and
 - c) the solids content, as the sum of aluminium oxide and zirconium dioxide, is from 50 to 85% by weight, based on the total amount of the slip.
- 10 2. Slip according to Claim 1, characterized in that the mean diameter of the zirconium dioxide particles is from 70 to 200 nm.
3. Slip according to Claim 1 or 2, characterized in that the zirconium dioxide powder is present in aggregated form.
- 15 4. Slip according to any of Claims 1 to 3, characterized in that the BET surface area of the zirconium dioxide powder is $60 \pm 15 \text{ m}^2/\text{g}$.

5. Slip according to any of Claims 1 to 4, characterized in that the zirconium dioxide powder is free of pores.
6. Slip according to any of Claims 1 to 5, characterized in that the upper limit to the mean diameter of the
5 aluminium oxide particles is 20 μm .
7. Slip according to any of Claims 1 to 6, characterized in that the BET surface area of the aluminium oxide powder is from 0.1 to 15 m^2/g .
8. Slip according to any of Claims 1 to 7, characterized
10 in that the coarse fraction has an alpha-aluminium oxide content of at least 95%.
9. Slip according to any of Claims 1 to 8, characterized in that the liquid phase is water.
10. Slip according to any of Claims 1 to 9, characterized
15 in that the dispersion contains up to 10% by weight of pH-regulating additives and/or surface-modifying additives.
11. Process for producing the slip according to any of Claims 1 to 10, characterized in that
- 20 a) a dispersion of zirconium dioxide powder which has a zirconium dioxide content of from 30 to 75% by weight and optionally contains up to 10% by weight of pH-regulating additives and/or surface-active additives and in which the particles have a mean diameter of less than 300 nm is added
- 25 b) continuously or in portions under dispersing conditions to
- c) a dispersion of aluminium oxide powder which has an aluminium oxide content of from 70 to 90% by weight, optionally contains up to 10% by weight of
30 pH-regulating additives and/or surface-active additives and has a mean particle diameter of more than 300 nm,

- d) wherein the amounts of aluminium oxide and zirconium dioxide are selected so that the ratio of zirconium dioxide to aluminium oxide is from 2:98 to 20:80 and
- e) the solids content, as the sum of aluminium oxide and zirconium dioxide, is from 50 to 85% by weight, based on the total amount of the slip.

12. Shaped body comprising aluminium oxide and zirconium dioxide and having a zirconium dioxide content of from 2 to 20% by weight, wherein the zirconium oxide
- 10 - is homogeneously distributed in the shaped body,
- shows tetragonal and monoclinic crystallites in the X-ray diffraction pattern, with the proportion of tetragonal phase being from 20 to 70%, and
- the size of the monoclinic crystallites is from 20 to
15 40 nm,
- the size of the tetragonal crystallites is from 30 to 50 nm.

13. Shaped body according to Claim 12, characterized in that the shaped body has no microporosity in the range
20 < 10 μm .

14. Process for producing the shaped body according to Claim 12 or 13, characterized in that
- the slip according to any of claims 1 to 11 is firstly cast in a mould and dried to produce a green body and
25 - the green body is then, after removal from the mould, sintered at temperatures from 1300°C to 1700°C in a gas atmosphere or under reduced pressure.

15. Use of the slip according to any of Claims 1 to 11 for producing tools, construction materials and bone implants.
- 30

INTERNATIONAL SEARCH REPORT

International application No

PCT/EP2006/061864

A. CLASSIFICATION OF SUBJECT MATTER
INV. C04B35/119

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
C04B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ, COMPENDEX, INSPEC

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 183 610 A (BROG ET AL) 2 February 1993 (1993-02-02) example 1	1-11,15
A	DE 34 45 948 A1 (KUREHA CHEMICAL INDUSTRY CO., LTD; KUREHA CHEMICAL INDUSTRY CO., LTD.,) 4 July 1985 (1985-07-04) page 10, last paragraph - page 11, paragraph 2 page 13, paragraph 1	1-11,15



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

Z document member of the same patent family

Date of the actual completion of the international search

28 July 2006

Date of mailing of the international search report

09/08/2006

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Raming, T

INTERNATIONAL SEARCH REPORT

International application No

PCT/EP2006/061864

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	BACH J P ET AL: "Fabrication and characterization of zirconia-toughened alumina obtained by inorganic and organic precursors" JOURNAL OF MATERIALS SCIENCE UK, vol. 24, no. 8, August 1989 (1989-08), pages 2711-2721, XP002392428 ISSN: 0022-2461 table V -----	12-15

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2006/061864

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5183610	A	02-02-1993	NONE	
DE 3445948	A1	04-07-1985	JP 60131860 A	13-07-1985