



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

| | | |
|---|-----------|--|
| (51) International Patent Classification⁵ : C09D 9/00 | A1 | (11) International Publication Number: WO 93/18101 (43) International Publication Date: 16 September 1993 (16.09.93) |
| (21) International Application Number: PCT/US93/01641 (22) International Filing Date: 23 February 1993 (23.02.93) (30) Priority data: 07/847,376 6 March 1992 (06.03.92) US (71) Applicant: MINNESOTA MINING AND MANUFACTURING COMPANY [US/US]; 3M Center, Post Office Box 33427, Saint Paul, MN 55133-3427 (US). (72) Inventor: GAUL, Kimberley, A. ; Post Office Box 33427, Saint Paul, MN 55133-3427 (US). (74) Agents: ODAR, Thomas, J. et al.; Office of Intellectual Property Counsel, Minnesota Mining and Manufacturing Company, Post Office Box 33427, Saint Paul, MN 55133-3427 (US). | | (81) Designated States: JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> |
| (54) Title: COMPOSITION CONTAINING LACTONE AND ESTER FOR REMOVING COATINGS (57) Abstract The present invention comprises a composition for removing coatings such as paints from substrates which comprises at least one ester and at least one lactone. The present invention further comprises a method for removing coatings. | | |

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

| | | | | | |
|----|--------------------------|----|--|----|--------------------------|
| AT | Austria | FR | France | MR | Mauritania |
| AU | Australia | GA | Gabon | MW | Malawi |
| BB | Barbados | GB | United Kingdom | NL | Netherlands |
| BE | Belgium | GN | Guinea | NO | Norway |
| BF | Burkina Faso | GR | Greece | NZ | New Zealand |
| BG | Bulgaria | HU | Hungary | PL | Poland |
| BJ | Benin | IE | Ireland | PT | Portugal |
| BR | Brazil | IT | Italy | RO | Romania |
| CA | Canada | JP | Japan | RU | Russian Federation |
| CF | Central African Republic | KP | Democratic People's Republic of Korea | SD | Sudan |
| CG | Congo | KR | Republic of Korea | SE | Sweden |
| CH | Switzerland | KZ | Kazakhstan | SK | Slovak Republic |
| CI | Côte d'Ivoire | LJ | Liechtenstein | SN | Senegal |
| CM | Cameroon | LK | Sri Lanka | SU | Soviet Union |
| CS | Czechoslovakia | LU | Luxembourg | TD | Chad |
| CZ | Czech Republic | MC | Monaco | TG | Togo |
| DE | Germany | MG | Madagascar | UA | Ukraine |
| DK | Denmark | MI | Mali | US | United States of America |
| ES | Spain | MN | Mongolia | VN | Viet Nam |
| FI | Finland | | | | |

COMPOSITION CONTAINING LACTONE AND ESTER
FOR REMOVING COATINGS

FIELD OF THE INVENTION

5 This invention relates to removing paint and/or coatings. In particular, this invention relates to compositions for removing paint and/or coatings.

BACKGROUND OF THE INVENTION

10 It is often desirable to remove deposits from a substrate in order to clean the substrate. For example, U.K. Patent No. 2,172,304 (Tsukada) discloses a composition used to remove thermoplastic resins and residues such as acetal and thermoplastic polyesters resins. Generally, acetal and thermoplastic polyester
15 resins are used as materials in molding processes such as injection molding to form objects such as steam iron housings, automotive electrical switches and television cathode-ray tube sockets. Tsukada's preferred composition comprises a β -, γ - or δ -lactone mixed with an alcohol. Tsukada also mentions that the
20 lactones can be mixed with an ester, in particular ethyl acetate, instead of an alcohol.

 In addition for the need to remove acetal and thermoplastic polyesters resins and their residues, there is a need to remove
25 paints and/or coatings from a substrate for a variety of reasons such as repainting or refinishing the substrate. Paints and/or coatings include conventional paints, varnishes, enamels, lacquers, water emulsion finishes and non-aqueous dispersions. The term "coating" hereinafter applies to both paints and coatings. Coatings can be removed in a number of different ways.
30 For example, they can be physically removed by use of a scraper or power sander or they can be chemically removed. However, methods utilizing chemical compositions have achieved considerable popularity because they are much easier to use than the non-chemical alternatives.

35 The chemical compositions used to remove coatings broadly fall within three general classes: (1) the alkali or acid class, (2) the organic solvent class and (3) the waterbased class. The first class generally comprises alkalis or acids which attack the coating by the chemical action of the ingredients thereof.
40 Representative examples of this class are described in U.S. Patent Nos. 3,681,250, 3,615,825 and 3,972,839. These alkali or acid compositions are undesirable because they often exhibit deleterious effects on wood or because they require considerable after treatment to insure the compositions complete removal from

the treated surface.

The second class of chemical compositions used to remove coatings generally comprises solvent based compositions which rely upon the solvent power of the composition to dissolve or at least
5 soften the coating. Representative examples of compositions of the second class include aromatic hydrocarbons, lower aliphatic esters, ketones, alcohols, chlorinated solvents such as methylene chloride or similar organic solvents. Many of the lower molecular weight solvents are undesirable because they are too volatile and
10 thus, readily evaporate once applied to the surface. Other solvents are highly flammable thereby posing handling and shipping problems. In addition to posing application and handling problems, some of these organic solvents are undesirable because of their adverse effects upon the atmosphere and their toxicity.

15 Therefore, attempts have been made to overcome some of the problems associated with the solvent based compositions. Higher molecular weight solvents including higher aliphatic esters have been used to overcome some of the problems associated with the lower molecular weight solvents. For example, U.S. Patent No.
20 4,120,810 (Palmer) discloses a paint remover which comprises an aromatic hydrocarbon and a second component which can include n-methyl-2-pyrrolidone or chemical analogs thereof, diacetone alcohol, or butyrolactone. U.S. Patent No. 4,508,634 (Elepano et al.) teaches the use of a composition suitable for removing paint
25 from skin comprising propylene carbonate, at least one organic cosolvent, at least one thickening agent, at least one buffering agent, at least one surfactant and water. U.S. Patent No. 4,780,235 (Jackson) teaches the use of a paint remover which comprises (a) at least one C₁-C₄ dialkyl ester of a C₄-C₆ aliphatic
30 ester, (b) an activator, (c) a surfactant and (d) at least one nonhalogen containing organic solvent such as N-methyl-2-pyrrolidone. U.S. Patent No. 5,030,290 (Davis) teaches the use of a paint stripper comprising (a) a high molecular weight polymeric resin such as polyvinyl formal resin, (2) a plasticizer such as a
35 dibasic ester and (3) a solvent which can be butyrolactone. U.S. Patent No. 5,035,829 (Suwala) teaches the use of paint removing comprising an organic acid, an alkylene glycol and a γ -lactam or γ -lactone. While the Palmer, Davis and Suwala compositions have overcome some of the problems associated with the second class of
40 removers, these compositions have either not been as effective as the solvent based paint and/or coating removers or have retained some of the adverse effects of the solvent based systems.

The third class of chemical compositions used to remove coatings generally comprises waterbased systems. An example of

such a system is U.S. Patent No. 4,927,556 (Pokorny) which discloses the use of a composition used to remove coatings from surfaces consisting essentially of water, at least one dibasic ester and at least one water soluble thickening agent. Although
5 eliminating many of the problems associated with solvents such as toxicity, the Pokorny composition did not perform as fast as solvent based systems.

Thus, there currently exists a need for a coating remover which is fast and effective and yet, does not exhibit many of the
10 adverse effects associated with alkali or solvent based compositions.

SUMMARY OF THE INVENTION

The present invention comprises a composition which can quickly
15 and effectively remove coatings from substrates. In addition, this composition eliminates many of the adverse effects associated with alkali or solvent based compositions.

The composition comprises at least one lactone, preferably selected from the group comprising β -lactones, γ -lactones, δ -
20 lactones, ϵ -lactones and mixtures thereof and at least one ester, preferably selected from the group comprising aliphatic esters or aromatic esters and mixtures thereof. If desired, water, aromatic solvents, organic solvents, surfactants, thickeners, corrosion inhibitors, fragrances or other additives can be added to the
25 composition.

The present invention also includes a method of removing a coating from a substrate utilizing the composition of the present invention.

30 DETAILED DESCRIPTION OF THE INVENTION

The composition of the present invention is used to remove coatings from substrates and comprises at least one lactone and at least one ester. Optionally, water, aromatic solvents, organic solvents, surfactants, thickeners, corrosion inhibitors,
35 fragrances and/or other additives can be added.

Lactones are cyclic esters in which the number of atoms constituting a main ring including a functional ester group is 4 to 7, two of which are provided by the ester group (-CO-O-). The different types of lactones are known as β -lactone (4 member
40 ring), γ -lactone (5 member ring), δ -lactone (6 member ring) and ϵ -lactone (7 member ring). Suitable lactones include, but are not limited to, β -propiolactone, β -butyrolactone, 4-hydroxy-3-pentenoic acid γ -lactone, 4-hydroxy-3-pentenoic acid γ -lactone, γ -butyrolactone, γ -crotonolactone, γ -valerolactone, γ -caprolactone,

δ -valerolactone and ϵ -caprolactone.

In order to form the composition of the present invention, the lactone is mixed with at least one ester. Generally, any ester can be used with the lactones. Suitable esters include, but
5 are not limited to, aliphatic and aromatic esters.

Esters of aliphatic acids include simple esters prepared by reacting a precursor alcohol such as a mono-, di- or polyhydric alcohol with an organic acid such as a mono-, di- or polycarboxylic acid. Among the suitable precursor alcohols are
10 linear alcohols, branched alcohols and oxo alcohols which are defined as a mixture of linear and methyl branched alcohols which have an oxygen group attached to the backbone. Examples of such reaction products include formic acid esters such as methyl and ethyl formate, glycol acetates, glycerol acetates, linear acetic
15 acid esters such butyl acetate and amyl acetate and oxo alcohol acetic acid esters such as oxohexyl acetate. Other examples include butyric acid esters and propionic acid esters.

Another suitable group of aliphatic acid esters are the dibasic acid esters. Dibasic acid esters can include aliphatic
20 diesters having a molecular weight up to about 200. These diesters are well known in the art and are commercially available as DuPont Dibasic Esters (DBEs), sold by the E.I. du Pont Nemours and Co. Dibasic esters that are preferred for the composition of the present invention are esters from adipic acid ($\text{COOH}(\text{CH}_2)_4\text{COOH}$),
25 glutaric acid ($\text{COOH}(\text{CH}_2)_3\text{COOH}$) and succinic acid ($\text{COOH}(\text{CH}_2)_2\text{COOH}$). Both dimethyl and diethyl esters of these acids can be used effectively in the composition of this invention.

Aromatic acid esters useful for the purposes of this invention include simple esters prepared by reacting a precursor
30 alcohol with an acid such as a benzoic or phthalic acid. Suitable aromatic acid esters include, but are not limited, to benzoic acid esters and esters of dibasic and polybasic aromatic acids such as phthalic and terephthalic acid esters.

Although water has been observed to reduce the effectiveness
35 of water-miscible solvent based compositions used as a coating removers, it has been unexpectedly observed that there is little reduction in the overall effectiveness of the lactone/ester composition if water is added to the composition. Therefore, water can be added to the composition if desired in an amount
40 where the composition remains stable.

Aromatic hydrocarbons can also be added to the composition. Aromatic hydrocarbons can be added in order to reduce the cost of the composition and to adjust the evaporation rates of the composition. Examples of aromatic hydrocarbons which can be used

include, toluene, xylene and naphthalene. Especially preferred aromatic hydrocarbons include: (a) a blend of aromatic distillates containing xylene, cumene and trimethyl benzene sold under the tradename Hi Sol 10 and commercially available from Ashland
5 Chemical Company or under the tradename Aromatic 100 commercially available from Exxon Company, (b) a blend of aromatic distillates containing naphthalene and trimethyl benzene sold under the tradename Hi Sol 15 by Ashland Chemical Company or under the tradename Aromatic 150 by the Exxon Company, and (c) an aromatic
10 solvent blend of hydrocarbons containing naphthalene and consisting predominantly of C₉-C₁₅ aromatic hydrocarbons sold under the tradename Aromatic 200 by the Exxon Company.

If desired, organic solvents can be also added to the composition. Any organic solvent can be used as long as the
15 composition remains stable. Examples of suitable solvents include ketones, aldehydes and alcohols. Generally, thickening agents are added to the composition in order to stabilize the composition and provide good flow control. For example, the presence of a thickening agent allows the composition
20 to be applied easily, level out and have the ability to cling to vertical surfaces. Suitable thickening agents include gums, polyvinyl alcohol, starches, clay derivatives, e.g., amine treated magnesium aluminum silicate, and cellulose derivatives, e.g., hydroxypropyl methylcellulose and waxes, e.g., amidized waxes,
25 castor oil derivatives. Preferably, the thickener comprises a system consisting of a clay derivative sold under the tradename Bentone 27 sold by Rheox Inc., located in Heightstown, New Jersey, an amide wax sold under the tradename Crayvallac Super by Cray Valley Products, Inc. of Stuyvesant, New York and a hydroxypropyl
30 cellulose sold under the tradename Methocel 240 commercially available by Dow Chemical Corp.

A surfactant is typically added to the composition to improve the stability of the composition. Any surfactant which helps to improve the stability of the composition can be utilized
35 although it is preferred that non-ionic surfactants be utilized. Especially preferred surfactants should have a hydrophilic-lipophilic balance (HLB) of about 10. Examples of suitable surfactants would include a blend of Span 80, a sorbitan monooleate available from ICI Americas, Inc. and Tween 80, a
40 polyoxyethylene 20 sorbitan monooleate also commercially available from ICI Americas, Inc.

Other additives can also be added. Examples of additives which can be added include corrosion inhibitors, fragrances, abrasive particles and colorants. Corrosion inhibitors help to

protect metal containers from pitting and rusting while in contact with the composition of the present invention. Examples of corrosion inhibitors include aromatic phosphate esters sold under the tradename Maphos JM-51 from PPG/Mazer or carboxylic acid salts available as Hamposyl L-30 from W.R. Grace & Company. Fragrances can be added to mask and/or improve the solvent odor of the composition. Abrasive particles physically assist in the mechanical removal of a coating. If desired, colorants such as pigments, i.e., iron oxide pigments, and dyes, i.e., oil soluble dyes can also be added.

The amounts of the lactones and esters vary in the composition according to use. For optimum results, the composition comprises from about 90 to about 10 percent by weight lactone and from about 10 to about 90 percent by weight ester. If water is added to the composition, the amount of lactone varies from about 10 to about 40 percent by weight lactone, from about 10 to about 80 percent by weight ester and up to about 50 percent by weight water. More preferably, if water is added to the composition, the amount of lactone varies from about 10 to about 40 percent, from about 15 to about 75 percent by weight ester and from about 5 to about 35 percent by weight water. If aromatic hydrocarbons are added, the composition comprises from about 10 to about 30 weight percent lactone, from about 10 to about 35 percent by weight ester, from about 0 to about 30 percent by weight water and from about 10 to about 55 weight percent aromatic hydrocarbon. More preferably, if aromatic hydrocarbons are added, the composition comprises from about from about 20 to about 30 weight percent lactone, from about 15 to about 35 percent by weight ester, from about 0 to about 30 percent by weight water and from about 20 to about 40 weight percent aromatic hydrocarbon.

The composition of this invention can be prepared in a number of ways. A preferred method includes first mixing at least one lactone with at least one ester in a dispersator equipped with a Cowles blade sold by Cowles. At the same time, a surfactant can be added to the composition. If desired, a thickener is slowly sifted into the composition. Finally, water can be added to the composition.

The composition can be applied to a coating in any conventional manner such as by brush or roller, by spraying the composition onto the coating or by dipping the coating. However, it should be coated onto the substrate in amount sufficient to remove the coating. The amount of composition applied varies according to use and can be tailored to the user's preference. After application, the composition penetrates into the coating and

either dissolves the coating or swells the coating to several times its original volume. The coating then either softens, wrinkles, bubbles and blisters resulting in its release from the substrate. After softening or blistering, the coating is removed
5 from the substrate.

The following examples are set forth to illustrate this invention and are not intended to limit the scope of this invention thereof.

10

TEST METHODS

COATING REMOVAL

The ability of a composition to remove a coating is tested by applying a composition onto a coated sample. The composition is allowed to loosen the coating material and upon loosening, the
15 material is removed from the sample by wiping or gently scraping it with a wooden tongue depressor. The time period to remove the coating(s) is then recorded.

VERTICAL CLING

20 The ability of a paint stripper to cling to a vertical surface is conducted in accordance with a modified version of the American Society for Testing and Materials Test D2202-84 entitled "Slump of Caulking Compounds and Sealants" described in Volume 4.07 entitled Building Seals and Sealants; Fire Standards;
25 Building Constructions of the 1987 Annual Book of Standards. A test jig constructed in accordance with the description in Test D2202-84 is cleaned with a solvent and then placed face upward. The coating remover composition is poured into the jig cavity flush with the surface of the jig. The jig is turned over and
30 placed in a vertical position. Readings are taken at five minutes and measured in milliliters to observe the slump of the coating remover compositions.

TEST SAMPLES

35 The samples used in the Examples 1-31 and Comparative Examples 1-16 are commercially available from Advanced Coating Technologies, Inc. of Hillsdale, MI. and were prepared by coating phosphate E treated cold rolled steel with primer PPG-80-703F commercially available from PPG Industries and then top coated
40 with white automotive lacquer sold as PPG-WALM-3967 by PPG Industries per General Motors Specification 9984052. After being coated, the panels were baked and then aged for at least four months before being tested.

EXAMPLE 1

The test sample of Example 1 was prepared in the following manner:

40.6 gms. of γ -butyrolactone, 40.6 gms of butyl acetate,
 5 .11 gms. of Tween 80 and .09 gms. of Span 80 were blended together
 in a dispersator fitted with a Cowles blade. Once blended
 together, 1.5 gms. of Crayvallac Super, 0.5 gms. of Methocel 240
 and 1.5 gms. of Bentone 27 were slowly sifted into the mixture.
 15.1 gms. of water was then added to the mixture and the mixture
 10 was thoroughly mixed. The resultant mixture was then coated onto
 a test sample and tested. The ingredients used, weight percentage
 of the ingredients and test results are reported in Table 1.

EXAMPLES 2-4

15 These examples, all of which were prepared utilizing the
 methods described in Example 1, illustrate various compositions
 found within the scope of the present invention. Examples 2-4
 varied from Example 1 in that different esters were utilized. The
 esters used, the ingredients and the weight percentage of the
 20 ingredients utilized and test results are reported in Table 1.

TABLE 1

| | Example 1 | Example 2 | Example 3 | Example 4 |
|----------------------------|--------------|--------------|--------------|-----------|
| 25 γ -butyrolactone | 40.60 | 40.60 | 40.60 | 40.60 |
| butyl acetate | 40.60 | - | - | - |
| oxohexyl acetate | - | 40.60 | - | - |
| DBE ¹ | - | - | 40.60 | - |
| methyl benzoate | - | - | - | 40.60 |
| 30 Tween 80 | 0.11 | 0.11 | 0.11 | 0.11 |
| Span 80 | 0.09 | 0.09 | 0.09 | 0.09 |
| Crayvallac Super | 1.50 | 1.50 | 1.50 | 1.50 |
| Methocel 240 | 0.50 | 0.50 | 0.50 | 0.50 |
| Bentone 27 | 1.50 | 1.50 | 1.50 | 1.50 |
| Water | 15.10 | 15.10 | 15.10 | 15.10 |
| 35 Removal Time (Mins.) | 5 | 5 | 12 | 5 |

¹DBE is a dibasic ester blend sold by the E.I. du Pont
 Nemours and Co.

EXAMPLE 5

The test sample of Example 5 illustrates the addition of an aromatic hydrocarbon to the composition. It was prepared in the following manner:

5 15 gms. of γ -butyrolactone, 20 gms of DBE, and 48.75 gms. of Hi Sol 15 were blended together in a dispersator fitted with a cowles blade. Once blended together, 1.25 gms. of Methocel 240 and 5 gms. of Bentone 27 were slowly sifted into the mixture. 10 gms. of water was then added to the mixture and the mixture is
10 thoroughly mixed. The mixture was then coated onto a test sample and tested in accordance with the procedures outlined above. The primer and the automotive lacquer were removed from the test sample in ten minutes.

15

EXAMPLES 6-8

Examples 6-8, all of which were prepared utilizing the methods described in Example 1, illustrate compositions utilizing different lactones and esters which are found within the scope of the present invention. The ingredients used, weight percentage of
20 the ingredients and test results are reported in Table 2.

TABLE 2

| | Example 6 | Example 7 | Example 8 |
|----------------------------|-----------|-----------|-----------|
| γ -butyrolactone | 22.00 | - | - |
| 25 δ -valerolactone | - | 15.00 | - |
| ϵ -caprolactone | - | - | 44.40 |
| DBE | 71.80 | 68.8 | - |
| butyl acetate | - | - | 44.40 |
| Tween 80 | 0.11 | 0.11 | 0.11 |
| 30 Span 80 | 0.09 | 0.09 | 0.09 |
| Methocel 240 | 1.00 | 1.00 | 1.00 |
| Bentone 27 | 5.00 | 5.00 | 5.00 |
| Water | - | 10.00 | 5.00 |
| 35 Removal Time (Mins.) | 12 | 15 | 11 |

EXAMPLES 9-16

40 Examples 9-16 were prepared utilizing the methods described in Example 1. These two examples illustrate various combinations of lactones, esters, surfactants, aromatics, thickeners and water. The ingredients used, weight percentage of the ingredients and

test results are reported in Table 3.

TABLE 3

| | Ex. 9 | Ex. 10 | Ex. 11 | Ex. 12 | Ex. 13 | Ex. 14 | Ex. 15 | Ex. 16 |
|----|-------|--------|--------|--------|--------|--------|--------|--------|
| 5 | | | | | | | | |
| | 8.4 | 42.0 | 22.0 | 10.0 | 32.0 | 10.0 | 20.0 | 14.0 |
| | | | | | | | | |
| 10 | 75.6 | 42.0 | - | - | 32.0 | 10.0 | 29.0 | 17.0 |
| | | | | | | | | |
| | - | - | 61.8 | 33.8 | - | - | - | - |
| | - | - | 0.11 | 0.11 | 0.14 | 0.14 | - | 0.11 |
| | - | - | 0.09 | 0.09 | 0.11 | 0.11 | - | 0.09 |
| 15 | 1.0 | 1.0 | 1.0 | 1.0 | 1.0 | 1.0 | 1.0 | 1.0 |
| | | | | | | | | |
| | 5.0 | 5.0 | 5.0 | 5.0 | 3.5 | 3.5 | 5.0 | 4.0 |
| | | | | | | | | |
| | 10.0 | 10.0 | 10.0 | 40.0 | 20.0 | 20.0 | 10.0 | 50.0 |
| 20 | - | - | - | - | 10.0 | 55.0 | 35.0 | 13.8 |
| | | | | | | | | |
| | 10 | 5 | 10 | >15 | 6 | 20 | 5 | 15 |

25

EXAMPLES 17-28

Examples 17-28 were prepared utilizing the methods described in Example 1 except that only two components were utilized, lactone and ester. The lactones and esters used, the weight percentage of these two ingredients and test results are reported in Table 4.

30

TABLE 4

| Ex. | Lactone | Ester(s) | Wt. % | Removal Time (mins.) |
|-------|-------------------------|---|-------|----------------------|
| 17 | γ -butyrolactone | propylene glycol methyl ether acetate | 50/50 | 10 |
| 18 | γ -butyrolactone | butyl acetate | 50/50 | 5 |
| 5 19 | γ -butyrolactone | methyl benzoate | 50/50 | 10 |
| 20 | γ -butyrolactone | amyl acetate | 50/50 | 5 |
| 21 | δ -valerolactone | butyl acetate | 50/50 | 11 |
| 22 | γ -butyrolactone | oxooctyl acetate | 50/50 | 13 |
| 23 | γ -butyrolactone | oxononyl acetate | 50/50 | 15 |
| 10 24 | γ -butyrolactone | dipropylene glycol methyl ether acetate | 50/50 | 17 |
| 25 | γ -butyrolactone | 2-ethyl-ethoxy-propionate | 50/50 | 7 |
| 26 | γ -butyrolactone | ethyl lactate | 50/50 | 13 |
| 27 | γ -butyrolactone | DBE | 10/90 | 15 |
| 15 28 | γ -butyrolactone | butyl acetate | 90/10 | 9 |

COMPARATIVE EXAMPLE 1

Comparative Example 1 which was prepared according to the instructions outlined in U.S. Patent No. 5,035,829 was made by mixing 32 gms. of n-methyl-2-pyrrolidone, 42 gms. of propylene glycol methyl ether, 26 gms. of acetic acid, 2 gms. of alkylphenoxypoly(oxyethylene) ethanol sold under the tradename Igepal CO-710 by Rhone-Poulenc, 2.0 gms. of triethanol amine and 0.9 gms. of hydroxypropyl cellulose sold under the tradename Klucel H sold by Hercules Inc. together and then coating it onto a test sample. The test sample was then tested in accordance with the test procedures outlined above. The primer and automotive lacquer were removed in 50 minutes.

30

COMPARATIVE EXAMPLE 2

Comparative Example 2 which was prepared according to the instructions outlined in U.S. Patent No. 5,035,829 was made by mixing together 40 gms. of n-methyl-2-pyrrolidone, 40 gms. of tripropylene glycol methyl ether, 12 gms. acetic acid, 4 gms. formic acid, 2 grams of Igepal CO-710, 2 gms. of triethanol amine and 0.8 gms. of Klucel H. This mixture was then coated onto a

test sample and tested with the aforementioned procedures. In a period of 60 minutes, not even the top paint layer was removed.

COMPARATIVE EXAMPLES 3-13

5 Comparative Examples 3-13 examined the ability of individual lactones or esters to remove a coating. The component used alone, the test results of the component and test results of a composition of the present invention comprising 50 weight percent component and 50 weight percent γ -butyrolactone are reported in
10 Table 5.

TABLE 5

| Comparative Example | Component | Removal Time (mins.) | Removal Time (mins.) 50 wt. % γ -butyrolactone |
|---------------------|--------------------------|----------------------|---|
| 15 C-3 | γ -butyrolactone | 10 | - |
| C-4 | butyl acetate | 9 | 5 |
| C-5 | amyl acetate | evaporated | 5 |
| C-6 | 2-ethyl-ethoxypropionate | 25 | 7 |
| C-7 | methyl benzoate | >15 | 10 |
| 20 C-8 | PMA ² | 35 | 10 |
| C-9 | Exxate 800 ³ | >60 | 13 |
| C-10 | ethyl lactate | 25 | 13 |
| C-11 | Exxate 900 ⁴ | >60 | 15 |
| C-12 | DBE | 25 | 15 |
| 25 C-13 | DPMA ⁵ | >60 | 17 |

² PMA is a propylene methyl ether acetate available from Dow Chemical Corporation

³ Exxate 800 is a oxyoctyl acetate sold by Exxon Company

30 ⁴ Exxate 900 is a oxynonyl acetate sold by Exxon Company

⁵ DPMA is a dipropylene glycol methyl ether acetate sold by Dow Chemical Corporation

EXAMPLES 29-31 AND COMPARATIVE EXAMPLES 14-16

35 Examples 29-31 and Comparative Examples 14-16 examined the vertical cling of the composition of the present invention and several solvent based compositions outside the scope of the present invention. The samples were prepared in accordance with the methods described in Example 1 and were tested for vertical
40 cling. The components, the weight percentage of the components

and the vertical cling test results are reported in Table 6.

TABLE 6

| | Ex. 29 | Ex. 30 | Ex. 31 | C-14 | C-15 | C-16 | |
|----|--------------------------------------|-----------|-----------|-------|------|------|------|
| 5 | γ -butyrolactone | 15.00 | - | 32.00 | - | - | - |
| | ϵ -caprolactone | - | 44.40 | - | - | - | - |
| | butyl acetate | - | 44.40 | 32.00 | - | - | - |
| | DBE | 20.00 | - | - | - | - | - |
| 10 | Tween 80 | - | 0.11 | 0.14 | - | - | - |
| | Span 80 | - | 0.09 | 0.11 | - | - | - |
| | Methocel 240 | 1.25 | 1.00 | 1.00 | - | - | - |
| | Bentone 27 | 5.00 | 5.00 | 3.50 | - | - | - |
| | Water | 10.00 | 5.00 | 20.00 | - | - | - |
| 15 | Hi Sol 15 | 48.75 | - | 10.00 | - | - | - |
| | Bix ^R 7 | - | - | - | 100 | - | - |
| | Wood Finisher's Pride [™] 8 | - | - | - | - | 100 | - |
| 20 | Zip Strip ^R 9 | - | - | - | - | - | 100 |
| | Slump (mm/5 mins.) | 0 | 16 | 20 | 100+ | 100+ | 100+ |

- 7 Bix^R Stripper is a product commercially available from Bix Manufacturing Company, Inc.
- 8 Wood Finisher's Pride[™] Paint Stripping Gel is distributed by the Scott Paper Company
- 9 Zip Strip^R Paint-Varnish and Finish Remover is sold by the Star Bronze Company.

30 It should be noted that the compositions of Comparative Examples 14-16 slumped beyond 100 mm. in less than thirty seconds.

EXAMPLES 32-37

- 35 Examples 32-37 explore the effect of the composition of the present invention on various types of coatings. Coatings were applied per manufacturer's directions to a 1/4 in. (0.64 cm.) board. The coatings were dried and then baked at 120°F (48.9°C) for two weeks. The coated boards were further aged for a year at
- 40 ambient conditions prior to testing. The ingredients used, the weight percentages, the type of coating, the number of coats removed and the removal time are reported in Table 7.

TABLE 7

| | Ex. 32 | Ex. 33 | Ex. 34 | Ex. 35 | Ex. 36 | Ex. 37 |
|----------------------------------|-----------|-----------|-----------|-----------|-----------|-----------|
| 5 | 15.0 | 15.0 | 20.0 | 15.0 | 8.4 | 20.0 |
| butyrolactone | | | | | | |
| butyl acetate | - | - | 29.0 | - | 75.6 | 29.0 |
| DBE | 20.0 | 20.0 | - | 20.0 | - | - |
| Methocel 240 | 1.25 | 1.25 | 1.0 | 1.25 | 1.0 | 1.0 |
| Bentone 27 | 5.0 | 5.0 | 5.0 | 5.0 | 5.0 | 5.0 |
| Water | 10.0 | 10.0 | 10.0 | 10.0 | 10.0 | 10.0 |
| 10 | 48.75 | 48.75 | 35.0 | 48.75 | - | 35.0 |
| Hi Sol 15 | | | | | | |
| Latex Paint ¹⁰ | X | | | | | |
| Oil-Based Paint ¹¹ | | X | X | | | |
| Polyurethane ¹² | | | | X | | |
| 15 | | | | | X | X |
| Lacquer ¹³ | | | | | | |
| Number of Coats | 6 | 2 | 2 | 3 | 3 | 3 |
| Removal Time (mins.) | 6 | 30 | 25 | 7 | 2 | 2 |

- 20 10 The latex paint comprised Glidden Spread Satin^R Latex wall paint sold by Glidden-Durkee, a Div. of SCM Corp.
- 11 The oil based paint comprised Glidden Spred Lustre^R Alkyd semi-gloss enamel manufactured by Glidden-Durkee, a Div. of SCM Corp.
- 25 12 The polyurethane comprised Minwax Fast Dry Polyurethane, gloss sold by Sterling Drug, Inc.
- 13 The lacquer comprised Parks Lacquer, satin commercially available from Parks Corporation of Somerset, Minnesota.
- 30

Samples treated with the composition of the present invention performed better than samples not treated with the composition of the present invention as illustrated by Comparative

35 Examples 1, 2, 14, 15 and 16. Moreover, compositions of the present invention showed a synergistic effect in the removal time of a coating when compared to either an ester or lactone when used alone as shown in Comparative Examples 3-13. In addition, there was little reduction in the effectiveness of the composition when

40 water was added to the composition. Similarly, the addition of an aromatic hydrocarbon did not reduce the effectiveness of the performance of the composition. Thus, the Examples show that effective performance could be obtained with the composition of the present invention.

In summary, a novel and unobvious composition utilized to remove coatings has been described. Although specific embodiments and examples have been disclosed herein, it should be borne in mind that these have been provided by way of explanation and illustration and present invention is not limited thereby. 5 Certainly modifications which are within the ordinary skill in the art are considered to lie within the scope of this invention as defined by the following claims including all equivalents.

I Claim:

1. A composition for removing coatings comprising:
 - a. at least one lactone; and
 - b. at least one ester wherein said ester is not
5 ethyl acetate.
2. The composition of Claim 1 wherein said lactone is selected from the group comprising β -lactones, γ -lactones, δ -lactones, ϵ -lactones and mixtures thereof.
10
3. The composition of Claim 1 wherein said ester is selected from the group comprising aliphatic esters, aromatic esters and mixtures thereof.
- 15 4. The composition of Claim 1 wherein said composition includes at least one aromatic solvent.
5. The composition of Claim 1 wherein said composition further includes water.
20
6. The composition of Claim 5 wherein said composition further includes at least one aromatic solvent.
7. The composition of Claim 1 wherein said composition
25 further includes at least one thickener.
8. The composition of Claim 1 wherein said composition further includes at least one additive.
- 30 9. The composition of Claim 1 wherein said composition further includes at least one surfactant.
10. The composition of Claim 1 wherein said composition further includes at least one solvent.
35
11. The composition of Claim 1 comprising from about 10 to about 90 parts by weight lactone and from about 90 to about 10 parts by weight ester.
- 40 12. The composition of Claim 5 comprising from about 10 to about 40 parts by weight lactone, from about 30 to about 80 parts by weight ester and from about 0 to about 50 parts by weight water.

13. A method of removing a coating from a substrate comprising the steps of:
- a. applying to a substrate a composition comprising at least one lactone and at least one ester;
 - 5 b. allowing said composition to penetrate said substrate; and
 - c. removing said coating from said substrate.
14. The method of Claim 13 wherein said lactone is
10 selected from the group comprising β -lactones, γ -lactones, δ -lactones, ϵ -lactones and mixtures thereof.
15. The method of Claim 13 wherein said ester is selected from the group comprising aliphatic esters, aromatic esters and
15 mixtures thereof.
16. The method of Claim 13 wherein said composition includes at least one aromatic solvent.
20. 17. The method of Claim 13 wherein said composition includes water.
18. The method of Claim 17 wherein said composition further includes at least one aromatic solvent.
25
19. The method of Claim 13 wherein said composition further includes at least one thickener.
30. 20. The method of Claim 13 wherein said composition includes at least one additive.
21. The method of Claim 13 wherein said composition includes at least one surfactant.
35
22. The method of Claim 13 wherein said composition includes at least one solvent.
23. The method of Claim 13 comprising from about 10 to about
40 90 parts by weight lactone and from about 90 to about 10 parts by weight ester.

24. The method of Claim 17 comprising from about 10 to about 40 parts by weight lactone, from about 30 to about 80 parts by weight ester and from about 0 to about 50 parts by weight water.

INTERNATIONAL SEARCH REPORT

PCT/US 93/01641

International Application No

| | | |
|---|--|-------------------------------------|
| I. CLASSIFICATION OF SUBJECT MATTER (if several classification symbols apply, indicate all) ⁶ | | |
| According to International Patent Classification (IPC) or to both National Classification and IPC | | |
| Int.Cl. 5 C09D9/00 | | |
| II. FIELDS SEARCHED | | |
| Minimum Documentation Searched ⁷ | | |
| Classification System | Classification Symbols | |
| Int.Cl. 5 | C09D | |
| Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in the Fields Searched ⁸ | | |
| III. DOCUMENTS CONSIDERED TO BE RELEVANT⁹ | | |
| Category ¹⁰ | Citation of Document, ¹¹ with indication, where appropriate, of the relevant passages ¹² | Relevant to Claim No. ¹³ |
| P,X | WO,A,9 206 169 (CREATIVE TECHNOLOGIES GROUP, INC.) 16 April 1992 see table 1 see page 5, line 1 - page 10, line 15 --- | 1-4, 7-11, 13-16, 19-23 |
| A | CH,A,670 832 (RICO S.A. LAUSANNE) 14 July 1989 see claim 1 see examples 3,4,5 --- | 1-24 |
| A | GB,A,2 191 501 (PROTECTIVE RESEARCH INDUSTRIES LIMITED) 16 December 1987 see page 1, line 5 see page 1, line 22 - line 58 see example 1 --- | 1-24 |
| | -/-- | |
| <p>¹⁰ Special categories of cited documents :</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"&" document member of the same patent family</p> | | |
| IV. CERTIFICATION | | |
| Date of the Actual Completion of the International Search | Date of Mailing of this International Search Report | |
| 27 MAY 1993 | 25.05.93 | |
| International Searching Authority | Signature of Authorized Officer | |
| EUROPEAN PATENT OFFICE | GOERKE H.R. | |

| III. DOCUMENTS CONSIDERED TO BE RELEVANT (CONTINUED FROM THE SECOND SHEET) | | |
|--|--|-----------------------|
| Category ° | Citation of Document, with indication, where appropriate, of the relevant passages | Relevant to Claim No. |
| A | GB,A,2 172 304 (POLYPLASTICS CO. LTD.) 17 September 1986 cited in the application see table 1: example 7 --- | 1-24 |
| A | WO,A,8 707 628 (CPS KEMI APS) 17 December 1987 see abstract --- | 1-24 |
| A | EP,A,0 327 290 (SERICOL GROUP LTD.) 9 August 1989 see example 6 ----- | 1-24 |

**ANNEX TO THE INTERNATIONAL SEARCH REPORT
ON INTERNATIONAL PATENT APPLICATION NO.**

US 9301641
SA 71009

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report. The members are as contained in the European Patent Office EDP file on The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information. 27/05/93

| Patent document cited in search report | Publication date | Patent family member(s) | Publication date |
|--|------------------|-------------------------|------------------|
| WO-A-9206169 | 16-04-92 | US-A- 5098592 | 24-03-92 |
| | | AU-A- 8746091 | 28-04-92 |
| | | CA-A- 2063739 | 02-04-92 |
| | | US-A- 5154848 | 13-10-92 |
| CH-A-670832 | 14-07-89 | None | |
| GB-A-2191501 | 16-12-87 | None | |
| GB-A-2172304 | 17-09-86 | JP-B- 5002720 | 13-01-93 |
| | | JP-A- 61159499 | 19-07-86 |
| WO-A-8707628 | 17-12-87 | EP-A, B 0270654 | 15-06-88 |
| EP-A-0327290 | 09-08-89 | GB-A- 2214924 | 13-09-89 |

EPO FORM P0479

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82