



Office de la Propriété
Intellectuelle
du Canada

Un organisme
d'Industrie Canada

Canadian
Intellectual Property
Office

An agency of
Industry Canada

CA 2034716 C 2001/12/25

(11)(21) **2 034 716**

(12) **BREVET CANADIEN
CANADIAN PATENT**

(13) **C**

(22) Date de dépôt/Filing Date: 1991/01/22
(41) Mise à la disp. pub./Open to Public Insp.: 1991/08/02
(45) Date de délivrance/Issue Date: 2001/12/25
(30) Priorité/Priority: 1990/02/01 (473,590) US

(51) Cl.Int.⁵/Int.Cl.⁵ C08L 23/18, C10M 143/04, C08L 23/04,
C10M 143/02
(72) Inventeur/Inventor:
Struglinski, Mark Joseph, US
(73) Propriétaire/Owner:
EXXONMOBIL CHEMICAL PATENTS INC., US
(74) Agent: BORDEN LADNER GERVAIS LLP

(54) Titre : COMPOSITIONS OLEAGINEUSES RENFERMANT UN NOUVEL ADDITIF AMELIORANT L'INDICE DE
VISCOSITE A BASE DE POLYMERE ALPHA-OLEFINIQUE DE L'ETHYLENE
(54) Title: OLEAGINOUS COMPOSITIONS CONTAINING NOVEL ETHYLENE ALPHA-OLEFIN POLYMER VISCOSITY
INDEX IMPROVER ADDITIVE

(57) **Abrégé/Abstract:**

The present invention is directed to a lubricating oil composition exhibiting improved viscosity index comprising lubricating oil and a viscosity improving effective amount of ethylene alpha-olefin polymer comprising monomer units derived from ethylene and at least one alpha-olefin represented by the formula $H^2C = CHR^1$ wherein R^1 is an alkyl group of from 1 to 18 carbon atoms, and wherein said polymer has a number average molecular weight of from above 20,000 to about 500,000, and an average of at least about 30% of the polymer chains contain terminal ethylidene unsaturation.



ABSTRACT OF THE DISCLOSURE

The present invention is directed to a lubricating oil composition exhibiting improved viscosity index comprising lubricating oil and a viscosity improving effective amount of ethylene alpha-olefin polymer comprising monomer units derived from ethylene and at least one alpha-olefin represented by the formula $H^2C = CHR^1$ wherein R^1 is an alkyl group of from 1 to 18 carbon atoms, and wherein said polymer has a number average molecular weight of from above 20,000 to about 500,000, and an average of at least about 30% of the polymer chains contain terminal ethylidene unsaturation.

- 1 -

FIELD OF THE INVENTION

This invention relates to oleaginous compositions, including lubricating oil compositions, fuel oil compositions, fuels, and the like containing ethylene alpha-olefin viscosity index improver additives.

BACKGROUND OF THE INVENTION

Lubricating oil viscosity index improvers have been widely used by the industry. Typically, these viscosity index improvers comprise a long chain hydrocarbon polymer. Ethylene-propylene copolymers and terpolymers have been widely used as the polymers of choice.

High molecular weight ethylene-propylene polymers and ethylene-propylene-diene terpolymers, having viscosity average molecular weights of from about 20,000 to 300,000, are generally produced employing Ziegler catalysts, generally VCl_4 or VOCl_3 with a halide source, such as organoaluminum halides and/or hydrogen halides. Such high molecular weight EP and EPDM polymers find use as viscosity index improvers. See, e.g., U.S. Patents 3,563,964; 3,697,429; 4,306,041; 4,540,753; 4,575,574; and 4,666,619.

The following disclosures include disclosures of EP/EPDM polymers of M_n of 700/500,000, also prepared by conventional Ziegler catalysts.

In accordance with the instant invention there are provided oleaginous compositions, particularly lubricating oil compositions, exhibiting improved viscosity index containing an additive comprised of a particular type of ethylene alpha-olefin polymer. This ethylene alpha-olefin polymer has vinylidene-type terminal unsaturation.

U.S. Patent 4,668,834 to Uniroyal Chemical discloses preparation (via certain metallocene and alumoxane catalyst systems) and composition of ethylene-alpha olefin copolymers and terpolymers having vinylidene-type terminal unsaturation, which are disclosed to be useful as intermediates in epoxy-grafted encapsulation compositions.

Japanese Published Patent Application 87-129,303A of Mitsui Petrochemical relates to narrow molecular weight distribution ($M_w/M_n < 2.5$) ethylene alpha-olefin copolymers containing 85-99 mol% ethylene, which are disclosed to be used for dispersing agents, modifiers or materials to produce toners. The copolymers (having crystallinity of from 5-85%) are prepared in the presence of a catalyst system comprising Zr compounds having at least one cycloalkadienyl group and alumoxane.

European Patent 128,046 discloses (co)polyolefin reactor blends of polyethylene and ethylene higher alpha-olefin copolymers prepared by employing described dual-metallocene/alumoxane catalyst systems.

European Patent Publication 129,368 discloses metallocene/alumoxane catalysts useful for the preparation of ethylene homopolymer and ethylene higher alpha-olefin copolymers.

European Patent Application Publication 257,696 A1 relates to a process for dimerizing alpha-olefins using a catalyst comprising certain metallocene/alumoxane systems.

PCT Published Patent Application WO 88/01626 relates to transition metal compound/alumoxane catalysts for polymerizing alpha-olefins.

SUMMARY OF THE INVENTION

The present invention is directed to oleaginous compositions, including lubricating oil, fuel oil, fuel, and the like, containing oil-soluble lubricating oil additives comprising ethylene alpha-olefin interpolymers of from greater than 20,000 to about 500,000 number average molecular weight, wherein the ethylene alpha-olefin polymer is a terminally unsaturated ethylene alpha-olefin polymer wherein the terminal unsaturation comprises ethenylidene unsaturation.

These ethylene alpha-olefin polymers function as viscosity index improvers and provide oleaginous compositions, particularly lubricating oil compositions, exhibiting improved viscosity index compared to oleaginous compositions which do not contain these ethylene alpha-olefin polymers.

DETAILED DESCRIPTION OF THE INVENTION

PREPARATION OF ETHYLENE ALPHA-OLEFIN POLYMER

The polymers employed in this invention are polymers of ethylene and at least one alpha-olefin having the formula $H_2C=CHR^1$ wherein R^1 is straight chain or branched chain alkyl radical comprising 1 to 18 carbon atoms and wherein the polymer contains a high degree of terminal ethenylidene unsaturation. Preferably R^1 in the above formula is alkyl of from 1 to 8 carbon atoms, and more preferably is alkyl of from 1 to 2 carbon atoms. Therefore, useful comonomers with ethylene in this invention include propylene, 1-butene, hexene-1, octene-1, 4-methylpentene-1, decene-1, dodecene-1, tridecene-1, tetradecene-1, pentadecene-1, hexadecene-1, heptadecene-1, octadecene-1, nonadecene-1 and mixtures thereof (e.g., mixtures of propylene and 1-butene, and the like).

Exemplary of such polymers are ethylene-propylene copolymers, ethylene-butene-1 copolymers and the like. Preferred polymers are copolymers of ethylene and propylene and ethylene and butene-1.

The molar ethylene content of the polymers employed in this invention is preferably in the range of between about 20 and about 80 percent, and more preferably between about 30 and about 70 percent. When propylene and/or butene-1 are employed as comonomer(s) with ethylene, the ethylene content of such copolymers is most preferably between about 45 and about 65 percent, although higher or lower ethylene contents may be present.

The polymers employed in this invention generally possess a number average molecular weight of at least greater than 20,000, preferably at least about 25,000, more preferably at least about 30,000, and most preferably at least about 35,000. Generally, the polymers should not exceed a number average molecular weight of about 500,000, preferably about 200,000, more preferably about 100,000, and most preferably about 50,000. The number average molecular weight for such polymers can be determined by several known techniques. A convenient method for such determination is by size exclusion chromatography (also known as gel permeation chromatography (GPC)) which additionally provides molecular weight distribution information, see W. W. Yau, J.J. Kirkland and D.D. Bly, "Modern Size Exclusion Liquid Chromatography", John Wiley and Sons, New York, 1979.

The polymers employed in this invention are further characterized in that up to about 95% and more of the polymer chains possess terminal ethenylidene-type unsaturation. Thus, one end of such polymers will be of the formula $\text{POLY-C(T}^1\text{)=CH}_2$ wherein T^1 is C_1 to C_{18} alkyl, preferably C_1 to C_8 alkyl, and more preferably C_1 to C_2

- 5 -

alkyl, (e.g., methyl or ethyl) and wherein POLY represents the polymer chain. The chain length of the T¹ alkyl group will vary depending on the comonomer(s) selected for use in the polymerization. A minor amount of the polymer chains can contain terminal ethenyl unsaturation, i.e. POLY-CH=CH₂, and a portion of the polymers can contain internal monounsaturations, e.g. POLY-CH=CH(T¹), wherein T¹ is as defined above.

The polymer employed in this invention comprises polymer chains, at least about 30 percent of which possess terminal ethenylidene unsaturation. Preferably at least about 50 percent, more preferably at least about 60 percent, and most preferably at least about 75 percent (e.g. 75-98%), of such polymer chains exhibit terminal ethenylidene unsaturation. The percentage of polymer chains exhibiting terminal ethenylidene unsaturation may be determined by FTIR spectroscopic analysis, titration, or C¹³NMR.

The polymer and the composition employed in this invention may be prepared as described in U.S. Patent Nos. 4,752,597, and 4,871,705, in European Patent Publications 128,046 and 129,368, and in U.S. Patent No. 5,324,800 and U.S. Patent No. 5,084,534.


The polymers for use in the present invention can be prepared by polymerizing monomer mixtures comprising ethylene in combination with other monomers such as alpha-olefins having from 3 to 20 carbon atoms (and preferably from 3-4 carbon atoms, i.e., propylene, butene-1, and mixtures thereof) in the presence of a catalyst system comprising at least one metallocene (e.g., a cyclopentadienyl-transition metal compound) and an alumoxane compound. The comonomer content can be controlled through

the selection of the metallocene catalyst component and by controlling the partial pressure of the various monomers.

The catalysts employed in the production of the reactant polymers are organometallic coordination compounds which are cyclopentadienyl derivatives of a Group 4b metal of the Periodic Table of the Elements (56th Edition of Handbook of Chemistry and Physics, CRC Press [1975]) and include mono, di and tricyclopentadienyls and their derivatives of the transition metals. Particularly desirable are the metallocene of a Group 4b metal such as titanium, zirconium, and hafnium. The alumoxanes employed in forming the reaction product with the metallocenes are themselves the reaction products of an aluminum trialkyl with water.

In general, at least one metallocene compound is employed in the formation of the catalyst. As indicated, supra, metallocene is a metal derivative of a cyclopentadiene. The metallocenes usefully employed in accordance with this invention contain at least one cyclopentadiene ring. The metal is selected from the Group 4b preferably titanium, zirconium, and hafnium, and most preferably hafnium and zirconium. The cyclopentadienyl ring can be unsubstituted or contain one or more substituents (e.g., from 1 to 5 substituents) such as, for example, a hydrocarbyl substituent (e.g., up to 5 C₁ to C₅ hydrocarbyl substituents) or other substituents, e.g. such as, for example, a trialkyl silyl substituent. The metallocene can contain one, two, or three cyclopentadienyl rings; however, two rings are preferred.

Useful metallocenes can be represented by the general formulas:



wherein Cp is a cyclopentadienyl ring, M is a Group 4b transition metal, R is a hydrocarbyl group or hydrocarboxy group having from 1 to 20 carbon atoms, X is a halogen, and m is a whole number from 1 to 3, n is a whole number from 0 to 3, and q is a whole number from 0 to 3.



wherein $(\text{C}_5\text{R}'_k)$ is a cyclopentadienyl or substituted cyclopentadienyl, each R' is the same or different and is hydrogen or a hydrocarbyl radical such as alkyl, alkenyl, aryl, alkylaryl, or arylalkyl radical containing from 1 to 20 carbon atoms, a silicon containing hydrocarbyl radical, or hydrocarbyl radicals wherein two carbon atoms are joined together to form a C_4 - C_6 ring, R'' is a C_1 - C_4 alkylene radical, a dialkyl germanium or silicon, or a alkyl phosphine or amine radical bridging two $(\text{C}_5\text{R}'_k)$ rings, Q is a hydrocarbyl radical such as aryl, alkyl, alkenyl, alkylaryl, or aryl alkyl radical having from 1-20 carbon atoms, hydrocarboxy radical having from 1-20 carbon atoms or halogen and can be the same or different from each other, Q' is an alkylidene radical having from 1 to about 20 carbon atoms, s is 0 or 1, g is 0, 1 or 2, s is 0 when g is 0, k is 4 when s is 1, and k is 5 when s is 0, and M is as defined above. Exemplary hydrocarbyl radicals are methyl, ethyl, propyl, butyl, amyl, isoamyl, hexyl, isobutyl, heptyl, octyl, nonyl, decyl, cetyl, 2-ethylhexyl, phenyl and the like. Exemplary silicon containing hydrocarbyl radicals are trimethylsilyl, triethylsilyl and triphenylsilyl. Exemplary halogen atoms include chlorine, bromine, fluorine and iodine and of these halogen atoms, chlorine is preferred. Exemplary hydrocarboxy radicals are methoxy, ethoxy, butoxy, amyloxy and the like. Exemplary of the

alkylidene radicals is methylenidene, ethylenidene and propylenidene.

Illustrative, but non-limiting examples of the metallocenes represented by formula I are dialkyl metallocenes such as bis(cyclopentadienyl)titanium dimethyl, bis(cyclopentadienyl)titanium diphenyl, bis(cyclopentadienyl)zirconium dimethyl, bis(cyclopentadienyl)zirconium diphenyl, bis(cyclopentadienyl)hafnium dimethyl and diphenyl, bis(cyclopentadienyl)titanium di-neopentyl, bis(cyclopentadienyl)zirconium di-neopentyl, bis(cyclopentadienyl)titanium dibenzyl, bis(cyclopentadienyl)zirconium dibenzyl, bis(cyclopentadienyl)vanadium dimethyl; the mono alkyl metallocenes such as bis(cyclopentadienyl)titanium methyl chloride, bis(cyclopentadienyl) titanium ethyl chloride bis(cyclopentadienyl)titanium phenyl chloride, bis(cyclopentadienyl)zirconium hydrochloride, bis(cyclopentadienyl)zirconium methyl chloride, bis(cyclopentadienyl)zirconium ethyl chloride, bis(cyclopentadienyl)zirconium phenyl chloride, bis(cyclopentadienyl)titanium methyl bromide, bis(cyclopentadienyl)titanium methyl iodide, bis(cyclopentadienyl)titanium ethyl bromide, bis(cyclopentadienyl) titanium ethyl iodide, bis(cyclopentadienyl)titanium phenyl bromide, bis(cyclopentadienyl)titanium phenyl iodide, bis(cyclopentadienyl)zirconium methyl bromide, bis(cyclopentadienyl)zirconium methyl iodide, bis(cyclopentadienyl)zirconium ethyl bromide, bis(cyclopentadienyl)zirconium ethyl iodide, bis(cyclopentadienyl)zirconium phenyl bromide, bis(cyclopentadienyl)zirconium phenyl iodide; the trialkyl metallocenes such as cyclopentadienyltitanium trimethyl, cyclopentadienyl zirconium triphenyl, and cyclopentadienyl

zirconium trineopentyl, cyclopentadienylzirconium trimethyl, cyclopentadienylhafnium triphenyl, cyclopentadienylhafnium trineopentyl, and cyclopentadienylhafnium trimethyl.

Illustrative, but non-limiting examples of II and III metallocenes which can be usefully employed are monocyclopentadienyls titanocenes such as, pentamethylcyclopentadienyl titanium trichloride, pentaethylcyclopentadienyl titanium trichloride, bis(pentamethylcyclopentadienyl) titanium diphenyl, the carbene represented by the formula $\text{bis}(\text{cyclopentadienyl})\text{titanium}=\text{CH}_2$ and derivatives of this reagent such as $\text{bis}(\text{cyclopentadienyl})\text{Ti}=\text{CH}_2\cdot\text{Al}(\text{CH}_3)_3$, $(\text{Cp}_2\text{TiCH}_2)_2$, $\text{Cp}_2\text{TiCH}_2\text{CH}(\text{CH}_3)\text{CH}_2$, $\text{Cp}_2\text{Ti}-\text{CH}_2\text{CH}_2\text{CH}_2$; substituted bis(Cp)Ti(IV) compounds such as bis(indenyl) titanium diphenyl or dichloride, bis(methylcyclopentadienyl)titanium diphenyl or dihalides; dialkyl, trialkyl, tetra-alkyl and penta-alkyl cyclopentadienyl titanium compounds such as bis(1,2-dimethylcyclopentadienyl)titanium diphenyl or dichloride, bis(1,2-diethylcyclopentadienyl)titanium diphenyl or dichloride and other dihalide complexes; silicon, phosphine, amine or carbon bridged cyclopentadiene complexes, such as dimethylsilyldicyclopentadienyl titanium diphenyl or dichloride, methyl phosphine dicyclopentadienyl titanium diphenyl or dichloride, methylenedicyclopentadienyl titanium diphenyl or dichloride and other complexes described by formulae II and III.

Illustrative but non-limiting examples of the zirconocenes of Formula II and III which can be usefully employed are, pentamethylcyclopentadienyl zirconium trichloride, pentaethylcyclopentadienyl zirconium trichloride, the alkyl substituted cyclopentadienes, such as bis(ethylcyclopentadienyl)zirconium dimethyl, bis(beta-phenylpropylcyclopentadienyl) zirconium dimethyl,

bis(methylcyclopentadienyl)zirconium dimethyl, bis(n-butylcyclopentadienyl)zirconium dimethyl
 bis(cyclohexylmethylcyclopentadienyl)zirconium dimethyl
 bis(n-octyl-cyclopentadienyl)zirconium dimethyl, and haloalkyl and dihydride, and dihalide complexes of the above; dialkyl, trialkyl, tetra-alkyl, and penta-alkyl cyclopentadienes, such as bis(pentamethylcyclopentadienyl)zirconium diphenyl, bis(pentamethylcyclopentadienyl)zirconium dimethyl, bis(1,2-dimethylcyclopentadienyl)zirconium dimethyl and mono and dihalide and hydride complexes of the above; silicon, phosphorus, and carbon bridged cyclopentadiene complexes such as dimethylsilyl-dicyclopentadienyl zirconium dimethyl, methyl halide or dihalide, and methylene dicyclopentadienyl zirconium dimethyl, methyl halide, or dihalide. Mono, di and tri-silyl substituted cyclopentadienyl compounds such as bis(trimethylsilylcyclopentadienyl)zirconium dichloride and dimethyl bis(1,3-di-trimethylsilylcyclopentadienyl)zirconium dichloride and dimethyl and bis(1,2,4-tri-trimethylsilylcyclopentadienyl)zirconium dichloride and dimethyl. Carbenes represented by the formulae $\text{Cp}_2\text{Zr}=\text{CH}_2\text{P}(\text{C}_6\text{H}_5)_2\text{CH}_3$, and derivatives of these compounds such as $\text{Cp}_2\text{ZrCH}_2\text{CH}(\text{CH}_3)\text{CH}_2$.

Mixed cyclopentadienyl metallocene compounds such as cyclopentadienyl (pentamethyl cyclopentadienyl)zirconium dichloride, (1,3-di-trimethylsilylcyclopentadienyl) (pentamethylcyclopentadienyl) zirconium dichloride, and cyclopentadienyl(indenyl) zirconium dichloride can be employed.

Most preferably, the polymers used in this invention are substantially free of ethylene homopolymer.

Bis(cyclopentadienyl)hafnium dichloride,
 bis(cyclopentadienyl)hafnium; dimethyl, bis(cyclo-

pentadienyl)vanadium dichloride and the like are illustrative of other metallocenes.

Some preferred metallocenes are bis(cyclopentadienyl)zirconium; dimethyl, bis(cyclopentadienyl)zirconium dichloride; bis(cyclopentadienyl)titanium dichloride; bis(methylcyclopentadienyl) zirconium dichloride; bis(methylcyclopentadienyl)titanium dichloride; bis(n-butylcyclopentadienyl)zirconium dichloride; dimethylsilyldicyclopentadienyl zirconium dichloride; bis(trimethylsilylcyclopentadienyl)zirconium dichloride; and dimethylsilyldicyclopentadienyl titanium dichloride; bis(indenyl)zirconium dichloride; bis(4,5,6,7-tetrahydroindenyl)zirconium dichloride; the racemic and/or meso isomer of 1,2-ethylene-bridged bis(4,5,6,7-tetrahydroindenyl)zirconium dichloride; the racemic and/or meso isomer of 1,1-dimethylsilyl-bridged bis(4,5,6,7-tetrahydroindenyl)zirconium dichloride; and the racemic and/or meso isomer of 1,1-dimethylsilyl-bridged bis(methylcyclopentadienyl)zirconium dichloride.

The alumoxane compounds useful in the polymerization process may be cyclic or linear. Cyclic alumoxanes may be represented by the general formula $(R-Al-O)_n$ while linear alumoxanes may be represented by the general formula $R(R-Al-O)_n'AlR_2$. In the general formula R is a C_1-C_5 alkyl group such as, for example, methyl, ethyl, propyl, butyl and pentyl, n is an integer of from 3 to 20, and n' is an integer from 1 to about 20. Preferably, R is methyl and n and n' are 4-18. Generally, in the preparation of alumoxanes from, for example, aluminum trimethyl and water, a mixture of the linear and cyclic compounds is obtained.

The alumoxane can be prepared in various ways. Preferably, they are prepared by contacting water with a solution of aluminum trialkyl, such as, for examples,

aluminum trimethyl, in a suitable organic solvent such as toluene or an aliphatic hydrocarbon. For example, the aluminum alkyl is treated with water in the form of a moist solvent. In an alternative method, the aluminum alkyl such as aluminum trimethyl can be desirably contacted with a hydrated salt such as hydrated copper sulfate or ferrous sulfate. Preferably, the alumoxane is prepared in the presence of a hydrated ferrous sulfate. The method comprises treating a dilute solution of aluminum trimethyl in, for example, toluene, with ferrous sulfate represented by the general formula $\text{FeSO}_4 \cdot 7\text{H}_2\text{O}$. The ratio of ferrous sulfate to aluminum trimethyl is desirably about 1 mole of ferrous sulfate for 6 to 7 moles of aluminum trimethyl. The reaction is evidenced by the evolution of methane.

The mole ratio of aluminum in the alumoxane to total metal in the metallocenes which can be usefully employed can be in the range of about 0.5:1 to about 1000:1, and desirably about 1:1 to about 100:1. Preferably, the mole ratio will be in the range of 50:1 to about 5:1 and most preferably 20:1 to 5:1.

The solvents used in the preparation of the catalyst system are inert hydrocarbons, in particular a hydrocarbon that is inert with respect to the catalyst system. Such solvents are well known and include, for example, isobutane, butane, pentane, hexane, heptane, octane, cyclohexane, methylcyclohexane, toluene, xylene and the like.

Polymerization is generally conducted at temperatures ranging between about 20° and about 300°C, preferably between about 30° and about 200°C. Reaction time is not critical and may vary from several hours or more to several minutes or less, depending upon factors such as reaction temperature, the monomers to be copolymerized, and

the like. One of ordinary skill in the art may readily obtain the optimum reaction time for a given set of reaction parameters by routine experimentation.

The catalyst systems described herein are suitable for the polymerization of olefins in solution over a wide range of pressures. Preferably, the polymerization will be completed at a pressure of from about 10 to about 3,000 bar, and generally at a pressure within the range from about 40 bar to about 2,000 bar, and most preferably, the polymerization will be completed at a pressure within the range from about 50 bar to about 1,500 bar.

After polymerization and, optionally, deactivation of the catalyst (e.g., by conventional techniques such as contacting the polymerization reaction medium with water or an alcohol, such as methanol, propanol, isopropanol, etc., or cooling or flashing the medium to terminate the polymerization reaction), the product polymer can be recovered by processes well known in the art. Any excess reactants may be flashed off from the polymer.

The polymerization may be conducted employing liquid monomer, such as liquid propylene, or mixtures of liquid monomers (such as mixtures of liquid propylene and 1-butene), as the reaction medium. Alternatively, polymerization may be accomplished in the presence of a hydrocarbon inert to the polymerization such as butane, pentane, isopentane, hexane, isooctane, decane, toluene, xylene, and the like.

In those situations wherein the molecular weight of the polymer product that would be produced at a given set of operating conditions is higher than desired, any of the techniques known in the prior art for control of molecular weight.

When carrying out the polymerization in a batch-type fashion, the reaction diluent (if any), ethylene and alpha-olefin comonomer(s) are charged at appropriate ratios to a suitable reactor. Care must be taken that all ingredients are dry, with the reactants typically being passed through molecular sieves or other drying means prior to their introduction into the reactor. Subsequently, either the catalyst and then the cocatalyst, or first the cocatalyst and then the catalyst are introduced while agitating the reaction mixture, thereby causing polymerization to commence. Alternatively, the catalyst and cocatalyst may be premixed in a solvent and then charged to the reactor. As polymer is being formed, additional monomers may be added to the reactor. Upon completion of the reaction, unreacted monomer and solvent are either flashed or distilled off, if necessary by vacuum, and the low molecular weight copolymer withdrawn from the reactor.

The polymerization may be conducted in a continuous manner by simultaneously feeding the reaction diluent (if employed), monomers, catalyst and cocatalyst to a reactor and withdrawing solvent, unreacted monomer and polymer from the reactor so as to allow a residence time of ingredients long enough for forming polymer of the desired molecular weight and separating the polymer from the reaction mixture.

The viscosity index improver or modifier additives of the present invention can be incorporated into an oleaginous composition, particularly a lubricating oil, in any convenient way. Thus, these additives can be added directly to the oil by dispersing or dissolving the same in the oil at the desired level of concentrations of the additive. Such blending into the additional lube oil can occur at room temperature or elevated temperatures. Alternatively, the additives can be blended with a suitable oil-soluble solvent and base oil to form a concentrate, and

then blending the concentrate with a lubricating oil basestock to obtain the final formulation.

The lubricating oil basestock for the viscosity index improver additive typically is adapted to perform a selected function by the incorporation of additional additives therein to form lubricating oil compositions (i.e., formulations). Such concentrates will typically contain (on an active ingredient (A.I.) basis) from about 5 to about 60 wt.%, preferably from about 10 to about 60, and more preferably from about 20 to about 50 wt.%, of the viscosity index improver additive of the instant invention, and typically from about 40 to 95 wt.%, preferably from about 40 to about 90 wt.%, and more preferably from about 50 to 80 wt.% base oil, based on the concentrate weight.

LUBRICATING COMPOSITIONS

The viscosity index improver additives of the present invention possess very good viscosity index improving properties as measured herein in a wide variety of environments. Accordingly, the additive mixtures are used by incorporation and dissolution into an oleaginous material such as lubricating oils.

The viscosity index improver additives of the present invention find their primary utility in lubricating oil compositions which employ a base oil in which the additives are dissolved or dispersed. Such base oils may be natural or synthetic. Base oils suitable for use in preparing the lubricating oil compositions of the present invention include those conventionally employed as crankcase lubricating oils for spark-ignited and compression-ignited internal combustion engines, such as automobile and truck engines, marine and railroad diesel engines, and the like. Advantageous results are also achieved by employing the additives of the present invention in base oils

- 16 -

conventionally employed in and/or adapted for use as power transmitting fluids, universal tractor fluids and hydraulic fluids, heavy duty hydraulic fluids, power steering fluids and the like. Gear lubricants, industrial oils, pump oils and other lubricating oil compositions can also benefit from the incorporation therein of the additives of the present invention.

These lubricating oil formulations conventionally contain several different types of additives that will supply the characteristics that are required in the formulations. Among these types of additives may be included viscosity index improvers other than those of the instant invention, antioxidants, corrosion inhibitors, detergents, dispersants, pour point depressants, antiwear agents, friction modifiers, and ashless dispersants (e.g., polyisobutenyl succinimides) and borated derivatives thereof), etc.

In the preparation of lubricating oil formulations it is common practice to introduce the additives in the form of 10 to 80 wt. %, e.g., 20 to 80 wt. % active ingredient concentrates in hydrocarbon oil, e.g. mineral lubricating oil, or other suitable solvent. Usually these concentrates may be diluted with 3 to 100, e.g., 5 to 40 parts by weight of lubricating oil, per part by weight of the additive package, in forming finished lubricants, e.g. crankcase motor oils. The purpose of concentrates, of course, is to make the handling of the various materials less difficult and awkward as well as to facilitate solution or dispersion in the final blend. Thus, a viscosity index improver would be usually employed in the form of a 40 to 50 wt. % concentrate, for example, in a lubricating oil fraction.

The viscosity index improver of the present invention will be generally used in admixture with a lube

oil basestock, comprising an oil of lubricating viscosity, including natural and synthetic lubricating oils and mixtures thereof.

Natural oils include animal oils and vegetable oils (e.g., castor, lard oil) liquid petroleum oils and hydrotreated, solvent-treated or acid-treated mineral lubricating oils of the paraffinic, naphthenic and mixed paraffinic-naphthenic types. Oils of lubricating viscosity derived from coal or shale are also useful base oils.

Alkylene oxide polymers and interpolymers and derivatives thereof where the terminal hydroxyl groups have been modified by esterification, etherification, etc., constitute another class of known synthetic lubricating oils. These are exemplified by polyoxyalkylene polymers prepared by polymerization of ethylene oxide or propylene oxide, the alkyl and aryl ethers of these polyoxyalkylene polymers (e.g., methyl-poly isopropylene glycol ether having an average molecular weight of 1000, diphenyl ether of polyethylene glycol having a molecular weight of 500-1000, diethyl ether of polypropylene glycol having a molecular weight of 1000-1500); and mono- and polycarboxylic esters thereof, for example, the acetic acid esters, mixed C_3 - C_8 fatty acid esters and C_{13} Oxo acid diester of tetraethylene glycol.

Another suitable class of synthetic lubricating oils comprises the esters of dicarboxylic acids (e.g., phthalic acid, succinic acid, alkyl succinic acids and alkenyl succinic acids, maleic acid, azelaic acid, suberic acid, sebacic acid, fumaric acid, adipic acid, linoleic acid dimer, malonic acid, alkylmalonic acids, alkenyl malonic acids) with a variety of alcohols (e.g., butyl alcohol, hexyl alcohol, dodecyl alcohol, 2-ethylhexyl alcohol, ethylene glycol, diethylene glycol monoether, propylene

glycol). Specific examples of these esters include dibutyl adipate, di(2-ethylhexyl)sebacate, di-n-hexyl fumarate, dioctyl sebacate, diisooctyl azelate, diisodecyl azelate, dioctyl phthalate, didecyl phthalate, dieicosyl sebacate, the 2-ethylhexyl diester of linoleic acid dimer, and the complex ester formed by reacting one mole of sebacic acid with two moles of tetraethylene glycol and two moles of 2-ethylhexanoic acid.

Esters useful as synthetic oils also include those made from C_5 to C_{12} monocarboxylic acids and polyols and polyol ethers such as neopentyl glycol, trimethylolpropane, pentaerythritol, dipentaerythritol and tripentaerythritol.

Silicon-based oils such as the polyalkyl-, polyaryl-, polyalkoxy-, or polyaryloxysiloxane oils and silicate oils comprise another useful class of synthetic lubricants; they include tetraethyl silicate, tetraisopropyl silicate, tetra-(2-ethylhexyl)silicate, tetra-(4-methyl-2-ethylhexyl)silicate, tetra-(p-tertbutylphenyl)silicate, hexa-(4-methyl-2-pentoxo)disiloxane, poly(methyl)siloxanes and poly(methylphenyl)siloxanes. Other synthetic lubricating oils include liquid esters of phosphorus-containing acids (e.g., tricresyl phosphate, trioctyl phosphate, diethyl ester of decylphosphonic acid) and polymeric tetrahydrofurans.

Unrefined, refined and rerefined oils can be used in the lubricants of the present invention. Unrefined oils are those obtained directly from a natural or synthetic source without further purification treatment. For example, a shale oil obtained directly from retorting operations, a petroleum oil obtained directly from distillation or ester oil obtained directly from an esterification process and used without further treatment would be an unrefined oil. Refined oils are similar to the unrefined oils except they

have been further treated in one or more purification steps to improve one or more properties. Many such purification techniques, such as distillation, solvent extraction, acid or base extraction, filtration and percolation are known to those skilled in the art. Rerefined oils are obtained by processes similar to those used to obtain refined oils applied to refined oils which have been already used in service. Such rerefined oils are also known as reclaimed or reprocessed oils and often are additionally processed by techniques for removal of spent additives and oil breakdown products.

Metal containing rust inhibitors and/or detergents are frequently used with viscosity index modifiers. Such detergents and rust inhibitors include the metal salts of sulphonic acids, alkyl phenols, sulphurized alkyl phenols, alkyl salicylates, naphthenates, and other oil soluble mono- and di-carboxylic acids. Usually these metal containing rust inhibitors and detergents are used in lubricating oil in amounts of about 0.01 to 10, e.g. 0.1 to 5 wt. %, based on the weight of the total lubricating composition. Marine diesel lubricating oils typically employ such metal-containing rust inhibitors and detergents in amounts of up to about 20 wt.%.

Highly basic alkaline earth metal sulfonates are frequently used as detergents. They are usually produced by heating a mixture comprising an oil-soluble sulfonate or alkaryl sulfonic acid, with an excess of alkaline earth metal compound above that required for complete neutralization of any sulfonic acid present and thereafter forming a dispersed carbonate complex by reacting the excess metal with carbon dioxide to provide the desired overbasing. The sulfonic acids are typically obtained by the sulfonation of alkyl substituted aromatic hydrocarbons such as those obtained from the fractionation of petroleum by distillation

and/or extraction or by the alkylation of aromatic hydrocarbons as for example those obtained by alkylating benzene, toluene, xylene, naphthalene, diphenyl and the halogen derivatives such as chlorobenzene, chlorotoluene and chloronaphthalene. The alkylation may be carried out in the presence of a catalyst with alkylating agents having from about 3 to more than 30 carbon atoms. For example haloparaffins, olefins obtained by dehydrogenation of paraffins, polyolefins produced from ethylene, propylene, etc. are all suitable. The alkaryl sulfonates usually contain from about 9 to about 70 or more carbon atoms, preferably from about 16 to about 50 carbon atoms per alkyl substituted aromatic moiety.

The alkaline earth metal compounds which may be used in neutralizing these alkaryl sulfonic acids to provide the sulfonates includes the oxides and hydroxides, alkoxides, carbonates, carboxylate, sulfide, hydrosulfide, nitrate, borates and ethers of magnesium, calcium, and barium. Examples are calcium oxide, calcium hydroxide, magnesium acetate and magnesium borate. As noted, the alkaline earth metal compound is used in excess of that required to complete neutralization of the alkaryl sulfonic acids. Generally, the amount ranges from about 100 to 220%, although it is preferred to use at least 125%, of the stoichiometric amount of metal required for complete neutralization.

Various other preparations of basic alkaline earth metal alkaryl sulfonates are known, such as U.S. Patents 3,150,088 and 3,150,089 wherein overbasing is accomplished by hydrolysis of an alkoxide-carbonate complex with the alkaryl sulfonate in a hydrocarbon solvent-diluent oil.

A preferred alkaline earth sulfonate additive is magnesium alkyl aromatic sulfonate having a total base

number ranging from about 300 to about 400 with the magnesium sulfonate content ranging from about 25 to about 32 wt. %, based upon the total weight of the additive system dispersed in mineral lubricating oil.


Neutral metal sulfonates are frequently used as rust inhibitors. Polyvalent metal alkyl salicylate and naphthenate materials are known additives for lubricating oil compositions to improve their high temperature performance and to counteract deposition of carbonaceous matter on pistons (U.S. Patent 2,744,069). An increase in reserve basicity of the polyvalent metal alkyl salicylates and naphthenates can be realized by utilizing alkaline earth metal, e.g. calcium, salts of mixtures of C_8 - C_{26} alkyl salicylates and phenates (see U.S. Patent 2,744,069) or polyvalent metal salts of alkyl salicyclic acids, said acids obtained from the alkylation of phenols followed by phenation, carboxylation and hydrolysis (U.S. Patent 3,704,315) which could then be converted into highly basic salts by techniques generally known and used for such conversion. The reserve basicity of these metal-containing rust inhibitors is usefully at TBN levels of between about 60 and 150. Included with the useful polyvalent metal salicylate and naphthenate materials are the methylene and sulfur bridged materials which are readily derived from alkyl substituted salicylic or naphthenic acids or mixtures of either or both with alkyl substituted phenols. Basic sulfurized salicylates and a method for their preparation is shown in U.S. Patent 3,595,791. Such materials include alkaline earth metal, particularly magnesium, calcium, strontium and barium salts of aromatic acids having the general formula:



(XX)


where Ar is an aryl radical of 1 to 6 rings, R_1 is an alkyl group having from about 8 to 50 carbon atoms, preferably 12 to 30 carbon atoms (optimally about 12), X is a sulfur (-S-) or methylene (-CH₂-) bridge, y is a number from 0 to 4 and n is a number from 0 to 4.

Preparation of the overbased methylene bridged salicylate-phenate salt is readily carried out by conventional techniques such as by alkylation of a phenol followed by phenation, carboxylation, hydrolysis, methylene bridging a coupling agent such as an alkylene dihalide followed by salt formation concurrent with carbonation. An overbased calcium salt of a methylene bridged phenol-salicylic acid of the general formula (XXI):



with a TBN of 60 to 150 is highly useful in this invention.

The sulfurized metal phenates can be considered the "metal salt of a phenol sulfide" which thus refers to a metal salt whether neutral or basic, of a compound typified by the general formula (XXII):



where $x = 1$ or 2 , $n = 0, 1$ or 2 ; or a polymeric form of such a compound, where R is an alkyl radical, n and x are each integers from 1 to 4, and the average number of carbon atoms in all of the R groups is at least about 9 in order to ensure adequate solubility in oil. The individual R groups may each contain from 5 to 40, preferably 8 to 20, carbon

atoms. The metal salt is prepared by reacting an alkyl phenol sulfide with a sufficient quantity of metal containing material to impart the desired alkalinity to the sulfurized metal phenate.

Regardless of the manner in which they are prepared, the sulfurized alkyl phenols which are useful generally contain from about 2 to about 14% by weight, preferably about 4 to about 12 wt. % sulfur based on the weight of sulfurized alkyl phenol.

The sulfurized alkyl phenol may be converted by reaction with a metal containing material including oxides, hydroxides and complexes in an amount sufficient to neutralize said phenol and, if desired, to overbase the product to a desired alkalinity by procedures well known in the art. Preferred is a process of neutralization utilizing a solution of metal in a glycol ether.

The neutral or normal sulfurized metal phenates are those in which the ratio of metal to phenol nucleus is about 1:2. The "overbased" or "basic" sulfurized metal phenates are sulfurized metal phenates wherein the ratio of metal to phenol is greater than that of stoichiometric, e.g. basic sulfurized metal dodecyl phenate has a metal content up to and greater than 100% in excess of the metal present in the corresponding normal sulfurized metal phenates wherein the excess metal is produced in oil-soluble or dispersible form (as by reaction with CO_2). The overbased sulfurized metal phenates desirably have a TBN value of at least 150, e.g. from 200 to 300.

Magnesium and calcium containing additives although beneficial in other respects can increase the tendency of the lubricating oil to oxidize. This is especially true of the highly basic sulphonates.

According to a preferred embodiment the invention therefore provides a crankcase lubricating composition also containing from 2 to 8000 parts per million of calcium or magnesium.

The magnesium and/or calcium is generally present as basic or neutral detergents such as the sulphonates and phenates, our preferred additives are the neutral or basic magnesium or calcium sulphonates. Preferably the oils contain from 500 to 5000 parts per million of calcium or magnesium. Basic magnesium and calcium sulphonates are preferred.

The viscosity index improvers of the instant invention may be used in conjunction with other conventional well-known V.I improvers. Viscosity modifiers impart high and low temperature operability to the lubricating oil and permit it to remain relatively viscous at elevated temperatures and also exhibit acceptable viscosity or fluidity at low temperatures. Viscosity modifiers are generally high molecular weight hydrocarbon polymers including polyesters. The viscosity modifiers may also be derivatized to include other properties or functions, such as the addition of dispersancy properties. These oil soluble viscosity modifying polymers will generally have number average molecular weights of from 10^3 to 10^6 , preferably 10^4 to 10^6 , e.g., 20,000 to 250,000, as determined by gel permeation chromatography or osmometry.

Examples of suitable hydrocarbon polymers include homopolymers and copolymers of two or more monomers of C_2 to C_{30} , e.g. C_2 to C_8 olefins, including both alpha olefins and internal olefins, which may be straight or branched, aliphatic, aromatic, alkyl-aromatic, cycloaliphatic, etc. Frequently they will be of ethylene with C_3 to C_{30} olefins, particularly preferred being the copolymers of ethylene and

propylene. Other polymers can be used such as polyisobutylenes, homopolymers and copolymers of C_6 and higher alpha olefins, atactic polypropylene, hydrogenated polymers and copolymers and terpolymers of styrene, e.g. with isoprene and/or butadiene and hydrogenated derivatives thereof. The polymer may be degraded in molecular weight, for example by mastication, extrusion, oxidation or thermal degradation, and it may be oxidized and contain oxygen. Also included are derivatized polymers such as post-grafted interpolymers of ethylene-propylene with an active monomer such as maleic anhydride which may be further reacted with an alcohol, or amine, e.g. an alkylene polyamine or hydroxy amine, e.g. see U.S. Patent Nos. 4,089,794; 4,160,739; 4,137,185; or copolymers of ethylene and propylene reacted or grafted with nitrogen compounds such as shown in U.S. Patent Nos. 4,068,056; 4,068,058; 4,146,489 and 4,149,984.

The preferred hydrocarbon polymers are ethylene copolymers containing from 15 to 90 wt. % ethylene, preferably 30 to 80 wt. % of ethylene and 10 to 85 wt. %, preferably 20 to 70 wt. % of one or more C_3 to C_{28} , preferably C_3 to C_{18} , more preferably C_3 to C_8 , alpha-olefins. While not essential, such copolymers preferably have a degree of crystallinity of less than 25 wt. %, as determined by X-ray and differential scanning calorimetry. Copolymers of ethylene and propylene are most preferred. Other alpha-olefins suitable in place of propylene to form the copolymer, or to be used in combination with ethylene and propylene, to form a terpolymer, tetrapolymer, etc., include 1-butene, 1-pentene, 1-hexene, 1-heptene, 1-octene, 1-nonene, 1-decene, etc.; also branched chain alpha-olefins, such as 4-methyl-1-pentene, 4-methyl-1-hexene, 5-methylpentene-1, 4,4-dimethyl-1-pentene, and 6-methylheptene-1, etc., and mixtures thereof.

Terpolymers, tetrapolymers, etc., of ethylene, said C₃-28 alpha-olefin, and a non-conjugated diolefin or mixtures of such diolefins may also be used. The amount of the non-conjugated diolefin generally ranges from about 0.5 to 20 mole percent, preferably from about 1 to about 7 mole percent, based on the total amount of ethylene and alpha-olefin present.

The polyester V.I. improvers are generally polymers of esters of ethylenically unsaturated C₃ to C₈ mono- and dicarboxylic acids such as methacrylic and acrylic acids, maleic acid, maleic anhydride, fumaric acid, etc.

Examples of unsaturated esters that may be used include those of aliphatic saturated mono alcohols of at least 1 carbon atom and preferably of from 12 to 20 carbon atoms, such as decyl acrylate, lauryl acrylate, stearyl acrylate, eicosanyl acrylate, docosanyl acrylate, decyl methacrylate, diamyl fumarate, lauryl methacrylate, cetyl methacrylate, stearyl methacrylate, and the like and mixtures thereof.

Other esters include the vinyl alcohol esters of C₂ to C₂₂ fatty or mono carboxylic acids, preferably saturated such as vinyl acetate, vinyl laurate, vinyl palmitate, vinyl stearate, vinyl oleate, and the like and mixtures thereof. Copolymers of vinyl alcohol esters with unsaturated acid esters such as the copolymer of vinyl acetate with dialkyl fumarates, can also be used.

The esters may be copolymerized with still other unsaturated monomers such as olefins, e.g. 0.2 to 5 moles of C₂ - C₂₀ aliphatic or aromatic olefin per mole of unsaturated ester, or per mole of unsaturated acid or anhydride followed by esterification. For example, copolymers of styrene with maleic anhydride esterified with

alcohols and amines are known, e.g., see U.S. Patent 3,702,300.

Such ester polymers may be grafted with, or the ester copolymerized with, polymerizable unsaturated nitrogen-containing monomers to impart dispersancy to the V.I. improvers. Examples of suitable unsaturated nitrogen-containing monomers include those containing 4 to 20 carbon atoms such as amino substituted olefins as p-(beta-diethylaminoethyl)styrene; basic nitrogen-containing heterocycles carrying a polymerizable ethylenically unsaturated substituent, e.g. the vinyl pyridines and the vinyl alkyl pyridines such as 2-vinyl-5-ethyl pyridine, 2-methyl-5-vinyl pyridine, 2-vinyl-pyridine, 4-vinylpyridine, 3-vinyl-pyridine, 3-methyl-5-vinyl-pyridine, 4-methyl-2-vinyl-pyridine, 4-ethyl-2-vinyl-pyridine and 2-butyl-1-5-vinyl-pyridine and the like.


N-vinyl lactams are also suitable, e.g. N-vinyl pyrrolidones or N-vinyl piperidones.

The vinyl pyrrolidones are preferred and are exemplified by N-vinyl pyrrolidone, N-(1-methylvinyl) pyrrolidone, N-vinyl-5-methyl pyrrolidone, N-vinyl-3, 3-dimethylpyrrolidone, N-vinyl-5-ethyl pyrrolidone, etc.

Dihydrocarbyl dithiophosphate metal salts are frequently used as anti-wear agents and also provide antioxidant activity. The zinc salts are most commonly used in lubricating oil in amounts of 0.1 to 10, preferably 0.2 to 2 wt. %, based upon the total weight of the lubricating oil composition. They may be prepared in accordance with known techniques by first forming a dithiophosphoric acid, usually by reaction of an alcohol or a phenol with P_2S_5 and then neutralizing the dithiophosphoric acid with a suitable zinc compound.

Mixtures of alcohols may be used including mixtures of primary and secondary alcohols, secondary generally for imparting improved anti-wear properties, with primary giving improved thermal stability properties. Mixtures of the two are particularly useful. In general, any basic or neutral zinc compound could be used but the oxides, hydroxides and carbonates are most generally employed. Commercial additives frequently contain an excess of zinc due to use of an excess of the basic zinc compound in the neutralization reaction.

The zinc dihydrocarbyl dithiophosphates useful in the present invention are oil soluble salts of dihydrocarbyl esters of dithiophosphoric acids and may be represented by the following formula:



wherein R and R' may be the same or different hydrocarbyl radicals containing from 1 to 18, preferably 2 to 12 carbon atoms and including radicals such as alkyl, alkenyl, aryl, aralkyl, alkaryl and cycloaliphatic radicals. Particularly preferred as R and R' groups are alkyl groups of 2 to 8 carbon atoms. Thus, the radicals may, for example, be ethyl, n-propyl, i-propyl, n-butyl, i-butyl, sec-butyl, amyl, n-hexyl, i-hexyl, n-octyl, decyl, dodecyl, octadecyl, 2-ethylhexyl, phenyl, butylphenyl, cyclohexyl, methylcyclopentyl, propenyl, butenyl etc. In order to obtain oil solubility, the total number of carbon atoms (i.e., R and R' in formula XXIII) in the dithiophosphoric acid will generally be about 5 or greater.

The antioxidants useful in this invention include oil soluble copper compounds. The copper may be blended into the oil as any suitable oil soluble copper compound.

By oil soluble we mean the compound is oil soluble under normal blending conditions in the oil or additive package. The copper compound may be in the cuprous or cupric form. The copper may be in the form of the copper dihydrocarbyl thio- or dithio-phosphates wherein copper may be substituted for zinc in the compounds and reactions described above although one mole of cuprous or cupric oxide may be reacted with one or two moles of the dithiophosphoric acid, respectively. Alternatively the copper may be added as the copper salt of a synthetic or natural carboxylic acid. Examples include C₁₀ to C₁₈ fatty acids such as stearic or palmitic, but unsaturated acids such as oleic or branched carboxylic acids such as naphthenic acids of molecular weight from 200 to 500 or synthetic carboxylic acids are preferred because of the improved handling and solubility properties of the resulting copper carboxylates. Also useful are oil soluble copper dithiocarbamates of the general formula (RR'NCSS)_nCu, where n is 1 or 2 and R and R' are the same or different hydrocarbyl radicals containing from 1 to 18 and preferably 2 to 12 carbon atoms and including radicals such as alkyl, alkenyl, aryl, aralkyl, alkaryl and cycloaliphatic radicals. Particularly preferred as R and R' groups are alkyl groups of 2 to 8 carbon atoms. Thus, the radicals may, for example, be ethyl, n-propyl, i-propyl, n-butyl, i-butyl, sec-butyl, amyl, n-hexyl, i-hexyl, n-heptyl, n-octyl, decyl, dodecyl, octadecyl, 2-ethylhexyl, phenyl, butylphenyl, cyclohexyl, methylcyclopentyl, propenyl, butenyl, etc. In order to obtain oil solubility, the total number of carbon atoms (i.e., R and R') will generally be about 5 or greater. Copper sulphonates, phenates, and acetylacetonates may also be used.

Exemplary of useful copper compounds are copper (Cu^I and/or Cu^{II}) salts of alkenyl succinic acids or anhydrides. The salts themselves may be basic, neutral or acidic. They may be formed by reacting (a) any of the

materials discussed above in the Ashless Dispersant section, which have at least one free carboxylic acid (or anhydride) group with (b) a reactive metal compound. Suitable acid (or anhydride) reactive metal compounds include those such as cupric or cuprous hydroxides, oxides, acetates, borates, and carbonates or basic copper carbonate.

Examples of the metal salts of this invention are Cu salts of polyisobutenyl succinic anhydride (hereinafter referred to as Cu-PIBSA), and Cu salts of polyisobutenyl succinic acid. Preferably, the selected metal employed is its divalent form, e.g., Cu^{+2} . The preferred substrates are polyalkenyl succinic acids in which the alkenyl group has a molecular weight greater than about 700. The alkenyl group desirably has a M_n from about 900 to 1400, and up to 2500, with a M_n of about 950 being most preferred. Especially preferred, of those listed above in the section on Dispersants, is polyisobutylene succinic acid (PIBSA). These materials may desirably be dissolved in a solvent, such as a mineral oil, and heated in the presence of a water solution (or slurry) of the metal bearing material. Heating may take place between 70° and about 200°C. Temperatures of 110° to 140°C are entirely adequate. It may be necessary, depending upon the salt produced, not to allow the reaction to remain at a temperature above about 140°C for an extended period of time, e.g., longer than 5 hours, or decomposition of the salt may occur.

The copper antioxidants (e.g., Cu-PIBSA, Cu-oleate, or mixtures thereof) will be generally employed in an amount of from about 50-500 ppm by weight of the metal, in the final lubricating composition.

The copper antioxidants used in this invention are inexpensive and are effective at low concentrations and therefore do not add substantially to the cost of the

product. The results obtained are frequently better than those obtained with previously used antioxidants, which are expensive and used in higher concentrations. In the amounts employed, the copper compounds do not interfere with the performance of other components of the lubricating composition, in many instances, completely satisfactory results are obtained when the copper compound is the sole antioxidant in addition to the ZDDP. The copper compounds can be utilized to replace part or all of the need for supplementary antioxidants. Thus, for particularly severe conditions it may be desirable to include a supplementary, conventional antioxidant. However, the amounts of supplementary antioxidant required are small, far less than the amount required in the absence of the copper compound.

While any effective amount of the copper antioxidant can be incorporated into the lubricating oil composition, it is contemplated that such effective amounts be sufficient to provide said lube oil composition with an amount of the copper antioxidant of from about 5 to 500 (more preferably 10 to 200, still more preferably 10 to 180, and most preferably 20 to 130 (e.g., 90 to 120)) part per million of added copper based on the weight of the lubricating oil composition. Of course, the preferred amount may depend amongst other factors on the quality of the basestock lubricating oil.

Corrosion inhibitors, also known as anti-corrosive agents, reduce the degradation of the metallic parts contacted by the lubricating oil composition. Illustrative of corrosion inhibitors are phosphosulfurized hydrocarbons and the products obtained by reaction of a phosphosulfurized hydrocarbon with an alkaline earth metal oxide or hydroxide, preferably in the presence of an alkylated phenol or of an alkylphenol thioester, and also preferably in the presence of carbon dioxide. Phosphosulfurized hydrocarbons are

prepared by reacting a suitable hydrocarbon such as a terpene, a heavy petroleum fraction of a C₂ to C₆ olefin polymer such as polyisobutylene, with from 5 to 30 weight percent of a sulfide of phosphorus for 1/2 to 15 hours, at a temperature in the range of 65° to 315°C. Neutralization of the phosphosulfurized hydrocarbon may be effected in the manner taught in U.S. Patent No. 1,969,324.

Oxidation inhibitors reduce the tendency of mineral oils to deteriorate in service which deterioration can be evidenced by the products of oxidation such as sludge and varnish-like deposits on the metal surfaces and by viscosity growth. Such oxidation inhibitors include alkaline earth metal salts of alkylphenolthioesters having preferably C₅ to C₁₂ alkyl side chains, calcium nonylphenol sulfide, barium t-octylphenyl sulfide, dioctylphenylamine, phenylalphanaphthylamine, phosphosulfurized or sulfurized hydrocarbons, etc.

Friction modifiers serve to impart the proper friction characteristics to lubricating oil compositions such as automatic transmission fluids.

Representative examples of suitable friction modifiers are found in U.S. Patent No. 3,933,659 which discloses fatty acid esters and amides; U.S. Patent No. 4,176,074 which describes molybdenum complexes of polyisobutenyl succinic anhydride-amino alkanols; U.S. Patent No. 4,105,571 which discloses glycerol esters of dimerized fatty acids; U.S. Patent No. 3,779,928 which discloses alkane phosphonic acid salts; U.S. Patent No. 3,778,375 which discloses reaction products of a phosphonate with an oleamide; U.S. Patent No. 3,852,205 which discloses S-carboxy-alkylene hydrocarbyl succinimide, S-carboxyalkylene hydrocarbyl succinamic acid and mixtures thereof; U.S. Patent No. 3,879,306 which discloses N-(hydroxyalkyl)

- 33 -

alkenyl-succinamic acids or succinimides; U.S. Patent No. 3,932,290 which discloses reaction products of di-(lower alkyl) phosphites and epoxides; and U.S. Patent No. 4,028,258 which discloses the alkylene oxide adduct of phosphosulfurized N-(hydroxyalkyl) alkenyl succinimides.

The most preferred friction modifiers are glycerol mono and dioleates, and succinate esters, or metal salts thereof, of hydrocarbyl substituted succinic acids or anhydrides and thiobis alkanols such as described in U.S. Patent No. 4,344,853.

Pour point depressants lower the temperature at which the lubricating oil will flow or can be poured. Such depressants are well known. Typical of those additives which usefully optimize the low temperature fluidity of the fluid are C₈-C₁₈ dialkylfumarate vinyl acetate copolymers, polymethacrylates, and wax naphthalene.

Foam control can be provided by an antifoamant of the polysiloxane type, e.g. silicone oil and polydimethyl siloxane.

Organic, oil-soluble compounds useful as rust inhibitors in this invention comprise nonionic surfactants such as polyoxyalkylene polyols and esters thereof, and anionic surfactants such as salts of alkyl sulfonic acids. Such anti-rust compounds are known and can be made by conventional means. Nonionic surfactants, useful as anti-rust additives in the oleaginous compositions of this invention, usually owe their surfactant properties to a number of weak stabilizing groups such as ether linkages. Nonionic anti-rust agents containing ether linkages can be made by alkoxylating organic substrates containing active hydrogens with an excess of the lower alkylene oxides (such

- 34 -

as ethylene and propylene oxides) until the desired number of alkoxy groups have been placed in the molecule.

The preferred rust inhibitors are polyoxyalkylene polyols and derivatives thereof. This class of materials are commercially available from various sources: PluronicTM Polyols from Wyandotte Chemicals Corporation; Polyglycol 112-2, a liquid triol derived from ethylene oxide and propylene oxide available from Dow Chemical Co.; and TergitolTM, dodecylphenyl or monophenyl polyethylene glycol ethers, and UconTM, polyalkylene glycols and derivatives, both available from Union Carbide Corp. These are but a few of the commercial products suitable as rust inhibitors in the improved composition of the present invention.

In addition to the polyols per se, the esters thereof obtained by reacting the polyols with various carboxylic acids are also suitable. Acids useful in preparing these esters are lauric acid, stearic acid, succinic acid, and alkyl- or alkenyl-substituted succinic acids wherein the alkyl-or alkenyl group contains up to about twenty carbon atoms.

The preferred polyols are prepared as block polymers. Thus, a hydroxy-substituted compound, $R-(OH)_n$ (wherein n is 1 to 6, and R is the residue of a mono- or polyhydric alcohol, phenol, naphthol, etc.) is reacted with propylene oxide to form a hydrophobic base. This base is then reacted with ethylene oxide to provide a hydrophylic portion resulting in a molecule having both hydrophobic and hydrophylic portions. The relative sizes of these portions can be adjusted by regulating the ratio of reactants, time of reaction, etc., as is obvious to those skilled in the art. Thus it is within the skill of the art to prepare polyols whose molecules are characterized by hydrophobic and hydrophylic moieties which are present in a ratio rendering


rust inhibitors suitable for use in any lubricant composition regardless of differences in the base oils and the presence of other additives.

If more oil-solubility is needed in a given lubricating composition, the hydrophobic portion can be increased and/or the hydrophylic portion decreased. If greater oil-in-water emulsion breaking ability is required, the hydrophylic and/or hydrophobic portions can be adjusted to accomplish this.

Compounds illustrative of $R-(OH)_n$ include alkylene polyols such as the alkylene glycols, alkylene triols, alkylene tetrols, etc., such as ethylene glycol, propylene glycol, glycerol, pentaerythritol, sorbitol, mannitol, and the like. Aromatic hydroxy compounds such as alkylated mono- and polyhydric phenols and naphthols can also be used, e.g., heptylphenol, dodecylphenol, etc.

Other suitable demulsifiers include the esters disclosed in U.S. Patents 3,098,827 and 2,674,619.

The liquid polyols available from Wyandotte Chemical Co. under the name Pluronic Polyols and other similar polyols are particularly well suited as rust inhibitors. These Pluronic Polyols correspond to the formula:



wherein x, y , and z are integers greater than 1 such that the $\text{CH}_2\text{CH}_2\text{O}$ — groups comprise from about 10% to about 40% by weight of the total molecular weight of the glycol, the average molecule weight of said glycol being from about 1000 to about 5000. These products are prepared by first

- 36 -

condensing propylene oxide with propylene glycol to produce the hydrophobic base



This condensation product is then treated with ethylene oxide to add hydrophylic portions to both ends of the molecule. For best results, the ethylene oxide units should comprise from about 10 to about 40% by weight of the molecule. Those products wherein the molecular weight of the polyol is from about 2500 to 4500 and the ethylene oxide units comprise from about 10% to about 15% by weight of the molecule are particularly suitable. The polyols having a molecular weight of about 4000 with about 10% attributable to $(\text{CH}_2\text{CH}_2\text{O})$ units are particularly good. Also useful are alkoxyated fatty amines, amides, alcohols and the like, including such alkoxyated fatty acid derivatives treated with C_9 to C_{16} alkyl-substituted phenols (such as the mono- and di-heptyl, octyl, nonyl, decyl, undecyl, dodecyl and tridecyl phenols), as described in U.S. Patent 3,849,501.

These compositions of our invention may also contain other additives such as those previously described, and other metal containing additives, for example, those containing barium and sodium.

The lubricating composition of the present invention may also include copper lead bearing corrosion inhibitors. Typically such compounds are the thiadiazole polysulphides containing from 5 to 50 carbon atoms, their derivatives and polymers thereof. Preferred materials are the derivatives of 1,3,4-thiadiazoles such as those described in U.S. Patents 2,719,125; 2,719,126; and 3,087,932; especially preferred is the compound 2,5 bis (t-octadithio)-1,3,4-thiadiazole commercially available as

- 37 -

AmocoTM 150. Other similar materials also suitable are described in U.S. Patents 3,821,236; 3,904,537; 4,097,387; 4,107,059; 4,136,043; 4,188,299; and 4,193,882.

Other suitable additives are the thio and polythio sulphenamides of thiadiazoles such as those described in U.K. Patent Specification 1,560,830. When these compounds are included in the lubricating composition, we prefer that they be present in an amount from 0.01 to 10, preferably 0.1 to 5.0 weight percent based on the weight of the composition.

Dispersants maintain oil insolubles, resulting from oxidation during use, in suspension in the fluid thus preventing sludge glocculation and precipitation or deposition on metal parts. Suitable dispersants include high molecular weight alkyl succinimides, the reaction product of oil-insoluble polyisobutylene succinic anhydride with ethylene amines such as tetraethylene pentamine and borated salts thereof.

The ashless dispersants include the polyalkenyl or borated polyalkenyl succinimide where the alkenyl groups is derived from a C₃ - C₄ olefin, especially polyisobutenyl having a number average molecular weight of about 700 to 5,000. Other well known dispersants include the oil soluble polyol esters of hydrocarbon substituted succinic anhydride, e.g., polyisobutenyl succinic anhydride, and the oil soluble oxazoline and lactone oxazoline dispersants derived from hydrocarbon substituted succinic anhydride and di-substituted amino alcohols. Lubricating oils typically contain about 0.5 to 5 wt.% of ashless dispersant.

A particular advantage of the viscosity index improvers of the present invention is use with dispersants,

particularly ashless dispersants, to form multigrade automobile engine lubricating oils.

Some of these numerous additives can provide a multiplicity of effects, e.g. a dispersant-oxidation inhibitor. This approach is well known and need not be further elaborated herein.

Compositions when containing these conventional additives are typically blended into the base oil in amounts effective to provide their normal attendant function. Representative effective amounts of such additives (as the respective active ingredients) in the fully formulated oil are illustrated as follows:

<u>Compositions</u>	<u>Wt.% A.I. (Preferred)</u>	<u>Wt.% A.I. (Broad)</u>
Viscosity Modifier	.01-4	0.01-12
Detergents	0.01-3	0.01-20
Corrosion Inhibitor	0.01-1.5	.01-5
Oxidation Inhibitor	0.01-1.5	.01-5
Dispersant	0.1-8	.1-20
Pour Point Depressant	0.01-1.5	.01-5
Anti-Foaming Agents	0.001-0.15	.001-3
Anti-Wear Agents	0.001-1.5	.001-5
Friction Modifiers	0.01-1.5	.01-5
Mineral Oil Base	Balance	Balance

When other additives are employed, it may be desirable, although not necessary, to prepare additive concentrates comprising concentrated solutions or dispersions of the viscosity index improvers of this invention (in concentrate amounts hereinabove described), together with one or more of said other additives (said concentrate when constituting an additive mixture being referred to herein as an additive-package) whereby several additives can be added simultaneously to the base oil to form the lubricating oil composition. Dissolution of the additive concentrate into

the lubricating oil may be facilitated by solvents and by mixing accompanied with mild heating, but this is not essential. The concentrate or additive-package will typically be formulated to contain the additives in proper amounts to provide the desired concentration in the final formulation when the additive-package is combined with a predetermined amount of base lubricant. Thus, the viscosity index improvers of the present invention can be added to small amounts of base oil or other compatible solvents along with other desirable additives to form additive-packages containing active ingredients in collective amounts of typically from about 2.5 to about 90%, and preferably from about 15 to about 75%, and most preferably from about 25 to about 60% by weight additives in the appropriate proportions with the remainder being base oil.

The final formulations may employ typically about 10 wt. % of the additive-package with the remainder being base oil.

The oleaginous compositions, particularly lubricating oil compositions, of the instant invention contain a viscosity index improving effective amount of the ethylene alpha-olefin polymers of the instant invention. By viscosity index improving effective amount is an amount effective to improve the viscosity index of an oleaginous composition compared to an oleaginous composition which does not contain viscosity index improver additive. Generally, this amount is from about 0.01 to about 20 wt. %, preferably from about 0.1 to about 12 wt. %, and more preferably from about 0.25 to about 6 wt. %, based upon the total weight of the oleaginous composition.

All of said weight percents expressed herein (unless otherwise indicated) are based on active ingredient (A.I.) content of the additive, and/or upon the total weight of any additive-package, or formulation which will be the

sum of the A.I. weight of each additive plus the weight of total oil or diluent.

This invention will be further understood by reference to the following examples, wherein all parts are parts by weight, unless otherwise noted.

EXAMPLE 1 - PREPARATION OF ETHYLENE-PROPYLENE COPOLYMER

A clean, dry autoclave is flushed with propylene and a 4 ml. solution of methylalumoxane in toluene is added by syringe. The autoclave is then charged with 500 ml. of liquid propylene and brought to 50°C for reaction. The pressure in the autoclave is then increased by 150 psi by addition of ethylene. One-half mg. of zirconocene (bis(n-butyl tetrahydroindenyl)zirconium dichloride) dissolved in 3 ml. of toluene is injected into the autoclave. Ethylene is supplied to maintain the initial total pressure in the autoclave. Reaction time is 30 minutes. The monomers are flashed off, and the temperature is brought to 25°C. The polymer product, which has a number average molecular weight in the range of about 209,000, is recovered from the autoclave and is dried in a vacuum oven at 50°C overnight.

EXAMPLE 2

An SAE 10W40 formulation crankcase motor oil composition is prepared by dissolving sufficient copolymer which is prepared substantially in accordance with the procedure of Example 1 in mineral oil to provide a composition containing 1.3 wt. % (active ingredient) of said copolymer. The oil also contains 4.3 wt. % of a detergent inhibitor package of conventional additives.

The principles, preferred embodiments, and modes of operation of the present invention have been described in the foregoing specification. The invention which is intended to be protected herein, however, is not to be

- 41 -

construed as limited to the particular forms disclosed, since these are to be regarded as illustrative rather than restrictive. Variations and changes may be made by those skilled in the art without departing from the spirit of the invention.

- 42 -

THE EMBODIMENTS OF THE INVENTION IN WHICH AN EXCLUSIVE PROPERTY OR PRIVILEGE IS CLAIMED ARE DEFINED AS FOLLOWS:

1. An oleaginous composition comprising oleaginous material and a viscosity modifying effective amount of ethylene alpha-olefin polymer comprising monomer units derived from ethylene and at least one alpha-olefin represented by the formula $H_2C = CHR^1$ wherein R^1 is an alkyl group of from 1 to 18 carbon atoms, and wherein said polymer has a number average molecular weight of from above 20,000 to about 500,000, and an average of at least about 30% of the polymer chains contain terminal ethenylidene unsaturation.
2. The composition of claim 1 wherein said polymer has a number average molecular weight of from about 25,000 to about 200,000.
3. The composition of claim 2 wherein said polymer has a number average molecular weight of from about 30,000 to about 100,000.
4. The composition of claim 1 wherein said polymer has a molar ethylene content of between about 20 and about 80 percent.
5. The composition of claim 4 wherein said polymer has a molar ethylene content of between about 45 and about 65 percent.
6. The composition of any of claims 1 to 5 wherein said polymer comprises an ethylene-propylene copolymer.
7. The composition of claim 1 which contains from about 0.01 to about 20 weight percent of said polymer.
8. The composition of claim 7 wherein said oleaginous material comprises lubricating oil.

- 43 -

9. The composition of claim 7 which contains from about 0.1 to about 12 weight percent of said polymer.

10. The composition of claim 9 wherein said oleaginous material comprises lubricating oil.

11. An oleaginous composition comprising oleaginous material, and a viscosity modifying effective amount of ethylene alpha-olefin polymer comprising monomer units derived from ethylene and at least one alpha-olefin represented by the formula $H_2C = CHR^1$ wherein R^1 is an alkyl group of from 1 to 18 carbon atoms, and wherein said polymer has a number average molecular weight of from above 20,000 to about 500,000, and an average of at least about 60% of the polymer chains contain terminal ethenylidene unsaturation.

12. The composition of claim 11 wherein said polymer has a number average molecular weight of from about 25,000 to about 200,000.

13. The composition of claim 12 wherein said polymer has a number average molecular weight of from about 30,000 to about 100,000.

14. The composition of claim 11 wherein said polymer contains from about 30 to 70 mole % ethylene.

15. The composition of claim 14 wherein said polymer contains from about 45 to 65 mole % ethylene.

16. The composition of any of claims 11 to 15 wherein said polymer comprises an ethylene-propylene copolymer.

17. The composition of claim 11 which contains from about 0.01 to about 20 weight percent of said polymer.

- 44 -

18. The composition of claim 17 wherein said oleaginous material comprises lubricating oil.

19. The composition of claim 17 which contains from about 0.1 to about 12 weight percent of said polymer.

20. The composition of claim 19 wherein said oleaginous material comprises lubricating oil.

21. An oil additive concentrate composition comprising mineral oil diluent and from about 5 to about 60 weight percent of ethylene alpha-olefin polymer comprising monomer units derived from ethylene and at least one alpha-olefin represented by the formula $H_2C = CHR^1$ wherein R^1 is an alkyl group of from 1 to 18 carbon atoms, and wherein said polymer has a number average molecular weight from greater than 20,000 to about 500,000, and an average of at least about 30% of the polymer chains contain terminal ethenylidene unsaturation.

22. The composition of claim 21 wherein said polymer has a number average molecular weight of from about 25,000 to about 200,000.

23. The composition of claim 22 wherein said polymer has a number average molecular weight of from about 30,000 to about 100,000.

24. The composition of claim 21 which contains from about 10 to about 60 weight percent of said polymer.

25. The composition of claim 21 wherein said polymer has a molar ethylene content of between about 20 and about 80 percent.

- 45 -

26. The composition of claim 25 wherein said polymer has a molar ethylene content of between about 45 and about 65 percent.

27. The composition of any of claims 21-26 wherein said polymer comprises ethylene-propylene copolymer.

28. An oil additive concentrate composition comprising mineral oil diluent and from about 5 to about 60 weight percent of ethylene alpha-olefin polymer comprising monomer units derived from ethylene and at least one alpha-olefin represented by the formula $H_2C = CHR^1$ wherein R^1 is an alkyl group of from 1 to 18 carbon atoms, and wherein said polymer has a number average molecular weight from greater than 20,000 to about 500,000, and an average of at least about 60% of the polymer chains contain terminal ethenylidene unsaturation.

29. The composition of claim 28 wherein said polymer has a number average molecular weight of from about 25,000 to about 200,000.

30. The composition of claim 29 wherein said polymer has a number average molecular weight of from about 30,000 to about 100,000.

31. The composition of claim 28 which contains from about 20 to about 50 weight percent of said polymer.

32. The composition of claim 28 wherein said polymer has a molar ethylene content of between about 20 and about 80 percent.

33. The composition of claim 32 wherein said polymer has a molar ethylene content of between about 45 and 65 percent.

- 46 -

34. The composition of any of claims 28 to 33 wherein said polymer comprises ethylene-propylene copolymer.