

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
13 November 2003 (13.11.2003)

PCT

(10) International Publication Number
WO 03/093342 A1

(51) International Patent Classification⁷: **C08G 59/62**,
59/50, 59/18, C09D 5/44

(21) International Application Number: PCT/EP03/50107

(22) International Filing Date: 16 April 2003 (16.04.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
102 19 102.6 29 April 2002 (29.04.2002) DE

(71) Applicant (*for all designated States except US*): **VAN-
TICO AG** [CH/CH]; Klybeckstrasse 200, CH-4057 Basel
(CH).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD,
SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US,
UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(72) Inventor; and

(75) Inventor/Applicant (*for US only*): **VOLLE, Jörg**
[DE/DE]; Luisenstrasse 37a, 59379 Selm-Bork (DE).

(74) Agent: **MAUÉ, Paul Georg**; Solvias AG, Patents, WKL-
402.4.26, Klybeckstrasse 191, CH-4002 Basel (CH).

Published:

— with international search report

*For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.*

(54) Title: MANNICH BASES FROM ISOLATED AMINE ADDUCTS

(57) Abstract: Mannich bases as curing agents for epoxy resins, characterized in that to prepare the Mannich base an isolated amine adduct is used obtainable by reacting a) an amine containing at least three active amine hydrogens with b) an epoxide compound containing on average one or more than one epoxide group in the molecule, optionally using a solvent, there being an excess of a) relative to reactive groups of components a) and b), and subsequently the adduct formed is isolated from free amines. Curable epoxy resin compositions comprising these Mannich bases are suitable owing to good obtainable surface properties in particular for coating, adhesively bonding and enhancing metallic and mineral substrates, as adhesive and sealant, and for producing mouldings and sheetlike structures.



WO 03/093342 A1

Mannich bases from isolated amine adducts

The present invention relates to Mannich bases prepared using isolated amine adducts obtainable by reacting amines with epoxide compounds and then isolating the adducts from free amines; in particular, in one preferred embodiment, the preparation of Mannich bases by transaminating the aforementioned isolated amine adducts with Mannich bases; and to the use of these Mannich bases as curing agents for epoxy resins.

Curable compositions based on amine compounds and epoxy resins have long been used in industry for coating and enhancing metallic and mineral surfaces, and also as adhesives and sealants. The cure rate of such systems is too low for many applications, particularly when coating is to be carried out at low temperatures, e.g. in winter. Numerous experiments have been performed aimed at achieving sufficient low-temperature curing through the addition of external accelerators. Use has been made, for example, of tertiary amines and phenols, with preference being given to tertiary amines such as trisdimethylaminomethylphenol, for example. However, since these external accelerators do not participate in the curing reaction, they are subsequently present in free form in the cured thermoset and can be washed out later on. Moreover, free phenols in particular are toxicologically objectionable. For this reason it is common to use reaction products of phenols, aldehydes and amine compounds as curatives or accelerators. The thermosets cured with epoxide compounds, however, generally have poor surface qualities. Thus, greasy films, formation of hydrates and development of texture are frequent occurrences, meaning that such Mannich bases can often not be used in the surface sector. The subsequent formation of adducts of the abovementioned compounds, although possibly contributing to improving the level of properties, is unable to eliminate these surface defects completely. The fraction of free residual amines results, moreover, in the abovementioned compounds having a strong odour nuisance effect and in some cases being toxicologically objectionable.

It was an object of the present invention, therefore, to provide curing agents which have a sufficient cure rate at low temperatures in combination with as long a pot life as possible and, at the same time, satisfactory surface qualities such as, for example, a low propensity to form texture or greasy films. This object is achieved in accordance with the invention through the use of specially prepared Mannich bases based on isolated amine adducts as curatives for

- 2 -

epoxy resins. These Mannich bases are obtainable by reacting an amine with aldehydes and phenols, characterized in that first of all, before the amine is reacted with the aldehyde and the phenol component, in a first step an adduct is formed from the amine with a preferably monofunctional compound, and this adduct is then isolated. This isolated adduct, in a second step, is reacted conventionally to form a Mannich base or, alternatively, is used for the transamination of a Mannich base starting compound.

Surprisingly, the use of these specially prepared Mannich bases as curing agents for epoxy resins leads to surface properties in the cured products which, comparatively, are much better than when using Mannich bases with a comparable degree of adduct formation but prepared not from amine adducts isolated to start with but rather from subsequent adducts of Mannich bases.

The isolated amine adducts are prepared using epoxide compounds, preferably monofunctional glycidyl ethers, such as phenyl glycidyl ether, cresyl glycidyl ether, glycidyl ethers based on distilled cashew nut shell oil, glycidyl ethers based on monoalcohols, styrene oxide, etc.

Amine compounds used are those amines which contain at least 3 active hydrogen atoms in the molecule. Preferred amines are polyalkylenamines, especially polyethylenepolyamines such as, for example, aminoethylpiperazine, ethylenediamine, diethylenetriamine, triethylenetetramine and tetraethylenepentamine.

To prepare the isolated amine adducts the epoxide compound is added to a 1.5 to 8 molar, preferably 2 to 3 molar, excess of the amine component at from 60°C to 80°C with stirring and, after reaction has taken place, the excess of amine compound is separated off by distillation, where appropriate under reduced pressure, to give a product isolated from free amines.

The isolated adducts, in particular those with monofunctional epoxide compounds, are liquid at room temperature.

As a phenol component for preparing the Mannich bases it is possible, for example, to use the following: monophenols, such as phenol, cresol, the isomeric xylenols, para-

- 3 -

tert-butylphenol, nonylphenol, naphthols and also diphenols and polyphenols such as resorcinol, hydroquinone, bisphenol A, bisphenol F or novolaks.

As an aldehyde component it is preferred to use trioxane, formaldehyde or paraformaldehyde.

The Mannich bases are prepared from the isolated amine compounds by methods known per se, by introducing the isolated amine adduct compound with the phenol component, where appropriate in the presence of diluents and/or solvents, and adding the aldehyde component in portions at elevated temperature, dissolving it, and, after heating up to 160°C, separating off the water of reaction. Examples of diluents and/or solvents which can be used include the following: xylene, toluene, alcohols, ethers, water. The nature of the diluents/solvents used is dependent on the dissolution capacity of the reactants. Thus, depending on the isolated adducts or phenols employed, the solubility may be better in one or another solvent. Good results are essentially obtained using xylene as solvent.


This invention firstly provides, therefore, Mannich bases characterized in that to prepare the Mannich bases an isolated amine adduct is used obtainable by reacting a) an amine containing at least three active amine hydrogens with b) an epoxide compound containing on average one or more than one epoxide group in the molecule, optionally using a solvent, there being an excess of a) relative to reactive groups of components a) and b), and subsequently the adduct formed is isolated from free amines.

The invention further provides Mannich bases characterized in that for the preparation of the Mannich base from an amine, an aldehyde and a phenol derivative the amine used is an isolated amine adduct obtainable as described above.

For the preparation of the Mannich bases, in addition to the isolated adducts, it is also possible to use as well, in part, polyamidoamides with or without imidazoline groups, prepared from polyamine compounds and organic acids.

One particularly preferred embodiment of the invention are Mannich bases characterized in that for the preparation of the Mannich bases a Mannich base obtained by reacting an amine, an aldehyde and a phenol derivative is subjected to transamination with an isolated amine adduct of the invention.

Mannich bases prepared by transamination are described in, for example, DE-A 28 05 853 and in EP-A 0 684 268. The advantage of these compounds is their extremely low phenol content and hence a lower toxicity. In such a transamination reaction amine compounds are exchanged for amine compounds of a Mannich base, preferably mono-, bis- or tris(dimethylamino)phenol, by heating both components to more than 110°C, in the course of which the secondary amine compound present on the phenol component, generally dimethylamine, is eliminated and removed from the reaction mixture by distillation. Also described therein are adducts of such exchange Mannich bases with various compounds, particularly glycidyl ethers. The disadvantage of such compounds, here again, is the still considerable fraction of free, unreacted amine. The source of this free amine fraction is the linkage products which are also formed, in accordance with the following scheme (using a diamine and dimethylaminomethylphenol by way of example):



where the dimethylamine, $\text{HN}(\text{CH}_3)_2$, leaves the reaction mixture at the temperatures customary during the transamination reaction and is collected in a cold trap. The unreacted residues of the normally low-volatility amine compounds used for the transamination remain in the product.

Free amines, however, have an intense odour and are thus a nuisance during processing, particularly in enclosed areas, and are frequently toxicologically objectionable. The aim of the invention was to eliminate the aforementioned disadvantages here as well and to provide curing agents which cure rapidly at low temperatures ($< 5^\circ\text{C}$) and have a low free amine content.

This object has been achieved through the curing agents of the invention, which are characterized in that, as already described above, in a first step an isolated adduct of an amine compound with an epoxide compound is prepared and, in a second step, this adduct is subjected to a transamination reaction with a Mannich base, the isolated amine adduct adding to the phenol of the Mannich base and being exchanged for the amine, preferably a secondary amine, which is present on the phenol.

- 5 -

Moreover, such products, particularly when tris(dimethylaminomethyl)phenol is used, have a very low phenol content. In addition to the isolated amine adducts it is also possible to prepare the Mannich bases in part from polyaminoamide compounds prepared from polyamines and organic acids.

The invention accordingly further provides curing agents for epoxide compounds, obtainable from isolated amine adducts and Mannich bases by means of a transamination reaction.

The Mannich bases needed to prepare the compounds of the invention are preferably Mannich bases of phenol, formaldehyde and dimethylamine, which are available commercially, for example, from the company Rohm & Haas under the name DMP. These products include DMP 10 or (dimethylaminomethyl)phenol, DMP20 or bis(dimethylaminomethyl)phenol and DMP 30 or tris(dimethylaminomethyl)phenol.

Preference is given here to tris(dimethylaminomethyl)phenol.

Tris(dimethylaminomethyl)phenol is also available commercially from Vantico as curative HY-960-1 CH. There is no need to make special mention of the fact that Mannich bases based on other phenols (e.g. bisphenol A or bisphenol F, cresol etc), aldehydes and amine compounds can also be used.

The degree of transamination is guided by the desired properties of the compounds of the invention. It can be between 1% and 100%. That is, between 1% and 100% of the amino groups, preferably secondary amino groups, that are present on the Mannich base used can be exchanged. This must be viewed as a function of the degree of substitution of the Mannich base employed. For example, in the case of bis (dimethylaminomethyl)phenol only one amino group can be exchanged, while in the case of bis(dimethylaminomethyl)phenol a maximum of 2 amino groups and in the case of tris(dimethylaminomethyl) phenol a maximum of 3 amino groups can be exchanged. Preferred in accordance with the invention are compounds in which the amino groups have not been completely exchanged. Taking tris(dimethylaminomethyl)phenol as the example, these are compounds containing unexchanged dimethylamine groups.

Particular preference is given to transamination products based on trisdimethylaminomethylphenol in which the degree of exchange is from 50% to 99%, more preferably from 60% to 95%. The isolated amine adducts used to prepare the compounds of the invention have been described above.

The compounds of the invention obtained by transamination may additionally have adducts formed from them with compounds capable of reaction with amine compounds, for the purpose of establishing specific properties or setting the amine equivalent. For this purpose it is also possible in particular to use the compounds used for forming adducts of the amine compounds.

The invention further provides curable compositions comprising a Mannich base of the invention, an epoxy resin, and, optionally, the auxiliaries and additives that are customary in epoxy resin chemistry.

The invention further provides for the use of the curable compositions for coating, adhesively bonding and enhancing metallic and mineral substrates, as adhesive and sealant, and also for producing mouldings and sheetlike structures.

Examples:

Example 1 (Preparation of an isolated adduct)

567 g of tetraethylenepentamine TEPA (3 mol) are charged to a reaction vessel. After heating to about 60°C, 185 g of cresyl glycidyl ether (1 epoxide equivalent) are added over the course of about 60 minutes. The temperature rises to 90°C. The reaction product is then heated to 260°C and the excess amine is separated off under reduced pressure (<1 mbar). Distillate: 380 g (2 mol) of TEPA. Viscosity/25°C: 1500 mPa•s (Haake rotational viscometer VT 550).

Example 2 (Preparation of a Mannich base from an isolated adduct)

374 g (about 1 mol) of the isolated adduct from Example 1 are charged to a reaction vessel together with 31.3 g of phenol (0.33 mol) and 200 g of xylene and the initial charge is homogenised. Then, after heating to 60°C, 30 g (1 mol) of paraformaldehyde are added in portions at not more than 90°C, and dissolved. After heating to 150°C, the water of reaction formed (18 g) is separated off using a water separator. When the total amount of water has been separated off the xylene is separated off under a reduced pressure of 50 mbar. This gives a yellowish product of high viscosity.

A) 70 g of the product is dissolved in 24 g of xylene and 6 of butanol. The 70% solution has a viscosity of 3400 mPa•s.

- 7 -

B) 70 g of the product are dissolved in 30 g of benzyl alcohol. The 70% solution has a viscosity 13100 mPa•s.

The theoretical amine equivalent of the solutions is approximately 120.

Example 3 (Transamination)

561 g (about 1.5 mol) of the isolated adduct from Example 1 are homogenised with 265 g of DMP 30 (about 1 mol) and heated at 145°C in a distillation apparatus with distillate cooling until 67.5 g of distillate have been eliminated. (This corresponds to a degree of transamination of 50%, based on all of the substitution possibilities.) Analysis by gas chromatography reveals the distillate to be pure dimethylamine. The amount of distillate corresponds to 1.5 mol of dimethylamine.

Cooling gives a yellowish product of high viscosity.

A) 70 g of the product are dissolved in 24 g of xylene and 6 g of n-butanol. The 70% solution has a viscosity of 2000 mPa•s.

B) 70 g of the product are dissolved in 30 g of benzyl alcohol. The 70% solution has a viscosity of 8700 mPa•s.

The theoretical amine equivalent of the solutions is approximately 145.

Example 4 (Transamination)

748 g (about 2 mol) of the isolated adduct from Example 1 are reacted in accordance with Example 2 with 265 g (1 mol) of DMP 30 until 90 g (2 mol) of dimethylamine have been eliminated.

(Degree of transamination 66%).

A) 70 g of the product are dissolved in 24 g of xylene and 6 of n-butanol. The 70% solution has a viscosity of 3200mPa•s.

B) 70 g of the product are dissolved in 30 g of benzyl alcohol. The 70% solution has a viscosity of 14400 mPa•s.

The theoretical amine equivalent of the solutions is approximately 132.

Example 5 (Subsequent adduct formation)

100 g of the solution from Example 4 are heated to 70°C and an adduct is subsequently formed with 5 g of cresyl glycidyl ether (epoxide equivalent 182). The product has a viscosity of 18800 mPa•s. The theoretical amine equivalent is approximately 145.

Example 6 (comparative example to Example 4, adduct formed subsequently from exchanged Mannich base, same amounts employed)

378 g (2 mol) of tetraethylenepentamine are reacted in accordance with Example 2 with 265 (1 mol) of DMP 30 (tris(dimethylaminomethyl)phenol) until 90 g (2 mol) of dimethylamine have been eliminated (degree of transamination 66%). An adduct is subsequently formed from the product using 370 g of cresyl glycidyl ether at from 80°C to 100°C.

A) 70g of the product are dissolved in 24 g of xylene and 6 g of n-butanol. 70% solution has a viscosity 3800 mPa•s.

B) 70g of the product are dissolved in 30 g of benzyl alcohol. The product has a viscosity of 16500 mPa•s.

The theoretical amine equivalent is approximately 132.

Example 7 (use example, surface comparison):

The solutions A) of the compounds of the invention from Examples 2 to 6 are homogenised with a bisphenyl A diglycidyl ether (epoxide equivalent: 185) Araldite GY 250 (Vantico AG) and a portion of the mixture is applied to a glass plate using a 100 μ spiral and stored in a controlled-climate cabinet at 5°C for 24 hours. An assessment is made of the surface quality. The amounts and results are given in Table 1.

Table 1

The surfaces are assessed on a scale from 1 to 10, where 1 denotes the best and 10 the worst evaluation. Water spotting is tested by applying water to the coating. A visual evaluation is made of the whitening of the film after 1 hour. Greasy film and sticking are determined by touch-testing the surface by hand, wearing a rubber glove for protection. The formation of hydrates is likewise assessed visually.

Example A) solutions	g curing agent per 100 g Araldite GY 250	a) Water spotting, 1 h	b) Greasy film	c) Hydrate formation	d) Sticking	Sum of a) to d)
2	65	4	3	4	5	16
3	78	3	3	3	4	13
4	71	3	3	3	4	13
5	78	2	2	2	3	9
6	71	6	3	6	4	19

Example 8 (use example, cure rate):

The solutions B) of the compounds of the invention from Examples 2 to 6 are homogenised with a mixture of a bisphenol A/F diglycidyl ether with a glycidylised fatty alcohol (epoxide equivalent of 194 g) Araldite GY 793 (Vantico). A portion of this mixture is poured into a sample vessel with a thickness of 6 mm and stored in a controlled-climate chamber at 5°C. A measurement is made of the cure rate to Shore D. The results are set out in Table 2.

Table 2

Example B) solutions	g curing agent per 100 g Araldite GY 793	1 day	2 days	3 days	7 days
2	62	25	48	67	75
3	75	34	56	74	76
4	68	30	52	69	74
5	75	37	60	76	78
6	68	29	52	70	77

Discussion of the results:

The cure rates of the products are comparable. As compared with the preferred embodiment of the transaminated products (Examples 3 to 5) the specimen cast with the directly prepared Mannich base (Example 6) has a somewhat lower initial hardness.

The surfaces of the products of the invention (Examples 2 to 5) surprisingly exhibit a lower level of hydrate formation and of water spotting than comparative Example 6. This is also evident from the direct comparison of Examples 4 and 6. This result was unforeseeable, since the reactants in these two products are present in equal amount and differ only in that, in the example according to the invention, an isolated adduct is used to prepare the Mannich base, and the comparative example is subsequently adducted with the same amount of glycidyl ether. A striking finding is the further significantly improved surface quality and

- 10 -

somewhat better cure rate of the inventive Example 5. Also surprising is the viscosity of the inventive Example 4, which is lower by about 15% in direct comparison with comparative Example 6.

Claims

1. Mannich base characterized in that to prepare the Mannich base an isolated amine adduct is used obtainable by reacting a) an amine containing at least three active amine hydrogens with b) an epoxide compound containing on average one or more than one epoxide group in the molecule, optionally using a solvent, there being an excess of a) relative to reactive groups of components a) and b), and subsequently the adduct formed is isolated from free amines.
2. Mannich base according to Claim 1, characterized in that for the preparation of the Mannich base from an amine, an aldehyde and a phenol derivative the amine used is an isolated amine adduct according to Claim 1 is used as amine.
3. Mannich base according to Claim 1, characterized in that for the preparation of the Mannich base a Mannich base obtained by reacting an amine, an aldehyde and a phenol derivative is subjected to transamination with an isolated amine adduct according to Claim 1.
4. Mannich base according to Claim 1, characterized in that monofunctional glycidyl ethers are used as epoxide compounds for the preparation of the isolated amine adducts.
5. Mannich base according to Claim 1, characterized in that polyalkylenepolyamines, especially polyethylenepolyamines, are used as amine compounds for the preparation of the isolated amine adducts.
6. Mannich base according to Claim 3, characterized in that Mannich bases based on phenol, cresol and bisphenols and dialkylamines are used as Mannich bases for the transamination reaction.
7. Mannich base according to Claim 6, characterized in that Mannich bases based on phenol and dimethylamines are used as Mannich bases for the transamination reaction.
8. Mannich base according to one of Claims 3, 6 and 7, characterized in that the degree of transamination is between 50% and 99%, preferably between 60 and 95%.

- 12 -

9. Curable composition comprising
 - a) a Mannich base according to one of Claims 1 to 8,
 - b) an epoxy resin, and optionally
 - c) auxiliaries and additives customary in epoxy resin technology.
10. Use of a curable composition according to Claim 9 for coating, adhesively bonding and enhancing metallic and mineral substrates, as adhesive and sealant, and for producing mouldings and sheetlike structures.
11. Mannich base according to one of Claims 1 to 8 as a curing agent for epoxy resins.

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/EP 03/50107

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08G59/62 C08G59/50 C08G59/18 C09D5/44

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08G C09D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,X	EP 1 209 206 A (SOLUTIA AUSTRIA GMBH) 29 May 2002 (2002-05-29) claims; table 1 ----	1-11
X	US 5 578 685 A (NEUMANN UWE ET AL) 26 November 1996 (1996-11-26) column 4, line 12; claims ----	1-11
X	US 4 568 709 A (GMOSE JOHANN ET AL) 4 February 1986 (1986-02-04) column 3, line 3; claims ----	1-11
A	US 4 444 634 A (KEMPTER FRITZ E ET AL) 24 April 1984 (1984-04-24) the whole document ----- -/--	1-11



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

° Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

S document member of the same patent family

Date of the actual completion of the international search

25 July 2003

Date of mailing of the international search report

07/08/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Ellrich, K

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP 03/50107

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>GB 1 457 932 A (BASF AG) 8 December 1976 (1976-12-08) the whole document</p> <p>-----</p>	1-11

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 03/50107

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 1209206	A	29-05-2002	AT 409964 B AT 19272000 A EP 1209206 A1 US 2002086918 A1	27-12-2002 15-05-2002 29-05-2002 04-07-2002
US 5578685	A	26-11-1996	DE 4331052 A1 AT 198483 T CA 2131756 A1 DE 59409625 D1 EP 0645408 A1 JP 7149877 A US 5576108 A	16-03-1995 15-01-2001 14-03-1995 08-02-2001 29-03-1995 13-06-1995 19-11-1996
US 4568709	A	04-02-1986	AT 378537 A AT 380484 A AT 382634 A AT 384434 B AT 88484 A CA 1257432 A1 DE 3509707 A1 DE 3561067 D1 EP 0158128 A1 ES 8602882 A1 PL 252391 A1 AT 224384 A AT 252684 A AT 360884 A	26-08-1985 26-05-1986 25-03-1987 10-11-1987 15-01-1985 11-07-1989 07-11-1985 07-01-1988 16-10-1985 16-03-1986 17-12-1985 15-10-1985 15-08-1986 15-04-1987
US 4444634	A	24-04-1984	DE 3123968 A1 AT 19640 T BR 8203530 A DE 3270968 D1 EP 0068243 A2 ES 8305018 A1 JP 58045217 A	13-01-1983 15-05-1986 07-06-1983 12-06-1986 05-01-1983 16-06-1983 16-03-1983
GB 1457932	A	08-12-1976	CA 1021493 A1 DE 2320301 A1 AT 334480 B BE 813979 A1 CH 615445 A5 FR 2226445 A1 JP 1142560 C JP 50013499 A JP 57031574 B NL 7405364 A , B SE 409334 B ZA 7402466 A AT 327974 A ES 425531 A1 IT 1011253 B	22-11-1977 10-04-1975 25-01-1976 21-10-1974 31-01-1980 15-11-1974 13-04-1983 12-02-1975 06-07-1982 23-10-1974 13-08-1979 28-05-1975 15-05-1976 01-06-1976 20-01-1977