

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
17 January 2008 (17.01.2008)

PCT

(10) International Publication Number  
**WO 2008/008077 A2**

(51) International Patent Classification:  
C08G 77/458 (2006.01) C08G 77/388 (2006.01)  
C08G 77/26 (2006.01) C08G 77/00 (2006.01)

(74) Agent: CARTER, Charles, G.; Foley & Lardner LLP, 777  
East Wisconsin Avenue, Milwaukee, WI 53202 (US).

(21) International Application Number:  
PCT/US2006/029035

(81) Designated States (unless otherwise indicated, for every  
kind of national protection available): AE, AG, AL, AM,  
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,  
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,  
GB, GD, GE, GH, GM, HN, HR, HU, ID, IL, IN, IS, JP,  
KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT,  
LU, LV, LY, MA, MD, ME, MG, MK, MN, MW, MX, MZ,  
NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU,  
SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT,  
TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(22) International Filing Date: 26 July 2006 (26.07.2006)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
60/703,532 29 July 2005 (29.07.2005) US

(84) Designated States (unless otherwise indicated, for every  
kind of regional protection available): ARIPO (BW, GH,  
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,  
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,  
FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT,  
RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA,  
GN, GQ, GW, ML, MR, NE, SN, TD, TG).


(71) Applicant (for all designated States except US): NDSU  
RESEARCH FOUNDATION [US/US]; North Dakota  
State University, Ndsu Research Foundation, 1735  
NDSU Research Park Drive, P.O. Box 5002, Fargo, ND  
58105-5002 (US).

**Published:**  
— without international search report and to be republished  
upon receipt of that report

(72) Inventors; and  
(75) Inventors/Applicants (for US only): WEBSTER, Dean,  
C. [US/US]; 2434 Parkview Drive, Fargo, ND 58103 (US).  
EKIN, Abdullah [TR/US]; 902 Oak Street, North, Apart-  
ment 10, Fargo, ND 58102 (US).

For two-letter codes and other abbreviations, refer to the "Guid-  
ance Notes on Codes and Abbreviations" appearing at the begin-  
ning of each regular issue of the PCT Gazette.

(54) Title: FUNCTIONALIZED POLYSILOXANE POLYMERS



(57) Abstract: Polysiloxanes terminated with one or more hydroxy functional carbamate groups are provided. The polymers may have the formula (I) wherein R<sup>1</sup>, R<sup>2</sup>, R<sup>3</sup>, and R<sup>4</sup> are independently hydrogen, C<sub>1</sub>-C<sub>10</sub> alkyl, C<sub>1</sub>-C<sub>10</sub> fluoro-substituted alkyl, cyclopentyl, cyclohexyl, benzyl, tolyl, xylyl and/or phenyl; R<sup>5</sup> and R<sup>6</sup> are linking groups; R<sup>15</sup> and R<sup>16</sup> are independently hydrogen, C<sub>1</sub>-C<sub>10</sub> alkyl, cyclopentyl, cyclohexyl, benzyl, tolyl, xylyl or phenyl; and L<sup>1</sup> and L<sup>2</sup> are linking groups. Typically, x is such that the polymer has a molecular weight of about 1,000 to 100,000. Other polymeric materials produced by reacting with an isocyanate functional compound or a lactone and coating compositions containing such polymeric materials are also provided.

WO 2008/008077 A2

# FUNCTIONALIZED POLYSILOXANE POLYMERS

## GOVERNMENT RIGHTS STATEMENT

[0001] The U.S. Government has a paid-up license in this invention and the right in limited circumstances to require the patent owner to license others on reasonable terms as provided for by the terms of Grant Nos. N00014-03-1-0702 and N00014-04-1-0597 awarded by the Department of Defense, Office of Naval Research.

## RELATED PATENT APPLICATIONS

[0002] This application claims priority of U.S. Provisional Patent Application Serial No. 60/703,532 (filed on July 29, 2005), entitled "Polysiloxane-Polylactone Block Copolymers with Carbamate Linkages," the entire disclosure of which is herein incorporated by reference.

## BACKGROUND

[0003] Polysiloxanes have received a lot of attention since their introduction because of their many desirable properties such as low glass transition temperature, hydrophobicity, UV stability and high chain flexibility. However, pure polysiloxanes are often unsuitable for some applications because of their poor mechanical properties. The polysiloxanes may be modified via functionalization or block copolymerization to provide more desirable mechanical properties.

[0004] Accordingly, it would be desirable to provide a modified polysiloxane, such as a modified poly(dimethyl siloxane) ("PDMS"), that is suitable for uses in marine coating applications, *e.g.*, to protect against fouling of marine structures, such as ships, boats, piers, and the like.

## SUMMARY

[0005] A number of functionalized polysiloxanes and polyorganosiloxanes are described herein. In particular, polysiloxanes that are terminated with a hydroxy functional carbamate group and polymers that include a subunit which is derived from a polysiloxane terminated with a hydroxy functional group are described. The functionalized polysiloxanes may include a carbamate linking group to link a polysiloxane segment to one or more other

segments to form single or multi-functional (e.g., di, tri, tetra, etc.) polysiloxane polymers. The functionalized polysiloxanes may be useful in a variety of settings. For example, the functionalized polysiloxanes may be useful as an antifouling material in marine environments. The polymers may be included in a coating which is applied to a surface such as the hull of a ship, pier, etc. that is susceptible to fouling by microorganisms in a marine environment. The polymers may serve to prevent fouling from taking place and/or make it easier to remove fouling. In particular, the low surface energy and low modulus may provide easy release of marine organisms in fouling release coatings. It should be appreciated that other uses for functionalized polysiloxane polymers are contemplated as well (e.g., anti-graffiti coatings, biocompatible polymers, etc.).

[0006] In one embodiment, the functionalized polysiloxane may include functionalized poly(dimethyl siloxane) (PDMS). In another embodiment, the functionalized polysiloxane may include segments derived from one or more lactones to form a polysiloxane/polylactone block copolymer. One or more carbamate linking groups may be used to link the polysiloxane segment to the polylactone segment. The functionalized polysiloxane polymer may take a variety of forms. For example, the polymer may be an oligomer, block copolymer, or star branched block copolymer.

[0007] The functionalized polysiloxane polymer may be synthesized by first synthesizing an aminoalkyl terminated polysiloxane polymer. A cyclic carbonate is added to form a hydroxy alkyl carbamate terminated polysiloxane polymer. A lactone monomer such as  $\epsilon$ -caprolactone may be added to form a polysiloxane/polylactone polymer.


[0008] A coating composition may be prepared that includes the functionalized polysiloxane polymer. In one embodiment, the coating composition may be prepared by reacting an isocyanate functionalized compound (e.g., polyisocyanate), an alcohol (e.g., polyol), and the hydroxy terminated polysiloxane polymer. The alcohol is typically a relatively low hydroxy equivalent weight polyol, e.g., with a hydroxy equivalent weight of no more than about 500. The isocyanate functionalized compound and/or the polyol can serve to cross-link the polysiloxane polymer. The hydroxy terminated polysiloxane polymer may be the polymer that is formed prior to addition of the lactone monomer (i.e., the polysiloxane polymer does not include any segments derived from a lactone) or after

addition of the lactone monomer (i.e., the polysiloxane includes segments derived from a lactone).

[0009] In another embodiment, a method for preparing and using the coating composition comprises adding isocyanate reaction catalyst to a composition comprising polyol, polyisocyanate, and the functionalized polysiloxane polymer to form a coating composition and applying the coating composition to a substrate. The coating composition cures on the substrate to form a polymeric material that may provide for easy fouling release.



### DETAILED DESCRIPTION

[0010] A variety of functionalized polysiloxanes are described herein. The polysiloxanes may be useful in a variety of settings. For example, the functionalized polysiloxanes may be used to provide anti-fouling materials which can be used to prevent microbiological fouling of surfaces in a marine environment. The low surface energy and low modulus make these materials particularly suitable for antifouling/foul release applications as well as other applications. The functionalized polysiloxanes may include a carbamate linking group which links the polysiloxane segment with other functional groups or segments to form oligomers, block copolymers, star branched block copolymers, etc. The functionalized polysiloxane polymers may have the following general formula:



[0011] Referring to the formula above,  $R^1$ ,  $R^2$ ,  $R^3$ ,  $R^4$ ,  $R^{15}$  and  $R^{16}$  may be independently hydrogen,  $C_1$ - $C_{10}$  alkyl,  $C_1$ - $C_{10}$  fluoro-substituted alkyl, cyclopentyl, cyclohexyl, benzyl, tolyl, xylyl and/or phenyl. In one embodiment,  $R^1$ ,  $R^2$ ,  $R^3$ , and  $R^4$  may be methyl and  $R^{15}$  and  $R^{16}$  may be hydrogen.  $L^1$  and  $L^2$  may be linking groups such as linear or branched alkylene having from 2 to 10 carbon atoms, or, desirably, 2 to 6 carbon atoms. In one embodiment  $L^1$  and  $L^2$  may be propylene. It should be appreciated that any of a number of suitable linking groups may be used for  $L^1$  and  $L^2$ .


[0012]  $R^5$  and  $R^6$  may each be a hydroxy-substituted terminal group. In one embodiment,  $R^5$  and  $R^6$  may be a hydroxy-alkyl terminal group. For example,  $R^5$  and  $R^6$  may have the formulas  $HO-R^7-$  and  $-R^8-OH$ , respectively, where  $R^7$  and  $R^8$  are linear and/or branched alkylene (e.g., ethylene). In some embodiments,  $R^7$  and  $R^8$  may be linear and/or branched alkylene which is substituted with one or more hydroxy and/or vinyl groups (where the vinyl group(s) may be substituted with one or more alkyl groups). For example,  $R^5$  and/or  $R^6$  may be a hydroxymethylethylene or vinyl ethylene group. In another embodiment,  $R^5$  and  $R^6$  may have the respective formulas shown below where  $R^7, R^9, R^{11}$ , and  $R^{13}$  may be linear and/or branched alkylene and  $R^8, R^{10}, R^{12}$ , and  $R^{14}$  may be hydrogen or linear and/or branched  $C_1-C_{10}$  alkyl.  $b, e, z$ , and  $u$  may be an integer from 0 to 6 and  $a, d, y$ , and  $t$  may be an integer from 1 to 300.  $m$  and  $n$  may be 0 or 1.



[0013] In one embodiment,  $b, e, z$ , and  $u$  may be 4;  $R^8, R^{10}, R^{12}$ , and  $R^{14}$  may be hydrogen;  $R^7$  and  $R^{11}$  may be  $-(\text{CH}_2)-\text{CH}-$ ;  $R^9$  and  $R^{13}$  are  $-\text{CH}_2-$ ;  $a, d, y$ , and  $t$  may be an integer from 1 to 10; and  $m$  and  $n$  may be 1. Also,  $a, d, y$ , and  $t$  may be 1 to 2.

[0014] In another embodiment, b, e, z, and u may be 4;  $R^8$ ,  $R^{10}$ ,  $R^{12}$ , and  $R^{14}$  may be hydrogen;  $R^7$  and  $R^{11}$  may be  $-(CH_2)_2-$ ; a and y may be an integer from 1 to 10; and m and n may be 0. Also, a and y may be 1 to 2.

[0015] The functionalized polysiloxane polymer may be synthesized by first synthesizing an amino alkyl terminated polysiloxane polymer. A cyclic carbonate such as glycerine carbonate, ethylene carbonate, propylene carbonate, butylenes carbonate, vinyl ethylene carbonate, is added to form a hydroxy alkyl carbamate terminated polysiloxane polymer. A lactone monomer such as  $\epsilon$ -caprolactone is added to form a polysiloxane/poly lactone polymer. A general structural formula for suitable cyclic carbonates that may be used is shown below. In the formula "s" may be 2-4 and  $R^{20}$  may be hydrogen, alkyl, vinyl, alkyl-substituted vinyl, or hydroxy-substituted alkyl.



[0016] The molecular weight of the polymer may be varied to provide a range of physical properties. In one embodiment, the average molecular weight of the polymer is changed by varying the length of the polysiloxane segment (i.e., the value of x in the formula above). In one embodiment, the value of x is such that the polymer has an average molecular weight of about 1,000 to 100,000, desirably, about 10,000 to 75,000, or, suitably, about 20,000 to 50,000.

[0017] The carbamate linked PDMS oligomers and block copolymers may also be incorporated into thermoset siloxane-polyurethane coatings. The coatings may be formed by mixing -an isocyanate functionalized compound, a polyol (e.g., polycaprolactone polyol such as Tone Polyol 0305 available from Dow Chemical), and the hydroxy terminated polysiloxane polymer. Specifically, the polyol, hydroxy terminated polysiloxane, and a pot-lift extender such as 2,4-pentanedione, alkane-2,4-dione, N,N-dialkyl acetoacetamide, and/or alkyl acetoacetate are initially mixed together. The isocyanate functionalized compound and a catalyst such as DBTDAc, dialkyl tin dicarboxylate, trialkyltin hydroxide, dialkyltin oxide, dialkyltin dialkoxide, and/or dialkyltin dihalide, are then combined with

mixture. The coating can then be applied to a surface once the viscosity of the mixture has reached a sufficient level.

**[0018]** Any suitable isocyanate functionalized compound may be used to form the polyurethane coating. Many isocyanate functionalized compounds are available commercially, but their exact composition is protected as a trade secret. Examples of suitable isocyanate functionalized compounds include alkyl diisocyanates and cycloalkyl diisocyanates such as isophorone diisocyanate, 1,6-hexamethylene diisocyanate, methylene dicyclohexyl diisocyanate, xylylene diisocyanate, trans-1,4 cyclohexane diisocyanate, tetramethyl xylylene diisocyanate, isopropenyl dimethylbenzyl diisocyanate, trimethylhexamethylene diisocyanate, 2,2,4-(2,4,4)trimethylhexamethylene diisocyanate, ethylene diisocyanate, 1,4-tetramethylene diisocyanate, 1,12-dodecane diisocyanate, cyclobutane-1,3 diisocyanate, cyclohexane-1,3 diisocyanate, cyclohexane-1,4 diisocyanate, 1-isocyanato-3,3,5-trimethyl-5-isocyanatoatom-ethyl cyclohexane, 2,4-hexahydrotoluene diisocyanate, 2,6-hexahydrotoluene diisocyanate, hexahydro-1,3-phenylene diisocyanate, hexahydro-1,4-phenylene diisocyanate, perhydro-2,4'-diphenylmethane diisocyanate, and norbornane diisocyanate and polyisocyanates such as isophorone diisocyanate trimer (available commercially as Tolonate XIDT-70B, a product of Rhodia PPMC and as Desmodur Z4470, a product of Bayer AG), hexamethylene diisocyanate trimer (available commercially as Tolonate AT, a product of Rhodia PPMC and as Desmodur N3390, a product of Bayer AG), and biurets and allophanates based on the diisocyanates exemplified supra.

**[0019]** Particularly suitable examples of polyisocyanates that may be employed in the present coating compositions include polyisocyanates that have at least three isocyanate groups to facilitate cross linking of the polymeric material. In one embodiment, the polyisocyanate may include an isophorone-based polyisocyanate. In another embodiment, the polyisocyanate may have an isocyanate equivalent weight of about 150 to 600 or, desirably about 250 to 450. The coating compositions may include about 30 wt % to 85 wt.% or, desirably, about 40 wt.% to 75 wt.% polyisocyanate, based on the total solids content of the polymeric material in the coating composition.

**[0020]** A wide variety of polyols may also be used to form the coating. For example, suitable polyols may include polyester polyols, polyether polyols, polycarbonate polyols,

and acrylic polyols. In one embodiment, the polyol may include polyol having at least three hydroxy groups. In another embodiment, the polyol may be a polycaprolactone triol. In certain embodiments, the polyol may have a hydroxy equivalent weight of no more than about 500, or, desirably, no more than about 250. Other examples of suitable polyols include glycerol, alkylene glycols (e.g., ethylene glycol, diethylene glycol, triethylene glycol and neopentylglycol), pentaerythritol, trimethylolethane, trimethylolpropane, sorbitol, cyclohexanediols, inositol, and polyglycerol.

[0021] The coating may have a number of foul release characteristics such as a high water contact angle after being immersed for 30 days (i.e., this is referred to herein as the water contact angle after immersion) and a low release force after water immersion, which indicate that the coating may be useful as a foul release/anti-fouling material. For example, in one embodiment, the coating may have a water contact angle after immersion of at least about 90°, desirably at least about 105°, or suitably, at least about 110°. In another embodiment, the coating may have a release force after water immersion of no more than about 30 N, desirably, no more than about 20 N, or, suitably, no more than about 15 N.

#### Examples

[0022] The following examples are provided to further describe the subject matter disclosed herein. The following examples should not be considered as being limiting in any way.

[0023] **Materials Used in Examples:** Bis(3-aminopropyl)-tetramethyldisiloxane (BAPTMDs) and octamethylcyclotetrasiloxane (D<sub>4</sub>) are obtained from Gelest Inc. 2,4-Pentanedione, ethyl 3-ethoxypropionate (EEP), dibutyltin diacetate (DBTDAc), tin(II)-2-ethylhexanoate, ethylene carbonate (EC) and benzyltrimethylammonium hydroxide (40% solution in methanol) are obtained from Aldrich. Toluene Polyol 0305 (Polycaprolactone (PCL) triol (hydroxyl equiv. wt. 180)) is obtained from Dow Chemical. Tolonate XIDT 70B isocyanate (i.e., isophorone diisocyanate trimer having an isocyanate equivalent weight of 342) is obtained from Rhodia. Methyl n-amyl ketone (MAK) is obtained from Eastman Corp. Caprolactone (CL) is obtained from Solvay Chemicals. Glycerine carbonate (GC) is obtained from Huntsman. All materials are used as received without further purification.

Example 1


[0024] In this example, libraries of carbamate linked PDMS oligomers and block copolymers with polycaprolactone blocks are synthesized.

[0025] Experimental designs for the synthesis of the siloxane libraries are prepared using Library Studio. The designs are shown in Figure 1. In library (a) the siloxane molecular weight is varied from 2500 to 7500 with EC and GC used to form the carbamate link. In libraries (b) and (c) the PDMS molecular weight is varied from 10,000 to 35,000 with the carbamate link derived from EC in library (b) and GC in library (c).


[0026] Synthesis of the functional oligomers and block copolymers is carried out using a Symyx batch reactor system. A robotic pipet dispenses the reagents into individual vials according to the calculated recipe.

[0027] In the first step of the reaction scheme, synthesis of 3-aminopropyl terminated PDMS oligomers is done as follows. Benzyltrimethylammonium hydroxide catalyst (0.1% by solids) is mixed with D<sub>4</sub>. Since benzyltrimethylammonium hydroxide is received in 40% methanol, methanol is removed under vacuum. The synthesis is mainly done by reacting the specified amount of D<sub>4</sub> and BAPTMS in the presence of benzyltrimethylammonium catalyst. The molecular weights of the oligomers are adjusted by changing the ratio of D<sub>4</sub> to BAPTMS. The reaction is run at 80° C for 10 hours. After completion of the reaction, the temperature is increased to 170° C and kept at that temperature for 1 hour to decompose the catalyst.

[0028] To synthesize carbamate linked PDMS oligomers and block copolymers, stoichiometric amounts of EC and GC are added to the vials and the reaction is run at 80° C for 10 hours. Next, the specified amount of caprolactone monomer is added to the vials. 1 drop of tin(II)-2-ethyl hexanoate catalyst in 10% toluene solution is added to the solutions. The reaction is run at 80° C for 10 hours, and then the reaction temperature is increased to 120° C and held for 10 more hours. Schemes 1 & 2 show examples of how to synthesize the polymers described in this example.



**Scheme 1:** Synthesis scheme of carbamate linked tetra functional PDMS oligomers and block copolymers.



**Scheme 2: Synthesis scheme of carbamate linked di functional PDMS oligomers and block copolymers.**

[0029] The formulation data for each compound prepared in the libraries a-c (see Figure 1) are shown in Tables 1-3 below.

Table 1

	Target PDMS Mn	D <sub>4</sub> (mg)	BAPTMDS (mg)	EC (mg)	GC (mg)	CL (mg)
A1	2500	5000.00	497.05	387.26	0.00	0.00
A2	2500	5000.00	497.05	0.00	519.32	0.00
A3	5000	5000.00	248.52	184.87	0.00	0.00
A4	5000	5000.00	248.52	0.00	247.92	0.00
A5	7500	5000.00	165.68	121.30	0.00	0.00
A6	7500	5000.00	165.68	0.00	162.67	0.00
B1	2500	5000.00	497.05	387.26	0.00	937.82
B2	2500	5000.00	497.05	0.00	519.32	1834.48
B3	5000	5000.00	248.52	184.87	0.00	462.95
B4	5000	5000.00	248.52	0.00	247.92	915.27
B5	7500	5000.00	165.68	121.30	0.00	307.24
B6	7500	5000.00	165.68	0.00	162.67	609.72
C1	2500	5000.00	497.05	387.26	0.00	1406.74
C2	2500	5000.00	497.05	0.00	519.32	2751.72
C3	5000	5000.00	248.52	184.87	0.00	694.42
C4	5000	5000.00	248.52	0.00	247.92	1372.91
C5	7500	5000.00	165.68	121.30	0.00	460.87
C6	7500	5000.00	165.68	0.00	162.67	914.58
D1	2500	5000.00	497.05	387.26	0.00	1875.65
D2	2500	5000.00	497.05	0.00	519.32	3668.96
D3	5000	5000.00	248.52	184.87	0.00	925.89
D4	5000	5000.00	248.52	0.00	247.92	1830.55
D5	7500	5000.00	165.68	121.30	0.00	614.49
D6	7500	5000.00	165.68	0.00	162.67	1219.44

\* Coating Libraries 101046, 101047, 101048 and 101049 (see Tables 4 and 5) were formulated using this siloxane library.

Table 2

	Target PDMS Mn	D <sub>4</sub> (mg)	BAPTMDS (mg)	EC (mg)	GC (mg)	CL (mg)
A1	10000	4684.40	116.42	84.55	0.00	0.00
A2	15000	4684.40	77.61	55.91	0.00	0.00
A3	20000	4684.40	58.21	41.76	0.00	0.00
A4	25000	4684.40	46.57	33.33	0.00	0.00
A5	30000	4684.40	38.81	27.73	0.00	0.00
A6	35000	4684.40	33.26	23.74	0.00	0.00
B1	10000	4588.80	114.04	82.83	0.00	219.19
B2	15000	4684.40	77.61	55.91	0.00	144.94
B3	20000	4684.40	58.21	41.76	0.00	108.26
B4	25000	4684.40	46.57	33.33	0.00	86.40
B5	30000	4684.40	38.81	27.73	0.00	71.88
B6	35000	4684.40	33.26	23.74	0.00	61.54
C1	10000	4397.60	109.29	79.38	0.00	322.07
C2	15000	4684.40	77.61	55.91	0.00	217.41
C3	20000	4684.40	58.21	41.76	0.00	162.40
C4	25000	4684.40	46.57	33.33	0.00	129.60
C5	30000	4684.40	38.81	27.73	0.00	107.82
C6	35000	4684.40	33.26	23.74	0.00	92.31
D1	10000	4302.00	106.91	77.65	0.00	411.53
D2	15000	4588.80	76.03	54.77	0.00	289.89
D3	20000	4684.40	58.21	41.76	0.00	216.53
D4	25000	4684.40	46.57	33.33	0.00	172.80
D5	30000	4684.40	38.81	27.73	0.00	143.76
D6	35000	4684.40	33.26	23.74	0.00	123.08

\* Coating Libraries 101107, 101108, 101109 and 101110 (see Tables 4 and 5) were formulated using this siloxane library.

Table 3

	Target PDMS Mn	D <sub>4</sub> (mg)	BAPTMDS (mg)	EC (mg)	GC (mg)	CL (mg)
A1	10000	4684.40	116.42	0.00	113.39	0.00
A2	15000	4684.40	77.61	0.00	74.98	0.00
A3	20000	4684.40	58.21	0.00	56.01	0.00
A4	25000	4684.40	46.57	0.00	44.69	0.00
A5	30000	4684.40	38.81	0.00	37.18	0.00
A6	35000	4684.40	33.26	0.00	31.83	0.00
B1	10000	4302.00	106.91	0.00	104.13	438.37
B2	15000	4493.20	74.44	0.00	71.92	289.89
B3	20000	4636.60	57.62	0.00	55.43	216.53
B4	25000	4684.40	46.57	0.00	44.69	172.80
B5	30000	4684.40	38.81	0.00	37.18	143.76
B6	35000	4684.40	33.26	0.00	31.83	123.08
C1	10000	4015.20	99.79	0.00	97.19	603.88
C2	15000	4397.60	72.86	0.00	70.39	417.08
C3	20000	4541.00	56.43	0.00	54.29	321.48
C4	25000	4636.60	46.09	0.00	44.24	259.20
C5	30000	4684.40	38.81	0.00	37.18	215.64
C6	35000	4684.40	33.26	0.00	31.83	184.62
D1	10000	4015.20	99.79	0.00	97.19	751.50
D2	15000	4302.00	71.28	0.00	68.86	544.28
D3	20000	4397.60	54.65	0.00	52.58	419.80
D4	25000	4541.00	45.14	0.00	43.33	342.07
D5	30000	4636.60	38.41	0.00	36.80	287.52
D6	35000	4684.40	33.26	0.00	31.83	246.16

\* Coating Libraries 101119, 101120, 101121 and 101122 (see Tables 4 and 5) were formulated using this siloxane library.

### Example 2

[0030] In this example, the libraries of carbamate linked PDMS oligomers and block copolymers with polycaprolactone blocks synthesized according to Example 1 are incorporated into thermoset siloxane-polyurethane coatings. The effect of polycaprolactone blocks, percent load of oligomers and molecular weight of the PDMS on the properties of these coatings is evaluated.

[0031] Coating formulations are composed of a siloxane from the library prepared as described in Example 1, Tone Polyol 0305 (polyol), 2,4-pentanedione, DBTDAc catalyst and Tolonate XIDT 70B (isocyanate crosslinker). Stock solutions of 30% siloxane polymer

(based on the total solids content of the coating composition) from the Ex. 1 library in EEP and Tone polyol in 10% MAK are prepared. A 1% solution of the catalyst DBTDAc is prepared in MAK.

[0032] Coating formulations are prepared by adding 10%, 20%, 30% and 40% by weight of siloxane from the library (wt.% of the total of the siloxane, polyol, and polyisocyanate, i.e., wt.% of the total solids content) into the formulations. Since each polymer is included at four different inclusion levels, a total of 288 coatings are formulated. The amount of catalyst DBTDAc is adjusted to 0.075% by solids for all coating formulations. The stoichiometric ratio of isocyanate to hydroxyl functional groups is kept as 1.1:1.0. To all formulations 10% by solids 2,4-pentanedione (pot life extender) is added.

[0033] Using an automated formulation system, the siloxane library, polyol, and 2,4-pentanedione are added to the vials first and mixed overnight. After overnight mixing isocyanate crosslinker and catalyst are added to the vials and continued mixing until sufficient viscosity is obtained for coating application.

[0034] The coating application is carried out using an automated coating application system. The formulations are applied in array format to 4" by 8" aluminum panels. After the application, the panels are left at room temperature for curing overnight. The panels are then placed into the oven for complete curing for 45 minutes at 80° C.

[0035] The surface energy and pseudo-barnacle pull-off adhesion is determined for each coating. Contact angles of water and methylene iodide are determined using an automated surface energy system and used to determine the surface energy with Owens-Wendt method. Coating surface energies are measured initially and after 30 days of water immersion. To determine the adhesive strength of epoxy to a coating surface (pseudo-barnacle adhesion) a Symyx automated pull-off adhesion system is used. Pull-off adhesion of the coatings is measured initially and after 30 days of water immersion.

[0036] The coatings were uniform and stable before and after water immersion. All of the coatings showed at least some hydrophobic properties. The results of the tests are shown in Figures 2-4 below. The coating formulations and numerical results of the tests are shown in Figure 4.


[0037] As shown in Fig. 2, the water contact angle (WCA) data following immersion indicates that most of the coatings remain hydrophobic ( $WCA > 90$ ), which means that PDMS predominates on the surface and that the coatings are stable. WCA change following water immersion is generally within  $\pm 5^\circ$ . Generally, WCA of the coatings increases as the number average molecular weight of the PDMS oligomers increases. Also, generally speaking, increasing the number of caprolactone blocks decreases the WCAs.

[0038] As shown in Figure 2, the coatings having the highest WCAs are achieved with the polymers which have no caprolactone units. As shown in Figure 3, the initial average force at release for the coatings showed a slight increase between carbamate linked functional oligomers and block copolymers.

[0039] As shown in Figure 4, the average force at release measured after water immersion decreases most of the time. Average force at release of carbamate linked PDMS block copolymers decreases more than the average force at release of carbamate linked PDMS oligomers.

### Example 3

[0040] In this example, the coatings prepared in Example 2 are compared to a number of coatings using conventional polymers prepared as shown in Scheme 3 below. The molecular weight of the PDMS and the number of caprolactone units per end group are varied to form 48 conventional polymers. Each of the 48 conventional polymers is used at four different inclusion levels (10 %, 20 %, 30 %, and 40 % based on the total solids content of the coating composition) to form 192 coatings in a manner similar to that described in Example 2.



Scheme 3

[0041] The initial WCA for the coatings using the conventional polymers is measured and compared to the initial WCA from the coatings prepared in Example 2. Figure 5 shows a plot of the results of these measurements. The leftmost column shows the results of the coatings prepared using conventional polymers and the other two columns show the results of the coatings prepared using carbamate linkages (i.e., middle column shows the results of coatings using ethylene carbonate derived carbamate linkages and the rightmost column shows the results for coatings using glycerine carbonate derived carbamate linkages). As shown in Figure 5, the use of a carbamate linkage results in coatings which are more reliably hydrophobic, which is a potential indication of usefulness as an anti-fouling material. The use of the carbamate linkage results in better control of the surface properties of the resulting polyurethane coatings. It should be noted that the color of each data point in Figures 5 and 6 represent the number of caprolactones per hydroxyl as shown in the legend.

[0042] Figure 6 shows a plot of the results of only those coatings (coatings using conventional polymers and coatings using polymers from Example 2) that did not have any caprolactone units. As shown in Figure 6, the difference between the coatings prepared using carbamate linkages and the coating prepared using conventional polymers is even more pronounced.

#### Example 4

[0043] Illustrative Coating Formulation Example. Coating formulations are prepared from the siloxane polymer or block copolymer, a polycaprolactone triol (Tone Polyol 0305) and a polyisocyanate crosslinker. The ratio of isocyanate groups to hydroxyl groups is held


constant at 1.1:1.0. A catalyst, dibutyl tin diacetate (DBTDAc), is used at a level of 0.075 wt.% based on total solid resin components. A pot life extender, 2,4-pentanedione, is also used to prevent premature gelation at a level of 10% (based on total solid resin components). Stock solutions of each of the resin components in solvent are prepared for ease of delivery using automated robotic pipets.

**[0044]** To prepare a polyurethane coating formulation containing 20% PDMS caprolactone triblock copolymer (B1-101108; see Tables 2, 4 and 5), using an automated formulation system, 695.17  $\mu$ l siloxane polymer solution (30% in EEP, 200.00 mg siloxane), 276.03  $\mu$ l Tone Polyol 0305 (90% in MAK, 254.14 mg polyol), and 104.49  $\mu$ l 2,4-pentanedione were dispensed to the vials. After overnight mixing, 735.66  $\mu$ l XIDT 70B isocyanate crosslinker (70% in BuAc, 545.86 mg isocyanate resin) and 92.02  $\mu$ l catalyst DBTDAc (1% in MAK, 0.75 mg catalyst) were added to the vials and continued mixing until sufficient viscosity was obtained for coating application.

#### Illustrative Embodiments

**[0045]** The present polymer and coatings are further illustrated by the embodiments described below, which are not intended to limit the scope of the present invention.

**[0046]** One embodiment provides a polymer including at least one subunit derived from a polysiloxane terminated with one or more hydroxy functional carbamate groups. For example, the polymer may be formed by cross-linking a polymer having the formula:



wherein x is such that the polymer has a molecular weight of about 1,000 to 100,000; e.g., with an isocyanate compound, optionally in the presence of a polyol. Quite commonly, the isocyanate functional compound comprises a polyisocyanate compound, such as a polyisocyanate compound which includes at least 3 isocyanate groups. The polyol compound suitably has a hydroxy equivalent weight of no more than about 500 and, very often, the polyol compound may have a hydroxy equivalent weight of no more than about 250.

[0047] In other embodiments, the hydroxy functional carbamate terminated polysiloxane may be reacted with a lactone, such as caprolactone.

[0048] The carbamate terminated polysiloxane may suitably be a polymer in which  $R^1$ ,  $R^2$ ,  $R^3$ , and  $R^4$  may independently be hydrogen,  $C_1$ – $C_{10}$  alkyl,  $C_1$ – $C_{10}$  fluoro-substituted alkyl, cyclopentyl, cyclohexyl, benzyl, toluyl, xylyl and/or phenyl;

$R^5$  and  $R^6$  are linking groups;

$R^{15}$  and  $R^{16}$  are independently hydrogen,  $C_1$ – $C_{10}$  alkyl, cyclopentyl, cyclohexyl, benzyl, toluyl, xylyl or phenyl; and

$L^1$  and  $L^2$  are linking groups.

[0049] The polymer may suitably have  $x$  such that the polymer has a molecular weight of about 10,000 to 75,000 and, in some instances, a molecular weight of about 20,000 to 50,000.

[0050] In such embodiments,  $R^5$  and  $R^6$  are independently linear and/or branched alkylene; linear and/or branched hydroxy-substituted alkylene; linear and/or branched vinyl-substituted alkylene; or a combination thereof. In such embodiments,  $R^5$  and  $R^6$  may have from 2 to 10 carbon atoms and are commonly independently selected from  $C_2$ – $C_4$  alkylene and/or  $C_2$ – $C_4$  hydroxysubstituted alkylene. For example,  $R^5$  and  $R^6$  may be independently ethylene, propylene and/or hydroxypropylene (e.g., 2-hydroxymethylethylene).

[0051] Quite commonly,  $L^1$  and  $L^2$  are independently linear or branched alkylene; preferably having from 2 to 10 carbon atoms, e.g.,  $L^1$  and  $L^2$  may independently be  $C_2$ – $C_6$  alkylene, such as an ethylene and/or propylene linker.


[0052] In one exemplary embodiment,  $R^1$ ,  $R^2$ ,  $R^3$ , and  $R^4$  are methyl; and  $R^{15}$  and  $R^{16}$  are hydrogen. In such a polymer,  $R^5$  and  $R^6$  may suitably be ethylene. In another exemplary embodiment,  $R^1$ ,  $R^2$ ,  $R^3$ , and  $R^4$  are methyl;  $R^5$  and  $R^6$  are ethylene;  $L^1$  and  $L^2$  are propylene; and  $R^{15}$  and  $R^{16}$  are hydrogen. In yet another,  $R^1$ ,  $R^2$ ,  $R^3$ , and  $R^4$  are methyl;  $R^5$  and  $R^6$  are hydroxymethylethylene;  $L^1$  and  $L^2$  are propylene; and  $R^{15}$  and  $R^{16}$  are hydrogen.

[0053] In one embodiment, the polymer may include one or more subunits derived from a polysiloxane terminated with a hydroxyalkyl functional carbamate group. In others, the polymer may contain one or more subunits derived from a polysiloxane terminated with a

hydroxy alkyl functional carbamate group. Such polymers may be formed by crosslinking the hydroxy functional polysiloxane using an isocyanate functional compound. The polymer may include a polyester subunit(s) and/or a polyurethane subunit(s).

[0054] The functionalized polysiloxanes described herein may be used to form coatings. Such coatings may have a water contact angle after immersion (e.g., in water for 30 days) of at least about 90°, desirably at least about 100°; and in some instances at least about 105°; more preferably at least about 110°. Such coatings may have a release force after water immersion for 30 days of no more than about 30 N; preferably no more than about 20 N; and, more preferably, no more than about 15 N.

[0055] One specific embodiment provides a polymer having the formula:



wherein x is such that the polymer has a molecular weight of about 1,000 to 100,000;

$R^1$ ,  $R^2$ ,  $R^3$ , and  $R^4$  are independently hydrogen,  $C_1$ - $C_{10}$  alkyl,  $C_1$ - $C_{10}$  fluoro-substituted alkyl, cyclopentyl, cyclohexyl, benzyl, tolyl, xylyl and/or phenyl;

$R^5$  and  $R^6$  are independently a hydroxy-substituted terminal group;


$R^{15}$  and  $R^{16}$  are independently hydrogen,  $C_1$ - $C_{10}$  alkyl, cyclopentyl, cyclohexyl, benzyl, tolyl, xylyl and/or phenyl; and

$L^1$  and  $L^2$  are linking groups.


[0056] In such a polymer x is suitably such that the polymer has a molecular weight of about 10,000 to 75,000 and, more desirably, a molecular weight of about 20,000 to 50,000.

$L^1$  and  $L^2$  are independently linear or branched alkylene, such as  $C_2$ - $C_6$  alkylene.

$R^5$  may suitably have the formula




and  $R^6$  the formula




wherein  $R^7$  and  $R^8$  are independently linear and/or branched alkylene; linear and/or branched hydroxy-substituted alkylene; linear and/or branched vinyl-substituted alkylene; or a combination thereof.

[0057] In other embodiments,  $R^5$  may have the formula



and  $R^6$  the formula



wherein  $R^7$ ,  $R^9$ ,  $R^{11}$ , and  $R^{13}$  are independently linear and/or branched alkylene;

$R^8$ ,  $R^{10}$ ,  $R^{12}$ , and  $R^{14}$  are independently hydrogen or linear and/or branched  $C_1$ - $C_{10}$  alkyl;

$b$ ,  $e$ ,  $z$ , and  $u$  are independently an integer from 0 to 6;

$a$ ,  $d$ ,  $y$ , and  $t$  are independently an integer from 1 to 300; and

$m$  and  $n$  are independently 0 or 1.

[0058] For example,  $b$ ,  $e$ ,  $z$ , and  $u$  may be 4; where  $R^8$ ,  $R^{10}$ ,  $R^{12}$ , and  $R^{14}$  are hydrogen;  $R^7$  and  $R^{11}$  are  $-(\text{CH}_2)-\text{CH}-$ ;  $R^9$  and  $R^{13}$  are  $-\text{CH}_2-$ ;  $a$ ,  $d$ ,  $y$ , and  $t$  are independently an integer from 1 to 10; and  $m$  and  $n$  are 1. Suitably,  $a$ ,  $d$ ,  $y$ , and  $t$  may independently be 1 to 2.

[0059] For instance, b, e, z, and u may be 4;  $R^8$ ,  $R^{10}$ ,  $R^{12}$ , and  $R^{14}$  are hydrogen;  $R^7$  and  $R^{11}$  are  $-(CH_2)_2-$ ; a and y are independently an integer from 1 to 10; and m and n are 0. For example, a and y may independently be 1 or 2.

[0060] The cross-linked polysiloxanes described herein may be formed via reaction with an isocyanate functional compound which comprises isophorone diisocyanate based polyisocyanate and/or a hexane diisocyanate based polyisocyanate. For example, the isophorone diisocyanate-based polyisocyanate may be isophorone diisocyanate-based polyisocyanate having an isocyanate equivalent weight of about 200 to 500. The diisocyanate-based polyisocyanate may be a hexane diisocyanate-based polyisocyanate having an isocyanate equivalent weight of about 150 to 300.

[0061] In other embodiments, the isocyanate functional compound may comprise hexamethylene diisocyanate, isophorone diisocyanate, diphenylmethane diisocyanate and/or toluene diisocyanate.

[0062] Coating compositions which include the functionalized polysiloxanes described herein may commonly also include a solvent component. The coating compositions may also include a polyol, e.g., a polyol which has at least 3 hydroxy groups. The present coating compositions may include about 5 to 50 wt.% on a total solids basis of the polymer described above. Such coating compositions may be used to form a polymeric coating, e.g., by applying the described coating compositions on at least one surface of an article; and removing solvent component from the coated surface.

[0063] Other embodiments provide a polysiloxane terminated with hydroxyalkyl carbamate groups, such as a polysiloxane wherein the hydroxyalkyl carbamate groups include dihydroxy branched alkyl carbamate groups. The hydroxyalkyl carbamate groups may include vinyl substituted hydroxyalkyl carbamate groups.

[0064] The polysiloxanes described herein may suitably have a molecular weight ( $M_n$ ) of about 10,000 to 75,000. Such polysiloxanes may include a polydimethyl siloxane terminated with hydroxyalkyl carbamate groups, wherein the hydroxyalkyl carbamate groups include hydroxyethyl carbamate groups, hydroxypropyl carbamate groups and/or dihydroxypropyl carbamate groups.

[0065] The terms recited in the claims should be given their ordinary and customary meaning as determined by reference to relevant entries (e.g., definition of “plane” as a carpenter’s tool would not be relevant to the use of the term “plane” when used to refer to an airplane, etc.) in dictionaries (e.g., common use and/or technical dictionaries), commonly understood meanings by those in the art, etc., with the understanding that the broadest meaning imparted by any one or combination of these sources should be given to the claim terms (e.g., two or more relevant dictionary entries should be combined to provide the broadest meaning of the combination of entries, etc.) subject only to the following exceptions: (a) if a term is used herein in a manner more expansive than its ordinary and customary meaning, the term should be given its ordinary and customary meaning plus the additional expansive meaning, or (b) if a term has been explicitly defined to have a different meaning by reciting the term followed by the phrase “as used herein shall mean” or similar language (e.g., “herein this term means,” “as defined herein,” “for the purposes of this disclosure [the term] shall mean,” etc.). References to specific examples, use of “i.e.,” use of the word “invention,” etc., are not meant to invoke exception (b) or otherwise restrict the scope of the recited claim terms. Accordingly, the subject matter recited in the claims is not coextensive with and should not be interpreted to be coextensive with any particular embodiment, feature, or combination of features other than those explicitly recited in the claims, even if only a single embodiment of the particular feature or combination of features is illustrated and described herein. Thus, the appended claims should be read to be given their broadest interpretation in view of the prior art and the ordinary meaning of the claim terms.

[0066] As used herein, spatial or directional terms, such as “left,” “right,” “front,” “back,” and the like, relate to the subject matter as it is shown in the drawing FIGS. However, it is to be understood that the subject matter described herein may assume various alternative orientations and, accordingly, such terms are not to be considered as limiting. Furthermore, as used herein (i.e., in the claims and the specification), articles such as “the,” “a,” and “an” can connote the singular or plural. Also, as used herein, the word “or” when used without a preceding “either” (or other similar language indicating that “or” is unequivocally meant to be exclusive – e.g., only one of x or y, etc.) shall be interpreted to be inclusive (e.g., “x or y” means one or both x or y). Likewise, as used herein, the term “and/or” shall also be interpreted to be inclusive (e.g., “x and/or y” means one or both x or y). In situations where “and/or” or “or” are used as a conjunction for a group of three or more items, the group

should be interpreted to include one item alone, all of the items together, or any combination or number of the items. Moreover, terms used in the specification and claims such as have, having, include, and including should be construed to be synonymous with the terms comprise and comprising.

[0067] Unless otherwise indicated, all numbers or expressions, such as those expressing dimensions, physical characteristics, etc. used in the specification are understood as modified in all instances by the term "about." At the very least, and not as an attempt to limit the application of the doctrine of equivalents to the claims, each numerical parameter recited in the specification or claims which is modified by the term "about" should at least be construed in light of the number of recited significant digits and by applying ordinary rounding techniques. Moreover, all ranges disclosed herein are to be understood to encompass any and all subranges subsumed therein. For example, a stated range of 1 to 10 should be considered to include any and all subranges between and inclusive of the minimum value of 1 and the maximum value of 10; that is, all subranges beginning with a minimum value of 1 or more and ending with a maximum value of 10 or less (e.g., 5.5 to 10).

**Table 4**

Coating ID	Target PDMS Mn (g/mole)	% Oligomer added	% actual PDMS added	EC=0; GC=1	Number of Caprolactone per Hydroxyl	Initial Water Contact Angle (deg)	Initial Average Force at Release (N)	Water Contact Angle after water immersion (deg)	Average Force at Release after water immersion (N)	Change in Water Contact Angle (deg)	Change in Force at Release (N)
A1-101046	2500	10	9.3	0	0	93.4	16.2	93.2	12.9	-0.2	-3.3
A2-101046	2500	10	9.1	1	0	97.5	14.8	97.5	22.4	0.0	
A3-101046	5000	10	9.7	0	0	97.1	13.7	96.5	17.5	-0.6	3.8
A4-101046	5000	10	9.5	1	0	98.1	18.2	97.0	20.7	-1.1	2.5
A5-101046	7500	10	9.8	0	0	97.9	20.8	96.0	13.6	-1.9	-7.1
A6-101046	7500	10	9.7	1	0	98.6	16.1	98.5	20.0	-0.1	3.9
B1-101046	2500	10	8.0	0	2	97.4	15.2	90.5	12.9	-6.9	-2.3
B2-101046	2500	10	6.9	1	2	98.2	14.6	91.4	9.9	-6.8	-4.8
B3-101046	5000	10	8.9	0	2	98.3	11.5	96.7	10.6	-1.6	-0.9
B4-101046	5000	10	8.1	1	2	98.1	12.1	96.0	17.1	-2.1	4.9
B5-101046	7500	10	9.2	0	2	97.2	14.5	96.8	13.5	-0.4	-1.0
B6-101046	7500	10	8.7	1	2	97.0	15.9	95.0	9.4	-2.0	-6.6
C1-101046	2500	10	7.4	0	3	98.3	13.0	88.8	13.6	-9.5	0.7
C2-101046	2500	10	6.1	1	3	98.3	17.9	82.3	12.0	16.0	-5.9
C3-101046	5000	10	8.5	0	3	96.9	17.4	95.5	11.0	-1.4	-6.5
C4-101046	5000	10	7.6	1	3	98.4	9.1	96.0	10.1	-2.4	1.0
C5-101046	7500	10	9.0	0	3	98.3	16.4	95.7	17.0	-2.6	0.6
C6-101046	7500	10	8.2	1	3	97.4	8.7	95.0	15.7	-2.4	7.0
D1-101046	2500	10	7.0	0	4	97.1	17.9	-	19.3	-	1.4
D2-101046	2500	10	5.5	1	4	98.2	14.9	87.7	11.3	10.5	-3.7
D3-101046	5000	10	8.2	0	4	97.6	18.7	93.5	9.0	-4.1	-9.7
D4-101046	5000	10	7.1	1	4	100.7	13.0	95.6	14.3	-5.1	1.3
D5-101046	7500	10	8.7	0	4	97.8	13.5	94.5	9.3	-3.3	-4.3
D6-101046	7500	10	7.8	1	4	97.7	19.7	97.9	12.2	0.2	-7.5
A1-101047	2500	20	18.7	0	0	94.6	20.7	95.0	19.8	0.4	-0.8
A2-101047	2500	20	18.3	1	0	99.4	24.0	99.2	21.2	-0.2	-2.8
A3-101047	5000	20	19.3	0	0	100.0	22.3	99.6	24.6	-0.4	2.3
A4-101047	5000	20	19.1	1	0	100.1	18.7	99.7	21.3	-0.4	2.6
A5-101047	7500	20	19.5	0	0	100.6	24.3	99.3	27.2	-1.3	2.9

Coating ID	Target PDMS Mn (g/mole)	% Oligomer added	% actual PDMS added	EC=0; GC=1	Number of Caprolactone per Hydroxyl	Initial Water Contact Angle (deg)	Initial Average Force at Release (N)	Water Contact Angle after water immersion (deg)	Average Force at Release after water immersion (N)	Change in Water Contact Angle (deg)	Change in Force at Release (N)
A6-101047	7500	20	19.4	1	0	100.4	20.9	100.7	23.4	0.3	2.5
B1-101047	2500	20	16.0	0	2	98.4	10.5	93.6	16.8	-4.8	6.3
B2-101047	2500	20	13.7	1	2	99.0	15.3	93.6	15.3	-5.4	-0.1
B3-101047	5000	20	17.8	0	2	100.4	28.3	97.5	20.1	-2.9	-8.2
B4-101047	5000	20	16.3	1	2	100.0	15.9	97.7	17.1	-2.3	1.3
B5-101047	7500	20	18.4	0	2	99.8	23.7	99.3	25.1	-0.5	1.4
B6-101047	7500	20	17.3	1	2	98.7	20.1	97.3	27.0	-1.4	6.9
C1-101047	2500	20	14.9	0	3	98.5	17.3	92.2	19.7	-6.3	2.3
C2-101047	2500	20	12.2	1	3	97.6	18.5	94.6	15.2	-3.0	-3.3
C3-101047	5000	20	17.1	0	3	98.6	22.5	96.1	19.0	-2.5	-3.4
C4-101047	5000	20	15.1	1	3	99.3	11.9	99.0	10.9	-0.3	-1.0
C5-101047	7500	20	17.9	0	3	99.6	16.2	97.1	9.1	-2.5	-7.1
C6-101047	7500	20	16.5	1	3	98.2	23.9	97.2	20.7	-1.0	-3.2
D1-101047	2500	20	13.9	0	4	97.4	24.3	97.8	17.9	0.4	-6.4
D2-101047	2500	20	11.0	1	4	99.6	22.5	96.1	13.9	-3.5	-8.7
D3-101047	5000	20	16.4	0	4	98.4	16.8	97.2	12.3	-1.2	-4.5
D4-101047	5000	20	14.2	1	4	97.2	18.5	100.4	14.4	3.2	-4.1
D5-101047	7500	20	17.5	0	4	98.4	12.5	101.1	12.0	2.7	-0.5
D6-101047	7500	20	15.7	1	4	80.8	21.5	101.7	22.1	20.9	0.7
A1-101048	2500	30	28.0	0	0	95.9	18.3	96.1	22.9	0.2	4.6
A2-101048	2500	30	27.4	1	0	100.5	17.4	98.0	20.1	-2.5	2.7
A3-101048	5000	30	29.0	0	0	100.3	23.6	97.7	31.0	-2.6	7.4
A4-101048	5000	30	28.6	1	0	101.4	19.9	99.9	24.9	-1.5	5.1
A5-101048	7500	30	29.3	0	0	101.2	27.5	99.6	29.7	-1.6	2.2
A6-101048	7500	30	29.1	1	0	102.4	27.2	100.5	20.6	-1.9	-6.7
B1-101048	2500	30	23.9	0	2	99.3	12.5	90.8	19.1	-8.5	6.5
B2-101048	2500	30	20.6	1	2	98.5	16.6	92.2	11.9	-6.3	-4.7
B3-101048	5000	30	26.6	0	2	101.7	29.9	98.7	24.6	-3.0	-5.3
B4-101048	5000	30	24.4	1	2	100.9	18.9	99.1	20.0	-1.8	1.1
B5-101048	7500	30	27.7	0	2	101.6	22.3	99.5	32.4	-2.1	10.1
B6-101048	7500	30	26.0	1	2	100.9	29.1	99.8	25.3	-1.1	-3.9

Coating ID	Target PDMS Mn (g/mole)	% Oligomer added	% actual PDMS added	EC=0; GC=1	Number of Caprolactone per Hydroxyl	Initial Water Contact Angle (deg)	Initial Average Force at Release (N)	Water Contact Angle after water immersion (deg)	Average Force at Release after water immersion (N)	Change in Water Contact Angle (deg)	Change in Force at Release (N)
C1-101048	2500	30	22.3	0	3	99.1	14.2	92.2	20.8	-6.9	6.6
C2-101048	2500	30	18.3	1	3	98.4	19.4	93.9	9.7	-4.5	-9.8
C3-101048	5000	30	25.6	0	3	98.9	25.3	97.4	20.5	-1.5	-4.8
C4-101048	5000	30	22.7	1	3	98.9	16.5	97.3	18.3	-1.6	1.9
C5-101048	7500	30	26.9	0	3	100.3	15.7	98.2	13.7	-2.1	-2.0
C6-101048	7500	30	24.7	1	3	98.2	21.8	97.9	18.6	-0.3	-3.2
D1-101048	2500	30	20.9	0	4	97.9	22.7	90.7	23.1	-7.2	0.4
D2-101048	2500	30	16.4	1	4	98.2	22.5	89.5	16.9	-8.7	-5.6
D3-101048	5000	30	24.6	0	4	97.2	19.6	96.0	24.3	-1.2	4.7
D4-101048	5000	30	21.2	1	4	98.3	11.1	95.6	15.7	-2.7	4.6
D5-101048	7500	30	26.2	0	4	99.9	11.8	98.1	20.2	-1.8	8.4
D6-101048	7500	30	23.5	1	4	98.9	18.1	97.4	15.0	-1.5	-3.1
A1-101049	2500	40	37.4	0	0	97.8	24.4	96.5	23.0	-1.3	-1.4
A2-101049	2500	40	36.5	1	0	100.9	24.3	99.8	19.9	-1.1	-4.4
A3-101049	5000	40	38.6	0	0	102.5	31.2	101.5	41.9	-1.0	10.7
A4-101049	5000	40	38.2	1	0	101.2	19.6	99.9	25.0	-1.3	5.4
A5-101049	7500	40	39.1	0	0	99.7	25.3	101.2	43.8	1.5	18.4
A6-101049	7500	40	38.8	1	0	102.7	28.4	103.0	30.6	0.3	2.2
B1-101049	2500	40	31.9	0	2	97.2	30.2	91.1	28.0	-6.1	-2.2
B2-101049	2500	40	27.4	1	2	98.0	21.6	97.2	20.1	-0.8	-1.6
B3-101049	5000	40	35.5	0	2	103.8	23.6	102.3	30.8	-1.5	7.2
B4-101049	5000	40	32.5	1	2	100.8	21.4	100.4	27.0	-0.4	5.6
B5-101049	7500	40	36.9	0	2	102.4	24.1	103.4	46.0	1.0	21.9
B6-101049	7500	40	34.7	1	2	103.8	23.1	105.4	23.8	1.6	0.6
C1-101049	2500	40	29.8	0	3	99.7	26.8	93.2	33.6	-6.5	6.9
C2-101049	2500	40	24.4	1	3	99.4	20.3	95.7	9.0	-3.7	-11.3
C3-101049	5000	40	34.1	0	3	103.2	32.0	101.5	38.0	-1.7	6.0
C4-101049	5000	40	30.3	1	3	100.4	19.6	100.2	32.4	-0.2	12.8
C5-101049	7500	40	35.9	0	3	101.4	32.7	102.4	30.8	1.0	-1.9
C6-101049	7500	40	32.9	1	3	101.5	25.6	105.2	39.1	3.7	13.5
D1-101049	2500	40	27.9	0	4	94.5	24.2	93.9	31.4	-0.6	7.2

Coating ID	Target PDMS Mn (g/mole)	% Oligomer added	% actual PDMS added	EC=0; GC=1	Number of Caprolactone per Hydroxyl	Initial Water Contact Angle (deg)	Initial Average Force at Release (N)	Water Contact Angle after water immersion (deg)	Average Force at Release after water immersion (N)	Change in Water Contact Angle (deg)	Change in Force at Release (N)
D2-101049	2500	40	21.9	1	4	97.1	19.4	91.6	20.7	-5.5	1.3
D3-101049	5000	40	32.8	0	4	99.8	39.1	97.5	26.6	-2.3	-12.5
D4-101049	5000	40	28.3	1	4	101.0	31.2	96.3	35.1	-4.7	3.9
D5-101049	7500	40	34.9	0	4	99.7	25.7	100.5	28.4	0.8	2.7
D6-101049	7500	40	31.4	1	4	100.5	-	96.4	26.8	-4.1	-
A1-101107	10000	10	9.8	0	0	98.6	11.1	100.0	20.1	1.4	9.0
A2-101107	15000	10	9.9	0	0	99.2	9.8	-	-	-	-
A3-101107	20000	10	9.9	0	0	95.7	9.8	-	-	-	-
A4-101107	25000	10	9.9	0	0	104.7	10.8	101.4	8.9	-3.3	-1.9
A5-101107	30000	10	9.9	0	0	107.6	9.2	-	-	-	-
A6-101107	35000	10	9.9	0	0	107.1	9.0	-	-	-	-
B1-101107	10000	10	9.4	0	2	103.8	19.5	102.5	11.9	-1.3	-7.6
B2-101107	15000	10	9.6	0	2	107.7	17.3	-	-	-	-
B3-101107	20000	10	9.7	0	2	109.1	20.8	-	-	-	-
B4-101107	25000	10	9.8	0	2	109.0	17.9	108.5	14.9	-0.5	-3.0
B5-101107	30000	10	9.8	0	2	109.8	22.7	109.2	13.8	-0.6	-9.0
B6-101107	35000	10	9.8	0	2	108.9	21.0	-	-	-	-
C1-101107	10000	10	9.2	0	3	99.9	10.3	99.1	11.9	-0.8	1.5
C2-101107	15000	10	9.5	0	3	106.8	22.3	103.1	16.2	-3.7	-6.1
C3-101107	20000	10	9.6	0	3	108.4	22.4	-	-	-	-
C4-101107	25000	10	9.7	0	3	109.1	23.5	107.3	19.6	-1.8	-3.8
C5-101107	30000	10	9.7	0	3	108.7	20.0	106.5	17.5	-2.2	-2.5
C6-101107	35000	10	9.8	0	3	107.8	31.7	-	-	-	-
D1-101107	10000	10	9.0	0	4	99.7	17.8	97.7	13.1	-2.0	-4.7
D2-101107	15000	10	9.3	0	4	104.5	23.2	101.3	21.2	-3.2	-2.0
D3-101107	20000	10	9.5	0	4	106.3	22.4	-	-	-	-
D4-101107	25000	10	9.6	0	4	107.1	35.5	-	-	-	-
D5-101107	30000	10	9.6	0	4	105.6	26.1	-	-	-	-
D6-101107	35000	10	9.7	0	4	106.1	25.8	-	-	-	-
A1-101108	10000	20	19.7	0	0	98.2	9.5	101.1	12.1	2.9	2.6
A2-101108	15000	20	19.8	0	0	102.9	9.4	102.3	8.9	-0.6	-0.5

Coating ID	Target PDMS Mn (g/mole)	% Oligomer added	% actual PDMS added	EC=0; GC=1	Number of Caprolactone per Hydroxyl	Initial Water Contact Angle (deg)	Initial Average Force at Release (N)	Water Contact Angle after water immersion (deg)	Average Force at Release after water immersion (N)	Change in Water Contact Angle (deg)	Change in Force at Release (N)
A3-101108	20000	20	19.8	0	0	94.8	9.5	96.6	8.6	1.8	-0.9
A4-101108	25000	20	19.9	0	0	103.5	10.1	103.5	8.5	0.0	-1.5
A5-101108	30000	20	19.9	0	0	107.2	8.9	106.5	8.7	-0.7	-0.2
A6-101108	35000	20	19.9	0	0	104.1	8.8	105.7	8.6	1.6	-0.2
B1-101108	10000	20	18.8	0	2	100.4	22.9	101.2	18.5	0.8	-4.4
B2-101108	15000	20	19.2	0	2	106.2	24.6	103.9	18.7	-2.3	-5.9
B3-101108	20000	20	19.4	0	2	109.3	31.3	106.0	12.2	-3.3	-19.1
B4-101108	25000	20	19.5	0	2	108.4	21.2	107.9	17.4	-0.5	-3.8
B5-101108	30000	20	19.6	0	2	108.4	25.2	108.8	19.1	0.4	-6.1
B6-101108	35000	20	19.6	0	2	106.9	28.6	108.7	10.1	1.8	-18.5
C1-101108	10000	20	18.4	0	3	98.4	25.4	95.8	13.8	-2.6	-11.6
C2-101108	15000	20	18.9	0	3	105.2	25.3	102.9	19.6	-2.3	-5.7
C3-101108	20000	20	19.2	0	3	107.5	29.6	105.8	23.0	-1.7	-6.6
C4-101108	25000	20	19.3	0	3	108.6	21.6	108.0	17.8	-0.6	-3.8
C5-101108	30000	20	19.4	0	3	107.9	22.1	107.9	17.2	0.0	-4.9
C6-101108	35000	20	19.5	0	3	107.7	24.7	107.6	14.1	-0.1	-10.6
D1-101108	10000	20	18.0	0	4	98.1	12.6	101.3	12.9	3.2	0.3
D2-101108	15000	20	18.6	0	4	103.3	20.0	103.1	19.4	-0.2	-0.6
D3-101108	20000	20	19.0	0	4	105.3	23.5	103.0	25.7	-2.3	2.3
D4-101108	25000	20	19.2	0	4	105.9	22.6	105.5	14.5	-0.4	-8.2
D5-101108	30000	20	19.3	0	4	106.5	20.8	105.3	21.2	-1.2	0.4
D6-101108	35000	20	19.4	0	4	106.8	35.7	106.4	19.5	-0.4	-16.3
A1-101109	10000	30	29.5	0	0	103.1	11.7	103.2	15.0	0.1	3.4
A2-101109	15000	30	29.7	0	0	107.2	15.1	104.3	13.9	-2.9	-1.1
A3-101109	20000	30	29.7	0	0	109.6	10.2	108.0	10.4	-1.6	0.2
A4-101109	25000	30	29.8	0	0	108.3	16.7	106.8	14.8	-1.5	-1.9
A5-101109	30000	30	29.8	0	0	109.6	10.9	108.5	9.2	-1.1	-1.7
A6-101109	35000	30	29.8	0	0	109.4	9.9	107.4	8.7	-2.0	-1.1
B1-101109	10000	30	28.2	0	2	102.9	23.5	101.3	19.3	-1.6	-4.3
B2-101109	15000	30	28.8	0	2	107.6	28.9	102.8	25.9	-4.8	-3.0
B3-101109	20000	30	29.1	0	2	108.8	28.8	104.6	21.5	-4.2	-7.3

Coating ID	Target PDMS Mn (g/mole)	% Oligomer added	% actual PDMS added	EC=0; GC=1	Number of Caprolactone per Hydroxyl	Initial Water Contact Angle (deg)	Initial Average Force at Release (N)	Water Contact Angle after water immersion (deg)	Average Force at Release after water immersion (N)	Change in Water Contact Angle (deg)	Change in Force at Release (N)
B4-101109	25000	30	29.3	0	2	109.1	21.7	104.1	27.7	-5.0	6.0
B5-101109	30000	30	29.4	0	2	109.4	19.0	106.7	23.7	-2.7	4.6
B6-101109	35000	30	29.5	0	2	107.9	21.6	105.6	15.9	-2.3	-5.7
C1-101109	10000	30	27.6	0	3	101.6	21.5	99.1	19.1	-2.5	-2.5
C2-101109	15000	30	28.4	0	3	105.7	30.8	102.9	24.3	-2.8	-6.5
C3-101109	20000	30	28.8	0	3	107.2	27.6	102.3	20.1	-4.9	-7.5
C4-101109	25000	30	29.0	0	3	109.7	29.1	105.0	19.6	-4.7	-9.5
C5-101109	30000	30	29.2	0	3	109.0	27.6	106.7	19.3	-2.3	-8.4
C6-101109	35000	30	29.3	0	3	107.7	24.8	104.8	19.5	-2.9	-5.3
D1-101109	10000	30	27.1	0	4	98.8	22.3	100.7	19.0	1.9	-3.3
D2-101109	15000	30	28.0	0	4	105.9	37.9	103.0	39.0	-2.9	1.1
D3-101109	20000	30	28.5	0	4	110.1	31.2	105.3	27.5	-4.8	-3.8
D4-101109	25000	30	28.7	0	4	107.4	27.2	104.6	25.9	-2.8	-1.3
D5-101109	30000	30	28.9	0	4	106.0	34.5	103.5	23.5	-2.5	-11.1
D6-101109	35000	30	29.1	0	4	106.8	23.3	108.6	19.1	1.8	-4.2
A1-101110	10000	40	39.3	0	0	101.1	10.9	110.2	13.3	9.1	2.4
A2-101110	15000	40	39.5	0	0	101.3	9.4	106.0	9.1	4.7	-0.3
A3-101110	20000	40	39.7	0	0	94.3	9.5	98.8	10.0	4.5	0.5
A4-101110	25000	40	39.7	0	0	108.4	9.0	109.7	9.0	1.3	-0.1
A5-101110	30000	40	39.8	0	0	109.9	9.1	114.7	8.6	4.8	-0.5
A6-101110	35000	40	39.8	0	0	111.8	8.9	112.7	8.8	0.9	-0.1
B1-101110	10000	40	37.6	0	2	106.7	46.4	107.4	22.7	0.7	-23.7
B2-101110	15000	40	38.4	0	2	109.4	30.2	108.0	21.1	-1.4	-9.1
B3-101110	20000	40	38.8	0	2	110.1	37.7	107.6	23.3	-2.5	-14.4
B4-101110	25000	40	39.0	0	2	111.0	34.8	108.4	21.3	-2.6	-13.5
B5-101110	30000	40	39.2	0	2	111.0	28.5	109.3	23.1	-1.7	-5.3
B6-101110	35000	40	39.3	0	2	110.8	22.8	110.3	11.5	-0.5	-11.3
C1-101110	10000	40	36.8	0	3	104.8	33.5	105.0	22.7	0.2	-10.8
C2-101110	15000	40	37.8	0	3	108.5	38.4	108.0	37.4	-0.5	-1.1
C3-101110	20000	40	38.3	0	3	109.9	54.5	108.7	33.8	-1.2	-20.7
C4-101110	25000	40	38.7	0	3	110.7	32.0	109.1	22.4	-1.6	-9.6

Coating ID	Target PDMS Mn (g/mole)	% Oligomer added	% actual PDMS added	EC=0; GC=1	Number of Caprolactone per Hydroxyl	Initial Water Contact Angle (deg)	Initial Average Force at Release (N)	Water Contact Angle after water immersion (deg)	Average Force at Release after water immersion (N)	Change in Water Contact Angle (deg)	Change in Force at Release (N)
C5-101110	30000	40	38.9	0	3	110.2	31.5	110.3	28.4	0.1	-3.1
C6-101110	35000	40	39.0	0	3	109.7	33.4	110.3	13.7	0.6	-19.6
D1-101110	10000	40	36.1	0	4	103.6	22.8	105.5	30.6	1.9	7.8
D2-101110	15000	40	37.3	0	4	107.9	44.5	108.8	31.3	0.9	-13.2
D3-101110	20000	40	37.9	0	4	109.1	52.0	108.5	30.8	-0.6	-21.3
D4-101110	25000	40	38.3	0	4	109.1	39.5	105.7	27.9	-3.4	-11.5
D5-101110	30000	40	38.6	0	4	109.1	44.3	107.8	29.1	-1.3	-15.2
D6-101110	35000	40	38.8	0	4	109.0	35.0	109.1	27.2	0.1	-7.8
A1-101119	10000	10	9.8	1	0	102.9	19.3	98.7	22.7	-4.2	3.5
A2-101119	15000	10	9.9	1	0	106.7	19.0	103.9	14.0	-2.8	-5.1
A3-101119	20000	10	9.9	1	0	110.1	12.3	105.6	11.9	-4.5	-0.4
A4-101119	25000	10	9.9	1	0	110.8	18.3	107.2	13.0	-3.6	-5.3
A5-101119	30000	10	9.9	1	0	112.1	11.9	110.8	9.1	-1.3	-2.7
A6-101119	35000	10	9.9	1	0	111.1	17.0	110.2	11.2	-0.9	-5.8
B1-101119	10000	10	9.4	1	2	101.1	17.6	95.6	9.4	-5.5	-8.1
B2-101119	15000	10	9.6	1	2	105.5	18.4	100.6	12.5	-4.9	-5.9
B3-101119	20000	10	9.7	1	2	106.7	17.3	102.1	15.9	-4.6	-1.4
B4-101119	25000	10	9.8	1	2	108.0	21.0	105.4	17.9	-2.6	-3.1
B5-101119	30000	10	9.8	1	2	107.9	25.6	103.6	17.4	-4.3	-8.2
B6-101119	35000	10	9.8	1	2	107.1	30.4	106.6	14.0	-0.5	-16.5
C1-101119	10000	10	9.2	1	3	99.5	16.5	95.3	9.9	-4.2	-6.6
C2-101119	15000	10	9.5	1	3	104.4	20.7	100.4	18.0	-4.0	-2.7
C3-101119	20000	10	9.6	1	3	106.6	17.3	99.8	20.8	-6.8	3.5
C4-101119	25000	10	9.7	1	3	106.9	21.3	103.5	21.5	-3.4	0.2
C5-101119	30000	10	9.7	1	3	107.2	23.2	104.3	18.8	-2.9	-4.4
C6-101119	35000	10	9.8	1	3	106.1	31.0	103.6	21.6	-2.5	-9.4
D1-101119	10000	10	9.0	1	4	99.3	14.2	94.6	18.9	-4.7	4.7
D2-101119	15000	10	9.3	1	4	102.3	21.7	97.6	16.6	-4.7	-5.1
D3-101119	20000	10	9.5	1	4	104.3	25.6	100.7	19.6	-3.6	-6.0
D4-101119	25000	10	9.6	1	4	105.0	20.8	99.6	21.1	-5.4	0.3
D5-101119	30000	10	9.6	1	4	105.7	26.9	101.0	18.8	-4.7	-8.1

Coating ID	Target PDMS Mn (g/mole)	% Oligomer added	% actual PDMS added	EC=0; GC=1	Number of Caprolactone per Hydroxyl	Initial Water Contact Angle (deg)	Initial Average Force at Release (N)	Water Contact Angle after water immersion (deg)	Average Force at Release after water immersion (N)	Change in Water Contact Angle (deg)	Change in Force at Release (N)
D6-101119	35000	10	9.7	1	4	106.0	29.9	105.0	17.6	-1.0	-12.3
A1-101120	10000	20	19.7	1	0	104.1	25.1	103.0	39.6	-1.1	14.5
A2-101120	15000	20	19.8	1	0	105.6	26.6	104.4	23.8	-1.2	-2.8
A3-101120	20000	20	19.8	1	0	107.4	21.0	106.4	24.2	-1.0	3.2
A4-101120	25000	20	19.9	1	0	107.1	19.3	108.4	13.5	1.3	-5.8
A5-101120	30000	20	19.9	1	0	108.6	13.1	108.5	10.5	-0.1	-2.6
A6-101120	35000	20	19.9	1	0	108.4	18.6	108.4	14.5	0.0	-4.1
B1-101120	10000	20	18.8	1	2	100.5	20.7	98.6	13.3	-1.9	-7.4
B2-101120	15000	20	19.2	1	2	103.7	25.5	102.8	20.3	-0.9	-5.2
B3-101120	20000	20	19.4	1	2	104.5	23.3	104.0	24.4	-0.5	1.1
B4-101120	25000	20	19.5	1	2	106.6	22.7	107.0	16.8	0.4	-5.9
B5-101120	30000	20	19.6	1	2	106.4	24.0	105.6	17.4	-0.8	-6.6
B6-101120	35000	20	19.6	1	2	106.6	28.0	107.7	17.5	1.1	-10.5
C1-101120	10000	20	18.4	1	3	99.0	20.4	97.4	11.4	-1.6	-9.0
C2-101120	15000	20	18.9	1	3	101.9	21.6	101.4	14.7	-0.5	-6.9
C3-101120	20000	20	19.2	1	3	104.7	26.7	104.2	13.1	-0.5	-13.6
C4-101120	25000	20	19.3	1	3	105.8	21.7	104.0	14.1	-1.8	-7.5
C5-101120	30000	20	19.4	1	3	106.4	28.4	105.4	12.7	-1.0	-15.7
C6-101120	35000	20	19.5	1	3	106.7	24.2	106.3	13.3	-0.4	-10.9
D1-101120	10000	20	18.0	1	4	99.0	9.4	96.0	14.8	-3.0	5.4
D2-101120	15000	20	18.6	1	4	98.8	9.2	98.4	8.4	-0.4	-0.8
D3-101120	20000	20	19.0	1	4	101.4	10.0	101.4	8.7	0.0	-1.4
D4-101120	25000	20	19.2	1	4	103.8	24.3	101.6	14.3	-2.2	-10.1
D5-101120	30000	20	19.3	1	4	105.0	25.7	103.6	12.0	-1.4	-13.7
D6-101120	35000	20	19.4	1	4	105.3	34.6	104.6	17.0	-0.7	-17.6
A1-101121	10000	30	29.5	1	0	100.6	23.7	102.6	29.3	2.0	5.5
A2-101121	15000	30	29.7	1	0	108.3	37.4	106.2	21.7	-2.1	-15.7
A3-101121	20000	30	29.7	1	0	110.2	21.6	107.8	10.9	-2.4	-10.7
A4-101121	25000	30	29.8	1	0	108.0	29.3	109.1	13.7	1.1	-15.7
A5-101121	30000	30	29.8	1	0	111.2	16.5	110.9	8.8	-0.3	-7.8
A6-101121	35000	30	29.8	1	0	111.3	23.3	114.0	10.7	2.7	-12.6

Coating ID	Target PDMS Mn (g/mole)	% Oligomer added	% actual PDMS added	EC=0; GC=1	Number of Caprolactone per Hydroxyl	Initial Water Contact Angle (deg)	Initial Average Force at Release (N)	Water Contact Angle after water immersion (deg)	Average Force at Release after water immersion (N)	Change in Water Contact Angle (deg)	Change in Force at Release (N)
B1-101121	10000	30	28.2	1	2	96.7	17.1	100.1	16.3	3.4	-0.8
B2-101121	15000	30	28.8	1	2	104.8	32.5	104.0	43.5	-0.8	10.9
B3-101121	20000	30	29.1	1	2	107.0	37.7	105.2	40.5	-1.8	2.8
B4-101121	25000	30	29.3	1	2	107.6	33.2	106.7	31.5	-0.9	-1.8
B5-101121	30000	30	29.4	1	2	108.0	46.0	109.9	22.7	1.9	-23.3
B6-101121	35000	30	29.5	1	2	107.7	52.0	111.1	32.0	3.4	-20.0
C1-101121	10000	30	27.6	1	3	96.0	22.7	96.6	29.9	0.6	7.2
C2-101121	15000	30	28.4	1	3	105.3	40.4	100.1	38.9	-5.2	-1.5
C3-101121	20000	30	28.8	1	3	107.2	39.8	104.6	33.6	-2.6	-6.2
C4-101121	25000	30	29.0	1	3	107.4	28.3	107.8	34.8	0.4	6.5
C5-101121	30000	30	29.2	1	3	107.5	40.7	109.2	27.5	1.7	-13.2
C6-101121	35000	30	29.3	1	3	107.5	45.0	110.2	14.6	2.7	-30.4
D1-101121	10000	30	27.1	1	4	95.3	21.9	98.3	14.6	3.0	-7.3
D2-101121	15000	30	28.0	1	4	100.7	10.0	101.1	19.0	0.4	9.0
D3-101121	20000	30	28.5	1	4	102.9	31.4	101.9	32.9	-1.0	1.5
D4-101121	25000	30	28.7	1	4	105.4	26.1	105.9	34.8	0.5	8.7
D5-101121	30000	30	28.9	1	4	104.3	27.1	108.3	25.7	4.0	-1.4
D6-101121	35000	30	29.1	1	4	106.2	31.8	109.2	26.0	3.0	-5.8
A1-101122	10000	40	39.3	1	0	103.5	39.4	102.4	45.7	-1.1	6.2
A2-101122	15000	40	39.5	1	0	104.9	38.0	106.2	21.2	1.3	-16.8
A3-101122	20000	40	39.7	1	0	107.2	17.8	106.9	18.9	-0.3	1.2
A4-101122	25000	40	39.7	1	0	107.9	25.3	108.9	17.6	1.0	-7.7
A5-101122	30000	40	39.8	1	0	112.2	18.8	112.6	9.4	0.4	-9.4
A6-101122	35000	40	39.8	1	0	108.4	22.5	111.4	8.5	3.0	-14.0
B1-101122	10000	40	37.6	1	2	103.8	35.0	102.9	23.9	-0.9	-11.1
B2-101122	15000	40	38.4	1	2	105.4	41.9	107.0	35.0	1.6	-6.8
B3-101122	20000	40	38.8	1	2	106.6	45.6	107.1	36.9	0.5	-8.7
B4-101122	25000	40	39.0	1	2	108.1	44.1	106.9	34.2	-1.2	-9.9
B5-101122	30000	40	39.2	1	2	107.4	58.2	107.1	31.4	-0.3	-26.8
B6-101122	35000	40	39.3	1	2	107.4	60.7	106.8	28.7	-0.6	-32.0
C1-101122	10000	40	36.8	1	3	98.7	21.9	97.5	18.6	-1.2	-3.3

Coating ID	Target PDMS Mn (g/mole)	% Oligomer added	% actual PDMS added	EC=0; GC=1	Number of Caprolactone per Hydroxyl	Initial Water Contact Angle (deg)	Initial Average Force at Release (N)	Water Contact Angle after water immersion (deg)	Average Force at Release after water immersion (N)	Change in Water Contact Angle (deg)	Change in Force at Release (N)
C2-101122	15000	40	37.8	1	3	104.9	41.0	106.2	30.5	1.3	-10.5
C3-101122	20000	40	38.3	1	3	106.7	46.3	107.5	35.9	0.8	-10.4
C4-101122	25000	40	38.7	1	3	107.4	35.6	106.1	30.5	-1.3	-5.1
C5-101122	30000	40	38.9	1	3	107.1	41.1	107.6	34.3	0.5	-6.8
C6-101122	35000	40	39.0	1	3	106.7	54.3	106.0	23.3	-0.7	-30.9
D1-101122	10000	40	36.1	1	4	101.5	25.0	99.5	27.1	-2.0	2.0
D2-101122	15000	40	37.3	1	4	101.5	34.1	101.1	27.4	-0.4	-6.8
D3-101122	20000	40	37.9	1	4	104.0	51.5	102.7	32.5	-1.3	-19.0
D4-101122	25000	40	38.3	1	4	104.3	27.9	103.2	30.0	-1.1	2.1
D5-101122	30000	40	38.6	1	4	104.9	56.6	100.9	39.3	-4.0	-17.3
D6-101122	35000	40	38.8	1	4	104.7	44.1	106.1	27.7	1.4	-16.4

**Table 5**

Coating ID	Target PDMS Mn (g/mole)	% Oligomer added	% actual PDMS added	EC=0; GC=1	Number of Caprolactone per Hydroxyl	Initial Water Contact Angle (deg)	Initial Methylene Iodide Contact Angle (deg)	Water Contact Angle after immersion (deg)	Methylene Iodide Contact Angle after immersion (deg)	Change in Water Contact Angle (deg)	Change in Methylene Iodide Contact Angle (deg)
A1-101046	2500	10	9.3	0	0	93.4	79.6	93.2	81.4	-0.2	1.8
A2-101046	2500	10	9.1	1	0	97.5	88.7	97.5	86.0	0.0	-2.7
A3-101046	5000	10	9.7	0	0	97.1	78.5	96.5	83.4	-0.6	4.9
A4-101046	5000	10	9.5	1	0	98.1	85.8	97.0	87.0	-1.1	1.2
A5-101046	7500	10	9.8	0	0	97.9	86.3	96.0	87.6	-1.9	1.3
A6-101046	7500	10	9.7	1	0	98.6	90.1	98.5	89.7	-0.1	-0.4
B1-101046	2500	10	8.0	0	2	97.4	75.5	90.5	80.6	-6.9	5.1
B2-101046	2500	10	6.9	1	2	98.2	78.3	91.4	78.3	-6.8	0.0
B3-101046	5000	10	8.9	0	2	98.3	76.0	96.7	83.0	-1.6	7.0
B4-101046	5000	10	8.1	1	2	98.1	77.5	96.0	83.0	-2.1	5.5
B5-101046	7500	10	9.2	0	2	97.2	82.9	96.8	80.7	-0.4	-2.2
B6-101046	7500	10	8.7	1	2	97.0	87.0	95.0	87.3	-2.0	0.3
C1-101046	2500	10	7.4	0	3	98.3	74.6	88.8	76.0	-9.5	1.4
C2-101046	2500	10	6.1	1	3	98.3	77.5	82.3	79.3	-16.0	1.8
C3-101046	5000	10	8.5	0	3	96.9	76.1	95.5	81.2	-1.4	5.1
C4-101046	5000	10	7.6	1	3	98.4	77.5	96.0	81.7	-2.4	4.2

Coating ID	Target PDMS Mn (g/mole)	% Oligomer added	% actual PDMS added	EC=0; GC=1	Number of Caprolactone per Hydroxyl	Initial Water Contact Angle (deg)	Initial Methylene Iodide Contact Angle (deg)	Water Contact Angle after immersion (deg)	Methylene Iodide Contact Angle after water immersion (deg)	Change in Water Contact Angle (deg)	Change in Methylene Iodide Contact Angle (deg)
C5-101046	7500	10	9.0	0	3	98.3	83.0	95.7	83.4	-2.6	0.4
C6-101046	7500	10	8.2	1	3	97.4	89.2	95.0	83.0	-2.4	-6.2
D1-101046	2500	10	7.0	0	4	97.1	77.8	-	80.1	-	2.3
D2-101046	2500	10	5.5	1	4	98.2	77.3	87.7	78.7	-10.5	1.4
D3-101046	5000	10	8.2	0	4	97.6	73.8	93.5	81.1	-4.1	7.3
D4-101046	5000	10	7.1	1	4	100.7	72.8	95.6	75.3	-5.1	2.5
D5-101046	7500	10	8.7	0	4	97.8	84.0	94.5	83.9	-3.3	-0.1
D6-101046	7500	10	7.8	1	4	97.7	78.2	97.9	83.7	0.2	5.5
A1-101047	2500	20	18.7	0	0	94.6	81.6	95.0	85.7	0.4	4.1
A2-101047	2500	20	18.3	1	0	99.4	88.7	99.2	84.5	-0.2	-4.2
A3-101047	5000	20	19.3	0	0	100.0	89.1	99.6	85.8	-0.4	-3.3
A4-101047	5000	20	19.1	1	0	100.1	89.6	99.7	78.9	-0.4	-10.7
A5-101047	7500	20	19.5	0	0	100.6	91.0	99.3	78.3	-1.3	-12.7
A6-101047	7500	20	19.4	1	0	100.4	91.7	100.7	85.0	0.3	-6.7
B1-101047	2500	20	16.0	0	2	98.4	78.3	93.6	78.7	-4.8	0.4
B2-101047	2500	20	13.7	1	2	99.0	76.8	93.6	77.1	-5.4	0.3
B3-101047	5000	20	17.8	0	2	100.4	85.3	97.5	76.8	-2.9	-8.5
B4-101047	5000	20	16.3	1	2	100.0	83.7	97.7	77.2	-2.3	-6.5
B5-101047	7500	20	18.4	0	2	99.8	89.0	99.3	78.7	-0.5	-10.3
B6-101047	7500	20	17.3	1	2	98.7	89.0	97.3	75.3	-1.4	-13.7

Coating ID	Target PDMS Mn (g/mole)	% Oligomer added	% actual PDMS added	EC=0; GC=1	Number of Caprolactone per Hydroxyl	Initial Water Contact Angle (deg)	Initial Methylene Iodide Contact Angle (deg)	Water Contact Angle after immersion (deg)	Methylene Iodide Contact Angle after water immersion (deg)	Change in Water Contact Angle (deg)	Change in Methylene Iodide Contact Angle (deg)
C1-101047	2500	20	14.9	0	3	98.5	84.1	92.2	75.4	-6.3	-8.7
C2-101047	2500	20	12.2	1	3	97.6	78.3	94.6	74.6	-3.0	-3.7
C3-101047	5000	20	17.1	0	3	98.6	81.4	96.1	76.5	-2.5	-4.9
C4-101047	5000	20	15.1	1	3	99.3	87.0	99.0	78.2	-0.3	-8.8
C5-101047	7500	20	17.9	0	3	99.6	85.7	97.1	76.2	-2.5	-9.5
C6-101047	7500	20	16.5	1	3	98.2	86.6	97.2	70.4	-1.0	-16.2
D1-101047	2500	20	13.9	0	4	97.4	81.6	97.8	80.4	0.4	-1.2
D2-101047	2500	20	11.0	1	4	99.6	80.5	96.1	72.0	-3.5	-8.5
D3-101047	5000	20	16.4	0	4	98.4	80.6	97.2	74.8	-1.2	-5.8
D4-101047	5000	20	14.2	1	4	97.2	88.6	100.4	74.3	3.2	-14.3
D5-101047	7500	20	17.5	0	4	98.4	84.5	101.1	71.8	2.7	-12.7
D6-101047	7500	20	15.7	1	4	80.8	87.1	101.7	85.5	20.9	-1.6
A1-101048	2500	30	28.0	0	0	95.9	84.1	96.1	86.4	0.2	2.3
A2-101048	2500	30	27.4	1	0	100.5	90.8	98.0	84.6	-2.5	-6.2
A3-101048	5000	30	29.0	0	0	100.3	91.7	97.7	89.2	-2.6	-2.5
A4-101048	5000	30	28.6	1	0	101.4	91.9	99.9	90.6	-1.5	-1.3
A5-101048	7500	30	29.3	0	0	101.2	92.6	99.6	94.4	-1.6	1.8
A6-101048	7500	30	29.1	1	0	102.4	93.6	100.5	95.2	-1.9	1.6
B1-101048	2500	30	23.9	0	2	99.3	81.1	90.8	77.8	-8.5	-3.3
B2-101048	2500	30	20.6	1	2	98.5	81.5	92.2	81.4	-6.3	-0.1

Coating ID	Target PDMS Mn (g/mole)	% Oligomer added	% actual PDMS added	EC=0; GC=1	Number of Caprolactone per Hydroxyl	Initial Water Contact Angle (deg)	Initial Methylene Iodide Contact Angle (deg)	Water Contact Angle after immersion (deg)	Methylene Iodide Contact Angle after water immersion (deg)	Change in Water Contact Angle (deg)	Change in Methylene Iodide Contact Angle (deg)
B3-101048	5000	30	26.6	0	2	101.7	90.8	98.7	89.2	-3.0	-1.6
B4-101048	5000	30	24.4	1	2	100.9	89.2	99.1	86.8	-1.8	-2.4
B5-101048	7500	30	27.7	0	2	101.6	93.3	99.5	92.8	-2.1	-0.5
B6-101048	7500	30	26.0	1	2	100.9	94.0	99.8	91.4	-1.1	-2.6
C1-101048	2500	30	22.3	0	3	99.1	80.4	92.2	77.1	-6.9	-3.3
C2-101048	2500	30	18.3	1	3	98.4	82.7	93.9	79.2	-4.5	-3.5
C3-101048	5000	30	25.6	0	3	98.9	85.9	97.4	85.6	-1.5	-0.3
C4-101048	5000	30	22.7	1	3	98.9	88.7	97.3	86.3	-1.6	-2.4
C5-101048	7500	30	26.9	0	3	100.3	88.0	98.2	87.6	-2.1	-0.4
C6-101048	7500	30	24.7	1	3	98.2	90.9	97.9	88.6	-0.3	-2.3
D1-101048	2500	30	20.9	0	4	97.9	82.0	90.7	80.0	-7.2	-2.0
D2-101048	2500	30	16.4	1	4	98.2	83.0	89.5	78.3	-8.7	-4.7
D3-101048	5000	30	24.6	0	4	97.2	86.6	96.0	86.8	-1.2	0.2
D4-101048	5000	30	21.2	1	4	98.3	87.6	95.6	88.1	-2.7	0.5
D5-101048	7500	30	26.2	0	4	99.9	92.2	98.1	88.2	-1.8	-4.0
D6-101048	7500	30	23.5	1	4	98.9	90.3	97.4	88.1	-1.5	-2.2
A1-101049	2500	40	37.4	0	0	97.8	75.4	96.5	83.6	-1.3	8.2
A2-101049	2500	40	36.5	1	0	100.9	87.2	99.8	86.7	-1.1	-0.5
A3-101049	5000	40	38.6	0	0	102.5	93.4	101.5	86.8	-1.0	-6.6
A4-101049	5000	40	38.2	1	0	101.2	84.8	99.9	88.3	-1.3	3.5

Coating ID	Target PDMS Min (g/mole)	% Oligomer added	% actual PDMS added	EC=0; GC=1	Number of Caprolactone per Hydroxyl	Initial Water Contact Angle (deg)	Initial Methylene Iodide Contact Angle (deg)	Water Contact Angle after immersion (deg)	Methylene Iodide Contact Angle after water immersion (deg)	Change in Water Contact Angle (deg)	Change in Methylene Iodide Contact Angle (deg)
A5-101049	7500	40	39.1	0	0	99.7	88.2	101.2	88.5	1.5	0.3
A6-101049	7500	40	38.8	1	0	102.7	87.2	103.0	83.5	0.3	-3.7
B1-101049	2500	40	31.9	0	2	97.2	77.4	91.1	80.0	-6.1	2.6
B2-101049	2500	40	27.4	1	2	98.0	80.1	97.2	83.1	-0.8	3.0
B3-101049	5000	40	35.5	0	2	103.8	89.7	102.3	87.5	-1.5	-2.2
B4-101049	5000	40	32.5	1	2	100.8	88.0	100.4	85.1	-0.4	-2.9
B5-101049	7500	40	36.9	0	2	102.4	86.7	103.4	90.2	1.0	3.5
B6-101049	7500	40	34.7	1	2	103.8	91.2	105.4	88.3	1.6	-2.9
C1-101049	2500	40	29.8	0	3	99.7	76.7	93.2	81.4	-6.5	4.7
C2-101049	2500	40	24.4	1	3	99.4	78.4	95.7	81.5	-3.7	3.1
C3-101049	5000	40	34.1	0	3	103.2	92.1	101.5	90.1	-1.7	-2.0
C4-101049	5000	40	30.3	1	3	100.4	87.1	100.2	88.9	-0.2	1.8
C5-101049	7500	40	35.9	0	3	101.4	85.0	102.4	83.7	1.0	-1.3
C6-101049	7500	40	32.9	1	3	101.5	90.6	105.2	89.2	3.7	-1.4
D1-101049	2500	40	27.9	0	4	94.5	81.9	93.9	80.4	-0.6	-1.5
D2-101049	2500	40	21.9	1	4	97.1	74.3	91.6	83.6	-5.5	9.3
D3-101049	5000	40	32.8	0	4	99.8	91.7	97.5	85.2	-2.3	-6.5
D4-101049	5000	40	28.3	1	4	101.0	90.5	96.3	89.8	-4.7	-0.7
D5-101049	7500	40	34.9	0	4	99.7	88.7	100.5	88.5	0.8	-0.2
D6-101049	7500	40	31.4	1	4	100.5	90.0	96.4	81.7	-4.1	-8.3

Coating ID	Target PDMS Mn (g/mole)	% Oligomer added	% actual PDMS added	EC=0; GC=1	Number of Caprolactone per Hydroxyl	Initial Water Contact Angle (deg)	Initial Methylene Iodide Contact Angle (deg)	Water Contact Angle after immersion (deg)	Methylene Iodide Contact Angle after immersion (deg)	Change in Water Contact Angle (deg)	Change in Methylene Iodide Contact Angle (deg)
A1-101107	10000	10	9.8	0	0	98.6	70.0	100.0	70.3	1.4	0.3
A2-101107	15000	10	9.9	0	0	99.2	72.9	-	-	-	-
A3-101107	20000	10	9.9	0	0	95.7	70.2	-	-	-	-
A4-101107	25000	10	9.9	0	0	104.7	79.5	101.4	75.9	-3.3	-3.6
A5-101107	30000	10	9.9	0	0	107.6	84.1	-	-	-	-
A6-101107	35000	10	9.9	0	0	107.1	85.6	-	-	-	-
B1-101107	10000	10	9.4	0	2	103.8	97.2	102.5	84.8	-1.3	-12.4
B2-101107	15000	10	9.6	0	2	107.7	98.8	-	-	-	-
B3-101107	20000	10	9.7	0	2	109.1	100.6	-	-	-	-
B4-101107	25000	10	9.8	0	2	109.0	99.3	108.5	87.4	-0.5	-11.9
B5-101107	30000	10	9.8	0	2	109.8	100.7	109.2	83.1	-0.6	-17.6
B6-101107	35000	10	9.8	0	2	108.9	103.5	-	-	-	-
C1-101107	10000	10	9.2	0	3	99.9	89.7	99.1	76.0	-0.8	-13.7
C2-101107	15000	10	9.5	0	3	106.8	98.0	103.1	80.6	-3.7	-17.4
C3-101107	20000	10	9.6	0	3	108.4	100.9	-	-	-	-
C4-101107	25000	10	9.7	0	3	109.1	100.6	107.3	87.8	-1.8	-12.8
C5-101107	30000	10	9.7	0	3	108.7	99.9	106.5	94.1	-2.2	-5.8
C6-101107	35000	10	9.8	0	3	107.8	97.6	-	-	-	-
D1-101107	10000	10	9.0	0	4	99.7	89.6	97.7	82.8	-2.0	-6.8
D2-101107	15000	10	9.3	0	4	104.5	98.1	101.3	88.4	-3.2	-9.7

Coating ID	Target PDMS Mn (g/mole)	% Oligomer added	% actual PDMS added	EC=0; GC=1	Number of Caprolactone per Hydroxyl	Initial Water Contact Angle (deg)	Initial Methylene Iodide Contact Angle (deg)	Water Contact Angle after immersion (deg)	Methylene Iodide Contact Angle after water immersion (deg)	Change in Water Contact Angle (deg)	Change in Methylene Iodide Contact Angle (deg)
D3-101107	20000	10	9.5	0	4	106.3	99.9	-	-	-	-
D4-101107	25000	10	9.6	0	4	107.1	99.1	-	-	-	-
D5-101107	30000	10	9.6	0	4	105.6	101.9	-	-	-	-
D6-101107	35000	10	9.7	0	4	106.1	101.8	-	-	-	-
A1-101108	10000	20	19.7	0	0	98.2	72.3	101.1	70.5	2.9	-1.8
A2-101108	15000	20	19.8	0	0	102.9	76.7	102.3	73.8	-0.6	-2.9
A3-101108	20000	20	19.8	0	0	94.8	69.8	96.6	68.8	1.8	-1.0
A4-101108	25000	20	19.9	0	0	103.5	77.1	103.5	73.6	0.0	-3.5
A5-101108	30000	20	19.9	0	0	107.2	83.1	106.5	78.0	-0.7	-5.1
A6-101108	35000	20	19.9	0	0	104.1	82.9	105.7	81.0	1.6	-1.9
B1-101108	10000	20	18.8	0	2	100.4	80.1	101.2	93.9	0.8	13.8
B2-101108	15000	20	19.2	0	2	106.2	84.4	103.9	97.0	-2.3	12.6
B3-101108	20000	20	19.4	0	2	109.3	86.0	106.0	95.7	-3.3	9.7
B4-101108	25000	20	19.5	0	2	108.4	84.1	107.9	100.0	-0.5	15.9
B5-101108	30000	20	19.6	0	2	108.4	79.5	108.8	101.5	0.4	22.0
B6-101108	35000	20	19.6	0	2	106.9	94.1	108.7	96.7	1.8	2.6
C1-101108	10000	20	18.4	0	3	98.4	68.7	95.8	82.8	-2.6	14.1
C2-101108	15000	20	18.9	0	3	105.2	86.0	102.9	94.2	-2.3	8.2
C3-101108	20000	20	19.2	0	3	107.5	83.5	105.8	98.6	-1.7	15.1
C4-101108	25000	20	19.3	0	3	108.6	83.4	108.0	99.1	-0.6	15.7

Coating ID	Target PDMS Mn (g/mole)	% Oligomer added	% actual PDMS added	EC=0; GC=1	Number of Caprolactone per Hydroxyl	Initial Water Contact Angle (deg)	Initial Methylene Iodide Contact Angle (deg)	Water Contact Angle after immersion (deg)	Methylene Iodide Contact Angle after water immersion (deg)	Change in Water Contact Angle (deg)	Change in Methylene Iodide Contact Angle (deg)
C5-101108	30000	20	19.4	0	3	107.9	84.6	107.9	98.8	0.0	14.2
C6-101108	35000	20	19.5	0	3	107.7	84.1	107.6	93.3	-0.1	9.2
D1-101108	10000	20	18.0	0	4	98.1	71.2	101.3	79.6	3.2	8.4
D2-101108	15000	20	18.6	0	4	103.3	84.3	103.1	92.6	-0.2	8.3
D3-101108	20000	20	19.0	0	4	105.3	83.5	103.0	83.4	-2.3	-0.1
D4-101108	25000	20	19.2	0	4	105.9	83.5	105.5	91.3	-0.4	7.8
D5-101108	30000	20	19.3	0	4	106.5	84.8	105.3	97.4	-1.2	12.6
D6-101108	35000	20	19.4	0	4	106.8	85.0	106.4	93.3	-0.4	8.3
A1-101109	10000	30	29.5	0	0	103.1	95.1	103.2	92.0	0.1	-3.1
A2-101109	15000	30	29.7	0	0	107.2	97.4	104.3	95.7	-2.9	-1.7
A3-101109	20000	30	29.7	0	0	109.6	97.4	108.0	96.9	-1.6	-0.5
A4-101109	25000	30	29.8	0	0	108.3	101.7	106.8	99.9	-1.5	-1.8
A5-101109	30000	30	29.8	0	0	109.6	102.1	108.5	97.5	-1.1	-4.6
A6-101109	35000	30	29.8	0	0	109.4	100.8	107.4	96.0	-2.0	-4.8
B1-101109	10000	30	28.2	0	2	102.9	95.8	101.3	94.0	-1.6	-1.8
B2-101109	15000	30	28.8	0	2	107.6	90.8	102.8	96.2	-4.8	5.4
B3-101109	20000	30	29.1	0	2	108.8	87.2	104.6	98.6	-4.2	11.4
B4-101109	25000	30	29.3	0	2	109.1	99.5	104.1	99.1	-5.0	-0.4
B5-101109	30000	30	29.4	0	2	109.4	101.0	106.7	100.2	-2.7	-0.8
B6-101109	35000	30	29.5	0	2	107.9	98.6	105.6	95.1	-2.3	-3.5

Coating ID	Target PDMS Mn (g/mole)	% Oligomer added	% actual PDMS added	EC=0; GC=1	Number of Caprolactone per Hydroxyl	Initial Water Contact Angle (deg)	Initial Methylene Iodide Contact Angle (deg)	Water Contact Angle after immersion (deg)	Methylene Iodide Contact Angle after water immersion (deg)	Change in Water Contact Angle (deg)	Change in Methylene Iodide Contact Angle (deg)
C1-101109	10000	30	27.6	0	3	101.6	91.1	99.1	81.6	-2.5	-9.5
C2-101109	15000	30	28.4	0	3	105.7	89.6	102.9	95.1	-2.8	5.5
C3-101109	20000	30	28.8	0	3	107.2	84.4	102.3	97.4	-4.9	13.0
C4-101109	25000	30	29.0	0	3	109.7	99.4	105.0	98.8	-4.7	-0.6
C5-101109	30000	30	29.2	0	3	109.0	100.6	106.7	99.6	-2.3	-1.0
C6-101109	35000	30	29.3	0	3	107.7	99.7	104.8	95.9	-2.9	-3.8
D1-101109	10000	30	27.1	0	4	98.8	89.5	100.7	88.5	1.9	-1.0
D2-101109	15000	30	28.0	0	4	105.9	94.3	103.0	93.5	-2.9	-0.8
D3-101109	20000	30	28.5	0	4	110.1	98.1	105.3	93.9	-4.8	-4.2
D4-101109	25000	30	28.7	0	4	107.4	101.6	104.6	97.1	-2.8	-4.5
D5-101109	30000	30	28.9	0	4	106.0	98.5	103.5	95.0	-2.5	-3.5
D6-101109	35000	30	29.1	0	4	106.8	100.4	108.6	93.7	1.8	-6.7
A1-101110	10000	40	39.3	0	0	101.1	72.5	110.2	85.2	9.1	12.7
A2-101110	15000	40	39.5	0	0	101.3	75.4	106.0	78.4	4.7	3.0
A3-101110	20000	40	39.7	0	0	94.3	71.4	98.8	73.9	4.5	2.5
A4-101110	25000	40	39.7	0	0	108.4	83.2	109.7	81.8	1.3	-1.4
A5-101110	30000	40	39.8	0	0	109.9	84.8	114.7	85.2	4.8	0.4
A6-101110	35000	40	39.8	0	0	111.8	88.1	112.7	88.6	0.9	0.5
B1-101110	10000	40	37.6	0	2	106.7	100.8	107.4	93.0	0.7	-7.8
B2-101110	15000	40	38.4	0	2	109.4	98.0	108.0	99.4	-1.4	1.4

Coating ID	Target PDMS Mn (g/mole)	% Oligomer added	% actual PDMS added	EC=0; GC=1	Number of Caprolactone per Hydroxyl	Initial Water Contact Angle (deg)	Initial Methylene Iodide Contact Angle (deg)	Water Contact Angle after immersion (deg)	Methylene Iodide Contact Angle after water immersion (deg)	Change in Water Contact Angle (deg)	Change in Methylene Iodide Contact Angle (deg)
B3-101110	20000	40	38.8	0	2	110.1	103.2	107.6	99.0	-2.5	-4.2
B4-101110	25000	40	39.0	0	2	111.0	103.2	108.4	98.7	-2.6	-4.5
B5-101110	30000	40	39.2	0	2	111.0	100.9	109.3	99.5	-1.7	-1.4
B6-101110	35000	40	39.3	0	2	110.8	101.7	110.3	100.7	-0.5	-1.0
C1-101110	10000	40	36.8	0	3	104.8	98.8	105.0	94.9	0.2	-3.9
C2-101110	15000	40	37.8	0	3	108.5	100.1	108.0	96.4	-0.5	-3.7
C3-101110	20000	40	38.3	0	3	109.9	101.8	108.7	97.8	-1.2	-4.0
C4-101110	25000	40	38.7	0	3	110.7	100.4	109.1	99.3	-1.6	-1.1
C5-101110	30000	40	38.9	0	3	110.2	101.9	110.3	98.1	0.1	-3.8
C6-101110	35000	40	39.0	0	3	109.7	100.4	110.3	100.6	0.6	0.2
D1-101110	10000	40	36.1	0	4	103.6	93.3	105.5	91.7	1.9	-1.6
D2-101110	15000	40	37.3	0	4	107.9	99.7	108.8	95.3	0.9	-4.4
D3-101110	20000	40	37.9	0	4	109.1	103.9	108.5	96.1	-0.6	-7.8
D4-101110	25000	40	38.3	0	4	109.1	103.3	105.7	75.0	-3.4	-28.3
D5-101110	30000	40	38.6	0	4	109.1	102.2	107.8	80.5	-1.3	-21.7
D6-101110	35000	40	38.8	0	4	109.0	101.4	109.1	92.1	0.1	-9.3
A1-101119	10000	10	9.8	1	0	102.9	98.3	98.7	94.7	-4.2	-3.6
A2-101119	15000	10	9.9	1	0	106.7	96.3	103.9	95.2	-2.8	-1.1
A3-101119	20000	10	9.9	1	0	110.1	98.3	105.6	86.3	-4.5	-12.0
A4-101119	25000	10	9.9	1	0	110.8	100.4	107.2	95.0	-3.6	-5.4

Coating ID	Target PDMS Mn (g/mole)	% Oligomer added	% actual PDMS added	EC=0; GC=1	Number of Caprolactone per Hydroxyl	Initial Water Contact Angle (deg)	Initial Methylene Iodide Contact Angle (deg)	Water Contact Angle after immersion (deg)	Methylene Iodide Contact Angle after immersion (deg)	Change in Water Contact Angle (deg)	Change in Methylene Iodide Contact Angle (deg)
A5-101119	30000	10	9.9	1	0	112.1	101.6	110.8	98.6	-1.3	-3.0
A6-101119	35000	10	9.9	1	0	111.1	101.3	110.2	101.5	-0.9	0.2
B1-101119	10000	10	9.4	1	2	101.1	90.9	95.6	87.6	-5.5	-3.3
B2-101119	15000	10	9.6	1	2	105.5	97.2	100.6	86.7	-4.9	-10.5
B3-101119	20000	10	9.7	1	2	106.7	96.0	102.1	77.2	-4.6	-18.8
B4-101119	25000	10	9.8	1	2	108.0	90.6	105.4	97.8	-2.6	7.2
B5-101119	30000	10	9.8	1	2	107.9	102.1	103.6	95.7	-4.3	-6.4
B6-101119	35000	10	9.8	1	2	107.1	99.8	106.6	81.8	-0.5	-18.0
C1-101119	10000	10	9.2	1	3	99.5	88.3	95.3	84.6	-4.2	-3.7
C2-101119	15000	10	9.5	1	3	104.4	97.1	100.4	90.4	-4.0	-6.7
C3-101119	20000	10	9.6	1	3	106.6	86.6	99.8	89.4	-6.8	2.8
C4-101119	25000	10	9.7	1	3	106.9	90.3	103.5	91.0	-3.4	0.7
C5-101119	30000	10	9.7	1	3	107.2	90.5	104.3	95.7	-2.9	5.2
C6-101119	35000	10	9.8	1	3	106.1	92.9	103.6	87.4	-2.5	-5.5
D1-101119	10000	10	9.0	1	4	99.3	94.5	94.6	82.5	-4.7	-12.0
D2-101119	15000	10	9.3	1	4	102.3	95.2	97.6	88.9	-4.7	-6.3
D3-101119	20000	10	9.5	1	4	104.3	97.3	100.7	86.1	-3.6	-11.2
D4-101119	25000	10	9.6	1	4	105.0	87.9	99.6	93.7	-5.4	5.8
D5-101119	30000	10	9.6	1	4	105.7	87.9	101.0	77.9	-4.7	-10.0
D6-101119	35000	10	9.7	1	4	106.0	98.5	105.0	71.6	-1.0	-26.9

Coating ID	Target PDMS Mn (g/mole)	% Oligomer added	% actual PDMS added	EC=0; GC=1	Number of Caprolactone per Hydroxyl	Initial Water Contact Angle (deg)	Initial Methylene Iodide Contact Angle (deg)	Water Contact Angle after immersion (deg)	Methylene Iodide Contact Angle after water immersion (deg)	Change in Water Contact Angle (deg)	Change in Methylene Iodide Contact Angle (deg)
A1-101120	10000	20	19.7	1	0	104.1	95.9	103.0	95.2	-1.1	-0.7
A2-101120	15000	20	19.8	1	0	105.6	97.4	104.4	81.4	-1.2	-16.0
A3-101120	20000	20	19.8	1	0	107.4	88.1	106.4	81.0	-1.0	-7.1
A4-101120	25000	20	19.9	1	0	107.1	89.1	108.4	80.7	1.3	-8.4
A5-101120	30000	20	19.9	1	0	108.6	87.4	108.5	83.5	-0.1	-3.9
A6-101120	35000	20	19.9	1	0	108.4	100.2	108.4	83.5	0.0	-16.7
B1-101120	10000	20	18.8	1	2	100.5	94.4	98.6	87.9	-1.9	-6.5
B2-101120	15000	20	19.2	1	2	103.7	96.4	102.8	79.1	-0.9	-17.3
B3-101120	20000	20	19.4	1	2	104.5	88.6	104.0	79.5	-0.5	-9.1
B4-101120	25000	20	19.5	1	2	106.6	100.6	107.0	81.6	0.4	-19.0
B5-101120	30000	20	19.6	1	2	106.4	85.4	105.6	82.6	-0.8	-2.8
B6-101120	35000	20	19.6	1	2	106.6	95.6	107.7	81.0	1.1	-14.6
C1-101120	10000	20	18.4	1	3	99.0	89.6	97.4	72.4	-1.6	-17.2
C2-101120	15000	20	18.9	1	3	101.9	95.2	101.4	76.8	-0.5	-18.4
C3-101120	20000	20	19.2	1	3	104.7	88.3	104.2	81.4	-0.5	-6.9
C4-101120	25000	20	19.3	1	3	105.8	86.3	104.0	81.6	-1.8	-4.7
C5-101120	30000	20	19.4	1	3	106.4	87.2	105.4	80.6	-1.0	-6.6
C6-101120	35000	20	19.5	1	3	106.7	93.7	106.3	80.7	-0.4	-13.0
D1-101120	10000	20	18.0	1	4	99.0	88.8	96.0	69.8	-3.0	-19.0
D2-101120	15000	20	18.6	1	4	98.8	86.6	98.4	72.3	-0.4	-14.3


Coating ID	Target PDMS Mn (g/mole)	% Oligomer added	% actual PDMS added	EC=0; GC=1	Number of Caprolactone per Hydroxyl	Initial Water Contact Angle (deg)	Initial Methylene Iodide Contact Angle (deg)	Water Contact Angle after immersion (deg)	Methylene Iodide Contact Angle after immersion (deg)	Change in Water Contact Angle (deg)	Change in Methylene Iodide Contact Angle (deg)
D3-101120	20000	20	19.0	1	4	101.4	75.9	101.4	75.2	0.0	-0.7
D4-101120	25000	20	19.2	1	4	103.8	88.5	101.6	78.4	-2.2	-10.1
D5-101120	30000	20	19.3	1	4	105.0	88.3	103.6	83.8	-1.4	-4.5
D6-101120	35000	20	19.4	1	4	105.3	99.2	104.6	89.2	-0.7	-10.0
A1-101121	10000	30	29.5	1	0	100.6	95.4	102.6	96.5	2.0	1.1
A2-101121	15000	30	29.7	1	0	108.3	90.9	106.2	99.4	-2.1	8.5
A3-101121	20000	30	29.7	1	0	110.2	87.6	107.8	93.3	-2.4	5.7
A4-101121	25000	30	29.8	1	0	108.0	86.0	109.1	99.5	1.1	13.5
A5-101121	30000	30	29.8	1	0	111.2	101.8	110.9	101.0	-0.3	-0.8
A6-101121	35000	30	29.8	1	0	111.3	102.8	114.0	100.5	2.7	-2.3
B1-101121	10000	30	28.2	1	2	96.7	90.2	100.1	91.8	3.4	1.6
B2-101121	15000	30	28.8	1	2	104.8	97.9	104.0	97.4	-0.8	-0.5
B3-101121	20000	30	29.1	1	2	107.0	82.1	105.2	94.8	-1.8	12.7
B4-101121	25000	30	29.3	1	2	107.6	86.7	106.7	99.4	-0.9	12.7
B5-101121	30000	30	29.4	1	2	108.0	100.0	109.9	94.5	1.9	-5.5
B6-101121	35000	30	29.5	1	2	107.7	100.1	111.1	98.1	3.4	-2.0
C1-101121	10000	30	27.6	1	3	96.0	89.6	96.6	89.1	0.6	-0.5
C2-101121	15000	30	28.4	1	3	105.3	98.1	100.1	96.3	-5.2	-1.8
C3-101121	20000	30	28.8	1	3	107.2	86.2	104.6	96.7	-2.6	10.5
C4-101121	25000	30	29.0	1	3	107.4	88.5	107.8	98.0	0.4	9.5

Coating ID	Target PDMS Mn (g/mole)	% Oligomer added	% actual PDMS added	EC=0; GC=1	Number of Caprolactone per Hydroxyl	Initial Water Contact Angle (deg)	Initial Methylene Iodide Contact Angle (deg)	Water Contact Angle after immersion (deg)	Methylene Iodide Contact Angle after immersion (deg)	Change in Water Contact Angle (deg)	Change in Methylene Iodide Contact Angle (deg)
C5-101121	30000	30	29.2	1	3	107.5	100.3	109.2	95.8	1.7	-4.5
C6-101121	35000	30	29.3	1	3	107.5	99.3	110.2	97.3	2.7	-2.0
D1-101121	10000	30	27.1	1	4	95.3	87.2	98.3	88.6	3.0	1.4
D2-101121	15000	30	28.0	1	4	100.7	87.5	101.1	89.1	0.4	1.6
D3-101121	20000	30	28.5	1	4	102.9	83.9	101.9	96.9	-1.0	13.0
D4-101121	25000	30	28.7	1	4	105.4	97.5	105.9	96.6	0.5	-0.9
D5-101121	30000	30	28.9	1	4	104.3	99.8	108.3	99.1	4.0	-0.7
D6-101121	35000	30	29.1	1	4	106.2	97.4	109.2	96.7	3.0	-0.7
A1-101122	10000	40	39.3	1	0	103.5	98.9	102.4	98.1	-1.1	-0.8
A2-101122	15000	40	39.5	1	0	104.9	87.8	106.2	97.5	1.3	9.7
A3-101122	20000	40	39.7	1	0	107.2	98.7	106.9	98.1	-0.3	-0.6
A4-101122	25000	40	39.7	1	0	107.9	99.0	108.9	98.0	1.0	-1.0
A5-101122	30000	40	39.8	1	0	112.2	99.4	112.6	102.3	0.4	2.9
A6-101122	35000	40	39.8	1	0	108.4	102.0	111.4	96.6	3.0	-5.4
B1-101122	10000	40	37.6	1	2	103.8	84.9	102.9	98.5	-0.9	13.6
B2-101122	15000	40	38.4	1	2	105.4	96.6	107.0	98.6	1.6	2.0
B3-101122	20000	40	38.8	1	2	106.6	98.4	107.1	97.7	0.5	-0.7
B4-101122	25000	40	39.0	1	2	108.1	100.4	106.9	98.0	-1.2	-2.4
B5-101122	30000	40	39.2	1	2	107.4	99.6	107.1	99.2	-0.3	-0.4
B6-101122	35000	40	39.3	1	2	107.4	101.8	106.8	103.5	-0.6	1.7

Coating ID	Target PDMS Mn (g/mole)	% Oligomer added	% actual PDMS added	EC=0; GC=1	Number of Caprolactone per Hydroxyl	Initial Water Contact Angle (deg)	Initial Methylene Iodide Contact Angle (deg)	Water Contact Angle after water immersion (deg)	Methylene Iodide Contact Angle after water immersion (deg)	Change in Water Contact Angle (deg)	Change in Methylene Iodide Contact Angle (deg)
C1-101122	10000	40	36.8	1	3	98.7	75.9	97.5	89.7	-1.2	13.8
C2-101122	15000	40	37.8	1	3	104.9	98.5	106.2	99.3	1.3	0.8
C3-101122	20000	40	38.3	1	3	106.7	100.0	107.5	99.1	0.8	-0.9
C4-101122	25000	40	38.7	1	3	107.4	98.9	106.1	100.1	-1.3	1.2
C5-101122	30000	40	38.9	1	3	107.1	99.8	107.6	100.0	0.5	0.2
C6-101122	35000	40	39.0	1	3	106.7	100.1	106.0	92.9	-0.7	-7.2
D1-101122	10000	40	36.1	1	4	101.5	88.3	99.5	89.0	-2.0	0.7
D2-101122	15000	40	37.3	1	4	101.5	92.6	101.1	95.7	-0.4	3.1
D3-101122	20000	40	37.9	1	4	104.0	100.9	102.7	97.8	-1.3	-3.1
D4-101122	25000	40	38.3	1	4	104.3	99.6	103.2	95.2	-1.1	-4.4
D5-101122	30000	40	38.6	1	4	104.9	97.5	100.9	98.0	-4.0	0.5
D6-101122	35000	40	38.8	1	4	104.7	100.2	106.1	98.8	1.4	-1.4

## WHAT IS CLAIMED IS:

1. A polymer having the formula:



wherein x is such that the polymer has a molecular weight of about 1,000 to 100,000;

$R^1$ ,  $R^2$ ,  $R^3$ , and  $R^4$  are independently hydrogen,  $C_1$ - $C_{10}$  alkyl,  $C_1$ - $C_{10}$  fluoro-substituted alkyl, cyclopentyl, cyclohexyl, benzyl, toluyl, xylyl and/or phenyl;

$R^5$  and  $R^6$  are independently a hydroxy-substituted terminal group;


$R^{15}$  and  $R^{16}$  are independently hydrogen,  $C_1$ - $C_{10}$  alkyl, cyclopentyl, cyclohexyl, benzyl, toluyl, xylyl and/or phenyl; and

$L^1$  and  $L^2$  are linking groups.


2. The polymer of claim 1 wherein  $R^5$  and  $R^6$  are independently linear and/or branched alkylene; linear and/or branched hydroxy-substituted alkylene; linear and/or branched vinyl-substituted alkylene; or a combination thereof.
3. The polymer of claim 2 wherein  $R^5$  and  $R^6$  are independently ethylene, propylene and/or hydroxypropylene.
4. The polymer of claim 1 wherein  $R^1$ ,  $R^2$ ,  $R^3$ , and  $R^4$  are independently  $C_1$ - $C_{10}$  alkyl,  $C_1$ - $C_{10}$  fluoro-substituted alkyl, cyclopentyl, cyclohexyl, benzyl, toluyl, xylyl or phenyl.
5. The polymer of claim 1 wherein  $L^1$  and  $L^2$  are independently linear or branched alkylene having from 2 to 10 carbon atoms.

6. The polymer of claim 1 wherein

$R^5$  has the formula



and  $R^6$  has the formula




wherein  $R^7$  and  $R^8$  are independently linear and/or branched alkylene; linear and/or branched hydroxy-substituted alkylene; linear and/or branched vinyl-substituted alkylene; or a combination thereof.


7. The polymer of claim 1 wherein  $R^1$ ,  $R^2$ ,  $R^3$ , and  $R^4$  are methyl; and  $R^{15}$  and  $R^{16}$  are hydrogen.

8. The polymer of claim 1 wherein

$R^5$  has the formula



and  $R^6$  has the formula



wherein  $R^7$ ,  $R^9$ ,  $R^{11}$ , and  $R^{13}$  are independently linear and/or branched alkylene;


$R^8$ ,  $R^{10}$ ,  $R^{12}$ , and  $R^{14}$  are independently hydrogen or linear and/or branched  $C_1$ - $C_{10}$  alkyl;

b, e, z, and u are independently an integer from 0 to 6;

a, d, y, and t are independently an integer from 1 to 300; and

m and n are independently 0 or 1.

9. A polymer prepared by reacting a mixture comprising the polymer of any of claims 1 to 8 and an isocyanate functional compound.
10. The polymer of claim 9 wherein the mixture further comprises a polyol compound.
11. A coating comprising the polymer of claim 10.
12. A polymer including at least one subunit derived from a polysiloxane terminated with a hydroxy functional carbamate group.
13. The polymer of claim 15 wherein the subunit is derived from a polysiloxane terminated with a hydroxy alkyl functional carbamate group.
14. The polymer of claim 15 wherein the polymer is derived by crosslinking the polysiloxane using an isocyanate functional compound.
15. The polymer of claim 15 wherein the polymer comprises at least one polyester subunit.
16. The polymer of claim 15 wherein the polymer comprises at least one polyurethane subunit.
17. A coating comprising the polymer of any of claims 9 to 16.
18. The coating of claim 17 having a water contact angle after immersion in water for 30 days of at least about  $90^\circ$ .
19. The coating of claim 17 having a water contact angle after immersion in water for 30 days of no more than about 30 N.
20. An article having at least one surface comprising the polymeric coating of claim 17.
21. A coating composition comprising a solvent component; and the polymer of any of claims 1-8.



(a) (b) (c)  
**Figure 1:** Experimental designs of siloxane libraries. (a) Low molecular weight siloxane library with EC and GC. (b) High molecular weight siloxane library with EC. (c) High molecular weight siloxane library with GC.





Figure 2: Plot of water contact angle after water immersion vs number of caprolactones per hydroxyl.



**Figure 3: Initial average force at release vs number of caprolactones per hydroxyl.**




Figure 4: Average force at release difference vs number of caprolactones per hydroxyl.




Figure 5




Figure 6