



(51) International Patent Classification:

H02N 13/00 (2006.01) H01L 21/64 (2006.01)

B23Q 3/15 (2006.01) H01L 21/683 (2006.01)

(21) International Application Number:

PCT/US2020/021996

(22) International Filing Date:

11 March 2020 (11.03.2020)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

62/816,687 11 March 2019 (11.03.2019) US

(71) Applicant: **TECHNETICS GROUP LLC** [US/US]; 5605 Carnegie Blvd., Suite 500, Charlotte, North Carolina 28209 (US).

(72) Inventors: **MCFADDEN, Angus**; 5605 Carnegie Blvd., Suite 500, Charlotte, North Carolina 28209 (US).

WRIGHT, Jason; 5605 Carnegie Blvd., Suite 500, Charlotte, North Carolina 28209 (US).

(74) Agent: **KINNEAR, Brian P.**; P.O. BOX 1247, SEATTLE, Washington 98111-1247 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JO, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, WS, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ,

(54) Title: METHODS OF MANUFACTURING ELECTROSTATIC CHUCKS




FIGURE 3

(57) Abstract: A method of depositing material to manufacture an electrostatic chuck is provided. The method first deposits at least one layer of a first dielectric material on a handle using spin coating and/or direct spraying method. A functional electric layer is next deposited on the at least one layer of the first dielectric material. Finally, the electrostatic chuck is formed by depositing at least one layer of a second dielectric material on the functional electric layer and the first dielectric material using spin coating and/or direct spraying method.



TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— *with international search report (Art. 21(3))*

METHODS OF MANUFACTURING ELECTROSTATIC CHUCKS

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] This application claims the benefit of United States Provisional Application No. 62/816,687, entitled "METHODS OF MANUFACTURING ELECTROSTATIC CHUCKS," filed on March 11, 2019, which is incorporated herein by reference in its entirety.

TECHNICAL FIELD

[0002] Described herein are methods of manufacturing an electrostatic chuck (ESC) in which at least a portion of the ESC is formed using spin coating or spraying techniques to deposit layers of the ESC on a handle.

BACKGROUND

[0003] With reference to Figure 1, electrostatic chucks 100 typically include a handle or base plate 110 upon which multiple layers of a dielectric material are deposited to form the chuck body 120. Dispersed between adjacent layers of dielectric material may be patterned metal sheets 130 that serve as electrical components (e.g., electrodes, heaters, etc.).

[0004] Conventional means for manufacturing an ESC having the configuration described above generally include using tape casting techniques to form the multiple layers of dielectric material on the handle. With reference to Figure 2, tape casting methods generally involve providing a moving belt onto which liquid dielectric material is dispersed from a reservoir. A doctor blade is used to ensure a constant height of the material dispersed from the reservoir on to the belt. As the dispersed material moves forward on the belt, it passes under a dryer in order to harden the material. Multiple tape casting passes can be used in order to build up the thickness of the chuck body.

[0005] Multiple issues arise out of the use of tape casting to manufacture portions of an ESC. The overall time required to manufacture an ESC is relatively long due to the slow nature of building up the chuck body using tape casting techniques. The tape casting process is also relatively complex. As such, the overall yield using these techniques is low, and the cost is relatively high.

[0006] Accordingly, a need exists for improved ESC manufacturing methods that resolve or mitigate some or all of the above described problems.

SUMMARY

[0007] Described herein are various embodiments of a method for manufacturing electrostatic chucks. In some embodiments, the method includes depositing at least one layer of a first dielectric material on a handle using spin coating and/or direct spraying, depositing a functional electric layer on the at least one layer of first dielectric material, and depositing at least one layer of a second dielectric material on the functional electric layer using spin coating and/or direct spraying. Additional optional steps, such as depositing a mechanical dielectric layer on the at least one layer of second dielectric material and patterning the mechanical dielectric layer, may also be carried out. In some embodiments, the material of the handle is Al_2O_3 , AlN or Y_2O_3 . In some embodiments, the first dielectric material and the second dielectric material are the same dielectric material, and the dielectric material is a material having a high dielectric constant. In some embodiments, the material of the mechanical dielectric layer is the same material as the handle.

BRIEF DESCRIPTION OF THE DRAWINGS

[0008] Figure 1 illustrates a configuration of an electrostatic chuck according to the prior art.

20 **[0009]** Figure 2 illustrates a tape casting technique according to the prior art.

[0010] Figure 3 is a flow diagram illustrating a method of manufacturing an electrostatic chuck according to various embodiments described herein.

[0011] Figure 4 illustrates an electrostatic chuck manufactured in accordance with methods described herein.

25 DETAILED DESCRIPTION

[0012] With reference to Figure 3, a method 300 for manufacturing an electrostatic chuck includes a step 310 of depositing at least one layer of first dielectric material on a handle using spin coating and/or direct spraying, a step 320 of depositing a functional electric layer on the at least one layer of a first dielectric material, and a step 330 of

depositing at least one layer of a second dielectric material on the functional electric layer using spin coating and/or direct spraying.

[0013] In step 310, at least one layer of a first dielectric material is deposited on a handle using spin coating and/or direct spraying. Spin coating techniques generally call for a small amount of liquid dielectric material to be applied to the center of the handle, followed by rotating the handle at relatively high speeds in order to spread the liquid dielectric material by centrifugal force. Any apparatus known to be suitable for carrying out spin coating (e.g., a spin coater or a spinner) may be used. Similarly, any suitable rotating speed that causes the dielectric material to spread may be used. The amount of material applied to the center of the handle is not limited and is generally determined based on the desired thickness of the layer being formed on the handle. In the event multiple layers of first dielectric material are deposited on the handle, the first layer is deposited directly on the handle using spin coating, and subsequent layers are formed on the preceding layer of dielectric material using spin coating.

[0014] Direct spraying may generally be carried out using a spray gun. The spray gun is loaded with the liquid dielectric material and is then used to spray the liquid dielectric material directly onto the handle (or preceding layer of dielectric material when multiple layers are deposited). The direct spraying is generally carried out such that the layer of material deposited has a uniform thickness.

[0015] Regardless of whether spin coating or direct spraying is used, the deposited layer will generally be cured after deposition in order to harden the material. Any suitable curing technique and parameters may be used. In some embodiments, the deposited material is cured by heating the material at a temperature of 600°C or higher.

[0016] When multiple layers of first dielectric material are deposited, the deposition method may be exclusively spin coating, exclusively direct spraying, or some layers may be deposited using spin coating while other layers are deposited using direct spraying.

[0017] The first dielectric material is generally not limited and may be any material known to be suitable for use as the chuck body of an ESC. In some embodiments, the first dielectric material is a dielectric material having a dielectric constant higher than 3. In some embodiments, the first dielectric material having a dielectric constant higher than 3 is a siloxane-based material. Such dielectric materials may further include a metal oxide component, such as Al₂O₃. However, a metal oxide component is not required.

The high dielectric constant dielectric material can be made up of an oxide, nitride, boride, carbide or fluoride of any combination of yttrium, iridium, scandium, erbium, hafnium, silicon carbide, zirconium oxide, or any lanthanoid. However, such compounds are not required.

5 **[0018]** The handle (also sometimes referred to as a plate or base plate) on which the first layer of first dielectric material is deposited may be made of any material known to be suitable for use as a handle of an ESC. In some embodiments, the material of the handle is a ceramic material. Exemplary ceramic materials include, but are not limited to, Al_2O_3 , AlN and Y_2O_3 . Other suitable materials can be glass or silicon.

10 **[0019]** Step 310 is carried out until the desired thickness of the first portion of the ESC is obtained. The desired thickness can be reached by depositing a single layer of first dielectric material having the desired thickness or by depositing multiple layers of the first dielectric material such that the thickness of the individual layers adds up to the desired overall thickness.

15 **[0020]** After a desired thickness has been reached, step 320 is performed, in which a functional electric layer is deposited on the layer or layers of first dielectric material. Any material known to be suitable for use as a functional electric layer in an ESC can be used. In some embodiments, the material is a metal material. The thickness of the metal layer is generally not limited and can be selected based on the electrical component
20 being formed. The manner of forming the electrical layer can be, for example, via known PVD methods or by screen printing. The electric layer can be patterned as desired using any known patterning techniques.

25 **[0021]** After the functional electric layer has been deposited on the layer or layers of first dielectric material, step 330 is performed, in which at least one layer of a second dielectric material is deposited on top of the functional electric layer. The at least one layer of second dielectric material is deposited on the functional electric layer using the same spin coating and/or direct spraying techniques as described above with respect to step 310. As with step 310, a single layer or multiple layers of second dielectric material can be deposited, so long as the desired thickness of the second portion of the chuck
30 body is achieved. In some embodiments, the second dielectric material is the same as the first dielectric material.

[0022] In some embodiments, steps 310, 320 and 330 may be repeated more than once such that the ESC includes multiple functional electric layers sandwiched between dielectric layers.

[0023] Optional additional manufacturing steps can be carried out after completion of steps 310, 320 and 330. For example, in some embodiments, a mechanical dielectric layer is formed on top of the at least one layer of second dielectric material. This mechanical dielectric layer serves as a sort of cap to the ESC structure. Any manner of depositing the mechanical dielectric layer on the at least one layer of second dielectric material can be used, including deposition via plasma spray, PVD, or a bonding process using ultra thin material. The material of the mechanical dielectric layer is not limited. In some embodiments, the mechanical dielectric layer is the same material as the handle. Thus, for example, when the handle is made from Al_2O_3 , AlN or Y_2O_3 , the mechanical dielectric material can be made from the same Al_2O_3 , AlN or Y_2O_3 material.

[0024] In embodiments where a mechanical dielectric layer is employed, the manufacturing method can further include a patterning step wherein the mechanical dielectric layer is patterned based on the desired application. Any suitable patterning techniques can be used, such as subtractive manufacturing. In a specific example, CNC grinding can be used to form helium channels, mesas, etc. on top of which the wafers can rest during use of the ESC.

[0025] With reference to Figure 4, an ESC 400 manufactured in accordance with the methods described above is shown. The ESC 400 includes a handle 410 on top of which is deposited a layer 420 of first dielectric material. While Figure 4 shows a single layer, it should be appreciated that layer 420 may actually be made of up several layers. On top of layer 420 is a patterned functional electric layer 430. On top of functional electric layer 430 is a layer 440 of the second dielectric material. While Figure 4 shows a single layer, it should be appreciated that layer 440 may actually be made up of several layers. On top of layer 440 is patterned mechanical dielectric layer 450. While Figure 4 shows a single layer 420, a single layer 430 and a single layer 440, it should be appreciated that the ESC could include one or more repeated stacks of layers 420, 430 and 440 on top of the stack shown in Figure 4.

[0026] The ESC manufacturing methods described herein can provide numerous benefits over previously known ESC manufacturing methods. For example, the disclosed

method utilizing spin coating and/or spraying reduces manufacturing costs as compared to methods that employ tape casting. Additionally, the ESC produced by manufacturing methods described herein may also have improved characteristics as compared to an ESC manufactured by previously known methods. For example, the ESC produced by
5 the methods described herein may provide increased clamp force, reduced ESC voltage (which reduces electrostatic particle attraction), reduced electron mobility to improve chucking and dechucking performance at high temperatures, reduced or eliminated residual charging (which is also related to improved chucking and dechucking performance at high temperatures), increased operating temperatures, increased
10 thermal response, and/or high heat flow.

[0027] From the foregoing, it will be appreciated that specific embodiments of the invention have been described herein for purposes of illustration, but that various modifications may be made without deviating from the scope of the invention. Accordingly, the invention is not limited except as by the appended claims.

15

CLAIMS

I/We claim:

1. A method of manufacturing an electrostatic chuck, comprising:

depositing at least a first layer of a first dielectric material on a handle using a
5 depositing method selected from the group of depositing methods consisting of: spin
coating, direct spray coating, or a combination thereof;

depositing a functional electric layer on the at least the first layer of the first
dielectric material; and

depositing at least a second layer of a second dielectric material on the
10 combination of the first layer of the first dielectric material and the functional electric layer
using a depositing method selected from the group of depositing methods consisting of:
spin coating, direct spray coating, or a combination thereof.

2. The method of claim 1, wherein the first dielectric material is identical to the
second dielectric material.

15 3. The method of claim 2, wherein the first dielectric material and the second
dielectric material are a high dielectric constant material.

4. The method of claim 1, wherein the first dielectric material and the second
dielectric material both have a dielectric constant greater than 3.

5. The method of claim 1, wherein depositing at least the first layer of the first
20 dielectric material comprises spin coating and wherein the spin coating comprises:

applying a small amount of a liquid dielectric material on the handle; and

rotating the handle at a velocity to spread the liquid dielectric material by centrifugal force.

6. The method of claim 1, wherein depositing at least the first layer of the first dielectric material comprises direct spray coating

5 7. The method of claim 1, further comprising curing the deposited the first layer of the first dielectric material at least prior to depositing a subsequent layer of dielectric material.

8. The method of claim 7, wherein curing comprises heating the first layer of the first dielectric material to at least 600 °C.

10 9. The method of claim 1, wherein depositing at least the first layer of the first dielectric material comprises depositing a plurality of layers of the first dielectric material.

10. The method of claim 9, wherein depositing the plurality of layers of the first dielectric material all use spin coating.

11. The method of claim 9, wherein depositing the plurality of layers of the first
15 dielectric material all use direct spray coating.

12. The method of claim 9, wherein depositing the plurality of layers of the first dielectric material has at least one of the plurality of layers deposited using spin coating at least one of the plurality of layers deposited using direct spray coating.

13. The method of claim 1, wherein depositing at least the second layer of the
20 second dielectric material comprises depositing a plurality of layers of the second dielectric material.

14. The method of claim 13, wherein depositing the plurality of layers of the second dielectric material all use spin coating.

15. The method of claim 13, wherein depositing the plurality of layers of the second dielectric material all use direct spray coating.

16. The method of claim 13, wherein depositing the plurality of layers of the second dielectric material has at least one of the plurality of layers deposited using spin
5 coating at least one of the plurality of layers deposited using direct spray coating.

17. The method of claim 1, further comprising:

depositing a mechanical dielectric layer on a final layer of the second dielectric material; and

patterning the mechanical dielectric layer.

10 18. The method of claim 1, wherein the first dielectric material and the second dielectric material include at least one of an oxide, a metal oxide, a nitride, a boride, a carbide, a fluoride.

19. The method of claim 1 wherein the first dielectric material and the second dielectric material include at least one of yttrium, iridium, scandium, erbium, hafnium,
15 silicon carbide, zirconium oxide, or a lanthanoid.

20. An electrostatic chuck manufactured by the method recited in claim 1.






FIGURE 1

**FIGURE 2**

3/4**FIGURE 3**




FIGURE 4

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US2020/021996

A. CLASSIFICATION OF SUBJECT MATTER

IPC(8) - H02N 13/00; B23Q 3/15; H01L 21/64; H01L 21/683 (2020.01)

CPC - G03F 7/70708; B05D 5/12; H01L 21/6833; H01L 2933/0025 (2020.02)

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

See Search History document

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

USPC - 361/234; 427/240; 427/258; 427/425 (keyword delimited)

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

See Search History document

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5,753,132 A (SHAMOUILIAN et al) 19 May 1998 (19.05.1998) entire document	1-4, 6, 7, 18, 20
Y		5, 8-17, 19
Y	US 2002/0045011 A1 (NAGASHIMA) 18 April 2002 (18.04.2002) entire document	5
Y	US 2008/0185738 A1 (CHUNG et al) 07 August 2008 (07.08.2008) entire document	8
Y	US 2014/0218711 A1 (BRINKHOF et al) 07 August 2014 (07.08.2014) entire document	9-11, 13-15
Y	US 2016/0170314 A1 (ASML NETHERLANDS BV) 16 June 2016 (16.06.2016) entire document	9, 12, 13, 16
Y	US 2017/0242345 A1 (ASML HOLDING NV) 24 August 2017 (24.08.2017) entire document	17
Y	US 2016/0268048 A1 (BLACKBERRY LIMITED) 15 September 2016 (15.09.2016) entire document	19

☐ Further documents are listed in the continuation of Box C.☐ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

23 April 2020

Date of mailing of the international search report

11 MAY 2020

Name and mailing address of the ISA/US

Mail Stop PCT, Attn: ISA/US, Commissioner for Patents
P.O. Box 1450, Alexandria, VA 22313-1450

Facsimile No. 571-273-8300

Authorized officer

Blaine R. Copenheaver

PCT Helpdesk: 571-272-4300
PCT OSP: 571-272-7774