



Office de la Propriété

Intellectuelle  
du Canada

Un organisme  
d'Industrie Canada

Canadian  
Intellectual Property  
Office

An agency of  
Industry Canada

CA 2278488 C 2007/03/20

(11)(21) **2 278 488**

(12) **BREVET CANADIEN**  
**CANADIAN PATENT**

(13) **C**

(86) Date de dépôt PCT/PCT Filing Date: 1998/01/08  
(87) Date publication PCT/PCT Publication Date: 1998/07/23  
(45) Date de délivrance/Issue Date: 2007/03/20  
(85) Entrée phase nationale/National Entry: 1999/07/16  
(86) N° demande PCT/PCT Application No.: EP 1998/000080  
(87) N° publication PCT/PCT Publication No.: 1998/031710  
(30) Priorités/Priorities: 1997/01/21 (DE197 01 876.9);  
1997/12/05 (DE197 54 064.3)

(51) Cl.Int./Int.Cl. *C08J 3/12* (2006.01),  
*C08B 11/20* (2006.01)

(72) Inventeurs/Inventors:  
WEBER, GUNTER, DE;  
REDEKER, DETMAR, DE;  
KLINKSIEK, BERND, DE;  
HINDERER, JURGEN, DE;  
ULFIK, BENNO, DE

(73) Propriétaire/Owner:  
WOLFF WALSRODE AG, DE

(74) Agent: FETHERSTONHAUGH & CO.

(54) Titre : PROCEDE DE PREPARATION DE DERIVES DE POLYSACCHARIDE A FINES PARTICULES

(54) Title: PROCESS FOR PREPARING FINE-PARTICLE POLYSACCHARIDE DERIVATIVES

**(57) Abrégé/Abstract:**

The invention concerns a novel, particularly economical, process for preparing powdery polysaccharide derivatives, in particular cellulose derivatives with a thermal flocculation point. The process includes the swelling or dissolution of the polysaccharide derivative in a solvent or solvent mixture, breaking up/communuting the swollen or dissolved polysaccharide derivative by thermal and/or mechanical liquid separation, and optionally a drying step.



**PCT** WELTORGANISATION FÜR GEISTIGES EIGENTUM  
Internationales Büro  
INTERNATIONALE ANMELDUNG VERÖFFENTLICH NACH DEM VERTRAG ÜBER DIE  
INTERNATIONALE ZUSAMMENARBEIT AUF DEM GEBIET DES PATENTWESENS (PCT)

<b>(51) Internationale Patentklassifikation<sup>6</sup> :</b> <b>C08B 11/20, C08J 3/12 // C08L 1/28</b>		<b>A1</b>	<b>(11) Internationale Veröffentlichungsnummer:</b> <b>WO 98/31710</b> <b>(43) Internationales Veröffentlichungsdatum:</b> <b>23. Juli 1998 (23.07.98)</b>
<b>(21) Internationales Aktenzeichen:</b> <b>PCT/EP98/00080</b>		<b>(81) Bestimmungsstaaten:</b> AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO Patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), eurasisches Patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), europäisches Patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI Patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).	
<b>(22) Internationales Anmeldedatum:</b> <b>8. Januar 1998 (08.01.98)</b>		<b>(71) Anmelder (für alle Bestimmungsstaaten ausser US):</b> WOLFF WALSRODE AG [DE/DE]; D-29655 Walsrode (DE).	
<b>(30) Prioritätsdaten:</b> 197 01 876.9 21. Januar 1997 (21.01.97) DE 197 54 064.3 5. Dezember 1997 (05.12.97) DE		<b>(72) Erfinder; und</b> <b>(75) Erfinder/Anmelder (nur für US):</b> WEBER, Gunter [DE/DE]; Am Hang 1a, D-29683 Fallingbostel (DE). REDEKER, Detmar [DE/DE]; Stormstrasse 19, D-29664 Walsrode (DE). KLINKSIEK, Bernd [DE/DE]; Obervolbach 10, D-51429 Bergisch Gladbach (DE). HINDERER, Jürgen [DE/DE]; Am Benthal 54, D-51381 Leverkusen (DE). ULFIK, Benno [DE/DE]; Altstadtstrasse 82, D-51379 Leverkusen (DE).	
<b>(74) Anwalt:</b> HELLFELDT, Kurt; Bayer Aktiengesellschaft, Konzernbereich RP, Patente und Lizenzen, D-51368 Leverkusen (DE).		<b>Veröffentlicht</b> <i>Mit internationalem Recherchenbericht. Vor Ablauf der für Änderungen der Ansprüche zugelassenen Frist. Veröffentlichung wird wiederholt falls Änderungen eintreffen.</i>	

**(54) Title:** PROCESS FOR PREPARING FINE-PARTICLE POLYSACCHARIDE DERIVATIVES

**(54) Bezeichnung:** VERFAHREN ZUR HERSTELLUNG VON FEINTEILIGEN POLYSACCHARIDDERIVATEN

**(57) Abstract**

The invention concerns a novel, particularly economical, process for preparing powdery polysaccharide derivatives, in particular cellulose derivatives with a thermal flocculation point. The process includes the swelling or dissolution of the polysaccharide derivative in a solvent or solvent mixture, breaking up/communting the swollen or dissolved polysaccharide derivative by thermal and/or mechanical liquid separation, and optionally a drying step.

**(57) Zusammenfassung**

Die Erfindung betrifft ein neues, besonders wirtschaftliches Verfahren zur Herstellung von pulverförmigen Polysaccharidderivaten, insbesondere Cellulosederivaten mit thermischem Flockpunkt, wobei das Verfahren die Quellung oder Lösung des Polysaccharidderivates in einem Lösungsmittel oder Lösungsmittelgemisch, die Zerteilung/Zerkleinerung des gequollenen oder gelösten Polysaccharidderivates unter thermischer und/oder mechanischer Flüssigkeitsabtrennung und gegebenenfalls einen Trocknungsschritt umfaßt.

30771-383

- 1 -

Process for preparing fine-particle polysaccharide derivatives

This invention relates to a new, particularly economic process for preparing pulverulent polysaccharide derivatives, in particular cellulose derivatives, having a  
5 thermal flocculation point.

After the reaction and, if applicable, after the purification of secondary products formed during the reaction, polysaccharide derivatives are in a form which may be friable or lumpy or may resemble cotton wool. In this form, the polysaccharide  
10 derivatives still retain the structures determined by the raw materials. Thus, for example, cellulose ethers still exhibit the fibrous structure of the initial cellulose. These polysaccharide derivatives are thus unsuitable for use, for example, as products soluble in organic and/or aqueous media.

15 It is also necessary to establish specific particle-size distributions, bulk densities, degrees of drying and degrees of viscosity for the various fields of application.

In principle, virtually all polysaccharide derivatives have therefore to be compacted, ground and dried in order to be made suitable for use.

20 The cellulose derivatives rank among the industrially important polysaccharide derivatives. Their preparation, properties and applications are described, for example, in: Ullmann's Encyclopedia of Industrial Chemistry, 5th Edition, (1986), Volume A5, pages 461-488, VCH Verlagsgesellschaft, Weinheim, Methoden der organischen Chemie, 4th Edition (1987), Volume E20, Makromolekulare Stoffe, Part Volume 3, pages 2048-2076, Georg Thieme Verlag, Stuttgart.  
25

30 DE-C 952 264 discloses a three-step process for converting moist, fibrous methyl celluloses into powder having a high rate of dissolution. Here the product, which contains 50 to 70 wt.% water, is first of all homogenised to form a plastic

composition and cooled to 10°C to 20°C, for which purpose a cooled screw press is used; the product is then ground using a hammer mill and dried in a forced-air dryer.

5 EP-A 0 049 815 (equivalent to US-A 4 415 124) describes a two-step process for preparing micropowders from cellulose ethers or cellulose, wherein the products, which have a finely fibrous or woolly structure, are first of all converted into a brittle, compacted form and the material thus treated is subjected to a grinding process until a particle-size distribution of at least 90% under 0.125 mm is attained. Oscillating mills or ball mills, preferably in cooled form, or pellet mills are used in 10 the embrittling step and jet mills, pin mills or impact disk mills are used in the grinding step.

15 DE-A 30 32 778 mentions a two-step process for the continuous homogenisation of moist cellulose ethers by subjecting the moist cellulose ether to a cutting, impacting or shearing action, produced by circulating rotary bodies having casings with different profiles, at the same time optionally pelletising the comminuted cellulose ethers with addition of water, and subsequently drying the pellets obtained.

20 EP-B 0 370 447 describes a process for the non-destructive grinding and simultaneous drying of moist cellulose ethers, wherein a cellulose ether having an initial moisture content of 20 to 70 wt. % is conveyed by means of a transport gas and simultaneously comminuted by impact and friction and, by means of the energy of grinding, is dried to a residual moisture content of 1 to 10 wt. %.

25 EP-B 0 384 046 describes a process for preparing cellulose ether particles which involves the comminution of cellulose ethers having a viscosity of greater than 100 Pa·s - determined as 2% aqueous solution at 20°C, using an Ubbelodhe tube - to a particle size of 0.4 to 0.035 mm in a high-speed air-swept rotary impact mill.

30 JP-A 79 74855 describes a process for the preparation of pulverulent, soluble cellulose derivatives by spray drying a solution of soluble cellulose derivatives.

30877-29

- 3 -

WO 96/0074 (equivalent to EP 0 767 811) mentions a process for comminuting cellulose ethers which involves the extrusion of a hydrated cellulose ether through orifices having a cross-sectional area of from  $0.0075 \text{ mm}^2$  to  $1 \text{ mm}^2$  ( $7.5 \times 10^{-9} \text{ m}^2$  to  $1 \times 10^{-6} \text{ m}^2$ ) and cutting up the extrudate thus produced to the desired length.

EP-B 0 201 895 describes a process for preparing largely non-fibrous CMC material, characterised by treating the fibrous CMC with water and recovering the non-fibrous CMC through the addition of a liquid which does not dissolve the CMC.

10 The known prior art processes are mostly multistep with a predryer or preliminary embrittlement or preliminary compaction. Furthermore, in all processes the chemical and/or thermal action on the macromolecules, particularly during the processing of highly viscous, highly substituted products, is invariably so high that during the grinding process the macromolecules are broken down in the sense that their chains

15 are reduced in length, which is manifested in particular by a more or less extensive breakdown of the viscosity compared with that of the products initially used. Moreover, the surfaces of the products treated by means of preliminary embrittlement or preliminary drying steps become keratinised. In addition, common to all processes is the high expenditure of energy for grinding the polysaccharide

20 derivatives after preliminary drying, preliminary embrittlement or preliminary compaction.

The present invention has developed a process, wherein

25 · specific degrees of grinding can be established  
· no keratinisation of the products occurs  
· the bulk density of the products is increased  
· no, or only minimal, unwanted breakdown of the viscosity compared with  
that of the starting products takes place

30 · a free-flowing product is obtained  
· the proportion of fine dust in the product is low

30877-29

- 4 -

the amount of energy which has to be expended for the compaction, drying and grinding is decreased and

the energy which of necessity has to be introduced can be partially recovered and subsequently reused.

5

This is achieved by a process wherein

- a) a polysaccharide derivative is soaked or dissolved in an adequate quantity of solvent or mixed solvent, preferably 35 to 99 wt. %, particularly preferably 10 60 to 80 wt. %, based on the total weight, so that primary structures which result from the polysaccharide starting material are largely removed, and subsequently
- b) is either converted into the solid state in a dryer-pulveriser in such a way 15 that, synergistically, on the one hand the solvent or mixed solvent contained in the soaked or dissolved polysaccharide derivative is converted into the vapour phase by means of the superheated vapour of the corresponding, or of a different, solvent or mixed solvent, and on the other hand, the dissolved or soaked polysaccharide derivative is converted into the solid by phase 20 transition, the change in form of the polysaccharide derivatives in these processes taking place as a result of the superimposition of external forces (steam mill drying), or discrete particles are produced by dispersion in a surrounding medium which does not dissolve them and, in subsequent comminuting, filtration and drying steps, these particles are processed into 25 pulverulent solid particles having the required particle size and properties, and then
- c) optionally, in a subsequent drying step, is dried to the required moisture content in prior art units.

30

30877-29

4a

In one aspect, the invention provides a process for preparing a finely divided polysaccharide derivative, comprising: (a) forming an aqueous composition comprising a polysaccharide derivative and water, said aqueous composition containing water in an amount of 35 to 99 wt. %, based on the total weight of said aqueous composition, said polysaccharide derivative being soaked or dissolved in said aqueous composition; (b) converting the polysaccharide derivative of said aqueous composition into finely divided solid particles by: (i) contacting said aqueous composition with super-heated water vapor in a dryer-pulverizer, thereby converting the water of said aqueous composition into the vapor phase, and converting the polysaccharide derivative of said aqueous composition into finely divided solid particles; or (ii) causing the polysaccharide derivative of said aqueous composition to flocculate, thereby converting the polysaccharide derivative of said aqueous composition into finely divided solid particles; and (c) optionally drying the finely divided solid particles of step (b).

Surprisingly, it was found that the polysaccharide derivatives prepared by this process have a high bulk density accompanied by good flow properties. The particles

thus produced have a shape factor\* of less than 5 and greater than/equal to 1, the majority (> 50 wt.%) having a shape factor\* of less than/equal to 2 and the proportion of fine dust in the product being low. There is no, or only minimal, unwanted breakdown of the viscosity compared with that of the starting products. In 5 addition, it was found that the total energy requirements of the steam mill drying are decreased compared with the prior art processes and, since the heat-transfer gas consists of superheated vapour of a solvent or mixed solvent, the energy introduced for the grinding and converted into heat energy is recovered in the heat-transfer gas and can therefore be utilised or advantageously converted into other forms of energy.

10

\* *In this context, shape factor means the ratio of the largest diameter to the smallest diameter of an (ideally ellipsoidal) body.*

The invention relates to a new, particularly economic process for preparing pulverulent 15 polysaccharide derivatives, in particular cellulose derivatives, having a thermal flocculation point; the process comprises soaking or dissolving the polysaccharide derivative in a solvent or mixed solvent, dividing/communuting the soaked or dissolved polysaccharide derivative by thermal and/or mechanical liquid separation and an optional drying step.

20

The polysaccharide derivatives used in this process are soluble or at least soakable in solvents or mixed solvents. They can have one or more substituents of the types:

hydroxyethyl, hydroxypropyl, hydroxybutyl, methyl, ethyl, propyl, dihydroxy- 25 propyl, carboxymethyl, sulfoethyl, hydrophobic long-chain branched and unbranched alkyl groups, hydrophobic long-chain branched and unbranched alkylaryl groups or aryl alkyl groups, cationic groups, acetate, propionate, butyrate, lactate, nitrate, sulfate,

30 of which some groups, such as, for example, hydroxyethyl, hydroxypropyl, hydroxybutyl, dihydroxypropyl, lactate, are capable of forming grafts and the

- 6 -

substituents of the polysaccharides according to the invention are not limited to these groups. Typical polysaccharide derivatives are guar derivatives, starch derivatives, chitin or chitosan derivatives, preferably cellulose derivatives, but the polysaccharide derivatives according to the invention are not limited to these.

5

Examples of cellulose derivatives are hydroxyethyl cellulose (HEC), hydroxypropyl cellulose (HPC), ethyl hydroxyethyl cellulose (EHEC), carboxymethyl hydroxyethyl cellulose (CMHEC), hydroxypropyl hydroxyethyl cellulose (HPHEC), methyl cellulose (MC), methyl hydroxypropyl cellulose (MHPC), methyl hydroxyethyl cellulose (MHEC), carboxymethyl cellulose (CMC), hydrophobically modified hydroxyethyl cellulose (hmHEC), hydrophobically modified hydroxypropyl cellulose (hmHPC), hydrophobically modified ethyl hydroxyethyl cellulose (hmEHEC), hydrophobically modified carboxymethyl hydroxyethyl cellulose (hmCMHEC), hydrophobically modified hydroxypropyl hydroxyethyl cellulose (hmHPHEC), 10 hydrophobically modified methyl cellulose (hmMC), hydrophobically modified methyl hydroxypropyl cellulose (hmMHPC), hydrophobically modified methyl hydroxyethyl cellulose (hmMHEC), hydrophobically modified carboxymethyl methyl cellulose (hmCMMC), sulfoethyl cellulose (SEC), hydroxyethyl sulfoethyl cellulose (HESEC), hydroxypropyl sulfoethyl cellulose (HPSEC), methyl hydroxyethyl sulfoethylcellulose (MHESEC), methyl hydroxypropyl sulfoethyl cellulose (MHPSEC), hydroxyethyl hydroxypropyl sulfoethyl cellulose (HEHPSEC), carboxymethyl sulfoethyl cellulose (CMSEC), hydrophobically modified sulfoethyl cellulose (hmSEC), hydrophobically modified hydroxyethyl sulfoethyl cellulose (hmHESEC), hydrophobically modified hydroxypropyl sulfoethyl cellulose (hmHPSEC), 15 hydrophobically modified hydroxyethyl hydroxypropyl sulfoethyl cellulose (hmHEHPSEC), hydrophobically modified hydroxyethyl hydroxypropyl sulfoethyl cellulose (hmHEHPSEC).

Particularly preferred cellulose derivatives are cellulose ethers having a thermal flocculation point in water, such as, for example, methyl cellulose, methyl 20 hydroxyethyl cellulose, methyl hydroxypropyl cellulose and hydroxypropyl cellulose.

Suitable solvents for the soaking or dissolving are solvents whose molecules have polar groups which preferably contain the hetero atoms nitrogen, sulfur and oxygen. However, hydrocarbons and halogenated hydrocarbons may also be used. Preferred 5 solvents are water, alcohols such as methanol, ethanol, isopropanol and esters such as ethyl acetate and butyl acetate. The particularly preferred solvent is water. The use of mixed solvents is in accordance with the invention.

Primary structures which result from the polysaccharide starting material are 10 removed by the soaking or dissolving process. Thus in cellulose ethers, for example, the fibrous structure is almost completely lost; here, of course, only the portion of the polysaccharide derivative in which derivatisation is adequate will be soaked or dissolved. The soaked or dissolved polysaccharide derivatives thus obtained contain less than 25 to 50 wt. %, based on the solids content, of soluble or soakable material 15 in the initial condition, in cellulose derivatives in the fibrous condition, preferably less than 10 wt. %, particularly preferably less than 5 wt. % and most preferably less than 1 wt. %.

The process also includes soaking and/or dissolving processes which are carried out 20 by addition of a substance which dissolves the polysaccharide to one which does not, or by converting a substance which does not dissolve the polysaccharide derivative into one which does so, for example, by changing the temperature. The resulting soaked or dissolved polysaccharide derivatives, depending on the quantity of solvent and on the polysaccharide derivative, range from liquids which flow freely without 25 the use of pressure to rigid compositions which are incapable of flowing even under pressure.

The proportion of solvent or mixed solvent is so chosen that a degree of soaking or dissolving which is sufficient to remove the primary structures is achieved. In a 30 preferred procedure, this is 35 to 99 wt. %, particularly preferably 60 to 80 wt. %, solvent or mixed solvent, based on the total weight.

In one embodiment of the process, polysaccharide derivatives having a thermal flocculation point, preferably cellulose ethers having a thermal flocculation point in water, particularly preferably methyl cellulose, methyl hydroxyethyl cellulose, 5 methyl hydroxypropyl cellulose, hydroxypropyl cellulose - through the cooling of a solvent-moistened, preferably water-moistened filter cake, optionally with the aid of additional solvent, preferably water - in a soaked condition or in solution are brought to temperatures below the flocculation point, so that primary structures, for example, fibrous structures, are largely lost.

10 The soaked or dissolved polysaccharide derivative is then converted into the solid state in a dryer-pulveriser in such a way that, synergistically, on the one hand the solvent or mixed solvent contained in the soaked or dissolved polysaccharide derivative is converted into the vapour phase by means of the superheated vapour of 15 the corresponding, or of a different, solvent or mixed solvent, and on the other hand, the dissolved or soaked polysaccharide derivative is converted into the solid by phase transition, the change in form of the polysaccharide derivatives in these processes taking place as a result of the superimposition of external forces (steam mill drying).

20 The introduction of the polysaccharide derivative into the dryer-pulveriser can, depending upon the consistency of the material to be introduced, be carried out by means of prior art feed devices. A preliminary breaking up of the strand to be introduced into individual strands, which optionally may be further cut up in the transverse direction, is in accordance with the invention, the individual strands 25 having cross-sectional areas of greater than  $1 \text{ mm}^2$ . The extruded strands can be fed directly into the pulverising zone by means of screw conveyors. More advantageously, the charged material is pressed through a passing screen and thus shaped into individual strands. These can be conveyed pneumatically into the dryer-pulveriser. In a similar way, single-shaft or twin-shaft screw-type machines having a perforated 30 disk attachment can be used. After the perforated disk, the continuous strands may optionally be cut into smaller sections by means of a cutting tool.

In one variant of the process, the steam mill drying is carried out in a gas- or air-swept mill, wherein the polysaccharide derivative is subjected to an impacting and/or shearing stress. Suitable mills are, for example, hammer mills, screen-type mills, pin mills, disk mills, jet mills, preferably classifier mills. Superheated vapour of a solvent or of a mixed solvent (superheated steam) is used as heat-transfer gas and transport gas for the steam mill drying and here the solvent or mixed solvent used can correspond to or differ from the solvent or mixed solvent contained in the soaked or dissolved polysaccharide derivative. Preferably superheated steam is used. The dissolved or soaked polysaccharide derivative is comminuted by repeated impacting and/or shearing stress between rotating and fixed or contrarotating grinding devices and/or by impact of several particles. At the same time, the solvent or mixed solvent contained in the solid matter is vaporised. The thermal energy required for this is only partly introduced by means of superheated vapour of a solvent or mixed solvent. The electrical energy of the mill drive, converted by friction into heat, simultaneously contributes to the drying process. The finely divided solid particles are separated from the flow of gas in a separator arranged in tandem with the dryer-pulveriser. The separator can be a centrifugal separator such as, for example, a cyclone, or a filtering separator. Depending on the construction of the mill, an air classification may already take place internally. Grit content which may possibly be present is separated from the fine material because the centrifugal force predominates over the pulling forces of the transport gas. The fine material is discharged from the pulverising chamber as finished product together with the transport gas. The grit is returned to the pulverising zone in an internal or external recycling system. Alternatively or additionally, it may be useful to arrange in tandem another classifying step, by air or preferably by screening. The coarse fraction separated there may optionally be returned to the mill or be mixed with the feed material.

In a preferred embodiment of the process, the superheated steam is recirculated and the excess superheated steam is transferred out as a subsidiary stream of vapour. A heat exchanger, which reheats the vapour produced by the vaporisation of the

solvent or mixed solvent contained in the polysaccharide derivative and cooled by heat loss, is arranged in front of the dryer-pulveriser. The temperature of the vapour of a solvent or mixed solvent required for the steam mill drying is chosen so that, depending on the chosen product throughput and/or the quantity of solvent or mixed 5 solvent in the polysaccharide derivative, at no point does it fall below the dew point.

The use of solvents or mixed solvents in the steam mill drying results in the attainment within the dryer-pulveriser of an atmosphere which is low in oxygen.

10 The stream of vapour or discharged subsidiary stream of vapour, optionally after a hot gas filtration, can be recondensed with the recovery of heat.

In another variant of the process according to the invention, the solution of a cellulose ether having a thermal flocculation point is dispersed in a hot ambient 15 medium, preferably water, above the flocculation point, with the consequent production of discrete particles, which can be processed into pulverulent solid particles in subsequent comminuting, filtration and drying steps. The required final particle sizes are established in the suspension by means of a dividing/comminuting system and by the dispersion process. The product is recovered by separating off the 20 suspending liquid, the separation being effected by a direct thermal drying or by a combination of mechanical separation of the liquid and thermal drying.

In another variant of the process according to the invention, a solution of a cellulose ether having a thermal flocculation point is dispersed in a hot ambient medium, 25 preferably water, above the flocculation point. This solution is dispersed in the form of droplets in a concentrated salt solution at temperatures above the flocculation point and precipitated. Owing to the high salt concentration in the ambient medium, the droplets containing cellulose ether become concentrated as a result of osmosis. After several filtration and washing steps at temperatures above the flocculation 30 point, a cellulose ether low in salt is obtained. After redispersion in a hot ambient medium, preferably water, above the flocculation point, the required final particle

- 11 -

size is established by means of a dividing/communuting system. The product is recovered by separating off the suspending liquid, the separation being effected by a direct thermal drying or by a combination of mechanical separation of the liquid and thermal drying.

5

The finely divided solid particles may optionally be dried to the required moisture content in prior art drying devices and optionally be subjected beforehand or afterwards to a classification by screening and/or by air. Drying is suitably carried out using convection dryers, preferably using pneumatic dryers, ring dryers or 10 similar units.

To modify the properties of the end product, modifiers, additives and/or active ingredients may optionally be added before, during or after one or more of the steps in the process - soaking or dissolving the solution of the polysaccharide derivative in 15 a solvent or mixed solvent, division/communution of the soaked or dissolved polysaccharide derivative and thermal and/or mechanical separation of the liquid, drying of the finely divided polysaccharide derivative.

By modifiers are meant substances which have a chemical effect on the polysaccharide derivative. Typical modifiers are oxidising agents, for example, hydrogen 20 peroxide, ozone, hypohalites, perborates and percarbonates, as well as cross-linking agents, for example, dialdehydes such as glyoxal or glutaric dialdehyde, polyfunctional epoxides, polyfunctional isocyanates, organic acids, mineral acids, organic and inorganic salts, but are not limited to these.

25

By additives are meant substances which have no chemical effect on the polysaccharide derivative. Typical additives are preservatives, dispersing agents, defoaming agents, air-entraining agents, pigments, non-ionic, anionic and cationic synthetic and natural polymers, organic and inorganic salts, but are not limited to these.

30

By active ingredients are meant substances which have no chemical effect on the polysaccharide derivative and use the polysaccharide derivative as a binder. Typical active ingredients are agricultural pesticides and pharmaceuticals, but are not limited to these.

5

The polysaccharide derivatives in this invention can be used in a large number of applications. They are used as thickeners, which may be soluble in water or in other solvents, for adhesives, dyes, building materials, cosmetics, foods. They can be used as coatings or as binders, for example, in pharmaceuticals. A further application is 10 as protective colloid, for example, in suspension polymerisation.

The products of this process are finely divided polysaccharide derivatives wherein the primary structures, for example, fibrous structures, originating from the starting materials have been largely removed. The individual solid particles have a shape 15 factor\* of less than 5 and greater than/equal to 1, the majority (> 50 wt. %) having a shape factor\* of less than/equal to 2. 100 wt. % of the finely divided solid particles can pass through a 1 mm screen, preferably 100 wt. % can pass through a 0.315 mm screen, particularly preferably more than 95 wt. % can pass through a 0.16 mm screen, most preferably more than 95 wt. % can pass through a 0.1 mm screen and 20 less than 10 wt. % of the product can pass through a 0.01 mm screen and more than 10 wt. % of the product is retained on a 0.03 mm screen. The proportion of agglomerated particles is low compared with the products of prior art. The product has good flow properties and high bulk densities, in the case of cellulose ethers, bulk densities of greater than/equal to 0.3 kg/l, preferably greater than/equal to 0.4 kg/l. 25 The dispersion and soaking performance of the products in solvents or mixed solvents is dependent on the conditions of the process according to the invention; it can be increased to above that of prior art products and decreased to below that of prior art products.

Examples of the soaking and dissolving of MC

Methyl hydroxyethyl cellulose filter cake (consisting of methyl hydroxyethyl cellulose having a methoxy group content of 19.9 to 30.5 per cent and a hydroxyethoxy group content of 3.1 to 14.8 per cent), solids content of 50 wt. %, based on the total weight, at 95°C was adjusted to a solids content of 20 to 30 wt. %, based on the total weight, with continual stirring in a stirrer vessel of water, the temperature of which was likewise 95°C. The suspension thus obtained was cooled to 45°C. An aqueous methyl hydroxyethyl cellulose gel (referred to below as gelled or as paste) 10 was thereby produced.

Alternatively, the separation of the methyl hydroxyethyl cellulose from the washing liquid after washing with hot water was carried out in such a way that filter cakes having a solids content of 30 to 50 wt. %, based on the total weight, were obtained 15 directly. The soaking or dissolving of the methyl hydroxyethyl cellulose was achieved by cooling to 25°C.

The methyl hydroxyethyl cellulose gels thus produced were converted into finely divided solids (Examples 1 to 3).

20

Example 1

Methyl hydroxyethyl cellulose paste (consisting of methyl hydroxyethyl cellulose having a methoxy group content of 19.9 to 27.1 per cent and a hydroxyethoxy group 25 content of 3.1 to 9.9 per cent and a viscosity in 2% aqueous solution of 15,000 mPa·s at 20°C and 2.55 l/s (Haake Rotovisko)) was introduced, at temperatures above the flocculation point, into a heated double-jacketed stirrer vessel (50 l) containing water. The gelled methyl hydroxyethyl cellulose was dispersed and comminuted by means of a rotor-stator system (Cavimix 1032, from the firm 30 Cavitron). The suspension thus produced was passed into a heated closed circular system by means of a heated gear pump (approx. 100 l/h). Another heated gear

pump rendered possible the regulated withdrawal of a subsidiary stream (1 - 5 l/h) from this closed circular system. This subsidiary stream was atomised in a spray tower (diameter 1 m) by means of a two-fluid nozzle. At the inlet, the air for drying was preheated to 200°C; at the outlet the temperature was approx. 120°C. The solid 5 matter was deposited by means of a combined cyclone and filter. A dry, free-flowing powder was obtained, of which more than 98 wt.%, based on the total weight, passed through a 0.1 mm screen and more than 91 wt.% passed through a 0.063 mm screen.

10 Example 2

A 2% methyl hydroxyethyl cellulose solution (consisting of methyl hydroxyethyl cellulose having a methoxy group content of 24.2 to 30.5 per cent and a hydroxyethoxy group content of 7.5 to 14.8 per cent and a viscosity in 2% aqueous solution 15 of 20,000 mPa·s at 20°C and 2.55 l/s (Haake Rotovisko)) was prepared at approx. 60°C in a heated double-jacketed stirrer vessel. The methyl hydroxyethyl cellulose solution was added dropwise through a nozzle (diameter 0.7 mm) into a 16% NaCl solution at temperatures above the flocculation point (95°C). Particle sizes of approx. 2 mm were obtained. Owing to the osmotic effect, the particles contained only 20 approx. 20% methyl cellulose. The suspension was filtered off in a pressure nutsche at temperatures above the flocculation point. The filter cake was washed with wash water at a temperature of 95°C, then made into a slurry by means of a slow stirrer, again filtered off and washed and, after four further washing/filtering cycles, finally dehumidified by filtration under suction. After redilution with water at above the 25 flocculation point to a methyl hydroxyethyl cellulose content of approx. 10%, the sample was comminuted in a heated receiver by means of a rotor-stator system, for example, Kotthoff-Mischsirene. The solution was atomised in a spray tower (diameter 1 m) by means of a two-fluid nozzle. At the inlet, the air for drying was preheated to 200°C; at the outlet the temperature was approx. 120°C. The solid 30 matter was deposited by means of a combined cyclone and filter. A dry, free-flowing powder having a salt content of less than 1% and a bulk density of approx. 340 g/l

- 15 -

was obtained, of which more than 76 wt.%, based on the total weight, passed through a 0.1 mm screen and more than 60 wt.% passed through a 0.063 mm screen.

5 Example 3

The pulverising equipment consisted of an air-swept mill with vertically arranged drive shaft and four grinding surfaces of 0.51 m in diameter, each having 16 impacting plates, which operated against a profiled opposing grinding surface. The 10 peripheral speed of the rotor was 78 m/s. A cyclone of 0.8 m in diameter, where the major part of the finely ground product was deposited, was arranged in tandem with the mill. After the cyclone, a blower forced the grinding gas back into the mill via a heat exchanger. The excess vapour component was transferred out and deposited in a Venturi washer.

15

An aqueous methyl hydroxyethyl cellulose paste (consisting of methyl hydroxyethyl cellulose having a methoxy group content of 24.2 to 27.1 per cent and a hydroxyethoxy group content of 7.5 to 11.8 per cent and a viscosity in 2% aqueous solution of 12,000 mPa·s at 20°C and 2.55 l/s (Haake Rotovisko)) with a solids content of 20 20%, based on the total weight, was passed to the pulverising chamber at a throughput of 50 kg per hour by the procedure described above. On entering, the superheated steam was at a temperature of 180°C to 200°C at normal pressure. At the outlet of the pulverising chamber, the temperature of the steam was 120°C to 140°C. The quantity of gas circulated was 2500 operating cubic metres, as measured 25 in air at room temperature.

A free-flowing methyl hydroxyethyl cellulose was obtained, of which more than 85 wt.%, based on the total weight, passed through a 0.1 mm screen and more than 57 wt.% passed through a 0.063 mm screen.

30

The particle-size analyses were carried out by means of a laboratory air-jet screen, with a weighed portion of 3 g and an operating time of 3 minutes. The residual moisture content was 4 wt. %, based on the total weight.

- 5 The maximum grain size was decreased by a subsequent screening on an air-jet screen having a screening surface of 0.28 m<sup>2</sup> and a throughput of 10 kg/h, so that 100 wt. % of the finely divided solid, based on the total weight, passed through a 0.08 mm screen.
- 10 At various stages of the process (prior to the dissolving and soaking step, as gel, as powder, as various screened fractions of the powder), the viscosity of the methyl hydroxyethyl cellulose was measured in aqueous solution and found to be unaffected by the process.
- 15 A paste of another methyl hydroxyethyl cellulose (consisting of methyl hydroxyethyl cellulose having a methoxy group content of 21.4 to 26.1 per cent and a hydroxyethoxy group content of 5.9 to 9.8 per cent and a viscosity in 2% aqueous solution of 28,000 mPa·s at 20°C and 2.55 l/s (Haake Rotovisko)), at a throughput of the feed material of 50 kg/h, a vapour inlet temperature of 200°C and outlet temperature of 20 150°C, yielded a product of which more than 84 wt. %, based on the total weight, passed through a 0.1 mm screen and more than 47 wt. % passed through a 0.063 mm screen. The bulk density of the product was 0.47 kg per litre.

For comparison, the same methyl hydroxyethyl cellulose paste was pulverised and 25 dried in an atmosphere of nitrogen. About 100 operating cubic metres of nitrogen was circulated round the pulverising equipment. Under otherwise identical conditions, the temperature of the gas discharged fell to 130°C. A product was obtained of which only 56 wt. %, based on the total weight, passed through a 0.1 mm screen and only 17 wt. % passed through a 0.063 mm screen. The bulk density was 30 0.43 kg/litre.

30877-29

17

CLAIMS:

1. A process for preparing a finely divided polysaccharide derivative, comprising:

(a) forming an aqueous composition comprising a polysaccharide derivative and water, said aqueous composition containing water in an amount of 35 to 99 wt. %, based on the total weight of said aqueous composition, said polysaccharide derivative being soaked or dissolved in said aqueous composition;

10 (b) converting the polysaccharide derivative of said aqueous composition into finely divided solid particles by:

(i) contacting said aqueous composition with super-heated water vapor in a dryer-pulverizer, thereby converting the water of said aqueous composition into the vapor phase, and  
15 converting the polysaccharide derivative of said aqueous composition into finely divided solid particles; or

(ii) causing the polysaccharide derivative of said aqueous composition to flocculate, thereby converting the polysaccharide derivative of said aqueous composition into  
20 finely divided solid particles; and

(c) optionally drying the finely divided solid particles of step (b).

2. The process of claim 1, wherein a member selected from the group consisting of a modifier, an additive, an active ingredient and a mixture thereof, is incorporated with or added to the polysaccharide derivative before, during or after one or more of the partial steps in the process according to claim 1.

30877-29

18

3. The process of claim 1 or 2, wherein the polysaccharide derivative has a thermal flocculation point, and the primary structures of the polysaccharide derivative which results from the polysaccharide starting material are largely removed by cooling a solvent-moistened filter cake, 5 optionally with the aid of additional solvent, to a temperature below the flocculation point.

4. The process of any one of claims 1 to 3, wherein the polysaccharide derivative is a cellulose derivative.

10 5. The process of claim 4, wherein the cellulose derivative is a cellulose ether, cellulose ester or cellulose ether ester.

6. The process of claim 5, wherein the cellulose ether is methyl cellulose, methyl hydroxyethyl cellulose, 15 methyl hydroxypropyl cellulose or hydroxypropyl cellulose.

7. The process of any one of claims 1 to 6, wherein said dryer-pulverizer is an air- or gas-swept mill, wherein the product is additionally subjected to an impacting and shearing stress.

20 8. The process of claim 7, wherein the impacting and shearing stress is applied by means of a hammer mill, screen-type mill, pin mill, disk mill, jet mill or classifier mill.

9. The process of claim 8, wherein in a device for 25 applying the impacting and shearing stress, the product is subjected to an air classification, and the grit is mixed with the feed material and/or returned to the pulverizing zone of the device and/or added to a finished product having coarser grain sizes.

30877-29

19

10. The process of claim 9, wherein the polysaccharide derivative product is optionally subjected to a classification by screening and/or by air.

11. The process of any one of claims 1 to 11, wherein 5 the finely divided polysaccharide derivative product thus obtained has a shape factor of less than 5 and greater than or equal to 1, wherein the shape factor is the ratio of the largest to the smallest diameter of the product.

12. The process of claim 11, wherein greater than 10 50 wt. % of the finely divided polysaccharide derivative product has a shape factor of less than 2.

13. The process of any one of claims 1 to 12, wherein the procedure of step (b) (i), optionally with the dryer arranged in tandem, is carried out in such a way that 15 condensation of the water vapor is prevented, in order to prevent a partial solution of the solid finely divided polysaccharide derivative obtained.

14. The process of claim 1, wherein in step (b) (ii) by 20 cooling a water-moistened filter cake of fibrous solid particles of cellulose ether to a temperature below the flocculation point, an aqueous solution of cellulose ether in a concentration range of from greater than 1 wt. % up to the maximum solubility limit, optionally with the aid of water, is produced, from which, by dispersing the aqueous 25 solution of cellulose ether in a hot ambient medium, above the flocculation point, discrete particles are produced and, in a subsequent comminuting and drying step, the discrete particles are processed into solid particles.

15. The process of claim 14, wherein the aqueous 30 solution of cellulose ether, by means of drop wise addition or a dividing/comminution system, is dispersed in an ambient

30877-29

20

medium having a temperature above the flocculation point, and the droplets produced in such a manner are converted into discrete particles on exceeding the flocculation temperature in the suspension.

5 16. The process of claim 15, wherein said ambient medium is water.

17. The process of any one of claims 14 to 16, wherein an aqueous solution of cellulose ether in a concentration range of less than 20 wt. % is dispersed in a salt solution at 10 maximum saturation concentration and at a temperature above the flocculation point, whereby, as a result of the osmotic pressure, water is extracted from the droplets produced in this manner and, on exceeding the flocculation temperature, the droplets are converted into discrete particles having a 15 concentration of cellulose ether higher than that of the starting solution.

18. The process of claim 17, wherein said salt solution is an aqueous NaCl solution.

19. The process of any one of claims 14 to 18, wherein 20 the final particle sizes are established in the suspension by means of comminution and/or division and by the dispersion process.

20. The process of any one of claims 14 to 19, wherein the dry end product is obtained by separating off the 25 suspending liquid, the separation being effected by a direct thermal drying or by a combination of mechanical separation of the liquid and thermal drying.

21. The process of any one of claims 14 to 20, wherein a member selected from the group consisting of a modifier, 30 an additive, an active ingredient and a mixture thereof is

30877-29

21

already incorporated into the cellulose solution and/or added to the finely divided cellulose ether particles.

22. The process of any one of claims 14 to 21, wherein the finely divided polysaccharide derivative product thus obtained has a shape factor of less than 5 and greater than 5 or equal to 1, wherein the shape factor is the ratio of the largest to the smallest diameter of the product.

23. The process of claim 22, wherein greater than 50 wt. % of the finely divided polysaccharide derivative product has a shape factor of less than 2.

24. The process of any one of claims 14 to 23, wherein the aqueous solution of cellulose ether contains cellulose ether in a concentration range of 1 wt. % up to 30 wt. %, and the hot ambient medium is water.

15 25. The process of any one of claims 1 to 24, wherein 100 wt. % of the finely divided solid particles can pass through a 1 mm screen.

26. The process of claim 25, wherein 100 wt. % of the finely divided solid particles can pass through a 0.315 mm screen.

27. The process of claim 25, wherein more than 95 wt. % of the finely divided solid particles can pass through a 0.16 mm screen.

28. The process of claim 25, wherein more than 95 wt. % of the finely divided solid particles can pass through a 0.1 mm screen, less than 10 wt. % of the finely divided solid particles can pass through a 0.01 mm screen, and more than 10 wt. % of the finely divided solid particles are retained on a 0.03 mm screen.

30877-29

22

29. The process of any one of claims 1 to 28, wherein said aqueous composition contains water in an amount of 60 to 80 wt. %, based on the total weight of said aqueous composition.

5 30. A finely divided polysaccharide derivative product prepared by a process as defined in any one of claims 1 to 29, wherein the product has a shape factor of less than 5 and greater than or equal to 1, wherein the shape factor is the ratio of the largest to the smallest diameter of the  
10 product.

FETHERSTONHAUGH & CO.  
OTTAWA, CANADA  
PATENT AGENTS