



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification⁵ : C09K 21/00, C10M 103/00	A1	(11) International Publication Number: WO 93/12197 (43) International Publication Date: 24 June 1993 (24.06.93)
(21) International Application Number: PCT/US92/07211 (22) International Filing Date: 26 August 1992 (26.08.92) (30) Priority data: 810,042 19 December 1991 (19.12.91) US (71) Applicant: FMC CORPORATION [US/US]; 1735 Market Street, Philadelphia, PA 19103 (US). (72) Inventor: PLACEK, Douglas, G. ; 702 Hood Boulevard, Fairless Hills, PA 19030 (US). (74) Agents: FELLOWS, Charles, C. et al.; FMC Corporation, 1735 Market Street, Philadelphia, PA 19103 (US).		(81) Designated States: AU, BB, BG, BR, CS, FI, HU, JP, KR, LK, MG, MN, MW, NO, RO, RU, SD, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: FIRE RESISTANT LOW TEMPERATURE GREASE		
(57) Abstract <p>A flame retardant grease composition is described for low temperature applications comprising mixed alkoxy and alkylated phenyl triesters of a phosphorus oxyacid as a base fluid and a siliceous microparticulate inorganic thickener. The grease has excellent low, medium and high temperature physical properties, which makes it suitable for service in applications with wide temperature (-40 °C to +150 °C) fluctuations. The benefits of reduced rolling resistance can be realized in significant energy savings and the possibility of constructing longer conveyor lines with existing drive motors.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NL	Netherlands
BE	Belgium	GN	Guinea	NO	Norway
BF	Burkina Faso	GR	Greece	NZ	New Zealand
BG	Bulgaria	HU	Hungary	PL	Poland
BJ	Benin	IE	Ireland	PT	Portugal
BR	Brazil	IT	Italy	RO	Romania
CA	Canada	JP	Japan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SK	Slovak Republic
CI	Côte d'Ivoire	LI	Liechtenstein	SN	Senegal
CM	Cameroon	LK	Sri Lanka	SU	Soviet Union
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	MC	Monaco	TG	Togo
DE	Germany	MG	Madagascar	UA	Ukraine
DK	Denmark	ML	Mali	US	United States of America
ES	Spain	MN	Mongolia	VN	Viet Nam
FI	Finland				

-1-

FIRE RESISTANT LOW TEMPERATURE GREASE

This invention relates to a fire resistant grease which is usable even at subzero temperatures.

There is a need for a fire resistant grease particularly one usable in subzero temperatures for lubricating bearings and other moving surfaces in mines but such greases may be useful in any other areas where fire is a hazard. Ordinary mineral lubricating base oils can obviously not be used for such greases. A convenient starting point for fire-resistant greases according to U.S. Patent 4,206,061 is the use of fire resistant hydraulic fluids as base oils, such as phosphorus acid esters or amides and more particularly trihydrocarbyl phosphates thickened with graphitic carbon. However, even with graphitic carbon as the thickener the viscosity of the base oil at subzero temperatures is unacceptable and too great to be practical. Furthermore, U.S. Patent 4,490,266 discloses that phosphate esters have an extremely poor viscosity-temperature behavior in the temperature range of -20°C to $+150^{\circ}\text{C}$, even though they present no corrosion problems and do not cause high wear at highly loaded points of friction. The patent discloses that when thickened with known polyacrylate and polyolefin viscosity modifiers the phosphate esters suffer a loss of effectiveness at high shear rates.

Instead, U.S. Patent 4,490,266 teaches incorporating a polyester having a weight average molecular weight of 20,000 to 300,000 into an aromatic phosphate ester such as tricresyl phosphate, dicresyl monophenyl phosphate, monocresyl diphenyl phosphate and other phosphate esters of monophenols, thereby improving the viscosity index measured between the temperatures of 38.7°C and 98.9°C , thereby making the esters suitable for use as a liquid hydraulic fluid.

-2-

U.S. Patent 4,879,054 discloses that many mechanisms such as bearings, actuator screws, gauges, instruments, aircraft, vehicles, tanks, and other military equipment are required to perform well at
5 ultra low temperatures, such as at -73°C . Lubricating greases for such mechanisms, therefore, not only must perform well at low temperatures but also such lubricating greases must have outstanding oxidation
10 resistance, good antiwear properties, superior pliability, and excellent stability at normal, as well as low temperatures. U.S. Patent 4,879,054 teaches a process for manufacturing low temperature greases
employing a dialkyl ester of a dicarboxylic acid thickened with a lithium soap. However, such an
15 extreme low temperature grease is flammable.

The present invention overcomes the deficiencies of the prior art by providing a fire resistant grease composition comprising:

- 20 a) between 85 and 95 parts by weight of a base fluid comprising mixed alkoxy and phenyl triesters of phosphorus oxyacids, wherein the mole ratio of esterified phenyl groups to esterified alkoxy groups ranges from 7:1 to 0.7:1, and wherein each esterified phenyl
25 group is either phenol, or a mono- or poly-alkylated phenol, the alkylating moieties thereof each containing from 1 to 5 carbon atoms, and each esterified alkoxy group contains between 3 and 10 carbon atoms thereby
30 providing a fire resistant grease base fluid with a single phase, a flash point of at least 200°C and a pour point of less than -40°C , and
- 35 b) between 5 and 15 parts by weight of a siliceous microparticulate inorganic thickener selected from the group consisting of clay and silica, thereby providing a fire resis-

-3-

tant grease composition with low viscosity at subzero temperatures.

For the purpose of this invention a phenyl phosphate ester and an alkylated phenyl phosphate ester collectively are referred to as aryl phosphates.

It is critical that the base fluid be a liquid with a pour point of less than -50°C , and preferably to have a pour point of less than -65°C if the grease is to be used at temperatures of less than -35°C .

The base fluid must not separate into two phases within the desired operating range. The mixed phosphorus triesters can be a mixture of two or more phosphate or phosphite esters, such as triaryl phosphate, triaryl phosphite, diaryl monoalkoxy phosphate, trialkoxy phosphite, monoaryl dialkoxy phosphate and trialkoxy phosphate. When a trialkoxy phosphite is incorporated into the base fluid it is often necessary to incorporate sufficient trialkoxy phosphate to prevent the formation of a second liquid phase at the lower temperatures. To illustrate the invention it is easiest to describe the base fluid in terms of mixtures of a triaryl phosphate and a trialkoxy phosphate. It is particularly desirable for the triaryl phosphorus esters to be mixtures of differently alkylated phenyl groups such as produced by the process of U.S. Patent 3,576,923 in which phenol, a C1 to C4 alkylated phenol or mixture is reacted with sufficient alkylating agent in the presence of a Lewis acid catalyst or a Bronstead acid catalyst to produce an alkylated phenol wherein the mole ratio of the added alkylating moiety to phenol moiety ranges from 0.005 to about 0.65 and the number of carbon atoms per each alkylating moiety ranges from 3 to 5.

The alkylated phenol may then be reacted with a phosphorylating agent, such as phosphorus oxychloride, optionally after adding to the alkylated phenol

other alkylated phenols, such as cresol and the like. The crude triaryl phosphate is subsequently purified by conventional treatment including distillation, caustic washing, adsorption and the like to produce a
5 tri(alkylated phenyl)phosphate ester (triaryl phosphate).

Such "synthetic" triaryl phosphate esters are readily available commercially. For example, one sample of a product trademarked Durad 220B by FMC
10 Corporation on analysis contained about 17% triphenyl phosphate, 43.4% butylphenyl diphenyl phosphate, 30.1% bis(butylphenyl)phenyl phosphate and 5.4% tris(butylphenyl)phosphate and had an average molecular weight of 423. The commercial product usually
15 contains about 7.9% phosphorus and has an average molecular weight of 392.

The base fluid could contain either a single esterified alkoxy group or a mixture of different esterified alkoxy groups. It is most convenient to
20 supply the esterified alkoxy groups as commercial triesters of a phosphorus oxyacid, such as tributyl phosphate, trioctyl phosphite, tributoxyethyl phosphate, trioctyl phosphate, and the like. These are also commercially available.

25 For the purpose of this invention a triester of a phosphorus oxyacid is a compound with a formula $(RO)_3P(O)_n$ wherein each R may be the same or different alkoxy or aryl group and n may be 1 or 0.

The viscosity at low temperatures can be varied
30 by adjusting the mole ratio of esterified aryl groups to esterified alkoxy groups in the phosphorus ester base fluid. As the mole ratio of aryl groups to alkoxy groups decreases, the pour point decreases and the viscosity of the base fluid decreases. Desirable
35 base fluid compositions for low temperature use includes aryl to alkyl mole ratios of 7:1 to 0.7:1, 7:1 to 1:1 for the higher temperatures and for the lower

-5-

temperatures a mole ratio should be between 4:1 to 0.7:1 and preferably for very low temperatures between 2:1 and 0.7:1.

To assure fire resistance, the thickener for the grease desirably should be non-flammable, such as an inorganic siliceous material. However, flammable thickeners could be used in small quantities. Suitable non-flammable thickeners are well known in the art and include microparticulate clays, such as bentonite and hectorite and other types of clays that are typically used in greases as well as microparticulate amorphous silica, preferably fumed silica, such as CAB-O-SIL® fumed silica (trademark Cabot Corp.).

The type and amount of thickener employed will vary with the specific application to obtain the desired quantities. One skilled in the art can easily select the preferred thickener and optimum proportions of base fluid and thickener to meet the specific application without undue experimentation. For example, the Cabot Corp. brochure "CAB-O-SIL Fumed Silica Properties and Functions," provides comparative information on the thickening of various liquids with fumed silica.

The scope of this invention is intended to include other usual additives for a base fluid or a grease, such as stabilizers, antioxidants, rust inhibitors, corrosion inhibitors, and the like.

For the purpose of describing this invention, it is important to avoid confusing terminology. The term "alkylating moiety" is used herein for an alkyl radical attached to an aromatic ring by a carbon-carbon bond; the term "alkoxy group" is used herein for an esterified alkyl radical attached by an oxygen to a phosphorus atom; and "aryl group" is used herein for an esterified phenol or alkylated phenol attached as an ester to a phosphorus atom.

A more detailed explanation of the invention is provided in the following examples.

EXAMPLES

5 The properties of the grease were measured by the following test procedures:

 A modified oxygen index (OI) test was performed on a 1.5 gram sample of grease (20 mm in diameter x 10 mm high) that was subjected to a direct propane
10 flame for 5 seconds. The OI was recorded as the minimum percentage of oxygen in an oxygen/nitrogen environment required for the grease to ignite and sustain combustion. This test is a modification of ASTM D-2863.

15 The vertical burn test evaluates the grease's ability to resist combustion in a standard air environment when subjected to a direct flame for 30 seconds. A grease was spread 1 mm thick evenly over a 2.54 x 12.7 cm steel mesh strip. The strip was
20 suspended vertically, and a 1 inch propane flame was held at the base. The grease was observed for ignition. This test is a modification of ASTM D-3801.

 The initial start-up and rolling resistance torques were measured and recorded before and after
25 the four hours "Burn In" time at ambient (approximately 65°F) on each roller. The resistance was measured by rotation of the inner shaft of the roller with a straining and calibrated shaft and slip ring assembly, while holding the outer roller stationary. The power was provided with a variable
30 drive electric motor and right angle gearbox which was pre-set to 330 RPM.

 The sub-zero (-40°C) temperature tests were conducted with the rollers (one at a time) placed in an
35 environmental chamber while accessing the shaft through a hole in the side of the chamber. The

-7-

rollers were allowed to soak at -40°C for a minimum of 24 hours prior to each test.

A variety of grease candidates were prepared based upon the following composition guidelines:

5 -Isopropylphenyl phosphate (IPP) or t-butylphenyl phosphate (TBPP) at 50-90 wt.%

 -Tributyl phosphate and/or tributoxyethyl phosphate and/or trioctyl phosphate and/or tri-isooctyl phosphite at 10-50 wt.%

10 -Fumed silica thickener at 5-15 wt.%. CAB-O-SIL[®] M-5 (Cabot Corp. trademark) was employed as it is intermediate between L-90 and EH-5 grades in surface area

 -Rust and oxidation inhibitors may also be added at 0.01-3.0 wt.%.

 The t-butylphenyl phosphate (TBPP) used contained on the average 0.20 to 0.25 t-butyl moieties per phenyl group. The additive containing about 8.7% by weight phosphorus (average molecular weight 356).

20 The isopropylphenyl phosphate (IPP) was FMC Corporation's Kronitex K-25 isopropylated triaryl phosphate which typically contains about 0.2 to 0.25 isopropyl moieties per phenol group resulting an average molecular weight of about 360 (8.61% by weight phosphorus).

 The compositions were prepared containing the following phosphate and phosphite esters and suitable additives as shown in Tables I-V.

EXAMPLE 1

30 IPP-73.99 parts by weight; tributyl phosphate 23.99 parts by weight (MW 266) to produce an aryl:alkyl group mole ratio of 2.28.

EXAMPLE 2

35 IPP-70.99 parts; tributyl phosphate 26.99 parts; aryl alkyl mole ratio 1.94.

EXAMPLE 3

IPP-68.94 parts; tri-butoxyethyl phosphate (FMC's KP-140) 28.99 parts (MW 398); aryl:alkyl mole ratio 2.62.

5

EXAMPLE 4

TBPP-68.99 parts; tributyl phosphate 28.99 parts; aryl:alkyl mole ratio 1.77.

EXAMPLE 5

IPP-72.99 parts; tributyl phosphate 16.99 parts (MW 434) trioctyl phosphate 8.0 parts; alkyl:aryl ratio 3.15.

10

The properties of the base fluids and greases thickened with CAB-O-SIL M5 brand fumed silica are disclosed in Tables I to V.

15

The additive package can be designed to enhance the oxidative and hydrolytic stability of the base fluid, and also to protect copper and steel system components from rust or corrosion.

Fumed silica was selected as an optimum thickener for the formulated phosphate ester base fluid. Silicon dioxide can be mixed in without heating or chemical reaction, it precludes the need to manufacture an organic soap thickener, and it does not contribute to the flammability of the final product.

20

Five different base fluid mixtures were prepared. Their formulations and performance attributes are presented as Examples 1 to 5 in Tables I to V. Table VI compares the five examples with commercial greases. From Table VI it is clear that the inventive compositions all have superior low temperature start up and rolling torque and resistance to burning as compared with the commercial compositions.

25

30

EXAMPLE 6

Base fluid compositions were prepared using a commercial tri-isooctyl phosphite and tri(alkylated phenyl)phosphate. On cooling two phases formed which

35

-9-

did not form a satisfactory grease on incorporating a thickener.

Subsequently, single phase base fluids were formed as follows: Sample A by incorporating, by weight
5 54 parts TBPP, 23 parts tri-isooctyl phosphate and 23 parts tributyl phosphate (ratio 1.3:1); and Sample B by incorporating 58 parts IPP, 25 parts tri-isooctyl phosphite and 17 parts tributyl phosphate (ratio
10 0.86:1). Sample A base fluid had a viscosity of 7.9 cSt at 100°C before the standard additive package was added as in Examples 1-5 and 8.9 cSt after; Sample B base fluid viscosity was 8.4 and 9.4 respectively. Both samples had pour points of -57°C and remained
15 single phase liquids. Both samples formed satisfactory greases containing 11% fumed silica solids.

20

25

30

35

-10-

TABLE I**Example 1**

<u>Base Fluid</u>	<u>Weight %</u>
Isopropylphenyl phosphate	73.99
Tributyl phosphate	23.99
Epoxy resin stabilizer	1.0
Amine antioxidant	1.0
Acid phosphate rust inhibitor	0.01
Benzotriazole corrosion inhibitor	0.01
<u>Base Fluid Properties</u>	
Viscosity, cSt @ 98.9°C	2.8
cSt @ 37.8°C	10.4
cSt @ -40°C	4100
Pour Point, °C	-54
ASTM D665 Rust Test	Pass, no rust
<u>Grease Properties</u>	
Thickener	Fumed Silica, 13 wt.%
Worked Penetration @ 25°C	280
4-ball wear scar, mm, ASTM D2266	0.63
Specific Gravity 20°/20°C	1.181
Oxygen Index, ASTM D2863 mod.	27.5
Initial Start-up Torque @ 25°C	105 in-oz (.74 nm)
Rolling Resistance Torque @ 25°C	105 in-oz (.74 nm)
Initial Start-up Torque @ -40°C	400 in-oz (2.82 nm)
Rolling Resistance Torque @ -40°C	400 in-oz (2.82 nm)

-12-

TABLE III**Example 3**

<u>Base Fluid</u>	<u>Weight %</u>
Isopropylphenyl phosphate	68.99
Tributoxyethyl phosphate	28.99
Epoxy resin stabilizer	1.0
Amine antioxidant	1.0
Acid phosphate rust inhibitor	0.01
Benzotriazole corrosion inhibitor	0.01

Base Fluid Properties

Viscosity, cSt @ 98.9°C	3.1
cSt @ 37.8°C	13.8
cSt @ -40°C	6000
Pour Point, °C	-48
ASTM D665 Rust Test	Pass, no rust

Grease Properties

Thickener	Fumed Silica, 14 wt.%
Worked Penetration @ 25°C	280
4-ball wear scar, mm, ASTM D2266	0.70
Specific Gravity 20°/20°C	1.090
Oxygen Index, ASTM D2863mod.	28.5
Initial Start-up Torque @ -40°C	450 in-oz (3.18 nm)
Rolling Resistance Torque @ -40°C	400 in-oz (2.82 nm)

-13-

TABLE IV**Example 4**

<u>Base Fluid</u>	<u>Weight %</u>
t-butylphenyl phosphate	68.99
Tributyl phosphate	28.99
Epoxy resin stabilizer	1.0
Amine antioxidant	1.0
Acid phosphate rust inhibitor	0.01
Benzotriazole corrosion inhibitor	0.01

Base Fluid Properties

Viscosity, cSt @ 98.9°C	2.6
cSt @ 37.8°C	10.0
cSt @ -40°C	3800
Pour Point, °C	-57
ASTM D665 Rust Test	Pass, no rust

Grease Properties

Thickener	Fumed Silica, 13 wt.%
Worked Penetration @ 25°C	280
4-ball wear scar, mm, ASTM D2266	0.62
Specific Gravity 20°/20°C	1.20
Oxygen Index, ASTM D2863mod.	27.3

-14-

TABLE V**Example 5**

<u>Base Fluid</u>	<u>Weight %</u>
Isopropylphenyl phosphate	72.99
Tributyl phosphate	16.99
Trioctyl phosphate	8.0
Epoxy resin stabilizer	1.0
Amine antioxidant	1.0
Acid phosphate rust inhibitor	0.01
Benzotriazole corrosion inhibitor	0.01

Base Fluid Properties

Viscosity, cSt @ 98.9°C	2.9
cSt @ 37.8°C	10.5
cSt @ -40°C	4600
Pour Point, °C	-51
ASTM D665 Rust Test	Pass, no rust

Grease Properties

Thickener	Fumed Silica, 13 wt.%
Worked Penetration @ 25°C	280
4-ball wear scar, mm, ASTM D2266	0.64
Specific Gravity 20°/20°C	1.120
Oxygen Index, ASTM D2863mod.	28.0

Claims:

1. A fire resistant grease composition characterized by:

- 5 a) between 85 and 95 parts by weight of a base fluid having a single liquid phase comprising mixed alkoxy and phenyl triesters of a phosphorus oxyacid, wherein the mole ratio of esterified phenyl groups to esterified alkyl groups ranges from 7:1 to 0.7:1, and wherein each esterified phenyl group is either
10 phenol, or a mono- or polyalkylated phenol, the alkylating moieties thereof each containing from 1 to 5 carbon atoms, and each esterified alkoxy group contains between 3 and 10
15 carbon atoms, thereby providing a fire resistant grease base fluid with a flash point of at least 200°C and a pour point of less than -40°C, and
- 20 b) between 5 and 15 parts by weight of a siliceous microparticulate inorganic thickener selected from the group consisting of clay and silica, thereby providing a fire resistant grease composition with low viscosity at subzero temperatures.

25 2. The composition of claim 1 characterized in that the microparticulate inorganic thickener is fumed silica.

30 3. The composition of claim 1 characterized in that the mole ratio of esterified phenyl groups to esterified alkoxy groups ranges from 4:1 to 0.7:1 to provide a fire resistant grease composition with an initial start-up torque at -40°C of less than 3.5 nm (500 in-oz.).

35 4. The composition of claim 2 characterized in that the mole ratio of esterified aryl groups to esterified alkoxy groups ranges from 4:1 to 0.7:1 to provide a fire resistant grease composition with an

initial start-up torque at -40°C of less than 3.5 nm (500 in-oz.).

5 5. The composition of claim 1 characterized in that the mixed alkoxy and phenyl triester of a phosphorus oxyacid is a mixture of a trialkoxy phosphate and a tri(alkylated phenyl)phosphate, wherein the alkoxy groups contain between 4 and 8 carbon atoms and the phenyl groups on the average contain from 0.2 to 0.6 alkyl moieties.

10 6. The composition of claim 1 characterized in that the mixed alkoxy and phenyl triester of a phosphorus oxyacid is a single phase mixture of a trialkoxy phosphite and a trialkoxy phosphate with a tri(alkylated phenyl)phosphate, wherein the alkoxy groups contain between 4 and 8 carbon atoms and the alkylated phenyl groups on the average contain from 0.2 to 0.6 alkyl moieties.

20 7. The composition of claim 2 characterized in that the mixed alkoxy and phenyl triester of a phosphorus oxyacid is a mixture of a trialkoxy phosphate and a tri(alkylated phenyl)phosphate, wherein the alkoxy groups contain between 4 and 8 carbon atoms and the alkylated phenyl groups on the average contain from 0.2 to 0.6 alkyl moieties.

25 8. The composition of claim 3 characterized in that the mixed alkoxy and phenyl phosphate triester is a mixture of a trialkoxy phosphate and a tri(alkylated phenyl)phosphate, wherein the alkoxy groups contain between 4 and 8 carbon atoms and the alkylated phenyl groups on the average contain from 0.2 to 0.6 alkyl moieties.

30 9. The composition of claim 4 characterized in that the mixed alkoxy and phenyl triester of a phosphorus oxyacid is a mixture of a trialkoxy phosphate and a tri(alkylated phenyl)phosphate, wherein the alkyl groups contain between 4 and 8 carbon atoms and

-18-

the alkylated phenyl groups on the average contain from 0.2 to 0.6 alkyl moieties.

10. A fire resistant grease composition characterized by between 85 and 95 parts by weight of a
5 base fluid having a flash point of at least 200°C and a pour point less than -40°C, the composition comprising a trialkoxy phosphate ester and a tri(alkylated phenyl)phosphate ester and between 5 and 15
10 parts by weight of a siliceous microparticulate inorganic thickener selected from the group consisting of clay and fumed silica, wherein each alkoxy group of the trialkoxy phosphate contains from 4 to 8 carbon atoms, and the alkylated phenyl groups contain on
15 the average between 0.2 and 0.6 alkyl moieties, and wherein the mole ratio of esterified alkylated alkoxy groups to esterified alkylated phenyl groups is between 0.7:1 to 4:1.

20

25

30

35

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US92/07211

<p>A. CLASSIFICATION OF SUBJECT MATTER IPC(5) :C09K 21/00; C10M 103/00 US CL :252/602,11,27,28,32.5,49.8 According to International Patent Classification (IPC) or to both national classification and IPC</p>																				
<p>B. FIELDS SEARCHED</p> <p>Minimum documentation searched (classification system followed by classification symbols) U.S. : 252/602,11,27,28,32.5,49.8</p> <p>Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched</p> <p>Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)</p>																				
<p>C. DOCUMENTS CONSIDERED TO BE RELEVANT</p> <table border="1"> <thead> <tr> <th>Category*</th> <th>Citation of document, with indication, where appropriate, of the relevant passages</th> <th>Relevant to claim No.</th> </tr> </thead> <tbody> <tr> <td>A</td> <td>US,A, 4,318,817 (HUEBNER), 09 MARCH 1982, Abstract, claims.</td> <td>1-10</td> </tr> <tr> <td>A</td> <td>US,A, 4,357,458 (ANTKOWIAK ET AL), 02 NOVEMBER 1982, Abstract, claims</td> <td>1-10</td> </tr> <tr> <td>A</td> <td>US,A, 4,490,266 (HENTSCHEL ET AL.),25 DECEMBER 1984, Abstract, claims.</td> <td>1-10</td> </tr> <tr> <td>A</td> <td>US,A, 4,770,670 (HAZBUN ET AL.), 12 SEPTEMBER 1988, Abstract, claims.</td> <td>1-10</td> </tr> <tr> <td>A</td> <td>US,A, 4,879,054 (WAYNICK), 07 NOVEMBER 1989, Abstract, claims.</td> <td>1-10</td> </tr> </tbody> </table>			Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.	A	US,A, 4,318,817 (HUEBNER), 09 MARCH 1982, Abstract, claims.	1-10	A	US,A, 4,357,458 (ANTKOWIAK ET AL), 02 NOVEMBER 1982, Abstract, claims	1-10	A	US,A, 4,490,266 (HENTSCHEL ET AL.),25 DECEMBER 1984, Abstract, claims.	1-10	A	US,A, 4,770,670 (HAZBUN ET AL.), 12 SEPTEMBER 1988, Abstract, claims.	1-10	A	US,A, 4,879,054 (WAYNICK), 07 NOVEMBER 1989, Abstract, claims.	1-10
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.																		
A	US,A, 4,318,817 (HUEBNER), 09 MARCH 1982, Abstract, claims.	1-10																		
A	US,A, 4,357,458 (ANTKOWIAK ET AL), 02 NOVEMBER 1982, Abstract, claims	1-10																		
A	US,A, 4,490,266 (HENTSCHEL ET AL.),25 DECEMBER 1984, Abstract, claims.	1-10																		
A	US,A, 4,770,670 (HAZBUN ET AL.), 12 SEPTEMBER 1988, Abstract, claims.	1-10																		
A	US,A, 4,879,054 (WAYNICK), 07 NOVEMBER 1989, Abstract, claims.	1-10																		
<p><input checked="" type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.</p>																				
<table border="0"> <tr> <td>* Special categories of cited documents:</td> <td>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</td> </tr> <tr> <td>"A" document defining the general state of the art which is not considered to be part of particular relevance</td> <td>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</td> </tr> <tr> <td>"E" earlier document published on or after the international filing date</td> <td>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</td> </tr> <tr> <td>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</td> <td>"&" document member of the same patent family</td> </tr> <tr> <td>"O" document referring to an oral disclosure, use, exhibition or other means</td> <td></td> </tr> <tr> <td>"P" document published prior to the international filing date but later than the priority date claimed</td> <td></td> </tr> </table>			* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention	"A" document defining the general state of the art which is not considered to be part of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone	"E" earlier document published on or after the international filing date	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art	"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"&" document member of the same patent family	"O" document referring to an oral disclosure, use, exhibition or other means		"P" document published prior to the international filing date but later than the priority date claimed							
* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention																			
"A" document defining the general state of the art which is not considered to be part of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone																			
"E" earlier document published on or after the international filing date	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art																			
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"&" document member of the same patent family																			
"O" document referring to an oral disclosure, use, exhibition or other means																				
"P" document published prior to the international filing date but later than the priority date claimed																				
<p>Date of the actual completion of the international search</p> <p>13 NOVEMBER 1992</p>		<p>Date of mailing of the international search report</p> <p>DEC 1992</p>																		
<p>Name and mailing address of the ISA/ Commissioner of Patents and Trademarks Box PCT Washington, D.C. 20231</p> <p>Facsimile No. NOT APPLICABLE</p>		<p>Authorized officer <i>Diane Moffett for</i> JOSEPH D. ANTHONY</p> <p>Telephone No. (703) 308-0446</p>																		

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US92/07211

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US,A, 4,898,683 (DEKURA), 06 FEBRUARY 1990, Abstract, claims.	1-10
A	US,A, 5,023,312 (ERICKSON ET AL.), 11 JUNE 1991, Abstract, claims.	1-10
&,P,A	US,A, 5,128,067 (PLACEK), 07 JULY 1992, Abstract, claims.	1-10