

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



WIPO | PCT

**(43) International Publication Date
18 May 2017 (18.05.2017)**

(10) International Publication Number

WO 2017/081056 A1

(51) **International Patent Classification:**
C08G 77/38 (2006.01) *C08G 77/388* (2006.01)
C08G 77/385 (2006.01) *G02F 1/1337* (2006.01)

(21) **International Application Number:** PCT/EP2016/077077

(22) **International Filing Date:** 9 November 2016 (09.11.2016)

(25) **Filing Language:** English

(26) **Publication Language:** English

(30) **Priority Data:**
15194024.4 11 November 2015 (11.11.2015) EP

(71) **Applicant:** ROLIC AG [CH/CH]; Chamerstrasse 50, 6300 Zug (CH).

(72) **Inventor:** CHAPPELLET, Sabrina; 37, rue des Jardins, 68128 Village-Neuf (FR).

(74) **Agent:** PEDUZZI, Elisa; Rolic Technologies Ltd., Gewerbestrasse 18, 4123 Allschwil (CH).

(81) **Designated States** (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) **Designated States** (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).


Published:

— with international search report (Art. 21(3))

Published:

— with international search report (Art. 21(3))

(54) Title: PHOTOALIGNMENT MATERIALS



(57) Abstract: The present invention relates to siloxane polymer, copolymer or oligomer for the photoalignment of liquid crystals, especially for the planar orientation of liquid crystals, and which derives from at least one monomer of formula (I), to compositions thereof, to a process for the preparation of said linear, branched or crosslinked siloxane polymer, and to its use for optical and electro optical devices, such as, liquid crystal devices (LCDs).

WO 2017/081056 A1

PHOTOALIGNMENT MATERIALS

5 The present invention relates to a siloxane oligomer, polymer or copolymer for the photoalignment of liquid crystals, namely for the planar orientation of liquid crystals or for the vertical alignment of liquid crystals, and to a process for preparing such a siloxane oligomer, polymer or copolymer. Further the present invention relates to compositions comprising said polymer, and to its use for optical and electro-optical 10 devices, such as liquid crystal devices (LCDs).

15 Several photo-aligning materials are already known in the art but there is still the demand to develop new photo-aligning materials having better optical qualities for the use for example in electro-optical applications. One example of such photo-aligning material is described in WO2013/050121 A1.

20 In the present invention new photo-aligning materials of formula (I) with superior optical properties are described. These photo-aligning materials give access to an economic manufacturing process and low energy consuming LCDs without decreasing the required technical properties. The present invention also provides a technologically implementable and economically favourable process for the production of the siloxane oligomer, polymer or copolymer of formula (I).

25 SUMMARY OF THE INVENTION

It is a first object of the present invention to provide a siloxane oligomer, polymer or copolymer comprising a monomer as described by formula (I) in its polymerized form.

30 It is a second object of the present invention to provide a composition comprising at least one said siloxane oligomer, polymer or copolymer and a second polymer which is different from the first one, and optionally an additive.

It is a third object of the present invention to provide a process for the preparation of said siloxane oligomer, polymer or copolymer.

It is a fourth object of the present invention to provide an orientation layer comprising
5 one said siloxane oligomer, polymer or copolymer, preferably further comprising a polymerisable liquid crystal or a polymerized liquid crystal.


It is a fifth object of the present invention to provide a method for preparing the orientation layer comprising said siloxane oligomer, polymer or copolymer and to
10 orientation layers obtained by such method.

It is a sixth object of the present invention to provide the use of said orientation layer to align liquid crystals, namely for the in plane switching (IPS) of liquid crystals or for the vertical alignment of liquid crystals, or for the alignment of liquid crystals comprising
15 polymerizable liquid crystals, or for the alignment of liquid crystals which are sandwiched between a pair of said orientation layers.

It is an seventh object of the present invention to provide a method for manufacturing a liquid crystal display comprising said photoaligning material or said orientation layer.

20 It is an eight object of the present invention to provide optical or electro-optical unstructured or structured elements comprising said siloxane oligomer, polymer or copolymer, or said orientation layer.

25 Thus, the present invention relates in a first aspect to a siloxane oligomer, polymer or copolymer for the photoalignment of liquid crystals, namely for the planar orientation of liquid crystals or for the vertical alignment of liquid crystals, and which derives from or comprises at least one monomer of formula (I):



5 wherein,

R_a represents OH, Cl, substituted or unsubstituted alkoxy group having 1 to 20 carbons, alkyl group having 1 to 20 carbons, or aryl group having 1 to 20 carbons;

10 S_1 represents a single bond or a straight-chain or branched, substituted or unsubstituted C_1-C_{24} alkylen, especially C_1-C_{12} alkylen, more especially C_1-C_8 alkylen, more especially C_1-C_6 alkylen, most especially C_1-C_4 alkylen, most especially C_1-C_2 alkylen in which one or more $-C-$, $-CH-$, CH_2- groups may be replaced by a linking group;

15 z is an integer from 0 to 15, preferably from 1 to 10, more preferably from 1 to 8, more preferably from 1 to 5, even more preferably from 1 to 3, most preferred n is 1;

20 Z_1 represents a single bond, or substituted or unsubstituted aliphatic or alicyclic group of C_3 to C_{12} , more preferably C_3 to C_{10} , even more preferably C_5 to C_8 , most preferably C_5 to C_6 .

n_0 is an integer from 0 to 4, preferably from 0 to 2; even more preferably from 1 to 2;

25 n_1 is an integer from 0 to 15, preferably from 1 to 10, more preferably from 1 to 8, more preferably from 1 to 5, most preferably from 1 to 3, most preferred n is 1;

n_2 is an integer from 1 to 15, preferably from 1 to 10, more preferably from 1 to 8, more preferably from 1 to 5, most preferably from 1 to 3, most preferred n is 1;

30

x_0 is an integer from 1 to 2;

X, Y each independently from each other represents H, F, Cl, CN;

5 S₂ represents a cyclic, aromatic, straight-chain or branched, substituted or unsubstituted C₁-C₂₄ alkylen, especially C₁-C₁₂ alkylen, more especially C₁-C₈ alkylen, more especially C₁-C₆ alkylen, most especially C₁-C₄ alkylen, most especially C₁-C₂ alkylen in which one or more -C-, -CH-, -CH₂- groups may be replaced by a linking group, wherein if more than one -C-, -CH-, -CH₂- group is replaced, the linking groups 10 may be the same or different;

15 E represents O, S, NH, C(C₁-C₆ alkyl), NR⁴, OC, OOC, OCONH, OCONR⁴, SCS, SC, wherein R⁴ is cyclic, straight chain or branched, substituted or unsubstituted C₁-C₂₄ alkyl wherein one or more -C-, -CH-, -CH₂- group(s) may be independently from each other be replaced by a linking group;

20 A represents halogen, H or substituted or unsubstituted C₁-C₂₄ alkyl, a substituted or unsubstituted C₁-C₂₄ alkenyl, a substituted or unsubstituted C₁-C₂₄ alkynyl, or a carboxylic acid, wherein one or more, -C-, -CH-, -CH₂- group may independently from each other be replaced by a heteroatom; preferably A is halogen, H, substituted or 25 unsubstituted C₁-C₂₄ alkyl or a C₁-C₂₄ alkoxy or a carboxylic acid; most preferably A is H, F, C₁-C₆ alkyl, C₁-C₆ alkoxy or a carboxylic acid;

25 R₀ represents OH, Cl, a linear or branched, substituted or unsubstituted alkoxy group having 1 to 20 carbons, in which a -C-, -CH-, -CH₂- could be replaced by unsubstituted or substituted C₆-C₂₀ aryl group;

30 Z₂ represents a chemical group having a delocalisation of its electronical density and/or inducing a delocalisation of the electronical density of its neighboring atom; and T represents a single bond or an unsubstituted or substituted, straight-chain C₁-C₁₆ alkyl.

In the context of the present invention the term "polymer" denotes linear, branched or crosslinked homo- or copolymer or oligomer.

The term "linking group", as used in the context of the present invention is preferably selected from an unsubstituted or substituted alicyclic group, preferably cyclohexylen, or an unsubstituted or substituted aromatic group, single bond, heteroatom, cationic carbohydrogen group such as

-(C+)-, -O-, -CO, -arylen-, -CO-O-, -O-CO-, $\text{--N}^<$, -CN, -NR¹-, -NR¹-CO-, -CO-NR¹,

-NR¹-CO-O-, -O-CO-NR¹-, -NR¹-CO-NR¹-, -CH=CH-, -C≡C-, -O-CO-O-, and -Si(CH₃)₂-O-Si(CH₃)₂-, and wherein:

R¹ represents a hydrogen atom or C₁-C₆alkyl;

with the proviso that oxygen atoms of linking groups are not directly linked to each other.

15

Substituents of the substituted alicyclic or aromatic group of the linking groups may be one or more and are preferably halogen, such as fluor, chloro, bromo, iodo, and preferably fluoro and chloro and more preferably fluor; or C₁-C₆ alkoxy, such as preferably methoxy, or trifluoromethyl.

20

In a preferred embodiment S_2 represents a single bond or a spacer unit, which is a cyclic, straight-chain or branched, substituted or unsubstituted C_1 - C_{24} alkylen, especially C_1 - C_{12} alkylen, especially C_1 - C_8 alkylen, more especially C_1 - C_6 alkylen, most especially C_1 - C_4 alkylen; in which one or more, preferably non-adjacent, $-C-$, $-CH-$,

25

preferably an unsubstituted or substituted alicyclic group, preferably cyclohexylen, or an unsubstituted or substituted aromatic group, preferably phenylene or naphthalene, single bond, heteroatom, -O-, -CO, -arylen-, -CO-O-, -O-CO-, -NR¹-, -NR¹-CO-,

and wherein:
R¹ represents a hydrogen atom or C₁-C₆alkyl; and more preferably an unsubstituted or substituted cyclohexylen, or an unsubstituted or substituted phenylen, single bond, -O-, -CO-, -arylen-, -CO-O-, -O-CO-, -NR¹-, -NR¹-CO-,

-CO-NR¹-, -NR¹-CO-O-, -O-CO-NR¹-, -NR¹-CO-NR¹-, -CH=CH-, -C≡C-, -O-CO-O- and wherein:

R¹ represents a hydrogen atom or C₁-C₆alkyl,

with the proviso that oxygen atoms of linking groups are not directly linked to each
5 other; or/and

C₁-C₂₄ alkylen, in which one or more, preferably non-adjacent, -C-, -CH-, -CH₂- group
may be unreplaced or at least once replaced by a non-aromatic, aromatic,
10 unsubstituted or substituted carbocyclic or heterocyclic group connected via bridging
groups; and , wherein if more than one -C-, -CH-, -CH₂- group is replaced, the linking
groups may be the same or different.

More preferably, S₂ is a single bond, straight-chain or branched, substituted or
unsubstituted C₁-C₈ alkylen, more especially C₁-C₆ alkylen, most especially C₁-C₄

15 alkylen within the above-given preferences; in which one or more, preferably non-
adjacent, -C-, -CH-, -CH₂- group may be unreplaced or at least once replaced

- by an unsubstituted or substituted alicyclic group, preferably cyclohexylen, or an
unsubstituted or substituted aromatic group, single bond, heteroatom, -O-, -CO,
-arylen-, -CO-O-, -O-CO-, -O-CO-O-; and more preferably

20 - by an unsubstituted or substituted cyclohexylen, or an unsubstituted or
substituted phenylen, single bond, -O-, -CO, -arylen-, -CO-O-, -O-CO-, -O-CO-
O-:

with the proviso that oxygen atoms of linking groups are not directly linked to each
other.

25 Substituents of the aromatic, alicyclic group or phenylene, cyclohexylen or the
carbocyclic or heterocyclic group S₂ are preferably, at least one halogen, such as
preferably chloro or fluoro, trifluoromethyl, C₁-C₆alkoxy, preferably methoxy, ethoxy,
propoxy, butoxy, pentoxy, hexoxy.

30 More preferably, S₂ is substituted or unsubstituted C₆-C₁₂ aromatic ring, or two C₆
aromatic rings connected by a single bond, or an alicyclic C₆ ring.

It is further encompassed by the present invention that if S_2 comprises an aromatic group, then the bonds to the remaining of the molecule can occur at any carbon atom of the aromatic ring.

5

More preferably S_1 is a single bond or a straight-chain or branched, substituted or unsubstituted C_1 - C_{24} alkylen in which one or more preferably non-adjacent -C-, -CH-, - CH_2 - group may be replaced by an heteroatom, a non-aromatic, aromatic, unsubstituted or substituted carbocyclic or heterocyclic group or $-(CH_2)_{n1}-$, $-(CH_2)_{n1}-O-(CH_2)_{n1}-$, $-(CH_2)_{n1}-O(OC)-(CH_2)_{n1}-$, $-(CH_2)_{n1}-(OC)O-(CH_2)_{n1}-$, $-(CH_2)_{n1}-NH-(CH_2)_{n1}-$, $-(CH_2)_{n1}-NH(OC)-(CH_2)_{n1}-$, $-(CH_2)_{n1}-(OC)NH-(CH_2)_{n1}-$, $-(CH_2)_{n1}-S-(CH_2)_{n1}-$, $-(CH_2)_{n1}-S(SC)-(CH_2)_{n1}-$, $-(CH_2)_{n1}-(SC)NH-(CH_2)_{n1}-$, $-(CH_2)_{n1}-NH(CS)-(CH_2)_{n1}-$, $-(CH_2)_{n1}-(SC)S-(CH_2)_{n1}-$, $-(CH_2)_{n1}-NHCONH-(CH_2)_{n1}-$, $-(CH_2)_{n1}-NHCSNH-(CH_2)_{n1}-$, $-(CH_2)_{n1}-O(CO)O-(CH_2)_{n1}-$, $-(CH_2)_{n1}-OCONH-(CH_2)_{n1}-$, $-(CH_2)_{n1}-NHOCO-(CH_2)_{n1}-$, wherein $n1$ is independently from each other 0, 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, preferably 0, 1, 2, 3, 4, 5, 6, 7, 8, more preferably 0, 1, 2, 3, 4, and most preferably 0, 1 or 2.

10

Most preferably S_1 is a single bond, a straight-chain C_1 - C_{24} alkylen, cyclohexylene, phenylene or $-(CH_2)_{n1}-$, $-(CH_2)_{n1}-O(OC)-(CH_2)_{n1}-$, $-(CH_2)_{n1}-NH(CO)O-(CH_2)_{n1}-$.

15

Preferably S_1 is a straight-chain C_1 - C_{24} alkylen, preferably a C_1 - C_{12} alkylen, more preferably a C_1 - C_6 alkylen, even more preferably a C_1 - C_4 alkylen, most preferred a C_1 - C_2 alkylen, even most preferred S_1 is an ethyl group.

20

In the context of the present invention the wording "chemical group having a delocalisation of its electronical density and/or inducing a delocalisation of the electronical density of its neighboring atom" means a "polar group". A polar group represents a chemical group having an asymmetrical electronic density distribution.

25

More preferably the polar group is selected from the group consisting of:

- groups containing oxygen, preferably hydroxy, carbonyl, such as a ketone or aldehyde group, carbonate ester, carboxylate, carboxyl acid, carboxyl ester, ether, such as C_1 - C_6 alkoxy, acetal or ketal group, orthocarbonate ester,

- groups containing cations, anions, salts;
- groups containing nitrogen, preferably carboxamide, primary amine, secondary amine, such as di-(C₁-C₁₆ alkyl)amino, tertiary amine, ammonium ion, primary ketimine, secondary ketimine, primary aldimine, secondary aldimine, aminocarbonyl, imide, azide, azo, cyanate, isocyanate, nitrate, nitrile, isonitrile, nitrosooxy, nitro, nitroso, pyridyl,
- 5 - groups containing sulfur, preferably sulfhydryl, sulfide, disulfide, sulfinyl, sulfonyl, sulfino, sulfo, thiocyanate, isothiocyanate, carbonothioyl
- groups containing phosphorus, preferably phosphino, phosphono, phosphate,
- 10 - unsubstituted or substituted, branched alkyl, wherein it may be at least one -C-, -CH-, or -CH₂- group be unreplaced or replaced by a heteroatom such as -O-, -S-, or by a primary, secondary, tertiary or quartary nitrogen, which is the ammonium cation; preferably isopropyl, tert-butyl, sec-butyl, neopentyl, isopentyl;
- 15 - unsubstituted or substituted, straight-chain alkyl, wherein at least one -C-, -CH-, or -CH₂- group is replaced by a heteroatom or by a primary, secondary, tertiary or quartary nitrogen, which is the ammonium cation;
- unsubstituted or substituted straight-chain or branched alkenyl, wherein one or more -C-, -CH-, -CH₂- group(s) may be independently from each other unreplaced or
- 20 replaced by a linking group, and preferably wherein the -en-group is in the terminal position of the alkenyl group, especially -O-alkenyl, -OOC-alkenyl, -OCO-alkenyl, -OCNHalkenyl, -NHCOalkenyl, which is preferably alkylacryloyloxy, preferably methacryloyloxy, acryloyloxy, vinyl, vinyloxy, allyl, allyloxy;
- unsubstituted or substituted straight-chain or branched alkynyl, wherein at least one
- 25 -C-, -CH-, or -CH₂- group be unreplaced or replaced by a linking group, and preferably wherein the -yl-group is in the terminal position of the alkynyl group, especially -O-alkynyl, -OOC-alkynyl, -OCO-alkynyl, -OCNHalkynyl, -NHCOalkynyl, which is preferably -Ξ-, -Ξ-CH₃, acetyl;
- 30 - unsubstituted or substituted carbocyclic or heterocyclic aromatic group or alicyclic group, incorporating preferably five, six, ten or 14 ring atoms, e.g. furan, benzyl or phenyl, pyridinyl, pyridinium cation, pyrimidinyl, pyrimidinium cation, naphthyl, which may form ring assemblies, such as biphenyl or triphenyl, which are uninterrupted or interrupted by at least a single heteroatom and/or at least a

single bridging group; or fused polycyclic systems, such as phenanthryl, tetralinyl. Preferably aromatic group are benzyl, phenyl, biphenyl or triphenyl. More preferred aromatic groups are benzyl, phenyl and biphenyl; further - unsubstituted or substituted alicyclic group is preferably a non-aromatic 5 carbocyclic or heterocyclic group, wherein heterocyclic group denotes a carbocyclic group, wherein at least one -C-, -CH-, or -CH₂- group is unreplaced or replaced by a heteroatom such as -O-, -S-, or by a primary, secondary, tertiary or quartinary nitrogen, which is the ammonium cation; and preferably the alicyclic group is a ring system, with 3 to 30 carbon atoms, and preferably 10 cyclopropyl, cyclobutyl, cyclopentyl, cyclopentyl, cyclohexyl, cyclohexyl, cyclohexadienyl, decalinyl, aziridinyl, oxiranyl, azirinyl, aziridium cation, oxirenyl, thiirenyl, diazirine diaziridium cation, oxaziridinyl, oxaziridium cation, dioxiranyl, azetidinyl, azetinium cation azete, azetidin cation, oxetanyl, oxetyl, thietanyl, thietyl, diazetidinyl, diazetidinium cation, dioxetanyl, dioxetyl, dithietanyl, dithietyl, 15 oxolanyl, thiolanyl, pyrrolidinyl, pyrrolidinium cationpyrrole, thiophe, pyrrolyl, furanyl, dioxanyl, dioxolanyl, dithiolanyl, maleinimidyl, maleinamidyl, oxazolinyl, oxazolidinyl, oxazolidinium cation, oxazolyl, isooxazolyl, imidazolyl, imidazolium cation, imidazolidinyl, imidazolidinium cation, pyrazolidinyl, pyrazolidinium cation, 20 pyrazolyl, pyrazolium cation, pyrazolinyl, thiazolidinyl, thiazolidinium cation, thiazolyl, thiazolium cation, thiazolinyl, isothiazolyl, furazanyl, oxadiazolyl, dithiazolyl, tetrazolyl, piperidinyl, a piperidium cation, a piperazium oxane, pyranyl, thianyl, thiopyranyl, piperazinyl, diazinyl, morpholinyl, oxazinyl, thiomorpholinyl, thiazinyl, dioxinyl, dioxanyl, dithiinyl, triazinyl, tetrazinyl, azepanyl, azepinyl, such as oxepanyl, oxepinyl, thiepanyl, thiepinyl, 25 homopiperazinyl, diazepinyl, thiazepinyl, azocanyl, azocinyl, oxeanyl, quinolinyl, quinolinium cation, benzothiphenyl, indolyl, benzofuranyl, acridinyl, dibenzothiophenyl, carbazolyl, dibenzofuranyl; ammonium cation, selected from an imidazolium cation, a pyrazolium cation.

30 Even more preferably the polar group is selected from the group consisting of:
- groups containing oxygen, preferably hydroxy, carbonyl, such as a ketone or aldehyde group, carbonate ester, carboxylate, carboxyl acid, carboxyl ester, ether, such as C₁-C₆alkoxy, acetal or ketal group, orthocarbonate ester,

- groups containing nitrogen, preferably carboxamide, primary amine, secondary amine, such as di-(C₁-C₁₆alkyl)amino, tertiary amine, ammonium ion, primary ketimine, secondary ketimine, primary aldimine, secondary aldimine, aminocarbonyl, imide, azide, azo, cyanate, isocyanate, nitrate, nitrile, isonitrile, nitrosooxy, nitro, nitroso, pyridyl,

5 - unsubstituted or substituted straight-chain or branched alkynyl, which is preferably –Ξ-, –Ξ-CH₃, acetyl;

- unsubstituted or substituted carbocyclic or heterocyclic aromatic group or alicyclic group, incorporating preferably five, six, ten or 14 ring atoms, e.g. furan, benzyl or phenyl, pyridinyl, pyridinium cation, pyrimidinyl, pyrimidinium cation, naphthyl, which may form ring assemblies, such as biphenyl or triphenyl, which are uninterrupted or interrupted by at least a single heteroatom and/or at least a single bridging group; or fused polycyclic systems, such as phenanthryl, tetralinyl. Preferably aromatic group are benzyl, phenyl, biphenyl or triphenyl.

10 15 More preferred aromatic groups are benzyl, phenyl and biphenyl;

More preferred are ether, such as C₁-C₆ alkoxy, di-(C₁-C₁₆ alkyl)amino, nitrile, pyridyl, unsubstituted or substituted straight-chain or branched alkynyl, which is preferably –Ξ-, –Ξ-CH₃, acetyl; unsubstituted or substituted carbocyclic or heterocyclic aromatic group

20 or alicyclic group, incorporating preferably five, six, ten or 14 ring atoms, e.g. furan, benzyl or phenyl, pyridinyl, pyridinium cation, pyrimidinyl, pyrimidinium cation, naphthyl, which may form ring assemblies, such as biphenyl or triphenyl, which are uninterrupted or interrupted by at least a single heteroatom and/or at least a single bridging group; or fused polycyclic systems, such as phenanthryl, tetralinyl. Preferably 25 aromatic group are benzyl, phenyl, biphenyl or triphenyl. More preferred aromatic groups are benzyl, phenyl and biphenyl.

30 Most preferred is ether, such as C₁-C₆ alkoxy, di-(C₁-C₁₆ alkyl)amino, nitrile, pyridyl, unsubstituted or substituted straight-chain or branched alkynyl, which is preferably –Ξ-, –Ξ-CH₃, acetyl; unsubstituted or substituted benzyl, phenyl or biphenyl; and especially preferred is nitrile, C₁-C₆ alkoxy.

In a preferred embodiment of the invention any substituent of the invention may represent a polar group.

A bridging group as used in the context of the present invention is preferably selected from -CH(OH)-, -CO-, -CH₂(CO)-, -SO-, -CH₂(SO)-, -SO₂-, -CH₂(SO₂)-, -COO-, -OCO-, -COCF₂-, -CF₂CO, -S-CO-, -CO-S-, -SOO-, -OSO-, -SOS-, -O-CO-O-, -CH₂-CH₂-, 5 -OCH₂-, -CH₂O-, -CH=CH-, -C≡C-, -(C₁—C₆alkyl)₁₋₆C=CH-COO-, -CH=CH-COO-, -OCO-CH=CH-, -OCO-CH=C(C₁—C₆alkyl)₁₋₆CH-, -CH=N-, -C(CH₃)=N-, -N=N-, heteroatom, cationic carbohydrogen group such as -(C+)-, or a single bond; or a 10 cyclic, straight-chain or branched, substituted or unsubstituted C₁-C₂₄alkylen, wherein one or more -C-, -CH-, -CH₂- groups may independently from each other be unreplaced or replaced by a linking group as described above.

In the context of the present invention alkyl has the meaning of unsubstituted or substituted alkyl, wherein substituted alkyl has also the meaning alkylen. Alkyl, alkyloxy, alkoxy, alkylcarbonyloxy, acryloyloxyalkoxy, acryloyloxyalkyl, 15 acryloyloxyalken, alkyloxycarbonyloxy, alkylacryloyloxy, methacryloyloxyalkoxy, methacryloyloxyalkyl, methacryloyloxyalken, alkylmethacryloyloxy, alkylmethacryloyloxy, alkylvinyl, alkylvinyloxy and alkylallyloxy and alkylene, as used in the context of the present invention denote with their alkyl residue, respectively their alkylene residue, a cyclic, straight-chain or branched, substituted or unsubstituted 20 alkyl, respectively alkylene, in which one or more, preferably non-adjacent, -C-, -CH-, or -CH₂- group may be unreplaced or replaced by a linking group, preferably replaced by -O-, NH, -COO, OCO.

Further, in the context of the present invention "alkyl" is branched or straight chain, 25 unsubstituted or substituted alkyl, preferably C₁-C₄₀ alkyl, especially C₁-C₃₀ alkyl, preferably C₁-C₂₀ alkyl, more preferably C₁-C₁₆ alkyl, most preferably C₁-C₁₀ alkyl and especially most preferably C₁-C₆ alkyl. Accordingly alkylen is for example C₁-C₄₀ alkylen, especially C₁-C₃₀ alkylen, preferably C₁-C₂₀ alkylen, more preferably C₁-C₁₆ alkylen, most preferably C₁-C₁₀ alkylen and especially most preferably C₁-C₆ alkylen. 30 In the context of the present invention the definitions for alkyl given below, are applicable to alkylene in analogy.

C_1 - C_6 alkyl is for example methyl, ethyl, propyl, isopropyl, butyl, sec.-butyl, tert.-butyl, pentyl or hexyl.

C_1 - C_{10} alkyl is for example methyl, ethyl, propyl, isopropyl, butyl, sec.-butyl, tert.-butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl.

5 C_1 - C_{16} alkyl is for example methyl, ethyl, propyl, isopropyl, butyl, sec.-butyl, tert.-butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl or hexadecyl.

C_1 - C_{20} alkyl is for example methyl, ethyl, propyl, isopropyl, butyl, sec.-butyl, tert.-butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, 10 pentadecyl, hexadecyl, heptadecyl, octadecyl, nondecyl, eicosyl.

C_1 - C_{24} alkyl is for example methyl, ethyl, propyl, isopropyl, butyl, sec.-butyl, tert.-butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl, nondecyl, eicosyl.

15 C_1 - C_{30} alkyl is for example methyl, ethyl, propyl, isopropyl, butyl, sec.-butyl, tert.-butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl, nondecyl, eicosyl, heneicosyl, tricosyl, tetracosy, pentacosyl, hexacosdy, heptacosyl, octacosyl, nonacosy or triacontyl.

20 C_1 - C_{40} alkyl is for example methyl, ethyl, propyl, isopropyl, butyl, sec.-butyl, tert.-butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl, nondecyl, eicosyl, heneicosyl, tricosyl, tetracosy, pentacosyl, hexacosdy, heptacosyl, octacosyl, nonacosy, triacontyl or tetacontyl.

C_1 - C_6 alkoxy is for example methoxy, ethoxy, propoxy, isopropoxy, butoxy, sec.-butoxy, tert.-butoxy, pentoxy or hexoxy.

25 C_1 - C_{20} acryloyloxyalkylene, preferably C_1 - C_{10} acryloyloxyalkylene, C_1 - C_6 acryloyloxyalkylene is for example acryloyloxymethylen, acryloyloxyethylene, acryloyloxypropylene, acryloyloxyisopropylene, acryloyloxybutylene, acryloyloxy-sec.-butylene, acryloyloxpentylene, acryloyloxyhexylene, acryloyloxyheptylene, acryloyloxyoctylene, acryloyloxyoctylene, acryloyloxyhexylene, acryloyloxydecylene, acryloyloxyundecylene, 30 acryloyloxydodecane, acryloyloxytridecylene, acryloyloxytetradecylene, acryloyloxpentyldecane, acryloyloxyhexadecylene, acryloyloxyheptadecylene, acryloyloxyoctadecylene, acryloyloxyhexadecylene, acryloyloxyeicosylene. C_1 - C_{20} methacryloyloxyalkylene, preferably C_1 - C_{10} methacryloyloxyalkylene,

C₁-C₆ methacryloyloxyalkylene is for example methacryloyloxymethylen, methacryloyloxyethylene, methacryloyloxypropylene, methacryloyloxyisopropylene, methacryloyloxybutylene, methacryloyloxy-sec.-butylene, methacryloyloxypentylene, methacryloyloxyhexylene, methacryloyloxyheptylene, methacryloyloxyoctylene, 5 methacryloyloxynonylene, methacryloyloxydecylene, methacryloyloxyundecylene, methacryloyloxydodecane, methacryloyloxytridecylene, methacryloyloxytetradecylene, methacryloyloxpentyldecane, methacryloyloxyhexadecylene, methacryloyloxyheptadecylene, methacryloyloxyoctadecylene, methacryloyloxynondecylene, methacryloyloxyeicosylene.

10 C₁-C₂₀ acryloyloxyalkoxy, preferably C₁-C₁₀ acryloyloxyalkoxy, C₁-C₆ acryloyloxyalkoxy is for example acryloyloxymethoxy, acryloyloxyethoxy, acryloyloxypropoxy, acryloyloxyisopropoxy, acryloyloxybutoxy, acryloyloxy-sec.-butoxy, acryloyloxpentoxy, acryloyloxyhexoxy, acryloyloxyheptoxy, acryloyloxyoctoxy, acryloyloxynonoxy, acryloyloxydecoxy, acryloyloxyundecoxy, acryloyloxydodecanoxy, 15 acryloyloxytridecyloxy.

C₁-C₂₀ methacryloyloxyalkoxy, preferably C₁-C₁₀ methacryloyloxyalkoxy, C₁-C₆ methacryloyloxyalkoxy is for example methacryloyloxymethoxy, methacryloyloxyethoxy, methacryloyloxypropoxy, methacryloyloxyisopropoxy, methacryloyloxybutoxy, methacryloyloxy-sec.-butoxy, methacryloyloxpentoxy, 20 methacryloyloxyhexoxy, methacryloyloxyheptoxy, methacryloyloxyoctoxy, methacryloyloxynonoxy, methacryloyloxydecoxy, methacryloyloxyundecoxy, methacryloyloxydodecanoxy, methacryloyloxytridecyloxy.

25 An aliphatic group is for example a saturated or unsaturated, mono-, bi-, tri-, tetra-, penta-, hexa-, hepta-, octa-, nona-, deca-valent alkyl, alkylene, alkyloxy, alkylcarbonyloxy, acryloyloxy, alkylacryl, alkylmethacryl, alkyl(en)acryl(en), alkyl(en)methacryl(en), alkyloxycarbonyloxy, alkyloxycarbonyloxy methacryloyloxy, alkylvinyl, alkylvinylloxy or alkylallyloxy, which may comprise one or more heteroatom and/or bridging group.

30 An alicyclic group is preferably a non-aromatic group or unit and may be substituted or unsubstituted. Preferably an alicyclic group is a non-aromatic carbocyclic or heterocyclic group and represents for example ring systems, with 3 to 30 carbon atoms, as for example cyclopropane, cyclobutane, cyclopentane, cyclopentene,

cyclohexane, cyclohexene, cyclohexadiene, decaline, tetrahydrofuran, dioxane, pyrrolidine, piperidine or a steroidal skeleton such as cholesterol. Preferred alicyclic group is cyclohexane. Substituents of an alicyclic group are halogene, preferably fluor or/and chloro, or C₁-C₆alkoxy which is substituted or unsubstituted with halogen,

5 leading to the formation of an ether group, preferably methoxy or triflourmethyl or one or more hydroxyl groups. Preferred is a cyclohexanol group or a cyclohexan group substituted with a C₁-C₆alkoxy, which is then called in the context of the present invention a cyclostanether group.

10 The term "aromatic", as used in the context of the present invention, preferably denotes unsubstituted or substituted carbocyclic and heterocyclic groups, incorporating five, six, ten or 14 ring atoms, e.g. furan, benzene or phenylene, pyridine, pyrimidine, naphthalen, which may form ring assemblies, such as biphenylene or triphenylen, which are uninterrupted or interrupted by at least a single heteroatom and/or at least a 15 single bridging group; or fused polycyclic systems, such as phenanthrene, tetraline. Preferably aromatic group are benzene, phenylene, biphenylene or triphenylen. More preferred aromatic group is benzene, phenylene and biphenylene. Especially preferred substituents of an aromatic group or of a carbocyclic and heterocyclic groups are halogene, preferably fluor or/and chloro, C₁-C₆alkoxy, preferably methoxy or 20 triflourmethyl.

A carbocyclic or heterocyclic aromatic group or alicyclic group incorporates preferably three, four, five, six, ten or 14 ring atoms, as for example aziridin, epoxy, cyclopropyl, furan, pyrrolidin, oxazolin, imidazol, benzene, pyridine, triazine, pyrimidine, 25 naphthalene, phenanthrene, biphenylene or tetraline units, preferably naphthalene, phenanthrene, biphenylene or phenylene, more preferably naphthalene, biphenylene or phenylene, and most preferably phenylene. Especially preferred substituents of carbocyclic and heterocyclic aromatic groups are halogene, preferably fluor or/and chloro, C₁-C₆alkoxy, preferably methoxy or 30 triflourmethyl.

The unsubstituted or substituted carbocyclic or heterocyclic aromatic or alicyclic group is for example unsubstituted or mono- or poly-substituted. Preferred substitutents of carbocyclic or heterocyclic aromatic groups are at least one triflourmethyl, halogen,

such as fluor, chloro, bromo, iodo, especially fluor or/and chloro, and more especially fluor; hydroxyl, a polar group, acryloyloxy, alkylacryloyloxy, alkoxy, especially methoxy, ethoxy, propoxy; alkylcarbonyloxy, alkyloxycarbonyloxy, alkyloxocarbonyloxy, methacryloyloxy, vinyl, vinyloxy and/or allyloxy group, wherein the alkyl residue has

5 preferably from 1 to 20 carbon atoms, and more preferably having from 1 to 10 carbon atoms. Preferred polar groups are nitro, nitrile or a carboxy group, and/or a cyclic, straight-chain or branched C₁-C₃₀ alkyl, which is unsubstituted, mono- or poly-substituted. Preferred substituents of C₁-C₃₀ alkyl are methyl, fluorine and/or chlorine, wherein one or more, preferably non-adjacent, -C-, -CH-, -CH₂- group may 10 independently of each other be replaced by a linking group. Preferably, the linking group is selected from -O-, -CO-, -COO- and/or -OCO-.

A monocyclic ring of five or six atoms is for example furan, benzene, preferably phenylene, pyridine, pyrimidine, pyridine cation, pyrimidine cation.

15 A bicyclic ring system of eight, nine or ten atoms is for example naphthalene, biphenylene or tetraline.

A tricyclic ring system of thirteen or fourteen atoms is for example phenanthrene.

The term "phenylene", as used in the context of the present invention, preferably denotes a 1,2-, 1,3- or 1,4-phenylene group, which is optionally substituted. Especially 20 preferred substituents of phenylene are halogen, preferably fluor or/and chloro, C₁-C₆ alkoxy, preferably methoxy or triflourmethyl. It is preferred that the phenylene group is either a 1,3- or a 1,4-phenylene group. 1,4-phenylene groups are especially preferred.

The term "halogen" denotes a chloro, fluoro, bromo or iodo substituent, preferably a 25 chloro or fluoro substituent, and more preferably fluoro.


The term "heteroatom", as used in the context of the present invention is a neutral, anionic or cationic heteroatom and primarily denotes oxygen, sulphur and nitrogen, halogen, such as fluoro, chloro, bromo, iodo, and more preferably fluoro and/or 30 chloro, and most preferably fluoro; preferably halogen, oxygen and nitrogen, in the latter case primary amine, secondary amine, tertiary amine or quartarnary ammonium cation, preferably in the form of -NH-.

The term "optionally substituted" as used in the context of the present invention

primarily means substituted by lower alkyl, such as C₁-C₆ alkyl, lower alkoxy, such as C₁-C₆ alkoxy, hydroxy, halogen or by a polar group as defined above.

With respect to straight chain or branched alkyl, alkylene, alkoxy, alkylcarbonyloxy, acryloyloxyalkoxy, acryloyloxyalkyl, acryloyloxyalkene, alkyloxycarbonyloxy, alkylacryloyloxy, methacryloyloxyalkoxy, methacryloyloxyalkyl, methacryloyloxyalkene, alkylmethacryloyloxy, alkylmethacryloyloxy, alkylvinyl, alkylvinyloxy, alkylallyloxy and alkylene groups it is repeatedly pointed out that some or several of the -C-, -CH-, -CH₂- groups may be replaced e.g. by heteroatoms, but also by other groups, preferably bridging groups. In such cases it is generally preferred that such replacement groups are not directly linked to each other. It is alternatively preferred that heteroatoms, and in particular oxygen atoms are not directly linked to each other.

In a preferred embodiment, the first aspect of the invention relates to siloxane oligomer, polymer or copolymer for the photoalignment of liquid crystals, especially for the planar orientation of liquid crystals, and which derives from or comprises at least one monomer of formula (I):



20

wherein

R_a, z, n₁, n₂, x, S₂, A, R₀, T are as described above; and

25

Z₁ represents a substituted or unsubstituted C₅-C₆ aliphatic or alicyclic group;

S₁ represents a substituted or unsubstituted C₁-C₂₄ straight chain alkyl;


30

E represents O, or S or NH;

X, Y are H; and

5 Z₂ is C₁-C₆ alkoxy, di-(C₁-C₁₆ alkyl)amino, nitrile, pyridyl, unsubstituted or substituted straight-chain or branched alkynyl, amine, acrylate, C₁-C₆ alkyl ester, unsubstituted or substituted carbocyclic or heterocyclic aromatic group or alicyclic group.

10 In another preferred embodiment, the first aspect of the invention relates to a siloxane oligomer, polymer or copolymer for the photoalignment of liquid crystals, especially for the planar orientation of liquid crystals, and which derives from or comprises at least one monomer (I):



15

wherein

20 R_a, z, n₁, n₂, x, S₂, R₀, T are as described above; and

A represents H, one or more halogens, one or more methoxy groups or one or more carboxylic groups;

25 Z₁ represents a substituted or unsubstituted C₅-C₆ alicyclic group;

S₁ represents a substituted or unsubstituted C₁-C₂₄ straight chain alkyl;

E represents O, or S or NH;


30 X, Y are H; and

Z_2 is C_1 - C_6 alkoxy, di- $(C_1$ - C_{16} alkyl)amino, nitrile, pyridyl, unsubstituted or substituted straight-chain or branched alkynyl, amine, acrylate, C_1 - C_6 alkyl ester, unsubstituted or substituted carbocyclic or heterocyclic aromatic group or alicyclic group.

5

In another preferred embodiment, the first aspect of the invention relates to a siloxane oligomer, polymer or copolymer for the photoalignment of liquid crystals, especially for the planar orientation of liquid crystals, and which derives from or comprises at least one monomer (I):

10



15

wherein

R_a , z , n_1 , n_2 , x , S_2 , R_0 , T are as described above; and

20

A represents H , one or more halogens, one or more methoxy groups or one or more carboxylic groups;

Z_1 represents a substituted or unsubstituted C_5 - C_6 alicyclic group;

S_1 represents a substituted or unsubstituted C_1 - C_{24} straight chain alkyl;

25


E represents O ;

X , Y are H ; and

Z_2 is C_1 - C_6 alkoxy, di- $(C_1$ - C_{16} alkyl)amino, nitrile, pyridyl, unsubstituted or substituted straight-chain or branched alkynyl, amine, acrylate, C_1 - C_6 alkyl ester, unsubstituted or substituted carbocyclic or heterocyclic aromatic group or alicyclic group.

5 In a further preferred embodiment the first aspect of the invention relates to a siloxane oligomer, polymer or copolymer for the photoalignment of liquid crystals, especially for the planar orientation of liquid crystals, and which derives from or comprises at least one monomer (I):

10



wherein:

R_a , z , n_1 , n_2 , x , S_2 , R_0 , Z_2 , B are as described above; and

15

A represents H , one or more halogens, one or more methoxy groups or one or more carboxylic groups;

Z_1 is a substituted or unsubstituted cyclohexanol group or a substituted or unsubstituted cyclohexanether group;

20

S_1 is ethyl group;

E is O ;

25

X , Y are H ; and

Z_2 is C_1 - C_6 alkoxy, di- $(C_1$ - C_{16} alkyl)amino, nitrile, pyridyl, unsubstituted or substituted straight-chain or branched alkynyl, amine, acrylate, C_1 - C_6 alkyl ester, unsubstituted or substituted carbocyclic or heterocyclic aromatic group or alicyclic group.

In the context of the present invention, a copolymer is defined as a polymer comprising at least two different types of monomers, wherein the first monomer is a compound of formula (I) and the at least second monomer is different from the first one.

5

Furthermore, a copolymer is defined as a polymer having different polymer backbones which are also called backbone chains or main chains of a polymer. The polymer backbone is a series of covalently bound atoms that together create the continuous chain of a polymer.

10

Further, the side chain of the polymer is a chemical group that is attached to the polymer backbone. The side chain may contain the photoreactive group, or the non-photoreactive group or the group represented by the parentheses in formula (I).

15

Further a copolymer is defined as a polymer having the same backbone chains and different side chains.

Further a copolymer is defined as a polymer having different backbone chains and different side chains.

20

In one embodiment of the invention, the copolymer comprises a first monomer of formula (I) and a second monomer comprising a photoreactive group.

25

In a further embodiment of the invention, the copolymer comprises a first monomer having a fist monomer of formula (I) and a second monomer having one non-photoreactive group.

30

The non-photoreactive group, can be a carbocyclic or heterocyclic aromatic and/or alicyclic or aliphatic group, which is unsubstituted or substituted by an acrylate group, vinyl group, allyl group, epoxy group, maleinimide group, straight-chain or branched C₁-C₁₆ alkyl group, C₁-C₁₆ alkylacrylate group, C₁-C₁₆ alkylvinyl group, C₁-C₁₆ alkylallyl group, C₁-C₁₆ alkylepoxy group, C₁-C₁₆ alkylmaleinimide group, preferably unsubstituted or substituted by C₁-C₁₆ alkylacrylate group, more preferably by C₁-C₆ alkylacrylate group.

Preferably the non-photoreactive group is an unsubstituted or substituted steroidal skeleton such as a cholesterol group, which is uninterrupted or interrupted by at least a single heteroatom and/or at least a single bridging group. Preferably, a cholesterol group is cholesteryl, cholestanyl, cholestan.

5 More preferred is a non-photoreactive group substituted or unsubstituted and selected from a carbocyclic or heterocyclic aromatic group, preferably a substituted or unsubstituted phenylen-(bridging group)-phenylene-, or -(phenylene)_{n1}-(bridging group)_{m1}-(phenylene)_{n2}-(bridging group)_{m2}-(cyclohexylen)_{n3}-, wherein bridging group has the same meaning and preferences as given below, and n1, n2, n3 represent an integer of 0, 1, 2, 3, 3 or 4 and m1, m2 an integer of 0 or 1, with proviso that at least one n1, n2, n3 or n4 is >1; or the non-photoreactive group is naphthylene or phenylene, which are unsubstituted or substituted by at least one, preferably two, 10 acrylate group, vinyl group, allyl group, epoxy group, maleinimide group, straight-chain or branched C₁-C₁₆ alkyl group, C₁-C₁₆ alkylacrylate group, C₁-C₁₆ alkylvinyl group, C₁-C₁₆ alkylallyl group, C₁-C₁₆ alkylepoxy group, C₁-C₁₆ alkyl-maleinimide group, preferably unsubstituted or substituted by C₁-C₁₆ alkylacrylate group, more preferably by C₁-C₆ alkylacrylate group; or selected from a carbocyclic or heterocyclic alicyclic group, 15 preferably a steroidal skeleton, preferred steroidal skeleton is a cholesterol group, which is uninterrupted or interrupted by at least a single heteroatom and/or at least a single bridging group. More preferred steroid skeleton is a cholesterol group, preferred is cholesteryl, cholestanyl, cholestan.

20 Especially more preferred is a non-photoreactive group substituted or unsubstituted a carbocyclic or heterocyclic aromatic group, preferably selected from di-(phenyl)alkylen, such as -phenylene-ethylene-phenylene-; -phenylene-propylene-phenylene-, -phenylene-isopropylene-phenylene-, phenylene-butylene-phenylene-, -phenylene-pentylene-phenylene-naphthylene, phenylene, fluorene, benzoic acid, 25 benzyl alcohol, benzoic acid, 2-methoxybenzoic acid, octafluoro-biphenyl, benzidine, fluorenone, 3,5,3',5'-tetrabromo-biphenyl, 2,2'-dichloro-1,1'-biphenyl, 1,11-dimethyl-5,7-dihydro-dibenzo(a,c)cyclohepten-6-one, dibenzo(1,2)dithiine, benzo-phenone, 30 diphenylmethane, 4,4-bis-(4-hydroxyphenyl)-valeric acid, 2,2-bis(4-hydroxyphenyl)-hexafluoropropane, 2,2-bis(4-methylphenyl)-hexafluoropropane, 2,2-bis(phenyl)hexa-

fluoropropane, bis-(4-chloro-phenyl)-methanone, bis-(4—dimethyl -phenyl)-methanone, benzidine-3,3'-dicarboxylic acid, 1,1'-binaphthyl, diphenyl-3,3'-diglycolic acid, dihydroethidium, 2,2'-dichloro-5,5'-dimethoxybenzidine, 3-methoxybenzidine, 3,3'-dichlorobenzidine (diphenyl-d6), 2,2'-

5 bis(trifluoromethyl)benzidine, 3,3'-bis(trifluoromethyl)-benzidine, 3,3'-dichloro-benzidine-d6, tetramethylbenzidine; or selected from a carbocyclic or heterocyclic alicyclic group, preferably a steroidal skeleton, preferred steroidal skeleton is a cholesterol group, which is uninterrupted or interrupted by at least a single heteroatom and/or at least a single bridging group. More preferred steroid skeleton is a cholesterol 10 group, preferably is cholesteryl, cholestanyl, cholestan.

A siloxane oligomer, polymer or copolymer is a polymer, oligomer or copolymer comprising silicon atoms in the polymer backbone or main chain of the polymer.

15 In a second embodiment the invention relates to a composition comprising at least one said siloxane oligomer, polymer or copolymer as described above and a second polymer which is different from the first one.

20 In a preferred second embodiment the invention relates to a composition comprising at least one siloxane oligomer, polymer or copolymer as described above and a second polymer which is different from the first one and an additive.

25 The second polymer of the second embodiment of the present invention is a polymer selected from the group consisting of: polyamic acids, polyamic esters, polyimides, polymerizable liquid crystals, polymerized liquid crystals (LCP), polysiloxanes, polyacrylate, polymethacrylate, polyacrylamide, polymethacrylamide, polyvinylether, polyvinylester, polyallylether, polyallylester, polystyrene, polyamidimide, polymaleic acid, polyfumaric acid, polyurethane and derivatives thereof, polystyrol, polyester, polyurethane, polyethylene, polypropylen, polyvinylchloride, polytetrafluoroethylen, 30 polycarbonate, polysilane, polymaleinimide, polynorbornene, polyterephthalate, polycyanostilbenes and dendrimere.

More preferred is polyamic acid or polyimide. Most preferred is polyamic acid.

The term "diamine" or "diamine compound" is to be understood as designating a chemical structure which has at least two amino groups, i.e. which may also have 3 or more amino groups.

5 If the second polymer is a diamine, the diamine represents an optionally substituted aliphatic, aromatic or alicyclic diamino group having from 1 to 40 carbon atoms and preferably made from or selected from the following group of structures: aniline, p-phenylenediamine, m-phenylenediamine, benzidine, diaminofluorene, or their derivatives, with the proviso that compounds listed which do not carry two amino

10 groups are taken as derivatives with at least one additional amino group, and more preferably made from or selected from the following commercially available amino compounds (example of suppliers: Aldrich, ABCR, ACROS, Fluka) which can also be used as comonomers:

15 4-amino-2,3,5,6-tetrafluorobenzoic acid
4-amino-3,5-diiodobenzoic acid, 3,4-diaminobenzoic acid
4-amino-3-methylbenzoic acid,
4-amino-2-chlorobenzoic acid
4-aminosalicylic acid

20 4-aminobenzoic acid
4-aminophthalic acid
1-(4-aminophenyl)ethanol
4-aminobenzyl alcohol
4-amino-3-methoxybenzoic acid

25 4-aminophenyl ethyl carbinol
4-amino-3-nitrobenzoic acid
4-amino-3,5-dinitrobenzoic acid
4-amino-3,5-dichlorobenzoic acid
4-amino-3-hydroxybenzoic acid

30 4-aminobenzyl alcohol hydrochloride
4-aminobenzoic acid hydrochloride
pararosaniline base
4-amino-5-chloro-2-methoxybenzoic acid
4-(hexafluoro-2-hydroxyisopropyl)aniline

5 piperazine-p-amino benzoate
4-amino-3,5-dibromobenzoic acid
isonicotinic acid hydrazide p-aminosalicylate salt
4-amino-3,5-diodosalicylic acid
4-amino-2-methoxybenzoic acid
2-[2-(4-aminophenyl)-2-hydroxy-1-(hydroxymethyl)ethyl]isoindoline-1,3-dione
4-amino-2-nitrobenzoic acid
2,4-diaminobenzoic acid
p-aminobenzoic acid,
10 [3,5-3h]-4-amino-2-methoxybenzoic acid
L-(+)-threo-2-amino-1-(4-aminophenyl)-1,3-propanediol
L-(+)-threo-2-(N,N-dimethylamino)-1-(4-aminophenyl)-1,3-propanediol
ethyl 2-(4-aminophenyl)-3,3,3-trifluoro-2-hydroxypropanoate
ethyl 2-(4-amino-3-methylphenyl)-3,3,3-trifluoro-2-hydroxypropanoate
15 ethyl 2-(4-amino-3-methoxyphenyl)-3,3,3-trifluoro-2-hydroxypropanoate
3,4-diaminobenzyl alcohol dihydrochloride
4-aminonaphthalene-1,8-dicarboxylic acid
4-amino-3-chloro-5-methylbenzoic acid
4-amino-2,6-dimethylbenzoic acid
20 4-amino-3-fluorobenzoic acid
4-amino-5-bromo-2-methoxybenzenecarboxylic acid
2,7-diaminofluorene
4,4'-diaminoctafluorobiphenyl
3,3'-diaminobenzidine
25 3,3',5,5'-tetramethylbenzidine
3,3'-dimethoxybenzidine
o-tolidine
3,3'-dinitrobenzidine
2-nitrobenzidine
30 3,3'-dihydroxybenzidine
o-tolidine sulfone
benzidine,
3,3'-dichlorobenzidine
2,2',5,5'-tetrachlorobenzidine,

benzidine-3,3'-dicarboxylic acid
4,4'-diamino-1,1'-binaphthyl
4,4'-diaminodiphenyl-3,3'-diglycolic acid
dihydroethidium
5 o-dianisidine
2,2'-dichloro-5,5'-dimethoxybenzidine
3-methoxybenzidine
3,3'-dichlorobenzidine (diphenyl-d6),
2,7-diamino-9-fluorenone
10 3,5,3',5'-tetrabromo-biphenyl-4,4'-diamine
2,2'-bis(trifluoromethyl)benzidine
2,2'-dichloro[1,1'-biphenyl]- 4,4'-diamine
3,9-diamino-1,11-dimethyl-5,7-dihydro-dibenzo(a,c)cyclohepten-6-one
3,3'-bis(trifluoromethyl)benzidine
15 dibenzo(1,2)dithiine-3,8-diamine
3,3'-tolidine-5-sulfonic acid
3,3'-dichlorobenzidine-d6
tetramethylbenzidine
3,3'-diaminobenzophenone, 3,3'-diaminodiphenylmethane,
20 4,4-bis-(3-amino-4-hydroxyphenyl)-valeric acid
2,2-bis(3-amino-4-hydroxyphenyl)hexafluoropropane
2,2-bis(3-amino-4-methylphenyl)hexafluoropropane
tetrabromo methylenedianiline
2,7-diamino-9-fluorenone
25 2,2-bis(3-aminophenyl)hexafluoropropane
bis-(3-amino-4-chloro-phenyl)-methanone
bis-(3-amino-4-dimethylamino-phenyl)-methanone
3-[3-amino-5-(trifluoromethyl)benzyl]-5-(trifluoromethyl)aniline
1,5-diaminonaphthalene
30 or their derivatives, again with the proviso that compounds listed which do not carry
two amino groups are taken as derivatives with at least one additional amino group.

Preferred examples of additional other diamines are:

ethylenediamine, 1,3-propylenediamine, 1,4-butylenediamine, 1,5-pentylenediamine, 1,6-hexylenediamine, 1,7-heptylenediamine, 1,8-octylenediamine, 1,9-nonylenediamine, 1,10-decylenediamine, 1,11-undecylenediamine, 1,12-dodecylenediamine, α,α' -diamino-m-xylene, α,α' -diamino-p-xylene, (5-amino-2,2,4-trimethylcyclopentyl)methylamine, 1,2-diaminocyclohexane, 4,4'-diaminodicyclohexylmethane, 1,3-bis(methylamino)cyclohexane, 4,9-dioxadodecane-1,12-diamine, 3,5-diaminobenzoic acid methyl ester, 3,5-diaminobenzoic acid hexyl ester, 3,5-diaminobenzoic acid dodecyl ester, 3,5-diaminobenzoic acid isopropyl ester, 4,4'-methylenedianiline, 4,4'-ethylenedianiline, 4,4'-diamino-3,3'-dimethyldiphenylmethane, 3,3',5,5'-tetramethylbenzidine, 4,4'-diaminodiphenyl sulfone, 4,4'-diaminodiphenyl ether, 1,5-diaminonaphthalene, 3,3'-dimethyl-4,4'-diaminobiphenyl, 3,4'-diaminodiphenyl ether, 3,3'-diaminobenzophenone, 4,4'-diaminobenzophenone, 4,4'-diamino-2,2'-dimethylbibenzyl, bis[4-(4-aminophenoxy)phenyl] sulfone, 1,4-bis(4-aminophenoxy)benzene, 1,3-bis(4-aminophenoxy)benzene, 1,3-bis(3-aminophenoxy)benzene, 2,7-diaminofluorene, 9,9-bis(4-aminophenyl)fluorene, 4,4'-methylenebis(2-chloroaniline), 4,4'-bis(4-aminophenoxy)biphenyl, 2,2',5,5'-tetrachloro-4,4'-diaminobiphenyl, 2,2'-dichloro-4,4'-diamino-5,5'-dimethoxybiphenyl, 3,3'-dimethoxy-4,4'-diaminobiphenyl, 4,4'-(1,4-phenyleneisopropylidene)bisaniline, 4,4'-(1,3-phenyleneisopropylidene)bisaniline, 2,2-bis[4-(4-aminophenoxy)phenyl]propane, 2,2-bis[3-(4-aminophenoxy)phenyl]hexafluoropropane, 2,2-bis[3-amino-4-methylphenyl]hexafluoropropane, 2,2-bis(4-aminophenyl)hexafluoropropane, 2,2-bis[4-(4-amino-2-trifluoromethylphenoxy)phenyl]hexafluoropropane, 4,4'-diamino-2,2'-bis(trifluoromethyl)biphenyl, and 4,4'-bis[(4-amino-2-trifluoromethyl)phenoxy]-2,3,5,6,2',3',5',6'-octafluorobiphenyl;

as well as diamines disclosed in US 6,340,506, WO 00/59966 and WO 01/53384, all of which are explicitly incorporated herein by reference;

The diamine compounds according to the present invention may be prepared using methods that are known to a person skilled in the art.

In addition, preferred diamines are the commercially available ones listed below:

Polymers

Poly(3,3',4,4'-benzophenonetetracarboxylic dianhydride-*co*-4,4'-oxydianiline/1,3-

5 phenylenediamine), amic acid solution

Poly(3,3',4,4'-benzophenonetetracarboxylic dianhydride-*co*-4,4'-oxydianiline/1,3-

phenylenediamine), amic acid solution

Poly(pyromellitic dianhydride-*co*-4,4'-oxydianiline), amic acid solution

10 Aromatic diamine

2,7-diaminofluorene

1,5-diaminoanthraquinone

2,6-diaminoanthraquinone

pararosaniline hydrochloride

15 3,6-acridinediamine

4,4'-diaminoctafluorobiphenyl

2,2'-dithiodianiline

3,3',5,5'-tetramethylbenzidine

3,3'-diaminodiphenyl sulfone

20 4,4'-diamino-2,2'-dimethylbibenzyl

4,4'-diaminodiphenyl ether

4,4'-dithiodianiline

4,4'-diaminodiphenyl sulfone

4,4'-diaminodiphenylmethane

25 4,4'-ethylenedianiline

3,3'-dimethoxybenzidine

2,2'-dithiobis(1-naphthylamine)

3,7-diamino-2-methoxyfluorene

3,6-diamino-10-methylacridinium chloride

30 propidium iodide

o-dianisidine dihydrochloride

2,7-diaminofluorene dihydrochloride

pararosaniline acetate

3,6-diamino-10-methylacridinium chloride hydrochloride

proflavine dihydrochloride
o-tolidine dihydrochloride
3,3',5,5'-tetramethylbenzidine dihydrochloride
3,3'-diaminobenzidine tetrahydrochloride
5 4,4'-diaminostilbene dihydrochloride
4,4'-diaminodiphenylamine sulfate
proflavine hemisulfate
2,2'-ethylenedianiline diphosphate
1,5-diamino-4,8-dihydroxyanthraquinone
10 o-tolidine
3,3'-diaminobenzophenone
3,3'-diaminodiphenylmethane
3,4'-diaminodiphenylmethane
2,2-bis[4-(4-aminophenoxy)phenyl]hexafluoropropane
15 4,4'-diamino-1,1'-dianthramide
3,3'-dinitrobenzidine
4,4'-diamino-5,5'-dimethyl-2,2'-biphenyldisulfonic acid
4,4'-diaminostilbene-2,2'-disulfonic acid
3-amino-4-hydroxyphenyl sulfone
20 4,4-bis-(3-amino-4-hydroxyphenyl)-valeric acid
2,2'-diamino-4,4'-difluorobibenzyl
2-amino-4-chlorophenyl disulfide
3,3'-(decamethylenedioxy)dianiline
3,3'-(pentamethylenedioxy)dianiline
25 4-(p-aminoanilino)-3-sulfoaniline
4-[3-(4-aminophenoxy)propoxy]aniline
2-nitrobenzidine
benzidine-3-sulfonic acid
4,4'-diaminodiphenyl sulfide
30 4,4'-diaminobenzanilide
n,n'-bis(3-aminophenylsulfonyl)ethylenediamine
2,2'-biphenyldiamine
3,4'-diaminodiphenyl ether
proflavine hemisulphate

phenosafranin

4,4'-diaminobenzophenone

2,2-bis(4-aminophenyl)hexafluoropropane

2,2-bis(3-amino-4-hydroxyphenyl)hexafluoropropane

5 2,2-bis(3-amino-4-methylphenyl)hexafluoropropane

3,3'-dihydroxybenzidine

3,3'-diamino-4,4'-dihydroxybiphenyl

4,4'-bis(4-aminophenoxy)biphenyl

2,2-bis[4-(4-aminophenoxy)phenyl]propane

10 1,4-bis(4-aminophenoxy)benzene

1,3-bis(4-aminophenoxy)benzene

bis[4-(4-aminophenoxy)phenyl]sulfone

9,9-bis(4-aminophenyl)fluorene

o-tolidine sulfone

15 benzidine

3,3'-dichlorobenzidine dihydrochloride

benzidine dihydrochloride

3,6-thioxanthenediamine-10,10-dioxide

4,4'-diamino-2,2'-biphenyldisulfonic acid

20 4,4'-azodianiline

2,5-bis-(4-aminophenyl)-(1,3,4)oxadiazole

3,3'-dimethylnaphthidine

benzidine sulfate

1,3-bis(3-aminophenoxy)benzene

25 3,3'-dichlorobenzidine

2,2',5,5'-tetrachlorobenzidine

4,4'-diamino-1,1'-binaphthyl

diamine bordeaux

benzoflavin

30 chrysaniline

2,2'-thiobis(5-aminobenzenesulfonic acid)

4,4'-methylene-bis(2-chloroaniline)

tetrabromo methylenedianiline

4,4'-diamino-3,3'-dinitrodiphenyl ether

benzidine pyrophosphate
3,6-diaminothioxanthene-10-dioxide, dihcl
4,4"-diamino-p-terphenyl
1,8-diamino-4,5-dihydroxyanthraquinone
5 bis(p-aminophenoxy)dimethylsilane
bis[4-(3-aminophenoxy)phenyl]sulfone
4,4'-methylenedi-2,6-xylidine
2-aminobenzaldehyde-ethylene-diimine
3-methylbenzidine dihydrochloride
10 3,3'-diethylbenzidine dihydrochloride
3,6-diaminoacridine hydrochloride
4,4'-diamino-5,5'-dimethyl-2,2'-biphenyl disulfonic acid disodium salt
4,4'-methylenebis(3-chloro-2,6-diethylaniline)
4,4'-methylene-bis-(2,6-diethylaniline)
15 4,4'-methylenebis-(2,6-diisopropylaniline)
toluylenediamine
3,8-diamino-6-phenylphenanthridine
thionin perchlorate
dihydroethidium
20 thionin
4,4-diamino benzene sulfonyl anilide
o-dianisidine hcl
2,2'-dichloro-5,5'-dimethoxybenzidine
3-methoxybenzidine
25 2,2'-(hexamethylenedioxy)dianiline
2,2'-(pentamethylenedioxy)dianiline
2,2'-(ethylenedioxy)dianiline
4-[4-(4-aminophenoxy)butoxy]aniline
2,2'-diamino-4'-methoxy-4-methylbenzanilide
30 5,5'-dimethyl-2,2'-dinitrobenzidine
n,n'-bis(2-aminophenyl)-1,3-propanediamine
3,4'-diaminochalcone
2,3',4,5',6-pentaphenyl-3,4'-biphenyldiamine
2-([1-(4-(1-[(2-aminophenyl)thio]-2-nitroethyl)phenyl]-2-nitroethyl]thio)an ilin

2-((2-[(2-aminophenyl)thio]ethyl)thio)aniline
2-((4-[(2-aminophenyl)thio]but-2-enyl)thio)aniline
4,4'-diamino-3,3'-dimethyldiphenyl methane
2,2'-diamino-bibenzyl
5 trimethylene bis(4-aminobenzoate)
fluoresceinamine
benzidines mixture
3-nitro-4,4'-methylenedianiline
4,4-diamino-2,2'-dichlorodiphenyl disulfide
10 1,6-diaminopyrene
1,8-diaminopyrene
3,6-diaminocarbazole
4,4'(5')-diamino-[2,4]-dibenzo-18-crown-6,dihydrochloride
4,4'-diaminostilbene-2,2'-disulfonic acid, disodium salt
15 (r)-(+)-2,2'-diamino-1,1'-binaphthyl
proflavine hemisulfate dihydrate
3,6-diaminoacridine hemisulfate hemihydrate
dimidium bromide monohydrate
o-tolidine dihydrochloride hydrate
20 3,3',5,5'-tetramethylbenzidine dihydrochloride hydrate
3,3'-diaminobenzidine tetrahydrochloride dihydrate
3,6-[bis(4-amino-3-(sodiumsulphonato)phenylamino)]-2,5-dichloro 4-benzoquinone
2,2'-dimethylbenzidine hydrochloride
2,2'-(phenylmethylenebis)bis(4-methylaniline)
25 3,4'-diaminobiphenyl
2,7-diamino-9-fluorenone
n,n'-bis(2-aminophenyl)oxamide
2-[2-(2-aminophenyl)diaz-1-enyl]aniline
3,5,3',5'-tetrabromo-biphenyl-4,4'-diamine
30 n,n'-bis(4-aminophenyl)-1,3-bis(aminomethyl)benzene dihydrochloride
4',4''(5'')-diaminodibenzo-15-crown-5
2,2'-bis(trifluoromethyl)benzidine
bis(4-amino-2,3-dichlorophenyl)methane
alpha,alpha'-bis(4-aminophenyl)-1,4-diisopropylbenzene

2,2-bis(3-aminophenyl)hexafluoropropane
3,10-diamino-6,13-dichlorobenzo[5,6][1,4]oxazino[2,3-b]phenoxazine-4,11-dis ulfo
n1-(2-amino-4-methylphenyl)-2-aminobenzamide
n1-(2-amino-4-chlorophenyl)-2-aminobenzamide
5 2,2'-dichloro[1,1'-biphenyl]-4,4'-diamine
4,4'(5')-diaminodibenzo-15-crown-5 dihydrochloride
rcl s19,413-1
bis-(4-amino-3-nitro-phenyl)-methanone
bis-(3-amino-4-chloro-phenyl)-methanone
10 bis-(3-amino-4-dimethylamino-phenyl)-methanone
n,n'-bis-(4-amino-2-chloro-phenyl)-isophthalamide
n,n'-bis-(4-amino-2-chloro-phenyl)-terephthalamide
3,9-diamino-1,11-dimethyl-5,7-dihydro-dibenzo(a,c)cyclohepten-6-one
2-aminobenzaldehyde n-[(z)-(2-aminophenyl)methylidene]hydrazone
15 3,3'-bis(trifluoromethyl)benzidine
dicarboxidine 2 hcl
4,4'-(1,3-phenylenediisopropylidene)bisaniline
1,4-phenylenebis[[4-(4-aminophenoxy)phenyl]methanone]
2-((5-[(2-aminophenyl)thio]-3,4-dinitro-2-thienyl)thio)aniline
20 n'1-(2-aminobenzoyl)-2-aminobenzene-1-carbohydrazide
2-[4-(5-amino-1h-benzimidazol-2-yl)phenyl]-1h-benzimidazol-5-amine
4-[4-(4-aminophenoxy)-2,3,5,6-tetrafluorophenoxy]aniline
3,3'-dinitro-4,4'-diaminodiphenyl sulfone
3,3',4,4'-tetraaminodiphenylsulfone
25 4-[1-(4-aminophenyl)-1-methylethyl]aniline
3,3-diamino diphenyl urea
bis(4-aminophenyl)acetylene
dibenzo(1,2)dithiine-3,8-diamine
ethidium homodimer-2
30 4,4'-bis-(2-aminobenzenesulfonyl)bis-phenolester
neopentyl glycol bis(4-aminophenyl) ether
2,2'-oxydianiline
4,4'-diaminodiphenylamine-2,2-disulphonic acid
4,4-diamino diphenyl urea

3,3'-tolidine-5-sulfonic acid
n1-(3-[(2-aminobenzoyl)amino]propyl)-2-aminobenzamide
2-((6-[(2-aminophenyl)sulfanyl]-5-nitro-2-pyridyl)sulfanyl)aniline
2-((6-amino-1,3-benzothiazol-2-yl)dithio)-1,3-benzothiazol-6-ylamine
5 tetramethylbenzidine
2-([6-[(2-aminophenyl)sulfanyl]-3,5-di(trifluoromethyl)-2-pyridyl]sulfanyl) anil
3,6-diaminothioxanthene-10-dioxide dihydrochloride
m-tolidine dihydrochloride hydrate
2-amino-n-[2-amino-4-(trifluoromethyl)phenyl]-5-methylbenzamide
10 2-([2-[(2-aminophenyl)thio]-6-nitro-4-(trifluoromethyl)phenyl]thio)aniline
2-[(3-[(2-aminophenyl)thio]methyl)-2,4,6-trimethylbenzyl]thio]aniline
3-[3-amino-5-(trifluoromethyl)benzyl]-5-(trifluoromethyl)aniline
2-((5-[(2-aminophenyl)thio]-4-chloro-2-nitrophenyl)thio)aniline
4-(1-(4-aminophenyl)-2-[4-(dimethylamino)phenyl]vinyl)aniline
15 1,5-bis(4-aminophenoxy)pentane
2,3'-dichlorobenzidine dihydrochloride
3,3'-diamino-4,4'-dichlorodiphenyl sulfone
3-(bis-(4-amino-phenyl)-methyl)-2,3-dihydro-isoindol-1-one
4,4-diamino diphenyl-2-sulphonic acid
20 4,4'-diamino-diphenylene-cyclohexane
4,5'-diamino-(1,1')bianthracenyl-9,10,9',10'-tetraone

Alicyclic diamines
4,4'-methylenebis(cyclohexylamine)
25 4,4'-methylenebis(2-methylcyclohexylamine)

Aliphatic diamines
1,8-diamino-p-menthane
4,4'-methylenebis(cyclohexylamine)
30 d-cystine
l-cystine dimethyl ester dihydrochloride
neamine
bis(2-aminopropyl)amine
(h-cys-beta-na)2 2 hcl

I-cystine dibenzyl ester ditosylate
1,4-diaminocyclohexane
(h-cys-pna)2
dl-2-aminopropionic anhydride
5 I-cystine(di-b-naphthylamide)hydrochloride
I-cystine-bis-p-nitroanilide dihydrobromide
I-cystine diethyl ester dihydrochloride
trans-1,4-cyclohexanediamine
4,4'-methylenebis(2-methylcyclohexylamine)
10 I-leucinethiol, oxidized dihydrochloride
1,3-diaminoadamantane dihydrochloride
I-leucinethiol disulfide 2 hcl
I-cystine disodium salt, monohydrate
I-homocystine methylester hydrochloride
15 1,3-adamantanediamine
tetracyclo[8.2.1.1(8,11).0(2,7)]tetradeca-2,4,6-triene-10,11-diamine
tricyclo[3.3.1.0(3,7)]nonane-3,7-diamine

From the class of commercially available diamines preferred are the below listed ones:

20 Alicyclic diamines
4,4'-methylenebis(cyclohexylamine)
4,4'-methylenebis(2-methylcyclohexylamine)
Aliphatic diamines
4,4'-methylenebis(cyclohexylamine)
25 1,4-diaminocyclohexane
trans-1,4-cyclohexanediamine
4,4'-methylenebis(2-methylcyclohexylamine)
1,3-adamantanediamine
Aromatic diamines
30 2,7-diaminofluorene
2,6-diaminoanthraquinone
4,4'-diaminoctafluorobiphenyl
4,4'-diaminodiphenyl ether
4,4'-dithiodianiline

4,4'-diaminodiphenylmethane
4,4'-ethylenedianiline
3,3'-dimethoxybenzidine
o-tolidine
5 3,3'-diaminobenzophenone
3,3'-diaminodiphenylmethane
3,4'-diaminodiphenylmethane
2,2-bis[4-(4-aminophenoxy)phenyl]hexafluoropropane
4-[3-(4-aminophenoxy)propoxy]aniline
10 4,4'-diaminodiphenyl sulfide
4,4'-diaminobenzophenone
2,2-bis(4-aminophenyl)hexafluoropropane
4,4'-bis(4-aminophenoxy)biphenyl
2,2-bis[4-(4-aminophenoxy)phenyl]propane
15 1,4-bis(4-aminophenoxy)benzene
1,3-bis(4-aminophenoxy)benzene
bis[4-(4-aminophenoxy)phenyl]sulfone
9,9-bis(4-aminophenyl)fluorene
benzidine
20 4,4'-azodianiline
1,3-bis(3-aminophenoxy)benzene
4,4'-diamino-1,1'-binaphthyl
4,4"-diamino-p-terphenyl
bis(p-aminophenoxy)dimethylsilane
25 4-[4-(4-aminophenoxy)butoxy]aniline
3,4'-diaminochalcone
trimethylene bis(4-aminobenzoate)
3,4'-diaminobiphenyl
2,7-diamino-9-fluorenone
30 4',4"(5")-diaminodibenzo-15-crown-5
2,2'-bis(trifluoromethyl)benzidine
alpha,alpha'-bis(4-aminophenyl)-1,4-diisopropylbenzene
3,3'-bis(trifluoromethyl)benzidine
4,4'-(1,3-phenylenediisopropylidene)bisaniline

1,4-phenylenebis[[4-(4-aminophenoxy)phenyl]methanone]
4-[4-(4-aminophenoxy)-2,3,5,6-tetrafluorophenoxy]aniline
4-[1-(4-aminophenyl)-1-methylethyl]aniline
neopentyl glycol bis(4-aminophenyl) ether

5 4,4-diamino diphenyl or
1,5-bis(4-aminophenoxy)pentane
From the class of commercially available diamines (L) more preferred are the below listed ones:
Aromatic diamines

10 2,7-diaminofluorene
4,4'-diaminoctafluorobiphenyl
4,4'-diaminodiphenyl ether
4,4'-diaminodiphenylmethane
4,4'-ethylenedianiline

15 3,3'-diaminobenzophenone
4-[3-(4-aminophenoxy)propoxy]aniline
4,4'-diaminodiphenyl sulfide
4,4'-diaminobenzophenone
2,2-bis(4-aminophenyl)hexafluoropropane

20 4,4'-bis(4-aminophenoxy)biphenyl
2,2-bis[4-(4-aminophenoxy)phenyl]propane
1,4-bis(4-aminophenoxy)benzene
1,3-bis(4-aminophenoxy)benzene
9,9-bis(4-aminophenyl)fluorene

25 benzidine
bis(p-aminophenoxy)dimethylsilane
4-[4-(4-aminophenoxy)butoxy]aniline
3,4'-diaminochalcone
trimethylene bis(4-aminobenzoate)

30 3,4'-diaminobiphenyl
2,7-diamino-9-fluorenone
4',4"(5")-diaminodibenzo-15-crown-5
4-[4-(4-aminophenoxy)-2,3,5,6-tetrafluorophenoxy]aniline
4-[1-(4-aminophenyl)-1-methylethyl]aniline

1,5-bis(4-aminophenoxy)pentane

Aliphatic diamines

4,4'-methylenebis(cyclohexylamine)

5 1,4-diaminocyclohexane


Alicyclic diamines

4,4'-methylenebis(cyclohexylamine)

Preferably, the further polymer, homo- or copolymer or oligomer comprises at least a

10 diamine as one of the basic building block, and a tetracarboxylic acid anhydride, preferably a tetracarboxylic acid anhydride of formula (II).

Preferably, the substituted or unsubstituted, preferably substituted within polar group or unsubstituted, tetracarboxylic acid anhydride is of formula (II)



15

(II)

wherein:

T represents a tetravalent organic radical.

20 The tetravalent organic radical T is preferably derived from an aliphatic, alicyclic or aromatic tetracarboxylic acid dianhydride.

The tetravalent organic radical T is preferably derived from an aliphatic, alicyclic or aromatic tetracarboxylic acid dianhydride.

25

Preferred examples of aliphatic or alicyclic tetracarboxylic acid dianhydrides are:

1,1,4,4-butanetetracarboxylic acid dianhydride, ethylenemaleic acid dianhydride,

1,2,3,4-cyclobutanetetracarboxylic acid dianhydride, 1,2,3,4-cyclopentanetetracarboxylic acid dianhydride; 2,3,5-tricarboxycyclopentylacetic acid dianhydride (with the term

30 "2,3,5-tricarboxycyclopentylacetic acid dianhydride" all isomers of this compound are

incorporated especially the exo and/or endo body), 2,3,5-tricarboxycyclopentylacetic-1,2:3,4-dianhydride is accessible for example by processes as described in JP59-190945, JP60-13740 and JP58-109479, respectively DE 1078120 and JP58-109479, or GB 872,355, and JP04458299, which processes are herewith incorporated by

5 reference;

tetrahydro-4,8-methanofuro[3,4-d]oxepine-1,3,5,7-tetron, 3-(carboxymethyl)-1,2,4-cyclopentanetricarboxylic acid 1,4:2,3-dianhydride,

hexahydrofuro[3',4':4,5]cyclopenta[1,2-c]pyran-1,3,4,6-tetron, 3,5,6-tricarboxy-norbornylacetic acid dianhydride,

10 2,3,4,5-tetrahydrofurantetracarboxylic acid dianhydride, rel-[1S,5R,6R]-3-oxabicyclo[3.2.1]octane-2,4-dione-6-spiro-3'-(tetrahydrofuran2',5'-dione),

4-(2,5-dioxotetrahydrofuran-3-yl)tetrahydronaphthalene-1,2-dicarboxylic acid dianhydride, 5-(2,5-dioxotetrahydro-furan-3-yl)-3-methyl-3-cyclohexene-1,2-dicarboxylic-acid dianhydride, bicyclo[2.2.2]oct-7-ene-2,3,5,6-tetra-

15 carboxylic acid dianhydride,

bicyclo[2.2.2]octane-2,3,5,6-tetracarboxylic acid dianhydride,

1,8-dimethylbicyclo[2.2.2]oct-7-ene-2,3,5,6-tetracarboxylic acid dianhydride,

pyromellitic acid dianhydride, 3,3',4,4'-benzophenonetetracarboxylic acid dianhydride, 4,4'-oxydiphtalic acid dianhydride,

20 3,3',4,4'-diphenylsulfonetetracarboxylic acid dianhydride,

1,3-dimethyl-1,2,3,4-cyclobutanetetracarboxylicacid dianhydride,

1,3-difluoro-1,2,3,4-cyclobutanetetracarboxylicacid dianhydride,

1,3-dichloro-1,2,3,4-cyclobutanetetracarboxylicacid dianhydride,

1,2,3-trimethyl-1,2,3,4-cyclobutanetetracarboxylicacid dianhydride,

25 1,2,3,4-tetramethyl-1,2,3,4-cyclobutanetetracarboxylicacid dianhydride,

1-methyl-1,2,3,4-cyclobutanetetracarboxylicacid dianhydride,

1,4,5,8-naphthalenetetracarboxylic acid dianhydride, 2,3,6,7-naphthalenetetracarboxylic acid dianhydride, 3,3',4,4'-dimethyldiphenylsilanetetracarboxylic acid dianhydride,

30 3,3',4,4'-tetraphenylsilanetetracarboxylic acid dianhydride, 1,2,3,4-furantetracarboxylic acid di-anhydride, 4,4'-bis(3,4-dicarboxyphenoxy)diphenyl sulfide dianhydride,

4,4'-bis(3,4-dicarboxyphenoxy)-diphenyl sulfone dianhydride,

4,4'-bis(3,4-dicarboxyphenoxy)diphenylpropane dianhydride,

3,3',4,4'-biphenyltetracarboxylic acid dianhydride,

ethylene glycol bis(trimellitic acid) dianhydride, 4,4'-(1,4-phenylene)bis(phthalic acid)

dianhydride, 4,4'-(1,3-phenylene)bis(phthalic acid) dianhydride, 4,4'-(hexafluoroisopropylidene)diphthalic acid dianhydride, 4-*tert*-butyl-6-(2,5-dioxotetrahydro-3-furanyl)-2-benzofuran-1,3-dione, 5-(2,5-dioxotetrahydro-3-furanyl)-3a,4,5,9b-tetrahydronaphtho[1,2-*c*]furan-1,3-dione, 5-(2,5-dioxotetrahydro-3-furanyl)-5-methyl-3a,4,5,9b-tetrahydronaphtho[1,2-*c*]furan-1,3-dione, 5-(2,5-dioxotetrahydro-3-furanyl)-6-methylhexahydro-2-benzofuran-1,3-dione, 5-(2,5-dioxotetrahydro-3-furanyl)-7-methyl-3a,4,5,7a-tetrahydro-2-benzofuran-1,3-dione, 6-(2,5-dioxotetrahydro-3-furanyl)-4-methylhexahydro-2-benzofuran-1,3-dione, 9-isopropyloctahydro-4,8-ethenofuro[3',4':3,4]cyclobuta[1,2-*f*][2]benzofuran-1,3,5,7-tetron, 1,2,5,6-cyclooctanetetracarboxylic acid dianhydride, octahydro-4,8-ethenofuro[3',4':3,4]cyclobuta[1,2-*f*][2]benzofuran-1,3,5,7-tetron, octahydrofuro[3',4':3,4]cyclobuta[1,2-*f*][2]benzofuran-1,3,5,7-tetron, tetrahydro-3,3'-bifuran-2,2',5,5'-tetron, 4,4'-oxydi(1,4-phenylene)bis(phthalic acid) dianhydride, and 4,4'-methylenedi(1,4-phenylene)bis(phthalic acid) dianhydride.

20 Preferred examples of aromatic tetracarboxylic acid dianhydrides are: pyromellitic acid dianhydride, 3,3',4,4'-benzophenonetetracarboxylic acid dianhydride, 4,4'-oxydiphthalic acid dianhydride, 3,3',4,4'-diphenylsulfonetetracarboxylic acid dianhydride, 25 1,4,5,8-naphthalenetetracarboxylic acid dianhydride, 2,3,6,7-naphthalenetetracarboxylic acid dianhydride, 3,3',4,4'-dimethyldiphenylsilanetetracarboxylic acid dianhydride, 3,3',4,4'-tetraphenylsilanetetracarboxylic acid dianhydride, 1,2,3,4-furantetracarboxylic acid dianhydride, 30 4,4'-bis(3,4-dicarboxyphenoxy)diphenyl sulfide dianhydride, 4,4'-bis(3,4-dicarboxyphenoxy)diphenyl sulfone dianhydride, 4,4'-bis(3,4-dicarboxyphenoxy)diphenylpropane dianhydride, 3,3',4,4'-biphenyltetracarboxylic acid dianhydride, ethylene glycol bis(trimellitic acid) dianhydride,

4,4'-(1,4-phenylene)bis(phthalic acid) dianhydride,
4,4'-(1,3-phenylene)bis(phthalic acid) dianhydride,
4,4'-(hexafluoroisopropylidene)diphthalic acid dianhydride,
4,4'-oxydi(1,4-phenylene)bis(phthalic acid) dianhydride,
5 4,4'-methylenedi(1,4-phenylene)bis(phthalic acid) dianhydride,
4-tert-butyl-6-(2,5-dioxotetrahydro-3-furanyl)-2-benzofuran-1,3-dione,
and the like.

More preferably the tetracarboxylic acid dianhydrides used to form the tetravalent
10 organic radical T are selected from:

1,2,3,4-cyclobutanetetracarboxylic acid dianhydride,
1,2,3,4-cyclopantanetetracarboxylic acid dianhydride,
2,3,5-tricarboxycyclopentylacetic acid dianhydride,
tetrahydro-4,8-methanofuro[3,4-d]oxepine-1,3,5,7-tetrone,
15 3-(carboxymethyl)-1,2,4-cyclopantanetricarboxylic acid 1,4:2,3-dianhydride,
hexahydrofuro[3',4':4,5]cyclopenta[1,2-c]pyran-1,3,4,6-tetrone,
5-(2,5-dioxotetrahydrofuran-3-yl)-3-methyl-3-cyclohexene-1,2-dicarboxylic acid
dianhydride,
pyromellitic acid dianhydride,
20 4-(2,5-dioxotetrahydrofuran-3-yl)tetrahydronaphthalene-1,2-dicarboxylic acid
dianhydride,
5-(2,5-dioxotetrahydro-3-furanyl)-5-methyl-3a,4,5,9b-tetrahydronaphtho[1,2-c]furan-
1,3-dione,
5-(2,5-dioxotetrahydro-3-furanyl)-3a,4,5,9b-tetrahydronaphtho[1,2-c]furan-1,3-dione,
25 5-(2,5-dioxotetrahydro-3-furanyl)-7-methyl-3a,4,5,7a-tetrahydro-2-benzofuran-1,3-
dione,
4-tert-butyl-6-(2,5-dioxotetrahydro-3-furanyl)-2-benzofuran-1,3-dione,
4,4'-(hexafluoroisopropylidene)diphthalic acid dianhydride and
bicyclo[2.2.2]oct-7-ene-2,3,5,6-tetracarboxylic acid dianhydride.

30 In the context of the present invention the term "polyimide" has the meaning of partially or completely imidised polyamic acid or polyamic ester. In analogy, the term "imidisation" has in the context of the present invention the meaning of partially or complete imidisation.

5 The second embodiment of the present invention relates more particularly to a composition wherein the second polymer is 100% imidised, or has an imidisation degree in the range of 1 to 99%, preferably 5 to 50%, more preferably 10 to 40% by weight.

More preferably the polymerizable liquid crystal or the polymerized liquid crystal contains a polar group.

10 In the context of the second embodiment of the present invention, the composition may comprise a siloxane oligomer, polymer or copolymer as described above, a second polymer which is different from the first one and at least one additional polymer which is different from the first and from the second polymer of the composition.

15 In the second preferred embodiment the invention relates to a composition comprising at least one siloxane oligomer, polymer or copolymer as described above and a second polymer which is different from the first one and an additive and wherein the additive is an additive which is known by the person skilled in the art.

20 The additive is selected from the group consisting of: nucleating agents, clarifying agents, antistatics, antioxidants, slip agents, silica, talc, stabilizers, UV stabilizers, lubricants, coupling agents, antimicrobial agents, crosslinking agents, agents enhancing the crosslinking of the polymer backbone, as for example an acid generator, a base generator or a tetra-alkoxy-siloxane as tetraethoxysilan, surfactants, 25 photo-active agents, photo-sensitizers, photo generators, in particular cationic photo-generators.

Additives such as silane-containing compounds and epoxy-containing crosslinking agents may be added.

30 Suitable silane-containing additives are described in Plast. Eng. 36 (1996), (Polyimides, fundamentals and applications), Marcel Dekker, Inc.

Suitable epoxy-containing cross-linking additives include 4,4'-methylene-bis-(N,N-diglycidylaniline), trimethylolpropane triglycidyl ether, benzene-1,2,4,5-tetracarboxylic acid 1,2,4,5-N,N'-diglycidylidimide, polyethylene glycol diglycidyl ether, N,N-diglycidylcyclohexylamine and the like.

5

Suitable photo-active agents include 2,2-dimethoxyphenylethanone, a mixture of diphenylmethanone and N,N-dimethylbenzenamine or ethyl 4-(dimethylamino)-benzoate, xanthone, thioxanthone, 1-Hydroxy-cyclohexyl-phenyl-ketone, 2-Benzyl-2-dimethylamino-1-(4-morpholinophenyl)-butanone-1, Irgacure[®] 500 (1:1 mixture by weight of 1-Hydroxy-cyclohexyl-phenyl-ketone and benzophenone) and 2,2-Dimethoxy-1,2-diphenylethan-1-one, Michler's ketone, triaryl sulfonium salt and the like.


10

The compositions, preferably blends comprising a polymer, copolymer or oligomer according to definition and preferences of the invention, optionally further comprise an organic solvent. Example of organic solvents are chlorobenzene, pyrrolidone solvents, 15 preferably, N-methyl-2- pyrrolidone, N-ethyl-2-pyrrolidone, N-cyclohexyl-2-pyrrolidone; imidazolidinone, dimethylsulfoxide, dimethylformamide, toluene, chloroform, organic ester, such as acetyl acetic ester or butyl acetic ester, pentyl acetic ester, hexyl acetic ester; further Y-butyrolactone, methyl cellosolve, butyl cellosolve, butyl carbitol, 20 tetrahydrofuran, ditehylene glycol diethylether, dipentylether dipropylene glycol dimethylether, diisobutyl ketone momoethylene glycol dimethyl ether, etc. These solvents can be used alone or in mixtures thereof.

20

In a third embodiment the present invention relates to a process for the preparation of 25 the siloxane oligomer, polymer or copolymer comprising the steps of:

- i. reacting at least one compound selected from the group consisting of siloxane monomers, polymers and oligomers comprising the monomer of formula (II)



(II)

wherein

5 R_0 represents OH, substituted or unsubstituted alkoxy group having 1 to 20 carbons, alkyl group having 1 to 20 carbons, or aryl group having 1 to 20 carbons;


10 R_a represents OH, Cl, a linear or branched, substituted or unsubstituted alkoxy group having 1 to 20 carbons, in which a C, CH could be replaced by unsubstituted or substituted $\text{C}_6\text{-C}_{20}$ aryl group;

15 S_1 represent a single bond or a straight-chain or branched, substituted or unsubstituted $\text{C}_1\text{-C}_{24}$ alkylen, especially $\text{C}_1\text{-C}_{12}$ alkylen, more especially $\text{C}_1\text{-C}_8$ alkylen, more especially $\text{C}_1\text{-C}_6$ alkylen, most especially $\text{C}_1\text{-C}_4$ alkylen, most especially $\text{C}_1\text{-C}_2$ alkylen in which one or more $-\text{C}\text{-}$, $-\text{CH}\text{-}$, $\text{CH}_2\text{-}$ groups may be replaced by a heteroatom;

20 z is an integer from 0 to 15, preferably from 1 to 10, more preferably from 1 to 5, even more preferably from 1 to 3, most preferred n is 1;

25 Z_3 represents a single bond or substituted or unsubstituted aliphatic or alicyclic group of C_3 to C_8 having an epoxy group, most preferably Z_3 represents an alicyclic C_5 to C_6 group having an epoxy group;

with at least another compound of formula (III)



(III)

wherein

5 E_1 represents an OH, SH, NH_2 , $NH(C_1-C_6\text{alkyl})$, NHR^4 , HOC , $HOOC$, $HOCONH$, $HOCONR^4$, HSCS, HSC, wherein R^4 is cyclic, straight chain or branched, substituted or unsubstituted C_1-C_{24} alkyl where in one or more $-C-$, $-CH-$, $-CH_2-$ group(s) may be independently from each other replaced by a linking group.

10 X , Y each independently from each other represents H, F, Cl, CN;

15 A represents halogen, H or substituted or unsubstituted C_1-C_{24} alkyl, a substituted or unsubstituted C_1-C_{24} alkenyl, a substituted or unsubstituted C_1-C_{24} alkyl, or a carboxylic acid, wherein one or more, $-C-$, $-CH-$, $-CH_2-$, group may independently from each other be replaced by a heteroatom; preferably A is halogen, or a C_1-C_{24} alkoxy; most preferably A is H, F, methoxy or a carboxylic acid;

20 S_2 represents a cyclic, aromatic, straight-chain or branched, substituted or unsubstituted C_1-C_{24} alkylen, especially C_1-C_{12} alkylen, more especially C_1-C_8 alkylen, more especially C_1-C_6 alkylen, most especially C_1-C_4 alkylen, most especially C_1-C_2 alkylen in which one or more $-C-$, $-CH-$, $-CH_2-$ groups may be replaced by a linking group;

25 n_1 is an integer from 1 to 15, preferably from 1 to 10, most preferably from 1 to 3, most preferred n is 1;

n_2 is an integer from 0 to 15, preferably from 1 to 10, most preferably from 1 to 3, most preferred n is 1;

30

Z_2 represents a chemical group having a delocalisation of its electronical density and/or inducing a delocalisation of the electronical density of its neighboring atom;

5 and T represents an unsubstituted or substituted, straight-chain C_1 - C_{16} alkyl,

in the presence of an organic solvent, water and a catalyst;

- 10 ii. optionally reacting the product obtained by step i) with a C_1 - C_{24} linear, branched or cyclic alcohol wherein one or more $-C-$, $-CH-$, $-CH_2-$ group(s) may be independently from each other be replaced by a linking group, under the presence of a catalyst; and
- iii. isolating and purifying the obtained product.

15 In the context of the present invention, organic solvent means any solvent commonly known in the art. More specifically the organic solvent is selected from the group consisting of: hydrocarbon, ketone, ester, ether and alcohol.

20 Examples of the above hydrocarbon include toluene and xylene; examples of the above ketone include methyl ethyl ketone, methyl isobutyl ketone, methyl n-amyl ketone, diethyl ketone and cyclohexanone; examples of the above ester include ethyl acetate, n-butyl acetate, i-amyl acetate, propylene glycol monomethyl ether acetate, 3-methoxybutyl acetate and ethyl lactate; examples of the above ether include ethylene glycol dimethyl ether, ethylene glycol diethyl ether, tetrahydrofuran and dioxane; and 25 examples of the above alcohol include 1-hexanol, 4-methyl-2-pentanol, ethylene glycol monomethyl ether, ethylene glycol monoethyl ether, ethylene glycol mono-n-propyl ether, ethylene glycol mono-n-butyl ether, propylene glycol monomethyl ether, propylene glycol monoethyl ether and propylene glycol mono-n-propyl ether. Out of these, water-insoluble organic solvents are preferred.

30 The amount of the organic solvent is preferably 0.5 to 10,000 parts by weight, more preferably 50 to 1,000 parts by weight based on 100 parts by weight of the total of all the silane compounds.

These organic solvents may be used alone or in combination of two or more.

The amount of water used to produce the siloxane is preferably 0.01 to 100 times,

5 more preferably 0.1 to 30 times the total molar amount of all the silane compounds.

In the context of the present invention, the catalyst is any catalyst known in the art. The catalyst is selected from the group consisting of: acid, alkali metal compound, organic base, curing accelerator, titanium compound or zirconium compound. Preferred are

10 organic base catalysts or curing accelerators. Examples of organic base catalysts

include but are not limited to primary and secondary organic amines, such as

ethylamine, diethylamine, piperazine, iperidine, pyrrolidine and pyrrole; tertiary organic amines such as trimethylamine, tri-n-propylamine, tri-n-butylamine, pyridine, 4-dimethylaminopyridine and diazabicycloundecene; and quaternary organic amines

15 such as tetramethylammonium hydroxide, U-CAT compounds from SAN-APRO Ltd as

for example, U-CAT SA 506, U-CAT 18X, U-CAT. Examples of curing accelerator include but are not limited to tertiary amines such as benzylidemethylamine, 2,4,6-tris(dimethylaminomethyl)phenol, cyclohexyldimethylamine and triethanolamine; imidazole compounds such as 2-methylimidazole, 2-n-heptylimidazole, 2-n-

20 undecylimidazole, 2-phenylimidazole, 2-phenyl-4-methylimidazole, 1-benzyl-2-

methylimidazole, 1-benzyl-2-phenylimidazole, 1,2-dimethylimidazole, 2-ethyl-4-methylimidazole 1-(2-cyanoethyl)-2-methylimidazole, 1-(2-cyanoethyl)-2-n-

undecylimidazole, 1-(2-cyanoethyl)-2-phenylimidazole, 1-(2-cyanoethyl)-2-ethyl-4-

25 methylimidazole, 2-phenyl-4-methyl-5-hydroxymethylimidazole, 2-phenyl-4,5-di(hydroxymethyl)imidazole, 1-(2-cyanoethyl)-2-phenyl-4,5-di[(2'-

cyanoethoxy)methyl]imidazole, 1-(2-cyanoethyl)-2-n-undecylimidazolium trimellitate, 1-

(2-cyanoethyl)-2-phenylimidazolium trimellitate, 1-(2-cyanoethyl)-2-ethyl-4-

methylimidazolium trimellitate, 2,4-diamino-6-[2'-methylimidazolyl-(1')]ethyl-s-triazine,

2,4-diamino-6-(2'-n-undecylimidazolyl)ethyl-s-triazine, 2,4-diamino-6-[2'-ethyl-4'-

30 methylimidazolyl-(1')]ethyl-s-triazine, isocyanuric acid adduct of 2-methylimidazole,

isocyanuric acid adduct of 2-phenylimidazole and isocyanuric acid adduct of 2,4-

diamino-6-[2'-methylimidazolyl-(1')]ethyl-s-triazine; organic phosphorus compounds

such as diphenyl phosphine, triphenyl phosphine and triphenyl phosphite; quaternary phosphonium salts such as benzyltriphenylphosphonium chloride, tetra-n-

butylphosphonium bromide, methyltriphenylphosphonium bromide, ethyltriphenylphosphonium bromide, n-butyltriphenylphosphonium bromide, tetraphenylphosphonium bromide, ethyltriphenylphosphonium iodide, ethyltriphenylphosphonium acetate, tetra-n-butylphosphonium o,o-
5 diethylphosphorodithionate, tetra-n-butylphosphonium benzotriazolate, tetra-n-butylphosphonium tetrafluoroborate, tetra-n-butylphosphonium tetraphenylborate and tetraphenylphosphonium tetraphenylborate; diazabicycloalkenes such as 1,8-diazabicyclo[5.4.0]undecene-7 and organic acid salts thereof; organic metal compounds such as zinc octylate, tin octylate and aluminum acetylacetone complex; 10 quaternary ammonium salts such as tetraethylammonium bromide, tetra-n-butylammonium bromide, tetraethylammonium chloride and tetra-n-butylammonium chloride; boron compounds such as boron trifluoride and triphenyl borate; metal halogen compounds such as zinc chloride and stannic chloride; and latent curing accelerators including high-melting point dispersible latent curing accelerators such as 15 amine adduct type accelerators including dicyandiamide and an adduct of an amine with epoxy resin; microcapsule type latent curing accelerators obtained by coating the surfaces of curing accelerators such as the above imidazole compounds, organic phosphorus compounds and quaternary phosphonium salts with a polymer; amine salt type latent curing accelerators; and high-temperature dissociation type thermally 20 cationic polymerization latent curing accelerators such as Lewis acid salts and Brønsted acid salts.

The catalyst is used in an amount of preferably not more than 100 parts by weight, more preferably 0.01 to 100 parts by weight, much more preferably 0.05 to 20 parts by 25 weight based on 100 parts by weight of the compound of formula (II).

The reaction temperature is preferably 0 to 200 °C, more preferably 50 °, 60 °, 70 °, 80 ° or 90 ° to 150 °, 140 °, 130 °, 120 °, 110 ° or 100 °.

30 The reaction time is 0.1 to 72 hours, more preferably 0.5 to 48 hours, even more preferably 1 to 20 hours.

The fourth object of the present invention is to provide an orientation layer comprising one said siloxane oligomer, polymer or copolymer. More preferably the orientation layer further comprises a polymerisable liquid crystal.

5 In the context of the present invention the wording "polymer or oligomer layer" has the meaning of "polymer layer, copolymer layer, homopolymer layer or oligomer layer".

In the context of the present invention the wording "orientation layer" has the same meaning as "orientation film".

10 In the context of the present invention polymer or oligomer layers are preferably orientation layers.

15 The polymers, homo- or copolymers or oligomers according to the invention may be used in form of polymer layers or oligomer layers alone or in combination with other polymers, oligomers, monomers, photo-active polymers, photo-active oligomers and/or photo-active monomers, depending upon the application to which the polymer or oligomer layer is to be added. Therefore it is understood that by varying the composition of the polymer or oligomer layer it is possible to control specific and 20 desired properties, such as an induced pre-tilt angle, or surpassing of tilt, good surface wetting, a high voltage holding ratio, a specific anchoring energy, etc.

25 The fifth object of the present invention is to provide a method for the preparation of the orientation layer by exposure of the siloxane oligomer, polymer or copolymer with aligning light.

The siloxane polymer, copolymer or oligomer, comprises in its polymer-, homo- or copolymer- or oligomer-side-chains at least one photo-reactive group. Preferably, the photo-reactive group of the side chains reacts by exposure to aligning light.

30 In the context of the present invention the term photoreactive groups have the meaning of groups, which are able to react by interaction with light, preferably aligning light.

The treatment with aligning light may be conducted in a single step or in several separate steps. In a preferred embodiment of the invention the treatment with aligning light is conducted in a single step.

5 In the context of the present invention photo-reactive group has preferably the meaning of a dimerizable, isomerizable, polymerizable and/or cross-linkable group.

In the context of the present invention, aligning light, preferably polarized light is light of wavelengths, which can initiate photoalignment. Preferably, the wavelengths are in 10 the UV-A, UVB and/or UV/C-range, or in the visible range. It depends on the photoalignment compound, which wavelengths are appropriate. Preferably, the photo-reactive groups are sensitive to visible and/or UV light. A further embodiment of the invention concerns the generating of aligning light by laser light.

15 The instant direction of the aligning light may be normal to the substrate or at any oblique angle.

More preferably, aligning light is at least partially linearly polarized, elliptically polarized, such as for example circulary polarized, or non-polarized; most preferably at least 20 circulary or partially linearly polarized light, or non-polarized light exposed obliquely. Especially, most preferred aligning light denotes substantially polarised light, especially linearly polarised light; or aligning light denotes non-polarised light, which is applied by an oblique irradiation.

25 A more preferred embodiment of the invention relates to a method for the preparation of the orientation layer by exposure of the linear, branched or crosslinked siloxane oligomer, polymer or copolymer with polarised light, especially linearly polarised light, or by oblique radiation with non-polarised light.

30 Further preferred are siloxane polymers, homo- or copolymers or oligomers of the present invention,
- wherein at least 1%, preferably at least 5%, more preferably at least 8%, most preferably at least 10%, especially most preferred at least 15 %, more especially

preferred at least, 30%, even more preferred at least 50%, 60% or 75% of the monomers include a side chain with a photo-reactive group; and/or

- wherein, the photo-reactive groups are able to dimerize, isomerize, polymerize; crosslink and/or
- 5 - wherein the polymer, homo- or copolymer or oligomer is a polymer gel or a polymer network, or an oligomer gel or an oligomer network, respectively; and/or
- wherein the polymer, homo- or copolymer or oligomer has an intrinsic viscosity in the range of 0.01 to 10 dL/g, preferably in the range of 0.02 to 5 dL/g; and/or
- wherein the polymer, homo- or copolymer or oligomer has a molecular weight of

10 1 to 6'000'000, 1'000 to 6'000'000, 2'000 to 1'000'000, 2'000 to 500'000, more preferably 5'000 to 100'000.

- wherein the polymer, homo- or copolymer or oligomer contains from 2 to 15000 repeating units, especially from 5 to 2000 repeating units, more especially 6 to 500 repeating units; and/or
- 15 - wherein the polymer, homo- or copolymer or oligomer is in the form of a homopolymer or of a copolymer, preferably of a statistical copolymer.

A further preferred embodiment of the present invention relates to siloxane polymers, copolymers or oligomers, having an intrinsic viscosity preferably in the range of 0.01 to 20 10 dL/g, more preferably in the range of 0.01 to 1 dL/g. Herein, the intrinsic viscosity ($\eta_{inh} = \ln \eta_{rel}/C$) is determined by measuring a solution containing a polymer, or copolymers or an oligomer in a concentration of 0.5 g/100 ml solution for the evaluation of its viscosity at 30 °C using N-methyl-2-pyrrolidone as solvent.

25 In addition, a preferred embodiment of the present invention relates to siloxane polymers, homo- or copolymers or oligomers, containing from 2 to 15000 monomers, especially from 5 to 2000 monomers, more especially 6 to 500.

30 Polymer or oligomer layers may readily be prepared from the siloxane polymers, copolymers or oligomers of the present invention and a further embodiment of the invention relates to a siloxane polymer, copolymer or oligomer layer comprising a siloxane polymer, copolymer or oligomer according to the present invention, which is preferably prepared by treatment with aligning light.

Preferably, the invention relates to a siloxane polymer-, copolymer-, or oligomer layer comprising a siloxane polymer, copolymer, or oligomer according to the present invention or as prepared according to the present invention.

5 The polymer or oligomer layer is preferably prepared by applying one or more siloxane polymers, copolymers or oligomers or compositions according to the invention to a support and, after imidisation or without imidisation, irradiating the polymer or oligomer or polymer mixture or oligomer mixture with aligning light. Aligning light has the above given meaning and preferences.

10

The term "support" as used in the context of the present invention is preferably transparent or not-transparent, preferably glass or plastic substrates, polymer films, such as polyethyleneterephthalat (PET), tri-acetyl cellulose (TAC), polypropylen, optionally coated with indium tin oxide (ITO), however not limited to them.

15 In general a composition comprising the siloxane polymers, copolymers or oligomers of the invention is applied by general coating and printing methods known in the art, such as spin-coating, meniscus-coating, wire-coating, slot-coating, offset-printing, flexo-printing, gravure-printing, ink jet printing may be used. Coating methods are for example spin coating, air doctor coating, blade coating, knife coating, reverse-roll

20 coating, transfer roll coating, gravure roll coating, kiss roll coating, cast coating, spray coating, slot-orifice coating, calendar coating, electrodepositing coating, dip coating or die coating.

25 Printing methods are for example relief printing such as flexographic printing, ink jet printing, intaglio printing such as direct gravure printing or offset gravure printing, lithographic printing such as offset printing, or stencil printing such as screen printing. A further preferred embodiment of the present invention relates to orientation layers which are unstructured or structured.

30 In addition the present invention relates to a process for the preparation of structured siloxane polymer layers, copolymer layers or oligomer layers comprising varying the direction of orientation and/or the tilt angle within the polymer or oligomer layer. This varying of the direction of orientation and/or the tilt angle can for example be conducted by controlling the direction of the irradiation of the aligning light. It is

understood that by selectively irradiating specific regions of the polymer or oligomer layer very specific regions of the layer can be aligned. In this way, layers with a defined tilt angle can be provided.

5 The irradiation time is dependent upon the output of the individual lamps and can vary from a few seconds to several hours. The photo-reaction can also be carried out, however, by irradiation of the homogeneous layer using filters that, for example, allow only the radiation suitable for the reaction to pass through.

10 Further preferred is a process for the preparation of a siloxane polymer layer, copolymer layer or oligomer layer; for the preparation of planar multi-domain alignment of a polymer layer or oligomer layer; and/or for the preparation of a polymer layer, copolymer or oligomer layer having a tilt angle within the given meaning and preferences of the invention.

15 A further preferred embodiment of the invention relates to an orientation layer comprising one or more siloxane polymers, copolymers or oligomers according to the invention.

20 In the context of the present invention orientation layer has the same meaning and preferences as alignment layer, polymer, homo- or copolymer or oligomer layer and is preferably a photo alignment layer.

25 In the context of the present invention, the orientation layer is used for the planar alignment (in plane switching) of liquid crystals or for the vertical alignment of liquid crystals.

In a more preferred embodiment the invention relates to an orientation layer according to the invention for the planar alignment of liquid crystals.

30 In the context of the present invention the wording "planar alignment of liquid crystals" means that the liquid crystals have tilt angle.

The term tilt angle as used in the context of the present invention is the angle between

the liquid crystal director and the surface of the alignment layer. The liquid crystal director shall mean the average direction of the long axes of the liquid crystal molecules. In the context of the present invention, planar alignment shall mean that the tilt angle is less than 30°, preferably 0 to 30°.

5

In preferred embodiments the tilt angle of the liquid crystals, induced by the photo-alignment layer is less than 10°, preferably 0 to 10°. In more preferred embodiments the tilt angle is less than 5°, preferably 0 to 5°, and in most preferred embodiments the tilt angle is less than 1°, preferably 0 to 1°, even more preferably from 0° to 0.5°.

10

Preferred are tilt angles of less than 0.2° or 0.1°.

The sixth embodiment of the present invention is the use of said orientation layer, for the alignment, especially the planar alignment, of

-a) liquid crystal composition comprising one or more polymerizable liquid crystal

15

monomers, or comprising one or more liquid crystal polymers or oligomers, which are the polymerized form of said polymerizable liquid crystal monomers, and/or

-b) liquid crystal compositions comprising one or more polymerizable liquid crystal monomers, or comprising one or more liquid crystal polymers or oligomers, which are the polymerized form of said polymerizable liquid crystal monomers, said liquid crystal

20

compositions being sandwiched between a pair of said orientation layers.

Examples of LCP are described in US2012/114907 A1, which is herewith incorporated by reference.

25

Further, the present invention relates preferably to the use of an orientation layer according to the invention for the induction of planar alignment of adjacent liquid crystalline layers, in particular for operating a cell wherein planar orientation is provided, such in IPS, such as IPS modes like S-IPS (Super IPS), AS-IPS (Advanced super IPS), E-IPS (Enhanced IPS), H-IPS (Horizontal IPS), UH-IPS, S-IPS II, e-IPS, p-IPS (performance IPS), PLS technology (plane to line switching), PS-IPS (polymer stabilized IPS), Field induced photoreactive alignment IPS FFS (fringe field switching), TN (twisted nematic), STN (supertwisted nematic).

Liquid crystal compositions of the present invention comprise a polymerizable monomer, or a polymer or oligomer, which is the polymerized form of said polymerizable monomer. The polymerizable monomer or the polymer or oligomer, is bifunctional and/or has a rigid core (e.g. benzene). Further preferred is a polymerizable monomer, or a polymer or oligomer, which have one or more ring or condensed ring structures and functional groups bonded directly to the ring or condensed ring structure.

More preferred liquid crystals have a monomer of formula (IV)

10

$P_1-S_1-A_1-(Z_1-A_2)_n-S_2-P_2$ (IV)

wherein

15 P_1 and P_2 are functional groups and are independently selected from acrylate, methacrylate, halogenacrylate, such as fluoroacrylate, chloroacrylate; oxetanyl, maleimidyl, allyl, allyloxy, vinyl, vinyloxy and epoxy groups,

20 S_1 and S_2 are independently from each other a single bond or a spacer unit, which is preferably a straight-chain or branched, substituted or unsubstituted C_1-C_{24} alkylen, in which one or more, preferably non-adjacent, C-atom, CH - or CH_2 -, group may be replaced by a linking group within the above given meaning and preferences, and,

preferably replaced by is a single bond, $-O-$, $-O(CO)-$, $-S-$, $-(CO)O-$ or $\begin{array}{c} -N\backslash \\ \backslash \end{array}$, $-NR^2-$, and wherein the substituent is preferably at least one C_1-C_6 alkyl, preferably methyl.

25

A_1 and A_2 are ring structures and independently selected from unsubstituted or substituted carbocyclic or heterocyclic aromatic or alicyclic group with the meaning and preferences given in the present invention, especially preferred are 1,4-phenylene naphthalene- 2,6-diyl, terphenyl, quarterphenyl, phenanthrene groups,

30

Z_1 is selected from $-O-$, $-CO-$, $-CH(OH)-$, $-CH_2(CO)-$, $-OCH_2-$, $-CH_2O-$, $-O-CH_2-O-$, $-COO-$, $-OCO-$, $-(CO)-(CO)-$, $-OCF_2-$, $-CF_2O-$, $-CF_2-$, $-CON(C_1-C_{16}$ alkyl)-, $-(C_1-C_{16}$ alkyl)NCO-, $-CONH-$, $-NHCO-$, $-HNOCO-$, $-OCONH-$, $-NHCONH-$, $-OCOO-$,

-CO-S-, -S-CO-, -CSS, -SOO-, -OSO-, -SOS-, -SO-, -CH₂(SO)-, -SO₂-, -CH=CH-, -C≡C-, -CH=CH-COO-, -OCO-CH=CH-, -CH=N-, -C(CH₃)=N-, -N=N-, or a single bond; or a cyclic, straight-chain or branched, substituted or unsubstituted C₁-C₂₄alkylen, wherein one or more C-atom, CH- or CH₂-group may independently from each other be replaced by a linking group;

5 preferably, Z₁ is -O-, -CO-, -COO-, -OCO-, -OCOO-, -OCF₂-, -CF₂O-, -CON(CH₃)-, -(CH₃)NCO-, -CONH-, -NHCO-, -CO-S-, -S-CO-, -CSS, -SOO-, -OSO-, -CSS-, -SOO-, -OSO-, -CH₂(SO₂)-, -CH₂-CH₂-, -OCH₂-, -CH₂O-, -CH=CH-, -C≡C-, -CH=CH-COO-, -OCO-CH=CH-, or a single bond;




10 more preferably Z₁ is -COO-, -OCO-, -OCOO-, -OCF₂-, -CF₂O-, -CON(CH₃)-, -(CH₃)NCO-, -CONH-, -NHCO-, -CO-S-, -S-CO-, -CS-S-, -SOO-, -OSO, especially -COO-, -OCO-, -OCF₂-, -CF₂O-, -CON(CH₃)-, -(CH₃)NCO-, -CONH-, -NHCO- or a single bond,

most preferred Z₁ is a single bond, -COO- or -OCO-; and

15 n is an integer of 1, 2, or 3.

In formula (II), P₁ and P₂ are preferably acrylate or methacrylate groups, S₁ and S₂ are a single bond Z₁ is preferably a single bond, and n is preferably 0 or 1.

20 Most preferred is a compound represented by any one of the formulae (V), (VI) or (VII)



5 wherein P_1 and P_2 are independently from each other an acrylate, methacrylate, oxetane, maleinimide, allyl, allyloxy, vinyl, vinylamide, vinyloxy and epoxy group, epoxy derivatives, butoxy and butoxy derivatives,

B is a single bond, $-\text{CO-C}(\text{C}_1\text{-C}_6\text{alkoxy})_2-$, $-\text{COO-}$, $-\text{OCO-}$,



10 Y_1 , Y_2 , Y_3 , Y_4 , Y_5 , Y_6 are independently from each other hydrogen, a straight-chain or branched $\text{C}_1\text{-C}_{16}\text{alkyl}$ group, which is unsubstituted or substituted by fluorine, di-($\text{C}_1\text{-C}_{16}\text{alkyl}$)amino, $\text{C}_1\text{-C}_{15}\text{alkyloxy}$, nitro, nitrile and/or chlorine; and wherein one or more C-atom, CH- or $\text{CH}_2\text{-}$ group may independently from each other be replaced by a linking group; halogen or nitrile; preferred substituents are $\text{C}_1\text{-C}_6\text{alkyl}$ group, especially methyl or ethyl, $\text{C}_1\text{-C}_6\text{alkoxy}$ group, especially methoxy or ethoxy, chlorine, fluorine, or 15 nitrile, more preferably methoxy, chlorine, fluorine, or CN and most preferably methoxy, chlorine or fluorine; further, if the aromatic group is substituted, then it is preferably substituted once or twice;

20 S_1 , S_2 , are independently from each other a single bond or a spacer unit, as described above.

In formula (IV), P_1 and P_2 are preferably acrylate or methacrylate groups, S_1 and S_2 are a single bond Z_1 is preferably a single bond, and n is preferably 0 or 1.

25 In formulae (V) and (VII) a substituent group for the benzene ring is present at the o-position, m-position, or p-position. In formula (VI), a substituent group for the naphthalene ring is present at the o-position, m-position, p-position, ana-position, E (epi)-position, kata-position, pen-position, pros-position, amphi-position, or 2,7-position. The substituent group for the benzene ring is preferably present at the p-position among the above positions. The substituent group for the naphthalene ring is 30 preferably present at the amphi-position among the above positions.

Preferred are:



In general the liquid crystals compositions or liquid crystal layers are not particularly limited, provided that they contain the mono- or/and multi-polymerizable monomer described above. The liquid crystals compositions or liquid crystal layers can thus be made of any of various liquid crystal materials that have been known publicly. The liquid crystals compositions or liquid crystal layers may be made of a liquid crystal material identical to or different from that for display use.

10

The oligomer, which is the polymerized form of the polymerizable monomer, is in general not limited to any molecular weight. Preferably the molecular weight is in the range of 200 to 5000 Dalton, more preferably in the range of 500 to 2000 Dalton and most preferred in the range of 500 to 1000 Dalton.

15

In the seventh embodiment the present invention relates to a method for manufacturing a liquid crystal display.

20

In the context of the present invention the term "display" has the same meaning as the term "panel".

The method for producing the liquid crystal display panel may involve using a polymerization initiator, such as methyl ethyl ketone peroxide and a benzoyl ether-based compound.

25

Preferably, the present invention relates to a method for manufacturing a liquid crystal display comprising applying at least a single LCP onto a siloxane polymer, copolymer or oligomer layer according to the first or second embodiment, or preferably on the orientation layer according to the fourth embodiment of the present invention, and polymerizing said LCP.

In general the polymerization of the LCP is conducted by irradiation or at elevated temperature.

5 The LCP may be applied onto the orientation layer in any amount, so the amount is not particularly limited. The amount may be set as appropriate in accordance with, for example, respective thicknesses of the LCP polymer films formed by polymerization of the monomeric LCP.

10 Further the present invention relates to a method for manufacturing a liquid crystal display comprising bringing into contact a liquid crystal composition comprising a polymerizable liquid crystal monomer according to the present invention, or a polymer or oligomer, which is the polymerized form of said polymerizable liquid crystal monomer; with at least a single orientation layer according to the present invention, 15 preferably two orientation layers facing each other; and polymerising said polymerizable liquid crystal monomer.

Generally the polymerization methods are not limited so far as they have no adverse effects on the manufactured device. Preferably the polymerization is conducted by 20 irradiation, especially UV radiation, or by heat.

More specifically the process for the preparation of liquid crystal displays, preferably LCDs comprising planar alignment of liquid crystals, more especially LCDs comprising the IPS mode, comprising an orientation layer according to the present invention and 25 electrodes, comprises performing an exposure, preferably a first exposure, of the material with the polarised light, wherein the exposure induces an orientation direction of the liquid crystals perpendicular to polarised light, or/and wherein an exposure, preferably a first exposure, induces an orientation direction of the liquid crystals and polarised light direction make an angle higher than 70°, or/and wherein an exposure, 30 preferably a first exposure, with polarized light is conducted with an angle >70° between the electrode and the polarized light direction.

The eight object of the present invention relates to optical or electro-optical unstructured or structured elements comprising the siloxane oligomer, polymer or copolymer or the orientation layer.

5 In a preferred embodiment the element is a liquid crystal display cell.

In the context of the present invention elements, device, cell, structure all refer to objects comprising polymerized or polymerizable liquid crystal to be oriented with the linear, branched or crosslinked siloxane polymer, copolymer or oligomer according to
10 the present invention.

Preferably, the present invention further relates to unstructured or structured elements optical or electrooptical devices, especially a LCD, comprising a pair of substrates facing each other; wherein the substrates is provided with a pair of orientation layers
15 according to the present invention and

- a) optionally, a LCP polymer film, wherein said polymer film is formed on that orientation layer, or
- b) a liquid crystal composition, preferably comprising a polymer made from at least a polymerizable liquid crystal monomer, wherein said liquid crystal composition is sandwiched between the pair of orientation layers.

The present invention also relates to the use of such orientation layers for the alignment, preferably planar alignment, of liquid crystals, preferably in the manufacture of unstructured or structured optical-or electro-optical elements, preferably in the
25 production of hybrid layer elements. Preferably, these optical or electro-optical devices have at least one orientation layer as well as unstructured and structured optical elements and multi-layer systems. The layer or each of the layers may contain one or more regions of different spatial orientation.

30 Polarised light direction shall mean the intersection line of the alignment layer surface and the plane of polarization of the polarised light during the exposure. If the polarised light is elliptically polarized, the plane of polarization shall mean the plane defined by the incident direction of the light and by the major axis of the polarization ellipse.

The term polarised light direction is used in the context of the present invention not only to describe a direction for the duration of the exposure process, but also after exposure to refer to the direction of the polarised light on the alignment layer as it was applied during exposure.

5

The electrodes are preferably in the form of parallel stripes, zig-zag or comb-like electrodes.

10

Preferably, the present invention concerns an optical and electro-optical unstructured or structured constructional elements, preferably liquid crystal display cells, multi-layer and hybrid layer elements, comprising at least one polymer layer, copolymer or oligomer layer according to the present invention.

15

The present invention the wording optical or electro-optical elements has preferably the meaning of multilayer systems, or devices for the preparation of a display waveguide, a security or brand protection element, a bar code, an optical grating, a filter, a retarder, a compensation film, a reflectively polarizing film, an absorptive polarizing film, an anisotropically scattering film compensator and retardation film, a twisted retarder film, a cholesteric liquid crystal film, a guest-host liquid crystal film, a monomer corrugated film, a smectic liquid crystal film, a polarizer, a piezoelectric cell, a thin film exhibiting non linear optical properties, a decorative optical element, a brightness enhancement film, a component for wavelength-band-selective compensation, a component for multi-domain compensation, a component of multiview liquid crystal displays, an achromatic retarder, a polarization state correction /

20

adjustment film, a component of optical or electro-optical sensors, a component of brightness enhancement film, a component for light-based telecommunication devices, a G/H-polarizer with an anisotropic absorber, a reflective circular polarizer, a reflective linear polarizer, a MC (monomer corrugated film), twisted nematic (TN) liquid crystal displays, hybrid aligned nematic (HAN) liquid crystal displays, electrically controlled birefringence (ECB) liquid crystal displays, supertwisted nematic (STN) liquid crystal displays, optically compensated birefringence (OCB) liquid crystal displays, pi-cell liquid crystal displays, PLS technology (plane to line switching), PS-IPS (polymer stabilized IPS), in-plane switching (IPS) liquid crystal displays, such as IPS modes like S-IPS (Super IPS), AS-IPS (Advanced super IPS), E-IPS (Enhanced IPS), H-IPS

(Horizontal IPS), UH-IPS, S-IPS II, e-IPS, p-IPS (performance IPS); Field induced photoreactive alignment IPS, fringe field switching (FFS) liquid crystal displays; (FPA) field-induced photo-reactive alignment; hybrid FPA; VA-IPS mode liquid crystal displays, or displays using blue phase liquid crystals; all above display types are applied in either transmissive or reflective or transflective mode.

5 More preferred optical or electro-optical elements are PLS technology (plane to line switching), PS-IPS (polymer stabilized IPS), in-plane switching (IPS) liquid crystal displays, such as IPS modes like S-IPS (Super IPS), AS-IPS (Advanced super IPS), E-IPS (Enhanced IPS), H-IPS (Horizontal IPS), UH-IPS, S-IPS II, e-IPS, p-IPS (performance IPS); Field induced photoreactive alignment IPS, fringe field switching (FFS) liquid crystal displays; (FPA) field-induced photo-reactive alignment; hybrid FPA; VA-IPS mode liquid crystal displays, or displays using blue phase liquid crystals; all above display types are applied in either transmissive or reflective or transflective mode.

10 The advantages of the present invention could not be foreseen by a skilled person. It has surprisingly been found, that the siloxane polymers of the present invention, upon irradiation with polarized light, orient polymerized or polymerizable liquid crystals. 15 Further, said photo-alignment material shows good and homogenous planar orientation quality. The further examples will demonstrate that the linear, branched or crosslinked siloxane polymers, copolymers or oligomers of the present invention have good or very good image sticking properties, contrast ratios, and voltage holding ratios.

20 25 The further examples are a non-limiting selection of examples which will further explain the invention.

30 Examples

Definitions used in the examples:

¹H NMR: ¹H nuclear magnetic resonance spectroscopy

DMSO-d₆:dimethylsulfoxid deuterated

300MHz: 300 Megahertz

M : multiplett

D : doublet

Dd : doublet doublet

5 t : triplet

s : singulet

q : quadruplet

qi : quintet

br : broad peak

10 HCl : hydrogen chloride

HCl solution (25%) : volume percent

NaOH : sodium hydroxide

NaOH (30%) : weight percent

MeOH: methanol

15 EtOAc: ethyl acetate

NMP: N-methyl-2-pyrrolidone

THF: tetrahydrofuran

TBME: tert. butyl methyl ether

DMF: N,N-dimethylformamide

20 DBU: 1,8-Diazabicyclo[5.4.0]undec-7-ene

NaHCO₃: sodium bicarbonate

H₂SO₄: sulphuric acid

RT : room temperature, usually in the range of 18 °C to 28 °C

[η]: viscosity

25 v.t.% : volume procent

GPC: Gel permeation chromatography. GPC is measured with UV detector and with polystyrene as standards.

Mw: Molecular weight

PI: Polydispersity index

30 MLC7067: is a mixture of liquid crystal available from Merck KGA with a dielectric anisotropy of 10.3, an optical anisotropy of 0.1025 and a rotational viscosity of 81 m.Pa.s.

Preparation of 4-(3-nitrilepropoxy)benzoic acid 1a

46.8 g (307 mmol) of methyl-4-hydroxybenzoate, 50 g (338 mmol) of 4-bromobutanenitrile are dissolved in 535 mL of NMP. 5.1 g (31 mmol) of potassium iodide and 128 g (93 mmol) of potassium carbonate are added and the suspension is heated up to 80 °C. After 48h, a mixture of 15 g of sodium hydroxide and 49 ml of water is added. The reaction mixture is heated up to 100 °C for 5 hours. Then the solution is cooled down and 480 mL of water is added. The aqueous layer is removed and the organic layer is poured to 1.5 L of icy water. 81 mL of a 25% HCl solution is added. The precipitate is filtered off and washed with 250 mL of water. The resulting product is incorporated in 600 mL of MeOH. The suspension is then stirred for 1 hour and filtered off to give 50.1g (80%) of 4-(3-nitrilepropoxy)benzoic acid as a white powder used without further purification.

The benzoic acid compounds 1b, 1c, 1d, 1l are prepared according to the process described for compound 1a with the proviso that 4-bromobutanenitrile is replaced by 7-bromoheptanitrile, respectively 1-bromobut-2-yne, respectively 1-bromopent-2-yne, respectively 5-bromopentanenitrile.

The benzoic acid compounds 1e, 1f, 1g, 1h, 1m, 1n are prepared according to the process described for compound 1a with the proviso that methyl 4-hydroxybenzoate is replaced by methyl 3-fluoro-4-hydroxybenzoate, respectively 4'-hydroxybiphenyl-4-carboxylic acid methyl ester, respectively methyl 3,5-dihydroxybenzoate, respectively methyl 3-hydroxybenzoate, respectively methyl 4-hydroxy-3,5-dimethyl-benzoate, respectively methyl 4-hydroxy-3-methoxy-benzoate.

Preparation of 4-(2-methoxyethoxy)benzoic acid 1i

4.3 mL (37.5 mmol) of methoxyethanol and 10.1 g (37.5 mmol) of triphenylphosphine are added to a solution of 61 g (30 mmol) of methyl 4-hydroxybenzoate in 120 ml of THF at room temperature. 7.7 mL (37.5 mmol) of diisopropyl azodicarboxylate (DIAD) in 110 mL of THF are incorporated slowly so that the temperature is maintained to 10 °C. After 18 hours at room temperature, the reaction mixture is poured onto icy water and acidified with a 1N HCl solution. The aqueous phase is extracted with ethyl acetate and the organic phase is then washed repeatedly with water, dried over sodium sulfate, filtered and concentrated by rotary evaporation. Chromatography of the

residue using cyclohexane: ethyl acetate 4:1 yielded 6.6 g (98%) of pure methyl 4-(2-methoxyethoxy)benzoate as a white powder. 4.3 g (64.95 mmol) of potassium hydroxide is added to a solution of 6.1 g (29 mmol) of methyl 4-(2-methoxyethoxy)benzoate in 100 mL of EtOH. The solution is heated up to reflux for 5 one hour and poured onto icy water and acidified with a 25% HCl solution. The mixture is filtered off and washed 2 times with 100 mL of water. The solid is suspended in 100 ml of acetonitrile for 1 hour and the precipitate is filtered off and dried under pressure to yield 3.9 g (70%) of pure 4-(2-methoxyethoxy)benzoic acid as a white powder.

10 Preparation of 4-(4-hydroxyphenoxy)butanenitrile compound 1j

To a solution of 1.7g of NaOH in 80 ml of H₂O:dioxane 1:1, 2.2 g (20 mmol) of hydroquinone are added. The solution is stirred for 15 min. Then, 3.5 g (24 mmol) of 3-bromopropanitrile is dropwise added. After complete addition, the mixture is heated up to reflux and stirred for 24 hours. 45 mL of a 1N HCl solution is added to the above 15 mixture. The solution is extracted with ethylacetate and concentrated under reduced pressure to give 2.8 g of 4-(4-hydroxyphenoxy)butanenitrile which is used without further purification.

20 The benzoic acid compounds 1k is prepared according to the process described for compound 1i with the proviso that methoxyethanol is replaced by ethoxyethanol.

The benzoic acid compounds 1x is prepared according to the process described for compound 1i with the proviso that methyl 4-hydroxybenzoate is replaced by methyl 3-fluoro-4-hydroxy-benzoate.

25 Preparation of (2E)-3-(4-{{[4-(3-nitrilepropoxy)benzoyl]oxy}phenyl)prop-2-enoic acid 2a

16.8 g (82 mmol) of 1a is suspended in 56 mL of toluene and few drops of DMF are added. The suspension is heated up to 75 °C and 10.7g (90 mmol) of thionylchloride are added. After 2 hours, the excess of thionyl chloride is removed under pressure. The solution is cooled down to room temperature. 10.2g (83 mmol) of 4-30 hydroxybenzaldehyde 0.5g (4 mmol) of 4-diaminopyridine and 28g (355 mmol) of pyridine are added. After 3 hours, 14.5 g (140 mmol) of malonic acid and 3 g (42 mmol) of pyrrolidine are added. The reaction mixture is allowed to react at 80 °C for 30 min. 16.8 mL of MeOH are then incorporated and the suspension is cooled down and kept at 0 °C for 1 hour. The product is filtered off and suspended for 2 hours in a

solution of 57 mL of MeOH, 11 mL of water and 7.5 g of a 25% HCL solution. The solid is filtered off and washed with MeOH and heptane. The product is crystallized in acetonitrile to give 23 g of (2E)-3-(4-{[4-(3-nitrilepropoxy)benzoyl]oxy}phenyl)prop-2-enoic acid as a white powder.

5

The compounds 2b, 2c, 2d, 2e, 2f, 2g, 2h, 2i, 3k, 2l, 2m, 2n, 2x are prepared according to the process described for compound 2 with the proviso that compound 1a is replaced by compound 1b, respectively 1c, respectively 1d, respectively 1e, respectively 1f, respectively 1g, respectively 1h, respectively 1i, , respectively 1k , respectively 1l , respectively 1m, , respectively 1n, respectively 1x,.

10

The compounds 2k, 2o, 2p, 3b are prepared according to the process described for compound 2a with the proviso that 4-hydroxybenzaldehyde is replaced by 4-hydroxy-3-methoxy-benzaldehyde, respectively 2-fluoro-4-hydroxy-benzaldehyde, respectively 4-aminobenzaldehyde, respectively methyl 5-formyl-2-hydroxy-benzoate.

15

The compounds 2r, 2s, 2t, 2u, 2v, 2w, 2y are prepared according to the process described for compound 2a with the proviso that 4-(3-nitrilepropoxy)benzoic acid 1a is replaced by 4-(2-prop-2-enoyloxyethoxy)benzoic acid, respectively 4-methoxycarbonylbenzoic acid, respectively 4-methoxycyclohexanecarboxylic acid, respectively 4-(dimethylamino)benzoic acid, respectively 1,3-benzodioxole-5-carboxylic acid, respectively 4-(acetoxymethyl)benzoic acid, respectively 4-methoxycarbonylcyclohexanecarboxylic acid .

20

The compound 2q is prepared according to the process described for compound 2a with the proviso that 4-hydroxybenzaldehyde is replaced by 4-formylbenzoic acid and 4-(3-nitrilepropoxy)benzoic acid 1a is replaced by 4-(4-hydroxyphenoxy)butanenitrile 1j.

25

30

The compound 2z is prepared according to the process described for compound 2a with the proviso that 4-hydroxybenzaldehyde is replaced by 2-fluoro-4-hydroxy-benzaldehyde and 4-(3-nitrilepropoxy)benzoic acid 1a is replaced by 4-(2-methoxyethoxy)benzoic acid 1i.

Preparation of the polymer P1

49.2 g of compound 2a are suspended in 375 ml of 4-Methyl-2-pentanone and water. 1.5 g of ammonium catalyst are added to give a white suspension. 38.4 g of 2-(3,4-Epoxycyclohexyl)ethyltriethoxysilane are added dropwise. The mixture is stirred at reflux for 48h. The suspension is allowed to cool down. The upper liquid phase is removed. The resulting yellowish solution is poured slowly into 1.5 L of cold 5 tert-butyl methyl ether. The solid is filtered off to give 70 g of polymer after drying.

The compounds P2, P3, P4, P5, P6, P7, P8, P9, P10, P14, P15, P16, P20, P21, P22, P23, P24, P26, P27, P30, P31, P32, P33, P34, P35, P36 are prepared according to 10 the process described for polysiloxane P1 with the proviso that compound 2a is replaced by compound 2b, respectively 2c, respectively 2d, respectively 2e, respectively 2f, respectively 2g, respectively 2h, respectively 2i, respectively 2k, respectively 2o, respectively 2p, respectively 2q, respectively 3k , respectively 2l, respectively 2m, respectively 2n, respectively 2x, respectively 2s, respectively 2t, 15 respectively 2w, respectively 2y, respectively 2z, respectively 2r, respectively 2u, respectively 2v, respectively 3b .

Preparation of the polymer P17

2.37 g (6.76 mmol) of compound 2a are suspended in 15 ml of 4-methyl-2-pentanone. 20 0.082 g of ammonium catalyst and 1.2 g of epoxycyclohexylethyl polysilsesquioxane (EP0408 manufactured by Hybrid Plastics) are added to give a white suspension. The mixture is stirred at reflux for 24h. The suspension is then allowed to cool down. The upper liquid phase is removed. 25 mL of tetrahydrofuran are added to give a solution. The resulting yellowish solution is poured slowly into 150 mL of tertbutylmethylether. 25 The solid is filtered and washed with 20 mL of tert-butyl methyl ether. The resulting white solid is dried under vacuum to give P17.

Preparation of the polymer P19

2 g (5.69 mmol) of compound 2a are suspended in 15 ml of 4-methyl-2-pentanone. 30 0.200 g of ammonium catalyst and 1.61 g (6.26 mmol) dimethoxy-methyl-[2-(7-oxabicyclo[4.1.0]heptan-4-yl)ethyl]silane are added to give a white suspension. The mixture is stirred at reflux for 24h. The suspension is then allowed to cool down. 25 mL of tetrahydrofuran are added to give a solution. The resulting yellowish solution is poured slowly into 200 mL of cold tertbutylmethylether. The solid is filtered and washed

with 20 mL of tert-butyl methyl ether. The resulting white solid is dried under vacuum to give 1.24 g of P19.








Polymer	Structure of the side chain	Mw determined by GPC	¹ H NMR (300MHz) in THF-d ₈
P1		17620 DA (PI:1.38)	8.06 (br., 2H), 7.61 (br., 3H), 7.2-6.95 (br., 4H), 6.49 (br., 1H), 4.91 (d, 1H), 4.12 (br., 3H), 3.77 (d, 1H), 2.57 (br., 2H), 2.07 (br., 2H), 1.9-1.2 (br., 9H), 0.75 (br., 2H).
P4		10310 DA (PI:1.12)	8.11 (br., 2H), 7.68 (br., 3H), 7.26 (br., 2H), 7.09 (br., 2H), 6.56 (br., 1H), 4.89 (br., 3H), 4.25 (br., 1H), 3.82 (br., 1H), 2.23 (br., 2H), 2.1-1.2 (br., 12H), 0.71 (br., 2H).
P19		3930 DA (PI:1.05)	8.11 (d, 2H), 7.68 (m, 3H), 7.27 (2H, d), 7.06 (d, 2H), 6.54 (d, 1H), 4.9 (d, 1H), 4.18 (br., 3H), 3.78 (d, 1H), 2.61 (t, 2H), 2.12 (q, 2H), 1.95 (br. 1H), 1.37 (br., 8H), 0.72 (br., 2H), 0.18 (s, 3H)
P17		11121 DA (PI:1.15)	8.09 (br., 2H), 7.63 (br., 3H), 7.22 (br., 2H), 7.02 (br., 2H), 6.51 (br., 1H), 4.91 (d, 1H), 4.14 (br., 3H), 3.77 (d, 1H), 2.58 (br., 2H), 2.10 (br., 3H), 1.47 (br., 8H), 0.71 (br., 2H).
P9		31730 DA (PI:1.99)	8.05 (br., 3H), 7.65 (br., 2H), 7.11 (br., 4H), 6.51 (br., 1H), 4.96 (br., 1H), 4.4-3.8 (br., 4H), 3.65 (br., 2H), 3.78 (br., 3H), 2.2-1.1 (br., 9H), 0.86 (br., 2H).


Polymer	Structure of the side chain	Mw determined by GPC	¹ H NMR (300MHz) in DMSO-d ₆
P2		16300 DA (PI:1.2)	7.97 (br., 2H), 7.57 (br., 3H), 7.2 (br., 2H), 7.03 (br., 2H),

	<chem>O=C[C@H](Oc1ccc(Oc2ccc(Oc3ccc(OCCCC#N)cc3)cc2)cc1)C(=O)c4ccc(OCCCC#N)cc4</chem>		6.7 (br., 1H), 4.77 (d, 2H), 3.97 (br., 2H), 3.67 (d, 1H), 2.55 (br., 2H), 1.9-1.2 (br., 17H), 0.78 (br., 2H).
P3	<chem>O=C[C@H](Oc1ccc(Oc2ccc(Oc3ccc(OCCCC#N)cc3)cc2)cc1)C#C</chem>	10270 DA (PI:1.20)	8.04 (br., 2H), 7.63 (br., 3H), 7.14 (br., 4H), 6.56 (br., 1H), 4.91 (br., 3H), 3.66 (br., 1H), 2.1-1.0 (br., 12H), 0.64 (br., 2H).
P10	<chem>O=C[C@H](Oc1ccc(Oc2ccc(Oc3ccc(OCCCC#N)cc3)cc2)cc1)C(=O)c4ccc(O)cc4</chem>	11154 DA (PI:1.3)	8.03 (br., 2H), 7.54 (br., 2H), 7.10 (br., 4H), 6.58 (br., 1H), 4.81 (br., 2H), 4.14 (br., 2H), 3.73 (br., 4H), 2.67 (br., 2H), 2.06 (br., 3H), 1.9-1.0 (br., 8H), 0.57 (br., 2H).
P7	<chem>O=C[C@H](Oc1ccc(Oc2ccc(Oc3ccc(OCCCC#N)cc3)cc2)cc1)C(=O)c4ccc(OCCCC#N)cc4</chem>	25220 DA (PI:3.11)	7.61 (br., 2H), 7.2 (br., 4H), 6.81 (br., 2H), 6.45 (br., 1H), 4.81 (br., 2H), 4.08 (br., 4H), 3.63 (br., 1H), 2.62 (br., 4H), 2.01 (br., 4H), 1.9-1.0 (br., 9H), 0.69 (br., 2H).
P6	<chem>O=C[C@H](Oc1ccc(Oc2ccc(Oc3ccc(OCCCC#N)cc3)cc2)cc1)C(=O)c4ccc(Oc5ccc(OCCCC#N)cc5)cc4</chem>	13100 DA (PI:1.4)	8.2-7.4 (br., 9H), 7.01-7.4 (br., 3H), 6.7 (br., 1H), 6.53 (br., 1H), 4.85 (br., 2H), 4.06 (br., 2H), 3.59 (br., 1H), 2.62 (br., 2H), 2.04 (br., 2H), 1.9-1.0 (br., 9H), 0.69 (br., 2H).
P14	<chem>O=C[C@H](Oc1ccc(Oc2ccc(Oc3ccc(OCCCC#N)cc3)cc2)cc1)C(=O)c4ccc(F)cc4</chem>	38190 DA (PI:3.5)	8.2-7.4 (br., 5H), 7.07 (br., 3H), 6.55 (br., 1H), 4.76 (d, 2H), 4.09 (br., 2H), 3.64 (d, 1H), 2.66 (br., 2H), 2.10-0.95 (br., 11H), 0.6 (br., 2H).
P5	<chem>O=C[C@H](Oc1ccc(Oc2ccc(Oc3ccc(OCCCC#N)cc3)cc2)cc1)C(=O)c4ccc(F)cc4</chem>	354300 DA (PI:19.07)	7.4 (br., 8H), 6.43 (br., 1H), 4.92 (br., 2H), 4.17 (br., 2H), 3.65 (br., 1H), 2.66 (br., 2H), 2.2-1(br., 11H), 0.61 (br., 2H).
P16	<chem>O=C[C@H](Oc1ccc(Oc2ccc(Oc3ccc(OCCCC#N)cc3)cc2)cc1)C(=O)c4ccc(Oc5ccc(OCCCC#N)cc5)cc4</chem>	926200 DA (PI:42)	8.1-7.6 (br., 5H), 6.97 (br., 4H), 6.52 (br., 1H), 4.79 (br., 2H), 4.2-3.4 (br., 3H), 2.6 (br., 2H), 2.1-0.9 (br., 11H), 0.66 (br., 2H).
P8	<chem>O=C[C@H](Oc1ccc(Oc2ccc(Oc3ccc(OCCCC#N)cc3)cc2)cc1)C(=O)c4ccc(OCCCC#N)cc4</chem>	417000 DA (PI:20.9)	8.2-7 (br., 8H), 6.70 (br., 1H), 6.50-6.10 (br., 1H), 4.79 (br., 2H), 4.20-3.40 (br., 3H), 2.61 (br., 2H), 2.07 (br.,

			2H), 2.2-1.00 (br., 11H), 0.57 (br, 2H).
P15		9690 DA (PI:3.5)	7.88 (br., 3H), 7.64 (br., 2.3H), 7.06 (br., 1.5H), 6.47 (br., 0.75H), 4.8 (br., 1.5H), 4.10 (br., 1.5H), 3.66 (d, 0.75H), 2.66 (br., 1.5H), 2.1-1.0 (br., 10.5H), 0.61 (br, 2H).
P20		11230 DA (PI:1.2)	7.9 (br., 2H), 7.6 (br., 3H), 7.1 (br., 4H), 6.5 (br., 1H), 4.9 (d, 2H), 4.2 (br., 2H), 3.7 (br., 2H), 3.5 (br., 3H), 1.9-1.2 (br., 12H), 0.6 (br., 2H).
P31		13220 DA (PI:1.4)	7.6 (br., 3H), 7.1 (br., 2H), 6.4 (br., 1H), 4.7 (br., 2H), 3.6 (br., 5H), 2.4-1.2 (br., 18H), 0.6 (br, 2H).

Polymer	Structure of the side chain	Mw determined by GPC	¹ H NMR (300MHz) in THF-d ₈
P21		14500 DA (PI:1.2)	8.0 (br., 2H), 7.6 (br., 3H), 7.2 (br., 2H), 7.0 (br., 2H), 6.5 (br., 1H), 4.9 (br., 1H), 4.5-3.6 (br., 4H), 2.2-1.2 (br., 13H), 0.8 (br, 2H).
P22		13170DA (PI:1.2)	7.9 (br., 2H), 7.7 (br., 3H), 7.2 (br., 2H), 6.5 (br., 1H), 4.9 (br., 1H), 4.6-3.6 (br., 4H), 2.5 (br., 2H), 2.2-1.2 (br., 11H), 0.8 (br, 2H).
P23		70950 DA (PI:5.1)	7.5 (br., 5H), 7.2 (br., 3H), 6.5 (br., 1H), 5.0 (br., 1H), 4.6-4 (br., 3H), 3.9 (br., 4H), 2.6 (br., 2H), 2.1 (br., 2H) 2.0-1.2 (br., 9H), 0.8 (br, 2H).
P24		11500 DA (PI:1.3)	7.9 (br., 2H), 7.6 (br., 3H), 7.2 (br., 3H), 6.5 (br., 1H), 4.9 (br., 1H), 4.2 (br., 3H), 3.9 (br., 1H), 3.7 (br., 2H), 3.4 (br., 3H), 2.2-1.2 (br.,

			9H), 0.8 (br, 2H).
P33		48000 (PI:2.0)	8.1 (br., 2H), 7.7 (br., 2H), 7.3 (br., 2H), 7.1 (br., 2H), 6.5 (br., 1H), 6.4 (br., 1H), 6.2 (dd, 1H), 5.9 (br., 1H), 4.9 (br., 1H), 4.5 (br., 2H), 4.3 (br., 3H), 3.9 (br., 1H), 3.01 (br., 0.5), 2.3-1.1 (br., 13.5H), 0.8 (br, 3H).
P26		39000 DA (PI:1.5)	8.1 (br., 4H), 7.7 (br., 3H), 7.3 (br., 2H), 6.5 (br., 1H), 4.2 (br., 1H), 3.9 (br., 4H), 2.3-1.1 (br., 9H), 0.8 (br, 2H).
P27		16100 DA (PI:1.4)	7.6 (br., 3H), 7.1 (br., 2H), 6.5 (br., 1H), 4.9 (br., 1H), 4.2 (br., 1H), 3.8 (br., 1H), 3.4 (br., 1H), 3.3 (br., 3H), 2.6 (br., 1H), 2.2-1.1 (br., 17H), 0.8 (br, 2H).
P34		22600 DA (PI:1.4)	8.0 (br., 2H), 7.7 (br., 3H), 7.3, (br., 2H), 6.80 (br., 2H), 6.50 (br., 1H), 4.9 (br., 1H), 4.20 (br., 1H), 3.1 (br., 6H), 2.2-1.1 (br., 9H), 0.8 (br, 2H).
P35		74000 DA (PI:1.2)	7.7 (br., 5H), 7.3 (br., 2H), 7.0 (br., 1H), 6.5 (br., 1H), 6.1 (br., 2H), 4.9 (br., 1H), 4.2 (br., 1H), 3.9 (br., 1H), 2.2-1.0 (br., 9H), 0.8 (br, 2H).
P30		10600 DA (PI:1.2)	8.1 (br., 2H) 7.7 (br., 3H), 7.4 (br., 2H), 7.3 (br., 2H), 6.6 (br., 1H), 5.2 (br., 2H), 4.9 (br., 1H), 4.2 (br., 1H), 3.8 (d, 1H), 2.2-1.1 (br., 12H), 0.8 (br, 2H).
P32		820000 DA (PI:35)	8.1 (br., 2H), 7.7 (br., 2H), 7.0 (br., 3H), 6.6 (br., 2H), 4.9 (br., 1H), 4.2 (br., 3H), 3.7 (d, 2H), 3.4 (br., 3H), 2.2-1.2 (br., 9H), 0.8 (br, 2H).

P36		6200000 DA (PI:257)	8.0 (br., 3H), 7.7 (br., 2H), 7.2 (br., 3H), 6.5 (br., 1H), 4.6 (br., 2H), 3.9 (br., 4H), 2.6 (br., 2H), 2.1 (br., 2H), 2.0-1.2 (br., 9H), 0.8 (br., 2H).
-----	---	---------------------------	---

Preparation of copolymer P25

10 g (28.46 mmol) of compound 2a are suspended in 75 ml of 4-methyl-2-pentanone and water. 0.299 g (1.42 mmol) of ammonium catalyst are added to give a white suspension. 3.88 g (13.66 mmol) of 2-(3,4-epoxycyclohexyl)ethylmethyldiethoxysilane and 3.53 g (13.66 mmol) of 2-(3,4-epoxycyclohexyl)ethyltriethoxysilane are added dropwise. The mixture is stirred at reflux for 48h. Then, the suspension is allowed to cool down. The upper liquid phase is removed and the polymer is rinsed with 25 ml of 4-Methyl-2-pentanone. 30 mL of tetrahydrofuran and 50 ml of ethylacetate are added and the mixture is extracted with 15 ml of water. The resulting solution is poured slowly into 1 L of cold tert-butyl methyl ether. The solid is filtered off and dried under vacuum to give 8.66 g of copolymer.

Mw: 12430 DA (PI:1.29)

15 ^1H NMR (300 MHz) in DMSO-d₆: 8.09 (br., 2H), 7.68 (br., 3H), 7.07 (br., 4), 6.51 (br., 1H), 4.78 (br., 2H), 4.11 (br., 2H), 3.64 (br., 1H), 2.65 (br., 2H), 2.05 (br., 2H), 1.95-0.95 (br., 9H), 0.62 (br., 2H), 0.18 (br., 1.22H)

Preparation of the copolymer P28

20 5 g (14.23 mmol) of compound 2a are suspended in 37.5 ml of 4-methyl-2-pentanone and water. 0.145 g (0.71 mmol) of ammonium catalyst are added to give a white suspension. 3.84 ml (13.3 mmol) of 2-(3,4-epoxycyclohexyl)ethyltriethoxysilane and 0.158 ml (0.71 mmol) of tetraethylorthosilicate are added dropwise. The mixture is stirred at reflux for 48h. Then, the suspension is allowed to cool down. The upper liquid phase is removed and the polymer is rinsed with 25 ml of 4-Methyl-2-pentanone. The mixture is extracted with 15 ml of water. The resulting solution is poured slowly into 600 ml of cold tert-butyl methyl ether. The solid is filtered off and dried under vacuum to give 6.58 g of polymer.

Mw: 24265 DA (PI: 1.66)

¹H NMR (300MHz) in DMSO-d₆: 7.96-6.5 (br., 9H), 6.44 (br., 1H), 4.80 (br., 2H), 4.09 (br., 2H), 3.58 (br., 1H), 2.62 (br., 2H), 2.1-0.9 (br., 11H), 0.61 (br, 1.9H).

Preparation of the copolymer P29

5 6.75 g (19 mmol) of compound 2a, and 0.42 g (1 mmol) of cholic acid are suspended in 50 ml of 4-methyl-2-pentanone and water. 0.21 g (1 mmol) of ammonium catalyst are added to give a white suspension. 5.65 g (19 mmol) of 2-(3,4-epoxycyclohexyl)ethyltriethoxysilane are added dropwise. The mixture is stirred at reflux for 48h. Then, the suspension is allowed to cool down. The upper liquid phase is
10 removed and the polymer is rinsed with 60 ml of 4-Methyl-2-pentanone. The organic phase was extracted 3 times with 15 ml of water. The resulting solution is poured slowly into 190 ml of cold tert-butyl methyl ether. The solid is filtered off and dried under vacuum to give 8.4 g of P29 .

Mw: 69800 DA (PI:4.1)

15 ¹H NMR (300MHz) in THF-d₈: 8.1 (br., 2H), 7.68 (br., 3H), 7.2-6.95 (br., 4H), 6.48 (br., 1H), 4.95 (br., 1H), 4.4-3.6 (br., 3H), 2.55 (br., 2H), 2.1-1.2 (br., 11H), 0.76 (br, 2H).

Preparation of PAA-1

20 0.666 g (3.4 mmol) of 1,2,3,4-cyclobutanetetracarboxylic acid is added to a solution of 0.69 g (3.47 mmol) of 4-(4-aminophenoxy)aniline in 8.6 g of NMP. Stirring is then carried out at 0 °C for 2 hours. The polymer mixture is diluted with 50 mL of NMP, precipitated into 300 mL of water to yield, after drying at 40 °C under vacuum, 2.1 g of polyamic acid PAA-1 in the form of a white powder.

[η]=0.40 dL/g

25

Preparation of PAA-2

30 0.69 g (3.1 mmol) of 2,3,5-tricarboxycyclopentylacetic-1,2:3,4-dianhydride is added to a solution of 1.5 g (3.1 mmol) of 4-(4-aminophenoxy)aniline in 5.1 g of NMP. Stirring is then carried out at 0 °C for 2 hours. The polymer mixture is diluted with 30 g of NMP, precipitated into 300 mL of water to yield, after drying at 40 °C under vacuum, 1.9 g of polyamic acid PAA-3 in the form of a white powder.

[η] = 0.40dL/g

Preparation of PAA-3 from 4,4'-ethylenedianiline

3.2 g (14.1 mmol) of 2,3,5-tricarboxycyclopentylacetic-1,2:3,4-dianhydride is added to a solution of 3 g (14.1 mmol) of 4,4'-ethylenedianiline in 35 g of NMP. Stirring is then carried out at 0 °C for 2 hours. The polymer mixture is then diluted with 47 g of

5 acetone, precipitated into 500 mL of water to yield, after drying at 40 °C under vacuum, 6.5 g of polyamic acid PAA-5 in the form of a white powder.

[η] = 0.52 dL/g

Preparation of PAA-4 from 4,4'-Methylenedianiline

10 5.6 g (25.2 mmol) of 2,3,5-tricarboxycyclopentylacetic-1,2:3,4-dianhydride is added to a solution of 5 g (25.2 mmol) of 4,4'-methylenedianiline in 60 g of NMP. Stirring is then carried out at 0 °C for 2 hours. The mixture is subsequently allowed to react for 1 hour at room temperature. The polymer mixture is then diluted with 100 g of NMP and 78 g of acetone, precipitated into 3500 mL of water to yield, after drying at 40 °C under

15 vacuum, 14 g of polyamic acid PAA-4 in the form of a white powder.

[η] = 0.52 dL/g

Preparation of PAA-5 from 4-(4-amino-2-methyl-phenyl)-3-methyl-aniline

5.6 g (25.2 mmol) of 2,3,5-tricarboxycyclopentylacetic-1,2:3,4-dianhydride is added to 20 a solution of 5 g (25.2 mmol) of 4-(4-amino-2-methyl-phenyl)-3-methyl-aniline in 60 g of NMP. Stirring is then carried out at 0 °C for 2 hours. The mixture is subsequently allowed to react for 1 hour at room temperature. The polymer mixture is then diluted with 100 g of NMP and 78 g of acetone, precipitated into 3500 mL of water to yield, after drying at 40 °C under vacuum, 14 g of polyamic acid PAA-5 in the form of a white

25 powder.

[η] = 0.62 dL/g

Preparation of PAA-6 from 4-(4-amino-2-methyl-phenyl)-3-methyl-aniline

PAA-6 is prepared according to the process described for PAA-5. [η] = 0.52 dL/g

30

APPLICATION EXAMPLESExample 1:

A liquid crystal cell is prepared wherein the liquid crystal is aligned by photo reactive P1 and the electric field is applied between two plan electrodes on each side of the cell gap.

A 8 wt% solution of polysiloxane P1 is prepared by mixing the solid P1 in NMP and stirred thoroughly till the solid is dissolved. Then a second solvent butyl cellusolve (BC) is added and the whole composition is stirred thoroughly to obtain final solution. The solvent ratio between NMP and butyl cellulose is 1:1. The above polymer solution was spin-coated onto the two ITO coated glass substrates at a spin speed of 2500 rpm for 30seconds. After spin coating the substrates are subjected to baking procedure

10 consisting of pre-baking for 1.5 minutes at 130°C and post-baking for 40 minutes at a temperature of 200°C. The resulting layer thickness is around 95-100 nm. The substrates with the coated polymer layer on top are exposed to linearly polarized UV light (LPUV) at an incidence angle of 0° relative to the normal of the substrate surface.

15 The plane of polarization was within the plane spanned by the substrate normal and the propagation direction of the light. The applied exposure dose is 100mJ/cm². After LPUV exposure, a cell is assembled with the 2 substrates, the exposed polymer layers facing to the inside of the cell. The substrates are adjusted relative to each other such that the induced alignment directions are parallel to each other. The cell is capillary filled with liquid crystal MLC7067 (Merck KGA), which had a positive dielectric

20 anisotropy. After that, the cell is optionally annealed at about 92° for 10 minutes and slowly cooled down to room temperature. Alignment quality of the liquid crystal in the cell is checked by placing the cell between two crossed polarizers and adjusted to obtain dark state. The alignment quality is defined to be good, if the dark state show no defects and the liquid crystal is well oriented. The alignment quality is defined to be

25 medium if the dark state has light leakage because of slight inhomogeneous orientation of liquid crystal in some areas of the cell. The alignment quality is defined to be worse, if liquid crystal is not oriented with absence of dark state.

The liquid crystal in the cell showed well defined and homogeneous planar orientation before and after thermal annealing of the cell. A tilt angle below 0.2° is measured using 30 the rotating analyzer method from Shintech.

Example 1a:

A liquid crystal cell is prepared according to the process described in example 1 except that an incidence angle of 40° relative to the normal of the substrate surface is used

for thr linearly polarized UV. The liquid crystal in the cell showed well defined and homogeneous planar orientation before and after thermal annealing of the cell. A tilt angle of about below 0.2° is measured using the rotating analyzer method from Shintech.

5

Example 2:

Cells are prepared with P3, P9, P5, P14, P17, P19P25, P28 according to the process described for example 1. The liquid crystal in the cell showed well defined and homogeneous planar orientation before and after thermal annealing of the cell. Tilt angles of below 0.2° are measured using the rotating analyzer method from Shintech.

10

Example 3:

The image sticking of the cells made in example 1 and 2 were measured. The image sticking of an IPS cell is measured by using an Optipro-250 from Shintech. A wavelength of 589 nm is used. The unbiased sample, consisting of 2 independent pixels, is placed between the crossed polarizers with the alignment direction of the sample being parallel to the first polarizer. The Voltage-Transmittance curve of both pixels is measured by applying 60 Hz square wave voltage in order to find the voltage amplitude V_{100} for maximum transmittance T_{100} and the voltage amplitude V_1 at which a transmittance of 1% of T_{100} is reached ($T_1[0]$). A 60 Hz square wave voltage with an amplitude V_{100} is applied to the first pixel (called measurement pixel) for a time period of 24 hours while the second (reference) pixel remains unbiased. The sample is stored protected from light and at room temperature during this time. After 24 hours the transmittances $T_1[24h]$ are measured again for both pixels by using the same voltages V_1 . The image sticking of the sample is

$$\text{Image sticking (24h)} = \frac{T_1^M(24h)}{T_1^M(0h)} \times \frac{T_1^R(0h)}{T_1^R(24h)} \times 100\%$$

where M refers to the measurement pixel and R refers to the reference pixel. The image sticking of a cell is considered very good for values below 110%, good for values between 110% to 120% and medium for values above 120%.

25

Polymer	Image sticking (%)
P1	Very good

P5	Very Good
P9	Good
P17	Very good
P3	Medium
P14	Medium

Example 4:

The alignment quality of the cells from example 1 and example 2 are quantified by contrast ratio (CR). The contrast of an unbiased IPS cell is determined by measuring

5 its light leakage using a transmission microscope consisting of a backlight, polarizer and analyzer, optics (condenser lenses, microscope objective) between the polarizers and a photomultiplier to measure the transmitted light power. As a light source an LED backlight from ELDIM is used, which is similar to the backlight from commercial displays. The measurement area in the focal plane (sample) of the microscope

10 objective is about 1 mm².

Without sample the polarizers from the microscope are brought to the perpendicular position (the detector signal displays a minimum value). The unbiased sample is placed under the microscope objective and rotated in-plane until the detector displays a minimum value V_0 (the alignment direction of the cell is parallel to the polarizer). By

15 keeping the in-plane position of the sample, the analyzer is rotated by 90° (until the detector displays a maximum value V_{max}). The contrast of the sample is $CR = V_{max}/V_0$. If CR is below 1000 the contrast is said “bad”, if CR is between 1000 and 2000 CR is “medium”, if CR is between 2000-3000 contrast is said “good” and if CR is above 3000 CR is said “very good”.

20

Polymer	CR
P1	Good
P3	Good
P4	Good
P5	Good
P9	Very Good
P7	Bad
P14	Good
P17	Medium

P19	Medium
-----	--------

Example 5:

5 A cell is prepared as in example 1, except that the solution to be coated comprised polysiloxane P1 and the polyamic acid PAA-1 in ratio of 10:90 per weight % to form a blend composition. A 6.4 % solution is prepared as for the procedure explained in example 1 except that the two polymers were mixed in the solvent at the same time and the spin speed used is 3800 rpm for 30seconds. The liquid crystal in the cell showed well defined and homogeneous planar orientation before and after thermal
10 annealing of the cell. A tilt angle of about 0.01 ° is measured using the rotating analyzer method.

Example 6:

15 A cell is prepared as in example 1, except that the solution to be coated comprised a polysiloxane P1 and the polyamic acid PAA-2 in ratio of 10:90 per weight % to form a blend composition. The liquid crystal in the cell showed well defined and homogeneous planar orientation before and after thermal annealing of the cell. A tilt angle below 0.1 ° is measured using the rotating analyzer method.

20 Example 6b:

A cell is prepared as in, except that the solution to be coated comprised a polysiloxane P1 and the polyamic acid PAA-4 in ratio of 10:90 per weight % to form a blend composition. The liquid crystal in the cell showed well defined and homogeneous planar orientation before and after thermal annealing of the cell. A tilt angle below 0.1 °
25 is measured using the rotating analyzer method.

Example 6c:

A cell is prepared as in, except that the solution to be coated comprised a polysiloxane P1 and the polyamic acid PAA-5 in ratio of 10:90 per weight % to form a blend
30 composition. The liquid crystal in the cell showed well defined and homogeneous planar orientation before and after thermal annealing of the cell. A tilt angle below 0.1 ° is measured using the rotating analyzer method.

Example 6d:

A cell is prepared as in, except that the solution to be coated comprised a polysiloxane P1 and the polyamic acid PAA-6 in ratio of 10:90 per weight % to form a blend composition. The liquid crystal in the cell showed well defined and homogeneous planar orientation before and after thermal annealing of the cell. A tilt angle below 0.1° is measured using the rotating analyzer method.

Example 7

Cells are prepared as in example 5 except that the solution to be coated comprised instead of P1 the polysiloxane P24, P21, P7, P14, P22, P23, P20, P26, P27, P31, P32, P33, P34, P36. The liquid crystal in the cells showed well defined and homogeneous planar orientation before and after thermal annealing of the cell.

Example 7a

Cells are prepared as in example 5 except that the applied exposure dose is 500 mJ/cm² and the solution to be coated comprised instead of P1 the polysiloxane P35, P30. The liquid crystal in the cells showed well defined and homogeneous planar orientation before and after thermal annealing of the cell.

Example 8:

The image sticking of the cells prepared in example 5, 6, 6b, 6c, 6d and 7, 7a were determined by using the same method described for example 3

Blend	Image sticking
P1/PAA-1	Very Good
P1/PAA-2	Very Good
P1/PAA-5	Very Good
P1/PAA-6	Medium
P7/PAA-1	Medium
P14/PAA-1	Good
P24/PAA-1	Very Good
P21 /PAA-1	Very good
P22/PAA-1	Good

P23/PAA-1	Good
P26/PAA-1	Very good
P27/PAA-1	Medium
P30/PAA-1	Good
P31/PAA-1	Good
P32/PAA-1	Good
P33/PAA-1	Medium
P35/PAA-1	Medium
P36/PAA-1	Medium
P29/PAA-1	Very good

Example 9:

5 The contrasts of the cells prepared in example 5, 6, 6b, 6c, 6d, 7 and 7a were determined by using the same method described for example 4

Blend	CR
P1/PAA-1	Very good
P1/PAA-5	Very Good
P1/PAA-6	Very good
P7/PAA-1	Good
P14/PAA-1	Very good
P24/PAA-1	Medium
P20/PAA-1	Medium
P21 /PAA-1	Very good
P22/PAA-1	Medium
P23/PAA-1	Good
P26/PAA-1	Medium
P27/PAA-1	Medium
P30/PAA-1	Good
P31/PAA-1	Good
P32/PAA-1	Very good
P33/PAA-1	Very Good

P35/PAA-1	Medium
P36/PAA-1	Good
P29/PAA-1	Very good


Example 10:

Voltage holding ratio (VHR) of the cells from example 7 was measured at room temperature using LCM-1 instrument from Toyo, Japan. The VHR was measured using a short and a long frame period (T). In the short one, the voltage decay V (at T=20ms) of a voltage surge of 64 μ s with V_0 (V at t=0) = 5V is then measured over a period of T=20ms. In the long one, the voltage decay V (at T=1667ms) of a voltage surge of 64 μ s with V_0 (V at t=0) = 1V is then measured over a period of T=1667ms. The voltage holding ratio is then determined, at room temperature, given by integration of the measurement curve between V_0 and V weighted by the area in the case of 100% VHR. The results show VHR \geq 99 % for all tested cells.

CLAIMS

1) A siloxane polymer or copolymer comprising at least the monomer of formula

5



wherein

10 R_a represents OH, Cl, substituted or unsubstituted alkoxyl group having 1 to 20 carbons, alkyl group having 1 to 20 carbons, or aryl group having 1 to 20 carbons;

S₁ represent a single bond or straight-chain or branched, substituted or unsubstituted C₁-C₂₄alkylen in which one or more preferably non-adjacent, -C-, -CH-, -CH₂- group may be replaced by an heteroatom;

15

z is an integer from 0 to 15;

Z_1 represents a single bond, or a substituted or unsubstituted aliphatic or alicyclic group of C_3 to C_{12} ;

n_0 is an integer from 0 to 4;

20

n_1 is an integer from 0 to 15;

n_2 is an integer from 1 to 15;

x_0 is an integer from 1 to 2;

X, Y each independently from each other represents H, F, Cl, CN;

S₂ represents a cyclic, aromatic, straight-chain or branched, substituted or unsubstituted C₁-C₂₄alkylen in which one or more -C-, -CH-, -CH₂- groups may be replaced by a linking group;

5 E represents O, S, NH, C(C₁-C₆ alkyl), NR⁴, OC, OOC, OCONH, OCONR⁴, SCS, SC, wherein R⁴ is cyclic, straight chain or branched, substituted or unsubstituted C₁-C₂₄ alkyl wherein one or more -C-, -CH-, -CH₂-, group(s) may be independently from each other be replaced by a linking group.

10 A represents halogen, H or substituted or unsubstituted C₁-C₂₄ alkyl, a substituted or unsubstituted C₁-C₂₄ alkenyl, a substituted or unsubstituted C₁-C₂₄ alkynyl, or a carboxylic acid, C₁-C₂₄ alkoxy, wherein one or more, -C-, -CH-, -CH₂-, group may independently from each other be replaced by a heteroatom;

R₀ represents OH, Cl, a linear or branched, substituted or unsubstituted alkoxy group having 1 to 20 carbons, wherein one or more, -C-, -CH-, -CH₂-, could be replaced by unsubstituted or substituted C₆-C₂₀ aryl group;

15 Z₂ represents a chemical group having a delocalisation of its electronical density and/or inducing a delocalisation of the electronical density of its neighboring atom;

and T represents an unsubstituted or substituted, straight-chain C₁-C₁₆alkyl.

20 2) A siloxane polymer or copolymer according to claim 1, wherein

R_a, z, n₁, n₂, x₀, S₂, A, R₀, T are as described above; and

Z₁ represents a substituted or unsubstituted C₅-C₆ alicyclic group;

S₁ represents a substituted or unsubstituted C₁-C₂₄ straight chain alkyl;

E represents O, or S or NH;

25 X, Y are H; and

Z₂ is C₁-C₆ alkoxy, di-(C₁-C₁₆ alkyl)amino, nitrile, pyridyl, unsubstituted or substituted straight-chain or branched alkynyl, amine, acrylate, C₁-C₆ alkyl ester,

unsubstituted or substituted carbocyclic or heterocyclic aromatic group or alicyclic group.

3) A siloxane polymer or copolymer according to claim 1 or 2, wherein

5 R_a , z , n_1 , n_2 , x_0 , S_2 , R_0 , T are as described above; and

A represents H, one or more halogens, one or more methoxy groups or one or more carboxylic groups;

Z_1 represents a substituted or unsubstituted C_5 - C_6 alicyclic group;

S_1 represents a substituted or unsubstituted C_1 - C_{24} straight chain alkyl;

10 E represents O, or S or NH;

X , Y are H; and

Z_2 is C_1 - C_6 alkoxy, di- $(C_1$ - C_{16} alkyl)amino, nitrile, pyridyl, unsubstituted or substituted straight-chain or branched alkynyl, amine, acrylate, C_1 - C_6 alkyl ester, unsubstituted or substituted carbocyclic or heterocyclic aromatic group or alicyclic group.

15

4) A siloxane polymer or copolymer according to any one of claims 1 to 3, wherein

R_a , z , n_1 , n_2 , x_0 , S_2 , R_0 , T are as described above; and

A represents H, one or more halogens, one or more methoxy groups or one or more carboxylic groups;

20

Z_1 represents a substituted or unsubstituted C_5 - C_6 alicyclic group;

S_1 represents a substituted or unsubstituted C_1 - C_{24} straight chain alkyl;

E represents O;

X , Y are H; and

Z_2 is C_1 - C_6 alkoxy, di-(C_1 - C_{16} alkyl)amino, nitrile, pyridyl, unsubstituted or substituted straight-chain or branched alkynyl, amine, acrylate, C_1 - C_6 alkyl ester, unsubstituted or substituted carbocyclic or heterocyclic aromatic group or alicyclic group.

5

5) A siloxane polymer or copolymer according to any one of claims 1 to 4, wherein

R_a , z , n_1 , n_2 , x_0 , S_2 , R_0 , Z_2 , T are as described above; and

A represents H, one or more halogens, one or more methoxy groups or one or more carboxylic groups;

10

Z_1 is a substituted or unsubstituted cyclohexanol group or substituted or unsubstituted cyclohexanether group;

S_1 is ethyl group;

X and Y are H;

E is O; and

15

Z_2 is C_1 - C_6 alkoxy, di-(C_1 - C_{16} alkyl)amino, nitrile, pyridyl, unsubstituted or substituted straight-chain or branched alkynyl, amine, acrylate, C_1 - C_6 alkyl ester, unsubstituted or substituted carbocyclic or heterocyclic aromatic group or alicyclic group.

20

6) A siloxane copolymer comprising the monomer of formula (I) according to any one of claims 1 to 5.

25

7) Composition comprising at least one first siloxane polymer or copolymer according to anyone of claims 1 to 6 and a second polymer or copolymer, which is not identical to the first siloxane polymer or copolymer, and optionally an additive.

8) Composition comprising at least one first siloxane polymer or copolymer according to anyone of claims 1 to 6 and a second polymer or copolymer, which is polyamic acid or polyimide, and optionally an additive.

5 9) Process for preparing a linear, branched or crosslinked siloxane polymer or copolymer according to any one of claims 1 to 5 comprising the steps of:

i. reacting at least one compound selected from the group consisting of siloxane monomers, polymers and oligomers comprising the monomer of formula (II)



10

(II)

wherein

R_a represents OH, Cl, substituted or unsubstituted alkoxy group having 1 to 20 carbons, alkyl group having 1 to 20 carbons, or aryl group having 6 to 20 carbons;

15

R_1 represents OH, Cl, a linear or branched, substituted or unsubstituted alkoxy group having 1 to 20 carbons, in which a C, CH could be replaced by unsubstituted or substituted $\text{C}_6\text{-C}_{20}$ aryl group;

20


S_1 represents a single bond or or a straight-chain or branched, substituted or unsubstituted $\text{C}_1\text{-C}_{24}$ alkylen, in which one or more preferably non-adjacent, -C-, -CH-, - CH_2 - group may be replaced by an heteroatom;

z is an integer from 0 to 15;

Z_3 represents substituted or unsubstituted cyclic group of C_3 to C_{12} having an epoxy group

25

with another compound of formula (III)



wherein

E_1 represents an OH, SH, NH₂, NH(C₁-C₆alkyl), NHR⁴, HOC, HOOC, HOCONH, HOCONR⁴, HSCS, HSC, wherein R⁴ is cyclic, straight chain or branched, substituted or unsubstituted C₁-C₂₄alkyl where in one or more C, CH, CH₂ group(s) may be independently from each other replaced by a linking group.

X , Y each independently from each other represent H, F, Cl, CN;

A represents substituted or unsubstituted C₁-C₂₄ alkyl, a substituted or unsubstituted C₁-C₂₄ alkenyl, a substituted or unsubstituted C₁-C₂₄ alkynyl, wherein one or more, -C-, -CH-, -CH₂-, group may independently from each other be replaced by a heteroatom;

S_2 represents a spacer unit;

n_1 is an integer from 0 to 15;

n_2 is an integer from 1 to 15;

Z_2 represents a chemical group having a delocalisation of its electronical density and/or inducing a delocalisation of the electronical density of its neighboring atom; and

T represents an unsubstituted or substituted, straight-chain C₁-C₁₆alkyl, in the presence of an organic solvent and a catalyst;

ii. optionally reacting the product obtained by step i) with a C₁-C₂₄ linear, branched or cyclic alcohol wherein one or more C, CH, CH₂ group(s) may be independently from each other be replaced by a linking group, under the presence of a base; and

25

iii. isolating and purifying the obtained product.

- 10) A siloxane polymer or copolymer obtainable by the process according to claim 8.
- 5 11) Orientation layer, comprising at least one siloxane polymer or copolymer according to any one of claims 1 to 6 or 9, or a composition according to claim 7.
- 12) Use of an orientation layer according to claims 10 or 11 for the orientation of liquid crystals.
- 10 13) Use according to claim 12, wherein the orientation of liquid crystal is a planar alignment.
- 14) Use of an orientation layer according to claims 10 or 11 for the alignment of
 - i. liquid crystal composition comprising one or more polymerizable liquid crystal monomers, or comprising one or more liquid crystal polymers or oligomers, which are the polymerized form of said polymerizable liquid crystal monomers, and/or
 - ii. liquid crystal compositions comprising one or more polymerizable liquid crystal monomers, or comprising one or more liquid crystal polymers or oligomers, which are the polymerized form of said polymerizable liquid crystal monomers, said liquid crystal compositions being sandwiched between a pair of said orientation layers.
- 20 15) Optical or electro-optical unstructured or structured elements, preferably liquid crystal display cells, multi-layer and hybrid layer elements, comprising at least one linear, branched or crosslinked polymer or copolymer according to any one of claims 1 to 6 or 9 or a composition according to claim 7 or an orientation layer according to claims 10 or 11.
- 25

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2016/077077

A. CLASSIFICATION OF SUBJECT MATTER
INV. C08G77/38 C08G77/385 C08G77/388 G02F1/1337
ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
C08G G02F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DATABASE WPI Week 200919 Thomson Scientific, London, GB; AN 2009-F00564 XP002754279, -& WO 2009/017240 A1 (JSR CORP) 5 February 2009 (2009-02-05) abstract Scheme 2 page 10; pages 7-8; examples 1-5 ----- -/-	1-6,9-15
Y		2-5

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier application or patent but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search	Date of mailing of the international search report
28 November 2016	06/12/2016
Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer Dalet, Pierre

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2016/077077

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DATABASE WPI Week 201149 Thomson Scientific, London, GB; AN 2011-H65369 XP002754280, -& JP 2011 132494 A (JSR CORP) 7 July 2011 (2011-07-07) abstract Synthesis examples 10-16; pages 10-22; examples 7-14 -----	1-15
Y	-----	2-5
X	WO 2013/050121 A1 (ROLIC AG [CH]) 11 April 2013 (2013-04-11) cited in the application	1-8, 10-15
Y	Especially compound (VIb) in claim 3; claims 1-16; examples 64,73 pages 4-7 -----	2-5
Y	US 6 277 502 B1 (BUCHECKER RICHARD [CH] ET AL) 21 August 2001 (2001-08-21) abstract columns 3-4 -----	2-5
1		

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2016/077077

Patent document cited in search report	Publication date	Patent family member(s)		Publication date
WO 2009017240	A1	05-02-2009	CN 101687996 A JP 5071644 B2 JP 2009036966 A KR 20100037125 A TW 200922975 A WO 2009017240 A1	31-03-2010 14-11-2012 19-02-2009 08-04-2010 01-06-2009 05-02-2009
JP 2011132494	A	07-07-2011	JP 5533416 B2 JP 2011132494 A	25-06-2014 07-07-2011
WO 2013050121	A1	11-04-2013	CN 103842329 A EP 2763957 A1 JP 2014529000 A KR 20140074982 A US 2014249244 A1 WO 2013050121 A1	04-06-2014 13-08-2014 30-10-2014 18-06-2014 04-09-2014 11-04-2013
US 6277502	B1	21-08-2001	CN 1195015 A DE 59807348 D1 HK 1010884 A1 JP 4205195 B2 JP H10324690 A SG 90026 A1 US 6277502 B1	07-10-1998 10-04-2003 13-06-2003 07-01-2009 08-12-1998 23-07-2002 21-08-2001