



HU000025800T2

(19) **HU****MAGYARORSZÁG**
Szellemi Tulajdon Nemzeti Hivatala(11) Lajstromszám: **E 025 800**(13) **T2****EURÓPAI SZABADALOM**
SZÖVEGÉNEK FORDÍTÁSA

- (21) Magyar ügyszám: **E 12 174196**
(22) A bejelentés napja: **2012. 06. 28.**
(96) Az európai bejelentés bejelentési száma:
EP 20120174196
(97) Az európai bejelentés közzétételi adatai:
EP 2679638 A1 **2014. 01. 01.**
(97) Az európai szabadalom megadásának meghirdetési adatai:
EP 2679638 B1 **2015. 09. 02.**
- (51) Int. Cl.: **D21H 17/66** (2006.01)
C09C 1/02 (2006.01)
D21H 17/67 (2006.01)
D21H 19/38 (2006.01)
D21H 17/69 (2006.01)
D21H 17/00 (2006.01)

(72) Feltaláló(k): BURI, Matthias, 4852 Rothrist (CH) Rentsch, Samuel, 4663 Aarburg (CH) Gane, Patrick A.C., 4852 Rothrist (CH)	(73) Jogosult(ak): Omya International AG, 4665 Oftringen (CH) (74) Képviselő: dr. Bódizs Árpád, SBGK Szabadalmi Ügyvivői Iroda, Budapest
---	---

- (54) **Magas szilárdanyag-tartalmú vizes ásvány és/vagy töltőanyag és/vagy pigment savas pH-jú közegben**

Az európai szabadalom ellen, megadásának az Európai Szabadalmi Közlönyben való meghirdetésétől számított kilenc hónapon belül, felszólalást lehet benyújtani az Európai Szabadalmi Hivatalnál. (Európai Szabadalmi Egyezmény 99. cikk(1))

A fordítást a szabadalmas az 1995. évi XXXIII. törvény 84/H. §-a szerint nyújtotta be. A fordítás tartalmi helyességét a Szellemi Tulajdon Nemzeti Hivatala nem vizsgálta.



(11) **EP 2 679 638 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
02.09.2015 Bulletin 2015/36

(51) Int Cl.:
D21H 17/66 ^(2006.01) **D21H 17/67** ^(2006.01)
D21H 17/69 ^(2006.01) **D21H 19/38** ^(2006.01)
C09C 1/02 ^(2006.01) **D21H 17/00** ^(2006.01)

(21) Application number: **12174196.1**

(22) Date of filing: **28.06.2012**

(54) **High solids aqueous mineral and/or filler and/or pigment suspension in acidic pH environment**

Wässriges Mineral mit hohem Feststoffanteil und/oder Füller und/oder Pigmentsuspension in einer sauren pH-Umgebung

Suspension aqueuse à haute teneur solide de minéraux et/ou de filler et/ou de pigment en milieu à pH acide.

(84) Designated Contracting States:
**AL AT BE BG CH CY CZ DE DK EE ES FI FR GB
GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO
PL PT RO RS SE SI SK SM TR**
Designated Extension States:
BA ME

- **Rentsch, Samuel**
4663 Aarburg (CH)
- **Gane, Patrick A.C.**
4852 Rothrist (CH)

(43) Date of publication of application:
01.01.2014 Bulletin 2014/01

(74) Representative: **Maiwald Patentanwalts GmbH**
Elisenhof
Elisenstrasse 3
80335 München (DE)

(73) Proprietor: **Omya International AG**
4665 Oftringen (CH)

(56) References cited:
EP-A1- 1 982 759 EP-A1- 2 264 108
EP-A1- 2 264 109

(72) Inventors:
• **Buri, Matthias**
4852 Rothrist (CH)

EP 2 679 638 B1

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

[0001] The present invention relates to high solids aqueous mineral and/or filler and/or pigment suspensions in acidic pH environment, to a method for producing such high solids aqueous mineral and/or filler and/or pigment suspension, to the use of the high solids aqueous mineral and/or filler and/or pigment suspension in paper making, paper coating, plastic, agricultural and/or paint applications and as filler in paper and to a coating color formulation comprising the high solids aqueous mineral and/or filler and/or pigment suspension.

[0002] In practice, aqueous preparations and especially suspensions of water-insoluble solids such as calcium carbonate containing materials are used extensively in the paper, paint, rubber and plastics industries as coatings, fillers, extenders and pigments for papermaking as well as lacquers and paints. For example, suspensions, also called slurries of calcium carbonate, talc or kaolin are used in the paper industry in large amounts as filler and/or as a component in the preparation of coated paper. Typical aqueous preparations of water-insoluble solids are characterized in that they VT:MJ comprise water, a water-insoluble dispersed solid compound and optionally further additives in the form of a suspension or slurry.

[0003] One problem in this regard resides in the fact that the adjustment of suitable mechanical properties for such aqueous suspensions is still a challenge under certain conditions. Since the transport of suspensions of calcium carbonate should be economically viable, the quantity of water in the suspension or the volume of the suspension should be as small as possible. However, especially at low temperatures such as typically reached in winter time the mechanical properties of such high solids aqueous suspensions significantly worsen due to a freezing of the suspension which makes the transport and further handling difficult. In addition thereto, high solids aqueous suspensions comprising calcium carbonate containing material tend to be instable under acidic conditions such as in the presence of e.g. acidic additives which can be typically part of such aqueous suspension and, thus, result in worsen mechanical properties over time.

[0004] In this regard, several approaches for improving the mechanical properties of aqueous suspensions comprising calcium carbonate containing material have been proposed. For example, WO 96/32448 describes a process for the processing of a dispersion of calcium carbonate (known in the industry as a "slurry") with a low concentration of carbonate (1 to 30% of solid matter) using polyDIMDAC (dimethyldiallyl ammonium homopolymer), which is a cationic aggregating agent of low molecular weight from 10,000 to 500,000, in order to obtain bulk. This patent uses both PCC and ground natural calcium carbonate, referred to as "G(N)CC" or ground natural calcium carbonate, or mixtures thereof. This process is mainly one of flocculation, an aggregation of small particles onto larger ones and the property of interaction with the fibres is principally obtained by the exclusively coarse granulometry of the particles. The physical properties of the paper are then unfavourably affected when its weight diminishes.

[0005] WO 96/32449 provides broadly the same information. The aim is to obtain a selective aggregation of fine and ultra-fine particles, using an aggregating agent presenting a charge opposed to the overall charge of the filler.

[0006] US 4,367,207 describes a process for treating CaCO_3 in the presence of an anionic organopolyphosphonate electrolyte, but the aim is simply to obtain a suspension of finely-divided carbonate.

[0007] EP 0 406 662 describes a process for manufacturing synthetic carbonate in which a pre-mix is made of CaCO_3 in aragonitic form with lime; to this slurry is added a "phosphoric acid derivative" such as phosphoric acid or its salts or various phosphates, and finally CO_2 is introduced in order to effect conventional carbonation. The purpose of this patent is specifically to obtain a PCC with a large particle size and a particular crystalline form (acicular), the industrial manufacture of which was not previously possible.

[0008] Phosphoric acid is used in EP 0 406 662 in order to produce specifically the aragonitic form via an unidentified "phosphoric acid calcium" which provides new nucleation seeds for the required crystalline form. The carbonate products obtained are useful in paper manufacture to allow the incorporation of greater quantities of mineral matter into the paper, producing incombustible interior papers. No properties such as the opacity, gloss or bulk of the paper are mentioned. Furthermore, the only application example concerns a carbonate/resin compound.

[0009] EP 1 982 759 A1 relates to a process for the purification of water, wherein a surface-reacted natural calcium carbonate is brought into contact with the water to be purified, the surface-reacted natural calcium carbonate being the reaction product of a natural calcium carbonate with an acid and carbon dioxide, which is formed in situ by the acid treatment and/or supplied externally.

[0010] EP 2 264 108 A1 relates to a process for preparing a surface-reacted calcium carbonate in an aqueous environment. The process aims at avoiding the mandatory implementation of medium-strong to strong acids. EP 2 264 108 A1 is also directed to an aqueous suspension of surface-reacted calcium carbonate which is obtainable by the process.

[0011] EP 2 264 109 A1 relates to a process for preparing surface-reacted calcium carbonate. The process comprising the following steps: a) providing a calcium carbonate; b) providing 5 wt.-% to 50 wt.-%, based on the weight of calcium carbonate, of at least one acid having a pKa of less than or equal to 2.5, wherein the corresponding acid anion is capable of forming water-insoluble calcium salts; c) providing gaseous CO_2 ; d) providing at least one water soluble non-polymeric organic and/or inorganic weak acid and/or a hydrogen salt of said at least one water soluble non-polymeric organic

and/or inorganic weak acid; and e) contacting said calcium carbonate with said at least one acid having a pKa of less than or equal to 2.5 of step b), with said gaseous CO₂ of step c) and with said at least one water soluble non-polymeric organic and/or inorganic weak acid and/or hydrogen salt of said at least one water soluble non-polymeric organic and/or inorganic weak acid of step d); wherein the at least one water soluble non-polymeric organic and/or inorganic weak acid

has a pKa of greater than 2.5 and wherein its corresponding acid anion is capable of forming water-insoluble calcium salts.

[0012] Processes are also known for giving particular properties to the carbonate-containing material.

[0013] We shall mention among others the obtaining of properties of resistance to acids, which are useful when the carbonate is employed as a filler in acidic paper-making processes, which are some of the traditional paper manufacture procedures. Thus, US 5,043,017 describes the stabilisation of calcium carbonate, and in particular of PCC by the action of a calcium-chelating agent such as calcium hexametaphosphate, and an associated base which can be an alkaline metal salt of a weak acid (phosphoric, citric, boric, acetic acid etc.).

[0014] US 4,219,590 describes a process for improving dry calcium carbonate by its treatment with a "totally dry anhydride gas". Herein, the improvement of the surface treatment is effected by a fatty acid or an acid resin or similar products. This process treats the carbonate by boil-off vapours of phosphoric, hydrochloric, nitric, capric or acrylic acid or chlorides or fluorides of aluminum, or of fumaric acid etc. The aim is to split the carbonate particles into fine particles.

[0015] US 5,230,734 is also known, which uses CO₂ to produce a Ca-Mg carbonate. WO 97/08247 describes a carbonate formulation, also for paper, obtained by a weak acid method. The carbonate is treated with a mixture of a weak acid and weak base, those being phosphoric acid and a derivative of an organic acid, respectively. WO 97/14847 also describes a carbonate resistant to acids, for paper, which is treated with a mixture of two weak acids in order to "de-activate" the surface of the carbonate.

[0016] WO 98/20079 also describes a process for rendering a carbonate resistant to acids, and in particular a PCC, by adding calcium silicate and a weak acid or alum. US 5,164,006 uses a treatment by CO₂ in order to obtain properties of resistance to an acid medium. However, the addition of products such as zinc chloride is then necessary, which does not meet environmental standards.

[0017] As already mentioned above, the aqueous suspensions typically comprise water, a water-insoluble dispersed solid compound and optionally further additives in such preparations. In this regard, it should be further noted that such dispersed calcium carbonate comprising aqueous suspensions in combination with calcium chloride can cause serious problems during e.g. the production of such suspension the production of a coating colour composition, its storage, and subsequent use. If such a calcium carbonate comprising aqueous suspension comes in contact with calcium chloride or other salts of monovalent, divalent or trivalent cations, the formation of agglomerated and flocculated particles in the aqueous suspension occurs which may lead to unwanted effects such as a severe worsen of mechanical properties and/or partial dissolution of acid sensitive material in the composition.

[0018] This problem is getting worse with increasing content of calcium carbonate and/or calcium chloride in the aqueous composition, and is especially pronounced in calcium carbonate comprising aqueous compositions having high solids content, i.e. compositions having solids content of more than 50 wt.-% based on the total weight of the composition.

[0019] Therefore, there is a continuous need for alternative high solids aqueous mineral and/or filler and/or pigment suspensions which provide a better performance than existing high solids aqueous mineral and/or filler and/or pigment suspensions and effectively maintain the mechanical properties of a suspension at low temperature and/or in acidic environment.

[0020] Accordingly, it is an objective of the present invention to provide an aqueous mineral and/or filler and/or pigment suspensions having high solids content. A further objective of the present invention is to provide a high solids aqueous mineral and/or filler and/or pigment suspension in which the formation of agglomerated and flocculated particles in the suspension is reduced or prevented in pH acidic environment and thus maintains sufficient mechanical properties for such suspension. Another objective of the present invention is to provide a high solids aqueous mineral and/or filler and/or pigment suspension being stable in pH acidic environment, i.e. maintains sufficient mechanical properties, over a period of at least 24 hours. An even further objective is to provide a high solids aqueous mineral and/or filler and/or pigment suspension having sufficient mechanical properties at temperatures of about -5 °C and even below, i.e. said suspension does not freeze under such conditions. A still further objective is to provide a high solids aqueous mineral and/or filler and/or pigment suspension which does not affect the other physical properties of the suspension, such as optical properties, in an unacceptable way. Another objective is to provide a high solids aqueous mineral and/or filler and/or pigment suspension having an acidic pH in the presence of calcium carbonate particles over a period of at least 24 hours, preferably over a period of at least 1 week and most preferably over a period of at least 1 month at a storage temperature between -5 °C to +23 °C.

[0021] The foregoing and other objectives are solved by a high solids aqueous mineral and/or filler and/or pigment suspension in acidic pH environment comprising:

- a) at least one calcium carbonate-containing material comprising calcium carbonate-containing particles, and
- b) at least one salt of at least one strong acid, wherein the at least one strong acid forming the at least one salt of

at least one strong acid is selected from the group consisting of acids having a pK_a value of less than or equal to zero at +23 °C,

wherein the high solids aqueous suspension has

- i) a solids content of at least 50 wt.-%, based on the total weight of the high solids aqueous suspension,
- ii) a Brookfield viscosity at 100 rpm of $\leq 1\,000$ mPas at a temperature of -5 °C
- iii) a pH of < 6 at +23 °C, and
- iv) a conductivity of between 10 and 100 mS/cm at -5 °C and at +23 °C, and wherein the high solids aqueous suspension comprises the at least one salt of at least one strong acid in an amount from 1 to 20 wt.-%, based on the total weight of the high solids aqueous suspension.

[0022] The inventors surprisingly found that the foregoing high solids aqueous mineral and/or filler and/or pigment suspension according to the present invention leads to a suspension in which the formation of agglomerated and flocculated particles in the suspension is reduced or prevented in pH acidic environment and thus maintains sufficient mechanical properties for such suspension and, furthermore, provides for a stability in acidic environment over a period of at least 24 hours. It was further observed that the high solids aqueous mineral and/or filler and/or pigment suspension has an acidic pH in the presence of calcium carbonate particles over a period of at least 24 hours at a storage temperature between -5 °C to +23 °C. Furthermore, the inventors found out that the high solids aqueous mineral and/or filler and/or pigment suspension does not freeze at temperatures of about -5 °C and even below and does not affect the other properties of the suspension, such as the optical properties, in an unacceptable way. In particular, this is achieved by the use of a combination of at least one calcium carbonate-containing material and at least one salt of at least one strong acid in a high solids aqueous mineral and/or filler and/or pigment suspension having solids content of at least 50 wt.-% based on the total weight of the high solids aqueous suspension. Thus, the instant high solids aqueous mineral and/or filler and/or pigment suspension enables the provision of a high solids aqueous suspension being stable in acidic environment.

[0023] It should be understood that for the purposes of the present invention, the following terms have the following meaning:

For the purpose of the present invention, the term "suspension" or "slurry" comprises insoluble solids and water and optionally further additives and usually contains large amounts of solids and, thus, is more viscous and generally of higher density than the liquid from which it is formed.

The term "pH acidic environment" in the meaning of the present invention refers to a high solids aqueous mineral and/or filler and/or pigment suspensions having a pH of < 6 at +23 °C.

The term "calcium carbonate-containing material" in the meaning of the present invention refers to a material that comprises "calcium carbonate-containing particles", at least one "comb polymer" and optionally at least one salt of at least one strong acid. Accordingly, the "calcium carbonate-containing material" corresponds to the total dry weight of solid material in the high solids aqueous mineral and/or filler and/or pigment suspension.

The term "calcium carbonate-containing particles" refers to a material that comprises at least 50 wt.-% calcium carbonate, based on the total dry weight of the calcium carbonate-containing particles.

[0024] In the meaning of the present invention, the term "comb polymer" refers to a comb-shaped polymer which is formed from a main chain, also referred to as back bone, to which carbonic acid groups and/or other acid groups are attached in the form of free acids or salts thereof, i.e. in a form of a carboxylate ion, as well as side chains comprising polyalkylene oxide, optionally end-capped with a hydrocarbon chain. The polyalkylene oxide side chains can be bonded to the main chain via ester bonds, amide bonds, or ether bonds. In addition to the carbonic acid groups and the polyalkylene oxide side chains, further functional or non-functional groups can be bonded to the main chain, e.g. positively charged functional groups such as amine, amide and/or quaternary ammonium groups.

[0025] The term "acid" in the present invention is defined according to the Brønsted-Lowry definition. In other words, an acid is defined as a substance that can act as proton donor. This means, that for example, the term " HSO_4^- " also exemplifies an acid.

[0026] For the purposes of the present invention, the term "viscosity" refers to Brookfield viscosity. According to the present invention the Brookfield viscosity is measured using a RVT model Brookfield™ viscometer at a temperature of +23 °C and -5 °C, and a rotation speed of 100 rpm (revolutions per minute) with the appropriate disc spindle No 1 to 5. The reported viscosity values are the values detected by the instrument after 1 minute of measurement. Before measuring

the Brookfield viscosity the suspension was stirred for 5 minutes using a Pendraulik laboratory dissolver, 0.25 - 2.5 kW, mechanically adjustable up to 8400 rpm with an appropriate tooth disc stirrer.

[0027] "Conductivity" according to the present invention shall mean the electrical conductivity of an aqueous carbonate-comprising material suspension as measured according to the measurement method defined in the examples section here below. The conductivity is specified in mS/cm and may be measured at -5 °C and at +23 °C.

[0028] According to another aspect of the present invention, a method for producing a high solids aqueous mineral and/or filler and/or pigment suspension is provided, comprising the steps of

- a) providing an aqueous suspension comprising at least one calcium carbonate-containing material, wherein the calcium carbonate-containing material has a charge density of between +2 and -2 C/g at pH 9,
- b) providing

- i) at least one strong acid selected from the group consisting of acids having a pK_a value of less than or equal to zero at +23 °C, and/or

- ii) at least one salt of at least one strong acid, wherein the at least one strong acid forming the at least one salt of at least one strong acid is selected from the group consisting of acids having a pK_a value of less than or equal to zero at +23 °C,

- c) adding the at least one strong acid and/or the at least one salt of at least one strong acid of step b) to the aqueous suspension comprising at least one calcium carbonate-containing material of step a),

- d) optionally grinding the aqueous suspension comprising at least one calcium carbonate-containing material of step a) before and/or during and/or after step c),

wherein the high solids aqueous suspension after step c) and/or d) has

- i) a solids content of at least 50 wt.-%, based on the total weight of the high solids aqueous suspension,

- ii) a Brookfield viscosity at 100 rpm of $\leq 1\,000$ mPas at a temperature of -5 °C

- iii) a pH of < 6 at +23 °C, and

- iv) a conductivity of between 10 and 100 mS/cm at -5 °C and at +23 °C, and wherein the high solids aqueous suspension comprises the at least one salt of at least one strong acid in an amount from 1 to 20 wt.-%, based on the total weight of the high solids aqueous suspension.

[0029] It is preferred that the method further comprises step e) of providing at least one medium strong acid selected from the group consisting of acids having a pK_a value of between 0 and 2.5 at +23 °C, preferably the at least one medium strong acid is selected from H_2SO_3 , HSO_4^- , H_3PO_4 , oxalic acid and mixtures thereof, and/or at least one weak acid selected from the group consisting of acids having a pK_a value of between >2.5 to 6 at +23 °C, preferably the at least one weak acid is selected from citric acid and/or tartaric acid. It is also preferred that the method further comprises step f) of contacting the aqueous suspension comprising at least one calcium carbonate-containing material of step a) with the at least one medium strong acid and/or at least one weak acid of step e) during and/or after step c), and/or during and/or after optional step d). It is further preferred that step c) and/or step d) and/or step f) is carried out at a temperature of between -5 °C and +99 °C, preferably between +20 °C and +85 °C and most preferably between +20 °C and +50 °C and most preferably between +50 °C and +85 °C. It is also preferred that the method further comprises step g) of concentrating the obtained high solids aqueous mineral and/or filler and/or pigment suspension. It is also preferred that the method further comprises drying the obtained high solids aqueous mineral and/or filler and/or pigment suspension.

[0030] According to a further aspect of the present invention, a calcium carbonate-containing material obtainable by drying the high solids aqueous mineral and/or filler and/or pigment suspension is provided. According to still another aspect of the present invention, the use of the high solids aqueous mineral and/or filler and/or pigment suspension and/or the calcium carbonate-containing material in paper making, paper coating, plastic, agricultural and/or paint applications is provided. According to a still further aspect of the present invention, the use of the high solids aqueous mineral and/or filler and/or pigment suspension and/or the calcium carbonate-containing material as filler in paper is provided. It is preferred that the high solids aqueous mineral and/or filler and/or pigment suspension and/or the calcium carbonate-containing material is used as a support for digital printing, preferred ink jet printing, or for flexo, rotogravure and/or offset printing, most preferably for black ink printing in inkjet printing.

[0031] According to a further aspect of the present invention, a coating color formulation comprising the high solids aqueous mineral and/or filler and/or pigment suspension and/or the calcium carbonate-containing material and a natural and/or synthetic binder is provided, the binder preferably consisting of styrene-butadiene, styrene-acrylate, polyvinyl acetate, polyvinyl alcohol, starch or mixtures thereof, and most preferably the binder contains or consists of polyvinyl alcohol.

[0032] Advantageous embodiments of the present invention are defined in the corresponding sub-claims.

[0033] According to one embodiment of the present invention, the calcium carbonate-containing particles of the at least one calcium carbonate-containing material are selected from among natural calcium carbonate, precipitated calcium carbonate or mixtures thereof.

[0034] According to another embodiment of the present invention, the calcium carbonate-containing particles of the at least one calcium carbonate-containing material have a weight median particle size d_{50} from 0.1 to 50 μm , preferably from 0.25 to 50 μm , more preferably from 0.3 to 5 μm , and most preferably from 0.4 to 3 μm .

[0035] According to yet another embodiment of the present invention, the calcium carbonate-containing particles of the at least one calcium carbonate-containing material have a specific surface area of from 0.1 m^2/g to 200 m^2/g , preferably from 0.1 m^2/g to 50 m^2/g and more preferably from 0.1 m^2/g to 20 m^2/g , measured using nitrogen and the BET method.

[0036] According to one embodiment of the present invention, the high solids aqueous suspension comprises the at least one calcium carbonate-containing material in an amount of at least 50 wt.-%, preferably from 50 to 82 wt.-%, more preferably from 55 to 82 wt.-%, even more preferably from 60 to 78 wt.-% and most preferably from 65 to 78 wt.-%, based on the total weight of the high solids aqueous suspension.

[0037] According to another embodiment of the present invention, the at least one calcium carbonate-containing material comprises at least one comb polymer, preferably the surface of the calcium carbonate-containing particles of the at least one calcium carbonate-containing material are coated with the at least one comb polymer.

[0038] According to yet another embodiment of the present invention, the at least one calcium carbonate-containing material comprises at least one comb polymer having an intrinsic viscosity in the range of 5 to 99 ml/g, preferably in the range of 10 to 80 ml/g and most preferably in the range of 10 to 50 ml/g.

[0039] According to one embodiment of the present invention, the at least one salt of at least one strong acid comprises a divalent and/or trivalent cation, preferably the divalent cation is selected from the group consisting of calcium, magnesium, strontium and mixtures thereof and/or the trivalent cation preferably is aluminum.

[0040] According to another embodiment of the present invention, the at least one strong acid forming the at least one salt of at least one strong acid is selected from the group consisting of hydrochloric acid, nitric acid and mixtures thereof.

[0041] According to yet another embodiment of the present invention, the high solids aqueous suspension comprises at least one comb polymer in an amount from 0.01 to 5 wt.-%, based on the total dry weight of the calcium carbonate-containing material in the suspension, preferably from 0.05 to 4 wt.-%, more preferably from 0.1 to 3 wt.-%, even more preferably from 0.2 to 2 wt.-%, and most preferably from 0.25 to 1.5 wt.-% or from 0.5 to 1.25 wt.-%.

[0042] According to one embodiment of the present invention, the high solids aqueous suspension has solids content from 50 to 82 wt.-%, preferably from 55 to 82 wt.-%, more preferably from 60 to 78 wt.-% and most preferably from 65 to 78 wt.-%, based on the total weight of the high solids aqueous suspension.

[0043] According to another embodiment of the present invention, the high solids aqueous suspension has a Brookfield viscosity at 100 rpm from 25 to 1 000 mPas at a temperature of -5 °C, preferably from 25 to 700 mPas at -5 °C, more preferably from 25 to 500 mPas at -5 °C and most preferably from 50 to 300 mPas at -5 °C.

[0044] According to yet another embodiment of the present invention, the high solids aqueous suspension has a pH of between 4 and < 6 at +23 °C, preferably a pH of between 4.5 and < 6 at +23 °C and preferably a pH of between 5 and < 6 at +23 °C.

[0045] According to one embodiment of the present invention, the high solids aqueous suspension has a conductivity of between 20 mS/cm and 100 mS/cm measured at -5 °C and +23 °C and preferably between 30 mS/cm and 100 mS/cm measured at -5 °C and +23 °C.

[0046] According to another embodiment of the present invention, the high solids aqueous suspension further comprises at least one reaction product or products of the at least one calcium carbonate-containing material with at least one medium strong acid and/or at least one reaction product or products of the at least one calcium carbonate-containing material with at least one weak acid. It is preferred that the at least one medium strong acid forming the at least one reaction product or products of the at least one calcium carbonate-containing material is selected from the group consisting of acids having a pK_a value of between 0 and 2.5 at +23 °C, preferably the at least one medium strong acid is selected from H_2SO_3 , HSO_4^- , H_3PO_4 , oxalic acid and mixtures thereof. It is noted that HSO_4^- can be added in the form of the alkali or earth alkali salt, and preferably in the form of the Na, Li, K, Mg, and Ca salt. It is further preferred that the at least one weak acid forming the at least one reaction product or products of the at least one calcium carbonate-containing material is selected from the group consisting of acids having a pK_a value of between >2.5 and 6 at +23 °C, preferably the at least one weak acid is selected from citric acid, tartaric acid and mixtures thereof.

[0047] According to yet another embodiment of the present invention, the molar quantity of the sum, expressed by the generated H_3O^+ ions, of the at least one medium strong acid forming the at least one reaction product or products of the at least one calcium carbonate-containing material and/or the at least one weak acid forming the at least one reaction product or products of the at least one calcium carbonate-containing material and the at least one strong acid forming the at least one salt of at least one strong acid relative to the quantity of moles of CaCO_3 is in total between

0.01 and 1.9.

[0048] According to one embodiment of the present invention, the high solids aqueous suspension further comprises aluminum hydroxide and/or magnesium hydroxide.

[0049] According to another embodiment of the present invention, the high solids aqueous suspension has a positive charge density at pH 5, preferably of at least +0.1 C/g at pH 5, more preferably of at least +0.5 C/g at pH 5, even more preferably of at least +1 C/g at pH 5 and most preferably of at least +1.5 C/g at pH 5.

[0050] In the following, it is referred to further details of the present invention and especially the foregoing components of the high solids aqueous mineral and/or filler and/or pigment suspension.

[0051] Where the term "comprising" is used in the present description and claims, it does not exclude other non-specified elements of major or minor functional importance. For the purposes of the present invention, the term "consisting of" is considered to be a preferred embodiment of the term "comprising of". If hereinafter a group is defined to comprise at least a certain number of embodiments, this is also to be understood to disclose a group, which preferably consists only of these embodiments.

[0052] Whenever the terms "including" or "having" are used, these terms are meant to be equivalent to "comprising" as defined above.

[0053] Where an indefinite or definite article is used when referring to a singular noun, e.g. "a", "an" or "the", this includes a plural of that noun unless something else is specifically stated.

[0054] One specific requirement of the present invention is that the high solids aqueous mineral and/or filler and/or pigment suspension in acidic pH environment comprises at least one calcium carbonate-containing material. In particular, the at least one calcium carbonate-containing material comprises calcium carbonate-containing particles.

[0055] According to one embodiment of the present invention, the calcium carbonate-containing particles being part of the at least one calcium carbonate-containing material are selected from among natural calcium carbonate, precipitated calcium carbonate or mixtures thereof.

[0056] "Ground calcium carbonate" (GCC) in the meaning of the present invention is a calcium carbonate obtained from natural sources, such as limestone, marble, calcite, dolomite or chalk, and processed through a wet and/or dry treatment such as grinding, screening and/or fractionating, for example by a cyclone or classifier.

[0057] A ground calcium carbonate (GCC) may feature, e.g. one or more of marble, limestone, chalk, and/or dolomite. According to one embodiment of the present invention the GCC is obtained by dry grinding. According to another embodiment of the present invention the GCC is obtained by wet grinding and subsequent drying.

[0058] In general, the grinding step can be carried out with any conventional grinding device, for example, under conditions such that refinement predominantly results from impacts with a secondary body, i.e. in one or more of: a ball mill, a rod mill, a vibrating mill, a roll crusher, a centrifugal impact mill, a vertical bead mill, an attrition mill, a pin mill, a hammer mill, a pulveriser, a shredder, a de-clumper, a knife cutter, or other such equipment known to the skilled man. In case the calcium carbonate-containing particles comprise wet ground calcium carbonate-containing particles, the grinding step may be performed under conditions such that autogenous grinding takes place and/or by horizontal ball milling, and/or other such processes known to the skilled man. The wet processed ground calcium carbonate-containing particles thus obtained may be washed and dewatered by well known processes, e.g. by flocculation, filtration or forced evaporation prior to drying. The subsequent step of drying may be carried out in a single step such as spray drying, or in at least two steps. It is also common that such calcium carbonate-containing particles undergo a beneficiation step (such as a flotation, bleaching or magnetic separation step) to remove impurities.

[0059] "Precipitated calcium carbonate" (PCC) in the meaning of the present invention is a synthesized material, generally obtained by precipitation following reaction of carbon dioxide and lime in an aqueous environment or by precipitation of a calcium and carbonate ion source in water.

[0060] A precipitated calcium carbonate (PCC) may feature, e.g. one or more of aragonitic, vateritic and/or calcitic mineralogical morphological forms. The aragonitic morphology is commonly in the acicular form, whereas vateritic morphology belongs to the hexagonal crystal system. The calcitic morphology can form scalenohedral, prismatic, spherulitic and rhombohedral forms. PCC can be produced in different ways, e.g. by precipitation with carbon dioxide, the lime soda process, or the Solvay process in which PCC is a by-product of ammonia production. The obtained PCC slurry can be mechanically dewatered and dried.

[0061] It is preferred that the calcium carbonate-containing particles comprise ground calcium carbonate (GCC). For example, the calcium carbonate-containing particles comprise one ground calcium carbonate (GCC). Alternatively, the calcium carbonate-containing particles comprise a mixture of two or more ground calcium carbonates (GCC) selected from different sources of ground calcium carbonate. For example, the calcium carbonate-containing particles comprise one ground calcium carbonate (GCC) selected from dolomite and one ground calcium carbonate (GCC) selected from marble.

[0062] In one preferred embodiment of the present invention, the calcium carbonate-containing particles comprise a mixture of ground calcium carbonate and a precipitated calcium carbonate.

[0063] In addition to calcium carbonate, the calcium carbonate-containing particles may comprise further metal oxides

such as titanium dioxide and/or aluminium trioxide, metal hydroxides such as aluminium tri-hydroxide and/or magnesium hydroxide, metal salts such as sulfates, silicates such as talc and/or kaolin clay and/or mica, carbonates such as magnesium carbonate and/or gypsum, satin white and mixtures thereof.

[0064] According to one embodiment of the present invention, the amount of calcium carbonate in the calcium carbonate-containing particles being part of the at least one calcium carbonate-containing material is at least 50 wt.-%, e.g. at least 60 wt.-%, preferably between 50 and 100 wt.-%, more preferably between 60 and 99 wt.-% and most preferably between 70 and 98 wt.-%, based on the total dry weight of the calcium carbonate-containing particles.

[0065] According to one embodiment of the present invention, the amount of calcium carbonate-containing particles in the at least one calcium carbonate-containing material is at least 50 wt.-%, preferably at least 75 wt.-%, more preferably at least 80 wt.-%, and most preferably at least 88 wt.-% or at least 99.9 wt.-%, based on the total dry weight of the calcium carbonate-containing material. For example, the amount of calcium carbonate-containing particles in the at least one calcium carbonate-containing material is between 85 wt.-% and 99.9 wt.-%, based on the total dry weight of the calcium carbonate-containing material.

[0066] Additionally or alternatively, the high solids aqueous mineral and/or filler and/or pigment suspension comprises the at least one calcium carbonate-containing material in an amount of at least 50 wt.-%, preferably from 50 to 82 wt.-%, more preferably from 55 to 82 wt.-%, even more preferably from 60 to 78 wt.-% and most preferably from 65 to 78 wt.-%, based on the total weight of the high solids aqueous suspension.

[0067] According to one embodiment of the present invention, the calcium carbonate-containing particles of the at least one calcium carbonate-containing material have a weight median particle size d_{50} from 0.1 to 50 μm , preferably from 0.25 to 50 μm , more preferably from 0.3 to 5 μm , and most preferably from 0.4 to 3 μm , as measured by Sedigraph 5120.

[0068] For example, the calcium carbonate-containing particles of the at least one calcium carbonate-containing material have a weight median particle size d_{50} from 0.4 to 0.3 μm or from 0.4 to 2.0 μm , as measured by Sedigraph 5120.

[0069] Throughout the present document, the "particle size" of the calcium carbonate-containing particles is described by its distribution of particle sizes. The value d_x represents the diameter relative to which x % by weight of the particles have diameters less than d_x . This means that the d_{20} value is the particle size at which 20 wt.-% of all particles are smaller, and the d_{75} value is the particle size at which 75 wt.-% of all particles are smaller. The d_{50} value is thus the weight median particle size, i.e. 50 wt.-% of all grains are bigger or smaller than this particle size. For the purpose of the present invention the particle size is specified as weight median particle size d_{50} unless indicated otherwise. For determining the weight median particle size d_{50} value for particles having a d_{50} value between 0.4 and 2 μm , a Sedigraph 5120 device from the company Micromeritics, USA, can be used. For measuring the size distribution and weight median diameter d_{50} by the Sedigraph, the samples were pre-diluted to the right concentration by using deionized water but no further additives, such as usually added dispersants like polyphosphate or polyacrylate.

[0070] Additionally or alternatively, the fraction of the calcium carbonate-containing particles of the at least one calcium carbonate-containing material having a particle size of less than 2 μm is greater than 60 wt.-%, preferably greater than 70 wt.-%, more preferably greater than 80 wt.-%, still more preferably greater than 85 wt.-% and most preferably about 90 wt.-%, based on the total weight of the at least one calcium carbonate-containing particles, as measured with a Sedigraph 5120.

[0071] For example, the fraction of the calcium carbonate-containing particles having a particle size of less than 0.2 μm is greater than 5 wt.-%, preferably greater than 7.5 wt.-%, more preferably greater than 10 wt.-%, still more preferably greater than 12.5 wt.-% and most preferably about 16 wt.-%, based on the total weight of the at least one calcium carbonate-containing particles, as measured with a Sedigraph 5120.

[0072] According to one embodiment of the present invention, the calcium carbonate-containing particles of the at least one calcium carbonate-containing material have a specific surface area of from 0.1 m^2/g to 200 m^2/g , preferably from 0.1 m^2/g to 50 m^2/g and more preferably from 0.1 m^2/g to 20 m^2/g , measured using nitrogen and the BET method.

[0073] For example, the calcium carbonate-containing particles are marble having a specific surface area of from 0.1 m^2/g to 200 m^2/g , preferably from 0.1 m^2/g to 50 m^2/g and more preferably from 0.1 m^2/g to 20 m^2/g , measured using nitrogen and the BET method and a weight median particle size d_{50} from 0.1 to 50 μm , from 0.25 to 50 μm , or from 0.3 to 5 μm , preferably from 0.4 to 3 μm , as measured by Sedigraph 5120.

[0074] A further requirement of the present invention is that the calcium carbonate-containing material used for preparing the high solids aqueous mineral and/or filler and/or pigment suspension has a charge density of between +2 and -2 C/g at pH 9. In one embodiment of the present invention, the at least one calcium carbonate-containing material used for preparing the high solids aqueous mineral and/or filler and/or pigment suspension has a charge density of between -0.01 and -2 C/g at pH 9, preferably of between -0.1 and -1 C/g at pH 9, more preferably of between -0.2 and -0.8 C/g at pH 9 and most preferably of between -0.3 and -0.7 C/g at pH 9.

[0075] It is preferred that the at least one calcium carbonate-containing material comprises at least one comb polymer, i.e. the at least one calcium carbonate-containing material comprises at least one kind of comb polymer.

[0076] The at least one comb polymer is preferably a comb-shaped polymer which is formed from a main chain, also

referred to as back bone, and at least one side chain attached thereto.

[0077] Without being bound to any theory, it is believed that the at least one comb polymer is adsorbed to the weakly positively charged particles of the calcium carbonate-containing particles due to its negatively charged main chain, also called polymer back bone. Furthermore, the side chains of the adsorbed at least one comb polymer cause a steric and/or osmotic repulsion between the particles, which may lead to a steric and/or osmotic stabilization of at least a part of the particles in the high solids aqueous suspension.

[0078] Accordingly, the surface of the calcium carbonate-containing particles being part of the at least one calcium carbonate-containing material is preferably at least partially coated with the at least one comb polymer.

[0079] The expression "at least one" or "at least one kind of" comb polymer means that one or more kinds of comb polymers may be part of the at least one calcium carbonate-containing material in the high solids aqueous mineral and/or filler and/or pigment suspension.

[0080] According to one preferred embodiment of the present invention, the at least one calcium carbonate-containing material being part of the high solids aqueous mineral and/or filler and/or pigment suspension comprises only one kind of comb polymer. According to another embodiment of the present invention, the at least one calcium carbonate-containing material being part of the high solids aqueous mineral and/or filler and/or pigment suspension comprises a mixture of at least two kinds of comb polymers.

[0081] Accordingly, it is also appreciated that the high solids aqueous mineral and/or filler and/or pigment suspension comprises only one kind of comb polymer. According to another embodiment of the present invention, the high solids aqueous mineral and/or filler and/or pigment suspension comprises a mixture of at least two kinds of comb polymers.

[0082] It is preferred that the at least one comb polymer of the present invention is at least one anionically charged comb polymer, i.e. the at least one comb polymer of the present invention is at least one kind of anionically charged comb polymer.

[0083] The term "anionically charged" as used in the present invention is to be understood to mean that the comb polymer has a total or net charge that is negative, i.e. the sum of all positive and negative charges is negative. In other words, the polymer must possess an excess of anionically charged functional groups or residues. This means that the at least one anionically charged comb polymer being part of the at least one calcium carbonate-containing material of the present invention may comprise both positively and negatively charged functional groups or residues, i.e. cationic and anionic functional groups or residues, as long as the total or net charge is negative, i.e. the comb polymer is anionic. For example, the at least one anionically charged comb polymer being part of the at least one calcium carbonate-containing material may comprise only anionically charged functional groups or residues or may comprise anionically and cationically charged functional groups or residues such that the total or net charge of the at least one comb polymer is negative.

[0084] In one embodiment of the present invention, the at least one comb polymer is at least one anionically charged comb polymer having a specific charge of -10 to -250 C/g at pH 9, preferably from -10 C/g to -200 C/g at pH 9 and most preferably from -10 C/g to -150 C/g at pH 9.

[0085] For example, the at least one comb polymer is at least one anionically charged comb polymer having a specific charge from -20 C/g to -100 C/g at pH 9, preferably from -30 C/g to -100 C/g at pH 9 and most preferably from -30 C/g to -70 C/g at pH 9.

[0086] According to one embodiment of the present invention, the at least one calcium carbonate-containing material comprises at least one comb polymer having an intrinsic viscosity in the range of 5 to 99 ml/g, preferably in the range of 10 to 80 ml/g and most preferably in the range of 10 to 50 ml/g.

[0087] Additionally or alternatively, it is preferred that the at least one comb polymer has a specific charge of -10 to -250 C/g at pH 9 and an intrinsic viscosity in the range of 5 to 99 ml/g. It is further preferred that the at least one comb polymer has a specific charge from -10 C/g to -200 C/g at pH 9 and an intrinsic viscosity in the range of 10 to 80 ml/g. It is even further preferred that the at least one anionically charged comb polymer has a specific charge from -10 C/g to -150 C/g at pH 9 and an intrinsic viscosity in the range of 10 to 50 ml/g.

[0088] For example, it is preferred that the at least one comb polymer has a specific charge from -20 C/g to -100 C/g at pH 9 and an intrinsic viscosity in the range of 10 to 50 ml/g or a specific charge from -30 C/g to -100 C/g at pH 9 and an intrinsic viscosity in the range of 10 to 50 ml/g. In one embodiment of the present invention, the at least one comb polymer has a specific charge from -30 C/g to -70 C/g at pH 9 and an intrinsic viscosity in the range of 10 to 50 ml/g.

[0089] Comb polymers that may be suitable in the present invention are described in e.g. US 2009/0199741 A1, US 6,387,176 B1, EP 1136508 A1, EP 1138697 A1, EP 1189955 A1, US 6,946,510 B1, US 7,514,488 B1 and EP 0736553 A1. These documents disclose processes to produce comb polymer as well as their use in mineral based binders such as cement. Suitable comb polymer are also described in the product brochure "SIKA ViscoCrete®, selbstver dickender Beton SCC" available on the website www.sika.ch.

[0090] Examples of comb polymers that may be used for the at least one calcium carbonate-containing material being part of the high solids aqueous suspension of the present invention are polymers of the MELFLUX® or MelPers® series, e.g. MelPers® 2450 by BASF (Trostberg, Germany), ETHACRYL® M dispersant by CoAtex, LLC (Chester, SC) or

MIGHTY EG® dispersant by Kao Specialties Americas, LLC, (High Point, NC).

[0091] In general, the average molecular weight M_w of the at least one comb polymer may vary in broad range and is typically in a range between 10 000 and 100 000 g/mol, preferably between 20 000 and 75 000 g/mol and most preferably between 25 000 and 50 000 g/mol.

[0092] In one preferred embodiment of the present invention, the high solids aqueous mineral and/or filler and/or pigment suspension comprises the at least one comb polymer in amount from 0.01 to 5 wt.-%, based on the total dry weight of the calcium carbonate-containing material in the suspension, preferably from 0.05 to 4 wt.-%, more preferably from 0.1 to 3 wt.-%, even more preferably from 0.2 to 2 wt.-%, and most preferably from 0.25 to 1.5 wt.-% or from 0.5 to 1.25 wt.-%. For example, the high solids aqueous mineral and/or filler and/or pigment suspension comprises the at least one comb polymer in an amount from 0.6 to 1.1 wt.-% or from 0.7 to 1 wt.-%, based on the total dry weight of the calcium carbonate-containing material in the suspension.

[0093] Additionally or alternatively, the at least one calcium carbonate-containing material comprises the at least one comb polymer in amount from 0.01 to 5 wt.-%, based on the total dry weight of the calcium carbonate-containing material in the suspension, preferably from 0.05 to 4 wt.-%, more preferably from 0.1 to 3 wt.-%, even more preferably from 0.2 to 2 wt.-%, and most preferably from 0.25 to 1.5 wt.-% or from 0.5 to 1.25 wt.-%. For example, the at least one calcium carbonate-containing material comprises the at least one comb polymer in an amount from 0.6 to 1.1 wt.-% or from 0.7 to 1 wt.-%, based on the total dry weight of the calcium carbonate-containing material in the suspension.

[0094] One further requirement of the inventive high solids aqueous mineral and/or filler and/or pigment suspension is that the suspension comprises at least one salt of at least one strong acid.

[0095] In particular, it is noted that the at least one strong acid forming the at least one salt of at least one strong acid is selected from the group consisting of acids having a pK_a value at 23 °C of less than or equal to 0.

[0096] The expression "at least one" salt of at least one strong acid means that one or more salts of at least one strong acid may be present in the high solids aqueous mineral and/or filler and/or pigment suspension.

[0097] According to one preferred embodiment of the present invention, only one salt of at least one strong acid is present in the high solids aqueous mineral and/or filler and/or pigment suspension comprising the at least one calcium carbonate-containing material. According to another embodiment of the present invention, a mixture of at least two salts of at least one strong acid is present in the high solids aqueous mineral and/or filler and/or pigment suspension comprising the at least one calcium carbonate-containing material.

[0098] Furthermore, the expression at least one salt of "at least one" strong acid means that salts of one or more strong acids may be present in the high solids aqueous mineral and/or filler and/or pigment suspension.

[0099] According to one preferred embodiment of the present invention, at least one salt of only one strong acid is present in the high solids aqueous mineral and/or filler and/or pigment suspension comprising the at least one calcium carbonate-containing material. According to another embodiment of the present invention, at least one salt of a mixture of at least two strong acids is present in the high solids aqueous mineral and/or filler and/or pigment suspension comprising the calcium carbonate-containing material.

[0100] With regard to the cationic part of the at least one salt of at least one strong acid, it should be noted that any divalent and/or trivalent cation is suitable as cationic part of the at least one salt of at least one strong acid. In particular, any divalent and/or trivalent cation is suitable as cationic part of the at least one salt of at least one strong acid which provides a water soluble salt of the at least one strong acid forming the at least one salt of at least one strong acid.

[0101] The term "divalent cation" in the meaning of the present invention refers to a cation having a valency of two, e.g. a metal cation having two valencies.

[0102] The term "trivalent cation" in the meaning of the present invention refers to a cation having a valency of three, e.g. a metal cation having three valencies.

[0103] For example, the at least one salt of at least one strong acid comprises a divalent cation selected from the group consisting of calcium, magnesium, strontium and mixtures thereof. Additionally or alternatively, the at least one salt of at least one strong acid comprises aluminum as trivalent cation.

[0104] Preferably, the cationic part of the at least one salt of at least one strong acid is derived from the at least one calcium carbonate-containing material. It is thus appreciated that the at least one salt of at least one strong acid comprises at least calcium as cationic part of the at least one salt of at least one strong acid.

[0105] In one preferred embodiment of the present invention, the at least one salt of at least one strong acid comprises only calcium as cationic part of the at least one salt of at least one strong acid. In another preferred embodiment of the present invention, the at least one salt of at least one strong acid comprises calcium and magnesium and/or aluminum as cationic part of the at least one salt of at least one strong acid.

[0106] Furthermore, there are no specific restrictions regarding the at least one strong acid forming the at least one salt of at least one strong acid as long as said at least one strong acid is selected from the group consisting of acids having a pK_a value of less than or equal to zero at +23 °C.

[0107] Preferably, any strong acid forming the at least one salt of at least one strong acid is suitable which provides a water soluble salt of the at least one strong acid forming the at least one salt of at least one strong acid with the at

least one calcium carbonate-containing material, that is to say at least the majority, preferably at least 75 wt.-%, more preferably at least 90 wt.-% and most preferably at least 96 wt.-% of the total amount of the at least one salt of at least one strong acid is dissolved within the water phase of the high solids aqueous mineral and/or filler and/or pigment suspension.

[0108] The term "dissolved" or "water soluble" in the meaning of the present invention refers to systems in which no discrete solid particles of the at least one salt of at least one strong acid are observed in the solvent.

[0109] According to one preferred embodiment of the present invention, the at least one strong acid forming the at least one salt of at least one strong acid is selected from the group consisting of hydrochloric acid, nitric acid and mixtures thereof.

[0110] For example, the at least one strong acid forming the at least one salt of at least one strong acid is hydrochloric acid.

[0111] The amount of the at least one salt of at least one strong acid in the high solids aqueous mineral and/or filler and/or pigment suspension may vary in a broad range. However, the high solids aqueous mineral and/or filler and/or pigment suspension comprises the at least one salt of at least one strong acid in an amount from 1 to 20 wt.-%, preferably from 2 to 15 wt.-%, more preferably from 3 to 12.5 wt.-% and most preferably from 4 to 10 wt.-%, based on the total weight of the high solids aqueous suspension.

[0112] Optionally, the high solids aqueous mineral and/or filler and/or pigment suspension further comprises further additives.

[0113] For example, the high solids aqueous mineral and/or filler and/or pigment suspension further comprises at least one reaction product or products of the at least one calcium carbonate-containing material with at least one medium strong acid.

[0114] The expression "at least one" reaction product or products means that one or more reaction product or products may be present in the high solids aqueous mineral and/or filler and/or pigment suspension.

[0115] According to one embodiment of the present invention, only one reaction product of the at least one calcium carbonate-containing material with at least one medium strong acid is present in the high solids aqueous mineral and/or filler and/or pigment suspension. According to another embodiment of the present invention, a mixture of at least two reaction products of the at least one calcium carbonate-containing material with at least one medium strong acid is present in the high solids aqueous mineral and/or filler and/or pigment suspension.

[0116] In particular, it is preferred that the at least one medium strong acid forming the at least one reaction product or products with the at least one calcium carbonate-containing material is chosen from amongst acids having a pK_a value of between 0 and 2.5 at +23 °C.

[0117] In one embodiment of the present invention, the at least one medium strong acid forming the at least one reaction product or products with the at least one calcium carbonate containing material is chosen from amongst medium strong acids forming divalent and/or trivalent cation salts. It is preferred that the at least one medium strong acid forming the at least one reaction product or products with the at least one calcium carbonate containing material is chosen from amongst medium strong acids forming divalent and/or trivalent cation salts, which are almost insoluble in water, that is to say with a solubility of less than 0.01% by weight acids having a pK_a value of between 0 and 2.5 at +23 °C.

[0118] For example, the at least one medium strong acid forming the at least one reaction product or products with the at least one calcium carbonate containing material is chosen from amongst medium strong acids forming divalent and/or trivalent cation salts, such as calcium and/or magnesium and/or aluminium salts.

[0119] In one embodiment of the present invention, the at least one medium strong acid forming the at least one reaction product or products with the at least one calcium carbonate containing material is selected from H_2SO_3 , HSO_4^- , H_3PO_4 , oxalic acid and mixtures thereof. For example, the at least one medium strong acid forming at least one reaction product or products with the at least one calcium carbonate containing material is selected from HSO_4^- and/or H_3PO_4 .

[0120] For example, the high solids aqueous mineral and/or filler and/or pigment suspension further comprises at least one reaction product or products of the at least one calcium carbonate-containing material with at least one weak acid.

[0121] The expression "at least one" reaction product or products means that one or more reaction product or products may be present in the high solids aqueous mineral and/or filler and/or pigment suspension.

[0122] According to one embodiment of the present invention, only one reaction product of the at least one calcium carbonate-containing material with at least one weak acid is present in the high solids aqueous mineral and/or filler and/or pigment suspension. According to another embodiment of the present invention, a mixture of at least two reaction products of the at least one calcium carbonate-containing material with at least one weak acid is present in the high solids aqueous mineral and/or filler and/or pigment suspension.

[0123] In particular, it is preferred that the at least one weak acid forming the at least one reaction product or products with the at least one calcium carbonate-containing material is chosen from amongst acids having a pK_a value of between >2.5 and 6 at +23 °C.

[0124] In one embodiment of the present invention, the at least one weak acid forming the at least one reaction product or products with the at least one calcium carbonate containing material is chosen from amongst weak acids forming

monovalent and/or divalent and/or trivalent cation salts. It is preferred that the at least one weak acid forming the at least one reaction product or products with the at least one calcium carbonate containing material is chosen from weak acids forming divalent and/or trivalent cation salts, which are soluble in water, that is to say with a solubility of above 0.01 % by weight acids having a pK_a value of between 0 and 2.5 at +23 °C.

[0125] For example, the at least one weak acid forming the at least one reaction product or products with the at least one calcium carbonate containing material is chosen from amongst weak acids forming divalent and/or trivalent cation salts, such as calcium and/or magnesium and/or aluminium salts.

[0126] In one embodiment of the present invention, the at least one weak acid forming the at least one reaction product or products with the at least one calcium carbonate containing material is selected from citric acid, tartaric acid and mixtures thereof. For example, the at least one weak acid forming the at least one reaction product or products with the at least one calcium carbonate containing material is selected from citric acid or tartaric acid.

[0127] According to one embodiment of the present invention, the molar quantity of the sum, expressed by the generated H_3O^+ ions, of the at least one medium strong acid forming the at least one reaction product or products of the at least one calcium carbonate-containing material and/or the at least one weak acid forming the at least one reaction product or products of the at least one calcium carbonate-containing material and the at least one strong acid forming the at least one salt of at least one strong acid relative to the quantity of moles of $CaCO_3$ is in total between 0.01 and 1.9.

[0128] For example, the molar quantity of the sum, expressed by the generated H_3O^+ ions, of the at least one medium strong acid forming the at least one reaction product or products of the at least one calcium carbonate-containing material and/or the at least one weak acid forming the at least one reaction product or products of the at least one calcium carbonate-containing material and the at least one strong acid forming the at least one salt of at least one strong acid relative to the quantity of moles of $CaCO_3$ is in total between 0.05 and 1 and most preferably between 0.5 and 1.

[0129] With regard to the amount of the at least one reaction product or products of the at least one calcium carbonate-containing material with at least one medium strong acid and/or with at least one weak acid in the high solids aqueous mineral and/or filler and/or pigment suspension it should be noted that the amount may vary in a broad range. However, the high solids aqueous mineral and/or filler and/or pigment suspension comprises the at least one reaction product or products of the at least one calcium carbonate-containing material with at least one medium strong acid and/or with at least one weak acid in an amount from 1 to 20 wt.-%, preferably from 2 to 15 wt.-%, more preferably from 3 to 12.5 wt.-% and most preferably from 4 to 10 wt.-%, based on the total weight of the high solids aqueous suspension.

[0130] Additionally or alternatively, the high solids aqueous mineral and/or filler and/or pigment suspension may further comprise aluminum hydroxide and/or magnesium hydroxide.

[0131] In one embodiment of the present invention, the high solids aqueous mineral and/or filler and/or pigment suspension comprises aluminum hydroxide and/or magnesium hydroxide in an amount from 0.1 to 20 wt.-%, preferably from 0.1 to 15 wt.-%, more preferably from 1 to 12.5 wt.-% and most preferably from 1 to 10 wt.-%, based on the total weight of the high solids aqueous suspension.

[0132] The high solids aqueous mineral and/or filler and/or pigment suspension in acidic pH environment according to the present invention comprises at least one calcium carbonate-containing material as defined above and at least one salt of at least one strong acid as defined above. The solids content of the high solids aqueous mineral and/or filler and/or pigment suspension is at least 50 wt.-%, based on the total weight of the high solids aqueous suspension.

[0133] According to one preferred embodiment of the present invention, the high solids aqueous suspension has solids content from 50 to 82 wt.-%, preferably from 55 to 82 wt.-%, more preferably from 60 to 78 wt.-% and most preferably from 65 to 78 wt.-%, based on the total weight of the high solids aqueous suspension.

[0134] The inventive high solids aqueous mineral and/or filler and/or pigment suspension does not freeze at temperatures of -5 °C or even below and thus features an advantageous Brookfield viscosity at such low temperature compared to suspensions described in the prior art. It is thus appreciated that the Brookfield viscosity of the high solids aqueous mineral and/or filler and/or pigment suspension at 100 rpm is $\leq 1\,000$ mPas at a temperature of -5 °C.

[0135] According to the present invention, the Brookfield viscosity is measured after 5 minutes of stirring by the use of an RVT model Brookfield™ viscometer at a temperature of about -5 °C and about +23 °C, and a rotation speed of 100 rpm (revolutions per minute) with the appropriate disc spindle No 1 to 5. The reported viscosity values are the values detected by the instrument after 1 minute of measurement.

[0136] According to one preferred embodiment of the present invention, the high solids aqueous mineral and/or filler and/or pigment suspension has a Brookfield viscosity at 100 rpm from 25 to 1 000 mPas at a temperature of -5 °C, preferably from 25 to 700 mPas at -5 °C, more preferably from 25 to 500 mPas at -5 °C and most preferably from 50 to 300 mPas at -5 °C.

[0137] In one preferred embodiment of the present invention, the Brookfield viscosity of the high solids aqueous mineral and/or filler and/or pigment suspension measured at -5 °C and at 100 rpm is equal to the Brookfield viscosity of the high solids aqueous mineral and/or filler and/or pigment suspension measured at +23 °C and at 100 rpm.

[0138] For the purposes of the present application, the Brookfield viscosity is considered as being equal if the Brookfield viscosity at -5 °C and +23 °C and measured at the same time at 100 rpm do not differ by more than 100 mPas, preferably

by not more than 75 mPas and most preferably by not more than 50 mPas.

[0139] For example, the Brookfield viscosity at 100 rpm of the high solids aqueous mineral and/or filler and/or pigment suspension is $\leq 1\,000$ mPas at $-5\text{ }^{\circ}\text{C}$ and at $+23\text{ }^{\circ}\text{C}$, preferably from 25 to $1\,000$ mPas at $-5\text{ }^{\circ}\text{C}$ and at $+23\text{ }^{\circ}\text{C}$, more preferably preferably from 25 to 700 mPas at $-5\text{ }^{\circ}\text{C}$ and at $+23\text{ }^{\circ}\text{C}$, even more preferably from 25 to 500 mPas at $-5\text{ }^{\circ}\text{C}$ and at $+23\text{ }^{\circ}\text{C}$ and most preferably from 50 to 300 mPas at $-5\text{ }^{\circ}\text{C}$ and at $+23\text{ }^{\circ}\text{C}$.

[0140] It is a further requirement of the instant invention that the high solids aqueous mineral and/or filler and/or pigment suspension has a pH of < 6 at $+23\text{ }^{\circ}\text{C}$. Preferably, the high solids aqueous mineral and/or filler and/or pigment suspension has a pH of < 6 at $+23\text{ }^{\circ}\text{C}$ measured after 24 hours after preparation of the high solids aqueous mineral and/or filler and/or pigment suspension.

[0141] According to one preferred embodiment of the present invention, the high solids aqueous suspension has a pH of between 4 and < 6 at $+23\text{ }^{\circ}\text{C}$, preferably a pH of between 4.5 and < 6 at $+23\text{ }^{\circ}\text{C}$ and preferably a pH of between 5 and < 6 at $+23\text{ }^{\circ}\text{C}$. Preferably, the high solids aqueous suspension has a pH between 4 and < 6 at $+23\text{ }^{\circ}\text{C}$, preferably a pH of between 4.5 and < 6 at $+23\text{ }^{\circ}\text{C}$ and preferably a pH of between 5 and < 6 at $+23\text{ }^{\circ}\text{C}$ measured after 24 hours after preparation of the high solids aqueous mineral and/or filler and/or pigment suspension.

[0142] The high solids aqueous mineral and/or filler and/or pigment suspension especially features a low electrical conductivity at $-5\text{ }^{\circ}\text{C}$ and at $+23\text{ }^{\circ}\text{C}$. It is preferred that the high solids aqueous mineral and/or filler and/or pigment suspension has a conductivity of between 10 and 100 mS/cm at $-5\text{ }^{\circ}\text{C}$ and at $+23\text{ }^{\circ}\text{C}$.

[0143] According to one preferred embodiment of the present invention, the conductivity of the high solids aqueous mineral and/or filler and/or pigment suspension is between 20 mS/cm and 100 mS/cm measured at $-5\text{ }^{\circ}\text{C}$ and at $+23\text{ }^{\circ}\text{C}$ and preferably between 30 mS/cm and 100 mS/cm measured at $-5\text{ }^{\circ}\text{C}$ and at $+23\text{ }^{\circ}\text{C}$.

[0144] In one preferred embodiment of the present invention, the conductivity of the high solids aqueous mineral and/or filler and/or pigment suspension at $-5\text{ }^{\circ}\text{C}$ is equal to the conductivity of the high solids aqueous mineral and/or filler and/or pigment suspension at $+23\text{ }^{\circ}\text{C}$.

[0145] For the purposes of the present application, the conductivity is considered as being equal if the conductivity at $-5\text{ }^{\circ}\text{C}$ and $+23\text{ }^{\circ}\text{C}$ and measured at the same time do not differ by more than 30 mS/cm , preferably by more than 20 mS/cm and most preferably by more than 15 mS/cm .

[0146] In one embodiment of the present invention, the high solids aqueous suspension has a positive charge density in acidic pH environment, preferably at pH 5. For example, the high solids aqueous suspension has a positive charge density of at least $+0.1\text{ C/g}$ at pH 5, preferably of at least $+0.5\text{ C/g}$ at pH 5, more preferably of at least $+1\text{ C/g}$ at pH 5 and most preferably of at least $+1.5\text{ C/g}$ at pH 5.

[0147] It is appreciated that the high solids aqueous mineral and/or filler and/or pigment suspension may be dried in order to obtain the calcium carbonate-containing material. The drying of the high solids aqueous mineral and/or filler and/or pigment suspension can be accomplished by any conventional means known to the skilled person, for example, thermally, e.g. by means of a spray drier or a microwave or in an oven, or mechanically, e.g. by filtration, or lowering the water content.

[0148] If the high solids aqueous mineral and/or filler and/or pigment suspension is dried, the water content of the obtained calcium carbonate-containing material is preferably below 5 wt.-%, more preferably below 4 wt.-%, even more preferably below 3 wt.-% and most preferably below 2 wt.-%, based on the total dry weight of the calcium carbonate-containing material. For example, the water content of the obtained calcium carbonate-containing material is below 1 wt.-% or below 0.5 wt.-%, based on the total dry weight of the calcium carbonate-containing material.

[0149] In view of the advantageous properties of the high solids aqueous mineral and/or filler and/or pigment suspension, especially the exceptional mechanical properties expressed by a Brookfield viscosity at 100 rpm of $\leq 1\,000$ mPas at a temperature of $-5\text{ }^{\circ}\text{C}$ and stability in acidic pH environment, the inventive high solids aqueous mineral and/or filler and/or pigment suspension is suitable in a broad variety of applications.

[0150] In view of the very good results regarding the mechanical and optical properties of the high solids aqueous mineral and/or filler and/or pigment suspension as defined above, a further aspect of the present invention is the use of said high solids aqueous suspension and/or the calcium carbonate-containing material obtained by drying said high solids aqueous suspension in paper making, paper coating, plastic, agricultural and/or paint applications. In one embodiment of the present invention, the high solids aqueous mineral and/or filler and/or pigment suspension and/or the calcium carbonate-containing material obtained by drying said high solids aqueous suspension is used as a support for digital printing, preferred ink jet printing, or for flexo, rotogravure and/or offset printing, most preferably for black ink printing in inkjet printing.

[0151] According to a further aspect of the present invention, the high solids aqueous mineral and/or filler and/or pigment suspension and/or the calcium carbonate-containing material obtained by drying said high solids aqueous suspension can be used as filler in paper.

[0152] According to another aspect of the present invention, a coating color formulation comprising the high solids aqueous mineral and/or filler and/or pigment suspension and/or the calcium carbonate-containing material obtained by drying said high solids aqueous suspension is provided.

[0153] It is preferred that the coating color formulation comprises the high solids aqueous mineral and/or filler and/or pigment suspension as defined above and/or the calcium carbonate-containing material obtained by drying said high solids aqueous suspension as defined above and a natural and/or synthetic binder.

[0154] According to one preferred embodiment of the present invention, the natural and/or synthetic binder consists of styrene-butadiene, styrene-acrylate, polyvinyl acetate, polyvinyl alcohol, starch or mixtures thereof. Preferably, the natural and/or synthetic binder contains or consists of polyvinyl alcohol.

[0155] If the natural and/or synthetic binder comprises a mixture of at least two natural and/or synthetic binders, one binder is preferably polyvinyl alcohol or polyvinyl acetate and a further binder is starch and/or carboxymethyl cellulose.

[0156] With regard to the amount of the natural and/or synthetic binder in the coating color formulation comprising the high solids aqueous mineral and/or filler and/or pigment suspension and/or the calcium carbonate-containing material obtained by drying said high solids aqueous suspension it should be noted that the amount may vary in a broad range as long as a sufficient binding capacity is achieved. However, it is preferred that the coating color formulation comprises the natural and/or synthetic binder in an amount between 2.5 and 20 wt.-% and preferably between 5 and 17 wt.-%, based on the total dry weight of the coating color formulation.

[0157] In particular, it should be noted that the aforementioned advantageous properties of the high solids aqueous mineral and/or filler and/or pigment suspension are not obtained if the at least one calcium carbonate containing material as defined above is contacted with calcium chloride. Accordingly, the high solids aqueous mineral and/or filler and/or pigment suspension is preferably obtainable by the method for producing a high solids aqueous mineral and/or filler and/or pigment suspension described below.

[0158] According to another aspect of the present invention, a method for producing an aqueous calcium carbonate containing composition is provided, comprising the steps of

a) providing an aqueous suspension comprising at least one calcium carbonate-containing material, wherein the calcium carbonate-containing material has a charge density of between +2 and -2 C/g at pH 9,

b) providing

i) at least one strong acid selected from the group consisting of acids having a pK_a value of less than or equal to zero at +23 °C, and/or

ii) at least one salt of at least one strong acid, wherein the at least one strong acid forming the at least one salt of at least one strong acid is selected from the group consisting of acids having a pK_a value of less than or equal to zero at +23 °C

c) adding the at least one strong acid and/or the at least one salt of at least one strong acid of step b) to the aqueous suspension comprising at least one calcium carbonate-containing material of step a),

d) optionally grinding the aqueous suspension comprising at least one calcium carbonate-containing material of step a) before and/or during and/or after step c),

wherein the high solids aqueous suspension after step c) and/or d) has

i) a solids content of at least 50 wt.-%, based on the total weight of the high solids aqueous suspension,

ii) a Brookfield viscosity at 100 rpm of $\leq 1\,000$ mPas at a temperature of -5 °C,

iii) a pH of < 6 at +23 °C, and

iv) a conductivity of between 10 and 100 mS/cm at -5 °C and at +23 °C, and wherein the high solids aqueous suspension comprises the at least one salt of at least one strong acid in an amount from 1 to 20 wt.-%, based on the total weight of the high solids aqueous suspension.

[0159] In one preferred embodiment of the present invention, the method further comprises step e) of providing at least one medium strong acid selected from the group consisting of acids having a pK_a value of between 0 and 2.5 at +23 °C, preferably the at least one medium strong acid is selected from H_2SO_3 , HSO_4^- , H_3PO_4 , oxalic acid and mixtures thereof, and/or at least one weak acid selected from the group consisting of acids having a pK_a value of between >2.5 to 6.0 at +23 °C, preferably the at least one weak acid is selected from citric acid and/or tartaric acid.

[0160] If the instant invention comprises step e) of providing at least one medium strong acid and/or at least one weak acid, the method preferably further comprises step f) of contacting the aqueous suspension comprising at least one calcium carbonate-containing material of step a) with the at least one medium strong acid and/or at least one weak acid during and/or after step c), and/or during and/or after optional step d).

[0161] The addition of the at least one strong acid and/or the at least one salt of at least one strong acid to the aqueous suspension comprising a calcium carbonate-containing material of step c) and the optional contacting of the aqueous suspension comprising a calcium carbonate-containing material of step f) can be accomplished by any conventional

means known to the skilled person. Preferably, the addition and/or contacting is/are carried out under mixing and/or homogenizing and/or particle dividing conditions. The skilled person will adapt these mixing and/or homogenizing and/or particle dividing conditions such as the mixing speed, dividing, and temperature according to his process equipment.

[0162] For example, the mixing and homogenizing may take place by means of a ploughshare mixer as e.g. already described above.

[0163] It is one specific requirement of the instant method that the aqueous suspension comprising a calcium carbonate-containing material is provided first such that the at least one strong acid and/or the at least one salt of at least one strong acid is added to the aqueous suspension comprising a calcium carbonate-containing material. Accordingly, it is appreciated that method step c) is carried out in that the at least one strong acid and/or the at least one salt of at least one strong acid is dosed into the aqueous suspension comprising a calcium carbonate-containing material.

[0164] According to one embodiment of the present invention, the aqueous suspension comprising a calcium carbonate-containing material of step a) is ground in optional method step d). If the calcium carbonate-containing material being part of the aqueous suspension of step a) comprises ground calcium carbonate particles, the aqueous suspension of step a) is preferably wet ground in optional method step d).

[0165] In one embodiment of the present invention, the aqueous suspension of step a) comprises a calcium carbonate-containing material comprising ground calcium carbonate particles which is obtained by grinding, preferably wet grinding, a calcium carbonate-containing material in method step d) and method steps c) and optional method step f) are independently carried out before and/or during and/or after grinding, preferably wet grinding, the calcium carbonate-containing material in method step d). Preferably, method steps c) and optional method step f) are carried out after grinding, preferably wet grinding, the calcium carbonate containing material of the aqueous suspension in method step d).

[0166] The method step c) and/or step d) and/or step f) may be carried out at a temperature of between -5 °C and +99 °C, preferably between +20 °C and +85 °C and most preferably between +20 °C and +50 °C and most preferably between +50 °C and +85 °C.

[0167] According to one embodiment of the present invention, method step c) and/or step d) and/or step f) may be carried out for at least 1 s, preferably for at least 1 min, e.g. for at least 15 min, 30 min, 1 hour, 2 hours, 4 hours, 6 hours, 8 hours, or 10 hours.

[0168] It is preferred that the addition of the at least one strong acid and/or the at least one salt of at least one strong acid of step b) to the aqueous suspension comprising at least one calcium carbonate-containing material of step a) according to method step c) is carried out after optional method step d). Accordingly, method step c) is carried out after optional method step d).

[0169] If optional method step f) is carried out, it is preferred that the contacting of the aqueous suspension comprising the calcium carbonate containing material of step a) with the at least one medium strong acid and/or at least one weak acid of step e) is carried out after the addition of the at least one strong acid and/or the at least one salt of at least one strong acid of step b) to the aqueous suspension comprising at least one calcium carbonate-containing material of step a) according to method step c). Accordingly, optional method step f) is carried out after method step c).

[0170] According to one embodiment of the present invention, the aqueous suspension comprising a calcium carbonate containing material of step a) is contacted with further additives known to the skilled person. For example, the aqueous suspension comprising a calcium carbonate containing material of step a) is further contacted with aluminium hydroxide and/or magnesium hydroxide, preferably in form of a dry product or suspension.

[0171] Preferably, the contacting of the aqueous suspension comprising a calcium carbonate containing material of step a) with the at least one further additive is carried out before and/or during and/or after step c) and/or before and/or during and/or after optional step d) and/or before and/or during and/or after optional step f). Preferably, the contacting of the aqueous suspension comprising a calcium carbonate containing material of step a) with the at least one further additive is carried out after step c) and/or after optional step d) and/or after optional step f).

[0172] The high solids aqueous mineral and/or filler and/or pigment suspension obtained according to the inventive method described above may be concentrated with any method known in the art according to method step g) which is suitable for lowering the water content of the obtained high solids aqueous mineral and/or filler and/or pigment suspension. The high solids aqueous mineral and/or filler and/or pigment suspension may be concentrated in method step g), for example, thermally or mechanically for lowering the water content. For example, the high solids aqueous suspension may be concentrated such that the solids content in the obtained aqueous suspension is at least 60 wt.-%, preferably 65 wt.-%, more preferably 70 wt.-% and most preferably 75 wt.-%, based on the total weight of the obtained high solids aqueous suspension.

[0173] The high solids aqueous mineral and/or filler and/or pigment suspension obtained according to the inventive method described above may be dried with any suitable method known in the art such that a calcium carbonate-containing material is obtained. The high solids aqueous mineral and/or filler and/or pigment suspension may be dried, for example, thermally, e.g. by means of a spray drier or a microwave or in an oven, or mechanically, e.g. by filtration.

[0174] The inventive high solids aqueous mineral and/or filler and/or pigment suspension can be mixed with water to obtain a diluted aqueous mineral and/or filler and/or pigment suspension of the inventive high solids aqueous mineral

and/or filler and/or pigment suspension.

[0175] The scope and interest of the invention will be better understood based on the following examples which are intended to illustrate certain embodiments of the invention and are non-limitative.

5 Examples

1. Measurement methods

pH measurement

[0176] The pH is measured at +23 °C using a Mettler Toledo Seven Easy pH meter and a Mettler Toledo InLab® Expert Pro pH electrode. A three point calibration (according to the segment method) of the instrument is first made using commercially available buffer solutions having pH values of 4, 7 and 10 at +20 °C (from Aldrich). The reported pH values are the endpoint values detected by the instrument (the endpoint is when the measured signal differs by less than 0.1 mV from the average over the last 6 seconds).

Brookfield viscosity

[0177] The Brookfield viscosity was measured by using a RVT model Brookfield™ viscometer at a temperature of +23 °C and -5 °C, and a rotation speed of 100 rpm (revolutions per minute) with the appropriate disc spindle from No 1 to 5. The reported viscosity values are the values detected by the instrument after 1 minute of measurement. Before measuring the Brookfield viscosity the suspension was stirred for 5 minutes using a Pendraulik laboratory dissolver, 0.25 - 2.5 kW, mechanically adjustable up to 8400 rpm with an appropriate tooth disc stirrer.

Electrical conductivity measurement

[0178] The conductivity of a suspension was measured at -5 °C and +23 °C using Mettler Toledo Seven Multi instrumentation equipped with the corresponding Mettler Toledo conductivity expansion unit and a Mettler Toledo InLab® 730 conductivity probe, directly following stirring this suspension at 1 500 rpm using a Pendraulik tooth disc stirrer.

[0179] The instrument was first calibrated in the relevant conductivity range using commercially available conductivity calibration solutions from Mettler Toledo. The influence of temperature on conductivity was automatically corrected by the linear correction mode.

[0180] Measured conductivities are reported for the reference temperature of +23 °C. The reported conductivity values are the endpoint values detected by the instrument (the endpoint is when the measured conductivity differs by less than 0.4 % from the average over the last 6 seconds).

Particle size distribution (mass % particles with a diameter < X) and weight median grain diameter (d_{50}) of particulate material

[0181] Weight median grain diameter and grain diameter mass distribution of a particulate material were determined via the sedimentation method, i.e. an analysis of sedimentation behaviour in a gravimetric field. The measurement was made with a Sedigraph™ 5120.

[0182] The method and the instrument are known to the skilled person and are commonly used to determine grain size of fillers and pigments. The samples were pre-diluted to the right concentration by using deionized water but no further additives, such as usually added dispersants like polyphosphate or polyacrylate as, and dispersed by using a high speed stirrer and ultrasonic.

Weight solids (wt. %) of a material in suspension

[0183] The weight solids were determined by dividing the weight of the solid material by the total weight of the aqueous suspension. The weight solids content was determined at +160 °C using a Moisture Analyser MJ 33, Mettler Toledo.

Specific surface (BET) measurement

[0184] The specific surface area (in m²/g) of the mineral filler was determined using the BET method, which is well known to the skilled man (ISO 9277:1995). The total surface area (in m²) of the mineral filler was then obtained by multiplication of the specific surface area and the mass (in g) of the mineral filler. The method and the instrument are known to the skilled person and are commonly used to determine specific surface of fillers and pigments.

Specific charge (C/g)

[0185] The cationic polymer demand that is necessary to achieve a charge value of zero was measured using the Mettler DL 77 titrator and the Müttec PCD-02 detector by means of the cationic titration method. The cationic reagent was N/200 (0.005 N) methyl glycol chitosan (chitosan), and the anionic reagent was N/400 (0.0025 N) K-polyvinyl-sulfate (KPVs), both sold by WAKO Chemicals GmbH.

[0186] If necessary, the sample was adjusted to pH 8.0 +/- 0.1 with NaOH (0.1M) prior to measurement.

[0187] Since experience showed that the first titration is not correct, 10 ml water were first prepared in the detector followed by the addition of 0.5 ml KPVs. Afterwards, titration with chitosan was made until it is back to shortly after the equivalence point. Subsequently, the measurements were started. Between 0.5 and 2.0 ml of 0.005 molar reagent were used up during the titration to obtain reproducible values.

[0188] To avoid rapid sedimentation, the sample was drawn under stirring, by means of a tared syringe. The content of the syringe was then rinsed into the sample vessel by means of distilled water. Afterwards, the detector was filled with distilled water up to the lower edge and the piston was inserted carefully. Subsequently, the cationic titration solution was put on the memotitrator and the top of the burette was fixed at the detector ensuring that it does not come into contact with the detector or the liquid. After each titration, the development of the titration was verified with the aid of the titration curve.

[0189] Calculation of the electrochemical charge:

$$\text{Charge } [\mu\text{Eq/g}] = \frac{V \cdot c \cdot z \cdot t}{E \cdot F} \cdot K$$

wherein $K = + 1\,000$

V: Consumption chitosan [ml]

c: Concentration chitosan [mol/l]

t: Titer factor chitosan

E: Weight-in quantity [g]

F: Mass fraction solids [g/g]

z: Valence (equivalence number)

[0190] The obtained charge value of $\mu\text{Val/g}$ was converted into C/g by multiplication with the Faraday constant as follows:

$$[\text{C/g}] = [\mu\text{Val/g}] \cdot 0.096485$$

Optical density

[0191] The optical density is a dimension for the thickness of the colour layer above the substrate. Optical density values are calculated based on the spectral measurement, therefore slight differences to the measurement with a densitometer may occur. The calculation is made according to the DIN Norm 16536-2.

2. Examples**A. Suspensions comprising calcium carbonate-containing material**

[0192] The details regarding the suspensions comprising calcium carbonate-containing material as used in the example section are described in the following:

Suspension 1

[0193] A natural calcium carbonate (marble) of Italian origin is obtained by first autogenously dry grinding 10 to 300 mm calcium carbonate rocks to a fineness corresponding to a d_{50} value of between 42 to 48 μm , and subsequently wet grinding this dry-ground product at +30 to +35°C in water in a 1.4-litre vertical attritor mill (Dynomill) at a weight solids content of about 75 wt.-%, based on the total weight of the slurry, until 90 wt.-% of the particles have a diameter < 2 μm ,

16 wt.-% have a diameter $< 0.2 \mu\text{m}$, and a d_{50} value of $0.9 \mu\text{m}$ was reached, using 0.82 wt.-% in respect to dry CaCO_3 of a comb polymer having a specific charge of -49 C/g measured at pH 5.9 and -69 C/g measured at pH 8 and an intrinsic viscosity of 30.3 ml/g (MelPers® 2450, available from BASF, Germany). The charge density of the calcium carbonate-containing material in the suspension was -0.3 C/g at pH 9. The specific surface (BET) was determined to be $10.9 \text{ m}^2/\text{g}$.

Suspension 2

[0194] A natural calcium carbonate (marble) of Italian origin is obtained by first autogenously dry grinding 10 to 300 mm calcium carbonate rocks to a fineness corresponding to a d_{50} value of between 42 to $48 \mu\text{m}$, and subsequently wet grinding this dry-ground product at +30 to +35°C in water in a 1.4-litre vertical attritor mill (Dynamill) at a weight solids content of about 75.9 wt.-%, based on the total weight of the slurry, until 90 wt.-% of the particles have a diameter $< 2 \mu\text{m}$, 12 wt.-% have a diameter $< 0.2 \mu\text{m}$, and a d_{50} value of $0.9 \mu\text{m}$ was reached, using 1.44 wt.-% in respect to dry CaCO_3 of a comb polymer having a specific charge of -92 C/g measured at pH 8 and an intrinsic viscosity of 12.5 ml/g (MelPers® 4343, available from BASF, Germany). The charge density of the calcium carbonate-containing material in the suspension was -0.75 C/g at pH 9. The specific surface (BET) was determined to be $10.5 \text{ m}^2/\text{g}$.

Suspension 3

[0195] A natural calcium carbonate (marble) of Italian origin is obtained by first autogenously dry grinding 10 to 300 mm calcium carbonate rocks to a fineness corresponding to a d_{50} value of between 42 to $48 \mu\text{m}$, and subsequently wet grinding this dry-ground product at +30 to +35°C in water in a 1.4-litre vertical attritor mill (Dynamill) at a weight solids content of about 76 wt.-%, based on the total weight of the slurry, until 92 wt.-% of the particles have a diameter $< 2 \mu\text{m}$, 18 wt.-% have a diameter $< 0.2 \mu\text{m}$, and a d_{50} value of $0.75 \mu\text{m}$ was reached, using 1.1 wt.-% in respect to dry CaCO_3 of a comb polymer having a specific charge of -49 C/g measured at pH 5.9 and -69 C/g measured at pH 8 and an intrinsic viscosity of 30.3 ml/g (MelPers® 2450, available from BASF, Germany). The charge density of the calcium carbonate-containing material in the suspension was -0.4 C/g at pH 9. The conductivity of the suspension was measured as being $510 \mu\text{S}/\text{cm}$, while the pH of the suspension was 7.9 at +23 °C. The specific surface (BET) was determined to be $11.9 \text{ m}^2/\text{g}$.

Example 1 (Comparative Example)

[0196] This example illustrates the prior art and concerns the processing of a suspension comprising a calcium carbonate-containing material in combination with a solution comprising a calcium salt of hydrochloric acid. In particular, the calcium carbonate-containing material is added to the solution comprising a calcium salt of hydrochloric acid.

[0197] 30 g CaCl_2 (Fluka) were dissolved in 70 ml distilled water. The obtained solution had a pH of 8.6 at +23 °C. Into this solution, 30 g CaCO_3 (Fluka) were dispersed under agitation to form a suspension of CaCO_3 in CaCl_2 solution. The obtained suspension had a pH of 8.6 at +23 °C. Into this suspension 0.4 g Melpers 4343 (available from BASF, Germany), in form of a 50 wt.-% solution (BASF), based on the total weight of the solution, corresponding to 0.66 wt.-% in respect to CaCO_3 in the suspension, were dosed under agitation. The obtained suspension had a pH of 8.6 at +23 °C after 1 hour.

[0198] As can be gathered from the details regarding the measured pH, no pH drop to below 6 at +23 °C was observed.

Example 2 (Comparative Example)

[0199] This example illustrates the prior art and concerns the processing of a suspension comprising a calcium carbonate-containing material in combination with a solution comprising a calcium salt of hydrochloric acid. In particular, the calcium carbonate-containing material is added to the solution comprising a calcium salt of hydrochloric acid.

[0200] 20 g CaCl_2 (Fluka) were dissolved in 60 ml distilled water in presence of 2.1 g Melpers 4343 (available from BASF, Germany), in form of a 50 wt.-% solution (BASF), based on the total weight of the solution, and at a temperature of +50 °C. The obtained solution had a pH of 7.7 at +23 °C. Into this solution, 100 g CaCO_3 (Fluka) were dispersed under agitation at about 35 °C to form a suspension of CaCO_3 in CaCl_2 solution. The obtained suspension had a pH of 7.3 at +23 °C after 1 hour.

[0201] As can be gathered from the details regarding the measured pH, no pH drop to below 6 at +23 °C was observed.

Example 3 (Inventive Example)

[0202] This example illustrates the invention and concerns the processing of a suspension comprising a calcium carbonate-containing material with high dry matter content in combination with hydrochloric acid as strong acid. In particular, the hydrochloric acid is added to the calcium carbonate-containing material.

[0203] 598 g of the 75 wt.-% of suspension 1 was placed in a stirred 1 liter glass backer and heated under agitation to +70 °C. To this suspension hydrochloric acid was added drop wise as a 10 wt.-% solution. The goal was to add 164 g of the hydrochloric acid solution in 45 minutes. The obtained aqueous suspension had solids content of 59.1 wt.-%, based on the total weight of the suspension.

[0204] The details regarding the measured Brookfield viscosities (determined at -5 °C and +23 °C and 100 rpm), pH at +23 °C and conductivity can be taken from Table 1.

Table 1

	-5 °C	+23 °C
Brookfield viscosity after 1 hour [mPas]		35
Brookfield viscosity after 1 day [mPas]	65	
pH after 1 hour		5.4
pH after 1 day		5.57
pH after 3 days		5.58
pH after 6 days		5.94
Conductivity after 6 days [mS/cm]	42.1	53.0

[0205] From Table 1 it can be gathered that the inventive high solids aqueous suspension comprising a calcium carbonate-containing material shows an unexpected drop of pH to below 6 compared to the prior art suspensions of Examples 1 and 2 and features a low viscosity at -5 °C as well as a good stability in acidic environment over more than 24 hours.

Example 4 (Inventive Example)

[0206] This example illustrates the invention and concerns the processing of a suspension comprising calcium carbonate-containing material with high dry matter content in combination with hydrochloric acid as strong acid. In particular, the hydrochloric acid is added to the calcium carbonate-containing material.

[0207] 610 g of the 75.9 wt.-% of suspension 3 was placed in a stirred 1 liter glass backer and heated under agitation to +75 °C.

[0208] To this suspension hydrochloric acid was added drop wise in form of a 10 wt.-% solution. The goal was to add 164 g of the hydrochloric acid solution in 45 minutes. The obtained aqueous suspension had solids content of 59.3 wt.-%, based on the total weight of the suspension (suspension 4).

[0209] The details regarding the measured Brookfield viscosities (determined at -5 °C and +23 °C and 100 rpm), pH at +23 °C and conductivity can be taken from Table 2.

Table 2

	-5 °C	+23 °C
Brookfield viscosity after 6 day [mPas]	65	70
pH after 1 hour		5.13
pH after 2 days		5.42
pH after 3 days		5.41
pH after 6 days		5.70
Conductivity after 6 days [mS/cm]	44.9	53.0

[0210] From Table 2 it can be gathered that the inventive high solids aqueous suspension comprising a calcium carbonate-containing material shows an unexpected drop of pH to below 6 compared to the prior art suspensions of Examples 1 and 2 and features a low viscosity at -5 °C as well as a good stability in acidic environment over more than 24 hours.

Example 5 (Inventive Example)

[0211] This example illustrates the invention and concerns the processing of a suspension comprising calcium carbonate-containing material with high dry matter content in combination with hydrochloric acid as strong acid. In particular, the hydrochloric acid is added to the calcium carbonate-containing material.

[0212] 598 g of the 75 wt.-% of suspension 1 was placed in a stirred 1 liter glass backer and heated under agitation to +80 °C. To this suspension hydrochloric acid was added drop wise as a 37 wt.-% solution. The goal was to add 12.7 g of the hydrochloric acid solution in 45 minutes. The obtained aqueous suspension had solids content of 67.4 wt.-%, based on the total weight of the suspension.

[0213] The details regarding the measured Brookfield viscosities (determined at -5 °C and +23 °C and 100 rpm), pH at +23 °C and conductivity can be taken from Table 3.

Table 3

	-5 °C	+23 °C
Brookfield viscosity after 1 hour [mPas]		60
Brookfield viscosity after 6 days [mPas]	85	
pH after 1 hour		4.6
pH after 2 days		4.78
pH after 6 days		5.22
Conductivity after 6 days [mS/cm]	89.7	80.0

[0214] From Table 3 it can be gathered that the inventive high solids aqueous suspension comprising a calcium carbonate-containing material shows an unexpected drop of pH to below 6 compared to the prior art suspensions of Examples 1 and 2 and features a low viscosity at -5 °C as well as a good stability in acidic environment over more than 24 hours.

Example 6 (Inventive Example)

[0215] This example illustrates the invention and concerns the processing of a suspension comprising calcium carbonate-containing material with high dry matter content in combination with nitric acid as strong acid. In particular, the nitric acid is added to the calcium carbonate-containing material.

[0216] 598 g of the 75 wt.-% of suspension 1 was placed in a stirred 1 liter glass backer and heated under agitation to +60 °C. To this suspension nitric acid was added drop wise as a 65 wt.-% solution. The goal was to add 46.8 g of the nitric acid solution in 45 minutes. The obtained aqueous suspension had solids content of 74.4 wt.-%, based on the total weight of the suspension.

[0217] The details regarding the measured Brookfield viscosities (determined at -5 °C and +23 °C and 100 rpm), pH at +23 °C and conductivity can be taken from Table 4.

Table 4

	-5 °C	+23 °C
Brookfield viscosity after 1 hour [mPas]		60
Brookfield viscosity after 6 day [mPas]	125	
pH after 1 hour		5.7
pH after 1 day		5.7
pH after 2 days		5.79
Conductivity after 6 days [mS/cm]	35.1	38.4

[0218] From Table 4 it can be gathered that the inventive high solids aqueous suspension comprising a calcium carbonate-containing material shows an unexpected drop of pH to below 6 compared to the prior art suspensions of Examples 1 and 2 and features a low viscosity at -5 °C as well as a good stability in acidic environment over more than

24 hours.

Example 7 (Inventive Example)

[0219] This example illustrates the invention and concerns the processing of a suspension comprising calcium carbonate-containing material with high dry matter content in combination with hydrochloric acid as strong acid. In particular, the hydrochloric acid is added to the calcium carbonate-containing material.

[0220] 1064 g of the 75 wt.-% of suspension 1 was placed in a stirred 1 liter glass backer and agitated. The Brookfield viscosity of the suspension was 60 mPas measured at 100 rpm and +23 °C. To this suspension hydrochloric acid was added drop wise at 20 °C as a 32 wt.-% solution. The goal was to add 182.5 g of the hydrochloric acid solution in 45 minutes. The obtained aqueous suspension had solids content of 68.2 wt.-%, based on the total weight of the suspension.

[0221] The Brookfield viscosity of the suspension was 60 mPas measured at 100 rpm and +23 °C, the pH at +23 °C was 4.45 measured 1 hour after the preparation of the suspension. 1 hour after the preparation of the suspension, the suspension was stored at +80 °C for 6 hours and cooled back to +23 °C.

[0222] The details regarding the measured Brookfield viscosities (determined at -5 °C and +23 °C and 100 rpm), pH at +23 °C and conductivity can be taken from Table 5.

Table 5

	-10°C	-5 °C	+5 °C	+23 °C
Brookfield viscosity after 3 days [mPas]	107	106	96	
Brookfield viscosity after 6 days [mPas]		80		
pH after 1 day				5.95
pH after 6 days				5.18
Conductivity after 6 days [mS/cm]		91.4		81.7

[0223] From Table 5 it can be gathered that the inventive high solids aqueous suspension comprising a calcium carbonate-containing material shows an unexpected drop of pH to below 6 compared to the prior art suspensions of Examples 1 and 2 and features a low viscosity at -5 °C as well as a good stability in acidic environment over more than 24 hours.

Example 8 (Inventive Example)

[0224] This example illustrates the invention and concerns the processing of suspension comprising calcium carbonate-containing material with high dry matter content in combination with nitric acid as strong acid and a salt of a strong acid. In particular, the nitric acid is added to the calcium carbonate-containing material.

[0225] 598 g of the 75 wt.-% of suspension 1 was placed in a stirred 1 liter glass backer and heated under agitation to +70 °C. To this suspension nitric acid was added drop wise as a 65 wt.-% solution. The goal was to add 46.8 g of the nitric acid solution in 45 minutes. The obtained aqueous suspension was cooled to +20 °C and 23.4 g lithium chloride was added to the suspension under agitation. The obtained aqueous suspension had solids content of 75.9 wt.-%, based on the total weight of the suspension.

[0226] The details regarding the measured Brookfield viscosities (determined at -5 °C and +23 °C and 100 rpm), pH at +23 °C and conductivity can be taken from Table 6.

Table 6

	-6 °C	-1 °C	+23 °C
Brookfield viscosity after 1 hour [mPas]			90
Brookfield viscosity after 1 day [mPas]	152		93
Brookfield viscosity after 2 days [mPas]			97
pH after 1 day		5.5	5.6
Conductivity after 6 days [mS/cm]		53.1	56.4

[0227] From Table 6 it can be gathered that the inventive high solids aqueous suspension comprising a calcium carbonate-containing material shows an unexpected drop of pH to below 6 compared to the prior art suspensions of Examples 1 and 2 and features a low viscosity at -5 °C as well as a good stability in acidic environment over more than 24 hours.

Example 9 (Inventive Example)

[0228] This example illustrates the invention and concerns the processing of a suspension comprising calcium carbonate containing material with high dry matter content in combination with hydrochloric acid as strong acid and a medium strong acid. In particular, the hydrochloric acid is added to the calcium carbonate-containing material.

[0229] 717 g of the 59.3 wt.-% of suspension 4, obtained in Example 4, were placed in a 500 ml glass flask. To this suspension phosphoric acid was slowly dosed under agitation as 85 wt.-% solution at +23 °C over a period of 20 min. The obtained aqueous suspension had solids content of 59.0 wt.-%, based on the total weight of the suspension (suspension 5).

[0230] The details regarding the measured Brookfield viscosities (determined at -5 °C and +23 °C and 100 rpm), pH at +23 °C and conductivity can be taken from Table 7.

Table 7

	-5 °C	+23 °C
Brookfield viscosity after 1 hour [mPas]		75
Brookfield viscosity after 4 days [mPas]	62	65
pH after 1 hour		4.8
pH after 1 day		5.5
pH after 4 days	5.97	5.7
pH after 3 weeks		5.5
pH after 6 weeks		5.4
Conductivity after 4 days [mS/cm]	52.4	47.7

[0231] From Table 7 it can be gathered that the inventive high solids aqueous suspension comprising a calcium carbonate-containing material and a medium strong acid as additive shows an unexpected drop of pH to below 6 compared to the prior art suspensions of Examples 1 and 2 and features a low viscosity at -5 °C as well as a good stability in acidic environment over more than 24 hours.

Example 10 (Inventive Example)

[0232] This example illustrates the invention and concerns the application of suspension 5, obtained in Example 9, as coating color in inkjet application.

[0233] A polyvinyl alcohol solution (1) was prepared by dissolving 3 g of PVA BP 05 A (Supplier, Chang Chun Petrochemical Co., Ltd, 301 Songkang Road, 7th Fl., Taipei, Taiwan, 10477) in 15 g deionized water at +90°C in 20 minutes under agitation.

[0234] 100 g of the aqueous suspension 5, obtained in Example 9, were mixed under agitation with 18 g of the PVA solution (1). The obtained coating color had solids content of 55 wt.-% based on the total weight of the coating color.

[0235] The obtained coating color was applied on 80 g/m² office paper "Centro Pro" hochweiss, holzfrei, matt (Art. No 105570, commercially available from Inapa, Switzerland) in a range of different coat weights (using different rods; rod 0 obtains a coat weight of 10.1 g/m², rod 1 obtains a coat weight of 12.1 g/m²) by using a laboratory coater Typ Model 624 from Ericksen, 58675 Hemer, Germany. The papers were dried for 10 min at +80 °C and conditioned before printing at +23 °C, 50 % rel. air humidity for 24 hour.

[0236] The coatings were tested at +23 °C and 50 % rel. air humidity by using a HP color inkjet printer (HP Deskjet 1000, product No CH340B, model No J110a) for black and color (HP Ink Cartridge 301 "black" CH561E and "tri-color" CH562E) on 4 x 4 cm squares and Rod 0 to Rod 3.

[0237] The optical density of the test samples, i.e. coated with the inventive coating color, was compared to non coated blank paper being a 80 g/m² office paper "Centro Pro" hochweiss, holzfrei, matt (Art. No 105570, commercially available from Inapa, Switzerland). The details regarding the measured optical density can be taken from Table 8.

Table 8

	Prior art blank / no coating	Invention Coat weight	
		10.1 g/m ²	12.1 g/m ²
OD Black ***	1.89	2.54	2.59
OD Blue ***	1.13	1.44	1.45
*** Optical density Spectrolino™, Spectrophotometer, Handheld system			

[0238] From Table 8 it can be gathered that the coating of the raw paper with the coating color comprising the inventive high solids aqueous suspension shows a clear improvement in color density compared to the non-coated blank paper of the prior art.

Example 11 (Inventive Example)

[0239] This example illustrates the invention and concerns the processing of a suspension comprising calcium carbonate-containing material with high dry matter content in combination with hydrochloric acid as strong acid and aluminium hydroxide. In particular, the hydrochloric acid is added to the calcium carbonate-containing material.

[0240] A suspension A was formed by dispersing 70 g Al(OH)₃ under agitation in 30 g of tap water. Furthermore, 2 g of a comb polymer having a specific charge of -49 C/g measured at pH 5.9 and -69 C/g measured at pH 8 and an intrinsic viscosity of 30.3 ml/g (MeiPers® 2450, available from BASF, Germany) was added. The pH of the suspension A at +23 °C after 1 hour of preparation was 8.4, the Brookfield viscosity after 1 hour and 24 hours of preparation was < 1 000 mPas measured at 100 rpm and +23 °C.

[0241] A suspension B was formed under agitation for 10 minutes by adding 14 g of AlCl₃ x 6 H₂O (Fluka, Switzerland Order No. 06232) to suspension A. The obtained aqueous suspension had solids content of 70.1 wt.-%, based on the total weight of the suspension B.

[0242] The details regarding the measured Brookfield viscosities (determined at +23 °C and 100 rpm), pH at +23 °C and conductivity can be taken from Table 9.

Table 9

	+23 °C
Brookfield viscosity after 1 hour [mPas]	< 1 000
Brookfield viscosity after 1 day [mPas]	< 1 000
pH after 10 min	0.70
pH after 1 hour	1.40
pH after 1 day	1.67
Conductivity after 1 days [mS/cm]	46.3

[0243] 100 g of the 59 wt.-% of suspension 5, obtained in Example 9, were placed in a 200 ml glass flask. To this aqueous suspension, 100 g of suspension B were slowly added under agitation at +23 °C over a period of 60 min. The obtained aqueous suspension had solids content of 62.9 wt.-%, based on the total weight of the suspension.

[0244] The details regarding the measured Brookfield viscosities (determined at -5 °C and +23 °C and 100 rpm), pH at +23 °C and conductivity can be taken from Table 10.

Table 10

	-5 °C	+23 °C
Brookfield viscosity after 1 hour [mPas]		288
Brookfield viscosity after 6 hours [mPas]		344
Brookfield viscosity after 10 days [mPas]	< 700	< 700
pH after 1 hour		4.2

(continued)

	-5 °C	+23 °C
pH after 6 hours		4.6
pH after 10 days		4.5

[0245] From Table 10 it can be gathered that the inventive high solids aqueous suspension comprising a calcium carbonate-containing material and aluminium hydroxide as additive shows an unexpected drop of pH to below 6 compared to the prior art suspensions of Examples 1 and 2 and features a low viscosity at -5 °C as well as a good stability in acidic environment over more than 24 hours.

Example 12 (Inventive Example)

[0246] This example illustrates the invention and concerns the processing of a suspension comprising a calcium carbonate-containing material with high dry matter content in combination with a calcium salt of hydrochloric acid. In particular, the calcium salt of hydrochloric acid is added to the calcium carbonate-containing material.

[0247] 315 g of the 76 wt.-% of suspension 3, having a pH of 7.9 at +23 °C, was placed in a stirred 250 ml glass backer at +23 °C. To this suspension 31.7 g $\text{CaCl}_2 \times 2 \text{H}_2\text{O}$ were added under agitation in 5 minutes. The goal was to add in total 23.9 g of the calcium salt of hydrochloric acid. The obtained aqueous suspension had solids content of 75.5 wt.-%, based on the total weight of the suspension.

[0248] The details regarding the measured Brookfield viscosities (determined at -5 °C and +23 °C and 100 rpm), pH at +23 °C and conductivity at +23 °C can be taken from Table 11.

Table 11

at Temp. of:	-5 °C	+23 °C
Brookfield viscosity after 6 hour [mPas]	45	45
pH after 1 hour		4.6
pH after 1 day		4.8
pH after 7 day		4.9
Conductivity after 1 hour [mS/cm]		64.6

[0249] From Table 11 it can be gathered that the inventive high solids aqueous suspension comprising a calcium carbonate-containing material shows an unexpected drop of pH to below 6 compared to the prior art suspensions of Examples 1 and 2 and features a low viscosity at -5 °C as well as a good stability in acidic environment over more than 24 hours.

[0250] In comparison reasons, 31.7 g $\text{CaCl}_2 \times 2 \text{H}_2\text{O}$ were dissolved in 75 g water under agitation. The goal was to have approximately the same concentration of the calcium salt of hydrochloric acid as in the liquid phase of the suspension of this example as described above. The details regarding the measured pH at +23 °C and conductivity at +23 °C can be taken from Table 12

Table 12

at Temp. of:	+23 °C
pH after 1 hour	9.4
pH after 7 day	9.2
Conductivity after 1 hour [mS/cm]	61.1

[0251] From the details set out in Table 11 versus Table 12, it can be gathered that totally surprising the inventive high solids aqueous suspension comprising a calcium carbonate-containing material has a stable acidic pH of far below 6 at +23 °C combining an alkaline suspension of calcium carbonate having a pH of 8.4 with an alkaline solution of calcium salt of hydrochloric acid having a pH of about 9.4 (as outlined in Table 12).

Example 13 (Inventive Example)

[0252] This example illustrates the invention and concerns the processing of a suspension comprising a calcium carbonate-containing material with high dry matter content in combination with a calcium salt of nitric acid. In particular, the calcium salt of nitric acid is added to the calcium carbonate-containing material.

[0253] 500 g of the 76 wt.-% of suspension 3 was placed in a stirred 1 000 ml glass backer at +23 °C. To this suspension 54 g $\text{Ca}(\text{NO}_3)_2 \times 4 \text{H}_2\text{O}$ were added under agitation in 5 minutes. The goal was to add in total 37.5 g of the calcium salt of nitric acid. The obtained aqueous suspension had solids content of 75.3 wt.-%, based on the total weight of the suspension.

[0254] The details regarding the measured Brookfield viscosities (determined at -5 °C and +23 °C and 100 rpm), pH at +23 °C and conductivity at +23 °C can be taken from Table 13.

Table 13

at Temp. of:	-5 °C	+23 °C
Brookfield viscosity after 6 hour [mPas]	55	65
pH after 1 hour		5.5
pH after 1 day		5.8
Conductivity after 1 hour [mS/cm]		34.6

[0255] From Table 13 it can be gathered that the inventive high solids aqueous suspension comprising a calcium carbonate-containing material shows an unexpected drop of pH to below 6 compared to the prior art suspensions of Examples 1 and 2 and features a low viscosity at -5 °C as well as a good stability in acidic environment over more than 24 hours.

Example 14 (inventive Example)

[0256] This example illustrates the invention and concerns the processing of a suspension comprising a calcium carbonate in combination with a solution comprising a calcium salt of hydrochloric acid. In particular, the calcium salt of hydrochloric acid is added to the calcium carbonate-containing material.

[0257] 70 g CaCO_3 (Fluka) were dispersed under agitation in 70 ml distilled water to form a suspension of CaCO_3 . Into this suspension 1.5 g Melpers 4343 (available from BASF, Germany), in form of a 50 wt.-% solution (BASF), based on the total weight of the solution, were added. The obtained suspension had a pH of 7.5 at +23 °C. Into this suspension, 3 g CaCl_2 (Fluka) were dosed under agitation to form a CaCO_3 suspension comprising CaCl_2 . Subsequently, further 4 g CaCl_2 (Fluka) were dosed under agitation into the suspension to form a CaCO_3 suspension comprising CaCl_2 .

[0258] The details regarding the measured pH at +23 °C can be taken from Table 14.

Table 14

at Temp. of:	+23 °C
pH after 1 hour	5.4
pH after 5 days	5.9

[0259] As can be gathered from the details regarding the measured pH, an unexpected drop of pH to below 6 at +23 °C was observed.

Claims

1. A high solids aqueous mineral and/or filler and/or pigment suspension in acidic pH environment comprising:

- a) at least one calcium carbonate-containing material comprising calcium carbonate-containing particles, and
- b) at least one salt of at least one strong acid, wherein the at least one strong acid forming the at least one salt of at least one strong acid is selected from the group consisting of acids having a pK_a value of less than or equal to zero at +23 °C,

wherein the high solids aqueous suspension has

- i) a solids content of at least 50 wt.-%, based on the total weight of the high solids aqueous suspension,
 - ii) a Brookfield viscosity at 100 rpm of $\leq 1\,000$ mPas at a temperature of $-5\text{ }^{\circ}\text{C}$
 - iii) a pH of < 6 at $+23\text{ }^{\circ}\text{C}$, and
 - iv) a conductivity of between 10 and 100 mS/cm at $-5\text{ }^{\circ}\text{C}$ and at $+23\text{ }^{\circ}\text{C}$, and wherein the high solids aqueous suspension comprises the at least one salt of at least one strong acid in an amount of from 1 to 20 wt.-%, based on the total weight of the high solids aqueous suspension.
2. The high solids aqueous mineral and/or filler and/or pigment suspension of claim 1, wherein the calcium carbonate-containing particles of the at least one calcium carbonate-containing material are selected from among natural calcium carbonate, precipitated calcium carbonate or mixtures thereof.
 3. The high solids aqueous mineral and/or filler and/or pigment suspension of claim 1 or 2, wherein the calcium carbonate-containing particles of the at least one calcium carbonate-containing material have a weight median particle size d_{50} from 0.1 to 50 μm , preferably from 0.25 to 50 μm , more preferably from 0.3 to 5 μm , and most preferably from 0.4 to 3 μm .
 4. The high solids aqueous mineral and/or filler and/or pigment suspension of any one of the preceding claims, wherein the calcium carbonate-containing particles of the at least one calcium carbonate-containing material have a specific surface area of from 0.1 m^2/g to 200 m^2/g , preferably from 0.1 m^2/g to 50 m^2/g and more preferably from 0.1 m^2/g to 20 m^2/g , measured using nitrogen and the BET method.
 5. The high solids aqueous mineral and/or filler and/or pigment suspension of any one of the preceding claims, wherein the high solids aqueous suspension comprises the at least one calcium carbonate-containing material in an amount of at least 50 wt.-%, preferably from 50 to 82 wt.-%, more preferably from 55 to 82 wt.-%, even more preferably from 60 to 78 wt.-% and most preferably from 65 to 78 wt.-%, based on the total weight of the high solids aqueous suspension.
 6. The high solids aqueous mineral and/or filler and/or pigment suspension of any one of the preceding claims, wherein the at least one calcium carbonate-containing material comprises at least one comb polymer, preferably the surface of the calcium carbonate-containing particles of the at least one calcium carbonate-containing material are coated with the at least one comb polymer.
 7. The high solids aqueous mineral and/or filler and/or pigment suspension of any one of the preceding claims, wherein the at least one calcium carbonate-containing material comprises at least one comb polymer having an intrinsic viscosity in the range of 5 to 99 ml/g, preferably in the range of 10 to 80 ml/g and most preferably in the range of 10 to 50 ml/g.
 8. The high solids aqueous mineral and/or filler and/or pigment suspension of any one of the preceding claims, wherein the at least one salt of at least one strong acid comprises a divalent and/or trivalent cation, preferably the divalent cation is selected from the group consisting of calcium, magnesium, strontium and mixtures thereof and/or the trivalent cation preferably is aluminum.
 9. The high solids aqueous mineral and/or filler and/or pigment suspension of any one of the preceding claims, wherein the at least one strong acid forming the at least one salt of at least one strong acid is selected from the group consisting of hydrochloric acid, nitric acid and mixtures thereof.
 10. The high solids aqueous mineral and/or filler and/or pigment suspension of any one of the preceding claims, wherein the high solids aqueous suspension comprises at least one comb polymer in an amount from 0.01 to 5 wt.-%, based on the total dry weight of the calcium carbonate-containing material in the suspension, preferably from 0.05 to 4 wt.-%, more preferably from 0.1 to 3 wt.-%, even more preferably from 0.2 to 2 wt.-%, and most preferably from 0.25 to 1.5 wt.-% or from 0.5 to 1.25 wt.-%.
 11. The high solids aqueous mineral and/or filler and/or pigment suspension of any one of the preceding claims, wherein the high solids aqueous suspension has solids content from 50 to 82 wt.-%, preferably from 55 to 82 wt.-%, more preferably from 60 to 78 wt.-% and most preferably from 65 to 78 wt.-%, based on the total weight of the high solids aqueous suspension.

12. The high solids aqueous mineral and/or filler and/or pigment suspension of any one of the preceding claims, wherein the high solids aqueous suspension has a Brookfield viscosity at 100 rpm from 25 to 1 000 mPas at a temperature of -5 °C, preferably from 25 to 700 mPas at -5 °C, more preferably from 25 to 500 mPas at -5 °C and most preferably from 50 to 300 mPas at -5 °C.
13. The high solids aqueous mineral and/or filler and/or pigment suspension of any one of the preceding claims, wherein the high solids aqueous suspension has a pH of between 4 and < 6 at +23 °C, preferably a pH of between 4.5 and < 6 at +23 °C and preferably a pH of between 5 and < 6 at +23 °C.
14. The high solids aqueous mineral and/or filler and/or pigment suspension of any one of the preceding claims, wherein the high solids aqueous suspension has a conductivity of between 20 mS/cm and 100 mS/cm measured at -5 °C and +23 °C and preferably between 30 mS/cm and 100 mS/cm measured at - 5 °C and +23 °C.
15. The high solids aqueous mineral and/or filler and/or pigment suspension of any one of the preceding claims, wherein the high solids aqueous suspension further comprises at least one reaction product or products of the at least one calcium carbonate-containing material with at least one medium strong acid and/or at least one reaction product or products of the at least one calcium carbonate-containing material with at least one weak acid.
16. The high solids aqueous mineral and/or filler and/or pigment suspension of claim 16, wherein the at least one medium strong acid forming the at least one reaction product or products of the at least one calcium carbonate-containing material is selected from the group consisting of acids having a pK_a value of between 0 and 2.5 at +23 °C, preferably the at least one medium strong acid is selected from H_2SO_3 , HSO_4^- , H_3PO_4 , oxalic acid and mixtures thereof and/or the at least one weak acid forming the at least one reaction product or products of the at least one calcium carbonate-containing material is selected from the group consisting of acids having a pK_a value of between >2.5 and 6 at +23 °C, preferably the at least one weak acid is selected from citric acid, tartaric acid and mixtures thereof.
17. The high solids aqueous mineral and/or filler and/or pigment suspension of any one of the preceding claims, wherein the molar quantity of the sum, expressed by the generated H_3O^+ ions, of the at least one medium strong acid forming the at least one reaction product or products of the at least one calcium carbonate-containing material and/or the at least one weak acid forming the at least one reaction product or products of the at least one calcium carbonate-containing material and the at least one strong acid forming the at least one salt of at least one strong acid relative to the quantity of moles of $CaCO_3$ is in total between 0.01 and 1.9.
18. The high solids aqueous mineral and/or filler and/or pigment suspension of any one of the preceding claims, wherein the high solids aqueous suspension further comprises aluminum hydroxide and/or magnesium hydroxide.
19. The high solids aqueous mineral and/or filler and/or pigment suspension of any one of the preceding claims, wherein the high solids aqueous suspension has a positive charge density at pH 5, preferably of at least +0.1 C/g at pH 5, more preferably of at least +0.5 C/g at pH 5, even more preferably of at least +1 C/g at pH 5 and most preferably of at least +1.5 C/g at pH 5.
20. A method for producing a high solids aqueous mineral and/or filler and/or pigment suspension as defined in any one of claims 1 to 19, comprising the steps of
 - a) providing an aqueous suspension comprising at least one calcium carbonate-containing material, as defined in any one of claims 1 to 7, wherein the calcium carbonate-containing material has a charge density of between +2 and -2 C/g at pH 9, ,
 - b) providing
 - i) at least one strong acid selected from the group consisting of acids having a pK_a value of less than or equal to zero at +23 °C as defined in any one of claims 1 or 9, and/or
 - ii) at least one salt of at least one strong acid, wherein the at least one strong acid forming the at least one salt of at least one strong acid is selected from the group consisting of acids having a pK_a value of less than or equal to zero at +23 °C as defined in any one of claims 1, 8 or 9,
 - c) adding the at least one strong acid and/or the at least one salt of at least one strong acid of step b) to the aqueous suspension comprising at least one calcium carbonate-containing material of step a),
 - d) optionally grinding the aqueous suspension comprising at least one calcium carbonate-containing material

of step a) before and/or during and/or after step c),

wherein the high solids aqueous suspension after step c) and/or d) has

- i) a solids content of at least 50 wt.-%, based on the total weight of the high solids aqueous suspension,
- ii) a Brookfield viscosity at 100 rpm of $\leq 1\,000$ mPas at a temperature of $-5\text{ }^{\circ}\text{C}$,
- iii) a pH of < 6 at $+23\text{ }^{\circ}\text{C}$, and
- iv) a conductivity of between 10 and 100 mS/cm at $-5\text{ }^{\circ}\text{C}$ and at $+23\text{ }^{\circ}\text{C}$, and wherein the high solids aqueous suspension comprises the at least one salt of at least one strong acid in an amount of from 1 to 20 wt.-%, based on the total weight of the high solids aqueous suspension.

21. The method of claim 20, wherein the method further comprises step e) of providing at least one medium strong acid selected from the group consisting of acids having a pK_a value of between 0 and 2.5 at $+23\text{ }^{\circ}\text{C}$, preferably the at least one medium strong acid is selected from H_2SO_3 , HSO_4^- , H_3PO_4 , oxalic acid and mixtures thereof, and/or at least one weak acid selected from the group consisting of acids having a pK_a value of between >2.5 to 6.0 at $+23\text{ }^{\circ}\text{C}$, preferably the at least one weak acid is selected from citric acid and/or tartaric acid.

22. The method of claim 21, wherein the method further comprises step f) of contacting the aqueous suspension comprising at least one calcium carbonate-containing material of step a) with the at least one medium strong acid and/or at least one weak acid of step e) during and/or after step c), and/or during and/or after optional step d).

23. The method of any one of claims 20 to 22, wherein step c) and/or step d) and/or step f) is carried out at a temperature of between $+5\text{ }^{\circ}\text{C}$ and $+99\text{ }^{\circ}\text{C}$, preferably between $+20\text{ }^{\circ}\text{C}$ and $+85\text{ }^{\circ}\text{C}$ and most preferably between $+20\text{ }^{\circ}\text{C}$ and $+50\text{ }^{\circ}\text{C}$ and most preferably between $+50\text{ }^{\circ}\text{C}$ and $+85\text{ }^{\circ}\text{C}$.

24. The method of any one of claims 20 to 23, wherein the method further comprises step g) of concentrating the obtained high solids aqueous mineral and/or filler and/or pigment suspension.

25. The method of any one of claims 20 to 24, wherein the method further comprises drying the obtained high solids aqueous mineral and/or filler and/or pigment suspension.

26. Calcium carbonate-containing material obtainable by drying the high solids aqueous mineral and/or filler and/or pigment suspension of any one of claims 1 to 19.

27. Use of the high solids aqueous mineral and/or filler and/or pigment suspension of any one of claims 1 to 19 and/or the calcium carbonate-containing material of claim 26 in paper making, paper coating, plastic, agricultural and/or paint applications.

28. Use of the high solids aqueous mineral and/or filler and/or pigment suspension of any one of claims 1 to 19 and/or the calcium carbonate-containing material of claim 26 as filler in paper.

29. The use of claim 27, wherein the high solids aqueous mineral and/or filler and/or pigment suspension and/or the calcium carbonate-containing material is used as a support for digital printing, preferred ink jet printing, or for flexo, rotogravure and/or offset printing, most preferably for black ink printing in inkjet printing.

30. A coating color formulation comprising the high solids aqueous mineral and/or filler and/or pigment suspension of any one of claims 1 to 19 and/or the calcium carbonate-containing material of claim 26 and a natural and/or synthetic binder, the binder preferably consisting of styrene-butadiene, styrene-acrylate, polyvinyl acetate, polyvinyl alcohol, starch or mixtures thereof, and most preferably the binder contains or consists of polyvinyl alcohol.

Patentansprüche

1. Wässrige Mineral- und/oder Füllstoff- und/oder Pigmentsuspension mit einem hohen Feststoffgehalt und in einer Umgebung mit saurem pH, umfassend:

- a) wenigstens ein Calciumcarbonat enthaltendes Material, das Calciumcarbonat enthaltende Partikel umfasst, und

b) wenigstens ein Salz von wenigstens einer starken Säure, wobei die wenigstens eine starke Säure, die das wenigstens eine Salz von wenigstens einer starken Säure bildet, ausgewählt ist aus der Gruppe bestehend aus Säuren mit einem pK_a -Wert kleiner oder gleich 0 bei +23°C,

wobei die wässrige Suspension mit einem hohen Feststoffgehalt aufweist:

- i) einen Feststoffgehalt von wenigstens 50 Gew.-%, bezogen auf das Gesamtgewicht der wässrigen Suspension mit einem hohen Feststoffgehalt,
 - ii) eine Brookfield-Viskosität bei 100 U/min von $\leq 1\,000$ mPa·s bei einer Temperatur von -5°C,
 - iii) einen pH von < 6 bei +23°C, und
 - iv) eine Leitfähigkeit zwischen 10 und 100 mS/cm bei -5°C und bei +23°C, und
- wobei die wässrige Suspension mit einem hohen Feststoffgehalt das wenigstens eine Salz von wenigstens einer starken Säure in einer Menge von 1 bis 20 Gew.-% umfasst, bezogen auf das Gesamtgewicht der wässrigen Suspension mit einem hohen Feststoffgehalt.

2. Wässrige Mineral- und/oder Füllstoff- und/oder Pigmentsuspension mit einem hohen Feststoffgehalt nach Anspruch 1, bei der die Calciumcarbonat enthaltenden Partikel des wenigstens einen Calciumcarbonat enthaltenden Materials ausgewählt sind aus natürlichem Calciumcarbonat, gefälltem Calciumcarbonat, oder Gemischen davon.
3. Wässrige Mineral- und/oder Füllstoff- und/oder Pigmentsuspension mit einem hohen Feststoffgehalt nach Anspruch 1 oder 2, bei der die Calciumcarbonat enthaltenden Partikel des wenigstens einen Calciumcarbonat enthaltenden Materials eine gewichtsgemittelte Partikelgrösse d_{50} von 0,1 bis 50 μm aufweisen, bevorzugt von 0,25 bis 50 μm , bevorzugter von 0,3 bis 5 μm , und am meisten bevorzugt von 0,4 bis 3 μm .
4. Wässrige Mineral- und/oder Füllstoff- und/oder Pigmentsuspension mit einem hohen Feststoffgehalt nach einem der vorhergehenden Ansprüche, bei der die Calciumcarbonat enthaltenden Partikel des wenigstens einen Calciumcarbonat enthaltenden Materials eine spezifische Oberfläche von 0,1 m^2/g bis 200 m^2/g aufweisen, bevorzugt von 0,1 m^2/g bis 50 m^2/g , und bevorzugter von 0,1 m^2/g bis 20 m^2/g , gemessen durch Verwenden von Stickstoff und dem BET-Verfahren.
5. Wässrige Mineral- und/oder Füllstoff- und/oder Pigmentsuspension mit einem hohen Feststoffgehalt nach einem der vorhergehenden Ansprüche, bei der die wässrige Suspension mit einem hohen Feststoffgehalt das wenigstens eine Calciumcarbonat enthaltende Material in einer Menge von wenigstens 50 Gew.-% umfasst, bevorzugt von 50 bis 82 Gew.-%, bevorzugter von 55 bis 82 Gew.-%, noch bevorzugter von 60 bis 78 Gew.-%, und am meisten bevorzugt von 65 bis 78 Gew.-%, bezogen auf das Gesamtgewicht der wässrigen Suspension mit einem hohen Feststoffgehalt.
6. Wässrige Mineral- und/oder Füllstoff- und/oder Pigmentsuspension mit einem hohen Feststoffgehalt nach einem der vorhergehenden Ansprüche, bei der das wenigstens eine Calciumcarbonat enthaltende Material wenigstens ein Kammpolymer umfasst, bevorzugt ist die Oberfläche der Calciumcarbonat enthaltenden Partikel des wenigstens einen Calciumcarbonat enthaltenden Materials mit dem wenigstens einen Kammpolymer beschichtet.
7. Wässrige Mineral- und/oder Füllstoff- und/oder Pigmentsuspension mit einem hohen Feststoffgehalt nach einem der vorhergehenden Ansprüche, bei der das wenigstens eine Calciumcarbonat enthaltende Material wenigstens ein Kammpolymer mit einer intrinsischen Viskosität im Bereich von 5 bis 99 ml/g umfasst, bevorzugt im Bereich von 10 bis 80 ml/g , und am meisten bevorzugt im Bereich von 10 bis 50 ml/g .
8. Wässrige Mineral- und/oder Füllstoff- und/oder Pigmentsuspension mit einem hohen Feststoffgehalt nach einem der vorhergehenden Ansprüche, bei der das wenigstens eine Salz von wenigstens einer starken Säure ein divalentes und/oder trivalentes Kation umfasst, bevorzugt ist das divalente Kation ausgewählt aus der Gruppe bestehend aus Calcium, Magnesium, Strontium und Gemischen davon, und/oder das trivalente Kation ist bevorzugt Aluminium.
9. Wässrige Mineral- und/oder Füllstoff- und/oder Pigmentsuspension mit einem hohen Feststoffgehalt nach einem der vorhergehenden Ansprüche, bei der die wenigstens eine starke Säure, die das wenigstens eine Salz von wenigstens einer starken Säure bildet, ausgewählt ist aus der Gruppe bestehend aus Salzsäure, Salpetersäure und Gemischen davon.
10. Wässrige Mineral- und/oder Füllstoff- und/oder Pigmentsuspension mit einem hohen Feststoffgehalt nach einem

der vorhergehenden Ansprüche, bei der die wässrige Suspension mit einem hohen Feststoffgehalt wenigstens ein Kammpolymer in einer Menge von 0,01 bis 5 Gew.-% umfasst, bezogen auf das Gesamttrockengewicht des Calciumcarbonat enthaltenden Materials in der Suspension, bevorzugt von 0,05 bis 4 Gew.-%, bevorzugter von 0,1 bis 3 Gew.-%, noch bevorzugter von 0,2 bis 2 Gew.-%, und am meisten bevorzugt von 0,25 bis 1,5 Gew.-%, oder von 0,5 bis 1,25 Gew.-%.

11. Wässrige Mineral- und/oder Füllstoff- und/oder Pigmentsuspension mit einem hohen Feststoffgehalt nach einem der vorhergehenden Ansprüche, bei der die wässrige Suspension mit einem hohen Feststoffgehalt einen Feststoffgehalt von 50 bis 82 Gew.-% aufweist, bevorzugt von 55 bis 82 Gew.-%, bevorzugter von 60 bis 78 Gew.-%, und am meisten bevorzugt von 65 bis 78 Gew.-%, bezogen auf das Gesamtgewicht der wässrigen Suspension mit einem hohen Feststoffgehalt.
12. Wässrige Mineral- und/oder Füllstoff- und/oder Pigmentsuspension mit einem hohen Feststoffgehalt nach einem der vorhergehenden Ansprüche, bei der die wässrige Suspension mit einem hohen Feststoffgehalt eine Brookfield-Viskosität bei 100 U/min von 25 bis 1 000 mPa·s bei einer Temperatur von -5°C aufweist, bevorzugt von 25 bis 700 mPa·s bei -5°C, bevorzugter von 25 bis 500 mPa·s bei -5°C, und am meisten bevorzugt von 50 bis 300 mPa·s bei -5°C.
13. Wässrige Mineral- und/oder Füllstoff- und/oder Pigmentsuspension mit einem hohen Feststoffgehalt nach einem der vorhergehenden Ansprüche, bei der die wässrige Suspension mit einem hohen Feststoffgehalt einen pH zwischen 4 und < 6 bei +23°C aufweist, bevorzugt einen pH zwischen 4,5 und < 6 bei +23°C, und bevorzugt einen pH zwischen 5 und < 6 bei +23°C.
14. Wässrige Mineral- und/oder Füllstoff- und/oder Pigmentsuspension mit einem hohen Feststoffgehalt nach einem der vorhergehenden Ansprüche, bei der die wässrige Suspension mit einem hohen Feststoffgehalt eine Leitfähigkeit zwischen 20 mS/cm und 100 mS/cm, gemessen bei -5°C und bei +23°C, aufweist, und bevorzugt zwischen 30 mS/cm und 100 mS/cm, gemessen bei -5°C und bei +23°C.
15. Wässrige Mineral- und/oder Füllstoff- und/oder Pigmentsuspension mit einem hohen Feststoffgehalt nach einem der vorhergehenden Ansprüche, bei der die wässrige Suspension mit einem hohen Feststoffgehalt ferner wenigstens ein Reaktionsprodukt oder Reaktionsprodukte des wenigstens einen Calciumcarbonat enthaltenden Materials mit wenigstens einer mittelstarken Säure umfasst, und/oder wenigstens ein Reaktionsprodukt oder Reaktionsprodukte des wenigstens einen Calciumcarbonat enthaltenden Materials mit wenigstens einer schwachen Säure.
16. Wässrige Mineral- und/oder Füllstoff- und/oder Pigmentsuspension mit einem hohen Feststoffgehalt nach einem der vorhergehenden Ansprüche, bei der die wenigstens eine mittelstarke Säure, die das wenigstens eine Reaktionsprodukt oder Reaktionsprodukte des wenigstens einen Calciumcarbonat enthaltenden Materials bildet, ausgewählt ist aus der Gruppe bestehend aus Säuren mit einem pK_a -Wert zwischen 0 und 2,5 bei +23°C, bevorzugt ist die wenigstens eine mittelstarke Säure ausgewählt aus H_2SO_3 , HSO_4^- , H_3PO_4 , Oxalsäure und Gemischen davon, und/oder die wenigstens eine schwache Säure, die wenigstens ein Reaktionsprodukt oder Reaktionsprodukte des wenigstens einen Calciumcarbonat enthaltenden Materials bildet, ist ausgewählt aus der Gruppe bestehend aus Säuren mit einem pK_a -Wert zwischen > 2,5 und 6 bei +23°C, bevorzugt ist die wenigstens eine schwache Säure ausgewählt aus Zitronensäure, Weinsäure und Gemischen davon.
17. Wässrige Mineral- und/oder Füllstoff- und/oder Pigmentsuspension mit einem hohen Feststoffgehalt nach einem der vorhergehenden Ansprüche, bei der die Summe der Molmenge, ausgedrückt durch die erzeugten H_3O^+ -Ionen, der wenigstens einen mittelstarken Säure, die das wenigstens eine Reaktionsprodukt oder Reaktionsprodukte des wenigstens einen Calciumcarbonat enthaltenden Materials bildet, und/oder der wenigstens einen schwachen Säure, die das wenigstens eine Reaktionsprodukt oder Reaktionsprodukte des wenigstens einen Calciumcarbonat enthaltenden Materials bildet, und der wenigstens einen starken Säure, die das wenigstens eine Salz von wenigstens einen starken Säure bildet, bezüglich der Molmenge an $CaCO_3$, insgesamt zwischen 0,01 und 1,9 beträgt.
18. Wässrige Mineral- und/oder Füllstoff- und/oder Pigmentsuspension mit einem hohen Feststoffgehalt nach einem der vorhergehenden Ansprüche, bei der die wässrige Suspension mit einem hohen Feststoffgehalt ferner Aluminiumhydroxid und/oder Magnesiumhydroxid umfasst.
19. Wässrige Mineral- und/oder Füllstoff- und/oder Pigmentsuspension mit einem hohen Feststoffgehalt nach einem der vorhergehenden Ansprüche, bei der die wässrige Suspension mit einem hohen Feststoffgehalt eine positive Ladungsdichte bei pH 5 aufweist, bevorzugt von wenigstens +0,1 C/g bei pH 5, bevorzugter von wenigstens +0,5

C/g bei pH 5, noch bevorzugter von wenigstens +1 C/g bei pH 5, und am meisten bevorzugt von wenigstens +1,5 C/g bei pH 5.

20. Verfahren zur Herstellung einer wässrigen Mineral- und/oder Füllstoff- und/oder Pigmentsuspension mit einem hohen Feststoffgehalt, wie in einem der Ansprüche 1 bis 19 definiert, umfassend die Schritte:

a) Bereitstellen von einer wässrigen Suspension, die wenigstens ein Calciumcarbonat enthaltendes Material umfasst, wie in einem der Ansprüche 1 bis 7 definiert, bei der das Calciumcarbonat enthaltende Material eine Ladungsdichte zwischen +2 und -2 C/g bei pH 9 aufweist,

b) Bereitstellen von

i) wenigstens einer starken Säure, ausgewählt aus der Gruppe bestehend aus Säuren mit einem pK_a -Wert kleiner oder gleich 0 bei +23°C, wie in einem der Ansprüche 1 oder 9 definiert, und/oder

ii) wenigstens einem Salz von wenigstens einer starken Säure, wobei die wenigstens eine starke Säure, die das wenigstens eine Salz von wenigstens einer starken Säure bildet, ausgewählt ist aus der Gruppe bestehend aus Säuren mit einem pK_a -Wert kleiner oder gleich 0 bei +23°C, wie in einem der Ansprüche 1, 8 oder 9 definiert,

c) Zugabe der wenigstens einen starken Säure und/oder des wenigstens einen Salzes von wenigstens einer starken Säure aus Schritt b) zu der wässrigen Suspension, die wenigstens ein Calciumcarbonat enthaltendes Material umfasst, aus Schritt a),

d) gegebenenfalls Vermahlen der wässrigen Suspension, die wenigstens ein Calciumcarbonat enthaltendes Material umfasst, aus Schritt a) vor und/oder während und/oder nach Schritt c),

wobei die wässrige Suspension mit einem hohen Feststoffgehalt nach Schritt c) und/oder d)

i) einen Feststoffgehalt von wenigstens 50 Gew.-% aufweist, bezogen auf das Gesamtgewicht der wässrigen Suspension mit einem hohen Feststoffgehalt,

ii) eine Brookfield-Viskosität bei 100 U/min von $\leq 1\,000$ mPa·s bei einer Temperatur von -5°C aufweist,

iii) einen pH von < 6 bei +23°C aufweist, und

iv) eine Leitfähigkeit zwischen 10 und 100 mS/cm bei -5°C und bei +23°C aufweist, und

wobei die wässrige Suspension mit einem hohen Feststoffgehalt das wenigstens eine Salz von wenigstens einer starken Säure in einer Menge von 1 bis 20 Gew.-% umfasst, bezogen auf das Gesamtgewicht der wässrigen Suspension mit einem hohen Feststoffgehalt.

21. Verfahren nach Anspruch 20, wobei das Verfahren ferner Schritt e) umfasst, bei dem wenigstens eine mittelstarke Säure bereitgestellt wird, ausgewählt aus der Gruppe bestehend aus Säuren mit einem pK_a -Wert zwischen 0 und 2,5 bei +23°C, bevorzugt ist die wenigstens eine mittelstarke Säure ausgewählt aus H_2SO_3 , HSO_4^- , H_3PO_4 , Oxalsäure und Gemischen davon, und/oder wenigstens eine schwache Säure, ausgewählt aus der Gruppe bestehend aus Säuren mit einem pK_a -Wert zwischen $> 2,5$ und 6,0 bei +23°C, bevorzugt ist die wenigstens eine schwache Säure ausgewählt aus Zitronensäure und/oder Weinsäure.

22. Verfahren nach Anspruch 21, wobei das Verfahren ferner Schritt f) umfasst, bei dem die wässrige Suspension, die wenigstens ein Calciumcarbonat enthaltendes Material umfasst, aus Schritt a) mit der wenigstens einen mittelstarken Säure und/oder wenigstens einen schwachen Säure aus Schritt e) während und/oder nach Schritt c), und/oder während und/oder nach dem optionalen Schritt d) in Kontakt gebracht wird.

23. Verfahren nach einem der Ansprüche 20 bis 22, bei dem Schritt c) und/oder Schritt d) und/oder Schritt f) bei einer Temperatur zwischen +5°C und +99°C ausgeführt wird bzw. werden, bevorzugt zwischen +20°C und +85°C, und am meisten bevorzugt zwischen +20°C und +50°C, und am meisten bevorzugt zwischen +50°C und +85°C.

24. Verfahren nach einem der Ansprüche 20 bis 23, wobei das Verfahren ferner Schritt g) umfasst, bei dem die erhaltene wässrige Mineral- und/oder Füllstoff- und/oder Pigmentsuspension mit einem hohen Feststoffgehalt konzentriert wird.

25. Verfahren nach einem der Ansprüche 20 bis 24, wobei das Verfahren ferner das Trocknen der erhaltenen wässrigen Mineral- und/oder Füllstoff- und/oder Pigmentsuspension mit einem hohen Feststoffgehalt umfasst.

26. Calciumcarbonat enthaltendes Material, erhältlich durch Trocknen der wässrigen Mineral- und/oder Füllstoff- und/oder Pigmentsuspension mit einem hohen Feststoffgehalt gemäss einem der Ansprüche 1 bis 19.
27. Verwendung der wässrigen Mineral- und/oder Füllstoff- und/oder Pigmentsuspension mit einem hohen Feststoffgehalt gemäss einem der Ansprüche 1 bis 19 und/oder des Calciumcarbonat enthaltenden Materials gemäss Anspruch 26 in Papierherstellungs-, Papierbeschichtungs-, Kunststoff-, Agrarindustrie- und/oder Farbanwendungen.
28. Verwendung der wässrigen Mineral- und/oder Füllstoff- und/oder Pigmentsuspension mit einem hohen Feststoffgehalt gemäss einem der Ansprüche 1 bis 19 und/oder des Calciumcarbonat enthaltenden Materials gemäss Anspruch 26 als Füllstoff in Papier.
29. Verwendung nach Anspruch 27, bei der die wässrige Mineral- und/oder Füllstoff- und/oder Pigmentsuspension mit einem hohen Feststoffgehalt und/oder das Calciumcarbonat enthaltende Material als ein Träger für Digitaldruck verwendet wird, bevorzugt Tintenstrahldruck, oder für Flexodruck, Tiefdruck- und/oder Offsetdruck, am meisten bevorzugt für Tintenstrahldruck mit schwarzer Tinte.
30. Streichfarbformulierung, umfassend die wässrige Mineral- und/oder Füllstoff- und/oder Pigmentsuspension mit einem hohen Feststoffgehalt gemäss einem der Ansprüche 1 bis 19 und/oder das Calciumcarbonat enthaltende Material gemäss Anspruch 26 und ein natürliches und/oder synthetisches Bindemittel, wobei das Bindemittel bevorzugt besteht aus Styrol-Butadien, Styrol-Acrylat, Polyvinylacetat, Polyvinylalkohol, Stärke oder Gemischen davon, und am meisten bevorzugt enthält oder besteht das Bindemittel aus Polyvinylalkohol.

Revendications

1. Suspension aqueuse de minéral et/ou charge et/ou pigment riche en solides dans un environnement à pH acide comprenant :
 - a) au moins une substance contenant du carbonate de calcium comprenant des particules contenant du carbonate de calcium, et
 - b) au moins un sel d'au moins un acide fort, l'acide fort formant le sel d'au moins un acide fort étant choisi dans le groupe constitué par les acides ayant une valeur de pK_a inférieure ou égale à zéro à +23 °C,la suspension aqueuse riche en solides ayant
 - i) une teneur en solides d'au moins 50 % en poids, par rapport au poids total de la suspension aqueuse riche en solides,
 - ii) une viscosité de Brookfield à 100 tr/min \leq 1000 mPas à une température de -5 °C,
 - iii) un pH < 6 à +23 °C, et
 - iv) une conductivité comprise entre 10 et 100 mS/cm à -5 °C et à +23 °C, etla suspension aqueuse riche en solides comprenant le sel d'au moins un acide fort en une quantité de 1 à 20 % en poids, par rapport au poids total de la suspension aqueuse riche en solides.
2. Suspension aqueuse de minéral et/ou charge et/ou pigment riche en solides selon la revendication 1, dans laquelle les particules contenant du carbonate de calcium de la substance contenant du carbonate de calcium sont choisies parmi le carbonate de calcium naturel, le carbonate de calcium précipité ou des mélanges de ceux-ci.
3. Suspension aqueuse de minéral et/ou charge et/ou pigment riche en solides selon la revendication 1 ou 2, dans laquelle les particules contenant du carbonate de calcium de la substance contenant du carbonate de calcium ont une granulométrie moyenne en poids d_{50} de 0,1 à 50 μm , de préférence de 0,25 à 50 μm , plus préférablement de 0,3 à 5 μm , et de manière préférée entre toutes de 0,4 à 3 μm .
4. Suspension aqueuse de minéral et/ou charge et/ou pigment riche en solides selon l'une quelconque des revendications précédentes, dans laquelle les particules contenant du carbonate de calcium de la substance contenant du carbonate de calcium ont une surface spécifique de 0,1 m^2/g à 200 m^2/g , de préférence de 0,1 m^2/g à 50 m^2/g et plus préférablement de 0,1 m^2/g à 20 m^2/g , mesurée selon la méthode BET et en utilisant de l'azote.
5. Suspension aqueuse de minéral et/ou charge et/ou pigment riche en solides selon l'une quelconque des revendi-

cations précédentes, dans laquelle la suspension aqueuse riche en solides comprend la substance contenant du carbonate de calcium en une quantité d'au moins 50 % en poids, de préférence de 50 à 82 % en poids, plus préférablement de 55 à 82 % en poids, encore plus préférablement de 60 à 78 % en poids et de manière préférée entre toutes de 65 à 78 % en poids, par rapport au poids total de la suspension aqueuse riche en solides.

6. Suspension aqueuse de minéral et/ou charge et/ou pigment riche en solides selon l'une quelconque des revendications précédentes, dans laquelle la substance contenant du carbonate de calcium comprend au moins un polymère en peigne, de préférence, la surface des particules contenant du carbonate de calcium de la substance contenant du carbonate de calcium est revêtue avec le polymère en peigne.
7. Suspension aqueuse de minéral et/ou charge et/ou pigment riche en solides selon l'une quelconque des revendications précédentes, dans laquelle la substance contenant du carbonate de calcium comprend un polymère en peigne ayant une viscosité intrinsèque comprise dans la plage allant de 5 à 99 ml/g, de préférence dans la plage allant de 10 à 80 ml/g et de manière préférée entre toutes dans la plage allant de 10 à 50 ml/g.
8. Suspension aqueuse de minéral et/ou charge et/ou pigment riche en solides selon l'une quelconque des revendications précédentes, dans laquelle le sel d'au moins un acide fort comprend un cation divalent et/ou trivalent, de préférence le cation divalent est choisi dans le groupe constitué par le calcium, le magnésium, le strontium et des mélanges de ceux-ci et/ou le cation trivalent est de préférence l'aluminium.
9. Suspension aqueuse de minéral et/ou charge et/ou pigment riche en solides selon l'une quelconque des revendications précédentes, dans laquelle l'acide fort formant le sel d'au moins un acide fort est choisi dans le groupe constitué par l'acide chlorhydrique, l'acide nitrique et des mélanges de ceux-ci.
10. Suspension aqueuse de minéral et/ou charge et/ou pigment riche en solides selon l'une quelconque des revendications précédentes, dans laquelle la suspension aqueuse riche en solides comprend au moins un polymère en peigne en une quantité de 0,01 à 5 % en poids, par rapport au poids total sec de la substance contenant du carbonate de calcium dans la suspension, de préférence de 0,05 à 4 % en poids, plus préférablement de 0,1 à 3 % en poids, encore plus préférablement de 0,2 à 2 % en poids, et de manière préférée entre toutes de 0,25 à 1,5 % en poids ou de 0,5 à 1,25 % en poids.
11. Suspension aqueuse de minéral et/ou charge et/ou pigment riche en solides selon l'une quelconque des revendications précédentes, dans laquelle la suspension aqueuse riche en solides a une teneur en solides de 50 à 82 % en poids, de préférence de 55 à 82 % en poids, plus préférablement de 60 à 78 % en poids et de manière préférée entre toutes de 65 à 78 % en poids, par rapport au poids total de la suspension aqueuse riche en solides.
12. Suspension aqueuse de minéral et/ou charge et/ou pigment riche en solides selon l'une quelconque des revendications précédentes, dans laquelle la suspension aqueuse riche en solides a une viscosité de Brookfield à 100 tr/min de 25 à 1000 mPas à une température de -5 °C, de préférence de 25 à 700 mPas à -5 °C, plus préférablement de 25 à 500 mPas à -5 °C et de manière préférée entre toutes de 50 à 300 mPas à -5 °C.
13. Suspension aqueuse de minéral et/ou charge et/ou pigment riche en solides selon l'une quelconque des revendications précédentes, dans laquelle la suspension aqueuse riche en solides a un pH compris entre 4 et < 6 à +23 °C, de préférence un pH compris entre 4,5 et < 6 à +23 °C et de préférence un pH compris entre 5 et < 6 à +23 °C.
14. Suspension aqueuse de minéral et/ou charge et/ou pigment riche en solides selon l'une quelconque des revendications précédentes, dans laquelle la suspension aqueuse riche en solides a une conductivité comprise entre 20 mS/cm et 100 mS/cm mesurée à -5 °C et +23 °C et de préférence comprise entre 30 mS/cm et 100 mS/cm mesurée à -5 °C et +23 °C.
15. Suspension aqueuse de minéral et/ou charge et/ou pigment riche en solides selon l'une quelconque des revendications précédentes, dans laquelle la suspension aqueuse riche en solides comprend en outre au moins un produit réactionnel de la substance contenant du carbonate de calcium avec au moins un acide moyennement fort et/ou au moins un produit réactionnel de la substance contenant du carbonate de calcium avec au moins un acide faible.
16. Suspension aqueuse de minéral et/ou charge et/ou pigment riche en solides selon la revendication 16, dans laquelle l'acide moyennement fort formant le ou les produits réactionnels de la substance contenant du carbonate de calcium est choisi dans le groupe constitué par les acides ayant une valeur de pK_a comprise entre 0 et 2,5 à +23 °C, de

préférence l'acide moyennement fort est choisi parmi H_2SO_3 , HSO_4^- , H_3PO_4 , l'acide oxalique et des mélanges de ceux-ci et/ou l'acide faible formant le ou les produits réactionnels de la substance contenant du carbonate de calcium est choisi dans le groupe constitué par les acides ayant une valeur de pK_a comprise entre $>2,5$ et 6 à $+23^\circ\text{C}$, de préférence l'acide faible est choisi parmi l'acide citrique, l'acide tartrique et des mélanges de ceux-ci.

17. Suspension aqueuse de minéral et/ou charge et/ou pigment riche en solides selon l'une quelconque des revendications précédentes, dans laquelle la quantité molaire de la somme, exprimée par les ions H_3O^+ générés, de l'acide moyennement fort formant le ou les produits réactionnels de la substance contenant du carbonate de calcium et/ou de l'acide faible formant le ou les produits réactionnels de la substance contenant du carbonate de calcium et de l'acide fort formant le sel d'au moins un acide fort par rapport à la quantité molaire de CaCO_3 est comprise entre $0,01$ et $1,9$ au total.

18. Suspension aqueuse de minéral et/ou charge et/ou pigment riche en solides selon l'une quelconque des revendications précédentes, dans laquelle la suspension aqueuse riche en solides comprend en outre de l'hydroxyde d'aluminium et/ou de l'hydroxyde de magnésium.

19. Suspension aqueuse de minéral et/ou charge et/ou pigment riche en solides selon l'une quelconque des revendications précédentes, dans laquelle la suspension aqueuse riche en solides a une densité de charge positive à pH 5 , de préférence d'au moins $+0,1$ C/g à pH 5 , plus préférablement d'au moins $+0,5$ C/g à pH 5 , encore plus préférablement d'au moins $+1$ C/g à pH 5 et de manière préférée entre toutes d'au moins $+1,5$ C/g à pH 5 .

20. Procédé de production d'une suspension aqueuse de minéral et/ou charge et/ou pigment riche en solides selon l'une quelconque des revendications 1 à 19, comprenant les étapes consistant à

- a) fournir une suspension aqueuse comprenant au moins une substance contenant du carbonate de calcium, tel que définie selon l'une quelconque des revendications 1 à 7, la substance contenant du carbonate de calcium ayant une densité de charge comprise entre $+2$ et -2 C/g à pH 9
- b) fournir

- i) au moins un acide fort choisi dans le groupe constitué par les acides ayant une valeur de pK_a inférieure ou égale à zéro à $+23^\circ\text{C}$ tel que défini selon l'une quelconque des revendications 1 ou 9, et/ou
- ii) au moins un sel d'un acide fort, l'acide fort formant le sel d'au moins un acide fort étant choisi dans le groupe constitué par les acides ayant une valeur de pK_a inférieure ou égale à zéro à $+23^\circ\text{C}$ tel que défini selon l'une quelconque des revendications 1, 8 ou 9,

- c) ajouter l'acide fort et/ou le sel d'au moins un acide fort de l'étape b) à la suspension aqueuse comprenant au moins une substance contenant du carbonate de calcium de l'étape a),
- d) broyer facultativement la suspension aqueuse comprenant au moins une substance contenant du carbonate de calcium de l'étape a) avant et/ou pendant et/ou après l'étape c),

la suspension aqueuse riche en solides après l'étape c) et/ou d) ayant

- i) une teneur en solides d'au moins 50% en poids, par rapport au poids total de la suspension aqueuse riche en solides,
- ii) une viscosité de Brookfield à 100 tr/min ≤ 1000 mPas à une température de -5°C ,
- iii) un pH < 6 à $+23^\circ\text{C}$, et
- iv) une conductivité comprise entre 10 et 100 mS/cm à -5°C et à $+23^\circ\text{C}$, et

la suspension aqueuse riche en solides comprenant le sel d'au moins un acide fort en une quantité de 1 à 20% en poids, par rapport au poids total de la suspension aqueuse riche en solides.

21. Procédé selon la revendication 20, le procédé comprenant en outre l'étape e) consistant à fournir au moins un acide moyennement fort choisi dans le groupe constitué par les acides ayant une valeur de pK_a comprise entre 0 et $2,5$ à $+23^\circ\text{C}$, de préférence l'acide moyennement fort est choisi parmi H_2SO_3 , HSO_4^- , H_3PO_4 , l'acide oxalique et des mélanges de ceux-ci et/ou au moins un acide faible choisi dans le groupe constitué par les acides ayant une valeur de pK_a comprise entre $>2,5$ et 6 à $+23^\circ\text{C}$, de préférence l'acide faible est choisi parmi l'acide citrique et/ou l'acide tartrique.

22. Procédé selon la revendication 21, le procédé comprenant en outre l'étape f) consistant à mettre en contact la suspension aqueuse comprenant au moins une substance contenant du carbonate de calcium de l'étape a) avec au moins un acide moyennement fort et/ou au moins un acide faible de l'étape e) pendant et/ou après l'étape c), et/ou pendant et/ou après l'étape d) facultative.
23. Procédé selon l'une quelconque des revendications 20 à 22, dans lequel l'étape c) et/ou l'étape d) et/ou l'étape f) est réalisée à une température comprise entre +5 °C et +99 °C, de préférence comprise entre +20 °C et +85 °C et de manière préférée entre toutes comprise entre +20 °C et +50 °C et de manière préférée entre toutes comprise entre +50 °C et +85 °C.
24. Procédé selon l'une quelconque des revendications 20 à 23, le procédé comprenant en outre l'étape g) consistant à concentrer la suspension aqueuse de minéral et/ou charge et/ou pigment riche en solides obtenue.
25. Procédé selon l'une quelconque des revendications 20 à 24, le procédé consistant en outre à sécher la suspension aqueuse de minéral et/ou charge et/ou pigment riche en solides.
26. Substance contenant du carbonate de calcium pouvant être obtenue par séchage de la suspension aqueuse de minéral et/ou charge et/ou pigment riche en solides selon l'une quelconque des revendications 1 à 19.
27. Utilisation de la suspension aqueuse de minéral et/ou charge et/ou pigment riche en solides selon l'une quelconque des revendications 1 à 19 et/ou de la substance contenant du carbonate de calcium selon la revendication 26 dans la fabrication de papier, le couchage du papier, les plastiques, les applications agricoles et/ou de peinture.
28. Utilisation de la suspension aqueuse de minéral et/ou charge et/ou pigment riche en solides selon l'une quelconque des revendications 1 à 19 et/ou de la substance contenant du carbonate de calcium selon la revendication 26 en tant que charge dans le papier.
29. Utilisation selon la revendication 27, dans laquelle la suspension aqueuse de minéral et/ou charge et/ou pigment riche en solides et/ou la substance contenant du carbonate de calcium est utilisée comme support pour une impression numérique, une impression à jet d'encre préférée ou pour une impression flexographique, rotogravure et/ou offset, de manière préférée entre toutes pour une impression d'encre noire lors d'une impression à jet d'encre.
30. Formulation de sauce de couchage comprenant la suspension aqueuse de minéral et/ou charge et/ou pigment riche en solides selon l'une quelconque des revendications 1 à 19 et/ou la substance contenant du carbonate de calcium selon la revendication 26 et un liant naturel et/ou synthétique, le liant se composant de préférence de styrène-butadiène, styrène-acrylate, acétate de polyvinyle, alcool polyvinylique, amidon ou de mélanges de ceux-ci, et de manière préférée entre toutes le liant comprend ou se compose d'alcool polyvinylique.

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- WO 9632448 A [0004]
- WO 9632449 A [0005]
- US 4367207 A [0006]
- EP 0406662 A [0007] [0008]
- EP 1982759 A1 [0009]
- EP 2264108 A1 [0010]
- EP 2264109 A1 [0011]
- US 5043017 A [0013]
- US 4219590 A [0014]
- US 5230734 A [0015]
- WO 9708247 A [0015]
- WO 9714847 A [0015]
- WO 9820079 A [0016]
- US 5164006 A [0016]
- US 20090199741 A1 [0089]
- US 6387176 B1 [0089]
- EP 1136508 A1 [0089]
- EP 1138697 A1 [0089]
- EP 1189955 A1 [0089]
- US 6946510 B1 [0089]
- US 7514488 B1 [0089]
- EP 0736553 A1 [0089]

**Magas szilárdanyag-tartalmú vizes ásvány és/vagy töltőanyag és/vagy pigment
savas pH-jú közegben**

SZABADALMI IGÉNYPONTOK

1. Magas szilárdanyag-tartalmú vizes ásvány és/vagy töltőanyag és/vagy pigment savas pH-jú közegben, amely magában foglal:

- a) legalább egy kalcium-karbonát-tartalmú anyagot, amely kalcium-karbonátot tartalmazó részecskéket tartalmaz, és
- b) legalább egy erős sav legalább egy sóját, ahol a legalább egy erős savat, amely a legalább egy erős sav legalább egy sóját képezi olyan savak csoportjából választjuk, amelyeknek pK_a értéke 23°C -on kisebb mint zero vagy ezzel egyenlő,

ahol a magas szilárdanyag-tartalmú vizes szuszpenzió

- i) szilárdanyag-tartalma, a magas szilárdanyag-tartalmú vizes szuszpenzió teljes tömegét véve alapul, legalább 50 tömeg%,
- ii) -5°C -on mért Brookfield-viszkozitása 100 rpm-nél ≤ 1000 mPas
- iii) 23°C -on mért pH-ja < 6 , és
- iv) vezetőképessége -5°C -on és $+23^\circ\text{C}$ -on 10 és 100 mS/cm közötti, és ahol a magas szilárdanyag-tartalmú vizes szuszpenzió a legalább egy erős sav legalább egy erős sóját, a magas szilárdanyag-tartalmú vizes szuszpenzió teljes tömegét véve alapul, 1-20 tömeg% mennyiségben tartalmazza.

2. Az 1. igénypont szerinti magas szilárdanyag-tartalmú vizes ásvány és/vagy töltőanyag és/vagy pigment, amelyben a legalább egy kalcium-karbonát-tartalmú anyag kalcium-karbonát tartalmú részecskéit a természetes kalcium-karbonát, kicsapott kalcium-karbonát vagy ezek keverékei közül választjuk.

3. Az 1. vagy 2. igénypont szerinti magas szilárdanyag-tartalmú vizes ásvány és/vagy töltőanyag és/vagy pigment, amelyben a legalább egy kalcium-karbonát-tartalmú anyag kalcium-karbonát tartalmú részecskéinek d_{50} súlyátlagolt részecske-mérete 0,1-50 μm , előnyösen 0,25-50 μm , előnyösebben 0,3-5 μm , legelőnyösebben 0,4-3 μm .

4. Az előző igénypontok egyike szerinti magas szilárdanyag-tartalmú vizes ásvány és/vagy töltőanyag és/vagy pigment, amelyben a legalább egy kalcium-karbonát-tartalmú anyag kalcium-karbonát tartalmú részecskéinek jellemző felületfel-

színe, nitrogént és a BET-módszer alkalmazásával mérve, $0,1 \text{ m}^2/\text{g}$ és $200 \text{ m}^2/\text{g}$ közötti, előnyösen $0,1 \text{ m}^2/\text{g}$ és $50 \text{ m}^2/\text{g}$ közötti, és előnyösebben $0,1 \text{ m}^2/\text{g}$ és $20 \text{ m}^2/\text{g}$ közötti.

5. Az előző igénypontok egyike szerinti magas szilárdanyag-tartalmú vizes ásvány és/vagy töltőanyag és/vagy pigment, amelyben a magas szilárdanyag-tartalmú vizes szuszpenzió a legalább egy kalcium-karbonát-tartalmú anyagot, a magas szilárdanyag-tartalmú vizes szuszpenzió teljes tömegét véve alapul, legalább 50 tömeg%, előnyösen 50-82 tömeg%, előnyösebben 55-82 tömeg%, még előnyösebben 60-78 tömeg% és legelőnyösebben 65-78 tömeg% mennyiségben tartalmazza.

6. Az előző igénypontok egyike szerinti magas szilárdanyag-tartalmú vizes ásvány és/vagy töltőanyag és/vagy pigment, amelyben a legalább egy kalcium-karbonát-tartalmú anyag tartalmaz legalább egy elágazó polimert (comb polimer), előnyösen a legalább egy kalcium-karbonát-tartalmú anyag kalcium-karbonát tartalmú részecskéinek a felülete be van vonva a legalább egy elágazó polimerrel.

7. Az előző igénypontok egyike szerinti magas szilárdanyag-tartalmú vizes ásvány és/vagy töltőanyag és/vagy pigment, amelyben a legalább egy kalcium-karbonát-tartalmú anyag tartalmaz legalább egy olyan elágazó polimert, amelynek intrinszek viszkozitása az $5\text{-}99 \text{ ml/g}$ tartományban van, előnyösen a $10\text{-}80 \text{ ml/g}$ tartományban van, és legelőnyösebben a $10\text{-}50 \text{ ml/g}$ tartományban van.

8. Az előző igénypontok egyike szerinti magas szilárdanyag-tartalmú vizes ásvány és/vagy töltőanyag és/vagy pigment, amelyben a legalább egy erős sav legalább egy sója tartalmaz egy kétértékű és/vagy háromértékű kationt, előnyösen a kétértékű kationt a kalcium, magnézium, stroncium és ezek keveréke közül választjuk, és/vagy a háromértékű kation előnyösen alumínium.

9. Az előző igénypontok egyike szerinti magas szilárdanyag-tartalmú vizes ásvány és/vagy töltőanyag és/vagy pigment, amelyben a legalább egy erős sav legalább egy sóját képező legalább egy erős savat a sósav, salétromsav és ezek keveréke által alkotott csoportból választjuk ki.

10. Az előző igénypontok egyike szerinti magas szilárdanyag-tartalmú vizes ásvány és/vagy töltőanyag és/vagy pigment, amelyben a magas szilárdanyag-tartalmú szuszpenzió tartalmaz legalább egy elágazó polimert, a szuszpenzióbeli kalcium-karbonát-tartalmú anyag teljes száraztömegét véve alapul, $0,01\text{-}5$ tömeg%, előnyösen $0,05\text{-}4$ tömeg%, előnyösebben $0,1\text{-}3$ tömeg%, még előnyösebben $0,2\text{-}2$

tömeg% és legelőnyösebben 0,25-1,5 tömeg% vagy 0,5-1,25 tömeg% mennyiségben.

11. Az előző igénypontok egyike szerinti magas szilárdanyag-tartalmú vizes ásvány és/vagy töltőanyag és/vagy pigment, amelyben a magas szilárdanyag-tartalmú szuszpenzió szilárdanyag-tartalma, a magas szilárdanyag-tartalmú szuszpenzió teljes tömegét véve alapul, 50-82 tömeg%, előnyösen 55-82 tömeg%, előnyösebben 60-78 tömeg%, és legelőnyösebben 65-78 tömeg%.

12. Az előző igénypontok egyike szerinti magas szilárdanyag-tartalmú vizes ásvány és/vagy töltőanyag és/vagy pigment, amelyben a magas szilárdanyag-tartalmú szuszpenzió Brookfield-viszkozitása 100 rpm értéknél 25-1000 mPas, -5°C hőmérsékleten, előnyösen 25-700 mPas -5°C-on, előnyösebben 25-500 mPas -5°C-on, és legelőnyösebben 50-300 mPas -5°C-on.

13. Az előző igénypontok egyike szerinti magas szilárdanyag-tartalmú vizes ásvány és/vagy töltőanyag és/vagy pigment, amelyben a magas szilárdanyag-tartalmú szuszpenzió pH-ja 4 és 6 közötti +23°C-on, előnyösen pH-ja 4,5 és 6 közötti +23°C-on, és előnyösen pH-ja 5 és 6 közötti +23°C-on.

14. Az előző igénypontok egyike szerinti magas szilárdanyag-tartalmú vizes ásvány és/vagy töltőanyag és/vagy pigment, amelyben a magas szilárdanyag-tartalmú szuszpenzió konduktivitása, -5°C-on és 23°C-on mérve, 20 mS/cm és 100 mS/cm közötti, és előnyösen -5°C-on és 23°C-on mérve, 30 mS/cm és 100 mS/cm közötti.

15. Az előző igénypontok egyike szerinti magas szilárdanyag-tartalmú vizes ásvány és/vagy töltőanyag és/vagy pigment, amelyben a magas szilárdanyag-tartalmú szuszpenzió továbbá tartalmazza a legalább egy kalcium-karbonát-tartalmú anyagnak legalább egy közepesen erős savval képzett legalább egy reakciótermékét vagy -termékeit és/vagy a legalább egy kalcium-karbonát-tartalmú anyagnak a legalább egy gyenge savval képzett legalább egy reakciótermékét vagy -termékeit.

16. A16. igénypont szerinti magas szilárdanyag-tartalmú vizes ásvány és/vagy töltőanyag és/vagy pigment, amelyben a legalább egy kalcium-karbonát-tartalmú anyagnak a legalább egy reakciótermékét vagy -termékeit képező legalább egy közepes erősségű savat olyan savak által alkotott csoportból választjuk, amelyeknek pK_a értéke +23°C-on 0 és 2,5 közötti, előnyösen a legalább egy közepesen erős savat a H_2SO_3 , HSO_4^- , H_3PO_4 , oxálsav és ezek keveréke közül választjuk ki, és/vagy a

legalább egy kalcium-karbonát-tartalmú anyagnak a legalább egy reakciótermékét vagy -termékeit képező legalább egy gyenge savat olyan savak által alkotott csoportból választjuk, amelyeknek pK_a értéke $+23^\circ\text{C}$ -on 2,5 és 6 közötti, előnyösen a legalább egy gyenge savat a citromsav, borkősav és ezek keveréke közül választjuk ki.

17. Az előző igénypontok egyike szerinti magas szilárdanyag-tartalmú vizes ásvány és/vagy töltőanyag és/vagy pigment, amelyben a legalább egy kalcium-karbonát-tartalmú anyagnak a legalább egy reakciótermékét vagy -termékeit képező legalább egy közepes erősségű sav és/vagy a legalább egy kalcium-karbonát-tartalmú anyagnak a legalább egy reakciótermékét vagy -termékeit képező legalább egy gyenge sav és a legalább egy erős sav legalább egy sóját képező legalább egy erős sav összegének, a képződött H_3O^+ ionokban kifejezett, moláris mennyisége és a CaCO_3 moláris mennyisége közötti arány összességében 0,01 és 1,9 között van.

18. Az előző igénypontok egyike szerinti magas szilárdanyag-tartalmú vizes ásvány és/vagy töltőanyag és/vagy pigment, amelyben a magas szilárdanyag-tartalmú vizes szuszpenzió továbbá tartalmaz alumínium-hidroxidot és/vagy magnézium-hidroxidot.

19. Az előző igénypontok egyike szerinti magas szilárdanyag-tartalmú vizes ásvány és/vagy töltőanyag és/vagy pigment, amelyben a magas szilárdanyag-tartalmú vizes szuszpenzió pozitív töltés sűrűsége 5-ös pH-értéken, előnyösen legalább $+0,1 \text{ C/g}$, 5-ös pH-n, előnyösebben legalább $+0,5 \text{ C/g}$, 5-ös pH-n, még előnyösebben legalább $+1 \text{ C/g}$, 5-ös pH-n, és legelőnyösebben legalább $+1,5 \text{ C/g}$, 5-ös pH-n.

20. Eljárás az 1-19. igénypontok egyike szerinti magas szilárdanyag-tartalmú vizes ásvány és/vagy töltőanyag és/vagy pigment szuszpenziójának az előállítására, amely magában foglalja a következő lépéseket:

- a) az 1-7. igénypontok bármelyikében meghatározott, legalább egy kalcium-karbonát-tartalmú anyagot tartalmazó olyan vizes szuszpenzió biztosítása, amelyben a kalcium-karbonát-tartalmú anyag töltés sűrűsége, 9-es pH-értéken $+2$ és -2 C/g között van,
- b) i) az 1-9. igénypontok bármelyikében meghatározott legalább egy olyan savnak a biztosítása, amelyet a $+23^\circ\text{C}$ -on zero vagy ennél kisebb pK_a értékű savak által alkotott csoportból választunk ki, és/vagy
- ii) az 1., 8. vagy 9. igénypontok bármelyikében meghatározott legalább egy legalább egy erős sav legalább egy sójának a biztosítása, ahol a legalább egy erős

sav legalább egy sóját képező legalább egy erős savat a $+23^{\circ}\text{C}$ -on zéró vagy ennél kisebb pK_a értékű savak által alkotott csoportból választunk ki

c) a b) lépés szerinti legalább egy erős savnak és/vagy legalább egy erős sav legalább egy sójának az a) lépés szerinti, legalább egy kalcium-karbonát-tartalmú anyagot tartalmazó vizes szuszpenzióhoz való hozzáadása,

d) az a) lépés szerinti, legalább egy kalcium-karbonát-tartalmú anyagot tartalmazó vizes szuszpenziónak a c) lépés előtti és/vagy közbeni és/vagy utáni, adott esetben megvalósított őrlése,

ahol a c) és/vagy d) lépést követően a magas szilárdanyag-tartalmú vizes szuszpenzió

i) szilárdanyag-tartalma, a magas szilárdanyag-tartalmú vizes szuszpenzió teljes tömegét véve alapul, legalább 50 tömeg%,

ii) -5°C -on mért Brookfield-viszkozitása 100 rpm-nél ≤ 1000 mPas

iii) 23°C -on mért pH-ja < 6 , és

iv) vezetőképessége -5°C -on és $+23^{\circ}\text{C}$ -on 10 és 100 mS/cm közötti, és ahol a magas szilárdanyag-tartalmú vizes szuszpenzió a legalább egy erős sav legalább egy erős sóját, a magas szilárdanyag-tartalmú vizes szuszpenzió teljes tömegét véve alapul, 1-20 tömeg% mennyiségben tartalmazza.

21. A 20. igénypont szerinti eljárás, amelyben az eljárás továbbá tartalmaz egy e) lépést, amelyben biztosítunk legalább egy közepesen erős savat, amelyet olyan savak által alkotott csoportból választunk ki, amelyeknek pK_a értéke $+23^{\circ}\text{C}$ -on 0 és 2,5 közötti, előnyösen a legalább egy közepesen erős savat a H_2SO_3 , HSO_4^- , H_3PO_4 , oxálsav és ezek keveréke közül választjuk ki, és/vagy egy gyenge savat, amelyet olyan savak által alkotott csoportból választunk ki, amelyeknek pK_a értéke $+23^{\circ}\text{C}$ -on 2,5 és 6,0 közötti, előnyösen a legalább egy gyenge savat a citromsav, borkősav és ezek keveréke közül választjuk ki.

22. A 21. igénypont szerinti eljárás, amelyben az eljárás továbbá tartalmaz egy f) lépést, amelyben az a) lépés szerinti, legalább egy kalcium-karbonát-tartalmú anyagot tartalmazó vizes szuszpenziót, a c) lépés közben és/vagy ezután, és/vagy az opcionális d) lépés közben és/vagy ezután, érintkeztetjük az e) lépés szerinti legalább egy közepesen erős savval és/vagy legalább egy gyenge savval.

23. A 20-22. igénypontok egyike szerinti eljárás, amelyben a c) lépést és/vagy a d) lépést és/vagy az f) lépést $+5^{\circ}\text{C}$ és $+99^{\circ}\text{C}$ közötti hőmérsékleten, előnyösen

+20°C és +85°C között és legelőnyösebben +20°C és +50°C között és legelőnyösebben +50°C és +85°C között valósítjuk meg.

24. A 20-23. igénypontok egyike szerinti eljárás, amelyben az eljárás továbbá magában foglal egy g) lépést, amelyben koncentráljuk a kapott magas szilárdanyag-tartalmú vizes ásvány és/vagy töltőanyag és/vagy pigment szuszpenziót.

25. A 20-24. igénypontok egyike szerinti eljárás, amelyben az eljárás továbbá magában foglalja a kapott magas szilárdanyag-tartalmú vizes ásvány és/vagy töltőanyag és/vagy pigment szuszpenzió szárítását.

26. Kalcium-karbonát tartalmú anyag, amely az 1-19. igénypontok egyike szerinti magas szilárdanyag-tartalmú ásványi és/vagy töltőanyag és/vagy pigment szuszpenzió szárításával nyerhető.

27. Az 1-19. igénypontok egyike szerinti magas szilárdanyag-tartalmú ásványi és/vagy töltőanyag és/vagy pigment szuszpenzió és/vagy a 26. igénypont szerinti kalcium-karbonát tartalmú anyagnak az alkalmazása papírgyártásban, papírbevonásban, műanyagipari, mezőgazdasági és/vagy festési alkalmazásokban.

28. Az 1-19. igénypontok egyike szerinti magas szilárdanyag-tartalmú ásványi és/vagy töltőanyag és/vagy pigment szuszpenzió és/vagy a 26. igénypont szerinti kalcium-karbonát tartalmú anyagnak az alkalmazása papírban töltőanyagként.

29. A 27. igénypont szerinti alkalmazás, amelyben a magas szilárdanyag-tartalmú vizes ásvány és/vagy töltőanyag és/vagy pigment szuszpenziót és/vagy a kalcium-karbonát tartalmú anyagot hordozóként használjuk digitális nyomtatásra, előnyösen tintasugaras nyomtatásra vagy flexo nyomtatásra, rotogravírozásra és/vagy offszet nyomtatásra, legelőnyösebben fekete tinta nyomtatásra tintasugaras nyomtatásban.

30. Bevonó színezék formuláció, amely tartalmazza az 1-19. igénypontok egyike szerinti magas szilárdanyag-tartalmú vizes ásványi és/vagy töltőanyag és/vagy pigment szuszpenziót és/vagy a 26. igénypont szerinti kalcium-karbonát tartalmú anyagot valamint egy természetes és/vagy szintetikus kötőanyagot, amely kötőanyag előnyösen sztirol-butadiénből, sztirol-akrilátból, polivinil-acetátból, polivinil-alkoholból, keményítőből vagy ezek keverékéből áll, és legelőnyösebben a kötőanyag tartalmaz polivinil-alkoholt vagy ebből áll.

A meghatalmazott:

Dr. Bódisz Árpád
szabadsáim ügyvéd
Szabadsáim Ügyvédi Iroda
1052 Budapest, Andrássy út 113.
Telefon: 463-1300 Fax: 463-1098
Email: bodisz@szig.hu