



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : C07C 51/265, 63/26	A1	(11) International Publication Number: WO 93/23359 (43) International Publication Date: 25 November 1993 (25.11.93)
(21) International Application Number: PCT/GB93/00992 (22) International Filing Date: 14 May 1993 (14.05.93) (30) Priority data: 9210832.3 21 May 1992 (21.05.92) GB 9304093.9 1 March 1993 (01.03.93) GB (71) Applicant (for all designated States except US): IMPERIAL CHEMICAL INDUSTRIES PLC [GB/GB]; Imperial Chemical House, Millbank, London SW1P 3JF (GB). (72) Inventors; and (75) Inventors/Applicants (for US only) : PENNINGTON, Alan [GB/GB]; 56 Chalford Oaks, Acklam, Middlesbrough TS5 8QG (GB). SMITH, Robert, Francis [GB/GB]; 17 Skripka Drive, Billingham, Cleveland TS22 5EZ (GB).		(74) Agents: COLLINGWOOD, Anthony, Robert et al.; ICI Group Patents Services Dept., P.O. Box 6, Shire Park, Welwyn Garden City, Hertfordshire AL7 1HD (GB). (81) Designated States: AU, BR, CA, JP, KR, RU, UA, US, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: BROMINE CATALYSED OXIDATION PROCESSES (57) Abstract In plant for the production and processing of an aromatic carboxylic acid such as terephthalic acid, at least some of the plant components (especially those exposed to an acidic reaction medium at elevated temperatures and pressures in excess of 180 °C and 8 bara respectively) are fabricated from duplex stainless steels and the conditions under which such plant components are exposed to the reaction medium are controlled to maintain a low corrosion rate.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NL	Netherlands
BE	Belgium	GN	Guinea	NO	Norway
BF	Burkina Faso	GR	Greece	NZ	New Zealand
BG	Bulgaria	HU	Hungary	PL	Poland
BJ	Benin	IE	Ireland	PT	Portugal
BR	Brazil	IT	Italy	RO	Romania
CA	Canada	JP	Japan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SK	Slovak Republic
CI	Côte d'Ivoire	LI	Liechtenstein	SN	Senegal
CM	Cameroon	LK	Sri Lanka	SU	Soviet Union
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	MC	Monaco	TG	Togo
DE	Germany	MG	Madagascar	UA	Ukraine
DK	Denmark	ML	Mali	US	United States of America
ES	Spain	MN	Mongolia	VN	Viet Nam
FI	Finland				

BROMINE CATALYSED OXIDATION PROCESSES

This invention relates to the oxidation of substituted aromatic compounds to aromatic carboxylic acids using a catalyst which comprises bromine or a bromine-containing compound. The invention has particular application in the production of terephthalic acid.

Aromatic carboxylic acids such as terephthalic acid have commonly been produced by the oxidation of substituted aromatic compounds such as p-xylene by means of molecular oxygen in a lower aliphatic monocarboxylic acid solvent (preferably having from 2 to 8, and more preferably from 2 to 6, carbon atoms, for example acetic acid) and in the presence of a catalyst comprising one or more heavy metal compounds and bromine or a bromine-containing compound.

It is widely recognised that the chemicals involved in this chemical reaction are particularly corrosive especially under the conditions of temperature and pressure usually employed to realise high yields. This necessarily leads to the extensive use of suitable corrosion resistant materials for construction of the reactor vessel and associated items of plant. Accordingly, expensive titanium and titanium alloys have figured extensively as construction materials in plant for effecting oxidation of for example p-xylene to terephthalic acid especially in circumstances where the oxidation reaction is carried out using a lower aliphatic monocarboxylic acid solvent in the presence of bromine or a bromine-containing compound. Thus, to quote from US-A-4330676 (Column 4, lines 47 to 54): "Where the catalyst contains a bromide a material must be used capable of withstanding the resulting highly corrosive reaction mixture, for example titanium, but in the absence of bromide less expensive materials such as stainless steels are suitable".

With a view to allowing the use of less expensive materials of construction such as stainless steels, proposals have been made from time to time involving modification of the reaction conditions, ie the materials employed in the oxidation reaction and/or parameters such as temperature and pressure under which the oxidation reaction is carried out. For instance, US-A-4278810 and GB-A-2094800 disclose processes for the production of terephthalic acid in which bromine is deliberately excluded from the oxidation reaction, water is used as a substitute for acetic acid and the reaction is carried out under relatively low temperature conditions.

-2-

According to one aspect of the present invention there is provided plant for the production and processing of an aromatic carboxylic acid (preferably terephthalic acid) wherein the aromatic carboxylic acid is produced by the liquid phase oxidation of a substituted aromatic compound such as paraxylene in an aqueous, lower aliphatic monocarboxylic acid reaction medium in the presence of a catalyst system comprising cobalt, manganese and bromine, characterised in that at least some of those plant components which, in use, are exposed to the reaction medium (especially those exposed at elevated temperatures and pressures in excess of 180°C and 8 bara respectively) are fabricated from duplex stainless steel.

By duplex steel, we mean a stainless steel composed of ferritic and austenitic phases, usually containing about equal parts of austenite and ferrite.

Components of the plant which are exposed to the reaction medium under the defined conditions include the reactor vessel in which said liquid phase oxidation reaction is carried out and also a first stage crystallisation vessel forming part of a series of crystallisation stages in which controlled crystallisation of the aromatic carboxylic from mother liquor is effected. The conditions prevailing in both of these vessels are particularly severe and, hitherto, it has been necessary to employ titanium and titanium alloys as the materials of construction for these vessels.

Preferably said components are fabricated from a nitrogen alloyed grade of duplex stainless steel having a molybdenum constituent and which, when exposed to a non-agitated liquid phase medium having the composition defined below at a temperature of 191°C for a duration of 14 days, exhibits a corrosion rate of no greater than 0.1 mm/year, the liquid phase medium composition being:

Acetic acid:	88.01% w/w
Water:	11.99% w/w
Bromide:	944 ppm
Cobalt:	410 ppm
Manganese:	412 ppm
Sodium	98 ppm

The above temperature and composition represents a typical temperature and composition for the reaction medium present in the first crystalliser of terephthalic acid production plant.

As used herein, the term corrosion rate is to be understood to be the corrosion rate C obtained from the following formula:

$$C = W / (S \cdot D) \times 3650 / E \quad (\text{units: mm/year})$$

5 where W is the weight loss (grams) suffered by a specimen having a surface area S (cm²) in the course of exposure to the liquid phase medium for E days, the specimen alloy having a density of D (gm/cm³).

Preferably the duplex stainless steel is one which, in the defined conditions, exhibits a corrosion rate no greater than 0.05 mm/year, more preferably no more than 0.04 mm/year and most
10 preferably no more than 0.025 mm/year.

According to a second aspect of the present invention there is provided a process for the production of an aromatic carboxylic acid, comprising oxidising an aromatic compound such as paraxylene in an aqueous, lower aliphatic monocarboxylic acid reaction medium at a
15 temperature within the range 180 to 220°C and a pressure within the range 8 to 20 bara and in the presence of an oxidation catalyst system comprising cobalt, manganese and bromine to produce said aromatic carboxylic acid, feeding mother liquor and said aromatic carboxylic acid from the oxidation reactor to a series of
20 crystalliser stages in which controlled crystallisation is effected, characterised by:

carrying out the oxidation process and/or at least said first crystallisation stage in an oxidation and/or crystallisation vessel of which those surfaces contacted by the reaction medium
25 are fabricated from a duplex stainless steel; and controlling the reaction conditions and, in particular, the water content of the reaction medium, to correspond to those for which the corrosion rate of a solution annealed duplex steel having the nominal composition specified below, when exposed to
30 liquid phase reaction medium under such conditions, does not exceed 0.15 mm/year, the said composition comprising the following constituents in the amounts specified, $\pm 5\%$:

-4-

	Carbon	0.017
	Silicon	0.21
	Manganese	0.44
	Phosphorus	0.018
5	Sulphur	0.001
	Chromium	24.74
	Nickel	6.72
	Molybdenum	3.8
	Nitrogen	0.28
10	Copper	<0.1
	Tungsten	<0.1
	Iron	Remainder

Preferably the reaction conditions are controlled to correspond to those for which the corrosion rate of a duplex steel having the defined duplex steel composition, when subject to such conditions, does not exceed 0.1, more preferably 0.05, mm/year.

Typically at least the first of said crystalliser stages is operated at a temperature and pressure greater than or equal to 180°C and 8 bara respectively,

In a more specific aspect of the invention, the reactor vessel and/or the crystalliser vessel and other components located within or associated with the reactor vessel and/or crystalliser vessel and which are exposed to liquid phase reaction medium under the defined temperature and pressure conditions are fabricated from a duplex stainless steel which, under the stated conditions, exhibits a corrosion rate no greater than 0.15 (more preferably, 0.1 and most preferably 0.05) mm/year.

Preferably the duplex stainless steel used for the fabrication of the reactor vessel and/or the first crystalliser vessel is one having a composition lying within the follow ranges:

-5-

	Carbon	0.03 max
	Silicon	2.0 max
	Manganese	2.0 max
	Phosphorus	0.04 max
5	Sulphur	0.04 max
	Chromium	24 - 26
	Nickel	5 - 8
	Molybdenum	3 - 4
	Nitrogen	0.2 - 0.3
	Tungsten	1.0 max
10	Copper	2.5 max
	Iron	Remainder

The components fabricated from duplex stainless steel may be substantially wholly fabricated from such materials; alternatively they may be fabricated from a first material which is less corrosion resistant than said duplex steel, with the duplex steel forming a lining or barrier over said less corrosion resistant material to protect the same from exposure to the corrosive fluids. For instance, the reactor vessel may be internally lined with duplex steel, the duplex steel lining being attached or bonded in any suitable fashion to a material which is less corrosion resistant, such as a carbon steel, so that the less corrosion resistant material is protected by the lining of duplex steel.

Furthermore, we do not exclude the possibility of parts of the plant and/or plant components being fabricated from two or more materials, including a duplex steel and material which has superior corrosion resistance to the duplex steel under the conditions of operation. For instance, we have found that in certain parts of the plant, such as the oxidation reactor, the chemical composition may be particularly corrosive in the vapour phase as a result of the water constituent in the vapour phase being greater than in the liquid phase. In such a case, it may be preferable to fabricate that part of the plant, eg the oxidation reactor and/or the first crystalliser vessel, in such a way that those zones exposed to the liquid phase are constructed using duplex steel (or a lining thereof) whilst those zones exposed to the vapour phase and the interface between the liquid and vapour phases are constructed using a material having superior corrosion resistance (or a lining thereof), eg titanium,

titanium alloy or a nickel-based alloy such as a suitable Hastelloy alloy.

The present invention has particular application in plant in which the oxidation process is carried out under relatively high temperature and pressure conditions in the presence of bromine and water such that the resulting crude terephthalic acid has a 4-carboxybenzaldehyde (4-CBA) content ranging from 300 to 7000 ppm relative to the crude terephthalic acid produced. Where the oxidation reaction is relatively mild such that the 4-CBA content is in the higher part of the specified range, the subsequent purification of the crude terephthalic acid may include a further oxidation reaction of an aqueous solution of the crude terephthalic acid by means of an oxidising agent such as gaseous oxygen or other agent (which need not be in the gaseous phase) so as to convert at least part of the 4-CBA content to terephthalic acid. This further oxidation reaction may be followed by a conventional hydrogenation reaction involving contacting an aqueous solution of the terephthalic acid with hydrogen under reducing conditions in order to convert remaining impurities to forms which are either tolerable in the end product and/or are soluble in the aqueous mother liquor (thereby permitting their removal by suitable separation techniques such as integrated filtration and washing using for instance a Pannevis belt filter system such as that described in Filtration & Separation, March/April 1979, Page 176 et seq).

The composition of the liquid phase mixture within the oxidation reactor vessel(s) typically comprises: 85-97 %w/w acetic acid, 3-15 %w/w water, 300-3000 ppm bromide concentration, 250-2000 ppm manganese content, 100-2000 ppm cobalt content and 0-250 ppm sodium content. Preferably the water content relative to the water/acetic acid content is from 3-10 %w/w and the cobalt and manganese contents may each be up to 750 ppm. Usually of the bromine present in the oxidation reaction, a minor proportion thereof (typically about 20% to 30%) is in the ionic form.

Surprisingly, the water content in the liquid phase mixture within the oxidation reactor has been found to be particularly important. We have found that the conditions prevailing in the vapour phase generated in the course of the oxidation reaction tend to be more severe than in the liquid phase and the main contributory factor

-7-

in this respect has been identified as the water component present in the vapour. The amount of water present in the vapour phase is governed by the amount present in the liquid phase. By limiting the amount of water present in the liquid phase, it is possible to maintain the water content in the vapour phase at a level which permits the use of duplex steels in those parts of the reactor exposed to the vapour phase in operation. Accordingly in a preferred aspect of the invention, the water content of the liquid phase mixture in the oxidation reactor is maintained at a level not exceeding 8 %w/w based on the water/acetic acid mixture, most preferably in the range 4 to 8 %w/w. In this manner, it is possible to maintain the water content of the vapour phase within a range which makes the use of duplex steels in the vapour phase zone viable.

The water content within the oxidation reactor is conveniently controlled by withdrawing vapour from the reactor, condensing monocarboxylic acid and water from the vapour, adjusting the water content of the condensed liquid and returning the condensed liquid after such adjustment to the reactor as a reflux.

A currently preferred duplex steel alloy for the fabrication of the reactor vessel and/or the first crystalliser vessel and associated components is Sandvik SAF 2507 alloy (UNS No. S32750) which is commercially available from Sandvik AB of Sandviken, Sweden. When exposed to the non-agitated liquid phase composition at 191°C for 14 days as mentioned hereinbefore, the SAF 2507 alloy was found to exhibit a corrosion rate of 0.01 mm/year. However, duplex steel alloys which are metallurgically similar and have similar compositions may be used, for instance Creusot-Loire Uranus UR52N+ alloy (UNS No. S32550) and Zeron 100 (UNS No. S32550) available from Weir Materials Services Limited of Manchester, England. The compositions of the Sandvik Type 2507, and equivalents thereof are given in Table 1 herein.

Unexpectedly, in the conditions (reaction medium composition and the stated elevated temperature and pressure conditions) typically prevailing in the oxidation reactor and the first crystalliser, Sandvik SAF 2507 alloy has been found to suffer much less corrosion than a number of higher alloyed austenitic stainless steels, including Sandvik 2RK65 alloy (UNS No. N08904), Avesta 254SMO alloy (UNS No. S31254) and Sandvik Sanicro 28 alloy (UNS No. N08028).

Moreover, Sandvik SAF 2507 duplex steel has been found, in such conditions, to exhibit significantly improved corrosion resistance over other duplex stainless steels such as Sandvik 2205 alloy and Ferralium 255 (UNS No. S32550), to the extent that the 2507 alloy possesses sufficient corrosion resistance to make it a much more viable alternative to titanium and titanium alloys in the fabrication of at least parts of the oxidation reactor and first crystalliser vessels.

Experimental evidence obtained from electrochemical noise measurements of corrosion rate demonstrates that the corrosion rate of the 2507 alloy increases as the water content of a typical oxidation reactor composition increases but, if the water content is maintained within the range of 4 to 8 %w/w in the liquid phase, the increased water content in the vapour phase can be kept within limits consistent with corrosion rates that can be tolerated, ie below 0.15 mm/year (more preferably 0.1, and most preferably, 0.05 mm/year). Electrochemical noise measurements also indicated that variation in oxidation reactor temperature (over the range 180 to 220°C) and bromine content (over the range 1000 to 2600 ppm) are relatively less important factors as far as corrosion rate is concerned. The technique of electrochemical noise measurement of corrosion rates is well-known - see for example Paper No. 223 entitled "Electrochemical Noise Techniques For Determining Corrosion Rates And Mechanisms" by A N Rothwell et al, from Corrosion 92, the NACE Annual Conference and Corrosion Show available from NACE Products Division, PO Box 218340, Houston, Texas 77218, USA.

A typical plant for the production of terephthalic acid further comprises a product recovery section, a solvent recovery section, a dehydration section and a catalyst removal/recovery section; in each of these sections processes are carried out in environments involving at least hot acetic acid and water and, in most cases, bromide, cobalt, manganese, and possibly sodium constituents, at various temperatures and pressures. Certain processes are carried out in the presence of acetic acid and water but under less severe temperature and pressure conditions and lower bromine content. In these cases, whilst conventional practice has been to employ titanium or titanium alloy as the material of construction, in accordance with the present invention a duplex stainless steel having suitable corrosion

resistance may be employed. Because the conditions are less severe however, such parts of the plant may be fabricated, in part or substantially wholly, of a duplex stainless steel such as Sandvik 2205 alloy (UNS No. S31803) which, though we do not exclude it as a possible material of construction for the oxidation reactor and first crystalliser vessel (and associated components such as overhead vessels, heat exchangers, vapour lift and reflux return systems, and associated piping, pumps, valvage and agitation equipment), has been found to have adequate corrosion resistance when exposed to fluids comprising acetic acid and water at temperatures and pressures lower than those prevailing in the oxidation reactor and first crystalliser vessel.

The composition of the Sandvik 2205 alloy is given in Table 2. It will be appreciated that duplex stainless steels which are metallurgically equivalent, and similar in composition to Sandvik 2205 alloy, may also be employed for these less arduous duties; examples of equivalent alloys are AFNOR Z3 CND 22.05.AZ, Uranus UR45N, SS 2377 and UNS No. S31803 alloys generally.

The invention will be further illustrated by way of example only with reference to the following Examples.

EXAMPLE 1

In the laboratory, the corrosion resistance of Sandvik SAF 2507 alloy was evaluated by exposing samples of predetermined dimensions to a liquid phase medium having the composition specified which is representative of the acetic acid/water reaction medium present in the first crystalliser stage of a typical terephthalic acid production plant:

Acetic acid:water	88.01:11.99 (Zw/w)
Bromide	994 ppm
Cobalt	410 ppm
Manganese	412 ppm
Sodium	98 ppm

The samples were of rectangular configuration dimensioned 50 x 25 x 3 mm and were exposed to the liquid phase medium within an autoclave without agitation for a period of 14 days at a temperature of 191°C, which is representative of the temperature prevailing within a typical first stage crystalliser vessel.

The corrosion rate was determined from the weight loss suffered by the samples over the period of exposure and was found to be 0.01 mm/year in such conditions.

Under the same conditions, Sandvik 2205 alloy was found to have a corrosion rate of the order of 0.06 - 0.07 mm/year while, for comparison, 317L stainless steel had a corrosion rate in excess of 0.5 mm/year.

Tests were carried out to assess the corrosion resistance of a number of commercially available stainless steels when exposed to the process conditions prevailing in those parts of terephthalic acid production plant which are currently fabricated from titanium or titanium alloy. The tests involved the installation of welded corrosion coupons of the steels at appropriate locations within the plant, each coupon of stainless steel measuring 125 mm x 50 mm x 3 mm. The exposure of the coupons was in all cases in excess of 3 months and, in some cases, considerably longer. The results of these tests are of a somewhat qualitative nature since the corrosion rates measured were distorted by the occurrence of greater material loss at the weld sites (and which could be substantially reduced by the adoption of more satisfactory welding techniques well known to those skilled in the art). Nevertheless, as all of the samples tested were subject to increased material loss at the weld sites, the results do provide an indicator as to the relative merits of the materials tested.

Example 2

First crystalliser: this is one of a number of vessels in which crystallisation of terephthalic acid from mother liquor is carried out following the oxidation of paraxylene in acetic acid solvent reaction in the presence of a catalyst system comprising cobalt, manganese and bromine. The conditions prevailing in the first crystalliser are typically:

	Liquid phase region	Vapour phase region
Acetic acid: water	88:12 Zw/w	77:23 (Zw/w)
Temperature	191°C	191°C
Catalyst metals	790 ppm	Trace
Total bromide	940 ppm	130
Ionic bromine	330 ppm	Trace

-11-

Exposure to these conditions for a duration of 350 days revealed the following results:

	Alloy Type	Liquid phase corrosion	Vapour phase corrosion
		rate (mm/year)	rate (mm/year)
5	2507	0.11	0.09
	F255	>0.44	0.11
	2205	>0.4	0.10
	2RK65	>0.4	0.25
	254SMO	0.32	0.16
10	Sanicro 28	>0.4	0.12

Of these alloys, Sandvik SAF 2507, Sandvik 2205 and Ferralium 255 (F255) are all duplex alloys whilst the remainder (Sandvik 2RK65, Avesta 254SMO and Sandvik Sanicro 28 alloys) are more expensive highly alloyed austenitic stainless steels.

From the foregoing, it will be seen that in the harsh liquid phase conditions prevailing in the first crystalliser (ie high temperature and substantial bromine content), the SAF 2507 suffered much less corrosion than the others in the liquid phase conditions. In the less severe vapour phase conditions, all of the duplex steel alloys showed significantly better corrosion resistance than the highly alloyed austenitic alloys.

Example 3

A similar test was carried out in the liquid phase region of the first crystalliser for a duration of 170 days, using a coupon of SAF 2507 alloy under the following conditions:

Acetic acid: water	92:8 (Zw/w)
Temperature	191°C
Catalyst metals	630 ppm
Total bromide	750 ppm
Ionic bromine	260 ppm

In this instance, the corrosion rate was found to be 0.06 mm/year, illustrating the effect of reducing the water content and bromine content in the liquid phase.

Example 4

Another similar test was carried out in the liquid phase region of a first crystalliser for a duration of 240 days, again using a coupon of SAF 2507 Alloy under the following conditions:

-12-

Acetic acid: water 94:6 (Zw/w)
 Temperature 200°C
 Catalyst metals 690 ppm
 Total bromide 810 ppm
 Ionic bromine 280 ppm

5

In this case, the corrosion rate for the SAF 2507 alloy was found to be less than 0.01 mm/year, again illustrating the effect of maintaining a low concentration of water in the reaction medium.

Example 5

10 A coupon of SAF 2507 Alloy was installed in an oxidation reactor for producing terephthalic acid by the liquid phase oxidation of paraxylene in acetic acid solvent in the presence of a catalyst comprising cobalt, manganese and bromine. The conditions prevailing in the oxidation reactor were:

15 Acetic acid: water 93:7 (Zw/w)
 Temperature 215°C
 Catalyst metals 650 ppm
 Total bromide 770 ppm
 Ionic bromine 190 ppm

20 After exposure to these conditions for a duration of 140 days, the corrosion rate of the 2507 Alloy was found to be 0.03 mm/year.

TABLE 1

	Constituent wt/%	<u>SAF 2507</u>	
		Specification	Typical
25	Carbon	0.03 max	0.02
	Silicon	1.2	1.2
	Manganese	0.8	0.3
	Phosphorus	0.035	0.02
	Sulphur	0.02	0.002
30	Chromium	24-26	25
	Nickel	5.5-7.5	7
	Molybdenum	3.5-4	3.9
	Nitrogen	0.25-0.3	0.28
	Tungsten	-	-
35	Copper	-	-
	Iron	Remainder	Remainder

-13-

	Constituent wt/%	<u>UR52N+</u>	
		Specification	Typical
5	Carbon	0.01-0.03	0.02
	Silicon	1.0-1.75	1.2
	Manganese	0.2-0.75	0.3
	Phosphorus	0.02-0.03	0.02
	Sulphur	0.0001-0.001	0.002
10	Chromium	24-26	25
	Nickel	5.5-7.5	6.5
	Molybdenum	3.2-3.9	3.7
	Nitrogen	0.2-0.25	0.24
	Copper	1.5-2.5	1.6
15	Tungsten	-	-
	Iron	Remainder	Remainder
	Constituent wt/%	<u>Zeron 100</u>	
		Specification	Typical
20	Carbon	0.03 max	0.02
	Silicon	1.0 max	0.7
	Manganese	1.0 max	0.4
	Phosphorus	0.025 max	0.02
	Sulphur	0.03 max	<0.01
25	Chromium	24-26	25
	Nickel	6-8	7
	Molybdenum	3-4	3.7
	Nitrogen	0.2-0.3	0.25
	Copper	0.5-1.0	0.7
	Tungsten	0.5-1.0	0.6
	Iron	Remainder	Remainder

-14-

TABLE 2

	Constituent wt/%	<u>2205 Alloy</u>	
		Specification	Typical
5	Carbon	0.03 max	0.02
	Silicon	2.0 max	1.0
	Manganese	2.0 max	0.5
	Phosphorus	0.03 max	0.02
	Sulphur	0.02 max	<0.01
10	Chromium	21 - 23	22
	Nickel	4.5 - 6.5	5.5
	Molybdenum	2.5 - 3.5	3.1
	Nitrogen	0.15 - 0.17	0.17
	Copper	-	-
15	Tungsten	-	-
	Iron	Remainder	Remainder

CLAIMS

1. Plant for the production and processing of an aromatic carboxylic acid wherein the aromatic carboxylic acid is produced by the liquid phase oxidation of a substituted aromatic compound such as paraxylene
5 in an aqueous, lower aliphatic monocarboxylic acid reaction medium in the presence of a catalyst system comprising cobalt, manganese and bromine, characterised in that at least some of those plant components which, in use, are exposed to the reaction medium are fabricated from duplex stainless steel.
10
2. Plant as claimed in Claim 1 in which at least those plant components which are exposed to the reaction medium at elevated temperatures and pressures in excess of 180°C and 8 bara respectively
15 are fabricated from duplex stainless steel.
3. Plant as claimed in Claim 2 wherein said plant components which are so fabricated include a reactor vessel in which said liquid phase oxidation reaction is carried out.
- 20 4. Plant as claimed in Claim 2 in which said plant components which are so fabricated include a first stage crystallisation vessel forming part of a series of crystallisation stages in which controlled crystallisation of the aromatic carboxylic from mother liquor is effected.
25
5. Plant as claimed in any one of Claims 1 to 4 in which said components are fabricated from a nitrogen alloyed grade of duplex stainless steel having a molybdenum constituent and which, when exposed to a non-agitated liquid phase medium having the composition
30 defined below at a temperature of 191°C for a duration of 14 days, exhibits a corrosion rate of no greater than 0.1 mm/year, the liquid phase medium composition being:

-16-

	Acetic acid:	88.01% w/w
	Water:	11.99% w/w
	Bromide:	944 ppm
	Cobalt:	410 ppm
5	Manganese:	412 ppm
	Sodium	98 ppm.

6. Plant as claimed in Claim 5 in which the duplex stainless steel is one which, in the defined conditions, exhibits a corrosion rate no greater than 0.04 (more preferably no greater than 0.025) mm/year.

7. Plant as claimed in Claim 5 in which the duplex stainless steel has the following composition:

	Carbon	0.03 max
15	Silicon	2.0 max
	Manganese	2.0 max
	Phosphorus	0.04 max
	Sulphur	0.04 max
	Chromium	24 - 26
20	Nickel	5 - 8
	Molybdenum	3 - 4
	Nitrogen	0.2 - 0.3
	Tungsten	1.0 max
	Copper	2.5 max
25	Iron	Remainder

8. A process for the production of an aromatic carboxylic acid, comprising oxidising an aromatic compound such as paraxylene in an aqueous, lower aliphatic monocarboxylic acid reaction medium at a temperature within the range 180 to 220°C and a pressure within the range 8 to 20 bara and in the presence of an oxidation catalyst system comprising cobalt, manganese and bromine to produce said aromatic carboxylic acid, feeding mother liquor and said aromatic carboxylic acid from the oxidation reactor to a series of crystalliser stages in which controlled crystallisation is effected, characterised by:

carrying out the oxidation process and/or at least said first crystallisation stage in an oxidation and/or crystallisation

-17-

vessel of which those surfaces contacted by the reaction medium are fabricated from a duplex stainless steel; and controlling the reaction conditions and, in particular, the water content of the reaction medium, to correspond to those for which the corrosion rate of a solution annealed duplex steel having the nominal composition specified below, when exposed to the liquid phase reaction medium under such conditions, does not exceed 0.15 mm/year, the said composition comprising the following constituents in the amounts specified, $\pm 5\%$:

5		
10	Carbon	0.017
	Silicon	0.21
	Manganese	0.44
	Phosphorus	0.018
	Sulphur	0.001
	Chromium	24.74
15	Nickel	6.72
	Molybdenum	3.8
	Nitrogen	0.28
	Copper	<0.1
	Tungsten	<0.1
20	Iron	Remainder

9. A process as claimed in Claim 8 in which the reaction conditions are controlled to correspond to those for which the corrosion rate of a duplex steel having the defined duplex steel composition, when exposed to the liquid phase reaction medium under such conditions, does not exceed 0.1 mm/year.

10. A process as claimed in Claim 8 in which the reactor vessel and/or the crystalliser vessel and other components located within or associated with the reactor vessel and/or crystalliser vessel and which are exposed to reaction medium under the defined temperature and pressure conditions are fabricated from a duplex stainless steel which, under such conditions, exhibits a corrosion rate no greater than 0.15 mm/year.

11. A process as claimed in Claim 8 in which said corrosion rate is no greater than 0.1 mm/year.

-18-

12. A process as claimed in any one of Claims 8 to 11 in which the reaction vessel and/or crystalliser vessel and/or said components are fabricated from a first material which is less corrosion resistant than said duplex steel and in which the duplex steel forms a lining over said less corrosion resistant material.

5

13. A process as claimed in any one of Claims 8 to 11 in which the water content of the reaction medium within the oxidation reactor is maintained within the range 3 to 10% w/w relative to the total monocarboxylic acid/water content.

10

14. A process as claimed in Claim 13 in which the water content of the reaction medium within the oxidation reactor is maintained within the range 4 to 8% w/w relative to the total monocarboxylic acid/water content.

15

15. A process as claimed in any one of Claims 8 to 14 in which the water content within the oxidation reactor is controlled by withdrawing vapour from the reactor, condensing monocarboxylic acid and water from the vapour, adjusting the water content of the condensed liquid and returning the condensed liquid after such adjustment to the reactor as a reflux.

20

16. Plant or a process as claimed in any one of Claims 1 to 4 or 8 to 15 respectively in which the duplex steel is a nitrogen alloyed duplex steel having a molybdenum content.

25

17. A process for the production of an aromatic carboxylic acid, comprising oxidising an aromatic compound such as paraxylene in an aqueous, lower aliphatic monocarboxylic acid reaction medium at a temperature within the range 180 to 220°C and a pressure within the range 8 to 20 bara and in the presence of an oxidation catalyst system comprising cobalt, manganese and bromine to produce said aromatic carboxylic acid, feeding mother liquor and said aromatic carboxylic acid from the oxidation reactor to a series of crystalliser stages in which controlled crystallisation is effected, characterised by:

35

-19-

carrying out the oxidation process and/or at least said first crystallisation stage in an oxidation and/or crystallisation vessel of which those surfaces contacted by the reaction medium are fabricated from a duplex stainless steel having the following composition:

5	Carbon	0.03 max
	Silicon	2.0 max
	Manganese	2.0 max
	Phosphorus	0.04 max
	Sulphur	0.04 max
10	Chromium	24 - 26
	Nickel	5 - 8
	Molybdenum	3 - 4
	Nitrogen	0.2 - 0.3
	Tungsten	1.0 max
15	Copper	2.5 max
	Iron	Remainder; and

controlling the water content within the oxidation reaction such that the water component in the liquid phase reaction mixture is no greater than 10 %w/w relative to the water/monocarboxylic acid content.

18. A process as claimed in Claim 17 in which the water component in the liquid phase reaction mixture is no greater than 8 %w/w.

19. Plant or a process as claimed in any one of Claims 1 to 4 or 8 to 18 respectively in which the oxidation reaction is carried out under conditions resulting in the production of crude terephthalic acid having a 4-CBA content within the range 300 to 7000 ppm relative to the crude terephthalic acid produced.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 93/00992

I. CLASSIFICATION OF SUBJECT MATTER (If several classification symbols apply, indicate all) ⁶		
According to International Patent Classification (IPC) or to both National Classification and IPC		
Int.Cl. 5 C07C51/265; C07C63/26		
II. FIELDS SEARCHED		
Minimum Documentation Searched ⁷		
Classification System	Classification Symbols	
Int.Cl. 5	C07C	
Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in the Fields Searched ⁸		
III. DOCUMENTS CONSIDERED TO BE RELEVANT⁹		
Category ¹⁰	Citation of Document, ¹¹ with indication, where appropriate, of the relevant passages ¹²	Relevant to Claim No. ¹³
X	PATENT ABSTRACTS OF JAPAN no. 1988 (C-78) & JP,A,53 071 019 (NIPPON GOSEI KAGAKU KOGYO K.K.) 24 June 1978 see abstract	1-3,5,6, 8-11,19
A	GB,A,832 995 (I.C.I.) 21 April 1960 see claims 1-13	1,8,17, 19
¹⁰ Special categories of cited documents: "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "&" document member of the same patent family		
IV. CERTIFICATION		
Date of the Actual Completion of the International Search		Date of Mailing of this International Search Report
09 AUGUST 1993		17. 08. 93
International Searching Authority		Signature of Authorized Officer
EUROPEAN PATENT OFFICE		KLAG M.J.

GB 9300992
SA 74211

09/08/9:

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
GB-A-832995		None	