



(51) International Patent Classification:

C07C 7/20 (2006.01) *C09K 15/18* (2006.01)
C08F 2/40 (2006.01) *C09K 15/24* (2006.01)

(21) International Application Number:

PCT/IB2013/056787

(22) International Filing Date:

21 August 2013 (21.08.2013)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

2465/MUM/2012 24 August 2012 (24.08.2012) IN

(71) Applicant: **DORF KETAL CHEMICALS (INDIA) PRIVATE LIMITED** [IN/IN]; Dorf Ketal Tower, D'Monte Street, Orlem, Malad (W), Mumbai - 400 064, Maharashtra (IN).

(72) Inventor; and

(71) Applicant (for US only): **SUBRAMANIYAM, Mahesh** [IN/IN]; Dorf Ketal Tower, D'Monte Street, Orlem, Malad (W), Mumbai - 400 064, Maharashtra (IN).

(74) Agents: **DR. MEHTA, Ramesh Kumar** et al.; Mehta & Mehta Associates, Mehta House, B – 474, Sushant Lok – I, Sector 27, Gurgaon 122 002 (IN).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY,

BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii))
- of inventorship (Rule 4.17(iv))

Published:

- with international search report (Art. 21(3))



(54) Title: COMPOSITION OF QUINONE METHIDE DERIVATIVES AND AMINES FOR CONTROL AND INHIBITION OF POLYMERIZATION OF MONOMERS, AND METHOD OF PREPARATION AND USE THEREOF

(57) Abstract: The present invention relates to additive composition for control and inhibition of polymerization of monomers including styrene, wherein the composition consists of: (a) one or more of quinone methide derivatives; and CHARACTERIZED IN THAT the composition further comprises: (b) one or more of tertiary amines, wherein said tertiary amine is selected from a group consisting of: (i) tri isopropanol amine (TIPA), (ii) N,N,N',N'-Tetrakis (2-hydroxyethyl) ethylene-diamine) (THEED), and (iii) mixture thereof. In one embodiment, the present invention relates to method of preparation thereof and uses thereof, and a method for controlling and inhibiting polymerization of monomers including styrene.

Title of the invention:

Composition of quinone methide derivatives and amines for control and inhibition of polymerization of monomers, and method of preparation and use thereof.

Field of the invention:

The present invention relates to additive composition comprising quinone methide (QM) derivatives and amines for control and inhibition of polymerization of aromatic vinyl monomers (may be referred to as ‘monomer’ or ‘monomers’ or ‘monomer stream’ or ‘monomers stream’), particularly of styrene.

In one embodiment, the present invention relates to a method of preparation of additive composition comprising quinone methide (QM) derivatives and amines for control and inhibition of polymerization of monomers, particularly of styrene.

In another embodiment, the present invention relates to a method for controlling and inhibition of polymerization of aromatic vinyl monomers including styrene by employing the additive composition comprising quinone methide (QM) derivatives and amines.

In still another embodiment, the present invention relates to use of or method of using the additive composition comprising quinone methide (QM) derivatives and amines to control and inhibit polymerization of monomers, particularly of styrene.

Background of the invention:

The polymerization of monomers, particularly of styrene during processing is a matter of concern, because it causes formation of unwanted polymers and results in loss of yield of end product and makes the process un-economical.

In the prior art use of inhibitors and retarders, and combination thereof to overcome problem of polymerization of styrene has been reported.

The problem of using the inhibitors alone is that these are to be added continuously or at regular interval, because once they are consumed, the polymerization will re-start.

The problem of using the retarders alone is that these are not very effective to reduce polymerization of styrene to a level of substantial inhibition or to the commercially acceptable level of inhibition.

The prior art discloses use of some of quinone methide (QM) derivatives including 4-benzylidene, 2,6 di tert butyl cyclohexa-2,5 dienone as polymerization inhibitor. However, the inventor has found [refer to examples – Table 1] that main problem of using the quinone methide (QM) is that it has to be used in higher amounts to achieve commercially acceptable level of inhibition, and such higher amount not only results in increase of cost of process, but also results in formation of undesired products due to unstable nature of quinone methide.

The prior art also proposes quinone methide based composition comprising quinone methide (QM) derivatives including 4-benzylidene, 2,6 di tert butyl cyclohexa-2,5 dienone and 4HT (4 hydroxy tempo 2,2,6,6-tetramethyl-1-oxide) as styrene polymerization inhibitor. However, the inventor has found that main problem of using this known composition of quinone methide is that even at higher amounts the problem of polymerization is not resolved to commercially acceptable level.

The prior art [US 7,651,635] discloses use of combination of an inhibitor and a retarder, wherein the inhibitor is “polymerization inhibitor” consisting of alkylhydroxylamine and retarder is 7-substituted quinone methide (substituted QM). The main problem of this composition is that it employs inhibitor, which are consumed continuously and get gradually depleted, and hence, the inhibitor has to be added continuously or intermittently or at least it has to be ensured that an appropriate amount of the inhibitor is maintained in the system [Col. 4, lines 7-13 of US'635].

Need of the Invention:

Therefore, there is still a need of additive composition which is not only suitable for substantial control and inhibition of polymerization of monomers including styrene, but is also required in very low dosage.

There is also a need to have a method of preparation of additive composition suitable for substantial control and inhibition of polymerization of monomers including styrene, particularly at a very low dosage.

There is also a need to have a method for controlling and inhibition of polymerization of monomers including styrene by employing the additive composition comprising quinone methide (QM) derivatives and amines, which is also required at lower dosage.

There is further a need to have a use of or method of using additive composition to substantially control and inhibit polymerization of monomers including styrene, particularly at a very low dosage.

Problem to be solved by the Invention:

Therefore, the present invention aims at providing a solution to above-described existing industrial problems by providing additive composition which is not only suitable for substantial control and inhibition of polymerization of monomers including styrene, but is also required in very low dosage.

The present invention also aims at providing a solution to above-described existing industrial problems by providing a method of preparation of additive composition suitable for substantial control and inhibition of polymerization of monomers including styrene, particularly at a very low dosage.

The present invention also aims at providing a solution to above-described existing industrial problems by providing a method for controlling and inhibition of polymerization of monomers including styrene by employing the additive composition

comprising quinone methide (QM) derivatives and amines, which is also required at a lower dosage.

The present invention also aims at providing a solution to above-described existing industrial problems by providing a use of or method of using additive composition to substantially control and inhibit polymerization of monomers including styrene, particularly at a very low dosage.

Objects of the Invention:

Accordingly, main object of the present invention is to provide additive composition which is not only suitable for substantial control and inhibition of polymerization of monomers including styrene, but is also required in a lower dosage as compared to dosage of the prior art additives for achieving the same or better level of inhibition of polymerization of monomers including styrene.

Another object of the present invention is to provide a method of preparation of the additive composition suitable for substantial control and inhibition of polymerization of monomers including styrene, particularly at a lower dosage as compared to dosage of the prior art additives for achieving the same or better level of inhibition of polymerization of monomers including styrene.

Still another object of the present invention is to provide a method for controlling and inhibition of polymerization of monomers including styrene by employing the additive composition comprising quinone methide (QM) derivatives and amines, which is to be employed at a lower dosage as compared to dosage of the prior art additives for achieving the same or better level of inhibition of polymerization of monomers including styrene.

Yet another object of the present invention is to provide use of or a method of using the additive composition to substantially control and inhibit polymerization of monomers including styrene, particularly at a lower dosage as compared to dosage of

the prior art additives for achieving the same or better level of inhibition of polymerization of monomers including styrene.

The present invention aims at providing additive composition which can give commercially acceptable level of inhibition of polymerization, that is, can reduce the polymerization of monomer including styrene even at lower active dosage as compared to dosage of the prior art additives for achieving the same or better level of inhibition of polymerization of monomers including styrene.

The present invention also aims at providing additive composition wherein amount of quinone methide (QM) derivative is substantially reduced in the additive composition, and therefore, the composition of present invention is comparatively economical. The quinone methide (QM) derivatives are expensive and not easily available.

Other objects and advantages of the present invention will become more apparent from the following description when read in conjunction with examples, which are not intended to limit scope of the present invention.

Description and Preferred Embodiments of the Invention:

With aim to overcome above-described problems of the prior art and to achieve above-described objects of the invention, the inventor has found that when a composition comprising:

- (a) one or more of quinone methide (QM) derivatives; and
- (b) one or more of preferred polymerization non-inhibiting amines

of the present invention is employed, the polymerization of monomers including styrene, surprisingly and unexpectedly, is substantially controlled and inhibited to the commercially acceptable level (as defined herein), that is, the performance of the additive consisting only of quinone methide (QM) derivative alone, or only of preferred polymerization non-inhibiting amine alone is substantially improved when a composition comprising the combination of (a) one or more of the QM derivatives and (b) one or more of the preferred polymerization non-inhibiting amines is used, which

confirms surprising, unexpected and synergistic effects of the presently provided composition. The inventor has found that the polymerization non-inhibiting amines, which have been found to have above-discussed surprising, unexpected and synergistic effects are tertiary amines, and as per inventor's findings the tertiary amine may be selected from a group consisting of:

- (i) tri isopropanol amine (TIPA),
- (ii) N,N,N',N'-Tetrakis (2-hydroxyethyl) ethylene-diamine) (THEED), and
- (iii) mixture thereof.

The inventor has further found that it is further surprising and unexpected that composition comprising the quinone methide (QM) derivative and a polymerization non-inhibiting amine, particularly a tertiary amine other than above-said tertiary amines (i), (ii), and (iii) may have effect in controlling and inhibiting the polymerization of monomers including styrene, and performance of that composition may be comparatively improved than that of performance of the additive composition consisting only of that tertiary amine, however, the performance of that composition is comparatively poorer than that of the performance of the additive composition consisting only of QM derivative alone, which also confirms surprising, unexpected and synergistic effects of the presently provided compositions.

Accordingly, in one embodiment, the present invention relates to additive composition for controlling and inhibiting polymerization of monomers including styrene, wherein the composition consists of:

- (a) one or more of quinone methide derivatives; and

CHARACTERIZED IN THAT the composition further comprises:


- (b) one or more of polymerization non-inhibiting amines, which are tertiary amines.

The term "polymerization non-inhibitor amine" means, contrary to disclosure and teachings of prior art, the amine per se is not capable of inhibiting polymerization of styrene to the (commercially) acceptable level as discussed above. It has been found that the "polymerization non-inhibiting amines" of the present invention and the comparative amines result in substantially high polymerization of about 14.64% to 17.80% polymerization of styrene as against 19.66% polymerization of styrene for


blank example run without amine (see Table 2), and therefore, the “tertiary amines” of the present invention and the comparative amines are named as “polymerization non-inhibitor amines”.

In accordance with one of the preferred embodiments of the present invention, the aliphatic tertiary amine of the present invention contains one or more hydroxyl groups, and wherein said one or more hydroxyl groups are in the alkyl chain of said tertiary amine.

In accordance with the present invention, when said aliphatic tertiary amine contains three hydroxyl groups, it is tri-isopropanol amine (TIPA) having following structural Formula – I, and when said aliphatic tertiary amine contains four hydroxyl groups, it is N,N,N’,N’-Tetrakis (2-hydroxyethyl) ethylene-diamine (THEED) having following structural formula – II.



Formula – I
(Tri-isopropanol amine [TIPA])



Formula – II
(N,N,N’,N’-Tetrakis (2-hydroxyethyl) ethylene-diamine) (THEED))

Accordingly, in another embodiment, the present invention relates to additive composition for controlling and inhibition of polymerization of aromatic vinyl monomers including styrene, wherein the composition consists of:

- (a) one or more of quinone methide derivatives; and

CHARACTERIZED IN THAT the composition further comprises:

(b) one or more of tertiary amines,

wherein said tertiary amine is selected from a group consisting of:

- (i) tri isopropanol amine (TIPA),
- (ii) N,N,N',N'-Tetrakis (2-hydroxyethyl) ethylene-diamine) (THEED), and
- (iii) mixture thereof.

Accordingly, in further embodiment, the present invention relates to additive composition for control and inhibition of polymerization of styrene, wherein the composition consists of:

(a) one or more of quinone methide derivatives; and

CHARACTERIZED IN THAT the composition further comprises:

(b) one or more of tertiary amines,

wherein said tertiary amine is tri isopropanol amine (TIPA).

Accordingly, in still another embodiment, the present invention relates to additive composition for control and inhibition of polymerization of styrene, wherein the composition consists of:

(a) one or more of quinone methide derivatives; and

CHARACTERIZED IN THAT the composition further comprises:

(b) one or more of tertiary amines,

wherein said tertiary amine is N,N,N',N'-Tetrakis (2-hydroxyethyl) ethylene-diamine) (THEED).

Accordingly, in yet another embodiment, the present invention relates to additive composition for control and inhibition of polymerization of styrene, wherein the composition consists of:

(a) one or more of quinone methide derivatives; and

CHARACTERIZED IN THAT the composition further comprises:

(b) one or more of tertiary amines,

wherein said tertiary amine is combination of:

- (i) tri isopropanol amine (TIPA), and
- (ii) N,N,N',N'-Tetrakis (2-hydroxyethyl) ethylene-diamine) (THEED).

In accordance with one of the embodiments of the present invention, the quinone methide derivative is selected from a group comprising:

- i) alkyl-(3,5-di-tert-butyl-4-oxocyclohexane-2,5-dienylidene)-cyano derivative of quinone methide;
- ii) alkyl-(3,5-di-tert-butyl-4-oxocyclohexane-2,5-dienylidene)-acid derivative of quinone methide;
- iii) alkyl-(3,5-di-tert-butyl-4-oxocyclohexane-2,5-dienylidene)-ester derivative of quinone methide; and
- iv) combination thereof.

In accordance with one of the preferred embodiments of the present invention, the quinone methide derivative is alkyl-(3,5-di-tert-butyl-4-oxocyclohexane-2,5-dienylidene)-ester derivative of quinone methide.

In accordance with one of the preferred embodiments of the present invention, the alkyl group is selected from a group comprising methyl-group, ethyl-group and propyl-group.

In accordance with one of the preferred embodiments of the present invention, the quinone methide derivative does not include 7-aryl quinone methide derivatives.

In accordance with one of the embodiments of the present invention, the quinone methide derivative and the tertiary amine are present in the present composition in a weight percent ratio, wherein the weight percent ratio is selected from the group comprising the weight percent ratio of quinone methide derivative : tertiary amine varying from

- i. about 99.99:0.01 to about 40:60,
- ii. about 99.9:0.1 to about 50:50,
- iii. about 99:1 to about 60:40,
- iv. about 95:5 to about 70:30, and
- v. about 90:10 to about 85:15.

In accordance with one of the preferred embodiments of the present invention, the polymerization of monomers including styrene, surprisingly and unexpectedly, reduces from about 5.90% when about 100 ppm of quinone methide ester derivative alone is used to about 4.3% when composition of the present invention consisting of about 100 ppm of quinone methide ester derivative and about 1 ppm of TIPA is used, i.e. when QM ester derivative and the tertiary amine are taken in a weight percent ratio of 99.01:0.99, which further reduces to 1.46% when about 100 ppm of quinone methide ester derivative and about 100 ppm of TIPA is used, i.e. when QM ester derivative and the tertiary amine are taken in a weight percent ratio of 1:1.

In accordance with another one of the preferred embodiments of the present invention, the polymerization of monomers including styrene, surprisingly and unexpectedly, substantially reduces from about 1.99% when about 150 ppm of quinone methide ester derivative alone is used to about 0.89% when composition of the present invention consisting of about 150 ppm of quinone methide ester derivative and about 0.75 ppm of TIPA is used, i.e. when QM ester derivative and the tertiary amine are taken in a weight percent ratio of 99.05:0.50, which further reduces to 0.08% when about 150 ppm of quinone methide ester derivative and about 150 ppm of TIPA is used, i.e. when QM ester derivative and the tertiary amine are taken in a weight percent ratio of 1:1.

In accordance with still another one of the preferred embodiments of the present invention, the polymerization of monomers including styrene, surprisingly and unexpectedly, reduces from about 0.90% when about 200 ppm of quinone methide ester derivative alone is used to about 0.78% when composition of the present invention consisting of about 200 ppm of quinone methide ester derivative and about 0.10 ppm of TIPA is used, i.e. when QM ester derivative and the tertiary amine are taken in a weight percent ratio of 99.95:0.05, which further reduces to 0.55% when about 200 ppm of quinone methide ester derivative and about 0.5 ppm of TIPA is used, i.e. when QM ester derivative and the tertiary amine are taken in a weight percent ratio of 99.75:0.25, which further substantially reduces to 0.07% when about 200 ppm of quinone methide ester derivative and about 30 ppm of TIPA is used, i.e. when QM ester derivative and the tertiary amine are taken in a weight percent ratio of 86.96:13.04, which further

substantially reduces to 0% when about 200 ppm of quinone methide ester derivative and about 40 ppm of TIPA is used, i.e. when QM ester derivative and the tertiary amine are taken in a weight percent ratio of 83.33:16.67.

In accordance with yet another one of the preferred embodiments of the present invention, the polymerization of monomers including styrene, surprisingly and unexpectedly, reduces from about 0.23% when about 300 ppm of quinone methide ester derivative alone is used to about 0.15% when composition of the present invention consisting of about 300 ppm of quinone methide ester derivative and about 0.10 ppm of TIPA is used, i.e. when QM ester derivative and the tertiary amine are taken in a weight percent ratio of 99.97:0.03, which substantially further reduces to 0.07% when about 300 ppm of quinone methide ester derivative and about 0.5 ppm of TIPA is used, i.e. when QM ester derivative and the tertiary amine are taken in a weight percent ratio of 99.83:0.17, which further substantially reduces to 0% when about 300 ppm of quinone methide ester derivative and about 1 ppm of TIPA is used, i.e. when QM ester derivative and the tertiary amine are taken in a weight percent ratio of 99.67:0.33.

Similar effects have been found when TIPA is replaced with THEED or when TIPA is combined with THEED.

It may be noted that in above embodiments, the polymerization of monomers including styrene has been substantially reduced, which in preferred embodiments has been reduced to less than about 2.0%, in other preferred embodiments has been reduced to less than about 1.5%, and in further preferred embodiments has been reduced to less than about 1.0%, and in still further preferred embodiments has been reduced to about 0% or 0%.

When comparing the results of the present composition with that of compositions consisting of only amine alone, these are far more superior for the present composition, i.e. the present composition is far more substantially improved than the composition consisting of only amine alone.

Therefore, the above findings confirm surprising, unexpected and synergistic effects of the presently provided compositions.

The inventor has found that if the polymerization non-inhibiting amine is selected from one or more of the following tertiary amines, then, surprisingly and unexpectedly, the efficiency of QM derivative does not improve, on the contrary, the polymerization of styrene increases, that is, the inventor has found that the polymerization of styrene, surprisingly and unexpectedly, increases when the tertiary amines of the present invention are replaced with one or more of the amines selected from a group consisting of:

- i) N,N,N',N'-Tetrakis (2-hydroxypropyl) ethylene-diamine) Quadrol®;
- ii) tetraethylenepentamine (TEPA);
- iii) triethanolamine (TEA); and
- iv) Tris(N-butylamine) (TBA).

For example, the polymerization of styrene, surprisingly and unexpectedly, increases from about 5.90% when about 100 ppm of quinone methide ester derivative alone is used to about 6.10% when composition consisting of about 100 ppm of quinone methide ester derivative and about 1 ppm of polymerization non-inhibiting amine, especially Quadrol® is used, and to about 8.38% when composition consisting of about 100 ppm of quinone methide ester derivative and about 1 ppm of polymerization non-inhibiting amine, especially tributylamine (TBA) is used, and to about 8.63% when composition consisting of about 100 ppm of quinone methide ester derivative and about 1 ppm of polymerization non-inhibiting amine, especially triethanol amine (TEA) is used.

Similarly, for example, the polymerization of styrene, surprisingly and unexpectedly, increases from about 0.90% when about 200 ppm of quinone methide ester derivative alone is used to about 1.10% when composition consisting of about 200 ppm of quinone methide ester derivative and about 5 ppm of Quadrol® is used, and increases to about 1.25% when composition consisting of about 200 ppm of quinone methide ester derivative and about 5 ppm of TBA is used, and increases to about 1.32%

when composition consisting of about 200 ppm of quinone methide ester derivative and about 5 ppm of TEA is used.

The inventor has further found that the polymerization of styrene, surprisingly and unexpectedly, increases when the tertiary amines of the present invention are replaced with one or more of nitroxide compound including 1-oxyl-2,2,6,6, tetramethylpiperidin-4-ol (or 4 Hydroxy Tempo or 4-HT).

For example, the polymerization of styrene, surprisingly and unexpectedly, increases from about 5.90% when about 100 ppm of quinone methide ester derivative alone is used to about 6.11% when composition consisting of about 100 ppm of quinone methide ester derivative and about 5 ppm of 4HT is used, and increases from about 1.99% when about 150 ppm of quinone methide ester derivative alone is used to about 2.70% when composition consisting of about 150 ppm of quinone methide ester derivative and about 5 ppm of 4HT is used, and increases from about 0.90% when about 200 ppm of quinone methide ester derivative alone is used to about 1.21% when composition consisting of about 200 ppm of quinone methide ester derivative and about 5 ppm of 4HT is used.

The inventor has further found that the polymerization of styrene, surprisingly and unexpectedly, increases even when composition consisting of quinone methide derivative and of TEPA is used.

Therefore, in accordance with one of the embodiments of the present invention, the Quadrol®, TEPA, TBA, TEA, and 4HT are excluded from scope of the present invention.

Therefore, in accordance with one of the embodiments of the present invention, the additive composition of the present invention does not comprise one or more of following amines:

- i) N,N,N',N'-Tetrakis (2-hydroxypropyl) ethylene-diamine) Quadrol®;
- ii) tetraethylenepentamine (TEPA);
- iii) triethanolamine (TEA); and

- iv) Tris(N-butylamine) (TBA).

Furthermore, in accordance with one of the embodiments of the present invention, the additive composition of the present invention does not comprise nitroxide (i.e. nitroxyl) compounds including 1-oxyl-2,2,6,6, tetramethylpiperidin-4-ol (or 4 Hydroxy Tempo or 4-HT).

However, as it can be observed, the comparison of the polymerization efficiency with the tertiary amines of the present invention confirms the surprising, unexpected and synergistic effects of the presently provided compositions.

It may be noted that as per the present invention, the QM derivatives may be prepared by any conventionally known method. For example, the QM derivatives, particularly the QM ester derivative may be prepared by a method disclosed in US patent No. 5,583,247.

In one embodiment of the present invention, the additive compositions of the present invention may be used in an amount which is selected from the group comprising the amount varying from:

- a. about 0.01 to about 2000 ppm,
- b. about 1 to about 1200 ppm,
- c. about 5 to about 1000 ppm,
- d. about 50 to about 500 ppm, and
- e. about 100 to about 300 ppm, and

which is added to the aromatic vinyl monomers stream based on weight of the monomer.

In one embodiment, the present invention relates to a method of preparation of the above-described additive composition of the present invention for controlling and inhibiting polymerization of monomers including styrene, wherein the additive composition consisting of one or more of the quinone methide derivatives and one or more of the tertiary amines is prepared by mixing one or more of the quinone methide derivatives and one or more of the tertiary amines of the present invention.

Accordingly, in one of the embodiments, the present invention relates to a method of preparation of the additive composition of the present invention for controlling and inhibiting polymerization of aromatic vinyl monomers including styrene, wherein the method comprises mixing one or more of the quinone methide derivatives and one or more of the tertiary amines of the present invention.

In accordance with one of the preferred embodiments of the present invention, the quinone methide derivatives and the tertiary amines are mixed in a weight percent ratio selected from the group comprising the weight percent ratio of quinone methide derivative : tertiary amine varying from

- i. about 99.99:0.01 to about 40:60,
- ii. about 99.9:0.1 to about 50:50,
- iii. about 99:1 to about 60:40,
- iv. about 95:5 to about 70:30, and
- v. about 90:10 to about 85:15.

In accordance with one of the preferred embodiments of the present invention, the quinone methide derivatives and the tertiary amines may be mixed directly, or after dissolving in a solvent, wherein the solvent is capable of dissolving the derivatives and the amines.

In another embodiment, the present invention relates to use of or a method of using above-described additive compositions of the present invention to control and inhibit polymerization of monomers including styrene, wherein the additive composition consists of one or more of the quinone methide derivatives and one or more of the tertiary amines of the present invention.

In accordance with the present invention, the additive compositions of the present invention may be used after mixing its components, i.e. as pre-blended composition or each ingredient of the composition may be added separately to the processing unit of styrene.

Accordingly, in one of the embodiments, the present invention also relates to use of or a method of using the additive compositions of the present invention for control and inhibition of polymerization of aromatic vinyl monomers including styrene, wherein the method comprises adding the additive composition of the present invention to a processing or manufacturing unit for styrene polymerization, wherein the additive composition consists of mixture of one or more of the quinone methide derivatives and one or more of the tertiary amines of the present invention.

Accordingly, in one embodiment, the present invention also relates to use of or a method of using the above-described additive compositions of the present invention for control and inhibition of polymerization of aromatic vinyl monomers including styrene, wherein the method comprises separately adding components of the additive composition of the present invention to a processing or manufacturing unit for styrene polymerization, wherein the additive composition consists of component a) one or more of the quinone methide derivatives and component b) one or more of the said tertiary amines of the present invention.

It may be added continuously to satisfy requirement of continuous flow of styrene in the processing or manufacturing unit. It may be added directly to the processing or manufacturing unit, or after dissolving in a suitable solvent or diluent which may include aromatic solvent or diluent. It may be added either in the beginning of process or when the manufacturing process has started.

In accordance with one of the preferred embodiments of the present invention, the quinone methide derivatives and the tertiary amines are added to the processing or manufacturing unit for styrene polymerization in a weight percent ratio selected from the group comprising the weight percent ratio of

quinone methide derivative : tertiary amine varying from

- i. about 99.99:0.01 to about 40:60,
- ii. about 99.9:0.1 to about 50:50,
- iii. about 99:1 to about 60:40,
- iv. about 95:5 to about 70:30, and
- v. about 90:10 to about 85:15.

In accordance with one of the embodiments of the present invention, the present compositions may be added in one of the following amounts selected from the group comprising:

- a. varying from about 0.01 to about 2000 ppm,
- b. varying from about 1 to about 1200 ppm,
- c. varying from about 5 to about 1000 ppm,
- d. varying from about 50 to about 500 ppm, and
- e. varying from about 100 to about 300 ppm,

to the aromatic vinyl monomers stream in the processing or manufacturing unit for styrene polymerization based on weight of the monomers.

In accordance with one of the preferred embodiments of the present invention, the quinone methide derivatives and the tertiary amines are added either separately or after mixing with each other.

In accordance with one of the preferred embodiments of the present invention, the quinone methide derivatives and the tertiary amines may also be added after mixing with a solvent which is capable of dissolving the derivatives and the amines.

In one of the embodiments, the present invention also relates to a method for controlling and inhibition of polymerization of aromatic vinyl monomers including styrene by adding the additive composition of the present invention to the monomer, or monomer stream, or monomers, or monomer stream, wherein the composition may be added in an amount as defined herein.

Accordingly, in one of the embodiments, the present invention relates to a method for controlling and inhibition of polymerization of aromatic vinyl monomers including styrene, wherein the method comprises adding the additive composition of the present invention to a processing or manufacturing unit for styrene polymerization, wherein the additive composition consists of one or more of the quinone methide derivatives and one or more of the tertiary amines of the present invention.

In accordance with one of the preferred embodiments of the present invention, the quinone methide derivatives and the tertiary amines are added in a weight percent ratio selected from the group comprising the weight percent ratio of quinone methide derivative : tertiary amine varying from

- i. about 99.99:0.01 to about 40:60,
- ii. about 99.9:0.1 to about 50:50,
- iii. about 99:1 to about 60:40,
- iv. about 95:5 to about 70:30, and
- v. about 90:10 to about 85:15.

In accordance with one of the preferred embodiments of the present invention, the quinone methide derivatives and the tertiary amines are added either separately or after mixing with each other.

In accordance with one of the preferred embodiments of the present invention, the quinone methide derivatives and the tertiary amines may also be added after mixing with a solvent which is capable of dissolving the derivatives and the amines.

In accordance with one of the preferred embodiments of the present invention, the composition consisting of one or more of the quinone methide derivatives and one or more of the tertiary amines is added to the aromatic vinyl monomers stream in the processing or manufacturing unit for styrene polymerization based on weight of the monomers in an amount selected from the group comprising:

- a. varying from about 0.01 to about 2000 ppm,
- b. varying from about 1 to about 1200 ppm,
- c. varying from about 5 to about 1000 ppm,
- d. varying from about 50 to about 500 ppm, and
- e. varying from about 100 to about 300 ppm.

In accordance with one of the preferred embodiments of the present invention, the additive compositions of the present invention or as prepared by the method of the present invention may be used or employed at a temperature range which is selected

from the group comprising the temperature varying from about 60⁰C to about 180⁰C, and from about 90⁰C to about 140⁰C.

In accordance with one of the preferred embodiments of the present invention, in the methods of the present invention as described herein, the monomers are in a processing stage.

In accordance with one of the preferred embodiments of the present invention, in the methods of the present invention as described herein, the monomers are at a temperature varying from about 60⁰C to about 180⁰C.

In accordance with one of the preferred embodiments of the present invention, in the methods of the present invention as described herein, the monomers are in a manufacturing stage.

It may be noted that the expression “are taken in percent ratio varying from about 99:1 to about 50:50” and so on are intended to include the ratio of 99:1 and 50:50, and so on.

It may also be noted that “in percent ratio” means “in weight percent ratio” or “in percent ratio by weight” unless specifically otherwise provided.

Examples:

The present invention is now described with the help of following examples, which are not intended to limit scope of the present invention.

Experiment:

10g distilled styrene and required amount of the amine are taken in a reactor (equivalent to processing or manufacturing unit of styrene polymerization, which for the laboratory experiments may be as a tube) equipped with thermometer and nitrogen inlet and outlet. Enough continuous N₂ flow varying from about 10-15 ml/min is

maintained to ensure proper agitation. The contents of the reactor are heated to about 120°C under continuous nitrogen flow for 2h. After 2h, the reactor is cooled to below 10°C by immersing in crushed ice. The contents of the reactor are then poured into a beaker containing methanol. The precipitate obtained is filtered, dried to remove methanol and weighed. Approximately, for 1.5-2g chilled polymerization, 80g methanol was used to precipitate the polymer formed in the styrene solution. The weight of the precipitate is reported as % polymer formed in below Tables. The styrene was distilled and purified before use to remove the stabilizers.

Examples – blank and with prior art additive - quinone methide:

The above experiment without additive is carried out to get the blank reading.

The above experiment with prior art additive - quinone methide (4-benzylidene, 2,6 di-tert-butyl-cyclohexa-2,5 dienone) (QM) is carried for active dosages of 100 ppm, and 150 ppm for QM and for comparison purpose.

Table 1

Example No.	Additive	Active Dosage (ppm)	% Polymerization
1	Blank	--	19.66
2	Quinone Methide (QM)	100	9.6
3	Quinone Methide (QM)	150	7.24

It can be seen from the above **Table 1** that with said prior art additive quinone methide for the dosage of about 150 ppm, the polymerization of styrene is substantially high of about 7.24%, and for the dosage of about 100 ppm, the polymerization of styrene is substantially further high of about 9.6%. Therefore, it is observed that quinone methide is not suitable at lower dosages.

Examples with amines per se of the present compositions and the comparative amines:

The above experiment with amines per se is carried out at 200 ppm to know whether these amines per se are capable of inhibiting the polymerization of styrene or not, and data is given in **Table 2**.

Table 2

Example No.	Additive	Active Dosage (ppm)	% Polymerization
4	TIPA [from Sterling]	200	17.08
5	TIPA [from DOW]	200	16.16
6	THEED	200	17.8
7	Quadrol®	200	14.64
8	TEA	200	16.9
9	TBA	200	16.21
10	DEA	200	15.27
11	MEA	200	15.47
12	UOP5	200	17.80

It can be seen from the above **Table 2** that all amines per se including the amines of the present compositions – TIPA and THEED and the comparative amines at a dosage of about 200 ppm result in polymerization of styrene to the extent varying from about 14.64% to 17.80%, which on comparison with data of blank experiment confirms that amines per se are not capable of inhibiting the polymerization of styrene, and therefore, the amines have been named as “polymerization non-inhibitors amines”.

Examples – blank and with prior art additive - quinone methide ester derivative:

The above experiment without additive is carried out to get the blank reading.

The above experiment with prior art additive - quinone methide ester derivative is carried for active dosages of 100 and 150 ppm for comparison purpose.

Table 3

Example No.	Additive	Active Dosage (ppm)	% Polymerization
1	Blank	--	19.66
13a	Quinone methide ester (purity 95% by HPLC)	100	5.90*
13b	- do -	150	1.99*

* It may be noted that we have corrected the typographical error in above table to correct the value of 5.89 as 5.90, and 1.59 as 1.99.

Examples with present composition vis-à-vis prior art or comparative compositions:

The above experiment was carried out with compositions of the present invention consisting of quinone methide ester derivative and tertiary amines (TIPA and THEED) to know the inhibition capability of compositions of the present invention and data has been compared with the prior art or comparative additives.

Table 4

Example No.	Additive	Active Dosage (ppm)	% Polymerization
14	QM Ester + TIPA	100 + 1	4.3*
15.	QM Ester + TIPA	150 + 0.75	0.89*
16.	QM Ester + Quadrol [®]	100 + 1	6.10
17.	QM Ester + Tributyl amine (TBA)	100 + 1	8.38
18	QM Ester + Triethanol amine (TEA)	100 + 1	8.63

* It may be noted that we have corrected the typographical error in above table to correct the value of 0.33 as 0.89.

Table 5

Example No.	Additive (combination of QM ester + TIPA) in active dosage (ppm)	% Polymerization
14	100 + 1	4.3
19	100 + 2	3.91
20	100 + 3	3.68
21	100 + 4	3.50
22	100 + 5	3.35
23	100 + 10	2.90
24	100 + 15	2.51
25	100 + 20	2.30
26	100 + 30	1.90
27	100 + 40	1.55
28	100 + 100	1.46

Table 6

Example No.	Additive (combination of QM ester + THEED) in active dosage (ppm)	% Polymerization
29	100 + 1	4.99
30	100 + 10	3.79
31	100 + 15	3.31
32	100 + 20	3.10
33	100 + 30	2.85
34	100 + 40	2.45

Table 7

Example No.	Additive (combination of QM ester + 4HT) in active dosage (ppm)	% Polymerization
35	100 + 5	6.11
36	100 + 10	6.16
37	100 + 15	6.08
38	100 + 20	6.21
39	100 + 30	6.25
40	100 + 40	6.28

Table 8

Example No.	Additive (combination of QM ester + TIPA) in active dosage (ppm)	% Polymerization
41	150 + 0.1	1.65
42	150 + 0.5	1.32
15	150 + 0.75	0.89
43	150 + 1.0	0.82
44	150 + 1.5	0.75
45	150 + 3.0	0.66
46	150 + 4.5	0.51
47	150 + 6.0	0.40
48	150 + 10	0.35
49	150 + 20	0.28
50	150 + 30	0.25
51	150 + 40	0.20
52	150 + 150	0.08

Table 9

Example No.	Additive (combination of QM ester + THEED) in active dosage (ppm)	% Polymerization
53	150 + 10	1.52
54	150 + 20	1.42
55	150 + 30	1.27
56	150 + 40	1.19

Table 10

Example No.	Additive (combination of QM ester + 4HT) in active dosage (ppm)	% Polymerization
57	150 + 5	2.70
58	150 + 10	2.80
59	150 + 20	2.75
60	150 + 30	2.79
61	150 + 40	2.69

Table 11

Example No.	Additive (combination of QM ester + TIPA) in active dosage (ppm)	% Polymerization
62	200 + 0.1	0.78
63	200 + 0.5	0.55
64	200 + 1	0.40
65	200 + 5	0.25
66	200 + 10	0.21
67	200 + 15	0.19
68	200 + 20	0.12
69	200 + 30	0.07
70	200 + 40	0

Table 12

Example No.	Additive (combination of QM ester + THEED) in active dosage (ppm)	% Polymerization
71	200 + 1	0.78
72	200 + 5	0.62
73	200 + 10	0.57
74	200 + 15	0.55
75	200 + 20	0.49
76	200 + 30	0.47
77	200 + 40	0.39

Table 13

Example No.	Additive (combination of QM ester + 4HT) in active dosage (ppm)	% Polymerization
78	200 + 5	1.21
79	200 + 10	1.27
80	200 + 15	1.24
81	200 + 20	1.32
82	200 + 30	1.33
83	200 + 40	1.36

Table 14

Example No.	Additive (combination of QM ester + Quadrol®) in active dosage (ppm)	% Polymerization
84	200 + 5	1.10
85	200 + 10	1.08
86	200 + 15	1.08
87	200 + 20	1.05
88	200 + 30	1.10
89	200 + 40	1.05

Table 15

Example No.	Additive (combination of QM ester + TBA) in active dosage (ppm)	% Polymerization
90	200 + 5	1.25
91	200 + 10	1.27
92	200 + 15	1.30

Table 16

Example No.	Additive (combination of QM ester + TEA) in active dosage (ppm)	% Polymerization
93	200 + 5	1.32
94	200 + 10	1.39
95	200 + 15	1.42

Table 17

Example No.	Additive (combination of QM ester + TIPA) in active dosage (ppm)	% Polymerization
96	300 + 0.1	0.15
97	300 + 0.5	0.07
98	300 + 1	0
99	300 + 5	0
100	300 + 10	0

Table 18

Example No.	Additive (combination of QM ester + THEED) in active dosage (ppm)	% Polymerization
101	300 + 0.1	0.20
102	300 + 0.5	0.15
103	300 + 1	0.12
104	300 + 5	0.10
105	300 + 10	0.08

The above experimental findings confirm surprising, unexpected and synergistic effects of the presently provided compositions.

The above findings also confirm that compositions of present invention have technical advantages and surprising effects over the prior art and comparative additives and compositions.

It may also be noted that the term “about” is not intended to enlarge scope of the range defined herein, but is intended to include the experimental errors permissible in the field of the invention.

Claims:

1. Additive composition for controlling and inhibition of polymerization of aromatic vinyl monomers including styrene consisting of:
 - (a) one or more of quinone methide derivatives; and

CHARACTERIZED IN THAT the composition further comprises:

 - (b) one or more of tertiary amines,
wherein said tertiary amine is selected from a group consisting of:
 - (i) tri isopropanol amine (TIPA),
 - (ii) N,N,N',N'-Tetrakis (2-hydroxyethyl) ethylene-diamine) (THEED), and
 - (iii) mixture thereof.
2. The additive composition as claimed in claim 1, wherein the composition consists of:
 - (a) one or more of quinone methide derivatives; and

CHARACTERIZED IN THAT the composition further comprises:

 - (b) one or more of tertiary amines,
wherein said tertiary amine is tri isopropanol amine (TIPA).
3. The additive composition as claimed in claim 1, wherein the composition consists of:
 - (a) one or more of quinone methide derivatives; and

CHARACTERIZED IN THAT the composition further comprises:

 - (b) one or more of tertiary amines,
wherein said tertiary amine is N,N,N',N'-Tetrakis (2-hydroxyethyl) ethylene-diamine) (THEED).
4. The additive composition as claimed in claim 1, wherein the composition consists of:
 - (a) one or more of quinone methide derivatives; and

CHARACTERIZED IN THAT the composition further comprises:

 - (b) one or more of tertiary amines,
wherein said tertiary amine is combination of:

- (i) tri isopropanol amine (TIPA), and
- (ii) N,N,N',N'-Tetrakis (2-hydroxyethyl) ethylene-diamine) (THEED).

5. The additive composition as claimed in any one of the preceding claims 1 to 4, wherein the quinone methide derivative is selected from a group comprising:

- i) alkyl-(3,5-di-tert-butyl-4-oxocyclohexane-2,5-dienylidene)-cyano derivative of quinone methide;
- ii) alkyl-(3,5-di-tert-butyl-4-oxocyclohexane-2,5-dienylidene)-acid derivative of quinone methide;
- iii) alkyl-(3,5-di-tert-butyl-4-oxocyclohexane-2,5-dienylidene)-ester derivative of quinone methide; and
- iv) combination thereof.

6. The additive composition as claimed in any one of the preceding claims 1 to 5, wherein the quinone methide derivative is alkyl-(3,5-di-tert-butyl-4-oxocyclohexane-2,5-dienylidene)-ester derivative of quinone methide.

7. The additive composition as claimed in claim 5 or claim 6, wherein the alkyl group is selected from a group comprising methyl- group, ethyl-group and propyl-group.

8. The additive composition as claimed in any one of the preceding claims 1 to 7, wherein the quinone methide derivative does not include 7-aryl quinone methide derivatives.

9. The additive composition as claimed in any one of the preceding claims 1 to 8, wherein the composition does not comprise one or more of following amines:

- i) N,N,N',N'-Tetrakis (2-hydroxypropyl) ethylene-diamine) Quadrol[®];
- ii) tetraethylenepentamine (TEPA);
- iii) triethanolamine (TEA);
- iv) Tris(N-butylamine) (TBA); and
- v) ethylene diamine (EDA).

10. The additive composition as claimed in any one of the preceding claims 1 to 9, wherein the composition does not comprise nitroxide (i.e. nitroxyl) compound including 1-oxyl-2,2,6,6, tetramethylpiperidin-4-ol (or 4 Hydroxy Tempo or 4-HT).
11. The additive composition as claimed in any one of the preceding claims 1 to 10, wherein the quinone methide derivative and the tertiary amine are present in a weight percent ratio, wherein the weight percent ratio is selected from the group comprising the weight percent ratio of quinone methide derivative: tertiary amine varying from:
 - i. about 99.99:0.01 to about 40:60,
 - ii. about 99.9:0.1 to about 50:50,
 - iii. about 99:1 to about 60:40,
 - iv. about 95:5 to about 70:30, and
 - v. about 90:10 to about 85:15.
12. The additive composition as claimed in any one of the preceding claims 1 to 11, wherein the composition is used in an amount which is selected from the group comprising the amount varying from:
 - a. about 0.01 to about 2000 ppm,
 - b. about 1 to about 1200 ppm,
 - c. about 5 to about 1000 ppm,
 - d. about 50 to about 500 ppm, and
 - e. about 100 to about 300 ppm, andis added to the aromatic vinyl monomers stream based on weight of the monomer.
13. A method of preparation of the additive composition for control and inhibition of polymerization of aromatic vinyl monomers including styrene as claimed in any one of the preceding claims 1 to 10, wherein the method comprises mixing one or more of the quinone methide derivatives and one or more of the tertiary amines.

14. The method as claimed in claim 13, wherein the quinone methide derivatives and the tertiary amines are mixed in a weight percent ratio selected from the group comprising the weight percent ratio of quinone methide derivative : tertiary amine varying from
 - i. about 99.99:0.01 to about 40:60,
 - ii. about 99.9:0.1 to about 50:50,
 - iii. about 99:1 to about 60:40,
 - iv. about 95:5 to about 70:30, and
 - v. about 90:10 to about 85:15.
15. A method of using the additive composition of any one of the preceding claims 1 to 10 for control and inhibition of polymerization of aromatic vinyl monomers including styrene, wherein the method comprises adding the additive composition to a processing or manufacturing unit for styrene polymerization, wherein the additive composition consists of mixture of one or more of the quinone methide derivatives and one or more of the tertiary amines.
16. A method of using the additive composition of any one of the preceding claims 1 to 10 for control and inhibition of polymerization of aromatic vinyl monomers including styrene, wherein the method comprises separately adding components of the additive composition to a processing or manufacturing unit for styrene polymerization, wherein the additive composition consists of component a) one or more of the quinone methide derivatives and component b) one or more of the said tertiary amines.
17. The method as claimed in claim 15 or claim 16, wherein the quinone methide derivatives and the tertiary amines are added to the processing or manufacturing unit for styrene polymerization in a weight percent ratio selected from the group comprising the weight percent ratio of quinone methide derivative : tertiary amine varying from
 - i. about 99.99:0.01 to about 40:60,
 - ii. about 99.9:0.1 to about 50:50,
 - iii. about 99:1 to about 60:40,

- iv. about 95:5 to about 70:30, and
- v. about 90:10 to about 85:15.

18. The method as claimed in any one of the preceding claims 15 to 17, wherein the compositions is added in an amount selected from the group comprising:

- a. varying from about 0.01 to about 2000 ppm,
- b. varying from about 1 to about 1200 ppm,
- c. varying from about 5 to about 1000 ppm,
- d. varying from about 50 to about 500 ppm, and
- e. varying from about 100 to about 300 ppm,

to the aromatic vinyl monomers stream in the processing or manufacturing unit for styrene polymerization based on weight of the monomers.

19. The method as claimed in any one of the preceding claims 15 to 18, wherein the quinone methide derivatives and the tertiary amines are added either separately or after mixing with each other.

20. The method as claimed in any one of the preceding claims 15 to 18, wherein the quinone methide derivatives and the tertiary amines are added after mixing with a solvent which dissolves the derivatives and the amines.

21. A method for controlling and inhibition of polymerization of aromatic vinyl monomers including styrene, wherein the method comprises adding the additive composition any one of the preceding claims 1 to 10 to a processing or manufacturing unit for styrene polymerization, wherein the additive composition consists of one or more of the quinone methide derivatives and one or more of the tertiary amines.

22. The method as claimed in claim 21, wherein the quinone methide derivatives and the tertiary amines are added in a weight percent ratio selected from the group comprising the weight percent ratio of
quinone methide derivative : tertiary amine varying from

- i. about 99.99:0.01 to about 40:60,

- ii. about 99.9:0.1 to about 50:50,
- iii. about 99:1 to about 60:40,
- iv. about 95:5 to about 70:30, and
- v. about 90:10 to about 85:15.

23. The method as claimed in claim 21 or claim 22, wherein the is added in an amount selected from the group comprising:

- a. varying from about 0.01 to about 2000 ppm,
- b. varying from about 1 to about 1200 ppm,
- c. varying from about 5 to about 1000 ppm,
- d. varying from about 50 to about 500 ppm, and
- e. varying from about 100 to about 300 ppm.

24. The method as claimed in any one of the preceding claims 21 to 23, wherein the quinone methide derivatives and the tertiary amines are added either separately or after mixing with each other.

25. The method as claimed in any one of the preceding claims 21 to 23, wherein the quinone methide derivatives and the tertiary amines are added after mixing with a solvent which dissolves the derivatives and the amines.

26. The method as claimed in any of the preceding claim 13 to 25, wherein said composition is used at a temperature range which is selected from the group comprising the temperature varying from about 60⁰C to about 180⁰C, and from about 90⁰C to about 140⁰C.

27. The method as claimed in any of the preceding claim 13 to 26, wherein said monomers are in a processing stage.

28. The method as claimed in any of the preceding claim 13 to 27, wherein said monomers are at a temperature varying from about 60⁰C to about 180⁰C.

29. The method as claimed in any of the preceding claim 13 to 28, wherein said monomers are in a manufacturing stage.
30. Additive composition for controlling and inhibition of polymerization of aromatic vinyl monomers including styrene substantially as herein described and illustrated with the help of foregoing examples.
31. A method of preparation of the additive composition for control and inhibition of polymerization of aromatic vinyl monomers including styrene substantially as herein described and illustrated with the help of foregoing examples.
32. A method of using the additive composition for control and inhibition of polymerization of aromatic vinyl monomers including styrene substantially as herein described and illustrated with the help of foregoing examples.
33. A method for controlling and inhibition of polymerization of aromatic vinyl monomers including styrene substantially as herein described and illustrated with the help of foregoing examples.

INTERNATIONAL SEARCH REPORT

International application No
PCT/IB2013/056787

A. CLASSIFICATION OF SUBJECT MATTER
INV. C07C7/20 C08F2/40 C09K15/18 C09K15/24
ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
C07C C09K C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X, P	WO 2013/054353 A1 (DORF KETAL CHEMICALS INDIA PRIVATE LTD [IN]; SUBRAMANIYAM MAHESH [IN]) 18 April 2013 (2013-04-18) page 4, line 30; claims 1, 2 -----	1-33
X, P	WO 2013/102930 A1 (DORF KETAL CHEMICALS INDIA PRIVATE LTD [IN]; SUBRAMANIYAM MAHESH [IN]) 11 July 2013 (2013-07-11) claims 1, 3, 4 -----	1-33
X	US 2004/034247 A1 (ELDIN SHERIF [US]) 19 February 2004 (2004-02-19) claim 1; tables 1, 2 -----	1-33
A	US 6 024 894 A (ARHANCET GRACIELA B [US]) 15 February 2000 (2000-02-15) the whole document ----- -/-	1-33

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier application or patent but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search	Date of mailing of the international search report
14 October 2013	18/10/2013
Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer Lux, Rudolf

INTERNATIONAL SEARCH REPORTInternational application No
PCT/IB2013/056787

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 670 692 A (NESVADBA PETER [CH] ET AL) 23 September 1997 (1997-09-23) the whole document -----	1-33
1		

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No PCT/IB2013/056787
--

Patent document cited in search report	Publication date	Patent family member(s)			Publication date
WO 2013054353	A1 18-04-2013	TW WO	201323585 A 2013054353 A1		16-06-2013 18-04-2013
WO 2013102930	A1 11-07-2013		NONE		
US 2004034247	A1 19-02-2004		NONE		
US 6024894	A 15-02-2000	AR BR CA DE EP ES TW US WO	017985 A1 9909042 A 2323870 A1 69933558 T2 1086192 A1 2270584 T3 539681 B 6024894 A 9948996 A1		24-10-2001 05-12-2000 30-09-1999 21-06-2007 28-03-2001 01-04-2007 01-07-2003 15-02-2000 30-09-1999
US 5670692	A 23-09-1997	CA DE DE EP JP JP US US US	2174061 A1 69609110 D1 69609110 T2 0737659 A1 3726198 B2 H09176215 A 5583247 A 5670692 A 5750765 A		15-10-1996 10-08-2000 22-03-2001 16-10-1996 14-12-2005 08-07-1997 10-12-1996 23-09-1997 12-05-1998