



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁷ : C08G 18/34, 18/81, C08F 220/36</p>	<p>A1</p>	<p>(11) International Publication Number: WO 00/69944 (43) International Publication Date: 23 November 2000 (23.11.00)</p>
<p>(21) International Application Number: PCT/US00/08319 (22) International Filing Date: 29 March 2000 (29.03.00) (30) Priority Data: 09/314,489 18 May 1999 (18.05.99) US (71) Applicant: 3M INNOVATIVE PROPERTIES COMPANY [US/US]; 3m Center, Post Office Box 33427, Saint Paul, MN 55133-3427 (US). (72) Inventors: SHEN, Byron, C.; Post Office Box 33427, Saint Paul, MN 55133-3427 (US). LEIR, Charles, M.; Post Office Box 33427, Saint Paul, MN 55133-3427 (US). DEVRIES, Amy, M.; Post Office Box 33427, Saint Paul, MN 55133-3427 (US). (74) Agents: SKOLNICK, Steven, E. et al.; Office of Intellectual Property Counsel, Post Office Box 33427, Saint Paul, MN 55133-3427 (US).</p>	<p>(81) Designated States: AE, AG, AL, AM, AT, AT (Utility model), AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, CZ (Utility model), DE, DE (Utility model), DK, DK (Utility model), DM, DZ, EE, EE (Utility model), ES, FI, FI (Utility model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KR (Utility model), KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (Utility model), SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).</p> <p>Published <i>With international search report.</i></p>	
<p>(54) Title: POLYMERIZABLE ACIDIC COMPOUNDS AND METHODS OF PREPARATION</p>		
<p>(57) Abstract</p>		
<p>Polymerizable urethane acid compounds are provided. Preferred compounds additionally comprise a hydroxy functionality. These compounds are made by reaction of hydroxy functional acid compounds with isocyanates.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

Polymerizable Acidic Compounds And Methods Of Preparation

Field of the Invention


The present invention relates to new polymerizable urethane acids. More specifically, the present invention relates to multi-functional compounds that may be generated by a highly selective reaction.

Background

Polymerizable acidic materials have previously been used in resin bonding systems and in hybrid cement systems. For example, polymerizable acidic materials are described in US Patent No 5,130,347 for use in glass ionomer cements. Such compounds are also described for use in dental adhesives in US Patent No 5,525,648.

Summary of the Invention


Novel polymerizable urethane acid compounds of the present invention have the formula:



wherein

n is 0, 1 or 2
m is 1, 2 or 3
and n + m = 3;





R^I is independently, C₁₋₁₂ alkyl, -O-C₁₋₁₂ alkyl; C₁₋₁₂ alkyl-OH;








R^V=alkyl or -OH

with the proviso that when m = 1, one of R^I is -CH₂OH

R^{II} is independently




5





10

wherein p is 1-12
or any combination thereof

R^{III} is independently



15



—acrylamide

—methacrylamide

20

R^{IV} is independently H, C1-12 alkyl.

Novel preparations of these compounds are also described.

Detailed Description of the Invention

5 The polymerizable urethane acids of the present invention have several advantages in comparison with previously known acidic monomers. Materials, especially dental materials, comprising these polymerizable acidic monomers exhibit high strength and toughness of the cured (crosslinked) material. Further, the present polymerizable acidic monomer is relatively low in viscosity as
10 compared to previously prepared polymerizable acidic monomers. The present invention therefore allows formulation of materials, such as dental materials, having a higher percentage of polymerizable acidic monomer in the material than previously possible at a desired viscosity or consistency. Unlike monomers recommended for use in the prior art for cement systems that contain multiple acid
15 groups, the present polymerizable urethane acids have only one carboxylic acid group. It has been found that in the glass-ionomer or compomer type formulations, having only one acid group helps to improve the stability of the paste. Further, unlike many other polyfunctional monomers which are often a mixture of different components, the present polymerizable acid monomers can be produced in high
20 purity. High purity is extremely helpful in achieving a consistent manufacturing process and making consistent end products.

 The polymerizable acid monomers of this invention are useful components in various dental materials where acid functionality is desired, such as compomers, composites, flowable composites, glass ionomers, resin cements, and dental
25 adhesives. These monomers also have applications in other industrial or biomedical adhesive products.

 Certain molecules of the present invention provide polymerizable chelating monomers. The β -hydroxyl carboxylic acid moiety on this molecule is capable of chelating metal ions, e.g., Calcium, so that a six-membered ring will form. The β -
30 hydroxyl carboxylic acid compounds of the present invention thus provide surprisingly good surface treatment activity as compared to materials that do not contain the β -hydroxyl carboxylic acid combination of functionalities, while being


polymerizable to provide a material that does not contain free acid monomers after polymerization of the overall resin. This material is therefore highly desirable for use in adhesive compositions, and substantially reduces or eliminates the need for prior surface treatment before bonding to the surface. The β -hydroxyl carboxylic acid compounds of the invention are also highly reactive with acid reactive glass, facilitating rapid cement reactions.

The polymerizable acid monomers of this invention are also useful as intermediates for other useful materials. For example, acidic polymerizable monomers of the present invention may be reacted with a metal fluoride, such as ZnF_2 , SnF_2 , AlF_3 , thereby preparing useful metal fluoro-complexes. These metal fluoro-complexes could then be used as additives in dental materials for fluoride release.

Alternatively, polymerizable acid monomers of this invention have at least one (and in the case of hydroxy functional compounds, two) active hydrogen site capable of further reaction to provide polymerizable materials having unique chemical structure for incorporation in polymerizable resins.

For example, the further functionalization of the hydroxyl groups on the hydroxy functional polymerizable acidic monomers of the present invention may be carried out in alternative conversion routes. For example, the hydroxyl groups may be converted into methacrylate groups directly via reaction with methacrylic acid or methacryl chloride; or in reacting with the epoxy groups in glycidyl methacrylate. Similarly, the present monomers may also be useful for making compounds having various spacers (e.g., aromatic groups, ethylene oxide units, more than two urethane linkages) in-between various functional groups and the propionic acid moiety.

Of the compounds described above, one preferred class of compounds has the formula:




wherein

n is 2

m is 1









one of R^I is —CH₂OH;

5 and the other of R^I is C₁₋₁₂ alkyl, -O- C₁₋₁₂ alkyl;



R^V=C₁₋₁₂ alkyl




R^{II} is independently



wherein p is 1-12

20 or any combination thereof

R^{III} is independently




—acrylamide

—methacrylamide

5

R^{IV} is independently H, C1-12 alkyl.

Another preferred class of compounds has the formula:




10

wherein

n is 1


m is 2

15 R^I is C₁₋₁₂ alkyl, -O- C₁₋₁₂ alkyl;









R^V=C₁₋₁₂alkyl

R^{II} is independently





20





5






wherein p is 1-12

or any combination thereof

10

R^{III} is independently



15

—acrylamide

—methacrylamide

R^{IV} is independently H, C1-12 alkyl.



20

A particularly preferred class of compounds of the present invention is
wherein

n = 1;


$$m = 2;$$

$$R^I = \text{CH}_3;$$




5

Another particularly preferred class are the compounds wherein $n=2$, $m=1$, one of R^I is $\text{CH}_2\text{-OH}$ and the other R^I is $-\text{CH}_3$, R^{II} is



and R^{III} is




10

Another particularly preferred class of compounds is where n is 2 and one of R^I is $\text{CH}_2\text{-OH}$.

Most preferably, the polymerizable carboxylic acid compound is selected from 2,2-di(N-methacryloxyethyl carbamoylmethyl) propionic acid ("PDMA") and 2-hydroxymethyl-2-[(N-methacryloxyethyl) carbamoylmethyl] propionic acid ("PAMA").

15

Another aspect of the present invention provides a method of making compounds of the formula:




20 wherein

n is 2

m is 1









one of R^I is —CH₂OH;

and the other of R^I is C₁₋₁₂ alkyl, -O- C₁₋₁₂ alkyl;



5 R^v= C₁₋₁₂ alkyl


R^{II} is independently





wherein p is 1-12

or any combination thereof

20 R^{III} is independently






—acrylamide

—methacrylamide


5

R^{IV} is independently H, C1-12 alkyl.

In this method, a compound of the formula



10 wherein the substituents are as defined immediately above, is reacted with a compound of the formula



wherein the substituents are as defined immediately above.

15 These compounds are reacted in the presence of a catalytic amount of a non-basic catalyst at a temperature between about 40 and 80° C for a time greater than about 15 hours.

Surprisingly, it has been found that undertaking this reaction as described above generates a high yield of the desired mono-hydroxy functional
 20 polymerizable acid. This is unexpected in view of the otherwise rapid reaction of isocyanato with primary hydroxyl compounds, such as disclosed in Saunders and Frisch, Polyurethanes Chemistry and Technology, (1962 John Wiley and Sons), pp. 73-75, 80-81. One would have expected all of the hydroxyl compounds to react under the present aggressive conditions. This yield is far higher than the
 25 statistically expected yield, with in excess of 80% of the reaction product being the desired material, with less than 20% of the reaction product being the bis-polymerizable compound (generated by reaction of the isocyanate with both

hydroxyl functionalities) and amido functional product (generated by reaction of the isocyanate with the acid functionality). More preferably, the reaction generates an excess of 85% of the reaction product being the desired mono-hydroxy functional polymerizable acid. This result is in surprising contrast to the expected
5 reaction product distribution, which would be expected to be a statistical distribution of reaction of the isocyanate with alcohols, resulting in about 66% of the mono-hydroxyl functional compound and 33% of the bis-polymerizable compound. One would further expect that any amido-functional compound would act only to reduce the yield of the desired product proportionally.


10 Because no base is used as a catalyst, the present reaction provides the significant benefit of not forming the salt of the acid, which would have to be reconverted back to the acid before use in the ultimate system where an acid is desired.

Preferred non-basic catalysts for use in the present invention include tin IV
15 catalysts, such as dibutyltin dilaurate, dibutyltin diacetate, dibutyltin dilaurate, dibutyltin dimercaptide, dibutyltin dithioglycolate, dimethyltin dilaurate, dimethyltin dimaleate, dimethyltin dimercaptide, dimethyltin dithioglycolate, dioctyltin dilaurate, dioctyltin dimercaptide, and dioctyltin dithioglycolate. Other tin II catalysts include stannous octoate and stannous stearate. Other urethane
20 metal catalysts include bismuth neodecanoate, phenylmercuric propionate, potassium octoate, and zinc stearate.

Preferably, this reaction is carried out such that the molar ratio of the hydroxy acid starting material to the isocyanate starting material is greater than about 1:1. This reaction condition provides a final product that is a mixture of
25 mono and di polymerizable functional compounds, with a predominant amount of the mono-polymerizable functional compound.

In another preferred reaction, the reaction is carried out such that the molar ratio of the hydroxy acid starting material to the isocyanate starting material is greater than about 2:1. This reaction condition provides a final product that is a
30 mixture of mono- and di- polymerizable functional compounds, with a surprisingly high predominance of the mono-polymerizable functional compound.


A further surprising aspect of the present invention is the method of making compounds of the formula:



wherein



- 5 n is 1
 m is 2

R^I is C₁₋₁₂ alkyl, -O- C₁₋₁₂ alkyl;







- 10 R^V = C₁₋₁₂ alkyl


R^{II} is independently



- 15 $\text{---} \left(\text{CH}_2 \text{CH}_2 \text{CH}_2 \text{---} \text{O} \right)_p \text{---}$




- 20 $\left(\text{---} \text{HC}=\text{CH} \text{---} \right)_p$





wherein p is 1-12
or any combination thereof

R^{III} is independently



5




—acrylamide

—methacrylamide

10


R^{IV} is independently H, C1-12 alkyl.

This compound is provided by reacting one part of a compound of the formula



15

wherein the substituents are as defined immediately above,
with two parts of a compound of the formula



wherein the substituents are as defined immediately above.

20

These reactants are reacted in the presence of a hydroxyl/isocyanato reaction catalyst at a temperature between about 22 and 80° C for a time greater than about 15 hours when only non-basic catalyst is used. The hydroxyl/isocyanato reaction catalyst for this reaction may be an organic basic

catalyst, a non-basic catalyst or combinations thereof. Preferably, the catalyst is a non-basic catalyst.

Under these reaction conditions, one would expect that the acid functionality would be either destroyed through the harsh reaction conditions, or
5 the isocyanate would react with the acid to form an amide or a urea. Such amide or urea formation reactions have previously been observed using different starting materials to be a reasonably rapid reaction under less aggressive conditions. An example of such a reaction at room temperature is disclosed in U.S. Patent No. 5,260,483.

10 Preferred organic basic catalysts are the tertiary amine catalysts, including triethylamine; triethylenediamine; bis(dimethylaminoethyl) ether; tris(dimethylaminomethyl) phenol; N,N'-dimorpholinodiethyl ether; N,N'-dimethyl cyclohexylamine; pentamethyl N,N'-dipropylenetriamine; 1,8-diazabicyclo-[5,4,0]-undecane 7, N,N'-dimethylethanol amine; and N-ethylmorpholine.

15 The following examples are provided for purposes of illustrating the present invention, and are not intended to be limiting of the broadest concepts of the present invention. Unless otherwise indicated, all parts and percentages are by weight and all molecular weights are weight average molecular weight.

20 Examples

Example 1

2,2-di(N-methacryloxyethyl carbamoylmethyl) propionic acid (PDMA) is synthesized by reacting 2,2-Bis(hydroxymethyl)propionic acid (BHMPA) and two equivalents of Isocyanatoethylmethacrylate (IEM) as follows:

25 2,2-Bis(hydroxymethyl)propionic acid (BHMPA, 225.21 g, 1.679 mole), small amounts of stabilizer(s) such as 2,6-Di-tert-butyl-4-methylphenol (BHT, 1.6781 g, 7.615 mmole) and/or Triphenyl antimony (TPS, 1.3463 g, 3.813 mmole), and a catalytic amount of Dibutyltin dilaurate (2.4396 g, 3.863 mmole) and dry THF or other suitable solvents were added first to the reactor. After the solution
30 was stirred for a short while, IEM (592.64 g, 3.823 mole) was added. The reaction was heated to 65 °C for about 30 hours while stirring constantly. The solvent was

stripped off after the conversion was completed. The final product, PDMA, was a colorless, viscous liquid.

Example 2

5 Alternatively, the above reaction can be carried out using Triethylamine as a base catalyst to speed up the reaction. 0.075 to 0.15 Equivalent of Triethylamine is typically needed. This reaction was undertaken as follows:

10 2,2-Bis(hydroxymethyl)propionic acid (14.9946 g, 0.112 mole), small amounts of 2,6-Di-tert-butyl-4-methylphenol (0.1012 g, 0.456 mmole) stabilizer [an alternative stabilizer, such as Triphenyl antimony (0.0831 g, 0.235 mmole) may be used], and a catalytic amount of Dibutyltin dilaurate (0.1450 g, 0.230 mmole), Triethylamine (1.132 g, 0.0112 mole) and dry THF were added first to the reactor. After the solution was stirred for a short while, IEM (35.55 g, 0.229 mole) was added. The reaction was heated to 65 °C for 8 hours while stirring constantly. After 15 the functionalization step, the triethylamine was removed by re-acidifying with 37% wt aq. HCl (1.218 g, 0.0124 mole) at low temperature. A white solid, triethylamine hydrochloride, precipitated out. After filtering out the white precipitate while the solution was still cold, the solvent was then stripped off. Re-acidification is not necessary if the presence of a small amount of triethylamine can 20 be tolerated in a given application.

Example 3


The reactor was first charged with an excess amount of BHMPA (139.94 g, 1.043 mole), 2,6-Di-tert-butyl-4-methylphenol (0.2322 g, 1.054 mmole), Triphenyl 25 antimony (0.1891 g, 0.536 mmole), and Dibutyltin dilaurate (0.6801 g, 1.077 mmole). The starting material, BHMPA, was only slightly soluble in THF at room temperature. IEM was gradually dripped (80.94 g, 0.522 mole) into the above mixture. The reaction was run at 60 °C for 24 hours while stirring constantly. At the end of the reaction, most of the unreacted BHMPA settled out as white solid 30 powder after the solution was cooled down. Unreacted BHMPA was filtered off by vacuum filtration, and the solvent was then stripped off. The recovered BHMPA could be used in future reactions.

After the removal of the solvent, the product became slightly cloudy due to slow precipitation of residual BHMPA. Enough diethyl ether was added to dissolve the product and then the solution was allowed to sit overnight (approximately 18 hours) undisturbed to precipitate out most of the remaining
5 BHMPA in solution. The white precipitate was filtered off by vacuum filtration, and diethyl ether was stripped off.

The resulting product, PAMA was a colorless, flowable liquid. The purity of PAMA in the final product was approximately 80% by molar ratio, with PDMA being the main side-product (approximately 17%) and small amounts of remaining
10 BHMPA (approximately 3%).

What is claimed is:

1. A compound of the formula



5


wherein

n is 0, 1 or 2

m is 1, 2 or 3

and $n + m = 3$;






10 R^{I} is independently, C_{1-12} alkyl, -O- C_{1-12} alkyl; C_{1-12} alkyl-OH;





$\text{R}^{\text{V}} = \text{C}_{1-12}$ alkyl or -OH



with the proviso that when $m = 1$, one of R^{I} is $\text{---CH}_2\text{OH}$

15 R^{II} is independently



20








wherein p is 1-12
or any combination thereof

5

R^{III} is independently



10


—acrylamide

—methacrylamide

R^{IV} is independently H, C1-12 alkyl;
or a salt thereof.

15

2. The compound of claim 1, having the formula:



wherein



n is 2

20

m is 1






one of R^I is —CH₂OH;

and the other of R^I is C₁₋₁₂ alkyl, -O- C₁₋₁₂ alkyl;







R^{II} is independently

5



10





wherein p is 1-12


15

or any combination thereof

R^{III} is independently



20




—acrylamide

—methacrylamide

R^{IV} is independently H, C₁₋₁₂ alkyl.

5

3. The compound of claim 1, having the formula:




wherein

n is 1

10

m is 2




R^I is C₁₋₁₂ alkyl, -O- C₁₋₁₂ alkyl;






R^V = C₁₋₁₂ alkyl




15

R^{II} is independently



20








wherein p is 1-12

5 or any combination thereof

R^{III} is independently



10

—acrylamide

—methacrylamide

R^{IV} is independently H, C1-12 alkyl.

15

4. The compound of claim 1 wherein


n = 1;

m = 2;

R^I = CH₃;

20


R^{II} = $\left(\text{CH}_2\text{CH}_2 \right)$;




5. The compound of claim 1, wherein

$n=2$, $m=1$, one of R^I is $\text{CH}_2\text{-OH}$

5 and the other R^I is $-\text{CH}_3$, R^{II} is



and R^{III} is



10


6. The compound of claim 1, wherein n is 2 and one of R^I is $\text{CH}_2\text{-OH}$.

7. The compound of claim 1, which is 2,2-di(N-methacryloxyethyl carbamoylmethyl) propionic acid (PDMA).

15

8. The compound of claim 1, which is 2-hydroxymethyl-2-[(N-methacryloxyethyl) carbamoylmethyl] propionic acid ("PAMA").

9. A method of making compounds of the formula:



20



wherein

n is 2









m is 1

25 one of R^I is $-\text{CH}_2\text{OH}$;

and the other of R^I is C_{1-12} alkyl, $-\text{O}-\text{C}_{1-12}$ alkyl;






R^{II} is independently



wherein p is 1-12

15 or any combination thereof


R^{III} is independently




—acrylamide

—methacrylamide

5 R^{IV} is independently H, C1-12 alkyl said method comprising reacting a compound of the formula



wherein the substituents are as defined immediately above,
with a compound of the formula



10 wherein the substituents are as defined immediately above, said reaction being in the presence of a catalytic amount of a non-basic catalyst at a temperature between about 22 and 80° C for a time greater than about 15 hours, said reaction generating an excess of 80% of the theoretical yield of the mono-hydroxy functional polymerizable acid.

15

10. The method of claim 9, wherein the reaction generates an excess of 85% of the theoretical yield of the mono-hydroxy functional polymerizable acid.

11. The method of claim 9, wherein said non-basic catalyst is selected from the
20 group consisting of tin IV catalysts and tin II catalysts.


12. The method of claim 9, wherein said non-basic catalyst is selected from the
group consisting of dibutyltin dilaurate, dibutyltin diacetate, dibutyltin dilaurate,
dibutyltin dimercaptide, dibutyltin dithioglycolate, dimethyltin dilaurate,
25 dimethyltin dimaleate, dimethyltin dimercaptide, dimethyltin dithioglycolate,
dioctyltin dilaurate, dioctyltin dimercaptide, and dioctyltin dithioglycolate,
stannous octoate, stannous stearate, bismuth neodecanoate, phenylmercuric
propionate, potassium octoate, and zinc stearate.

13. The method of claim 9, wherein the molar ratio of the compound of the hydroxy acid starting material to the isocyanate starting material is greater than about 1:1.

5

14. The method of claim 9, wherein the molar ratio of the compound of the hydroxy acid starting material to the isocyanate starting material is greater than about 2:1.

10 15. A method of making compounds of the formula:




wherein

n is 1

m is 2





15

R^I is C₁₋₁₂ alkyl, -O-C₁₋₁₂ alkyl;




R^V = C₁₋₁₂ alkyl

20 R^{II} is independently



wherein the substituents are as defined immediately above,
with a compound of the formula



wherein the substituents are as defined immediately above,
5 at a temperature between about 22 and 80° C for a time greater than about 15
hours, wherein said reaction generates less than 5% amide and urea reaction
products of the theoretical yield of products.

16. The method of claim 15, wherein said reaction takes place in the presence
10 of a hydroxyl/isocyanate reaction catalyst.

17. The method of claim 16, wherein said hydroxyl/isocyanate reaction catalyst
is an organic basic catalyst is selected from the group consisting of tertiary amine
catalysts.

15
18. The method of claim 17, wherein the tertiary amine catalyst is selected
from the group consisting of triethylamine; triethylenediamine;
bis(dimethylaminoethyl) ether; tris(dimethylaminomethyl) phenol;
N,N'-dimorpholinodiethyl ether; N,N'-dimethyl cyclohexylamine; pentamethyl
20 dipropylenetriamine; 1,8-diazabicyclo-[5,4,0]-undecane 7, N,N'-dimethylethanol
amine; and N-ethylmorpholine.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 00/08319

A. CLASSIFICATION OF SUBJECT MATTER
 IPC 7 C08G18/34 C08G18/81 C08F220/36

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
 IPC 7 C08G C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 243 890 A (EASTMAN KODAK CO) 4 November 1987 (1987-11-04) page 2, line 8 -page 4, line 32 examples 1,2 ---	1-5, 9, 11, 12, 15, 16
A	US 5 270 431 A (BLUM RAINER) 14 December 1993 (1993-12-14) column 3, line 32 -column 9, line 17 column 11, line 52 -column 12, line 34; example 1 ---	1, 9, 15-18
A	US 5 364 903 A (TAKAYAMA YUJI ET AL) 15 November 1994 (1994-11-15) column 2, line 32 - line 65 example 1 ---	1, 9, 11, 12, 15
	-/--	

Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search <p style="text-align: center;">25 July 2000</p>	Date of mailing of the international search report <p style="text-align: center;">08/08/2000</p>
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016	Authorized officer <p style="text-align: center;">Neugebauer, U</p>

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 00/08319

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 323 120 A (MINNESOTA MINING & MFG) 5 July 1989 (1989-07-05) cited in the application page 2, line 45 -page 3, line 14 examples 1,6-8 -----	1,9,11, 12,15

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 00/08319

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0243890 A	04-11-1987	JP 62267258 A	19-11-1987
		US 4727126 A	23-02-1988
US 5270431 A	14-12-1993	DE 3724368 A	02-02-1989
		DE 3872329 A	30-07-1992
		EP 0303069 A	15-02-1989
		JP 1040513 A	10-02-1989
US 5364903 A	15-11-1994	JP 3247610 A	05-11-1991
		DE 69022941 D	16-11-1995
		DE 69022941 T	15-05-1996
		EP 0419043 A	27-03-1991
		JP 3163116 A	15-07-1991
EP 0323120 A	05-07-1989	AU 2709388 A	06-07-1989
		BR 8806957 A	29-08-1989
		CA 1337619 A	21-11-1995
		DE 3888815 D	05-05-1994
		DE 3888815 T	13-10-1994
		DK 724788 A	01-07-1989
		ES 2061697 T	16-12-1994
		HK 1007688 A	23-04-1999
		JP 2006358 A	10-01-1990
		JP 2869078 B	10-03-1999
		KR 9701246 B	04-02-1997
		MX 169784 B	26-07-1993
		RU 2051939 C	10-01-1996
		RU 2057777 C	10-04-1996
		RU 2070208 C	10-12-1996
		US 5130347 A	14-07-1992
		US 5925715 A	20-07-1999
ZA 8809642 A	30-08-1989		