



Office de la Propriété
Intellectuelle
du Canada

Un organisme
d'Industrie Canada

Canadian
Intellectual Property
Office

An agency of
Industry Canada

CA 2038788 C 2002/07/02

(11)(21) **2 038 788**

(12) **BREVET CANADIEN
CANADIAN PATENT**

(13) **C**

(22) Date de dépôt/Filing Date: 1991/03/21

(41) Mise à la disp. pub./Open to Public Insp.: 1991/10/25

(45) Date de délivrance/Issue Date: 2002/07/02

(30) Priorité/Priority: 1990/04/24 (513,680) US

(51) Cl.Int.⁵/Int.Cl.⁵ C09J 7/02, B32B 7/12, B05D 5/10,
B32B 27/08

(72) Inventeurs/Inventors:
Paquette, Susan Z., US;
Johannsen, Heiner, US

(73) Propriétaire/Owner:
MINNESOTA MINING AND MANUFACTURING
COMPANY, US

(74) Agent: SMART & BIGGAR

(54) Titre : FILM COMPOSITE A ADHESIF REPOSITIONNABLE LUI PERMETTANT D'ETRE LIAISONNE A UN
SUBSTRAT PLASTIFIE

(54) Title: FILM COMPOSITE HAVING REPOSITIONABLE ADHESIVE BY WHICH IT CAN BECOME PERMANENTLY
BONDED TO A PLASTICIZED SUBSTRATE

(57) **Abrégé/Abstract:**

A film composite has a thin flexible decorative backing bearing a layer of adhesive which affords good repositionability and yet can become permanently bonded to highly plasticized substrates such as vinyl films containing migratable monomeric plasticizers. Such substrates include wall coverings and vinyl coated fabrics. The adhesive is a blend of an acrylic latex adhesive and a heat-activatable urethane latex adhesive, which blend has been coated onto the backing from an aqueous emulsion. Useful backings include vinyl, polyurethane, and polyolefin films.



Abstract of the Disclosure

5 A film composite has a thin flexible decorative
backing bearing a layer of adhesive which affords good
repositionability and yet can become permanently bonded to
highly plasticized substrates such as vinyl films
containing migratable monomeric plasticizers. Such
substrates include wall coverings and vinyl coated
fabrics. The adhesive is a blend of an acrylic latex
adhesive and a heat-activatable urethane latex adhesive,
10 which blend has been coated onto the backing from an
aqueous emulsion. Useful backings include vinyl,
polyurethane, and polyolefin films.

15

20

25

30

35

FILM COMPOSITE HAVING REPOSITIONABLE ADHESIVE BY WHICH IT
CAN BECOME PERMANENTLY BONDED TO A PLASTICIZED SUBSTRATE

5

Background of the Invention

Field of the Invention

10 The invention is concerned with a flexible,
adhesive-backed film composite that has an adhesive layer
by which it can become permanently bonded to substrates
containing migratable monomeric plasticizers, in spite of
the tendency of such plasticizers to migrate into and to
15 soften the adhesive. The invention is particularly
concerned with the adhesive layer of such a film
composite.

Description of the Related Art

20 As is pointed out in U.S. Pat. No. 4,605,592
(Paquette et al.), highly plasticized vinyl substrates
previously had been decorated by hand painting or air
brushing screen-printing inks. While prefabricated
graphics in the form of adhesive-backed vinyl film bearing
screen-printed graphics would have been less expensive,
25 they had not been adapted for such use "due to the
wrinkling of the vinyl film and loss of adhesion to the
vinyl substrate ... attributable, at least in part, to the
migration of monomeric plasticizers from the vinyl
substrate into the vinyl film and adhesive" (col. 1, lines
30 24-33). These vinyl substrates contain as much as 25-100
parts of monomeric plasticizer, usually dioctylphthalate,
to 100 parts of vinyl resin.

35 In general, low-cost monomeric plasticizers are
more migratory than are those of higher cost, so that

attempts by manufacturers of plasticized substrates to economize often exacerbate the problem of adhering a decorative, adhesive-backed flexible film to those substrates.

5 The Paquette patent provides a composite decorative, article that is capable of maintaining adhesion and remaining substantially wrinkle free when adhered to vinyl substrates that contain migratable monomeric plasticizer. The decorative film composite of
10 the Paquette patent has (1) a polyvinyl chloride film layer that preferably is receptive to screen printing inks, (2) a layer of a plasticizer-resistant pressure-sensitive adhesive, e.g., a terpolymer of by weight 52.5 parts of n-butylacrylate, 37.5 parts methyl
15 acrylate, and 10 parts acrylic acid, and (3) an intermediate, migratable-plasticizer barrier layer such as an aliphatic polyurethane resin. After being coated and dried, the adhesive can be crosslinked, e.g., by exposure to UV radiation when it contains a photocrosslinker such as benzophenone, thus making the adhesive layer more
20 resistant to any plasticizer that migrates from a vinyl substrate. The pressure-sensitive adhesives of the examples of the Paquette patent are polymerized in solution and coated from solution.

25

Summary of the Invention

 The present invention provides an adhesive-backed film composite which, like the composite decorative article of the Paquette patent, has a thin,
30 flexible backing that can be decorative. Like the composite decorative article of the Paquette composite, the adhesive of the novel film composite employs an acrylic polymer and can be pressure-sensitive, although it does not need to be tacky to the touch at ordinary room
35 temperatures, and even when its adhesive layer is nontacky

to the touch, the novel film composite becomes permanently bonded at room temperature under fingertip pressure to highly plasticized substrates such as vinyl films or vinyl coated papers, fabrics or scrims containing migratable monomeric plasticizer. Such substrates are used extensively, e.g., as wall coverings, soft side truck coverings, flexible signs, and awnings. Because the adhesive blend is resistant to plasticizers even without crosslinking, the manufacturing expense associated with crosslinking can be avoided.

In addition, the novel film composite has excellent positionability, repositionability, and removability features when first applied to a plasticized substrate. Then, after being properly positioned and subjected to pressure comparable to fingertip pressure, the novel composite quickly becomes permanently bonded to the substrate and, within a short time, would be very difficult to remove. It has also been shown that this adhesive blend when incorporated in with vinyl film composites can improve the appearance of the construction when applied and aged on plasticized substrates.

Briefly, the film composite of the invention has a thin, flexible backing which bears a layer of adhesive comprising, by weight, a blend of

- 1) from 10 to 99% of an acrylic latex adhesive and
 - 2) from 1 to 90% of a heat-activatable urethane latex adhesive, a film of which has an elongation of at least 100%,
- which blend has been coated from an aqueous emulsion.

As compared to an otherwise identical composite except omitting the heat-activatable urethane latex adhesive from the adhesive layer, the adhesive blend of the novel composite tends to provide better adhesive values even though the bonds are made at ordinary room temperatures. This improvement is surprising, considering that the urethane latex adhesive by itself must be heat activated.

The acrylic latex adhesive and heat-activatable urethane latex adhesive are most easily blended together when approximately equal in pH and emulsifier charge. Preferably, their emulsifiers are both anionic or both cationic or one is anionic while the other is nonionic.

In general, any coalescing agent present in either latex should be compatible with the other latex.

A preferred acrylic latex adhesive is an acrylic emulsion polymer of

a) from 84 to 100 parts of acrylic acid ester of nontertiary alcohol, the alkyl groups of which contain an average of from 2 to 12 carbon atoms, and

b) correspondingly from 16 to 0 parts of an ethylenically unsaturated, copolymerizable monomer.

Optimum resistance to migratable monomeric plasticizer is achieved when the relationship of said average number of carbon atoms in the alkyl groups is from 2 to 5, more preferably from 2 to 3. By keeping that average low, the adhesive blend tends to have low initial adhesion values, thus enhancing repositionability, but adhesion tends to build to a desirably high level within a reasonably short period of times. Furthermore, when said average number of carbon atoms is low, the adhesive blends tend to have superior resistance to shear forces.

When the above-identified monomer a) or blend of monomers a) and b) is or are emulsified in a surfactant system with a free-radical initiator, polymerization readily proceeds to completion (>98% conversion) at moderately elevated temperatures, and an inherent viscosity of more than 5.0 is readily attained without further processing. When the resulting latex is filtered, typically less than 0.01 g of coagulum per 1000 g latex is collected.

60557-4094

5

Because the blend of acrylic latex and urethane latex adhesive is coated from an aqueous emulsion, it should be unnecessary to employ apparatus to prevent volatiles from polluting the atmosphere.

5 The adhesive layer of the novel film composite can be a blend of the urethane latex adhesive and an acrylic emulsion homopolymer of monomer a). However, stronger bonds to plasticized substrates are obtained from the use of acrylic emulsion copolymers of monomers a) and b), especially when
10 monomer b) is highly polar, and there is no current economic advantage in avoiding the use of a highly polar monomer b). Useful highly polar monomers include acrylic acid, methacrylic acid, acrylamide, methacrylamide, itaconic acid, acrylonitrile, methacrylonitrile, and itaconic acid. Other useful
15 copolymerizable monomers b) include methylmethacrylate, vinyl acetate, N-vinyl pyrrolidone, and styrene sulfonate.

 The heat-activatable urethane latex adhesive employed in the adhesive layer of the novel film composite should have an elongation of at least 200% and preferably at least 400%.
20 Otherwise, the adhesive may be unduly firm and may afford undesirably low adhesion values. Best results have been obtained with polyester polyurethanes when compared with polycarbonate polyurethanes and polyether polyurethanes. Similar functionality of the plasticizer in the vinyl,
25 typically a phthalate ester or polymeric polyester, and the polyester polyurethane is the reason for the improved performance of this construction.

 According to one aspect of the present invention, there is provided an adhesive-backed film composite comprising
30 a thin flexible backing bearing a layer of adhesive by which the film composite can become permanently bonded to a substrate

60557-4094

5a

containing monomeric plasticizer, said adhesive comprising, by weight, a blend of 1) from about 10 to 99% of an acrylic latex adhesive, wherein said acrylic latex adhesive has a glass transition temperature of 0°C to -50°C and is an acrylic emulsion polymer of a) from 84 to 100 parts of acrylic acid ester of nontertiary alcohol, the alkyl groups of which contain an average of from 2 to 12 carbon atoms, and b) correspondingly from 16 to 0 parts of an ethylenically unsaturated copolymerizable monomer, wherein said monomer is selected from the group consisting of acrylic acid, methacrylic acid, acrylamide, methacrylamide, itaconic acid, acrylonitrile, methacrylonitrile, methylmethacrylate, vinyl acetate, N-vinyl pyrrolidone and styrene sulfonate; 2) from 1 to 90% of a heat-activatable urethane latex adhesive, a film of which has an elongation of at least 100%, wherein said blend has been coated onto the backing from an aqueous emulsion.

According to another aspect of the present invention, there is provided a laminate of a vinyl substrate containing migratable plasticizer and an adhesive-backed film composite comprising a thin flexible backing selected from vinyl, polyurethane, and polyolefin films, which backing bears a layer of adhesive comprising, by weight, a blend of 1) from about 10 to 99% of an acrylic latex adhesive, wherein said acrylic latex adhesive is an acrylic emulsion polymer of a) from 84 to 100 parts of acrylic acid ester of nontertiary alcohol, the alkyl groups of which contain an average of from 2 to 12 carbon atoms, and b) correspondingly from 16 to 0 parts of an ethylenically unsaturated, copolymerizable monomer, wherein said monomer is selected from the group consisting of acrylic acid, methacrylic acid, acrylamide, methacrylamide, itaconic acid, acrylonitrile, methacrylonitrile, methylmethacrylate, vinyl acetate, N-vinyl pyrrolidone and styrene sulfonate; 2) from 1 to 90% of a heat-activatable urethane latex adhesive,

60557-4094

5b

wherein said urethane latex adhesive is polyester polyurethane and a film of which has an elongation of at least 100%, wherein said blend has been coated onto the backing from an aqueous emulsion.

5

Detailed Description

The flexible backing of the novel film composite preferably is a decorative polymeric film such as polyurethane, polyolefin, and plasticized vinyl films or a soft metallic film such as aluminum. When the backing is a polyurethane film, it is more durable when it is aliphatic. Plasticized vinyl films are currently less

60557-4094

6

expensive than polyurethane films and are widely used in the graphics industry because of their versatility, durability, and low cost. When the backing is a plasticized vinyl film, its plasticizer preferably is primarily a nonmigratable polymeric plasticizer. Preferred vinyl backings are disclosed in the Paquette patent and are available as SCOTCHCAL TM Film Series 3650 and CONTROLTAC TM Film Series 180 from 3M, to which the present application is assigned.

A novel film composite that has a vinyl backing preferably incorporates a barrier layer as disclosed in the Paquette patent, thus better protecting the film backing from becoming wrinkled by migratable monomeric plasticizers of substrates to which the novel film composite may be adhered.

A preferred heat-activatable urethane latex adhesive is a polyester-polyurethane latex, a film of which has an elongation of about 500% and is commercially available as "Baybond"™ 402A from Mobay.

The acrylic latex adhesive of the adhesive blend of the film composite of the invention preferably is a copolymer of monomer a) selected from ethyl acrylate and n-butyl acrylate and a highly polar monomer b). For example, preferred adhesive blends employ acrylic emulsion copolymers of, by weight

from 50 to 90 parts of ethyl acrylate,
from 10 to 50 parts of n-butyl acrylate, and
from 2 to 12 parts of a copolymerizable, highly polar monomer selected from acrylic acid and methacrylic acid.

Optimum resistance to migratable plasticizers is achieved when at least 65% of ethyl acrylate is employed.

60557-4094

7

Preferably, the acrylic latex adhesive has a calculated Tg of from 0°C to -50°C. If its calculated Tg were substantially above that preferred range, the adhesion of the novel film composite might fail at low temperatures upon being subjected to stresses such as from impact or vibrations. If its calculated Tg were substantially below that preferred range, the adhesive layer of the novel film composite might be too tacky to permit it to be repositioned before it has been pressed into full contact with a substrate.

TESTING

180° Pullback Value

180° pullback adhesions are run according to ASTM D-1000, Method B, with an InstronTM tester. The adhesion tests are conducted on specimens after dwell as indicated.

In the following examples, all parts are by weight.

Example 1

A titanium dioxide pigmented, plasticized poly(vinylchloride) film 50 μ m in thickness while supported by a paper carrier web was coated with a 40% solids aqueous emulsion of a blend of equal parts of

- 1) an acrylic emulsion copolymer of 80 parts ethyl acrylate, 16 parts n-butyl acrylate, and 4 parts acrylic acid, and
- 2) a heat-activatable polyester-polyurethane latex ("Baybond" 402A from Mobay).

The coating was dried 10 minutes at 66°C to a dry coating weight of 50 mg/m². The adhesive side was then laminated to a silicone release liner, and the paper carrier web was discarded to provide an adhesive-backed film composite of the invention.

60557-4094

8

The composite was tested for 180° Pullback Adhesion Value from a plasticized vinyl substrate, viz., "Duraskin"TM from Verseidag Industrie texilien, West Germany, and having a weight of 18 ounces/yd² (610 g/m²). Table I reports the results after the indicated dwell.

Table I

180° Pullback Adhesion Value (N/cm)				
<u>Initial</u>	<u>2 hr, R.T.</u>	<u>24 hr, R.T.</u>	<u>1 wk., 66°C</u>	<u>2 wk., 66°C</u>
3.9	5.6	5.6	7.7	12.0

The relatively low initial adhesion was the result of good repositionability of the adhesive, but as shown after accelerated aging, adhesion eventually built to a satisfactory level.

Examples 2-8

A series of adhesive-backed film composites were prepared and tested as in Example 1 except using differing ratios of the acrylic latex adhesive and urethane latex adhesive as indicated in Table II. Also, the 180° Pullback Adhesion Values were from a different plasticized vinyl substrate, viz., "Prismax"TM 14 oz awning material from Advanced Vinyl, Inc. The composite of Example 5 was identical to that of Example 1, and Examples 2 and 8 were comparative.

60557-4094

9

Table II

<u>Example</u>	acrylic/ urethane <u>ratio</u>	180° Pullback Adhesion Value (N/cm)		
		after <u>24 hr, R.T.</u>	<u>1 wk., 66°C</u>	<u>2 wk., 66°C</u>
2	100/0	1.4	*	*
3	90/10	3.9	13.0	13.0
4	75/25	4.6	12.8	13.0
5	50/50	6.9	12.8	13.0
6	25/75	6.0	9.5	9.1
7	10/90	5.3	7.9	7.0
8	0/100	5.1	5.6	5.5

* Inadequate initial adhesion

Example 9

An adhesive-backed film composite was prepared as in example 1 except replacing the acrylic emulsion copolymer with a commercially available acrylic latex adhesive, viz., "EVA-TAK"TM 72-9685 from National Starch. The resulting composite was tested on the plasticized vinyl substrate ("Prismax") employed in Examples 2-8. Test results are reported in Table III together with a comparative composite A that was an identical acrylic adhesive from the adhesive blend.

Table III

<u>Example</u>	acrylic/ urethane <u>ratio</u>	180° Pullback Adhesion Value (N/cm)		
		after <u>24 hr, R.T.</u>	<u>1 wk., 66°C</u>	<u>2 wk., 66°C</u>
9		5.3	9.5	10.0
A		6.3	1.6	1.4

60557-4094

10

CLAIMS:

1. An adhesive-backed film composite comprising a thin flexible backing bearing a layer of adhesive by which the film composite can become permanently bonded to a substrate
5 containing monomeric plasticizer, said adhesive comprising, by weight, a blend of

1) from about 10 to 99% of an acrylic latex adhesive, wherein said acrylic latex adhesive has a glass transition temperature of 0°C to -50°C and is an acrylic emulsion polymer
10 of

a) from 84 to 100 parts of acrylic acid ester of nontertiary alcohol, the alkyl groups of which contain an average of from 2 to 12 carbon atoms, and

b) correspondingly from 16 to 0 parts of an
15 ethylenically unsaturated copolymerizable monomer, wherein said monomer is selected from the group consisting of acrylic acid, methacrylic acid, acrylamide, methacrylamide, itaconic acid, acrylonitrile, methacrylonitrile, methylmethacrylate, vinyl acetate, N-vinyl pyrrolidone and styrene sulfonate;

20 2) from 1 to 90% of a heat-activatable urethane latex adhesive, a film of which has an elongation of at least 100%, wherein said blend has been coated onto the backing from an aqueous emulsion.

2. The adhesive-backed film composite as defined in
25 claim 1 wherein said acrylic acid ester is a mixture of, by weight,

from 50 to 90% of ethyl acrylate and correspondingly from 50 to 10% of n-butyl acrylate, and said ethylenically unsaturated, copolymerizable monomer is 1 to 16% of highly

60557-4094

11

polar monomer, wherein said polar monomer is selected from the group consisting of acrylic acid, methacrylic acid, acrylamide, methacrylamide, itaconic acid, acrylonitrile, and methacrylonitrile.

5 3. The adhesive-backed film composite as defined in claim 2 wherein the amount of said highly polar monomer is from 2 to 12% by weight.

4. A laminate of a vinyl substrate containing migratable plasticizer and an adhesive-backed film composite comprising a
10 thin flexible backing selected from vinyl, polyurethane, and polyolefin films, which backing bears a layer of adhesive comprising, by weight, a blend of

1) from about 10 to 99% of an acrylic latex adhesive, wherein said acrylic latex adhesive is an acrylic emulsion
15 polymer of

a) from 84 to 100 parts of acrylic acid ester of nontertiary alcohol, the alkyl groups of which contain an average of from 2 to 12 carbon atoms, and

b) correspondingly from 16 to 0 parts of an
20 ethylenically unsaturated, copolymerizable monomer, wherein said monomer is selected from the group consisting of acrylic acid, methacrylic acid, acrylamide, methacrylamide, itaconic acid, acrylonitrile, methacrylonitrile, methylmethacrylate, vinyl acetate, N-vinyl pyrrolidone and styrene sulfonate;

25 2) from 1 to 90% of a heat-activatable urethane latex adhesive, wherein said urethane latex adhesive is polyester polyurethane and a film of which has an elongation of at least 100%, wherein said blend has been coated onto the backing from an aqueous emulsion.

60557-4094

12

5. The laminate as defined in claim 4 wherein said vinyl substrate is selected from the group consisting of vinyl films, vinyl-coated paper, fabric, and scrim.

SMART & BIGGAR

OTTAWA, CANADA

PATENT AGENTS