

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
14 May 2009 (14.05.2009)

PCT

(10) International Publication Number
WO 2009/061351 A1

(51) International Patent Classification:
B41M 5/50 (2006.01) *B41M 5/52* (2006.01)

(74) Common Representative: EASTMAN KODAK COMPANY; 343 State Street, Rochester, NY 14650-2201 (US).

(21) International Application Number:
PCT/US2008/012094

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(22) International Filing Date: 24 October 2008 (24.10.2008)

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(25) Filing Language: English
(26) Publication Language: English
(30) Priority Data:
11/936,810 8 November 2007 (08.11.2007) US

Published:

— with international search report

(71) Applicant (for all designated States except US): EASTMAN KODAK COMPANY [US/US]; 343 State Street, Rochester, NY 14650-2201 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **SHAW-KLEIN, Lori Jeanne** [US/US]; 343 State Street, Rochester, NY 14650 (US). **ROMANO, Charles, Eugene, Jr.** [US/US]; 343 State Street, Rochester, NY 14650 (US).



WO 2009/061351 A1

(54) Title: PROCESS FOR MAKING INKJET RECORDING ELEMENT

(57) **Abstract:** A method of making an inkjet recording element is disclosed in which the inkjet recording element has a support and, on the support, (a) a porous base layer comprising particles of fumed silica and a hydrophilic binder and (b) an optional porous gloss layer above the base layer comprising particles of colloidal silica and a hydrophilic binder, wherein the particles of fumed silica and colloidal silica are anionic. The method can produce an inkjet recording element having improved image quality, including reduced coalescence and higher gloss.

PROCESS FOR MAKING INKJET RECORDING ELEMENT

FIELD OF THE INVENTION

The invention relates to a method of making an inkjet recording element. More specifically, the invention relates to a method of making a porous recording element comprising an ink-receiving layer comprising anionic fumed silica and a hydrophilic hydroxyl-containing polymer, wherein the layer is crosslinked with a boron-containing crosslinker that diffuses into the layer from below.

10

BACKGROUND OF THE INVENTION

In a typical inkjet recording or printing system, ink droplets are ejected from a nozzle at high speed towards a recording element or medium to produce an image on the medium. The ink droplets, or recording liquid, generally comprise a recording agent, such as a dye or pigment, and a large amount of solvent. The solvent, or carrier liquid, typically is made up of water, an organic material such as a monohydric alcohol, a polyhydric alcohol, or mixtures thereof.

An inkjet recording element typically comprises a support having on at least one surface thereof at least one ink-receiving layer. There are generally two types of ink-receiving layers (IRL's). The first type of IRL comprises a non-porous coating of a polymer with a high capacity for swelling and absorbing ink by molecular diffusion. Cationic or anionic substances are typically added to the coating to serve as a dye fixing agent or mordant for the anionic or cationic dye, respectively. This coating is optically transparent and very smooth, leading to a high gloss "photo-grade" receiver. However, with this type of IRL, the ink is usually absorbed slowly into the IRL and the print is not instantaneously dry to the touch.

The second type of IRL comprises a porous coating of inorganic, polymeric, or organic-inorganic composite particles, a polymeric binder, and additives such as dye-fixing agents or mordants. These particles can vary in chemical composition, size, shape, and intra/inter-particle porosity. In this case,

the printing liquid is substantially absorbed into the open pores of the IRL to obtain a print that is instantaneously dry to the touch.

Organic and/or inorganic particles in a porous layer form pores by the spacing between the particles. The binder is used to hold the particles

5 together. However, to maintain a high pore volume, it is desirable that the amount of binder is limited. Too much binder would start to fill the pores between the particles or beads, which would reduce ink absorption. On the other hand, too little binder may reduce the integrity of the coating, thereby causing cracking.

As the quality and density of inkjet printing increases, so does the 10 amount of ink applied to the inkjet recording element (also referred to as the “receiver”). For this reason, it is important to provide sufficient void capacity in the medium to prevent puddling or coalescence and inter-color bleed. At the same time, print speeds are increasing in order to provide convenience to the user.

Thus, not only is sufficient capacity required to accommodate the increased 15 amount of ink, but in addition, the medium should be able to handle increasingly greater ink flux in terms of ink volume/unit area/unit time.

A porous ink jet recording element usually contains at least two layers: a lower layer, sometimes referred to as a base layer as the main sump for the liquids in the applied inkjet ink, and an optional upper layer, sometimes

20 referred to as a gloss layer, often an image-receiving layer, coated in that order on a support. The layers may be sub-divided or additional layers may be coated between the support and the uppermost gloss layer. The layers may be coated on a resin coated or a non-resin coated support. The layers may be coated in one or more passes using known coating techniques such as roll coating, premetered 25 coating (slot or extrusion coating, slide or cascade coating, or curtain coating) or air knife coating. When coating on a non-resin coated paper, in order to provide a smooth, glossy surface, special coating processes may be utilized, such as cast coating or film transfer coating. Calendering with pressure and optionally heat may also be used to increase gloss to some extent.

30 Recently, higher speed printing has been demanded of inkjet printers. A problem arises when multiple ink droplets are deposited in very close

proximity in a short time. If the porosity of the receiver is not adequate, the drops will coalesce, severely degrading the image quality. The amount of binder in the coated layers is important in the performance of the ink-recording element. If too much binder is present, the porosity of the receiver is diminished resulting in 5 coalescence, and if too little binder is present, unacceptable cracking is observed.

EP Patent Publication No. 1,464,511 to Bi et al. discloses a two-layer inkjet receiver on a resin-coated support. The bottom layer comprises a dispersion of fumed silica treated with aluminum chlorohydrate to transform the silica particles into a cationic form, as indicated by a zeta potential above +27 mv 10 after treatment. The cationic silica particle dispersion was mixed with boric acid and poly(vinyl alcohol) to form a coating composition for the bottom layer. The coating composition for the top layer comprised a dispersion of cationic colloidal silica, glycerol, and a minor amount of coating aid. The top and bottom layers were cascade coated at the same time in one pass, that is, simultaneous coating is 15 disclosed in context. The coating weight of the bottom layer was 28 to 30 g/m² and the top layer was 0.2 g/m². However, there is a problem with this type of inkjet receiver in that image quality is reduced by coalescence when high ink levels are printed.

In the comparative example 4 of the above-mentioned EP Patent 20 Publication No. 1,464,511, a comparative inkjet recording element with a cationic fumed silica base layer and an anionic colloidal silica upper layer is made and tested.

US Patent Publication No. 2003/0224129 to Miyachi et al. discloses an inkjet recording element similar to the above-mentioned EP Patent 25 Publication No. 1,464,511 in which a layer mainly containing cationic colloidal silica is over a base layer containing cationized anionic inorganic particles that can be fumed silica.

US Patent No. 7,015,270 to Scharfe et al. discloses an inkjet recording element comprising fumed silica and a cationic polymer in which the 30 dispersion used to make the inkjet recording element has a positive zeta potential.

It is known to provide crosslinker, for a binder in an ink-receiving layer, by diffusion of the crosslinker into the layer. For example, Riou, et al., in US Patent No. 4,877,686, describe a recording sheet for inkjet printing and a process for its preparation. The coating composition comprises filler, such as an inorganic particle, and a polyhydroxylic polymeric binder, such as poly (vinyl alcohol). In the coating process, the PVA is gelled or coagulated by borax. The gelling agent may be deposited on the base material prior to the coating. Alternatively, the gelling agent can be incorporated in the coating composition, but should be temporarily deactivated. For example, boric acid may be used in the coating composition and activated by contact with a higher pH base layer. A drawback of this incorporated crosslinker process is that although the boric acid does not completely gel the PVA coating composition, viscosity increases may be expected, which may have a negative impact on coating quality throughout a coating event. The disclosure of Riou, et al., is mainly directed to providing more regular-shaped dots. High print density and gloss demanded of a photographic quality print are not addressed by Riou, et al.

Kuroyama, et al., in EP Patent Publication No. 493,100, disclose an inkjet recording paper comprising a substrate which is coated with boric acid or borate and an inkjet recording layer formed on the borax-coating and comprising synthetic silica and poly(vinyl alcohol). The silica may be wet-process silica, silica gel, or ultrafine silica obtained by a dry process. The exemplary silica materials are silica gels with high surface area, but with large secondary particle size of several microns or more. These materials do not provide a high gloss expected for a photo-quality print. Cationic polyelectrolytes may be added to improve water resistance, thus implying a composition compatible with cationic species.

Liu, et al., in Patent Publication No. 2004/0022968, disclose an inkjet recording element including a substrate having thereon a) a subbing layer for a binder and a borate derivative and b) an image-receiving layer including a cross-linkable polymer and inorganic particles of, for example, cationically modified fumed silica or naturally cationic fumed alumina.

PROBLEM TO BE SOLVED BY THE INVENTION

It is an object of this invention to provide a method of making an inkjet receiver that, in various embodiments, can provide improved color print density, reduced coalescence, and improved gloss while avoiding excessive 5 cracking of the one or more ink-receiving layers in the receiver.

SUMMARY OF THE INVENTION

The present invention is directed to overcoming one or more of the problems set forth above. Briefly summarized, according to one aspect of the present invention, a method of manufacturing an inkjet recording element 10 comprises the steps of:

- (a) providing a support;
- (b) treating the support with a subbing composition comprising a boron-containing crosslinking compound; and
- (c) coating in order over the support:
 - 15 (i) a first coating composition, for an ink-receiving layer, comprising particles of anionic fumed silica and hydrophilic hydroxyl-containing polymer, as the primary binder, capable of being substantially cross-linked by the boron-containing crosslinking compound not contained in the first composition; and
 - 20 (ii) an optional second coating composition, for a gloss layer, comprising particles of anionic colloidal silica and a binder; wherein said particles of fumed silica and colloidal silica exhibit a zeta potential below negative 15 mv;
 - 25 wherein the weight of binder to total solids in the first and second coating compositions is independently between 5% and 30%; and wherein the boron-containing crosslinking compound diffuses into at least the ink-receiving layer to crosslink the hydrophilic hydroxyl-containing polymer in the layer.

In other words, the fumed silica in the ink-receiving layer and the 30 colloidal silica in the optional gloss layer are both anionic particles. In one embodiment, the colloidal silica in the gloss layer also comprises hydrophilic

hydroxyl-containing polymeric binder that is crosslinked with a crosslinking compound.

In another embodiment, for manufacturing an inkjet recording element especially designed for use with dye-based inks, the colloidal silica gloss layer is present and the median particle size of the colloidal silica is less than 45 nm. In another preferred embodiment, for manufacturing an inkjet recording element especially designed for use with pigment-based inks, the support is a resin-coated paper, there is no gloss layer, and the weight of total binder in the ink-receiving layer is less than 15 percent.

The present method is capable of making inkjet receivers having improved image quality (reduced coalescence) and higher dye ink optical densities in an inkjet recording element. The inventive process also has the advantage of ease of handling precursor dispersions and improved properties of the resulting inkjet recording element, including improved gloss and reduced cracking for the elements having higher porosity in one or more layers of the element.

It is very unexpected that an anionic composition for the ink-receiving layers in the inkjet recording element tends to provide better dye density than a comparable cationic formulation, especially since cationic materials would be expected to mordant more readily the typically used anionic dyes than anionic compositions for the ink-receiving layers. Surprising also, anionic compositions comprising anionic fumed silica tend to require less binder than comparable cationic fumed silica, as shown in examples.

In describing the invention herein, the following definitions generally apply:

The term “porous layer” is used herein to define a layer that is characterized by absorbing applied ink substantially by means of capillary action rather than liquid diffusion. The porosity is based on pores formed by the spacing between particles, although porosity can be affected by the particle to binder ratio. The porosity of a layer may be predicted based on the critical pigment volume concentration (CPVC). An inkjet recording element having one or more porous

layers, preferably substantially all layers, over the support can be referred to as a “porous inkjet recording element,” even if the support is not porous.

Particle sizes referred to herein, unless otherwise indicated, are number weighted median particle sizes. In particular, in the case of colloidal 5 silica, the median particle size is a number weighted median measured by electron microscopy, using high-resolution TEM (transmission electron microscopy) images, as will be appreciated by the skilled artisan. Herein each particle diameter is the diameter of a circle that has the same area as the equivalent projection area of each particle. In the case of colloidal silica, as compared to fumed silica, the 10 colloidal particles may be aggregated on average up to twice the primary particle diameter, which does not unduly affect the measurement of primary particle size.

In the case of mixtures of two populations of particles, the median particle size of the mixture is merely the median particle size of the mixture.

Typically, for equal weights of two median particle sizes in a mixture, the median 15 particle size of the mixture is relatively closer to the median particle size of the component having the smaller median particle size.

It is difficult to measure the secondary size of fumed metal oxide particles because the methods commonly used treat the particles as spheres and the results are calculated accordingly. (The primary particle size of fumed silica in 20 dispersion can be measured by TEM, as with colloidal silica.) Fumed silica particles are not spheres but consist of aggregates of primary particles. In the case of fumed silica, the median secondary particle size is as determined by light scattering measurements of diluted particles dispersed in water, as measured using laser diffraction or photon correlation spectroscopy (PCS) techniques employing 25 NANOTRAC (Microtac Inc.), MALVERN, or CILAS instruments or essentially equivalent means. Unless otherwise indicated, particle sizes refer to secondary particle size. The median particle size of inorganic particles in various products sold by commercial manufacturers is usually provided in the product literature. However, for the purpose of making accurate comparisons among products, the 30 particular measurement technique may need to be taken into consideration. Use of

a single testing method eliminates potential variations among different testing methods.

As used herein, the terms “over,” “above,” “upper,” “under,” “below,” “lower,” and the like, with respect to layers in inkjet media, refer to the 5 order of the layers over the support, but do not necessarily indicate that the layers are immediately adjacent or that there are no intermediate layers.

In regard to the present method, the term “image-receiving layer” is intended to define a layer that is used as a pigment-trapping layer, dye-trapping layer, or dye-and-pigment-trapping layer, in which the printed image substantially 10 resides throughout the layer. In the case of a dye-based ink, the image may optionally reside in more than one adjacent image-receiving layer.

In regard to the present method, the term “gloss layer” is intended to define an uppermost coated layer in the inkjet recording element that provides additional gloss compared to the base layer alone. It is an image-receiving layer.

15 In regard to the present method, the term “base layer” (sometimes also referred to as a “sump layer” or “ink-carrier-liquid receptive layer”) is used herein to mean a layer that is adjacent to the support or an optional subbing layer (that is with no intervening ink-receiving layer) that absorbs a substantial amount of ink-carrier liquid. Such a layer can be under another ink-receiving layer or, if it 20 is the only layer in the inkjet recording element, it is also the uppermost layer. In use, a substantial amount, preferably most, of the carrier fluid for the ink is received and remains in the base layer until dried. The base layer can be an image-containing layer (a pigment-trapping layer or dye-trapping layer), especially if it is the only layer. Even with an upper layer, for example, a gloss layer, 25 relatively small amounts of the ink colorant, in the case of a dye, may leave the gloss layer and enter the base layer, mostly in an upper portion. Preferably, the base layer is the ink-retaining layer nearest the support, with the exception of subbing layers. The base layer is the thickest layer in the inkjet recording element if there are other ink-receiving layers such as a gloss layer.

30 The term “subbing layer” refers to any layer between the base layer and the support having a dry weight of less than 5 g/m², preferably less than 1

g/m². The subbing layer may be porous or non-porous and may be used to improve adhesion or accomplish some other function such as providing a crosslinking agent for diffusion.

The term “ink-receptive layer” or “ink-retaining layer” includes any 5 and all layers above the support that are receptive to an applied ink composition, that absorb or trap any part of the one or more ink compositions used to form the image in the inkjet recording element, including the ink-carrier fluid and/or the colorant, even if later removed by drying. An ink-receptive layer, therefore, can include an image-receiving layer, in which the image is formed by a dye and/or 10 pigment, a base layer, a subbing layer, or any additional layers, for example between a base layer and a topmost layer of the inkjet recording element. Typically, all layers above the support are ink-receptive. The support on which 15 ink-receptive layers are coated may also absorb ink-carrier fluid. Whereas an ink-receptive layer is coated onto a support, the support is a solid material over which all the ink-receptive layers are coated during manufacture of the inkjet recording element.

DETAILED DESCRIPTION OF THE INVENTION

As indicated above, the present invention relates to a method of 20 making a porous inkjet recording element comprising, over the support, a porous base layer nearest the support, and an optional porous upper gloss layer. The porous base layer nearest the support and optional porous upper gloss layer may optionally be divided into sub-layers, preferably immediately adjacent sub-layers, in which case independently the sub-layers individually and collectively meet the claim limitations of the layer, except for the thickness limitations. However, the 25 layers, described herein, are preferably coated as a single layer.

In one embodiment, the invention is directed to a method of making an inkjet recording element consisting of a single porous base layer and a single upper gloss layer over the support, with the possible exception of layers less than 5 micrometer thick such as subbing layers below the base layer.

In a preferred embodiment, the 60-degree gloss of the unprinted inkjet recording element is at least 15 Gardner gloss units, preferably at least 20 Gardner gloss units.

5 In a preferred embodiment, the present invention is directed to a method of making an inkjet recording element comprising, in order:

(a) a porous base layer comprising particles of anionic fumed silica, and hydrophilic hydroxyl-containing polymer as the primary binder, wherein the base layer has a dry weight of 10 to 35 g/m², preferably 15 to 25 g/m², wherein the hydrophilic hydroxyl-containing polymer is crosslinked with 10 crosslinker comprising boron-containing compound, wherein the weight percent of total binder to total solids in the base layer is greater than 5.0 percent and less than 15.0 percent, preferably less than 12 percent, most preferably less than 10 percent; and

15 (b) an optional porous gloss layer above the base layer comprising particles of anionic colloidal silica and a hydrophilic binder and having a dry weight of 0.2 to 7.5 g/m², wherein the median particle size of the particles of colloidal silica is 10 to 200 nm, preferably 20 to 120 nm.

20 In one embodiment, for making inkjet recording elements designed for dye based inks, the porous gloss layer is present above the base layer and comprises particles of colloidal silica and a hydrophilic binder and has a dry weight of 1.0 to 7.5 g/m², wherein the median particle size of the particles of colloidal silica is 10 to less than 45 nm, preferably less than 40 nm, advantageously in some embodiments less than 30 nm, more preferably less than 25 nm.

25 In any case, the particles of both the fumed and colloidal silica exhibit a zeta potential below negative 15 mv.

30 The zeta potential is a measure of the surface charge of the particles, which can be shifted, for example, by any substances that become attached to the surface of the particles. Zeta potential is understood to mean the potential on the shearing surface of a particle in dispersion. In dispersions in which the particles carry acid or basic groups on the surface, the charge can be

changed by setting the pH value. An important value in connection with the zeta potential is the isoelectric point (IEP) of a particle, which can also be considered the point of zero charge. The IEP gives the pH value at which the zeta potential is zero. The IEP of silicon dioxide is less than pH 3.8. The greater the difference 5 between the pH value and IEP, the more stable the dispersion.

Particles of the same material will have the same surface charge sign and will thus repel each other. However, if the zeta potential is too small, the repelling force cannot compensate for the van der Waals attraction of the particles and this will lead to flocculation and in some cases sedimentation of the particles.

10 The zeta potential can be determined in accordance with any method known in the art and preferably for example by measuring the colloidal vibration current (CVI) of the dispersion or by determining its electrophoretic mobility. The zeta potentials of the present compositions was measured on a Malvern Instrument ZETASIZER NANO-ZS. Dispersions were diluted in water 15 of matching pH and rolled to assure good dispersion.

The colloidal silica particles in the optional gloss layer may be further characterized by surface area BET surface measurement. The preferred surface areas for the colloidal silica particles are above 50 m²/g. Relatively larger surface areas among different colloidal silica products tend to be associated with 20 smaller diameter particles. As used herein, the BET surface area measurement relies on the nitrogen adsorption method of S. Brunauer, P.H. Emmet and I. Teller, *J. Am. Chemical Society*, vol. 60, page 309 (1938).

As mentioned above, the amount of binder in an ink-receiving layer is desirably limited, because when ink is applied to inkjet media, the (typically 25 aqueous) liquid carrier tends to swell the binder and close the pores and may cause bleeding or other problems. Preferably, therefore, the base layer comprises a less than an maximum amount of binder in the base layer, to maintain the desired porosity, preferably above a minimum amount of binder sufficient to prevent or eliminate cracking and other undesirable properties.

Any suitable hydrophilic hydroxyl-containing polymer crosslinkable by a boron-containing compound may be used as the primary binder in the base layer (optionally in the gloss layer) of the inkjet recording element.

The crosslinkable hydrophilic hydroxyl-containing polymer

5 employed in at least the base layer may be, for example, poly(vinyl alcohol), partially hydrolyzed poly(vinyl acetate/vinyl alcohol), or copolymers containing hydroxyethylmethacrylate, copolymers containing hydroxyethylacrylate, copolymers containing hydroxypropylmethacrylate, hydroxy cellulose ethers such as hydroxyethylcellulose, etc. In a preferred embodiment, the crosslinkable

10 polymer containing hydroxyl groups is poly(vinyl alcohol), including partially hydrolyzed poly(vinyl acetate/vinyl alcohol) or modified or unmodified PVA, or a copolymer of PVA comprising primarily (more than 50 mole percent) monomeric repeat units containing a hydroxy group, more preferably at least 70 mole percent of such monomeric repeat units.

15 In general, particularly good results are obtained employing, as the primary binder, poly(vinyl alcohol), also referred herein as "PVA." As indicated above, the term "poly(vinyl alcohol)" includes modified and unmodified poly(vinyl alcohol), for example, acetoacetylated, sulfonated, carboxylated PVA, and the like. Copolymers of PVA, for example with ethylene oxide, are also

20 preferred as primary binder.

The poly(vinyl alcohol) preferably employed in the present invention includes common poly(vinyl alcohol), which is prepared by hydrolyzing polyvinyl acetate, and also modified poly(vinyl alcohol) such as poly(vinyl alcohol) having an anionic or non-cationic group.

25 In one embodiment, the average degree of polymerization of the poly(vinyl alcohol) prepared by hydrolyzing vinyl acetate is preferably at least 300, but is more preferably 1000 to 10,000, or a preferred viscosity of at least 30 cP, more preferably at least 40 cP in water at a concentration of 4 percent by weight at 20°C. The saponification ratio of the poly(vinyl alcohol) is preferably

30 70% to 100%, but is more preferably 75% to 95%.

5 Lesser amounts of supplemental non-hydrophilic (hydrophobic) binders may also be included in various compositions. Preferred polymers are water-soluble, but latex polymer can also be included for various reasons. (As used herein, the term "primary" refers to greater than fifty percent by weight of all binder.)

In a preferred embodiment, the supplemental polymeric binder, if different from the primary binder, may be a compatible, preferably water-soluble hydrophilic polymer such as poly(vinyl pyrrolidone), gelatin, cellulose ethers, poly(oxazolines), poly(vinylacetamides), poly(acrylic acid), poly(acrylamide), 10 poly(alkylene oxide), sulfonated or phosphated polyesters and polystyrenes, casein, zein, albumin, chitin, chitosan, dextran, pectin, collagen derivatives, collodian, agar-agar, arrowroot, guar, carrageenan, tragacanth, xanthan, rhamsan, methyl cellulose, hydroxypropyl cellulose, hydroxypropyl methyl cellulose, poly(2-ethyl-2-oxazoline), poly(2-methyl-2-oxazoline), poly(alkylene oxide), 15 poly(vinyl pyrrolidinone), poly(vinyl acetate), polyurethanes, vinyl acetate-ethylene copolymers, ethylene-vinyl chloride copolymers, vinyl acetate-vinyl chloride-ethylene terpolymers, acrylic, polymers, copolymers or derivatives thereof and the like, or combinations thereof.

Preferred hydrophobic materials can include, for example, 20 poly(styrene-co-butadiene), polyurethane latex, polyester latex, poly(n-butyl acrylate), poly(n-butyl methacrylate), poly(2-ethylhexyl acrylate), copolymers of n-butylacrylate and ethylacrylate, copolymers of vinylacetate and n-butylacrylate, and the like. Mixtures of hydrophilic and latex binders may be useful, for example, mixtures of poly(vinyl alcohol) and poly(styrene-co-butadiene) latex.

25 With respect to the boron-containing crosslinker, most preferably, a boron-containing compound such as borate or borate derivative, is contained in a subbing layer and diffuses into base layer to crosslink the crosslinkable binder in at least the base layer.

A borate or borate derivative employed in the subbing layer of the 30 ink jet recording element can be, for example, borax, sodium tetraborate, and the like, preferably not an acidic boron-containing compound such as boric acid.

In one embodiment, the crosslinking compound is a borate salt such as sodium tetraborate decahydrate (borax), sodium borate, and derivatives of boric acid, boric anhydride, and the like, employed in combination with, as binder in the base layer, a poly(vinyl alcohol), that is, "PVA." This combination has been 5 found to be especially advantageous. It is known that PVA and borax interact to form a high viscosity or gelled mixture in solution that forms a crosslinked coating on drying. According to one embodiment, the borax is pre-coated on a web and then an aqueous coating composition containing the PVA is applied. The water from the coating composition solubilizes the borax, thus allowing it to diffuse 10 through the coating, quickly thickening the composition.

The boron-containing compound, for example, the borate or borate derivative, is preferably used in an amount in a subbing layer of up to twenty percent of the weight of the binder in the base layer. It is believed that upon coating of the base layer over such a dried subbing layer, most of the borate or 15 borate derivative in the subbing layer diffuses into the base layer to crosslink most of the binder in the base layer, since such diffusion is typically rapid.

In order to impart further mechanical durability to the base layer, one or more supplemental non-boron-containing crosslinkers that act upon the binder discussed above may be added in small quantities to the coating 20 composition for at least the base layer. Such an additive can further improve the cohesive strength of the layer. Crosslinkers such as carbodiimides, polyfunctional aziridines, aldehydes, isocyanates, epoxides, vinyl sulfones, pyridinium, pyridylium dication ether, methoxyalkyl melamines, triazines, dioxane derivatives, chrom alum, zirconium sulfate, and the like may be used. Thus, a non-boron- 25 containing crosslinker can be used in combination with the boron-containing crosslinker.

In one preferred embodiment, the base layer has a dry weight of at least 10 g/m², more preferably 15 to 25 g/m², and most preferably 17 g/m² to 24 g/m². At lower dry weight of the base layer, any increased coalescence that is 30 observed may be compensated further by adjusting the base layer composition to increase absorption capacity of the base layer or to improve wettability of the

receiver. For example, the addition of fluorosurfactant to the base layer can reduce coalescence at low base-layer coverage. Also, coalescence may be reduced by adding absorption capacity in the form of an intermediate layer. Other possible adjustments to the composition of the base layer can include changing the surface area of the particles and/or the addition of other particulate materials.

5 In one embodiment of the present inkjet recording element, the base layer is at least two times, preferably 3 times, more preferably at least 6 times, most preferably at least 9 times the thickness of an upper gloss layer.

10 The inorganic particles in the base layer can comprise a mixture of two different populations of fumed silica that are separately made and then admixed.

15 Preferably, the anionic fumed silica (or mixed-oxide fumed particle containing silicon) in the base layer comprises at least 70 percent, more preferably at least 90 percent, by weight of the total weight of inorganic particles in the base layer.

20 The base layer may further comprise a minor amount of one or more other non-cationic inorganic particles in addition to the fumed silica, if any, for example, colloidal silica, titanium oxide, tin oxide, zinc oxide, and the like, and/or mixtures thereof. Examples of other useful non-cationic inorganic particles include clay or calcium carbonate. Preferably, any optional non-aggregated colloidal particles comprise anionic colloidal (non-aggregated) silica, as described above for the porous gloss layer, other than particle size.

25 In addition to the inorganic particles mentioned above, the base layer may independently contain non-cationic organic particles or beads such as poly(methyl methacrylate), polystyrene, poly(butyl acrylate), etc. Preferably, substantially all the particles in the base layer have a median primary and secondary particle size of not more than 300 nm.

30 Preferably, the one or more other non-cationic inorganic materials in the base layer comprise particles of a silicon-oxide containing material in which at least 70 percent, preferably at least 80 percent, of the metal or silicon atoms are silicon, in combination with oxygen or other non-metallic or metallic atoms.

In a preferred embodiment, the base layer comprises between 5 and 15.0 weight percent binder. The base layer can comprise both hydrophilic and hydrophobic binder. Most preferably, the binder in the base layer comprises poly(vinyl alcohol). In addition, it is preferred that the base layer further 5 comprises crosslinker crosslinking the poly(vinyl alcohol).

In one embodiment, the base layer further comprises fluorosurfactant, suitably in the amount of 0.1 to 5 %, preferably 0.8 to 2% of the total weight of the coating composition. Preferred fluorosurfactants are non-ionic, linear, perfluorinated polyethoxylated alcohols, as disclosed in US Patent 10 Application Publication No. 2005/0013947. In some embodiments, such fluorosurfactants can improve gloss and coalescence.

The inkjet recording element preferably comprises, in the base layer fumed silica having an average primary particle size of up to 50 nm, preferably 5 to 40 nm, but which is aggregated having a median secondary particle 15 size preferably up to 300 nm, more preferably 150 to 250 nm.

The base layer is characterized by the absence of cationic materials that affect the surface charge or zeta potential of the anionic silica particles in the invention such as cationic polymer, a hydroxyl-containing polyvalent metal salt, for example aluminum chlorohydrate, or a silane coupling agent. “Absence” is 20 defined herewith as below a limit in which there are sufficient cationic groups to critically change the zeta potential of the anionic silica particles, rendering the zeta potential more positive than negative 15 mv. The term “cationic polymer,” for example, includes polymers with at least one quaternary ammonium group, phosphonium group, an acid adduct of a primary, secondary or tertiary amine 25 group, polyethylene imines, polydiallylamines or polyallylamines, polyvinylamines, dicyandiamide condensates, dicyandiamide-polyamine co-condensates or polyamide-formaldehyde condensates, and the like.

Preferably, the fumed silica, like the colloidal silica in the optional gloss layer, is characterized by at least 70, preferably at least 90 percent of the 30 metal or silicon atoms in the particles being silicon, in combination with oxygen or other non-metallic non-silicon atoms. For example, various dopants,

impurities, variations in the composition of starting materials, surface agents, and other modifying agents may be added to the silicon oxide in limited amounts during its preparation, as long as the resulting surface is anionic. Fumed silica can include mixed metal oxides, as long as the zeta potential requirements are met.

5 See, for example, US Patent No. 7,015,270 to Scharfe et al. and US Patent No. 6,808,769 to Batz-Sohn et al. Silicon-oxide-mixed oxide particles can include, for example, titanium, aluminum, cerium, lanthanum, or zirconium atoms. Mixed oxides include intimate mixtures of oxide powders at an atomic level with the formation of mixed oxygen-metal/non-metal bonds.

10 Silicon-oxide particles can be divided roughly into particles that are made by a wet process and particles made by a dry process (vapor phase process). The latter type of particles is also referred to as fumed or pyrogenic particles. In a vapor phase method, flame hydrolysis methods and arc methods have been commercially used. The term "flame hydrolysis" is understood to mean the 15 hydrolysis of metal or non-metal compounds in the gas phase of a flame, generated by reaction of a fuel gas, preferably hydrogen, and oxygen. Highly disperse, non-porous primary particles are initially formed which, as the reaction continues, coalesce to form aggregates, and these aggregates may congregate further to form agglomerates. In a preferred embodiment, the BET surface of area 20 of these primary particles are 5 to 600 m²/g. Fumed silica is produced in a vapor phase process, whereas colloidal silica is not and can be distinguished from both fumed silica made by a dry process and other silicas made by a wet process such as relatively more porous silica gel.

25 Fumed particles exhibit different properties than non-fumed or wet-process particles, which are referred to herein as "colloidal silica." In the case of fumed silica, this may be due to the difference in density of the silanol group on the surface. Fumed particles are suitable for forming a three-dimensional structure having high void ratio.

30 Fumed or pyrogenic particles are aggregates of smaller, primary particles. Although the primary particles are not porous, the aggregates contain a significant void volume, and hence are capable of rapid liquid absorption. These

void-containing aggregates enable a coating to retain a significant capacity for liquid absorption even when the aggregate particles are densely packed, which minimizes the inter-particle void volume of the coating. For example, fumed silica, for selective optional use in the present invention, are described in US

5 Patent No. 6,808,769 to Batz-Sohn, US Patent No. 6,964,992 to Morris et al. and US Patent No. 5,472,493 to Regan. Examples of fumed silica are provided in the Examples below and are commercially available, for example, from Cabot Corp. under the family trademark CAB-O-SIL silica, or Degussa under the family trademark AEROSIL silica.

10 Fumed silicas having relatively lower surface area are preferred for their lower binder requirement, but fumed silicas with surface areas that are too low decrease gloss. In one embodiment, a range of 150 to 350 m²/g is preferred, more preferably 170 to 270 m²/g.

15 In one embodiment, an upper gloss layer is present and comprises less than 10 weight percent binder, based on total solids in the layer. The binders in the upper gloss layer can be selected from the same binders as in the base layer. Poly(vinyl alcohol) is again the preferred binder.

20 The gloss layer is characterized by the absence of cationic materials that affect the surface charge or zeta potential of the anionic silica particles in the invention such as cationic polymer, a hydroxyl-containing polyvalent metal salt, for example aluminum chlorohydrate, or a silane coupling agent. “Absence” is defined herewith as below a limit in which there are sufficient cationic groups to critically change the zeta potential of the anionic silica particles, rendering the zeta potential more positive than negative 15 mv.

25 Preferably, the colloidal silica in the gloss layer comprises at least 80 percent, more preferably 90 percent, by weight of the inorganic particles in the gloss layer.

30 The term “colloidal silica” refers to particles comprising silicon dioxide that are dispersed to become colloidal. Such colloidal particles characteristically are primary particles that are substantially spherical. Larger particles, aggregates of primary particles relatively limited in number and

aggregation, may be present to a minor extent, depending on the particular material and its monodispersity or polydispersity, but the larger particles have relatively minor effect on the number weighted median particle size. Examples of these colloidal silica are described in the Examples below and are commercially 5 available from a number of manufacturers, including Nissan Chemical Industries, Degussa, Grace Davison (for example under the family trademarks SYLOJET and LUDOX), Nalco Chemical Co., etc. Typically, colloidal silica naturally has an anionic charge, resulting from the loss of protons from silanol groups present on the particles' surface. Such particles typically originate from dispersions or sols in 10 which the particles do not settle from dispersion over long periods of time. Most commercially available colloidal silica sols contain sodium hydroxide, which originates at least partially from the sodium silicate used to make the colloidal silica.

The average metallic composition of said colloidal particles 15 comprises at least 70 percent, more preferably at least 90 percent silicon, wherein silicon is considered a metallic element for this calculation, as described above for the fumed silica in the base layer.

The gloss layer may further comprise a minor amount of one or more other non-cationic inorganic particles, if any, for example, fumed silica, 20 titanium oxide, and/or mixtures thereof. Preferably, any optional aggregated particles comprise anionic fumed silica, as described above for the porous base layer, other than particle size. Also suitable are anionic colloidal particles of zinc oxide, tin oxide, and the like.

In addition to the inorganic particles mentioned above, the gloss 25 layer may independently contain non-cationic organic particles or beads such as the ones mentioned above for the base layer. Preferably, substantially all the particles in the base layer have an average primary particle size of not more than 45 nm, except for particles used as matte beads.

Preferably, the one or more other inorganic materials in the gloss 30 layer comprise particles of a silicon-oxide containing material in which at least 80

percent of the metal or silicon atoms are silicon, in combination with oxygen or other non-metallic or metallic atoms.

Conventional additives may be included in the ink-receiving layers in the present invention, which may depend on the particular use for the recording element. Such additives that optionally can be included in the ink-receiving layers of the inkjet recording element include cross-linkers, rheology modifiers, surfactants, UV-absorbers, biocides, lubricants, dyes, optical brighteners, and other conventionally known additives. Additives may be added in light of the fact that the inkjet recording element may come in contact with other image recording articles or the drive or transport mechanisms of image-recording devices, so that additives such as matte particles and the like may be added to the inkjet recording element to the extent that they do not degrade the properties of interest. Also the additives should be compatible with anionic silica.

The inkjet recording element can be specially adapted for either pigmented inks or dye-based inks, or designed for both. In the case of pigment-based inks, the upper gloss layer can function as a pigment-trapping layer. In the case of dye-based inks, both the upper gloss layer and the lower base layer, or an upper portion thereof, may contain the image, depending on the particular embodiment, thickness of the layers, particle composition, binder, etc.

The term “pigment-trapping layer” is used herein to mean that, in use, preferably at least 75% by weight, more preferably substantially all, of the pigment colorant in the inkjet ink composition used to print an image remains in the pigment-trapping layer.

The support for the coated ink-retaining layers may be selected from plain papers or resin-coated paper. Preferably the resin-coated paper comprises a polyolefin coating on both sides, more preferably polyethylene. The thickness of the support employed in the invention can be from 12 to 500 μm , preferably from 75 to 300 μm .

If desired, in order to improve the adhesion of the base layer to the support, the surface of the support or a subbing layer may be corona-discharge-treated prior to applying the base layer to the support.

In a particularly preferred method, the subbing layer is coated in a single layer at a single station and all of the one or more ink-receiving layers in the inkjet recording element, comprising the base and optional gloss layer, are simultaneously coated in a single station. In one embodiment, the entire inkjet 5 recording element is coated in a single coating pass.

The term “single coating pass” or “one coating pass” refers to a coating operation comprising coating one or more layers, optionally at one or more stations, in which the coating operation occurs prior to winding the inkjet recording material in a roll. A coating operation, in which a further coating step 10 occurs before and again after winding the inkjet recording material on a roll, but prior to winding the inkjet recording material in a roll a second time, is referred to as a two-pass coating operation.

In one embodiment, in the case where two ink-receiving layers are present, the layers are simultaneously coated, preferably by curtain coating. Other 15 methods can be selected from, for example, extrusion hopper coating, slide hopper coating, and the like.

In one preferred embodiment, the method of manufacturing an inkjet recording element comprises the steps of:

- (a) providing a support;
- 20 (b) treating the support with a subbing composition comprising a boron-containing crosslinking compound; and
- (c) simultaneously coating in order over the support:
 - (i) a first coating composition, for an base layer, comprising particles of anionic fumed silica and hydrophilic hydroxyl-containing polymer as 25 the primary binder capable of being substantially cross-linked by crosslinking compound not contained in the first composition; and
 - (ii) a second coating composition, for a gloss layer, the uppermost layer of the inkjet-receiving element, comprising particles of anionic colloidal silica and a binder, wherein colloidal silica has an median particle size of 10 to 45 30 nm; and

wherein said particles of fumed silica and colloidal silica exhibit a zeta potential below negative 15 mv and the weight of binder to total solids in the first and second coating compositions is between 5 percent and 30 percent.

Accordingly, the boron-containing crosslinking compound diffuses into at least

5 the ink-receiving layer to crosslink hydrophilic binder in at least the base layer.

The binder in the optional gloss layer can also be capable of being substantially cross-linked by boron-containing crosslinking compound not contained in the second composition, wherein said crosslinking compound in the subbing layer also diffuses into the gloss layer to substantially crosslink the binder 10 in the gloss layer. In other words, the boron-containing crosslinking compound may migrate to some extent into the upper gloss layer, depending on various factors such as the thickness of the base layer.

In another embodiment, in the case where one ink-receiving layer is present, the method of manufacturing an inkjet recording element comprises the

15 steps of:

(a) providing a resin-coated support;

(b) treating the support with a subbing composition comprising a boron-containing crosslinking compound; and

(c) coating a coating composition, for an ink-receiving layer, comprising 20 particles of anionic fumed silica and hydrophilic hydroxyl-containing polymer as the primary binder capable of being substantially cross-linked by crosslinking compound not contained in the first composition; wherein the ink-receiving layer is the only layer in the inkjet receiving element above the support and any subbing layer, said particles of fumed silica exhibit a zeta potential below negative 15 mv;

25 and the weight of binder to total solids in the first and second coating compositions is less than 15 percent. The boron-containing crosslinking compound diffuses into at least the ink-receiving layer to crosslink hydrophilic binder in the base layer.

The subbing composition can optionally comprise a binder or may 30 simply comprise a liquid carrier such as water.

Inkjet inks used to image the recording elements of the present invention are well known in the art. The ink compositions used in inkjet printing typically are liquid compositions comprising a solvent or carrier liquid, dyes or pigments, humectants, organic solvents, detergents, thickeners, preservatives, and the like. The solvent or carrier liquid can be solely water or can be water mixed with other water-miscible solvents such as polyhydric alcohols. Inks in which organic materials such as polyhydric alcohols are the predominant carrier or solvent liquid may also be used. Particularly useful are mixed solvents of water and polyhydric alcohols. If dyes are used in such compositions, they are typically water-soluble direct or acid type dyes. Such liquid compositions have been described extensively in the prior art including, for example, US Patent Nos. 4,381,946; 4,239,543; and 4,781,758.

Typically the colorants used in inkjet printing are anionic in character. In dye based printing systems, the dye molecules contain anionic moieties. In pigment based printing systems, the dispersed pigments are functionalized with anionic moieties. Colorants should be fixed near the surface of the inkjet receiver in order to provide the maximum image density. In the case of pigment based printing systems, the inkjet receiver is designed with the optimum pore size in the top layer to provide effective trapping of ink pigment particles near the surface. Dye-based printing systems known in the conventional art require a fixative or mordant in the top layer or layers of the receiver.

Polyvalent metal ions and insoluble cationic polymeric latex particles provide effective mordants for anionic dyes. Both pigment and dye based printing systems are widely available. For the convenience of the user, a universal porous inkjet receiver known in the conventional art will comprise a dye fixative in the topmost layer or layers.

Although the recording elements disclosed herein have been referred to primarily as being useful for inkjet printers, they also can be used as recording media for pen plotter assemblies. Pen plotters operate by writing directly on the surface of a recording medium using a pen consisting of a bundle of capillary tubes in contact with an ink reservoir.

The following examples further illustrate the invention.

EXAMPLE 1

A support comprising a paper with polyethylene resin coating on both sides was treated on one side by coating with an aqueous composition 5 comprising poly (vinyl alcohol) (PVA, CELVOL 103), a styrene-butadiene latex (DOW CP692NA), and sodium tetraborate in a ratio of 1:1:2, at a total solids of 0.6% and dried to provide a dry coverage of 0.32 g/m².

A first aqueous coating composition (17.9% solids) for a base layer comprising a dispersion (DEGUSSA W7520) containing anionic fumed silica 10 (AEROSIL 200), 7.5% PVA (NIPPON GOHSEI KH20), 0.75% (1,4-dioxane-2,3-diol (DHD)), 1% fluorosurfactant (ZONYL FS300), and a second aqueous coating composition (10% solids) for a gloss layer comprising a dispersion of anionic colloidal silica (1:1 mixture of Grace Davison SYLOJET 4000A and LUDOX TM-50), 8% succinylated gelatin (GELITA IMAGEL MS), a crosslinker (0.8% 15 1,4-dioxane-2,3-diol (DHD)), and a coating aid (1% ZONYL FS300) were simultaneously coated on the subbing layer to provide layers of dry weight 21.5 g/m² and 2.2 g/m², respectively, and dried to form inventive Sample I-1.

Comparative Samples C1 to C5 employed an identical treated support as described above. A first aqueous coating composition (17.9% solids) 20 for a base layer comprising a dispersion (DEGUSSA WK7330) containing cationic fumed silica (cationically modified AEROSIL 130); PVA (NIPPON GOHSEI KH20), 2.5% (1,4-dioxane-2,3-diol (DHD)), 0.5% boric acid and 1.85% coating aid (10G, DIXIE CHEMICAL) and a second aqueous coating composition (10% solids) for a gloss layer comprising a dispersion of cationic colloidal silica 25 (Grace Davison SYLOJET 4000C); 3.5% polyvinyl alcohol (NIPPON GOHSEI GH23); 1% 1,4-dioxane-2,3-diol and 1% ZONYL FS300 were coated simultaneously on the subbing layer to provide layers of dry weight 21.5 g/m² and 2.2 g/m² respectively. The fumed silica-containing layer was varied with respect to PVA level, and the fumed silica level was adjusted to compensate. The 30 amounts of PVA used in Comparative Samples C1 to C5 are given in Table 1 below.

Cracking of the coated samples was assessed visually. The gloss of the unprinted samples was measured at 20 and 60 degrees. The samples were printed using a KODAK EASYSHARE 5100 Inkjet Printer with a driver setting selected such that print speed and ink laydown were maximized (KODAK 5 ULTRA PREMIUM STUDIO GLOSS PAPER selection). Coalescence, or local density non-uniformity in solid color patches, was assessed visually and rated on a scale of 1 (none visible) to 5 (significant coalescence observed under conditions in which the selected printer mode provides a very high ink flux, up to, but not including "flooding"). Ratings up to 4 may be considered acceptable for some 10 printing applications. Samples that were flooded with ink as well as coalesced were rated higher than 5. The samples were also printed with an EPSON R320 dye-based printer, and densities of solid color patches were measured. Averages of densities for cyan, magenta, and yellow were compared, as well as average values for red, green, and blue patches and pure black patches. The results are 15 shown in Table 1 below.

TABLE 1

Sample	Silica Type	Base Layer Binder (%)	Cracking	Pigment-based Ink Coalescence	Dye-based Ink Density (Ave of CMY)	Dye-based Ink Density (Ave of RGB)	Dye-based Ink Density (K)
C-1	Cationic	9	Yes	3	1.88	1.66	2.38
C-2	Cationic	11	Slight	2.5	1.84	1.67	2.36
C-3	Cationic	13	No	3	1.84	1.63	2.34
C-4	Cationic	15	No	5	1.85	1.63	2.19
C-5	Cationic	16.4	No	7	1.82	1.66	2.19
I-1	Anionic	7.5	No	1.5	2.18	1.69	2.38

As demonstrated by the results in Table 1, the present inventors have discovered that a recording element of the present invention comprising 20 anionic fumed silica in the ink receiving layer and anionic colloidal silica in the gloss layer may be coated with a lower binder content in the ink-receiving layer without cracking. As a result, reduced coalescence is obtained with pigment-based inks. Surprisingly, the color density of dye-based inks is improved as well. In the art, standard practice for inkjet receivers is to employ cationic particles such 25 as alumina or cationically modified silica, and optionally to incorporate cationic

mordants compatible with the cationic particles, in order to fix the standard anionic ink colorants near the receiver surface for maximum color density. In the present invention, essentially no cationic particles or additives are employed in the receiver, but superior results are obtained for printing with inks comprising 5 standard anionic colorants.

EXAMPLE 2

The present invention comprises an uppermost gloss layer comprising colloidal silica. Sample I-2 was prepared as in the Sample I-1, except that instead of coating the gloss layer, the dry coverage of the ink-receiving layer 10 was increased by a corresponding dry weight. The samples were evaluated as in Example 1 and the results are reported in Table 2.

TABLE 2

Sample	Coverage (Base Layer)	Coverage (Gloss layer)	Gloss (20 Deg)	Gloss (60 Deg)	Density (Ave of CMY)	Density (Ave of RGB)	Density (K)
I-1	21.5	2.2	21.4	47.3	2.18	1.69	2.38
I-2	23.7	0	6.1	17.0	1.42	1.09	1.72

The results shown in Table 2 demonstrate a gloss improvement when a 15 gloss layer is provided on top of the ink-receiving layer. When present, the gloss layer provides improved densities of all colors when printed with a dye-based ink.

EXAMPLE 3

The present invention comprises a porous base layer comprising particles of anionic fumed silica. Inventive Samples I-3, I-4, and I-5 were 20 prepared identically to inventive coating Sample I-1, except the topcoat coverage was increased to 3.2 grams/m²; and anionic colloidal silica (Grace Davison SYLOJET 4000A) was partially substituted for the fumed silica in the bottom layer in the amounts described in Table 3 below. Samples were evaluated as in Example 1

TABLE 3

Sample	% Fumed Silica	Coalescence	Density (Ave of CMY)	Density (Ave of RGB)	Density (K)	20 degree gloss
I-3	0	1.5	2.20	1.80	2.38	32
I-4	10	2.5	2.18	1.77	2.33	30
I-5	20	5	2.15	1.77	2.39	33

The results of Table 3 demonstrate that a base layer comprising anionic fumed silica provides excellent printed color density with dye-based inks
 5 without unacceptable coalescence of pigment-based inks even with the addition of other compatible anionic inorganic particles.

EXAMPLE 4

A series of coatings was prepared according to the procedure for coating Sample I-1 of Example 1, except that the coating composition of the gloss 10 layer was changed to 15% solids and the laydown was varied. Samples of the coating were evaluated as in Example 1 and the test results are reported in Table 4 below.

TABLE 4

Sample	Gloss layer coverage, g/m ²	Coalesce- nce	Density (Ave of CMY)	Density (Ave of RGB)	Density (K)	20 degree gloss
I-6	4.3	2	2.21	1.83	2.45	32
I-7	3.2	1.8	2.17	1.69	2.37	33
I-8	2.2	1.5	2.02	1.55	2.28	31
I-9	1.1	1.5	1.73	1.34	1.95	24

15 As demonstrated in Table 4, at lower gloss layer weight, the printed color density may decline. A slight increase in coalescence appears for gloss layer dry weight above 5 g/m².

EXAMPLE 5

A series of coatings was prepared according to the procedure for 20 Coating Sample I-1 in Example 1, except that the mixture of anionic colloidal silica types of the gloss layer was replaced by a single component, Grace Davison

SYLOJET 4000A, and the gelatin binder in the gloss layer was replaced by poly(vinyl alcohol). The poly(vinyl alcohol) level in the gloss layer was adjusted through a range of 4% by weight to 10% by weight. The level of crosslinker in the gloss layer was adjusted to 10% by weight of the binder level. The base layer was 5 prepared at a constant binder level of 6% by weight.

Bronzing occurs when a printed dark area exhibits enhanced gloss with the appearance of a bronze color. A visual assessment of bronzing was made by observing an imaged black area printed by an EPSON R260 printer with dye-based inks.

10

TABLE 5

Sample	Gloss layer binder level (weight %)	Bronzing	Density (Ave of CMY)	Density (Ave of RGB)	Density (K)
I-10	10	Poor	1.73	1.49	1.94
I-11	7.5	Good	1.73	1.45	1.92
I-12	5.6	Good	1.69	1.42	1.90
I-13	4	Good	1.64	1.39	1.82

The data in Table 5 demonstrates that a binder proportion in the gloss layer up to 10% provides excellent printed dye density. For inks prone to bronzing, lower binder proportions are preferred in the gloss layer.

15

EXAMPLE 6

A series of coatings was prepared according to the procedure of Example 5, except that the binder level in the ink-receiving layer was 7% by weight. The coat weights of the gloss layer and the ink-receiving layer were varied as shown in Table 6 below.

TABLE 6

Sample	Base Layer coverage, g/m ²	Gloss Layer coverage, g/m ²	Total layer coverage, g/m ²	Coalescence	Cracking
I-14	21.5	4.3	25.8	2	Slight
I-15	21.5	3.2	24.7	2	Very slight
I-16	21.5	2.2	23.7	2.5	Good
I-17	19.4	4.3	23.7	3	Very slight
I-18	19.4	3.2	22.6	4	Good
I-19	19.4	2.2	21.6	3	Good
I-20	16.1	4.3	20.4	6	Good
I-21	16.1	3.2	19.3	6	Good
I-22	16.1	2.2	18.3	6	Good

The results shown in Table 6 show preferred ranges for some embodiments of the invention, and demonstrate that an ink-receiving layer comprising at least 17 g/m² reduces coalescence compared with layers of less dry weight. The increased coalescence observed at lower base-layer dry weight may be compensated further by adjusting the base layer composition to increase absorption capacity or wetting. For example, as indicated in Example 17 below, increasing the amount of fluorosurfactant in the base layer can reduce coalescence at low base-layer coverage. As total dry weight of the combined base layer and gloss layer increases beyond 25 g/m², the receiver may be more prone to cracking during manufacture. The gloss coat coverage has a relatively larger effect on cracking, while the ink-receiving dry layer weight has a relatively larger influence on image quality.

15

EXAMPLE 7

A series of coatings was prepared according to the procedure for coating Sample I-1 in Example 1, except that the mixture of anionic colloidal silica types of the gloss layer was replaced by a single component, Grace Davison SYLOJET 4000A and the gloss layer dry weight was set at 3.2 g/m². The binder level for the ink-receiving layer was varied as shown in Table 7 below.

TABLE 7

Sample	Base Layer coverage, g/m ²	Base Layer binder level	Coalescence	Cracking
I-23	19.4	7.5%	3	Good
I-24	19.4	10%	4	Good
I-25	19.4	12.5%	5	Good
I-26	28	7.5%	1.5	Poor
I-27	28	10%	2	Slight
I-28	28	12.5%	2.5	Very slight

The results shown in Table 7 demonstrate that base layer dry weights above 24 g/m² may result in increased cracking, whereas increasing 5 relative dry binder content tends to increase coalescence.

EXAMPLE 8

A treated support was prepared according to the procedure for coating Sample I-1 in Example 1, except that the borax-containing treatment layer comprised a 1:1 mixture of polyvinyl pyrrolidone (K-90, ISP Corp) and sodium 10 tetraborate. A series of coatings was prepared with dispersions of cationic fumed silica for the ink-receiving layer. Aqueous cationic coating composition A (total solids 17.9%) was prepared to yield 82.6% cationic silica from a commercial dispersion WK7330 (dispersion of AEROSIL 130, Degussa); 12.5% poly(vinyl alcohol) (KH-20); 2.5% Dihydroxy dioxane; 0.5% boric acid; and 1.9% 10G 15 surfactant.

Cationic coating composition B was prepared according to the same formula as Composition A, except WK7525 (a cationic dispersion of AEROSIL 200 from Degussa) was used in place of WK7330 and cationic coating Composition C was prepared according to the same formula as composition B, 20 except that the poly(vinyl alcohol) binder level was raised to 15%; and the level of silica was lowered to compensate. An aqueous cationic coating composition for the gloss layer was prepared at 10% solids, comprising 83.8% cationic colloidal silica (from SYLOJET 4000C dispersion available from Grace Davison); 10%

cationic fumed silica (WK7330; Degussa); 4% poly(vinyl alcohol) (KH20); 1.1% dihydroxy dioxane and 1.1% ZONYL FS300 surfactant.

A series of coating Samples C-6 to C-8 was prepared by simultaneously coating the cationic coating compositions for the ink-receiving layer and the cationic coating composition for the gloss layer in combination to yield dry coating weights of 21.5 g/m² for the ink-receiving layer and 2.2 g/m² for the gloss layer. In addition, an anionic coating identical in composition to Example 1 was prepared, except that the binder in the gloss layer was changed to poly(vinyl alcohol), and the layers were coated on the same borax treatment layer used for the cationic comparative examples to provide coating Sample I-29. The samples were evaluated as in Example 1 and the results are shown in Table 8.

TABLE 8

Sample	Gloss layer type	Base layer type	Base layer binder	Cracking	Ave density (CMY)	Density (Ave of RGB)	Density (K)	Coalescence
C-6	Cationic	Cationic A	12.5 %	Good	1.83	1.62	2.39	3.5
C-7	Cationic	Cationic B	12.5 %	Flaked off	(N/A)	(N/A)	(N/A)	(N/A)
C-8	Cationic	Cationic C	15 %	Poor	1.65	1.52	2.95	3.5
I-29	Anionic	Anionic	7.5%	Good	2.19	1.77	2.36	3

The results shown in Table 8 show that a larger particle size is preferable for the ink-receiving layer containing cationic silica than is preferred for a layer containing anionic silica, along with increased binder content relative to the formula employing anionic silica. While coalescence and cracking levels can approach those seen for the anionic layers used in the invention, dye density is not as high.

EXAMPLE 9

The Example demonstrates zeta potentials of silica particles used in various examples and comparative examples of the invention. The zeta potentials were measured using a Malvern Zetasizer Nano-ZS. The results are shown in Table 9 below.

TABLE 9

Dispersion	Silica	Type	Zeta (mV)
SYLOJET 4000A silica	Colloidal	Anionic	-40.1
SYLOJET 4000C silica	Colloidal	Cationic	+36.1
W7520 (AEROSIL 200) silica	Fumed	Anionic	-31.5
W7330 (AEROSIL 130) silica	Fumed	Cationic	+33.8

As seen by the results in Table 9, anionic silica dispersions used in the invention have zeta potentials more negative than negative 15 mv. The cationic 5 silica dispersions have zeta potentials greater than +15 mv.

EXAMPLE 10

Anionic coating compositions for the base layer and gloss layer were prepared corresponding to those used in Example 5. Cationic coating compositions for the base layer and gloss layer were prepared corresponding to 10 those used in Example 8. The melts were combined with stirring at room temperature to assess compatibility. The observations are recorded in Table 10.

TABLE 10

Base Layer Composition	Gloss Layer Composition	Result upon combining
Anionic	Anionic	Compatible
Anionic	Cationic	Particles formed
Cationic	Cationic	Compatible
Cationic	Anionic	Agglomeration

These observations suggest that the particles in the coating 15 compositions should possess like charges in order to be compatible for successful simultaneous coating

EXAMPLE 11

A coating was prepared identical to Example 1, except that the dry weight of the gloss layer was increased to 3.2 g/m². A comparison coating C-9 20 was prepared by a sequential coating method, that is, the image-receiving layer was coated and dried and then the gloss layer was coated on top and dried. The printed gloss was evaluated using a KODAK EASYSHARE 5100 printer. Patches of cyan, magenta, yellow, and protective ink were printed and then the 20-degree

gloss of each patch was measured and the values averaged. The results are shown in Table 11.

TABLE 11

Sample	Coating type	Unprinted 20 deg gloss	Printed 20 degree gloss (Ave CMY)	Coalescence
I-30	Simultaneous	31	79	2
C-9	Sequential	21	57	3

5 The results of the simultaneous and sequential coating methods for anionic silica coating compositions shown in Table 11 demonstrate that the unprinted gloss and printed gloss are superior for the preferred simultaneous coating method and the coalescence is reduced. While not wishing to be bound by any particular theory, the inventors surmise that the simultaneous coating method
10 sufficiently alters the microstructure at the interface of the gloss and base layers of the receiver that it significantly improves the printed gloss and reduces coalescence with pigmented inks.

EXAMPLE 12

Anionic coating compositions for the base and gloss layers were
15 prepared as for Example 5, and cationic coating compositions for the base and gloss layers were prepared as in Example 8. The base layers were each coated over a borax-containing subbing layer as described in Example 1 and dried. The dried anionic base layer was subsequently coated with the cationic gloss composition and dried, while the cationic base layer was subsequently coated with
20 the anionic gloss composition and dried. For comparison, the anionic base and gloss layer compositions were also coated simultaneously and dried, as were the cationic base and gloss layer compositions. The samples were evaluated as in Example 1 and the results are shown in Table 12.

TABLE 12

Sample	Base Layer	Gloss Layer	20 degree gloss	Density (Ave of RGB)	Density (K)	Coalescence
C-10	Anionic	Cationic	43	1.43	2.40	4
C-11	Cationic	Anionic	23	1.54	2.28	3
C-12	Cationic	Cationic	41	1.56	2.33	4
I-31	Anionic	Anionic	32	1.80	2.38	1.5

The results shown in Table 12 demonstrate that the anionic structure I-30 of the invention provides the best composite color density and least 5 amount of coalescence with very good gloss, compared to structures C-10 to C-12 comprising cationically modified silica.

EXAMPLE 13

A series of coatings were prepared identical to sample I-29, except that alternative anionic fumed silica dispersions from anionic fumed silica 10 particles of different surface areas were used and with the exception of the highest surface area silica (sample I-35) that the binder level in the base layer was increased to 10%. The dispersions (all from Degussa) and their corresponding silica particle identity were, respectively, W7525 (AEROSIL 90), W7330N (AEROSIL 130), and W7622 (AEROSIL 300). The samples were evaluated for 15 cracking and unprinted gloss and the results are shown in Table 13.

TABLE 13

Sample	Silica Specific Surface area, m ² /g	Cracking	Unprinted 20 degree gloss
I-32	90	Good	3
I-33	130	Good	8
I-34	200	Good	31
I-35	300	Poor	13

The results shown in Table 13 demonstrate that preferred specific surface areas of anionic fumed silica useful in the ink-receiving layer are between 20 150 m²/g and 350 m²/g for glossy receivers. The poor cracking behavior and low gloss of sample I-35 could be resolved by increasing the binder level, but this

option may be less attractive from a manufacturing standpoint as it is likely that increased viscosity would require that the solid weight of the coating composition be reduced, hence slower coating, less productive drying speeds would be required.

5

EXAMPLE 14

A series of coatings was prepared according to the procedure for Sample I-1 in Example 1, except that the relative weight of binder in the ink-receiver was lowered from 7.5 to 7.0% and a series of commercially available anionic colloidal silica particles were substituted in the coating composition for the gloss layer. The identity and particle size as provided by the manufacturer are given below in Table 14. In some cases, the commercially available colloidal silica dispersions comprise more than one particle size.

10

TABLE 14

Sample	Colloidal silica	Colloidal silica particle size, nm	Unprinted 20 degree gloss	Ave density (CMY)	Density (Ave of RGB)	Density (K)
I- 36	SYLOJET 4000A	22	29	1.75	1.46	2.01
I-37	NALCO 2329	75	22	1.58	1.31	1.74
I-38	FUSO PL-3	35	18	1.77	1.48	2.05
I-39	FUSO PL-7	70	7	1.39	1.19	1.54
I-40	NALCO 1060	60	12	1.65	1.40	1.85
I-41	NALCO 1140	15	21	2.09	1.70	2.62
I-42	LUDOX TM-50	22	20	1.98	1.67	2.19
I-43	LUDOX LS	12	22	1.84	1.60	2.36

15

The results shown in Table 14 demonstrate that colloidal silica particles of median particle size smaller than 37 nm provide improved unprinted gloss and printed color density. A combination of colloidal silica dispersions of different median particle sizes below 37 nm may be more preferred, as it can offer a balance of better porosity (lower coalescence) with acceptable gloss and dye-density performance. Larger particle size, however, may be preferred in the case of inkjet receivers used exclusively for printing of images with pigmented-inks, since larger particle size may provide improved coalescence.

20

EXAMPLE 15

A further series of coatings was made according to the procedure of Example 1 except that, as in Example 14, the binder in the base layer was lowered from 7.5% to 7%, and the colloidal silica in the coating composition was replaced

5 by an equivalent weight of a mixture of colloidal silica particle types of different median particle size. The combinations tested are shown in Table 16 below.

Samples of the coatings were printed with the EPSON R320 printer using Epson recommended dye-based ink. The unprinted gloss and the printed color density were measured and the results are shown in Table 15.

10

TABLE 15

Sample	Particles in gloss layer	Unprinted 20 degree gloss	Ave density (CMY)	Density (Ave of RGB)	Density (K)
I-44	NALCO 1060/NALCO 1140 1:1	16.1	1.78	1.62	2.10
I-45	LUDOX TM50/LUDOX LS 3:1	27.1	1.87	1.73	2.33
I-46	LUDOX TM50/LUDOX LS 1:1	24.0	1.88	1.63	2.41
I-47	LUDOX TM50/LUDOX LS 1:3	22.5	1.90	1.60	2.37

The results shown in Table 15 demonstrate that mixtures of anionic colloidal silica particles in the gloss layer provide excellent unprinted gloss and printed color density when the median particle size falls below 37 nm as in

15 Samples I-45 through I-47, whereas the unprinted gloss and color print density are reduced for the Sample I-44 in which the median particle size is 37 nm. However, a relatively larger particle size may be preferred in the case of inkjet receivers used exclusively for printing of images with pigmented-inks, since larger particle size may provide improved coalescence.

EXAMPLE 16

This Example shows that crosslinking of the binder in the base layer and gloss layer can be accomplished by diffusion of crosslinker from a subbing layer. A fumed silica base layer and gloss layer were prepared as in Example 5 except that the base layer binder level was 8% and the gloss layer binder level was also 8%. The total PVA level was 1.6 g/m². A subbing layer was prepared as in Example 8, but the borax concentration in the subbing layer was adjusted so that varying amounts of sodium tetraborate were deposited. Coating quality and gloss were assessed.

10

TABLE 16

Sample	Sodium Tetraborate, g/m ²	Weight Ratio of Sodium Tetraborate to PVA	Cracking	20 degree gloss
I-48	0.11	0.06	Very slight	13
I-49	0.16	0.19	Good	30
I-50	0.22	0.14	Good	31
I-51	0.32	0.20	Slight	11

The results shown in Table 16 demonstrate that preferred borate levels between 0.14 and 0.27 g/m² of binder provide improved unprinted gloss and reduced cracking. Preferred borate levels are correspondingly between 6% and 20% by weight of binder.

EXAMPLE 17

A series of coatings were made identical to those in Sample I-29 of Example 8, except the amounts of PVA, fluorosurfactant ZONYL FS300, and total weight were varied. Gloss was measured and coalescence was assessed by printing with a KODAK EASYSHARE 5100 printer.

TABLE 17

Sample	PVA g/m ²	Coverage, g/m ²	FS	20 deg gloss	Coalescence
I-52	8	21.5	Yes	26	1.5
I-53	8	19.4	Yes	29	2
I-54	8	17.2	Yes	27	2
I-55	8	21.5	No	15	1
I-56	8	19.4	No	15	2
I-57	8	17.2	No	16	7
I-58	10	21.5	Yes	24	1.5
I-59	10	19.4	Yes	28	2
I-60	10	17.2	Yes	24	3.5
I-61	10	21.5	No	18	2.5
I-62	10	19.4	No	20	2.5
I-63	10	17.2	No	21	4
I-64	12.5	21.5	Yes	24	1.5
I-65	12.5	19.4	Yes	24	2.5
I-66	12.5	17.2	Yes	21	3.5
I-67	12.5	21.5	No	21	2.5
I-68	12.5	19.4	No	19	3.5
I-69	12.5	17.2	No	19	7

This data shows the complex relationship between binder level, fluorosurfactant level, gloss, and coalescence. As binder level increases, gloss decreases in the presence of fluorosurfactant, but slightly decreases without it. Fluorosurfactant always improves coalescence, but at some binder levels coalescence and gloss may be sufficient for some applications even without fluorosurfactant.

EXAMPLE 18

A series of coatings was prepared according to the procedure of Example 1, except that the base layer coverage was 23.7 g/m², the gloss layer coverage was 3.2 g/m², and poly(vinyl alcohol) type used in the ink-receiving layer was varied with respect to degree of hydrolysis and molecular weight. The

molecular weight is typically characterized in the art by the viscosity of a 4% solution in water at 20°C, the values of which are supplied by the manufacturer. The degree of cracking was visually assessed and the unprinted gloss was measured. The results are given in Table 18 below.

5

TABLE 18

Sample	PVA trademark (Nippon Gohsei)	Viscosity (cP)	Degree of Hydrolysis	Unprinted 20 degree gloss	Cracking
I-70	KH20	44-52	78.5-81.5	31	Good
I-71	KH17	32-38	78.5-81.5	30	Very slight
I-72	KP-08	6-8	71-73.5	2	Poor
I-73	GH23	48-56	86.5-89	24	Good
I-74	AH22	50-58	97.5-98.5	10	Poor

The results presented in Table 18 demonstrate that the preferred poly(vinyl alcohol) binders have a molecular weight high enough to provide a viscosity 30 cP or more in a 4% solution in water at 20°C; and a degree of hydrolysis of approximately 90 or less in order to provide preferred cracking resistance, gloss and compatibility with dispersions of anionic fumed silica without making other changes in the coating compositions such as limiting the thickness of the base layer or increasing the amount of binder.

10

EXAMPLE 19

15

A resin-coated paper support was coated with a subbing layer comprising borax (0.16 g/m²) and PVP (K-90) poly(vinyl pyrrolidone) binder (0.16 g/m²) and dried. Aqueous coating compositions (17.9 % solids) comprising a dispersion (Degussa W7520) of anionic fumed silica (AEROSIL 200), PVA (Nippon Gohsei KH20), DHD (0.8%), and fluorosurfactant ZONYL FS300 (1%) were coated over the subbed support. Total dry weight was 19.4 g/m². The relative proportions of PVA in the compositions are given in Table 1; the silica dispersions made up the remainder of the dry weight. Comparative aqueous coating compositions comprising a dispersion (Degussa WK7525) of cationic fumed silica (AEROSIL 200), instead of the anionic fumed silica, were also prepared in the absence of fluorosurfactant and coated over an identical subbed

20

25

support. In Table 19 below the column Gloss P (20 degree) refers to the gloss at 20 degrees of a patch printed with colorless protective ink used in the KODAK EASYSHARE printer, and Gloss Y similarly refers to a patch printed with yellow pigment-based ink used in the KODAK EASYSHARE printer.

5

TABLE 19

Sample	Type	PVA (% total solid)	Cracking	Dmin Gloss (20 deg)	Gloss (P) (20 deg)	Gloss (Y) (20 Deg)
I-75	Anionic	8	No	19	56	53
I-76	Anionic	10	No	35	54	54
I-77	Anionic	12.5	No	20	52	50
C-13	Cationic	12.5	Yes	n/a	n/a	N/a
C-14	Cationic	15	Yes	n/a	n/a	N/a
C-15	Cationic	17.5	Yes	n/a	n/a	N/a
C-16	Cationic	20	No	17	42	35

The results of the evaluations shown in Table 1 demonstrate that crack-free single-layer coatings providing 19 g/m² of total dry weight are obtainable with a coating composition of anionic fumed silica when the relative 10 amount of binder is from 8 to 12.5%. In order to provide a crack-free coating comprising cationically modified fumed silica of identical surface area, the relative proportion of binder should be increased to at least 20%. Surprisingly, the gloss of an unprinted area as well as areas printed with protective ink or with yellow pigment-based ink is significantly greater for the anionic silica 15 formulations. In addition, the higher binder level used for the cationically modified silica might require a reduction of solids in the coating composition for coating at a manufacturing scale.

CLAIMS:

1. A method of manufacturing an inkjet recording element comprising the steps of:

(a) providing a support;

5 (b) treating the support with a subbing composition comprising a boron-containing crosslinking compound; and

(c) coating in order over the support:

(i) a first coating composition, for an ink-receiving layer, comprising particles of anionic fumed silica and hydrophilic hydroxyl-containing

10 polymer, as the primary binder, capable of being substantially cross-linked by crosslinking compound not contained in the first composition; and

(ii) an optional second coating composition, for a gloss layer, comprising particles of anionic colloidal silica and a binder; and

15 wherein the particles of anionic fumed silica and anionic colloidal silica exhibit a zeta potential below negative 15 mv and wherein the weight of binder to total solids in the first and the second coating compositions is between 5% and 30%; whereby the boron-containing crosslinking compound diffuses into at least the ink-receiving layer to crosslink hydrophilic binder in at least the ink-receiving layer.

20

2. The method of claim 1 wherein the first coating composition, for the ink-receiving layer, as coated provides a dry weight of 10 to 35 g/m² and wherein the weight percent of total binder to total solids in the ink-receiving layer is greater than 5.0 percent and less than 15.0 percent.

25

3. The method of claim 1 wherein the optional second coating composition, for a gloss layer, as coated provides a dry weight of 0.2 to 7.5 g/m², wherein the median particle size of the particles of anionic colloidal silica is 10 to 200 nm.

30

4. The method of claim 1 wherein the median primary particle size of the particles of anionic fumed silica is under 40 nm.

5. The method of claim 1 wherein the second coating composition for the gloss layer is present and the first coating composition for the ink-receiving layer as coated provides at least two times, preferably three times, more preferably at least six times, most preferably at least nine times the dry weight of the second coating composition for the gloss layer.

10 6. The method of claim 5 wherein the particles in the second coating composition for the gloss layer comprise a mixture of two different populations of colloidal silica that are separately made and then admixed.

15 7. The method of claim 1 wherein the particles of anionic fumed silica in the first coating composition for the ink-receiving layer comprises at least 70 percent by weight of the total inorganic particles in the ink-receiving layer.

20 8. The method of claim 1 wherein the first coating composition for the ink-receiving layer comprises less than 12 weight percent binder.

25 9. The method of claim 8 wherein the binder in the first coating composition for the ink-receiving layer comprises modified or unmodified poly(vinyl alcohol) or copolymers thereof.

10. The method of claim 8 wherein the binder comprises poly(vinyl alcohol).

30 11. The method of claim 10 wherein the poly(vinyl alcohol) has a degree of hydrolysis of at least 70 percent.

12. The method of claim 1 wherein the first coating composition for the ink-receiving layer further comprises fluorosurfactant.

13. The method of claim 1 wherein the second coating 5 composition for the gloss layer is present and characterized by the absence of cationic polymer.

14. The element of claim 1 wherein the anionic colloidal silica in the second coating composition for the gloss layer comprises at least 70 percent 10 by weight of the total inorganic particles in the gloss layer.

15. The inkjet recording element of claim 1 wherein the support comprises resin-coated cellulosic paper.

16. The inkjet recording element of claim 1 wherein the inkjet recording element consists of the ink-receiving layer and the upper gloss layer over the support and any optional subbing layer.

17. A method of manufacturing an ink-recording element 20 comprising the steps of:

(a) providing a support;
(b) treating the support with a subbing composition comprising a boron-containing crosslinking compound; and

(c) simultaneously coating in order over the support:
25 (i) a first coating composition, for an ink-receiving layer, comprising particles of anionic fumed silica and hydrophilic hydroxyl-containing polymer as the primary binder capable of being substantially cross-linked by the boron-containing crosslinking compound not contained in the first coating composition; and

30 (ii) a second coating composition, for a gloss layer, the uppermost layer of the inkjet-receiving element, comprising particles of anionic

colloidal silica and a binder, wherein colloidal silica has an median particle size of 10 to 45 nm; and

5 wherein the particles of anionic fumed silica and anionic colloidal silica exhibit a zeta potential below negative 15 mv and wherein the weight of binder to total solids in the first coating composition is between 5% and 30%; whereby the boron-containing crosslinking compound diffuses into at least the ink-receiving layer to crosslink hydrophilic binder in at least the ink-receiving layer.

10 18. A method of manufacturing an inkjet recording element comprising the steps of:

15 (a) providing a resin-coated support;
 (b) treating the support with a subbing composition comprising a boron-containing crosslinking compound; and
 (c) coating a coating composition, for an ink-receiving layer, comprising particles of anionic fumed silica and hydrophilic hydroxyl-containing polymer as the primary binder capable of being substantially cross-linked by crosslinking compound not contained in the coating composition; wherein the ink-receiving layer is the only layer in the inkjet receiving element above the support
20 and any subbing layer; and

 wherein the particles of anionic fumed silica exhibit a zeta potential below negative 15 mv and wherein the weight of binder to total solids in the coating composition is less than 15 percent; whereby the boron-containing crosslinking compound diffuses into at least the ink-receiving layer to crosslink hydrophilic binder in at least the ink-receiving layer.

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2008/012094

A. CLASSIFICATION OF SUBJECT MATTER
INV. B41M5/50 B41M5/52

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
B41M

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 2007/050462 A (HEWLETT PACKARD DEVELOPMENT CO [US]; ILFORD IMAGING CH GMBH [CH]; BI Y) 3 May 2007 (2007-05-03) paragraphs [0022], [0038], [0041], [0044] ----- A WO 2004/094158 A (EASTMAN KODAK CO [US]; HOWE ANDREW [GB]; WESLEY ROBIN [GB]) 4 November 2004 (2004-11-04) pages 18-20; claims 1,5; table 1 pages 7-11 ----- A WO 2006/003391 A (EASTMAN KODAK CO [US]; BAKER JULIE [GB]) 12 January 2006 (2006-01-12) pages 6-8 ----- -/-	1-18
		1-18
		1-18 2

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

26 January 2009

Date of mailing of the international search report

12/02/2009

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Spyropoulou, E

INTERNATIONAL SEARCH REPORT

International application No PCT/US2008/012094

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 2006/078696 A1 (FURHOLZ URS [CH] ET AL) 13 April 2006 (2006-04-13) paragraphs [0023] - [0030], [0050], [0071] -----	1-18
P,A	WO 2008/082475 A (EASTMAN KODAK CO [US]; GHYZEL PETER JOHN [US]; BRINGLEY JOSEPH FRANCIS) 10 July 2008 (2008-07-10) pages 29,30 -----	1-18
P,A	WO 2008/075047 A (EASTMAN KODAK CO [US]; DESRousseaux STEPHANIE [GB]; FIOUR GERARD [FR];) 26 June 2008 (2008-06-26) pages 21,22,26 -----	1-18

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2008/012094

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 2007050462	A	03-05-2007	NONE	
WO 2004094158	A	04-11-2004	DE 602004008444 T2 EP 1613482 A1 JP 2006523555 T US 2006210730 A1	21-05-2008 11-01-2006 19-10-2006 21-09-2006
WO 2006003391	A	12-01-2006	EP 1773598 A1 JP 2008505780 T US 2008062234 A1	18-04-2007 28-02-2008 13-03-2008
US 2006078696	A1	13-04-2006	AU 2005293632 A1 CN 101035868 A EP 1655348 A1 WO 2006040304 A1 JP 2006111527 A KR 20070058691 A	20-04-2006 12-09-2007 10-05-2006 20-04-2006 27-04-2006 08-06-2007
WO 2008082475	A	10-07-2008	US 2008160228 A1	03-07-2008
WO 2008075047	A	26-06-2008	NONE	