



(11)

EP 3 533 892 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention of the grant of the patent:

02.11.2022 Bulletin 2022/44

(21) Application number: **17865353.1**

(22) Date of filing: **13.09.2017**

(51) International Patent Classification (IPC):

C21D 8/10 (2006.01)	C22C 38/50 (2006.01)
C22C 38/48 (2006.01)	C22C 38/44 (2006.01)
C22C 38/42 (2006.01)	C22C 38/06 (2006.01)
C22C 38/04 (2006.01)	C22C 38/02 (2006.01)
C22C 38/00 (2006.01)	C21D 9/08 (2006.01)
C22C 38/46 (2006.01)	C22C 38/52 (2006.01)

(52) Cooperative Patent Classification (CPC):

C21D 9/085; C21D 8/105; C22C 38/00;
C22C 38/001; C22C 38/02; C22C 38/04;
C22C 38/06; C22C 38/42; C22C 38/44;
C22C 38/46; C22C 38/48; C22C 38/50;
C22C 38/52; C21D 2211/008

(86) International application number:

PCT/JP2017/033008

(87) International publication number:

WO 2018/079111 (03.05.2018 Gazette 2018/18)

(54) **SEAMLESS PIPE OF MARTENSITIC STAINLESS STEEL FOR OIL WELL PIPE, AND METHOD FOR PRODUCING SEAMLESS PIPE**

NAHTLOSES ROHR AUS ROSTFREIEM MARTENSITISCHEN STAHL FÜR EIN ÖLBOHRROHR UND VERFAHREN ZUR HERSTELLUNG DES NAHTLOSEN ROHRS

SEAMLESS PIPE OF MARTENSITIC STAINLESS STEEL FOR OIL WELL PIPE, AND METHOD FOR PRODUCING SEAMLESS PIPE

(84) Designated Contracting States:

AL AT BE BG CH CY CZ DE DK EE ES FI FR GB
GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO
PL PT RO RS SE SI SK SM TR

(30) Priority: **25.10.2016 JP 2016208420**

(43) Date of publication of application:

04.09.2019 Bulletin 2019/36

(73) Proprietor: **JFE Steel Corporation**

Tokyo, 100-0011 (JP)

(72) Inventors:

- **ENDO Mami**
Tokyo 100-0011 (JP)
- **EGUCHI Kenichiro**
Tokyo 100-0011 (JP)

• **YUGA Masao**

Tokyo 100-0011 (JP)

(74) Representative: **Grünecker Patent- und Rechtsanwälte**

PartG mbB

Leopoldstraße 4

80802 München (DE)

(56) References cited:

EP-A1- 3 604 591	WO-A1-2014/112353
WO-A1-2015/178022	WO-A1-2015/178022
CN-B- 101 397 637	JP-A- 2003 003 243
JP-A- 2006 144 069	JP-A- 2007 169 776
JP-A- 2012 136 742	US-A1- 2005 224 143
US-A1- 2008 213 120	

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

Technical Field

[0001] The present invention relates to a martensitic stainless steel seamless pipe for use in oil country tubular goods used in oil well and gas well applications such as in crude oil wells and natural gas wells, and to a method for producing such a martensitic stainless steel seamless pipe. The invention particularly relates to improvement of corrosion resistance in a severe corrosive environment containing carbon dioxide gas (CO₂), chlorine ions (Cl⁻), and the like, and improvement of sulfide stress corrosion cracking resistance (SSC resistance) in a hydrogen sulfide (H₂S)-containing environment.

Background Art

[0002] Rising crude oil prices, and the increasing shortage of petroleum resources have prompted active development of deep oil fields that were unthinkable in the past, and oil fields and gas fields of a severe corrosive environment containing carbon dioxide gas, chlorine ions, and hydrogen sulfide. Steel pipes for oil country tubular goods (OCTG) intended for such an environment need to be made of materials having high strength, and excellent corrosion resistance.

[0003] Oil country tubular goods used for mining of oil fields and gas fields of an environment containing CO₂ gas, Cl⁻, and the like often use 13% Cr martensitic stainless steel pipes. In order to meet the increasing demand for higher SSC resistance arising out of the world-wide development of oil fields of a severe corrosive environment containing hydrogen sulfide, there has been increasing use of modified 13% Cr martensitic stainless steel pipes containing a reduced carbon content, and increased Ni and Mo contents.

[0004] PTL 1 discloses a 13% Cr steel basic composition containing Ni, Mo, and Cu, and a much smaller carbon content than in traditional compositions. These elements are contained to satisfy $Cr + 2Ni + 1.1Mo + 0.7Cu \leq 32.5$, and $Nb + V \geq 0.05\%$ for at least one of Nb: 0.20% or less, and V: 0.20% or less. The composition is described as being capable of providing high strength with a yield strength of 965 MPa or more, and high toughness with a Charpy absorption energy at -40°C of 50 J or more, in addition to desirable corrosion resistance.

[0005] PTL 2 describes a 13% Cr martensitic stainless steel pipe having an extremely low carbon content of 0.015% or less, and a Ti content of 0.03% or more. With such a composition, the 13% Cr martensitic stainless steel pipe can have high strength with a yield stress in the order of 95 ksi (655 to 758 MPa), low hardness with a Rockwell hardness HRC of less than 27, and excellent SSC resistance. PTL 3 describes a martensitic stainless steel that satisfies $6.0 \leq Ti/C \leq 10.1$, where Ti/C has a correlation with a value obtained by subtracting the yield stress from the tensile stress. The technique described in this publication can produce a value of 20.7 MPa or more as the difference of the yield stress from the tensile stress, and can reduce the hardness variation, which deteriorates the SSC resistance.

[0006] PTL 4 describes a martensitic stainless steel containing a specified amount of molybdenum satisfying $Mo \geq 2.3 - 0.89Si + 32.2C$, and having a metal structure that is configured primarily from tempered martensite, carbides that have precipitated during tempering, and intermetallic compounds, such as the Laves phase and the δ phase, that have finely precipitated during tempering. The technique described in this publication can achieve high strength with a 0.2% proof stress of 860 MPa or more, and excellent carbon dioxide corrosion resistance, and excellent sulfide stress corrosion cracking resistance.

[0007] WO 2015/178022 discloses a further high-strength stainless steel seamless pipe for oil wells having resistance to sulfide stress corrosion cracking and a method for producing the same.

Citation List

Patent Literature

[0008]

PTL 1: JP-A-2007-332442

PTL 2: JP-A-2010-242163

PTL 3: WO2008/023702

PTL 4: WO2004/057050

Summary of Invention

Technical Problem

[0009] Recent oil fields and gas fields are developed in severe corrosive environments containing CO₂, Cl⁻, and H₂S.

There are also rising concerns over increased H₂S concentrations due to aging. The oil country tubular goods used in these environments are thus required to have excellent sulfide stress corrosion cracking resistance (SSC resistance), in addition to carbon dioxide corrosion resistance. The technique of PTL 1 is described as providing excellent carbon dioxide corrosion resistance. However, there is no investigation of sulfide stress corrosion cracking resistance, and the technique cannot be said as providing the level of corrosion resistance that can withstand a severe corrosive environment.

[0010] It is stated in PTL 2 that sulfide stress corrosion cracking resistance can be maintained under an applied stress of 655 MPa in an atmosphere of a 5% NaCl aqueous solution (H₂S: 0.10 bar) with an adjusted pH of 3.5. PTL 3 describes providing sulfide stress corrosion cracking resistance in an atmosphere of a 20% NaCl aqueous solution (H₂S: 0.03 atm, CO₂ balance.) with an adjusted pH of 4.5. PTL 4 describes providing sulfide stress corrosion cracking resistance in an atmosphere of a 25% NaCl aqueous solution (H₂S: 0.003 MPa, CO₂ balance.) with an adjusted pH of 4.0. However, these techniques do not investigate sulfide stress corrosion cracking resistance in other atmospheres, and cannot be said as providing the level of sulfide stress corrosion cracking resistance that can withstand the today's more severe corrosive environments.

[0011] It is accordingly an object of the present invention to provide a martensitic stainless steel seamless pipe having high strength, and excellent sulfide stress corrosion cracking resistance, intended for oil country tubular goods. The invention is also intended to provide a method for producing such a martensitic stainless steel seamless pipe for oil country tubular goods.

[0012] As used herein, "high-strength" means a yield stress of 758 MPa (110 ksi) or more. Preferably, the yield stress is 896 MPa or less.

[0013] As used herein, "excellent sulfide stress corrosion cracking resistance" means that a test piece dipped in a test solution (a 0.165 mass% NaCl aqueous solution; liquid temperature: 25°C, H₂S: 1 bar, CO₂ balance) having an adjusted pH of 3.5 with addition of sodium acetate and hydrochloric acid does not crack even after 720 hours under an applied stress equal to 90% of the yield stress.

Solution to Problem

[0014] In order to achieve the foregoing objects, the present inventors conducted intensive studies of various alloy elements in a basic composition of a 13% Cr stainless steel pipe with regard to the effects of these elements on sulfide stress corrosion cracking resistance (SSC resistance) in a corrosive environment containing CO₂, Cl⁻, and H₂S. As a result of the investigation, the present inventors have found that a martensitic stainless steel seamless pipe for oil country tubular goods having the desired strength, and excellent SSC resistance in a CO₂-, Cl⁻-, and H₂S-containing corrosive environment under an applied stress close to the yield stress can be produced when a composition containing C, Mn, Cr, Cu, Ni, Mo, W, Nb, N, and Ti in adjusted amounts that satisfy appropriate relations and ranges is subjected to appropriate quenching and tempering treatments.

[0015] The present invention was completed on the basis of these findings after further studies, and the invention is specified in the appended claims.

Advantageous Effects of Invention

[0016] The present invention can produce a martensitic stainless steel seamless pipe for oil country tubular goods having excellent sulfide stress corrosion cracking resistance (SSC resistance) in a CO₂-, Cl⁻-, and H₂S-containing corrosive environment, and high strength with a yield stress YS of 758 MPa (110 ksi) or more.

Description of Embodiments

[0017] A seamless stainless steel pipe of the present invention is a martensitic stainless steel seamless pipe for oil country tubular goods. The martensitic stainless steel seamless pipe has a basic

[0018] composition that contains, in mass%, C: 0.035% or less, Si: 0.5% or less, Mn: 0.05 to 0.5%, P: 0.03% or less, S: 0.005% or less, Cu: 2.6% or less, Ni: 5.3 to 7.3%, Cr: 11.8 to 14.5%, Al: 0.1% or less, Mo: 1.8 to 3.0%, V: 0.2% or less, N: 0.1% or less, and the balance Fe and unavoidable impurities, and that satisfies the following formula (4) with the following formulae (1), (2), and (3). The martensitic stainless steel seamless pipe has a yield stress of 758 MPa or more.

Formula (1)

$$-109.37C + 7.307Mn + 6.399Cr + 6.329Cu + 11.343Ni - 13.529Mo + 1.276W + 2.925Nb + 196.775N - 2.621Ti - 120.307$$

Formula (2)

$$-0.0278\text{Mn} + 0.0892\text{Cr} + 0.00567\text{Ni} + 0.153\text{Mo} - 0.0219\text{W} - 1.984\text{N} + 0.208\text{Ti} - 1.83$$

Formula (3)

$$-1.324\text{C} + 0.0533\text{Mn} + 0.0268\text{Cr} + 0.0893\text{Cu} + 0.00526\text{Ni} + 0.0222\text{Mo} - 0.0132\text{W} - 0.473\text{N} - 0.5\text{Ti} - 0.514$$

[0019] In the formulae (1) to (3), C, Mn, Cr, Cu, Ni, Mo, W, Nb, N, and Ti represent the content of each element in mass% the content being 0 (zero) percent for elements that are not contained.

Formula (4)

$$-10 \leq \text{formula (1)} \leq 45, -0.25 \leq \text{formula (2)} \leq -0.20, \text{ and } 0.10 \leq \text{formula (3)} \leq 0.20$$

Formula (5) (not part of the invention)

$$-10 \leq \text{formula (1)} \leq 5, -0.35 \leq \text{formula (2)} \leq -0.25, \text{ and } 0.025 \leq \text{formula (3)} \leq 0.10$$

Formula (6) (not part of the invention)

$$-10 \leq \text{formula (1)} \leq -5, -0.39 \leq \text{formula (2)} \leq -0.35, \text{ and } -0.15 \leq \text{formula (3)} \leq 0.025$$

[0020] The reasons for specifying the composition of the steel pipe of the present invention are as follows. In the following, "%" means percent by mass, unless otherwise specifically stated.

C: 0.035% or Less

[0021] Carbon is an important element involved in the strength of the martensitic stainless steel, and effectively improves the strength. However, a carbon content of more than 0.035% makes the hardness excessively high, and increases the sensitivity to sulfide stress corrosion cracking. For this reason, the C content is limited to 0.035% or less in the present invention. Preferably, the C content is 0.015% or less. More preferably, the C content is 0.0090% or less. Further preferably, the C content is 0.0075% or less. Desirably, carbon is contained in an amount of 0.005% or more to provide the desired strength.

Si: 0.5% or Less

[0022] Silicon acts as a deoxidizing agent, and should be contained in an amount of 0.05% or more. A Si content of more than 0.5% deteriorates carbon dioxide corrosion resistance and hot workability. For this reason, the Si content is limited to 0.5% or less. The lower limit of Si content is preferably 0.10% or more, and the upper limit of Si content is preferably 0.30% or less.

EP 3 533 892 B1

Mn: 0.05 to 0.5%

[0023] Manganese is an element that improves hot workability, and is contained in an amount of 0.05% or more. When contained in excess of 0.5%, the effect becomes saturated, and this leads to increased cost. For this reason, the Mn content is limited to 0.05 to 0.5%. Preferably, the Mn content is 0.40% or less.

P: 0.03% or Less

[0024] Phosphorus is an element that deteriorates carbon dioxide corrosion resistance, pitting corrosion resistance, and sulfide stress corrosion cracking resistance, and should be contained in as small an amount as possible in the present invention. However, an excessively small P content leads to increased manufacturing cost. The P content is therefore limited to 0.03% or less, a content that does not bring about an excessive loss of characteristics, and that is industrially feasible in terms of cost. Preferably, the P content is 0.02% or less.

S: 0.005% or Less

[0025] Sulfur is an element that seriously deteriorates hot workability, and should desirably be contained in as small an amount as possible. A S content of 0.005% or less enables pipe production using common procedures, and accordingly the S content is limited to 0.005% or less in the present invention. Preferably, the S content is 0.003% or less.

Cu: 2.6% or Less

[0026] Copper adds strength to the protective coating, and improves sulfide stress corrosion cracking resistance. However, a Cu content of more than 2.6% causes precipitation of CuS, and deteriorates hot workability. For this reason, the Cu content is limited to 2.6% or less. The lower limit of Cu content is preferably 0.5% or more, and the upper limit of Cu content is preferably 2.0% or less.

Ni: 5.3 to 7.3%

[0027] When contained in an amount of 5.3% or more, nickel adds strength to the protective coating, and improves corrosion resistance. Nickel also forms a solid solution, and increases the steel strength in this content range. A Ni content of more than 7.3% makes the martensite phase unstable, and the strength deteriorates. For this reason, the Ni content is limited to 5.3 to 7.3%. Preferably, the Ni content is 5.7% or more, more preferably 6.0% or more.

Cr: 11.8 to 14.5%

[0028] Chromium is an element that forms a protective coating, and improves the corrosion resistance. Chromium provides the corrosion resistance necessary for oil country tubular goods applications when contained in an amount of 11.8% or more. A Cr content of more than 14.5% facilitates ferrite generation, and the martensite phase cannot remain stable. For this reason, the Cr content is limited to 11.8 to 14.5%. The lower limit of Cr content is preferably 12.0% or more, and the upper limit of Cr content is preferably 13.5% or less.

Al: 0.1% or Less

[0029] Aluminum acts as a deoxidizing agent. An Al content of 0.01% or more effectively provides this effect. Because an Al content of more than 0.1% adversely affects toughness, the Al content is limited to 0.1% or less in the present invention. Preferably, the Al content is 0.01 to 0.03%.

Mo: 1.8 to 3.0%

[0030] Molybdenum is an element that improves the pitting corrosion resistance caused by Cl⁻. Molybdenum needs to be contained in an amount of 1.8% or more to obtain the corrosion resistance necessary for a severe corrosive environment. The effect becomes saturated when the Mo content is more than 3.0%. Molybdenum is also an expensive element, and increases the manufacturing cost. For these reasons, the Mo content is limited to 1.8 to 3.0%. The lower limit of Mo content is preferably 2.4% or more, and the upper limit of Mo content is preferably 2.9% or less.

V: 0.2% or Less

[0031] Vanadium is contained in an amount of desirably 0.01% or more, in order to improve steel strength by precipitation strengthening, and to improve sulfide stress corrosion cracking resistance. A V content of more than 0.2% deteriorates toughness, and the V content is limited to 0.2% or less in the present invention. The lower limit of V content is preferably 0.01% or more, and the upper limit of V content is preferably 0.08% or less.

N: 0.1% or Less

[0032] Nitrogen is an element that greatly improves the pitting corrosion resistance. However, a N content of more than 0.1% causes formation of various nitrides, and deteriorates toughness. For this reason, the N content is limited to 0.1% or less in the present invention. Preferably, the N content is 0.003% or more. The lower limit of N content is more preferably 0.004% or more, further preferably 0.005% or more. The upper limit of N content is more preferably 0.08% or less, further preferably 0.05% or less.

[0033] In the present invention, C, Mn, Cr, Cu, Ni, Mo, W, Nb, N, and Ti are contained in the foregoing ranges, and these are contained so as to satisfy the formula (4), with the formulae (1), (2), and (3) below. Formula (5) and (6) are not part of the present invention. Formula (1) is a formula that correlates with the residual γ amount. By making the calculated value of formula (1) smaller, the residual austenite is reduced, and the hardness reduces, with the result that the sulfide stress corrosion cracking resistance improves. Formula (2) is a formula that correlates with the repassivation potential. Regeneration of the passivation coating occurs more easily, and repassivation improves by containing C, Mn, Cr, Cu, Ni, Mo, W, Nb, N, and Ti in such amounts that formula (1) yields a value that satisfies the range of formula (4) and by containing Mn, Cr, Cu, Ni, Mo, W, N, and Ti in such amounts that formula (2) yields a value that satisfies the range of formula (4), (5), or (6). Formula (3) is a formula that correlates with the pitting corrosion potential. Pitting corrosion, which becomes an origin of sulfide stress corrosion cracking, can be suppressed, and the sulfide stress corrosion cracking resistance greatly improves by containing C, Mn, Cr, Cu, Ni, Mo, W, N, and Ti in such amounts that formula (3) yields a value that satisfies the range of formula (4). With the calculated value of formula (1) satisfying the range of formula (4), the hardness increases when the calculated value of formula (1) is 10 or more. However, regeneration of a passivation coating occurs more prominently, and the pitting corrosion can be suppressed more effectively when the calculated values of formulae (2) and (3) satisfy the range of formula (4). This improves the sulfide stress corrosion cracking resistance.

[0034] The calculated value of formula (1) is preferably 5 to 45 in the following formula (4).

Formula (1)

$$-109.37C + 7.307Mn + 6.399Cr + 6.329Cu + 11.343Ni - 13.529Mo + 1.276W + 2.925Nb + 196.775N - 2.621Ti - 120.307$$

Formula (2)

$$-0.0278Mn + 0.0892Cr + 0.00567Ni + 0.153Mo - 0.0219W - 1.984N + 0.208Ti - 1.83$$

Formula (3)

$$-1.324C + 0.0533Mn + 0.0268Cr + 0.0893Cu + 0.00526Ni + 0.0222Mo - 0.0132W - 0.473N - 0.5Ti - 0.514$$

[0035] In the formulae (1) to (3), C, Mn, Cr, Cu, Ni, Mo, W, Nb, N, and Ti represent the content of each element in mass% the content is 0 (zero) percent for elements that are not contained.

Formula (4)

$$-10 \leq \text{formula (1)} \leq 45, -0.25 \leq \text{formula (2)} \leq -0.20, \text{ and}$$

$$0.10 \leq \text{formula (3)} \leq 0.20$$

Formula (5) (not part of the invention)

$$-10 \leq \text{formula (1)} \leq 5, -0.35 \leq \text{formula (2)} \leq -0.25, \text{ and}$$

$$0.025 \leq \text{formula (3)} \leq 0.10$$

Formula (6) (not part of the invention)

$$-10 \leq \text{formula (1)} \leq -5, -0.39 \leq \text{formula (2)} \leq -0.35, \text{ and}$$

$$-0.15 \leq \text{formula (3)} \leq 0.025$$

[0036] In addition to the foregoing components, the composition contains the balance Fe and unavoidable impurities. The foregoing basic composition may further contain one or more selectable elements selected from Ti: 0.19% or less, Nb: 0.25% or less, W: 1.1% or less, and Co: 0.45% or less, as needed.

[0037] Titanium and niobium form carbides, and can reduce the solid-solution carbon. This makes it possible to reduce hardness. Excessively high Ti and Nb contents may deteriorate toughness, and the Ti and Nb contents are limited to 0.19% or less for Ti, and 0.25% or less for Nb when containing these elements.

[0038] Tungsten and cobalt are elements that improve the pitting corrosion resistance. However, excessively high W and Co contents may deteriorate toughness, and increase the material cost. For this reason, the W and Co contents are limited to 1.1% or less for W, and 0.45% or less for Co when containing these elements.

[0039] A preferred method for producing the martensitic stainless steel seamless pipe for oil country tubular goods of the present invention is described below.

[0040] The present invention uses a steel pipe material of the composition described above. The method of production of the steel pipe material, or a seamless stainless steel pipe, is not particularly limited, and any known seamless steel pipe production method may be used.

[0041] Preferably, a molten steel of the foregoing composition is made into steel using a steel making process such as by using a converter furnace, and formed into a steel pipe material, for example, a billet, using a method such as continuous casting, and ingot casting-slab rolling. The steel pipe material is heated, and hot worked using a known pipe manufacturing process, for example, such as the Mannesmann-plug mill process, and the Mannesmann-mandrel mill process to produce a seamless steel pipe of the foregoing composition.

[0042] The process that follows the production of the steel pipe from the steel pipe material is not particularly limited. Preferably, the steel pipe is subjected to quenching, in which the steel pipe is heated to a temperature equal to or greater than the Ac_3 transformation point, and air cooled to a cooling stop temperature of 100°C or less at a cooling rate of 0.1°C/s or more, and this is followed by tempering at a temperature equal to or less than the Ac_1 transformation point.

Quenching

[0043] In the present invention, the steel pipe is subjected to quenching, in which the steel pipe is reheated to a temperature equal to or greater than the Ac_3 transformation point, maintained for preferably at least 5 min, and air cooled to a cooling stop temperature of 100°C or less. This produces a fine martensite phase, and high toughness. When the quenching heating temperature is less than the Ac_3 transformation point, heating cannot be made in the single austenite phase region, and a sufficient martensite structure cannot be obtained in the subsequent cooling. In this case, the desired high strength cannot be obtained. For this reason, the quenching heating temperature is limited to a temperature equal to or greater than the Ac_3 transformation point. Here, "air cooling" means a cooling rate of 0.1°C/s or more.

Tempering

[0044] Quenching of the steel pipe is followed by tempering. The tempering is a process by which the steel pipe is

heated to a temperature equal to or less than the Ac_1 transformation point, maintained for preferably at least 10 min, and air cooled. When the tempering temperature is higher than the Ac_1 transformation point, the martensite phase precipitates after the tempering, and it is not possible to obtain the desired high toughness and excellent corrosion resistance. For this reason, the tempering temperature is limited to a temperature equal to or less than the Ac_1 transformation point. The Ac_3 transformation point ($^{\circ}C$), and the Ac_1 transformation point ($^{\circ}C$) can be measured by a Formaster test, in which the test piece is given a heating and cooling temperature history, and the transformation point is detected from a small displacement due to expansion and contraction.

Examples

[0045] The present invention is further described below through Examples.

[0046] Molten steels of the compositions shown in Table 1 were made into steel with a converter furnace, and cast into billets (steel pipe material) by continuous casting. The steel pipe material was then hot worked with a model seamless rolling machine, and air cooled (cooling rate of $0.5^{\circ}C/s$) to produce a seamless steel pipe measuring 83.8 mm in outer diameter and 12.7 mm in wall thickness.

[0047] The seamless steel pipe was cut to obtain a test material, which was then subjected to quenching and tempering under the conditions shown in Table 2. A test piece for structure observation was collected from the quenched and tempered test material, and was polished, and measured for residual austenite (γ) amount by an X-ray diffraction method.

[0048] Specifically, the diffraction X-ray integral intensities of the γ (220) plane and the α (211) plane were measured. The results were then converted using the following equation.

$$\gamma \text{ (Volume fraction)} = 100 / (1 + (I_{\alpha}R_{\gamma} / I_{\gamma}R_{\alpha}))$$

[0049] In the equation, I_{α} represents the integral intensity of α , R_{α} represents a crystallographic theoretical value for α , I_{γ} represents the integral intensity of γ , and R_{γ} represents a crystallographic theoretical value for γ .

[0050] A strip specimen specified by API standard 5CT was collected from the quenched and tempered test material, and subjected to a tensile test according to the API specifications to determine its tensile characteristics (yield stress YS, tensile stress TS). The Ac_3 point ($^{\circ}C$) and the Ac_1 point ($^{\circ}C$) shown in Table 2 were measured by conducting a Formaster test for a test piece (measuring 4 mm in diameter $\phi \times 10$ mm) collected from the quenched test material. Specifically, the test piece was heated to $500^{\circ}C$ at $5^{\circ}C/s$, maintained for 10 minutes after raising the temperature to $920^{\circ}C$ at $0.25^{\circ}C/s$, and cooled to room temperature at $2^{\circ}C/s$. The Ac_3 point ($^{\circ}C$) and the Ac_1 point ($^{\circ}C$) were found by detecting the expansion and contraction of the test piece with the temperature history.

[0051] The SSC test was conducted according to NACE TM0177, Method A. The test environment was created by using a 0.165 mass% NaCl test solution after adjusting the solution pH to 3.5 by addition of 0.41 g/L of CH_3COONa and HCl, and the test was conducted under a hydrogen sulfide partial pressure of 0.1 MPa, and an applied stress equal to 90% of the yield stress.

[0052] The results are presented in Table 2.

[Table 1]

Steel No.	Composition (mass%)													Applied formula (*4)	Remarks			
	C	Si	Mn	P	S	Cu	Ni	Cr	Al	Mo	V	N	Ti, Nb, W, Co			Value of formula (1) (*1)	Value of formula (2) (*2)	Value of formula (3) (*3)
A	0.0088	0.205	0.11	0.013	0.0009	2.04	7.25	14.16	0.052	2.513	0.010	0.0471	Nb: 0.091	40.8	-0.238	0.114	(4)	Compliant Example
B	0.0075	0.200	0.45	0.015	0.0010	2.50	6.40	13.30	0.020	2.600	0.015	0.0085	Ti: 0.025, Nb: 0.08	22.4	-0.234	0.155	(4)	Compliant Example
C	0.0075	0.200	0.40	0.015	0.0010	2.40	6.25	13.20	0.020	2.550	0.015	0.0085	Ti:0.05, Nb: 0.01	19.4	-0.245	0.126	(4)	Compliant Example
D	0.0075	0.200	0.40	0.015	0.0010	1.80	6.00	12.30	0.040	2.850	0.015	0.0075	Ti:0.05, Nb: 0.005	2.8	-0.278	0.054	(5)	Reference Example
E	0.0075	0.200	0.40	0.015	0.0010	0.40	5.70	12.00	0.040	2.550	0.015	0.0075	Ti:0.05, Nb: 0.005	-7.4	-0.353	-0.087	(6)	Reference Example
F	0.0075	0.200	0.40	0.015	0.0010	1.60	5.70	12.20	0.040	2.600	0.015	0.0075	Ti:0.05, Nb: 0.005	0.8	-0.327	0.026	(5)	Reference Example
G	0.0075	0.204	0.41	0.015	0.0009	2.40	6.24	13.22	0.020	2.553	0.015	0.0043	-	18.7	-0.245	0.154	(4)	Compliant Example
H	0.0059	0.198	0.41	0.014	0.0010	1.81	5.99	12.32	0.042	2.850	0.014	0.0065	-	3.0	-0.285	0.084	(5)	Reference Example

(continued)

[Table 1] Continued																
Steel No.	Composition (mass%)											Value of formula (1) (*1)	Value of formula (2) (*2)	Value of formula (3) (*3)	Applied formula (*4)	Remarks
	C	Si	Mn	P	S	Cu	Ni	Cr	Al	Mo	V	N	Ti, Nb, W, Co			
I	0.0063	0.200	0.40	0.015	0.0009	0.41	5.71	12.02	0.043	2.552	0.014	0.0066	-	-7.0	-0.359	-0.059
J	0.0076	0.210	0.45	0.014	0.0011	2.51	6.40	13.30	0.020	2.605	0.015	0.0032	W:0.16	21.3	-0.231	0.168
K	0.0072	0.195	0.40	0.013	0.0010	0.39	5.71	12.00	0.042	2.550	0.016	0.0074	Co:0.2	-7.2	-0.363	-0.063
L	0.0069	0.189	0.42	0.014	0.0009	1.95	6.34	12.57	0.046	2.555	0.018	0.0070	-	13.5	-0.307	0.097
M	0.0080	0.192	0.11	0.013	0.0009	2.03	7.21	12.32	0.052	2.529	0.013	0.0067	-	20.2	-0.320	0.084
N	0.0060	0.195	0.10	0.012	0.0008	2.00	7.16	12.38	0.043	2.519	0.014	0.0064	-	20.0	-0.315	0.084
O	0.0064	0.216	0.21	0.018	0.0011	0.01	5.85	12.62	0.044	2.179	0.018	0.0056	-	-0.7	-0.355	-0.096
P	0.0072	0.223	0.20	0.014	0.0011	0.01	5.98	12.04	0.037	2.168	0.018	0.0076	-	-2.5	-0.411	-0.113
The balance is Fe and unavoidable impurities																
(*1) Formula (1): -109.37C+7.307Mn+6.399Cr+6.329Cu+11.343Ni-13.529Mo+1.276W+2.925Nb+196.775N-2.621Ti-120.307																
(*2) Formula (2): -0.0278Mn+0.0892Cr+0.00567Ni+0.153Mo-0.0219W-1.984N+0.208Ti-1.83																
(*3) Formula (3): -1.324C+0.0533Mn+0.0268Cr+0.0893Cu+0.00526Ni+0.0222Mo-0.0132W-0.473N-0.5Ti-0.514																
(*4) The formula used for determination																

EP 3 533 892 B1

Formula (4): $-10 \leq \text{formula (1)} \leq 45$, $-0.25 \leq \text{formula (2)} \leq -0.20$, and $0.10 \leq \text{formula (3)} \leq 0.20$

5

Formula (5): $-10 \leq \text{formula (1)} \leq 5$, $-0.35 \leq \text{formula (2)} \leq -0.25$, and $0.025 \leq \text{formula (3)} \leq 0.10$

Formula (6): $-10 \leq \text{formula (1)} \leq -5$, $-0.39 \leq \text{formula (2)} \leq -0.35$, and $-0.15 \leq \text{formula (3)} \leq 0.025$

10

15

20

25

30

35

40

45

50

55

[Table 2]

Steel pipe No.	Steel No.	Quenching						Tempering			Structure	Tensile characteristics		SSC resistance test	Remarks
		Ac ₃ point (°C)	Heating temperature (°C)	Holding time (min)	Cooling	Cooling stop temperature (°C)	Ac ₁ point (°C)	Heating temperature (°C)	Holding time (min)	Residual γ (*) (volume%)		Yield stress YS (MPa)	Tensile stress TS (MPa)		
1	A	750	920	20	Air cooling	25	640	615	60	43.5	835	986	Absent	Present Example	
2	B	750	920	20	Air cooling	25	645	625	60	25.6	828	952	Absent	Present Example	
3	C	755	920	20	Air cooling	25	635	630	60	21.7	851	967	Absent	Present Example	
4	D	750	920	20	Air cooling	25	630	615	60	5.3	846	929	Absent	Reference Example	
5	E	755	920	20	Air cooling	25	660	565	60	0.0	829	864	Absent	Reference Example	
6	F	745	920	20	Air cooling	25	635	625	60	2.4	863	892	Absent	Reference Example	
7	G	755	920	20	Air cooling	25	635	625	60	22.1	830	964	Absent	Present Example	
8	H	750	920	20	Air cooling	25	625	615	60	6.3	851	903	Absent	Reference Example	
9	I	755	920	20	Air cooling	25	655	600	60	0.0	832	871	Absent	Reference Example	
10	J	750	920	20	Air cooling	25	640	605	60	24.2	842	975	Absent	Present Example	
11	K	750	920	20	Air cooling	25	660	610	60	0.0	836	862	Absent	Reference Example	
12	L	755	990	20	Air cooling	25	630	605	60	15.3	906	1009	Present	Comparative Example	

(continued)

Steel pipe No.	Steel No.	Quenching						Tempering			Structure	Tensile characteristics		SSC resistance test	Remarks
		Ac ₃ point (°C)	Heating temperature (°C)	Holding time (min)	Cooling	Cooling stop temperature (°C)	Ac ₁ point (°C)	Heating temperature (°C)	Holding time (min)	Residual γ (*1) (volume%)		Yield stress YS (MPa)	Tensile stress TS (MPa)		
13	M	720	920	20	Air cooling	25	625	620	60	24.1		835	965	Present	Comparative Example
14	N	730	930	20	Air cooling	25	620	600	60	23.5		859	958	Present	Comparative Example
15	<u>O</u>	740	920	20	Air cooling	25	660	595	60	0.1		852	885	Present	Reference Comparative Example
16	P	730	920	20	Air cooling	25	630	590	60	0.0		847	880	Present	Reference Comparative Example
17	A	750	730	20	Air cooling	25	640	615	60	49.8		792	866	Present	Comparative Example
18	C	755	920	20	Air cooling	25	635	650	60	34.6		772	811	Present	Comparative Example
(*1) Residual γ : Residual austenite															

[0053] The martensitic stainless steel seamless pipes of the present examples all had high strength with a yield stress of 758 MPa or more, and excellent SSC resistance that did not involve cracking even under the applied stress in the H₂S environment. Comparative Examples outside the range of the present invention did not show excellent SSC resistance, though the desired levels of high strength were obtained.

Claims

1. A martensitic stainless steel seamless pipe for oil country tubular goods,

the martensitic stainless steel seamless pipe having a composition that comprises, in mass%, C: 0.035% or less, Si: 0.5% or less, Mn: 0.05 to 0.5%, P: 0.03% or less, S: 0.005% or less, Cu: 2.6% or less, Ni: 5.3 to 7.3%, Cr: 11.8 to 14.5%, Al: 0.1% or less, Mo: 1.8 to 3.0%, V: 0.2% or less, N: 0.1% or less, optionally, in mass%, at least one selected from Ti: 0.19% or less, Nb: 0.25% or less, W: 1.1% or less, and Co: 0.45% or less, and the balance Fe and unavoidable impurities, and that satisfies the following formula (4) with the following formulae (1), (2), and (3),

the martensitic stainless steel seamless pipe having a yield stress of 758 MPa or more measured in accordance with API standard 5CT.

Formula (1)

$$-109.37C + 7.307Mn + 6.399Cr + 6.329Cu + 11.343Ni - 13.529Mo + 1.276W + 2.925Nb + 196.775N - 2.621Ti - 120.307$$

Formula (2)

$$-0.0278Mn + 0.0892Cr + 0.00567Ni + 0.153Mo - 0.0219W - 1.984N + 0.208Ti - 1.83$$

Formula (3)

$$-1.324C + 0.0533Mn + 0.0268Cr + 0.0893Cu + 0.00526Ni + 0.0222Mo - 0.0132W - 0.473N - 0.5Ti - 0.514$$

In the formulae (1) to (3), C, Mn, Cr, Cu, Ni, Mo, W, Nb, N, and Ti represent the content of each element in mass%, the content being 0 (zero) percent for elements that are not contained.

Formula (4)

$$-10 \leq \text{formula (1)} \leq 45, -0.25 \leq \text{formula (2)} \leq -0.20, \text{ and } 0.10 \leq \text{formula (3)} \leq 0.20$$

2. A method for producing the martensitic stainless steel seamless pipe for oil country tubular goods of claim 1, the method comprising:

making a steel pipe out of a steel pipe material with a composition as defined in claim 1;
subjecting the steel pipe to quenching in which the steel pipe is heated to a temperature equal to or greater than the Ac₃ transformation point, and air cooled to a cooling stop temperature of 100°C or less at a cooling rate of 0.1°C/s or more; and
tempering the steel pipe at a temperature equal to or less than the Ac₁ transformation point.

Patentansprüche**1. Nahtloses Rohr aus martensitischem Edelstahl für Ölfeldrohre,**

wobei das nahtlose Rohr aus martensitischem Edelstahl eine Zusammensetzung hat, die, in Masse-%, 0,035 % oder weniger C, 0,5 % oder weniger Si, 0,05 bis 0,5 % Mn, 0,03 % oder weniger P, 0,005 % oder weniger S, 2,6 % oder weniger Cu, 5,3 bis 7,3 % Ni, 11,8 bis 14,5 % Cr, 0,1 % oder weniger Al, 1,8 bis 3,0 % Mo, 0,2 % oder weniger V, 0,1 % oder weniger N und optional wenigstens einen Bestandteil umfasst, der ausgewählt wird aus: 0,19 % oder weniger Ti, 0,25 % oder weniger Nb, 1,1 % oder weniger W, sowie 0,45 % oder weniger Co, und der Rest Fe sowie unvermeidbare Verunreinigungen sind, und die die folgende Formel (4) mit den untenstehenden Formeln (1), (2) und (3) erfüllt, wobei das nahtlose Rohr aus martensitischem Edelstahl eine Streckspannung von 758 MPa oder mehr, gemessen gemäß dem API-Standard 5CT, hat.

Formel (1)

$$-109,37C + 7,307Mn + 6,399Cr + 6,329Cu + 11,343Ni - 13,529Mo + 1,276W + 2,925Nb + 196,775N - 2,621Ti - 120,307$$

Formel (2)

$$-0,0278Mn + 0,0892Cr + 0,00567Ni + 0,153Mo - 0,0219W - 1,984N + 0,208Ti - 1,83$$

Formel (3)

$$-1,324C + 0,0533Mn + 0,0268Cr + 0,0893Cu + 0,00526Ni + 0,0222Mo - 0,0132W - 0,473N - 0,5Ti - 0,514$$

wobei in den Formeln (1) bis (3) C, Mn, Cr, Cu, Ni, Mo, W, Nb, N und Ti für den Gehalt der einzelnen Elemente in Masse-% stehen und der Gehalt für nicht enthaltene Elemente 0 (null) Prozent beträgt,

Formel (4)

$$-10 \leq \text{Formel (1)} \leq 45, -0,25 \leq \text{Formel (2)} \leq -0,20, \text{ und } 0,10 \leq \text{Formel (3)} \leq 0,20.$$

2. Verfahren zum Herstellen des nahtlosen Rohrs aus martensitischem Edelstahl für Ölfeldrohre nach Anspruch 1, wobei das Verfahren umfasst:

Erzeugen eines Stahlrohrs aus einem Stahlrohrmaterial mit einer Zusammensetzung wie in Anspruch 1 definiert; Durchführen von Abschrecken des Stahlrohrs, bei dem das Stahlrohr auf eine Temperatur erhitzt wird, die auf oder über dem AC_3 -Umwandlungspunkt liegt, und mit einer Abkühlgeschwindigkeit von 0,1 °C/s oder mehr auf eine Abkühl-Endtemperatur von 100 °C oder darunter luftgekühlt wird; sowie Anlassen des Stahlrohrs bei einer Temperatur auf oder unter dem AC_1 -Umwandlungspunkt.

Revendications**1. Tube sans soudure en acier inoxydable martensitique pour produits tubulaires pétroliers,**

le tube sans soudure en acier inoxydable martensitique ayant une composition qui comprend, en % massique, C : 0,035 % ou moins, Si : 0,5 % ou moins, Mn : 0,05 à 0,5 %, P : 0,03 % ou moins, S : 0,005 % ou moins, Cu : 2,6 % ou moins, Ni : 5,3 à 7,3 %, Cr : 11,8 à 14,5 %, Al : 0,1 % ou moins, Mo : 1,8 à 3,0 %, V : 0,2 % ou moins, N : 0,1 % ou moins, éventuellement, en % massique, au moins un élément choisi parmi Ti : 0,19 % ou moins, Nb : 0,25 % ou moins, W : 1,1 % ou moins et Co : 0,45 % ou moins, le reste étant du Fe et des impuretés inévitables, et qui satisfait à la formule (4) suivante avec les formules (1), (2) et (3) suivantes, le tube sans soudure en acier inoxydable martensitique ayant une limite d'élasticité de 758 MPa ou plus mesurée

conformément à la norme API 5CT.

Formule (1)

$$-109,37C + 7,307Mn + 6,399Cr + 6,329Cu + 11,343Ni - 13,529Mo + 1,276W + 2,925Nb + 196,775N - 2,621Ti - 120,307$$

Formule (2)

$$-0,0278Mn + 0,0892Cr + 0,00567Ni + 0,153Mo - 0,0219W - 1,984N + 0,208Ti - 1,83$$

Formule (3)

$$-1,324C + 0,0533Mn + 0,0268Cr + 0,0893Cu + 0,00526Ni + 0,0222Mo - 0,0132W - 0,473N - 0,5Ti - 0,514$$

Dans les formules (1) à (3), C, Mn, Cr, Cu, Ni, Mo, W, Nb, N et Ti représentent la teneur de chaque élément en % massique, la teneur étant de 0 (zéro) pourcent pour les éléments non présents.

Formule (4)

$$-10 \leq \text{formule (1)} \leq 45, -0,25 \leq \text{formule (2)} \leq -0,20 \text{ et } 0,10 \leq \text{formule (3)} \leq 0,20.$$

2. Procédé de production du tube sans soudure en acier inoxydable martensitique pour produits tubulaires pétroliers selon la revendication 1, le procédé comprenant :

la fabrication d'un tube en acier à partir d'un matériau de tube d'acier ayant la composition définie à la revendication 1 ;

la soumission du tube en acier à une trempe au cours de laquelle le tube en acier est chauffé à une température supérieure ou égale au point de transformation Ac_3 , et refroidi à l'air jusqu'à une température d'arrêt du refroidissement de 100 °C ou moins à une vitesse de refroidissement de 0,1 °C/s ou plus ; et

le revenu du tube en acier à une température inférieure ou égale au point de transformation Ac_1 .

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- WO 2015178022 A [0007]
- JP 2007332442 A [0008]
- JP 2010242163 A [0008]
- WO 2008023702 A [0008]
- WO 2004057050 A [0008]