



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification<sup>4</sup> :</b>  <b>C08L 71/04, 77/00, 51/04</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 87/ 03893</b>  <b>(43) International Publication Date:</b> 2 July 1987 (02.07.87)
<b>(21) International Application Number:</b> PCT/US86/02725 <b>(22) International Filing Date:</b> 19 December 1986 (19.12.86)  <b>(31) Priority Application Number:</b> 811,808 <b>(32) Priority Date:</b> 20 December 1985 (20.12.85) <b>(33) Priority Country:</b> US  <b>(71) Applicant:</b> GENERAL ELECTRIC COMPANY [US/ US]; 1 River Road, Schenectady, NY 12305 (US). <b>(72) Inventors:</b> BATES, Gary, Mell ; RD 1, Box 331, Voor- heesville, NY 12186 (US). CHAMBERS, Gregory, Robert ; 17 Parkwyn Drive, Delmar, NY 12158 (US). TING, Sai-Pei ; 494 Stratton Place, Delmar, NY 12054 (US). <b>(74) Agents:</b> KING, Arthur, M.; International Patent Opera- tion, General Electric Company, 1285 Boston Avenue, Bridgeport, CT 06602 (US) et al.		<b>(81) Designated States:</b> DE (European patent), FR (Euro- pean patent), GB (European patent), IT (European patent), JP, NL (European patent).  <b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the</i> <i>claims and to be republished in the event of the receipt</i> <i>of amendments.</i>
<b>(54) Title:</b> IMPACT MODIFIED POLYPHENYLENE ETHER-POLYAMIDE COMPOSITIONS  <b>(57) Abstract</b>  Thermoplastic compositions comprised of compatible combinations of a polyphenylene ether resin and a polyamide resin and which require improved thermal properties can be impact modified with a modifying agent having a core-shell structure comprised of a crosslinked acrylate core and a crosslinked styrenic shell.		

***FOR THE PURPOSES OF INFORMATION ONLY***

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	ML	Mali
AU	Australia	GA	Gabon	MR	Mauritania
BB	Barbados	GB	United Kingdom	MW	Malawi
BE	Belgium	HU	Hungary	NL	Netherlands
BG	Bulgaria	IT	Italy	NO	Norway
BJ	Benin	JP	Japan	RO	Romania
BR	Brazil	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	LI	Liechtenstein	SN	Senegal
CH	Switzerland	LK	Sri Lanka	SU	Soviet Union
CM	Cameroon	LU	Luxembourg	TD	Chad
DE	Germany, Federal Republic of	MC	Monaco	TG	Togo
DK	Denmark	MG	Madagascar	US	United States of America
FI	Finland				

- 1 -

IMPACT MODIFIED POLYPHENYLENE ETHER-  
POLYAMIDE COMPOSITIONS

Field of the Invention

5 Compositions comprising a combination of  
polyphenylene ether resin and polyamide resin can be  
impact modified with a compound comprised of a  
crosslinked butylacrylate core/crosslinked styrenic  
shell which is particularly effective for thermoplastic  
applications requiring thermal stability.

10 Background of the Invention

Polyphenylene ether resins have been modified with  
polyamide resins to provide a wide variety of  
beneficial properties such as excellent heat  
resistance, chemical resistance, impact strength,  
15 hydrolytic stability and dimensional stability compared  
to either unmodified resin alone.

The improved properties of polyphenylene  
ether-polyamide compositions have found great utility  
in thermoplastic applications which take advantage of  
such properties. Exterior automotive applications such  
20 as body panels and wheel covers all benefit from the  
improved thermal properties of polyphenylene  
ether-polyamide compositions (PPE/PA compositions). In  
an automotive application such as a fender part, a  
satisfactory thermoplastic must be processed at  
25 elevated extrusion and molding temperatures. Such  
parts also experience high temperature finishing  
processes such as oven baking for paint and other  
finishes.

30 Many important thermoplastic applications for  
PPE/PA compositions also require that the resin be  
impact modified to provide adequate performance.

- 2 -

Impact modification of plastics by incorporation of rubber-like modifiers offers many advantages and disadvantages. Conventional impact modifiers for PPE/PA compositions are either costly or ineffective compared to the impact modification system of the present invention.

Conventional unsaturated impact modifiers such as SBS rubber (styrene-butadiene-styrene copolymer) have shown deficiencies in PPE/PA compositions requiring thermal stability. A rapid drop in impact strength of PPE/PA compositions after high temperature molding conditions over a prolonged period has been attributed to the use of unsaturated rubber impact modifiers.

It has now been discovered that PPE/PA compositions can be improved by combining the base resin with an impact modifier comprised of crosslinked acrylate core/crosslinked styrenic shell in accordance with the description below. In contrast to conventional PPE/PA compositions, those of the present invention have improved melt stability and heat aging characteristics.

#### SUMMARY OF THE INVENTION

Thermoplastic compositions of the present invention are comprised of:

a. a base resin which is a compatible combination of a polyphenylene ether resin and a polyamide resin; and

b. a property improving amount of an impact modifying agent having a core/shell structure wherein the core is a crosslinked acrylate such as butyl acrylate and the shell, which surrounds and interpenetrates the core, is a crosslinked styrenic shell. The crosslinked styrenic shell will preferably

- 3 -

be crosslinked polystyrene since this material is particularly useful in combination with PPE resins. It is expected that the crosslinked styrenic shell will typically be comprised of greater than 85 weight percent styrene although other monomer components (such as acrylonitrile) may be useful in small amounts.

Preferred polyphenylene ether resins and polyamide resins as well as means for providing compatible combinations thereof are described below.

In general it is desirable that the polyamide component comprise a continuous phase in the overall composition and, therefore, typically at least 35 percent by weight of the total PPE-polyamide-modifier composition will be comprised of the polyamide component. The remainder of the composition will be comprised of the PPE and core-shell modifier, in typical weight ratios described below.

The preferred modifying component is itself comprised of 40 to 90 weight percent of a crosslinked acrylate such as butyl acrylate, which is surrounded and interpenetrated by 60 to 10 weight percent of a crosslinked polystyrene.

#### Description of the Invention

Polyphenylene ethers are a well known class of compounds sometimes referred to as polyphenylene oxides. Examples of suitable polyphenylene ethers and processes for preparation can be found in U.S. Patent Nos. 3,306,874; 3,306,875; 3,257,357; and 3,257,358. Compositions of the present invention will encompass homopolymers, copolymers and graft copolymers obtained by the oxidative coupling of phenolic compounds. The preferred polyphenylene ethers used as base resins in compositions of the present invention will be comprised

- 4 -

of units derived from 2,6-dimethyl phenol. Also contemplated are PPE copolymers comprised of units derived from 2,6-dimethyl phenol and 2,3,6-trimethyl phenol.

5 A particularly useful polyphenylene ether would be poly(2,6-dimethyl-1,4-phenylene ether) having an intrinsic viscosity (I.V.) greater than, approximately 0.10 dl/g as measured in chloroform at 25°C. The I.V. will typically be between 0.40 and 0.50 dl/g. PPE having high glass transition temperatures will  
10 ordinarily improve the stiffness of the resin compositions.

The polyamide resins useful in the practice of the present invention are a generic family of resins known as nylons, characterized by the presence of an amide  
15 group (-CONH-). Nylon-6 and nylon-6,6 are the generally preferred polyamides and are available from a variety of commercial sources. Other polyamides, however, such as nylon-4, nylon-12, nylon-6,10, nylon-6,9 or others such as the amorphous nylons may be  
20 useful for particular polyphenylene ether-polyamide applications.

The polyamides can be provided by a number of well known processes. Nylon-6, for example, is a polymerization product of caprolactam. Nylon-6,6 is a  
25 condensation product of adipic acid and hexamethylenediamine. A nylon-6,6 having an average molecular weight of approximately 10,000 is especially preferred for many useful polyphenylene ether-polyamide thermoplastic applications. Preferred polyamides will  
30 typically have a relative viscosity of at least 35, in accordance with ASTM Test Method D789.

- 5 -

In the preferred embodiments of the present invention, a compatibilizing agent will be employed in the preparation of the composition. When used herein, the expression "compatibilizing agent" refers to those polyfunctional, non-rubbery compounds which interact with either the polyphenylene ether, the polyamide or both. This interaction may be chemical (e.g. grafting) or physical (e.g. effecting the surface characteristics of the dispersed phases). In either instance the resulting polyphenylene ether-polyamide composition appears to exhibit improved compatibility, particularly as evidenced by enhanced impact strength, mold line strength and/or elongation.

Many suitable compatibilizing agents are well known for polyphenylene ether-polyamide compositions. Among these compatibilizing agents may be mentioned: liquid diene polymers, epoxy compounds, quinones, oxidized polyolefin waxes, organosilane compounds, and certain polyfunctional organic acids. Suitable polyphenylene ether-polyamide compositions can be provided in the manner taught by U.S. Patent 4,315,086 which is hereby incorporated by reference. In particular, it has been found that a small amount of a material having in its molecule both an anhydride group and a carbon to carbon double bond (e.g. maleic anhydride) is a suitable compatibilizer of polyphenylene ether-polyamide blends. There are, however, many other effective compatibilizing agents.

Those skilled in the art will be able to provide impact improved compositions comprising various proportions of the polyphenylene ether resin, the polyamide resin and the core-shell impact modifier. In general, however, where chemical resistance is a

- 6 -

desirable property of the thermoplastic resin, it will ordinarily be necessary that the polyamide resin form a continuous phase of the resin composition. Therefore, to avoid a phase inversion whereby the polyamide phase is discontinuous, the preferred compositions of the present invention will be comprised of a polyamide resin in an amount equal to or greater than approximately 35 percent by weight of the total composition (i.e. the PPE, PA, and core-shell components taken together). The remaining components will be comprised of the PPE and core-shell impact modifier, and may together account for up to approximately 65 percent by weight of the total composition.

Regarding the PPE and core-shell fractions, the ratio of PPE to core shell modifier may range from approximately 99:1 to 50:50 and will typically range from approximately 75 to 80 parts PPE and 20 to 25 parts core-shell modifier.

As might be expected, lower amounts of the core-shell modifier would achieve little useful effect, whereas excess amounts could detract from the physical properties of the thermoplastic resin composition.

The above-described weight ratios and percentages represent the compositional formulations of the present invention. The order of combining the components to provide final products may be varied as will be described below.

The preferable core-shell interpolymer modifiers are those having a crosslinked acrylate rubber core, such as butyl acrylate. Surrounding this crosslinked core is a shell-like structure of crosslinked styrenic resin, preferably styrene, which surrounds and



- 7 -

interpenetrates the crosslinked core. Incorporation of small amounts of other monomers such as acrylonitrile and/or methyl methacrylate with styrene in the shell can also provide useful products if the resulting  
5 copolymer shell does not cause significant incompatibility with the polyphenylene ether-polyamide matrix. The integrity of such preferable core-shell structures is maintained by the interpenetrating network of the several crosslinked moieties rather than  
10 by grafting the structures together.

The core-shell interpolymer compositions may be formed by the following type of two-step, sequential polymerization process:

1. emulsion polymerizing an acrylate monomer  
15 charge (herein designated "acrylate", for purposes of the present invention), of at least one  $C_2$ - $C_{10}$  alkyl acrylate,  $C_8$ - $C_{22}$  alkyl(meth)acrylate, or compatible mixtures thereof, in an aqueous polymerization medium in the presence of an effective amount of a suitable  
20 di- or polyethyleneically unsaturated crosslinking agent for such type of monomer, with the  $C_4$ - $C_8$  alkyl acrylates being the preferred acrylate monomers for use in this step;

2. emulsion polymerizing a monomer charge of  
25 styrene in an aqueous polymerization medium, also in the presence of an effective amount of a suitable di- or polyethyleneically unsaturated crosslinking agent for such monomers, said polymerization being carried out in the presence of the product from Step 1 so that  
30 the crosslinked (meth)acrylate and crosslinked styrene components form an interpolymer wherein the respective phases surround and penetrate one another.

- 8 -

Such a two-stage polymerization process is analogous to the three step process for producing an acrylate-styrene-acrylonitrile (ASA) terpolymer, as taught by Yu, et al. in U.S. Patent 3,944,631 (which is hereby incorporated by reference).

This core-shell product, which is used as the interpolymer impact modifier in the PPE-polyamide blends of the present invention generally comprises from about 40% to about 90%, by weight, of at least one of the above-identified crosslinked acrylates, and from about 10% to about 60%, by weight, of the crosslinked styrene component. It contains little graft polymerization between the crosslinked styrenic copolymer components and the crosslinked acrylate polymeric component. In the preferred embodiments, the core will comprise 50 to 80 weight percent crosslinked acrylate, based on the weight of crosslinked core and crosslinked shell taken together. Further details regarding this type of polymer composition can be found in the aforementioned U.S. Pat. No. 3,044,731 to A.J. Yu et al. The core-shell interpolymer provided by the foregoing process can be isolated and dried by conventional means and can be provided in powder or pellet form.

Typical PPE-polyamide polymer compositions of the present invention will be comprised of approximately 1 to 30 parts by weight of the core-shell interpolymer modifier based upon 100 parts of the polyphenylene ether-polyamide base resin. It is particularly preferred that about 10 to 20 parts by weight of the core-shell interpolymer additive will be used per 100 parts of the PPE-polyamide base resin. When less than about 2 parts additive are utilized, insufficient

- 9 -

beneficial effect will be achieved for typical applications. When greater than approximately 20 parts of additives are utilized, little additional benefit is achieved while other advantageous properties may be diminished for certain applications.

The foregoing constituent ingredients can be compounded and molded by conventional means. The order of mixing and degree of shear experienced during extrusion can be varied. It would be expected that the physical properties could vary as such processing conditions are varied. Those skilled in the art will be able to achieve optimum processing conditions which may vary for different thermoplastic applications.

Thus in one instance, each of the ingredients could be blended and extruded at once, thereby providing thermoplastic resin having a particular property profile. Alternatively it may be desirable to pre-blend or precompound some of the ingredients while the remaining ingredients are charged later in a compounding or extrusion process.

In one embodiment, the polyphenylene ether, with or without a compatibilizing agent, could be pre-compounded with the core-shell interpolymer impact modifier. Thereafter, the polyamide resin could be charged to the extruder downstream, at a point sufficient to provide adequate mixing but with minimum risk of degradation due to excess heat.

Additionally, it is expected that conventional additives such as fillers, pigments and flame retarding compounds can be incorporated in the thermoplastic compositions of the present invention, thereby providing a variety of useful products.

- 10 -

Specific embodiments of the present invention are taught in the following examples which are not limiting in any way. All parts are by weight unless otherwise indicated.

5     Synthesis of Core-Shell Additives

Preparation A: crosslinked core/crosslinked styrene shell

      A crosslinked polybutylacrylate core having an interpenetrating, crosslinked polystyrene shell was  
10     prepared in a five liter, three-necked flask equipped with a heating/cooling jacket, a Teflon blade agitator, a thermometer and a nitrogen purge.

      The following solutions were prepared:

15	Solution A:	n-butyl acrylate	751.4 g
		1-3 butyleneglycol diacrylate	1.27 g
	Solution B:	Sodium Metabisulfite	1.75 g
		deionized water	27.4 g
20	Solution C:	Ammonium Persulfate	4.84 g
		deionized water	76.1 g
25	Solution D:	styrene	250.6 g
		divinyl benzene	2.65 g
		(55% active solution from Dow Chemical)	

      Into the reaction flask was charged: 3,460 g deionized water, the following emulsifying agents: 2.1 g Sipex UB sodium lauryl sulfate (from Alcolac, Inc.) and 4.2 g Aerosol A-268, a disodium sulfosuccinate  
30     (from American Cyannamid), and 14.6 g of Solution B. The flask was stirred with N<sub>2</sub> sparge at room temperature for 30 minutes, to reduce th O<sub>2</sub> content.

- 11 -

Thereafter, 150.5 g of N<sub>2</sub> sparged Solution A was added. The flask contents were heated to 55°C and then 13.5 g of Solution C was added to initiate polymerization.

5       After 1.5 hours of reaction, a sample showed 4.1% resin solids indicating approximately 96% conversion. The remainder of solution A as well as 14.6 g Solution B and 40.4 g Solution C were added. After 2.5 hours of additional reaction time at 55°C a sample showed 17.2%  
10       resin solids, indicating greater than 97% conversion.

The reaction mixture was cooled to 35°C and Solution D was added and mixed for 15 minutes at 35°C. The reaction mixture was then heated to 60°C and the remainder of Solution C was added. The mixture was  
15       reacted for 1.25 hours. The temperature was raised to 75°C and maintained for 45 minutes. A final sample showed 22.4% resin solids indicating a conversion greater than 98%.

The product latex was coagulated in a solution of  
20       0.25 weight percent CaCl<sub>2</sub> in methanol at a rate of 1600 ml methanol per 800 ml latex. The coagulum was filtered, rinsed with fresh methanol, and dried in a vacuum oven at 60°C.

The product had a number average latex particle  
25       diameter of 211 nanometers, a swell index in methyl ethyl ketone (MEK) of 8.1 and a percent Gel fraction from MEK extraction of 91.1%.

Preparation B Crosslinked Core/Uncrosslinked Styrene Shell

30       A crosslinked polybutyl acrylate core with an interpenetrating but uncrosslinked styrene shell was provided in the same manner as for Preparation A,

- 12 -

except that the divinyl benzene crosslinker in Solution D was eliminated. A product having a final conversion of approximately 97% was recovered as in Preparation A. The product of preparation B had an average latex  
5 particle diameter of 203 nanometers, a swell index in MEK of 14.4 and a % Gel from MEK extraction of 63.4%.

#### Examples

Experimental thermoplastic blends were mixed by a Henschel mixer, extruded by a 28mm Werner & Pfleiderer  
10 twin screw extruder having a temperature profile (set) of 480, 520, 550, 550, 556°F, and injection molded into ASTM specimens by a 3 ounce Newbury injection molding machine at a melt temperature of 570°F and a mold temperature of 150°F.

15 The formulations had the compositions shown in Table 1, parts are by weight.

-13-

Table 1

	$\frac{A^*}{49}$	$\frac{1}{49}$	$\frac{B^*}{49}$
polyphenylene ether resin (a)	49	49	49
nylon 6/6 (b)	41	41	41
maleic anhydride (f)	1.0	1.0	1.0
rubber modifiers:			
(i) styrene-butadiene-styrene (c)	10	--	--
and styrene-butadiene			
(ii) crosslinked butyl acrylate core (d)	--	10	--
with crosslinked styrene shell			
(iii) crosslinked butyl acrylate core	--	--	10
with uncrosslinked shell (e)			

## \* Comparisons

## Notes:

(a) poly(2,6-dimethyl-1,4-phenylene)ether having an intrinsic viscosity of approximately 0.45 dl/g as measured in chloroform at 25°C

(b) Nylon 6/6: NP-10,000 from Nylon Polymer Co.

(c) 80:20 sty-bd-sty triblock / sty-bd diblock mixture, Kraton KD-1102, Shell Chemical Co.)

(d) Preparation A, above

(e) Preparation B, above (f) Maleic anhydride was incorporated to facilitate compatibility of the polyphenylene ether-polyamide base resin.

Additionally, each blend contained 2 parts TiO<sub>2</sub>, 0.3 parts Irganox 1076 stabilizer and 0.1 part KI.

- 14 -

The effect of the various impact modifiers in polyphenylene ether-polyamide compositions is depicted by the physical properties indicated in Table 2:



Table 2

Properties	BLEND	
	<u>A*</u>	<u>B*</u>
Heat Distortion Temperature	372	377
(°F @ 66 psi)		
Izod Impact	6.0	1.5
(ft-lb/in, notched)		
Dynatup Impact	451	27
(in-lb, max. load)		
Tensile Yield Strength (psi)	7350	7300
Tensile Elongation (%)	81	18
Flow Channel (in)	31	33.5

- 16 -

It will be evident from the foregoing that the physical properties of polyphenylene ether-polyamide compositions are improved as comparable upon the addition of the crosslinked acrylate core/crosslinked styrene shell modifier utilized by the present invention. Table 3 demonstrates the improved thermal aging characteristics of a composition for the present invention compared to a PPE/PA composition containing a conventional non-hydrogenated impact modifier. The table shows the retention of Dynatup Impact Strength for PPE/PA blends having different impact modifiers, after thermal aging at 375°F.

Table 3

	Initial Dynatup Impact	Retention of Dynatup After	
		2 HRS	4 HRS.
Blend A (a)	<u>452 in-lb</u>	<u>73%</u>	<u>23%</u>
Blend 1 (b)	381	106%	96%

20

(a) from Table 1 above, contains unsaturated Kraton D-1102 modifier

(b) from Table 1 above, contains crosslinked acrylate core/crosslinked styrene shell modifier.

- 17 -

1. A thermoplastic resin composition comprising:
  - a. a base resin comprising a compatible combination of a polyphenylene ether resin and a polyamide resin; and
  - b. a property improving amount of a modifying agent comprised of a crosslinked acrylate core and a crosslinked styrenic shell.
2. A composition as in Claim 1 wherein said polyphenylene ether resin is a polymer or copolymer comprised of units selected from the groups consisting of 2,6 dimethyl phenylene units and 2,3,6 trimethyl phenylene units.
3. A composition as in Claim 2 wherein said polyphenylene ether resin is poly (2,6-dimethyl-1,4-phenylene ether).
4. A composition as in Claim 2 wherein said polyphenylene ether resin has an intrinsic viscosity of, approximately 0.30 to 0.60 dl/g as measured in chloroform at 25°C.
5. A composition as in Claim 1 wherein said polyamide resin is selected from the group consisting of polyamide-6, polyamide-6,6, polyamide-12, and polyamide-6,9.
6. A composition as in Claim 1 wherein the polyamide resin comprises at least 35 percent by weight of the total composition.
7. A composition as in Claim 1 wherein the weight ratio of polyphenylene ether resin to said core-shell modifying agent varies from, approximately, 99:1 to 50:50.
8. A composition as in Claim 1 wherein said crosslinked acrylate core is a crosslinked acrylate core.

- 18 -

9. A composition as in Claim 9 wherein said acrylate is butylacrylate.
10. A composition as in Claim 1 wherein said modifying agent is comprised of 40 to 90 weight percent crosslinked acrylate core and 60 to 10 weight percent crosslinked styrenic shell, based upon the weight of core and shell together.
11. A composition as in Claim 1 wherein said crosslinked styrenic shell is at least 85 weight percent polystyrene, based upon the weight of said shell.
12. A composition as in Claim 11 wherein said crosslinked styrenic shell is crosslinked polystyrene.
13. In a method for improving the thermal stability of impact modified polyphenylene ether-polyamide compositions, wherein the thermoplastic base resin is a compatible combination of a polyphenylene ether resin and a polyamide resin, the improvement which comprises combining such thermoplastic base resin with a property improving amount of an impact modifier having a core-shell structure comprised of a crosslinked acrylate core and a crosslinked styrenic shell.
14. A method as in Claim 11 wherein said polyamide resin comprises, at least approximately, 35 parts by weight per 100 parts of the total composition
15. A method as in Claim 11 wherein said impact modifier is comprised of, approximately, 50 to 90 weight percent crosslinked acrylate, and 50 to 10 percent by weight of said crosslinked styrene component.
16. A product made by the method of Claim 11.

# INTERNATIONAL SEARCH REPORT

International Application No PCT/US 86/02725

<b>I. CLASSIFICATION OF SUBJECT MATTER</b> (if several classification symbols apply, indicate all) <sup>6</sup> According to International Patent Classification (IPC) or to both National Classification and IPC IPC <sup>4</sup> : C 08 L 71/04; C 08 L 77/00; C 08 L 51/04																	
<b>II. FIELDS SEARCHED</b> <div style="text-align: center; border-top: 1px solid black; border-bottom: 1px solid black; margin: 5px 0;">Minimum Documentation Searched <sup>7</sup></div> <table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 25%; border-bottom: 1px solid black; padding: 5px;">Classification System</td> <td style="border-bottom: 1px solid black; padding: 5px;">Classification Symbols</td> </tr> <tr> <td style="padding: 5px;">IPC<sup>4</sup></td> <td style="padding: 5px;">C 08 L</td> </tr> </table> <div style="text-align: center; border-top: 1px solid black; border-bottom: 1px solid black; margin: 5px 0;">Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in the Fields Searched <sup>8</sup></div>			Classification System	Classification Symbols	IPC <sup>4</sup>	C 08 L											
Classification System	Classification Symbols																
IPC <sup>4</sup>	C 08 L																
<b>III. DOCUMENTS CONSIDERED TO BE RELEVANT <sup>9</sup></b> <table style="width: 100%; border-collapse: collapse;"> <tr> <th style="width: 10%; border-bottom: 1px solid black; padding: 5px;">Category <sup>9</sup></th> <th style="width: 70%; border-bottom: 1px solid black; padding: 5px;">Citation of Document, <sup>11</sup> with indication, where appropriate, of the relevant passages <sup>12</sup></th> <th style="width: 20%; border-bottom: 1px solid black; padding: 5px;">Relevant to Claim No. <sup>13</sup></th> </tr> <tr> <td style="text-align: center; vertical-align: top; padding: 5px;">X</td> <td style="padding: 5px;">WO, A, 85/05372 (GENERAL ELECTRIC) 5 December 1985, see claims; page 16, lines 17-36</td> <td style="text-align: center; vertical-align: top; padding: 5px;">1-16</td> </tr> <tr> <td colspan="3" style="text-align: center; padding: 5px;">--</td> </tr> <tr> <td style="text-align: center; vertical-align: top; padding: 5px;">E</td> <td style="padding: 5px;">WO, A, 87/00540 (GENERAL ELECTRIC) 29 January 1987, see claims; page 13, lines 23-33</td> <td style="text-align: center; vertical-align: top; padding: 5px;">1-16</td> </tr> <tr> <td colspan="3" style="text-align: center; padding: 5px;">-----</td> </tr> </table>			Category <sup>9</sup>	Citation of Document, <sup>11</sup> with indication, where appropriate, of the relevant passages <sup>12</sup>	Relevant to Claim No. <sup>13</sup>	X	WO, A, 85/05372 (GENERAL ELECTRIC) 5 December 1985, see claims; page 16, lines 17-36	1-16	--			E	WO, A, 87/00540 (GENERAL ELECTRIC) 29 January 1987, see claims; page 13, lines 23-33	1-16	-----		
Category <sup>9</sup>	Citation of Document, <sup>11</sup> with indication, where appropriate, of the relevant passages <sup>12</sup>	Relevant to Claim No. <sup>13</sup>															
X	WO, A, 85/05372 (GENERAL ELECTRIC) 5 December 1985, see claims; page 16, lines 17-36	1-16															
--																	
E	WO, A, 87/00540 (GENERAL ELECTRIC) 29 January 1987, see claims; page 13, lines 23-33	1-16															
-----																	
<div style="display: flex; justify-content: space-between;"> <div style="width: 45%;"> <p><sup>10</sup> Special categories of cited documents:</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> </div> <div style="width: 45%;"> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"A" document member of the same patent family</p> </div> </div>																	
<b>IV. CERTIFICATION</b> <table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; border-bottom: 1px solid black; padding: 5px;">Date of the Actual Completion of the International Search</td> <td style="width: 50%; border-bottom: 1px solid black; padding: 5px;">Date of Mailing of this International Search Report</td> </tr> <tr> <td style="text-align: center; padding: 5px;">25th March 1987</td> <td style="text-align: center; padding: 5px;">29 APR 1987</td> </tr> <tr> <td style="border-bottom: 1px solid black; padding: 5px;">International Searching Authority</td> <td style="border-bottom: 1px solid black; padding: 5px;">Signature of Authorized Officer</td> </tr> <tr> <td style="text-align: center; padding: 5px;">EUROPEAN PATENT OFFICE</td> <td style="padding: 5px;">M. VAN MOL </td> </tr> </table>			Date of the Actual Completion of the International Search	Date of Mailing of this International Search Report	25th March 1987	29 APR 1987	International Searching Authority	Signature of Authorized Officer	EUROPEAN PATENT OFFICE	M. VAN MOL							
Date of the Actual Completion of the International Search	Date of Mailing of this International Search Report																
25th March 1987	29 APR 1987																
International Searching Authority	Signature of Authorized Officer																
EUROPEAN PATENT OFFICE	M. VAN MOL																

ANNEX TO THE INTERNATIONAL SEARCH REPORT ON  
-----

INTERNATIONAL APPLICATION NO.      PCT/US 86/02725 (SA    15530)  
-----

This Annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report. The members are as contained in the European Patent Office EDP file on 03/04/87

The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

---

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A- 8505372	05/12/85	AU-A-      4409985	13/12/85
		EP-A-      0185054	25/06/86
		JP-T-      61502195	02/10/86
-----			
WO-A- 8700540	29/01/87	AU-A-      6199686	10/02/87

---

---

For more details about this annex :  
see Official Journal of the European Patent Office, No. 12/82