



(51) International Patent Classification:

C07F 7/18 (2006.01) C08J 3/28 (2006.01)
C08G 77/04 (2006.01) C08F 2/40 (2006.01)

(21) International Application Number:

PCT/CN2012/085935

(22) International Filing Date:

5 December 2012 (05.12.2012)

(25) Filing Language:

English

(26) Publication Language:

English

(71) Applicant: HENKEL (CHINA) COMPANY LIMITED
[CN/CN]; Zhangheng Road No.928, Pudong New Area,
Shanghai 201203 (CN).

(72) Inventors: LI, Zhimjing Pasing; Room 403, Zaozhuang
Road 1029, No.27, Pudong New Area, Shanghai 201203
(CN). ZHANG, Yong; 69-102, Lane 828, Heze Rd., Pud-
ong District, Shanghai 201203 (CN). LI, Jinyou; 928
Zhangheng Rd, Pudong District, Shanghai 201203 (CN).
LU, Zhixiang; 1 Henkel Way, Rocky Hill, Connecticut
06067 (US). LU, Zheng; 1 Henkel Way, Rocky Hill, Con-
necticut 06067 (US).

(74) Agent: NTD PATENT & TRADEMARK AGENCY
LIMITED; 10th Floor, Block A, Investment Plaza, 27 Jin-
rongdajie, Xicheng District, Beijing 100033 (CN).



(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY,
BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM,
DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT,
HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP,
KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD,
ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI,
NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU,
RW, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ,
TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA,
ZM, ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ,
UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ,
TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK,
EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV,
MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM,
TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW,
ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: Silicone-compatible photoinitiators



(57) Abstract: The present invention provides a compound represented by the following formula (I): CCOSi* O R 2 R 3 R (I), wherein - R and R 2 each independently designates an alkyl group of 1 to 12 carbon atoms or a cycloalkyl group of 5 or 6 carbon atoms or R and R 2 form together with the carbon atom to which they are attached a cycloaliphatic ring of 5 or 6 carbon atoms, - Si* represents an organopolysiloxane residue bonded via a silicon atom of this residue to the oxygen shown in formula (I), or a silane group Si R 4 R 6, wherein R 4, R and R 6 each independently designates an alkyl group of 1 to 12 carbon atoms, a cycloalkyl group of 5 or 6 carbon atoms or an aryl group of 6 to carbon atoms, and - R 3 designates a hydrogen atom or a group represented by the following formula (II) CCOSi** O CH 2 R 8 R 7 (II), wherein - R 7 and R 8 each independently designates an alkyl group of 1 to 12 carbon atoms or a cycloalkyl group of 5 or 6 carbon atoms or R 7 and R 8 form together with the carbon atom to which they are attached a cycloaliphatic ring of 5 or 6 carbon atoms, and - Si** represents an organopolysiloxane residue bonded via a silicon atom of this residue to the oxygen shown in formula (II), or a silane group Si R 9 R 10 R 11, wherein R 9, R 10 and R 11 each independently designates an alkyl group of 1 to 12 carbon P2012941C 20 atoms, a cycloalkyl group of 5 or 6 carbon atoms or an aryl group of 6 to 10 carbon atoms, a method to produce this compound and the use thereof as photoinitiator and/or photosensitizer.

Silicone-compatible photoinitiators

Field of the Invention

The present invention relates to novel silicone-compatible photoinitiators based on an α -hydroxy ketone moiety chemically bonded to an organopolysiloxane (silicone) or a silane, the production thereof by dehydrogenation, as well as their use. The photoinitiators are soluble in silicones and, hence, particularly useful to initiate photocuring of compositions comprising silicones having unsaturated free-radical curable functional groups. Due to their remarkable stability the photoinitiators do not give rise to yellowing and may be used for example in the preparation of optically clear silicone sealants and coatings.

Background Art

The photoinduced polymerization of monomers or oligomers comprising functional groups prone to radical reactions is a widely used technique in the production of polymers. To start the reaction usually photoinitiators are added to the monomers or oligomers and the mixture is then exposed to electromagnetic radiation. Many photoinitiators are available which are readily soluble in unsaturated organic resins, and effectively cure these. However, many of these photoinitiators have poor solubility, and therefore unsatisfactory curing effectiveness, in silicones. Such photoinitiators separate from the silicone matrix during storage causing severe haze in any cured product produced. This is not acceptable if the products are intended to be used for optical clear display applications. In order to increase solubility in and hence compatibility with silicones it has been proposed to chemically bond the photoinitiators to organopolysiloxanes or silanes.

US 4,273,907 discloses a novel class of organopolysiloxane compounds comprising at least one benzoin group chemically bonded to a silicon atom of the organopolysiloxane molecule. Such compounds may be prepared by the dehydrohalogenation, dehydrogenation, dehydration or dealkoholation condensation reaction between a corresponding organopolysiloxane having silicon-bonded halogen atoms, hydrogen atoms, hydroxyl groups or alkoxy groups and a benzoin compound in the presence of a suitable reaction promoter or a condensation catalyst. They are soluble in silicone

compositions and useful as a photosensitizer in photocurable organopolysiloxane compositions. However, the compounds do not show sufficient stability and tend to cause yellowing upon exposure to heat and/or UV radiation over a longer period. Hence, they are not suitable to be used in high-performance transparent coatings, encapsulants or sealants.

US 4,391,963 also discloses novel photosensitizers, being organopolysiloxane compounds bearing at least one chemically bonded benzoin group. Here, however, the compounds are prepared by hydrosilylation of an alkenyl-substituted benzoin and a silicon compound containing at least one silicon-bonded hydrogen atom. Hence, the organopolysiloxane moiety and the benzoin group are bonded via a divalent hydrocarbon group. This results in an increased stability against hydrolysis, however, requires a comparatively elaborate preparation process since alkenyl-substituted benzoin compounds are not readily available, but have to be synthesized in a separate reaction step.

From US 4,536,265 are known further organopolysiloxane photoinitiators. At least one siloxane unit per molecule comprises an acetophenone photomoiety bonded to the silicon atom of the siloxane unit via a divalent hydrocarbon group having between 2 and 10 carbon atoms. Such a binding group shows high stability against hydrolysis. However, again alkenyl-substituted acetophenones are not readily available, but have to be synthesized in a separate reaction step, making the overall process to produce the organopolysiloxane photoinitiators complex. Moreover, acetophenone moieties tend to cause yellowing upon exposure to heat and/or UV radiation over a longer period.

US 5,776,658 describes silicone-compatible photoinitiators comprising a silane or organopolysiloxane residue bearing a chemically bonded radical of a compound which has one or more of a photoinitiator or photosensitizer activity and which has at least one carbonyl group located on an aromatic nucleus. Again, the bonding of the silane or organopolysiloxane residue and the photomoiety is effected via a divalent hydrocarbon group. This divalent hydrocarbon group is attached to an aromatic carbon atom which is positioned ortho to the carbonyl group of the photomoiety. The photoinitiators show good stability against hydrolysis. The examples disclose preparation of the photoinitiators via a one-pot reaction. However, the resulting product mixture needs to be concentrated and

worked up by chromatography. So the overall process is complex and time-consuming. Moreover, the yields of photoinitiator are rather low, e.g. only 17 % in example 5.

EP 1072326 A2 provides siloxane-containing surface-active photoinitiators which concentrate on the surface of the formulation. These photoinitiators are used in a method for producing scratch-resistant coatings from formulations containing ethylenic compounds. The photomoiety comprises an aromatic ring which is linked via a bridging unit Y to a silicon atom of the siloxane residue. Due to the surface-active properties of these photoinitiators they will not be homogeneously distributed throughout the formulation and, hence, are not suitable to be used in high-performance transparent coatings, encapsulants or sealants.


It is evident from the above documents that although many photoinitiators have been developed which may be used in the curing of silicone resins there is still need for improvement.

Summary of the Invention

The object of the invention is to provide novel silicone-compatible photoinitiators, which are accessible from readily available starting materials via a simple one-step reaction. They shall be highly soluble in photocurable silicones and stable against thermal stress, UV radiation and hydrolysis to avoid yellowing of any cured product comprising such photoinitiator. Such photoinitiators are useful for example in the production of optically clear displays.


The inventors found that specific compounds based on α -hydroxy ketone photomoieties bonded to a silicon atom of an organopolysiloxane or silane via a –O-Si bond show the desired properties.

In a first aspect the invention relates to a compound represented by the following formula (I):



wherein

- R^1 and R^2 each independently designates an alkyl group of 1 to 12 carbon atoms or a cycloalkyl group of 5 or 6 carbon atoms or R^1 and R^2 form together with the carbon atom to which they are attached a cycloaliphatic ring of 5 or 6 carbon atoms,
- Si^* represents an organopolysiloxane residue bonded via a silicon atom of this residue to the oxygen shown in formula (I), or a silane group $\text{SiR}^4\text{R}^5\text{R}^6$, wherein R^4 , R^5 and R^6 each independently designates an alkyl group of 1 to 12 carbon atoms, a cycloalkyl group of 5 or 6 carbon atoms or an aryl group of 6 to 10 carbon atoms, and
- R^3 designates a hydrogen atom or a group represented by the following formula (II)




wherein

- R^7 and R^8 each independently designates an alkyl group of 1 to 12 carbon atoms or a cycloalkyl group of 5 or 6 carbon atoms or R^7 and R^8 form together with the carbon atom to which they are attached a cycloaliphatic ring of 5 or 6 carbon atoms, and
- Si^{**} represents an organopolysiloxane residue bonded via a silicon atom of this residue to the oxygen shown in formula (II), or a silane group $\text{SiR}^9\text{R}^{10}\text{R}^{11}$, wherein R^9 , R^{10} and R^{11} each independently designates an alkyl group of 1 to 12 carbon atoms, a cycloalkyl group of 5 or 6 carbon atoms or an aryl group of 6 to 10 carbon atoms.


These compounds are readily soluble in photocurable silicones and stable against thermal stress, UV radiation and hydrolysis and, hence, useful photoinitiators to produce cured products based on silicones which do not show yellowing even after a long time.

The present invention furthermore provides a convenient method to produce these compounds by reacting at least one α -hydroxy ketone of formula (I')



wherein

- R^1 and R^2 each independently designates an alkyl group of 1 to 12 carbon atoms or a cycloalkyl group of 5 or 6 carbon atoms or R^1 and R^2 form together with the carbon atom to which they are attached a cycloaliphatic ring of 5 or 6 carbon atoms, and
- R^3 designates a hydrogen atom or a group represented by the following formula (II')



wherein

- R^7 and R^8 each independently designates an alkyl group of 1 to 12 carbon atoms or a cycloalkyl group of 5 or 6 carbon atoms or R^7 and R^8 form together with the carbon atom to which they are attached a cycloaliphatic ring of 5 or 6 carbon atoms,

and at least one organopolysiloxane having at least one SiH group per molecule or at least one silane $\text{HSiR}^4\text{R}^5\text{R}^6$, wherein R^4 , R^5 and R^6 each independently designates an alkyl group of 1 to 12 carbon atoms, a cycloalkyl group of 5 or 6 carbon atoms or an aryl group of 6 to 10 carbon atoms, in the presence of a dehydrogenation catalyst.

Furthermore, the present invention relates to the use of these compounds as photoinitiator and/or photosensitizer, and in particular a method of using these compounds as photoinitiator and/or photosensitizer, comprising addition of the compound to a photopolymerizable organopolysiloxane or silicone resin and exposure of the resulting mixture to electromagnetic radiation.

Detailed Description

The compounds according to the invention may be used as photoinitiators and/or photosensitizers, being particularly effective if used in compositions based on photocurable silicones.

They show particularly advantageous properties, if both R^1 and R^2 each independently designates methyl, ethyl, n-propyl or isopropyl, or R^1 and R^2 form together with the carbon atom to which they are attached a cyclohexyl ring. Such compounds are therefore preferred. Preferably, R^1 and R^2 each independently designates methyl or ethyl, or R^1 and R^2 form together with the carbon atom to which they are attached a cyclohexyl ring. Particularly preferred, R^1 and R^2 both designate methyl, or R^1 and R^2 form together with the carbon atom to which they are attached a cyclohexyl ring.

In a first preferred embodiment, R^3 designates a hydrogen atom.


In a second preferred embodiment R^3 designates a group represented by formula (II), wherein R^7 and R^8 each independently designates methyl, ethyl, n-propyl or isopropyl, or R^7 and R^8 form together with the carbon atom to which they are attached a cyclohexyl ring. Particularly preferred, R^7 and R^8 both designate methyl, or R^7 and R^8 form together with the carbon atom to which they are attached a cyclohexyl ring. In this particular embodiment it is preferred that R^7 and R^8 are identical to R^1 and R^2 .

Si^* in formula (I) represents an organopolysiloxane residue bonded via a silicon atom of this residue to the oxygen shown in formula (I), or a silane group $SiR^4R^5R^6$, wherein R^4 , R^5 and R^6 each independently designates an alkyl group of 1 to 12 carbon atoms, a cycloalkyl group of 5 or 6 carbon atoms or an aryl group of 6 to 10 carbon atoms.

If Si^* represents a silane group $SiR^4R^5R^6$, it is preferred that R^4 , R^5 and R^6 each independently designates an alkyl group of 1 to 10 carbon atoms, preferably selected from methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, tert.-butyl, n-pentyl, isopentyl,

2,2-dimethylpropyl, n-hexyl, isohexyl, 2,2-dimethylbutyl, n-octyl, n-nonyl, and n-decyl, a cycloalkyl group of 5 or 6 carbon atoms, preferably selected from cyclopentyl and cyclohexyl, or an aryl group of 6 to 10 carbon atoms, preferably selected from phenyl and benzyl. It is particularly preferred that R^4 , R^5 and R^6 each independently designates an alkyl group selected from methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl and tert.-butyl, a cycloalkyl group selected from cyclopentyl and cyclohexyl, or an aryl group selected from phenyl and benzyl. More preferred R^4 , R^5 and R^6 each independently designates an alkyl group selected from methyl, ethyl, n-propyl, and isopropyl, a cyclohexyl group, or a phenyl group. Even more preferred R^4 , R^5 and R^6 each independently designate methyl, ethyl, n-propyl or isopropyl.

If Si^* represents an organopolysiloxane residue this residue is bonded via a silicon atom of this residue to the oxygen shown in formula (I). In other words the organopolysiloxane has at least one siloxane unit $X_aR_bO_{(4-a-b)/2}$, wherein a is an integer of 1 to 3, b is an integer of 0 to 2 and a+b equals 1 to 3; R is a hydrocarbon group of 1 to 10 carbon atoms which may be substituted by one or more halogen atoms; and X is a residue of formula (I'')




wherein R^1 , R^2 and R^3 each has the meaning and preferred meaning outlined above.

It is preferred that R is an alkyl group of 1 to 10 carbon atoms, preferably selected from methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, tert.-butyl, n-pentyl, isopentyl, 2,2-dimethylpropyl, n-hexyl, isohexyl, 2,2-dimethylbutyl, n-octyl, n-nonyl, and n-decyl, an alkenyl group of 2 to 10 carbon atoms, preferably selected from vinyl, allyl, but-1-enyl, but-2-enyl, and but-3-enyl, a cycloalkyl group of 5 or 6 carbon atoms, preferably selected from cyclopentyl and cyclohexyl, or an aryl group of 6 to 10 carbon atoms, preferably selected from phenyl and benzyl. It is particularly preferred that R designates an alkyl group selected from methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl and tert.-butyl, an alkenyl group selected from vinyl, allyl, and but-3-enyl, a cycloalkyl group selected from cyclopentyl and cyclohexyl, or an aryl group selected from phenyl and benzyl. More preferred R designates an alkyl group selected from methyl, ethyl, n-propyl, isopropyl, and tert.-butyl, an alkenyl group selected from vinyl, and allyl, a cyclohexyl group, or a phenyl group. Even more preferred R designate methyl or phenyl.

Si** in formula (II) represents an organopolysiloxane residue bonded via a silicon atom of this residue to the oxygen shown in formula (II), or a silane group $\text{SiR}^9\text{R}^{10}\text{R}^{11}$, wherein R^9 , R^{10} and R^{11} each independently designates an alkyl group of 1 to 12 carbon atoms, a cycloalkyl group of 5 or 6 carbon atoms or an aryl group of 6 to 10 carbon atoms.

If Si** represents a silane group $\text{SiR}^9\text{R}^{10}\text{R}^{11}$, it is preferred that R^9 , R^{10} and R^{11} each independently designates an alkyl group of 1 to 10 carbon atoms, preferably selected from methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, tert.-butyl, n-pentyl, isopentyl, 2,2-dimethylpropyl, n-hexyl, isohexyl, 2,2-dimethylbutyl, n-octyl, n-nonyl, and n-decyl, a cycloalkyl group of 5 or 6 carbon atoms, preferably selected from cyclopentyl and cyclohexyl, or an aryl group of 6 to 10 carbon atoms, preferably selected from phenyl and benzyl. It is particularly preferred that R^9 , R^{10} and R^{11} each independently designates an alkyl group selected from methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl and tert.-butyl, a cycloalkyl group selected from cyclopentyl and cyclohexyl, or an aryl group selected from phenyl and benzyl. More preferred R^9 , R^{10} and R^{11} each independently designates an alkyl group selected from methyl, ethyl, n-propyl, and isopropyl, a cyclohexyl group, or a phenyl group. Even more preferred R^9 , R^{10} and R^{11} each independently designate methyl, ethyl, n-propyl or isopropyl.

If Si** represents an organopolysiloxane residue this residue is bonded via a silicon atom of this residue to the oxygen shown in formula (II). In other words the organopolysiloxane has at least one siloxane unit $\text{X}'_a\text{R}'_b\text{O}_{(4-a-b)/2}$, wherein a' is an integer of 1 to 3, b' is an integer of 0 to 2 and $a'+b'$ equals 1 to 3; R' is a hydrocarbon group of 1 to 10 carbon atoms which may be substituted by one or more halogen atoms; and X' is a residue of formula (II'')



wherein Si^* , R^1 , R^2 , R^7 and R^8 each has the meaning and preferred meaning outlined above.

It is preferred that R' is an alkyl group of 1 to 10 carbon atoms, preferably selected from methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, tert.-butyl, n-pentyl, isopentyl, 2,2-dimethylpropyl, n-hexyl, isohexyl, 2,2-dimethylbutyl, n-octyl, n-nonyl, and n-decyl, an alkenyl group of 2 to 10 carbon atoms, preferably selected from vinyl, allyl, but-1-enyl,


but-2-enyl, and but-3-enyl, a cycloalkyl group of 5 or 6 carbon atoms, preferably selected from cyclopentyl and cyclohexyl, or an aryl group of 6 to 10 carbon atoms, preferably selected from phenyl and benzyl. It is particularly preferred that R' designates an alkyl group selected from methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl and tert.-butyl, an alkenyl group selected from vinyl, allyl, and but-3-enyl, a cycloalkyl group selected from cyclopentyl and cyclohexyl, or an aryl group selected from phenyl and benzyl. More preferred R' designates an alkyl group selected from methyl, ethyl, n-propyl, isopropyl, and tert.-butyl, an alkenyl group selected from vinyl, and allyl, a cyclohexyl group, or a phenyl group. Even more preferred R' designate methyl or phenyl.

If R³ in formula (I) designates a group represented by formula (II), it is preferred that Si** is identical to Si*. Particularly preferred Si** is identical to Si*, and R⁷ and R⁸ are identical to R¹ and R².

Especially preferred according to the invention are the following compounds:

- compound of formula (1), wherein R¹ and R² each designates methyl and R³ designates a hydrogen atom;
- compound of formula (1), wherein R¹ and R² form together with the carbon atom to which they are attached a cyclohexyl ring and R³ designates a hydrogen atom; and
- compound of formula (1), wherein R¹ and R² each designates methyl and R³ designates a group represented by formula (II), wherein R⁷ and R⁸ each designates methyl.

Compounds according to the invention are readily available by reacting at least one α -hydroxy ketone of formula (I')



wherein R¹, R² and R³ have the meaning and preferred meanings as outlined above and at least one organopolysiloxane having at least one SiH group per molecule or at least one silane HSiR⁴R⁵R⁶, wherein R⁴, R⁵ and R⁶ have the meaning and preferred meanings as outlined above, in the presence of a dehydrogenation catalyst.

Preferably, the α -hydroxy ketone of formula (I') and the organopolysiloxane having at least one SiH group per molecule or the silane $\text{HSiR}^4\text{R}^5\text{R}^6$ are reacted in respective amounts to provide a molar ratio of hydroxyl groups of the α -hydroxy ketone of formula (I') to SiH groups of 0.8 to 1.2, preferably 1.0 to 1.2.

Preferably, the reaction is carried out at a temperature of from 20 to 100°C, particularly preferred of from 20 to 60°C, more preferred of from 30 to 60°C.

It is preferred to provide a mixture of the α -hydroxy ketone and the dehydrogenation catalyst and to add the organopolysiloxane or silane dropwise under stirring.

Reaction time is preferably from 0.5 to 24 hours, particularly preferred from 0.5 to 5 hours.

There are no particular restrictions with regard to the dehydrogenation catalyst. All known dehydrogenation catalyst may be used. However, the dehydrogenation catalyst is preferably selected from tris(pentafluorobenzene)borane, zinc dust, and platinum catalysts, tris(pentafluorobenzene)borane being particularly preferred.

The obtained photoinitiators are clear and highly soluble in silicone compositions and, hence, can be blended in high amounts into such compositions.

A further object of the invention is the use of these compounds as photoinitiator and/or photosensitizer, in particular a method of using the compound according to the invention as photoinitiator and/or photosensitizer, comprising addition of the compound to a photopolymerizable organopolysiloxane or silicone resin and exposure of the resulting mixture to electromagnetic radiation. Although there is no particular limitation regarding the photopolymerizable organopolysiloxane or silicone resin, it is preferred to add the compound according to the invention to a composition based solely or predominately on (meth)acryloxysiloxanes, since photo curing such mixtures results in products having a degree of haze of less than 1 %, and showing very good thermal, hydrolytic, and UV stability. Useful electromagnetic radiation is any radiation which will provoke forming of radicals and, hence, start a free-radical polymerization of the photopolymerizable organopolysiloxane or silicone resin. An example thereof is actinic radiation.

A further object of the invention is a curable composition comprising at least a compound according to the invention and at least one photopolymerizable organopolysiloxane or

silicone resin, preferably a (meth)acryloxysiloxane. The amount of the compound according to the invention in such compositions may vary within broad limits. Preferably, the composition comprises the compound according to the invention or a mixture of several compounds according to the invention in a total amount of 0.1 to 30 % by weight, preferably 0.2 to 15 % by weight, based on the weight of the composition. The remainder generally consists solely or predominantly of photopolymerizable organopolysiloxane or silicone resin.

Below is a description of particular aspects of the present invention using a series of examples, however, the present invention is in no way restricted to the below presented examples.

Examples

Synthesis Example 1:

16.42 g (0.1 mol) Darocur 1173 (CAS 7473-98-5; 2-hydroxy-2-methylpropiophenone available from BASF SE) and 0.12 g tris(pentafluorobenzene)borane were added into a 100 ml glass flask and heated to 60°C. 24.37 g (0.11 mol) of bis(trimethylsiloxy)methylsilane was added dropwise under stirring (30 minutes). The resulting mixture was stirred for another 30 minutes and then distilled under reduced pressure to obtain the desired siloxane modified photoinitiator. The obtained siloxane modified photoinitiator was a clear, light yellowish liquid.

The conversion yield of Darocur 1173 was 98.0% of the theoretical value.

Synthesis Example 2:

20.43 g (0.1 mol) Irgacure 184 (CAS 947-19-3; 1-hydroxycyclohexyl phenyl ketone available from BASF SE) and 0.03 g tris(pentafluorobenzene)borane were added into a 100 ml glass flask and heated to 30°C. 13.95 g (0.12 mol) of triethylsilane was added dropwise under stirring (60 minutes). The resulting mixture was stirred for another 10 minutes and then distilled under reduced pressure to obtain the desired siloxane modified photoinitiator. The obtained siloxane modified photoinitiator was a clear, light yellowish liquid.

The conversion yield of Irgacure 184 was 98.0% of the theoretical value.

Synthesis Example 3:

34.04 g (0.1 mol) Irgacure 127 (CAS 474510-57-1; 2-hydroxy-1-(4-(4-(2-hydroxy-2-methylpropionyl)benzyl)phenyl)-2-methylpropan-1-one available from BASF SE) and 0.127 g tris(pentafluorobenzene)borane were added into a 250 ml glass flask and heated to 50°C. 29.67 g (0.2 mol) of pentamethyldisiloxane was added dropwise under stirring (60 minutes). The resulting mixture was stirred for another 60 minutes. Thereafter 6.0 g basic aluminum oxide (Brockmann I, particle size ~150 mesh, available from Sigma-Aldrich) were added and the mixture was stirred for 15 minutes to absorb tris(pentafluorobenzene)borane. Finally, the mixture was filtrated to obtain the desired

siloxane modified photoinitiator. The obtained siloxane modified photoinitiator was a clear, light yellowish liquid.

Application Examples 1 and 2 and Comparative Examples 1 and 2:

To test the performance of photoinitiators according to the invention (Application Examples 1 and 2), and commercial available photoinitiators (Comparative Examples 1 and 2), the photoinitiators outlined in table 1 below had been added to a UV curable organosilicone. The UV curable organosilicone polymer used was a methacrylic endcapped silanol terminated polydimethylsiloxane (polymer), which was prepared as described in Example 3 of US 5,663,269. Each resulting mixture of photoinitiator and polymer was placed in between 2 layers of glass being 750 microns apart, and then subjected to UV irradiation using a Fusion System UV chamber with an H bulb for 30 seconds at 180 mW/cm² to cause curing.

After curing of the samples transmittance, haze and the b* value (yellowness) were measured by a Datacolor 650 apparatus available from Datacolor Corporation, in compliance with ASTM D1003 Standard Test Method. Thereafter the samples were subjected to reliability test conditions and the measurements were repeated.

Reliability test conditions: the cured samples were put in high temperature and high humidity chamber (85°C, 85% relative humidity) for 1000 hours.

The compositions of the mixtures tested, their appearance before curing, as well as the test results after curing and after having subjected the samples to reliability test conditions, i.e. after the aging test, are shown in Table 1.

Table 1:


		Application example 1	Application example 2	Comparative example 1	Comparative example 2
Polymer [parts by weight]		99.2	99.2	99.2	99.2
Photoinitiator [parts by weight]		0.8 Compound of synthesis example 1	0.8 Compound of synthesis example 2	0.8 Darocur 1173	0.8 Irgacure 184
Appearance before curing		Clear liquid	Clear liquid	Clear liquid*	Hazy liquid
Results after curing	Haze, %	0.1	0.1	0.3	--
	b* (yellowness)	0.2	0.2	0.2	
	Transmittance, %	> 99%	> 99%	> 99%	
Results after aging test	Haze, %	0.2	0.2	1.1	--
	b* (yellowness)	0.4	0.4	0.4	
	Transmittance, %	> 98%	> 98%	> 98%	

* After 1 week's storage at ambient conditions, the clear liquid became hazy.

The results show that using photoinitiators according to the invention yields mixtures of lower haze than the comparative ones, indicating that photoinitiators according to the invention have improved compatibility with silicone material without sacrificing other important properties, in particular transmittance and non-yellowing.


Claims:

1. A compound represented by the following formula (I):



wherein

- R¹ and R² each independently designates an alkyl group of 1 to 12 carbon atoms or a cycloalkyl group of 5 or 6 carbon atoms or R¹ and R² form together with the carbon atom to which they are attached a cycloaliphatic ring of 5 or 6 carbon atoms,
- Si* represents an organopolysiloxane residue bonded via a silicon atom of this residue to the oxygen shown in formula (I), or a silane group SiR⁴R⁵R⁶, wherein R⁴, R⁵ and R⁶ each independently designates an alkyl group of 1 to 12 carbon atoms, a cycloalkyl group of 5 or 6 carbon atoms or an aryl group of 6 to 10 carbon atoms, and
- R³ designates a hydrogen atom or a group represented by the following formula (II)




wherein

- R⁷ and R⁸ each independently designates an alkyl group of 1 to 12 carbon atoms or a cycloalkyl group of 5 or 6 carbon atoms or R⁷ and R⁸ form together with the carbon atom to which they are attached a cycloaliphatic ring of 5 or 6 carbon atoms, and
- Si** represents an organopolysiloxane residue bonded via a silicon atom of this residue to the oxygen shown in formula (II), or a silane group SiR⁹R¹⁰R¹¹, wherein R⁹, R¹⁰ and R¹¹ each independently designates an alkyl group of 1 to 12 carbon

atoms, a cycloalkyl group of 5 or 6 carbon atoms or an aryl group of 6 to 10 carbon atoms.


2. The compound according to claim 1, wherein R^1 and R^2 each independently designates methyl, ethyl, n-propyl or isopropyl.
3. The compound according to claim 1, wherein R1 and R2 form together with the carbon atom to which they are attached a cyclohexyl ring.
4. The compound according to any of claims 1 to 3, wherein R3 designates a hydrogen atom.
5. The compound according to any of claims 1 to 3, wherein R3 designates a group represented by formula (II), wherein R7 and R8 are identical to R1 and R2.
6. The compound according to claim 1, wherein Si* represents a silane group SiR4R5R6, wherein R4, R5 and R6 each independently designates methyl, ethyl, n-propyl or isopropyl.
7. The compound according to claim 1, wherein R3 designates a group represented by formula (II), wherein Si** is identical to Si*.
8. The compound according to claim 1, wherein R1 and R2 each designates methyl and R3 designates a hydrogen atom.
9. The compound according to claim 1, wherein R1 and R2 form together with the carbon atom to which they are attached a cyclohexyl ring and R3 designates a hydrogen atom.
10. The compound according to claim 1, wherein R1 and R2 each designates methyl and R3 designates a group represented by formula (II), wherein R7 and R8 each designate methyl.

11. A method to produce a compound according to any of claims 1 to 10, reacting at least one α -hydroxy ketone of formula (I')



wherein

- R^1 and R^2 each independently designates an alkyl group of 1 to 12 carbon atoms or a cycloalkyl group of 5 or 6 carbon atoms or R^1 and R^2 form together with the carbon atom to which they are attached a cycloaliphatic ring of 5 or 6 carbon atoms, and
- R^3 designates a hydrogen atom or a group represented by the following formula (II')



wherein

- R^7 and R^8 each independently designates an alkyl group of 1 to 12 carbon atoms or a cycloalkyl group of 5 or 6 carbon atoms or R^7 and R^8 form together with the carbon atom to which they are attached a cycloaliphatic ring of 5 or 6 carbon atoms,

and at least one organopolysiloxane having at least one SiH group per molecule or at least one silane $\text{HSiR}^4\text{R}^5\text{R}^6$, wherein R^4 , R^5 and R^6 each independently designates an alkyl group of 1 to 12 carbon atoms, a cycloalkyl group of 5 or 6 carbon atoms or an aryl group of 6 to 10 carbon atoms, in the presence of a dehydrogenation catalyst.

12. The method according to claim 11, wherein the α -hydroxy ketone of formula (I') and the organopolysiloxane having at least one SiH group per molecule or the silane $\text{HSiR}^4\text{R}^5\text{R}^6$ are reacted in respective amounts to provide a molar ratio of hydroxyl groups of the α -hydroxy ketone of formula (I') to SiH groups of 0.8 to 1.2.

13. A method according to any of claims 11 and 12, wherein the dehydrogenation catalyst is selected from tris(pentafluorobenzene)borane, zinc dust, and platinum catalysts.
14. A method according to any of claims 11 and 12, wherein the reaction is carried out at a temperature of from 20 to 100°C.
15. A method of using the compound according to any one of claims 1 to 10 as photoinitiator and/or photosensitizer, comprising addition of the compound to a photopolymerizable organopolysiloxane or silicone resin and exposure of the resulting mixture to electromagnetic radiation.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/CN2012/085935

A. CLASSIFICATION OF SUBJECT MATTER

See the extra sheet

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC: C07F 7, C08G 77, C08J 3, C08F 2

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

WPI, EPDOC, CNKI, CNPAT, CAPLUS, REGISTRY (STN)

photoinitiator, photosensitizer, hydroxy, ketone, siloxane, silicone, silane, soluble, stable, haze, yellow, dehydrogenation, structure search according to formula (I) of claim 1

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 2004009651 A1 (BASF SE ET AL.) 29 January 2004 (29.01.2004) see example 7, the last paragraph of page 27 to the first paragraph of page 28 in the description	1-10
A	the same as above	11-15
X	JAMES M. BLACKWELL ET AL., B(C ₆ F ₅) ₃ -catalyzed silylation of alcohols: a mild, general method for synthesis of silyl ethers, J. Org. Chem., 1999, Vol. 64, No. 13, pages 4887-4892, see entry 10 in table 2 of page 4889	1-2, 4, 6, 8, 11-14
X	MITSURU SHINDO ET AL., Geteroatom-guided torquoselective olefination of α -oxy and α -amino ketones via ynolates, Chemistry - A European Journal, 2006, Vol. 12, No. 2, pages 524-536, see compound 8f in table 2 of page 526	1-2, 4, 6, 8

☒ Further documents are listed in the continuation of Box C.☒ See patent family annex.

* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A" document defining the general state of the art which is not considered to be of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"E" earlier application or patent but published on or after the international filing date	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"L" document which may throw doubts on priority claim (S) or which is cited to establish the publication date of another citation or other special reason (as specified)	"&" document member of the same patent family
"O" document referring to an oral disclosure, use, exhibition or other means	
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search 26 August 2013 (26.08.2013)	Date of mailing of the international search report 19 Sep. 2013 (19.09.2013)
--	--

Name and mailing address of the ISA/CN
The State Intellectual Property Office, the P.R.China
6 Xitucheng Rd., Jimen Bridge, Haidian District, Beijing, China
100088
Facsimile No. 86-10-62019451

Authorized officer

MA, Jin

Telephone No. (86-10)62084381

INTERNATIONAL SEARCH REPORT

International application No.

PCT/CN2012/085935

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	GEORGE A. OLAH ET AL., Trifluoromethanesulfonic (Triflic) acid catalyzed transformations of α -hydroxy carbonyl compounds, J. Org. Chem., 1991, Vol. 56, No. 7, pages 2531-2534, see line 2 of page 2534	1, 3-4, 6, 9
X	HUENIG SIEGFRIED ET AL., Trimethylsilyl cyanide - a reagent for umpolung. XVI. Effect of umpolung moieties on the diastereoselectivity of the nucleophilic acylation of α -chiral carbonyl compounds, Chemische Berichte, 1989, Vol. 122, No. 7, pages 1329-1339, see compound 5cd in page 1338	1-2, 4, 6, 8
X	XAVIER CREARY ET AL., Diels-Alder approach to bicyclic α -hydroxy ketones. facile keto1 rearrangements of strained α -hydroxy ketones, J. Org. Chem., 1985, Vol. 50, No. 11, pages 1932-1938, see the last but two line in page 1938	1, 3-4, 6, 9
X	US 4560709 A (CIBA GEIGY AG) 24 December 1985 (24.12.1985) see co-catalyst 3 in example 1	1-10
A	US 4273907 A (SHINETSU CHEM IND CO LTD) 16 June 1981 (16.06.1981) see the whole document	1-15

INTERNATIONAL SEARCH REPORT
Information on patent family members

International application No.
PCT/CN2012/085935

Patent Documents referred in the Report	Publication Date	Patent Family	Publication Date
WO 2004009651 A1	29.01.2004	AU 2003246675 A1	09.02.2004
		BR 0311729 A	01.03.2005
		EP 1523506 A1	20.04.2005
		KR 20050029228 A	24.03.2005
		TW 200403260 A	01.03.2004
		MXPA 04012672 A	01.04.2005
		US 2005239971 A1	27.10.2005
		JP 2005533156 A	04.11.2005
		CN 1668648 A	14.09.2005
		NZ 537094 A	29.09.2006
		MX 247046 B	06.07.2007
		CN 100523007 C	05.08.2009
		TW I308154 B	01.04.2009
		JP 4461013 B2	12.05.2010
		US 7723397 B2	25.05.2010
		EP 1523506 B1	12.09.2012
		CA 2486784 A	29.01.2004
		ES 2394202 T	23.01.2013
US 4560709 A	24.12.1985	GB 2070615 A	09.09.1981
		FR 2477167 A	04.09.1981
		JPS 56135520 A	23.10.1981
		DE 3107087 A	24.12.1981
		GB 2070615 B	13.07.1983
		CA 1157995 A	29.11.1983
US 4273907 A	16.06.1981	None	

INTERNATIONAL SEARCH REPORT

International application No.

PCT/CN2012/085935

CLASSIFICATION OF SUBJECT MATTER

C07F 7/18 (2006.01) i

C08G 77/04 (2006.01) i

C08J 3/28 (2006.01) i

C08F 2/40 (2006.01) i