

(12) STANDARD PATENT
(19) AUSTRALIAN PATENT OFFICE

(11) Application No. **AU 2009220068 B2**

(54) Title
Flexible packaging structure with built-in tamper-evidence features and method for making same

(51) International Patent Classification(s)
B65D 75/58 (2006.01) **B29C 59/00** (2006.01)

(21) Application No: **2009220068** (22) Date of Filing: **2009.02.16**

(87) WIPO No: **WO09/111153**

(30) Priority Data

(31) Number (32) Date (33) Country
12/043,442 **2008.03.06** **US**

(43) Publication Date: **2009.09.11**
(44) Accepted Journal Date: **2012.02.09**

(71) Applicant(s)
Sonoco Development, Inc.

(72) Inventor(s)
Davis, Benjamin;Huffer, Scott William

(74) Agent / Attorney
Pizzeys, Level 2, Woden Plaza Offices Woden Town Square Woden, Canberra, ACT, 2606

(56) Related Art
US 2005/0276525

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
11 September 2009 (11.09.2009)

(10) International Publication Number
WO 2009/111153 A1

(51) International Patent Classification:
B65D 75/58 (2006.01) *B29C 59/00* (2006.01)

(21) International Application Number:
PCT/US2009/034185

(22) International Filing Date:
16 February 2009 (16.02.2009)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
12/043,442 6 March 2008 (06.03.2008) US

(71) Applicant (for all designated States except US): **SONOCO DEVELOPMENT, INC.** [US/US]; 1 North Second Street, Hartsville, SC 29550 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **DAVIS, Benjamin** [US/US]; 708 Ridge Trail Drive, Columbia, SC 29229 (US). **HUFFER, Scott, William** [US/US]; 1216 Oakhaven Circle, Hartsville, SC 29550 (US).

(74) Agents: **HILL, Donald, M., Jr.** et al.; Alston & Bird LLP, Bank Of America Plaza, 101 South Tryon Street, Suite 4000, Charlotte, NC 28280-4000 (US).


(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: FLEXIBLE PACKAGING STRUCTURE WITH BUILT-IN TAMPER-EVIDENCE FEATURES AND METHOD FOR MAKING SAME



(57) Abstract: A flexible packaging laminate has built-in opening/reclose and tamper-evidence features by forming the laminate from an outer structure (10) joined in face-to-face relation to an inner structure (42). Score lines (52,62) are formed in both structures to enable an opening to be formed through the laminate by lifting a flap or the like out of the plane of the laminate. The score line through the outer structure defines a larger opening than the score line through the inner structure, such that a marginal region of the outer structure extends beyond the edge of the opening portion of the inner structure. A pressure-sensitive adhesive (20) is used to re-adhere the marginal region to an underlying surface of the inner structure adjacent the opening through the laminate. The outer score line (52) includes at least one tear portion that is torn through upon initial opening, thus indicating the package has been at least partially opened.

FLEXIBLE PACKAGING STRUCTURE WITH BUILT-IN TAMPER-EVIDENCE FEATURES AND METHOD FOR MAKING SAME

BACKGROUND OF THE INVENTION

This disclosure relates to product packaging formed in whole or in part by a flexible film, in which the film has a score line that defines a flap that can be lifted to create an opening through the film to gain access to the product, and wherein the flap can
5 be reattached to the remainder of the film to close the opening.

A variety of food and non-food products are packaged using flexible packaging materials formed primarily of laminations of one or more of polymer films, metallized polymer films, paper, metal foil, and the like. In many instances, packages contain products that may be used or consumed a little at a time, and the products may be
10 susceptible to being adversely affected (e.g., becoming soggy, drying out, etc.) by exposure to the surrounding environment. Accordingly, there is frequently a desire to be able to reclose a package after its initial opening to keep product that remains in the package fresh.

Various opening and reclose arrangements have been developed for flexible
15 packaging, for example as disclosed in U.S. Patent Application Serial No. 11/098,872 ("the '872 Application"), filed on April 5, 2005, incorporated herein by reference. Often, reclosability is achieved by using a pressure-sensitive adhesive label that is attached to the exterior of the package adjacent the location where the package is opened. Such labels are formed separately from the packaging structure itself and are added to the packaging
20 structure. Thus, the labels thus represent additional expense. Furthermore, it is often necessary to ship a roll of the packaging material to a converter for application of the labels, after which the roll is shipped back to the packager for manufacture of the packages. This manufacturing process is inefficient. The use of labels also entails waste in that it is typically necessary to employ a release liner with the labels, which liner is

removed and discarded. The labels are usually die cut from a web of material, and the skeleton left over after the die-cutting operation is also wasted.

Because of the drawbacks of using labels as noted above, the assignee of the present application has developed a flexible packaging structure with a built-in opening and reclose feature, as described in the aforementioned '872 application. Packages made
5 using the flexible packaging structure of the '872 application avoid the disadvantages associated with the use of labels, and have additional advantages.

Consumers feel more confident about purchasing such types of packages if the packages have a tamper-evidence capability so that the consumer can readily see whether
10 the package has already been opened. Presently, various flexible packages have features allowing a user to determine if a package has already been opened or tampered with. Unfortunately, the tamper-evidence features of such packages may be difficult to discern upon a visual inspection of the package. Further, such temper-evidence features often require removing a portion of the packaging, and thus, creating unwanted trash and
15 potential choking hazards. The present disclosure is directed toward providing improved tamper-evidence capabilities.

BRIEF SUMMARY OF THE DISCLOSURE

The present disclosure addresses the above needs and achieves other advantages, by providing a flexible packaging structure and method for making same, in which the
20 structure has opening/reclose and tamper-evidence features built into the structure. In accordance with one embodiment of the invention, the score line or die cut through the film for creating the flap includes one or more tear portions in which the flap includes a tab with an end attached to the structure, and/or an interrupted area of the flap that is not cut. When the flap is peeled back, a portion of the tab or the film in the interrupted area is
25 torn. The tab can include an indentation and/or a prong, while the interrupted area can be formed by a transverse cut that is U-shaped or V-shaped to ensure that the tear will connect with the die cut. The presence of a tear or slit in the tab or the interrupted area indicates that the package has already been opened or tampered with.

In some embodiments, the package itself is formed to have a built-in opening and
30 reclose feature by forming the packaging structure as a two-part structure, having an outer structure joined in face-to-face relation with an inner structure. Each of the outer and

inner structures can comprise one or more layers of flexible packaging material such as polymer film, paper, metal foil, and the like. An outer line of weakness is formed in the outer structure to define an outer opening portion that can be lifted out of the plane of the outer structure. Similarly, an inner line of weakness is formed in the inner structure to
5 define an inner opening portion that can be lifted out of the plane of the inner structure. The outer and inner opening portions are attached to each other such that the outer and inner opening portions can be lifted out of the plane as a unit, thereby creating an opening through the packaging structure defined by the inner line of weakness. The outer line of weakness includes a tear portion whose torn or untorn condition is readily apparent from a
10 visual inspection of the outer structure.

The outer opening portion is larger in area than the inner opening portion and has a marginal region that extends beyond the peripheral edge of the inner opening portion. When the outer and inner opening portions are lifted out of the plane to create the opening, an underlying portion of the inner structure in registration with the marginal region of the
15 outer opening portion is exposed adjacent the opening. A pressure-sensitive adhesive is applied to either the marginal region of the outer opening portion or the underlying portion of the inner structure. Therefore, after initial lifting of the outer and inner opening portions, the opening through the structure can be reclosed by adhering the marginal region of the outer opening portion to the underlying portion of the inner structure via the
20 pressure-sensitive adhesive.

In accordance with one embodiment, the pressure-sensitive adhesive is pattern-applied onto one surface of the outer structure, the pressure-sensitive adhesive forming a strip having an outer perimeter and an inner perimeter, and a permanent laminating adhesive is pattern-applied onto the one surface of the outer structure such that the
25 permanent adhesive does not cover the strip of pressure-sensitive adhesive. Next, the outer structure is adhesively joined to the inner structure via the permanent adhesive so as to form a laminate. The outer structure and inner structure in preferred embodiments are coextensive with each other, and advantageously are each continuous webs drawn from respective supply rolls and laminated together to form a laminate that is a continuous web.

30 The laminate is then advanced to a scoring station at which an outer line of weakness (also referred to herein as a "score line") is formed through the thickness of the outer structure, and an inner score line is formed through the thickness of the inner

structure. Advantageously, each of the score lines is registered with respect to the strip of pressure-sensitive adhesive such that neither score line is located where there is permanent laminating adhesive between the outer and inner structures. The outer score line delineates the outer opening portion of the outer structure that is separable from the outer structure along the outer score line, and the inner score line delineates the inner opening portion of the inner structure that is affixed to the outer opening portion by the permanent adhesive and is separable from the inner structure along the inner score line. The outer score line includes the interrupted area.

The score lines can be formed by laser scoring or by mechanical scoring or cutting such as by die cutting or kiss cutting or the like. The adhesive(s) can be applied to the outer structure as noted, but alternatively can be applied to the inner structure. The adhesive(s) can be applied using any suitable equipment and technique, such as by a gravure roll or the like.

The pressure-sensitive adhesive can be applied such that there is a region that is free of the adhesive, such as a tab, to form a grasping portion of the opening portion that can be readily grasped and pulled back to initiate opening.

The outer line of weakness or score line preferably penetrates through the thickness of the outer structure but not through the inner structure. Similarly, the inner score line preferably penetrates through the thickness of the inner structure but not through the outer structure.

The inner structure of the laminate advantageously includes a sealant layer forming the inner surface of the laminate. The sealant layer can comprise a heat seal material such as polyethylene, polypropylene, ionomer resin such as SURLYN®, or the like, or a cold seal material. The heat seal or cold seal layer can comprise either a film or a coating. The inner structure advantageously also includes a barrier layer providing a barrier against the passage of moisture and/or oxygen. In some applications such as the packaging of moisture-sensitive products (e.g., cookies or similar products that tend to be degraded when exposed to the environment), it is important to provide a moisture barrier. The barrier layer can comprise any of various polymer-based barrier materials including barrier polymer films such as ethylene vinyl alcohol copolymer (EVOH), polyamide, and the like; metallized polyolefin films such as polyethylene, polypropylene, oriented polypropylene,

and the like; AlOx-coated polymer films; SiOx-coated polymer films; metal foil such as aluminum foil; and others. Although the term “barrier layer” is used in connection with metallized films to refer to the entire metallized film, it will be recognized that it is the layer of metal that provides the barrier function. Likewise, it is the AlOx or SiOx coating that provides the barrier function in the ceramic-coated films, but the entire film nevertheless is referred to herein as a “barrier layer”.

The outer structure advantageously includes a layer of polyester such as polyethylene terephthalate, which has a desirable crisp feel and is readily printed. The polyester layer can be printed with inks to provide graphics and indicia. In preferred embodiments, the polyester layer is transparent and is reverse-printed on the surface that faces the inner structure.

The process in accordance with the present disclosure comprises an in-line process wherein the opening and reclose features and the tamper-evidence feature are formed in the packaging laminate during the production of the laminate. Accordingly, it is not necessary to ship the laminate to a converter for application of labels or the like. Thus, the waste and the various material and shipping expenses associated with the use of separate labels are avoided.

BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWINGS

Having thus described the disclosure in general terms, reference will now be made to the accompanying drawings, which are not necessarily drawn to scale, and wherein:

FIG. 1 is a diagrammatic depiction of a first phase of a manufacturing method for making a flexible packaging structure in accordance with one embodiment of the invention;

FIG. 1a is a view of the first structure along line 1a-1a in FIG. 1;

FIG. 1b is a view of the first structure along line 1b-1b in FIG. 1;

FIG. 2 is a diagrammatic depiction of a second phase of the method in accordance with one embodiment of the invention;

FIG. 3 is a diagrammatic depiction of a second phase of the method in accordance with another embodiment of the invention;

FIG. 4 is a perspective view of a package that can be formed from a flexible packaging structure made in accordance with embodiments of the invention;

5 FIG. 5 shows the package of FIG. 4 after being opened;

FIG. 6 is a cross-sectional view along line 6-6 in FIG. 4;

FIG. 7 is a cross-sectional view along line 7-7 in FIG. 5;

FIG. 8 is a perspective view of stand-up pouch that can be formed from a flexible packaging structure with a tamper-evidence feature made in accordance with embodiments
10 of the invention;

FIG. 9 is a perspective view of another stand-up pouch that can be formed from a flexible packaging structure with a tamper-evidence feature made in accordance with embodiments of the invention;

FIG. 10 is a perspective view of yet another stand-up pouch that can be formed
15 from a flexible packaging structure with a tamper-evidence feature made in accordance with embodiments of the invention;

FIG. 11 is a perspective view of an additional stand-up pouch that can be formed from a flexible packaging structure with a tamper-evidence feature made in accordance with embodiments of the invention; and

20 FIG. 12 shows a perspective view of a package with a container body and having a tamper-evidence feature in accordance with the invention.

DETAILED DESCRIPTION OF THE DRAWINGS

The present inventions now will be described more fully hereinafter with reference to the accompanying drawings, in which some but not all embodiments of the invention
25 are shown. Indeed, these inventions may be embodied in many different forms and should not be construed as limited to the embodiments set forth herein; rather, these embodiments

are provided so that this disclosure will satisfy applicable legal requirements. Like numbers refer to like elements throughout.

As an initial overview of preferred embodiments of the invention, a flexible packaging laminate is constructed to have a built-in opening and reclose function and a tamper-evidence feature. The laminate is constructed as a multi-layer structure by adhesively laminating a first structure to a second structure, wherein each of the first and second structures comprise one or more layers of flexible material. Pressure-sensitive adhesive is applied to one of the structures before lamination. Once the laminate is formed in this manner, scoring operations are performed on both sides of the laminate, but each scoring operation penetrates only through a part of the thickness of the laminate; in particular, a scoring operation performed on the side of the laminate adjacent the first structure results in penetration through the first structure, but without complete penetration through the second structure, and preferably without any substantial penetration, and more preferably without any penetration, into the second structure. Likewise, the scoring operation performed on the side of the laminate adjacent the second structure results in penetration through the second structure, but without complete penetration through the first structure, and preferably without any substantial penetration, and more preferably without any penetration, into the first structure. The scoring operation also forms the tamper-evidence feature, as further described below.

More particularly, with reference to FIG. 1, a first phase of the manufacturing process is depicted. A first structure **10** is advanced from a supply roll **12** by suitable web driving and handling equipment (not shown) to an optional print station **14** comprising a printing apparatus, such as a rotogravure printer or the like, for printing graphics and/or indicia on the first structure by applying inks to a surface of the first structure. The first structure **10** comprises one or more layers of flexible packaging material. Various materials can be used for the layer(s) of the first structure, including polymers such as polyesters, polyolefins (including homopolymers and copolymers), polyamides, and others; paper; metal foil; and the like. In a preferred embodiment of the invention, the first structure **10** includes an outer layer (not illustrated) that is substantially transparent and is reverse-printed in the print station **14**, i.e., the inks are applied to the surface of the first structure **10** that is subsequently laminated to another structure, as described below, from the opposite side of the first structure, which will form an exterior of a package

constructed from the packaging laminate, the inks are visible through the first structure. As an example, the first structure **10** can comprise a layer of polyester such as polyethylene terephthalate or the like.

Prior to printing the first structure in the print station, the surface of the first structure that is subsequently laminated to the other structure can be treated by a corona discharge or flame treatment apparatus **16** to render the surface more receptive to the inks and/or to render the surface more readily bondable to the pressure-sensitive adhesive that is subsequently applied to the surface as described below. Alternatively, the first structure **10** can have already been so treated prior to being wound into the supply roll **12**, such that the treatment apparatus **16** is unnecessary.

Following the optional corona/flame treatment and/or optional printing operation, and with reference to FIGS. 1 and 1a, the first structure **10** is advanced to a first adhesive application station **18** at which a pressure-sensitive adhesive **20** is applied to the first structure in a predetermined pattern **22** that recurs at regular intervals along the lengthwise direction of the first structure. The predetermined pattern **22** is generally in the form of a strip of various forms or shapes. As illustrated, a preferred shape for the strip pattern **22** is generally U-shaped, for reasons that will become apparent in the description of FIGS. 4-8; however, other shapes for the pattern **22** can be used, the invention not being limited to any particular pattern. The pattern can include a region **23** that is free of adhesive and will ultimately form a thumb tab or grasping portion of the first structure **10** as further described below. It is also possible in alternative embodiments to flood-coat the pressure-sensitive adhesive onto the entire surface of the first structure.

The pressure-sensitive adhesive **20** can comprise various compositions. Pressure-sensitive adhesives form viscoelastic bonds that are aggressively and permanently tacky, adhere without the need of more than a finger or hand pressure, and require no activation by water, solvent or heat. Pressure-sensitive adhesives are often based on non-crosslinked rubber adhesives in a latex emulsion or solvent-borne form, or can comprise acrylic and methacrylate adhesives, styrene copolymers (SIS / SBS), and silicones. Acrylic adhesives are known for excellent environmental resistance and fast-setting time when compared with other resin systems. Acrylic pressure-sensitive adhesives often use an acrylate system. Natural rubber, synthetic rubber or elastomer sealants and adhesives can be based on a variety of systems such as silicone, polyurethane, chloroprene, butyl, polybutadiene,

isoprene, or neoprene. When the packaging laminate of the invention is to be used for food packaging, the pressure-sensitive adhesive **20** generally must be a food-grade composition. Various pressure-sensitive adhesives are approved by the U.S. Food and Drug Administration for use in direct food contact, as regulated by 21 CFR Part 175.300.

5 A preferred food-grade pressure-sensitive adhesive **20** for use in the present invention is Jonbond 743 available from Bostik Findley. Additives (e.g., particulates or the like) can be added to the pressure-sensitive adhesive **20** to reduce the tenacity of the bond to the underlying second structure **42**, if necessary, so that the pressure-sensitive adhesive **20** readily detaches from the second structure on opening (particularly on the very first
10 opening).

When applied in a pattern as opposed to being flood-coated or applied everywhere on the first structure **10**, the pattern **22** of pressure-sensitive adhesive **20** is applied to the first structure **10** at regular intervals along the first structure **10**. The spacing or index distance *d* between the patterns **22** can correspond to a dimension, such as a length, of
15 packages to be produced from the packaging laminate.

The adhesive application station **18** can comprise any suitable device capable of accurately applying the pressure-sensitive adhesive **20** to the first structure **10** in the desired pattern **22**, at regular intervals along the structure. For example, as shown, the adhesive application station can comprise a gravure roll **24** that picks up the pressure-
20 sensitive adhesive **20** from a reservoir **26** on the outer surface of the roll such that the adhesive fills one or more recessed areas in the surface. A doctor blade **28** scrapes off excess adhesive so that it remains essentially only in the recessed area(s). The first structure **10** is contacted by the gravure roll **24**; a backing roll **30** provides support on the opposite side of the first structure **10**.

25 After application of the pressure-sensitive adhesive **20**, the first structure **10** is advanced to a dryer **31** such as an oven or the like, to dry the pressure-sensitive adhesive **20**. In the case of the pressure-sensitive adhesive **20** being pattern-applied, the first structure **10** is then advanced to a second adhesive application station **32** at which a permanent laminating adhesive **34** (FIG. 1b) is applied to the first structure **10** in such a
30 manner that a sufficiently large proportion of the surface is covered by the permanent adhesive **34** to permit the first structure **10** to be adhesively attached to a second structure **42** at a downstream laminating station **40**. The permanent adhesive **34** does not cover the

pressure-sensitive adhesive **20**. Furthermore, when the pattern of pressure-sensitive adhesive **20** includes an adhesive-free region to form a thumb tab or grasping portion **23** as previously noted, the pattern of the permanent adhesive also does not cover the adhesive-free region. Thus, the permanent adhesive **34** must be applied by an apparatus capable of accurately applying the adhesive in a predetermined pattern, in registration with the pressure-sensitive adhesive **20** but not covering it or the adhesive-free region if present. A suitable adhesive application device **32**, as shown, can be a gravure roll **24** of the type previously described. The permanent adhesive **34** can comprise various compositions. Suitable examples include two-component polyurethane adhesive systems, such as Tycel 7900/7283 available from Henkel. After the application of the permanent adhesive **34**, the first structure **10** is advanced to a dryer **33** such as an oven or the like. Alternatively, when the pressure-sensitive adhesive **20** is applied to the entire surface of the first structure **10**, the steps of applying and drying the permanent adhesive **34** are skipped.

The first structure **10** is then advanced to a laminating station **40**, comprising a pair of rolls forming a nip therebetween. The first structure **10** is passed through the nip along with a second structure **42** that is advanced from its own supply roll **44**, and the first and second structures **10/42** are laminated to each other. The second structure **42** comprises one or more layers of flexible material, and is coextensive with the first structure **10**—i.e., the width of the second structure **42** is substantially equal to the width of the first structure **10** and the longitudinal edges of the second structure **42** substantially coincide with the longitudinal edges of the first structure **10**. The resulting laminate **46** is then advanced to a reel-up (not shown) where it is wound into a roll for subsequent processing in the second phase of the manufacturing process as described below. Alternatively, it is possible for the reel-up operation to be omitted, such that the laminate is directly advanced to the second phase.

With reference to FIGS. 2 and 6, the second phase of the process is now described. A supply roll **48** of the laminate **46** formed in the first phase of the process is shown. The laminate is advanced from the supply roll to a first scoring station **50** at which a first, or outer, score line **52** (FIG. 6) is formed through the thickness of the first structure **10**. When the pressure-sensitive adhesive **20** has been pattern-applied, the first score line **52** is in registration with (i.e., coincides with) the outer perimeter **22a** (FIG. 1a) of the strip-shaped pattern **22** of pressure-sensitive adhesive **20**. The first score line **52** extends

substantially through the thickness of the first structure **10**, but preferably does not extend to any substantial extent into the second structure **42**, as illustrated in FIG. 6.

The first scoring station **50** can comprise a laser **54** as depicted in FIG. 2. The use of lasers for scoring through flexible materials is generally known, for example as
5 described in U.S. Patent No. 5,158,499, incorporated herein by reference. The depth of the score line formed by the laser can be regulated by regulating the power output or beam intensity of the laser beam, the width or spot size of the laser beam, and the amount of time a given spot on the film surface is irradiated by the beam. These factors generally are selected based on the characteristics of the material being scored. Some materials are
10 more readily scored by lasers than other materials, as known in the art.

As noted, the first score line **52** must be in registration with the outer perimeter **22a** of the pressure-sensitive adhesive strip **20** (and the outer perimeter of the thumb tab **23**, if present). To accomplish this registration, the operation of the laser **54** is controlled to be synchronized with the advancement of the laminate **46**. A sensor **56** disposed adjacent the
15 laminate **46** can be used for detecting a feature on the laminate whose location in relation to the strip of pressure-sensitive adhesive **20** is known, and the sensor's output signal can be used by a suitable controller (not shown) for controlling the laser **54**.

The first score line **52** may also include one or more tear portions **65** as a tamper-evidence feature. A tear portion **65** may comprise one or more interrupted areas **57** in
20 which the first structure **10** is not cut or scored, and whose uncut condition is readily apparent from a visual inspection of the first structure **10**. The interrupted areas **57** are located such that when the flap or outer opening portion **86** bounded by the first score line **52** is peeled back to create an opening through the laminate, the first structure **10** tears through the interrupted areas **57** to connect the two portions of the first score line **52** on
25 opposite sides of each interrupted area **57**. To help ensure that the two portions of the score line will be connected even if the tear line tends to wander in direction, the score line **52** at the "downstream" side of each interrupted area **57** can terminate in a U- or V-shaped portion **58** that extends generally transverse to the direction along which the score line **52** extends. The "downstream" side refers to the side of the interrupted area **57** that is located
30 farthest along the downstream direction (generally left-to-right in FIGS. 4 and 5) in which the outer opening portion **86** is peeled back when opening the package. The first structure **10** is cut through its thickness along the transverse portions **58**, similar to the rest of the

score line **52**. Accordingly, even if the tear line wanders to one side or the other, it will connect with the transverse portion **58** and thereby allow the score line **52** to continue to sever or separate as the outer opening portion **86** is peeled farther back.

Next, the laminate is advanced to a second scoring station **60** at which a second, or
5 inner, score line **62** is formed through the thickness of the second structure **42**. When the pressure-sensitive adhesive **20** has been pattern-applied, the second score line **62** is in registration with (i.e., coincides with) the inner perimeter **22b** (FIG. 1a) of the strip-shaped pattern **22** of pressure-sensitive adhesive **20**. The second score line **62** extends
substantially through the thickness of the second structure **42**, but preferably does not
10 extend to any substantial extent into the first structure **10**, as illustrated in FIG. 6. The second score line **62** is spaced inwardly of the first score line **52** so as to define an inner opening portion **88** of smaller area than the outer opening portion **86**. As further described below, the inner opening portion **88** is adhered to the outer opening portion **86** (either by the permanent adhesive when present, or by the pressure-sensitive adhesive **20** when it is
15 applied everywhere between the two structures **10**, **42**), such that both portions **86**, **88** are lifted together when opening the package.

As shown in FIGS. 4 and 5, preferably the interrupted areas **57** are located with respect to the second score line **62** such that in order to lift the outer opening portion **86** far enough to just begin lifting the inner opening portion **88** and thereby begin to create an
20 opening into the package, the interrupted areas **57** must be torn through. In this regard, the downstream side of each interrupted area **57** (which coincides with the vertex of the U- or V-shaped transverse score line **58**) preferably is not farther along the downstream direction, or at least is not substantially farther along the downstream direction, than is the most-upstream portion of the second score line **62**.

25 The second scoring station **60** can comprise a laser **64**. The operation of the laser **64** is synchronized with the advancement of the laminate in a manner as described above. A sensor **66** can detect a feature, such as an eye mark, on the laminate whose location in relation to the pressure-sensitive adhesive strip **20** is known, and the sensor **66** output can be used for regulating the laser operation so that the second score line **62** is in registration
30 with the inner perimeter of the pressure-sensitive adhesive strip **20**.

As an alternative to the use of lasers for scoring the laminate, the score lines **52, 62** can be formed in the laminate by mechanical scoring or cutting. For instance, as depicted in FIG. 3, a first scoring station **50'** can comprise a kiss roll **51** and backing roll **53** that form a nip through which the laminate is passed. The kiss roll **51** comprises a rotary
5 cutting die defining a cutting edge (not shown). The kiss roll acts in conjunction with the backing roll to cut partially through the thickness of the laminate starting from the outer surface of the first structure **10**, such that the first structure **10** is substantially scored through while the second structure **42** is left intact. The second scoring station **60'** likewise comprises a kiss roll **61** and backing roll **63** for scoring through the second
10 structure **42**.

Additionally, it is within the scope of the invention to laser-score one side of the laminate and to kiss cut or otherwise mechanically score the other side. This can be advantageous, for example, when one of the structures making up the laminate is readily scored by a laser but the other structure is not. For instance, when the first structure **10** is
15 a polyester such as PET, it can readily be scored with a laser, but if a polyethylene heat seal layer is employed on the opposite side, laser scoring may not be the best choice because polyethylene does not score well with a laser. In this case, kiss cutting or other mechanical scoring can be used to score the inner structure **42**.

After the scoring operations, the laminate **46** can be sent to a reel-up (not shown)
20 and wound into a roll for subsequent processing. The laminate can also be slit into a plurality of partial widths and wound into multiple rolls. In this latter instance, each partial width would have the recurring patterns of pressure-sensitive and permanent adhesives applied with suitably configured adhesive applicators to the full-width material, and would have the recurring score lines formed by suitably configured scoring devices
25 acting on either the full-width laminate prior to slitting or acting on each partial-width portion after slitting.

An advantage of the invention, versus the formation of a web having discrete labels applied to a partial portion of the web surface as in the prior art, is that the laminate has a uniform thickness throughout (because the first and second structures are
30 coextensive) and therefore winds well into good-quality rolls. In contrast, a web with labels centrally located in the width of the web tends to produce wound rolls that are soft in the radial direction at the two ends of the roll where the labels are not present.

Additionally, the web with labels is much thicker than laminates made in accordance with the invention, and hence the laminates of the invention can achieve a greater square footage per roll of a given diameter. As already noted, a further drawback to the use of labels is the necessity of applying the labels to the web in an "off-line" process, which often entails shipping a roll of the web to a converter that applies the labels and then ships the roll back to the package manufacturer. In the process of the invention, the manufacture of the laminate and the incorporation of the opening/reclose and tamper-evidence features in the laminate are conducted in an in-line fashion as part of the same overall process. The process of the invention thus is much more efficient and less costly.

Additionally, the invention avoids other drawbacks associated with the use of labels. More specifically, pressure-sensitive adhesive labels typically require a release liner that is peeled off and thrown away, which represents waste, and create a potential choke hazard. Furthermore, there is the additional waste of the skeleton material left over after die-cutting the labels from the label web material. The present invention eliminates such waste and attendant costs.

Some possible applications for the resulting laminate are now explained with reference to FIGS. 4-11. FIGS. 4 and 5 show a flexible package 70. The package includes an outer wrapper 74 that envelopes the package contents and is sealed to enclose the contents. The outer wrapper 74 comprises a packaging laminate made by a method in accordance with the invention, such as the laminate 46 previously described. The outer wrapper 74 is manipulated into a tubular shape and the longitudinal edges of the wrapper 74 are sealed together by a suitable sealant material to form a longitudinal seal (not shown), typically adjacent the bottom surface of the package. The opposing portions of the wrapper 74 are sealed together along transverse seal lines 76, 78 adjacent the opposite ends of the tubular wrapper. The ends of the wrapper 74 can be gusseted if desired, as known in the art.

In the illustrated package, the portion of the outer wrapper 74 having the score lines 52, 62 is provided to be on the top surface of the package. The area of the wrapper 74 bounded by the score lines can constitute any fraction of the total top surface of the package, but advantageously the area is a majority of the total surface area of the top surface.

Based on the previous description of the laminate **46** and its formation process, it will be appreciated that the presence of the score lines **52, 62** has little or no impact on the barrier function of the outer wrapper **74** because each score line extends only partially through the total thickness of the wrapper **74** and the score lines are not aligned with each other. Additionally, the pressure-sensitive adhesive **20** fills the space between the score lines so that even if the score lines overlap somewhat in the thickness direction, there is still no open route between them. Furthermore, the score lines typically have a small width, on the order of a few thousandths of an inch.

Various materials can be used for the construction of the outer wrapper **74**. With reference to FIG. 6, in the illustrated embodiment, the first structure **10** that forms the outer surface of the wrapper **74** comprises a single layer **80** of flexible material. The layer **80** can comprise various materials. A preferred material is a polyester such as polyethylene terephthalate (PET). As noted, the PET layer can be reverse-printed if desired, although alternatively it can be printed on its exterior and covered by an over-lacquer (not shown). The second structure **42** forming the inner surface of the wrapper **74** comprises a barrier layer **82** and a sealant layer **84**. The sealant layer **84** constitutes the innermost surface of the wrapper **74**, and can comprise various sealant materials such as heat seals or cold seals. Heat seals generally are preferred because they provide stronger seals than cold seals typically are capable of achieving. Any suitable heat seal materials can be employed, such as polyethylene, polypropylene, ionomer resins such as SURLYN®, or others.

The barrier layer **82** can comprise any of various barrier materials including barrier polymer films such as: ethylene vinyl alcohol copolymer (EVOH), polyamide, and the like; metallized polyolefin films such as polyethylene, polypropylene, oriented polypropylene, and the like; AlOx-coated polymer films; SiOx-coated polymer films; metal foil; and others.

The barrier layer **82** and sealant layer **84** can be joined in various ways, including adhesive lamination, extrusion lamination, or coextrusion.

Advantageously, the laminate includes a metallization layer or a metal foil layer between the first structure **10** and the second structure **42**, for example by providing a metallization layer **85** on the surface of the layer **82** that faces the first structure **10**. This

is beneficial in enhancing the barrier performance of the laminate as already noted. Additionally, however, the metallization layer or **85** metal foil layer can also be helpful when a laser is used for scoring the second structure **42**. In particular, when the sealant layer **84** comprises polyethylene, which is not as readily scored by laser as some other materials such as polyester, it can be difficult to employ a sufficiently high laser energy to score through the polyethylene sealant layer without scoring through the laminate more deeply than desired. In some cases, the entire thickness of the laminate may be scored through, which is undesirable. The metallization layer or metal foil layer can be helpful in “tuning” the laser to penetrate only up to the metallization layer **85** or foil layer.

10 The function of the opening/reclose and tamper-evidence features provided by the pattern-applied adhesives and the score lines will now be described. With reference to FIGS. 4 and 6, the package **70** is shown in a closed condition, for example as initially filled and sealed in a packaging plant. On the top surface of the outer wrapper **74**, the first or outer structure **10** is adhesively joined to the second or inner structure **42** via the permanent adhesive **34**. The first score line **52** bounds an outer opening portion **86** of the outer structure **10**. In this embodiment, the outer opening portion **86** has a generally U-shaped perimeter having three sides defined by the score line **52**, and is attached to the remainder of the outer wrapper **74** along a fourth side (i.e., an imaginary line extending between the free ends of the two legs of the U-shaped score line **52**). The second score line **62** is generally parallel to the first score line **52**, but is spaced inwardly of the outer score line so as to define an inner opening portion **88** of smaller area than the outer opening portion **86**; the second score line **62** can be a closed curve such as a rectangle, or can be generally U-shaped like the first score line **52**, as desired. In any event, there is a marginal region **90** of the outer opening portion **86** that extends beyond the edge of the inner opening portion **88**. The pressure-sensitive adhesive **20** is disposed between this marginal region **90** and an underlying surface **92** of the inner structure **42**. The outer opening portion **86** and inner opening portion **88** are permanently joined by the permanent adhesive **34** when present, or by the pressure-sensitive adhesive when it is applied everywhere between the structures.

30 The first score line **52** includes the interrupted areas **57** and transverse score lines **58** as previously described. Prior to initial opening of the package, the uncut condition of

the interrupted areas 57 is readily apparent, such that the consumer can see that the package has not yet been opened.

When the outer opening portion 86 is detached from the outer wrapper along the first score line 52 and is peeled back as in FIG. 5, the outer layer of the wrapper tears through the interrupted areas 57. The inner opening portion 88 remains affixed to the outer opening portion and comes with it, thereby creating an opening 94 in the top surface of the outer wrapper 74 as defined by the second score line 62. The outer and inner opening portions essentially form a flap that remains attached along a hinge line defined between the free ends of the two legs of the U-shaped score lines.

The package is reclosable by re-attaching the pressure-sensitive adhesive 20 to the surface 92 of the inner structure 42 to restore the package to a closed condition as shown in FIG. 6. It will, however, be readily apparent that the package has already been opened, because the film will be torn through the tear portions 65. No amount of care in replacing the flap in its original position can erase the fact that the interrupted areas have been torn through. Accordingly, the invention provides a reliable tamper-evidence feature that is not easily circumvented. Furthermore, in some embodiments, the outer structure 10 can be substantially non-transparent or opaque without compromising the functionality of the tamper-evidence feature; this is in contrast to some prior-art structures in which the outer structure must be transparent because the tamper-evidence feature is formed in the inner structure and is covered by the outer structure. The non-transparent or opaque character of the outer structure 10 can be a characteristic of the film material itself, or can be achieved by a coating of ink or the like on the film.

The outer structure 10 preferably has a greater affinity for bonding with the pressure-sensitive adhesive 20 than does the surface 92 of the inner structure 42, and hence the pressure-sensitive adhesive 20 is detached from the surface 92 and remains attached to the marginal region 90 of the outer opening portion 86 as shown in FIGS. 5 and 7. The greater bonding affinity of the outer structure 10 can be achieved in various ways. When the outer structure comprises a layer of PET and the layer 82 of the inner structure to which the pressure-sensitive adhesive is attached comprises a polyolefin such as polypropylene, oriented polypropylene, or metallized oriented polypropylene, the PET will naturally have a greater affinity for bonding to the adhesive than will the polyolefin layer. Additionally or alternatively, the surface of the outer structure 10 can be treated, as

previously noted, by corona discharge or flame treatment, to increase the surface energy and enhance the bonding affinity. It is also possible, as already noted, to control the bond strength of the pressure-sensitive adhesive to the layer **82** by including an additive in the adhesive to reduce the bond strength, if desired.

5 Although it is preferred to have the pressure-sensitive adhesive be applied to the outer structure and to remain on the outer structure upon opening, it is also within the scope of the invention to apply the pressure-sensitive adhesive to the inner structure and to remain on the inner structure upon opening. This is less preferred, however, because of the greater tendency for crumbs or the like from the contained products to become adhered
10 to the pressure-sensitive adhesive and thereby reduce its adhesiveness with repeated openings and reclosings. It is believed that this tendency is reduced when the pressure-sensitive adhesive remains with the outer structure, since it is out of the way of the package opening when products are being removed.

 It will be appreciated from the above description that laminates made in
15 accordance with the invention provide a tamper-evidence function for a package because after opening it is impossible to replace the opening portions **86, 88** in such a way as to completely restore the package to its original unopened condition, as previously noted. When printing is included on the laminate, it is even more noticeable when the package has been opened because it is difficult to achieve perfect registration of the printed matter
20 across the score line when reclosing the package.

 The printing on the laminate can include text adjacent to the interrupted areas **57** of the first score line **52**, calling the consumer's attention to the presence of the interrupted areas and indicating that if they are torn through at a tear portion **65**, the consumer should not purchase the package.

25 The laminates made in accordance with the invention can be used for forming other types of packages or tamper-evidence features. For instance, FIG. 8 shows a stand-up pouch **100** constructed from the laminate **46** as described above. The first score line **52** and second score line **62** are formed in a side wall of the pouch. The opening/reclose and tamper-evidence features operate in a manner similar to that described above. An
30 alternative form of a thumb "tab," **25** is included, wherein a corner portion of the outer flap defined by the first score line **52** is left free of pressure-sensitive adhesive **20**.

The packages illustrated in FIGS. 9, 10 and 11 show other stand-up pouches **100** with alternative types of tamper-evidence features. In particular, the stand-up pouch **100** of FIG. 9 includes a tab **25** that extends from an edge of outer portion **86**. Preferably, tab **25** is defined by first score line **52** and is free from pressure sensitive adhesive **20** or lamination to the second structure **42**. The end of the tab **25** is then attached or anchored to a portion of the outer layer **74** or along the transverse seal line **76**. The tab **25** illustrated in FIG. 9 may also include an indentation **55** between the outer portion **86** and where the end of tab **25** is attached to the stand-up pouch **100**. By forming the tab **25** in this way, a user may easily access an underside of the tab **25** with a finger and open the stand-up pouch **100** by pulling the tab generally along the downstream direction (generally top-to-bottom in FIGS. 8-10). By pulling on the tab **25** in this way, the tab **25** will tear at or near the indentation **55**, or tear portion **65**, and allow the stand-up pouch **100** to open. Thus, the stand-up pouch **100** cannot be opened without introducing a tear into the tab **25** thereby creating a tamper-evidence feature that is clearly visible.

The stand-up pouch **100** of FIGS. 10 and 11 show other embodiments of tab **25** with a tamper-evidence feature. In FIG. 10, tab **25** also is defined by first score line **52** and extends from an edge of outer portion **86**. The end of the tab **25** is attached or anchored to a portion of the outer layer **74** or along the transverse seal line **76** and is free from pressure sensitive adhesive **20** or lamination to the second structure **42**. The tab **25** in FIG. 10 includes a prong **59** extending from a side of the tab **25** between the outer portion **86** and where the end of tab **25** is attached to the stand-up pouch **100**. The presence of prong **59** facilitates the task of a user tearing through a portion of the tab **25** at a tear portion **65** before opening the stand-up pouch **100** by providing a surface that is easily grasped.

The embodiment in FIG. 11 includes two tabs **25** that include tear portions **65** in addition to a thumb tab **23**. Both tabs **23** and **25** also are defined by first score line **52** and extend from an edge of outer portion **86** and are free from pressure sensitive adhesive **20** or lamination to the second structure **42**. The end of tabs **25** are attached or anchored to a portion of the outer layer **74** or along the transverse seal line **76**. In use, tab **23** may be used to open the pouch **100** and to assist in tearing through tear portions **65** of tabs **25**.

It should be noted that the terms "line of weakness" and "score line" as used herein refer either to a complete cutting through the thickness of one or more layers of the

lamine or to a partial cutting through of the thickness of such layer(s) allowing the layer(s) to be severed along the score line.

The packages described above are formed by completely enveloping the contents in the flexible laminate. Alternatively, however, it is within the scope of the invention to
5 employ the flexible laminate as a lidding stock for forming flexible lids that can be secured (e.g., by heat-sealing or the like) to a flange of a tray or other container that contains the contents. In this manner, the lid includes a built-in opening and reclose feature as previously described. For instance, FIG. 12 shows a package **110** comprising a container body **112** having a side wall **114** and a flange **116** extending from the upper edge
10 of the side wall. The container body **112** can comprise various materials (e.g., polymer, paper, foil, etc.) and can be formed by various methods (e.g., thermoforming, molding, etc.). The open top of the container body is closed by a lid **118** formed of a flexible laminate **46** in accordance with the invention. The lid is sealed to the flange **116** by any suitable technique, such that the lid is firmly attached to the flange. The lid includes an
15 opening/reclose feature formed by a first score line **52** and a second score line **62** and pressure-sensitive adhesive **20**, and a tamper-evidence feature as previously described. The package **110** also includes a thumb "tab" **25** generally as described in connection with FIG. 8; alternatively, a thumb tab of the type shown in FIGS. 4 and 5 can be used.

Many modifications and other embodiments of the inventions set forth herein will
20 come to mind to one skilled in the art to which these inventions pertain having the benefit of the teachings presented in the foregoing descriptions and the associated drawings. Therefore, it is to be understood that the inventions are not to be limited to the specific embodiments disclosed and that modifications and other embodiments are intended to be included within the scope of the appended claims. Although specific terms are employed
25 herein, they are used in a generic and descriptive sense only and not for purposes of limitation.

5

In the specification the term “comprising” shall be understood to have a broad meaning similar to the term “including” and will be understood to imply the inclusion of a stated integer or step or group of integers or steps but not the exclusion of any other integer or step or group of integers or steps. This definition also applies to variations on the term “comprising” such as “comprise” and “comprises.”

10

The reference to any prior art in this specification is not, and should not be taken as an acknowledgement or any form of suggestion that the referenced prior art forms part of the common general knowledge in Australia.

WHAT IS CLAIMED IS:

1. A flexible packaging structure having built-in opening/reclose and tamper-evidence features, comprising:

an outer structure adhesively joined in face-to-face relation to an inner structure,
5 the outer structure comprising a first flexible material and the inner structure comprising a second flexible material;

an outer line of weakness formed in the outer structure, the outer line of weakness defining an outer opening portion that is separable from the outer structure along the outer line of weakness;

10 an inner line of weakness formed in the inner structure, the inner line of weakness defining an inner opening portion that is separable from the inner structure along the inner line of weakness;

wherein the inner opening portion is joined to the outer opening portion such that lifting the outer opening portion out of the plane of the flexible packaging structure
15 causes the inner opening portion to be lifted along with the outer opening portion so as to create an opening through the flexible packaging structure;

wherein a marginal region of the outer opening portion is defined between the inner and outer lines of weakness, the marginal region overlying an underlying surface of the inner structure;

20 wherein a pressure-sensitive adhesive is disposed on one of an overlying surface of the outer opening portion and the underlying surface of the inner structure for re-adhering the overlying surface to the underlying surface after opening; and

a tamper-evidence feature that is initially in an untorn condition prior to initial creation of the opening, and whose untorn condition is apparent from a visual inspection
25 of the outer structure, wherein the tamper-evidence feature comprises a first tab having one end integrally joined to an outer edge of the marginal region and an opposite end anchored to a portion of the outer structure spaced from the outer edge, the first tab being torn through upon initial creation of the opening through the flexible packaging structure.

2. The flexible packaging structure of claim 1, wherein the first tab further comprises an indentation.
3. The flexible packaging structure of claim 1, wherein the first tab includes a prong extending from a side of the first tab.
- 5 4. The flexible packaging structure of claim 1, wherein the first tab is free from pressure-sensitive adhesive or lamination to the inner structure.
5. The flexible packaging structure of claim 1, wherein the tamper-evidence feature further comprises a second tab spaced from the first tab, the second tab having one end integrally joined to the outer edge of the marginal region and an opposite end
10 anchored to a portion of the outer structure spaced from the outer edge.
6. The flexible packaging structure of claim 5, wherein the second tab is free from pressure-sensitive adhesive or lamination to the inner structure.
7. A method for making a flexible packaging laminate having built-in opening/reclose and tamper-evidence features, comprising the steps of:
15 applying a pressure-sensitive adhesive onto one surface of a first structure comprising at least one layer of flexible material;
adhesively joining the first structure to a second structure so as to form a laminate, the second structure comprising at least one layer of flexible material, wherein one of the first and second structures comprises an outer structure and the other comprises an inner
20 structure;
advancing the laminate to a scoring station at which an outer score line is formed through the thickness of the outer structure and an inner score line is formed through the thickness of the inner structure in registration with the outer score line, the outer score line delineating an outer opening portion of the outer structure that is separable from the
25 outer structure along the outer score line, the inner score line delineating an inner opening portion of the inner structure that is affixed to the outer opening portion and is separable from the inner structure along the inner score line, wherein a region of the outer opening portion between the outer and inner score lines is attached to an underlying surface of the

inner structure via the pressure-sensitive adhesive, the outer opening portion being peelable from the underlying surface of the inner structure so as to cause the inner opening portion to also be peeled back to create an opening in the laminate, and the outer opening portion being re-attachable to the underlying surface of the inner structure via the pressure-sensitive adhesive for reclosing the opening; and

forming a tamper-evidence feature in the outer structure that is initially in an untorn condition prior to initial creation of the opening, and whose untorn condition is apparent from a visual inspection of the first structure, wherein the step of forming the tamper-evidence feature comprises forming a first tab having one end integrally joined to an outer edge of the outer opening portion and an opposite end anchored to a portion of the outer structure spaced from the outer edge, the first tab being torn through upon initial creation of the opening through the flexible packaging laminate.


8. The method of claim 7, wherein the first tab is formed to have an indentation.

9. The method of claim 7, wherein the first tab is formed to have a prong extending from a side of the first tab.

10. The method of claim 7, wherein the step of forming the tamper-evidence feature further comprises forming a second tab spaced from the first tab, the second tab having one end integrally joined to the outer edge of the outer opening portion and an opposite end anchored to a portion of the outer structure spaced from the outer edge.

11. A flexible packaging structure substantially as herein described.

12. A method for making a flexible packaging laminate substantially as herein described.






FIG. 1a.




FIG. 1b.




FIG. 4.




FIG. 5.




FIG. 6.




FIG. 7.

4/6




Fig. 8




Fig. 9

5/6




Fig. 10




Fig. 11




Fig. 12