



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A61K 9/00, 9/16, 9/50	A1	(11) International Publication Number: WO 99/32083 (43) International Publication Date: 1 July 1999 (01.07.99)
<p>(21) International Application Number: PCT/GB98/03853</p> <p>(22) International Filing Date: 21 December 1998 (21.12.98)</p> <p>(30) Priority Data: 9727102.7 22 December 1997 (22.12.97) GB</p> <p>(71) Applicant (for all designated States except US): QUADRANT HEALTHCARE (UK) LIMITED [GB/GB]; 1 Mere Way, Ruddington, Nottingham, NG11 6JS (GB).</p> <p>(72) Inventors; and (75) Inventors/Applicants (for US only): ROGERSON, Cheryl, Vanessa [GB/GB]; Quadrant Healthcare (UK) Limited, 1 Mere Way, Ruddington, Nottingham NG11 6JS (GB). OSBORNE, Nicholas, David [GB/GB]; Quadrant Healthcare (UK) Limited, 1 Mere Way, Ruddington, Nottingham NG11 6JS (GB).</p> <p>(74) Agent: GILL JENNINGS & EVERY; Broadgate House, 7 Eldon Street, London EC2M 7LH (GB).</p>		<p>(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).</p> <p>Published <i>With international search report.</i></p>
<p>(54) Title: MICROPARTICLES AND THEIR THERAPEUTIC OR DIAGNOSTIC USE</p>		
<p>(57) Abstract</p> <p>Microcapsules having a wall thickness of no more than 500 nm, and a bulk density of no more than 0.2 g.cm⁻³, are suitable for therapeutic or diagnostic use. They are aerodynamically light, and can be used for delivery to the lung, or diagnosis by ultrasound.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

MICROPARTICLES AND THEIR THERAPEUTIC OR DIAGNOSTIC USEField of the Invention

This invention relates to microparticles and their therapeutic or diagnostic use. More particularly, the invention relates to the delivery of an active agent to the lungs, by inhalation, and to diagnostic imaging using ultrasound.

Background of the Invention

Edwards *et al*, Science 276: 1868-71 (1997), reports the production of particles of small mass density and large size, for use in pulmonary drug delivery. The objective was to provide an insoluble matrix which could act as a reservoir for sustained drug release, analogous to a sustained release tablet. Porous and non-porous particles were prepared, the porous particles being preferred for their "high efficiency". The "particle mass density" values for these particles were about 0.1 g.cm^{-3} and 0.8 g.cm^{-3} , respectively. The porous particles apparently comprised a solid matrix including pores, the matrix being essentially a carrier for a therapeutic agent (the given examples being testosterone and insulin) held within the matrix.

Note 14 of Edwards *et al* states that the density is determined by non-mercury porosimetry or tap density measurements. The latter at least would not give a true particle density. Reference 15 (French *et al*, J. Aerosol Sci. 27:769 (1996)) clearly shows bulk densities. Note 14 refers to Vidgren *et al*, Int. J. Pharm. 35:139 (1987), which uses an "effective density". Hence, little can be concluded as to the meaning of "particle mass density".

WO 98/31346 apparently relates to products similar to those disclosed by Edwards et al. The particles are aerodynamically light, and generally porous.

A difficulty with many sustained release inhalation therapies is that solid (or more dense) particles will be subject to clearance mechanisms and therefore unable to act as a reservoir. Any such particles landing in the trachea or bronchi will be rapidly removed by mucociliary clearance mechanisms. Similarly, particles reaching the non-ciliated regions of the deep lung are rapidly cleared by macrophage activity. The material reported by Edwards et al is intended to avoid both these problems, by providing a particle of relatively large geometric diameter ($> 5 \mu\text{m}$) which will avoid phagocytosis by macrophages, but which is aerodynamically small (i.e. a low density with respect to geometric diameter), and which will reach the non-ciliated region of the deep lung. Sustained release is then achieved by use of an insoluble matrix of material.

The particles disclosed by Edwards et al. were prepared by double- and single-emulsion solvent evaporation techniques. It is also stated that porous particles comprising therapeutics and pharmaceutical excipients can easily be formed by spray-drying, and refers in this context to an article by Sacchetti and Van Oort in "Inhalation Aerosols" (May 1996) A J Hickey ed., Dekker NY pub., pages 337-384. No specific indication is given as to how particles of low density might be obtained by spray-drying. For inhalation therapy, a dry powder must be dispersed into an airstream as discrete particles, to ensure controlled reproducible administration of a standard dose. To achieve this, the powder is usually loaded onto a carrier such as lactose, through blending. The objective

is to produce a blend in which the drug powder is distributed as discrete particles evenly over the carrier. If this is not achieved, and the particles are agglomerates, there is an apparent increase in aerodynamic size and a reduction in dosing efficiency.

While compounds that can be administered without carrier are known, e.g. sodium cromoglycate and terbutaline, these are usually either extremely safe or relatively inactive, allowing therapeutic effects to be achieved as a result of the inefficient administration of enormous quantities of material. Moreover, the use of carriers can cause additional drug formulation difficulties. For example, lactose, the most commonly used material for this purpose, is a reducing sugar and can react chemically with some drug substances, such as proteins and peptides.

The mechanical manipulation of lactose, such as blending and sieving, also results in "high energy spots" on the surface of the carrier. This results in a reduction of inhalation efficiency, because of the additional energy required to disperse the drug material.

The use of spray-drying in pharmaceutical processing is not new. However, it is usually used to bind particles together, for the purposes of obtaining powders with good flow properties.

US-A-5202159 describes spray-drying a slurry of diclofenac, excipients, methacrylic acid-ethyl acrylate copolymers and polyethylene glycol, and formulating the product into tablets. US-A-4971787 discloses spray-drying a medicament with sugar, and formulating the product with a specific gum base, to give a chewing gum composition.

US-A-4180593 discloses producing free-flowing blown bead food products, by spray-drying the foodstuff with a blowing agent, and then quenching, in order to control the bulk density. The reported bulk density in the only
5 Example is about 0.1 g.cm^{-3} (6 lb/ft^3).

Summary of the Invention

By contrast to the prior use of spray-drying, for bonding particles together in a medicament, the present invention uses spray-drying for the production of large,
10 light particles. More particularly, it has now been found that microcapsules having properties that are particularly suitable for use in ultrasound diagnostic procedures, i.e. non-porous, and for the delivery of a therapeutic agent by inhalation, can be prepared by the simple expedient of
15 including a blowing agent in the formulation to be spray-dried. As a result, microcapsules having a bulk density of no more than 0.2 g.cm^{-3} can be obtained.

Microcapsules of the invention are very suitable for formulation in an inhaler. If they comprise a therapeutic
20 agent, they provide rapid release and subsequent uptake of drug in the lung, and avoid drug encapsulation, quite by contrast to any sustained release formulation. Further, products of this invention do not require a carrier, for effective administration to the lung. An inhaler including
25 microcapsules of the invention may therefore contain the microcapsules as the sole or predominant component of the inhalable formulation.

Thus, the present invention allows the controlled, reproducible administration of small quantities of potent
30 and/or expensive medicines without the need for carrier material. Problems associated with the use of lactose can be avoided.

Moreover, if the microcapsules contain only wall-forming material, and no therapeutic agent is included as such, they are particularly suitable for use in ultrasonic imaging. The relatively thin walls of the microcapsules
5 apparently provides improved echogenicity.

Description of the Invention

Procedures for preparing microparticles by spray-drying, suitable wall-forming materials (such as albumin), and processes for stabilising the microparticles, e.g. by
10 heat or chemically, are fully described in, *inter alia*, WO 92/18164 and WO 96/15814 (describing the currently preferred process), the contents of which are incorporated herein by reference. According to the present invention, these procedures are modified by the inclusion of a blowing
15 agent, in the feedstock for spray-drying.

The blowing agent is a volatile substance which releases a gas or gases during the spray-drying process. Blowing agents are used in the present invention, to produce hollow microcapsules. Suitable blowing agents
20 include ammonium acetate, ammonium hydroxide, ammonium carbonate, ammonium bicarbonate, acetic acid, formic acid and hydrochloric acid. The pH at which these blowing agents are used may vary; this implies that compounds with pH-dependent solubilities can be spray-dried with the
25 addition of a suitable blowing agent.

By way of example, the blowing agent used in the production of albumin microcapsules is ammonium carbonate which releases ammonia, carbon dioxide and water vapour. During spray-drying, these three gases expand in the
30 atomised droplets, causing the droplet to increase in size, to produce larger, thinner-walled microcapsules.

Products of the invention may have various characteristics, depending on the conditions of their preparation. For example, their median size is 1 to 20 μm , and their wall thickness is no more than 500 nm, e.g. 10 to 250 nm, more preferably 100 to 150 nm. Their bulk density may be 0.01 to 0.15 $\text{g}\cdot\text{cm}^{-3}$, more preferably 0.04 to 0.1 $\text{g}\cdot\text{cm}^{-3}$.

The microcapsules of the invention comprise a wall-forming material and, if desired, a therapeutic agent (which may be the same). If the wall-forming material and the therapeutic agent are different, the microcapsules may be formed by co-spray-drying.

As indicated above, the microcapsules may comprise albumin, and preferably human serum albumin. Albumin may be used as a therapeutic agent *per se*, or as a wall-forming material in combination with a therapeutic agent. Other active agents for use in the invention will be chosen having regard to the desired effect. Examples of active agents that may be used include cotranscytosis factors, fibrinogen, thrombin, insulin, growth hormone, calcitonin, α -antitrypsin, FSH, α -interferon, β -interferon, heparin, Factor VIII, Factor IX, interleukins and blood coagulation factors. Other wall-forming materials that may be used are described in WO 92/18164.

For the preferred route of administration, the soluble microcapsules obtained by spray-drying are used. As indicated above, stabilisation may be used, if another route of administration is required and/or for diagnostic purposes. The amount of microcapsules to be administered can readily be determined by the skilled man.

The following Examples illustrate the invention.

Example 1

212 ml diafiltered 10% w/w HSA solution containing 60 g ammonium carbonate was spray-dried on a standard Mobile Minor spray-dryer. The conditions were as follows:

5	Inlet temperature	- 220°C
	Atomisation pressure	- 2.0 barg
	Feed rate	- 21.4 g/min
	Atomisation type	- 2-fluid nozzle
	Liquid insert	- 0.5 mm

10 The non-fixed microcapsules obtained by spray-drying, which are soluble, behaved as a powder, demonstrating liquid fluidised properties. They are suitable for use as such, in an inhaler.

For testing purposes, 4 g microcapsules obtained by 15 spray-drying were heat-stabilised for 55 minutes at 176°C in a hot air oven. After heat stabilisation, the microcapsules retained their fluidized properties.

A 50 mg aliquot of heat-stabilised microcapsules was dispersed in de-ionised water (sonication in ethanol was 20 not necessary). The suspension was then microscopically examined and sized using a Coulter Counter fitted with a 50 µm aperture tube.

Microscopic examination showed the presence of 2 distinct populations of microcapsules. The first 25 population consisted of hollow, air-containing microcapsules approx. 5 µm in size, and the second population consisted of larger, blown microcapsules containing the suspension fluid. Microcapsules of both populations may be suitable for use in accordance with the 30 invention, independently or in combination.

The microcapsules had very thin walls. They were self-fluidising and had a density of approximately 0.07

g/cm³. They were therefore suitable for testing as products for delivery by the pulmonary route. The median size by volume distribution of these microcapsules was shown to be 10.7 μm by Coulter Counter sizing.

5 Using a multi-stage liquid impinger (MLSI) and a Dinkihaler, the aerodynamic diameter of the microcapsules was determined.

Three gelatin capsules were each filled with 10 mg of the microcapsules. Each stage of the MLSI was filled with
10 20 ml purified water, and the air flow set to 60 l/minute.

A single gelatin capsule was pierced at both ends and placed in the Dinkihaler. The air flow was turned on for 30 seconds and then switched off.

The device and throat were each washed with 20 ml
15 purified water. Each stage was washed in a total of 25 ml purified water and the filter was washed in 10 ml purified water. They were then assayed for protein by standard methods.

The MLSI was washed thoroughly and prepared for a
20 second run as described above. 3 runs were carried out. Results are shown in the following Table.

Stage	Percentage Accumulation		
	Run 1	Run 2	Run 3
Device	17.02	8.85	14.27
Throat	22.62	11.57	18.08
25 1 (>13.4 μm)	4.78	2.66	5.31
2 (13.4-6.8 μm)	14.58	18.30	12.99
3 (6.8-3.1 μm)	25.92	32.63	23.56
4 (3.1-1.7 μm)	7.96	15.59	11.09
Filter (<1.7 μm)	1.38	4.64	7.58
30 Total Recovery (%)	94.30	94.23	92.87

The respirable fractions (defined as particles below 6.8 μm) for runs 1 - 3 were 33%, 53% and 42%, respectively. The results are also representative of the non-stabilised microcapsules, and suggest that this type of microcapsule is suitable for pulmonary delivery.

Example 2

100 ml of diafiltered 20% w/w HSA solution containing 10 g ammonium carbonate was spray-dried on a Niro Mobile Minor spray-dryer. The following conditions were used:

Inlet temperature	- 220°C
Atomisation pressure	- 7.5 barg
Feed rate	- 3.96 g/min
Atomisation type	- 2-fluid nozzle
15 Liquid insert	- 0.5 mm

5g of the spray-dried microcapsules thus obtained were heat-stabilised for 55 minutes at 177°C in a hot air oven. The stabilised microcapsules were then deagglomerated with an equal mass of glucose using a Fritsch centrifugal pin mill.

The microcapsules were sized using a Coulter Counter fitted with a 100 μm orifice tube which found that the volume median diameter of the microcapsules was 10.1 μm . The echogenic properties were characterised as described in Example 5 of WO 96/15814. The known microcapsules were found to have echogenicities of around 26 VDU's; for the microcapsules of this Example, containing a blowing agent, the corresponding value was 69 VDU's.

CLAIMS

1. Microcapsules having a wall thickness of no more than 500 nm, and a bulk density of no more than 0.2 g.cm^{-3} , for therapeutic or diagnostic use.
- 5 2. Microcapsules according to claim 1, whose median size is 1 to 20 μm .
3. Microcapsules according to claim 1 or claim 2, whose wall thickness is 10 to 250 nm.
4. Microcapsules according to claim 3, whose wall
10 thickness is 100 to 150 nm.
5. Microcapsules according to any preceding claim, whose bulk density is 0.01 to 0.15 g.cm^{-3} .
6. Microcapsules according to claim 5, whose bulk density is 0.04 to 0.1 g.cm^{-3} .
- 15 7. Microcapsules according to any preceding claim, whose walls are comprised at least predominantly of albumin.
8. Microcapsules according to any preceding claim, obtainable by spray-drying a wall-forming material, in combination with a blowing agent.
- 20 9. Microcapsules according to any preceding claim, which comprise a therapeutic agent.
10. Microcapsules according to claim 9, which comprise a cotranscytosis factor.
11. Microcapsules according to claim 9, which comprise
25 fibrinogen or thrombin.
12. Microcapsules according to claim 9, which comprise an active agent selected from insulin, growth hormone, calcitonin, α -antitrypsin, FSH, α -interferon, β -interferon, heparin, Factor VIII, Factor IX, interleukins and blood
30 coagulation factors.
13. Microcapsules according to any of claims 9 to 12, which are soluble.

14. An inhaler comprising a inhalable formulation of microcapsules according to claim 13.

15. An inhaler according to claim 14, wherein the formulation comprises the microcapsules as the sole or the
5 predominant component thereof.

16. Use of a therapeutic agent for the manufacture of a medicament for use in therapy of a condition for which the therapeutic agent is active when administered to the lung, wherein the medicament comprises microcapsules of the
10 therapeutic agent, according to any of claims 9 to 13.

17. Microcapsules according to any of claims 1 to 8, which are insoluble.

18. Use of microcapsules according to claim 17, for the manufacture of a medicament for use in diagnosis, by
15 ultrasound imaging.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 98/03853

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 A61K9/00 A61K9/16 A61K9/50

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 202 159 A (LI J. CHEN, ET AL.) 13 April 1993 see the whole document ---	1-18
A	US 4 180 593 A (ALLAN N. COHAN) 25 December 1979 see the whole document ---	1-18
A	US 4 971 787 A (SUBRAMAN R. CHERUKURI) 20 November 1990 see the whole document -----	1-18

Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

° Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

15 March 1999

Date of mailing of the international search report

22/03/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Ventura Amat, A

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/GB 98/03853

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5202159 A	13-04-1993	JP 4230625 A	19-08-1992
US 4180593 A	25-12-1979	NONE	
US 4971787 A	20-11-1990	US 4581234 A	08-04-1986
		AU 4598585 A	06-03-1986
		CA 1262420 A	24-10-1989
		DE 3585195 A	27-02-1992
		DK 358385 A	28-02-1986
		EG 17504 A	30-06-1989
		EP 0176237 A	02-04-1986
		FI 853062 A	28-02-1986
		GR 851969 A	13-12-1985
		JP 61078350 A	21-04-1986
		PT 81022 B	18-09-1987
		US 4579738 A	01-04-1986
		US 4587125 A	06-05-1986
		AU 588971 B	28-09-1989
		AU 6919387 A	03-09-1987
		CA 1288343 A	03-09-1991
		DE 3772223 A	26-09-1991
		EP 0236271 A	09-09-1987
		GR 3002589 T	25-01-1993
		JP 1752460 C	08-04-1993
		JP 4038724 B	25-06-1992
		JP 62258317 A	10-11-1987
		PT 84363 B	10-11-1989