

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
10 February 2005 (10.02.2005)

PCT

(10) International Publication Number
WO 2005/012686 A1

(51) International Patent Classification⁷: **E21B 33/12**

(21) International Application Number:
PCT/EP2004/051572

(22) International Filing Date: 22 July 2004 (22.07.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
03254738.2 29 July 2003 (29.07.2003) EP

(71) Applicant (*for AE, AG, AL, AM, AT, AU, AZ, BA, BB, BE, BG, BR, BW, BY, BZ, CH, CN, CO, CR, CU, CY, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, SZ, TJ, TM, TN, TR, TT, TZ,*

UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW only): **SHELL INTERNATIONALE RESEARCH MAATSCHAPPIJ B.V.** [NL/NL]; Carel van Bylandtlaan 30, NL-2596 HR The Hague (NL).

(71) Applicant (*for CA only*): **SHELL CANADA LIMITED** [CA/CA]; 400 - 4th Avenue S.W., Calgary, Alberta T2P 2H5 (CA).


(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **BOSMA, Martin Gerard Rene** [NL/NL]; Kesslerpark 1, NL-2288 GS Rijswijk (NL). **CORNELISSEN, Erik Kerst** [NL/NL]; Kesslerpark 1, NL-2288 GS Rijswijk (NL). **CUIJPERS, Juul** [NL/NL]; Den Dolech 2, NL-5612 AZ Eindhoven (NL). **PICCHIONI, Francesco** [IT/NL]; Nijenborgh 4, NL-9747 AG Groningen (NL). **RASTOGI, Sanjay** [NL/NL]; Den Dolech 2, NL-5612 AZ Eindhoven (NL).

(81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM,

[Continued on next page]

(54) Title: SYSTEM FOR SEALING A SPACE IN A WELLBORE



(57) Abstract: A system is provided for sealing a space (7) in a wellbore (1) formed in an earth formation (2). The system comprises a swellable body (12) arranged in the wellbore in a manner so as to seal said space upon swelling of the swellable body, the swellable body being susceptible of being in contact with formation water (4) flowing into the wellbore, the swellable body including a matrix material provided with a compound soluble in said formation water. The matrix material substantially prevents or restricts migration of the compound out of the swellable body and allows migration of said formation water into the swellable body by osmosis so as to induce swelling of the swellable body upon migration of said formation water into the swellable body.



AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,

FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- *with international search report*
- *before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments*

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

- 1 -

SYSTEM FOR SEALING A SPACE IN A WELLBORE

The invention relates to a system and a method for sealing a space in a wellbore formed in an earth formation, the earth formation containing formation water susceptible of flowing into the wellbore.

5 In the production of hydrocarbon fluid from a wellbore, it is common practice to install one or more tubular casing sections in the wellbore to stabilize the wellbore and to control inflow of fluid into the wellbore from the surrounding formation. In conventional
10 applications the casing sections are of stepwise decreasing diameter in downward direction, which is a consequence of the installation procedure whereby each next casing section must pass through the previously installed section.

15 It has been proposed to provide alternative casing schemes which overcome the problem of stepwise decreasing casing diameters. For example in one such alternative casing scheme, each casing section is installed in the wellbore by lowering the casing section through the
20 previously installed section to the desired depth whereby a short overlap section of the casing section extends into the previously installed section. Next the casing section is radially expanded in the wellbore to allow lowering of a drill string having a drill bit of
25 relatively large diameter therethrough. After deepening the wellbore using the drill bit of relatively large diameter, a further casing section is lowered through the expanded casing section. Thereafter the cycle of expanding the casing section, further drilling the

- 2 -

wellbore, and lowering a new casing section, is repeated. As a result a wellbore of substantially uniform diameter is achieved.

5 The installed casing sections are in the conventional well construction process fixed and sealed in the wellbore by pumping a layer of cement between the casing and the wellbore wall. This technology could be applied to the Expandable Open Hole Liner, as well. The sealing function of the cement layer relates to the requirement
10 that migration of formation fluids, such as formation water, through the annular space between the casing and the wellbore wall should be prevented. However it has been experienced that adequate sealing by pumping a layer of cement in the annular space, is sometimes difficult to
15 achieve. For example if the drilling fluid used to drill the wellbore is not fully replaced by cement in the annular space, or if adequate filling of the annular space with cement is hampered by irregularities in the wellbore wall, there is a risk that formation fluids
20 migrate in axial direction through the annular space.

WO 03/008756 discloses an alternative system for sealing an annular space in a wellbore, wherein a swelleable annular seal is arranged in the annular space. The seal is made of a rubber material susceptible of
25 swelling upon contact with oil or water, depending of the type of application. In use the seal swells when formation fluid enters the wellbore thereby sealing the annular space and preventing axial migration of formation fluid through the wellbore.

30 Examples of materials which swell when in contact with water are 1) Poly-Electrolytes such as Super Absorbing Polymers (SAP) such as Sodium Polyacrylate and Acrylic Acids, 2) hydrophilic clays such as Sodium

- 3 -

Bentonite particles (e.g. Wyoming Bentonite), or 3) natural water swelling material such as wood, cork or cellulose fillers. Hydrophilic elastomers are used in civil engineering applications, for example as tunnelling gaskets.

Although adequate swelling results have been obtained with the above materials when in contact with fresh (non-saline) water it has been experienced that seals made of these materials swell insufficiently when in contact with saline formation water. For example, Sodium Polyacrylate particles and Bentonite particles immersed in water have a sharply declining swelling ratio when the water changes from fresh water to saline water, especially if divalent cations such as Ca^{2+} and Mg^{2+} are present which is usually the case for common oilfield formation aquifers. The declining swelling ratio of SAP's in saline water, especially in bi-valent cation containing solutions, is reviewed in "Modern super absorbent polymer technology", Buchholz, F.L. and Graham, A.T., Wiley New York 1998, page 57 and Fig. 2.16, where the dramatic reduction in swelling capacity of a crosslinked sodium polyacrylate in 0.9 wt% NaCl solutions, is indicated for increasing CaCl_2 concentrations. Here, swelling ratio is defined as the ratio of the volume of a body after swelling thereof over the volume of the body before swelling thereof. Furthermore, hydrophilic Polyurethanes (such as Sanyo's Aquaprene C-520® Kuriyama's Aquaquell 8V®, Denbi's Hydrotite®) which do swell in saline solutions are considered unsuitable for most well applications in view of their limited long term resistance to higher temperatures.

It is an object of the invention to provide an improved system for sealing a space in a wellbore formed

- 4 -

in an earth formation, which overcomes the drawbacks of the prior art.

5 In accordance with the invention there is provided a system for sealing a space in a wellbore formed in an earth formation, comprising a swelleable body arranged in the wellbore in a manner so as to seal said space upon swelling of the swelleable body, the swelleable body being susceptible of being in contact with formation water flowing into the wellbore, the swelleable body including a matrix material provided with a compound
10 soluble in said formation water, wherein the matrix material substantially prevents or restricts migration of the compound out of the swelleable body and allows migration of said formation water into the swelleable
15 body by osmosis so as to induce swelling of the swelleable body upon migration of said formation water into the swelleable body.

The invention also relates to a method of sealing a space in a wellbore formed in an earth formation, the
20 method comprising arranging a swelleable body in the wellbore in a manner so as to seal said space upon swelling of the swelleable body, the swelleable body being susceptible of being in contact with formation water flowing into the wellbore, the swelleable body including a matrix material provided with a compound
25 soluble in said formation water, wherein the matrix material substantially prevents or restricts migration of the compound out of the swelleable body and allows migration of said formation water into the swelleable
30 body by osmosis so as to induce swelling of the swelleable body upon migration of said formation water into the swelleable body.

- 5 -

In this manner it is achieved that swelling of the swelleable body, and thus sealing of the space, is obtained by virtue of chemical osmosis whereby the matrix material act as a membrane permeable to water but
5 (substantially) impermeable to said compound.

To prevent or reduce leaching of said compound out of the body of swelleable material, it is preferred that said body includes a matrix material substantially impermeable to said compound or to ions formed of said
10 compound.

Preferably the matrix material includes a polymer matrix material, for example a thermoset elastomer matrix material or a thermoplastic elastomer matrix material.

In a preferred embodiment the polymer matrix material
15 is obtained or obtainable by mixing the compound in a mass of polymer material and thereafter vulcanizing the mass of polymer material to form said polymer matrix material. For example, the compound is formed by salt particles, which are mixed into the mass of polymer
20 material prior to cross-linking (vulcanization) thereof, followed by cross-linking of the polymer material to form the elastomer matrix material in which the salt particles are embedded.

Suitable thermoset elastomer materials capable of
25 withstanding the high wellbore temperatures for a prolonged period of time are:

1) rubber materials which, apart from swelling in water, also swell in crude oil present in petroleum wells, such as Ethylene Propylene Rubber (EPM and EPDM), Ethylene-
30 Propylene-diene Terpolymer rubber (EPT), butyl rubber (IIR), brominated butyl rubber (BIIR), chlorinated butyl rubber (CIIR), chlorinated polyethylene (CM/CPE), neoprene rubber (CR), styrene butadiene copolymer

- 6 -

rubber (SBR), sulphonated polyethylene (CSM), ethylene acrylate rubber (EAM/AEM), epichlorohydrin ethylene oxide copolymer (CO, ECO), Silicone Rubbers (VMQ) and Fluorsilicone Rubber (FVMQ);

5 2) rubber materials which do not swell in crude oil, such as Butadiene acrylonitrile copolymer (Nitrile Rubber, NBR), Hydrogenated NBR (HNBR, HNS) such as ZETPOL®, TORNAC®, TERBAN®, NBR with reactive groups (X-NBR), Fluoro Rubbers (FKM), such as VITON®, FLUOREL®,
10 Perfluoro Rubbers (FFKM) such as KALREZ®, CHEMRAZ® and Tetrafluorethylene/propylene (TFE/P), such as AFLAS®, which would not swell when exposed to oil field crudes.

Most of these elastomers can be crosslinked by more than one crosslinking agent (e.g. either "Sulphur cross-linked of Peroxide cross-linked").
15

Apart from the thermoset (non swelling and oil swelling) elastomer matrix materials quoted above, also blends of elastomers can be applied ('elastomeric alloys'). Although an almost inexhaustible combination of
20 thermoplastic and thermoset elastomers are feasible, the most preferable are the EPDM/Polypropylene blends such as SARLINK®, Levaflex®, Santoprene®, NBR- Polypropylene blends such as GEOLAST®, NBR/Polyvinylchloride blends and NR/Polypropylene blends. All of these have a tendency to
25 swell in Petroleum crudes, especially at the targeted downhole well temperatures.

Preferably said compound is incorporated in a plurality of particles homogeneously distributed through the matrix material.

30 Suitable particles are fine particles of salt, preferably dissociating salt, which can be uniformly compounded into the base rubber. For example extremely fine salt particles which are water soluble are applied,

- 7 -

the salt being selected from the group of: acetates; M-(CH₃COO), bicarbonates; M-(HCO₃), carbonates; M-(CO₃), formates M-(HCO₂), halides; Mx-Hy (H = Cl, Br or I), hydrosulphides; M-(HS), hydroxides; M-(OH), imides; M-(NH), nitrates; M-(NO₃), nitrides; M-N, nitrites; M-(NO₂), phosphates; M-(PO₄), sulphides; M-S and sulphates; M-(SO₄), where M can be any metal of the periodic table. Other salts are can be applied where the cation is a non-metal like NH₄Cl.

10 However the preferred salts are NaCl and CaCl₂.

 To limit leaching out of the salt from the elastomer, suitably the swelleable body includes any hydrophilic polymer containing polar groups of either oxygen or nitrogen in the backbone or side groups of the polymer. These side groups can be partially or fully neutralised. Polymers of such type are, for example, hydrophilic polymer types such as alcohols, acrylates, methacrylates, acetates, aldehydes, ketones, sulfonates, anhydrides, maleic anhydrides, nitriles, acrylonitriles, amines, amides, oxides (polyethylene oxide), cellulose types including all derivatives of these types, all copolymers including one of the above all grafted variants. Suitably a ternary system is applied which includes an elastomer, a polar SAP and a salt, whereby the polar SAP is grafted onto the backbone of the elastomer. Such system has the advantage that the polar SAP particles tend to retain the salt particles in the elastomer matrix thereby reducing leaching of the salt from the elastomer. The polar salt is attracted by electrostatic forces to the polar SAP molecules, which are grafted ('glued') to the backbone of the rubber.

 Generally the swelleable body should be capable of swelling in water of salinity as high as 140 g/Sodium

- 8 -

Chloride, and containing considerable concentrations of bivalent ions, such as at least 40 g/l Calcium Chloride and 8 g/l Magnesium Chloride, and at temperatures of at least 40 °C but preferably 100-150 °C which is typical
5 for the static bottom hole temperatures of petroleum wells. The transition from non-swollen to fully swollen state preferably takes place within a timeframe of 2-3 weeks, and the swollen state should be maintained for a period of at least one year.

10 The invention will be described further in more detail and by way of example, with reference to the accompanying drawing in which:

Fig. 1 schematically shows the swelling behaviour of a material not according to the invention when immersed
15 in water, for various water salinities;

Fig. 2a schematically shows the swelling behaviour of various rubber compositions when immersed in saline water, over a relatively long period of time;

Fig. 2b schematically shows the swelling behaviour of
20 the rubber compositions of Fig. 2a over a relatively short period of time;

Fig. 3 schematically shows the swelling behaviour of a rubber composition when immersed in saline water, for various concentrations of salt contained in the rubber
25 composition;

Fig. 4 schematically shows an embodiment of the system of the invention whereby an annular seal is arranged around a casing extending into a wellbore formed into an earth formation; and

30 Fig. 5 schematically shows a side view of the casing and the annular seal of Fig. 4.

In the Figures like reference numerals relate to like components.

- 9 -

Referring to Fig. 1 there is shown a diagram giving the swelling ratio of Sodium Polyacrylate immersed in water as a function of NaCl salinity, and for different cross-linking densities (X), whereby

- 5 Q = swelling ratio
 C = NaCl concentration of the water (wt%)
 line a: X = 0.025 wt% Sodium Polyacrylate
 line b: X = 0.04 wt% Sodium Polyacrylate
 line c: X = 0.06 wt% Sodium Polyacrylate
10 line d: X = 0.08 wt% Sodium Polyacrylate
 line e: X = 0.10 wt% Sodium Polyacrylate

From the diagram it is clear that water swelleable elastomers prepared by addition of Super Absorbent Polymer (SAP) particles to the rubber matrix material are
15 unsuitable for saline wellbore conditions. Formation
 aquifers can be extremely saline (saturated at downhole
 temperatures), typically 4-6 times the salinity of common
 sea water. Especially the presence of di-valent cations
 such as Ca^{2+} and Mg^{2+} which are commonly present in
20 oilfield aquifers, causes dramatic reduction of the
 swelling capability. Such SAP particles can be classified
 into starch systems, cellulose systems and synthetic
 resin systems. The SAP's have hydrophilic characteristics
 by virtue of the presence of alcohols, carboxylic acids,
25 amides or sulphuric acids. Due to cross-linking, the
 particles have a three-dimensional network so that the
 material is capable of swelling to at least 100 times its
 original volume. Other potentially swelling polymers such
 as polyurethanes, polyesters, polyethers are considered
30 unsuitable due to their intrinsic instability as a result
 of hydrolysis.

In Figs. 2a, 2b is shown the swelling ratio (S) of three compositions marketed by RUMA®, Hoogeveen, The

- 10 -

Netherlands, as a function of time. The compositions are available under the names:

900-70-1236, indicated by line a'

900-70-1354, indicated by line b'

5 900-70-1211, indicated by line c'

These compositions have as a base compound EPDM rubber matrix material available from Bayer®, Leverkusen, Germany under the trade name Buna EP® EPT-5459/6950.

10 Furthermore, these compositions include conventional reinforcing agents, fillers, vulcanising agents, and stabilisers.

Additionally:

15 composition 900 70-1236 includes NaCl particles available from AKZO, The Netherlands under the trade name MICROZO® moulded into the rubber matrix material to a concentration of 35 wt% of the rubber matrix material;

composition 900-70-1354 includes a SAP (and no salt);

composition 900-70-1211 includes salt and a SAP.

20 From the Figures it is clear that composition 900 70-1236 shows an excellent swelling ratio of more than 200 volume % in highly saline petroleum aquifer brines containing appreciable quantities of Bi-valent ions, Ca^{2+} , Mg^{2+} . Composition 900-70-1354 has a poor swelling performance (about 18 volume %), and the hybrid
25 composition 900-70-1211 has a swelling performance inbetween the performance of compositions 900-70-1354 and 900-70-1236.

30 Referring to Fig. 3 there is shown a diagram indicating the swelling ratio (S) of compositions based on composition 900-70-1236, but now for different concentrations of NaCl particles in the rubber matrix material Buna EP® EPT-5459/6950. The salt particle concentrations are:

- 11 -

34.8 wt%, indicated by line a"

26.3 wt%, indicated by line b"

41.6 wt%, indicated by line c"

15.1 wt%, indicated by line d"

5 All other additives in these compositions were kept constant.

It appeared that the optimum swelling ratio was achieved for NaCl particle concentrations in the range of 32-37 wt% based on the weight of the matrix material.

10 In Figs. 4 and 5 is shown a wellbore 1 formed in an earth formation 2 which includes an earth formation layer 4 containing saline formation water. A wellbore casing 6 is arranged in the wellbore 1 whereby an annular space 7 is formed between the casing 6 and the wellbore wall 8. A wellhead 10 is arranged on top of the wellbore, at the earth surface. An annular seal in the form of a number of rings 12 (only one ring 12 is shown) is arranged in the annular space 7, in a portion of the wellbore opposite the earth formation layer 4.

20 The rings 12 are composed of one or more of the thermoset or thermoplastic elastomer materials susceptible of swelling in water, referred to above. The rings 12 are, for example, formed of strips 14 extending around the casing 6. Each ring 12 typically has a length of between 0.05-0.5 m, and a thickness of between 0.003-0.07 m. A bonding agent is applied between the rings and the casing to fix the rings 12 to the outer surface of the casing 6, the bonding agent preferably being effective during vulcanisation of the elastomer material. Furthermore, the rings 12 include a high concentration (at least 20 wt%, preferably between 30-35 wt% of the base elastomer) of salt particles so as to induce swelling of the elastomer material upon

- 12 -

permeation of saline formation water into the elastomer material by osmosis. In the present example the salt particles are NaCl particles, but any high concentration of a mono-, di- or tri-valent water soluble salt can be used.

In order to protect the rings 12 during installation of the casing 6 in the wellbore, optionally the set of rings 12 is additionally provided with one or more rings ("wear pads") or sleeves which do not swell in water, such as NBR, HNBR, FKM, XNBR, FFKM, TFE/P rubber rings. Such additional rings should have a high abrasion resistance, and are preferably arranged at either side of each swelling elastomer ring 12. Alternatively these rings could be arranged at the ends of the set of rings 12 only.

During normal operation the NaCl particles are mixed into the rubber matrix material prior to vulcanisation thereof, using a suitable moulding apparatus (not shown) such as a) the two roll mill, b) the mixing mill, or c) the Gordon Plasticator. For a complete review of such techniques reference can be made to:

Werner Hofmann, Rubber Technology Handbook, 2nd ed. (1996), Hanser/Gardner Publications, Cincinnati, ISBN 1-56990-145-7 Chapter 5: Processing of elastomers, 'Compound Preparation'.

The rubber matrix material is then formed into the strip 14, which is radially or slightly helically wrapped around the casing 6 at surface. In a next step the rubber matrix material, and optionally also the material of the wear pads, is vulcanised in an oven at temperatures of typically 150-180 °C to form the rings 12. Thereafter the casing 6 is lowered into the wellbore 1 until the rings 12 are positioned in said portion of the wellbore 1

- 13 -

opposite the earth formation layer 4. The thickness of the rings 12 is selected sufficiently small to allow unhampered lowering of the casing 6.

5 Upon flow of saline formation water from formation layer 4 into the wellbore 1, the saline formation water thereby comes into contact with the water swelling rings 12. Due to the salt concentration in the salt particles (pure salt) being much higher than the salinity of the formation water itself, permeation of formation
10 water into the rubber matrix material will occur as a result of osmosis, which leads to swelling of the rings 12 whereby the rings 12 become pressed against the wellbore wall and thereby completely seal the annular space 7. In this manner any further migration of
15 formation water through the annular space 7 is prevented.

If required the casing 6 is radially expanded in the wellbore, preferably before swelling of the rings 12 occurs.

20 All samples referred to in Figs. 2a, 2b and 3 were immersed in saline aquifer water ("100% Oman aquifer water") including 139 gram/litre NaCl, 41 gram/litre CaCl₂, 7.5gram/litre MgCl₂, and having a temperature of 95 °C.

25 Instead of applying the rings (referred to in Figs. 4 and 5) on a casing, the rings can be applied on one or more sections of blank pipe arranged between sections of sandscreen, for example expandable sandscreen. In this manner it is feasible to create separate sandscreen inflow sections which can be selectively shut-off during
30 the lifetime of the well.

Suitably the casing is an expandable casing which is radially expanded in the wellbore before or after

- 14 -

swelling of the rings, preferably before swelling of the rings.

- 15 -

C L A I M S

1. A system for sealing a space in a wellbore formed in an earth formation, comprising a swelleable body arranged in the wellbore in a manner so as to seal said space upon swelling of the swelleable body, the swelleable body
5 being susceptible of being in contact with formation water flowing into the wellbore, the swelleable body including a matrix material provided with a compound soluble in said formation water, wherein the matrix material substantially prevents or restricts migration of
10 the compound out of the swelleable body and allows migration of said formation water into the swelleable body by osmosis so as to induce swelling of the swelleable body upon migration of said formation water into the swelleable body.
- 15 2. The system of claim 1, wherein said matrix material is substantially impermeable to said compound or to ions of said compound.
3. The system of claim of claim 1 or 2, wherein the matrix material includes a polymer matrix material.
- 20 4. The system of claim 3, wherein the polymer matrix material is an elastomer matrix material.
5. The system of claim 4, wherein the elastomer matrix material includes a rubber selected from NBR, HNBR, XNBR, FKM, FFKM, TFE/P or EPDM base rubber.
- 25 6. The system of any one of claims 3-5, wherein the polymer matrix material is obtained or obtainable by mixing the compound in a mass of polymer material and thereafter vulcanizing the mass of polymer material to form said polymer matrix material.

- 16 -

7. The system of any one of claims 1-6, wherein the compound is present in the matrix material in the form of a plurality of particles dispersed in the matrix material.

5 8. The system of claim 7, wherein the particles are substantially uniformly dispersed in the matrix material.

9. The system of claim 7 or 8, wherein the particles are embedded in the matrix material.

10 10. The system of any one of claims 1-9, wherein said compound comprises a salt, for example a dissociating salt.

11. The system of claim 10, wherein the salt is one of the group of acetates ($M-CH_3COO$), bicarbonates ($M-HCO_3$), carbonates ($M-CO_3$), formates ($M-HCO_2$), halides (M_{x-}
15 H_y) ($H = Cl, Br$ or I), hydrosulphides ($M-HS$), hydroxides ($M-OH$), imides ($M-NH$), nitrates ($M-NO_3$), nitrides ($M-N$), nitrites ($M-NO_2$), phosphates ($M-PO_4$), sulphides ($M-S$) and sulphates ($M-SO_4$), where M is a metal selected from the group of metals of the periodic table.

20 12. The system of claim 10 or 11, wherein the swelleable body contains at least 20 wt% salt based on the combined weight of the matrix material and the salt, preferably at least 35 wt% salt based on the combined weight of the matrix material and the salt.

25 13. The system of any one of claims 1-12, wherein said space is an annular space formed between a tubular element extending into the wellbore and a substantially cylindrical wall surrounding the tubular element,

30 14. The system of claim 13, wherein said tubular element is a wellbore casing or wellbore liner, and said substantially cylindrical wall is the wellbore wall.

- 17 -

15. The system of claim 13 or 14, wherein the swelleable body is formed by one or more rings, each ring extending around the tubular element.

5 16. The system of any one of claims 1-15, wherein the swelleable body is arranged in a portion of the wellbore opposite an earth formation layer containing said formation water.

17. The system of any one of claims 1-16, wherein the formation water is saline formation water.

10 18. A method of sealing a space in a wellbore formed in an earth formation, comprising arranging a swelleable body in the wellbore in a manner so as to seal said space upon swelling of the swelleable body, the swelleable body being susceptible of being in contact with formation
15 water flowing into the wellbore, the swelleable body including a matrix material provided with a compound soluble in said formation water, wherein the matrix material substantially prevents or restricts migration of the compound out of the swelleable body and allows
20 migration of said formation water into the swelleable body by osmosis so as to induce swelling of the swelleable body upon migration of said formation water into the swelleable body.

25 19. The method of claim 18, wherein the matrix material includes a polymer matrix material, and wherein the polymer matrix material is obtained by mixing the compound in a mass of polymer material and thereafter vulcanizing the mass of polymer material to form said polymer matrix material.

30 20. The method of claim 19, wherein the compound is mixed in the mass of polymer material in the form of a plurality of particles of the compound.

- 18 -

21. The system substantially as described hereinbefore with reference to the accompanying drawing.

22. The method substantially as described hereinbefore with reference to the accompanying drawing.

1/5

Fig.1.




Fig.5.




Fig.2(a).







Fig.2(b).





5/5

Fig.4.



INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP2004/051572

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 E21B33/12

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 E21B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 3 385 367 A (PAUL KOLLSMAN) 28 May 1968 (1968-05-28) column 9, line 5 - line 18; figures 13-15 -----	1-20
A	WO 03/008756 A (SHELL CANADA LTD ; BOSMA MARTIN GERARD RENE (NL); CORNELISSEN ERIK KER) 30 January 2003 (2003-01-30) cited in the application the whole document -----	1,14
A	US 5 195 583 A (BELSHAW DOUGLAS J ET AL) 23 March 1993 (1993-03-23) the whole document -----	1,18
A	WO 02/059452 A (THOMSON NEIL ; E2 TECH LTD (NL)) 1 August 2002 (2002-08-01) the whole document -----	1,18
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

° Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *G* document member of the same patent family

Date of the actual completion of the international search

10 December 2004

Date of mailing of the international search report

22/12/2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Ott, S

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP2004/051572

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4 936 386 A (COLANGELO ROBERT V) 26 June 1990 (1990-06-26) the whole document -----	1,18

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP2004/051572

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 3385367	A	28-05-1968	NONE	
WO 03008756	A	30-01-2003	BR 0211253 A CA 2453660 A1 WO 03008756 A1 EP 1407113 A1	27-07-2004 30-01-2003 30-01-2003 14-04-2004
US 5195583	A	23-03-1993	GB 2248255 A CA 2052308 A1	01-04-1992 28-03-1992
WO 02059452	A	01-08-2002	CA 2435382 A1 WO 02059452 A1 GB 2388136 A NO 20033338 A US 2004194971 A1	01-08-2002 01-08-2002 05-11-2003 17-09-2003 07-10-2004
US 4936386	A	26-06-1990	US 4919989 A	24-04-1990