

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 463 737 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication of patent specification: 25.01.95 (51) Int. Cl.⁶: **C09D 11/00**

(21) Application number: **91304845.0**

(22) Date of filing: **29.05.91**

(54) **Use of ink formulations comprising mixtures of anionic waterfast dyes containing two or more carboxyl groups in thermal ink-jet printers to reduce nozzle clogging of the printer.**

(30) Priority: **22.06.90 US 542862**

(43) Date of publication of application:
02.01.92 Bulletin 92/01

(45) Publication of the grant of the patent:
25.01.95 Bulletin 95/04

(84) Designated Contracting States:
DE FR GB IT

(56) References cited:
EP-A- 0 356 080
EP-A- 0 494 522

(73) Proprietor: **Hewlett-Packard Company**
Mall Stop 20 B-O,
3000 Hanover Street
Palo Alto,
California 94304 (US)

(72) Inventor: **Radke, Garold E.**
29615 N.E. Weslinn
Corvallis, OR 97333 (US)
Inventor: **Hindagolla, Suraj L.**
2819 NW Angelica Drive
Corvallis, OR 97330 (US)
Inventor: **Adamic, Raymond J.**
1840 NW 14th Street
Corvallis, OR 97330 (US)
Inventor: **Wickramanayake, Palitha**
3163 Powderhorn Place
Corvallis, OR 97330 (US)
Inventor: **Halko, David J.**
2903 NW Angelica Drive
Corvallis, OR 97330 (US)

(74) Representative: **Colgan, Stephen James et al**
CARPMAELS & RANSFORD
43 Bloomsbury Square
London WC1A 2RA (GB)

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid (Art. 99(1) European patent convention).

EP 0 463 737 B1

Description

TECHNICAL FIELD

5 This application relates to ink formulations for ink-jet printers.

BACKGROUND ART


10 Thermal ink-jet printers operate by employing a plurality of resistor elements to expel droplets of ink through an associated plurality of nozzles. In particular, each resistor element, which is typically a pad of a resistive material measuring about $50\text{ }\mu\text{m} \times 50\text{ }\mu\text{m}$, is located in a chamber filled with ink supplied from a reservoir. A nozzle plate, comprising a plurality of nozzles or fine openings, with each nozzle associated with a resistor element, defines one side of the chamber. Upon energizing of a particular resistor element, a droplet of ink is expelled through the nozzle toward the print medium, whether paper, transparent film, or
15 the like. The firing of ink droplets is typically under the control of a microprocessor, the signals of which are conveyed by electrical traces to the resistor elements, thereby forming alphanumeric and other characters on the print medium.

The tight tolerances of the nozzles (typically 40 to $50\text{ }\mu\text{m}$ diameter) require that the ink not clog the nozzles. Further, repeated firings of the resistor elements, which must withstand many millions of firings
20 over the life of the ink cartridge to be commercially practical, can result in fouling of the resistor elements. This is unique to thermal ink-jet printers and is known as kogation.

The ink composition must be capable of interacting with the print medium, especially paper, to penetrate the paper without undue spreading and a subsequent decrease in print quality. Finally, the printed characters must dry rapidly and be waterfast and smear resistant.

25 Inks are known which possess one or more of the foregoing properties. However, few ink compositions are known that possess all the foregoing properties, since an improvement in one property often results in the degradation of another property. Thus, many inks used commercially represent a compromise in an attempt to achieve an ink evidencing at least an adequate response in each of the foregoing considerations. Accordingly, investigations continue into developing ink formulations which have improved properties and
30 which do not elevate one property at the expense of the others.

In a related patent application entitled "Waterfast Ink Formulations with a Novel Series of Anionic Dyes Containing two or More Carboxyl Groups", EP-A-0415581, inks are disclosed which include a dye corresponding to the formula in the free acid state of



wherein

- 50 W is COOH,
X is H or COOH,
Y is H, COOH, or SO_3H ,
Z is H, COOH, or SO_3H , and
R is H, CH_2COOH , or $\text{CH}_2\text{CH}_2\text{COOH}$;

55 provided that there are at least two COOH groups and that the number of COOH groups is equal to or greater than the number of SO_3H groups. The concentration of the dye in the inks ranges from 0.5 to 20 wt%. The inks further include up to 30 wt% of a water-soluble organic solvent for the dye and the balance water.

EP-A-0356080 describes anionic dyes suitable for use in ink-jet printing. The dyes have general Formula I above, with side-groups defined as follows:-

W is COOH

X is H, COOH, SO₃H, halo, hydroxy, nitro, cyano, C₁₋₆-alkyl, C₁₋₆-alkoxy, or C₁₋₆-acylamino;

5 Y is H, COOH or SO₃H;

Z is H, COOH or SO₃H;

R & R' are each independently H or C₁₋₆-alkyl substituted by 0, 1 or 2-COOR² groups;

R² is H or C₁₋₆-alkyl;


10 provided that there are at least two COOH groups and that the number of COOH groups is equal to or greater than the number of SO₃H groups.

The printing inks described in EP-A-0356080 can contain one or two dyes of the above formula in an aqueous medium. The ink preferably contains 0.5% to 20% by weight of the dye based on the total weight of the ink. The ink can also contain various water-soluble organic solvents for the dye.

15 While the above inks are suitably employed in thermal ink-jet printers and evidence excellent waterfast printing on paper, efforts continue to develop further improvements in ink formulations.

The present invention provides the use of an ink comprising, by wt%:

a) from 0.5% to 20% of a mixture of at least two different dyes, each of which, in the free acid state, independently corresponds to the formula



wherein

35 W is COOH,

X is H or COOH,

Y is H, COOH, or SO₃H,

Z is H, COOH, or SO₃H, and

R is H, CH₂COOH, or CH₂CH₂COOH;

40 provided that there are at least two COOH groups and that the number of COOH groups is equal to or greater than the number of SO₃H groups,

b) up to 30% of a water-soluble organic solvent for said dye, and

c) water

in a thermal ink-jet printer to reduce nozzle clogging of the printer.

45 Preferably, each dye comprises at least 10% by weight of the dye mixture. Preferably, the two different dyes are present in the mixture in a ratio of from 15:85 to 70:30, more preferably 50:50 by weight.

It is preferred that there are from 2 to 4 COOH groups. It is also preferred that at least two of the COOH groups are attached directly to an aromatic carbon atom.

50 Where X is H, W may be in the ortho, meta, or para position with respect to the azo group, but is preferably in the para position. However, it is preferred that X is COOH and that the two COOH groups are in the 3,5-, 3,4-, or 2,5-position with respect to the azo group.

It is preferred that there are not more than two SO₃H groups, i.e., that Y and Z are not both SO₃H. It is also preferred that there are more COOH groups than SO₃H groups.

55 The inks used in this invention comprise, by weight, from 0.5 to 20 wt% dye (total), up to 30% organic solvent, and the balance mostly water. A buffer is also employed to maintain the ink at a pH between 7 and 9.5. Other adjuncts commonly found in ink-jet inks, such as a biocide, may also be added to the inks.

Use of at least two such dyes results in better ink and pen performance. However, even better performance is achieved by adding a phosphate, such as ammonium phosphate, to reduce kogation and by adding a metal chelating agent, such as EDTA, to prevent metal ion precipitates and, consequently, further

improve resistance to nozzle clogging.

The dyes of the above formula can be prepared by diazotization of the corresponding amines, as described in the above-referenced EP-A-0415581. Examples of suitable mixtures of dyes for use in the inks of this invention are as follows:

Dye I: W and X are COOH,

Y is H,

Z is SO₃H,

R is H;

Dye II: W and X are COOH,

Y and Z are H,

R is H;

Dye III: W and X are COOH,

Y is SO₃H,

Z is H,

R is H.

Preferably, each dye is present in an amount of at least 10% by weight, based on the combined weight of the dyes. However, for some applications, ink formulations of equal absorbances may be desirably employed, in order to obtain the best compromise in properties of the ink.

The dyes of the present invention are preferably used in the form of their salts, such as alkali metal (Na⁺, K⁺ or Li⁺) or ammonium or substituted ammonium salt. These are formed by mixing a dye which is in the acid form with a stoichiometric amount of the appropriate base in water. If one starts with the sodium salt of the dye and wishes to convert it to another salt, e.g., ammonium, the sodium form should be acidified to precipitate out the acid form. The acid form is then treated with the appropriate base, e.g., NH₄OH. It may be necessary to repeat the acid step and again mix with the base in order to remove all the sodium ions. Preferably, the ammonium salt (NH₄⁺) of the dyes is employed in the practice of the invention.

The dyes may also be converted to the ammonium salt by an ion exchange process using the ammonium form of a strong acid cation exchange resin. The resin is converted to the ammonium form from the acid form with ammonium hydroxide. This process is described more fully in U.S. Patent 4,786,327, issued November 22, 1988, and assigned to the same assignee as the present application.

The inks contain from 0.5% to 20%, preferably from 1% to 10%, by weight of the dyes based on the total weight of the ink, there being at least two dyes present.

Liquid media used for preparing the present inks include water and mixtures of water with various water-soluble organic solvents. When a water-soluble organic solvent is present, it preferably constitutes from 2% to 30% of the ink.

The water-soluble organic solvents include C₁-C₄ alkanols such as methanol, ethanol, n-propanol, isopropanol, n-butanol, sec-butanol, tert-butanol, isobutanol; amides such as formamide and dimethylacetamide; ketones or ketone alcohols such as acetone and diacetone alcohol; ethers such as tetrahydrofuran and dioxane; nitrogen-containing heterocyclic ketones such as 2-pyrrolidone, N-methylpyrrolid-2-one and 1,3-dimethylimidazolid-2-one; polyalkylene glycols such as polyethylene glycol and polypropylene glycol; alkylene glycols and thioglycols containing C₂-C₆ alkylene groups such as ethylene glycol, propylene glycol, butylene glycol, triethylene glycol; thiodiglycol, hexylene glycol, and diethylene glycol; other polyols such as glycerol and 1,2,6-hexanetriol; and lower alkyl ethers of polyhydric alcohols such as 2-methoxyethanol, 2-(2-methoxyethoxy)ethanol, 2-(2-ethoxyethoxy)ethanol, 2-methoxy-2-ethoxy-2-ethoxyethanol, 2-[2-(2-methoxyethoxy)ethoxy]ethanol, and 2-[2-(2-ethoxy-ethoxy)ethoxy]ethanol.

Preferred water-soluble organic solvents among these are glycols and glycol ethers, such as ethylene glycol, diethylene glycol, triethylene glycol and 2-methoxy-2-ethoxy-2-ethoxyethanol; polyethylene glycols with molecular weights up to 500; and heterocyclic ketones such as 2-pyrrolidone, N-methylpyrrolid-2-one and 1,3-dimethylimidazolid-2-one. Preferred specific solvent mixtures are a binary mixture of water and diethylene glycol and a binary mixture of water and 2-pyrrolidone.

Use of at least two such dyes in thermal ink-jet printing results in better ink and pen performance, including the following properties:

- 1) reduction of nozzle clogging,
- 2) reduction of pen bearding,
- 3) reduction of ink bronzing on paper,
- 4) greater pH flexibility, and
- 5) control of hue characteristics of ink.

Reduction of nozzle clogging is defined as a missing or misaligned nozzle(s) due to crusted or dried ink in the orifice.

Pen bearding is a process where ink crystallizes out of the pen nozzles and can grow to 5 mm or greater in height. The bearding occurs when the pen is left off the capping station of a printer and is exposed to air.

5 Bronzing of ink on paper refers to a reddish-brown color of the ink upon drying. Many factors affect the amount of bronzing; it is an undesirable property of black inks because of lowered optical densities produced.

As the pH of the ink is lowered, the tendency for clogging and bronzing increases. Stabilization of the pH in the operating range of 7 to 9.5 is maintained by the addition of pH buffers. This may include one or more buffers (mixed buffer system) at a concentration from 0.1 to 5 wt%. The buffers will have pKa's
10 ranging from 6.5 to 10. Buffers such as TES (N-tris[hydroxymethyl]methyl-2-aminoethanesulfonic acid), BICINE (N,N-bis[2-hydroxyethyl]glycine), TEA (triethanolamine), TRIS (tris[hydroxymethyl]aminomethane, and BORAX (sodium borate decahydrate) may be used alone or in combination with each other or with other buffers.

The hue of a black ink is important with respect to appearance and acceptance by the viewer. For
15 example, a bluish hue tends to be more acceptable to the viewer than a purplish hue.

Biocides may be used in formulating the inks of the invention. Examples of suitable biocides include PROXEL CRL® and PROXEL GXL® (available from ICI (Great Britain)), and NUOSEPT C® and NUOSEPT
95® (available from Nuodex, Inc. (Piscataway, NJ), although other biocides may be used as well.

Other additives may be added to the ink to provide further improvement in specific properties. These
20 additives are in addition to the pH adjusters and biocides discussed above.

Specifically, a phosphate may be added to the ink to reduce kogation. Kogation is a coined term unique to thermal ink-jet printing and refers to the build-up of residue (koga) on the resistor surface from repeated firings. The build-up of residue tends to degrade pen performance.

Both monobasic (H_2PO_4^-) and dibasic (HPO_4^{2-}) phosphate are desirably employed. Since the cation
25 associated with the dyes is preferably ammonium, then the ammonium form of the phosphate is preferably employed. However, other cations may alternately be employed. The concentration of the phosphate ranges from 0.005 to 0.5 wt%, and most preferably is about 0.07 wt%.

One or more metal chelating agents is added to the ink. In particular, the use of metal chelating agents inhibits or prevents the formation of precipitates in the pen which would inhibit normal operation.

30 It is known from chemical analysis that the inks prepared with carboxyl dyes contain various metal ions, including calcium, iron, and magnesium. Precipitates formed in the nozzle could result in misdirected ink drops or a nozzle which is completely plugged. Precipitates on or near the resistor could also result in lower than normal drop size, which would result in light print or prevent a resistor from ejecting a drop at all.

Complexing agents which have a chelate effect (multiple metal binding sites in a single molecule) are
35 the most desirable additives for preventing metal ion precipitates. Such additives will form complexes with metal ions and thus render them more soluble in the ink, thereby inhibiting the formation of precipitates. Examples of chelating agents that may be used are ethylenediaminetetraacetic acid (EDTA), malonic acid, and salicylic acid. EDTA is well-known for its ability to complex with metal ions, especially calcium. The concentration of the metal complexing agent ranges from 0.01 to 0.5 wt% of the ink. Preferably, the
40 concentration of EDTA is about 0.1 wt%.

An example of an ink having a combination of the desirable properties disclosed herein is given by:

1.1 wt% Dye I
1.1 wt% Dye II
7.5 wt% 2-pyrrolidone 0.4 wt% buffer (0.2 wt% TRIS and 0.2 wt% BORAX)
45 0.07 wt% phosphate anion
0.1 wt% EDTA
0.3 wt% PROXEL GXL®
the balance water.

This ink has a pH of about 8.5, a viscosity of about 1.3 mPas (cp), a surface tension of about 50 dyne/cm, a
50 conductivity of about 8 mS/cm, and an absorbance maximum at 575 nm.

The preparation of the dyes to be used in the claimed inks is illustrated in the above-referenced EP-A-0415581. The formulation of inks and their resulting properties is now presented by the following examples in which all parts and percentages are by weight unless otherwise indicated.

EXAMPLESExample 1:

5 Inks were formulated using the following dyes:

Dye I: W and X are COOH,
Y and R are H,
Z is SO₃H;

10 Dye II: W and X are COOH
Y, Z, and R are H;

Dye III: W and X are COOH,
Y is SO₃H,
Z and R are H.

15 In one ink using a mixture of dyes, 1.1 wt% of Dye I and 1.1 wt% of Dye II were dissolved in aqueous solutions containing diethylene glycol (DEG) or 2-pyrrolidone (2P), 0.2 to 0.4 wt% BORAX and/or TRIS buffers, up to about 0.3 wt% biocide, and up to about 0.07 wt% phosphate anion (provided by ammonium dibasic phosphate). In this Example, the amounts of the two dyes were chosen to provide substantially equal absorbances.

20 In another ink using a mixture of dyes, 1.1 wt% of Dye I and 1.1 wt% of Dye III were dissolved in aqueous solutions containing DEG, BORAX 0.2 wt% and TRIS 0.2 wt% buffers, and 0.07 wt% phosphate anion.

Inks having only one of the two dyes present were also prepared for purposes of comparison. In most cases, single dye or dye mixture, the ammonium form of the dye was employed; in one case, a 50:50 mixture of ammonium and methyl amine (MA) counterions was employed.

25 The inks were tested for various properties as described below.

A. Reduction of Nozzle Clogging.

30 Mixing of Dyes I and II greatly alleviates clogging as noted in Table I below, compared to either Dye I or Dye II alone.

Table I. Results of Nozzle Clogging Tests.

			% of Missing Nozzles	
<u>Dye(s)</u>	<u>Ion</u>	<u>Vehicle</u>	<u>3 days</u>	<u>7 days</u>
Dye I	NH ₄ ⁺	10% DEG	>10%	--
40 Dye I	NH ₄ ⁺	10% 2P	>90%	>100%
Dye I	NH ₄ ⁺ /MA ⁽¹⁾	10% 2P	4%	≥4%
Dye II	NH ₄ ⁺	10% 2P	4-10%	>10%
45 Dye I+II	NH ₄ ⁺⁽²⁾	10% 2P	0%	0%
Dye I+II	NH ₄ ⁺⁽²⁾	7.5% 2P	0%	2%
Dye I	NH ₄ ⁺	5.5% DEG	12% (9 days)	
50 Dye I+III	NH ₄ ⁺⁽²⁾	5.5% DEG	0% (14 days)	

Notes: (1) A 50:50 mixture of counter-ions.

(2) A 50:50 mixture of dyes in terms of absorbances.

Clogging tests were done on mixtures with varying ratios of Dye I and Dye II. These inks also included 0.1 wt% EDTA (the effects of EDTA are discussed in Examples 2-5). The results are listed in Table II below.

Table II. Results of Nozzle Clogging Tests for Various Mixtures of Dyes.

			% of Missing Nozzles
<u>Dye I:II⁽¹⁾</u>	<u>Ion</u>	<u>Vehicle</u>	<u>3 weeks</u>
30:70	NH ₄ ⁺	7.5% 2P	<0.1%
40:60	NH ₄ ⁺	7.5% 2P	<0.1%
50:50	NH ₄ ⁺	7.5% 2P	<0.1%
60:40	NH ₄ ⁺	7.5% 2P	<0.1%
70:30	NH ₄ ⁺	7.5% 2P	<0.1%

Notes: (1) Wt % in terms of absorbances.

By varying the ratio of the two dyes, good resistance to nozzle clogging can also be achieved, as was shown in Table I for a 50:50 mixture.

B. Reduction of Pen Bearding.

Mixing of Dyes I and II greatly reduces pen bearding as noted in Table III below, compared to either Dye I or Dye II alone.

Table III. Results of Pen Bearding Tests.

			Height of Beard	
<u>Dye(s)</u>	<u>Ion</u>	<u>Vehicle</u>	<u>3 days</u>	<u>7 days</u>
Dye I	NH ₄ ⁺	10% DEG	<0.25 mm	--
Dye I	NH ₄ ⁺	10% 2P	None ⁽¹⁾	None ⁽¹⁾
Dye I	NH ₄ ⁺ /MA ⁽²⁾	10% 2P	5 mm	≥5 mm
Dye II	NH ₄ ⁺	10% 2P	5 mm	≥5 mm
Dye I+II	NH ₄ ⁺⁽³⁾	10% 2P	1 mm	≥1 mm
Dye I+II	NH ₄ ⁺⁽³⁾	7.5% 2P	0.25 mm	<0.5 mm

Notes: (1) None because of nozzle clogging.

(2) A 50:50 mixture of counter-ions.

(3) A 50:50 mixture of dyes in terms of absorbances.

C. Reduction of Ink Bronzing.

Quantification of bronzing may be done by measuring the optical densities of a blackout pattern on paper and the $L^*a^*b^*$ coordinates. L^* is a function of darkness of a sample; a^* refers to the amount of red-green component; and b^* refers to the amount of blue-yellow component. Typically, a sample which shows a significant amount of bronzing has a larger a^* component; however, correlation between a^* and bronzing is not perfect. Optical density (O.D.) usually diminishes with bronzing, and can be used as a semi-quantitative measure.

Values of $L^*a^*b^*$ and O.D. for various separate dye formulations and mixtures are listed below in Table

IV. All samples were printed on Gilbert Bond paper using a DeskJet printer.

Mixing of Dyes I and II reduces bronzing as noted in Table IV below, compared to either Dye I or Dye II alone.

Table IV. Results of Bronzing Measurements.

Dye(s)	Ion	Vehicle	O.D.	$L^*a^*b^*$		
				L^*	a^*	b^*
Dye I	NH_4^+	10% DEG	1.28	29.79	3.52	-1.89
Dye I	NH_4^+	10% 2P	1.31	27.22	1.80	-4.97
Dye I	$NH_4^+/MA^{(1)}$	10% 2P	1.31	27.36	1.43	-5.33
Dye II	NH_4^+	10% 2P	1.32	27.68	2.29	-6.62
Dye II	NH_4^+	7.5% 2P	1.29	ND	ND	ND
Dye I+II	$NH_4^{(2)}$	10% 2P	1.34	26.35	1.32	-6.17
Dye I+II	$NH_4^{(2)}$	7.5% 2P	1.32	26.49	1.12	-6.84
Dye I	NH_4^+	5.5% DEG	1.34	ND	ND	ND
Dye I+III	$NH_4^{(2)}$	5.5% DEG	1.30	ND	ND	ND
30:70	$NH_4^{(2)}$	7.5% 2P	1.34	ND	ND	ND
15:85	$NH_4^{(2)}$	7.5% 2P	1.32	ND	ND	ND

Notes: (1) A 50:50 mixture of counter-ions.

(2) A 50:50 mixture of dyes in terms of absorbances.

ND = Not determined.

(3) Ratio of Dye I to Dye II.

Bronzing tests were also done on various mixtures of Dyes I and II. Increasing the amount of Dye I from 0 to 15 and 30% in the mixture increases the optical density from 1.29 to 1.34 as noted in Table IV above.

D. Greater pH Flexibility.

Ink formulations with Dye I have a smaller operating pH range than similar Dye II formulations. Mixing of Dye I with Dye II was observed to extend the effective operating pH range of Dye I. For example, a Dye I/II

ratio of 4:1 at pH 7.5 resulted in irreversible nozzle clogging; a 1:1 ratio showed no clogged nozzles after two weeks at this pH. Optical density of a 1:1 ratio of Dye I/II gave a value of 1.30 O.D. at pH 7.5; for Dye I alone, a value of 1.27 O.D. was obtained. Therefore, an operating range of pH 7.5 to 9 can be specified with greater confidence to a mixed dye ink, than Dye I alone.

E. Control of the Hue Characteristics of Ink.

Dye I is bluish in hue and is preferred over that of Dye II which has a purplish hue. A blue hue ink would have a small positive a^* coordinate with respect to a large negative b^* component. Conversely, a purplish hue would have a correspondingly higher a^* coordinate. As can be seen from Tables IV (above) and V (below), a mixture of Dye I and Dye II produces an ink with a more bluish hue; a^* is less than in Dye II alone.

Table V. Hue Characteristics of Ink by Mixing Dyes

			L*a*b*			
Dye I:II ⁽¹⁾	Ion	Vehicle	O.D.	L*	a*	b*
60:40	NH ₄ ⁺	7.5% 2P	1.34	26.29	0.92	-6.45
50:50	NH ₄ ⁺	7.5% 2P	1.36	25.78	1.00	-6.28
45:55	NH ₄ ⁺	7.5% 2P	1.34	25.90	1.03	-6.46
40:60	NH ₄ ⁺	7.5% 2P	1.35	26.62	1.25	-6.30

Notes: (1) Wt % in terms of absorbances.

As can be seen in Table V, an increase in the amount of Dye I results in more bluish character, while a decrease in Dye I produces more purplish hue.

From the foregoing results, it is apparent that a mixture of Dye I and Dye II in terms of the properties mentioned above gives better overall performance than either Dye I or Dye II alone.

In the following examples, EDTA was used as the disodium salt. All inks had the following formulation: a 50:50 mixture of two carboxyl-containing dyes with ammonium ion as the cation, 7.5% 2-pyrrolidone, 0.1 wt% of ammonium phosphate (dibasic) to provide a phosphate concentration of 0.07 wt%, 0.3 wt% PROXEL GXL biocide, and the balance water. The two dyes, referring to the formula above, were

Dye I: W and X are COOH
Y and R are H
Z is SO₃H;

Dye II: W and X are COOH
Y, Z, and R are H.

The pH of the ink was about 8.5. Two different buffering systems were used: Ink A (0.2 wt% sodium borate decahydrate buffer) and Ink B (0.2 wt% sodium borate decahydrate and 0.2 wt% tris[hydroxymethyl]-aminomethane buffers).

Example 2:

EDTA was added to Ink A to a concentration of 0.1% (Ink A + EDTA). Pens were filled with both inks (Ink A alone and Ink A + EDTA) and left uncapped at ambient conditions for seven days. At the end of this period, the pens were printed with a DeskJet printer. Pens with Ink A alone did not print properly (most nozzles were clogged), whereas pens containing Ink A + EDTA did print properly.

Example 3:

The experiment described in Example 1 was repeated with lower concentrations of EDTA, 0.01% and 0.04%. After being left uncapped for seven days, the pens containing ink with EDTA added printed properly; however, the pens filled with ink that did not contain EDTA did not print (i.e., most of the nozzles were plugged).

Analysis of Ink A used in the above Examples showed the presence of calcium, iron, and magnesium (combined concentration of approximately 10 mg/L), all of which are considered significant impurities at this level. Autopsy of some of these pens revealed deposits in the interior of the pen, specifically, in the inlet channel to the resistor (the "fang area"). Analysis of the deposits by Auger Electron Spectroscopy showed that deposits in Ink A pens contained calcium and iron. However, Ink A + EDTA pens did not have detectable amounts of calcium and had lower concentrations of iron than Ink A deposits.

Further experiments were conducted comparing the performance of Ink B and Ink B + EDTA. Pens were left uncapped for extended periods of time (to allow ample time for deposit formation), with various printing intervals early in this time period and no printing before pen autopsy. The printing cycles and environmental conditions were the same for inks with and without EDTA. The combined concentration of calcium, iron, and magnesium was less than 3 mg/L for Ink B.

Example 4:

The total elapsed uncapped time was 17 weeks at ambient conditions without printing the last 12 weeks. Pens containing ink B were found to have heavy deposits in the fang area and some deposits uniformly over the resistors. However, pens containing Ink B + 0.1% EDTA evidenced relatively smaller residues in the fang area and only traces on the resistors.

Example 5:

The total elapsed time in this Example was 15 weeks at ambient conditions with no printing at the end before autopsy. Again, the Ink B pens had heavier deposits in the fang and resistor areas compared to Ink B + 0.1% EDTA pens. Analysis by Auger Electron Spectroscopy confirmed that the deposits were thicker for the Ink B pens.


From the foregoing, it is evident that the addition of EDTA is beneficial to the performance of inks made with a mixture of two dyes which have carboxyl groups. This has been demonstrated both by differences in printing (EDTA-containing inks survive longer uncapped periods) as well as less precipitation in the firing chambers.

INDUSTRIAL APPLICABILITY

The inks of this invention can be used to print a wide range of papers, especially uncoated papers, using an ink-jet printer.

Claims**1. Use of an ink comprising, by wt%:**

- a) from 0.5% to 20% of a mixture of at least two different dyes, each of which, in the free acid state, independently corresponds to the formula



wherein

W is COOH,

X is H or COOH,

Y is H, COOH, or SO₃H,

Z is H, COOH, or SO₃H, and

R is H, CH₂COOH, or CH₂CH₂COOH;

provided that there are at least two COOH groups and that the number of COOH groups is equal to or greater than the number of SO₃H groups,

b) up to 30% of a water-soluble organic solvent for said dye, and

c) water

in a thermal ink-jet printer to reduce nozzle clogging of the printer.

2. Use according to claim 1 wherein each dye comprises at least 10% by weight of the said mixture.

3. Use according to claim 1 or 2 wherein the two different dyes are present in a ratio of from 15:85 to 70:30 by weight.

4. Use according to claim 3 wherein said two different dyes are present in a ratio of 50:50 by weight.

5. Use according to any of claims 1 to 4 wherein:

(a) in the first dye, W and X are COOH, Y and R are H, and Z is SO₃H, and

(b) in the second dye, W and X are COOH, and either Y, Z and R are H or Y is SO₃H and Z and R are H.

6. Use according to any of claims 1 to 5 wherein the dyes are present in the form of their alkali metal salts or ammonium or substituted ammonium salts.

7. Use according to claim 6 wherein the alkali metal is Na, K or Li, and the ammonium or substituted ammonium is NH₄, (CH₃)₄N, (CH₃)₃NH, (CH₃)₂NH₂ or CH₃NH₃.

8. Use according to any of claims 1 to 7 wherein the ink has a pH of from 7 to 9.5.

9. Use according to claim 8 wherein the ink comprises a buffer to maintain said pH at 7 to 9.5.

10. Use according to any of claims 1 to 9 wherein the ink comprises

(a) from 1 to 10% by weight of said mixture, and

(b) from 2 to 30% by weight of said water-soluble organic solvent.


11. Use according to any of claims 1 to 10 wherein the water-soluble organic solvent is an alkanol having from 1 to 4 carbon atoms, an amide, a ketone, a ketone alcohol, an ether, a nitrogen containing heterocyclic ketone, a polyalkylene glycol, an alkylene glycol, an alkylene thioglycol, thiodiglycol, hexylene glycol, diethylene glycol, a polyol, and a lower alkyl ether of a polyhydric alcohol.

12. Use according to claim 11 wherein the organic solvent is diethylene glycol or 2-pyrrolidone.

13. Use according to any of claims 1 to 12, the ink additionally containing from 0.005 to 0.5% by weight of a monobasic or dibasic phosphate, and from 0.01 to 0.5% by weight of a metal chelating agent.
14. Use according to claim 13 wherein the metal chelating agent is ethylenediaminetetraacetic acid, present in an amount of about 0.1% by weight.
15. Use according to claim 14 wherein the ink consists essentially of:
- (a) about 1.1 wt% each of a first dye in which W and X are COOH, Y and R are H, and Z is SO₃H, and a second dye in which W and X are COOH, and Y, Z and R are H;
 - (b) 7.5 wt% of 2-pyrrolidone;
 - (c) 0.2 wt% of sodium borate decahydrate and 0.2 wt% of tris[hydroxymethyl]aminomethane;
 - (d) 0.07 wt% of phosphate anion;
 - (e) 0.1 wt% of ethylenediaminetetraacetic acid;
 - (f) 0.3 wt% of a biocide; and
 - (g) the balance water.

Patentansprüche

1. Verwendung einer Tinte, die folgende Merkmale aufweist, in % Masseanteil:
- a) von 0,5% bis 20% eines Gemisches von zumindest zwei unterschiedlichen Farbstoffen, von denen jeder in Säureform unabhängig folgender Formel entspricht:



wobei gilt:

- W ist COOH,
- X ist H oder COOH,
- Y ist H, COOH oder SO₃H,
- Z ist H, COOH oder SO₃H, und
- R ist H, CH₂COOH oder CH₂CH₂COOH;

vorausgesetzt es existieren zumindest zwei COOH-Gruppen und die Anzahl der COOH-Gruppen ist größer oder gleich der Anzahl der SO₃H-Gruppen,

- b) bis zu 30% eines wasserlöslichen organischen Lösungsmittels für den Farbstoff, und
- c) Wasser

in einem thermischen Tintenstrahldrucker, um die Düsenverstopfung des Druckers zu reduzieren.


2. Verwendung gemäß Anspruch 1, bei der jeder Farbstoff zumindest 10% Masseanteil des Gemisches umfaßt.
3. Verwendung gemäß Anspruch 1 oder 2, bei der die zwei unterschiedlichen Farbstoffe in einem gewichtsmäßigen Verhältnis von 15:85 bis 70:30 vorliegen.
4. Verwendung gemäß Anspruch 3, bei der die zwei unterschiedlichen Farbstoffe in einem gewichtsmäßigen Verhältnis von 50:50 vorliegen.
5. Verwendung gemäß einem beliebigen der Ansprüche 1 bis 4, bei der gilt:

- a) W und X sind COOH, Y und R sind H, und Z ist SO₃H in dem ersten Farbstoff, und
b) W und X sind COOH und entweder Y, Z und R sind H oder Y ist SO₃H und Z und R sind H in dem zweiten Farbstoff.

- 5 6. Verwendung gemäß einem beliebigen der Ansprüche 1 bis 5, bei der die Farbstoffe in der Form ihrer Alkali-Metall-Salze oder Ammonium oder substituierten Ammonium-Salzen vorliegen.
7. Verwendung gemäß Anspruch 6, bei der das Alkalimetall Na, K oder Li ist, und bei der das Ammonium oder das substituierte Ammonium NH₄, (CH₃)₄N, (CH₃)₃NH, (CH₃)₂NH₂ oder CH₃NH₂ ist.
- 10 8. Verwendung gemäß einem beliebigen der Ansprüche 1 bis 7, bei der die Tinte einen pH-Wert von 7 bis 9,5 aufweist.
9. Verwendung gemäß Anspruch 8, bei der die Tinte einen Puffer aufweist, um den pH-Wert bei 7 bis 9,5 beizubehalten.
- 15 10. Verwendung gemäß einem beliebigen der Ansprüche 1 bis 9, bei der die Tinte folgende Merkmale aufweist:
a) einen Masseanteil von 1 bis 10% des Gemisches, und
20 b) einen Masseanteil von 2 bis 30% des wasserlöslichen organischen Lösungsmittels.
11. Verwendung gemäß einem beliebigen der Ansprüche 1 bis 10, bei der das wasserlösliche organische Lösungsmittel ein Alkanol mit von 1 bis 4 Kohlenstoffatomen, ein Amid, ein Keton, ein Ketonalkohol, ein Ether, ein Stickstoff, der heterozyklisches Keton enthält, ein Polyalkylen-Glykol, ein Alkylen-Glykol, ein Alkylen-Thioglykol, Thiodiglykol, Hexylen-Glykol, Diethylen-Glykol, ein Polyol und ein niederes Alkyl-Ether eines polyhydrierten Alkohols ist.
- 25 12. Verwendung gemäß Anspruch 11, bei der das organische Lösungsmittel Diethylenglykol oder 2-Pyrrolidon ist.
13. Verwendung gemäß einem beliebigen der Ansprüche 1 bis 12, bei der die Tinte zusätzlich einen Masseanteil von 0,005 bis 0,5% von einbasigem oder zweibasigem Phosphat und einen Masseanteil von 0,01 bis 0,5% eines metallischen chelatbildenden Agens enthält.
- 30 14. Verwendung gemäß Anspruch 13, bei der das metallische chelatbildende Agens Ethylen-Diamin-Tetraessigsäure ist, die in einer Menge von etwa 0,1% Masseanteil vorliegt.
- 35 15. Verwendung gemäß Anspruch 14, bei der die Tinte aus folgender Zusammensetzung besteht:
a) etwa 1,1% Masseanteil von sowohl einem ersten Farbstoff, in dem W und X COOH sind, Y und R H sind und Z SO₃H ist, als auch einem zweiten Farbstoff, in dem W und X COOH sind und Y, Z und R H sind;
40 b) 7,5% Masseanteil von 2-Pyrrolidon;
c) 0,2% Masseanteil von Natriumtetraborat-Zehnhidrat und 0,2% Masseanteil von Tris-[Hydroxymethyl]Aminomethan;
45 d) 0,07% Masseanteil eines Phosphat-Anions;
e) 0,1% Masseanteil von Ethylen-Diamin-Tetraessigsäure;
f) 0,3% Masseanteil eines Biozids; und
g) als Rest Wasser.

50 Revendications

1. Utilisation d'une encre comprenant, en pourcentage en poids:
a) de 0,5% à 20% d'un mélange d'au moins deux colorants différents qui correspondent indépendamment chacun, à l'état d'acide libre, à la formule



où

W est COOH,

X est H ou COOH,

Y est H, COOH, ou SO₃H,

Z est H, COOH, ou SO₃H, et

R est H, CH₂COOH, ou CH₂CH₂COOH;

pourvu qu'il existe au moins deux groupes COOH et que le nombre COOH soit égal ou supérieur au nombre de groupes SO₃H,

b) jusqu'à 30% d'un solvant organique soluble dans l'eau pour ledit colorant, et

c) de l'eau

dans une imprimante thermique à jets d'encre pour réduire le bouchage des buses de l'imprimante.

2. Utilisation selon la revendication 1, dans laquelle chaque colorant constitue au moins 10% en poids dudit mélange.

3. Utilisation selon la revendication 1 ou 2, dans lequel les deux colorants différents sont présents selon un rapport compris entre 15:85 et 70:30 en poids.

4. Utilisation selon la revendication 3, dans laquelle lesdits deux colorants différents sont présents selon un rapport de 50:50 en poids.

5. Utilisation selon l'une quelconque des revendications 1 à 4, dans laquelle:

(a) dans le premier colorant, W et X sont COOH, Y et R sont H et Z est SO₃H, et

(b) dans le deuxième colorant, W et X sont COOH, et soit Y, soit Z et R sont H, soit Y est SO₃H et Z et R sont H.

6. Utilisation selon l'une quelconque des revendications 1 à 5, dans laquelle les colorants sont présents sous la forme de leur sels de métaux alcalins ou de leurs sels d'ammonium ou d'ammonium substitués.

7. Utilisation selon la revendication 6, dans laquelle le métal alcalin est Na, K ou Li, et l'ammonium ou l'ammonium substitué est NH₄, (CH₃)₄N, (CH₃)₃NH, (CH₃)₂NH₂ ou CH₃NH₃.

8. Utilisation selon l'une quelconque des revendications 1 à 7, dans laquelle le pH de l'encre est compris entre 7 et 9,5.

9. Utilisation selon la revendication 8, dans laquelle l'encre comprend un tampon pour maintenir ledit pH à une valeur comprise entre 7 et 9,5.

10. Utilisation selon l'une quelconque des revendications 1 à 9, dans laquelle l'encre comprend:

(a) de 1 à 10% en poids dudit mélange, et

(b) de 2 à 30% en poids dudit solvant organique soluble dans l'eau.

11. Utilisation selon l'une quelconque des revendications 1 à 10, dans laquelle le solvant organique soluble dans l'eau est un alkanol à 1 à 4 atomes de carbone, un amide, une cétone, une cétone alcool, un éther, une cétone hétérocyclique contenant de l'azote, un polyalkylène glycol, un alkylène glycol, un alkylène thioglycol, le thiodiglycol, l'hexylène glycol, le diéthylène glycol, un polyol, et un alkyl éther inférieur d'un alcool polyhydrique.
12. Utilisation selon la revendication 11, dans lequel le solvant organique est le diéthylène glycol ou la 2-pyrrolidone.
13. Utilisation selon l'une quelconque des revendications 1 à 12, l'encre contenant en outre de 0,005 à 0,5% en poids d'un phosphate monobasique ou dibasique, et de 0,01 à 0,5% en poids d'un agent chélatant des métaux.
14. Utilisation selon la revendication 13, dans laquelle l'agent chélatant des métaux est l'acide éthylènediaminetétraacétique, présent selon une proportion d'environ 0,1% en poids.
15. Utilisation selon la revendication 14, dans laquelle l'encre est essentiellement constituée par:
 - (a) environ 1,1% en poids chacun d'un premier colorant dans lequel W et X sont COOH, Y et R sont H, et Z est SO₃H, et un deuxième colorant dans lequel W et X sont COOH, et Y, Z et R sont H;
 - (b) 7,5% en poids de 2-pyrrolidone;
 - (c) 0,2% en poids de décahydrate de borate de sodium et 0,2% en poids de tris[hydroxyméthyl]aminométhane;
 - (d) 0,07% en poids d'anion phosphate;
 - (e) 0,1% en poids d'acide éthylènediaminetétraacétique;
 - (f) 0,3% en poids d'un biocide; et
 - (g) de l'eau pour le solde.

REGISTER ENTRY FOR EP0463737

European Application No EP91304845.0 filing date 29.05.1991

Priority claimed:

22.06.1990 in United States of America - doc: 542862

Designated States DE FR GB IT

Title INK FORMULATIONS BY MIXING ANIONIC WATERFAST DYES CONTAINING TWO OR MORE CARBOXYL GROUPS.

Applicant/Proprietor

HEWLETT-PACKARD COMPANY, Mail Stop 20 B-O, 3000 Hanover Street, Palo Alto, California 94304, United States of America [ADP No. 50014570001]

Inventors

GAROLD E. RADKE, 29615 N.E. Weslinn, Corvallis, OR 97333, United States of America [ADP No. 59273953001]

SURAJ L. HINDAGOLLA, 2819 NW Angelica Drive, Corvallis, OR 97330, United States of America [ADP No. 59273961001]

RAYMOND J. ADAMIC, 1840 NW 14th Street, Corvallis, OR 97330, United States of America [ADP No. 59273979001]

PALITHA WICKRAMANAYAKE, 3163 Powderhorn Place, Corvallis, OR 97330, United States of America [ADP No. 59273987001]

DAVID J. HALKO, 2903 NW Angelica Drive, Corvallis, OR 97330, United States of America [ADP No. 59273995001]

Classified to
C09D

Address for Service

CARPMAELS & RANSFORD, 43 Bloomsbury Square, LONDON, WC1A 2RA, United Kingdom [ADP No. 00000083001]

EPO Representative

STEPHEN JAMES COLGAN, CARPMAELS & RANSFORD 43 Bloomsbury Square, London WC1A 2RA, United Kingdom [ADP No. 50906551001]

Publication No EP0463737 dated 02.01.1992

Publication in English

Examination requested 19.03.1993

Patent Granted with effect from 25.01.1995 (Section 25(1)) with title USE OF INK FORMULATIONS COMPRISING MIXTURES OF ANIONIC WATERFAST DYES CONTAINING TWO OR MORE CARBOXYL GROUPS IN THERMAL INK-JET PRINTERS TO REDUCE NOZZLE CLOG.

See pg 2.

14.09.1992 EPO: Search report published on 14.10.1992

Entry Type 25.11 Staff ID. RD06 Auth ID. EPT

03.11.1994 CARPMAELS & RANSFORD, 43 Bloomsbury Square, LONDON, WC1A 2RA,
United Kingdom [ADP No. 00000083001]
registered as address for service

Entry Type 8.11 Staff ID. SS1 Auth ID. AA

22.12.1994 Title truncated for publication date 25.01.1995 by UK Patent
Office. See below for full title. (Use of ink formulations
comprising mixtures of anionic waterfast dyes containing two or
more carboxyl groups in thermal ink-jet printers to reduce nozzle
clogging of the printer.)

Entry Type 25.18 Staff ID. Auth ID. EPT

**** END OF REGISTER ENTRY ****

OA80-01
EP

OPTICS - PATENTS

28/04/95

12:00:08
PAGE: 1

RENEWAL DETAILS

PUBLICATION NUMBER

EP0463737

PROPRIETOR(S)

Hewlett-Packard Company, Mail Stop 20 B-O, 3000 Hanover Street,
Palo Alto, California 94304, United States of America

DATE FILED

29.05.1991

DATE GRANTED

25.01.1995

DATE NEXT RENEWAL DUE

29.05.1995

DATE NOT IN FORCE

DATE OF LAST RENEWAL

YEAR OF LAST RENEWAL

00

STATUS

PATENT IN FORCE

**** END OF REPORT ****