

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization

International Bureau



(10) International Publication Number

WO 2012/082068 A1

(43) International Publication Date

21 June 2012 (21.06.2012)

(51) International Patent Classification:

B05D 5/08 (2006.01) C09K 3/18 (2006.01)
B05D 1/02 (2006.01)

(21) International Application Number:

PCT/SE2011/051532

(22) International Filing Date:

16 December 2011 (16.12.2011)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

1051341-4 17 December 2010 (17.12.2010) SE
61/424,183 17 December 2010 (17.12.2010) US

(71) Applicant (for all designated States except US):
SWETREE TECHNOLOGIES AB [SE/SE]; Box 4095, SE-90403 Umeå (SE).

(72) Inventor; and

(75) Inventor/Applicant (for US only): **RUDA, Marcus** [SE/SE]; Skebokvarnsvägen 265, SE-124 53 Bandhagen (SE).

(74) Agent: **STRÖM & GULLIKSSON AB (LUND)**; Box 793, SE-220 07 Lund (SE).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))



WO 2012/082068 A1

(54) Title: NOVEL METHOD FOR PRODUCTION OF SUPERHYDROPHOBIC SURFACES

(57) Abstract: The present invention provides a method for the production of a superhydrophobic film, surface or material comprising the steps of: (i) providing a composition comprising a hydrophobic substance and a hydrophilic solvent, the hydrophilic solvent being a liquid at a temperature of 25 °C and atmospheric pressure; and (ii) spraying the composition towards a substrate for deposition of a solid residue onto the surface of the substrate for generation of the superhydrophobic film, surface or material; wherein the temperature of the composition is higher than the temperature of the substrate when carrying out step (ii). A composition, use of the composition and a substrate is also provided.

NOVEL METHOD FOR PRODUCTION OF SUPERHYDROPHOBIC SURFACES

TECHNICAL FIELD

5 The present invention relates to a process for production of superhydrophobic surfaces by spraying a composition comprising a hydrophobic material onto a surface.

BACKGROUND

10 In certain technological processes and fabrication procedures, as well as in many every-day situations, it is of crucial importance to utilize objects with strongly water repellent and/or self cleaning surfaces that are stable enough to retain the water-repellent and/or self 15 cleaning property even after water exposure.

15 The water repellent ability of a surface is positively correlated to the hydrophobicity and the degree of unevenness on a colloidal length scale, i.e. about 10^{-8} - 10^{-5} m, thereof. A highly water repellent surface is resulting when the actual contact surface with water, on the microscopic scale, is much larger than the projected macroscopic surface. Hydrophobic surfaces with a suitable microscopic geometry may be highly water repellent as indicated by a contact angle toward pure water in the range between about 150 and 180 degrees. Such 20 surfaces are commonly denoted *superhydrophobic surfaces*. A well-known example taken from nature itself is the leaf of the lotus plant (*Nelumbo nucifera*). A superhydrophobic surface is, as a rule, "self-cleaning" which means that particles of dust and dirt which at first adhere to the surface are being transferred to water droplets sprinkled onto the surface and then removed when the droplets roll off the surface.

25 Much effort has been devoted to the application of waxes and similar hydrophobic materials, e.g. alkylketenedimer (AKD), onto various surfaces for rendering these water repellent and, occasionally, even superhydrophobic.

30 Torkkeli et al., Micro Electro Mechanical Systems, 2001, pp 475 – 478, describes a method for rendering the surface of an electric insulator superhydrophobic by spraying a chloroform solution of AKD onto the same. Disadvantages of this method include a low reproducibility and a high toxicity of the chloroform employed. Chloroform is e.g. generally considered as carcinogenic and is associated with a negative environmental impact. Furthermore, the use of chloroform as solvent limits the spraying device employed to only such spraying devices in which contacting parts, e.g. gaskets and other polymeric materials, 35 are not unacceptably affected by chloroform, which is a solvent with a high dissolution capability for many polymeric materials and/or which may cause such to swell.

WO2009005465A1 describes a method for the preparation of a superhydrophobic surface by expansion of a pressurized fluid in which a hydrophobic substance is dissolved. The substance crystallize/precipitate after expansion whereby particles are formed and deposited to form a superhydrophobic surface. Disadvantages of this method include the need

of equipment capable of storing and handling pressurized solutions. Furthermore, the solubility of the hydrophobic substance in the pressurized solvent, typically supercritical CO₂, is relatively low. Hence, a relatively large volume of pressurized solvent is needed for the deposition of a relatively small amount of hydrophobic substance.

5

Hence, improved methods for the production of superhydrophobic surfaces are highly desired.

SUMMARY

10 The present invention seeks to mitigate, alleviate, circumvent or eliminate at least one, such as one or more, of the above-identified deficiencies.

According to one aspect of the invention, there is provided a method for the production of a superhydrophobic film, surface or material comprising the steps of: (i) 15 providing a composition comprising a hydrophobic substance and a hydrophilic solvent, the hydrophilic solvent being a liquid at a temperature of 25 °C and atmospheric pressure; and (ii) spraying the composition towards a substrate for deposition of a solid residue onto the surface of the substrate for generation of the superhydrophobic film, surface or material; wherein the temperature of the composition is higher than the temperature of the substrate when carrying 20 out step (ii).

According to another aspect of the invention, there is provided a superhydrophobic film, surface or material obtainable by the method according to the invention.

According to yet another aspect of the invention, there is provided a substrate comprising a superhydrophobic film, surface or material according to the invention.

25 According to yet another aspect of the invention, there is provided a composition comprising alkylketenedimer and HOC1-8 alkyl or a mixture of different HOC1-8 alkyls, wherein the concentration of the alkylketenedimer in the composition may be at least 1 mg/ml; for use in the production of a superhydrophobic film, surface or material.

30 According to yet another aspect of the invention, there is provided use of a composition according to the invention for the production of a superhydrophobic film, surface or material.

Further, advantageous features of various embodiments of the invention are defined in the dependent claims and within the detailed description below.

35

Brief description of the drawings

These and other aspects, features and advantages of which the invention is capable of will be apparent and elucidated from the following description of non-limiting embodiments of the present invention, reference being made to the accompanying figures, in which

5 Figure 1 is a SEM-image (2000 times enlargement) of the superhydrophobic surface obtained by spraying an ethanol solution of AKD on Whatman no. 1 filter paper as described in Example 1 herein below, clearly showing the deposited solid residue having a form of mountainous landscape with deep valleys and rounded peaks, according to an embodiment of the present invention;

10 Figure 2 is a SEM-image (2000 times enlargement) of the superhydrophobic surface obtained by spraying an *i*-propanol solution of AKD on Whatman no. 1 filter paper as described in Example 1 herein below, clearly showing the deposited solid residue having a form of mountainous landscape with deep valleys and rounded peaks, according to an embodiment of the present invention ;

15 Figure 3 is a SEM-image (2000 times enlargement) of the superhydrophobic surface obtained by spraying a methanol solution of AKD on Whatman no. 1 filter paper as described in Example 1 herein below, clearly showing the deposited solid residue having a form of mountainous landscape with deep valleys and rounded peaks, according to an embodiment of the present invention; and

20 Figure 4 is a SEM-image (2000 times enlargement) of the surface obtained by spraying a chloroform solution of AKD on Whatman no. 1 filter paper as described in Example 1 herein below, clearly differing in appearance in comparison to any of Figs. 1 to 3 by being more similar to a flat landscape than a mountainous one.

DETAILED DESCRIPTION

25 **Definitions:**

The terms "room temperature" and "ambient temperature" shall mean, unless otherwise specified, a temperature between 16 and 25°C.

30 As used herein, "roll off angle" refers to the angle which a solid flat, horizontal arranged surface has to be tilted, in relation to a horizontal plane, in order for a droplet of a given liquid and of given size, e.g. 20 µl of water, deposited on the surface to start sliding or rolling.

35 As used herein, "alkyl" used alone or as a suffix or prefix, is intended to include both branched and straight chain saturated aliphatic hydrocarbon groups having from 1 to 23 carbon atoms or if a specified number of carbon atoms is provided then that specific number is intended. For example "C1-6 alkyl" denotes alkyl having 1, 2, 3, 4, 5 or 6 carbon atoms. Examples of alkyl include, but are not limited to, methyl, ethyl, *n*-propyl, *i*-propyl, *n*-butyl, *i*-butyl, *sec*-butyl and *t*-butyl.

As used herein, "alkenyl" used alone or as a suffix or prefix, is intended to include both branched and straight chain unsaturated olefinic hydrocarbon groups having from 2 to 23 carbon atoms and from 1 to 4 double bonds that may, independently, be either *Z* or *E*. For example "C2-6 alkenyl" denotes alkenyl having 2, 3, 4, 5 or 6 carbon atoms. Examples of 5 alkenyl include, but are not limited to, vinyl, allyl and oct-4-en-2-yl.

As used herein, "fluoroalkyl" used alone or as a suffix or prefix, refers to groups in which one, two, three or more of the hydrogen(s) attached to any of the carbons of the corresponding alkyl-group are replaced by fluoro.

10 Embodiments


A superhydrophobic film, surface or material may be prepared by a method provided herein comprising two steps (i and ii). In the first step (i), a composition comprising a hydrophobic substance and a hydrophilic solvent is provided. The hydrophilic solvent may be a liquid at ambient temperature and pressure, e.g. at a temperature of 25 °C and atmospheric 15 pressure. In the second step (ii) the composition, e.g. a homogenous solution, may be sprayed towards a substrate for deposition of a solid residue onto the surface of the substrate for generation of the superhydrophobic film, surface or material. The temperature of the composition may be higher than the temperature of the substrate when carrying out the second step.

20

It was surprisingly found that hot solutions of a hydrophobic substance, e.g. alkylketenedimer (AKD) comprising long chain straight alkyl chains, in hydrophilic solvents, e.g. alcohols, such as HOC1-8 alkyl, provide superhydrophobic surfaces when sprayed onto various substrates having a lower temperature. The superhydrophobic film, surface or material 25 produced by the method disclosed herein has, on the microscopic scale, the appearance of a mountain landscape with deep valleys and rounded mountain peaks on e.g. Whatman no. 1 filter paper as substrate. Its appearance may also be described as resembling pieces of cauliflower with a flaky surface randomly placed next to each other or on top of each other, with the stem-side facing away from the viewer. Use of hydrophobic solvents, e.g. 30 chloroform, according to methods of the prior art, results in a landscape that is more flat. Furthermore, measurables indicative of superhydrophobic properties, e.g. the roll off angle, are more in line with a true superhydrophobic surface when produced by the method disclosed herein as compared to this method of the prior art.

Without being bound to any theory, the present inventor believes that the high 35 difference in solubility of the hydrophobic substance in the hydrophilic solvent when lowering the temperature is causing the hydrophobic substance to crystallize in a crystalline form which is beneficial for the formation of a superhydrophobic surface.


Without being bound to any theory, the present inventor further believes that a part of the hydrophobic substance may react with the hydrophilic solvent to form a reaction product which may exist in trace amounts or more in the final superhydrophobic surface and/or hot solution. The reaction product may thus exist in amount of 0.01 to 50 wt%, such as 5 0.1 to 10 wt% or 0.5 to 5 wt%, of the total amount of the hydrophobic substance in the composition of the invention or in the superhydrophobic film, surface or material of the invention. This reaction product may be beneficial in the formation, e.g. crystallization, of the superhydrophobic film, surface or material according to the invention. Examples of such 10 reaction products include ester (Ia) and ketone (Ib), depicted below, which may be formed by nucleophilic ring opening by an aliphatic alcohol, such as methanol, ethanol or *i*-propanol, of alkylketenedimer (AKD) of formula (I), wherein R1 and R2 may be, for example, straight chain C16 or C14 alkyl, followed by hydrolysis and decarboxylation, as depicted below. Hence, "alkyl" as depicted below may be, for example, methyl, ethyl or *i*-propyl.



Hydrophobic substances of the invention, which may be solids at 25 °C, include compounds and mixtures of compounds that are practically insoluble in water. Such 5 compounds may, for example have an aqueous solubility of less than 1 mg/L, such as less than 0.5 or less than 0.1 mg/L, at 25 °C. Examples of such hydrophobic substances include natural and synthetic waxes, natural and synthetic compounds containing long aliphatic or olefinic carbon chains, such as commercially available alkylketenedimer (AKD) or long chain carboxylic acids or amides comprising at least 18 carbon atoms, triglycerides that are solid at 10 room temperature and long chain hydrocarbons or ketones. Additional examples of hydrophobic substances of the invention include fluorinated compounds, such as any of the before mentioned substances wherein one or several hydrogen atoms, such as 1 to 10, have been replaced by fluoro.

15 Hydrophilic solvents of the invention, which may be liquids at room temperature and ambient pressure, include compounds and mixtures of compounds that are either fully miscible with water in any proportion or aliphatic alcohols comprising 1 to 8 carbon atoms.

According to one embodiment, the hydrophobic substance may be a compound of formula (I)




20 R1 and R2 of a compound of formula (I) may be independently selected from C12-22 alkyl, such as C14 or C16 alkyl, and C12-22 fluoroalkyl. The stereochemistry of the double bond connecting R1 to the four membered ring of a compound of formula (I) may be E or Z.

25 According to one embodiment, the hydrophobic substance may be a mixture of compounds of formula (I). In such a mixture, R1 and R2 of one of the compounds of formula (I) may be straight chain C14 alkyl and R1 and R2 of another may be straight chain C16 alkyl. The former may constitute 30 to 40 wt%, such as 35 wt%, or less than 11 wt%, such as 1 to 10 wt%, of the mixture. The latter may constitute 60 to 70 wt%, such as 65 wt%, or more than 30 89 wt%, such as 90 to 99 wt%, of the mixture.

According to one embodiment, the hydrophobic substance may be a mixture of compounds of formula (I). In such a mixture, R1 may be straight chain C14 alkyl or straight chain C16 alkyl and R2 may be straight chain C14 alkyl or straight chain C16 alkyl. The ratio between the straight chain C14 alkyl and the straight chain C16 alkyl groups may be in the 5 range from 5:95 to 4:6.

According to one embodiment, the hydrophobic substance may be AKD derived from stearic acid or palmitic acid, i.e. the products obtained upon condensation of two molecules of stearic acid or palmitic acid, or one molecule stearic acid and one molecule palmitic acid, with elimination of two molecules of water. Such AKD derivatives are readily 10 available from commercial sources.

According to one embodiment, the hydrophobic substance may be a compound of formula (II)



15 R1 may be C12-22 alkyl or C12-22 fluoroalkyl. R3 may be selected from OH, NH₂, OC1-8 alkyl, OC1-8 fluoroalkyl, NHC1-8 alkyl, NHC1-8 fluoroalkyl and OCH₂CHR₄CH₂R₅. R4 and R5 may be independently selected from O(CO)C13-23 alkyl, O(CO)C13-23 fluoroalkyl and O(CO)C13-23 alkenyl.

20 According to one embodiment, the hydrophobic substance may be a mixture of a compound of formula (I) and a compound of formula (II).

According to one embodiment, the hydrophobic substance may be a mixture of a compound of formula (I) and a compound of formula (II).

25 According to one embodiment, the hydrophilic solvent may have a boiling point in the range from 50 to 150 °C, such as 65 to 100 °C. Advantages of a hydrophilic solvents with a relatively high boiling point include the possibility to dissolve a relatively large amount of the hydrophobic compound in a relatively small volume of the hydrophilic solvent by heating the composition to a temperature slightly below the boiling point without the need for pressurized containers. The amount of solvent needed is thus minimized, which results in a minimized cost and environmental impact. Advantages of hydrophilic solvents with a 30 relatively low boiling point include an effective vaporization of the solvent upon spraying of the composition of the invention towards a substrate. Hence, the solid residue constituting the superhydrophobic film, surface or material of the invention may be formed more rapidly as compared to the case when another solvent with a higher boiling point is used at the same temperature. The choice of solvent with a specific boiling point is dependent on e.g. the type 35 of application and the temperature of the substrate, as well understood by the one skilled in

the art. Other factors of importance for the choice of solvent include the level of acceptable toxicity and the time available for production of the superhydrophobic film, surface or material according to the invention in a specific application. The one skilled in the art is well capable of taking these and other factors into account to selecting a suitable solvent for a 5 specific application. Even if the composition is heated to a temperature slightly above the boiling point in the method disclosed herein, whereby a container that withstands a slight positive pressure may be needed, this type of container is simpler and less expensive as compared to containers of the prior art that contains supercritical fluids.

According to one embodiment, the hydrophilic solvent may be an alcohol of the 10 generic formula $\text{HOC}_1\text{-}8\text{ alkyl}$, i.e. an aliphatic alcohol with 1 to 8 carbon atoms.

According to one embodiment, the hydrophilic solvent may be an alcohol that is 15 fully miscible with water, such as methanol, ethanol, *i*-propanol and *n*-propanol. Advantages of using a hydrophilic solvent which is fully miscible with water include facile removal of condensed solvent residues near the treated substrate by simple cleaning with water. Another 15 advantage includes the facile recycling of the hydrophobic substance in unused composition of the invention by addition of water until precipitation of the hydrophobic substance.

According to one embodiment, the hydrophilic solvent may be an alcohol that has a 20 solubility in water which is greater than about 5 g/ml water, such as methanol, ethanol, *i*-propanol, *n*-propanol, 1-butanol and 2-butanol.

According to one embodiment, the hydrophilic solvent may have a capability to 25 dissolve more than 100 mg/ml, such as more than 150, 200, 250 or 300 mg/ml, of the hydrophobic substance at a temperature near the boiling point (at atmospheric pressure) of the solvent, such as in a range from about 10 °C below the boiling point to about 10 °C above the boiling point. In the latter case, a container that withstands a slight positive pressure may be used to contain the composition when carrying out the method disclosed herein to prevent the solvent from boiling.

According to one embodiment, the solubility of the hydrophobic substance in the 30 hydrophilic solvent may be less than 30 mg/ml, such as less than 20, 10, 5, 1, 0.5, 0.1 or 0.05 mg/ml, at the temperature of the substrate, e.g. from -30 to 30 °C, such as 25 °C, treated by the method disclosed herein. The solubility of the hydrophobic substance in the hydrophilic 35 solvent may be more than 200 mg/ml, such as more than 250, 300 or 400 mg/ml, at a temperature within 10 °C from the boiling point of the hydrophilic solvent at atmospheric pressure, e.g. from 50 to 150 °C, such as from 50 to 100 °C or from 50 to 60 °C, e.g. 55 °C. The use of a hydrophilic solvent to dissolve a hydrophobic substance according to the method disclosed herein maximizes the difference in solubility of the latter in the former as dependant on the temperature. For example, the solubility of the hydrophobic substance in the hydrophilic solvent may be less than 30 mg/ml at a temperature of 25 °C or less, and more than 200 mg/ml at a temperature of 55 °C or more. Advantageously, the solvent volume may

thus be minimized by the method according to the invention. For example, use of supercritical CO₂ to dissolve AKD according to a method of the prior art typically requires more than 300 L of pressurized CO₂ to produce a superhydrophobic surface comprising 1 kg of AKD. In comparison, when using the method according to the invention, the volume of hydrophilic solvent, e.g. ethanol, needed to produce a comparable superhydrophobic film is less than 5 L.

According to one embodiment, 30 wt% or less, such as less than 25, 20, 15, 10, 5 or 3 wt%, of the hydrophobic substance of the composition of the invention may exist in a dissolved state at a temperature of the composition from less than -30 to 40 °C, such as 15 to 30 or about 25 °C. The other part of the hydrophobic substance may exist in a solid state without being dissolved in the hydrophilic solvent. For example, the hydrophobic substance may be fully dissolved in the hydrophilic solvent at a temperature of the composition which is in the range from e.g. 70 to 80 °C. At the same time, less than 30 wt% of the hydrophobic substance may be dissolved at a temperature of the composition which is about 25 °C. The composition of this example may be used in the method according to the invention. Hence, the hot (70 to 80 °C) composition, in which the hydrophobic substance is fully dissolved, may be sprayed towards a substrate which has a temperature of about 25 °C, according to the method of the invention.

According to one embodiment, the melting point of the hydrophobic substance is at least 10 °C, such as at least 15, 20, 25, 30, 40 or 50 °C, higher than the temperature of the substrate, when carrying out the method of the invention.

According to one embodiment, 90 wt% or more, such as more than 95 or preferably 100 wt%, of the hydrophobic substance of the composition of the invention exists in a dissolved state at a temperature near the boiling point at ambient pressure of the hydrophilic solvent, such as in a range from about 10 °C below the boiling point to about 10 °C above the boiling point, such as a temperature of 40 to 100 °C.

According to one embodiment, the hydrophilic solvent may consist of a mixture of two or more hydrophobic solvents mentioned in embodiments herein. The boiling point of the solvent may thus be tuned to be optimal for the particular application by e.g. formation of various azeotropic mixtures, as well known in the art. The properties of the hydrophilic solvent with regard to its ability to dissolve the hydrophobic substance at different temperatures may also be tuned by employment of such mixtures to be optimal for a particular application and hydrophobic substance, as well known in the art.

According to one embodiment, the composition may be used in the method disclosed herein at a temperature above the boiling point, such as 5 to 20 °C above the boiling point at atmospheric pressure, of the hydrophilic solvent. The composition may then be held in a container capable of withstanding a slight to medium positive pressure, as well known in the art. Advantageously, such positive pressure may be used to press the composition via e.g. a

nozzle when spraying it towards the substrate without the need for other additional means, such as a pump, to accomplish a stream of spray of the composition.

According to one embodiment, the substrate and its immediate surrounding atmosphere may be at least 5 °C colder than the temperature of the composition when carrying out the method according to the invention. Hence, the difference between the temperature of the liquid composition of the invention and the temperature of the substrate may be at least 5°C. A typical temperature difference may be in the range from 30 to 100 °C, such as 35 to 45 °C. A substrate which is colder than the composition facilitates the deposition of the hydrophobic substance and thus the formation of a superhydrophobic film, surface or material.

According to one embodiment, the superhydrophobic film, surface or material produced by the method disclosed may have a density of less than 2 g/cm², such as less than 1, 0.5, 0.1, 0.05 or 0.01 g/cm², of the hydrophobic substance at the treated area of the substrate, i.e. at the area of the deposited residue comprising the hydrophobic substance.

According to one embodiment, the superhydrophobic film, surface or material produced by the method of the invention may display a contact angle in the range from 140 to 180 °, such as from 150 to 180 ° or 155 to 180 °, and a roll off angle in the range from 0.01 to 48 °, such as from 1 to 10 ° or 1 to 5 °.

According to one embodiment, the superhydrophobic film, surface or material produced by the method of the invention may display a contact angle in the range 100 to 180 °, 110 to 180 °, 120 to 180 °, 130 to 180 °, 140 to 180 °, 150 to 180 °, 160 to 180 ° or 170 to 180 °.

According to one embodiment, the substrate treated by the method of the invention may be selected from the group consisting of paper, wood, cellulose, textile, metal, ceramic, glass, rubber, stone, marble, plastic, silica, carbon tape and paint.

According to one embodiment, the method disclosed herein may be used for making a paper or wood surface water repellent.

According to one embodiment, the composition of the invention may comprise an alcohol as the hydrophilic solvent of the formula HOC1-8 alkyl, such as methanol, ethanol, *i*-propanol, *n*-propanol or mixtures thereof, and AKD of formula (I), wherein R1 and R2 may be independently C14 or C16 straight chain alkyl, at a concentration of at least 1 mg/ml, at least 10 mg/ml, at least 50 mg/ml, at least 100 mg/ml or at least 200 mg/ml, such as at least 250 mg/ml. Such a composition may be useful for production of a superhydrophobic film, surface or material by the method of the invention. The composition may be heated to a suitable temperature, such as just below the boiling point of the solvent, to dissolve all of the AKD. The composition may then be sprayed by suitable means known in the art towards the substrate. Such means include, for example, commercially available spraying devices normally used for spray painting and containers with integrated nozzles well known in the art.

A longer spraying time may be needed when the concentration of AKD in the composition is relatively low, such as 10 mg/ml, as compared to a relatively high concentration of AKD, such as 250 mg/ml, in order to obtain a comparable superhydrophobic film, surface or material.

5 According to one embodiment, substrates that may be treated by the method of the invention include, for example, electronic circuit boards, electronic devices, roofing tiles, outdoor wall panel (e.g. bricks, wood, painted wood), boat hull, various parts of aircrafts (e.g. the wings), clothes, shoes, boots and tents. The substrate may be made of, for example, paper, plastic, glass, metal, wood, cellulose, silica, carbon tape, textile or paint.

10

Although the present invention has been described above with reference to specific illustrative embodiments, it is not intended to be limited to the specific form set forth herein. Any combination of the above mentioned embodiments should be appreciated as being within the scope of the invention. Rather, the invention is limited only by the accompanying claims 15 and other embodiments than the specific above are equally possible within the scope of these appended claims.

Examples

20

General Methods

All materials were obtained from commercial sources and were used without further purification unless otherwise noted. AKD granules (DR SF 300) comprising a mixture of >90% of C18-AKD and <10% of C16-AKD with a melting point of ~ 62°C, were obtained from EKA Chemicals (Bohus, Sweden).

25

Contact angles were measured to study the properties of the, by the method according to the invention or other methods for comparison, obtained hydrophobic film, surface or material with the aid of a semi-automatic CAM200 contact angle system (KSV Instruments Ltd., Helsinki, Finland). This system comprises a video camera which rapidly records live pictures of a water droplet over time. The volume of the water droplet for each measurement 30 was kept at 5 μ L. For each measurement, three individual spots of droplets were measured for three minutes. Contact angles were calculated from the generated images with the integrated software (CAM software) utilizing the Young–Laplace method.

35

Roll off angles were measured with a digital angle meter from MARKTOP® tools for domestic construction work. Flat planar substrates, treated by the method according to the invention or other methods for comparison, were attached to the digital angle meter by tape, adhesive on both sides. A 20 μ l droplet was applied to the surface. The lever of the digital angle meter was then raised slowly until the droplet moved whereby the roll off angle was determined.

A hobby airbrush device for painting e.g. scaled model aircrafts was used for spraying.

Solutions of hydrophobic substances, e.g. AKD granules (DR SF 300), in various solvents were prepared by mixing the hydrophobic substance in the solvent at room temperature, followed by heating to ~74 °C for about 30 min.

5

Below follows non-limiting examples on the production of a superhydrophobic film, surface or material according the invention.

Example 1

10 **Comparison between the use of hydrophilic solvents and chloroform as an example of a hydrophobic solvent**

A hot (~74 °C) solution (250 mg AKD/ml solvent), prepared as described above, of AKD granules (DR SF 300) in a hydrophilic or hydrophobic solvent were sprayed towards a substrate of Whatman 1 paper having a surface area of 104 cm². The spraying was done from 15 a distance of about 30 cm from the paper surface for about 17 seconds. The stream of spray was moved over the paper in a way commonly employed for spray painting of surfaces, i.e. first in a continuous S-shaped movement from top to bottom, followed by the same type of movement from side to side. The substrate and its surrounding atmosphere had a temperature of about 25 °C. Contact angels, roll off angels and the amount of AKD deposited on the 20 substrate were measured for the use of various solvents as depicted in the table below:

Solvent	Contact angle (°)	Roll off angle (°)	Amount deposited AKD (mg)
Chloroform	151,7	48,075	572,3
Methanol (kept in a sealed container)	159,8	3,95	537,3
Ethanol	162,4	4,575	538,5
<i>i</i> -Propanol	164,9	2,375	545,6

Example 2

25 **Treatment of various substrates by the method according to the invention**

A hot (~74 °C) solution (250 mg AKD/ml ethanol), prepared as described above, of AKD granules (DR SF 300) in ethanol was sprayed towards various substrates until the surface was covered by a deposit of AKD as determined visually. Additional experimental conditions used were the same as those used in example 1. Contact angels and roll off angels 30 were measured for the various treated substrates as depicted in the table below:

Substrate	Contact angle (°)	Roll off angle (°)
Glass (Microscope Slides)	165,6	4,175
Aluminium sheet	157	6,4
Rough aluminium sheet surface (made rough with a P120 sand paper)	168	5,05
Polypropylene surface	152,1	2,725
Rough polypropylene surface Polyethylene surface (Hard plastic surface)	162,9	2,725
Polyethylene surface (Hard plastic surface)	155,3	2
Rough polyethylene surface (Hard plastic surface) (made rough with a P120 sand paper)	158,2	3,5
Sawn timber (Pine; rough surface)	145,4	4,45
Wood veneer (Birch; smooth surface)	164	4,725
Natural rubber (Smooth surface; back side of IKEA Patrull, shower mat)	156,6	4,1
Natural rubber (rough surface; the front side of IKEA Patrull, shower mat)	156	7,8
Corrugated fibreboard (Smooth surface)	155,2	2,05

5 In the claims, the term “comprises/comprising” does not exclude the presence of other species or steps. Additionally, although individual features may be included in different claims, these may possibly advantageously be combined, and the inclusion in different claims does not imply that a combination of features is not feasible and/or advantageous. In addition, singular references do not exclude a plurality. The terms “a”, “an”, “first”, “second” etc do
10 not preclude a plurality.

CLAIMS

1. A method for the production of a superhydrophobic film, surface or material comprising the steps of:


5 (i) providing a composition comprising a hydrophobic substance and a hydrophilic solvent, said hydrophilic solvent being a liquid at a temperature of 25 °C and atmospheric pressure; and


(ii) spraying said composition towards a substrate for deposition of a solid residue onto the surface of said substrate for generation of said superhydrophobic film, surface or material; wherein

10 the temperature of said composition is higher than the temperature of said substrate when carrying out step (ii).

2. The method according to claim 1, wherein said hydrophobic substance is a compound of formula (I) or (II),

15

R1 
(I)

R1 
(II)

or a mixture of a compound of formula (I) and a compound of formula (II), wherein

20 R1 and R2 are independently selected from C12-22 alkyl and C12-22 fluoroalkyl; and R3 is selected from OH, NH₂, OC1-8 alkyl, OC1-8 fluoroalkyl, NHC1-8 alkyl, NHC1-8 fluoroalkyl and OCH₂CHR₄CH₂R₅, said R4 and R5 being independently selected from O(CO)C13-23 alkyl, O(CO)C13-23 fluoroalkyl and O(CO)C13-23 alkenyl.


25 3. The method according to claim 1, wherein said hydrophobic substance is alkylketenediimide derived from stearic acid, palmitic acid or a mixture of stearic acid and palmitic acid.

4. The method according to any one of the preceding claims, wherein said hydrophilic solvent has a boiling point in the range of 50 to 150°C.

30 5. The method according to any one of claims 1 to 3, wherein said hydrophilic solvent is HOC1-8 alkyl.

6. The method according to claim 5, wherein said hydrophilic solvent is methanol, ethanol, *i*-propanol, or any mixture thereof.
7. The method according to any one of the preceding claims, wherein
 - 5 -at least 10% of said hydrophobic substance exists in a solid state when said composition is kept at a temperature of 25°C or less for at least 1h; and
 - at least 90% of said hydrophobic substance is dissolved in said hydrophilic solvent when said composition is kept at a temperature of 55°C or more for at least 1h.
- 10 8. The method according to any one of claims 1 to 6, wherein the solubility of said hydrophobic substance in said hydrophilic solvent is less than 30 mg/ml at a temperature of 25 °C or less, and more than 200 mg/ml at a temperature of 55°C or more.
- 15 9. The method according to any one of the preceding claims, wherein said substrate is selected from the group consisting of paper, wood, cellulose, textile, metal, ceramic, glass, rubber, stone, marble, plastic, silica, carbon tape and paint.
10. A superhydrophobic film, surface or material obtainable by a method according to any one of claims 1 to 9.
- 20 11. The superhydrophobic film, surface or material according to claim 10, wherein said hydrophobic substance has a weight of less than 2 g/cm² of the surface area of the deposited residue comprising said hydrophobic substance.
- 25 12. A substrate comprising a superhydrophobic film, surface or material according to claims 10 or 11.
13. A composition comprising alkylketenedimer and HOC1-8 alkyl or a mixture of different HOC1-8 alkyls, wherein
 - 30 - the concentration of said alkylketenedimer in said composition is at least 1 mg/ml; for use in the production of a superhydrophobic film, surface or material.
14. The composition according to claim 13, wherein said alkylketenedimer is a compound of formula (I),

35



wherein R1 and R2 are independently selected from C12-22 alkyl.

5 15. Use of a composition according to claims 13 or 14 for the production of a superhydrophobic film, surface or material.




FIG. 1




FIG. 2




FIG. 3




FIG. 4

INTERNATIONAL SEARCH REPORT

International application No.
PCT/SE2011/051532

A. CLASSIFICATION OF SUBJECT MATTER

IPC: see extra sheet

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC: B05D, C09K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE, DK, FI, NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, PAJ, WPI data, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	Torkkeli A., Saarilahti J., Haara A. Electrostatic transportation of water droplets on superhydrophobic surfaces (2001) Proceedings of the IEEE Micro Electro Mechanical Systems (MEMS), pp. 475-478.; whole document --	1-15
A	WO 02090653 A2 (AKZO NOBEL NV ET AL), 14 November 2002 (2002-11-14); See Example 1 -- -----	1-15



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents:	“T” later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
“A” document defining the general state of the art which is not considered to be of particular relevance	“X” document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
“E” earlier application or patent but published on or after the international filing date	“Y” document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
“L” document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	“&” document member of the same patent family
“O” document referring to an oral disclosure, use, exhibition or other means	
“P” document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search
31-01-2012

Date of mailing of the international search report
20-02-2012

Name and mailing address of the ISA/SE
Patent- och registreringsverket
Box 5055
S-102 42 STOCKHOLM
Facsimile No. + 46 8 666 02 86

Authorized officer
Carolina Gomez Lagerlöf
Telephone No. + 46 8 782 25 00

Continuation of: second sheet

International Patent Classification (IPC)

B05D 5/08 (2006.01)

B05D 1/02 (2006.01)

C09K 3/18 (2006.01)

Download your patent documents at www.prv.se

The cited patent documents can be downloaded:

- From "Cited documents" found under our online services at www.prv.se
(English version)
- From "Anförläda dokument" found under "e-tjänster" at www.prv.se
(Swedish version)

Use the application number as username. The password is **XLFTJEBFJT**.

Paper copies can be ordered at a cost of 50 SEK per copy from PRV InterPat (telephone number 08-782 28 85).

Cited literature, if any, will be enclosed in paper form.

INTERNATIONAL SEARCH REPORT
Information on patent family members

International application No.
PCT/SE2011/051532

WO	02090653 A2	14/11/2002	AU	2002258324 B2	14/10/2004
			BR	0209519 A	13/07/2004
			CA	2446338 A1	14/11/2002
			CN	1279244 C	11/10/2006
			CN	1507520 A	23/06/2004
			JP	2004526072 A	26/08/2004
			RU	2003135626 A	20/03/2005
			RU	2260026 C2	10/09/2005