




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08G 59/42, 59/14, 63/676, G02B 1/04		A1	(11) International Publication Number: WO 98/17704
			(43) International Publication Date: 30 April 1998 (30.04.98)
(21) International Application Number: PCT/EP97/05738	(22) International Filing Date: 17 October 1997 (17.10.97)		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).
(30) Priority Data: 96810700.3 21 October 1996 (21.10.96) EP (34) Countries for which the regional or international application was filed: DE et al.			
(71) Applicant (for all designated States except US): NOVARTIS AG [CH/CH]; Schwarzwaldallee 215, CH-4058 Basel (CH).	(72) Inventor; and	Published	With international search report.
(75) Inventor/Applicant (for US only): STEINMANN, Bettina [CH/CH]; Les Russilles, CH-1724 Praroman (CH).	(74) Agent: ROTH, Bernhard, M.; Novartis AG, Patent- und Markenabteilung, Lichtstrasse 35, CH-4002 Basel (CH).		Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.

(54) Title: CROSSLINKABLE POLYMERS



(57) Abstract

The invention relates to novel crosslinkable prepolymers comprising structural units of formula (1) wherein the variables are as defined in the claims, to crosslinked polymers, to either homo-polymers or co-polymers prepared from those novel prepolymers, to mouldings produced from the said homo- or co-polymers, and especially to contact lenses produced from those homo- or co-polymers.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Crosslinkable polymers


The present invention relates to novel water-soluble block copolymers comprising polyoxy-alkylene units and having crosslinkable side groups, to processes for their preparation, and to their use in the production of mouldings, especially contact lenses.

Polymers comprising polyalkylene oxide and having polymerisable end groups and their use in the production of contact lenses are already known, for example from EP-A-273 763.


Furthermore, there are known, for example from A. Kameyama *et al.* Macromol. **25**, 2307 (1992), H. Itoh *et al.* Macromol. **28**, 883 (1995) or H. Itoh *et al.* J. Pol. Sci. A, Pol. Chem. **34**, 217 (1996), polyesters having chloromethyl side groups, polymers derived therefrom that have side groups comprising carboxy groups, and polyesters having vinyl ether side groups.

Surprisingly, novel crosslinkable polyether-polyester copolymers have now been found, which are suitable especially for the production of contact lenses.




The present invention relates to prepolymers comprising structural units of the formula



wherein R is a radical



- 2 -



Z is straight-chained or branched C₁-C₁₂alkylene or unsubstituted or C₁-C₄alkyl- or C₁-C₄-alkoxy-substituted phenylene or C₇-C₁₂aralkylene,

x and t are each independently of the other the number 0 or 1,

R₅ is hydrogen, C₁-C₄alkyl or halogen,


R₆ is hydrogen, C₁-C₄alkyl, phenyl, carboxy or halogen,

R₇ is hydrogen when R₆ is phenyl or carboxy, or is hydrogen or carboxy when R₆ is hydrogen, C₁-C₄alkyl or halogen,

R₈ is a C₂-C₁₂alkylene radical, a phenylene radical or a C₇-C₁₂aralkylene radical,


R₉ and R_{9'} are each independently of the other hydrogen, C₁-C₄alkyl or halogen,

R₁ is a radical of the formula



or an alkylene radical having up to 20 carbon atoms which may be interrupted by one or more ester, urethane or ureido groups and/or may be substituted by hydroxy; or a cycloalkylene radical having from 6 to 20 carbon atoms; or an arylene radical having from 6 to 20 carbon atoms; or an arylenealkylene, alkylenearylene, alkylenearylenealkylene or arylene-alkylenearylene radical,

R₂ is a radical of the formula



or an alkylene radical having up to 20 carbon atoms which may be interrupted by one or more ester, urethane or ureido groups and/or may be substituted by hydroxy; or a cycloalkylene radical having from 6 to 20 carbon atoms; or an arylene radical having from 6 to 20 carbon atoms; or an arylenealkylene, alkylenearylene, alkylenearylenealkylene or arylene-alkylenearylene radical,

R', R" and R* are each independently of the others hydrogen or C₁-C₄alkyl,
R₃ is an alkylene radical having up to 20 carbon atoms; or a cycloalkylene radical having from 6 to 20 carbon atoms; or an arylene radical having from 6 to 20 carbon atoms, and n, m, p and q are each independently of the others a number from 1 to 30, with the proviso that at least one of the radicals R₁ and R₂ is a radical of formula (3a), (3b), (4) or (5).

Z as an alkylene radical is preferably linear or branched C₁-C₈alkylene, especially linear C₁-C₄alkylene and more especially linear C₁-C₂alkylene. In a preferred embodiment of the invention, Z is methylene.

Z as a phenylene radical is, for example, unsubstituted or methyl- or methoxy-substituted 1,2-, 1,3- or 1,4-phenylene. Z as a phenylene radical is preferably 1,3- or 1,4-phenylene.

Z as an aralkylene radical is, for example, unsubstituted or methyl- or methoxy-substituted benzylene, the methylene group in each case being bonded to the amine nitrogen. Z as an aralkylene radical is preferably the 1,3- or 1,4-phenylenemethylene radical, the methylene group in each case being bonded to the amine nitrogen -NH-.

Z is preferably unsubstituted or methyl- or methoxy-substituted phenylene or phenylene-methylene or C₁-C₈alkylene, especially 1,3- or 1,4-phenylene or C₁-C₄alkylene, more especially C₁-C₂alkylene and most especially methylene.

x is preferably the number 0. t is preferably the number 1.

R₅ is preferably hydrogen, C₁-C₄alkyl or chlorine, especially hydrogen or C₁-C₄alkyl, more especially hydrogen, methyl or ethyl and most especially hydrogen or methyl.

- 4 -

R₆ is preferably hydrogen, methyl or phenyl and especially hydrogen.

R₇ is preferably hydrogen.

R₈ is preferably a C₂-C₆alkylene radical or a 1,3- or 1,4-phenylene radical, especially a C₂-C₃alkylene radical. R₉ and R_{9'} are each independently of the other preferably hydrogen, methyl or chlorine. R₉ and R_{9'} are each independently of the other especially hydrogen or methyl.


Each of R', R" and R* as C₁-C₄alkyl is preferably methyl or ethyl and especially methyl.

R' and R" are each independently of the other preferably hydrogen, methyl or ethyl and especially hydrogen or methyl.

R* is especially hydrogen or methyl and more especially hydrogen.

m is preferably a number from 1 to 6 and especially a number from 1 to 4. q is, for example, a number from 1 to 6, preferably a number from 2 to 4 and especially the number 2.

R in formula (1) is preferably a radical of the formula



wherein the variables contained therein each have the meanings and preferred meanings indicated above.

In an especially preferred embodiment of the invention, R in formula (1) is a radical of formula (2a') indicated above wherein R₅ is hydrogen or methyl.


In formulae (3a) and (3b), n is, for example, a number from 5 to 30, advantageously from 5 to 25, preferably from 8 to 25 and especially from 10 to 25.

When R₁ is an alkylene radical it is, for example, straight-chained or branched C₁-C₂₀-alkylene which is unsubstituted or substituted, for example by hydroxy, and/or, with the exception of methylene, may be interrupted by one or more groups -COO-, -OCO-,


- 5 -

-NHCO-O-, -OCONH- or -NHCONH-. R_1 as an alkylene radical is preferably unsubstituted or hydroxy-substituted C_1 - C_{20} alkylene, especially unsubstituted C_1 - C_{12} alkylene and more especially unsubstituted C_1 - C_6 alkylene. Examples of alkylene radicals R_1 that are very especially preferred are methylene, 1,2-ethylene, 1,3-propylene and 1,4-butylene.

R_1 as cycloalkylene is, for example, 1,2-, 1,3- or 1,4-cyclohexylene which may be substituted by C_1 - C_4 alkylene, or is a radical of the formula




R_1 as arylene is, for example, 1,2-, 1,3- or 1,4-phenylene which is unsubstituted or is substituted by C_1 - C_4 alkyl, C_1 - C_4 alkoxy or by halogen, or is a radical of the formula



wherein B is, for example, a group -O-, -NH-, -OCO-, -CONH- or -NHCONH-. R_1 as arylene is preferably 1,2-, 1,3- or 1,4-phenylene.


R_1 as arylenealkylene, alkylenearylene or alkylenearylenealkylene is, for example, a radical $-C_6H_5-C_1-C_4$ alkylene-, $-C_1-C_4$ alkylene- C_6H_5- or $-C_1-C_4$ alkylene- $C_6H_5-C_1-C_4$ alkylene, preferably the radical $-C_6H_5-CH_2-$, $-CH_2-C_6H_5-$ or $-CH_2-C_6H_5-CH_2-$.

R_1 as arylenealkylenearylene is, for example, a radical of the formula



wherein B_1 is straight-chained or branched C_1 - C_6 alkylene which is unsubstituted or is substituted by hydroxy, preferably straight-chained or branched C_1 - C_4 alkylene. Examples of suitable radicals B_1 are $-CH_2-$, $-C(CH_3)_2-$ and $-CH_2-CH_2-$.

R_1 is advantageously a radical of formula (3a) or (3b) indicated above, or C_1 - C_{20} alkylene, 1,2-, 1,3- or 1,4-phenylene or a radical of the formula



wherein B_1 is straight-chained or branched C_1 - C_4 alkylene.

R_1 is preferably a radical of formula (3a) indicated above, or C_1 - C_{20} alkylene, especially a radical of formula (3a) indicated above wherein n is a number from 5 to 25 and R'' is hydrogen or methyl, or C_1 - C_{12} alkylene, and more especially a radical of formula (3a) indicated above wherein n is a number from 8 to 25 and R'' is hydrogen or methyl, or C_1 - C_6 -alkylene.

In formulae (4) and (5), p is preferably a number from 5 to 25, especially from 8 to 25 and more especially from 10 to 25.


R_3 as an alkylene radical is preferably straight-chained or branched C_1 - C_{12} alkylene, especially straight-chained or branched C_1 - C_6 alkylene and more especially straight-chained or branched C_1 - C_4 alkylene. Examples of alkylene radicals R_4 that are very especially preferred are methylene, 1,2-ethylene, 1,3-propylene and 1,4-butylene.

When R_3 is a cycloalkylene or arylene radical, the definitions and preferred meanings mentioned above for R_2 apply independently.

R_3 is preferably a straight-chained C_1 - C_4 alkylene radical.

When R_2 is an alkylene, cycloalkylene, arylene, arylenealkylene, alkylenearylene, alkylene-arylenealkylene or arylenealkylenearylene radical, the definitions and preferred meanings given above for R_1 apply independently.

R_2 is preferably a radical of formula (4) or (5) indicated above, or C_1 - C_{20} alkylene, 1,2-, 1,3- or 1,4-phenylene or a radical of the formula



wherein B_1 is straight-chained or branched C_1 - C_4 alkylene.


R_2 is especially a radical of formula (4) indicated above, or C_1 - C_{20} alkylene, more especially a radical of formula (4) indicated above wherein p is a number from 5 to 25 and R^* is hydrogen or methyl, or C_1 - C_{12} alkylene, and most especially a radical of formula (4) indicated above wherein p is a number from 8 to 25 and R'' is hydrogen, or C_1 - C_6 alkylene.

A preferred embodiment of the present invention relates to prepolymers comprising structural units of formula (1) indicated above wherein R_1 is a radical of formula (3a) indicated above and R_2 is a C_1 - C_{20} alkylene radical. Special preference is given to such polymers in which R_1 is a radical of formula (3a) indicated above wherein n is a number from 5 to 25 and R'' is hydrogen or methyl, and R_2 is C_1 - C_6 alkylene.

Another preferred embodiment of the present invention relates to prepolymers comprising structural units of formula (1) indicated above wherein R_1 is a C_1 - C_{20} alkylene radical and R_2 is a radical of formula (4) indicated above. Special preference is given to such polymers in which R_1 is C_1 - C_6 alkylene and R_2 is a radical of formula (4) indicated above wherein p is a number from 5 to 25 and R^* is hydrogen.

Another preferred embodiment of the present invention relates to prepolymers comprising structural units of formula (1) indicated above wherein the above-mentioned definitions and preferred meanings apply to each of R_1 and R_2 , and R is the acrylate or methacrylate radical $-O(O)C-CH=CH_2$ or $-O(O)C-C(CH_3)=CH_2$.

In addition to the structural units of formula (1) mentioned above, the prepolymers of the invention may comprise, for example, structural units of the formula



wherein R_0 is halogen or a radical $-O-(O)C-R_4$ and R_4 is C_1 - C_{20} alkyl, C_6 - C_{20} cycloalkylene, C_6 - C_{20} arylene or C_7 - C_{12} aralkylene.

When R_0 is halogen, it may be, for example, fluorine, bromine, iodine or, especially, chlorine.

R_4 as alkyl is, for example, a straight-chained or branched C_1 - C_{20} alkyl radical which is unsubstituted or is substituted by hydroxy, preferably a straight-chained or branched C_1 - C_{12} alkyl radical and especially a straight-chained or branched C_1 - C_6 alkyl radical. Examples are methyl, ethyl, n- or iso-propyl, n-, iso-, sec- or tert-butyl or straight-chained or branched pentyl or hexyl and, especially, methyl or ethyl.

R_4 as cycloalkyl is, for example, unsubstituted or C_1 - C_4 alkyl-substituted cyclohexyl, preferably cyclohexyl which is unsubstituted or is substituted by from 1 to 3 methyl groups, and especially unsubstituted cyclohexyl.

R_4 as aryl is, for example, phenyl which is unsubstituted or is substituted by halogen, hydroxy, carboxy, C_1 - C_4 alkyl or by C_1 - C_4 alkoxy, preferably phenyl which is unsubstituted or is substituted by chlorine, methyl, methoxy or by carboxy, and especially unsubstituted phenyl.

R_4 as aralkyl is, for example, phenylmethyl or phenylethyl.

R_4 is preferably C_1 - C_{12} alkyl, cyclohexyl which is unsubstituted or is substituted by from 1 to 3 methyl groups, phenyl which is unsubstituted or is substituted by chlorine, methyl, methoxy or by carboxy, or phenylmethyl or phenylethyl.


R_4 is especially C_1 - C_6 alkyl, cyclohexyl or phenyl.

Preferred constituents of the prepolymers of the invention are those units of formula (1a) wherein R_0 is chlorine or a radical $-O-(O)C-R_4$ and R_4 is C_1 - C_6 alkyl, cyclohexyl or phenyl.

The crosslinkable prepolymers of the invention comprise, for example, from 100 to 60 mol. % of units of formula (1) and from 0 to 40 mol. % of units of formula (1a). Preference is given to such polymers that comprise from 100 to 80 mol. % of units of formula (1) and from 0 to 20 mol. % of units of formula (1a).


The crosslinkable prepolymers of the invention can be prepared, for example, by

(a) polymerising a compound of the formula



(6)


with a compound of the formula



(7)

in the presence of a catalyst, and

(b) reacting the polymer obtainable according to (a), which comprises structural units of the formula



with a compound of the formula



(8)

in the presence of a base, R_1 and R_2 each being as defined above, X being halogen, preferably chlorine, and R being a radical of formula (2a), (2c), (2d) or (2b) indicated above wherein t is the number 1.

The compounds of formula (1) wherein R is a radical of formula (2b) and t is the number 0 can be obtained, for example, by converting a polymer of formula (1a) prepared in the manner described above into a corresponding polymer wherein X is hydroxy and reacting the latter with an isocyanate of the formula $O=C=N-(CH_2)_q-O-(O)C-CHR'=CH_2$ wherein R' and q are as defined above.

The reaction of the diacid dihalide with the diglycidyl compound to form a polyester according to step (a) is known *per se* and can be carried out by methods known *per se*. The reaction of the acid dihalide with the diglycidyl compound is usually carried out in an inert solvent, for example in a higher-boiling alkane or alkane mixture, such as petroleum ether, in a xylene mixture or in toluene, at elevated temperature, for example at from 30 to 120°C,

- 10 -


preferably from 40 to 100°C and especially from 60 to 100°C, in the presence of a basic catalyst.

Suitable catalysts are, for example, crown ether complexes, pyridine, quaternary phosphonium salts, tertiary amines or, preferably, quaternary ammonium salts. Examples of suitable catalysts are pyridine, tri-C₁-C₄alkylamines, especially tributylamine, and tetra-C₁-C₄alkylammonium halides, especially tetrabutylammonium halides, such as tetrabutylammonium chloride, tetrabutylammonium iodide or, especially, tetrabutylammonium bromide.

The catalyst is used in the polymerisation reaction, for example, in a molar ratio of from 1:10 to 1:50, preferably from 1:15 to 1:30 and especially of about 1:20, in each case based on the diacid dihalide. The molar ratio of diglycidyl compound to diacid dihalide can vary, for example, from 0.5:1 to 2:1 and is preferably about 1:1.

The reaction of the halide-group-containing polyester obtainable according to (a) with the carboxylic acid of formula (8) is advantageously carried out at elevated temperature, for example at from 30 to 100°C, preferably from 40 to 100°C and especially from 60 to 90°C, in an aprotic-dipolar solvent, for example in DMSO, in the presence of a base, 1,8-diaza-bicyclo[5.4.0]undec-7-ene (DBU) having proved especially advantageous. The acid is used in a molar excess, based on the halide-group-containing polymer, and the base is advantageously present in about equimolar amounts, based on the acid of formula (8).

Depending on the chosen stoichiometric ratios and reaction conditions, the prepolymer of the invention obtainable after isolation in customary manner consists essentially of structural units of formula (1) indicated above or comprises, in addition to the structural units of formula (1), structural units of formula (1a) indicated above wherein R₀ is halogen. If step (b) is carried out using a mixture of an acid of formula (8) indicated above and an acid of the formula



wherein R₄ is as defined above, the prepolymer comprises a mixture of structural units of formula (1), structural units of formula (1a) wherein R₀ is a radical -O-(O)C-R₄, and, where appropriate, structural units of formula (1a) wherein R₀ is halogen.

The prepolymers of the invention are crosslinkable but are uncrosslinked or at least substantially uncrosslinked; moreover, they are stable, that is to say spontaneous crosslinking by homopolymerisation does not take place.

The prepolymers of the invention are advantageously liquid or readily meltable or water-soluble; their average molecular weight can vary within wide limits. An average molecular weight of, for example, from 1000 to 20 000 has proved advantageous for the prepolymers of the invention.

Furthermore, the prepolymers comprising structural units of formula (1) and, where appropriate, (1a) can be purified in a manner known *per se*, for example by precipitation with acetone, dialysis or ultrafiltration, with ultrafiltration being especially preferred. By means of that purification process it is possible to obtain the prepolymers of the invention in an extremely pure form, for example in the form of solvent-free liquids or melts or in the form of concentrated aqueous solutions that are free or at least substantially free of reaction products, such as salts, and of starting materials or other non-polymeric constituents.

The preferred process for purifying the prepolymers of the invention, ultrafiltration, can be carried out in a manner known *per se*. It is possible to carry out the ultrafiltration repeatedly, for example from two to ten times. Alternatively, the ultrafiltration can be carried out continuously until the desired degree of purity has been achieved. The degree of purity can in principle be as high as desired and is preferably so adjusted that the content of undesirable constituents in the prepolymers is, for example, $\leq 0.001\%$, especially $\leq 0.0001\%$ (1 ppm). The prepolymers may, for example depending on their synthesis, comprise in addition constituents that are acceptable from a physiological point of view, for example sodium chloride, such constituents advantageously being present in an amount of $\leq 1\%$, preferably $\leq 0.1\%$ and especially $\leq 0.01\%$.

As has already been mentioned above, the prepolymers of the invention comprising structural units of formula (1) and, where appropriate, (1a) are crosslinkable in an extremely effective and specific manner, especially by means of photocrosslinking.

Accordingly, the present invention relates also to a polymer that can be obtained by photocrosslinking a prepolymer comprising units of formula (1) and, where appropriate, (1a), in the absence or presence of an additional vinyl comonomer. Those crosslinked polymers are insoluble in water.

In the photocrosslinking, a photoinitiator capable of initiating radical crosslinking is suitably added. Examples thereof are known to the person skilled in the art, but there may be mentioned specifically as suitable photoinitiators benzoin methyl ether, 1-hydroxycyclohexyl phenyl ketone, Darocure 1173 or Irgacure types. Crosslinking can then be induced by actinic radiation, for example UV light, or ionising radiation, for example gamma radiation or X-rays.

Photopolymerisation can be carried out without the addition of a solvent, for example when the prepolymer is liquid or readily meltable, or takes place in a suitable solvent. Suitable solvents are in principle any solvents that dissolve the polymers of the invention and the vinyl comonomers that may additionally be used, for example water, alcohols, such as lower alkanols, for example ethanol or methanol, also carboxylic acid amides, such as dimethylformamide, or dimethyl sulfoxide, as well as mixtures of suitable solvents, for example mixtures of water with an alcohol, for example a water/ethanol or water/methanol mixture.

Photocrosslinking is preferably carried out without a solvent or substantially without a solvent or directly from an aqueous solution of the prepolymers of the invention (which solution can be obtained as a result of the preferred purification step, ultrafiltration), where appropriate after the addition of an additional vinyl comonomer. For example, photocrosslinking of an approximately 15 to 90 % strength aqueous solution can be carried out.

The process for the preparation of the crosslinked polymers of the invention comprises, for example, photocrosslinking a prepolymer comprising units of formula (1) and, where appropriate, (1a), especially in substantially pure form, that is to say, for example, after ultrafiltration once or several times, without a solvent or substantially without a solvent or in solution, especially in an aqueous solution, in the absence or presence of an additional vinyl comonomer.

The vinyl comonomer that may additionally be used according to the invention in the photo-crosslinking may be hydrophilic, hydrophobic or a mixture of a hydrophobic and a hydrophilic vinyl monomer. Suitable vinyl monomers include especially those which are customarily used in the production of contact lenses. A hydrophilic vinyl monomer is understood as being a monomer that, as a homopolymer, typically yields a polymer that is water-soluble or can absorb at least 10 % by weight water. By analogy, a hydrophobic vinyl monomer is understood as being a monomer that, as a homopolymer, typically yields a polymer that is insoluble in water and can absorb less than 10 % by weight water.

In general, approximately from 0.01 to 80 units of a typical vinyl comonomer react per unit of formula (1) and, as the case may be, (1a).

The proportion of vinyl comonomers, where used, is preferably from 0.5 to 80 units per unit of formula (1), especially from 1 to 30 units of vinyl comonomer per unit of formula (1) and more especially from 5 to 20 units per unit of formula (1).

It is further preferred to use a hydrophobic vinyl comonomer or a mixture of a hydrophobic vinyl comonomer and a hydrophilic vinyl comonomer, the mixture containing at least 50 % by weight of a hydrophobic vinyl comonomer. In this manner, the mechanical properties of the polymer can be improved without the water content dropping substantially. In principle, however, both conventional hydrophobic vinyl comonomers and conventional hydrophilic vinyl comonomers are suitable for the copolymerisation with a prepolymer comprising groups of formula (1).

Suitable hydrophobic vinyl comonomers include the following, this list not being exhaustive: C₁-C₁₈alkyl acrylates and methacrylates, C₃-C₁₈alkyl-acrylamides and -methacrylamides, acrylonitrile, methacrylonitrile, vinyl C₁-C₁₈alkanoates, C₂-C₁₈alkenes, C₂-C₁₈haloalkenes, styrene, C₁-C₆alkylstyrene, vinyl alkyl ethers in which the alkyl moiety has from 1 to 6 carbon atoms, C₂-C₁₀perfluoroalkyl acrylates and methacrylates or correspondingly partially fluorinated acrylates and methacrylates, C₃-C₁₂perfluoroalkyl-ethyl-thiocarbonylaminoethyl acrylates and methacrylates, acryloxy- and methacryloxy-alkylsiloxanes, N-vinylcarbazole, C₁-C₁₂alkyl esters of maleic acid, fumaric acid, itaconic acid, mesaconic acid and the like. Preference is given, for example, to C₁-C₄alkyl esters of vinylically unsaturated carboxylic

acids having from 3 to 5 carbon atoms or vinyl esters of carboxylic acids having up to 5 carbon atoms.

Examples of suitable hydrophobic vinyl comonomers include methyl acrylate, ethyl acrylate, propyl acrylate, isopropyl acrylate, cyclohexyl acrylate, 2-ethylhexyl acrylate, methyl methacrylate, ethyl methacrylate, propyl methacrylate, vinyl acetate, vinyl propionate, vinyl butyrate, vinyl valerate, styrene, chloroprene, vinyl chloride, vinylidene chloride, acrylonitrile, 1-butene, butadiene, methacrylonitrile, vinyltoluene, vinyl ethyl ether, per-fluorohexylethylthiocarbonylaminoethyl methacrylate, isobornyl methacrylate, trifluoroethyl methacrylate, hexafluoroisopropyl methacrylate, hexafluorobutyl methacrylate, tris-tri-methylsilyloxy-silyl-propyl methacrylate, 3-methacryloxypropylpentamethyldisiloxane and bis(methacryloxypropyl)tetramethyldisiloxane.

Suitable hydrophilic vinyl comonomers include the following, this list not being exhaustive: hydroxy-substituted lower alkyl acrylates and methacrylates, acrylamide, methacrylamide, lower alkyl acrylamides and methacrylamides, ethoxylated acrylates and methacrylates, hydroxy-substituted lower alkyl-acrylamides and -methacrylamides, hydroxy-substituted lower alkyl vinyl ethers, sodium ethylenesulfonate, sodium styrenesulfonate, 2-acrylamido-2-methylpropanesulfonic acid, N-vinylpyrrole, N-vinylsuccinimide, N-vinylpyrrolidone, 2- or 4-vinylpyridine, acrylic acid, methacrylic acid, amino- (the term "amino" also including quaternary ammonium), mono-lower alkylamino- or di-lower alkylamino-lower alkyl acrylates and methacrylates, allyl alcohol and the like. Preference is given, for example, to hydroxy-substituted C₂-C₄alkyl (meth)acrylates, five- to seven-membered N-vinylactams, N,N-di-C₁-C₄alkyl(meth)acrylamides, and vinylically unsaturated carboxylic acids having a total of from 3 to 5 carbon atoms.

Examples of suitable hydrophilic vinyl comonomers include hydroxyethyl methacrylate, hydroxyethyl acrylate, acrylamide, methacrylamide, dimethylacrylamide, allyl alcohol, vinylpyridine, vinylpyrrolidone, glycerol methacrylate, N-(1,1-dimethyl-3-oxobutyl)acrylamide and the like.

Preferred hydrophobic vinyl comonomers are methyl methacrylate and vinyl acetate.

Preferred hydrophilic vinyl comonomers are 2-hydroxyethyl methacrylate, N-vinyl-pyrrolidone and acrylamide.

The prepolymers of the invention can be processed in a manner known *per se* to form mouldings, especially contact lenses, for example by carrying out the photocrosslinking of the prepolymers of the invention in a suitable contact lens mould. Accordingly, the invention relates also to mouldings consisting essentially of a prepolymer of the invention. Other examples of mouldings of the invention, in addition to contact lenses, are biomedical mouldings and, especially, ophthalmic mouldings, for example intraocular lenses, eye dressings, mouldings for use in surgery, such as heart valves, artificial arteries or the like, and also films or membranes, for example membranes for controlling diffusion, photostructurable foils for information storage, or photoresist materials, for example membranes or mouldings for etching resist or screen printing resist.

A preferred process for the production of mouldings comprises the following steps:

- a) introducing into a mould a prepolymer comprising structural units of formula (1) and, where appropriate, (1a) that is liquid at room temperature or is readily meltable and is substantially free of solvents, in the absence or presence of an additional vinyl comonomer and/or photoinitiator,
- b) inducing the photocrosslinking,
- c) opening the mould so that the moulding can be removed from the mould.

Another preferred process for the production of mouldings comprises the following steps:

- a) preparing a substantially aqueous solution of a water-soluble prepolymer comprising structural units of formula (1) and, where appropriate, (1a) in the absence or presence of an additional vinyl comonomer and/or photoinitiator,
- b) introducing the resulting solution into a mould,
- c) inducing the photocrosslinking,
- d) opening the mould so that the moulding can be removed from the mould.

In the preferred processes outlined above it is in each case especially preferred to introduce the prepolymer into the mould in the absence of an additional vinyl comonomer and in the presence of a photoinitiator.

For the introduction of the prepolymers of the invention into a mould, processes known *per se* can be used, such as, especially, conventional metering in, for example by means of dropwise introduction. If vinyl comonomers are present, the above-mentioned comonomers in the amounts mentioned there are suitable. Vinyl comonomers that may be present are advantageously first mixed with the prepolymer of the invention and then introduced into the mould.

Appropriate moulds are manufactured, for example, from polypropylene. Suitable materials for reusable moulds are, for example, quartz, sapphire glass or metals.

When the mouldings to be produced are contact lenses, they can be produced in a manner known *per se*, for example in a conventional "spin-casting mold", as described, for example, in US-A-3 408 429, or by the so-called full-mold process in a static mould, as described, for example, in US-A-4 347 198.

The photocrosslinking can be induced in the mould, for example by actinic radiation, e.g. UV light, or ionising radiation, e.g. gamma radiation or X-rays.

As has already been mentioned, the photocrosslinking is advantageously carried out in the presence of a photoinitiator capable of initiating radical crosslinking. The photoinitiator is advantageously added to the prepolymers of the invention before introduction into the mould, preferably by mixing the polymers and the photoinitiator together. The amount of photoinitiator can be chosen within wide limits, an amount of up to 0.05 g/g of polymer and especially of up to 0.003 g/g of polymer having proved advantageous.

It is to be emphasised that according to the invention the crosslinking can be effected in a very short time, for example in \leq 60 minutes, advantageously in \leq 20 minutes, preferably in \leq 10 minutes, especially in \leq 5 minutes, more especially in \leq 1 minute and most especially in \leq 30 seconds.

Opening of the mould so that the moulding can be removed from the mould can be carried out in a manner known *per se*.

When the moulding produced according to the invention is a contact lens and when the latter has been produced without a solvent from a previously purified prepolymer of the invention, then it is generally not necessary, after removing the moulding, to carry out subsequent purification steps, for example extraction. This is because the prepolymers used do not contain any undesirable low-molecular-weight constituents; consequently, the crosslinked product is also free or substantially free of such constituents and subsequent extraction is unnecessary. Accordingly, the contact lens can be converted directly into a ready-to-use contact lens in customary manner by hydration. Suitable forms of hydration, by means of which ready-to-use contact lenses having different water contents are obtainable, are known to the person skilled in the art. The contact lens is swelled, for example, in water, in an aqueous salt solution, especially in an aqueous salt solution having an osmolarity of approximately from 200 to 450 milliosmol in 1000 ml (unit: mOsm/l), preferably approximately from 250 to 350 mOsm/l and especially approximately 300 mOsm/l, or in a mixture of water or an aqueous salt solution with a physiologically tolerable polar organic solvent, for example glycerol. Swelling of the prepolymer in water or in aqueous salt solutions is preferred.

The aqueous salt solutions used for the hydration are advantageously solutions of physiologically tolerable salts, such as buffer salts that are customary in the field of contact lens care, for example phosphate salts, or agents for establishing isotonicity that are customary in the field of contact lens care, such as, especially, alkali metal halides, for example sodium chloride, or solutions of mixtures thereof. An example of an especially suitable salt solution is a synthetic, preferably buffered lachrymal fluid that is adapted to natural lachrymal fluid as regards pH and osmolarity, for example an unbuffered sodium chloride solution, preferably a sodium chloride solution that is buffered, for example buffered with phosphate buffers, and the osmolarity and pH of which correspond to the osmolarity and pH of human lachrymal fluid.

The hydration fluids defined above are preferably pure, that is to say free or substantially free of undesirable constituents. Special preference is given to pure water or to a synthetic lachrymal fluid as described above.

When the moulding produced according to the invention is a contact lens and when the latter has been produced from an aqueous solution of a previously purified prepolymer of the invention, then the crosslinked product does not contain any troublesome impurities either. Subsequent extraction is therefore unnecessary. Since the crosslinking is carried out in a substantially aqueous solution, subsequent hydration is also unnecessary. The contact lenses obtainable according to that process are therefore distinguished, according to an advantageous embodiment, by the fact that they are suitable for their designated use without extraction. In this connection, designated use is understood as meaning especially that the contact lenses can be inserted into the human eye.

The contact lenses obtainable according to the invention have a range of unusual and extremely advantageous properties. Of those properties there may be mentioned, for example, their excellent tolerability by the human cornea, which is based on a balance of water content, oxygen permeability and mechanical properties. Moreover, the contact lenses of the invention exhibit a high degree of dimensional stability. No changes in shape were discernible even after autoclaving at, for example, about 120°C.

It can also be emphasised that the contact lenses of the invention, that is to say especially those comprising a crosslinked polymer of a prepolymer comprising units of formula (1) and, where appropriate, (1a), can be produced in a very simple and efficient manner as compared with the prior art. This is the result of several factors. Firstly, the starting materials are inexpensive to obtain or prepare. Secondly, there is the advantage that the prepolymers are surprisingly stable, so that they can be subjected to a high degree of purification. Accordingly, it is possible to use for the crosslinking a polymer that requires virtually no subsequent purification, such as, especially, the complicated extraction of unpolymerised constituents. Moreover, the crosslinking can be carried out without a solvent or in an aqueous solution, so that the subsequent exchange of solvents or the hydration step, respectively, is not required. Finally, the photopolymerisation takes place in a short time, so that the process for the production of the contact lenses of the invention can be made extraordinarily economical from that point of view also.

All the advantages mentioned above naturally apply not only to contact lenses but also to other mouldings according to the invention. The sum of the various advantageous aspects in the production of the mouldings of the invention leads to the mouldings of the invention

being suitable especially as mass-produced articles, for example as contact lenses that are worn for a short period of time and are then replaced by new lenses.


In the Examples which follow, unless expressly indicated to the contrary, quantities are by weight and temperatures are given in degrees Celsius. Unless indicated otherwise, molecular weights M_n are determined by means of gel permeation chromatography (GPC) [size exclusion chromatography (SEC)] using DMF as solvent, and are related to the calibration standard of polymethyl methacrylate (PMMA).

Preparation Examples

Example 1:

(a) 63.7 g of polyethylene glycol 600 diacid dichloride (prepared by reacting polyethylene glycol 600 diacid with thionyl chloride) are dissolved in 500 ml of toluene. 1.6 g of tetrabutylammonium bromide (TBAB) and 20.2 g of diglycidyl ether of butane-1,4-diol are added thereto and the mixture is heated to 90°C, with stirring. When the epoxy groups have reacted completely (which takes about 2 hours), the product is precipitated from tert-butyl methyl ether in the form of a yellow oil.

(b) 25.2 g of the product prepared according to (a) are dissolved in 200 ml of DMSO. 19.5 g of acrylic acid and 41.1 g of 1,8-diazabicyclo[5.4.0]undec-7-ene (DBU) are added thereto and the mixture is heated to 70°C, with stirring. After 24 hours at that temperature, 300 ml of water are added to the clear brown reaction mixture. The product is extracted with chloroform and the organic phase is washed first with 0.1N hydrochloric acid and then with 5 % strength NaHCO_3 solution. After removal of the solvent, a polymer comprising structural units of the formula




- 20 -

wherein R is the radical $-\text{O}-(\text{CH}_2)_4-\text{O}-$ and $n \approx 14$, is obtained in the form of a viscous yellow oil ($M_n = 3000$, $M_w = 4000$).

Example 2:

(a) 120 g of diglycidyl ether of polyethylene glycol 600 are dissolved in 100 ml of toluene. 3.2 g of TBAB and 36.6 g of adipic acid dichloride are added thereto and the mixture is heated to 90°C, with stirring. When the epoxy groups have reacted completely (which takes about 1 hour), the product is precipitated from tert-butyl methyl ether in the form of a yellow oil.

(b) 23.5 g of the product prepared according to (a) are dissolved in 200 ml of DMSO. 25.8 g of methacrylic acid and 41.1 g of DBU are added thereto and the mixture is heated to 90°C, with stirring. After 24 hours at that temperature, the reaction mixture is diluted with 300 ml of water and the product is then extracted therefrom with chloroform. The organic phase is washed with 0.1N hydrochloric acid and then with 5 % strength NaHCO_3 solution. After removal of the solvent, a polymer comprising structural units of the formula




($n \approx 14$)

is obtained in the form of a viscous yellow oil ($M_n = 3800$, $M_w = 4900$).

Example 3: Reaction of 70 g of diglycidyl ether of polyethylene glycol 1000 with 12.8 g of adipic acid dichloride, with the addition of 1.1 g of TBAB, by the process according to Example 2(a), and reaction of 26.5 g of the resulting product with 17.4 g of methacrylic acid, with the addition of 30.7 g of DBU, according to Example 2(b) yields a polymeric oil comprising structural units of the formula indicated in Example 2 wherein $n \approx 23$ ($M_n = 3300$, $M_w = 4200$).

Example 4: 23.5 g of the product obtained according to Example 2(a) are dissolved in 200 ml of DMSO. 20.6 g of glycolic acid and 41.2 g of DBU are added thereto and the mixture is heated to 90°C, with stirring. After 24 hours at that temperature, the reaction mixture is diluted with 300 ml of water and the product is then extracted therefrom with chloroform.

23.9 g of the product so prepared are dissolved in 170 ml of dioxane, and 0.18 g of N,N-dimethylcyclohexylamine is added thereto while introducing air. 43 g of isocyanatoethyl methacrylate, dissolved in 40 ml of dioxane, are added dropwise thereto and the mixture is then heated at 80°C for 5 hours. At the end of that time, the product is precipitated from tert-butyl methyl ether, yielding a polymer comprising structural units of the formula



($M_n = 5990$, $M_w = 7350$).

Application Examples

Example 5: 1.5 mg of Irgacure® 2959 are dissolved in 0.5 g of the polymer obtained according to Example 1. A 0.1 mm thick film is prepared from the clear viscous solution between two glass plates having spacers. The film is irradiated for 1.5 minutes using a Höne lamp. A


clear, flexible film is obtained which swells in water to form a clear hydrogel having a water content of 40 %.

Example 6: 3 mg of Irgacure® 2959 are dissolved in 1 g of the polymer obtained according to Example 2. A 0.1 mm thick film is prepared from the clear viscous solution between two glass plates having spacers. The film is irradiated for 1.5 minutes using a Hönlé lamp. A clear, flexible film is obtained which swells in water to form a clear hydrogel having a water content of 40 %.





Example 7: 3 mg of Irgacure® 2959 are dissolved in 1 g of the polymer obtained according to Example 3. A 0.1 mm thick film is prepared from the clear viscous solution between two glass plates having spacers. The film is irradiated for 30 seconds using a Hönlé lamp. A clear, solid film is obtained.

What is claimed is:

1. A prepolymer comprising structural units of the formula



wherein R is a radical



Z is straight-chained or branched C₁-C₁₂alkylene or unsubstituted or C₁-C₄alkyl- or C₁-C₄-alkoxy-substituted phenylene or C₇-C₁₂aralkylene,

x and t are each independently of the other the number 0 or 1,

R₅ is hydrogen, C₁-C₄alkyl or halogen,



R₆ is hydrogen, C₁-C₄alkyl, phenyl, carboxy or halogen,

R₇ is hydrogen when R₆ is phenyl or carboxy, or is hydrogen or carboxy when R₆ is hydrogen, C₁-C₄alkyl or halogen,

R₈ is a C₂-C₁₂alkylene radical, a phenylene radical or a C₇-C₁₂aralkylene radical,

R₉ and R_{9'} are each independently of the other hydrogen, C₁-C₄alkyl or halogen,

R₁ is a radical of the formula



or an alkylene radical having up to 20 carbon atoms which may be interrupted by one or more ester, urethane or ureido groups and/or may be substituted by hydroxy; or a cycloalkylene radical having from 6 to 20 carbon atoms; or an arylene radical having from 6 to 20 carbon atoms; or an arylenealkylene, alkylenearylene, alkylenearylenealkylene or arylene-alkylenearylene radical,

R₂ is a radical of the formula




or an alkylene radical having up to 20 carbon atoms which may be interrupted by one or more ester, urethane or ureido groups and/or may be substituted by hydroxy; or a cycloalkylene radical having from 6 to 20 carbon atoms; or an arylene radical having from 6 to 20 carbon atoms; or an arylenealkylene, alkylenearylene, alkylenearylenealkylene or arylene-alkylenearylene radical,

R', R'' and R* are each independently of the others hydrogen or C₁-C₄alkyl,

R₃ is an alkylene radical having up to 20 carbon atoms; or a cycloalkylene radical having from 6 to 20 carbon atoms; or an arylene radical having from 6 to 20 carbon atoms, and n, m, p and q are each independently of the others a number from 1 to 30,

with the proviso that at least one of the radicals R₁ and R₂ is a radical of formula (3a), (3b), (4) or (5).

2. A prepolymer according to claim 1, wherein R is a radical of the formula




R₅ and R' are each independently of the other hydrogen or C₁-C₄alkyl, and m and q are each independently of the other a number from 1 to 30.

- 25 -

3. A prepolymer according to claim 2, wherein R is a radical of formula (2a') wherein R₅ is hydrogen or methyl.


4. A prepolymer according to any one of claims 1 to 3, wherein R₁ is a radical of formula (3a) or (3b) indicated in claim 1, C₁-C₂₀alkylene, 1,2-, 1,3- or 1,4-phenylene, or a radical of the formula



wherein B₁ is straight-chained or branched C₁-C₄alkylene.

5. A prepolymer according to any one of claims 1 to 4, wherein R₁ is a radical of formula (3a) indicated in claim 1, or is C₁-C₂₀alkylene.

6. A prepolymer according to any one of claims 1 to 5, wherein R₂ is a radical of formula (4) or (5) indicated in claim 1, C₁-C₂₀alkylene, 1,2-, 1,3- or 1,4-phenylene, or a radical of the formula




wherein B₁ is straight-chained or branched C₁-C₄alkylene.

7. A prepolymer according to any one of claims 1 to 6, wherein R₂ is a radical of formula (4) indicated in claim 1, or is C₁-C₂₀alkylene.

8. A prepolymer according to any one of claims 1 to 7, wherein R₁ is a radical of formula (3a) indicated above and R₂ is a C₁-C₂₀alkylene radical.

9. A prepolymer according to any one of claims 1 to 7, wherein R₁ is a C₁-C₂₀alkylene radical and R₂ is a radical of formula (4) indicated above.

10. A prepolymer according to any one of claims 1 to 9 which comprises, in addition to the structural units of formula (1), structural units of the formula




wherein R_0 is halogen or a radical $-O-(O)C-R_4$ and R_4 is C_1-C_{20} alkyl, C_6-C_{20} cycloalkylene, C_6-C_{20} arylene or C_7-C_{12} aralkylene.

11. A prepolymer according to claim 10, wherein R_0 is halogen, preferably chlorine.

12. A process for the preparation of a prepolymer according to claim 1, which comprises

(a) polymerising a compound of the formula




with a compound of the formula



in the presence of a catalyst, and

(b) reacting the polymer obtainable according to (a), which comprises structural units of the formula



with a compound of the formula



in the presence of a base, R_1 and R_2 each being as defined in claim 1, X being halogen, preferably chlorine, and R being a radical of formula (2a), (2c), (2d) or (2b) indicated in claim 1 wherein t is the number 1.

13. A polymer that is obtainable by crosslinking a prepolymer according to any one of claims 1 to 11 in the absence or presence of an additional vinyl comonomer.

14. A polymer according to claim 13 that is obtainable by photocrosslinking a prepolymer according to any one of claims 1 to 11 in the absence of an additional vinyl comonomer.

15. A polymer according to claim 13 that is obtainable by photocrosslinking a prepolymer according to any one of claims 1 to 11 in the presence of from 0.5 to 80 units of an additional vinyl comonomer per unit of formula (1), especially from 1 to 30 units of vinyl comonomer per unit of formula (1) and more especially from 5 to 20 units per unit of formula (1).

16. A process for the preparation of a polymer according to claim 13, which comprises photocrosslinking a prepolymer according to any one of claims 1 to 11 in the absence or presence of an additional vinyl comonomer.

17. A process according to claim 16, wherein the prepolymer is used in substantially pure form.

18. A process for the production of a moulding, which comprises the following steps:

- a) introducing into a mould a prepolymer comprising structural units of formula (1) and, where appropriate, (1a) that is liquid at room temperature or is readily meltable and is substantially free of solvents, in the absence or presence of an additional vinyl comonomer and/or photoinitiator,
- b) inducing the photocrosslinking,
- c) opening the mould so that the moulding can be removed from the mould.

19. A process for the production of a moulding, which comprises the following steps:

- a) preparing a substantially aqueous solution of a water-soluble prepolymer comprising structural units of formula (1) and, where appropriate, (1a) in the absence or presence of an additional vinyl comonomer and/or photoinitiator,
- b) introducing the resulting solution into a mould,
- c) inducing the crosslinking,
- d) opening the mould so that the moulding can be removed from the mould.

20. A process according to either claim 18 or claim 19, wherein the moulding is a contact lens.

21. A moulding, especially a contact lens, that is obtainable by the process according to either claim 18 or claim 19.
22. A contact lens according to claim 21 that is suitable for its designated use without extraction.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 97/05738

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08G59/42 C08G59/14 C08G63/676 G02B1/04

According to International Patent Classification(IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08G G02B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>HIDEYUKI ITOH ET AL.: "Synthesis of new hybrid monomers and oligomers containing cationic and radical polymerizable vinyl groups and their photoinitiated polymerization" JOURNAL OF POLYMER SCIENCE, POLYMER CHEMISTRY EDITION, vol. 34, no. 2, 30 January 1996, NEW YORK US, pages 217-225, XP002028011 cited in the application</p> <p>---</p> <p style="text-align: center;">-/-</p>	1-16

Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

° Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

1

Date of the actual completion of the international search	Date of mailing of the international search report
24 February 1998	03/03/1998
Name and mailing address of the ISA	Authorized officer
European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016	Decocker, L

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 97/05738

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	ATSUSHI KAMEYAMA ET AL.: "Synthesis of reactive polyesters by a regioselective addition reaction of diepoxides with diacylchlorides and their chemical modification" MACROMOLECULES, vol. 25, no. 9, 27 April 1992, EASTON US, pages 2307-2311, XP000266489 cited in the application see the whole document ---	1-16
A	US 5 428 057 A (KIM ET AL.) 27 June 1995 see claims 1-4 ---	1
A	US 5 039 769 A (MOLOCK ET AL.) 13 August 1991 see abstract; claim 1 -----	1,20-22

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 97/05738

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5428057 A	27-06-95	KR 9608127 B KR 9515125 B JP 2113075 C JP 6220161 A JP 8022901 B	20-06-96 22-12-95 21-11-96 09-08-94 06-03-96
US 5039769 A	13-08-91	NONE	